

SECTION II
MATERIALS

2025

ASME Boiler and
Pressure Vessel Code
An International Code

Part D
Properties (Customary)

Markings such as “ASME,” “ASME Standard,” or any other marking including “ASME,” ASME logos, or the ASME Single Certification Mark shall not be used on any item that is not constructed in accordance with all of the applicable requirements of the Code or Standard. Use of the ASME Single Certification Mark requires formal ASME certification; if no certification program is available, such ASME markings may not be used. (For Certification and Accreditation Programs, see <https://www.asme.org/certification-accreditation>.)

Items produced by parties not formally possessing an ASME Certificate may not be described, either explicitly or implicitly, as ASME certified or approved in any code forms or other document.

AN INTERNATIONAL CODE

2025 ASME Boiler & Pressure Vessel Code

2025 Edition

July 1, 2025

II MATERIALS

Part D

Properties (Customary)

ASME Boiler and Pressure Vessel Committee
on Materials



The American Society of
Mechanical Engineers

Two Park Avenue • New York, NY • 10016 USA

Date of Issuance: July 1, 2025

This international code or standard was developed under procedures accredited as meeting the criteria for American National Standards and it is an American National Standard. The standards committee that approved the code or standard was balanced to ensure that individuals from competent and concerned interests had an opportunity to participate. The proposed code or standard was made available for public review and comment, which provided an opportunity for additional public input from industry, academia, regulatory agencies, and the public-at-large.

ASME does not “approve,” “certify,” “rate,” or “endorse” any item, construction, proprietary device, or activity. ASME does not take any position with respect to the validity of any patent rights asserted in connection with any items mentioned in this document, and does not undertake to insure anyone utilizing a standard against liability for infringement of any applicable letters patent, nor does ASME assume any such liability. Users of a code or standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Participation by federal agency representatives or persons affiliated with industry is not to be interpreted as government or industry endorsement of this code or standard.

ASME accepts responsibility for only those interpretations of this document issued in accordance with the established ASME procedures and policies, which precludes the issuance of interpretations by individuals.

The endnotes and preamble in this document (if any) are part of this American National Standard.



ASME Collective Membership Mark



ASME Single Certification Mark

All rights reserved. “ASME” and the above ASME symbols are registered trademarks of The American Society of Mechanical Engineers. No part of this document may be copied, modified, distributed, published, displayed, or otherwise reproduced in any form or by any means, electronic, digital, or mechanical, now known or hereafter invented, without the express written permission of ASME. No works derived from this document or any content therein may be created without the express written permission of ASME. Using this document or any content therein to train, create, or improve any artificial intelligence and/or machine learning platform, system, application, model, or algorithm is strictly prohibited.

Library of Congress Catalog Card Number: 56-3934

Adopted by the Council of The American Society of Mechanical Engineers, 1914; latest edition 2025.

The American Society of Mechanical Engineers
Two Park Avenue, New York, NY 10016-5990

Copyright © 2025 by
THE AMERICAN SOCIETY OF MECHANICAL ENGINEERS
All rights reserved
Printed in U.S.A.

TABLE OF CONTENTS

List of Sections	xiii
Foreword	xiv
Statement of Policy on the Use of the ASME Single Certification Mark and Code Authorization in Advertising	xvi
Statement of Policy on the Use of ASME Marking to Identify Manufactured Items	xvi
Personnel	xvii
Correspondence With the Committee	xl
Summary of Changes	xlvi
Cross-Referencing in the ASME BPVC	xlvi
Subpart 1	
Stress Tables	1
Statement of Policy on Information Provided in the Stress Tables	1
Guideline on Locating Materials in Stress Tables, and in Tables of Mechanical and Physical Properties	3
Subpart 2	
Physical Properties Tables	1151
Introduction	1151
Subpart 3	
Charts and Tables for Determining Shell Thickness of Components Under External Pressure	1192
Mandatory Appendix 1	
1-100	
Basis for Establishing Stress Values in Tables 1A and 1B	1322
Derivation of Allowable Stress Values	1322
Mandatory Appendix 2	
2-100	
Basis for Establishing Design Stress Intensity Values for Tables 2A, 2B, and 4, and Allowable Stress Values for Table 3	1324
Derivation of Stress Intensity Values	1324
Mandatory Appendix 3	
3-100	
3-200	
3-300	
3-400	
3-500	
3-600	
3-700	
3-800	
3-900	
Basis for Establishing External Pressure Charts	1327
General	1327
Basis of Charts in Subpart 3	1327
Use of Charts in Subpart 3	1327
Background and Development of Theory	1327
Design Basis	1327
Criteria for Allowable Stresses	1328
Procedure and Responsibility for Chart Development	1330
Alternate Procedure for Determining Allowable Compressive Stresses	1333
References	1333
Mandatory Appendix 5	
5-100	
5-200	
5-300	
5-400	
5-500	
5-600	
5-700	
5-800	
5-900	
5-1000	
5-1100	
5-1200	
Guidelines on the Approval of New Materials Under the ASME Boiler and Pressure Vessel Code	1334
Code Policy	1334
Application	1334
Chemical Composition	1336
Metallurgical Structure and Heat Treatment	1336
Mechanical Properties	1336
Definitions for Data Collection Purposes	1336
Required Sampling	1337
Time-Independent Properties	1337
Time-Dependent Properties	1337
Low-Temperature Properties	1339
Toughness Data	1339
Stress-Strain Curves	1339

5-1300	Fatigue Data	1339
5-1400	Physical Properties	1340
5-1500	Data Requirements for Welds, Weldments, and Weldability	1340
5-1600	Long-Term Properties Stability	1342
5-1700	Requests for Additional Data	1342
5-1800	New Materials Checklist	1342
5-1900	Requirements for Recognized National or International Specifications	1342
5-2000	Publication of Recognized National or International Specifications	1343
5-2100	CEN Specifications	1343
Mandatory Appendix 6	Basis for Establishing Stress Values in Tables 6A, 6B, 6C, and 6D	1344
6-100	Derivation of Allowable Stress Values	1344
Mandatory Appendix 7	Guidelines on Multiple Marking of Materials	1346
7-100	Background	1346
7-200	Guidelines	1346
Mandatory Appendix 9	Standard Units for Use in Equations	1348
Mandatory Appendix 10	Basis for Establishing Maximum Allowable Stress Values for Tables 5A and 5B	1349
10-100	Derivation of Allowable Stress Values	1349
Nonmandatory Appendix A	Issues Associated With Materials Used in ASME Code Construction	1351
A-100	General	1351
A-200	Metallurgical Changes That Can Occur in Service	1352
A-300	Uniform Corrosion	1359
A-400	Localized Corrosion	1362
A-500	Metallurgically Influenced Corrosion	1363
A-600	Mechanically Assisted Corrosion	1364
A-700	Environmentally Induced Embrittlement and Cracking	1365
A-800	Mechanical Damage Mechanisms	1369
Nonmandatory Appendix B	Developing Nominal Composition Designations for ASME Code Materials	1371
B-100	Background	1371
B-200	General Guideline for All Materials	1371
B-300	Guidelines for Developing Nominal Composition Designations for Ferrous Materials	1372
B-400	Guidelines for Developing Nominal Composition Designations for Nonferrous Materials	1372
B-500	Summary	1373
Nonmandatory Appendix C	Guidance for the Use of U.S. Customary and SI Units in the ASME Boiler and Pressure Vessel Code	1374
C-100	Use of Units in Equations	1374
C-200	Guidelines Used to Develop SI Equivalents	1374
C-300	Soft Conversion Factors	1376
Nonmandatory Appendix D	Guidelines for Rounding Minimum Specified Tensile and Yield Strength Values and for Establishing Anchor Points for Tensile and Yield Strength Trend Curves in Tables 1A, 1B, 2A, 2B, 3, 4, 5A, 5B, U, and Y-1	1377
D-100	Minimum Tensile Strength and Minimum Yield Strength Columns	1377
D-200	Selecting Anchor Point for Tensile and Yield Strength Trend Curves for All Situations in Which the Minimum RT Specified Values in One Unit System Are Not Precise Conversions of the Units in the Other System	1377
D-300	Significant Figures in the Allowable Stress, Tensile Strength, and Yield Strength Tables in Section II, Part D and in Code Cases	1378

Nonmandatory Appendix E	Material Data for Stress Analysis in the Time-Dependent Regime	1379
E-100	Introduction	1379

FIGURES

G	Geometric Chart for Components Under External or Compressive Loadings (for All Materials)	1193
CS-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Carbon or Low Alloy Steels With Specified Minimum Yield Strength Less Than 30,000 psi	1195
CS-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Carbon or Low Alloy Steels With Specified Minimum Yield Strength 30,000 psi and Higher	1196
CS-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Carbon Steel and Low Alloy Steels With Specified Minimum Yield Strength 38,000 psi and Higher for Temperatures 300°F and Less	1197
CS-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for SA-537 Thickness $2\frac{1}{2}$ in. and Less	1198
CS-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for SA-508 Class 1, Grades 2 and 3; SA-508 Class 2, Grade 2; SA-533 Class 1, Grades A, B, C, and D; SA-533 Class 2, Grades A, B, C, and D; or SA-541 Grades 2 and 3	1199
CS-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Carbon Steel With Specified Minimum Yield Strength of 20,000 psi	1200
HT-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Quenched and Tempered Low Alloy Steel With Specified Minimum Yield Strength of 100,000 psi and Thickness $2\frac{1}{2}$ in. and Less	1201
HT-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for SA-508 Grade 4N, Class 2 or SA-543 Types B and C, Class 2 With Specified Minimum Yield Strength of 100,000 psi	1202
HA-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 18Cr-8Ni, Type 304	1203
HA-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 16Cr-12Ni-2Mo, Type 316	1204
HA-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 18Cr-8Ni-0.035 Maximum Carbon, Type 304L	1205
HA-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 18Cr-8Ni-Mo-0.035 Maximum Carbon, Type 316L	1206
HA-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic-Ferritic Steel 18Cr-5Ni-3Mo S31500 and Austenitic-Ferritic Steel 25Cr-6Ni-Mo-N S32053	1207
HA-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 21Cr-11Ni-N S30815	1208
HA-7	Chart for Determining Shell Thickness of Components Under External Pressure Developed for SA-564 Type 630 H1150 (17Cr-4Ni-4Cu S17400)	1209
HA-8	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic-Ferritic Steel 25Cr-7Ni-3Mo-2W-0.28N S39274	1210
HA-9	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Steel 25Cr-7.5Ni-3.5Mo-N-Cu-W S32760	1211
HA-10	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Austenitic Stainless Steel 24Cr-17Ni-6Mn-4.5Mo-N S34565	1212
CI-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Cast Iron	1213
CD-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Cast Ductile Iron With a Specified Minimum Yield Strength of 40,000 psi	1214
CD-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Cast Ductile Iron With a Specified Minimum Yield Strength of 29,000 psi	1215
NFA-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 3003 in O Temper	1216
NFA-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 3003 in H14 Temper	1217

NFA-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 3004 in O Temper	1218
NFA-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 3004 in H34 Temper	1219
NFA-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5154 in O Temper	1220
NFA-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5454 in O Temper	1221
NFA-7	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 1060 in O Temper	1222
NFA-8	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5052 in O Temper	1223
NFA-9	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5086 in O Temper	1224
NFA-10	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5456 in O Temper	1225
NFA-11	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Alloy 5083 in O Temper	1226
NFA-12	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Welded Aluminum Alloy 6061-T6	1227
NFA-13	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Welded Aluminum Alloy 6061-T4	1228
NFC-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Copper, Type DHP	1229
NFC-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Copper-Silicon Alloy C65500	1230
NFC-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed 90-10 Copper-Nickel Alloy	1231
NFC-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed 70-30 Copper-Nickel Alloy	1232
NFC-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Welded Copper-Iron Alloy Tube C19400 (SB-543 Welded)	1233
NFC-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for SB-75 and SB-111 Light Drawn Seamless Copper Tubes, Alloys C10200, C12000, C12200, and C14200	1234
NFC-7	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Copper, SB-75, UNS C12200, Temper O50	1235
NFC-8	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Aluminum Bronze Alloy C61400	1236
NFN-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Low Carbon Nickel N02201	1237
NFN-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel N02200	1238
NFN-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel-Copper Alloy N04400	1239
NFN-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel-Chromium-Iron Alloy N06600	1240
NFN-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum Alloy N10001	1241
NFN-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum-Chromium-Iron Alloy N10003	1242
NFN-7	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Iron-Chromium-Molybdenum-Copper Alloy N08825	1243
NFN-8	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel-Iron-Chromium Alloy N08800	1244

NFN-9	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel-Iron-Chromium Alloy N08810	1245
NFN-10	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Low Carbon Nickel-Molybdenum-Chromium Alloy N10276	1246
NFN-11	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Solution Treated Nickel-Chromium-Iron-Molybdenum-Copper Alloy N06007	1247
NFN-12	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Chromium-Nickel-Iron-Molybdenum-Copper-Columbium Alloy N08020	1248
NFN-13	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Iron-Chromium-Silicon Alloy N08330	1249
NFN-14	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Chromium-Molybdenum Alloy N06455	1250
NFN-15	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum Alloy N06002	1251
NFN-16	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum Alloy N10665	1252
NFN-17	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Annealed Nickel-Chromium-Molybdenum-Columbium Alloy N06625 (SB-443, SB-444, and SB-446)	1253
NFN-18	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum-Chromium-Iron-Copper Alloy N06985 Having a Minimum Yield Strength of 35 ksi	1254
NFN-19	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Molybdenum-Chromium-Iron-Copper Alloy N06985 Having a Minimum Yield Strength of 30 ksi	1255
NFN-20	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Work-Hardened Nickel	1256
NFN-21	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel-Chromium-Iron Alloy N06600 (Specified Minimum Yield Strength 40,000 psi) ...	1257
NFN-22	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Solution Annealed Ni-Cr-Mo-Cb Alloy, Grade 2 N06625	1258
NFN-23	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Cold Worked Nickel-Iron-Chromium Alloy N08800	1259
NFN-24	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Nickel Alloy N06230	1260
NFN-25	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Stress Relieved Nickel Alloy N02200	1261
NFN-26	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Alloy S31277	1262
NFN-27	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Alloy N06035	1263
NFT-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Unalloyed Titanium Grade 3 (UNS R50550)	1264
NFT-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Unalloyed Titanium Grade 2 (UNS R50400)	1265
NFT-3	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Titanium Grade 1 (UNS R50250)	1266
NFT-4	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Titanium Grade 9 Alloy (UNS R56320)	1267
NFT-5	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Titanium Grade 12 Alloy (UNS R53400)	1268
NFT-6	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Titanium Grade 38 (UNS R54250)	1269
NFZ-1	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Zirconium Alloy (UNS R60702)	1270

NFZ-2	Chart for Determining Shell Thickness of Components Under External Pressure Developed for Zirconium Alloy (UNS R60705)	1271
3-500.1	Temperature Limits for Application of Section II External Pressure Charts for Cylinder Under External Pressure	1329
3-500.2	Temperature Limits for Application of Section II External Pressure Charts for Cylinder Under Axial Compression	1330
3-500.3	Temperature Limits for Application of Section II External Pressure Charts for Sphere Under External Pressure	1331
3-700.1	Normalization of Test σ - ϵ to σ_{ymin} and E_{code}	1332
E-100.2-1	Permissible Time/Temperature Conditions for Material That Has Been Cold Worked >5% and <20% and Subjected to Short-Time High Temperature Transients	1381
E-100.4-1	S_{mt} — Allowable Stress Intensity Values, ksi, Type 304 SS — 30-YS, 75-UTS (30-YS, 70-UTS)	1384
E-100.4-2	S_{mt} — Allowable Stress Intensity Values, ksi, Type 316 SS — 30-YS, 75-UTS (30-YS, 70-UTS)	1385
E-100.4-3	S_{mt} — Allowable Stress Intensity Values, ksi, Ni-Fe-Cr (Alloy 800H)	1386
E-100.4-4	S_{mt} — Allowable Stress Intensity Values, ksi, 2 $\frac{1}{4}$ Cr-1Mo	1388
E-100.4-5	S_{mt} — Allowable Stress Intensity Values, ksi, 9Cr-1Mo-V	1389
E-100.5-1	S_t — Allowable Stress Intensity Values, ksi, Type 304 SS	1390
E-100.5-2	S_t — Allowable Stress Intensity Values, ksi, Type 316 SS	1391
E-100.5-3	S_t — Allowable Stress Intensity Values, ksi, Ni-Fe-Cr (Alloy 800H)	1392
E-100.5-4	S_t — Allowable Stress Intensity Values, ksi, 2 $\frac{1}{4}$ Cr-1Mo	1393
E-100.5-5	S_t — Allowable Stress Intensity Values, ksi, 9Cr-1Mo-V	1394
E-100.7-1	Expected Minimum Stress-to-Rupture Values, ksi, Type 304 SS	1396
E-100.7-2	Expected Minimum Stress-to-Rupture Values, ksi, Type 316 SS	1397
E-100.7-3	Expected Minimum Stress-to-Rupture Values, ksi, Ni-Fe-Cr (Alloy 800H)	1398
E-100.7-4	Expected Minimum Stress-to-Rupture Values, ksi, 2 $\frac{1}{4}$ Cr-1Mo	1399
E-100.7-5	Expected Minimum Stress-to-Rupture Values, ksi, Ni-Cr-Fe-Mo-Cb (Alloy 718)	1400
E-100.7-6	Expected Minimum Stress-to-Rupture Values, ksi, 9Cr-1Mo-V	1401
E-100.15-1	S_{mt} — Allowable Stress Intensity, Type 304 SS, Bolting	1406
E-100.15-2	S_{mt} — Allowable Stress Intensity, Type 316 SS, Bolting	1407
E-100.15-3	S_{mt} — Allowable Stress Values, ksi, Alloy 718, Bolting	1408
E-100.16-1	Design Fatigue Strain Range, ϵ_t , for 304 SS	1409
E-100.16-2	Design Fatigue Strain Range, ϵ_t , for 316 SS	1410
E-100.16-3	Design Fatigue Strain Range, ϵ_t , for Ni-Fe-Cr Alloy 800H	1411
E-100.16-4	Design Fatigue Strain Range, ϵ_t , for 2 $\frac{1}{4}$ Cr-1Mo Steel	1412
E-100.16-5	Design Fatigue Strain Range, ϵ_t , for 9Cr-1Mo-V Steel	1413
E-100.17-1	Time-Temperature Limits for Application of Section II External Pressure Charts for Cylinder Under Axial Compression	1414
E-100.17-2	Time-Temperature Limits for Application of Section II External Pressure Charts for Sphere Under External Pressure	1415
E-100.17-3	Temperature Limits for Application of Section II External Pressure Charts for Cylinder Under External Pressure	1416
E-100.18-1	Average Isochronous Stress-Strain Curves for Type 304 SS at 800°F	1417
E-100.18-2	Average Isochronous Stress-Strain Curves for Type 304 SS at 850°F	1418
E-100.18-3	Average Isochronous Stress-Strain Curves for Type 304 SS at 900°F	1419
E-100.18-4	Average Isochronous Stress-Strain Curves for Type 304 SS at 950°F	1420
E-100.18-5	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,000°F	1421
E-100.18-6	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,050°F	1422
E-100.18-7	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,100°F	1423
E-100.18-8	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,150°F	1424
E-100.18-9	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,200°F	1425
E-100.18-10	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,250°F	1426
E-100.18-11	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,300°F	1427
E-100.18-12	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,350°F	1428
E-100.18-13	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,400°F	1429
E-100.18-14	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,450°F	1430
E-100.18-15	Average Isochronous Stress-Strain Curves for Type 304 SS at 1,500°F	1431

E-100.19-1	Average Isochronous Stress–Strain Curves for Type 316 SS at 800°F	1432
E-100.19-2	Average Isochronous Stress–Strain Curves for Type 316 SS at 850°F	1433
E-100.19-3	Average Isochronous Stress–Strain Curves for Type 316 SS at 900°F	1434
E-100.19-4	Average Isochronous Stress–Strain Curves for Type 316 SS at 950°F	1435
E-100.19-5	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,000°F	1436
E-100.19-6	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,050°F	1437
E-100.19-7	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,100°F	1438
E-100.19-8	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,150°F	1439
E-100.19-9	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,200°F	1440
E-100.19-10	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,250°F	1441
E-100.19-11	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,300°F	1442
E-100.19-12	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,350°F	1443
E-100.19-13	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,400°F	1444
E-100.19-14	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,450°F	1445
E-100.19-15	Average Isochronous Stress–Strain Curves for Type 316 SS at 1,500°F	1446
E-100.20-1	Average Isochronous Stress–Strain Curves for Alloy 800H at 800°F and 850°F	1447
E-100.20-2	Average Isochronous Stress–Strain Curves for Alloy 800H at 900°F	1448
E-100.20-3	Average Isochronous Stress–Strain Curves for Alloy 800H at 950°F	1449
E-100.20-4	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,000°F	1450
E-100.20-5	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,050°F	1451
E-100.20-6	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,100°F	1452
E-100.20-7	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,150°F	1453
E-100.20-8	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,200°F	1454
E-100.20-9	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,250°F	1455
E-100.20-10	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,300°F	1456
E-100.20-11	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,350°F	1457
E-100.20-12	Average Isochronous Stress–Strain Curves for Alloy 800H at 1,400°F	1458
E-100.21-1	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 700°F	1459
E-100.21-2	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 750°F	1460
E-100.21-3	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 800°F	1461
E-100.21-4	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 850°F	1462
E-100.21-5	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 900°F	1463
E-100.21-6	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 950°F	1464
E-100.21-7	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 1,000°F	1465
E-100.21-8	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 1,050°F	1466
E-100.21-9	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 1,100°F	1467
E-100.21-10	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 1,150°F	1468
E-100.21-11	Average Isochronous Stress–Strain Curves for Annealed 2¼Cr–1Mo at 1,200°F	1469
E-100.22-1	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 700°F	1470
E-100.22-2	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 750°F	1470
E-100.22-3	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 800°F	1471
E-100.22-4	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 850°F	1471
E-100.22-5	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 900°F	1472
E-100.22-6	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 950°F	1472
E-100.22-7	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 1,000°F	1473
E-100.22-8	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 1,050°F	1473
E-100.22-9	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 1,100°F	1474
E-100.22-10	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 1,150°F	1474
E-100.22-11	Average Isochronous Stress–Strain Curves for 9Cr–1Mo–V at 1,200°F	1475

TABLES

1A	Section I; Section III, Division 1, Classes 2 and 3; Section VIII, Division 1; and Section XII Maximum Allowable Stress Values, S , for Ferrous Materials	8
1B	Section I; Section III, Division 1, Classes 2 and 3; Section VIII, Division 1; and Section XII Maximum Allowable Stress Values, S , for Nonferrous Materials	176
2A	Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5 Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable Stress Values, S , for Ferrous Materials	308
2B	Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5 Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable Stress Values, S , for Nonferrous Materials	402
3	Section III, Division 1, Classes 2 and 3; Section VIII, Divisions 1 and 2; and Section XII Maximum Allowable Stress Values, S , for Bolting Materials	430
4	Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5 Design Stress Intensity Values, S_m , and Section VIII, Division 2 Maximum Allowable Stress Values, S , for Bolting Materials	460
5A	Section VIII, Division 2, Class 2 Maximum Allowable Stress Values, S , for Ferrous Materials	472
5B	Section VIII, Division 2, Class 2 Maximum Allowable Stress Values, S , for Nonferrous Materials	534
6A	Section IV Maximum Allowable Stress Values, S , for Ferrous Materials	560
6B	Section IV Maximum Allowable Stress Values, S , for Nonferrous Materials	570
6C	Section IV Maximum Allowable Stress Values, S , for Lined Water Heater Materials	578
6D	Section IV Maximum Allowable Stress Values, S , for Unlined Water Heater Materials	584
U	Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials	592
Y-1	Yield Strength Values, S_y , for Ferrous and Nonferrous Materials	814
Y-2	Factors for Limiting Permanent Strain in Austenitic Stainless Steels, High-Nickel Alloy Steels, Nickel, Nickel Alloys, Copper, and Copper Alloys	1150
TE-1	Thermal Expansion for Ferrous Materials	1152
TE-2	Thermal Expansion for Aluminum Alloys	1157
TE-3	Thermal Expansion for Copper Alloys	1158
TE-4	Thermal Expansion for Nickel Alloys	1159
TE-5	Thermal Expansion for Titanium Alloys	1169
TCD	Nominal Coefficients of Thermal Conductivity (TC) and Thermal Diffusivity (TD)	1170
TM-1	Moduli of Elasticity E of Ferrous Materials for Given Temperatures	1184
TM-2	Moduli of Elasticity E of Aluminum and Aluminum Alloys for Given Temperatures	1187
TM-3	Moduli of Elasticity E of Copper and Copper Alloys for Given Temperatures	1188
TM-4	Moduli of Elasticity E of High Nickel Alloys for Given Temperatures	1189
TM-5	Moduli of Elasticity E of Titanium and Zirconium for Given Temperatures	1190
PRD	Poisson's Ratio and Density of Materials	1190
G	Tabular Values for Figure G	1272
CS-1	Tabular Values for Figure CS-1	1274
CS-2	Tabular Values for Figure CS-2	1275
CS-3	Tabular Values for Figure CS-3	1276
CS-4	Tabular Values for Figure CS-4	1277
CS-5	Tabular Values for Figure CS-5	1277
CS-6	Tabular Values for Figure CS-6	1278
HT-1	Tabular Values for Figure HT-1	1278
HT-2	Tabular Values for Figure HT-2	1279
HA-1	Tabular Values for Figure HA-1	1279
HA-2	Tabular Values for Figure HA-2	1280
HA-3	Tabular Values for Figure HA-3	1280
HA-4	Tabular Values for Figure HA-4	1281
HA-5	Tabular Values for Figure HA-5	1281
HA-6	Tabular Values for Figure HA-6	1282
HA-7	Tabular Values for Figure HA-7	1283
HA-8	Tabular Values for Figure HA-8	1283

HA-9	Tabular Values for Figure HA-9	1284
HA-10	Tabular Values for Figure HA-10	1285
CI-1	Tabular Values for Figure CI-1	1286
CD-1	Tabular Values for Figure CD-1	1286
CD-2	Tabular Values for Figure CD-2	1286
NFA-1	Tabular Values for Figure NFA-1	1287
NFA-2	Tabular Values for Figure NFA-2	1288
NFA-3	Tabular Values for Figure NFA-3	1289
NFA-4	Tabular Values for Figure NFA-4	1290
NFA-5	Tabular Values for Figure NFA-5	1290
NFA-6	Tabular Values for Figure NFA-6	1291
NFA-7	Tabular Values for Figure NFA-7	1291
NFA-8	Tabular Values for Figure NFA-8	1292
NFA-9	Tabular Values for Figure NFA-9	1292
NFA-10	Tabular Values for Figure NFA-10	1293
NFA-11	Tabular Values for Figure NFA-11	1293
NFA-12	Tabular Values for Figure NFA-12	1294
NFA-13	Tabular Values for Figure NFA-13	1294
NFC-1	Tabular Values for Figure NFC-1	1294
NFC-2	Tabular Values for Figure NFC-2	1295
NFC-3	Tabular Values for Figure NFC-3	1295
NFC-4	Tabular Values for Figure NFC-4	1296
NFC-5	Tabular Values for Figure NFC-5	1296
NFC-6	Tabular Values for Figure NFC-6	1297
NFC-7	Tabular Values for Figure NFC-7	1297
NFC-8	Tabular Values for Figure NFC-8	1298
NFN-1	Tabular Values for Figure NFN-1	1298
NFN-2	Tabular Values for Figure NFN-2	1299
NFN-3	Tabular Values for Figure NFN-3	1299
NFN-4	Tabular Values for Figure NFN-4	1300
NFN-5	Tabular Values for Figure NFN-5	1300
NFN-6	Tabular Values for Figure NFN-6	1301
NFN-7	Tabular Values for Figure NFN-7	1301
NFN-8	Tabular Values for Figure NFN-8	1302
NFN-9	Tabular Values for Figure NFN-9	1303
NFN-10	Tabular Values for Figure NFN-10	1304
NFN-11	Tabular Values for Figure NFN-11	1304
NFN-12	Tabular Values for Figure NFN-12	1305
NFN-13	Tabular Values for Figure NFN-13	1305
NFN-14	Tabular Values for Figure NFN-14	1306
NFN-15	Tabular Values for Figure NFN-15	1307
NFN-16	Tabular Values for Figure NFN-16	1308
NFN-17	Tabular Values for Figure NFN-17	1309
NFN-18	Tabular Values for Figure NFN-18	1310
NFN-19	Tabular Values for Figure NFN-19	1311
NFN-20	Tabular Values for Figure NFN-20	1312
NFN-22	Tabular Values for Figure NFN-22	1312
NFN-23	Tabular Values for Figure NFN-23	1313
NFN-24	Tabular Values for Figure NFN-24	1313
NFN-25	Tabular Values for Figure NFN-25	1314
NFN-26	Tabular Values for Figure NFN-26	1314
NFN-27	Tabular Values for Figure NFN-27	1315
NFT-1	Tabular Values for Figure NFT-1	1316
NFT-2	Tabular Values for Figure NFT-2	1317
NFT-3	Tabular Values for Figure NFT-3	1317
NFT-4	Tabular Values for Figure NFT-4	1318

NFT-5	Tabular Values for Figure NFT-5	1319
NFT-6	Tabular Values for Figure NFT-6	1320
NFZ-1	Tabular Values for Figure NFZ-1	1321
NFZ-2	Tabular Values for Figure NFZ-2	1321
1-100	Criteria for Establishing Allowable Stress Values for Tables 1A and 1B	1323
2-100(a)	Criteria for Establishing Design Stress Intensity Values for Tables 2A and 2B	1325
2-100(b)	Criteria for Establishing Allowable Stress Values for Table 3	1326
2-100(c)	Criteria for Establishing Allowable Stress or Design Stress Intensity Values for Table 4	1326
5-100	Hot Isostatically Pressed Component Requirements for Austenitic Stainless Steels, Austenitic-Ferritic (Duplex) Stainless Steels, Martensitic Stainless Steels, Ferritic Steels, and Nickel Alloys	1335
5-800	ASTM Test Methods and Units for Reporting	1338
5-1500	Example of a Comparison of Allowable Stresses of Base Metals With Compositions Similar to Those of Selected Welding Consumables and the Proposed New Base Metal	1341
6-100(a)	Criteria for Establishing Allowable Stress Values for Tables 6A and 6B	1345
6-100(b)	Criteria for Establishing Allowable Stress Values for Table 6C	1345
6-100(c)	Criteria for Establishing Allowable Stress Values for Table 6D	1345
9-100	Standard Units for Use in Equations	1348
10-100	Criteria for Establishing Allowable Stress Values for Tables 5A and 5B	1350
E-100.1-1	Tensile Strength Values, S_u	1379
E-100.1-2	Tensile and Yield Strength Reduction Factor Due to Long Time Prior Elevated Temperature Service	1380
E-100.1-3	Yield Strength Reduction Factors for $2\frac{1}{4}\text{Cr}-1\text{Mo}$	1380
E-100.1-4	Tensile Strength Reduction Factors for $2\frac{1}{4}\text{Cr}-1\text{Mo}$	1380
E-100.1-5	Tensile Strength Reduction Factors for $9\text{Cr}-1\text{Mo}-\text{V}$	1381
E-100.3-1	Permissible Base Materials for Structures Other Than Bolting	1382
E-100.3-2	Permissible Weld Materials	1383
E-100.3-3	S_o — Maximum Allowable Stress Intensity, ksi, for Design Condition Calculations	1383
E-100.6-1	Yield Strength Values, S_y , Versus Temperature	1395
E-100.8-1	Stress Rupture Factors for Type 304 Stainless Steel Welded With SFA-5.22 E308T and E308LT, SFA-5.4 E308 and E308L, and SFA-5.9 ER308 and ER308L	1402
E-100.8-2	Stress Rupture Factors for Type 304 Stainless Steel Welded With SFA-5.22 EXXXT-G (16-8-2 Chemistry), SFA-5.4 E16-8-2, and SFA-5.9 ER16-8-2	1402
E-100.8-3	Stress Rupture Factors for Type 304 Stainless Steel Welded With SFA-5.22 E316T and E316LT-1, -2, and -3; SFA-5.4 E316 and E316L; and SFA-5.9 ER316 and ER316L	1402
E-100.9-1	Stress Rupture Factors for Type 316 Stainless Steel Welded With SFA-5.22 E308T and E308LT, SFA-5.4 E308 and E308L, and SFA-5.9 ER308 and ER308L	1403
E-100.9-2	Stress Rupture Factors for Type 316 Stainless Steel Welded With SFA-5.22 EXXXT-G (16-8-2 Chemistry), SFA-5.4 E16-8-2, and SFA-5.9 ER16-8-2	1403
E-100.9-3	Stress Rupture Factors for Type 316 Stainless Steel Welded With SFA-5.22 E316T and E316LT-1 and -2, SFA-5.4 E316 and E316L, and SFA-5.9 ER316 and ER316L	1403
E-100.10-1	Stress Rupture Factors for Alloy 800H Welded With SFA-5.11 ENiCrFe-2 (INCO A)	1404
E-100.10-2	Stress Rupture Factors for Alloy 800H Welded With SFA-5.14 ERNiCr-3 (INCO 82)	1404
E-100.11-1	Stress Rupture Factors for $2\frac{1}{4}\text{Cr}-1\text{Mo}$ (60/30) Welded With SFA-5.28 E90C-B3, SFA-5.28 ER90S-B3, SFA-5.5 E90XX-B3 (>0.05C), SFA-5.23 EB3, SFA-5.23 ECB3 (>0.05C), and SFA-5.29 E90T1-B3 (>0.05C)	1404
E-100.12-1	Stress Rupture Factors for $9\text{Cr}-1\text{Mo}-\text{V}$ Welded With SFA-5.28 ER90S-B9, SFA-5.5 E90XX-B9, and SFA-5.23 EB9	1405
E-100.13-1	Permissible Materials for Bolting	1405
E-100.14-1	S_o — Maximum Allowable Stress Intensity, ksi, for Design Condition Calculations of Bolting Materials	1406
E-100.23-1	Recommended Restrictions	1476
E-100.24-1	Cross-Reference Table of Section II, Part D and Section III, Subsection NH 2015 Edition	1476
ENDNOTES		1481

LIST OF SECTIONS

(25)

SECTIONS

- I Rules for Construction of Power Boilers
- II Materials
 - Part A — Ferrous Material Specifications
 - Part B — Nonferrous Material Specifications
 - Part C — Specifications for Welding Rods, Electrodes, and Filler Metals
 - Part D — Properties (Customary)
 - Part D — Properties (Metric)
- III Rules for Construction of Nuclear Facility Components
 - Subsection NCA — General Requirements for Division 1 and Division 2
 - Appendices
 - Division 1
 - Subsection NB — Class 1 Components
 - Subsection NCD — Class 2 and Class 3 Components
 - Subsection NE — Class MC Components
 - Subsection NF — Supports
 - Subsection NG — Core Support Structures
 - Division 2 — Code for Concrete Containments
 - Division 3 — Containment Systems for Transportation and Storage of Spent Nuclear Fuel and High-Level Radioactive Material
 - Division 4 — Fusion Energy Devices
 - Division 5 — High Temperature Reactors
- IV Rules for Construction of Heating Boilers
- V Nondestructive Examination
- VI Recommended Rules for the Care and Operation of Heating Boilers
- VII Recommended Guidelines for the Care of Power Boilers
- VIII Rules for Construction of Pressure Vessels
 - Division 1
 - Division 2 — Alternative Rules
 - Division 3 — Alternative Rules for Construction of High Pressure Vessels
- IX Welding, Brazing, and Fusing Qualifications
- X Fiber Reinforced Plastic Pressure Vessels
- XI Rules for Inservice Inspection of Nuclear Reactor Facility Components
 - Division 1 — Rules for Inservice Inspection of Nuclear Power Plant Components
 - Division 2 — Requirements for Reliability and Integrity Management (RIM) Programs for Nuclear Reactor Facilities
- XII Rules for Construction and Continued Service of Transport Tanks
- XIII Rules for Overpressure Protection

FOREWORD*

In 1911, The American Society of Mechanical Engineers established the Boiler and Pressure Vessel Committee to formulate standard rules for the construction of steam boilers and other pressure vessels. In 2009, the Boiler and Pressure Vessel Committee was superseded by the following committees:

- (a) Committee on Power Boilers (I)
- (b) Committee on Materials (II)
- (c) Committee on Construction of Nuclear Facility Components (III)
- (d) Committee on Heating Boilers (IV)
- (e) Committee on Nondestructive Examination (V)
- (f) Committee on Pressure Vessels (VIII)
- (g) Committee on Welding, Brazing, and Fusing (IX)
- (h) Committee on Fiber-Reinforced Plastic Pressure Vessels (X)
- (i) Committee on Nuclear Inservice Inspection (XI)
- (j) Committee on Transport Tanks (XII)
- (k) Committee on Overpressure Protection (XIII)
- (l) Technical Oversight Management Committee (TOMC)

Where reference is made to “the Committee” in this Foreword, each of these committees is included individually and collectively.

The Committee’s function is to establish rules of safety relating to pressure integrity. The rules govern the construction** of boilers, pressure vessels, transport tanks, and nuclear components, and the inservice inspection of nuclear components and transport tanks. For nuclear items other than pressure-retaining components, the Committee also establishes rules of safety related to structural integrity. The Committee also interprets these rules when questions arise regarding their intent. The technical consistency of the Sections of the Code and coordination of standards development activities of the Committees is supported and guided by the Technical Oversight Management Committee. The Code does not address other safety issues relating to the construction of boilers, pressure vessels, transport tanks, or nuclear components, or the inservice inspection of nuclear components or transport tanks. Users of the Code should refer to the pertinent codes, standards, laws, regulations, or other relevant documents for safety issues other than those relating to pressure integrity and, for nuclear items other than pressure-retaining components, structural integrity. Except for Sections XI and XII, and with a few other exceptions, the rules do not, of practical necessity, reflect the likelihood and consequences of deterioration in service related to specific service fluids or external operating environments. In formulating the rules, the Committee considers the needs of users, manufacturers, and inspectors of components addressed by the Code. The objective of the rules is to afford reasonably certain protection of life and property, and to provide a margin for deterioration in service to give a reasonably long, safe period of usefulness. Advancements in design and materials and evidence of experience have been recognized.

The Code contains mandatory requirements, specific prohibitions, and nonmandatory guidance for construction activities and inservice inspection and testing activities. The Code does not address all aspects of these activities and those aspects that are not specifically addressed should not be considered prohibited. The Code is not a handbook and cannot replace education, experience, and the use of engineering judgment. The phrase *engineering judgment* refers to technical judgments made by knowledgeable engineers experienced in the application of the Code. Engineering judgments must be consistent with Code philosophy, and such judgments must never be used to overrule mandatory requirements or specific prohibitions of the Code.

The Committee recognizes that tools and techniques used for design and analysis change as technology progresses and expects engineers to use good judgment in the application of these tools. The designer is responsible for complying with Code rules and demonstrating compliance with Code equations when such equations are mandatory. The Code

* The information contained in this Foreword is not part of this American National Standard (ANS) and has not been processed in accordance with ANSI’s requirements for an ANS. Therefore, this Foreword may contain material that has not been subjected to public review or a consensus process. In addition, it does not contain requirements necessary for conformance to the Code.

** *Construction*, as used in this Foreword, is an all-inclusive term comprising materials, design, fabrication, examination, inspection, testing, certification, and overpressure protection.

neither requires nor prohibits the use of computers for the design or analysis of components constructed to the requirements of the Code. However, designers and engineers using computer programs for design or analysis are cautioned that they are responsible for all technical assumptions inherent in the programs they use and the application of these programs to their design.

The rules established by the Committee are not to be interpreted as approving, recommending, or endorsing any proprietary or specific design, or as limiting in any way the manufacturer's freedom to choose any method of design or any form of construction that conforms to the Code rules.

The Committee meets regularly to consider revisions of the rules, new rules as dictated by technological development, Code cases, and requests for interpretations. Only the Committee has the authority to provide official interpretations of the Code. Requests for revisions, new rules, Code cases, or interpretations shall be addressed to the staff secretary in writing and shall give full particulars in order to receive consideration and action (see the Correspondence With the Committee page). Proposed revisions to the Code resulting from inquiries will be presented to the Committee for appropriate action. The action of the Committee becomes effective only after confirmation by ballot of the Committee and approval by ASME. Proposed revisions to the Code approved by the Committee are submitted to the American National Standards Institute (ANSI) and published at <http://go.asme.org/BPVCPublicReview> to invite comments from all interested persons. After public review and final approval by ASME, revisions are published at regular intervals in Editions of the Code.

The Committee does not rule on whether a component shall or shall not be constructed to the provisions of the Code. The scope of each Section has been established to identify the components and parameters considered by the Committee in formulating the Code rules.

Questions or issues regarding compliance of a specific component with the Code rules are to be directed to the ASME Certificate Holder (Manufacturer). Inquiries concerning the interpretation of the Code are to be directed to the Committee. ASME is to be notified should questions arise concerning improper use of the ASME Single Certification Mark.

When required by context in the Code, the singular shall be interpreted as the plural, and vice versa.

The words "shall," "should," and "may" are used in the Code as follows:

- *Shall* is used to denote a requirement.
- *Should* is used to denote a recommendation.
- *May* is used to denote permission, neither a requirement nor a recommendation.

STATEMENT OF POLICY ON THE USE OF THE ASME SINGLE CERTIFICATION MARK AND CODE AUTHORIZATION IN ADVERTISING

ASME has established procedures to authorize qualified organizations to perform various activities in accordance with the requirements of the ASME Boiler and Pressure Vessel Code. It is the aim of the Society to provide recognition of organizations so authorized. An organization holding authorization to perform various activities in accordance with the requirements of the Code may state this capability in its advertising literature.

Organizations that are authorized to use the ASME Single Certification Mark for marking items or constructions that have been constructed and inspected in compliance with the ASME Boiler and Pressure Vessel Code are issued Certificates of Authorization. It is the aim of the Society to maintain the standing of the ASME Single Certification Mark for the benefit of the users, the enforcement jurisdictions, and the holders of the ASME Single Certification Mark who comply with all requirements.

Based on these objectives, the following policy has been established on the usage in advertising of facsimiles of the ASME Single Certification Mark, Certificates of Authorization, and reference to Code construction. The American Society of Mechanical Engineers does not “approve,” “certify,” “rate,” or “endorse” any item, construction, or activity and there shall be no statements or implications that might so indicate. An organization holding the ASME Single Certification Mark and/or a Certificate of Authorization may state in advertising literature that items, constructions, or activities “are built (produced or performed) or activities conducted in accordance with the requirements of the ASME Boiler and Pressure Vessel Code,” or “meet the requirements of the ASME Boiler and Pressure Vessel Code.” An ASME corporate logo shall not be used by any organization other than ASME.

The ASME Single Certification Mark shall be used only for stamping and nameplates as specifically provided in the Code. However, facsimiles may be used for the purpose of fostering the use of such construction. Such usage may be by an association or a society, or by a holder of the ASME Single Certification Mark who may also use the facsimile in advertising to show that clearly specified items will carry the ASME Single Certification Mark.

STATEMENT OF POLICY ON THE USE OF ASME MARKING TO IDENTIFY MANUFACTURED ITEMS

The ASME Boiler and Pressure Vessel Code provides rules for the construction of boilers, pressure vessels, and nuclear components. This includes requirements for materials, design, fabrication, examination, inspection, and stamping. Items constructed in accordance with all of the applicable rules of the Code are identified with the ASME Single Certification Mark described in the governing Section of the Code.

Markings such as “ASME,” “ASME Standard,” or any other marking including “ASME” or the ASME Single Certification Mark shall not be used on any item that is not constructed in accordance with all of the applicable requirements of the Code.

Items shall not be described on ASME Data Report Forms nor on similar forms referring to ASME that tend to imply that all Code requirements have been met when, in fact, they have not been. Data Report Forms covering items not fully complying with ASME requirements should not refer to ASME or they should clearly identify all exceptions to the ASME requirements.

PERSONNEL

ASME Boiler and Pressure Vessel Standards Committees, Subgroups, and Working Groups

January 1, 2025

TECHNICAL OVERSIGHT MANAGEMENT COMMITTEE (TOMC)

R. E. McLaughlin, *Chair*
N. A. Finney, *Vice Chair*
S. J. Rossi, *Staff Secretary*
R. W. Barnes
T. L. Bedeaux
C. T. Brown
R. P. Deubler
G. W. Galanes
J. A. Hall
T. E. Hansen
G. W. Hembree
R. B. Keating
B. Linnemann
W. M. Lundy
D. I. Morris

M. D. Rana
S. C. Roberts
F. J. Schaaf, Jr.
G. Scribner
W. J. Sperko
D. Srnic
R. W. Swayne
J. Vattappilly
M. Wadkinson
D. W. Lamond, *Ex-Officio Member*
B. K. Nutter, *Ex-Officio Member*
E. M. Ortman, *Ex-Officio Member*
M. J. Pischke, *Ex-Officio Member*
J. F. Henry, *Honorary Member*

Task Group on Remote Inspection and Examination (SI-TOMC)

S. C. Roberts, *Chair*
M. Frediani, *Staff Secretary*
P. J. Coco
N. A. Finney
S. A. Marks
R. Rockwood

C. Stevens
M. Tannenbaum
J. Cameron, *Alternate*
A. Byk, *Contributing Member*
S. J. Rossi, *Contributing Member*
C. A. Sanna, *Contributing Member*

Special Working Group on High Temperature Technology (TOMC)

D. Dewees, *Chair*
F. W. Brust
T. D. Burchell
P. R. Donavin

B. F. Hantz
R. I. Jetter
P. Smith

Subgroup on Research and Development (TOMC)

S. C. Roberts, *Chair*
S. J. Rossi, *Staff Secretary*
R. W. Barnes
N. A. Finney
G. W. Galanes

R. B. Keating
R. E. McLaughlin
E. M. Ortman
D. Andrei, *Contributing Member*

Honors and Awards Committee (TOMC)

E. M. Ortman,
G. W. Galanes
D. W. Lamond

B. K. Nutter
R. E. McLaughlin

Subgroup on Strategic Initiatives (TOMC)

N. A. Finney, *Chair*
S. J. Rossi, *Staff Secretary*
R. W. Barnes
G. W. Galanes
G. W. Hembree

R. B. Keating
R. E. McLaughlin
E. M. Ortman
S. C. Roberts
M. Wadkinson

ADMINISTRATIVE COMMITTEE

R. E. McLaughlin, *Chair*
N. A. Finney, *Vice Chair*
S. J. Rossi, *Staff Secretary*
G. W. Galanes
R. B. Keating
D. W. Lamond
B. Linnemann

B. K. Nutter
E. M. Ortman
M. J. Pischke
M. D. Rana
S. C. Roberts
R. R. Stevenson
M. Wadkinson

Task Group on Field Sites (TOMC)

R. V. Wielgoszinski, *Chair*
M. Vazquez, *Staff Secretary*
P. Becker
T. Bedeaux

J. Hoskinson
D. T. Peters
G. Scribner

MARINE CONFERENCE GROUP

J. Oh, *Staff Secretary*
J. G. Hungerbuhler, Jr.
G. Nair

H. N. Patel
N. Prokopuk
J. D. Reynolds

CONFERENCE COMMITTEE

R. D. Troutt — Texas, *Chair*
J. T. Amato — Ohio, *Secretary*
M. O. Amuzie — New Jersey
R. Becker — Colorado
H. Berny — Minnesota
T. D. Boggs — Missouri
R. A. Boillard — Indiana
D. P. Brockerville —
Newfoundland and Labrador,
Canada
R. J. Bunte — Iowa
A. Buquis — Arizona
J. H. Burpee — Maine
M. Carlson — Washington
T. Carter — Mississippi
N. Chiasson — Prince Edward
Island, Canada
T. G. Clark — Oregon
B. J. Crawford — Georgia
E. L. Creaser — New Brunswick,
Canada
J. J. Dacanay — Hawaii
M. Davidian — California
R. DeLury — Manitoba, Canada
A. Denham — Michigan
C. Derks — Wisconsin
C. Dinic — Ontario, Canada
D. A. Ehler — Nova Scotia, Canada
S. D. Frazier — Washington
A. Gibbs — Wisconsin
T. J. Granneman II — Oklahoma
M. L. Jordan — Kentucky
R. Kamboj — British Columbia,
Canada
E. Kawa — Massachusetts
A. Khssassi — Quebec, Canada
D. Kinney — North Carolina
K. S. Lane — Alaska
A. M. Lorimor — South Dakota
T. Maher — Illinois
M. Mailman — Northwest
Territories, Canada
W. McGivney — City of New York,
New York
S. F. Noonan — Maryland
B. S. Oliver — New Hampshire
J. L. Oliver — Nevada
P. B. Polick — Illinois
B. Ricks — Montana
W. J. Ross — Pennsylvania
M. H. Sansone — New York
T. S. Seime — North Dakota
C. S. Selinger — Saskatchewan,
Canada
J. E. Sharier — Ohio
R. Spiker — North Carolina
D. Srnic — Alberta, Canada
D. J. Stenrose — Michigan
R. J. Stimson II — Kansas
R. K. Sturm — Utah
D. K. Sullivan — Arkansas
J. Taveras — Rhode Island
R. Termini — Louisiana
S. Van Slavens — Delaware
D. M. Warburton — Florida
E. Wiggins — Alabama

INTERNATIONAL INTEREST REVIEW GROUP

V. Felix
Y.-G. Kim
S. H. Leong
W. Lin
O. F. Manafa
C. Minu
Y.-W. Park
A. R. Reynaga Nogales
P. Williamson

COMMITTEE ON POWER BOILERS (BPV I)

E. M. Ortman, *Chair*
D. E. Tompkins, *Vice Chair*
U. D'Urso, *Staff Secretary*
D. I. Anderson
R. Antoniuk
J. L. Arnold
K. K. Coleman
S. Fincher
G. W. Galanes
P. F. Gilston
T. E. Hansen
J. S. Hunter
M. Ishikawa
M. Lemmons
M. Lewis
C. T. McDaris
R. E. McLaughlin
L. Moedinger
Y. Oishi
M. Ortolani
A. Spangenberg
D. E. Tuttle
J. Vattappilly
M. Wadkinson
F. Zeller
H. Michael, *Contributing Member*
D. Berger, *Honorary Member*
P. D. Edwards, *Honorary Member*
J. G. Feldstein, *Honorary Member*
D. N. French, *Honorary Member*
J. Hainsworth, *Honorary Member*
J. F. Henry, *Honorary Member*
P. A. Molvie, *Honorary Member*
J. T. Pillow, *Honorary Member*
B. W. Roberts, *Honorary Member*
J. M. Tanzosh, *Honorary Member*
R. V. Wielgoszinski, *Honorary Member*
R. L. Williams, *Honorary Member*

Executive Committee (BPV I)

D. E. Tompkins, *Chair*
E. M. Ortman, *Vice Chair*
P. Becker
J. R. Braun
P. F. Gilston
A. Hantodkar
M. Lewis
C. T. McDaris
L. S. Nicol
A. Spangenberg
K. Thanupillai
M. Wadkinson

Subgroup on Design (BPV I)

C. T. McDaris, *Chair*
L. S. Tsai, *Secretary*
T. K. Acharya
D. I. Anderson
P. Becker
T. Huynh
L. Krupp
N. S. Ranck
J. Vattappilly
M. Wadkinson
C. Welles

Subgroup on Fabrication and Examination (BPV I)

P. F. Gilston, *Chair*
P. Becker, *Vice Chair*
J. L. Arnold
K. K. Coleman
S. Fincher
G. W. Galanes
T. E. Hansen
M. Lewis
S. J. Lombardo
C. T. McDaris
R. E. McLaughlin
Y. Oishi

Subgroup on General Requirements and Piping (BPV I)

D. E. Tompkins, *Chair*
M. Wadkinson, *Vice Chair*
M. Lemmons, *Secretary*
R. Antoniuk
T. E. Hansen
M. Ishikawa
S. J. Lombardo
R. E. McLaughlin
L. Moedinger
E. M. Ortman
D. E. Tuttle
J. Vattappilly

Subgroup on Locomotive Boilers (BPV I)

J. R. Braun, *Chair*
S. M. Butler, *Secretary*
G. W. Galanes
S. A. Lee
L. Moedinger
G. M. Ray
M. W. Westland

Subgroup on Materials (BPV I)

M. Lewis, *Chair*
L. S. Nicol, *Vice Chair*
S. H. Bowes
K. K. Coleman
G. W. Galanes
P. F. Gilston
K. Hayes
J. S. Hunter
E. Liebl
F. Masuyama
M. Ortolani
D. W. Rahoi
F. Zeller
B. W. Roberts, *Contributing Member*
J. M. Tanzosh, *Contributing Member*

Subgroup on Solar Boilers (BPV I)

R. E. Hearne, *Secretary*
S. Fincher
J. S. Hunter
P. Swarnkar

Task Group on Additive Manufacturing (BPV I)

K. K. Coleman, *Chair*
P. Becker, *Secretary*
J. L. Arnold
G. W. Galanes
P. F. Gilston
L. Moedinger
J. Vattappilly

Task Group on Modernization (BPV I)

S. J. Lombardo, <i>Chair</i>	G. W. Galanes
U. D'Urso, <i>Staff Secretary</i>	R. E. McLaughlin
D. I. Anderson	E. M. Ortman
J. L. Arnold	D. E. Tuttle

European International Working Group (BPV I)

A. Spangenberg, <i>Chair</i>	H. Michael
B. Daume	F. Miunske
J. Fleischfresser	M. Sykora
C. Jaekel	P. Chavdarov, <i>Contributing Member</i>
R. Kauer	J. Henrichsmeyer, <i>Contributing Member</i>
D. Koelbl	B. Müller, <i>Contributing Member</i>
S. Krebs	
T. Ludwig	
R. A. Meyers	

India International Working Group (BPV I)

K. Thanupillai, <i>Chair</i>	R. Madnani
A. Hantodkar, <i>Vice Chair</i>	S. Purkait
A. Ghosh, <i>Secretary</i>	A. Relekar
P. Brahma	M. Shiroya
H. Dalal	D. K. Shrivastava
T. Dhanraj	K. Singha
A. S. Ganesh	R. Sundararaj
S. Gopalakrishnan	S. Velu
A. Jain	S. Venkataramana

COMMITTEE ON MATERIALS (BPV II)

G. W. Galanes, <i>Chair</i>	F. Zeller
M. Ortolani, <i>Vice Chair</i>	J. Cameron, <i>Contributing Member</i>
C. E. Rodrigues, <i>Staff Secretary</i>	A. Chaudouet, <i>Contributing Member</i>
A. Appleton	K. K. Coleman, <i>Contributing Member</i>
P. Chavdarov	D. W. Gandy, <i>Contributing Member</i>
J. F. Grubb	K. L. Hayes, <i>Contributing Member</i>
J. A. Hall	W. Hoffelner, <i>Contributing Member</i>
D. O. Henry	K. E. Orie, <i>Contributing Member</i>
K. M. Hottle	D. T. Peters, <i>Contributing Member</i>
M. Ishikawa	B. W. Roberts, <i>Contributing Member</i>
M. Kowalczyk	J. M. Tanzosh, <i>Contributing Member</i>
D. L. Kurle	E. Uptis, <i>Contributing Member</i>
F. Masuyama	T. M. Cullen, <i>Honorary Member</i>
S. Neilsen	G. C. Hsu, <i>Honorary Member</i>
L. S. Nicol	
D. W. Rahoi	
W. Ren	
E. Shapiro	
R. C. Sutherland	

Executive Committee (BPV II)

G. W. Galanes, <i>Chair</i>	K. L. Hayes
C. E. Rodrigues, <i>Staff Secretary</i>	K. M. Hottle
E. Alexis	W. MacDonald
A. Appleton	M. Ortolani
J. Cameron	P. K. Rai
P. Chavdarov	J. Robertson
J. F. Grubb	E. Shapiro
S. Guzey	

Subgroup on External Pressure (BPV II)

E. Alexis, <i>Chair</i>	J. F. Grubb
S. Guzey, <i>Vice Chair</i>	S. Krishnamurthy
J. A. A. Morrow, <i>Secretary</i>	D. L. Kurle
L. F. Campbell	R. W. Mikitka
H. Chen	P. K. Rai
M. Ghorashi	M. Wadkinson
D. S. Griffin	

Subgroup on Ferrous Specifications (BPV II)

K. M. Hottle, <i>Chair</i>	Y.-J. Kim
A. Appleton, <i>Vice Chair</i>	W. C. Mack
C. Hyde, <i>Secretary</i>	J. Nickel
D. Amire-Brahimi	D. Poweleit
G. Cuccio	R. Rezaeifar
O. Elkadim	R. Schmidt
D. Fialkowski	E. Uptis
J. Grimm	L. Watzke
J. F. Grubb	C. Meloy, <i>Contributing Member</i>
D. S. Janikowski	

Subgroup on International Material Specifications (BPV II)

P. Chavdarov, <i>Chair</i>	D. O. Henry
M. Ishikawa, <i>Vice Chair</i>	W. M. Lundy
C. Zhou, <i>Secretary</i>	F. Zeller
A. Chaudouet	T. F. Miskell, <i>Contributing Member</i>
H. Chen	E. Uptis, <i>Contributing Member</i>
A. F. Garbolevsky	

Subgroup on Nonferrous Alloys (BPV II)

J. Robertson, <i>Chair</i>	R. Rezaeifar
W. MacDonald, <i>Vice Chair</i>	E. Shapiro
R. M. Beldyk	J. Shubilla
J. M. Downs	R. C. Sutherland
H. Dutta	R. Wright
J. F. Grubb	S. Yem
J. A. Hall	D. B. Denis, <i>Contributing Member</i>
D. Maitra	D. T. Peters, <i>Contributing Member</i>
D. W. Rahoi	

Subgroup on Physical Properties (BPV II)

P. K. Rai, <i>Chair</i>	P. K. Lam
S. Neilsen, <i>Vice Chair</i>	D. W. Rahoi
D. Chandiramani	E. Shapiro
H. Eshraghi	D. K. Verma
J. F. Grubb	S. Yem
B. F. Hantz	D. B. Denis, <i>Contributing Member</i>
R. D. Jones	

Subgroup on Strength, Ferrous Alloys (BPV II)

M. Ortolani, <i>Chair</i>	F. Masuyama
S. Rosinski, <i>Vice Chair</i>	M. Osterfoss
L. S. Nicol, <i>Secretary</i>	D. W. Rahoi
G. W. Galanes	M. Ueyama
J. A. Hall	F. Zeller
M. Ishikawa	F. Abe, <i>Contributing Member</i>
S. W. Knowles	

Subgroup on Strength of Weldments (BPV II & BPV IX)

K. L. Hayes, <i>Chair</i>	W. F. Newell, Jr.
G. W. Galanes, <i>Vice Chair</i>	J. A. Penso
S. H. Bowes, <i>Secretary</i>	D. W. Rahoi
K. K. Coleman, <i>Chair</i>	W. J. Sperko
M. Denault	J. P. Swezy, Jr.
D. W. Gandy	B. W. Roberts, <i>Contributing Member</i>
M. Ghahremani	

China International Working Group (BPV II)

Sanjiang Liu, <i>Chair</i>	C. Wang
H. Zhang, <i>Vice Chair</i>	Jinguang Wang
T. Xu, <i>Secretary</i>	Jiongxiang Wang
W. Cai	Q.-J. Wang
W. Fang	H.-C. Yang
F. Kong	J. Yang
H. Li	L. Yin
J. Li	X.-H. Zhang
Z. Rongcan	Y. Zhang
S. Tan	

Working Group on Creep Strength Enhanced Ferritic Steels (BPV II)

M. Ortolani, <i>Chair</i>	J. J. Sanchez-Hanton
G. W. Galanes, <i>Vice Chair</i>	J. A. Siefert
P. Becker, <i>Secretary</i>	W. J. Sperko
S. H. Bowes	F. Zeller
K. Kimura	F. Abe, <i>Contributing Member</i>
M. Lang	K. K. Coleman, <i>Contributing Member</i>
S. Luke	J. M. Tanzosh, <i>Contributing Member</i>
F. Masuyama	
T. Melfi	
W. F. Newell, Jr.	

Working Group on Data Analysis and the Materials Properties Database (BPV II)

W. MacDonald, <i>Chair</i>	D. Andrei, <i>Contributing Member</i>
C. E. Rodrigues, <i>Staff Secretary</i>	J. Cameron, <i>Contributing Member</i>
J. F. Grubb	G. W. Galanes, <i>Contributing Member</i>
F. Masuyama	W. C. Mack, <i>Contributing Member</i>
S. Neilsen	D. T. Peters, <i>Contributing Member</i>
M. Ortolani	W. Ren, <i>Contributing Member</i>
R. C. Sutherlin	E. Shapiro, <i>Contributing Member</i>
M. J. Swindeman	
F. Abe, <i>Contributing Member</i>	

Task Group on Modernization of Materials Data (BPV II)

C. E. Rodrigues, <i>Staff Secretary</i>	S. Neilsen
E. Alexis	L. S. Nicol
M. Brijlani	W. Ren
D. B. Denis	J. C. Sowinski
G. W. Galanes	M. Wadkinson
J. A. Hall	J. Cameron, <i>Contributing Member</i>
B. F. Hantz	J. F. Grubb, <i>Contributing Member</i>
A. Hassan	W. Hoffelner, <i>Contributing Member</i>
W. MacDonald	

COMMITTEE ON CONSTRUCTION OF NUCLEAR FACILITY COMPONENTS (BPV III)

R. B. Keating, <i>Chair</i>	K. Matsunaga
T. M. Adams, <i>Vice Chair</i>	B. McGlone
D. E. Matthews, <i>Vice Chair</i>	S. McKillop
A. Maslowski, <i>Staff Secretary</i>	J. B. McLean
A. Appleton	J. C. Minichiello
S. Asada	M. N. Mitchell
R. W. Barnes	T. Nagata
W. H. Borter	J. B. Ossmann
M. E. Cohen	S. Pellet
R. P. Deubler	E. L. Pleins
P. R. Donavin	W. J. Sperko
A. C. Eberhardt	Y. J. Wang
J. V. Gardiner	W. Windes
W. J. Geringer	C. Basavaraju, <i>Alternate</i>
J. Grimm	T. P. Davis, <i>Contributing Member</i>
S. Hunter	T.-L. Sham, <i>Contributing Member</i>
R. J. Jetter	C. T. Smith, <i>Contributing Member</i>
J. I. Kim	R. M. Jessee, <i>Honorary Member</i>
G. H. Koo	E. B. Branch, <i>Honorary Member</i>
D. W. Lewis	M. N. Bressler, <i>Honorary Member</i>
M. A. Lockwood	G. D. Cooper, <i>Honorary Member</i>
D. W. Mann	D. F. Landers, <i>Honorary Member</i>
K. A. Manoly	C. Pieper, <i>Honorary Member</i>

Executive Committee (BPV III)

R. B. Keating, <i>Chair</i>	K. A. Manoly
A. Maslowski, <i>Secretary</i>	D. E. Matthews
T. M. Adams	B. McGlone
T. P. Davis	S. McKillop
P. R. Donavin	J. B. McLean
D. W. Lewis	Yanli Wang
D. Mann	K. A. Kavanagh, <i>Alternate</i>

Latin America International Working Group (BPV III)

M. F. Liendo, <i>Chair</i>	A. J. Dall'Osto
J. Fernández, <i>Vice Chair</i>	J. I. Duo
O. Martinez, <i>Staff Secretary</i>	M. M. Gamizo
P. Yamamoto, <i>Secretary</i>	I. M. Guerreiro
E. H. Aldaz	I. A. Knorr
G. O. Anteri	D. E. Matthews
A. P. Antipasti	A. E. Pastor
D. O. Bordato	M. Rivero
G. Bourguigne	R. Taboada
M. Brusa	O. A. Verastegui
A. Claus	M. D. Vigliano
R. G. Cocco	M. Zunino

China International Working Group (BPV III)

Yong Wang, <i>Chair</i>	C. Peiyin
J. Gu, <i>Vice Chair</i>	Z. Sun
C. Jiang, <i>Vice Chair</i>	G. Tang
H. Yu, <i>Secretary</i>	L. Ting
L. Feng	J. Wen
L. Guo	F. Wu
D. Kang	C. Yang
Y. Li	P. Yang
H. Lin	W. Yang
Shenghua Liu	H. Yin
W. Liu	D. Yuangang
J. Ma	D. Zhao
K. Mao	Z. Zhong
D. E. Matthews	Q. Zhou
J. Ming	H. Zhu
W. Pei	

Korea International Working Group (BPV III)

G. H. Koo, <i>Chair</i>	B. Lee
O.-S. Kim, <i>Secretary</i>	D. Lee
H. Ahn	D. W. Lee
S. Cho	Sanghoon Lee
G.-S. Choi	Sungjae Lee
M. Choi	S.-G. Lee
M.-J. Choi	H. Lim
S. Choi	I.-K. Nam
J. Y. Hong	C.-K. Oh
N.-S. Huh	C.-Y. Oh
S. S. Hwang	E.-J. Oh
C. Jang	C. Park
I.-S. Jeong	H. Park
S. H. Kang	Y.-H. Park
J. Kim	Y. S. Pyun
J. I. Kim	J. H. Seo
J.-S. Kim	T. Shin
M.-W. Kim	S. Song
S.-S. Kim	T.-K. Song
Y.-B. Kim	W. J. Sperko
Y.-S. Kim	J. S. Yang
D. Kwon	O. Yoo

European International Working Group (BPV III)

J. Wendt, <i>Chair</i>	F. Juettemann
D. Koelbl, <i>Vice Chair</i>	M. H. Koeppen
R. Gersinska, <i>Secretary</i>	C. Kuschke
P. Ancion	H.-W. Lange
P. R. Donavin	T. Ludwig
R. Döring	M. Reichert
C. G. Frantescu	G. Roos
T. Hantzka	J. Rudolph
A. Huber	L. Sybertz
R. E. Hueggenberg	I. Tewes
E. Iacopetta	R. Tiete
A. Juengert	F. Wille

Seismic Design Steering Committee (BPV III)

T. M. Adams, <i>Chair</i>	R. M. Pace
K. Gresh, <i>Secretary</i>	M. Pérès
C. Basavaraju	K. Shibukuwa
D. Chowdhury	F. G. Abatt, <i>Contributing Member</i>
R. Döring	M. Arcaro, <i>Contributing Member</i>
G. H. Koo	P. R. Donavin, <i>Contributing Member</i>
A. Maekawa	
J. B. McLean	R. W. Haupt, <i>Contributing Member</i>

Task Group on Alternate Requirements (BPV III)

J. Wen, <i>Chair</i>	K. A. Manoly
R. R. Romano, <i>Secretary</i>	D. E. Matthews
T. Basso	S. McKillop
P. J. Coco	B. P. Nolan
P. R. Donavin	J. B. Ossmann
J. V. Gardiner	E. C. Renaud
F. Grant	M. A. Richter
J. Grimm	R. Summitt
R. S. Hill III	K. Voelsing
M. Kris	Yanli Wang
M. A. Lockwood	I. H. Tseng, <i>Alternate</i>

India International Working Group (BPV III)

S. B. Parkash, <i>Chair</i>	T. Mukherjee
V. Sehgal, <i>Vice Chair</i>	D. Narain
M. Brijlani, <i>Secretary</i>	A. D. Paranjpe
S. Aithal	J. R. Patel
A. D. Bagdare	E. L. Pleins
H. Dalal	S. Ponnappan
S. K. Goyal	T. J. P. Rao
D. Kulkarni	S. Singh
Raj Kumar	B. K. Sreedhar
Ritesh Kumar	N. Mistry, <i>Alternate</i>
S. Kumar	

United Kingdom International Working Group (BPV III)

P. M. James, <i>Chair</i>	S. A. Jones
J. Emslie, <i>Vice Chair</i>	B. McGlone
C. B. Carpenter, <i>Secretary</i>	B. Pellereau
T. Bann	E. I. S. Pendry
M. J. Chevalier	J. Randles
A. J. Cole-Baker	C. R. Schneider
M. Consonni	J. W. Stairmand
M. J. Crathorne	J. Sulley
P. Gill	J. Talamantes-Silva
G. Innes	A. J. Holt, <i>Contributing Member</i>

Special Working Group on New Plant Construction Issues (BPV III)

J. B. Ossmann, <i>Chair</i>	Z. McLucas
A. Maslowski, <i>Staff Secretary</i>	N. J. McTiernan
M. C. Buckley, <i>Secretary</i>	K. Pigg
M. Arcaro	E. L. Pleins
K. Burnett	J. Pollak
A. Cardillo	D. W. Sandusky
P. J. Coco	M. C. Scott
K. Harris	R. R. Stevenson
E. Henry	H. Xu
J. Honcharik	J. Yan
M. Kris	J. C. Minichiello, <i>Contributing Member</i>
R. E. McLaughlin	
A. McLendon	

Special Working Group on Editing and Review (BPV III)

D. E. Matthews, <i>Chair</i>	J. C. Minichiello
R. P. Deubler	J. F. Strunk
A. C. Eberhardt	Yanli Wang
S. Hunter	C. Wilson
B. McGlone	

Special Working Group on HDPE Stakeholders (BPV III)

S. Patterson, <i>Secretary</i>	J. E. O'Sullivan
M. Kuntz	

Special Working Group on Honors and Awards (BPV III)

R. W. Barnes, <i>Chair</i>	D. E. Matthews
A. Appleton	J. C. Minichiello
R. M. Jessee	

Special Working Group on International Meetings and IWG Liaisons (BPV III)

D. E. Matthews, <i>Chair</i>	P. R. Donavin
A. Maslowski, <i>Staff Secretary</i>	E. L. Pleins
R. W. Barnes	W. J. Sperko

Joint ACI-ASME Committee on Concrete Components for Nuclear Service (BPV III)

J. B. McLean, <i>Chair</i>	J. S. Saini
L. J. Colarusso, <i>Vice Chair</i>	J. F. Strunk
A. Dinizulu, <i>Staff Secretary</i>	G. Thomas
S. Bae	A. Varma
C. J. Bang	S. Wang
A. C. Eberhardt	A. Istar, <i>Alternate</i>
B. D. Hovis	A. Adediran, <i>Contributing Member</i>
T. C. Inman	J.-B. Domage, <i>Contributing Member</i>
C. Jones	P. S. Ghosal, <i>Contributing Member</i>
T. Kang	M. R. Senecal, <i>Contributing Member</i>
N.-H. Lee	Z. Shang, <i>Contributing Member</i>
S. Malushte	M. Sircar, <i>Contributing Member</i>
J. A. Munshi	C. T. Smith, <i>Contributing Member</i>
T. Muraki	

Special Working Group on Modernization (SG Div 2) (BPV III)

A. Varma, <i>Chair</i>	S. Wang
J. B. McLean, <i>Vice Chair</i>	I. Zivanovic
J. S. Saini, <i>Vice Chair</i>	R. Janowiak, <i>Contributing Member</i>
A. Adediran	F. Lin, <i>Contributing Member</i>
S. Malushte	J. A. Pires, <i>Contributing Member</i>

Task Group on Steel-Concrete Composite Containments (SG Div 2) (BPV III)

A. Varma, <i>Chair</i>	J. B. McLean
R. Janowiak	J. A. Pires
S. Malushte	J. S. Saini

Working Group on Design (SG Div 2) (BPV III)

N.-H. Lee, <i>Chair</i>	S. Wang
S. Bae	A. Istar, <i>Alternate</i>
L. J. Colarusso	P. S. Ghosal, <i>Contributing Member</i>
A. C. Eberhardt	S.-Y. Kim, <i>Contributing Member</i>
B. D. Hovis	J. Kwon, <i>Contributing Member</i>
T. C. Inman	S. E. Ohler-Schmitz, <i>Contributing Member</i>
C. Jones	B. B. Scott, <i>Contributing Member</i>
J. A. Munshi	Z. Shang, <i>Contributing Member</i>
T. Muraki	M. Shin, <i>Contributing Member</i>
J. S. Saini	M. Sircar, <i>Contributing Member</i>
G. Thomas	

Working Group on Materials, Fabrication, and Examination (SG Div 2) (BPV III)

C. Jones, <i>Chair</i>	Z. Shang
A. Eberhardt, <i>Vice Chair</i>	J. F. Strunk
C. J. Bang	I. Zivanovic
B. Birch	A. A. Aboelmagd, <i>Contributing Member</i>
J.-B. Domage	P. S. Ghosal, <i>Contributing Member</i>
T. Kang	
N.-H. Lee	

Subcommittee on Design (BPV III)

P. R. Donavin, <i>Chair</i>	M. N. Mitchell
S. McKillop, <i>Vice Chair</i>	B. Pellereau
R. P. Deubler, <i>Secretary</i>	Yanli Wang
T. P. Davis	W. F. Weitz
M. A. Gray	C. Basavaraju, <i>Alternate</i>
R. I. Jetter	G. L. Hollinger, <i>Contributing Member</i>
R. B. Keating	W. J. O'Donnell, Sr., <i>Contributing Member</i>
J. I. Kim	K. Wright, <i>Contributing Member</i>
K. A. Manoly	
D. E. Matthews	

Subgroup on Component Design (SC-D) (BPV III)

D. E. Matthews, <i>Chair</i>	J. C. Minichiello
P. Vock, <i>Vice Chair</i>	T. Mitsuhashi
D. Chowdhury, <i>Secretary</i>	D. Murphy
D. J. Ammerman	T. M. Musto
G. A. Antaki	T. Nagata
J. J. Arthur	S. Pellet
S. Asada	S. Willoughby-Braun
C. Basavaraju	C. Wilson
N. A. Costanzo	T. M. Adams, <i>Contributing Member</i>
R. P. Deubler	R. B. Keating, <i>Contributing Member</i>
P. Hirschberg	O.-S. Kim, <i>Contributing Member</i>
M. Kassir	R. J. Masterson, <i>Contributing Member</i>
D. Keck	H. S. Mehta, <i>Contributing Member</i>
T. R. Liszkai	G. Z. Tokarski, <i>Contributing Member</i>
K. A. Manoly	J. P. Tucker, <i>Contributing Member</i>
R. Martin	
K. R. May	

Task Group on Pressurized Heavy Water Reactor (SG-CD) (BPV III)

R. W. Barnes, <i>Chair</i>	E. L. Pleins
M. Brijlani	W. D. Reinhardt
D. E. Matthews	C. A. Sanna
B. McGlone	V. Sehgal
J. B. Ossmann	S. Singh
S. B. Parkash	

Task Group to Improve Section III/XI Interface (SG-CD) (BPV III)

P. Vock, <i>Chair</i>	C. A. Nove
E. Henry, <i>Secretary</i>	T. Nuoffer
G. A. Antaki	J. B. Ossmann
A. Cardillo	A. T. Roberts III
D. Chowdhury	J. Sciulli
J. Honcharik	A. Udyawar
J. Hurst	S. Willoughby-Braun
J. Lambin	

Working Group on Core Support Structures (SG-CD) (BPV III)

R. Martin, <i>Chair</i>	M. D. Snyder
R. Z. Ziegler, <i>Secretary</i>	R. O. Vollmer
G. W. Delpont	T. M. Wiger
L. C. Hartless	C. Wilson
D. Keck	Y. Wong
T. R. Liszkai	K. Hsu, <i>Alternate</i>
M. Nakajima	H. S. Mehta, <i>Contributing Member</i>

Working Group on Design of Division 3 Containment Systems (SG-CD) (BPV III)

D. J. Ammerman, <i>Chair</i>	D. Siromani
S. Klein, <i>Secretary</i>	C. R. Sydnor
J. Bignell	R. Sypulski
G. Bjorkman	R. Williamson
V. Broz	X. Zhai
D. D. Imholte	X. Zhang
D. W. Lewis	J. Smith, <i>Alternate</i>
A. Rigato	J. C. Minichiello, <i>Contributing Member</i>
P. Sakalaukus, Jr.	

Working Group on HDPE Design of Components (SG-CD) (BPV III)

M. Brandes	K. A. Manoly
J. R. Hebeisen	D. P. Munson
P. Krishnaswamy	R. Stakenborghs
M. Kuntz	B. Lin, <i>Alternate</i>

Working Group on Piping (SG-CD) (BPV III)

G. A. Antaki, <i>Chair</i>	W. F. Weitze
S. Weindorf, <i>Secretary</i>	K. Hsu, <i>Alternate</i>
C. Basavaraju	R. B. Keating, <i>Contributing Member</i>
J. Catalano	T. B. Littleton, <i>Contributing Member</i>
C. M. Faidy	Y. Liu, <i>Contributing Member</i>
R. G. Gilada	J. F. McCabe, <i>Contributing Member</i>
M. A. Gray	J. C. Minichiello, <i>Contributing Member</i>
R. J. Gurdal	A. N. Nguyen, <i>Contributing Member</i>
R. W. Haupt	M. S. Sills, <i>Contributing Member</i>
A. Hirano	N. C. Sutherland, <i>Contributing Member</i>
P. Hirschberg	G. Z. Tokarski, <i>Contributing Member</i>
M. Kassir	E. A. Wais, <i>Contributing Member</i>
D. Lieb	C.-I. Wu, <i>Contributing Member</i>
M. Moenssens	
I.-K. Nam	
K. E. Reid II	
B. Still	
D. Vlaicu	

Working Group on Pressure Relief (SG-CD) (BPV III)

K. R. May, <i>Chair</i>	B. J. Yonsky
J. F. Ball, <i>Vice Chair</i>	Y. Wong, <i>Alternate</i>
R. Krithivasan, <i>Secretary</i>	J. Yu, <i>Alternate</i>
J. W. Dickson	M. Brown, <i>Contributing Member</i>
N. Hansing	S. T. French, <i>Contributing Member</i>
S. Jones	S. Ruesenberg, <i>Contributing Member</i>
D. Miller	
T. Patel	

Working Group on Pumps (SG-CD) (BPV III)

D. Chowdhury, <i>Chair</i>	K. J. Noel
J. V. Gregg, Jr., <i>Secretary</i>	D. Skidmore
B. Busse	J. Sulley
R. Ibrahim	Y. Wong
T. Johnson	N. Chandran, <i>Alternate</i>

Working Group on Supports (SG-CD) (BPV III)

N. A. Costanzo, <i>Chair</i>	G. Z. Tokarski
U. S. Bandyopadhyay, <i>Secretary</i>	L. Vandersip
K. Avrithi	P. Wiseman
N. M. Bisceglia	J. Bozga, <i>Alternate</i>
R. P. Deubler	R. J. Masterson, <i>Contributing Member</i>
N. M. Graham	R. Roche-Rivera, <i>Contributing Member</i>
Y. Matsubara	J. R. Stinson, <i>Contributing Member</i>
S. Pellet	
G. Thomas	

Working Group on Valves (SG-CD) (BPV III)

P. Vock, <i>Chair</i>	C. A. Mizer
S. Jones, <i>Secretary</i>	H. O'Brien
M. C. Buckley	J. O'Callaghan
N. Hansing	M. Rain
G. A. Jolly	K. E. Reid II
J. Lambin	J. Sulley
T. Lippucci	Y. Wong, <i>Alternate</i>

Working Group on Vessels (SG-CD) (BPV III)

D. Murphy, <i>Chair</i>	M. C. Scott
S. Willoughby-Braun, <i>Secretary</i>	J. Shupert
J. J. Arthur	D. Vlaicu
C. Basavaraju	C. Wilson
M. Brijlani	R. Z. Ziegler
L. Constantinescu	M. R. Breach, <i>Alternate</i>
J. I. Kim	B. Basu, <i>Contributing Member</i>
D. E. Matthews	R. B. Keating, <i>Contributing Member</i>
T. Mitsuhashi	W. F. Weitze, <i>Contributing Member</i>
T. J. Schrieffer	

Subgroup on Design Methods (SC-D) (BPV III)

S. McKillop, <i>Chair</i>	W. D. Reinhardt
P. R. Donavin, <i>Vice Chair</i>	P. Smith
J. Wen, <i>Secretary</i>	R. O. Vollmer
K. Avrithi	W. F. Weitze
M. A. Gray	Y. Wong, <i>Alternate</i>
J. V. Gregg, Jr.	S. R. Gosselin, <i>Contributing Member</i>
K. Hsu	H. T. Harrison III, <i>Contributing Member</i>
E. Isom	W. J. O'Donnell, Sr., <i>Contributing Member</i>
R. Kalnas	K. Wright, <i>Contributing Member</i>
D. Keck	
J. I. Kim	
B. Pellereau	

Special Working Group on Computational Modeling for Explicit Dynamics (SG-DM) (BPV III)

G. Bjorkman, <i>Chair</i>	P. Sakalaukus, Jr.
D. J. Ammerman, <i>Vice Chair</i>	D. Siromani
V. Broz, <i>Secretary</i>	C.-F. Tso
J. Bignell	M. C. Yaksh
S. Kuehner	U. Zencker
D. Molitoris	X. Zhang
W. D. Reinhardt	M. R. Breach, <i>Contributing Member</i>
E. Rosvall	Y. Wong, <i>Contributing Member</i>

Working Group on Design Methodology (SG-DM) (BPV III)

B. Pellereau, <i>Chair</i>	W. F. Weitze
R. O. Vollmer, <i>Secretary</i>	J. Wen
K. Avrithi	T. M. Wiger
C. Basavaraju	J. Wu
F. Berkepile	K. Hsu, <i>Alternate</i>
M. Cho	G. Banyay, <i>Contributing Member</i>
D. Clarkson	D. S. Bartran, <i>Contributing Member</i>
C. M. Faigy	R. D. Blevins, <i>Contributing Member</i>
Y.-J. Gao	M. R. Breach, <i>Contributing Member</i>
M. Kassir	H. T. Harrison III, <i>Contributing Member</i>
J. I. Kim	P. Hirschberg, <i>Contributing Member</i>
T. R. Liszkai	S. McKillop, <i>Contributing Member</i>
D. Lytle	A. Walker, <i>Contributing Member</i>
K. Matsunaga	K. Wright, <i>Contributing Member</i>
S. Ranganath	
W. D. Reinhardt	
S. Wang	

Working Group on Environmental Fatigue Evaluation Methods (SG-DM) (BPV III)

M. A. Gray, <i>Chair</i>	B. Pellereau
W. F. Weitze, <i>Secretary</i>	T. Seppanen
S. Asada	D. Vlaicu
K. Avrithi	K. Wang
R. C. Cipolla	K. A. Manoly, <i>Alternate</i>
T. M. Damiani	S. Cuvilliez, <i>Contributing Member</i>
C. M. Faigy	T. D. Gilman, <i>Contributing Member</i>
A. Hirano	S. R. Gosselin, <i>Contributing Member</i>
P. Hirschberg	Y. He, <i>Contributing Member</i>
K. Hsu	H. S. Mehta, <i>Contributing Member</i>
A. Morley	K. Wright, <i>Contributing Member</i>
J.-S. Park	

Working Group on Fatigue Strength (SG-DM) (BPV III)

P. R. Donavin, <i>Chair</i>	Y. Zou
T. M. Damiani	C. E. Hinnant, <i>Contributing Member</i>
D. W. DeJohn	P. Hirschberg, <i>Contributing Member</i>
C. M. Faigy	S. H. Kleinsmith, <i>Contributing Member</i>
P. Gill	S. Majumdar, <i>Contributing Member</i>
R. J. Gurdal	H. S. Mehta, <i>Contributing Member</i>
K. Hsu	W. J. O'Donnell, Sr., <i>Contributing Member</i>
J. I. Kim	S. Ranganath, <i>Contributing Member</i>
A. Morley	K. Wright, <i>Contributing Member</i>
B. Pellereau	
M. S. Shelton	
I. Viscarra	
Yanli Wang	
W. F. Weitze	

Working Group on Probabilistic Methods in Design (SG-DM) (BPV III)

M. Golliet, <i>Chair</i>	K. A. Manoly
R. Kalnas, <i>Vice Chair</i>	A. Morley
G. Brouette	B. Pellereau
R. Fougereusse	A. Weaver
J. Hakii	M. Yagodich
E. Hanson	I. H. Tseng, <i>Alternate</i>
D. O. Henry	K. Avrithi, <i>Contributing Member</i>
A. Hirano	R. S. Hill III, <i>Contributing Member</i>

Subgroup on Containment Systems for Spent Nuclear Fuel and High-Level Radioactive Material (BPV III)

D. W. Lewis, <i>Chair</i>	C. R. Sydnor
D. J. Ammerman, <i>Vice Chair</i>	R. Sypulski
S. Klein, <i>Secretary</i>	J. Wellwood
J. Bignell	X. J. Zhai
G. Bjorkman	X. Zhang
V. Broz	J. Smith, <i>Alternate</i>
D. D. Imholte	W. H. Borter, <i>Contributing Member</i>
A. Rigato	E. L. Pleins, <i>Contributing Member</i>
P. Sakalaukus, Jr.	N. M. Simpson, <i>Contributing Member</i>
D. Siromani	

Subgroup on Fusion Energy Devices (BPV III)

T. P. Davis, <i>Chair</i>	I. Kimihiro
A. Maslowski, <i>Staff Secretary</i>	P. Mokaria
M. Ellis, <i>Secretary</i>	F. J. Schaaf, Jr.
L. Babu	P. Smith
M. Bashir	Y. Song
J. P. Blanchard	D. White
B. R. Doshi	R. W. Barnes, <i>Contributing Member</i>
L. El-Guebaly	W. K. Sowder, Jr., <i>Contributing Member</i>
R. Holmes	
D. Johnson	

Special Working Group on Fusion Stakeholders (SG-FED) (BPV III)

R. Holmes, <i>Chair</i>	S. S. Desai
C. Barnes	F. Deschamps
R. W. Barnes	M. Hua
J. Brister	S. Krishnan
A. A. Campbell	W. K. Sowder, Jr.
V. Chugh	N. Young
T. P. Davis	

Working Group on General Requirements (SG-FED) (BPV III)

P. Smith, <i>Chair</i>	B. McGlone
L. Babu	P. Mokaria
T. P. Davis	W. K. Sowder, Jr.
M. Ellis	D. White, <i>Contributing Member</i>

Working Group on In-Vessel Components (SG-FED) (BPV III)

M. Bashir, <i>Chair</i>	S. T. Madabusi
T. P. Davis	

Working Group on Magnets (SG-FED) (BPV III)

D. S. Bartran	W. K. Sowder, Jr., <i>Contributing Member</i>

Working Group on Materials (SG-FED) (BPV III)

T. P. Davis

Working Group on Vacuum Vessels (SG-FED) (BPV III)

I. Kimihiro, <i>Chair</i>	D. Johnson
B. R. Doshi	

Subgroup on General Requirements (BPV III)

B. McGlone, <i>Chair</i>	L. Noyes
A. McLendon, <i>Secretary</i>	E. C. Renaud
V. Apostolescu	T. N. Rezk
A. Appleton	J. Rogers
S. Bell	B. S. Sandhu
G. Brouette	R. Spuhl
P. J. Coco	J. L. Williams
G. C. Deleanu	Y. Diaz-Castillo, <i>Alternate</i>
N. DeSantis	J. DeKleine, <i>Contributing Member</i>
O. Elkadim	S. F. Harrison, Jr., <i>Contributing Member</i>
J. V. Gardiner	H. Michael, <i>Contributing Member</i>
J. Grimm	D. J. Roszman, <i>Contributing Member</i>
J. Harris	C. T. Smith, <i>Contributing Member</i>
J. W. Highlands	G. E. Szabatura, <i>Contributing Member</i>
E. V. Imbro	
K. A. Kavanagh	
Y.-S. Kim	
D. T. Meisch	

Working Group on General Requirements for Graphite and Ceramic Composite Core Components and Assemblies (SG-GR) (BPV III)

W. J. Geringer, <i>Chair</i>	M. N. Mitchell
A. Appleton	J. Potgieter
J. R. Berry	E. C. Renaud
A. A. Campbell	S. Sekar
C. Cruz	R. Spuhl
Y. Diaz-Castillo	W. Windes
J. Lang	B. Lin, <i>Alternate</i>

Subgroup on High Temperature Reactors (BPV III)

Yanli Wang, <i>Chair</i>	X. Wei
N. Broom	W. Windes
F. W. Brust	R. Wright
M. E. Cohen	G. L. Zeng
W. J. Geringer	J. Bass, <i>Alternate</i>
B. F. Hantz	P. Carter, <i>Contributing Member</i>
M. Hiser	W. O'Donnell, Sr., <i>Contributing Member</i>
R. I. Jetter	T.-L. Sham
K. Kimura	L. Shi, <i>Contributing Member</i>
G. H. Koo	R. W. Swindeman, <i>Contributing Member</i>
W. Li	
M. C. Messner	

Special Working Group on High Temperature Reactor Stakeholders (SG-HTR) (BPV III)

M. E. Cohen, <i>Chair</i>	R. I. Jetter
M. C. Albert	G. H. Koo
M. Arcaro	N. J. McTiernan
R. W. Barnes	M. N. Mitchell
R. Bass	K. J. Noel
N. Broom	J. Roll
K. Burnett	B. Song
A. A. Campbell	Yanli Wang
V. Chugh	X. Wei
W. Corwin	G. L. Zeng
G. C. Deleanu	R. M. Iyengar, <i>Alternate</i>
R. A. Fleming	T. Asayama, <i>Contributing Member</i>
K. Harris	

Task Group on Alloy 709 Code Case (SG-HTR) (BPV III)

Yanli Wang, <i>Chair</i>	W. J. Sperko
H. Mahajan, <i>Secretary</i>	R. Wright
R. I. Jetter	T.-L. Sham, <i>Contributing Member</i>
M. C. Messner	

Working Group on Allowable Stress Criteria (SG-HTR) (BPV III)

R. Wright, <i>Chair</i>	M. C. Messner
M. McMurtrey, <i>Secretary</i>	T. Patterson
R. W. Barnes	Yanli Wang
R. Bass	X. Wei
K. Kimura	R. M. Iyengar, <i>Alternate</i>
W. Li	R. W. Swindeman, <i>Contributing Member</i>
D. Maitra	
R. J. McReynolds	

Task Group on Class A Rewrite (SG-HTR) (BPV III)

Yanli Wang, <i>Chair</i>	N. J. McTiernan
R. W. Barnes	M. C. Messner
M. E. Cohen	T. Nguyen
R. I. Jetter	D. Pease
H. Mahajan	X. Wei
S. McKillop	J. Young

Working Group on Analysis Methods (SG-HTR) (BPV III)

M. C. Messner, <i>Chair</i>	X. Song
H. Mahajan, <i>Secretary</i>	Yanli Wang
R. Adibi-Asl	X. Wei
R. W. Barnes	S. X. Xu
J. A. Blanco	J. Young
P. Carter	J. Bass, <i>Alternate</i>
R. I. Jetter	M. R. Breach, <i>Contributing Member</i>
G. H. Koo	Y.-J. Gao, <i>Contributing Member</i>
T. Nguyen	T. Hassan, <i>Contributing Member</i>
M. Petkov	S. Krishnamurthy, <i>Contributing Member</i>
K. Pigg	M. J. Swindeman, <i>Contributing Member</i>
H. Qian	
T. Riordan	

Task Group on Division 5 AM Components (SG-HTR) (BPV III)

R. Wright, <i>Chair</i>	T. Patterson
R. W. Barnes	E. C. Renaud
F. W. Brust	D. Rudland
Z. Feng	B. Sutton
S. Lawler	I. J. Van Rooyen
X. Lou	Yanli Wang
M. McMurtrey	X. Wei
M. C. Messner	R. Bass, <i>Alternate</i>

Working Group on Creep-Fatigue and Negligible Creep (SG-HTR) (BPV III)

W. Li, <i>Chair</i>	M. McMurtrey
J. Bass	M. C. Messner
C. M. Brusconi	H. Qian
P. Carter	R. Rajasekaran
M. E. Cohen	M. Shah
J. I. Duo	Yanli Wang
R. I. Jetter	X. Wei
G. H. Koo	J. Young
H. Mahajan	R. Bass, <i>Alternate</i>

Task Group on Graphite Design Analysis (SG-HTR) (BPV III)

A. Mack, <i>Chair</i>	P.-A. Juan
J. Bass	J. Potgieter
S. Baylis	J. Quick
G. Beirnaert	M. Saitta
O. Booler	A. Walker

Working Group on Nonmetallic Design and Materials (SG-HTR) (BPV III)

W. Windes, <i>Chair</i>	J. Parks
W. J. Geringer, <i>Vice Chair</i>	K. Pigg
J. Potgieter, <i>Secretary</i>	J. Podhiny
G. Beirnaert	J. Roll
A. A. Campbell	A. Tzelepi
C. Chen	A. Walker
A. N. Chereskin	Yanli Wang
V. Chugh	G. L. Zeng
C. Contescu	J. Bass, <i>Alternate</i>
N. Gallego	A. Appleton, <i>Contributing Member</i>
S. T. Gonczy	R. W. Barnes, <i>Contributing Member</i>
K. Harris	S.-H. Chi, <i>Contributing Member</i>
M. G. Jenkins	Y. Katoh, <i>Contributing Member</i>
P.-A. Juan	J. B. Ossmann, <i>Contributing Member</i>
J. Lang	
A. Mack	J. Quick, <i>Contributing Member</i>
M. P. Metcalfe	M. Saitta, <i>Contributing Member</i>
M. N. Mitchell	

Task Group on High Temperature Piping Design (SG-HTR) (BPV-III)

G. A. Antaki, <i>Chair</i>	H. Mahajan
S. Weindorf, <i>Secretary</i>	J. C. Minichiello
R. Adibi-Asl	D. Pease
T. D. Al-Shawaf	Yanli Wang
D. Bankston, Jr.	C. D. Weary
R. P. Deubler	T.-L. Sham, <i>Contributing Member</i>
R. I. Jetter	

Subgroup on Materials, Fabrication, and Examination (BPV III)

D. W. Mann, <i>Chair</i>	M. Kris
J. Grimm, <i>Vice Chair</i>	T. Melfi
J. B. Ossmann, <i>Vice Chair</i>	I.-K. Nam
S. Hunter, <i>Secretary</i>	J. E. O'Sullivan
W. H. Borter	M. C. Scott
M. Brijlani	W. J. Sperko
G. R. Cannell	J. F. Strunk
A. Cardillo	W. Windes
S. Cho	R. Wright
P. J. Coco	H. Xu
R. H. Davis	S. Yee
D. B. Denis	J. Wise, Jr., <i>Alternate</i>
B. D. Frew	S. Wolbert, Jr., <i>Alternate</i>
D. W. Gandy	R. W. Barnes, <i>Contributing Member</i>
S. E. Gingrich	S. Levitus, <i>Contributing Member</i>
M. Golliet	H. Michael, <i>Contributing Member</i>
L. S. Harbison	

Working Group on Advanced Manufacturing (SG-MFE) (BPV III)

D. W. Mann, <i>Chair</i>	E. C. Renaud
D. W. Gandy, <i>Secretary</i>	W. J. Sperko
D. Chowdhury	J. F. Strunk
P. J. Coco	J. Sulley
B. D. Frew	S. Tate
J. Grimm	J. Wise
J. Lambin	S. Wolbert
T. Lippucci	H. Xu
T. Melfi	R. H. Davis, <i>Alternate</i>
A. Mori	S. Malik, <i>Contributing Member</i>

Joint Working Group on HDPE (SG-MFE) (BPV III)

M. Brandes, <i>Chair</i>	K. Manoly
T. M. Musto, <i>Chair</i>	D. P. Munson
J. B. Ossmann, <i>Secretary</i>	J. O'Sullivan
G. Brouette	V. Rohatgi
M. C. Buckley	F. Schaaf, Jr.
S. Choi	S. Schuessler
M. Golliet	R. Stakenborghs
J. Hebeisen	M. Troughton
J. Johnston, Jr.	P. Vibien
P. Krishnaswamy	J. Wright
M. Kuntz	T. Adams, <i>Contributing Member</i>
B. Lin	

COMMITTEE ON HEATING BOILERS (BPV IV)

M. Wadkinson, <i>Chair</i>	J. A. Hall
J. L. Kleiss, <i>Vice Chair</i>	M. Mengon
C. R. Ramcharran, <i>Staff Secretary</i>	Y. Teng
B. Ahee	D. Picart, <i>Delegate</i>
L. Badziagowski	Y. R. Cho, <i>Alternate</i>
T. L. Bedeaux	B. J. Iske, <i>Alternate</i>
B. Calderon	T. Wagner, <i>Alternate</i>
J. P. Chicoine	H. Michael, <i>Contributing Member</i>
C. Dinic	P. A. Molvie, <i>Contributing Member</i>
J. M. Downs	

Executive Committee (BPV IV)

M. Wadkinson, <i>Chair</i>	J. P. Chicoine
C. R. Ramcharran, <i>Staff Secretary</i>	J. A. Hall
T. L. Bedeaux	J. L. Kleiss

Subgroup on Cast Boilers (BPV IV)

J. P. Chicoine, <i>Chair</i>	J. L. Kleiss
J. M. Downs, <i>Vice Chair</i>	M. Mengon
C. R. Ramcharran, <i>Staff Secretary</i>	B. J. Iske, <i>Alternate</i>
T. L. Bedeaux	T. Wagner, <i>Alternate</i>
J. A. Hall	

Subgroup on Materials (BPV IV)

J. A. Hall, <i>Chair</i>	T. L. Bedeaux
J. M. Downs, <i>Vice Chair</i>	Y. Teng
C. R. Ramcharran, <i>Staff Secretary</i>	M. Wadkinson
L. Badziagowski	

Subgroup on Water Heaters (BPV IV)

J. L. Kleiss, <i>Chair</i>	C. Dinic
L. Badziagowski, <i>Vice Chair</i>	M. Mengon
C. R. Ramcharran, <i>Staff Secretary</i>	Y. Teng
B. Ahee	B. J. Iske, <i>Alternate</i>
M. Carlson	T. Wagner, <i>Alternate</i>
J. P. Chicoine	P. A. Molvie, <i>Contributing Member</i>

Subgroup on Welded Boilers (BPV IV)

T. L. Bedeaux, <i>Chair</i>	J. L. Kleiss
J. P. Chicoine, <i>Vice Chair</i>	M. Mengon
C. R. Ramcharran, <i>Staff Secretary</i>	M. Wadkinson
B. Ahee	M. Washington
E. Alexis	B. J. Iske, <i>Alternate</i>
L. Badziagowski	M. J. Melita, <i>Alternate</i>
B. Calderon	T. J. Wagner, <i>Alternate</i>
M. Carlson	P. A. Molvie, <i>Contributing Member</i>
C. Dinic	

COMMITTEE ON NONDESTRUCTIVE EXAMINATION (BPV V)

N. A. Finney, <i>Chair</i>	P. Lang
C. May, <i>Vice Chair</i>	T. R. Lerohl
C. R. Ramcharran, <i>Staff Secretary</i>	J. Schoneweis
D. Bajula	P. B. Shaw
P. L. Brown	C. Vorwald
M. A. Burns	M. Carlson, <i>Alternate</i>
N. Carter	J. E. Batey, <i>Contributing Member</i>
C. Emslander	T. Clausing, <i>Contributing Member</i>
A. F. Garbolevsky	J. F. Halley, <i>Contributing Member</i>
P. T. Hayes	R. W. Kruzic, <i>Contributing Member</i>
G. W. Hembree	L. E. Mullins, <i>Contributing Member</i>
F. B. Kovacs	H. C. Graber, <i>Honorary Member</i>
K. Krueger	T. G. McCarty, <i>Honorary Member</i>
B. D. Laite	

Executive Committee (BPV V)

C. May, <i>Chair</i>	F. B. Kovacs
N. A. Finney, <i>Vice Chair</i>	K. Krueger
C. R. Ramcharran, <i>Staff Secretary</i>	B. D. Laite
V. F. Godinez-Azcuaga	E. Peloquin
P. T. Hayes	C. Vorwald
G. W. Hembree	

**Subgroup on General Requirements/Personnel Qualifications and
Inquiries (BPV V)**

C. Vorwald, <i>Chair</i>	P. Lang
K. Krueger, <i>Vice Chair</i>	T. R. Lerohl
D. Bajula	C. May
N. Carter	J. Schoneweis
P. Chavdarov	T. Clausing, <i>Contributing Member</i>
C. Emslander	J. F. Halley, <i>Contributing Member</i>
N. A. Finney	D. I. Morris, <i>Contributing Member</i>
G. W. Hembree	J. P. Swezy, Jr., <i>Contributing Member</i>
F. B. Kovacs	

Subgroup on Volumetric Methods (BPV V)

C. May, <i>Chair</i>	K. Krueger
P. T. Hayes, <i>Vice Chair</i>	N. Pasemko
P. L. Brown	E. Peloquin
N. A. Finney	J. Schoneweis
A. F. Garbolevsky	C. Vorwald
V. F. Godinez-Azcuaga	J. F. Halley, <i>Contributing Member</i>
C. Hansen	R. W. Kruzic, <i>Contributing Member</i>
R. W. Hardy	L. E. Mullins, <i>Contributing Member</i>
G. W. Hembree	C. Wassink, <i>Contributing Member</i>
F. B. Kovacs	

Working Group on Radiography (SG-VM) (BPV V)

C. Vorwald, <i>Chair</i>	B. D. Laite
D. M. Woodward, <i>Vice Chair</i>	T. R. Lerohl
D. Bajula	C. May
P. L. Brown	R. J. Mills
C. Emslander	J. F. Molinaro
A. F. Garbolevsky	N. Pasemko
R. W. Hardy	J. Schoneweis
G. W. Hembree	T. L. Clifford, <i>Contributing Member</i>
P. Howie	R. W. Kruzic, <i>Contributing Member</i>
F. B. Kovacs	

Working Group on Ultrasonics (SG-VM) (BPV V)

K. Krueger, <i>Chair</i>	C. May
D. Bajula, <i>Vice Chair</i>	E. Peloquin
D. Adkins	J. Schoneweis
C. T. Brown	D. Van Allen
C. Emslander	C. Vorwald
N. A. Finney	J. F. Halley, <i>Contributing Member</i>
P. Furr	R. W. Kruzic, <i>Contributing Member</i>
C. Hansen	P. Mudge, <i>Contributing Member</i>
P. T. Hayes	L. E. Mullins, <i>Contributing Member</i>
G. W. Hembree	M. J. Quarry, <i>Contributing Member</i>
B. D. Laite	J. Vanvelsor, <i>Contributing Member</i>
T. R. Lerohl	

**Special Working Group for Advance UT Techniques
(WG-UT) (BPV V)**

K. Krueger, <i>Chair</i>	P. Hayes
J. Schoneweis, <i>Vice Chair</i>	B. D. Laite
D. Bajula	T. R. Lerohl
C. David	E. Peloquin
N. A. Finney	D. Tompkins
P. Furr	D. Van Allen
J. Garner	C. Wassink
C. Hansen	

Working Group on Acoustic Emissions (SG-VM) (BPV V)

V. F. Godinez-Azcuaga, <i>Chair</i>	S. R. Doctor
J. Catty, <i>Vice Chair</i>	N. F. Douglas, Jr.

Working Group on Full Matrix Capture (SG-VM) (BPV V)

E. Peloquin, <i>Chair</i>	M. Lozev
P. T. Hayes, <i>Vice Chair</i>	R. Nogueira
D. Bajula	D. Richard
J. Catty	M. Sens
N. A. Finney	D. Tompkins
J. L. Garner	J. F. Halley, <i>Contributing Member</i>
R. T. Grotenhuis	L. E. Mullins, <i>Contributing Member</i>
G. W. Hembree	C. Wassink, <i>Contributing Member</i>
K. Krueger	

**Subgroup on Inservice Examination Methods and Techniques
(BPV V)**

P. T. Hayes, <i>Chair</i>	V. F. Godinez-Azcuaga
E. Peloquin, <i>Vice Chair</i>	C. Hansen
D. Bajula	G. W. Hembree
R. Barker	K. Krueger
R. J. Bunte	C. May
M. A. Burns	N. Pasemko
M. Carlson	D. D. Raimander
T. Demmer	B. Ray
N. Douglas, Jr.	J. Schoneweis
N. A. Finney	C. Vorwald

Working Group on Assisted Analysis (SG-ISI) (BPV V)

T. Demmer, <i>Chair</i>	G. W. Hembree
C. Hansen, <i>Vice Chair</i>	G. I. Kraljic
J. Aldrin	G. M. Lozev
J. Chen	R. S. F. Orozco
M. Elen	E. Peloquin
N. A. Finney	T. Thulien
V. F. Godinez-Azcuaga	J. Williams
R. T. Grotenhuis	S. Zafar
K. Hayes	

Working Group on Methods and Techniques (SG-ISI) (BPV V)

C. May, <i>Chair</i>	P. T. Hayes
R. J. Bunte, <i>Vice Chair</i>	K. Krueger
D. Bajula	B. D. Laite
R. Barker	G. Morais
M. A. Burns	N. Pasemko
M. Carlson	J. Schoneweis
J. Catty	

**Working Group on Supplemental Requirements for Corrosion and
Other Damage Mechanisms (SG-ISI) (BPV V)**

J. Schoneweis, <i>Chair</i>	C. Hansen
N. Pasemko, <i>Vice Chair</i>	P. T. Hayes
D. Bajula	K. Krueger
R. Barker	E. Peloquin
N. A. Finney	I. Roux

Subgroup on Surface Examination Methods (BPV V)

B. D. Laite, <i>Chair</i>	C. May
D. Bajula	G. Morais
R. Behe	J. Schoneweis
R. M. Beldyk	P. B. Shaw
P. L. Brown	R. Tedder
N. Carter	C. Vorwald
C. Emslander	D. M. Woodward
N. Farenbaugh	T. Clausing, <i>Contributing Member</i>
N. A. Finney	J. F. Halley, <i>Contributing Member</i>
A. F. Garbolevsky	K. Hayes, <i>Contributing Member</i>
G. W. Hembree	R. W. Kruzic, <i>Contributing Member</i>
K. Krueger	L. E. Mullins, <i>Contributing Member</i>
T. R. Lerohl	C. Wassink, <i>Contributing Member</i>

Germany International Working Group (BPV V)

P. Chavdarov, <i>Chair</i>	C. Kringe
V. Pohl, <i>Vice Chair</i>	S. Mann
H.-P. Schmitz, <i>Secretary</i>	V. Reusch
D. Kaiser	P. Van IJS

India International Working Group (BPV V)

P. Kumar, <i>Chair</i>	J. V. Muthukumaraswamy
A. V. Bhagwat, <i>Vice Chair</i>	A. Relekar
V. Ligade, <i>Secretary</i>	V. J. Sonawane
S. Jobanputra	N. Suryawanshi
D. Joshi	D. B. Tanpure
G. R. Joshi	

Italy International Working Group (BPV V)

D. D. Raimander, <i>Chair</i>	E. Ferrari
O. Oldani, <i>Vice Chair</i>	M. A. Grimoldi
C. R. Ramcharan, <i>Staff Secretary</i>	G. Luoni
P. Campli, <i>Secretary</i>	U. Papponetti
M. Agostini	P. Pedersoli
T. Aldo	A. Veroni
F. Bresciani	M. Zambon
N. Caputo	G. Gobbi, <i>Contributing Member</i>
M. Colombo	A. Gusmaroli, <i>Contributing Member</i>
P. L. Dinelli	G. Pontiggia, <i>Contributing Member</i>
F. Ferrarese	

COMMITTEE ON PRESSURE VESSELS (BPV VIII)

S. C. Roberts, <i>Chair</i>	J. P. Swezy, Jr.
M. D. Lower, <i>Vice Chair</i>	S. Terada
J. Oh, <i>Staff Secretary</i>	E. Upitis
S. J. Rossi, <i>Staff Secretary</i>	A. Viet
S. R. Babka	K. Xu
L. Bower	K. Oyamada, <i>Delegate</i>
P. Chavdarov	M. E. Papponetti, <i>Delegate</i>
B. F. Hantz	G. Auriolles, Sr., <i>Contributing Member</i>
C. S. Hinson	R. J. Basile
J. Hoskinson	A. Chaudouet, <i>Contributing Member</i>
M. Kowalczyk	D. B. DeMichael, <i>Contributing Member</i>
D. L. Kurle	K. T. Lau, <i>Contributing Member</i>
R. Mahadeen	H. Michael, <i>Contributing Member</i>
S. A. Marks	R. W. Mikitka, <i>Contributing Member</i>
P. Matkovics	D. A. Swanson, <i>Contributing Member</i>
D. T. Peters	G. G. Karcher, <i>Honorary Member</i>
M. J. Pischke	U. R. Miller, <i>Honorary Member</i>
M. D. Rana	T. P. Pastor, <i>Honorary Member</i>
G. B. Rawls, Jr.	K. K. Tam, <i>Honorary Member</i>
F. L. Richter	
C. D. Rodery	
J. C. Sowinski	
D. Sronic	
P. L. Sturgill	
K. Subramanian	

Executive Committee (BPV VIII)

M. D. Lower, <i>Chair</i>	J. Hoskinson
S. J. Rossi, <i>Staff Secretary</i>	P. Matkovics
G. Auriolles, Sr.	S. C. Roberts
C. W. Cary	J. C. Sowinski
P. Chavdarov	K. Subramanian
T. Halligan	K. Xu

Subgroup on Design (BPV VIII)

J. C. Sowinski, <i>Chair</i>	S. Terada
C. S. Hinson, <i>Vice Chair</i>	K. Xu
S. R. Babka	K. Oyamada, <i>Delegate</i>
O. A. Barsky	M. E. Papponetti, <i>Delegate</i>
M. Faulkner	G. Auriolles, Sr., <i>Contributing Member</i>
D. Francis	R. J. Basile, <i>Contributing Member</i>
B. F. Hantz	D. Chandiramani, <i>Contributing Member</i>
C. E. Hinnant	M. H. Jawad, <i>Contributing Member</i>
S. Krishnamurthy	P. K. Lam, <i>Contributing Member</i>
D. L. Kurle	K. Mokhtarian, <i>Contributing Member</i>
K. Kescu	C. D. Rodery, <i>Contributing Member</i>
M. D. Lower	D. A. Swanson, <i>Contributing Member</i>
R. W. Mikitka	K. K. Tam, <i>Contributing Member</i>
B. Millet	E. Upitis, <i>Contributing Member</i>
M. D. Rana	
G. B. Rawls, Jr.	
S. C. Roberts	
T. G. Seipp	
D. Sronic	

Working Group on Design-by-Analysis (BPV VIII)

B. F. Hantz, <i>Chair</i>	S. Krishnamurthy
T. W. Norton, <i>Secretary</i>	C. Nadarajah
J. Bedoya	T. G. Seipp
A. Feller	M. Shah
S. Guzey	S. Terada
C. E. Hinnant	D. A. Arnett, <i>Contributing Member</i>
S. Kataoka	A. Mann, <i>Contributing Member</i>
S. Kilambi	K. Saboda, <i>Contributing Member</i>
K. D. Kirkpatrick	

Task Group on Electrochemical Cell Stacks (TG-ECS) (BPV VIII)

K. Xu, <i>Chair</i>	K. Choi, <i>Contributing Member</i>
K. Quackenbush, <i>Vice Chair</i>	L. T. Dalton, <i>Contributing Member</i>
N. Barkley	M. Duda, <i>Contributing Member</i>
E. Gadsby	R. Fournier, <i>Contributing Member</i>
S. Goyette	E. Gernot, <i>Contributing Member</i>
T. Halligan	S. Grimm, <i>Contributing Member</i>
R. Kauer	N. Hart, <i>Contributing Member</i>
P. Matkovics	R. Müller, <i>Contributing Member</i>
L. Moulthrop	P. K. Panigrahy, <i>Contributing Member</i>
J. Panicker	R. Robles, <i>Contributing Member</i>
E. Prause	M. Stelzel, <i>Contributing Member</i>
P. T. Shanks	M. Sweetland, <i>Contributing Member</i>
S. Ulemek	
E. Andrade, <i>Contributing Member</i>	
B. D. Carter, <i>Contributing Member</i>	

Working Group on Elevated Temperature Design (BPV I and VIII)

C. Nadarajah, <i>Chair</i>	C. T. McDaris
L. S. Tsai, <i>Secretary</i>	M. C. Messner
D. Anderson	M. N. Mitchell
D. Dewees	P. Prueter
B. F. Hantz	A. Ramos
R. I. Jetter	M. Rathinasabapathy
S. Kataoka	M. J. Swindeman
S. Krishnamurthy	A. Mann, <i>Contributing Member</i>
S. R. Kummari	N. McMurray, <i>Contributing Member</i>
T. Le	B. J. Mollitor, <i>Contributing Member</i>
B.-L. Lyow	

Task Group on Fired Heater Pressure Vessels (BPV VIII)

J. Hoskinson, <i>Chair</i>	P. T. Shanks
D. Nelson	E. Smith
R. Robles	D. Srnic
J. Rust	

Subgroup on Fabrication and Examination (BPV VIII)

T. Halligan, <i>Chair</i>	B. F. Shelley
D. I. Morris, <i>Vice Chair</i>	P. L. Sturgill
D. Smith, <i>Secretary</i>	J. P. Swezy, Jr.
J. Lu	E. Uptis
S. A. Marks	C. Violand
O. Mulet	K. Oyamada, <i>Delegate</i>
M. J. Pischke	W. J. Bees, <i>Contributing Member</i>
M. J. Rice	L. F. Campbell, <i>Contributing Member</i>
J. Roberts	N. Carter, <i>Contributing Member</i>
C. D. Rodery	

Subgroup on Heat Transfer Equipment (BPV VIII)

P. Matkovics, <i>Chair</i>	E. Smith
L. Bower, <i>Vice Chair</i>	A. M. Voytko
T. Bunyarattaphantu, <i>Secretary</i>	R. P. Wiberg
S. R. Babka	G. Auriolles, Sr., <i>Contributing Member</i>
J. H. Barbee	K. M. Chikhaliya, <i>Contributing Member</i>
O. A. Barsky	J. Pasek, <i>Contributing Member</i>
A. Chaudouet	D. Srnic, <i>Contributing Member</i>
D. L. Kurlle	Z. Tong, <i>Contributing Member</i>
R. Mahadeen	
S. Mayeux	
S. Neilsen	

Subgroup on General Requirements (BPV VIII)

J. Hoskinson, <i>Chair</i>	J. Rust
M. Faulkner, <i>Vice Chair</i>	P. T. Shanks
N. Barkley	J. C. Sowinski
T. P. Beirne	P. Speranza
R. Darby	D. Srnic
Z. Jakovljevic	D. B. Stewart
M. D. Lower	D. B. DeMichael, <i>Contributing Member</i>
T. Newman	T. P. Pastor, <i>Contributing Member</i>
I. A. Powell	R. Robles, <i>Contributing Member</i>
J. Qu	D. A. Swanson, <i>Contributing Member</i>
G. B. Rawls, Jr.	Y. Yang, <i>Contributing Member</i>
F. L. Richter	
S. C. Roberts	

Working Group on Plate Heat Exchangers (BPV VIII)

D. I. Morris, <i>Chair</i>	P. Matkovics
S. R. Babka	M. J. Pischke
V. Gudge	P. T. Shanks
T. Halligan	E. Smith
Z. Jakovljevic	D. Srnic

Subgroup on High Pressure Vessels (BPV VIII)

K. Subramanian, <i>Chair</i>	F. W. Tatar
M. Sarzynski, <i>Vice Chair</i>	S. Terada
A. Dinizulu, <i>Staff Secretary</i>	Y. Xu
L. P. Antalffy	A. M. Clayton, <i>Contributing Member</i>
N. Barkley	R. Cordes, <i>Contributing Member</i>
J. Barlow	R. D. Dixon, <i>Contributing Member</i>
R. C. Biel	J. Hademenos, <i>Contributing Member</i>
P. N. Chaku	R. M. Hoshman, <i>Contributing Member</i>
L. Fridlund	F. Kirkemo, <i>Contributing Member</i>
D. Fuenmayor	G. M. Mital, <i>Contributing Member</i>
J. Gibson	M. Parr, <i>Contributing Member</i>
R. T. Hallman	M. D. Rana, <i>Contributing Member</i>
K. Karpanan	C. Tipple, <i>Contributing Member</i>
A. K. Khare	K.-J. Young, <i>Contributing Member</i>
G. T. Nelson	D. J. Burns, <i>Honorary Member</i>
D. T. Peters	G. J. Mraz, <i>Honorary Member</i>
E. D. Roll	
J. R. Sims	
E. Smith	

Argentina International Working Group (BPV VIII)

A. Dominguez, <i>Chair</i>	M. A. Mendez
R. Robles, <i>Vice Chair</i>	J. J. Monaco
G. Glissent, <i>Secretary</i>	C. Parente
A. Antipasti	M. A. A. Pipponzi
D. A. Bardelli	L. C. Rigoli
R. A. Barey	A. Rivas
O. S. Bretones	D. Rizzo
A. Burgueno	M. A. Sena
G. Casanas	G. Telleria
D. A. Del Teglia	C. Alderetes, <i>Contributing Member</i>
M. Favareto	D. H. Da Rold, <i>Contributing Member</i>
J. A. Labastidas	J. C. Rubeo, <i>Contributing Member</i>
F. P. Larrosa	

Subgroup on Materials (BPV VIII)

P. Chavdarov, <i>Chair</i>	D. Pugh
M. Kowalczyk, <i>Vice Chair</i>	D. W. Rahoi
S. Kilambi, <i>Secretary</i>	E. Uptis
J. Cameron	K. Xu
H. Dutta	M. Katcher, <i>Contributing Member</i>
J. F. Grubb	R. C. Sutherlin, <i>Contributing Member</i>
D. Maitra	
R. K. Patadia	

China International Working Group (BPV VIII)

X. Chen, <i>Chair</i>	C. Miao
B. Shou, <i>Vice Chair</i>	L. Sun
Z. Fan, <i>Secretary</i>	C. Wu
Y. Chen	J. Xiaobin
J. Cui	F. Xu
R. Duan	G. Xu
J.-G. Gong	F. Yang
B. Han	Y. Yang
J. Hu	Y. Yuan
Q. Hu	Yanfeng Zhang
H. Hui	Yijun Zhang
K. Li	S. Zhao
D. Luo	J. Zheng
Y. Luo	G. Zhu

Subgroup on Toughness (BPV VIII)

K. Xu, <i>Chair</i>	J. P. Swezy, Jr.
T. Halligan, <i>Vice Chair</i>	S. Terada
T. Finn	E. Uptis
C. S. Hinson	J. Vattappilly
S. Kilambi	K. Oyamada, <i>Delegate</i>
D. L. Kurle	L. Dong, <i>Contributing Member</i>
T. Newman	S. Krishnamurthy, <i>Contributing Member</i>
J. Qu	D. A. Swanson, <i>Contributing Member</i>
M. D. Rana	
F. L. Richter	
K. Subramanian	

Germany International Working Group (BPV VIII)

R. Kauer, <i>Chair</i>	S. Krebs
M. Sykora, <i>Vice Chair</i>	T. Ludwig
A. Aloui	R. A. Meyers
P. Chavdarov	H. Michael
M. Delzeit	R. Müller
A. Emrich	S. Reich
C. Jaekel	A. Spangenberg
S. Jetzlsperger	C. Stobbe
D. Koelbl	

India International Working Group (BPV VIII)

D. Chandiramani, <i>Chair</i>	T. Mukherjee
D. Kulkarni, <i>Vice Chair</i>	P. C. Pathak
A. D. Dalal, <i>Secretary</i>	D. Prabhu
P. Arulkumar	A. Sadasivam
P. Gandhi	M. P. Shah
U. Ganesan	Y. Z. Shaikh
S. K. Goyal	R. Tiru
V. Jayabalan	V. T. Valavan
V. K. Joshi	M. Sharma, <i>Contributing Member</i>
A. Kakumanu	

Subgroup on Graphite Pressure Equipment (BPV VIII)

C. W. Cary, <i>Chair</i>	H. Lee, Jr.
A. Viet, <i>Vice Chair</i>	S. Mehrez
G. C. Becherer	T. Rudy
F. L. Brown	A. A. Stupica
J. D. Clements	J. Wince

Italy International Working Group (BPV VIII)

M. Millefanti, <i>Chair</i>	A. F. Magri
P. Campli, <i>Secretary</i>	L. Moracchioli
P. Aliprandi	P. Pacor
A. Avogadri	S. Sarti
A. Camanni	A. Teli
M. Camposaragna	N. Wagner
N. Caputo	V. Calo, <i>Contributing Member</i>
M. Colombo	G. Gobbi, <i>Contributing Member</i>
P. Conti	A. Gusmaroli, <i>Contributing Member</i>
D. Cortassa	G. Pontiggia, <i>Contributing Member</i>
A. Fabiano	D. D. Raimander, <i>Contributing Member</i>
F. Finco	
M. Guglielmetti	

COMMITTEE ON WELDING, BRAZING, AND FUSING (BPV IX)

M. J. Pischke, <i>Chair</i>	E. G. Reichelt
P. L. Sturgill, <i>Vice Chair</i>	M. J. Rice
R. Rahaman, <i>Staff Secretary</i>	W. J. Sperko
D. Barborak	J. P. Swezy, Jr.
M. Bernasek	A. D. Wilson
M. A. Boring	L. Costa, <i>Delegate</i>
D. A. Bowers	D. Pojatar, <i>Delegate</i>
N. Carter	D. D. Raimander, <i>Delegate</i>
J. G. Feldstein	A. Roza, <i>Delegate</i>
P. Gilston	M. Consonni, <i>Contributing Member</i>
S. E. Gingrich	R. M. Jessee, <i>Contributing Member</i>
K. L. Hayes	P. L. Van Fosson, <i>Contributing Member</i>
J. S. Lee	R. K. Brown, Jr., <i>Honorary Member</i>
W. M. Lundy	M. L. Carpenter, <i>Honorary Member</i>
D. W. Mann	B. R. Newmark, <i>Honorary Member</i>
S. A. Marks	S. D. Reynolds, Jr., <i>Honorary Member</i>
T. Melfi	
W. F. Newell, Jr.	

Special Working Group on Bolted Flanged Joints (BPV VIII)

W. Brown, <i>Chair</i>	R. W. Mikitka
M. Osterfoss, <i>Vice Chair</i>	D. Nash
D. Bankston, Jr.	M. Ruffin
C. W. Cary	M. Siddiqui
A. Chaudouet	E. Jamalyaria, <i>Contributing Member</i>
H. Chen	G. Van Zyl, <i>Contributing Member</i>
D. Francis	J. Veiga, <i>Contributing Member</i>
H. Lejeune	R. Wacker, <i>Contributing Member</i>
A. Mann	
W. McDaniel	

Subgroup on Brazing (BPV IX)

S. A. Marks, <i>Chair</i>	M. J. Pischke
E. W. Beckman	P. L. Sturgill
A. F. Garbolevsky	J. P. Swezy, Jr.
N. Mohr	

Subgroup on General Requirements (BPV IX)

N. Carter, <i>Chair</i>	K. Meszaros
P. Gilston, <i>Vice Chair</i>	H. B. Porter
S. A. Marks, <i>Secretary</i>	D. Smith
J. P. Bell	P. L. Sturgill
D. A. Bowers	J. P. Swezy, Jr.
T. Bunyarattaphantu	E. W. Woelfel
M. Cox	L. Costa, <i>Delegate</i>
M. Heinrichs	E. W. Beckman, <i>Contributing Member</i>
R. M. Jessee	A. Davis, <i>Contributing Member</i>
P. Matkovics	B. R. Newmark, <i>Honorary Member</i>
W. May	

Subgroup on Interpretations (BPV VIII)

P. Matkovics, <i>Chair</i>	D. T. Peters
J. Oh, <i>Staff Secretary</i>	J. Qu
S. R. Babka	F. L. Richter
L. Bower	S. C. Roberts
T. Bunyarattaphantu	C. D. Rodery
J. Cameron	T. G. Seipp
C. W. Cary	E. Smith
P. Chavdarov	J. C. Sowinski
M. Faulkner	K. Subramanian
T. Halligan	J. P. Swezy, Jr.
B. F. Hantz	A. Viet
J. Hoskinson	K. Xu
M. Kowalczyk	G. Auriolos, Sr., <i>Contributing Member</i>
D. L. Kurlie	R. J. Basile, <i>Contributing Member</i>
K. Kescu	D. A. Swanson, <i>Contributing Member</i>
M. D. Lower	
S. A. Marks	
D. I. Morris	

Subgroup on Materials (BPV IX)

M. Bernasek, <i>Chair</i>	D. D. Raimander
T. Anderson	A. Roza
L. Constantinescu	C. E. Sainz
E. Cutlip	P. L. Sturgill
S. E. Gingrich	C. Zafir
L. S. Harbison	L. Costa, <i>Delegate</i>
M. James	V. G. V. Giunto, <i>Delegate</i>
R. M. Jessee	D. J. Kotecki, <i>Contributing Member</i>
T. Melfi	B. Krueger, <i>Contributing Member</i>
S. D. Nelson	W. J. Sperko, <i>Contributing Member</i>
M. J. Pischke	M. J. Stanko, <i>Contributing Member</i>

Subgroup on Plastic Fusing (BPV IX)

K. L. Hayes, <i>Chair</i>	M. J. Rice
M. Brandes	S. Schuessler
R. M. Jessee	M. Troughton
J. Johnston, Jr.	C. Violand
J. E. O'Sullivan	E. W. Woelfel
E. G. Reichelt	J. Wright

Subgroup on Welding Qualifications (BPV IX)

T. Melfi, <i>Chair</i>	M. J. Rice
A. D. Wilson, <i>Vice Chair</i>	M. B. Sims
K. L. Hayes, <i>Secretary</i>	A. Spangenberg
M. Bernasek	W. J. Sperko
M. A. Boring	P. L. Sturgill
D. A. Bowers	J. P. Swezy, Jr.
R. Campbell	C. Violand
R. B. Corbit	L. Costa, <i>Delegate</i>
L. S. Harbison	D. D. Raimander, <i>Delegate</i>
M. Heinrichs	D. Chandiramani, <i>Contributing Member</i>
J. S. Lee	M. Consonni, <i>Contributing Member</i>
W. M. Lundy	M. Dehghan, <i>Contributing Member</i>
D. W. Mann	T. C. Wiesner, <i>Contributing Member</i>
K. Meszaros	
W. F. Newell, Jr.	
E. G. Reichelt	

Argentina International Working Group (BPV IX)

A. Burgueno, <i>Chair</i>	J. Caprarulo
A. R. G. Frinchaboy, <i>Vice Chair</i>	M. Favareto
R. Rahaman, <i>Staff Secretary</i>	J. A. Gandola
M. D. Kuhn, <i>Secretary</i>	M. A. Mendez
P. J. Cabot	A. E. Pastor

Germany International Working Group (BPV IX)

P. Chavadarov, <i>Chair</i>	P. Müller
R. Rahaman, <i>Staff Secretary</i>	S. Wegener
P. Khwaja, <i>Secretary</i>	J. Daldrup, <i>Contributing Member</i>
B. Daume	E. Floer, <i>Contributing Member</i>
D. Haase	A. Scherpenisse, <i>Contributing Member</i>
S. Krebs	K.-G. Toelle, <i>Contributing Member</i>
T. Ludwig	

Italy International Working Group (BPV IX)

D. D. Raimander, <i>Chair</i>	P. Pacor
F. Ferrarese, <i>Vice Chair</i>	G. Signoretta
R. Rahaman, <i>Staff Secretary</i>	V. Calo, <i>Contributing Member</i>
P. Campli, <i>Secretary</i>	G. Gobbi, <i>Contributing Member</i>
M. Bernasek	A. Gusmaroli, <i>Contributing Member</i>
A. Camanni	G. Pontiggia, <i>Contributing Member</i>
M. Mandina	P. Siboni, <i>Contributing Member</i>
A. S. Monastra	
L. Moracchioli	

Spain International Working Group (BPV IX)

F. J. Q. Pandelo, <i>Chair</i>	B. B. Miguel
F. Manas, <i>Vice Chair</i>	A. D. G. Munoz
R. Rahaman, <i>Staff Secretary</i>	A. B. Pascual
F. R. Hermda, <i>Secretary</i>	G. Gobbi, <i>Contributing Member</i>
C. A. Celimendiz	R. G. Garcia, <i>Contributing Member</i>
M. A. F. Garcia	

COMMITTEE ON FIBER-REINFORCED PLASTIC PRESSURE VESSELS (BPV X)

J. L. Bustillos, <i>Chair</i>	D. H. McCauley
D. Eisberg, <i>Vice Chair</i>	N. L. Newhouse
C. R. Ramcharran, <i>Staff Secretary</i>	G. Ramirez
A. L. Beckwith	J. R. Richter
B. R. Colley	B. F. Shelley
T. W. Cowley	G. A. Van Beek
I. L. Dinovo	S. L. Wagner
J. Eihusen	D. O. Yancey, Jr.
K. L. Gilmore	P. H. Ziehl
M. R. Gorman	D. H. Hodgkinson, <i>Contributing Member</i>
B. Hebb	D. L. Keeler, <i>Contributing Member</i>
L. E. Hunt	
B. Linnemann	

COMMITTEE ON NUCLEAR INSERVICE INSPECTION (BPV XI)

D. W. Lamond, <i>Chair</i>	G. C. Park
S. D. Kulat, <i>Vice Chair</i>	D. A. Scarth
A. T. Roberts III, <i>Vice Chair</i>	F. J. Schaaf, Jr.
D. Miro-Quesada, <i>Staff Secretary</i>	R. W. Swayne
M. L. Benson	S. Takaya
C. T. Brown	A. Udyawar
S. B. Brown	D. Vetter
T. L. Chan	J. G. Weicks
R. C. Cipolla	M. Weis
R. Clow	B. K. Welch
D. R. Cordes	Y.-K. Chung, <i>Delegate</i>
H. Do	C. Ye, <i>Delegate</i>
E. V. Farrell, Jr.	M. Homiack, <i>Alternate</i>
M. J. Ferlisi	C. Latiolais, <i>Alternate</i>
J. Hakii	R. O. McGill, <i>Alternate</i>
M. L. Hall	T. J. Griesbach, <i>Contributing Member</i>
P. J. Hennessey	J. T. Lindberg, <i>Contributing Member</i>
D. O. Henry	T. V. Vo, <i>Contributing Member</i>
R. Hinkle	C. D. Cowfer, <i>Honorary Member</i>
K. Hojo	E. B. Gerlach, <i>Honorary Member</i>
A. E. Keyser	R. E. Gimple, <i>Honorary Member</i>
H. Malikowski	F. E. Gregor, <i>Honorary Member</i>
S. L. McCracken	R. D. Kerr, <i>Honorary Member</i>
L. A. Melder	P. C. Riccardella, <i>Honorary Member</i>
S. A. Norman	R. A. West, <i>Honorary Member</i>
T. Nuoffer	C. J. Wirtz, <i>Honorary Member</i>
J. Nygaard	R. A. Yonekawa, <i>Honorary Member</i>
J. E. O'Sullivan	
N. A. Palm	

Executive Committee (BPV XI)

S. D. Kulat, <i>Chair</i>	N. A. Palm
D. W. Lamond, <i>Vice Chair</i>	G. C. Park
D. Miro-Quesada, <i>Staff Secretary</i>	A. T. Roberts III
M. L. Benson	R. W. Swayne
M. J. Ferlisi	D. Vetter
D. O. Henry	M. Homiack, <i>Alternate</i>
S. L. McCracken	

Latin American International Working Group (BPV XI)

O. Martinez, <i>Staff Secretary</i>	F. J. Schaaf, Jr.
A. Claus	F. M. Schroeter
I. M. Guerreiro	P. Yamamoto
L. R. Miño	

China International Working Group (BPV XI)

T. Yuchun, <i>Chair</i>	W. N. Pei
J. F. Cai, <i>Vice Chair</i>	L. Shiwei
C. Ye, <i>Vice Chair</i>	S. Shuo
M. W. Zhou, <i>Secretary</i>	Y. Sixin
M. Chao	Y. X. Sun
H. D. Chen	Z. Wan
Y. Cheng	Q. Wang
C. Gao	Q. W. Wang
Y. Guanghua	Z. S. Wang
Y. B. Guo	L. Xing
Y. Hongqi	F. Xu
D. R. Horn	S. X. Xu
Y. Hou	Q. Yin
Y. S. Li	Y. Zhe
Shangyuan Liu	Z. M. Zhong
Y. Nie	

Working Group on Spent Nuclear Fuel Storage and Transportation Containment Systems (BPV XI)

K. Hunter, <i>Chair</i>	K. Mauskar
M. Orihuela, <i>Secretary</i>	R. M. Meyer
D. J. Ammerman	R. M. Pace
J. Broussard	M. A. Richter
C. R. Bryan	B. Sarno
T. Carraher	R. Sindelar
D. Dunn	M. Staley
N. Fales	J. Tatman
R. C. Folley	J. Wellwood
A. Gonzalez	K. A. Whitney
G. Grant	X. J. Zhai
B. Gutherman	P.-S. Lam, <i>Alternate</i>
M. W. Joseph	G. White, <i>Alternate</i>
M. Keene	H. Smith, <i>Contributing Member</i>
M. Liu	

European International Working Group (BPV XI)

R. Döring, <i>Chair</i>	H.-W. Lange
M. Hagenbruch, <i>Vice Chair</i>	N. Legl
R. Piel, <i>Secretary</i>	T. Ludwig
P. Ancion	M. Reichert
A. Casse	L. Sybertz
C. G. Frantescu	I. Tewes
T. Hantzka	R. Tiete
E. Iacopetta	Yixing Wang
A. Juengert	J. Wendt
S. D. Kulat	

Task Group on Mitigation and Repair of Spent Nuclear Fuel Canisters (WG-SNFS & TCS) (BPV XI)

J. Tatman, <i>Chair</i>	M. Kris
D. J. Ammerman	M. Liu
J. Broussard	K. Mauskar
C. R. Bryan	S. L. McCracken
G. R. Cannell	M. Orihuela
K. Dietrich	M. Richter
D. Dunn	K. E. Ross
N. Fales	B. Sarno
R. C. Folley	R. Sindelar
D. Jacobs	J. Wellwood
N. Klymyshyn	A. Williams

India International Working Group (BPV XI)

S. B. Parkash, <i>Chair</i>	K. K. Rai
D. Narain, <i>Vice Chair</i>	D. Rawal
Z. M. Mansuri	R. Sahai
M. R. Nadgouda	R. K. Sharma
N. Palm	

Subgroup on Evaluation Standards (BPV XI)

N. A. Palm, <i>Chair</i>	R. O. McGill
S. X. Xu, <i>Secretary</i>	R. M. Pace
M. L. Benson	S. Ranganath
R. C. Cipolla	C. J. Sallaberry
C. M. Faigy	D. A. Scarth
M. M. Farooq	D. J. Shim
T. J. Griesbach	A. Udyawar
K. Hojo	T. V. Vo
M. Kirk	G. M. Wilkowski
D. R. Lee	K. Hasegawa, <i>Contributing Member</i>
Y. S. Li	H. S. Mehta, <i>Contributing Member</i>

Special Working Group on Editing and Review (BPV XI)

R. W. Swayne, <i>Chair</i>	M. Orihuela
R. C. Cipolla	D. A. Scarth
D. O. Henry	A. Udyawar

Task Group on Inspectability (BPV XI)

E. Henry, <i>Chair</i>	J. Honcharik
B. Langston, <i>Secretary</i>	C. Latiolais
D. Brown	J. T. Lindberg
A. Bushmire	L. Loomis
A. Cardillo	S. Matsumoto
K. Caver	D. E. Matthews
D. R. Cordes	P. J. O'Regan
D. O. Henry	J. B. Ossmann

Task Group on Evaluation of Beyond Design Basis Events (SG-ES) (BPV XI)

R. M. Pace, <i>Chair</i>	S. A. Kleinsmith
S. X. Xu, <i>Secretary</i>	M. Moenssens
G. A. Antaki	T. V. Vo
P. R. Donavin	K. Voelsing
R. G. Gilada	G. M. Wilkowski
T. J. Griesbach	F. G. Abatt, <i>Contributing Member</i>
M. Hayashi	H. S. Mehta, <i>Contributing Member</i>
K. Hojo	

**Working Group on Flaw Evaluation
(SG-ES) (BPV XI)**

R. C. Cipolla, <i>Chair</i>	C. Liu
S. X. Xu, <i>Secretary</i>	M. Liu
M. L. Benson	G. A. Miessi
H. D. Chung	S. Noronha
N. G. Cofie	R. K. Qashu
M. A. Erickson	D. A. Scarth
C. M. Faidy	W. L. Server
M. M. Farooq	D. J. Shim
B. R. Ganta	S. Smith
R. G. Gilada	M. Uddin
C. Guzman-Leong	A. Udyawar
K. Hojo	T. V. Vo
F. Iwamatsu	M. Walter
S. Kalyanam	K. Wang
Y. Kim	B. Wasiluk
V. Lacroix	G. M. Wilkowski
D. R. Lee	H. S. Mehta, <i>Contributing Member</i>
Y. S. Li	

**Working Group on Flaw Evaluation Reference Curves
(SG-ES) (BPV XI)**

A. Udyawar, <i>Chair</i>	A. Morley
D. A. Scarth, <i>Secretary</i>	B. Pellereau
M. L. Benson	S. Ranganath
F. W. Brust	D. J. Shim
R. C. Cipolla	S. Smith
M. M. Farooq	M. Uddin
A. E. Freed	T. V. Vo
K. Hasegawa	G. White
K. Hojo	S. X. Xu
F. Iwamatsu	H. S. Mehta, <i>Contributing Member</i>
V. Lacroix	

**Working Group on High Temperature Flaw Evaluation
(SG-ES) (BPV XI)**

C. J. Sallaberry, <i>Chair</i>	M. Petkov
F. W. Brust	H. Qian
P. Carter	D. A. Scarth
K. Gresh	D. J. Shim
S. Kalyanam	A. Udyawar
B. Lin	X. Wei
B.-L. Lyow	S. X. Xu
M. C. Messner	J. Bass, <i>Alternate</i>

Working Group on Operating Plant Criteria (SG-ES) (BPV XI)

M. Kirk, <i>Chair</i>	R. M. Pace
D. Rudland, <i>Secretary</i>	N. A. Palm
D. B. Denis	S. Ranganath
M. A. Erickson	W. L. Server
A. E. Freed	C. A. Tomes
T. J. Griesbach	A. Udyawar
B. Hall	T. V. Vo
M. Hayashi	H. Q. Xu
R. Janowiak	M. Yamamoto
S. A. Kleinsmith	E. Haywood, <i>Alternate</i>
H. Kobayashi	H. S. Mehta, <i>Contributing Member</i>
A. D. Odell	

Task Group on Appendix L (WG-OPC) (SG-ES) (BPV XI)

N. Glunt, <i>Chair</i>	A. D. Odell
R. M. Pace, <i>Secretary</i>	C.-S. Oh
C. Coleman	H. Park
J. I. Duo	S. Ranganath
A. E. Freed	A. Scott
M. A. Gray	D. J. Shim
T. J. Griesbach	S. Smith
H. Nam	A. Udyawar
A. Nana	T. V. Vo

Working Group on Pipe Flaw Evaluation (SG-ES) (BPV XI)

D. A. Scarth, <i>Chair</i>	Y. S. Li
S. Kalyanam, <i>Secretary</i>	R. O. McGill
K. Azuma	G. A. Miessi
F. W. Brust	S. M. Parker
H. D. Chung	S. H. Pellet
R. C. Cipolla	D. Rudland
N. G. Cofie	C. J. Sallaberry
C. M. Faidy	W. L. Server
M. M. Farooq	D. J. Shim
B. R. Ganta	S. Smith
R. G. Gilada	M. F. Uddin
S. R. Gosselin	A. Udyawar
C. E. Guzman-Leong	T. V. Vo
K. Hasegawa	K. Wang
K. Hojo	B. Wasiluk
D. N. Hopkins	G. M. Wilkowski
E. J. Houston	S. X. Xu
F. Iwamatsu	Y. Zou
R. Janowiak	K. Gresh, <i>Alternate</i>
Y. Kim	H. S. Mehta, <i>Contributing Member</i>
V. Lacroix	

Task Group on Code Case N-513 (WG-PFE) (SG-ES) (BPV XI)

R. O. McGill, <i>Chair</i>	R. Janowiak
S. M. Parker, <i>Secretary</i>	M. Kassab
G. A. Antaki	S. H. Pellet
R. C. Cipolla	D. Rudland
M. M. Farooq	D. A. Scarth
K. Gresh	S. X. Xu
E. J. Houston	

**Task Group on Evaluation Procedures for Degraded Buried Pipe
(WG-PFE) (SG-ES) (BPV XI)**

R. O. McGill, <i>Chair</i>	M. Kassab
S. X. Xu, <i>Secretary</i>	M. Moenssens
F. G. Abatt	R. M. Pace
G. A. Antaki	S. H. Pellet
R. C. Cipolla	D. Rudland
R. G. Gilada	D. A. Scarth
R. Janowiak	

**Task Group on Flaw Evaluation for HDPE Pipe
(WG-PFE) (SG-ES) (BPV XI)**

S. Kalyanam, <i>Chair</i>	D. J. Shim
P. Krishnaswamy	M. Troughton
C. Liu	R. Wolfe
M. Moenssens	J. Wright
D. P. Munson	S. X. Xu
D. A. Scarth	

Subgroup on Nondestructive Examination (BPV XI)

D. O. Henry, <i>Chair</i>	J. Harrison
T. Cinson, <i>Secretary</i>	D. A. Kull
C. T. Brown	C. Latiolais
A. Bushmire	J. T. Lindberg
T. L. Chan	F. J. Schaaf, Jr.
D. R. Cordes	D. R. Slivon
S. E. Cumblidge	R. V. Swain
K. J. Hacker	C. A. Nove, <i>Alternate</i>

Task Group on Nonmetallic Component Degradation and Failure Monitoring (SG-RIM) (BPV XI)

M. P. Metcalfe, <i>Chair</i>	N. Craft
A. Tzelepi, <i>Secretary</i>	W. J. Geringer
M. T. Audrain	K. Harris
S. Baylis	P.-A. Juan
G. Beirnaert	J. Lang
A. A. Campbell	C. Marks
C. Chen	J. Potgieter

Working Group on Personnel Qualification and Surface Visual and Eddy Current Examination (SG-NDE) (BPV XI)

C. T. Brown, <i>Chair</i>	D. O. Henry
M. Orihuela, <i>Secretary</i>	B. Langston
D. Brown	C. Shinsky
T. Cinson	R. Tedder
S. E. Cumblidge	T. Thulien
N. Farenbaugh	J. T. Timm
J. Harrison	

ASME/JSME Joint Working Group on RIM Processes and System-Based Code (SG-RIM) (BPV XI)

S. Takaya, <i>Chair</i>	R. Meyer
C. Wax, <i>Vice Chair</i>	T. Muraki
M. T. Audrain	S. Okajima
K. Dozaki	A. T. Roberts III
J. T. Fong	C. J. Sallaberry
J. Hakii	F. J. Schaaf, Jr.
K. Harris	R. Vayda
M. Hayashi	D. Watanabe
S. Kalyanam	H. Yada
D. R. Lee	K. Yamada
H. Machida	T. Asayama, <i>Contributing Member</i>
M. Mallet	T. Lupold, <i>Contributing Member</i>
R. J. McReynolds	

Working Group on Procedure Qualification and Volumetric Examination (SG-NDE) (BPV XI)

J. Harrison, <i>Chair</i>	C. Latiolais
D. A. Kull, <i>Secretary</i>	C. A. Nove
A. Bushmire	D. R. Slivon
D. R. Cordes	R. V. Swain
K. J. Hacker	D. Van Allen
R. E. Jacob	J. Williams
W. A. Jensen	B. Lin, <i>Alternate</i>

Subgroup on Repair/Replacement Activities (BPV XI)

S. L. McCracken, <i>Chair</i>	L. A. Melder
E. V. Farrell, Jr., <i>Secretary</i>	G. T. Olson
M. Brandes	J. E. O'Sullivan
S. B. Brown	G. C. Park
R. Clow	A. Patel
S. J. Findlan	R. A. Patel
M. L. Hall	R. R. Stevenson
R. Hinkle	R. W. Swayne
J. Honcharik	J. G. Weicks
A. B. Meichler	

Subgroup on Reliability and Integrity Management Program (BPV XI)

A. T. Roberts III, <i>Chair</i>	M. P. Metcalfe
D. Vetter, <i>Secretary</i>	R. Meyer
T. Anselmi	M. Orihuela
M. T. Audrain	C. J. Sallaberry
N. Broom	F. J. Schaaf, Jr.
F. W. Brust	H. M. Stephens, Jr.
S. R. Doctor	R. W. Swayne
J. D. Fletcher	S. Takaya
J. T. Fong	C. Wax
K. Harris	B. K. Welch
P. J. Hennessey	R. W. Youngblood
S. Kalyanam	B. Lin, <i>Alternate</i>
D. R. Lee	V. Chugh, <i>Contributing Member</i>
C. Mallet	R. Grantom, <i>Contributing Member</i>
R. J. McReynolds	T. Lupold, <i>Contributing Member</i>

Working Group on Design and Programs (SG-RRR) (BPV XI)

S. B. Brown, <i>Chair</i>	A. B. Meichler
R. A. Patel, <i>Secretary</i>	G. C. Park
O. Bhatti	M. A. Pyne
R. Clow	A. Rezaei
R. R. Croft	R. R. Stevenson
E. V. Farrell, Jr.	K. Sullivan
K. Harris	R. W. Swayne
H. Malikowski	

Task Group on Repair and Replacement Optimization (WG-D&P) (SG-RRR) (BPV XI)

S. L. McCracken, <i>Chair</i>	M. L. Hall
S. J. Findlan, <i>Secretary</i>	D. Jacobs
T. Basso	H. Malikowski
R. Clow	G. C. Park
K. Dietrich	A. Patel
E. V. Farrell, Jr.	R. R. Stevenson
M. J. Ferlisi	J. G. Weicks
R. C. Folley	

Working Group on MANDE (SG-RIM) (BPV XI)

H. M. Stephens, Jr., <i>Chair</i>	J. T. Fong
M. Orihuela, <i>Vice Chair</i>	D. O. Henry
M. Turnbow, <i>Secretary</i>	R. J. McReynolds
T. Anselmi	R. Meyer
M. T. Audrain	K. Yamada
S. R. Doctor	T. Lupold, <i>Contributing Member</i>
N. A. Finney	

**Working Group on Nonmetals Repair/Replacement Activities
(SG-RRR) (BPV XI)**

J. E. O'Sullivan, <i>Chair</i>	A. Rezaei
S. Schuessler, <i>Secretary</i>	S. Rios
M. Brandes	F. J. Schaaf, Jr.
S. W. Choi	R. Stakenborghs
M. Golliet	P. Vibien
J. Johnston, Jr.	M. P. Marohl, <i>Contributing Member</i>
T. M. Musto	A. Pridmore, <i>Contributing Member</i>

Subgroup on Water-Cooled Systems (BPV XI)

M. J. Ferlisi, <i>Chair</i>	D. W. Lamond
J. Nygaard, <i>Secretary</i>	T. Nomura
S. T. Chesworth	S. A. Norman
J. Collins	M. A. Pyne
H. Q. Do	H. M. Stephens, Jr.
K. W. Hall	M. Weis
P. J. Hennessey	B. K. Welch
A. Keller	I. A. Anchondo-Lopez, <i>Alternate</i>
A. E. Keyser	Y.-K. Chung, <i>Contributing Member</i>
S. D. Kulat	

**Task Group on Repair by Carbon Fiber Composites
(WG-NMRR) (SG-RRR) (BPV XI)**

S. W. Choi, <i>Chair</i>	R. P. Ojdovic
W. Bushika	J. E. O'Sullivan
D. Cimock	N. Otten
M. J. Constable	A. Pridmore
M. Elen	S. Rios
M. Golliet	J. Sealey
P. Krishnaswamy	R. Stakenborghs
M. Kuntz	D. J. Swaim
H. Lu	M. Tatkowski
L. Nadeau	M. F. Uddin
C. A. Nove	J. Wen

Task Group on High Strength Nickel Alloys Issues (SG-WCS) (BPV XI)

H. Malikowski, <i>Chair</i>	H. Kobayashi
C. Waskey, <i>Secretary</i>	S. E. Marlette
T. Cinson	J. Robinson
J. Collins	D. Van Allen
O. Cruz	G. White
K. Dietrich	K. A. Whitney

Working Group on Containment (SG-WCS) (BPV XI)

M. J. Ferlisi, <i>Chair</i>	M. Sircar
S. Walden, <i>Secretary</i>	P. C. Smith
H. T. Hill	R. S. Spencer
S. Johnson	A. Staller
A. E. Keyser	J. Swan
P. Lehniger	C. Tillotson
J. A. Munshi	G. Z. Wang
S. Richter	M. Weis

**Working Group on Welding and Special Repair Processes
(SG-RRR) (BPV XI)**

J. G. Weicks, <i>Chair</i>	D. Jacobs
G. T. Olson, <i>Secretary</i>	M. Kris
D. Barborak	S. E. Marlette
K. Dietrich	S. L. McCracken
S. J. Findlan	L. A. Melder
R. C. Folley	J. E. O'Sullivan
M. L. Hall	A. Patel
J. Honcharik	

**Working Group on Inspection of Systems and Components
(SG-WCS) (BPV XI)**

H. Q. Do, <i>Chair</i>	A. Keller
M. Weis, <i>Secretary</i>	E. E. Keyser
R. W. Blyde	S. D. Kulat
J. Collins	E. Lantz
M. J. Ferlisi	J. C. Nygaard
M. L. Garcia Heras	S. Orita
K. W. Hall	R. S. Spencer
E. Henry	M. Walter
J. Howard	A. W. Wilkens

**Task Group on Temper Bead Welding
(WG-W&SRP) (SG-RRR) (BPV XI)**

S. J. Findlan, <i>Chair</i>	H. Kobayashi
J. Tatman, <i>Secretary</i>	S. L. McCracken
D. Barborak	N. Mohr
D. Barton	G. T. Olson
R. C. Folley	J. E. O'Sullivan
J. Graham	A. Patel
M. L. Hall	J. G. Weicks
D. Jacobs	

Working Group on Pressure Testing (SG-WCS) (BPV XI)

S. A. Norman, <i>Chair</i>	S. Levitus
M. Moenssens, <i>Secretary</i>	R. A. Nettles
T. Anselmi	J. Swan
A. Knighton	K. Whitney
D. W. Lamond	

Task Group on Weld Overlay (WG-W&SRP) (SG-RRR) (BPV XI)

S. L. McCracken, <i>Chair</i>	S. E. Marlette
S. Hunter, <i>Secretary</i>	S. K. Min
D. Barborak	G. T. Olson
D. Barton	A. Patel
S. J. Findlan	D. W. Sandusky
J. Graham	J. Tatman
M. L. Hall	J. G. Weicks
D. Jacobs	

Working Group on Risk-Informed Activities (SG-WCS) (BPV XI)

M. A. Pyne, <i>Chair</i>	J. T. Jewell
S. T. Chesworth, <i>Secretary</i>	S. D. Kulat
G. Brouette	D. W. Lamond
R. Fougerousse	E. Lantz
J. Hakii	P. J. O'Regan
K. W. Hall	N. A. Palm
M. J. Homiack	S. E. Woolf

Working Group on General Requirements (BPV XI)

D. Vetter, <i>Chair</i>	A. Mills
S. E. Woolf, <i>Secretary</i>	G. Ramaraj
T. L. Chan	T. N. Rezk
P. J. Hennessey	A. T. Roberts III
R. Hinkle	B. K. Welch
K. A. Kavanagh	B. Harris, <i>Alternate</i>

Subgroup on Nonmandatory Appendices (BPV XII)

T. A. Rogers, <i>Chair</i>	T. J. Rishel
S. Staniszewski, <i>Secretary</i>	R. C. Sallash
P. Chilukuri	D. G. Shelton
N. J. Paulick	Y. Doron, <i>Contributing Member</i>
M. Pitts	

COMMITTEE ON TRANSPORT TANKS (BPV XII)

N. J. Paulick, <i>Chair</i>	J. Roberts
M. D. Rana, <i>Vice Chair</i>	T. A. Rogers
J. Oh, <i>Staff Secretary</i>	R. C. Sallash
A. N. Antoniou	M. Shah
K. W. A. Cheng	S. Staniszewski
P. Chilukuri	A. P. Varghese
O. Mulet	R. Meyers, <i>Contributing Member</i>
M. Pitts	

COMMITTEE ON OVERPRESSURE PROTECTION (BPV XIII)

B. K. Nutter, <i>Chair</i>	J. F. Ball, <i>Contributing Member</i>
A. Donaldson, <i>Vice Chair</i>	R. W. Barnes, <i>Contributing Member</i>
C. E. Rodrigues, <i>Staff Secretary</i>	R. D. Danzy, <i>Contributing Member</i>
R. Antoniuk	J. Grace, <i>Contributing Member</i>
T. P. Beirne	S. F. Harrison, Jr., <i>Contributing Member</i>
Joey Burgess	A. Hassan, <i>Contributing Member</i>
D. B. DeMichael	P. K. Lam, <i>Contributing Member</i>
J. W. Dickson	M. Mengon, <i>Contributing Member</i>
B. Engman	J. Mize, <i>Contributing Member</i>
K. R. May	M. Mullavey, <i>Contributing Member</i>
D. Miller	J. Phillips, <i>Contributing Member</i>
T. Patel	S. Ruesenberg, <i>Contributing Member</i>
B. F. Pittel	
T. R. Tarbay	K. Shores, <i>Contributing Member</i>
D. E. Tompkins	D. E. Tezzo, <i>Contributing Member</i>
J. A. West	A. Wilson, <i>Contributing Member</i>
M. Edwards, <i>Alternate</i>	

Executive Committee (BPV XII)

M. D. Rana, <i>Chair</i>	M. Pitts
N. J. Paulick, <i>Vice Chair</i>	T. A. Rogers
J. Oh, <i>Staff Secretary</i>	S. Staniszewski
P. Chilukuri	

Executive Committee (BPV XIII)

A. Donaldson, <i>Chair</i>	K. R. May
B. K. Nutter, <i>Vice Chair</i>	T. Patel
C. E. Rodrigues, <i>Staff Secretary</i>	B. F. Pittel
T. Beirne	

Subgroup on Design and Materials (BPV XII)

P. Chilukuri, <i>Chair</i>	A. P. Varghese
K. W. A. Cheng	K. Xu
S. L. McWilliams	D. K. Chandiramani, <i>Contributing Member</i>
N. J. Paulick	Y. Doron, <i>Contributing Member</i>
M. D. Rana	M. Pitts, <i>Contributing Member</i>
T. J. Rishel	D. G. Shelton, <i>Contributing Member</i>
T. A. Rogers	B. E. Spencer, <i>Contributing Member</i>
R. C. Sallash	J. Zheng, <i>Contributing Member</i>
M. Shah	
S. Staniszewski	

Subgroup on Design and Materials (BPV XIII)

T. Patel, <i>Chair</i>	D. Miller
V. Kalyanasundaram, <i>Vice Chair</i>	T. R. Tarbay
A. Williams, <i>Secretary</i>	J. A. West
T. K. Acharya	D. J. Azukas, <i>Contributing Member</i>
W. E. Chapin	R. D. Danzy, <i>Contributing Member</i>
B. Joergensen	M. Mullavey, <i>Contributing Member</i>
R. Krithivasan	G. Ramirez, <i>Contributing Member</i>
J. Latshaw	S. Zalar, <i>Contributing Member</i>

Subgroup on Fabrication, Inspection, and Continued Service (BPV XII)

M. Pitts, <i>Chair</i>	J. Roberts
P. Chilukuri, <i>Secretary</i>	R. C. Sallash
K. W. A. Cheng	S. Staniszewski
Y. Doron	K. Mansker, <i>Contributing Member</i>
M. Koprivnak	G. McRae, <i>Contributing Member</i>
O. Mulet	T. A. Rogers, <i>Contributing Member</i>
T. J. Rishel	

Subgroup on General Requirements (BPV XIII)

B. F. Pittel, <i>Chair</i>	D. E. Tezzo
J. Grace, <i>Secretary</i>	D. E. Tompkins
R. Antoniuk	J. F. White
J. F. Ball	M. Edwards, <i>Alternate</i>
Joey Burgess	P. Chavdarov, <i>Contributing Member</i>
John Burgess	J. L. Freiler, <i>Contributing Member</i>
D. B. DeMichael	G. D. Goodson, <i>Contributing Member</i>
A. Donaldson	B. Joergensen, <i>Contributing Member</i>
S. T. French	P. K. Lam, <i>Contributing Member</i>
J. Horne	E. Pearson, <i>Contributing Member</i>
R. Klimas, Jr.	J. Phillips, <i>Contributing Member</i>
Z. E. Kumana	S. Ruesenberg, <i>Contributing Member</i>
D. Mainiero-Cessna	S. Zalar, <i>Contributing Member</i>
K. R. May	
J. Mize	
L. Moedinger	
M. Mullavey	
A. Peck	

Subgroup on General Requirements (BPV XII)

S. Staniszewski, <i>Chair</i>	T. J. Rishel
A. N. Antoniou	R. C. Sallash
P. Chilukuri	Y. Doron, <i>Contributing Member</i>
J. L. Freiler	S. L. McWilliams, <i>Contributing Member</i>
O. Mulet	
B. F. Pittel	
M. Pitts	

Subgroup on Nuclear (BPV XIII)

K. R. May, <i>Chair</i>	S. Jones
J. F. Ball, <i>Vice Chair</i>	D. Miller
R. Krithivasan, <i>Secretary</i>	T. Patel
M. Brown	B. J. Yonsky
J. W. Dickson	J. Yu, <i>Alternate</i>
N. Hansing	S. T. French, <i>Contributing Member</i>

Subgroup on Testing (BPV XIII)

T. P. Beirne, <i>Chair</i>	R. Lack, <i>Alternate</i>
J. W. Dickson, <i>Vice Chair</i>	M. Brown, <i>Contributing Member</i>
C. Hofmeister, <i>Secretary</i>	J. Mize, <i>Contributing Member</i>
V. Chicola III	M. Mullavey, <i>Contributing Member</i>
B. Engman	S. Ruesenberg, <i>Contributing Member</i>
R. J. Garnett	C. Sharpe, <i>Contributing Member</i>
R. Houk	K. Shores, <i>Contributing Member</i>
N. Jump	A. Strecker, <i>Contributing Member</i>
B. K. Nutter	A. Wilson, <i>Contributing Member</i>
J. R. Thomas, Jr.	
C. Bauer, <i>Alternate</i>	

COMMITTEE ON NUCLEAR CERTIFICATION (CNC)

R. R. Stevenson, <i>Chair</i>	T. N. Rezk
M. A. Lockwood, <i>Vice Chair</i>	E. A. Whittle
H. Ruan, <i>Secretary</i>	T. Aldo, <i>Alternate</i>
S. Andrews	M. Blankinship, <i>Alternate</i>
A. Appleton	G. Brouette, <i>Alternate</i>
G. Claffey	Y. Diaz-Castillo, <i>Alternate</i>
N. DeSantis	P. D. Edwards, <i>Alternate</i>
C. Dinic	R. Hinkle, <i>Alternate</i>
G. Gobbi	K. M. Hottle, <i>Alternate</i>
J. Grimm	J. Kiefer, <i>Alternate</i>
J. W. Highlands	S. J. Montano, <i>Alternate</i>
K. A. Kavanagh	R. Spuhl, <i>Alternate</i>
J. C. Krane	M. Wilson, <i>Alternate</i>
B. McGlone	S. Yang, <i>Alternate</i>
I. Olson	M. Burke, <i>Contributing Member</i>
E. L. Pleins	S. F. Harrison, Jr., <i>Contributing Member</i>
L. Ponce	
T. E. Quaka	

COMMITTEE ON BOILER AND PRESSURE VESSEL CONFORMITY ASSESSMENT (CBPVCA)

L. E. McDonald, <i>Chair</i>	P. Williams
E. Whittle, <i>Vice Chair</i>	T. P. Beirne, <i>Alternate</i>
G. Moino, <i>Staff Secretary</i>	N. Caputo, <i>Alternate</i>
P. Chavdarov	J. M. Downs, <i>Alternate</i>
J. P. Chicoine	Y.-S. Kim, <i>Alternate</i>
A. Donaldson	B. L. Krasiun, <i>Alternate</i>
T. E. Hansen	K. Roewe, <i>Alternate</i>
W. Hibdon	B. C. Turczynski, <i>Alternate</i>
M. Prefumo	R. Underwood, <i>Alternate</i>
R. Rockwood	J. Yu, <i>Alternate</i>
G. Scribner	D. Cheetham, <i>Contributing Member</i>
D. E. Tuttle	A. J. Spencer, <i>Honorary Member</i>
R. V. Wielgoszinski	

CORRESPONDENCE WITH THE COMMITTEE

General

ASME codes and standards are developed and maintained by committees with the intent to represent the consensus of concerned interests. Users of ASME codes and standards may correspond with the committees to propose revisions or cases, report errata, or request interpretations. Correspondence for this Section of the ASME Boiler and Pressure Vessel Code (BPVC) should be sent to the staff secretary noted on the Section's committee web page, accessible at <https://go.asme.org/CSCcommittees>.

NOTE: See ASME BPVC Section II, Part D for guidelines on requesting approval of new materials. See Section II, Part C for guidelines on requesting approval of new welding and brazing materials ("consumables").

Revisions and Errata

The committee processes revisions to this Code on a continuous basis to incorporate changes that appear necessary or desirable as demonstrated by the experience gained from the application of the Code. Approved revisions will be published in the next edition of the Code.

In addition, the committee may post errata and Special Notices at <http://go.asme.org/BPVCerrata>. Errata and Special Notices become effective on the date posted. Users can register on the committee web page to receive email notifications of posted errata and Special Notices.

This Code is always open for comment, and the committee welcomes proposals for revisions. Such proposals should be as specific as possible, citing the paragraph number, the proposed wording, and a detailed description of the reasons for the proposal, including any pertinent background information and supporting documentation.

Cases

(a) The most common applications for cases are

(1) to permit early implementation of a revision based on an urgent need

(2) to provide alternative requirements

(3) to allow users to gain experience with alternative or potential additional requirements prior to incorporation directly into the Code

(4) to permit use of a new material or process

(b) Users are cautioned that not all jurisdictions or owners automatically accept cases. Cases are not to be considered as approving, recommending, certifying, or endorsing any proprietary or specific design, or as limiting in any way the freedom of manufacturers, constructors, or owners to choose any method of design or any form of construction that conforms to the Code.

(c) The committee will consider proposed cases concerning the following topics only:

(1) equipment to be marked with the ASME Single Certification Mark, or

(2) equipment to be constructed as a repair/replacement activity under the requirements of Section XI

(d) A proposed case shall be written as a question and reply in the same format as existing cases. The proposal shall also include the following information:

(1) a statement of need and background information

(2) the urgency of the case (e.g., the case concerns a project that is underway or imminent)

(3) the Code Section and the paragraph, figure, or table number to which the proposed case applies

(4) the editions of the Code to which the proposed case applies

(e) A case is effective for use when the public review process has been completed and it is approved by the cognizant supervisory board. Cases that have been approved will appear in the next edition or supplement of the Code Cases books, "Boilers and Pressure Vessels" or "Nuclear Components." Each Code Cases book is updated with seven Supplements. Supplements will be sent or made available automatically to the purchasers of the Code Cases books until the next edition of the Code. Annulments of Code Cases become effective six months after the first announcement of the annulment in a Code Case Supplement or Edition of the appropriate Code Case book. The status of any case is available at <http://go.asme.org/BPVCCDatabase>. An index of the complete list of Boiler and Pressure Vessel Code Cases and Nuclear Code Cases is available at <http://go.asme.org/BPVCC>.

Interpretations

(a) Interpretations clarify existing Code requirements and are written as a question and reply. Interpretations do not introduce new requirements. If a revision to resolve conflicting or incorrect wording is required to support the interpretation, the committee will issue an intent interpretation in parallel with a revision to the Code.

(b) Upon request, the committee will render an interpretation of any requirement of the Code. An interpretation can be rendered only in response to a request submitted through the online Inquiry Submittal Form at <http://go.asme.org/InterpretationRequest>. Upon submitting the form, the inquirer will receive an automatic email confirming receipt.

(c) ASME does not act as a consultant for specific engineering problems or for the general application or understanding of the Code requirements. If, based on the information submitted, it is the opinion of the committee that the inquirer should seek assistance, the request will be returned with the recommendation that such assistance be obtained. Inquirers may track the status of their requests at <http://go.asme.org/Interpretations>.

(d) ASME procedures provide for reconsideration of any interpretation when or if additional information that might affect an interpretation is available. Further, persons aggrieved by an interpretation may appeal to the cognizant ASME committee or subcommittee. ASME does not “approve,” “certify,” “rate,” or “endorse” any item, construction, proprietary device, or activity.

(e) Interpretations are published in the ASME Interpretations Database at <http://go.asme.org/Interpretations> as they are issued.

Committee Meetings

The ASME BPVC committees regularly hold meetings that are open to the public. Persons wishing to attend any meeting should contact the secretary of the applicable committee. Information on future committee meetings can be found at <http://go.asme.org/BCW>.

SUMMARY OF CHANGES

Changes listed below are identified on the pages by a margin note, **(25)**, placed next to the affected area.

<i>Page</i>	<i>Location</i>	<i>Change</i>
xiii	List of Sections	Title of Section XI, Division 1 revised
xiv	Foreword	Third, fourth, seventh, tenth, and eleventh paragraphs editorially revised
xvii	Personnel	Updated
1	Statement of Policy on Information Provided in the Stress Tables	Last paragraph added
8–11	Table 1A	(1) Lines 9 and 15 revised (2) Line 14 deleted
12–15	Table 1A	Lines 24–27 and 30–33 revised
16–19	Table 1A	(1) Lines 11, 27, and 30 revised (2) Line 33 deleted
20–23	Table 1A	Lines 19 and 22 revised
24–27	Table 1A	(1) Lines 7 and 31 revised (2) Line 15 deleted (3) Lines 32 and 38 added
32–35	Table 1A	Lines 10, 14, and 19 revised
36–39	Table 1A	Lines 7, 14, 32, and 44 revised
40–43	Table 1A	Lines 1, 17, and 37 revised
44–47	Table 1A	Line 13 revised
52–55	Table 1A	Lines 10, 15, 24, 27, 30, 36, 37, 39, 40, 42, and 43 revised
56–59	Table 1A	Lines 5, 6, and 22–25 deleted
60–63	Table 1A	Line 34 revised
64–67	Table 1A	Lines 11, 13, 28, and 30 added
72–75	Table 1A	Lines 3–45 added
76–79	Table 1A	(1) Lines 1, 3–22, and 31–45 added (2) Line 27 revised
80–83	Table 1A	Lines 1–44 added
88–91	Table 1A	Lines 15, 16, 19, 20, 22, 23, 26, 27, 33, 40, and 41 revised
92–95	Table 1A	Lines 1, 2, 4, 5, 7, 8, 36, 37, 40, 41, 43, and 44 revised
96–99	Table 1A	Lines 1 and 2 revised
100–103	Table 1A	Lines 25 and 26 revised
104–107	Table 1A	Lines 4, 9, 10, 13, 14, 17, 18, 21, 22 and 26–29 revised
108–111	Table 1A	Lines 31, 32, 36, 37, 39, and 40 revised

<i>Page</i>	<i>Location</i>	<i>Change</i>
112–115	Table 1A	Lines 12, 13, 19–24, 27, 28, 31–34, 39, 40, and 43–45 revised
116–119	Table 1A	Lines 1, 2, 4, 7, 9–14, 17–28, 42, and 43 revised
120–123	Table 1A	Lines 19, 20, 36, 37, 42, and 45 revised
124–127	Table 1A	Lines 1–5, 19, 20, 25–27, 31–34, 36–42, and 45 revised
128–131	Table 1A	Lines 1, 6–9, 11, 17, and 18 revised
148–151	Table 1A	Lines 20, 21, 31, 32, 38, and 39 revised
152–155	Table 1A	Lines 37, 39, 40, and 44 revised
156–159	Table 1A	Lines 33 and 34 revised
160–163	Table 1A	Lines 21, 22, 40, and 41 revised
172, 173	Notes to Table 1A	General Note (a) revised and Notes H3 and H4 deleted
196–199	Table 1B	Lines 36–42 revised
200–203	Table 1B	Lines 5–25 revised
204–207	Table 1B	(1) Lines 2, 3, and 28 added (2) Lines 8–18, 23, 36, and 37 revised
208–211	Table 1B	(1) Lines 3, 6, 7, 23, 24, 29, 30, 35, and 36 added (2) Lines 4, 16–22, 25, 28, 31, 34, 37, 42, and 43 revised
212–215	Table 1B	Lines 1, 2, 5–23, and 28–31 revised
228–231	Table 1B	Lines 16–21 and 31 revised
252–255	Table 1B	Lines 21 and 27 revised
312–314	Table 2A	Lines 26 and 27 revised
316–318	Table 2A	(1) Line 22 revised (2) Lines 23 and 25 added
324–326	Table 2A	Lines 29 and 30 revised
328–330	Table 2A	Line 40 revised
336–338	Table 2A	Lines 35 and 36 revised
340–342	Table 2A	Line 32 deleted
344–346	Table 2A	Lines 13, 15, 26, and 28 added
348–350	Table 2A	Lines 28–38 added
399, 400	Notes to Table 2A	(1) General Note (a) and Note E4 revised (2) Notes G22, G23, and W8 added
406–408	Table 2B	(1) Lines 11–14 added (2) Lines 22–25, 27–29, 31–41, 43, and 44 revised
410–412	Table 2B	Lines 26, 36, and 37 revised
430–433	Table 3	(1) Line 4 deleted (2) Lines 5 and 29 revised
438–441	Table 3	Lines 16 and 17 added
446–449	Table 3	Lines 11–14, 16–18, 35, 40, 44, and 45 revised
450–453	Table 3	Lines 1–4 revised

<i>Page</i>	<i>Location</i>	<i>Change</i>
460–462	Table 4	Line 8 revised
472–475	Table 5A	Lines 38 and 39 revised
476–479	Table 5A	(1) Line 21 revised (2) Lines 22 and 24 added
484–487	Table 5A	Lines 5 and 6 revised
488–491	Table 5A	Line 5 revised
492–495	Table 5A	Lines 22, 23, and 30–32 revised
496–499	Table 5A	(1) Line 10 deleted (2) Lines 35, 37, and 45 added
500–503	Table 5A	Lines 2 and 39–45 added
504–507	Table 5A	Lines 1–4 added
520–523	Table 5A	Lines 33–38 revised
532	Notes to Table 5A	General Note (a) revised and Notes G17 through G19 added
538–541	Table 5B	(1) Lines 17–20 added (2) Lines 34–39 and 42 revised
560, 561	Table 6A	Line 32 added
562, 563	Table 6A	(1) Lines 20 and 32–35 revised (2) Line 22 added (3) Line 25 deleted
564, 565	Table 6A	(1) Line 13 revised (2) Line 29 deleted
566, 567	Table 6A	Lines 1–5 and 10 added
570, 571	Table 6B	(1) Lines 5, 17, and 18 added (2) Lines 25–45 revised
572, 573	Table 6B	Lines 1–24, 28–30, 33, 36, 39, and 44 revised
574, 575	Table 6B	Lines 1 and 25–28 revised
586, 587	Table 6D	Lines 21–40 added
588, 589	Table 6D	Lines 1–5 added
592–595	Table U	(1) Lines 1–5, 8, 14, 22, 28, 35, and 39 added (2) Line 20 deleted
600–603	Table U	(1) Line 16 deleted (2) Line 43 added
604–607	Table U	Line 37 deleted
608–611	Table U	(1) Line 7 added (2) Lines 9 and 14 revised
612–615	Table U	(1) Lines 2, 7, 13, 15–17, 22, and 28–37 added (2) Line 18 deleted (3) Line 19 revised
616–619	Table U	Lines 12 and 13 added
620–623	Table U	(1) Lines 18–30 and 35 added (2) Line 36 revised

<i>Page</i>	<i>Location</i>	<i>Change</i>
624–627	Table U	Line 1 added
632–635	Table U	Line 19 revised
640–643	Table U	Lines 44 and 45 revised
644–647	Table U	Lines 1–12 and 30–44 revised
648–651	Table U	(1) Lines 4 and 6 added (2) Lines 9, 20, and 21 deleted
652–655	Table U	Lines 31, 32, and 39 added
656–659	Table U	Lines 2, 3, 18, 20, 34, and 36 added
660–663	Table U	Lines 12–15, 17, 19, 21, 22, and 43–45 added
664–667	Table U	Lines 1–12, 17–23, and 29–45 added
668–671	Table U	Lines 1 and 2 added
676–679	Table U	Line 31 added
688–691	Table U	Lines 16 and 17 added
740–743	Table U	Line 36 revised
744–747	Table U	Lines 11–16 and 24–41 revised
748–751	Table U	(1) Lines 21–26 and 43 revised (2) Line 36 added
752–755	Table U	Lines 14–18, 23, 24, 29, 30, 35, 36, 39, 41, and 43 revised
756–759	Table U	Lines 7, 10, 11, 22, 23, 25, and 27–29 revised
776–779	Table U	Line 45 revised
780–783	Table U	Line 6 revised
788–791	Table U	Lines 24–34 added
792–795	Table U	Lines 16–21 added
808–811	Table U	Lines 17 and 25 added
814–818	Table Y-1	(1) Lines 3, 9, 17, 23, 30, and 34 added (2) Line 15 deleted
826–830	Table Y-1	Line 25 deleted
832–836	Table Y-1	(1) Line 12 added (2) Lines 14 and 18 revised
838–842	Table Y-1	(1) Line 16 deleted (2) Lines 31, 34, and 40 added (3) Line 33 revised
844–848	Table Y-1	Lines 30, 35, 41, and 43–45 added
850–854	Table Y-1	(1) Line 1 deleted (2) Line 2 revised (3) Lines 5, 44, and 45 added
862–866	Table Y-1	(1) Lines 11 and 24 added (2) Lines 41 and 43 revised
874–878	Table Y-1	Line 25 revised

<i>Page</i>	<i>Location</i>	<i>Change</i>
892–896	Table Y-1	Lines 7–20 and 38–45 revised
898–902	Table Y-1	(1) Lines 1–7 revised (2) Lines 12 and 14 added (3) Lines 17, 28, and 29 deleted
910–914	Table Y-1	Lines 10, 11, 26, 28, 42, and 44 added
916–920	Table Y-1	Lines 21–24 added
922–926	Table Y-1	Lines 7–21, 26–32, and 38–45 added
928–932	Table Y-1	Lines 1–11 added
940–944	Table Y-1	Line 41 added
958–962	Table Y-1	Lines 30 and 31 added
1042–1046	Table Y-1	Lines 29–34 and 42–45 revised
1048–1052	Table Y-1	Lines 1–14 and 35–39 revised
1054–1058	Table Y-1	(1) Line 4 added (2) Lines 11, 27–31, 36, 37, 42, and 43 revised
1060–1064	Table Y-1	(1) Lines 4, 6, 9, 11, 12, 14–17, 29, 30, 43, and 44 revised (2) Line 32 deleted
1066–1070	Table Y-1	Lines 1 and 3–5 revised
1096–1100	Table Y-1	Lines 26 and 32 revised
1114–1118	Table Y-1	Lines 9–19 added
1120–1124	Table Y-1	Lines 1–6 added
1144–1148	Table Y-1	Lines 13 and 21 added
1149	Notes to Table Y-1	General Note (a) revised
1152	Table TE-1	Note (1) revised
1159	Table TE-4	N06617 added
1170	Table TCD	N06617 added and Note (5) revised
1184	Table TM-1	Note (2) revised
1188	Table TM-3	Modulus of elasticity of C62300 for 300°F corrected by errata
1189	Table TM-4	Modulus of elasticity for 1,600°F, 1,700°F, and 1,800°F added for N06617
1280	Table HA-2	Revised
1334	5-100	Second and last paragraphs revised
1336	5-300	Revised
1336	5-400	First paragraph revised
1337	5-700	First paragraph revised
1337	5-900	Revised
1340	5-1500	(1) First paragraph and subparas. (b) and (b)(2)(-a) through (b)(2)(-e) revised (2) Subparagraph (c) added

CROSS-REFERENCING IN THE ASME BPVC

Paragraphs within the ASME BPVC may include subparagraph breakdowns, i.e., nested lists. The following is a guide to the designation and cross-referencing of subparagraph breakdowns:

(a) Hierarchy of Subparagraph Breakdowns

- (1) First-level breakdowns are designated as (a), (b), (c), etc.
- (2) Second-level breakdowns are designated as (1), (2), (3), etc.
- (3) Third-level breakdowns are designated as (-a), (-b), (-c), etc.
- (4) Fourth-level breakdowns are designated as (-1), (-2), (-3), etc.
- (5) Fifth-level breakdowns are designated as (+a), (+b), (+c), etc.
- (6) Sixth-level breakdowns are designated as (+1), (+2), etc.

(b) Cross-References to Subparagraph Breakdowns. Cross-references within an alphanumerically designated paragraph (e.g., PG-1, UIG-56.1, NCD-3223) do not include the alphanumeric designator of that paragraph. The cross-references to subparagraph breakdowns follow the hierarchy of the designators under which the breakdown appears.

The following examples show the format:

- (1) If X.1(c)(1)(-a) is referenced in X.1(c)(1), it will be referenced as (-a).
- (2) If X.1(c)(1)(-a) is referenced in X.1(c)(2), it will be referenced as (1)(-a).
- (3) If X.1(c)(1)(-a) is referenced in X.1(e)(1), it will be referenced as (c)(1)(-a).
- (4) If X.1(c)(1)(-a) is referenced in X.2(c)(2), it will be referenced as X.1(c)(1)(-a).

INTENTIONALLY LEFT BLANK

SUBPART 1

STRESS TABLES

STATEMENT OF POLICY ON INFORMATION PROVIDED IN THE STRESS TABLES

(25)

The purpose of this Statement of Policy is to clarify which information in the stress tables is mandatory and which is not. The information and restrictions provided in the Notes found throughout the various stress tables provided in Section II, Part D, [Subpart 1](#), are mandatory. It is vital to recognize that lines of information in Tables 1A, 1B, 2A, 2B, 3, 4, 5A, 5B, 6A, 6B, 6C, and 6D frequently have essential information referenced in the Notes column. These Notes are organized as follows:

(a) EXX: defining onset of values based on successful experience in service

(b) GXX: general requirements

(c) HXX: heat treatment requirements

(d) SXX: size requirements

(e) TXX: defining onset of time-dependent behavior

(f) WXX: welding requirements

The specifications and grades or types, coupled with the assigned Notes for each line, provide the complete description of material in the context of the allowable stresses or design stress intensities. Additional requirements for particular types of construction must also be obtained from the rules governing the construction.

In Tables 1A, 2A, 5A, 6A, 6C, and 6D, the information in the Nominal Composition column is nonmandatory and is for information only. However, these nominal compositions are the primary sorting used in these six tables. See the Guideline on Locating Materials in Stress Tables, and in Tables of Mechanical and Physical Properties. The information in the Alloy Designation/UNS Number column is nonmandatory for specifications for which a grade or type is provided. This is primarily true for the non-stainless steel alloys in these tables. For specifications for which no type or grade is listed, the UNS number is mandatory. Particularly for the stainless steels, for which no type or grade is listed, the UNS number is the grade.

The only difference between Tables 1A, 2A, 5A, 6A, 6C, and 6D and Tables 1B, 2B, 5B, and 6B, with regard to the mandatory/nonmandatory nature of the information, is

that in Tables 1B, 2B, 5B, and 6B, the UNS number information is used as the basis of the sorting scheme for materials and is almost always mandatory.

Where provided, the information in the columns for Product Form, Specification Number, Type/Grade, Class/Condition/Temper, and External Pressure Chart Number is mandatory. The information in the P-Number and Group Number columns is also mandatory; however, the primary source for this information is Table QW/QB-422 in Section IX. When there is a conflict between the P-number and Group number information in these stress tables and that in Section IX, the numbers in Section IX shall govern.

The information in the Minimum Tensile Strength, Minimum Yield Strength, and Size/Thickness dimension columns is also mandatory; however, the primary source for this information is the material specifications in Section II, Parts A and B. These values are a primary basis for establishing the allowable stresses and design stress intensities. When there is a conflict between the tensile and yield strength values in the stress tables and those in the material specifications in Section II, Parts A and B, the minimum tensile and yield strength values in Parts A and B shall govern. For dual-unit specifications and for product forms for which separate U.S. Customary and Metric specifications are provided, for the Size/Thickness dimensions for size breaks at which the Minimum Specified Yield or Tensile Strengths, or both, decrease with increasing size or thickness, the values in the material specifications in Parts A and B shall govern. When there is a conflict between the maximum size or thickness values in the stress tables and those in the material specifications, the values in the stress tables shall govern.

The information in the Applicability and Maximum Temperature Limits columns is mandatory. Where a material is permitted for use in more than one Construction Code, and in the SI units version of these tables, the maximum use temperature limit in these columns is critical. The temperature to which allowable stress or design stress intensity values are listed is not necessarily the

temperature to which use is permitted by a particular Construction Code. Different Construction Codes often have different use temperature limits for the same material and condition. Further, values may be listed in the stress tables at temperatures above the maximum use temperature limit. These stress values are provided to permit interpolation to be used to determine the allowable stress or design stress intensity at temperatures between the next lowest temperature for which stress values are listed and the maximum-use temperature limit listed in these columns.

The stress tables contain External Pressure Chart assignments. The assignments shown in the stress tables are mandatory. The titles shown for the individual charts are for information only and do not establish whether the chart is suitable for any material. The highest temperature shown on the chart represents the maximum temperature that an assigned material can be used for compression or external pressure loading, unless the allowable stress tables' Notes, the chart, or construction code rules say otherwise.

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary)

GUIDELINE ON LOCATING MATERIALS IN STRESS TABLES, AND IN TABLES OF MECHANICAL AND PHYSICAL PROPERTIES

1 INTRODUCTION

The goal of this Guideline is to assist the users of Section II, Part D in locating materials in stress tables (Tables 1A, 1B, 2A, 2B, 3, 4, 5A, 5B, 6A, 6B, 6C, and 6D), tables of mechanical properties (Tables U and Y-1), and tables of physical properties (Tables TE-1 through TE-5, TCD, TM-1 through TM-5, and PRD). This Guideline defines the logic used to place materials within these tables.

2 STRESS TABLES

Stress tables are all found within Section II, Part D, Subpart 1. Tables 1A, 1B, 3, 5A, 5B, 6A, 6B, 6C, and 6D cover allowable stresses, while Tables 2A, 2B, and 4 cover design stress intensities. The governing allowable stresses for those materials are provided in ASME BPVC, Section IV. Although Subpart 1 also covers ultimate tensile strength and yield strength, the organization of those mechanical property tables will be discussed separately in para. 3. A table-by-table listing of the materials-organization logic used to place materials within the designated tables follows.

2.1 TABLE 1A

Table 1A provides allowable stresses for ferrous¹ materials used in Section I; Section III, Division 1, Classes 2 and 3; Section VIII, Division 1; and Section XII construction. Within Table 1A, the first step in ordering materials is to use their nominal compositions. These nominal compositions are nothing more than accepted compositional fingerprints or widely recognized designators for each alloy or alloy class. These nominal compositions are arranged in Table 1A as follows:

- (a) carbon steels
- (b) carbon steels with small additions of Cb, Ti, and V (microalloyed steels)
- (c) C- $\frac{1}{2}$ Mo steels
- (d) chromium steels, including ferritic stainless steels, by increasing Cr content [$\frac{1}{2}$ Cr, $\frac{3}{4}$ Cr, 1Cr, $1\frac{1}{4}$ Cr, $2\frac{1}{4}$ Cr, 3Cr, 5Cr, 9Cr, 11Cr, 12Cr, 13Cr, 15Cr, 17Cr (including 17Cr-4Ni-4Cu and 17Cr-4Ni-6Mn), 18Cr, 26Cr, 27Cr, and 29Cr]
- (e) manganese steels (Mn- $\frac{1}{4}$ Mo, Mn- $\frac{1}{2}$ Mo, Mn- $\frac{1}{2}$ Ni, and Mn-V)
- (f) silicon steel ($1\frac{1}{2}$ Si- $\frac{1}{2}$ Mo)
- (g) nickel steels ($\frac{1}{2}$ Ni, $\frac{3}{4}$ Ni, 1Ni, $1\frac{1}{4}$ Ni, 2Ni, $2\frac{1}{2}$ Ni, $2\frac{3}{4}$ Ni, 3Ni, $3\frac{1}{2}$ Ni, 4Ni, 5Ni, 8Ni, and 9Ni)

(h) other high nickel steels [25Ni-15Cr-2Ti (Grade 660) and 29Ni-20Cr-3Cu-2Mo (CN7M)]

(i) high alloy steels, including the duplex stainless steels, in order of increasing chromium content [beginning with 14Cr-16Ni-6Si-Cu-Mo, then 16Cr-9Mn-2Ni-N, then 16Cr-12Ni-2Mo (316L), etc.], then by increasing nickel content within a given chromium or other alloy content [18Cr-8Ni, 18Cr-8Ni-N, 18Cr-8Ni-4Si-N, 18Cr-10Ni-Cb (first S34700, then S34709, S34800, and S34809), 18Cr-10Ni-Ti, 18Cr-11Ni, etc., ending with 29Cr-6.5Ni-2Mo-N]

Unfortunately, most specifications for materials do not give nominal compositions — and without that information, one may not know the nominal composition for a particular material in Table 1A. If the specification number and alloy grade or type designation are known, then one can go to Section IX, Table QW/QB-422 and find the corresponding nominal composition.

Now, for a given nominal composition, Table 1A is arranged by increasing strength — first tensile strength and then yield strength. For a given nominal composition, tensile strength, and yield strength, stress listings are provided in order of increasing specification number. Sometimes, for a given nominal composition, tensile strength, yield strength, and specification number/grade or type, there may be more than one line of stresses. At this point, the Notes referenced on the second page of each page set within Table 1A will define why there are two or more lines of stresses and when each applies.

2.2 TABLE 1B

Table 1B provides allowable stresses for nonferrous materials used in Section I; Section III, Division 1, Classes 2 and 3; Section VIII, Division 1; and Section XII construction. Aluminum alloys (UNS AXXXXX materials) are the first materials covered in Table 1B, followed by copper alloys (UNS CXXXXX), nickel alloys (UNS NXXXXX), and the reactive and refractory metals and alloys (UNS RXXXXX). Within this latter category there are the following:

- (a) chromium alloys (R2XXXX)
- (b) cobalt alloys (R3XXXX)
- (c) titanium alloys (R5XXXX)
- (d) zirconium alloys (R6XXXX)

Within each of these material class groupings, stress lines are first organized by increasing UNS (Unified Numbering System) number. The nonferrous specifications now show these numbers in association with grade designations. Then, for a given UNS number, stress lines are

next ordered by strength — first tensile strength and then yield strength. Finally, for a given UNS number, tensile strength, and yield strength, stress lines are ordered by increasing specification number. Again, some materials may have two or more stress lines even if their UNS number, tensile strength, yield strength, and specification number are the same. The Notes provide direction for the applicability of each line.

For those material specifications that may not show UNS numbers associated with alloy grades, one again can refer to Section IX, Table QW/QB-422 for that information.

For Table 1B, nominal compositions are shown only for the NXXXXX and RXXXXX materials, but they have no influence on the location of alloys in the table. In this Table, the nominal compositions are simply for information.

2.3 TABLE 2A

Table 2A provides design stress intensities for ferrous materials for Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5 construction; and allowable stresses for ferrous materials for Section VIII, Division 2, Class 1 construction. This Table is organized in the same manner as Table 1A. Refer back to para. 2.1 for that description.

2.4 TABLE 2B

Table 2B provides design stress intensities for nonferrous materials for Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5 construction; and allowable stresses for nonferrous materials for Section VIII, Division 2, Class 1 construction. Table 2B materials are ordered in the same manner as in Table 1B. Refer back to para. 2.2 for that description.

2.5 TABLE 3

Table 3 provides allowable stresses for bolting materials for use in Section III, Division 1, Classes 2 and 3; Section VIII, Division 1; Section VIII, Division 2 (using Section VIII, Division 2, Part 4.16); and Section XII construction. The table first covers ferrous materials and then nonferrous materials. For the ferrous materials, the ordering logic parallels that used in Tables 1A and 2A — first by nominal composition, then by increasing ultimate tensile strength, then by increasing yield strength, and finally by increasing specification number. Again, refer back to para. 2.1 for a discussion on nominal composition.

Nonferrous materials are presented using the same logic as in Tables 1B and 2B; see para. 2.2 for that discussion.

2.6 TABLE 4

Table 4 provides design stress intensities for bolting materials used in Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5;

and allowable stresses for bolting materials used in Section VIII, Division 2 (using Section VIII, Division 2, Part 5 and Annex 5.F).

Table 4 is organized in the same manner as Table 3 — first covering ferrous materials and then nonferrous materials — except that Table 4 covers far fewer materials. For the ordering logic, again refer to paras. 2.1 and 2.2 for ferrous and nonferrous materials, respectively.

2.7 TABLE 5A

Table 5A provides allowable stresses for ferrous materials for Section VIII, Division 2, Class 2 construction. This Table is organized in the same manner as Table 1A. Refer back to para. 2.1 for that description.

2.8 TABLE 5B

Table 5B provides allowable stresses for nonferrous materials for Section VIII, Division 2, Class 2 construction. This Table is organized in the same manner as Table 1B. Refer back to para. 2.2 for that description.

2.9 TABLE 6A

Table 6A provides allowable stresses for ferrous materials for Section IV construction. This Table is organized in the same manner as Table 1A. Refer back to para. 2.1 for that description.

2.10 TABLE 6B

Table 6B provides allowable stresses for nonferrous materials for Section IV construction. This Table is organized in the same manner as Table 1B. Refer back to para. 2.2 for that description.

2.11 TABLE 6C

Table 6C provides allowable stresses for Section IV construction of lined water heaters. This Table is organized in the same manner as Table 1A. Refer back to para. 2.1 for that description.

2.12 TABLE 6D

Table 6D provides allowable stresses for Section IV construction of unlined water heaters. This Table is organized in the same manner as Table 1A. Refer back to para. 2.1 for that description.

3 MECHANICAL PROPERTY TABLES

Ultimate tensile strength values and yield strength values are to be used in design calculations according to the rules of the Construction Codes. However, they are not to be construed as minimum strength values at temperature. This is explained in the General Notes to these tables. Paragraphs 3.1 through 3.3 provide a table-by-table listing of the materials-organization logic.

Tensile (Table U) and yield (Table Y-1) strengths at elevated temperatures are based on trend curves determined by statistical curve fitting of submitted mechanical property data. Wrought materials and cast materials are considered different materials. A material has only one trend curve for tensile strengths and one trend curve for yield strengths. Each curve is anchored to the minimum value at room temperature in its set of units. See Nonmandatory Appendix D for more information.

3.1 TABLE U

Table U provides tensile strength values for ferrous and nonferrous materials, in that order. The ordering logic for ferrous materials is the same as used in Table 1A, except yield strength level is not shown. Using the logic described in para. 2.1, stress lines are organized by nominal composition, then by increasing tensile strength level, and then by increasing specification number.

Nonferrous materials coverage begins following the last of the high alloy steels (25Cr-22Ni-2Mo-N). Coverage of nonferrous alloys begins with the UNS AXXXXX alloys, followed by NXXXXX and RXXXXX alloys. The ordering of materials within these three groups has been previously described in para. 2.2.

3.3 TABLE Y-1

Table Y-1 provides yield strength values for ferrous and nonferrous materials, in that order. Again, the ordering of yield strength lines parallels the logic described for ferrous and nonferrous materials in paras. 2.1 and 2.2, respectively. Unlike Table U, for ferrous materials, the tensile strength level does enter into the ordering process, again following nominal composition designation. Table Y-1's nonferrous materials listings begin with the aluminum-base alloys (UNS AXXXXX). These are followed by the copper materials (CXXXXX), nickel-base materials (NXXXXX), and the reactive and refractory metals and alloys (RXXXXX).

4 PHYSICAL PROPERTY TABLES

Since physical properties (thermal conductivity, thermal diffusivity, thermal expansion, and density), Young's modulus, and Poisson's ratio values can be shown for numerous materials with a single set of property values, most of the tables found in Section II, Part D, Subpart 2 are based on nominal composition. Paragraphs 4.1 through 4.4 describe how these tables are organized.

4.1 TABLE TE

Table TE covers thermal expansion behavior, presented in terms of A (instantaneous coefficient of thermal expansion), B (mean coefficient of thermal expansion), and C (linear thermal expansion). This Table is split into five parts as follows:

(a) Table TE-1 covers numerous individual ferrous materials and ferrous material groupings. Notes at the end of Table TE-1 list the nominal compositions covered by the designated groupings. Again, knowledge of the nominal composition for a given material is essential, and it was noted previously that these can be extracted from Section IX, Table QW/QB-422, given the specification number and grade or type designation.

(b) Table TE-2 covers aluminum alloys. One set of A/B/C values covers all of the aluminum-base materials listed in General Note (a) of Table TE-2.

(c) Table TE-3 covers copper alloys, currently in five general groupings: C1XXXX alloys, bronze alloys, brass alloys, 70Cu-30Ni, and 90Cu-10Ni. According to an article in ASM International's "Advanced Materials & Processes" (December 1999), the general terms of bronze and brass cover the following alloys:

(1) wrought copper-base alloys

(-a) C20500-C28580 — brasses (Cu-Zn)

(-b) C31200-C38590 — leaded brasses (Cu-Zn-Pb)

(-c) C40400-C49080 — tin brasses (Cu-Zn-Sn-Pb)

(-d) C60600-C64400 — aluminum bronzes (Cu-Al-Ni-Fe-Si-Sn)

(-e) C64700-C66100 — silicon bronzes (Cu-Si-Sn)

(2) cast copper-base alloys

(-a) C83300-C85800 — red and leaded red brasses (Cu-Zn-Sn-Pb)

(-b) C86100-C86800 — manganese bronzes and leaded manganese bronzes (Cu-Zn-Mn-Fe-Pb)

(-c) C90200-C94500 — tin bronzes and leaded tin bronzes (Cu-Sn-Zn-Pb)

(-d) C95300-C95810 — aluminum bronzes (Cu-Al-Fe-Ni)

This guidance should help define which group of A/B/C values of thermal expansion to select for a given brass or bronze.

(d) Table TE-4 provides thermal expansion values for nickel alloys and refractory alloys. The thermal expansion value sets for the nickel alloys are arranged by increasing UNS NXXXXX numbers.

(e) Table TE-5 provides thermal expansion values for two groupings of titanium-base alloys. One group covers only Grade 9; the other group covers the other alloys. In this Table, there is no reference to the UNS number, just to the grade number.

4.2 TABLE TCD

Table TCD provides both thermal conductivity (TC) and thermal diffusivity (TD) values for numerous ferrous and nonferrous materials and material groupings. The table begins with ferrous materials, split into groups of carbon and low alloy steels, followed by groups of high chromium steels and groups of high alloy steels. For each

of these groups, there is a listing of nominal composition designations found at the end of the table, defining the extent of coverage.

The next series of materials are the nickel-base alloys, covered by TC/TD listings for nickel alloys (arranged by increasing UNS number) and refractory alloys. Then there are TC/TD listings for individual titanium and aluminum alloys (arranged by increasing UNS number). [Table TCD](#) does not currently provide values for copper or zirconium alloys.

4.3 TABLE TM

Table TM provides moduli of elasticity for five categories of materials, as follows:

(a) [Table TM-1](#) covers ferrous materials in nine general categories and with additional lines for specific materials. Groups A through G are subdivided by nominal composition; see the Notes at the end of [Table TM-1](#).

(b) [Table TM-2](#) covers aluminum alloys, listed by UNS number designation.

(c) [Table TM-3](#) covers copper alloys, listed by UNS number designation.

(d) [Table TM-4](#) covers nickel alloys, listed by UNS number designation.

(e) [Table TM-5](#) covers titanium alloys, listed by increasing grade numbers, and zirconium-base alloys, listed by increasing UNS number (or grade) designation.

4.4 TABLE PRD

[Table PRD](#) provides Poisson's ratio and density for ferrous and nonferrous materials.

5 REFERENCES

The official reference for UNS numbers is *Metals & Alloys in the Unified Numbering System*, ASTM DS-56. This document is periodically updated as various material specifications are revised, added, or deleted by their sponsoring organizations. Only UNS numbers published in this reference appear in Section II, Part A and Part B specifications, and in the various Section II, Part D stress tables, mechanical property tables, and physical property tables.

Nominal compositions are defined by various groups within the ASME Code committee structure and there are no published guidelines describing how these designations are developed. These designations have the greatest relevance in the arrangement of ferrous materials and, as indicated previously, the simplest way to obtain these designations is to look in Section IX of the ASME Boiler and Pressure Vessel Code and use Table QW/QB-422, which is arranged by increasing specification number. These start with the "SA" specification numbers, followed by the "SB" numbers.

INTENTIONALLY LEFT BLANK

Table 1A
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Carbon steel	Sheet	SA-1008	CS-A	...	...	...
2	Carbon steel	Sheet	SA-1008	CS-B	...	...	...
3	Carbon steel	Bar	SA-675	45	...	...	...
4	Carbon steel	Wld. pipe	SA-134	A283A	...	...	...
5	Carbon steel	Plate	SA-285	A	K01700	...	...
6	Carbon steel	Wld. pipe	SA-672	A45	K01700	...	...
7	Carbon steel	Sheet	SA-414	A	K01501	...	...
8	Carbon steel	Wld. tube	SA-178	A	K01200	...	...
(25) 9	Carbon steel	Wld. tube	SA-178	A	K01200	...	...
10	Carbon steel	Smls. tube	SA-179	...	K01200	...	...
11	Carbon steel	Smls. tube	SA-192	...	K01201	...	...
12	Carbon steel	Wld. tube	SA-214	...	K01807	...	...
13	Carbon steel	Smls. tube	SA-556	A2	K01807	...	...
(25) 14	...	...	...	...	...	...	...
(25) 15	Carbon steel	Wld. pipe	SA-53	E/A	K02504	...	...
16	Carbon steel	Wld. pipe	SA-53	E/A	K02504	...	...
17	Carbon steel	Wld. pipe	SA-53	E/A	K02504	...	...
18	Carbon steel	Wld. pipe	SA-53	F/A	...	...	...
19	Carbon steel	Smls. pipe	SA-53	S/A	K02504	...	...
20	Carbon steel	Smls. pipe	SA-53	S/A	K02504	...	...
21	Carbon steel	Smls. pipe	SA-106	A	K02501	...	...
22	Carbon steel	Wld. pipe	SA-135	A	...	...	...
23	Carbon steel	Forged pipe	SA-369	FPA	K02501	...	...
24	Carbon steel	Wld. pipe	SA-587	...	K11500	...	...
25	Carbon steel	Wld. pipe	SA-587	...	K11500	...	...
26	Carbon steel	Bar	SA-675	50	...	...	...
27	Carbon steel	Bar	SA-675	50	...	...	...
28	Carbon steel	Wld. pipe	SA-134	A283B	...	...	...
29	Carbon steel	Plate	SA-285	B	K02200	...	...
30	Carbon steel	Plate	SA-285	B	K02200	...	...
31	Carbon steel	Wld. pipe	SA-672	A50	K02200	...	...
32	Carbon steel	Sheet	SA-414	B	K02201	...	...
33	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...	$6 < t \leq 10$
34	Carbon steel	Plate	SA/EN 10028-2	P235GH	...	...	$\leq 2\frac{1}{4}$
35	Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...	$1\frac{5}{8} < t \leq 2\frac{1}{2}$
36	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...	$4 < t \leq 6$
37	Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...	$\frac{5}{8} < t \leq 1\frac{5}{8}$
38	Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...	$t \leq \frac{5}{8}$
39	Carbon steel	Sheet, strip	SA-1011	36	SS	Type 1	$t \leq 0.23$
40	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...	$2\frac{1}{4} < t \leq 4$
41	Carbon steel	Sheet, strip	SA-1011	40	SS	...	$t \leq 0.23$
42	Carbon steel	Sheet, strip	SA-1011	45	HSLAS	2	...
43	Carbon steel	Bar	SA-675	55	...	...	...
44	Carbon steel	Bar	SA-675	55	...	...	...
45	Carbon steel	Wld. pipe	SA-134	A283C	K02401	...	...

Table 1A
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	1	40	20	NP	NP	650	NP	CS-6	...
2	1	1	40	20	NP	NP	650	NP	CS-6	...
3	1	1	45	22.5	NP	650 (Cl. 3 only)	900	650	CS-6	G10, G22, T10
4	1	1	45	24	NP	300 (Cl. 3 only)	NP	NP	CS-1	W12
5	1	1	45	24	900	700	900	650	CS-1	G10, T2
6	1	1	45	24	NP	700	NP	NP	CS-1	S6, W10, W12
7	1	1	45	25	NP	NP	900	650	CS-1	G10, T2
8	1	1	47	26	1000	NP	NP	NP	CS-1	G4, G10, S1, T2, W13
9	1	1	47	26	1000	NP	1000	650	CS-1	G10, G24, S1, T2, W6
10	1	1	47	26	NP	NP	900	650	CS-1	G10, T2
11	1	1	47	26	1000	NP	1000	650	CS-1	G10, S1, T2
12	1	1	47	26	NP	NP	1000	650	CS-1	G24, T2, W6
13	1	1	47	26	NP	NP	1000	650	CS-1	G10, T2
14	...	...	...	...	...	...	...	...	...	...
15	1	1	48	30	900	NP	NP	NP	CS-2	G10, S1, T2
16	1	1	48	30	900	300 (Cl. 3 only)	NP	NP	CS-2	G10, S1, T2, W12, W13
17	1	1	48	30	NP	NP	900	650	CS-2	G24, T2, W6
18	1	1	48	30	750	NP	NP	NP	CS-2	G2, G10, S10, T2, W15
19	1	1	48	30	900	300 (Cl. 3 only)	NP	NP	CS-2	G10, S1, T2
20	1	1	48	30	NP	700 (SPT)	900	650	CS-2	G10, T2
21	1	1	48	30	1000	700	1000	650	CS-2	G10, S1, T1
22	1	1	48	30	NP	NP	900	650	CS-2	G24, T2, W6
23	1	1	48	30	1000	NP	NP	NP	CS-2	G10, S1, T1
24	1	1	48	30	NP	300 (Cl. 3 only)	NP	NP	CS-2	...
25	1	1	48	30	NP	NP	850	650	CS-2	G24, T2, W6
26	1	1	50	25	NP	650 (Cl. 3 only)	NP	NP	CS-1	...
27	1	1	50	25	850	700 (SPT)	900	650	CS-1	G10, G15, G22, S1, T2
28	1	1	50	27	NP	300 (Cl. 3 only)	NP	NP	CS-1	W12
29	1	1	50	27	900	NP	NP	NP	CS-1	G10, S1, T1
30	1	1	50	27	NP	700	900	650	CS-1	G10, T1
31	1	1	50	27	NP	700	NP	NP	CS-1	S6, T1, W10, W12
32	1	1	50	30	NP	NP	900	650	CS-2	G10, T1
33	1	1	51	31	NP	NP	400	NP	CS-2	G10
34	1	1	52	31	NP	NP	700	NP	CS-2	T11
35	1	1	52	31	1000	NP	1000	NP	CS-2	G10, S1, T2, W14
36	1	1	52	32.5	NP	NP	400	NP	CS-2	G10
37	1	1	52	32.5	1000	NP	1000	NP	CS-2	G10, S1, T2, W14
38	1	1	52	34	1000	NP	1000	NP	CS-2	G10, S1, T2, W14
39	...	...	53	36	NP	NP	600	600	CS-2	...
40	1	1	53.5	34	NP	NP	400	NP	CS-2	G10
41	...	...	55	40	NP	NP	600	600	CS-2	...
42	...	...	55	45	NP	NP	600	600	CS-3	...
43	1	1	55	27.5	850	700 (SPT)	900	650	CS-1	G10, G15, G22, S1, T2
44	1	1	55	27.5	NP	650 (Cl. 3 only)	NP	NP	CS-1	...
45	1	1	55	30	NP	300 (Cl. 3 only)	NP	NP	CS-2	W12

Table 1A
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	11.4	11.4	11.4	...	11.4	11.4	10.9	10.2	9.99	...	...	...	...	...
2	11.4	11.4	11.4	...	11.4	11.4	10.9	10.2	9.9	...	...	...	...	...
3	12.9	12.9	12.9	...	12.9	12.8	12.2	11.5	11.1	10.7	10.4	9.2	7.9	5.9
4	12.9	...	12.9	...	12.9	...	...	...	...	...	...	...	...	...
5	12.9	12.9	12.9	...	12.9	12.9	12.9	12.3	11.9	11.5	10.7	9.2	7.9	5.9
6	12.9	...	12.9	...	12.9	12.9	12.9	12.3	11.9	11.5	...	...	...	...
7	12.9	12.9	12.9	...	12.9	12.9	12.9	12.8	12.4	11.9	10.7	9.2	7.9	5.9
8	13.4	...	13.4	...	13.4	13.4	13.4	13.3	12.8	12.4	10.7	9.2	7.9	5.9
9	11.4	11.4	11.4	...	11.4	11.4	11.4	11.3	10.9	10.5	9.1	7.8	6.7	5.0
10	13.4	13.4	13.4	...	13.4	13.4	13.4	13.3	12.8	12.4	10.7	9.2	7.9	5.9
11	13.4	13.4	13.4	...	13.4	13.4	13.4	13.3	12.8	12.4	10.7	9.2	7.9	5.9
12	11.4	11.4	11.4	...	11.4	11.4	11.4	11.3	10.9	10.5	9.1	7.8	6.7	5.0
13	13.4	13.4	13.4	...	13.4	13.4	13.4	13.3	12.8	12.4	10.7	9.2	7.9	5.9
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	11.7	...	11.7	...	11.7	11.7	11.7	11.7	11.7	10.6	9.1	7.7	6.1	4.3
16	13.7	...	13.7	...	13.7	13.7	13.7	13.7	13.7	12.5	10.7	9.0	7.1	5.0
17	11.7	11.7	11.7	...	11.7	11.7	11.7	11.7	11.7	10.6	9.1	7.9	6.7	5.5
18	8.2	...	8.2	...	8.2	8.2	8.2	8.2	8.2	7.5	6.4	...	...	...
19	13.7	...	13.7	...	13.7	13.7	13.7	13.7	13.7	12.5	10.7	9.0	7.1	5.0
20	13.7	13.7	13.7	...	13.7	13.7	13.7	13.7	13.7	12.5	10.7	9.3	7.9	6.5
21	13.7	13.7	13.7	...	13.7	13.7	13.7	13.7	13.7	12.5	10.7	9.3	7.9	6.5
22	11.7	11.7	11.7	...	11.7	11.7	11.7	11.7	11.7	10.6	9.1	7.9	6.7	5.5
23	13.7	...	13.7	...	13.7	13.7	13.7	13.7	13.7	12.5	10.7	9.0	7.1	5.0
24	13.7	...	13.7	...	13.7	...	...	...	...	...	...	...	...	...
25	11.7	11.7	11.7	...	11.7	11.7	11.7	11.7	11.7	10.6	9.1	7.9	6.7	...
26	14.3	...	14.3	...	14.3	14.2	13.6	12.8	12.4	...	...	...	...	...
27	14.3	14.3	14.3	...	14.3	14.2	13.6	12.8	12.4	11.9	10.7	9.3	7.9	6.5
28	14.3	...	14.3	...	14.3	...	...	...	...	...	...	...	...	...
29	14.3	...	14.3	...	14.3	14.3	14.3	13.8	13.3	12.5	11.0	9.4	7.3	5.0
30	14.3	14.3	14.3	...	14.3	14.3	14.3	13.8	13.3	12.5	11.2	9.6	8.1	5.9
31	14.3	...	14.3	...	14.3	14.3	14.3	13.8	13.3	12.5	...	...	...	...
32	14.3	14.3	14.3	...	14.3	14.3	14.3	14.3	14.3	12.5	11.2	9.6	8.1	5.9
33	14.5	14.5	14.5	...	14.5	14.5	...	...	...	...	...	...	...	...
34	14.9	14.9	14.9	14.9	14.9	14.9	14.9	14.9	14.9	14.6	12.5	...	...	...
35	14.9	...	14.9	...	14.9	14.9	14.9	14.9	14.9	14.9	13.0	10.8	8.7	5.9
36	14.9	14.9	14.9	...	14.9	14.9	...	...	...	...	...	...	...	...
37	14.9	...	14.9	...	14.9	14.9	14.9	14.9	14.9	14.9	13.0	10.8	8.7	5.9
38	14.9	...	14.9	...	14.9	14.9	14.9	14.9	14.9	14.9	13.0	10.8	8.7	5.9
39	15.1	15.1	15.1	15.1	15.1	15.1	15.1	15.1	...	...	...	...	...	...
40	15.3	15.3	15.3	...	15.3	15.3	...	...	...	...	...	...	...	...
41	15.7	15.7	15.7	15.7	15.7	15.7	15.7	15.7	...	...	...	...	...	...
42	15.7	15.7	15.7	15.7	15.7	15.7	15.7	15.7	...	...	...	...	...	...
43	15.7	15.7	15.7	...	15.7	15.7	14.9	14.1	13.6	13.1	12.7	10.8	8.7	5.9
44	15.7	...	15.7	...	15.7	15.7	14.9	14.1	13.6	...	...	...	...	...
45	15.7	...	15.7	...	15.7	...	...	...	...	...	...	...	...	...

Table 1A
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
9	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
12	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
13	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	4.5	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	3.0	1.5	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.
1	Carbon steel	Plate	SA-283	C	K02401	...	...
2	Carbon steel	Plate	SA-285	C	K02801	...	...
3	Carbon steel	Smls. & wld. pipe	SA-333	1	K03008	...	...
4	Carbon steel	Smls. & wld. tube	SA-334	1	K03008	...	...
5	Carbon steel	Wld. tube	SA-334	1	K03008	...	...
6	Carbon steel	Plate	SA-516	55	K01800	...	...
7	Carbon steel	Smls. pipe	SA-524	II	K02104	...	...
8	Carbon steel	Wld. pipe	SA-671	CA55	K02801	...	...
9	Carbon steel	Wld. pipe	SA-671	CE55	K02202	...	...
10	Carbon steel	Wld. pipe	SA-672	A55	K02801	...	...
11	Carbon steel	Wld. pipe	SA-672	B55	K02001	...	...
12	Carbon steel	Wld. pipe	SA-672	C55	K01800	...	...
13	Carbon steel	Wld. pipe	SA-672	E55	K02202	...	...
14	Carbon steel	Sheet	SA-414	C	K02503	...	...
15	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...	$\leq 2\frac{1}{4}$
16	Carbon steel	Bar	SA-36	...	K02600	...	...
17	Carbon steel	Plate, sheet	SA-36	...	K02600	...	...
18	Carbon steel	Plate, sheet	SA-662	A	K01701	...	...
19	Carbon steel	Sheet, strip	SA-1011	36	SS	Type 2	$t \leq 0.23$
20	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...	$t > 1\frac{1}{2}$
21	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...	$t > 1\frac{1}{2}$
22	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...	$t > 1\frac{1}{2}$
23	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...	$t > 1\frac{1}{2}$
(25) 24	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...	$\frac{3}{4} \leq t \leq 1\frac{1}{2}$
(25) 25	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...	$\frac{3}{4} \leq t \leq 1\frac{1}{2}$
(25) 26	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...	$\frac{3}{4} \leq t \leq 1\frac{1}{2}$
(25) 27	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...	$\frac{3}{4} \leq t \leq 1\frac{1}{2}$
28	Carbon steel	Plate	SA/EN 10028-2	P265GH	...	...	$\leq 2\frac{1}{4}$
29	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...	$1\frac{5}{8} < t \leq 2\frac{1}{2}$
(25) 30	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...	$t < \frac{3}{4}$
(25) 31	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...	$t < \frac{3}{4}$
(25) 32	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...	$t < \frac{3}{4}$
(25) 33	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...	$t < \frac{3}{4}$
34	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...	$\frac{5}{8} < t \leq 1\frac{5}{8}$
35	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...	$t \leq \frac{5}{8}$
36	Carbon steel	Forgings	SA-181	...	K03502	60	...
37	Carbon steel	Castings	SA-216	WCA	J02502	...	...
38	Carbon steel	Forgings	SA-266	1	K03506	...	...
39	Carbon steel	Forgings	SA-350	LF1	K03009	1	...
40	Carbon steel	Castings	SA-352	LCA	J02504	...	...
41	Carbon steel	Cast pipe	SA-660	WCA	J02504	...	...
42	Carbon steel	Bar	SA-675	60	...	...	...
43	Carbon steel	Bar	SA-675	60	...	...	...
44	Carbon steel	Forgings	SA-765	I	K03046	...	...
45	Carbon steel	Plate	SA-515	60	K02401	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	1	55	30	NP	300 (Cl. 3 only)	650	650	CS-2	...
2	1	1	55	30	900	700	900	650	CS-2	G10, S1, T2
3	1	1	55	30	NP	700	650	650	CS-2	W12, W14
4	1	1	55	30	NP	700	650	650	CS-2	W12, W14
5	1	1	55	30	NP	NP	650	650	CS-2	G24, W6
6	1	1	55	30	850	700	1000	650	CS-2	G10, S1, T2
7	1	1	55	30	NP	NP	1000	650	CS-2	G10, T2
8	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
9	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
10	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
11	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
12	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
13	1	1	55	30	NP	700	NP	NP	CS-2	S6, W10, W12
14	1	1	55	33	NP	700	900	650	CS-2	G10, T1
15	1	1	56.5	...	NP	NP	400	400	CS-2	G10, G18
16	1	1	58	36	650	650 (SPT)	900	650	CS-2	G10, G15, T1
17	1	1	58	36	NP	700	650	650	CS-2	G9, G10, T1
18	1	1	58	40	NP	NP	700	650	CS-2	T1
19	...	...	58	36	NP	NP	600	600	CS-2	...
20	1	1	59.5	33.4	NP	NP	650	650	CS-2	...
21	1	1	59.5	33.4	NP	NP	650	650	CS-2	...
22	1	1	59.5	36.3	NP	NP	650	650	CS-2	...
23	1	1	59.5	33.4	NP	NP	650	NP	CS-2	...
24	1	1	59.5	34.8	NP	NP	650	650	CS-2	...
25	1	1	59.5	34.8	NP	NP	650	650	CS-2	...
26	1	1	59.5	34.8	NP	NP	650	650	CS-2	...
27	1	1	59.5	34.8	NP	NP	650	650	CS-2	...
28	1	1	59.5	35.5	NP	NP	700	NP	CS-2	T1
29	1	1	59.5	35.5	1000	NP	1000	NP	CS-2	G10, S1, T2
30	1	1	59.5	36.3	NP	NP	650	650	CS-2	...
31	1	1	59.5	36.3	NP	NP	650	650	CS-2	...
32	1	1	59.5	33.4	NP	NP	650	650	CS-2	...
33	1	1	59.5	36.3	NP	NP	650	650	CS-2	...
34	1	1	59.5	37	1000	NP	1000	NP	CS-2	G10, S1, T2
35	1	1	59.5	38.5	1000	NP	1000	NP	CS-2	G10, S1, T2
36	1	1	60	30	1000	700	1000	650	CS-2	G10, S1, T2
37	1	1	60	30	1000	700	1000	650	CS-2	G1, G10, G17, S1, T2
38	1	1	60	30	1000	700	1000	650	CS-2	G10, S1, T2
39	1	1	60	30	NP	700	1000	650	CS-2	G10, T2
40	1	1	60	30	NP	700	NP	NP	CS-2	G17
41	1	1	60	30	1000	700	NP	NP	CS-2	G1, G10, G17, S1, T2
42	1	1	60	30	850	700 (SPT)	NP	NP	CS-2	G10, G15, S1, T2
43	1	1	60	30	NP	650 (Cl. 3 only)	900	650	CS-2	G10, G22, T2
44	1	1	60	30	NP	NP	1000	650	CS-2	G10, T2
45	1	1	60	32	1000	700	1000	650	CS-2	G10, S1, T2

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	15.7	15.7	15.7	...	15.7	15.7	15.7	15.3	14.8	...	...	...	...	...
2	15.7	15.7	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	13.0	10.8	8.7	5.9
3	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
4	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
5	13.4	13.4	13.4	...	13.4	13.4	13.4	13.0	12.6	...	...	...	...	...
6	15.7	15.7	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	13.0	10.8	8.7	5.9
7	15.7	15.7	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	13.0	10.8	8.7	5.9
8	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
9	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
10	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
11	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
12	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
13	15.7	...	15.7	...	15.7	15.7	15.7	15.3	14.8	14.3	...	...	...	...
14	15.7	15.7	15.7	...	15.7	15.7	15.7	15.7	15.7	15.6	13.0	10.8	8.7	5.9
15	16.2	16.2	16.2	...	16.2	16.2	...	...	...	...	...	...	...	...
16	16.6	16.6	16.6	...	16.6	16.6	16.6	16.6	16.6	15.6	13.0	10.8	8.7	5.9
17	16.6	...	16.6	...	16.6	16.6	16.6	16.6	16.6	15.6	...	...	...	...
18	16.6	16.6	16.6	...	16.6	16.6	16.6	16.6	16.6	15.6	...	...	...	...
19	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	...	...	...	...	...	...
20	17.0	...	17.0	...	17.0	17.0	17.0	17.0	16.5	...	...	...	...	...
21	17.0	...	17.0	...	17.0	17.0	17.0	17.0	16.5	...	...	...	...	...
22	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
23	17.0	...	17.0	...	17.0	17.0	17.0	17.0	16.5	...	...	...	...	...
24	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
25	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
26	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
27	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
28	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	15.6	...	...	...	...
29	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	17.0	13.0	10.8	8.7	5.9
30	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
31	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
32	17.0	...	17.0	...	17.0	17.0	17.0	17.0	16.5	...	...	...	...	...
33	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	...	...	...	...	...
34	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	17.0	13.0	10.8	8.7	5.9
35	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	17.0	13.0	10.8	8.7	5.9
36	17.1	17.1	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
37	17.1	...	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
38	17.1	17.1	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
39	17.1	17.1	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
40	17.1	...	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	...	...	...	...
41	17.1	...	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
42	17.1	...	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	...
43	17.1	17.1	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
44	17.1	17.1	17.1	...	17.1	17.1	16.3	15.3	14.8	14.3	13.0	10.8	8.7	5.9
45	17.1	17.1	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	13.0	10.8	8.7	5.9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
7	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
35	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
36	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
37	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
39	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
45	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Carbon steel	Plate	SA-516	60	K02100	...	...
2	Carbon steel	Wld. pipe	SA-671	CB60	K02401	...	...
3	Carbon steel	Wld. pipe	SA-671	CC60	K02100	...	...
4	Carbon steel	Wld. pipe	SA-671	CE60	K02402	...	...
5	Carbon steel	Wld. pipe	SA-672	B60	K02401	...	...
6	Carbon steel	Wld. pipe	SA-672	C60	K02100	...	...
7	Carbon steel	Wld. pipe	SA-672	E60	K02402	...	...
8	Carbon steel	Wld. pipe	SA-134	A283D	K02702	...	...
9	Carbon steel	Plate	SA-283	D	K02702	...	...
10	Carbon steel	Wld. pipe	SA-53	E/B	K03005	...	...
(25) 11	Carbon steel	Wld. pipe	SA-53	E/B	K03005	...	...
12	Carbon steel	Smls. pipe	SA-53	S/B	K03005	...	...
13	Carbon steel	Smls. pipe	SA-53	S/B	K03005	...	...
14	Carbon steel	Smls. pipe	SA-106	B	K03006	...	...
15	Carbon steel	Wld. pipe	SA-135	B	...	...	...
16	Carbon steel	Smls. & wld. fittings	SA-234	WPB	K03006	...	...
17	Carbon steel	Smls. & wld. pipe	SA-333	6	K03006	...	...
18	Carbon steel	Wld. pipe	SA-333	6	K03006	...	...
19	Carbon steel	Smls. & wld. tube	SA-334	6	K03006	...	...
20	Carbon steel	Wld. tube	SA-334	6	K03006	...	...
21	Carbon steel	Forged pipe	SA-369	FPB	K03006	...	...
22	Carbon steel	Forgings	SA-372	A	K03002	...	...
23	Carbon steel	Sheet	SA-414	D	K02505	...	...
24	Carbon steel	Smls. & wld. fittings	SA-420	WPL6	...	...	...
25	Carbon steel	Smls. pipe	SA-524	I	K02104	...	...
26	Carbon steel	Bar	SA-696	B	K03200	...	...
(25) 27	Carbon steel	Forgings	SA-727	...	K02506	...	...
28	Carbon steel	Wld. tube	SA-178	C	K03503	...	...
29	Carbon steel	Wld. tube	SA-178	C	K03503	...	...
(25) 30	Carbon steel	Wld. tube	SA-178	C	K03503	...	...
31	Carbon steel	Smls. tube	SA-210	A-1	K02707	...	...
32	Carbon steel	Smls. tube	SA-556	B2	K02707	...	...
(25) 33	...	...	...	...	...	...	...
34	Carbon steel	Plate, bar	SA/CSA-G40.21	38W	...	...	...
35	Carbon steel	Plate, sheet, bar	SA-572	42	...	...	$t \leq 6$
36	Carbon steel	Sheet, strip	SA-1011	45	HSLAS	1	...
37	Carbon steel	Sheet, strip	SA-1011	45	SS	...	$t \leq 0.23$
38	Carbon steel	Sheet, strip	SA-1011	50	HSLAS	2	...
39	Carbon steel	Plate	SA/AS 1548	PT430N	...	Normalized	≤ 6
40	Carbon steel	Plate	SA/AS 1548	PT430NR	...	Norm. rld.	≤ 6
41	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...	$6 < t \leq 10$
42	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...	$4 < t \leq 6$
43	Carbon steel	Bar	SA-675	65	...	...	...
44	Carbon steel	Castings	SA-352	LCB	J03003	...	...
45	Carbon steel	Plate	SA-515	65	K02800	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	1	60	32	850	700	1000	650	CS-2	G10, S1, T2
2	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
3	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
4	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
5	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
6	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
7	1	1	60	32	NP	700	NP	NP	CS-2	S6, W10, W12
8	1	1	60	33	NP	300 (Cl. 3 only)	NP	NP	CS-2	W12
9	1	1	60	33	NP	300 (Cl. 3 only)	650	650	CS-2	...
10	1	1	60	35	900	300 (Cl. 3 only)	NP	NP	CS-2	G10, S1, T1, W12, W13
11	1	1	60	35	900	NP	900	650	CS-2	G10, G24, S1, T1, W6
12	1	1	60	35	900	300 (Cl. 3 only)	NP	NP	CS-2	G10, S1, T1
13	1	1	60	35	NP	700 (SPT)	900	650	CS-2	G10, T1
14	1	1	60	35	1000	700	1000	650	CS-2	G10, S1, T1
15	1	1	60	35	NP	NP	900	650	CS-2	G24, T1, W6
16	1	1	60	35	1000	700	1000	650	CS-2	G10, S1, T1
17	1	1	60	35	700	700	1000	650	CS-2	G10, T1, W12, W13, W14
18	1	1	60	35	700	NP	NP	NP	CS-2	T1
19	1	1	60	35	NP	700	650	650	CS-2	T1, W12, W14
20	1	1	60	35	NP	NP	650	650	CS-2	G24, W6
21	1	1	60	35	1000	NP	NP	NP	CS-2	G10, S1, T1
22	1	1	60	35	NP	NP	650	650	CS-2	...
23	1	1	60	35	NP	NP	900	650	CS-2	G10, T1
24	1	1	60	35	NP	700	850	650	CS-2	G10, T1, W14
25	1	1	60	35	NP	NP	1000	650	CS-2	G10, T1
26	1	1	60	35	NP	700	NP	NP	CS-2	T1
27	1	1	60	36	NP	700	1000	650	CS-2	G10, T1
28	1	1	60	37	1000	NP	NP	NP	CS-2	G4, G10, S1, T2
29	1	1	60	37	1000	700	NP	NP	CS-2	G10, S1, T1, W13
30	1	1	60	37	1000	NP	1000	650	CS-2	G10, G24, S1, T2, W6
31	1	1	60	37	1000	700	1000	650	CS-2	G10, S1, T1
32	1	1	60	37	NP	NP	1000	650	CS-2	G10, T1
33	...	...	...	...	...	...	...	...	...	...
34	1	1	60	38	NP	NP	650	650	CS-2	...
35	...	...	60	42	NP	NP	600	600	CS-3	...
36	...	...	60	45	NP	NP	600	600	CS-3	...
37	...	...	60	45	NP	NP	600	600	CS-3	...
38	...	...	60	50	NP	NP	600	600	CS-3	...
39	1	1	62.5	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
40	1	1	62.5	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
41	1	1	62.5	32	850	NP	1000	NP	CS-2	G10, S1, T2
42	1	1	64	34	850	NP	1000	NP	CS-2	G10, S1, T2
43	1	1	65	32.5	850	650 (Cl. 3 only)	1000	650	CS-2	G10, G15, G22, S1, T2
44	1	1	65	35	NP	700	650	650	CS-2	G1, G17
45	1	1	65	35	1000	700	1000	650	CS-2	G10, S1, T2

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.1	17.1	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	13.0	10.8	8.7	5.9
2	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
3	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
4	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
5	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
6	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
7	17.1	...	17.1	...	17.1	17.1	17.1	16.4	15.8	15.3	...	...	...	...
8	17.1	...	17.1	...	17.1	...	...	...	...	...	...	...	...	...
9	17.1	17.1	17.1	...	17.1	17.1	17.1	16.9	16.3	...	...	...	...	...
10	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
11	14.6	14.6	14.6	...	14.6	14.6	14.6	14.6	14.6	13.3	11.1	9.2	7.4	5.0
12	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
13	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
14	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
15	14.6	14.6	14.6	...	14.6	14.6	14.6	14.6	14.6	13.3	11.1	9.2	7.4	5.0
16	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
17	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
18	14.6	14.6	14.6	...	14.6	14.6	14.6	14.6	14.6	13.3	...	...	...	...
19	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	...	...	...	...
20	14.6	14.6	14.6	...	14.6	14.6	14.6	14.6	14.6	...	...	...	...	...
21	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
22	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...
23	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
24	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	...
25	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
26	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	...	...	...	...
27	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
28	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.0
29	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
30	14.6	...	14.6	...	14.6	14.6	14.6	14.6	14.6	13.3	11.1	9.2	7.4	5.0
31	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
32	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	15.6	13.0	10.8	8.7	5.9
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...
35	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...	...
36	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...	...
37	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...	...
38	17.1	17.1	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...	...
39	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	16.9	13.9	11.4	8.7	5.9
40	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	16.9	13.9	11.4	8.7	5.9
41	17.9	17.9	17.9	17.9	17.9	17.9	17.4	16.4	15.8	15.3	13.9	11.4	8.7	5.9
42	18.3	18.3	18.3	18.3	18.3	18.3	18.3	17.4	16.8	16.2	13.9	11.4	8.7	5.9
43	18.6	18.6	18.6	18.6	18.6	18.5	17.7	16.6	16.1	15.5	13.9	11.4	8.7	5.0
44	18.6	18.6	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	...	...	...	...
45	18.6	18.6	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	13.9	11.4	8.7	5.9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
17	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
28	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
29	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
30	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
31	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
32	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
40	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
41	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
42	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
43	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Carbon steel	Plate	SA-516	65	K02403	...	...
2	Carbon steel	Wld. pipe	SA-671	CB65	K02800	...	...
3	Carbon steel	Wld. pipe	SA-671	CC65	K02403	...	...
4	Carbon steel	Wld. pipe	SA-672	B65	K02800	...	...
5	Carbon steel	Wld. pipe	SA-672	C65	K02403	...	...
6	Carbon steel	Sheet	SA-414	E	K02704	...	...
7	Carbon steel	Plate	SA-662	B	K02203	...	...
8	Carbon steel	Plate	SA-537	...	K12437	1	$2\frac{1}{2} < t \leq 4$
9	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...	$2\frac{1}{2} < t \leq 4$
10	Carbon steel	Plate, sheet, bar	SA-572	50	...	...	$t \leq 4$
11	Carbon steel	Round bar	SA-572	50	...	...	$t \leq 11$
12	Carbon steel	Sheet, strip	SA-1011	50	SS	...	$t \leq 0.23$
13	Carbon steel	Sheet, strip	SA-1011	50	HSLAS	1	...
14	Carbon steel	Sheet, strip	SA-1011	55	HSLAS	2	...
15	Carbon steel	Plate, bar	SA/CSA-G40.21	44W	...	...	$t \leq 8$
16	Carbon steel	Plate, bar	SA/CSA-G40.21	50W	...	...	$t \leq 6$
17	Carbon steel	Plate	SA/AS 1548	PT460N	...	Normalized	≤ 6
18	Carbon steel	Plate	SA/AS 1548	PT460NR	...	Norm. rld.	≤ 6
(25) 19	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$1.4 < t \leq 6.3$
20	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...	$2\frac{1}{4} < t \leq 4$
21	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...	$\leq 2\frac{1}{4}$
(25) 22	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$t \leq 1.4$
23	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$6 < t \leq 10$
24	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$6 < t \leq 10$
25	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$4 < t \leq 6$
26	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$4 < t \leq 6$
27	Carbon steel	Plate	SA-455	...	K03300	...	$0.58 < t \leq \frac{3}{4}$
28	Carbon steel	Bar	SA-675	70	...	...	...
29	Carbon steel	Forgings	SA-105	...	K03504	...	...
30	Carbon steel	Forgings	SA-181	...	K03502	70	...
31	Carbon steel	Castings	SA-216	WCB	J03002	...	...
32	Carbon steel	Forgings	SA-266	2	K03506	...	...
33	Carbon steel	Forgings	SA-266	4	K03017	...	...
34	Carbon steel	Forgings	SA-350	LF2	K03011	1	...
35	Carbon steel	Forgings	SA-350	LF2	K03011	2	...
36	Carbon steel	Forgings	SA-508	1	K13502	...	...
37	Carbon steel	Forgings	SA-508	1A	K13502	...	...
38	Carbon steel	Forgings	SA-541	1	K03506	...	...
39	Carbon steel	Forgings	SA-541	1A	K03020	...	...
40	Carbon steel	Cast pipe	SA-660	WCB	J03003	...	...
41	Carbon steel	Forgings	SA-765	II	K03047	...	...
42	Carbon steel	Plate	SA-515	70	K03101	...	...
43	Carbon steel	Plate	SA-516	70	K02700	...	...
44	Carbon steel	Wld. pipe	SA-671	CB70	K03101	...	...
45	Carbon steel	Wld. pipe	SA-671	CC70	K02700	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	1	65	35	850	700	1000	650	CS-2	G10, S1, T2
2	1	1	65	35	NP	700	NP	NP	CS-2	S6, W10, W12
3	1	1	65	35	NP	700	NP	NP	CS-2	S6, W10, W12
4	1	1	65	35	NP	700	NP	NP	CS-2	S6, W10, W12
5	1	1	65	35	NP	700	NP	NP	CS-2	S6, W10, W12
6	1	1	65	38	NP	NP	900	650	CS-2	G10, T1
7	1	1	65	40	NP	NP	700	650	CS-2	T1
8	1	2	65	45	NP	700	650	650	CS-2	T1
9	1	2	65	45	NP	700	NP	NP	CS-2	G26, T1, W10, W12
10	...	...	65	50	NP	NP	600	600	CS-3	...
11	...	...	65	50	NP	NP	600	600	CS-3	...
12	...	...	65	50	NP	NP	600	600	CS-3	...
13	...	...	65	50	NP	NP	600	600	CS-3	...
14	...	...	65	55	NP	NP	600	600	CS-3	...
15	1	1	65	...	650	NP	650	650	CS-2	G18
16	1	1	65	...	650	NP	650	650	CS-2	G18
17	1	1	66.5	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
18	1	1	66.5	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
19	1	1	66.5	37	1000	NP	1000	NP	CS-2	G10, S1, T2
20	1	1	66.5	37.5	850	NP	1000	NP	CS-2	G10, S1, T1
21	1	1	66.5	...	850	NP	1000	650	CS-2	G10, G18, S1, T1
22	1	1	66.5	40.5	1000	NP	1000	NP	CS-2	G10, S1, T2
23	1	2	68	38.5	800	NP	800	NP	CS-2	T1
24	1	2	68	40.5	850	NP	1000	NP	CS-2	G10, S1, T1
25	1	2	69.5	41.5	800	NP	800	NP	CS-2	T1
26	1	2	69.5	43	850	NP	1000	NP	CS-2	G10, S1, T1
27	1	2	70	35	NP	400 (Cl. 3 only)	650	650	CS-2	...
28	1	2	70	35	850	650 (Cl. 3 only)	1000	650	CS-2	G10, G15, G22, S1, T2
29	1	2	70	36	1000	700	1000	650	CS-2	G10, S1, T2
30	1	2	70	36	1000	700	1000	650	CS-2	G10, S1, T2
31	1	2	70	36	1000	700	1000	650	CS-2	G1, G10, G17, S1, T2
32	1	2	70	36	1000	700	1000	650	CS-2	G10, S1, T2
33	1	2	70	36	NP	NP	1000	650	CS-2	G10, T2
34	1	2	70	36	850	700	1000	650	CS-2	G10, T2
35	1	2	70	36	850	700	1000	650	CS-2	G10, T2
36	1	2	70	36	NP	700	1000	650	CS-2	G10, T2
37	1	2	70	36	NP	700	1000	650	CS-2	G10, T2
38	1	2	70	36	NP	700	1000	650	CS-2	G10, T2
39	1	2	70	36	NP	700	1000	650	CS-2	G10, T2
40	1	2	70	36	1000	700	NP	NP	CS-2	G1, G10, G17, S1, T2
41	1	2	70	36	NP	NP	1000	650	CS-2	G10, T2
42	1	2	70	38	1000	700	1000	650	CS-2	G10, S1, T2
43	1	2	70	38	850	700	1000	650	CS-2	G10, S1, T2
44	1	2	70	38	NP	700	NP	NP	CS-2	S5, W10, W12
45	1	2	70	38	NP	700	NP	NP	CS-2	S6, W10, W12

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	18.6	18.6	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	13.9	11.4	8.7	5.9
2	18.6	...	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	...	...	...	...
3	18.6	...	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	...	...	...	...
4	18.6	...	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	...	...	...	...
5	18.6	...	18.6	...	18.6	18.6	18.6	17.9	17.3	16.7	...	...	...	...
6	18.6	18.6	18.6	...	18.6	18.6	18.6	18.6	18.6	16.9	13.9	11.4	8.7	5.9
7	18.6	18.6	18.6	...	18.6	18.6	18.6	18.6	18.6	16.9	...	...	...	...
8	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	16.9	...	...	...	...
9	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	16.9	...	...	...	...
10	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...	...
11	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...	...
12	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...	...
13	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...	...
14	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...	...
15	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...
16	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	...	...	...	...	...
17	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	16.9	13.9	11.4	8.7	5.9
18	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	16.9	13.9	11.4	8.7	5.9
19	19.1	...	19.1	...	19.1	19.1	19.1	18.8	18.1	17.5	14.8	12.0	9.3	6.7
20	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	18.5	16.7	13.9	11.4	8.7	5.9
21	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	16.7	13.9	11.4	8.7	5.9
22	19.1	...	19.1	...	19.1	19.1	19.1	19.1	19.1	19.1	14.8	12.0	9.3	6.7
23	19.5	...	19.5	...	19.5	19.5	19.5	19.5	19.0	18.3	14.8	12.0	...	...
24	19.5	19.5	19.5	19.5	19.5	19.5	19.5	19.5	19.5	18.3	14.8	12.0	9.3	6.7
25	19.9	...	19.9	...	19.9	19.9	19.9	19.9	19.9	18.3	14.8	12.0	...	...
26	19.9	19.9	19.9	19.9	19.9	19.9	19.9	19.9	19.9	18.3	14.8	12.0	9.3	6.7
27	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	...	...	...	...	...
28	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.7	14.8	12.0	9.3	6.7
29	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
30	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
31	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
32	20.0	...	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
33	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
34	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
35	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
36	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
37	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
38	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
39	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
40	20.0	...	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
41	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.2	14.8	12.0	9.3	6.7
42	20.0	20.0	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	14.8	12.0	9.3	6.7
43	20.0	20.0	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	14.8	12.0	9.3	6.7
44	20.0	...	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	...	...	...	...
45	20.0	...	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
18	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
19	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
20	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
21	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
22	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
29	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
30	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
31	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
32	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
33	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
34	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
35	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
36	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
37	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
39	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
40	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
41	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
42	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
43	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Carbon steel	Wld. pipe	SA-672	B70	K03101	...	...
2	Carbon steel	Wld. pipe	SA-672	C70	K02700	...	...
3	Carbon steel	Plate	SA/JIS G3118	SGV480	...	...	...
4	Carbon steel	Smls. pipe	SA-106	C	K03501	...	...
5	Carbon steel	Wld. tube	SA-178	D	...	...	...
(25) 6	Carbon steel	Wld. tube	SA-178	D	...	...	...
7	Carbon steel	Wld. tube	SA-178	D	...	...	...
8	Carbon steel	Smls. tube	SA-210	C	K03501	...	...
9	Carbon steel	Castings	SA-216	WCC	J02503	...	...
10	Carbon steel	Smls. & wld. fittings	SA-234	WPC	K03501	...	...
11	Carbon steel	Castings	SA-352	LCC	J02505	...	...
12	Carbon steel	Castings	SA-487	16	...	A	...
13	Carbon steel	Plate	SA-537	...	K12437	3	$4 < t \leq 6$
14	Carbon steel	Smls. tube	SA-556	C2	K03006	...	...
(25) 15	...	...	...	...	...	...	...
16	Carbon steel	Cast pipe	SA-660	WCC	J02505	...	...
17	Carbon steel	Bar	SA-696	C	K03200	...	...
18	Carbon steel	Sheet	SA-414	F	K03102	...	...
19	Carbon steel	Plate	SA-662	C	K02007	...	...
20	Carbon steel	Plate	SA-537	...	K12437	2	$4 < t \leq 6$
21	Carbon steel	Plate	SA-738	C	K02008	...	$4 < t \leq 6$
22	Carbon steel	Plate	SA-537	...	K12437	1	$\leq 2\frac{1}{2}$
23	Carbon steel	Wld. pipe	SA-671	CD70	K12437	...	$\leq 2\frac{1}{2}$
24	Carbon steel	Wld. pipe	SA-672	D70	K12437	...	$\leq 2\frac{1}{2}$
25	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...	$\leq 2\frac{1}{2}$
26	Carbon steel	Plate	SA-841	A	...	1	≤ 4
27	Carbon steel	Plate, sheet, bar	SA-572	55	...	...	$t \leq 2$
28	Carbon steel	Round bar	SA-572	55	...	...	$t \leq 3\frac{1}{2}$
29	Carbon steel	Sheet, strip	SA-1011	55	HSLAS	1	...
30	Carbon steel	Sheet, strip	SA-1011	60	HSLAS	2	...
(25) 31	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$2.8 < t \leq 6.3$
(25) 32	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$1.4 < t \leq 2.8$
33	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$2\frac{1}{4} < t \leq 4$
34	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$2.5 < t \leq 4$
35	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$1.5 < t \leq 2\frac{1}{4}$
36	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$\frac{5}{8} < t \leq 1.5$
37	Carbon steel	Plate	SA-455	...	K03300	...	$\frac{3}{8} < t \leq 0.58$
(25) 38	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$t \leq 1.4$
39	Carbon steel	Plate	SA/GB 713	Q345R	...	...	$\frac{1}{8} \leq t \leq \frac{5}{8}$
40	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	≤ 2.5
41	Carbon steel	Forgings	SA-266	3	K05001	...	...
42	Carbon steel	Plate	SA-455	...	K03300	...	$\leq \frac{3}{8}$
43	Carbon steel	Plate	SA-299	A	K02803	...	> 1
44	Carbon steel	Wld. pipe	SA-671	CK75	K02803	...	> 1
45	Carbon steel	Wld. pipe	SA-672	N75	K02803	...	> 1

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature											
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes	
					(NP = Not Permitted)						
					(SPT = Supports Only)						
					I	III	VIII-1	XII			
1	1	2	70	38	NP	700	NP	NP	CS-2	S5, W10, W12	
2	1	2	70	38	NP	700	NP	NP	CS-2	S6, W10, W12	
3	1	2	70	38	850	NP	NP	NP	CS-2	G10, S1, T2	
4	1	2	70	40	1000	700	1000	650	CS-2	G10, S1, T1	
5	1	2	70	40	1000	NP	NP	NP	CS-2	G10, S1, T1, W13	
6	1	2	70	40	1000	NP	NP	NP	CS-2	G4, G10, S1, T4	
7	1	2	70	40	1000	NP	NP	NP	CS-2	G10, G24, S1, T2	
8	1	2	70	40	1000	NP	1000	650	CS-2	G10, S1, T1	
9	1	2	70	40	1000	700	1000	650	CS-2	G1, G10, G17, S1, T1	
10	1	2	70	40	800	700	800	650	CS-2	G10, T1, W14	
11	1	2	70	40	NP	700	NP	NP	CS-2	G17, T1	
12	1	2	70	40	NP	700	NP	NP	CS-2	...	
13	1	3	70	40	NP	NP	700	650	CS-2	G23, W11	
14	1	2	70	40	NP	NP	800	650	CS-2	G10, T1	
15	...	...	...	...	...	...	...	...	...	...	
16	1	2	70	40	1000	700	NP	NP	CS-2	G1, G10, G17, S1, T1	
17	1	2	70	40	NP	700	NP	NP	CS-2	T1	
18	1	2	70	42	NP	NP	900	650	CS-2	G10, T1	
19	1	2	70	43	NP	NP	700	650	CS-3	T1	
20	1	3	70	46	NP	700	700	650	CS-3	G23, T1, W11	
21	1	3	70	46	NP	650	650	650	CS-3	G23, W11	
22	1	2	70	50	NP	700	650	650	CS-3	G23, T1	
23	1	2	70	50	NP	700	NP	NP	CS-3	S6, T1, W10, W12	
24	1	2	70	50	NP	700	NP	NP	CS-3	S6, T1, W10, W12	
25	1	2	70	50	NP	700	NP	NP	CS-3	S6, T1, W10, W12	
26	1	2	70	50	NP	NP	650	NP	CS-3	...	
27	...	...	70	55	NP	NP	600	600	CS-3	...	
28	...	...	70	55	NP	NP	600	600	CS-3	...	
29	...	...	70	55	NP	NP	600	600	CS-3	...	
30	...	...	70	60	NP	NP	600	600	CS-3	...	
31	1	2	71	40.5	1000	NP	1000	NP	CS-2	G10, S1, T2	
32	1	2	74	41.5	1000	NP	1000	NP	CS-2	G10, S1, T2	
33	1	2	71	44	800	NP	800	NP	CS-2	T1	
34	1	2	71	45.5	850	NP	1000	NP	CS-2	G10, S1, T1	
35	1	2	71	45.5	800	NP	800	NP	CS-2	T1	
36	1	2	72.5	47	800	NP	800	NP	CS-2	T1	
37	1	2	73	37	NP	400 (Cl. 3 only)	650	650	CS-2	...	
38	1	2	74	44	1000	NP	1000	NP	CS-2	G10, S1, T1	
39	1	2	74	50	800	NP	800	NP	CS-2	T1	
40	1	2	74	...	850	NP	1000	NP	CS-2	G10, G18, S1, T1	
41	1	2	75	37.5	1000	700	1000	NP	CS-2	G10, S1, T2, W11	
42	1	2	75	38	NP	400 (Cl. 3 only)	650	650	CS-2	...	
43	1	2	75	40	1000	700	1000	650	CS-2	G10, S1, T2	
44	1	2	75	40	NP	700	NP	NP	CS-2	S6, W10, W12	
45	1	2	75	40	NP	700	NP	NP	CS-2	S6, W10, W12	

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	...	...	...	...
2	20.0	...	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	...	...	...	...
3	20.0	20.0	20.0	...	20.0	20.0	20.0	19.4	18.8	18.1	14.8	12.0	9.3	...
4	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	6.7
5	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	6.7
6	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	5.7
7	17.0	...	17.0	...	17.0	17.0	17.0	17.0	16.8	15.5	12.6	10.2	7.9	5.7
8	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	6.7
9	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	6.7
10	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	...	...
11	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	...	...	...	...
12	20.0	...	19.9	...	18.8	18.1	17.9	17.9	17.9	17.9	...	...	...	...
13	20.0	20.0	20.0	...	19.7	19.5	18.9	18.0	17.6	17.2	...	...	...	...
14	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	14.8	12.0	9.3	6.7
17	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.8	18.3	...	...	...	...
18	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	18.3	14.8	12.0	9.3	6.7	...
19	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	18.3	...	...	...	...	...
20	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	18.3	...	...	...	...
21	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	...	...	...	...	...
22	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	18.3	...	...	...	...
23	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	18.3	...	...	...	...
24	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	18.3	...	...	...	...
25	20.0	...	20.0	...	19.7	19.5	19.5	19.5	19.5	18.3	...	...	...	...
26	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...
28	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...
29	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...
30	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...
31	20.3	...	20.3	...	20.3	20.3	20.3	20.3	19.9	19.2	14.8	12.0	9.3	6.7
32	21.1	...	21.1	...	21.1	21.1	21.1	21.0	20.3	19.6	14.8	12.0	9.3	6.7
33	20.3	...	20.3	...	20.3	20.3	20.3	20.3	20.3	18.3	14.8	12.0	...	...
34	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	18.3	14.8	12.0	9.3	6.7
35	20.3	...	20.3	...	20.3	20.3	20.3	20.3	20.3	18.3	14.8	12.0	...	...
36	20.7	...	20.7	...	20.7	20.7	20.7	20.7	20.7	18.3	14.8	12.0	...	...
37	20.9	20.9	20.9	...	20.9	20.9	20.1	18.9	18.3	...	...	...	...	...
38	21.1	...	21.1	...	21.1	21.1	21.1	21.1	21.1	20.0	14.8	12.0	9.3	6.7
39	21.1	...	21.1	...	21.1	21.1	21.1	21.1	21.1	18.3	14.8	12.0	...	...
40	21.1	21.1	21.1	21.1	21.1	21.1	21.1	21.1	21.1	18.3	14.8	12.0	9.3	6.7
41	21.4	21.4	21.4	...	21.4	21.4	20.4	19.2	18.5	17.9	15.7	12.6	9.3	6.7
42	21.4	21.4	21.4	...	21.4	21.4	20.6	19.4	18.8	...	...	...	...	...
43	21.4	21.4	21.4	...	21.4	21.4	21.4	20.4	19.8	19.1	15.7	12.6	9.3	6.7
44	21.4	...	21.4	...	21.4	21.4	21.4	20.4	19.8	19.1	...	...	...	...
45	21.4	...	21.4	...	21.4	21.4	21.4	20.4	19.8	19.1	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
5	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
7	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...	...	...
8	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
9	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
32	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
41	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...	>1
2	Carbon steel	Plate	SA-299	A	K02803	...	≤1
3	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...	≤1
4	Carbon steel	Forgings	SA-372	B	K04001	...	...
5	Carbon steel	Sheet	SA-414	G	K03103	...	...
6	Carbon steel	Plate	SA-738	A	K12447	...	...
7	Carbon steel	Plate	SA-537	...	K12437	3	$2\frac{1}{2} < t \leq 4$
8	Carbon steel	Plate	SA-537	...	K12437	2	$2\frac{1}{2} < t \leq 4$
9	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...	$2\frac{1}{2} < t \leq 4$
10	Carbon steel	Plate	SA-738	C	K02008	...	$2\frac{1}{2} < t \leq 4$
11	Carbon steel	Plate, sheet, bar	SA-572	60	...	...	$t \leq 1\frac{1}{4}$
12	Carbon steel	Round bar	SA-572	60	...	...	$t \leq 3\frac{1}{2}$
13	Carbon steel	Sheet, strip	SA-1011	60	HSLAS	1	...
14	Carbon steel	Plate	SA-299	B	K02803	...	>1
15	Carbon steel	Plate	SA-299	B	K02803	...	≤1
16	Carbon steel	Forgings	SA-765	IV	K02009	...	...
17	Carbon steel	Plate	SA-537	...	K12437	3	$\leq 2\frac{1}{2}$
18	Carbon steel	Plate	SA-537	...	K12437	2	$\leq 2\frac{1}{2}$
19	Carbon steel	Wld. pipe	SA-671	CD80	K12437	...	$\leq 2\frac{1}{2}$
20	Carbon steel	Wld. pipe	SA-672	D80	K12437	...	$\leq 2\frac{1}{2}$
21	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...	$\leq 2\frac{1}{2}$
22	Carbon steel	Plate	SA-738	C	K02008	...	$\leq 2\frac{1}{2}$
23	Carbon steel	Plate	SA-841	B	...	2	≤4
24	Carbon steel	Plate, sheet, bar	SA-572	65	...	...	$t \leq 1\frac{1}{4}$
25	Carbon steel	Plate	SA-612	...	K02900	...	$\frac{1}{2} < t \leq 1$
26	Carbon steel	Plate	SA-612	...	K02900	...	$\leq \frac{1}{2}$
27	Carbon steel	Plate	SA-738	B	K12007	...	...
28	Carbon steel	Forgings	SA-372	C	K04801	...	...
29	Carbon steel	Plate	SA-724	A	K11831	...	...
30	Carbon steel	Plate	SA-724	C	K12037	...	...
31	Carbon steel	Plate	SA-724	B	K12031	...	...
32	C-Mn-Si-Cb	Plate	SA-737	B	K12001	...	...
33	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490N	...	Normalized	≤6
34	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490NR	...	Norm. rld.	≤6
35	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized	$2.5 < t \leq 4$
36	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized	$1.5 < t \leq 2.5$
37	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized	$0.6 < t \leq 1.5$
38	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized	$0.4 \leq t \leq 0.6$
39	C-Mn-Si-V	Plate	SA-737	C	K12202	...	...
40	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...	≤2
41	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...	≤2
42	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...	$\leq 1\frac{1}{2}$
43	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...	$\leq 1\frac{1}{2}$
44	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...	≤1
45	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...	≤1

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	2	75	40	NP	700	NP	NP	CS-2	S6, W10, W12
2	1	2	75	42	1000	700	1000	650	CS-2	G10, S1, T1
3	1	2	75	42	NP	700	NP	NP	CS-2	T1, W10, W12
4	1	2	75	45	NP	NP	650	650	CS-3	W11
5	1	2	75	45	NP	NP	900	650	CS-3	G10, T1
6	1	2	75	45	NP	NP	700	650	CS-2	T1
7	1	3	75	50	NP	NP	700	650	CS-5	G23, T1, W11
8	1	3	75	55	NP	700	650	650	CS-5	G23, T1, W11
9	1	3	75	55	NP	700	NP	NP	CS-5	G26, T1, W10, W12
10	1	3	75	55	NP	650	650	650	CS-5	G23, W11
11	...	...	75	60	NP	NP	600	600	CS-3	...
12	...	...	75	60	NP	NP	600	600	CS-3	...
13	...	...	75	60	NP	NP	600	600	CS-3	...
14	1	3	80	45	800	NP	1000	650	CS-3	G10, S1, T1
15	1	3	80	47	800	NP	1000	650	CS-3	G10, S1, T1
16	1	3	80	50	NP	NP	700	NP	CS-3	...
17	1	3	80	55	NP	NP	700	650	CS-5	G23, T1, W11
18	1	3	80	60	NP	700	650	650	CS-5	G23, S6, T1, W10, W11, W12
19	1	3	80	60	NP	700	NP	NP	CS-5	S6, T1, W10, W12
20	1	3	80	60	NP	700	NP	NP	CS-5	S6, T1, W10, W12
21	1	3	80	60	NP	700	NP	NP	CS-5	S6, T1, W10, W12
22	1	3	80	60	NP	650	650	650	CS-5	G23, W11
23	1	3	80	60	NP	NP	650	NP	CS-3	...
24	...	...	80	65	NP	NP	600	600	CS-3	...
25	10C	1	81	50	NP	700	650	650	CS-3	T1
26	10C	1	83	50	NP	650	650	650	CS-3	...
27	1	3	85	60	NP	650	650	650	CS-5	...
28	...	...	90	55	NP	NP	650	650	CS-3	W11
29	1	4	90	70	NP	NP	700	650	CS-5	...
30	1	4	90	70	NP	NP	700	650	CS-5	...
31	1	4	95	75	NP	NP	700	650	CS-5	...
32	1	2	70	50	NP	700	700	650	CS-3	T1
33	1	2	71	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
34	1	2	71	...	1000	NP	1000	NP	CS-2	G10, G18, S1, T1
35	1	2	74	48	800	NP	NP	NP	CS-3	T1
36	1	2	75.5	49.5	800	NP	NP	NP	CS-3	T1
37	1	2	77	52	800	NP	NP	NP	CS-3	T1
38	1	2	77	53.5	800	NP	NP	NP	CS-3	T1
39	1	3	80	60	NP	700	700	650	CS-3	...
40	1	1	60	50	NP	NP	NP	650	...	...
41	1	1	60	50	NP	NP	NP	650	...	...
42	1	2	70	60	NP	NP	NP	650	...	...
43	1	2	70	60	NP	NP	NP	650	...	...
44	1	3	80	70	NP	NP	NP	650	...	...
45	1	3	80	70	NP	NP	NP	650	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	21.4	...	21.4	...	21.4	21.4	21.4	20.4	19.8	19.1	...	...	...	...
2	21.4	21.4	21.4	...	21.4	21.4	21.4	21.4	20.8	19.6	15.7	12.6	9.3	6.7
3	21.4	...	21.4	...	21.4	21.4	21.4	21.4	20.8	19.6	...	...	...	...
4	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	...	...	...	...	...
5	21.4	21.4	21.4	...	21.4	21.4	21.4	21.4	21.4	19.6	15.7	12.6	9.3	6.7
6	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	19.6	...	...	...	...
7	21.4	...	21.4	...	21.1	20.9	20.9	20.9	20.9	18.3	...	...	...	...
8	21.4	...	21.4	...	21.1	20.9	20.9	20.9	20.9	19.6	...	...	...	...
9	21.4	...	21.4	...	21.1	20.9	20.9	20.9	20.9	19.6	...	...	...	...
10	21.4	...	21.4	...	21.1	20.9	20.9	20.9	20.9	...	...	...	...	...
11	21.4	21.4	21.4	21.3	21.1	20.9	20.9	20.9	...	...	...	...	...	...
12	21.4	21.4	21.4	21.3	21.1	20.9	20.9	20.9	...	...	...	...	...	...
13	21.4	21.4	21.4	21.3	21.1	20.9	20.9	20.9	...	...	...	...	...	...
14	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.2	19.6	15.7	12.6	9.3	6.7
15	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	19.6	15.7	12.6	9.3	6.7
16	22.9	...	22.9	...	22.9	22.6	22.6	22.6	22.5	22.2	...	...	...	...
17	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	19.6	...	...	...	...
18	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	19.6	...	...	...	...
19	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	19.6	...	...	...	...
20	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	19.6	...	...	...	...
21	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	19.6	...	...	...	...
22	22.9	...	22.9	...	22.6	22.3	22.3	22.3	22.3	...	...	...	...	...
23	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...	...	...	...
24	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...	...	...	...	...
25	23.1	...	23.1	...	22.8	22.6	22.6	22.5	22.0	19.6	...	...	...	...
26	23.7	...	23.7	...	23.4	23.2	23.2	22.5	22.0	...	...	...	...	...
27	24.3	24.3	24.3	24.3	24.3	24.3	24.3	24.1	23.7	...	...	...	...	...
28	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	24.4	...	...	...	...	...
29	25.7	25.7	25.7	25.6	25.4	25.1	25.1	25.1	24.4	21.9	...	...	...	...
30	25.7	25.7	25.7	25.6	25.4	25.1	25.1	25.1	24.4	21.9	...	...	...	...
31	27.1	27.1	27.1	27.0	26.8	26.5	26.5	26.5	24.4	23.1	...	...	...	...
32	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	20.0	19.6	...	...	...	...
33	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	18.3	14.8	12.0	9.3	6.7
34	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.3	18.3	14.8	12.0	9.3	6.7
35	21.1	21.1	21.1	21.1	21.1	21.1	21.1	21.1	21.1	19.6	15.7	12.6	...	...
36	21.5	...	21.5	...	21.5	21.5	21.5	21.5	21.5	19.6	15.7	12.6	...	...
37	22.0	...	22.0	...	22.0	22.0	22.0	22.0	22.0	19.6	15.7	12.6	...	...
38	22.0	...	22.0	...	22.0	22.0	22.0	22.0	22.0	19.6	15.7	12.6	...	...
39	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	20.0	...	...	...	...
40	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...
41	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...
42	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...
43	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...
44	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	...	...	...	...	...
45	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
15	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
34	4.0	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...	$\leq \frac{3}{4}$
2	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...	$\leq \frac{3}{4}$
3	C-Mn-Ti	Plate, sheet	SA-562	...	K11224	...	...
4	C-Si-Ti	Forgings	SA-836	...	...	1	...
5	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...	$1\frac{5}{8} < t \leq 2\frac{1}{2}$
6	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...	$\frac{5}{8} < t \leq 1\frac{5}{8}$
7	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...	$t \leq \frac{5}{8}$
8	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1b	K11422	...	...
9	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1b	K11422	...	...
(25) 10	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1b	K11422	...	...
11	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1	K11522	...	...
12	C- $\frac{1}{2}$ Mo	Smls. & wld. fittings	SA-234	WP1	K12821	...	...
13	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1	K11522	...	...
(25) 14	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1	K11522	...	...
15	C- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P1	K11522	...	...
16	C- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP1	K11522	...	...
17	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1a	K12023	...	...
18	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1a	K12023	...	...
(25) 19	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1a	K12023	...	...
20	C- $\frac{1}{2}$ Mo	Castings	SA-217	WC1	J12524	...	...
21	C- $\frac{1}{2}$ Mo	Castings	SA-352	LC1	J12522	...	...
22	C- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP1	J12521	...	...
23	C- $\frac{1}{2}$ Mo	Plate	SA-204	A	K11820	...	...
24	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L65	K11820	...	...
25	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-65	K11820	...	...
26	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-65	K11820	...	...
27	C- $\frac{1}{2}$ Mo	Forgings	SA-182	F1	K12822	...	...
28	C- $\frac{1}{2}$ Mo	Plate	SA-204	B	K12020	...	...
29	C- $\frac{1}{2}$ Mo	Forgings	SA-336	F1	K12520	...	...
30	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L70	K12020	...	...
31	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-70	K12020	...	...
32	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-70	K12020	...	...
33	C- $\frac{1}{2}$ Mo	Plate	SA-204	C	K12320	...	...
34	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L75	K12320	...	...
35	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-75	K12320	...	...
36	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-75	K12320	...	...
37	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	55	...
38	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	55	...
39	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	65	...
40	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	65	...
41	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	70	...
42	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	70	...
43	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo-V	Plate	SA-517	B	K11630	...	$\leq 1\frac{1}{4}$
44	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Plate	SA-517	A	K11856	...	$\leq 1\frac{1}{4}$
45	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Forgings	SA-592	A	K11856	...	$\leq 2\frac{1}{2}$

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	1	4	90	80	NP	NP	NP	650	...	...
2	1	4	90	80	NP	NP	NP	650	...	...
3	1	1	71	30	NP	NP	650	NP	CS-6	G7
4	1	1	55	25	NP	NP	650	650	CS-1	...
5	3	1	65.5	37.5	1000	NP	1000	NP	CS-2	G11, S2, T4
6	3	1	65.5	39	1000	NP	1000	NP	CS-2	G11, S2, T4
7	3	1	65.5	40.5	1000	NP	1000	NP	CS-2	G11, S2, T4
8	3	1	53	28	1000	NP	1000	650	CS-1	G11, S3, T5
9	3	1	53	28	1000	NP	NP	NP	CS-1	G11, S2, T5, W13
10	3	1	53	28	1000	NP	1000	650	CS-1	G11, G24, S2, T5
11	3	1	55	30	1000	NP	1000	650	CS-2	G11, S3, T4
12	3	1	55	30	1000	700	1000	650	CS-2	G11, T4, W14
13	3	1	55	30	1000	NP	NP	NP	CS-2	G11, S2, T4, W13
14	3	1	55	30	1000	NP	1000	650	CS-2	G11, G24, S2, T4
15	3	1	55	30	1000	700	1000	650	CS-2	G11, S2, T4
16	3	1	55	30	1000	700	1000	650	CS-2	G11, S2, T4
17	3	1	60	32	1000	NP	1000	650	CS-2	G11, S3, T4
18	3	1	60	32	1000	NP	NP	NP	CS-2	G11, S2, T4, W13
19	3	1	60	32	1000	NP	1000	650	CS-2	G11, G24, S2, T4
20	3	1	65	35	1000	700	1000	650	CS-2	G1, G11, G17, S2, T4
21	3	1	65	35	NP	700	650	650	CS-2	G1, G17
22	3	1	65	35	NP	700	NP	NP	CS-2	G17
23	3	1	65	37	1000	700	1000	650	CS-2	G11, S2, T4
24	3	1	65	37	NP	700	NP	NP	CS-2	G26, W10, W12
25	3	1	65	37	NP	700	NP	NP	CS-2	G26, W10, W12
26	3	1	65	37	NP	300 (Cl. 3 only)	NP	NP	CS-2	G27, W10, W12
27	3	2	70	40	1000	700	1000	650	CS-2	G11, S2, T4
28	3	2	70	40	1000	700	1000	650	CS-2	G11, S2, T4
29	3	2	70	40	1000	700	1000	650	CS-2	G11, S2, T4
30	3	2	70	40	NP	700	NP	NP	CS-2	G26, W10, W12
31	3	2	70	40	NP	700	NP	NP	CS-2	G26, W10, W12
32	3	2	70	40	NP	300 (Cl. 3 only)	NP	NP	CS-2	G27, W10, W12
33	3	2	75	43	1000	700	1000	650	CS-2	G11, S2, T4, W12
34	3	2	75	43	NP	700	NP	NP	CS-2	G26, W10, W12
35	3	2	75	43	NP	700	NP	NP	CS-2	G26, W10, W12
36	3	2	75	43	NP	300 (Cl. 3 only)	NP	NP	CS-2	G27, W10, W12
37	...	...	85	55	NP	NP	600	600	CS-3	W11
38	...	...	85	55	NP	NP	600	600	CS-3	W11
39	...	...	105	65	NP	NP	600	600	CS-3	W11
40	...	...	105	65	NP	NP	600	600	CS-3	W11
41	...	...	120	70	NP	NP	200	200	CS-3	W11
42	...	...	120	70	NP	NP	200	200	CS-3	W11
43	11B	4	115	100	NP	650 (SPT)	650	650	HT-1	...
44	11B	1	115	100	NP	650 (SPT)	650	650	HT-1	...
45	11B	1	115	100	NP	650 (SPT)	650	650	HT-1	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	...	...	...	...	...
2	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	...	...	...	...	...
3	12.9	...	11.5	...	10.6	10.4	10.4	10.4	10.4	...	...	...	...	...
4	15.7	...	14.3	...	13.3	13.0	13.0	12.9	12.7	...	...	...	...	...
5	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.2	13.7
6	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.2	13.7
7	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.2	13.7
8	15.1	15.1	15.1	...	15.1	15.1	15.1	15.1	15.0	14.7	14.3	14.0	13.5	13.0
9	15.1	...	15.1	...	15.1	15.1	15.1	15.1	15.0	14.7	14.3	14.0	13.5	13.0
10	12.9	12.9	12.9	...	12.9	12.9	12.9	12.9	12.7	12.5	12.2	11.9	11.5	11.1
11	15.7	15.7	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.7
12	15.7	15.7	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.7
13	15.7	...	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.7
14	13.4	13.4	13.4	...	13.4	13.4	13.4	13.4	13.4	13.4	13.1	12.7	12.3	11.6
15	15.7	15.7	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.7
16	15.7	15.7	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.7
17	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	16.8	16.4	15.9	15.4	13.7
18	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	16.8	16.4	15.9	15.4	13.7
19	14.6	...	14.6	...	14.6	14.6	14.6	14.6	14.6	14.3	13.9	13.6	13.1	11.6
20	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.4	17.9	17.4	16.9	13.7
21	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.4	...	...	...	...
22	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.4	...	...	...	...
23	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	18.6	18.4	17.9	13.7
24	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...
25	18.6	...	18.6	...	18.6	18.6	18.6	18.6	18.6	18.6	...	...	...	...
26	18.6	...	18.6	...	18.6	...	...	...	...	...	...	...	...	...
27	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.3	13.7
28	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.3	13.7
29	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.3	13.7
30	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
31	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
32	20.0	...	20.0	...	20.0	...	...	...	...	...	...	...	...	...
33	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	21.4	21.4	20.7	13.7
34	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	...	...	...	...
35	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	...	...	...	...
36	21.4	...	21.4	...	21.4	...	...	...	...	...	...	...	...	...
37	24.3	...	24.3	...	24.3	24.3	24.3	24.3	...	...	...	...	...	...
38	24.3	...	24.3	...	24.3	24.3	24.3	24.3	...	...	...	...	...	...
39	30.0	...	30.0	...	30.0	30.0	30.0	30.0	...	...	...	...	...	...
40	30.0	...	30.0	...	30.0	30.0	30.0	30.0	...	...	...	...	...	...
41	34.3	...	34.3	...	...	...	...	...	...	...	...	...	...	...
42	34.3	...	34.3	...	...	...	...	...	...	...	...	...	...	...
43	32.9	...	32.9	32.9	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...
44	32.9	...	32.9	32.9	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...
45	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
6	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
7	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
8	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
10	7.0	4.1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
12	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
13	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
14	7.0	4.1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
16	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
17	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
18	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
19	7.0	4.1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
28	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
29	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P2	K11547	...	...
2	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP2	K11547	...	...
3	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2	K12143	1	...
4	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$	K12143	...	...
5	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$	K12143	...	...
(25) 6	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T2	K11547	...	...
7	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. tube	SA-250	T2	K11547	...	...
8	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. tube	SA-250	T2S1	K11547	...	...
9	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP2	J11547	...	...
10	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F2	K12122	...	...
11	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2	K12143	2	...
12	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$	K12143	...	...
(25) 13	$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	Smls. & wld. tube	SA-423	1	K11535	...	...
14	$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	Wld. tube	SA-423	1	K11535	...	...
15	$\frac{3}{4}\text{Cr}-\frac{3}{4}\text{Ni}-\text{Cu}-\text{Al}$	Pipe	SA-333	4	K11267	...	...
16	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	55	...
17	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	55	...
18	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	55	...
19	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	65	...
20	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	65	...
21	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	65	...
22	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	70	...
23	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	70	...
24	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	70	...
25	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	G41370	110	...
26	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	12	K11757	1	...
27	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	1CR	K11757	...	...
28	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP12	J11562	...	...
29	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F12	K11562	1	...
30	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T12	K11562	...	...
(25) 31	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. & wld. fittings	SA-234	WP12	K12062	1	...
32	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. tube	SA-250	T12	K11562	...	...
33	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. tube	SA-250	T12S1	K11562	...	...
34	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P12	K11562	...	...
35	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP12	K11562	...	...
36	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$10 < t \leq 20$
37	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$6 < t \leq 10$
38	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$4 < t \leq 6$
39	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/GB 713	15CrMoR	...	NT	$4 < t \leq 8$
40	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$4 < t \leq 10$
41	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$2.5 < t \leq 4$
42	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$2.8 < t \leq 4$
(25) 43	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA/EN 10216-2	13CrMo4-5	...	...	$1\frac{5}{8} < t \leq 2\frac{1}{2}$
44	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$1.4 < t \leq 2.8$
45	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA/EN 10216-2	13CrMo4-5	...	...	$t \leq 1\frac{5}{8}$

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	3	1	55	30	1000	700	1000	650	CS-2	T5
2	3	1	55	30	1000	700	1000	650	CS-2	T5
3	3	1	55	33	1000	700	1000	650	CS-2	T5
4	3	1	55	33	NP	700	NP	NP	CS-2	G26, W10, W12
5	3	1	55	33	NP	300 (Cl. 3 only)	NP	NP	CS-2	G27, W10, W12
6	3	1	60	30	1000	700	1000	650	CS-2	T5
7	3	1	60	30	1000	NP	NP	NP	CS-2	G24, T5
8	3	1	60	30	1000	NP	NP	NP	CS-2	T5, W13
9	3	1	60	30	NP	700	NP	NP	CS-2	G17
10	3	2	70	40	1000	NP	1000	650	CS-2	T5
11	3	2	70	45	NP	700	1000	650	CS-3	T5
12	3	2	70	45	NP	700	NP	NP	CS-3	G26, W10, W12
13	4	2	60	37	700	NP	650	NP	CS-2	W13, W14
14	4	2	60	37	700	NP	650	NP	CS-2	G24
15	4	2	60	35	NP	700	650	NP	CS-2	...
16	...	...	85	55	NP	NP	600	600	CS-3	W11
17	...	...	85	55	NP	NP	600	600	CS-3	W11
18	...	...	85	55	NP	NP	600	600	CS-3	W11
19	...	...	105	65	NP	NP	650	650	CS-2	W11
20	...	...	105	65	NP	NP	600	600	CS-3	W11
21	...	...	105	65	NP	NP	650	650	CS-2	W11
22	...	...	120	70	NP	NP	650	650	CS-5	W11
23	...	...	120	70	NP	NP	650	650	CS-5	W11
24	...	...	120	70	NP	NP	650	650	CS-5	W11
25	...	...	135	110	NP	NP	650	650	HT-1	W11
26	4	1	55	33	1200	700	1200	NP	CS-2	S4, T5
27	4	1	55	33	NP	700	NP	NP	CS-2	G26, W10, W12
28	4	1	60	30	NP	700	NP	NP	CS-2	G17
29	4	1	60	32	1200	NP	1200	NP	CS-2	T5
30	4	1	60	32	1200	700	1200	NP	CS-2	S4, T5
31	4	1	60	32	1200	700	1200	NP	CS-2	S4, T5, W14
32	4	1	60	32	1200	NP	NP	NP	CS-2	G24, S4, T5
33	4	1	60	32	1200	NP	NP	NP	CS-2	S4, T5, W13
34	4	1	60	32	1200	700	1200	NP	CS-2	S4, T5
35	4	1	60	32	1200	700	1200	NP	CS-2	S4, T5
36	4	1	61	35	1200	NP	1200	NP	CS-2	S4, T5
37	4	1	61	35.5	1200	NP	1200	NP	CS-2	S4, T5
38	4	1	62.5	37	1200	NP	1200	NP	CS-2	S4, T5
39	4	1	64	37	1200	NP	NP	NP	CS-2	S4, T5
40	4	1	64	38.5	1200	NP	1200	NP	CS-2	S4, T5
41	4	1	64	39	1200	NP	1200	NP	CS-2	S4, T5
42	4	1	64	40	1200	NP	1200	NP	CS-2	S4, T5
43	4	1	64	40.5	1200	NP	1200	NP	CS-2	T5
44	4	1	64	41.5	1200	NP	1200	NP	CS-2	S4, T5
45	4	1	64	42	1200	NP	1200	NP	CS-2	T5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	15.7	...	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.9
2	15.7	...	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.4	14.9	14.5	13.9
3	15.7	...	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	15.7	15.7	15.3	14.3
4	15.7	...	15.7	...	15.7	15.7	15.7	15.7	15.7	15.7	...	...	...	...
5	15.7	...	15.7	...	15.7	...	...	...	...	...	...	...	...	...
6	17.1	...	17.1	...	17.1	17.1	16.9	16.4	16.1	15.7	15.4	14.9	14.5	13.9
7	14.5	...	14.5	...	14.5	14.5	14.4	13.9	13.7	13.3	13.1	12.7	12.3	11.8
8	17.1	...	17.1	...	17.1	17.1	16.9	16.4	16.1	15.7	15.4	14.9	14.5	13.9
9	17.1	...	17.1	...	17.1	17.1	16.9	16.4	16.1	15.7	...	...	...	...
10	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.3	18.6
11	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.5	18.6
12	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
13	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...
14	14.6	...	14.6	...	14.6	14.6	14.6	14.6	14.6	14.6	...	...	...	...
15	17.1	17.1	17.1	...	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...
16	24.3	...	24.3	...	24.3	24.3	24.3	24.3	...	...	...	...	...	...
17	24.3	...	24.3	...	24.3	24.3	24.3	24.3	...	...	...	...	...	...
18	24.3	...	24.3	...	24.3	24.3	24.3	24.3	...	...	...	...	...	...
19	30.0	...	30.0	...	30.0	30.0	30.0	30.0	29.8	...	...	...	...	...
20	30.0	...	30.0	...	30.0	30.0	30.0	30.0	...	...	...	...	...	...
21	30.0	...	30.0	...	30.0	30.0	30.0	30.0	29.8	...	...	...	...	...
22	34.3	34.3	34.3	...	34.3	34.3	34.3	34.3	34.1	...	...	...	...	...
23	34.3	...	34.3	...	34.3	34.3	34.3	34.3	34.1	...	...	...	...	...
24	34.3	...	34.3	...	34.3	34.3	34.3	34.3	34.1	...	...	...	...	...
25	38.5	...	36.9	...	36.7	36.5	36.1	35.9	34.3	...	...	...	...	...
26	15.7	...	15.4	...	15.1	15.1	15.1	15.1	15.1	15.1	15.1	15.1	15.1	14.7
27	15.7	...	15.4	...	15.1	15.1	15.1	15.1	15.1	15.1	...	...	...	...
28	17.1	...	16.8	...	16.5	16.2	15.7	15.2	15.0	14.8	...	...	...	...
29	17.1	17.1	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
30	17.1	...	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
31	17.1	...	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
32	14.5	14.5	14.3	...	14.0	14.0	14.0	13.8	13.6	13.4	13.2	13.0	12.7	12.3
33	17.1	17.1	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
34	17.1	...	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
35	17.1	...	16.8	...	16.5	16.5	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
36	17.4	...	17.2	...	16.7	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.3	15.8
37	17.4	17.2	17.1	16.9	16.8	16.8	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1
38	17.8	17.7	17.5	17.3	17.2	17.2	17.1	17.1	17.1	17.1	17.1	17.1	17.0	16.7
39	18.2	...	17.9	...	17.6	17.6	17.1	16.6	16.4	16.1	15.9	15.5	15.2	14.8
40	18.2	...	18.0	...	17.5	17.4	17.4	17.4	17.4	17.4	17.4	17.4	17.3	16.9
41	18.2	18.1	17.9	17.7	17.6	17.6	17.5	17.5	17.5	17.5	17.5	17.5	17.4	17.1
42	18.2	...	18.0	...	17.5	17.4	17.4	17.4	17.4	17.4	17.4	17.4	17.3	16.9
43	18.2	...	18.2	...	18.2	18.2	18.2	18.2	18.2	18.2	18.2	18.2	17.7	17.0
44	18.2	...	18.0	...	17.5	17.4	17.4	17.4	17.4	17.4	17.4	17.4	17.3	16.9
45	18.2	...	18.2	...	18.2	18.2	18.2	18.2	18.2	18.2	18.2	18.2	17.7	17.0

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
2	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
3	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
7	7.8	5.0	...	...	...	...	...	...	...	...	...	...	...	...	...
8	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
11	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
30	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
31	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
32	9.6	6.1	3.8	2.4	1.5	0.94	...	...	...	...	...	...	...	...	...
33	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
34	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
35	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
36	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
37	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
38	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
39	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
40	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
41	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
42	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
43	11.3	7.2	4.5	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
44	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
45	11.3	7.2	4.5	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25)	1 1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$t \leq 1.4$
	2 1Cr- $\frac{1}{2}$ Mo	Plate	SA-387	12	K11757	2	...
	3 1Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	1CR	K11757	...	...
	4 1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR	...	NT	$2.5 < t \leq 4$
	5 1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$\frac{5}{8} < t \leq 2.5$
	6 1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR	...	NT	$0.25 \leq t \leq 2.5$
	7 1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$t \leq \frac{5}{8}$
	8 1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12	K11564	2	...
	9 1Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F12	K11564	...	...
	10 1Cr-V	Smls. tube	SA-213	T17	K12047	...	...
	11 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC6	J12072	...	...
	12 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP11	J12072	...	...
	13 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Bar	SA-739	B11	K11797	...	...
	14 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11597	1	...
	15 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T11	K11597	...	...
(25)	16 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. & wld. fittings	SA-234	WP11	...	1	...
	17 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. tube	SA-250	T11	K11597	...	...
	18 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. tube	SA-250	T11S1	K11597	...	...
	19 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P11	K11597	...	...
	20 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11597	1	...
	21 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forged pipe	SA-369	FP11	K11597	...	...
	22 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	1	...
	23 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	$\frac{1}{4}$ CR	K11789	...	...
	24 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	$\frac{1}{4}$ CR	K11789	...	...
	25 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11572	2	...
	26 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	2	...
	27 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	3	...
	28 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	2	...
	29 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	$\frac{1}{4}$ CR	K11789	...	...
	30 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	$2\frac{1}{2} < t \leq 4$
(25)	31 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	$\leq 2\frac{1}{2}$
	32 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	$2\frac{1}{2} < t \leq 6$
	33 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	$\leq 2\frac{1}{2}$
	34 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	1	...
	35 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA-213	T22	K21590	...	...
	36 $\frac{1}{4}$ Cr-1Mo	Smls. & wld. fittings	SA-234	WP22	K21590	1	...
	37 $\frac{1}{4}$ Cr-1Mo	Wld. tube	SA-250	T22	K21590	...	...
	38 $\frac{1}{4}$ Cr-1Mo	Wld. tube	SA-250	T22S1	K21590	...	...
	39 $\frac{1}{4}$ Cr-1Mo	Smls. pipe	SA-335	P22	K21590	...	...
	40 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	1	...
	41 $\frac{1}{4}$ Cr-1Mo	Forged pipe	SA-369	FP22	K21590	...	...
	42 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	1	...
	43 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	$\frac{1}{4}$ CR	K21590	...	...
	44 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$6 < t \leq 10$
	45 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	$8 < t \leq 20$

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	4	1	64	43	1200	NP	1200	NP	CS-2	S4, T5
2	4	1	65	40	1200	700	1200	NP	CS-2	S4, T5
3	4	1	65	40	NP	700	NP	NP	CS-2	G26, W10, W12
4	4	1	65.5	40	1200	NP	NP	NP	CS-2	S4, T5
5	4	1	65.5	42	1200	NP	1200	NP	CS-2	S4, T5
6	4	1	65.5	43	1200	NP	NP	NP	CS-2	S4, T5
7	4	1	65.5	43.5	1200	NP	1200	NP	CS-2	S4, T5
8	4	1	70	40	1200	700	1200	NP	CS-2	S4, T4
9	4	1	70	40	1200	700	1200	NP	CS-2	S4, T4
10	10B	1	60	30	NP	NP	650	650	CS-2	...
11	4	1	70	40	1100	700	1100	NP	CS-2	G1, G17, T4
12	4	1	70	40	NP	700	NP	NP	CS-2	G17
13	4	1	70	45	NP	700	1200	NP	CS-3	T4
14	4	1	60	30	1200	NP	1200	NP	CS-2	S4, T5
15	4	1	60	30	1200	700	1200	NP	CS-2	S4, T5
16	4	1	60	30	1200	700	1200	NP	CS-2	S4, T5, W14
17	4	1	60	30	1200	NP	NP	NP	CS-2	G24, S4, T5
18	4	1	60	30	1200	NP	NP	NP	CS-2	S4, T5, W13
19	4	1	60	30	1200	700	1200	NP	CS-2	S4, T5
20	4	1	60	30	1200	NP	NP	NP	CS-2	S4, T5
21	4	1	60	30	1200	700	1200	NP	CS-2	S4, T5
22	4	1	60	35	1200	700	1200	NP	CS-2	S4, T4
23	4	1	60	35	NP	300 (Cl. 3 only)	NP	NP	CS-2	G27, W10, W12
24	4	1	60	35	NP	700	NP	NP	CS-2	G26, W10, W12
25	4	1	70	40	1200	700	1200	NP	CS-2	S4, T4
26	4	1	70	40	1200	NP	1200	NP	CS-2	S4, T4
27	4	1	75	45	NP	NP	1200	NP	CS-3	T3
28	4	1	75	45	1200	700	1200	NP	CS-3	S4, T3
29	4	1	75	45	NP	700	NP	NP	CS-3	G26, W10, W12
30	11B	2	105	90	NP	650 (SPT)	650	650	CS-5	S7
31	11B	2	115	100	NP	NP	650	650	HT-1	...
32	11B	2	105	90	NP	700 (Cl. MC & SPT)	650	650	CS-5	...
33	11B	2	115	100	NP	700 (Cl. MC & SPT)	650	650	HT-1	...
34	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
35	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
36	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9, W14
37	5A	1	60	30	1200	NP	NP	NP	CS-2	G24, S4, T4, W9
38	5A	1	60	30	1200	NP	NP	NP	CS-2	S4, T4, W9, W13
39	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
40	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
41	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
42	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T4, W7, W9
43	5A	1	60	30	NP	700	NP	NP	CS-2	G26, W10, W12
44	5A	1	65.5	36.5	1100	NP	1100	NP	CS-3	S4, T4, W7, W9
45	5A	1	65.5	38.5	1200	NP	1200	NP	CS-3	S4, T5, W7, W9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	18.2	...	18.0	...	17.5	17.4	17.4	17.4	17.4	17.4	17.4	17.4	17.3	16.9
2	18.6	18.6	18.2	...	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.4
3	18.6	...	18.2	...	17.9	17.9	17.9	17.9	17.9	17.9	...	...	...	...
4	18.6	...	18.3	...	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1
5	18.6	18.5	18.3	18.1	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.8	17.5
6	18.6	...	18.3	...	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1
7	18.6	18.5	18.3	18.1	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.8	17.5
8	20.0	...	19.6	...	19.2	19.2	19.2	19.2	19.2	19.2	19.2	19.1	18.6	18.0
9	20.0	20.0	19.6	...	19.2	19.2	19.2	19.2	19.2	19.2	19.2	19.1	18.6	18.0
10	17.1	17.1	17.1	...	17.1	16.8	16.2	15.7	15.4	...	...	...	...	...
11	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	19.7	19.2	18.7	13.7
12	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
13	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.4	13.7
14	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
15	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
16	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
17	14.5	...	14.5	...	14.5	14.3	13.8	13.3	13.1	12.8	12.6	12.2	11.9	11.6
18	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
19	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
20	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
21	17.1	...	17.1	...	17.1	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
22	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	17.1	17.1	16.8	16.4	13.7
23	17.1	...	17.1	...	17.1	...	...	...	...	...	...	...	...	...
24	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	17.1	...	...	...	...
25	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	19.7	19.2	18.7	13.7
26	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	19.7	19.2	18.7	13.7
27	21.4	21.4	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	21.4	21.4	20.2	13.7
28	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	21.4	21.4	20.2	13.7
29	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	...	...	...	...
30	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	...	...	...	...	...
31	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.9	...	...	...	...	...
32	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	...	...	...	...
33	32.9	...	32.9	32.9	32.9	32.9	32.9	32.9	32.9	32.7	...	...	...	...
34	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
35	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
36	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
37	14.5	...	14.5	...	14.1	14.1	14.1	14.1	14.1	14.1	14.1	14.1	14.1	11.6
38	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
39	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
40	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
41	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
42	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	13.6
43	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	...	...	...	...
44	18.6	...	18.6	...	18.2	18.0	17.9	17.7	17.6	17.4	17.2	16.8	16.3	15.8
45	18.6	...	18.6	...	18.3	18.0	17.9	17.8	17.7	17.5	17.3	16.9	16.3	15.7

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
2	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
5	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
6	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
7	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
8	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
9	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	9.3	6.3	4.2	2.8	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
14	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
15	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
16	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
17	7.9	5.4	3.6	2.4	1.6	1.0	...	...	...	...	...	...	...	...	...
18	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
19	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
20	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
21	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
22	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
26	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
27	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
28	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
35	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
36	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
37	9.2	6.8	4.8	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
38	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
39	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
40	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
41	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
42	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...	...	...	...
45	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	4 < t ≤ 6
2	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	2.5 < t ≤ 4
3	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA/EN 10216-2	10CrMo9-10	...	...	1 $\frac{5}{8}$ < t ≤ 2 $\frac{1}{2}$
4	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA/EN 10216-2	10CrMo9-10	...	...	t ≤ 1 $\frac{5}{8}$
5	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	t ≤ 2.5
6	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9	J21890	...	...
7	2 $\frac{1}{4}$ Cr-1Mo	Cast pipe	SA-426	CP22	J21890	...	...
8	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	3	...
9	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	3	...
10	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	2	...
11	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR	K21590	...	...
12	2 $\frac{1}{4}$ Cr-1Mo	Bar	SA-739	B22	K21390	...	...
(25) 13	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	t ≤ 8
14	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-487	8	J22091	A	...
15	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-508	22	K21590	3	...
16	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	3	...
17	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-542	B	K21590	4	...
18	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-182	F22V	K31835	...	...
19	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-336	F22V	K31835	...	...
20	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-541	22V	K31835	...	...
21	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-542	D	K31835	4a	...
22	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-832	22V	K31835	...	...
23	3Cr-1Mo	Smls. tube	SA-213	T21	K31545	...	...
24	3Cr-1Mo	Smls. pipe	SA-335	P21	K31545	...	...
25	3Cr-1Mo	Forgings	SA-336	F21	K31545	1	...
26	3Cr-1Mo	Forged pipe	SA-369	FP21	K31545	...	...
27	3Cr-1Mo	Plate	SA-387	21	K31545	1	...
28	3Cr-1Mo	Cast pipe	SA-426	CP21	J31545	...	...
29	3Cr-1Mo	Forgings	SA-182	F21	K31545	...	...
30	3Cr-1Mo	Forgings	SA-336	F21	K31545	3	...
31	3Cr-1Mo	Plate	SA-387	21	K31545	2	...
32	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-182	F3V	K31830	...	...
33	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-336	F3V	K31830	...	...
34	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-508	3V	K31830	...	...
35	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-541	3V	K31830	...	...
36	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-542	C	K31830	4a	...
37	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-832	21V	K31830	...	...
38	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-182	F3VCb	...	...	...
39	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-336	F3VCb	...	...	...
40	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-508	3VCb	...	...	...
41	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-541	3VCb	...	...	...
42	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-542	E	...	4a	...
43	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-832	23V	...	...	...
44	5Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T5	K41545	...	...
45	5Cr- $\frac{1}{2}$ Mo	Smls. & wld. fittings	SA-234	WP5	K41545	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	5A	1	66.5	37.5	1100	NP	1100	NP	CS-3	S4, T4, W7, W9
2	5A	1	68	40.5	1100	NP	1100	NP	CS-3	S4, T4, W7, W9
3	5A	1	69.5	39	1200	NP	1200	NP	CS-2	T4, W7, W9
4	5A	1	69.5	40.5	1200	NP	1200	NP	CS-2	T4, W7, W9
5	5A	1	69.5	...	1100	NP	1100	NP	CS-3	G18, S4, T4, W7, W9
6	5A	1	70	40	1200	700	1200	NP	CS-2	G1, G17, S4, T4, W7, W9
7	5A	1	70	40	NP	700	NP	NP	CS-2	G17
8	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T4, W7, W9
9	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T4, W7, W9
10	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T4, W7, W9
11	5A	1	75	45	NP	700	NP	NP	CS-3	G26, W10, W12
12	5A	1	75	45	NP	700	1200	NP	CS-3	T4, W7
13	5A	1	75.5	45	1200	NP	1200	NP	CS-3	S4, T4, W7, W9
14	5C	1	85	55	NP	NP	1000	NP	CS-3	G1, T4, W7
15	5C	1	85	55	NP	NP	850	NP	CS-2	...
16	5C	1	85	55	NP	NP	850	NP	CS-2	...
17	5C	1	85	55	NP	NP	850	NP	CS-2	...
18	5C	1	85	60	NP	NP	900	NP	CS-2	...
19	5C	1	85	60	NP	NP	900	NP	CS-2	...
20	5C	1	85	60	NP	NP	900	NP	CS-2	...
21	5C	1	85	60	NP	NP	900	NP	CS-2	...
22	5C	1	85	60	NP	NP	900	NP	CS-2	...
23	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T3
24	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T3
25	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T3
26	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T3
27	5A	1	60	30	1200	700	1200	NP	CS-2	S4, T3
28	5A	1	60	30	NP	700	NP	NP	CS-2	G17
29	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T3
30	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T3
31	5A	1	75	45	1200	700	1200	NP	CS-3	S4, T3
32	5C	1	85	60	NP	NP	900	NP	CS-3	...
33	5C	1	85	60	NP	NP	900	NP	CS-3	...
34	5C	1	85	60	NP	NP	900	NP	CS-3	...
35	5C	1	85	60	NP	NP	900	NP	CS-3	...
36	5C	1	85	60	NP	NP	900	NP	CS-3	...
37	5C	1	85	60	NP	NP	900	NP	CS-3	...
38	5C	1	85	60	NP	NP	900	NP	CS-3	...
39	5C	1	85	60	NP	NP	900	NP	CS-3	...
40	5C	1	85	60	NP	NP	900	NP	CS-3	...
41	5C	1	85	60	NP	NP	900	NP	CS-3	...
42	5C	1	85	60	NP	NP	900	NP	CS-3	...
43	5C	1	85	60	NP	NP	900	NP	CS-3	...
44	5B	1	60	30	1200	700	1200	NP	CS-2	T4
45	5B	1	60	30	1200	700	1200	NP	CS-2	T4, W14

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	19.1	...	19.1	...	18.6	18.4	18.3	18.1	18.0	17.8	17.5	17.2	16.7	15.8
2	19.5	...	19.5	...	19.0	18.8	18.7	18.5	18.4	18.2	17.9	17.5	17.0	15.8
3	19.9	...	19.9	...	19.4	19.2	19.1	18.9	18.8	18.6	18.3	17.9	17.4	15.8
4	19.9	...	19.9	...	19.4	19.2	19.1	18.9	18.8	18.6	18.3	17.9	17.4	15.8
5	19.9	...	19.9	...	19.4	19.2	19.1	18.9	18.8	18.6	18.3	17.9	17.4	15.8
6	20.0	...	20.0	...	19.7	19.4	19.3	19.2	19.1	18.8	18.5	17.9	17.2	15.8
7	20.0	...	20.0	...	19.7	19.4	19.3	19.2	19.1	18.8	...	...	...	...
8	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.7	15.8
9	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.7	15.8
10	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.7	15.8
11	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	...	...	...	...
12	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.7	15.8
13	21.5	...	21.5	...	21.1	20.8	20.7	20.6	20.5	20.3	19.9	19.5	18.9	15.8
14	24.3	24.3	24.3	...	23.7	23.5	23.5	23.3	23.2	22.9	22.4	21.7	20.8	15.8
15	24.3	...	24.3	...	24.3	24.3	23.8	23.3	23.1	22.9	22.6	21.9	20.4	...
16	24.3	...	24.3	...	24.3	24.3	23.8	23.3	23.1	22.9	22.6	21.9	20.4	...
17	24.3	...	24.3	...	24.3	24.3	23.8	23.3	23.1	22.9	22.6	21.9	20.4	...
18	24.3	...	24.3	...	24.3	24.3	24.3	23.7	23.2	22.8	22.2	21.6	21.0	20.3
19	24.3	...	24.3	...	24.3	24.3	24.3	23.7	23.2	22.8	22.2	21.6	21.0	20.3
20	24.3	...	24.3	...	24.3	24.3	24.3	23.7	23.2	22.8	22.2	21.6	21.0	20.3
21	24.3	...	24.3	...	24.3	24.3	24.3	23.7	23.2	22.8	22.2	21.6	21.0	20.3
22	24.3	...	24.3	...	24.3	24.3	24.3	23.7	23.2	22.8	22.2	21.6	21.0	20.3
23	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.0	12.0
24	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.0	12.0
25	17.1	17.1	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.0	12.0
26	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.0	12.0
27	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.6	16.0	12.0
28	17.1	...	17.1	...	16.6	16.6	16.6	16.6	16.6	16.6	...	...	...	...
29	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.1	13.1
30	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.1	13.1
31	21.4	...	21.4	...	20.9	20.6	20.5	20.4	20.2	20.0	19.7	19.3	18.1	13.1
32	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
33	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
34	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
35	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
36	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
37	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
38	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
39	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
40	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
41	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
42	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
43	24.3	...	24.3	...	23.3	22.6	22.2	21.8	21.6	21.4	21.1	20.8	20.4	20.0
44	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
45	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...	...	...	...
2	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...	...	...	...
3	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
4	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
5	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...	...	...	...
6	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
9	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
10	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
13	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...	...	...	...
14	11.4	7.8	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...	...	...	...
24	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...	...	...	...
25	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...	...	...	...
26	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...	...	...	...
27	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...	...	...	...
30	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...	...	...	...
31	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
45	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...

(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	5Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P5	K41545	...	...
2	5Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP5	K41545	...	...
3	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	1	...
4	5Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	5CR	K41545	...	...
5	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5	K41545	...	...
6	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5	K41545	...	...
7	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	2	...
8	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5A	K42544	...	...
9	5Cr- $\frac{1}{2}$ Mo	Castings	SA-217	C5	J42045	...	...
10	5Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP5	J42045	...	...
11	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5a	K42544	...	...
12	5Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T5b	K51545	...	...
13	5Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P5b	K51545	...	...
14	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. tube	SA-213	T5c	K41245	...	...
15	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. pipe	SA-335	P5c	K41245	...	...
16	9Cr-1Mo	Smls. tube	SA-213	T9	K90941	...	...
17	9Cr-1Mo	Fittings	SA-234	WP9	K90941	...	...
18	9Cr-1Mo	Smls. pipe	SA-335	P9	K90941	...	...
19	9Cr-1Mo	Forged pipe	SA-369	FP9	K90941	...	...
20	9Cr-1Mo	Forgings	SA-182	F9	K90941	...	...
21	9Cr-1Mo	Forgings	SA-336	F9	K90941	...	...
22	9Cr-1Mo	Castings	SA-217	C12	J82090	...	...
23	9Cr-1Mo	Cast pipe	SA-426	CP9	J82090	...	...
24	9Cr-1Mo-V	Smls. tube	SA-213	T91 Type 1	K90901	...	...
25	9Cr-1Mo-V	Fittings	SA-234	WP91 Type 1	K90901	...	...
26	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Type 1	K90901	...	$t \leq 3$
27	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Type 1	K90901	...	$t > 3$
28	9Cr-1Mo-V	Forged pipe	SA-369	FP91 Type 1	K90901	...	...
29	9Cr-1Mo-V	Plate	SA-387	91 Type 1	K90901	2	$t \leq 3$
30	9Cr-1Mo-V	Plate	SA-387	91 Type 1	K90901	2	$t > 3$
31	9Cr-1Mo-V	Forgings	SA-182	F91 Type 1	K90901	...	$t \leq 3$
32	9Cr-1Mo-V	Forgings	SA-182	F91 Type 1	K90901	...	$t > 3$
33	9Cr-1Mo-V	Forgings	SA-336	F91 Type 1	K90901	...	...
34	9Cr-1Mo-V	Smls. tube	SA-213	T91 Type 2	K90901	...	...
35	9Cr-1Mo-V	Fittings	SA-234	WP91 Type 2	K90901	...	...
36	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Type 2	K90901	...	...
37	9Cr-1Mo-V	Forged pipe	SA-369	FP91 Type 2	K90901	...	...
38	9Cr-1Mo-V	Plate	SA-387	91 Type 2	K90901	2	...
39	9Cr-1Mo-V	Forgings	SA-182	F91 Type 2	K90901	...	...
40	9Cr-1Mo-V	Forgings	SA-336	F91 Type 2	K90901	...	...
41	11Cr-Ti	Plate	SA-240	...	S40910	...	...
42	11Cr-Ti	Plate	SA-240	...	S40920	...	...
43	11Cr-Ti	Plate	SA-240	...	S40930	...	...
44	11Cr-Ti	Wld. tube	SA-268	TP409	S40900	...	...
45	11Cr-Ti	Smls. tube	SA-268	TP409	S40900	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	5B	1	60	30	1200	700	1200	NP	CS-2	T4
2	5B	1	60	30	1200	700	1200	NP	CS-2	T4
3	5B	1	60	30	1200	700	1200	NP	CS-2	T4
4	5B	1	60	30	NP	700	NP	NP	CS-2	G26, W10, W12
5	5B	1	60	36	1200	NP	1200	NP	CS-2	T4
6	5B	1	70	40	1200	700	1200	NP	CS-2	T3
7	5B	1	75	45	NP	700	1200	NP	CS-3	T3
8	5B	1	80	50	1200	NP	1200	NP	CS-3	T3
9	5B	1	90	60	1200	700	1200	NP	CS-3	G1, G17, T3
10	5B	1	90	60	NP	700	NP	NP	CS-3	G17
11	5B	1	90	65	1200	NP	1200	NP	CS-5	T3
12	5B	1	60	30	1200	NP	1200	NP	CS-2	T4
13	5B	1	60	30	1200	NP	1200	NP	CS-2	T4
14	5B	1	60	30	1200	NP	1200	NP	CS-2	T4
15	5B	1	60	30	1200	NP	1200	NP	CS-2	T4
16	5B	1	60	30	1200	700	1200	NP	CS-2	T5
17	5B	1	60	30	1200	NP	1200	NP	CS-2	T5
18	5B	1	60	30	1200	700	1200	NP	CS-2	T5
19	5B	1	60	30	1200	700	1200	NP	CS-2	T5
20	5B	1	85	55	1200	NP	1200	NP	CS-3	T4
21	5B	1	85	55	NP	NP	1200	NP	CS-3	T4
22	5B	1	90	60	1200	700 (SPT)	1200	NP	CS-3	G1, T4
23	5B	1	90	60	NP	700	NP	NP	CS-3	G17
24	15E	1	85	60	1200	700	1200	NP	CS-3	T6
25	15E	1	90	60	1200	NP	NP	NP	CS-3	T6
26	15E	1	85	60	1200	700	1200	NP	CS-3	T6
27	15E	1	85	60	1200	NP	1200	NP	CS-3	T6
28	15E	1	85	60	1200	NP	NP	NP	CS-3	T6
29	15E	1	85	60	1200	700	1200	NP	CS-3	T6
30	15E	1	85	60	1200	NP	1200	NP	CS-3	T6
31	15E	1	90	60	1200	700	1200	NP	CS-3	T6
32	15E	1	90	60	1200	NP	1200	NP	CS-3	T6
33	15E	1	90	60	1200	NP	1200	NP	CS-3	T6
34	15E	1	85	60	1200	NP	NP	NP	CS-3	T7
35	15E	1	90	60	1200	NP	NP	NP	CS-3	T6
36	15E	1	85	60	1200	NP	NP	NP	CS-3	T7
37	15E	1	85	60	1200	NP	NP	NP	CS-3	T7
38	15E	1	85	60	1200	NP	NP	NP	CS-3	T7
39	15E	1	90	60	1200	NP	NP	NP	CS-3	T6
40	15E	1	90	60	1200	NP	NP	NP	CS-3	T6
41	7	1	55	25	NP	NP	800	NP	CS-1	...
42	7	1	55	25	NP	NP	800	NP	CS-1	...
43	7	1	55	25	NP	NP	800	NP	CS-1	...
44	7	1	55	25	NP	NP	800	650	CS-1	G24
45	7	1	55	25	NP	NP	800	650	CS-1	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
2	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
3	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
4	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	...	...	...	...
5	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
6	20.0	...	20.0	...	19.4	19.2	19.2	18.9	18.6	18.2	17.6	17.0	14.3	10.9
7	21.4	...	21.4	...	20.8	20.6	20.5	20.2	19.9	19.5	18.9	18.2	14.3	10.9
8	22.9	...	22.8	...	22.1	22.0	21.9	21.6	21.3	20.8	20.2	19.1	14.3	10.9
9	25.7	...	25.7	...	24.9	24.7	24.6	24.3	23.9	23.4	22.7	19.1	14.3	10.9
10	25.7	...	25.7	...	24.9	24.7	24.6	24.3	23.9	23.4	...	...	...	...
11	25.7	...	25.7	...	24.9	24.7	24.6	24.3	23.9	23.4	22.7	19.1	14.3	10.9
12	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
13	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
14	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
15	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	10.9
16	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	13.0
17	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	13.0
18	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	13.0
19	17.1	...	17.1	...	16.6	16.5	16.4	16.2	15.9	15.6	15.1	14.5	13.8	13.0
20	24.3	...	24.2	...	23.5	23.4	23.3	22.9	22.6	22.1	21.4	20.6	19.6	16.4
21	24.3	...	24.2	...	23.5	23.4	23.3	22.9	22.6	22.1	21.4	20.6	19.6	16.4
22	25.7	...	25.7	...	24.9	24.7	24.6	24.3	23.9	23.4	22.7	21.8	20.8	16.4
23	25.7	...	25.7	...	24.9	24.7	24.6	24.3	23.9	23.4	...	...	...	...
24	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
25	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
26	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
27	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
28	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
29	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
30	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
31	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
32	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
33	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
34	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
35	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
36	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
37	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
38	24.3	...	24.3	...	24.3	24.2	24.1	23.7	23.4	22.9	22.2	21.3	20.3	19.1
39	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
40	25.7	...	25.7	...	25.7	25.6	25.5	25.1	24.7	24.2	23.5	22.6	21.5	20.2
41	15.7	...	14.5	...	13.1	12.1	11.6	11.3	11.3	11.3	11.2	11.1	...	...
42	15.7	...	14.5	...	13.1	12.1	11.6	11.3	11.3	11.3	11.2	11.1	...	...
43	15.7	...	14.5	...	13.1	12.1	11.6	11.3	11.3	11.3	11.2	11.1	...	...
44	13.4	...	12.3	...	11.1	10.3	9.9	9.6	9.6	9.6	9.5	9.4	...	...
45	15.7	...	14.5	...	13.1	12.1	11.6	11.3	11.3	11.3	11.2	11.1	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
2	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
3	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
6	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
7	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
8	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
9	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
12	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
13	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
14	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
15	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
16	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
17	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
18	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
19	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
20	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
21	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
22	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
25	18.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
26	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
27	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
28	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
29	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
30	17.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
31	18.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
32	18.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
33	18.8	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...	...	...	...
34	17.8	16.3	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
35	18.8	16.7	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
36	17.8	16.3	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
37	17.8	16.3	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
38	17.8	16.3	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
39	18.8	16.7	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
40	18.8	16.7	12.6	9.1	6.1	3.7	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	12Cr	Plate	SA-1010	40	S41003	...	$t \leq \frac{3}{4}$
2	12Cr	Bar	SA-479	403	S40300	A	...
3	12Cr	Bar	SA-479	403	S40300	1	...
4	12Cr	Plate	SA-1010	50	S41003	...	$t \leq \frac{3}{4}$
5	12Cr-Al	Plate	SA-240	405	S40500	...	...
6	12Cr-Al	Plate	SA-240	405	S40500	...	...
7	12Cr-Al	Bar	SA-479	405	S40500	...	...
8	12Cr-Al	Bar	SA/JIS G4303	SUS405	...	...	...
9	12Cr-Al	Smls. & wld. tube	SA-268	TP405	S40500	...	...
(25) 10	12Cr-Al	Wld. tube	SA-268	TP405	S40500	...	...
11	12Cr-Ti	Wld. tube	SA-268	...	S40800	...	...
12	12Cr-Ti	Smls. tube	SA-268	...	S40800	...	...
13	13Cr	Plate	SA-240	410S	S41008	...	...
14	13Cr	Smls. & wld. tube	SA-268	TP410	S41000	...	...
(25) 15	13Cr	Wld. tube	SA-268	TP410	S41000	...	...
16	13Cr	Plate	SA-240	410	S41000	...	...
17	13Cr	Forgings	SA-182	F6a	S41000	1	...
18	13Cr	Bar	SA-479	410	S41000	...	...
19	13Cr	Bar	SA-479	410	S41000	A	...
20	13Cr	Bar	SA-479	410	S41000	1	...
21	13Cr	Forgings	SA-182	F6a	S41000	2	...
22	13Cr	Castings	SA-217	CA15	J91150	...	...
23	13Cr	Cast pipe	SA-426	CPCA15	J91150	...	...
(25) 24	13Cr	Bar	SA/EN 10088-3	X12Cr13	...	QT650	$t \leq 6.25$
25	13Cr-4Ni	Castings	SA-487	CA6NM	J91540	A	...
26	13Cr-4Ni	Forgings	SA-182	F6NM	S41500	...	...
(25) 27	15Cr	Wld. tube	SA-268	TP429	S42900	...	...
28	15Cr	Smls. & wld. tube	SA-268	TP429	S42900	...	...
29	15Cr	Plate	SA-240	429	S42900	...	...
(25) 30	17Cr	Wld. tube	SA-268	TP430	S43000	...	...
31	17Cr	Smls. & wld. tube	SA-268	TP430	S43000	...	...
32	17Cr	Plate	SA-240	430	S43000	...	...
33	17Cr	Bar	SA-479	430	S43000	...	...
34	17Cr-4Ni-3Cu	Castings	SA-747	CB7Cu-1	J92180	...	...
35	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1150	...
(25) 36	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1150	...
(25) 37	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1150	...
38	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1100	...
(25) 39	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1100	...
(25) 40	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1100	...
41	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1075	...
(25) 42	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1075	...
(25) 43	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1075	...
44	18Cr-2Mo	Plate	SA-240	...	S44400	...	...
45	18Cr-2Mo	Wld. tube	SA-268	...	S44400	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	7	1	66	40	NP	NP	600	600	CS-2	...
2	6	1	70	40	NP	700	NP	NP	...	...
3	6	1	70	40	NP	700	NP	NP	...	...
4	7	1	70	50	NP	NP	600	600	CS-3	...
5	7	1	60	25	700	NP	1000	650	CS-1	G19, T5
6	7	1	60	25	NP	700	NP	NP	CS-1	G19
7	7	1	60	25	NP	700	1000	650	CS-1	G19, T5
8	7	1	60	25	NP	700	1000	NP	CS-1	G19, T5
9	7	1	60	30	700	NP	1000	650	CS-2	G19, T5, W13, W14
10	7	1	60	30	700	NP	1000	650	CS-2	G19, G24, T5
11	7	1	55	30	NP	NP	800	650	CS-2	G19, W14
12	7	1	55	30	NP	NP	800	650	CS-2	G19
13	7	1	60	30	NP	700	1200	650	CS-2	T4
14	6	1	60	30	700	NP	1200	650	CS-2	T4, W13, W14
15	6	1	60	30	700	NP	1200	650	CS-2	G24, T4
16	6	1	65	30	NP	NP	1200	650	CS-2	T4
17	6	1	70	40	NP	700	1000	650	CS-2	T4
18	6	1	70	40	NP	NP	1000	650	CS-2	G22, T4
19	6	1	70	40	NP	700	NP	NP	CS-2	...
20	6	1	70	40	700	700	NP	NP	CS-2	...
21	6	3	85	55	NP	700	1200	650	CS-3	T3
22	6	3	90	65	NP	700	1200	650	CS-5	G1, G17, T3
23	6	3	90	65	NP	700	NP	NP	CS-5	G17
24	...	...	94.5	65.5	NP	700 (SPT)	NP	NP	...	W1
25	6	4	110	80	NP	700	800	650	CS-5	G1, G17
26	6	4	115	90	NP	700	NP	NP	CS-3	G17
27	6	2	60	35	700	NP	700	650	CS-2	G19, G24, W14
28	6	2	60	35	700	NP	1200	650	CS-2	G19, T4, W13, W14
29	6	2	65	30	NP	NP	1200	650	CS-2	G19, T4
30	7	2	60	35	700	NP	1200	650	CS-2	G19, G24, T4
31	7	2	60	35	700	700	1200	650	CS-2	G19, T4, W12, W13, W14
32	7	2	65	30	NP	NP	1200	650	CS-2	G19, T4
33	7	2	70	40	700	700	1000	650	CS-2	G19, G22, T4
34	...	...	150	140	NP	NP	200	NP	HT-1	G1, G28, W1
35	...	...	135	105	NP	650	650	NP	HT-1	G8, G19, W1
36	...	...	135	105	NP	650	650	NP	HT-1	G19, W2
37	...	...	135	105	NP	650	650	NP	HT-1	G19, W2
38	...	...	140	115	NP	650	650	NP	HT-1	G8, G19, W1
39	...	...	140	115	NP	650	650	NP	HT-1	G19, W2
40	...	...	140	115	NP	650	650	NP	HT-1	G19, W2
41	...	...	145	125	NP	650	NP	NP	HT-1	G19, W1
42	...	...	145	125	NP	650	650	NP	HT-1	G19, W2
43	...	...	145	125	NP	650	650	NP	HT-1	G19, W2
44	7	2	60	40	NP	NP	650	650	CS-2	G19
45	7	2	60	40	NP	NP	650	650	CS-2	G19, G24

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	18.9	...	18.9	...	18.9	18.4	17.7	17.1	...	...	...	...	...	...
2	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	...	...	...	...
3	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	...	...	...	...
4	20.0	...	20.0	...	20.0	19.5	18.8	18.1	...	...	...	...	...	...
5	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	13.1	12.6	12.0	11.3
6	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	...	...	...	...
7	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	13.1	12.6	12.0	11.3
8	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	13.1	12.6	12.0	11.3
9	17.1	...	17.1	...	16.8	16.5	16.3	15.9	15.6	15.2	14.7	14.1	13.4	12.6
10	14.6	...	14.6	...	14.3	14.0	13.8	13.5	13.2	12.9	12.5	12.0	11.4	10.7
11	13.4	...	13.4	...	13.1	12.9	12.7	12.4	12.1	11.8	11.4	11.0	...	...
12	15.7	...	15.7	...	15.4	15.1	14.9	14.5	14.3	13.9	13.5	12.9	...	...
13	17.1	...	17.1	...	16.8	16.5	16.3	15.9	15.6	15.2	14.7	14.1	13.4	12.3
14	17.1	...	17.1	...	16.8	16.5	16.3	15.9	15.6	15.2	14.7	14.1	13.4	12.3
15	14.6	...	14.6	...	14.3	14.0	13.8	13.5	13.2	12.9	12.5	12.0	11.4	10.5
16	18.6	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	14.4	12.3
17	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	17.1	16.4	15.6	12.3
18	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	17.1	16.4	15.6	12.3
19	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	...	...	...	...
20	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	...	...	...	...
21	24.3	...	24.3	...	23.8	23.4	23.0	22.5	22.0	21.5	20.8	19.9	17.2	12.3
22	25.7	...	25.7	...	25.2	24.8	24.4	23.8	23.3	22.7	22.0	21.1	15.9	11.0
23	25.7	...	25.7	...	25.2	24.8	24.4	23.8	23.3	22.7	...	...	...	...
24	26.9	...	26.9	...	26.4	25.9	25.5	24.9	24.5	23.8	...	...	...	...
25	31.4	...	31.4	31.3	30.8	30.1	29.4	28.8	28.4	27.9	27.4	26.7	...	...
26	32.9	...	32.9	...	32.9	32.5	31.3	30.0	29.4	28.7	...	...	...	...
27	14.6	...	14.6	...	14.3	14.0	13.8	13.5	13.2	12.9	...	...	...	...
28	17.1	...	17.1	...	16.8	16.5	16.3	15.9	15.6	15.2	14.7	14.1	13.4	12.0
29	18.6	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	14.4	12.0
30	14.6	...	14.6	...	14.3	14.0	13.8	13.5	13.2	12.9	12.5	12.0	11.4	10.2
31	17.1	...	17.1	...	16.8	16.5	16.3	15.9	15.6	15.2	14.7	14.1	13.4	12.0
32	18.6	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	14.4	12.0
33	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	17.1	16.4	15.6	12.0
34	32.0	...	32.0	...	...	...	...	...	...	...	...	...	...	...
35	38.6	...	38.6	...	38.6	37.5	36.8	36.2	35.9	...	...	...	...	...
36	38.6	...	38.6	...	38.6	37.5	36.8	36.2	35.9	...	...	...	...	...
37	38.6	...	38.6	...	38.6	37.5	36.8	36.2	35.9	...	...	...	...	...
38	40.0	...	40.0	...	40.0	38.9	38.1	37.5	37.2	...	...	...	...	...
39	40.0	...	40.0	...	40.0	38.9	38.1	37.5	37.2	...	...	...	...	...
40	40.0	...	40.0	...	40.0	38.9	38.1	37.5	37.2	...	...	...	...	...
41	41.4	...	41.4	...	41.4	40.3	39.5	38.9	38.5	...	...	...	...	...
42	41.4	...	41.4	...	41.4	40.3	39.5	38.9	38.5	...	...	...	...	...
43	41.4	...	41.4	...	41.4	40.3	39.5	38.9	38.5	...	...	...	...	...
44	17.1	...	17.1	...	16.6	16.2	15.9	15.4	15.1	...	...	...	...	...
45	14.6	...	14.6	...	14.1	13.8	13.5	13.1	12.8	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	8.4	4.0	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	8.4	4.0	...	...	...	...	...	...	...	...	...	...	...	...	...
8	8.4	4.0	...	...	...	...	...	...	...	...	...	...	...	...	...
9	8.4	4.0	...	...	...	...	...	...	...	...	...	...	...	...	...
10	7.1	3.4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
14	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
15	7.5	5.4	3.7	2.5	1.5	0.85	...	...	...	...	...	...	...	...	(25)
16	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
17	8.8	6.4	...	...	...	...	...	...	...	...	...	...	...	...	...
18	8.8	6.4	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...	...	...	...
22	7.6	5.0	3.3	2.2	1.5	1.0	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...	...	...	...
29	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...	...	...	...
30	7.8	5.5	3.8	2.7	2.0	1.5	...	...	...	...	...	...	...	...	(25)
31	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...	...	...	...
32	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...	...	...	...
33	9.2	6.5	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-2Mo	Smls. tube	SA-268	...	S44400	...	...
2	18Cr-Ti	Plate	SA-240	...	S43932	...	...
3	18Cr-Ti	Wld. tube	SA-268	TP439	S43035	...	...
4	18Cr-Ti	Smls. tube	SA-268	TP439	S43035	...	...
(25) 5	...	...	...	...	...	...	...
(25) 6	...	...	...	...	...	...	...
7	18Cr-Ti	Wld. tube	SA-803	TP439	S43035	...	...
8	18Cr-Ti	Smls. tube	SA-268	TP430 Ti	S43036	...	...
9	18Cr-Ti	Wld. tube	SA-268	TP430 Ti	S43036	...	...
10	18Cr-Ti	Bar	SA-479	439	S43035	...	...
11	26Cr-3Ni-3Mo	Plate	SA-240	26-3-3	S44660	...	$\leq \frac{2}{10}$
12	26Cr-3Ni-3Mo	Smls. tube	SA-268	26-3-3	S44660	...	$\leq \frac{2}{10}$
13	26Cr-3Ni-3Mo	Wld. tube	SA-268	26-3-3	S44660	...	$\leq \frac{2}{10}$
14	26Cr-3Ni-3Mo	Wld. tube	SA-268	26-3-3	S44660	...	$\leq \frac{2}{10}$
15	26Cr-3Ni-3Mo	Wld. tube	SA-803	26-3-3	S44660	...	$\leq \frac{2}{10}$
16	27Cr	Smls. tube	SA-268	TP446-1	S44600	...	...
17	27Cr-1Mo	Forgings	SA-182	FXM-27Cb	S44627	...	...
18	27Cr-1Mo	Plate	SA-240	XM-27	S44627	...	...
19	27Cr-1Mo	Wld. tube	SA-268	TPXM-27	S44627	...	...
20	27Cr-1Mo	Smls. tube	SA-268	TPXM-27	S44627	...	...
21	27Cr-1Mo	Bar	SA-479	XM-27	S44627	...	...
(25) 22	...	...	...	...	...	...	...
(25) 23	...	...	...	...	...	...	...
(25) 24	...	...	...	...	...	...	...
(25) 25	...	...	...	...	...	...	...
26	27Cr-1Mo-Ti	Plate	SA-240	XM-33	S44626	...	...
27	27Cr-1Mo-Ti	Smls. tube	SA-268	TPXM-33	S44626	...	...
28	27Cr-1Mo-Ti	Wld. tube	SA-268	TPXM-33	S44626	...	...
29	29Cr-4Mo	Bar	SA-479	...	S44700	...	...
30	29Cr-4Mo	Plate	SA-240	...	S44700	...	...
31	29Cr-4Mo	Smls. tube	SA-268	29-4	S44700	...	...
32	29Cr-4Mo	Wld. tube	SA-268	29-4	S44700	...	...
33	29Cr-4Mo-2Ni	Bar	SA-479	...	S44800	...	...
34	29Cr-4Mo-2Ni	Plate	SA-240	...	S44800	...	...
35	29Cr-4Mo-2Ni	Smls. tube	SA-268	29-4-2	S44800	...	...
36	29Cr-4Mo-2Ni	Wld. tube	SA-268	29-4-2	S44800	...	...
37	29Cr-4Mo-Ti	Smls. tube	SA-268	...	S44735	...	...
38	29Cr-4Mo-Ti	Wld. tube	SA-268	...	S44735	...	...
39	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	...	...
40	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2	J13005	A	...
41	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2	J13005	B	...
42	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	A	K12021	...	...
43	Mn- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	H75	K12021	...	...
44	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	B	K12022	...	...
45	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	1	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature											
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes	
					(NP = Not Permitted)						
					(SPT = Supports Only)						
					I	III	VIII-1	XII			
1	7	2	60	40	NP	NP	650	650	CS-2	G19	
2	7	2	60	30	NP	NP	600	600	CS-2	G19	
3	7	2	60	30	800	NP	800	650	CS-2	G19, G24	
4	7	2	60	30	800	NP	800	650	CS-2	G19	
5	...	...	...	...	...	...	...	...	...	...	
6	...	...	...	...	...	...	...	...	...	...	
7	7	2	60	30	NP	NP	600	600	CS-2	G19, G24	
8	7	2	60	35	NP	NP	800	NP	CS-2	G19	
9	7	2	60	35	NP	NP	800	NP	CS-2	G19, G24	
10	7	2	70	40	NP	NP	1000	650	CS-2	G19, G22, T4	
11	10K	1	85	65	NP	NP	700	650	HA-5	G19	
12	10K	1	85	65	NP	700	700	650	HA-5	G19, H5	
13	10K	1	85	65	NP	700	NP	NP	HA-5	G19, H5, W12	
14	10K	1	85	65	NP	NP	700	650	HA-5	G19, G24	
15	10K	1	85	65	NP	NP	600	600	HA-5	G19, G24	
16	10I	1	70	40	700	NP	650	650	CS-2	G19	
17	10I	1	60	35	NP	NP	650	650	HA-2	G19	
18	10I	1	65	40	NP	650	650	650	HA-2	G19	
19	10I	1	65	40	NP	NP	650	650	HA-2	G19, G24	
20	10I	1	65	40	NP	650	650	650	HA-2	G19	
21	10I	1	65	40	NP	700	650	650	HA-2	G19, G22	
22	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	
26	10I	1	68	45	NP	NP	650	650	HA-6	G19	
27	10I	1	68	45	NP	NP	650	650	HA-6	G19	
28	10I	1	68	45	NP	NP	650	650	HA-6	G19, G24	
29	10J	1	70	55	NP	NP	600	600	HA-6	G19, G22	
30	10J	1	80	60	NP	NP	600	600	HA-6	G19	
31	10J	1	80	60	NP	NP	600	600	HA-6	G19	
32	10J	1	80	60	NP	NP	600	600	HA-6	G19, G24	
33	10K	1	70	55	NP	NP	600	600	HA-6	G19, G22	
34	10K	1	80	60	NP	NP	600	600	HA-6	G19	
35	10K	1	80	60	NP	NP	600	600	HA-6	G19	
36	10K	1	80	60	NP	NP	600	600	HA-6	G19, G24	
37	10J	1	75	60	NP	NP	600	600	HA-6	G19	
38	10J	1	75	60	NP	NP	600	600	HA-6	G19, G24	
39	...	...	105	65	NP	650	650	650	CS-5	G25, W2, W11	
40	3	3	85	53	NP	700 (SPT)	650	650	CS-3	G1	
41	3	3	90	65	NP	NP	650	650	CS-5	G1	
42	3	2	75	45	1000	700	1000	650	CS-3	G11, S2, T3	
43	3	2	75	45	NP	700	NP	NP	CS-3	S6, W10, W12	
44	3	3	80	50	1000	700	1000	650	CS-3	G11, S2, T3	
45	3	3	80	50	NP	700	1000	NP	CS-5	G23, T4	

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.1	...	17.1	...	16.6	16.2	15.9	15.4	15.1	...	...	...	...	...
2	17.1	...	17.1	...	15.7	14.6	13.9	13.6	...	...	...	...	...	...
3	14.6	...	14.6	...	13.3	12.4	11.8	11.6	11.5	11.5	11.4	11.2	...	...
4	17.1	...	17.1	...	15.7	14.6	13.9	13.6	13.6	13.5	13.4	13.2	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	14.6	...	14.6	...	13.3	12.4	11.8	11.6	...	...	...	...	...	...
8	17.1	...	17.1	...	16.6	16.1	15.8	15.4	15.1	14.8	14.5	14.0	...	...
9	14.6	...	14.6	...	14.1	13.7	13.4	13.1	12.9	12.6	12.3	11.9	...	...
10	20.0	...	20.0	...	19.3	18.8	18.4	17.9	17.7	17.3	16.9	16.4	15.8	12.2
11	24.3	...	24.3	...	24.2	23.9	23.8	23.6	23.5	23.4	...	...	...	...
12	24.3	...	24.3	...	24.2	23.9	23.8	23.6	23.5	23.4	...	...	...	...
13	24.3	...	24.3	...	24.2	23.9	23.8	23.6	23.5	23.4	...	...	...	...
14	20.6	...	20.6	...	20.6	20.3	20.2	20.1	20.0	19.9	...	...	...	...
15	20.6	...	20.6	...	20.6	20.3	20.2	20.1	...	...	...	...	...	...
16	20.0	...	20.0	...	19.3	18.8	18.4	17.9	17.7	17.3	...	...	...	...
17	17.1	...	17.1	...	16.6	16.1	16.1	16.1	16.1	...	...	...	...	...
18	18.6	...	18.6	...	18.3	18.1	18.1	18.1	18.1	...	...	...	...	...
19	15.8	...	15.8	...	15.5	15.4	15.4	15.4	15.4	...	...	...	...	...
20	18.6	...	18.6	...	18.3	18.1	18.1	18.1	18.1	...	...	...	...	...
21	18.6	...	18.6	...	18.3	18.1	18.1	18.1	18.1	18.1	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	19.4	...	19.4	...	19.3	19.0	18.8	18.4	18.1	...	...	...	...	...
27	19.4	...	19.4	...	19.3	19.0	18.8	18.4	18.1	...	...	...	...	...
28	16.5	...	16.5	...	16.4	16.2	16.0	15.7	15.4	...	...	...	...	...
29	20.0	...	20.0	...	19.3	19.2	19.2	19.2	...	...	...	...	...	...
30	22.9	...	22.8	...	22.1	21.9	21.9	21.9	...	...	...	...	...	...
31	22.9	...	22.8	...	22.1	21.9	21.9	21.9	...	...	...	...	...	...
32	19.4	...	19.4	...	18.8	18.6	18.6	18.6	...	...	...	...	...	...
33	20.0	...	19.6	...	19.3	19.2	18.9	18.6	...	...	...	...	...	...
34	22.9	...	22.4	...	22.1	21.9	21.6	21.3	...	...	...	...	...	...
35	22.9	...	22.4	...	22.1	21.9	21.6	21.3	...	...	...	...	...	...
36	19.4	...	19.1	...	18.8	18.6	18.4	18.1	...	...	...	...	...	...
37	21.4	...	21.0	...	20.7	20.5	20.3	20.0	...	...	...	...	...	...
38	18.2	...	17.9	...	17.6	17.5	17.2	17.0	...	...	...	...	...	...
39	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...	...
40	24.3	...	24.3	...	24.3	24.2	24.2	24.2	24.1	24.1	...	...	...	...
41	25.7	...	25.7	...	25.7	25.6	25.6	25.6	25.6	...	...	...	...	...
42	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	21.4	21.4	20.0	13.7
43	21.4	...	21.4	...	21.4	21.4	21.4	21.4	21.4	21.4	...	...	...	...
44	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	20.0	13.7
45	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.1	13.3

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	9.2	6.5	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
45	10.0	6.3	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	2	...
2	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	3	...
3	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	1	...
4	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	2	...
5	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	3	...
6	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-302	C	K12039	...	...
7	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	1	...
8	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	H80	K12039	...	...
9	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J80	K12539	...	...
10	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	2	...
11	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J90	K12539	...	...
12	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	3	...
13	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J100	K12539	...	...
14	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-302	D	K12054	...	...
15	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	1	...
16	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	1	...
17	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	2	...
18	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	2	...
19	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	3	...
20	Mn- $\frac{1}{2}$ Ni-V	Plate	SA-225	C	K12524	...	...
21	Mn-V	Castings	SA-487	1	J13002	A	...
22	Mn-V	Castings	SA-487	1	J13002	A	...
23	Mn-V	Castings	SA-487	1	J13002	B	...
24	1 $\frac{1}{2}$ Si- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P15	K11578	...	...
25	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	A	...
26	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	B	...
27	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	E	...
28	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	1	...
29	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	2	...
30	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$2\frac{1}{2} < t \leq 4$
31	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Plate	SA-517	F	K11576	...	$\leq 2\frac{1}{2}$
32	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$\leq 2\frac{1}{2}$
33	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Smls. & wld. tube	SA-423	2	K11540	...	...
34	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Wld. tube	SA-423	2	K11540	...	...
35	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	1	...
36	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	1	...
37	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	2	...
38	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	2	...
39	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	1	...
40	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	2	...
41	$\frac{3}{4}$ Ni-1Mo- $\frac{3}{4}$ Cr	Castings	SA-217	WC5	J22000	...	...
42	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC4	J12082	...	...
43	1 $\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$2\frac{1}{2} < t \leq 4$
44	1 $\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$\leq 2\frac{1}{2}$
45	1 $\frac{1}{2}$ Ni	Forgings	SA-350	LF5	K13050	1	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	3	3	90	70	NP	700	800	NP	CS-5	...
2	11A	4	100	83	NP	700	NP	NP	CS-5	...
3	3	3	80	50	NP	700	NP	NP	CS-5	...
4	3	3	90	70	NP	700	800	NP	CS-5	...
5	11A	4	100	83	NP	700	750	650	CS-5	...
6	3	3	80	50	1000	700	1000	650	CS-3	G11, S2, T3
7	3	3	80	50	NP	700	800	NP	CS-5	G23
8	3	3	80	50	NP	700	NP	NP	CS-3	G26, W10, W12
9	3	3	80	50	NP	700	NP	NP	CS-5	G26, W10, W12
10	3	3	90	70	NP	700	800	NP	CS-5	...
11	3	3	90	70	NP	700	NP	NP	CS-5	G26, W10, W12
12	11A	4	100	83	NP	700	750	650	CS-5	...
13	11A	4	100	83	NP	700	NP	NP	CS-5	G26, W10, W12
14	3	3	80	50	1000	700	1000	650	CS-3	G11, S2, T3
15	3	3	80	50	NP	700	800	NP	CS-5	G23
16	3	3	80	50	NP	NP	800	NP	CS-5	G23
17	3	3	90	70	NP	700	800	NP	CS-5	...
18	3	3	90	70	NP	NP	800	NP	CS-5	...
19	11A	4	100	83	NP	700	NP	NP	CS-5	...
20	10A	1	105	70	NP	NP	700	650	CS-5	...
21	10A	1	85	55	NP	700 (SPT)	NP	NP	CS-3	...
22	10A	1	85	55	NP	NP	650	650	CS-3	G1
23	10A	1	90	65	NP	NP	650	650	CS-5	G1
24	3	1	60	30	NP	NP	1000	650	CS-2	T3
25	3	3	90	60	NP	650	650	650	CS-3	G1
26	11A	3	105	85	NP	NP	700	650	CS-5	G1
27	11A	3	115	95	NP	NP	700	650	CS-5	G1
28	3	3	80	50	NP	700	800	650	CS-5	G23
29	3	3	90	65	NP	700	700	NP	CS-5	...
30	11B	3	105	90	NP	650 (SPT)	650	650	CS-5	S7
31	11B	3	115	100	NP	650 (SPT)	650	650	HT-1	...
32	11B	3	115	100	NP	NP	650	650	HT-1	...
33	4	2	60	37	650	NP	650	NP	CS-2	W13, W14
34	4	2	60	37	650	NP	650	NP	CS-2	G24
35	3	3	80	50	NP	700	800	650	CS-5	G23
36	3	3	80	50	NP	700	800	650	CS-5	G23
37	3	3	90	65	NP	700	700	NP	CS-5	...
38	3	3	90	65	NP	700	700	NP	CS-5	...
39	3	3	80	50	NP	700	800	650	CS-5	G23
40	3	3	90	65	NP	700	700	NP	CS-5	...
41	4	1	70	40	1100	700	1100	NP	CS-2	G1, G17, T4
42	4	1	70	40	1000	700	1000	NP	CS-2	G1, G17, T4
43	11B	8	105	90	NP	700 (SPT)	650	650	CS-5	...
44	11B	8	115	100	NP	650 (SPT)	650	650	HT-1	...
45	9A	1	60	30	NP	NP	500	500	CS-2	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...
2	28.6	...	28.6	...	28.6	28.6	28.6	28.6	28.6	28.6	...	...	...	...
3	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	...	...	...	...
4	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...
5	28.6	...	28.6	28.6	28.6	28.6	28.6	28.6	28.6	28.6	28.6	...	...	...
6	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	20.0	13.7
7	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
8	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	...	...	...	...
9	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	...	...	...	...
10	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...
11	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...
12	28.6	...	28.6	28.6	28.6	28.6	28.6	28.6	28.6	28.6	28.6	...	...	...
13	28.6	...	28.6	...	28.6	28.6	28.6	28.6	28.6	28.6	...	...	...	...
14	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	20.0	13.7
15	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
16	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
17	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...
18	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...
19	28.6	...	28.6	...	28.6	28.6	28.6	28.6	28.6	28.6	...	...	...	...
20	30.0	30.0	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
21	24.3	...	23.0	...	22.4	22.4	22.4	21.9	21.5	20.9	...	...	...	...
22	24.3	...	23.1	...	22.5	22.5	22.5	21.9	21.5	...	...	...	...	...
23	25.7	...	24.6	...	24.2	24.1	24.1	23.9	23.4	...	...	...	...	...
24	17.1	17.1	17.1	...	17.1	17.1	17.1	16.8	16.6	16.3	15.9	15.4	13.8	12.5
25	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...	...
26	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
27	32.9	32.9	32.9	32.9	32.9	32.9	32.9	32.9	32.9	32.9	...	...	...	...
28	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
29	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...
30	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	...	...	...	...	...
31	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...
32	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...
33	17.1	...	17.1	...	17.1	17.1	17.1	17.1	17.1	...	...	...	...	...
34	14.6	...	14.6	...	14.6	14.6	14.6	14.6	14.6	...	...	...	...	...
35	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
36	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
37	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...
38	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...
39	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	22.9	22.9	22.9	22.9	...	...
40	25.7	...	25.7	...	25.7	25.7	25.7	25.7	25.7	25.7	...	...	...	...
41	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	16.3
42	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	15.0
43	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.4	...	...	...	...
44	32.9	...	32.9	32.9	32.9	32.9	32.9	32.9	32.8	...	...	...	...	...
45	17.1	...	16.5	...	15.7	15.3	15.3	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	8.2	4.8	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	10.0	6.3	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	11.0	6.9	4.6	2.8	...	...	...	...	...	...	...	...	...	...	...
42	9.2	5.9	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	1½Ni	Forgings	SA-350	LF5	K13050	2	...
2	1¾Ni-¾Cr-Mo	Forgings	SA-372	L	K24055	...	...
3	2Ni-1Cu	Forgings	SA-182	FR	K22035	...	...
4	2Ni-1Cu	Fittings	SA-234	WPR	K22035	...	...
5	2Ni-1Cu	Pipe	SA-333	9	K22035	...	...
6	2Ni-1Cu	Smls. pipe	SA-333	9	K22035	...	...
7	2Ni-1Cu	Wld. pipe	SA-333	9	K22035	...	...
8	2Ni-1Cu	Tube	SA-334	9	K22035	...	...
9	2Ni-1Cu	Forgings	SA-350	LF9	K22036	...	...
10	2Ni-1Cu	Smls. & wld. fittings	SA-420	WPL9	K22035	...	...
(25) 11	2Ni-1½Cr-¼Mo-V	Forgings	SA-372	N	K23550	100	...
12	2Ni-1½Cr-¼Mo-V	Forgings	SA-723	1	K23550	1	...
(25) 13	2Ni-1½Cr-¼Mo-V	Forgings	SA-372	N	K23550	120	...
14	2Ni-1½Cr-¼Mo-V	Forgings	SA-723	1	K23550	2	...
15	2Ni-1½Cr-¼Mo-V	Forgings	SA-723	1	K23550	3	...
16	2Ni-1½Cr-¼Mo-V	Forgings	SA-723	1	K23550	4	...
17	2Ni-1½Cr-¼Mo-V	Forgings	SA-723	1	K23550	5	...
18	2½Ni	Pipe	SA-333	7	K21903	...	...
19	2½Ni	Wld. pipe	SA-333	7	K21903	...	...
20	2½Ni	Tube	SA-334	7	K21903	...	...
21	2½Ni	Wld. tube	SA-334	7	K21903	...	...
22	2½Ni	Plate	SA-203	A	K21703	...	...
23	2½Ni	Plate	SA-203	B	K22103	...	...
24	2½Ni	Castings	SA-352	LC2	J22500	...	...
25	2¾Ni-1½Cr-½Mo	Plate	SA-543	C	...	3	...
26	2¾Ni-1½Cr-½Mo	Plate	SA-543	C	...	1	...
27	2¾Ni-1½Cr-½Mo	Plate	SA-543	C	...	2	...
(25) 28	2¾Ni-1½Cr-½Mo-V	Forgings	SA-372	P	K34035	100	...
29	2¾Ni-1½Cr-½Mo-V	Forgings	SA-723	2	K34035	1	...
(25) 30	2¾Ni-1½Cr-½Mo-V	Forgings	SA-372	P	K34035	120	...
31	2¾Ni-1½Cr-½Mo-V	Forgings	SA-723	2	K34035	2	...
32	2¾Ni-1½Cr-½Mo-V	Forgings	SA-723	2	K34035	3	...
33	2¾Ni-1½Cr-½Mo-V	Forgings	SA-723	2	K34035	4	...
34	2¾Ni-1½Cr-½Mo-V	Forgings	SA-723	2	K34035	5	...
35	3Ni-1¾Cr-½Mo	Plate	SA-543	B	K42339	3	...
36	3Ni-1¾Cr-½Mo	Forgings	SA-372	M	K42365	85	...
37	3Ni-1¾Cr-½Mo	Plate	SA-543	B	K42339	1	...
38	3Ni-1¾Cr-½Mo	Plate	SA-543	B	K42339	2	...
39	3Ni-1¾Cr-½Mo	Forgings	SA-372	M	K42365	100	...
40	3½Ni	Pipe	SA-333	3	K31918	...	...
41	3½Ni	Wld. pipe	SA-333	3	K31918	...	...
42	3½Ni	Tube	SA-334	3	K31918	...	...
43	3½Ni	Wld. tube	SA-334	3	K31918	...	...
44	3½Ni	Fittings	SA-420	WPL3	...	...	...
45	3½Ni	Plate	SA-203	D	K31718	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	9A	1	70	37.5	NP	NP	500	500	CS-2	...
2	...	...	155	135	NP	NP	650	650	...	W11
3	9A	1	63	46	NP	NP	100	100	CS-3	...
4	9A	1	63	46	NP	NP	100	NP	CS-3	...
5	9A	1	63	46	NP	NP	100	100	CS-3	...
6	9A	1	63	46	NP	100	NP	NP	CS-3	...
7	9A	1	63	46	NP	NP	100	100	CS-3	G24
8	9A	1	63	46	NP	NP	100	100	CS-3	...
9	9A	1	63	46	NP	NP	100	100	CS-3	...
10	9A	1	63	46	NP	100	100	100	CS-3	W14
11	...	...	115	100	NP	NP	650	NP	HT-1	W1
12	...	...	115	100	NP	700 (SPT)	NP	NP	HT-1	W1
13	...	...	135	120	NP	NP	650	NP	HT-1	W1
14	...	...	135	120	NP	700 (SPT)	NP	NP	HT-1	W1
15	...	...	155	140	NP	700 (SPT)	NP	NP	HT-1	W1
16	...	...	175	160	NP	700 (SPT)	NP	NP	HT-1	W1
17	...	...	190	180	NP	700 (SPT)	NP	NP	HT-1	W1
18	9A	1	65	35	NP	NP	650	650	CS-2	...
19	9A	1	65	35	NP	NP	650	650	CS-2	G24
20	9A	1	65	35	NP	NP	650	650	CS-2	...
21	9A	1	65	35	NP	NP	650	650	CS-2	G24
22	9A	1	65	37	NP	700	1000	650	CS-2	T2
23	9A	1	70	40	NP	650	1000	650	CS-2	T2
24	9A	1	70	40	NP	100	650	650	CS-2	G1
25	3	3	90	70	NP	NP	650	NP	CS-5	...
26	11A	5	105	85	NP	NP	650	NP	CS-5	...
27	11B	10	115	100	NP	NP	650	NP	HT-1	...
28	...	...	115	100	NP	NP	650	NP	HT-1	W1
29	...	...	115	100	NP	700 (SPT)	NP	NP	HT-1	W1
30	...	...	135	120	NP	NP	650	NP	HT-1	W1
31	...	...	135	120	NP	700 (SPT)	NP	NP	HT-1	W1
32	...	...	155	140	NP	700 (SPT)	NP	NP	HT-1	W1
33	...	...	175	160	NP	700 (SPT)	NP	NP	HT-1	W1
34	...	...	190	180	NP	700 (SPT)	NP	NP	HT-1	W1
35	3	3	90	70	NP	NP	650	NP	CS-5	...
36	...	...	105	85	NP	NP	650	650	...	W11
37	11A	5	105	85	NP	NP	650	NP	CS-5	...
38	11B	10	115	100	NP	NP	650	NP	HT-1	...
39	...	...	120	100	NP	NP	650	650	...	W11
40	9B	1	65	35	NP	NP	650	650	CS-2	...
41	9B	1	65	35	NP	NP	650	650	CS-2	G24
42	9B	1	65	35	NP	NP	650	650	CS-2	...
43	9B	1	65	35	NP	NP	650	650	CS-2	G24
44	9B	1	65	35	NP	NP	650	650	CS-2	...
45	9B	1	65	37	NP	700	1000	650	CS-2	T2

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	19.2	...	18.3	17.8	17.8	...	...	...	...	...	...	...
2	44.3	...	44.3	...	44.3	44.3	44.3	44.1	42.9	...	...	...	...	...
3	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
4	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
5	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
6	17.9	...	...	...	...	...	...	...	...	...	...	...	...	...
7	15.3	...	...	...	...	...	...	...	...	...	...	...	...	...
8	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
9	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
10	18.1	...	...	...	...	...	...	...	...	...	...	...	...	...
11	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.4	...	...	...	...	...
12	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.4	31.6	...	...	...	...
13	38.6	...	38.6	...	38.6	38.6	38.6	38.6	38.0	...	...	...	...	...
14	38.6	...	38.6	...	38.6	38.6	38.6	38.6	38.0	37.1	...	...	...	...
15	44.3	...	44.3	...	44.3	44.3	44.3	44.3	43.6	42.6	...	...	...	...
16	50.0	...	50.0	...	50.0	50.0	50.0	50.0	49.2	48.0	...	...	...	...
17	54.3	...	54.3	...	54.3	54.3	54.3	54.3	53.5	52.2	...	...	...	...
18	18.6	18.6	18.6	...	18.6	18.6	18.6	17.5	16.7	...	...	...	...	...
19	15.8	...	15.8	...	15.8	15.8	15.8	14.9	14.2	...	...	...	...	...
20	18.6	18.6	18.6	...	18.6	18.6	18.6	17.5	16.7	...	...	...	...	...
21	15.8	15.8	15.8	...	15.8	15.8	15.8	14.9	14.2	...	...	...	...	...
22	18.6	18.6	18.6	...	18.6	18.6	18.6	18.5	17.6	16.6	13.9	11.4	9.0	6.5
23	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	19.0	18.0	14.8	12.0	9.3	6.5
24	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	19.0	...	...	...	...	...
25	25.7	...	25.7	25.7	25.7	25.5	25.3	25.0	24.6	...	...	...	...	...
26	30.0	...	30.0	30.0	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
27	32.9	...	32.9	32.9	32.9	32.5	32.3	31.9	31.5	...	...	...	...	...
28	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.4	...	...	...	...	...
29	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.4	31.6	...	...	...	...
30	38.6	...	38.6	...	38.6	38.6	38.6	38.6	38.0	...	...	...	...	...
31	38.6	...	38.6	...	38.6	38.6	38.6	38.6	38.0	37.1	...	...	...	...
32	44.3	...	44.3	...	44.3	44.3	44.3	44.3	43.6	42.6	...	...	...	...
33	50.0	...	50.0	...	50.0	50.0	50.0	50.0	49.2	48.0	...	...	...	...
34	54.3	...	54.3	...	54.3	54.3	54.3	54.3	53.5	52.2	...	...	...	...
35	25.7	...	25.7	25.7	25.7	25.5	25.3	25.0	24.6	...	...	...	...	...
36	30.0	...	30.0	30.0	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
37	30.0	...	30.0	30.0	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
38	32.9	...	32.9	32.9	32.9	32.5	32.3	31.9	31.5	...	...	...	...	...
39	34.3	...	34.3	34.3	34.3	33.9	33.7	33.3	32.9	...	...	...	...	...
40	18.6	18.6	18.6	...	18.6	18.6	18.6	17.5	16.7	...	...	...	...	...
41	15.8	...	15.8	...	15.8	15.8	15.8	14.9	14.2	...	...	...	...	...
42	18.6	18.6	18.6	...	18.6	18.6	18.6	17.5	16.7	...	...	...	...	...
43	15.8	15.8	15.8	...	15.8	15.8	15.8	14.9	14.2	...	...	...	...	...
44	18.6	18.6	18.6	...	18.6	18.6	18.6	17.5	16.7	...	...	...	...	...
45	18.6	18.6	18.6	...	18.6	18.6	18.6	18.5	17.6	16.6	13.9	11.4	9.0	6.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	4.5	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
23	4.5	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	4.5	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	3½Ni	Forgings	SA-350	LF3	K32025	1	...
2	3½Ni	Forgings	SA-350	LF3	K32025	2	...
3	3½Ni	Forgings	SA-765	III	K32026	...	...
4	3½Ni	Plate	SA-203	E	K32018	...	...
5	3½Ni	Plate	SA-203	E	K32018	...	...
6	3½Ni	Castings	SA-352	LC3	J31550	...	...
7	3½Ni	Plate	SA-203	F	...	...	>2
8	3½Ni	Plate	SA-203	F	...	...	≤2
9	3½Ni-1¾Cr-½Mo-V	Forgings	SA-508	4N	K22375	3	...
10	3½Ni-1¾Cr-½Mo-V	Forgings	SA-508	4N	K22375	1	...
11	3½Ni-1¾Cr-½Mo-V	Forgings	SA-508	4N	K22375	2	...
12	4Ni-1½Cr-½Mo-V	Forgings	SA-723	3	K44045	1	...
13	4Ni-1½Cr-½Mo-V	Forgings	SA-723	3	K44045	2	...
14	4Ni-1½Cr-½Mo-V	Forgings	SA-723	3	K44045	3	...
15	4Ni-1½Cr-½Mo-V	Forgings	SA-723	3	K44045	4	...
16	4Ni-1½Cr-½Mo-V	Forgings	SA-723	3	K44045	5	...
17	5Ni-¼Mo	Plate	SA-645	A	K41583	...	...
18	7Ni	Plate	SA-553	III	K61365	...	≤2
19	7Ni	Plate	SA-553	III	K61365	...	≤2
20	8Ni	Forgings	SA-522	II	K71340	...	...
21	8Ni	Plate	SA-553	II	K71340	...	...
22	8Ni	Plate	SA-553	II	K71340	...	...
23	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	NNT640	≤2
24	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	QT640	≤2
25	9Ni	Plate	SA/EN 10028-4	X7Ni9	...	QT	≤2
26	9Ni	Plate	SA/EN 10028-4	X7Ni9	...	QT	≤2
27	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	QT680	≤2
28	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	QT680	≤2
29	9Ni	Smls. & wld. pipe	SA-333	8	K81340	...	...
30	9Ni	Smls. & wld. pipe	SA-333	8	K81340	...	...
31	9Ni	Smls. pipe	SA-333	8	K81340	...	...
32	9Ni	Smls. pipe	SA-333	8	K81340	...	...
33	9Ni	Wld. pipe	SA-333	8	K81340	...	...
34	9Ni	Wld. tube	SA-334	8	K81340	...	...
35	9Ni	Smls. & wld. tube	SA-334	8	K81340	...	...
36	9Ni	Smls. tube	SA-334	8	K81340	...	...
37	9Ni	Smls. tube	SA-334	8	K81340	...	...
38	9Ni	Wld. tube	SA-334	8	K81340	...	...
39	9Ni	Plate	SA-353	...	K81340	...	...
40	9Ni	Plate	SA-353	...	K81340	...	...
41	9Ni	Plate	SA-353	...	K81340	...	...
42	9Ni	Smls. & wld. fittings	SA-420	WPL8	K81340	...	...
43	9Ni	Smls. & wld. fittings	SA-420	WPL8	K81340	...	...
44	9Ni	Forgings	SA-522	I	K81340	...	...
45	9Ni	Forgings	SA-522	I	K81340	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits				External Pressure Chart No.	Notes
					Limits					
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	9B	1	70	37.5	NP	650	650	650	CS-2	...
2	9B	1	70	37.5	NP	650	650	650	CS-2	...
3	9B	1	70	37.5	NP	NP	650	650	CS-2	...
4	9B	1	70	40	NP	300 (SPT)	NP	NP	CS-2	...
5	9B	1	70	40	NP	650	1000	650	CS-2	T2
6	9B	1	70	40	NP	100	650	650	CS-2	G1
7	9B	1	75	50	NP	NP	650	650	CS-3	...
8	9B	1	80	55	NP	NP	650	650	CS-3	...
9	3	3	90	70	NP	NP	650	650	CS-5	...
10	11A	5	105	85	NP	600 (SPT)	650	NP	CS-5	...
11	11B	10	115	100	NP	NP	650	NP	HT-1	...
12	...	...	115	100	NP	700 (SPT)	NP	NP	HT-1	W1
13	...	...	135	120	NP	700 (SPT)	NP	NP	HT-1	W1
14	...	...	155	140	NP	700 (SPT)	NP	NP	HT-1	W1
15	...	...	175	160	NP	700 (SPT)	NP	NP	HT-1	W1
16	...	...	190	180	NP	700 (SPT)	NP	NP	HT-1	W1
17	11A	2	95	65	NP	NP	250	250	CS-3	...
18	11A	1	100	85	NP	NP	150	NP	CS-3	G20, W4
19	11A	1	100	85	NP	NP	150	NP	CS-3	G20, W5
20	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W5
21	11A	1	100	85	NP	200 (Cl. 3 only)	250	250	CS-3	G20, W5
22	11A	1	100	85	NP	200 (Cl. 3 only)	250	250	CS-3	G20, W4
23	11A	1	93	69.5	NP	NP	250	250	CS-3	G20
24	11A	1	93	69.5	NP	NP	250	250	CS-3	G20
25	11A	1	98.5	83.5	NP	NP	250	250	CS-3	G20, W4
26	11A	1	98.5	83.5	NP	NP	250	250	CS-3	G20, W5
27	11A	1	98.5	83.5	NP	NP	250	250	CS-3	G20, W4
28	11A	1	98.5	83.5	NP	NP	250	250	CS-3	G20, W5
29	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W12
30	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W5, W12
31	11A	1	100	75	NP	NP	250	250	CS-3	G20, W4
32	11A	1	100	75	NP	NP	250	250	CS-3	G20, W5
33	11A	1	100	75	NP	NP	250	250	CS-3	G20, G24, W3
34	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W12
35	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W5, W12
36	11A	1	100	75	NP	NP	250	250	CS-3	G20, W4
37	11A	1	100	75	NP	NP	250	250	CS-3	G20, W5
38	11A	1	100	75	NP	NP	250	250	CS-3	G20, G24, W3
39	11A	1	100	75	NP	200 (Cl. 3 only)	250	250	CS-3	G20, W4
40	11A	1	100	75	NP	NP	250	250	CS-3	G20, W5
41	11A	1	100	75	NP	200 (Cl. 3 only)	NP	NP	CS-3	G20, W5
42	11A	1	100	75	NP	NP	250	250	CS-3	G20, W4
43	11A	1	100	75	NP	NP	250	250	CS-3	G20, W3
44	11A	1	100	75	NP	200 (Cl. 3 only)	250	250	CS-3	G20, S8, W4
45	11A	1	100	75	NP	NP	250	250	CS-3	G20, S8, W5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	20.0	20.0	18.8	17.9	...	...	...	...	...
2	20.0	...	20.0	...	20.0	20.0	20.0	18.8	17.9	...	...	...	...	...
3	20.0	20.0	20.0	...	20.0	20.0	20.0	18.8	17.9	...	...	...	...	...
4	20.0	...	20.0	...	20.0	...	...	...	...	...	...	...	...	...
5	20.0	...	20.0	...	20.0	20.0	20.0	20.0	19.0	18.0	14.8	12.0	9.3	6.5
6	20.0	20.0	20.0	...	20.0	20.0	20.0	20.0	19.0	...	...	...	...	...
7	21.4	21.4	21.4	...	21.4	21.4	21.4	21.4	20.5	...	...	...	...	...
8	22.9	22.9	22.9	...	22.9	22.9	22.9	22.9	20.5	...	...	...	...	...
9	25.7	...	25.7	25.7	25.7	25.5	25.3	25.0	24.6	...	...	...	...	...
10	30.0	...	30.0	30.0	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
11	32.9	...	32.9	32.9	32.9	32.5	32.3	31.9	31.5	...	...	...	...	...
12	32.9	...	32.9	...	32.9	32.9	32.9	32.9	32.4	31.6	...	...	...	...
13	38.6	...	38.6	...	38.6	38.6	38.6	38.6	38.0	37.1	...	...	...	...
14	44.3	...	44.3	...	44.3	44.3	44.3	44.3	43.6	42.6	...	...	...	...
15	50.0	...	50.0	...	50.0	50.0	50.0	50.0	49.2	48.0	...	...	...	...
16	54.3	...	54.3	...	54.3	54.3	54.3	54.3	53.5	52.2	...	...	...	...
17	27.1	...	27.1	26.6	...	...	...	...	...	...	...	...	...	...
18	28.6	28.6	...	...	...	...	...	...	...	...	...	...	...	...
19	27.1	27.1	...	...	...	...	...	...	...	...	...	...	...	...
20	27.1	27.1	25.4	...	...	...	...	...	...	...	...	...	...	...
21	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
22	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
23	26.5	26.5	26.5	26.5	...	...	...	...	...	...	...	...	...	...
24	26.5	26.5	26.5	26.5	...	...	...	...	...	...	...	...	...	...
25	28.2	28.2	28.2	28.2	...	...	...	...	...	...	...	...	...	...
26	27.1	27.1	27.1	27.1	...	...	...	...	...	...	...	...	...	...
27	28.2	28.2	28.2	28.2	...	...	...	...	...	...	...	...	...	...
28	27.1	27.1	27.1	27.1	...	...	...	...	...	...	...	...	...	...
29	28.6	28.6	26.7	...	...	...	...	...	...	...	...	...	...	...
30	27.1	27.1	25.4	...	...	...	...	...	...	...	...	...	...	...
31	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
32	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
33	24.3	24.3	22.7	22.1	...	...	...	...	...	...	...	...	...	...
34	28.6	28.6	26.7	...	...	...	...	...	...	...	...	...	...	...
35	27.1	27.1	25.4	...	...	...	...	...	...	...	...	...	...	...
36	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
37	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
38	24.3	24.3	22.7	22.1	...	...	...	...	...	...	...	...	...	...
39	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
40	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
41	27.1	27.1	25.4	...	...	...	...	...	...	...	...	...	...	...
42	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
43	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
44	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
45	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	4.5	2.5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	9Ni	Plate	SA-553	I	K81340	...	...
2	9Ni	Plate	SA-553	I	K81340	...	...
(25) 3	46Fe-24Ni-21Cr-6Mo-N	Smls. & wld. fittings	SA-403	...	N08367	...	...
(25) 4	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-182	F62	N08367	...	...
(25) 5	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-182	F62	N08367	...	...
(25) 6	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-965	F62	N08367	...	...
(25) 7	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-965	F62	N08367	...	...
(25) 8	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...	$>^{3/16}$
(25) 9	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...	$>^{3/16}$
(25) 10	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe	SA-312	...	N08367	...	$>^{3/16}$
(25) 11	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe	SA-312	...	N08367	...	$>^{3/16}$
(25) 12	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...	$>^{3/16}$
(25) 13	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...	$>^{3/16}$
(25) 14	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...	$>^{3/16}$
(25) 15	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...	$>^{3/16}$
(25) 16	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-688	...	N08367	...	$>^{3/16}$
(25) 17	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-688	...	N08367	...	$>^{3/16}$
(25) 18	46Fe-24Ni-21Cr-6Mo-N	Plate	SA-240	...	N08367	...	$\geq^{3/16}$
(25) 19	46Fe-24Ni-21Cr-6Mo-N	Plate	SA-240	...	N08367	...	$\geq^{3/16}$
(25) 20	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...	$>^{3/16}$
(25) 21	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...	$>^{3/16}$
(25) 22	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-276	...	N08367	...	...
(25) 23	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-276	...	N08367	...	...
(25) 24	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-479	...	N08367	...	...
(25) 25	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-479	...	N08367	...	...
(25) 26	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...	$\leq^{3/16}$
(25) 27	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...	$\leq^{3/16}$
(25) 28	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe	SA-312	...	N08367	...	$\leq^{3/16}$
(25) 29	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe	SA-312	...	N08367	...	$\leq^{3/16}$
(25) 30	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...	$\leq^{3/16}$
(25) 31	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...	$\leq^{3/16}$
(25) 32	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...	$\leq^{3/16}$
(25) 33	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...	$\leq^{3/16}$
(25) 34	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-688	...	N08367	...	$\leq^{3/16}$
(25) 35	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-688	...	N08367	...	$\leq^{3/16}$
(25) 36	46Fe-24Ni-21Cr-6Mo-N	Sheet, strip	SA-240	...	N08367	...	$<^{3/16}$
(25) 37	46Fe-24Ni-21Cr-6Mo-N	Sheet, strip	SA-240	...	N08367	...	$<^{3/16}$
(25) 38	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...	$\leq^{3/16}$
(25) 39	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...	$\leq^{3/16}$
(25) 40	25Ni-47Fe-21Cr-5Mo	Forgings	SA-182	F700	N08700	...	...
(25) 41	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SA-240	...	N08700	...	...
(25) 42	25Ni-47Fe-21Cr-5Mo	Bar	SA-276	...	N08700	...	...
(25) 43	25Ni-47Fe-21Cr-5Mo	Wld. pipe	SA-358	...	N08700	...	...
(25) 44	25Ni-47Fe-21Cr-5Mo	Fittings	SA-403	700	N08700	...	...
(25) 45	25Ni-47Fe-21Cr-5Mo	Bar	SA-479	...	N08700	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	11A	1	100	85	NP	200 (Cl. 3 only)	250	250	CS-3	G20, W4
2	11A	1	100	85	NP	200 (Cl. 3 only)	250	250	CS-3	G20, W5
3	45	...	95	45	NP	800	800	NP	NFN-12	G5, W12, W14
4	45	...	95	45	NP	800	800	650	NFN-12	...
5	45	...	95	45	NP	800	800	650	NFN-12	G5
6	45	...	95	45	NP	800	800	650	NFN-12	...
7	45	...	95	45	NP	800	800	650	NFN-12	G5
8	45	...	95	45	NP	800	800	650	NFN-12	G24
9	45	...	95	45	NP	800	800	650	NFN-12	G5, G24
10	45	...	95	45	NP	800	800	650	NFN-12	...
11	45	...	95	45	NP	800	800	650	NFN-12	G5
12	45	...	95	45	NP	800	800	650	NFN-12	G24
13	45	...	95	45	NP	800	800	650	NFN-12	G5, G24
14	45	...	95	45	NP	800	800	650	NFN-12	G24
15	45	...	95	45	NP	800	800	650	NFN-12	G5, G24
16	45	...	95	45	NP	800	800	650	NFN-12	...
17	45	...	95	45	NP	800	800	650	NFN-12	G5
18	45	...	95	45	NP	800	800	650	NFN-12	...
19	45	...	95	45	NP	800	800	650	NFN-12	G5
20	45	...	95	45	NP	800	800	650	NFN-12	...
21	45	...	95	45	NP	800	800	650	NFN-12	G5
22	45	...	95	45	NP	800	800	650	NFN-12	...
23	45	...	95	45	NP	800	800	650	NFN-12	G5
24	45	...	95	45	NP	800	800	650	NFN-12	...
25	45	...	95	45	NP	800	800	650	NFN-12	G5
26	45	...	100	45	NP	800	800	650	NFN-12	G24
27	45	...	100	45	NP	800	800	650	NFN-12	G5, G24
28	45	...	100	45	NP	800	800	650	NFN-12	...
29	45	...	100	45	NP	800	800	650	NFN-12	G5
30	45	...	100	45	NP	800	800	650	NFN-12	G24
31	45	...	100	45	NP	800	800	650	NFN-12	G5, G24
32	45	...	100	45	NP	800	800	650	NFN-12	G24
33	45	...	100	45	NP	800	800	650	NFN-12	G5, G24
34	45	...	100	45	NP	800	800	650	NFN-12	...
35	45	...	100	45	NP	800	800	650	NFN-12	G5
36	45	...	100	45	NP	800	800	650	NFN-12	...
37	45	...	100	45	NP	800	800	650	NFN-12	G5
38	45	...	100	45	NP	800	800	650	NFN-12	...
39	45	...	100	45	NP	800	800	650	NFN-12	G5
40	45	...	80	35	NP	NP	650	650	NFN-8	...
41	45	...	80	35	NP	NP	650	650	NFN-8	...
42	45	...	80	35	NP	NP	650	650	NFN-8	...
43	45	...	80	35	NP	NP	650	650	NFN-8	W14
44	45	...	80	35	NP	NP	650	650	NFN-8	W14
45	45	...	80	35	NP	NP	650	650	NFN-8	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	28.6	28.6	26.7	25.9	...	...	...	...	...	...	...	...	...	...
2	27.1	27.1	25.4	24.6	...	...	...	...	...	...	...	...	...	...
3	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
4	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
5	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
6	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
7	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
8	23.1	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
9	23.1	...	23.1	...	21.8	20.9	20.2	19.8	19.6	19.5	19.4	19.2	...	...
10	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
11	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
12	23.1	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
13	23.1	...	23.1	...	21.8	20.9	20.2	19.8	19.6	19.5	19.4	19.2	...	...
14	23.1	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
15	23.1	...	23.1	...	21.8	20.9	20.2	19.8	19.6	19.5	19.4	19.2	...	...
16	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
17	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
18	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
19	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
20	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
21	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
22	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
23	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
24	27.1	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
25	27.1	...	27.1	...	25.7	24.6	23.8	23.3	23.1	22.9	22.8	22.6	...	...
26	24.3	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
27	24.3	...	24.3	...	23.0	22.0	21.3	20.8	20.7	20.5	20.4	20.2	...	...
28	28.6	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
29	28.6	...	28.6	...	27.0	25.8	25.0	24.5	24.3	24.1	24.0	23.8	...	...
30	24.3	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
31	24.3	...	24.3	...	23.0	22.0	21.3	20.8	20.7	20.5	20.4	20.2	...	...
32	24.3	...	22.2	...	20.2	18.7	17.4	16.5	16.1	15.8	15.5	15.3	...	...
33	24.3	...	24.3	...	23.0	22.0	21.3	20.8	20.7	20.5	20.4	20.2	...	...
34	28.6	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
35	28.6	...	28.6	...	27.0	25.8	25.0	24.5	24.3	24.1	24.0	23.8	...	...
36	28.6	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
37	28.6	...	28.6	...	27.0	25.8	25.0	24.5	24.3	24.1	24.0	23.8	...	...
38	28.6	...	26.2	...	23.8	21.9	20.5	19.4	19.0	18.6	18.3	18.0	...	...
39	28.6	...	28.6	...	27.0	25.8	25.0	24.5	24.3	24.1	24.0	23.8	...	...
40	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
41	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
42	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
43	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
44	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
45	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25) 1	25Ni-47Fe-21Cr-5Mo	Forgings	SA-965	F700	N08700	...	...
2	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660	S66286	...	...
(25) 3	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SA-240	...	N08925	...	...
(25) 4	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SA-240	...	N08925	...	...
(25) 5	25Ni-20Cr-6Mo-Cu-N	Bar	SA-276	...	N08925	...	...
(25) 6	25Ni-20Cr-6Mo-Cu-N	Bar	SA-276	...	N08925	...	...
(25) 7	25Ni-20Cr-6Mo-Cu-N	Bar	SA-479	...	N08925	...	...
(25) 8	25Ni-20Cr-6Mo-Cu-N	Bar	SA-479	...	N08925	...	...
(25) 9	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SA-312	...	N08925	...	...
(25) 10	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SA-312	...	N08925	...	...
(25) 11	25Ni-20Cr-6Mo-Cu-N	Smls. pipe	SA-312	...	N08925	...	...
(25) 12	25Ni-20Cr-6Mo-Cu-N	Smls. pipe	SA-312	...	N08925	...	...
(25) 13	25Ni-20Cr-6Mo-Cu-N	Smls. tube	SA-213	...	N08925	...	...
(25) 14	25Ni-20Cr-6Mo-Cu-N	Smls. tube	SA-213	...	N08925	...	...
(25) 15	44Fe-25Ni-21Cr-Mo	Forgings	SA-182	F904L	N08904	...	...
(25) 16	44Fe-25Ni-21Cr-Mo	Smls. tube	SA-213	...	N08904	...	...
(25) 17	44Fe-25Ni-21Cr-Mo	Plate, sheet, strip	SA-240	904L	N08904	...	...
(25) 18	44Fe-25Ni-21Cr-Mo	Wld. tube	SA-249	...	N08904	...	...
(25) 19	44Fe-25Ni-21Cr-Mo	Smls. pipe	SA-312	...	N08904	...	...
(25) 20	44Fe-25Ni-21Cr-Mo	Wld. pipe	SA-312	...	N08904	...	...
(25) 21	44Fe-25Ni-21Cr-Mo	Fittings	SA-403	WP904L/CR904L	N08904	...	...
(25) 22	44Fe-25Ni-21Cr-Mo	Bar	SA-479	904L	N08904	...	...
23	27Ni-22Cr-7Mo-Mn-Cu-N	Smls. tube	SA-213	...	S31277	...	...
24	27Ni-22Cr-7Mo-Mn-Cu-N	Smls. tube	SA-213	...	S31277	...	...
25	27Ni-22Cr-7Mo-Mn-Cu-N	Plate	SA-240	...	S31277	...	...
26	27Ni-22Cr-7Mo-Mn-Cu-N	Plate	SA-240	...	S31277	...	...
(25) 27	27Ni-22Cr-7Mo-Mn-Cu-N	Wld. tube	SA-249	...	S31277	...	...
28	27Ni-22Cr-7Mo-Mn-Cu-N	Wld. tube	SA-249	...	S31277	...	...
29	29Ni-20Cr-3Cu-2Mo	Castings	SA-351	CN7M	J95150	...	...
30	29Ni-20Cr-3Cu-2Mo	Castings	SA-351	CN7M	J95150	...	...
(25) 31	35Ni-35Fe-20Cr-Cb	Forgings	SA-182	F20	N08020	...	...
(25) 32	35Ni-35Fe-20Cr-Cb	Forgings	SA-182	F20	N08020	...	...
(25) 33	35Ni-35Fe-20Cr-Cb	Forgings	SA-965	F20	N08020	...	...
(25) 34	35Ni-35Fe-20Cr-Cb	Forgings	SA-965	F20	N08020	...	...
(25) 35	35Ni-35Fe-20Cr-Cb	Plate	SA-240	...	N08020	...	...
(25) 36	35Ni-35Fe-20Cr-Cb	Plate	SA-240	...	N08020	...	...
(25) 37	35Ni-35Fe-20Cr-Cb	Bar	SA-276	Alloy 20	N08020	...	...
(25) 38	35Ni-35Fe-20Cr-Cb	Bar	SA-276	Alloy 20	N08020	...	...
(25) 39	35Ni-35Fe-20Cr-Cb	Bar	SA-479	Alloy 20	N08020	...	...
(25) 40	35Ni-35Fe-20Cr-Cb	Bar	SA-479	Alloy 20	N08020	...	...
(25) 41	35Ni-35Fe-20Cr-Cb	Smls. pipe	SA-312	Alloy 20	N08020	...	...
(25) 42	35Ni-35Fe-20Cr-Cb	Smls. pipe	SA-312	Alloy 20	N08020	...	...
(25) 43	35Ni-35Fe-20Cr-Cb	Wld. pipe	SA-312	Alloy 20	N08020	...	...
(25) 44	35Ni-35Fe-20Cr-Cb	Wld. pipe	SA-312	Alloy 20	N08020	...	...
(25) 45	35Ni-35Fe-20Cr-Cb	Wld. pipe	SA-312	Alloy 20	N08020	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	45	...	80	35	NP	NP	650	650	NFN-8	...
2	...	...	130	85	NP	700	700	NP	HA-5	W1
3	45	...	87	43	NP	NP	800	650	NFN-12	...
4	45	...	87	43	NP	NP	800	650	NFN-12	G5
5	45	...	87	43	NP	NP	800	650	NFN-12	...
6	45	...	87	43	NP	NP	800	650	NFN-12	G5
7	45	...	87	43	NP	NP	800	650	NFN-12	...
8	45	...	87	43	NP	NP	800	650	NFN-12	G5
9	45	...	87	43	NP	NP	800	650	NFN-12	G24
10	45	...	87	43	NP	NP	800	650	NFN-12	G5, G24
11	45	...	87	43	NP	NP	800	650	NFN-12	...
12	45	...	87	43	NP	NP	800	650	NFN-12	G5
13	45	...	87	43	NP	NP	800	650	NFN-12	...
14	45	...	87	43	NP	NP	800	650	NFN-12	G5
15	45	...	71	31	NP	700	700	650	NFN-9	W14
16	45	...	71	31	NP	700	700	650	NFN-9	...
17	45	...	71	31	NP	700	700	650	NFN-9	...
18	45	...	71	31	NP	700	700	650	NFN-9	G24
19	45	...	71	31	NP	700	700	650	NFN-9	...
20	45	...	71	31	NP	700	700	650	NFN-9	G24
21	45	...	71	31	NP	700	700	650	NFN-9	W14
22	45	...	71	31	NP	700	700	650	NFN-9	...
23	45	...	112	52	NP	NP	800	NP	NFN-26	G5
24	45	...	112	52	NP	NP	800	NP	NFN-26	...
25	45	...	112	52	NP	NP	800	NP	NFN-26	G5
26	45	...	112	52	NP	NP	800	NP	NFN-26	...
27	45	...	112	52	NP	NP	800	NP	NFN-26	G5, G24
28	45	...	112	52	NP	NP	800	NP	NFN-26	...
29	45	...	62	25	600	600 (Cl. 3 only)	600	NP	NFN-9	G1, G5
30	45	...	62	25	600		NP	600	NP	NFN-9
31	45	...	80	35	NP	800	800	650	NFN-12	G5
32	45	...	80	35	NP	NP	800	650	NFN-12	...
33	45	...	80	35	NP	800	800	650	NFN-12	G5
34	45	...	80	35	NP	NP	800	650	NFN-12	...
35	45	...	80	35	NP	NP	800	650	NFN-12	...
36	45	...	80	35	NP	800	800	650	NFN-12	G5
37	45	...	80	35	NP	800	800	650	NFN-12	G5
38	45	...	80	35	NP	NP	800	650	NFN-12	...
39	45	...	80	35	NP	800	800	650	NFN-12	G5
40	45	...	80	35	NP	NP	800	650	NFN-12	...
41	45	...	80	35	NP	NP	800	650	NFN-12	...
42	45	...	80	35	NP	NP	800	650	NFN-12	G5
43	45	...	80	35	NP	800	NP	NP	NFN-12	G5, W12
44	45	...	80	35	NP	NP	800	650	NFN-12	G24
45	45	...	80	35	NP	NP	800	650	NFN-12	G5, G24

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	22.9	...	21.0	...	19.0	17.7	17.1	16.5	15.8	...	...	...	...	...
2	37.1	...	37.1	...	37.1	37.1	36.5	35.8	35.4	35.0	...	...	...	...
3	24.9	...	23.2	...	21.3	19.8	18.3	17.3	17.0	16.9	16.9	16.9	...	...
4	24.9	...	24.9	...	23.9	23.0	22.1	21.4	21.1	20.8	20.4	20.1	...	...
5	24.9	...	23.2	...	21.3	19.8	18.3	17.3	17.0	16.9	16.9	16.9	...	...
6	24.9	...	24.9	...	23.9	23.0	22.1	21.4	21.1	20.8	20.4	20.1	...	...
7	24.9	...	23.2	...	21.3	19.8	18.3	17.3	17.0	16.9	16.9	16.9	...	...
8	24.9	...	24.9	...	23.9	23.0	22.1	21.4	21.1	20.8	20.4	20.1	...	...
9	21.1	...	19.7	...	18.1	16.8	15.6	14.7	14.4	14.4	14.4	14.4	...	...
10	21.1	...	21.1	...	20.4	19.5	18.8	18.2	17.9	17.7	17.4	17.0	...	...
11	24.9	...	23.2	...	21.3	19.8	18.3	17.3	17.0	16.9	16.9	16.9	...	...
12	24.9	...	24.9	...	23.9	23.0	22.1	21.4	21.1	20.8	20.4	20.1	...	...
13	24.9	...	23.2	...	21.3	19.8	18.3	17.3	17.0	16.9	16.9	16.9	...	...
14	24.9	...	24.9	...	23.9	23.0	22.1	21.4	21.1	20.8	20.4	20.1	...	...
15	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
16	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
17	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
18	17.2	...	14.2	...	12.9	11.8	10.8	10.1	9.9	9.7	...	...	...	...
19	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
20	17.2	...	14.2	...	12.9	11.8	10.8	10.1	9.9	9.7	...	...	...	...
21	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
22	20.3	...	16.7	...	15.1	13.8	12.7	11.9	11.6	11.4	...	...	...	...
23	32.0	32.0	32.0	31.5	30.7	29.4	28.4	27.5	27.1	26.8	26.5	26.3	...	...
24	32.0	32.0	32.0	30.4	28.8	26.5	25.5	25.4	25.4	25.3	25.1	24.9	...	...
25	32.0	32.0	32.0	31.5	30.7	29.4	28.4	27.5	27.1	26.8	26.5	26.3	...	...
26	32.0	32.0	32.0	30.4	28.8	26.5	25.5	25.4	25.4	25.3	25.1	24.9	...	...
27	27.2	27.2	27.2	26.8	26.1	24.9	24.1	23.4	23.1	22.7	22.5	22.3	...	...
28	27.2	27.2	27.2	25.8	24.5	22.5	21.7	21.6	21.6	21.5	21.3	21.2	...	...
29	16.7	...	16.0	...	13.6	12.8	12.1	11.6	...	...	...	...	...	...
30	16.7	...	14.4	...	12.9	11.8	10.8	10.0	...	...	...	...	...	...
31	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
32	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
33	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
34	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
35	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
36	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
37	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
38	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
39	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
40	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
41	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
42	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
43	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
44	19.4	...	17.5	...	16.7	16.1	15.5	15.0	14.9	14.8	14.6	14.3	...	...
45	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25) 1	35Ni-35Fe-20Cr-Cb	Smls. tube	SA-213	Alloy 20	N08020	...	...
(25) 2	35Ni-35Fe-20Cr-Cb	Smls. tube	SA-213	Alloy 20	N08020	...	...
(25) 3	35Ni-35Fe-20Cr-Cb	Wld. tube	SA-249	Alloy 20	N08020	...	...
(25) 4	35Ni-35Fe-20Cr-Cb	Wld. tube	SA-249	Alloy 20	N08020	...	...
(25) 5	35Ni-35Fe-20Cr-Cb	Wld. tube	SA-249	Alloy 20	N08020	...	...
(25) 6	35Ni-35Fe-20Cr-Cb	Smls. & wld. fittings	SA-403	...	N08020	...	...
(25) 7	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10	N08810	...	...
(25) 8	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10	N08810	...	...
(25) 9	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H	N08810	...	...
(25) 10	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H	N08810	...	...
(25) 11	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...	...
(25) 12	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...	...
(25) 13	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H	N08810	...	...
(25) 14	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H	N08810	...	...
(25) 15	42Fe-33Ni-21Cr	Bar	SA-276	800H	N08810	...	...
(25) 16	42Fe-33Ni-21Cr	Bar	SA-276	800H	N08810	...	...
(25) 17	42Fe-33Ni-21Cr	Smls. & wld. pipe	SA-312	800H	N08810	...	...
(25) 18	42Fe-33Ni-21Cr	Smls. & wld. pipe	SA-312	800H	N08810	...	...
(25) 19	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H	N08810	...	...
(25) 20	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H	N08810	...	...
(25) 21	42Fe-33Ni-21Cr	Bar	SA-479	800H	N08810	...	...
(25) 22	42Fe-33Ni-21Cr	Bar	SA-479	800H	N08810	...	...
(25) 23	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H	N08810	...	...
(25) 24	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H	N08810	...	...
(25) 25	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10	N08810	...	...
(25) 26	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10	N08810	...	...
(25) 27	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC11	N08811	...	...
(25) 28	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC11	N08811	...	...
(25) 29	42Fe-33Ni-21Cr	Smls. tube	SA-213	...	N08811	...	...
(25) 30	42Fe-33Ni-21Cr	Smls. tube	SA-213	...	N08811	...	...
(25) 31	42Fe-33Ni-21Cr	Plate	SA-240	...	N08811	...	...
(25) 32	42Fe-33Ni-21Cr	Plate	SA-240	...	N08811	...	...
(25) 33	42Fe-33Ni-21Cr	Wld. tube	SA-249	...	N08811	...	...
(25) 34	42Fe-33Ni-21Cr	Wld. tube	SA-249	...	N08811	...	...
(25) 35	42Fe-33Ni-21Cr	Bar	SA-276	...	N08811	...	...
(25) 36	42Fe-33Ni-21Cr	Bar	SA-276	...	N08811	...	...
(25) 37	42Fe-33Ni-21Cr	Smls. pipe	SA-312	...	N08811	...	...
(25) 38	42Fe-33Ni-21Cr	Smls. pipe	SA-312	...	N08811	...	...
(25) 39	42Fe-33Ni-21Cr	Bar	SA-479	...	N08811	...	...
(25) 40	42Fe-33Ni-21Cr	Bar	SA-479	...	N08811	...	...
(25) 41	42Fe-33Ni-21Cr	Wld. tube	SA-688	...	N08811	...	...
(25) 42	42Fe-33Ni-21Cr	Wld. tube	SA-688	...	N08811	...	...
(25) 43	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC11	N08811	...	...
(25) 44	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC11	N08811	...	...
(25) 45	14Cr-16Ni-6Si-Cu-Mo	Smls. tube	SA-213	...	S38815	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	45	...	80	35	NP	NP	800	650	NFN-12	...
2	45	...	80	35	NP	NP	800	650	NFN-12	G5
3	45	...	80	35	NP	800	NP	NP	NFN-12	G5, W12
4	45	...	80	35	NP	NP	800	650	NFN-12	G24
5	45	...	80	35	NP	NP	800	650	NFN-12	G5, G24
6	45	...	85	40	NP	800	800	650	NFN-12	G5, W12, W14
7	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9
8	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8
9	45	...	65	25	NP	NP	1650	NP	NFN-9	G6, T9
10	45	...	65	25	NP	800	1650	NP	NFN-9	G5, G6, T8
11	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9
12	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8
13	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, G24, T9
14	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, G24, T8
15	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9
16	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8
17	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9, W5, W12
18	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8, W5, W12
19	45	...	65	25	NP	NP	1650	NP	NFN-9	G6, G24, T9
20	45	...	65	25	NP	NP	1650	NP	NFN-9	G5, G6, G24, T8
21	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9
22	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8
23	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, G24, T9
24	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, G24, T8
25	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T9
26	45	...	65	25	1500	800	1650	NP	NFN-9	G5, G6, T8
27	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
28	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
29	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
30	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
31	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
32	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
33	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, G24, T12
34	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, G24, T9
35	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
36	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
37	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
38	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
39	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
40	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
41	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, G24, T12
42	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, G24, T9
43	45	...	65	25	1500	NP	1650	NP	NFN-9	G6, T12
44	45	...	65	25	1500	NP	1650	NP	NFN-9	G5, G6, T8
45	8	1	78	37	NP	NP	800	NP	HA-2	G5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	22.9	...	20.6	...	19.7	18.9	18.2	17.7	17.5	17.4	17.2	16.8	...	...
2	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
3	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
4	19.4	...	17.5	...	16.7	16.1	15.5	15.0	14.9	14.8	14.6	14.3	...	...
5	19.4	...	19.4	...	19.2	18.8	18.8	18.8	18.7	18.6	18.5	18.5	...	...
6	22.9	...	22.9	...	22.6	22.2	22.1	22.1	22.0	21.9	21.8	21.8	...	...
7	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
8	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
9	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
10	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
11	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
12	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
13	14.2	...	13.1	...	12.3	11.6	10.9	10.4	10.1	9.9	9.7	9.5	9.3	9.1
14	14.2	...	14.2	...	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
15	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
16	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
17	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
18	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
19	14.2	...	13.1	...	12.3	11.6	10.9	10.4	10.1	9.9	9.7	9.5	9.3	9.1
20	14.2	...	14.2	...	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
21	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
22	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
23	14.2	...	13.1	...	12.3	11.6	10.9	10.4	10.1	9.9	9.7	9.5	9.3	9.1
24	14.2	...	14.2	...	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
25	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
26	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
27	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
28	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
29	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
30	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
31	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
32	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
33	14.2	...	13.1	...	12.3	11.6	10.9	10.4	10.1	9.9	9.7	9.5	9.3	9.1
34	14.2	...	14.2	...	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
35	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
36	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
37	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
38	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
39	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
40	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
41	14.2	...	13.1	...	12.3	11.6	10.9	10.4	10.1	9.9	9.7	9.5	9.3	9.1
42	14.2	...	14.2	...	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
43	16.7	...	15.4	...	14.4	13.6	12.9	12.2	11.9	11.6	11.4	11.1	10.9	10.7
44	16.7	...	16.7	...	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
45	22.3	...	22.3	...	22.2	21.5	21.0	20.7	20.6	20.6	20.6	20.5	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
8	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
9	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
10	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
11	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
12	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
13	9.0	8.8	8.7	8.5	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
14	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
15	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
16	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
17	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
18	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
19	9.0	8.8	8.7	8.5	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
20	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
21	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
22	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
23	9.0	8.8	8.7	8.5	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
24	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73 (25)
25	10.5	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
26	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86 (25)
27	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
28	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
29	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
30	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
31	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
32	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
33	9.0	8.8	8.7	8.5	8.3	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77 (25)
34	12.1	11.9	11.7	11.5	8.8	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77 (25)
35	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
36	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
37	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
38	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
39	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
40	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
41	9.0	8.8	8.7	8.5	8.3	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77 (25)
42	12.1	11.9	11.7	11.5	8.8	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77 (25)
43	10.5	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
44	14.2	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91 (25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	14Cr-16Ni-6Si-Cu-Mo	Smls. tube	SA-213	...	S38815	...	...
2	14Cr-16Ni-6Si-Cu-Mo	Plate	SA-240	...	S38815	...	...
3	14Cr-16Ni-6Si-Cu-Mo	Plate	SA-240	...	S38815	...	...
4	14Cr-16Ni-6Si-Cu-Mo	Wld. tube	SA-249	...	S38815	...	...
5	14Cr-16Ni-6Si-Cu-Mo	Wld. tube	SA-249	...	S38815	...	...
6	14Cr-16Ni-6Si-Cu-Mo	Wld. pipe	SA-312	...	S38815	...	...
7	14Cr-16Ni-6Si-Cu-Mo	Wld. pipe	SA-312	...	S38815	...	...
8	14Cr-16Ni-6Si-Cu-Mo	Smls. & wld. fittings	SA-403	...	S38815	...	...
9	14Cr-16Ni-6Si-Cu-Mo	Smls. & wld. fittings	SA-403	...	S38815	...	...
10	14Cr-16Ni-6Si-Cu-Mo	Bar	SA-479	...	S38815	...	...
11	14Cr-16Ni-6Si-Cu-Mo	Bar	SA-479	...	S38815	...	...
12	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...
13	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...
14	16Cr-9Mn-2Ni-N	Plate	SA-240	204	S20400	...	...
15	16Cr-9Mn-2Ni-N	Plate	SA-240	204	S20400	...	...
16	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	>5
17	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	>5
18	16Cr-12Ni-2Mo	Forgings	SA-965	F316L	S31603	...	...
19	16Cr-12Ni-2Mo	Forgings	SA-965	F316L	S31603	...	...
20	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	≤5
21	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	≤5
22	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...	...
23	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...	...
24	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...	...
25	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...	...
26	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...
27	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...
28	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...
29	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316L	S31603	...	...
30	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	...	...
31	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...
32	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...
33	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	1	...
34	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316L	S31603	...	...
35	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316L	S31603	...	...
36	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	...	...
37	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	...	...
38	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L	S31603	...	...
39	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L	S31603	...	...
40	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L	S31603	...	...
41	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316L	S31603	...	...
42	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316L	S31603	...	...
43	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316L	...	...	...
44	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	>5
45	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	>5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	78	37	NP	NP	800	NP	HA-2	...
2	8	1	78	37	NP	NP	800	NP	HA-2	G5
3	8	1	78	37	NP	NP	800	NP	HA-2	...
4	8	1	78	37	NP	NP	800	NP	HA-2	G5
5	8	1	78	37	NP	NP	800	NP	HA-2	...
6	8	1	78	37	NP	NP	800	NP	HA-2	G5
7	8	1	78	37	NP	NP	800	NP	HA-2	...
8	8	1	78	37	NP	NP	800	NP	HA-2	G5, W14
9	8	1	78	37	NP	NP	800	NP	HA-2	W14
10	8	1	78	37	NP	NP	800	NP	HA-2	G5
11	8	1	78	37	NP	NP	800	NP	HA-2	...
12	8	3	95	45	NP	NP	800	650	HA-6	G5
13	8	3	95	45	NP	NP	800	650	HA-6	...
14	8	3	95	48	NP	NP	900	650	HA-6	G5
15	8	3	95	48	NP	NP	900	650	HA-6	...
16	8	1	65	25	850	800	1200	650	HA-4	G5, T12
17	8	1	65	25	850	NP	1200	650	HA-4	G21, T12
18	8	1	65	25	850	800	1200	650	HA-4	G5, T12
19	8	1	65	25	850	NP	1200	650	HA-4	G21, T12
20	8	1	70	25	850	800	1200	650	HA-4	G5, T12
21	8	1	70	25	850	NP	1200	650	HA-4	G21, T12
22	8	1	70	25	850	800	1200	NP	HA-4	G5, T12
23	8	1	70	25	850	NP	1200	NP	HA-4	G21, T12
24	8	1	70	25	850	800	1200	650	HA-4	G5, T12
25	8	1	70	25	850	NP	1200	650	HA-4	G21, T12
26	8	1	70	25	NP	800	NP	NP	HA-4	G5, W12
27	8	1	70	25	850	NP	1200	650	HA-4	G5, G21, G24, T12
28	8	1	70	25	850	NP	1200	650	HA-4	G21, G24, T12
29	8	1	70	25	850	800	1200	650	HA-4	G5, G21, T12, W12, W14
30	8	1	70	25	850	NP	1200	650	HA-4	G21, T12
31	8	1	70	25	850	NP	1200	650	HA-4	G5, G21, G24, T12
32	8	1	70	25	850	NP	1200	650	HA-4	G21, G24, T12
33	8	1	70	25	NP	800	NP	NP	HA-4	G5
34	8	1	70	25	NP	800	1200	650	HA-4	G5, T12, W12, W14
35	8	1	70	25	NP	800	NP	NP	HA-4	G5
36	8	1	70	25	850	800	1200	650	HA-4	G5, G21, G22, T12
37	8	1	70	25	850	NP	1200	650	HA-4	G21, G22, T12
38	8	1	70	25	NP	800	NP	NP	HA-4	G5, W12
39	8	1	70	25	NP	NP	850	650	HA-4	G5, G24
40	8	1	70	25	NP	NP	850	650	HA-4	G24
41	8	1	70	25	NP	800	NP	NP	HA-4	G5, W12
42	8	1	70	25	NP	800	NP	NP	HA-4	G5, W12
43	8	1	70	25	850	800	850	NP	HA-4	G5, G21, G22
44	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T8
45	8	1	70	30	1500	NP	1500	650	HA-2	G12, T9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	22.3	...	20.8	...	18.5	17.1	16.3	16.0	16.0	16.0	16.0	16.0	...	...
2	22.3	...	22.3	...	22.2	21.5	21.0	20.7	20.6	20.6	20.6	20.5	...	...
3	22.3	...	20.8	...	18.5	17.1	16.3	16.0	16.0	16.0	16.0	16.0	...	...
4	18.9	...	18.9	...	18.9	18.3	17.8	17.6	17.5	17.5	17.5	17.5	...	...
5	18.9	...	17.7	...	15.7	14.5	13.8	13.6	13.6	13.6	13.6	13.6	...	...
6	18.9	...	18.9	...	18.9	18.3	17.8	17.6	17.5	17.5	17.5	17.5	...	...
7	18.9	...	17.7	...	15.7	14.5	13.8	13.6	13.6	13.6	13.6	13.6	...	...
8	22.3	...	22.3	...	22.2	21.5	21.0	20.7	20.6	20.6	20.6	20.5	...	...
9	22.3	...	20.8	...	18.5	17.1	16.3	16.0	16.0	16.0	16.0	16.0	...	...
10	22.3	...	22.3	...	22.2	21.5	21.0	20.7	20.6	20.6	20.6	20.5	...	...
11	22.3	...	20.8	...	18.5	17.1	16.3	16.0	16.0	16.0	16.0	16.0	...	...
12	27.1	...	23.7	...	21.2	20.1	20.0	19.6	19.6	19.4	19.2	18.8	...	...
13	27.1	...	23.7	...	21.2	20.1	19.7	19.2	18.6	18.0	17.4	16.7	...	...
14	27.1	...	23.6	...	20.6	18.9	18.1	17.9	17.9	17.9	17.8	17.7	17.4	16.9
15	27.1	...	23.6	...	20.3	17.9	16.5	15.8	15.6	15.5	15.3	15.1	14.8	14.3
16	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
17	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
18	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
19	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
20	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
21	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
22	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
23	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
24	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
25	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
26	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
27	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	10.8	10.5
28	14.2	...	12.1	...	10.8	9.9	9.3	8.8	8.7	8.5	8.3	8.1	8.0	7.8
29	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
30	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
31	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	10.8	10.5
32	14.2	...	12.1	...	10.8	9.9	9.3	8.8	8.7	8.5	8.3	8.1	8.0	7.8
33	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
34	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
35	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
36	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	12.4
37	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	9.2
38	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
39	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	10.8	...
40	14.2	...	12.1	...	10.8	9.9	9.3	8.8	8.7	8.5	8.3	8.1	8.0	...
41	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
42	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
43	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	...
44	20.0	...	20.0	...	19.4	19.2	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
45	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
17	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
18	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
19	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
20	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
21	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
22	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
23	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
24	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
25	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	10.3	10.1	9.9	9.7	7.5	5.4	...	...	...	...	...	...	...	...	...
28	7.7	7.5	7.3	7.1	7.1	5.4	...	...	...	...	...	...	...	...	...
29	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
30	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
31	10.3	10.1	9.9	9.7	7.5	5.4	...	...	...	...	...	...	...	...	...
32	7.7	7.5	7.3	7.1	7.1	5.4	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	12.1	11.9	11.6	11.4	8.8	6.4	...	...	...	...	...	...	...	...	...
37	9.0	8.8	8.6	8.4	8.3	6.4	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
45	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	16Cr-12Ni-2Mo	Forgings	SA-965	F316	S31600	...	...
2	16Cr-12Ni-2Mo	Forgings	SA-965	F316	S31600	...	...
3	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	>5
4	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	>5
5	16Cr-12Ni-2Mo	Forgings	SA-965	F316H	S31609	...	...
6	16Cr-12Ni-2Mo	Forgings	SA-965	F316H	S31609	...	...
7	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	≤5
8	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	≤5
9	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...	...
10	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...	...
11	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...	...
12	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...	...
13	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...
14	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...
(25) 15	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...
(25) 16	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...
17	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316	S31600	...	...
18	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316	S31600	...	...
(25) 19	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...
(25) 20	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...
21	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	1	...
(25) 22	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316	S31600	...	...
(25) 23	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316	S31600	...	...
24	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316	S31600	...	...
25	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316	S31600	...	...
(25) 26	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	...	...
(25) 27	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	...	...
28	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...
29	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...
30	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...
31	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316	S31600	...	...
32	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316	S31600	...	...
(25) 33	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316	...	...	...
34	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	≤5
35	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	≤5
36	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H	S31609	...	...
37	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H	S31609	...	...
38	16Cr-12Ni-2Mo	Plate	SA-240	316H	S31609	...	...
39	16Cr-12Ni-2Mo	Plate	SA-240	316H	S31609	...	...
(25) 40	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...
(25) 41	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...
42	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...
43	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...
44	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316H	S31609	...	...
45	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316H	S31609	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T8
2	8	1	70	30	1500	NP	1500	650	HA-2	G12, T9
3	8	1	70	30	1500	800	1500	NP	HA-2	G5, G12, T8
4	8	1	70	30	1500	NP	1500	NP	HA-2	T9
5	8	1	70	30	NP	800	1500	NP	HA-2	G5, T8
6	8	1	70	30	NP	NP	1500	NP	HA-2	T9
7	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T8
8	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T9
9	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T8
10	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T9
11	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T8
12	8	1	75	30	1500	NP	1500	650	HA-2	G12, T9
13	8	1	75	30	1500	NP	NP	NP	HA-2	G12, T9, W13
14	8	1	75	30	1500	800	NP	NP	HA-2	G5, G12, T8, W12, W13
15	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T7
16	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T9
17	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T8, W12, W13, W14
18	8	1	75	30	1500	NP	1500	650	HA-2	G12, T9, W13, W14
19	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T7
20	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T9
21	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
22	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T8, W12
23	8	1	75	30	1500	NP	1500	650	HA-2	G12, T9
24	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T8, W12, W14
25	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
26	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, G22, T8
27	8	1	75	30	1500	NP	1500	650	HA-2	G12, G22, T9
28	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
29	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T7
30	8	1	75	30	NP	NP	1500	650	HA-2	G12, G24, T9
31	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
32	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
33	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, G22, T8
34	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
35	8	1	75	30	1500	NP	1500	NP	HA-2	T9
36	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
37	8	1	75	30	1500	NP	1500	NP	HA-2	T9
38	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
39	8	1	75	30	1500	NP	1500	NP	HA-2	T9
40	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T7
41	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T9
42	8	1	75	30	1500	NP	NP	NP	HA-2	T9, W13
43	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8, W12, W13
44	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8, W12, W13
45	8	1	75	30	1500	NP	1500	NP	HA-2	T9, W13

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	19.4	19.2	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
2	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
3	20.0	...	20.0	...	19.4	19.2	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
4	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
5	20.0	...	20.0	...	19.4	19.2	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
6	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
7	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
8	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
9	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
10	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
11	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
12	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
13	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
14	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
15	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
16	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
17	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
18	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
19	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
20	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
21	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
22	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
23	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
24	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
25	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
26	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
27	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
28	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
29	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
30	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
31	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
32	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
33	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
34	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
35	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
36	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
37	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
38	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
39	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
40	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
41	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
42	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
43	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
44	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
45	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
2	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
3	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
4	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
5	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
6	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
7	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
8	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
9	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
10	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
11	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
12	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
13	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
14	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
15	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
16	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
17	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
18	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
19	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
20	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	... (25)
23	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	... (25)
24	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	... (25)
27	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	... (25)
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	...
30	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	... (25)
34	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
35	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
36	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
37	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
38	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
39	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
40	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
41	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	... (25)
42	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
43	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
44	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
45	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temp	Size/Thickness, in.
(25) 1	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316H	S31609	...	...
(25) 2	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316H	S31609	...	...
3	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	1	...
(25) 4	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H	S31609	...	...
(25) 5	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H	S31609	...	...
6	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316H	S31609	...	...
(25) 7	16Cr-12Ni-2Mo	Bar	SA-479	316H	S31609	...	...
(25) 8	16Cr-12Ni-2Mo	Bar	SA-479	316H	S31609	...	...
9	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316H	S31609	...	...
10	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316H	S31609	...	...
11	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2	...	...	≤3
12	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2	...	...	≤3
13	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2	...	...	≤3
14	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2	...	...	≤3
15	16Cr-12Ni-2Mo-Cb	Plate	SA-240	316Cb	S31640	...	...
16	16Cr-12Ni-2Mo-Cb	Plate	SA-240	316Cb	S31640	...	...
17	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...	>5
18	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316LN	S31653	...	...
19	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...	≤5
20	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316LN	S31653	...	...
21	16Cr-12Ni-2Mo-N	Plate	SA-240	316LN	S31653	...	...
22	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316LN	S31653	...	...
23	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316LN	S31653	...	...
24	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	1	...
25	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316LN	S31653	...	...
26	16Cr-12Ni-2Mo-N	Fittings	SA-403	316LN	S31653	...	...
27	16Cr-12Ni-2Mo-N	Bar	SA-479	316LN	S31653	...	...
28	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316LN	S31653	...	...
29	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316N	S31651	...	...
30	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N	S31651	...	...
31	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N	S31651	...	...
32	16Cr-12Ni-2Mo-N	Plate	SA-240	316N	S31651	...	...
33	16Cr-12Ni-2Mo-N	Plate	SA-240	316N	S31651	...	...
34	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...
35	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...
(25) 36	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...
(25) 37	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...
38	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316N	S31651	...	...
39	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316N	S31651	...	...
(25) 40	16Cr-12Ni-2Mo-N	Wld. pipe	SA-312	TP316N	S31651	...	...
(25) 41	16Cr-12Ni-2Mo-N	Wld. pipe	SA-312	TP316N	S31651	...	...
42	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	1	...
(25) 43	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N	S31651	...	...
(25) 44	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N	S31651	...	...
45	16Cr-12Ni-2Mo-N	Smls. & wld. fittings	SA-403	316N	S31651	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T7
2	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T9
3	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
4	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
5	8	1	75	30	1500	NP	1500	NP	HA-2	T9
6	8	1	75	30	NP	800	1500	NP	HA-2	G5, G12, T8, W12, W14
7	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8
8	8	1	75	30	1500	NP	NP	NP	HA-2	T9
9	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
10	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
11	8	1	75	32	NP	NP	850	650	HA-4	G5, G30
12	8	1	75	32	NP	NP	850	650	HA-4	G30
13	8	1	75	32	NP	NP	1022	650	HA-2	G5, G12, G30
14	8	1	75	32	NP	NP	1022	650	HA-2	G12, G30
15	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, T8
16	8	1	75	30	NP	NP	1500	650	HA-2	G12, T9
17	8	1	70	30	NP	800	NP	NP	HA-2	G5
18	8	1	70	30	NP	800	NP	NP	HA-2	G5
19	8	1	75	30	NP	800	NP	NP	HA-2	G5
20	8	1	75	30	NP	800	NP	NP	HA-2	G5
21	8	1	75	30	NP	800	NP	NP	HA-2	G5
22	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
23	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
24	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
25	8	1	75	30	NP	800	NP	NP	HA-2	G5
26	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
27	8	1	75	30	NP	800	NP	NP	HA-2	G5
28	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
29	8	1	80	35	NP	800	NP	NP	HA-2	G5
30	8	1	80	35	1200	800	1200	NP	HA-2	G5, G12, T7
31	8	1	80	35	1200	NP	1200	NP	HA-2	G12, T8
32	8	1	80	35	NP	800	1200	650	HA-2	G5, G12, T7
33	8	1	80	35	NP	NP	1200	650	HA-2	G12, T8
34	8	1	80	35	1200	NP	NP	NP	HA-2	G5, G12, T7, W13
35	8	1	80	35	1200	NP	NP	NP	HA-2	G12, T8, W13
36	8	1	80	35	1200	NP	1200	650	HA-2	G12, G24, T8
37	8	1	80	35	1200	NP	1200	650	HA-2	G5, G12, G24, T7
38	8	1	80	35	1200	800	1200	650	HA-2	G5, G12, T7, W12, W13, W14
39	8	1	80	35	1200	NP	1200	650	HA-2	G12, T8, W13, W14
40	8	1	80	35	1200	NP	1200	650	HA-2	G12, G24, T8
41	8	1	80	35	1200	NP	1200	650	HA-2	G5, G12, G24, T7
42	8	1	80	35	NP	800	NP	NP	HA-2	G5, W12
43	8	1	80	35	1200	800	1200	650	HA-2	G5, G12, T7
44	8	1	80	35	1200	NP	1200	650	HA-2	G12, T8
45	8	1	80	35	NP	800	1200	650	HA-2	G5, G12, T7, W12, W14

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
2	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
3	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
4	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
5	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
6	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
7	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
8	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
9	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
10	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
11	21.3	...	21.3	...	21.3	20.1	18.8	17.9	17.6	17.2	16.9	16.6	16.2	...
12	21.3	...	18.1	...	16.2	14.9	13.9	13.3	13.0	12.8	12.5	12.3	12.0	...
13	21.3	...	21.3	...	21.3	20.5	19.1	18.1	17.7	17.4	17.2	16.9	16.7	16.6
14	21.3	...	18.4	...	16.6	15.2	14.2	13.4	13.1	12.9	12.7	12.5	12.4	12.3
15	20.0	...	20.0	...	20.0	19.4	17.8	16.8	16.5	16.2	16.0	15.9	15.8	15.7
16	20.0	...	17.7	...	15.8	14.3	13.2	12.4	12.2	12.0	11.9	11.8	11.7	11.6
17	20.0	...	20.0	...	18.9	17.9	17.2	16.5	16.0	15.6	15.2	14.8	...	...
18	20.0	...	20.0	...	18.9	17.9	17.2	16.5	16.0	15.6	15.2	14.8	...	...
19	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
20	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
21	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
22	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
23	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
24	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
25	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
26	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
27	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
28	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
29	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	...	...
30	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
31	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
32	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
33	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
34	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
35	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
36	19.4	...	17.6	...	16.1	15.0	14.0	13.3	12.9	12.6	12.3	12.1	11.9	11.6
37	19.4	...	19.4	...	18.7	18.2	18.1	17.9	17.4	17.0	16.7	16.3	16.0	15.7
38	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
39	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
40	19.4	...	17.6	...	16.1	15.0	14.0	13.3	12.9	12.6	12.3	12.1	11.9	11.6
41	19.4	...	19.4	...	18.7	18.2	18.1	17.9	17.4	17.0	16.7	16.3	16.0	15.7
42	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	...	...
43	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
44	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
45	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	...
2	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
5	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
6	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
7	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
8	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	16.4	16.3	16.1	...	...	...	...	...	...	...	...	...	...	...	...
14	12.1	12.0	11.9	...	...	...	...	...	...	...	...	...	...	...	...
15	15.5	15.3	15.1	12.3	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
16	11.5	11.4	11.2	11.0	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
31	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
32	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
33	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
34	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
35	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
36	11.4	11.2	11.0	10.5	8.3	6.3	...	...	...	...	...	...	...	...	...
37	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...	...	...	...
38	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
39	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
40	11.4	11.2	11.0	10.5	8.3	6.3	...	...	...	...	...	...	...	...	...
41	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
44	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
45	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25) 1	16Cr-12Ni-2Mo-N	Bar	SA-479	316N	S31651	...	...
(25) 2	16Cr-12Ni-2Mo-N	Bar	SA-479	316N	S31651	...	...
3	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316N	S31651	...	...
4	16Cr-12Ni-2Mo-N	Wld. pipe	SA-813	TP316N	S31651	...	...
5	16Cr-12Ni-2Mo-N	Wld. pipe	SA-814	TP316N	S31651	...	...
6	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N	S31651	...	...
7	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N	S31651	...	...
8	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-11-2	...	...	≤3
9	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-13-3	...	...	≤3
10	16Cr-12Ni-2Mo-Ti	Plate	SA-240	316Ti	S31635	...	...
11	16Cr-12Ni-2Mo-Ti	Plate	SA-240	316Ti	S31635	...	...
12	17Cr-4Ni-6Mn	Plate	SA-240	201-1	S20100	...	...
13	17Cr-4Ni-6Mn	Plate	SA-240	201-1	S20100	...	...
14	17Cr-4Ni-6Mn	Plate	SA-666	201-1	S20100	...	...
15	17Cr-4Ni-6Mn	Plate	SA-666	201-1	S20100	...	...
16	17Cr-4Ni-6Mn	Plate	SA-240	201-2	S20100	...	...
17	17Cr-4Ni-6Mn	Plate	SA-666	201-2	S20100	...	...
18	17Cr-7Ni	Plate, sheet, strip	SA-240	301	S30100	...	...
19	17Cr-7Ni	Plate, sheet, strip	SA-240	301	S30100	...	...
20	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...	S30601	Sol. ann.	...
21	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...	S30601	Sol. ann.	...
22	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	...
23	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	...
24	18Cr-3Ni-12Mn	Wld. tube	SA-249	XM-29	S24000	...	...
25	18Cr-3Ni-12Mn	Wld. tube	SA-249	XM-29	S24000	...	...
26	18Cr-3Ni-12Mn	Wld. pipe	SA-312	XM-29	S24000	...	...
27	18Cr-3Ni-12Mn	Wld. pipe	SA-312	XM-29	S24000	...	...
28	18Cr-3Ni-12Mn	Bar	SA-479	XM-29	S24000	...	...
29	18Cr-3Ni-12Mn	Bar	SA-479	XM-29	S24000	...	...
30	18Cr-3Ni-12Mn	Wld. tube	SA-688	TPXM-29	S24000	...	...
31	18Cr-3Ni-12Mn	Wld. tube	SA-688	TPXM-29	S24000	...	...
32	18Cr-5Ni-3Mo	Smls. tube	SA-789	...	S31500	...	...
33	18Cr-5Ni-3Mo	Wld. tube	SA-789	...	S31500	...	...
34	18Cr-5Ni-3Mo	Smls. pipe	SA-790	...	S31500	...	...
35	18Cr-5Ni-3Mo	Wld. pipe	SA-790	...	S31500	...	...
36	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	>5
37	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	>5
38	18Cr-8Ni	Forgings	SA-965	F304L	S30403	...	...
39	18Cr-8Ni	Forgings	SA-965	F304L	S30403	...	...
40	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	≤5
41	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	≤5
42	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...	...
43	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...	...
44	18Cr-8Ni	Plate	SA-240	304L	S30403	...	...
45	18Cr-8Ni	Plate	SA-240	304L	S30403	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	80	35	1200	800	NP	NP	HA-2	G5, G12, T7
2	8	1	80	35	1200	NP	NP	NP	HA-2	G12, T8
3	8	1	80	35	NP	800	NP	NP	HA-2	G5, W12
4	8	1	80	35	NP	800	NP	NP	HA-2	G5, W12
5	8	1	80	35	NP	800	NP	NP	HA-2	G5, W12
6	8	1	80	35	NP	800	1200	650	HA-2	G5, G12, T7
7	8	1	80	35	NP	NP	1200	650	HA-2	G12, T8
8	8	1	84	41	NP	NP	800	650	HA-2	G5, G30
9	8	1	84	41	NP	NP	800	650	HA-2	G5, G30
10	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, T8
11	8	1	75	30	NP	NP	1500	650	HA-2	G12, T9
12	8	3	75	38	NP	NP	300	300	HA-2	...
13	8	3	75	38	NP	NP	300	300	HA-2	G5
14	8	3	75	38	NP	NP	300	300	HA-2	...
15	8	3	75	38	NP	NP	300	300	HA-2	G5
16	8	3	95	45	NP	NP	300	300	HA-6	...
17	8	3	95	45	NP	NP	300	300	HA-6	...
18	8	1	75	30	NP	NP	800	NP	HA-1	G5
19	8	1	75	30	NP	NP	800	NP	HA-1	...
20	8	1	78	37	NP	NP	500	NP	HA-1	G5, H6
21	8	1	78	37	NP	NP	500	NP	HA-1	H6
22	8	3	100	55	NP	NP	800	650	HA-6	G5
23	8	3	100	55	NP	NP	800	650	HA-6	...
24	8	3	100	55	NP	NP	800	650	HA-6	G5, G24
25	8	3	100	55	NP	NP	800	650	HA-6	G24
26	8	3	100	55	NP	NP	800	650	HA-6	G5, G24
27	8	3	100	55	NP	NP	800	650	HA-6	G24
28	8	3	100	55	NP	NP	800	650	HA-6	G5, G22
29	8	3	100	55	NP	NP	800	650	HA-6	G22
30	8	3	100	55	NP	NP	800	650	HA-6	G5, G24
31	8	3	100	55	NP	NP	800	650	HA-6	G24
32	10H	1	92	64	NP	NP	750	650	HA-5	G19
33	10H	1	92	64	NP	NP	750	650	HA-5	G19, G24
34	10H	1	92	64	NP	NP	750	650	HA-5	G19
35	10H	1	92	64	NP	NP	750	650	HA-5	G19, G24
36	8	1	65	25	800	800	1200	650	HA-3	G5, G21, T4
37	8	1	65	25	800	NP	1200	650	HA-3	G21, T6
38	8	1	65	25	800	800	1200	650	HA-3	G5, G21, T4
39	8	1	65	25	800	NP	1200	650	HA-3	G21, T6
40	8	1	70	25	800	800	1200	650	HA-3	G5, G21, T4
41	8	1	70	25	800	NP	1200	650	HA-3	G21, T6
42	8	1	70	25	800	800	1200	NP	HA-3	G5, G21, T4
43	8	1	70	25	800	NP	1200	NP	HA-3	G21, T6
44	8	1	70	25	800	800	1200	650	HA-3	G5, G21, T4
45	8	1	70	25	800	NP	1200	650	HA-3	G21, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
2	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
3	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	...	...
4	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	...	...
5	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	...	...
6	22.9	...	22.9	...	22.0	21.5	21.2	21.0	20.5	20.0	19.6	19.2	18.8	18.5
7	22.9	...	20.7	...	19.0	17.6	16.5	15.6	15.2	14.9	14.5	14.2	13.9	13.7
8	24.0	...	24.0	...	24.0	23.7	22.8	22.3	21.7	21.1	20.6	20.1	...	...
9	24.0	...	24.0	...	24.0	23.7	22.8	22.3	21.7	21.1	20.6	20.1	...	...
10	20.0	...	20.0	...	20.0	19.4	17.8	16.8	16.5	16.2	16.0	15.9	15.8	15.7
11	20.0	...	17.7	...	15.8	14.3	13.2	12.4	12.2	12.0	11.9	11.8	11.7	11.6
12	21.4	...	18.7	...	16.6	...	...	...	...	...	...	...	...	...
13	21.4	...	18.7	...	17.2	...	...	...	...	...	...	...	...	...
14	21.4	...	18.7	...	16.6	...	...	...	...	...	...	...	...	...
15	21.4	...	18.7	...	17.2	...	...	...	...	...	...	...	...	...
16	27.1	...	22.8	...	19.7	...	...	...	...	...	...	...	...	...
17	27.1	...	22.8	...	19.7	...	...	...	...	...	...	...	...	...
18	20.0	...	17.5	...	15.7	15.4	15.4	15.4	15.4	15.3	15.0	14.6	...	...
19	20.0	...	16.1	...	14.4	13.5	13.0	12.5	12.2	11.9	11.5	11.1	...	...
20	22.3	...	22.3	...	21.1	20.0	18.9	...	...	...	...	...	...	...
21	22.3	...	20.3	...	18.1	16.5	15.1	...	...	...	...	...	...	...
22	28.6	...	27.9	...	26.0	24.9	24.3	23.8	23.4	23.0	22.4	21.8	...	...
23	28.6	...	27.9	...	25.0	21.9	20.1	19.2	18.8	18.5	18.2	17.8	...	...
24	24.3	...	23.7	...	22.1	21.2	20.7	20.2	19.9	19.5	19.1	18.5	...	...
25	24.3	...	23.7	...	21.3	18.7	17.1	16.3	16.0	15.7	15.4	15.1	...	...
26	24.3	...	23.7	...	22.1	21.2	20.7	20.2	19.9	19.5	19.1	18.5	...	...
27	24.3	...	23.7	...	21.3	18.7	17.1	16.3	16.0	15.7	15.4	15.1	...	...
28	28.6	...	27.9	...	26.0	24.9	24.3	23.8	23.4	23.0	22.4	21.8	...	...
29	28.6	...	27.9	...	25.0	21.9	20.1	19.2	18.8	18.5	18.2	17.8	...	...
30	24.3	...	23.7	...	22.1	21.2	20.7	20.2	19.9	19.5	19.1	18.5	...	...
31	24.3	...	23.7	...	21.3	18.7	17.1	16.3	16.0	15.7	15.4	15.1	...	...
32	26.3	...	25.4	...	24.4	24.2	24.2	24.2	24.2	24.2	24.2	...	...	...
33	22.3	...	21.6	...	20.7	20.6	20.6	20.6	20.6	20.6	20.6	...	...	...
34	26.3	...	25.4	...	24.4	24.2	24.2	24.2	24.2	24.2	24.2	...	...	...
35	22.3	...	21.6	...	20.7	20.6	20.6	20.6	20.6	20.6	20.6	...	...	...
36	16.7	...	16.7	...	16.2	15.6	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
37	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
38	16.7	...	16.7	...	16.2	15.6	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
39	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
40	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
41	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
42	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
43	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
44	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
45	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
2	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
7	13.4	13.2	12.9	12.3	9.8	7.4	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	15.5	15.3	15.1	12.3	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
11	11.5	11.4	11.2	11.0	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
37	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
38	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
39	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
40	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
41	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
42	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
43	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
44	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
45	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...
2	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...
3	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...
4	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304L	S30403	...	...
5	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	...	...
6	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...
7	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...
8	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	1	...
9	18Cr-8Ni	Smls. & wld. fittings	SA-403	304L	S30403	...	...
10	18Cr-8Ni	Wld. pipe	SA-409	TP304L	S30403	...	...
11	18Cr-8Ni	Bar	SA-479	304L	S30403	...	...
12	18Cr-8Ni	Bar	SA-479	304L	S30403	...	...
13	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...
14	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...
15	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...
16	18Cr-8Ni	Wld. pipe	SA-813	TP304L	S30403	...	...
17	18Cr-8Ni	Wld. pipe	SA-814	TP304L	S30403	...	...
18	18Cr-8Ni	Bar	SA/JIS G4303	SUS304L	...	...	...
19	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	>5
20	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	>5
21	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	>5
22	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	>5
23	18Cr-8Ni	Castings	SA-351	CF3	J92500	...	...
24	18Cr-8Ni	Castings	SA-351	CF3	J92500	...	...
(25) 25	18Cr-8Ni	Castings	SA-351	CF8	J92600	...	...
(25) 26	18Cr-8Ni	Castings	SA-351	CF8	J92600	...	...
27	18Cr-8Ni	Castings	SA-351	CF8	J92600	...	...
28	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	≥8
29	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	≥8
30	18Cr-8Ni	Cast pipe	SA-451	CPF3	J92500	...	...
31	18Cr-8Ni	Cast pipe	SA-451	CPF8	J92600	...	...
32	18Cr-8Ni	Forgings	SA-965	F304	S30400	...	...
33	18Cr-8Ni	Forgings	SA-965	F304	S30400	...	...
34	18Cr-8Ni	Forgings	SA-965	F304H	S30409	...	...
35	18Cr-8Ni	Forgings	SA-965	F304H	S30409	...	...
36	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9	...	...	≤3
37	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9	...	...	≤3
38	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	≤5
39	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	≤5
40	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	≤5
41	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	≤5
42	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...	...
43	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...	...
44	18Cr-8Ni	Smls. tube	SA-213	TP304H	S30409	...	...
45	18Cr-8Ni	Smls. tube	SA-213	TP304H	S30409	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
2	8	1	70	25	800	NP	1200	650	HA-3	G5, G21, G24, T4
3	8	1	70	25	800	NP	1200	650	HA-3	G21, G24, T6
4	8	1	70	25	800	800	1200	650	HA-3	G5, G21, T4, W12, W14
5	8	1	70	25	800	NP	1200	650	HA-3	G21, T6
6	8	1	70	25	800	NP	1200	650	HA-3	G5, G21, G24, T4
7	8	1	70	25	800	NP	1200	650	HA-3	G21, G24, T6
8	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
9	8	1	70	25	NP	800	1200	650	HA-3	G5, T4, W12, W14
10	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
11	8	1	70	25	800	800	1200	650	HA-3	G5, G21, G22, T4
12	8	1	70	25	800	NP	1200	650	HA-3	G21, G22, T6
13	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
14	8	1	70	25	NP	NP	1200	650	HA-3	G5, G24, T4
15	8	1	70	25	NP	NP	1200	650	HA-3	G24, T6
16	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
17	8	1	70	25	NP	800	NP	NP	HA-3	G5, W12
18	8	1	70	25	800	800	1200	NP	HA-3	G5, G21, G22, T4
19	8	1	70	30	1500	800	1500	650	HA-1	G5, G12, T7
20	8	1	70	30	1500	NP	1500	650	HA-1	G12, T8
21	8	1	70	30	1500	800	1500	NP	HA-1	G5, T7
22	8	1	70	30	1500	NP	1500	NP	HA-1	T8
23	8	1	70	30	NP	800	800	650	HA-3	G1, G5, G16, G17, G19
24	8	1	70	30	NP	NP	800	650	HA-3	G1, G19
25	8	1	70	30	1500	800	NP	NP	HA-1	G1, G5, G12, G16, G17, G19, T6
26	8	1	70	30	1500	NP	1500	650	HA-1	G1, G12, G19, T7
27	8	1	70	30	NP	NP	1500	650	HA-1	G1, G5, G12, G19, T6
28	8	1	70	30	NP	800	1500	650	HA-1	G5, G12, S9, T7
29	8	1	70	30	NP	NP	1500	650	HA-1	G12, S9, T8
30	8	1	70	30	NP	800	NP	NP	HA-3	G5, G16, G17, G19
31	8	1	70	30	NP	800	NP	NP	HA-1	G5, G16, G17, G19
32	8	1	70	30	1500	800	1500	650	HA-1	G5, G12, T7
33	8	1	70	30	1500	NP	1500	650	HA-1	G12, T8
34	8	1	70	30	NP	800	1500	NP	HA-1	G5, T7
35	8	1	70	30	NP	NP	1500	NP	HA-1	T8
36	8	1	72.5	29	NP	NP	1022	650	HA-3	G5, G30, T4
37	8	1	72.5	29	NP	NP	1022	650	HA-3	G30, T6
38	8	1	75	30	1500	NP	1500	NP	HA-1	G12, T8
39	8	1	75	30	1500	800	1500	NP	HA-1	G5, G12, T7
40	8	1	75	30	1500	NP	1500	NP	HA-1	T8
41	8	1	75	30	1500	800	1500	NP	HA-1	G5, T7
42	8	1	75	30	1500	NP	1500	NP	HA-1	G12, T8
43	8	1	75	30	1500	800	1500	NP	HA-1	G5, G12, T7
44	8	1	75	30	1500	NP	1500	NP	HA-1	T8
45	8	1	75	30	1500	800	1500	NP	HA-1	G5, T7

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
2	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	10.9	10.1
3	14.2	...	12.1	...	10.9	9.9	9.3	8.8	8.6	8.5	8.3	8.2	8.1	7.9
4	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
5	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
6	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	10.9	10.1
7	14.2	...	12.1	...	10.9	9.9	9.3	8.8	8.6	8.5	8.3	8.2	8.1	7.9
8	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
9	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
10	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
11	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
12	16.7	...	14.3	...	12.8	11.7	10.9	10.4	10.2	10.0	9.8	9.7	9.5	9.3
13	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
14	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	10.9	10.1
15	14.2	...	12.1	...	10.9	9.9	9.3	8.8	8.6	8.5	8.3	8.2	8.1	7.9
16	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
17	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
18	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	12.8	11.9
19	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
20	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
21	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
22	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
23	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	...	...
24	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	...	...
25	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
26	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
27	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
28	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
29	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
30	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	...	...
31	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	...	...
32	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
33	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
34	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	14.9	14.6
35	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
36	19.3	...	19.3	...	19.3	18.3	17.1	16.2	15.9	15.6	15.4	15.2	14.9	11.9
37	19.3	...	16.5	...	14.9	13.6	12.6	12.0	11.8	11.6	11.4	11.2	11.0	10.8
38	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
39	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
40	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
41	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
42	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
43	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
44	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
45	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	8.4	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
3	7.7	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
4	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
5	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
6	8.4	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
7	7.7	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
12	9.1	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	8.4	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
15	7.7	6.6	5.4	4.3	3.4	2.7	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	9.9	7.8	6.3	5.1	4.0	3.2	...	...	...	...	...	...	...	...	...
19	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
20	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
21	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
22	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	14.3	12.2	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7	...	...	...
26	10.6	10.4	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7	...	...	...
27	14.3	12.2	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7	...	...	...
28	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
29	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
33	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
34	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
35	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
36	9.9	7.8	6.3	...	...	...	...	...	...	...	...	...	...	...	...
37	10.6	7.8	6.3	...	...	...	...	...	...	...	...	...	...	...	...
38	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
39	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
40	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
41	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
42	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
43	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
44	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
45	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-8Ni	Plate	SA-240	302	S30200	...	...
2	18Cr-8Ni	Plate	SA-240	302	S30200	...	...
3	18Cr-8Ni	Plate	SA-240	304	S30400	...	...
(25) 4	18Cr-8Ni	Plate	SA-240	304	S30400	...	...
5	18Cr-8Ni	Plate	SA-240	304H	S30409	...	...
6	18Cr-8Ni	Plate	SA-240	304H	S30409	...	...
7	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...
8	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...
(25) 9	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...
(25) 10	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...
11	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...
12	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...
(25) 13	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...
(25) 14	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...
15	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304	S30400	...	...
16	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304	S30400	...	...
(25) 17	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...
(25) 18	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...
19	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304H	S30409	...	...
20	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304H	S30409	...	...
(25) 21	18Cr-8Ni	Wld. pipe	SA-312	TP304H	S30409	...	...
(25) 22	18Cr-8Ni	Wld. pipe	SA-312	TP304H	S30409	...	...
23	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	1	...
24	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	1	...
25	18Cr-8Ni	Wld. pipe	SA-358	304LN	S30453	1	...
(25) 26	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	<8
(25) 27	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	<8
(25) 28	18Cr-8Ni	Smls. pipe	SA-376	TP304H	S30409	...	...
(25) 29	18Cr-8Ni	Smls. pipe	SA-376	TP304H	S30409	...	...
30	18Cr-8Ni	Smls. & wld. fittings	SA-403	304	S30400	...	...
31	18Cr-8Ni	Smls. & wld. fittings	SA-403	304H	S30409	...	...
32	18Cr-8Ni	Wld. pipe	SA-409	TP304	S30400	...	...
33	18Cr-8Ni	Bar	SA-479	302	S30200	...	...
34	18Cr-8Ni	Bar	SA-479	302	S30200	...	...
35	18Cr-8Ni	Bar	SA-479	304	S30400	...	...
36	18Cr-8Ni	Bar	SA-479	304	S30400	...	...
37	18Cr-8Ni	Bar	SA-479	304H	S30409	...	...
38	18Cr-8Ni	Bar	SA-479	304H	S30409	...	...
39	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...
40	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...
41	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...
42	18Cr-8Ni	Wld. pipe	SA-813	TP304	S30400	...	...
43	18Cr-8Ni	Wld. pipe	SA-813	TP304H	S30409	...	...
44	18Cr-8Ni	Wld. pipe	SA-814	TP304	S30400	...	...
45	18Cr-8Ni	Wld. pipe	SA-814	TP304H	S30409	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature											
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes	
					(NP = Not Permitted)						
					(SPT = Supports Only)						
					I	III	VIII-1	XII			
1	8	1	75	30	NP	NP	750	650	HA-1	G5	
2	8	1	75	30	NP	NP	750	650	HA-1	...	
3	8	1	75	30	1500	NP	1500	650	HA-1	G12, T8	
4	8	1	75	30	1500	800	1500	650	HA-1	G5, G12, T7	
5	8	1	75	30	1500	800	1500	NP	HA-1	G5, T7	
6	8	1	75	30	1500	NP	1500	NP	HA-1	T8	
7	8	1	75	30	1500	NP	NP	NP	HA-1	G12, T8, W13	
8	8	1	75	30	1500	800	NP	NP	HA-1	G5, G12, T7, W12, W13	
9	8	1	75	30	1500	NP	1500	650	HA-1	G5, G12, G24, T7	
10	8	1	75	30	1500	NP	1500	650	HA-1	G12, G24, T8	
11	8	1	75	30	1500	NP	NP	NP	HA-1	T8, W13	
12	8	1	75	30	1500	800	NP	NP	HA-1	G5, T7, W12, W13	
13	8	1	75	30	1500	NP	1500	NP	HA-1	G5, G24, T7	
14	8	1	75	30	1500	NP	1500	NP	HA-1	G24, T8	
15	8	1	75	30	1500	800	1500	650	HA-1	G5, G12, T7, W12, W13, W14	
16	8	1	75	30	1500	NP	1500	650	HA-1	G12, T8, W13, W14	
17	8	1	75	30	1500	NP	1500	650	HA-1	G5, G12, G24, T7	
18	8	1	75	30	1500	NP	1500	650	HA-1	G12, G24, T8	
19	8	1	75	30	1500	800	1500	NP	HA-1	G5, T7, W12, W13, W14	
20	8	1	75	30	1500	NP	1500	NP	HA-1	T8, W13, W14	
21	8	1	75	30	1500	NP	1500	NP	HA-1	G5, G24, T7	
22	8	1	75	30	1500	NP	1500	NP	HA-1	G24, T8	
23	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
24	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
25	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
26	8	1	75	30	1500	800	1500	650	HA-1	G5, G12, S11, T7	
27	8	1	75	30	1500	NP	1500	650	HA-1	G12, S11, T8	
28	8	1	75	30	1500	800	1500	NP	HA-1	G5, T7	
29	8	1	75	30	1500	NP	1500	NP	HA-1	T8	
30	8	1	75	30	NP	800	1500	650	HA-1	G5, G12, T7, W12, W14	
31	8	1	75	30	NP	800	1500	NP	HA-1	G5, T7, W12, W14	
32	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
33	8	1	75	30	NP	800	750	650	HA-1	G5, G24	
34	8	1	75	30	NP	NP	750	650	HA-1	G22	
35	8	1	75	30	1500	800	1500	650	HA-1	G5, G12, G22, T7	
36	8	1	75	30	1500	NP	1500	650	HA-1	G12, G22, T8	
37	8	1	75	30	1500	800	1500	NP	HA-1	G5, G22, T7	
38	8	1	75	30	1500	NP	1500	NP	HA-1	G22, T8	
39	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
40	8	1	75	30	NP	NP	1500	650	HA-1	G5, G12, G24, T7	
41	8	1	75	30	NP	NP	1500	650	HA-1	G12, G24, T8	
42	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
43	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
44	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	
45	8	1	75	30	NP	800	NP	NP	HA-1	G5, W12	

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	...	...	...
2	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	...	...	...
3	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
4	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
5	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
6	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
7	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
8	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
9	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
10	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
11	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
12	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
13	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
14	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
15	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
16	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
17	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
18	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
19	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
20	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
21	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
22	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
23	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
24	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
25	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
26	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
27	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
28	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
29	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
30	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
31	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
32	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
33	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
34	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	...	...	...
35	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
36	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
37	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
38	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
39	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
40	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
41	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
42	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
43	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
44	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
45	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
4	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
5	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
6	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
7	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
8	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
9	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
10	9.0	8.8	8.6	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
11	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
12	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
13	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
14	9.0	8.8	8.6	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
15	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
16	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
17	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
18	9.0	8.8	8.6	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
19	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
20	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
21	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
22	9.0	8.8	8.6	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
27	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
28	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
29	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
30	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
31	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
36	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
37	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
38	10.6	10.4	10.1	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
41	9.0	8.8	8.6	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-8Ni	Bar	SA/JIS G4303	SUS302	...	...	...
2	18Cr-8Ni	Bar	SA/JIS G4303	SUS304	...	...	...
3	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10	...	...	≤3
4	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10	...	...	≤3
5	18Cr-8Ni	Castings	SA-351	CF3A	J92500	...	...
6	18Cr-8Ni	Castings	SA-351	CF3A	J92500	...	...
7	18Cr-8Ni	Castings	SA-351	CF8A	J92600	...	...
8	18Cr-8Ni	Castings	SA-351	CF8A	J92600	...	...
9	18Cr-8Ni	Cast pipe	SA-451	CPF3A	J92500	...	...
10	18Cr-8Ni	Cast pipe	SA-451	CPF8A	J92600	...	...
11	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...	>5
12	18Cr-8Ni-N	Forgings	SA-965	F304LN	S30453	...	...
13	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...	≤5
14	18Cr-8Ni-N	Smls. tube	SA-213	TP304LN	S30453	...	...
15	18Cr-8Ni-N	Plate	SA-240	304LN	S30453	...	...
16	18Cr-8Ni-N	Wld. tube	SA-249	TP304LN	S30453	...	...
17	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304LN	S30453	...	...
18	18Cr-8Ni-N	Smls. pipe	SA-376	TP304LN	S30453	...	...
19	18Cr-8Ni-N	Smls. & wld. fittings	SA-403	304LN	S30453	WP	...
20	18Cr-8Ni-N	Bar	SA-479	304LN	S30453	...	...
21	18Cr-8Ni-N	Wld. tube	SA-688	TP304LN	S30453	...	...
22	18Cr-8Ni-N	Wld. pipe	SA-813	TP304LN	S30453	...	...
23	18Cr-8Ni-N	Wld. pipe	SA-814	TP304LN	S30453	...	...
24	18Cr-8Ni-N	Forgings	SA-182	F304N	S30451	...	...
25	18Cr-8Ni-N	Smls. tube	SA-213	TP304N	S30451	...	...
26	18Cr-8Ni-N	Smls. tube	SA-213	TP304N	S30451	...	...
27	18Cr-8Ni-N	Plate	SA-240	304N	S30451	...	...
28	18Cr-8Ni-N	Plate	SA-240	304N	S30451	...	...
29	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...
30	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...
(25) 31	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...
(25) 32	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...
33	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...
34	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304N	S30451	...	...
35	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304N	S30451	...	...
(25) 36	18Cr-8Ni-N	Wld. pipe	SA-312	TP304N	S30451	...	...
(25) 37	18Cr-8Ni-N	Wld. pipe	SA-312	TP304N	S30451	...	...
38	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	1	...
(25) 39	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N	S30451	...	...
(25) 40	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N	S30451	...	...
41	18Cr-8Ni-N	Smls. & wld. fittings	SA-403	304N	S30451	...	...
42	18Cr-8Ni-N	Bar	SA-479	304N	S30451	...	...
43	18Cr-8Ni-N	Bar	SA-479	304N	S30451	...	...
44	18Cr-8Ni-N	Wld. tube	SA-688	TP304N	S30451	...	...
45	18Cr-8Ni-N	Wld. tube	SA-688	TP304N	S30451	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	75	30	NP	800	750	NP	HA-1	G5, G24
2	8	1	75	30	1500	800	1500	NP	HA-1	G5, G12, G22, T7
3	8	1	75	31	NP	NP	1022	650	HA-1	G5, G12, G30, H1, T7
4	8	1	75	31	NP	NP	1022	650	HA-1	G12, G30
5	8	1	77	35	NP	650	700	650	HA-3	G1, G5, G16, G17, G19
6	8	1	77	35	NP	NP	700	650	HA-3	G1, G19
7	8	1	77	35	NP	650	650	650	HA-1	G1, G5, G16, G17, G19
8	8	1	77	35	NP	NP	650	650	HA-1	G1, G19
9	8	1	77	35	NP	650	NP	NP	HA-3	G5, G16, G17, G19
10	8	1	77	35	NP	650	NP	NP	HA-1	G5, G16, G17, G19
11	8	1	70	30	NP	800	800	NP	HA-1	G5
12	8	1	70	30	NP	800	800	NP	HA-1	G5
13	8	1	75	30	NP	800	800	NP	HA-1	G5
14	8	1	75	30	NP	800	800	NP	HA-1	G5
15	8	1	75	30	NP	800	800	NP	HA-1	G5
16	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
17	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
18	8	1	75	30	NP	800	800	NP	HA-1	G5
19	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
20	8	1	75	30	NP	800	800	NP	HA-1	G5
21	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
22	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
23	8	1	75	30	NP	800	800	NP	HA-1	G5, W12, W14
24	8	1	80	35	NP	800	NP	NP	HA-1	G5
25	8	1	80	35	1200	800	1200	NP	HA-1	G5, G12, T7
26	8	1	80	35	1200	NP	1200	NP	HA-1	G12, T8
27	8	1	80	35	NP	800	1200	650	HA-1	G5, G12, T7
28	8	1	80	35	NP	NP	1200	650	HA-1	G12, T8
29	8	1	80	35	1200	NP	NP	NP	HA-1	G5, G12, T7, W13
30	8	1	80	35	1200	NP	NP	NP	HA-1	G12, T8, W13
31	8	1	80	35	1200	NP	NP	NP	HA-1	G5, G12, G24, T5
32	8	1	80	35	1200	NP	1200	650	HA-1	G12, G24, T8
33	8	1	80	35	NP	NP	1200	650	HA-1	G5, G12, G24, T5
34	8	1	80	35	1200	800	1200	650	HA-1	G5, G12, T7, W12, W13, W14
35	8	1	80	35	1200	NP	1200	650	HA-1	G12, T8, W13, W14
36	8	1	80	35	1200	NP	1200	650	HA-1	G5, G12, G24, T5
37	8	1	80	35	1200	NP	1200	650	HA-1	G12, G24, T8
38	8	1	80	35	NP	800	NP	NP	HA-1	G5, W12
39	8	1	80	35	1200	800	1200	650	HA-1	G5, G12, T7
40	8	1	80	35	1200	NP	1200	650	HA-1	G12, T8
41	8	1	80	35	NP	800	1200	650	HA-1	G5, T7, W12, W14
42	8	1	80	35	1200	NP	NP	NP	HA-1	G12, T8
43	8	1	80	35	1200	800	NP	NP	HA-1	G5, G12, T7
44	8	1	80	35	NP	800	NP	NP	HA-1	G5, W12
45	8	1	80	35	NP	NP	1200	650	HA-1	G5, G12, G24, T7

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
2	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
3	20.3	...	20.3	...	20.3	18.9	17.7	16.8	16.4	16.1	15.7	15.4	15.1	14.8
4	20.3	...	16.9	...	15.2	14.0	13.1	12.5	12.2	11.9	11.7	11.4	11.2	11.0
5	22.0	...	20.8	...	19.4	18.8	18.6	18.6	18.6	18.5	...	...	...	...
6	22.0	...	19.5	...	17.5	16.1	15.1	14.3	14.0	13.7	...	...	...	...
7	22.0	...	20.8	...	19.4	18.8	18.6	18.6	18.6	...	...	...	...	...
8	22.0	...	19.5	...	17.5	16.1	15.1	14.3	14.0	...	...	...	...	...
9	22.0	...	20.8	...	19.4	18.8	18.6	18.6	18.6	...	...	...	...	...
10	22.0	...	20.8	...	19.4	18.8	18.6	18.6	18.6	...	...	...	...	...
11	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	...	...
12	20.0	...	18.9	...	17.7	17.1	16.9	16.6	16.2	15.8	15.5	15.2	...	...
13	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
14	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
15	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
16	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
17	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
18	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
19	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
20	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
21	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
22	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
23	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
24	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
25	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
26	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
27	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
28	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
29	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
30	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
31	19.4	...	19.4	...	18.5	17.3	16.0	15.2	14.9	14.6	14.4	14.1	13.8	13.6
32	19.4	...	16.2	...	14.2	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.0
33	19.4	...	19.4	...	18.5	17.3	16.0	15.2	14.9	14.6	14.4	14.1	13.8	13.6
34	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
35	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
36	19.4	...	19.4	...	18.5	17.3	16.0	15.2	14.9	14.6	14.4	14.1	13.8	13.6
37	19.4	...	16.2	...	14.2	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.0
38	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
39	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
40	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
41	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
42	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
43	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
44	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
45	19.4	...	19.4	...	18.5	17.3	16.0	15.2	14.9	14.6	14.4	14.1	13.8	13.6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
3	14.5	14.2	12.4	...	...	...	...	...	...	...	...	...	...	...	...
4	10.7	10.5	10.3	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
26	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
27	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
28	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
29	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
30	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
31	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...	...	...	(25)
32	9.8	9.6	9.4	8.3	6.6	5.2	...	...	...	...	...	...	...	...	(25)
33	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...	...	...	...
34	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
35	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
36	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...	...	...	(25)
37	9.8	9.6	9.4	8.3	6.6	5.2	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	(25)
40	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	(25)
41	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
42	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
43	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-8Ni-N	Wld. tube	SA-688	TP304N	S30451	...	...
2	18Cr-8Ni-N	Wld. pipe	SA-813	TP304N	S30451	...	...
3	18Cr-8Ni-N	Wld. pipe	SA-814	TP304N	S30451	...	...
4	18Cr-8Ni-N	Forgings	SA-965	F304N	S30451	...	...
5	18Cr-8Ni-N	Forgings	SA-965	F304N	S30451	...	...
6	18Cr-8Ni-N	Plate	SA/EN 10028-7	X2CrNiN18-10	...	...	≤3
7	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9	...	...	≤3
8	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9	...	...	≤3
9	18Cr-8Ni-4Si-N	Bar	SA-479	...	S21800	...	...
10	18Cr-9Ni-3Cu-Cb-N	Smls. tube	SA-213	...	S30432	...	...
11	18Cr-9Ni-3Cu-Cb-N	Smls. tube	SA-213	...	S30432	...	...
(25) 12	18Cr-10Ni-Cb	Forgings	SA-965	F348H	S34809	...	...
(25) 13	18Cr-10Ni-Cb	Forgings	SA-965	F348H	S34809	...	...
14	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	...
15	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	...
16	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	...
17	18Cr-10Ni-Cb	Cast pipe	SA-451	CPF8C	J92710	...	...
18	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	>5
(25) 19	18Cr-10Ni-Cb	Forgings	SA-965	F347	S34700	...	...
(25) 20	18Cr-10Ni-Cb	Forgings	SA-965	F347	S34700	...	...
(25) 21	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	>5
(25) 22	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	>5
(25) 23	18Cr-10Ni-Cb	Forgings	SA-965	F347H	S34709	...	...
(25) 24	18Cr-10Ni-Cb	Forgings	SA-965	F347H	S34709	...	...
25	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	>5
26	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	>5
(25) 27	18Cr-10Ni-Cb	Forgings	SA-965	F348	S34800	...	...
(25) 28	18Cr-10Ni-Cb	Forgings	SA-965	F348	S34800	...	...
29	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	>5
30	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	>5
(25) 31	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	≤5
(25) 32	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	≤5
(25) 33	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347	S34700	...	...
(25) 34	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347	S34700	...	...
35	18Cr-10Ni-Cb	Plate	SA-240	347	S34700	...	...
36	18Cr-10Ni-Cb	Plate	SA-240	347	S34700	...	...
37	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...
38	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...
(25) 39	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...
(25) 40	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...
41	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347	S34700	...	...
42	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347	S34700	...	...
(25) 43	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347	S34700	...	...
(25) 44	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347	S34700	...	...
(25) 45	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	1	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	(NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	8	1	80	35	NP	NP	1200	650	HA-1	G12, G24, T8
2	8	1	80	35	NP	800	NP	NP	HA-1	G5, W12
3	8	1	80	35	NP	800	NP	NP	HA-1	G5, W12
4	8	1	80	35	NP	800	1200	650	HA-1	G5, G12, T7
5	8	1	80	35	NP	NP	1200	650	HA-1	G12, T8
6	8	1	80	39	NP	NP	800	650	HA-1	G5, G30
7	8	1	80	39	NP	NP	1022	650	HA-1	G5, G12, G30, T7
8	8	1	80	39	NP	NP	1022	650	HA-1	G12, G30
9	8	3	95	50	NP	800	NP	NP	HA-6	...
10	8	1	86	34	1500	NP	1500	NP	HA-2	G5, T12
11	8	1	86	34	1500	NP	1500	NP	HA-2	T12
12	8	1	65	25	NP	NP	1500	NP	HA-2	G5, T9
13	8	1	65	25	NP	NP	1500	NP	HA-2	T9
14	8	1	70	30	NP	800	NP	NP	HA-2	G5, G16, G17, G19
15	8	1	70	30	NP	NP	1500	650	HA-2	G1, G5, G12, G19, T7
16	8	1	70	30	NP	NP	1500	650	HA-2	G1, G12, G19, T7
17	8	1	70	30	NP	800	NP	NP	HA-2	G5, G16, G17, G19
18	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T7
19	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T7
20	8	1	70	30	1500	NP	1500	650	HA-2	G12, T7
21	8	1	70	30	1500	NP	NP	NP	HA-2	T9
22	8	1	70	30	1500	800	1500	NP	HA-2	G5, T8
23	8	1	70	30	NP	NP	1500	NP	HA-2	T9
24	8	1	70	30	NP	800	1500	NP	HA-2	G5, T8
25	8	1	70	30	1500	NP	NP	NP	HA-2	T7
26	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T7
27	8	1	70	30	NP	NP	1500	650	HA-2	G5, G12, T7
28	8	1	70	30	NP	NP	1500	650	HA-2	G12, T7
29	8	1	70	30	1500	NP	NP	NP	HA-2	T9
30	8	1	70	30	1500	800	1500	NP	HA-2	G5, T8
31	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T6
32	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
33	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T6
34	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
35	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T6
36	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7
37	8	1	75	30	1500	NP	NP	NP	HA-2	G12, T7, W13
38	8	1	75	30	1500	800	NP	NP	HA-2	G5, G12, T6, W12, W13
39	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T6
40	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T7
41	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T6, W12, W13, W14
42	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7, W13, W14
43	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T6
44	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T7
45	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	19.4	...	16.2	...	14.2	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.0
2	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
3	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
4	22.9	...	22.9	...	21.7	20.3	18.9	17.9	17.5	17.2	16.9	16.6	16.3	16.0
5	22.9	...	19.1	...	16.7	15.1	14.0	13.3	13.0	12.8	12.5	12.3	12.1	11.8
6	22.8	...	22.8	...	22.3	21.4	21.1	21.1	21.1	20.7	20.2	19.8	...	...
7	22.8	...	22.8	...	22.8	22.7	21.1	20.0	19.6	19.3	18.9	18.6	18.2	17.8
8	22.8	...	21.3	...	18.7	16.8	15.6	14.8	14.5	14.3	14.0	13.8	13.5	13.2
9	27.1	...	25.9	...	22.1	19.8	18.4	17.6	17.3	17.1	16.9	16.8	...	...
10	22.7	...	22.7	...	22.7	22.7	21.9	21.1	20.7	20.4	20.1	19.8	19.5	19.2
11	22.7	...	19.8	...	18.2	17.1	16.3	15.6	15.3	15.1	14.9	14.6	14.4	14.2
12	16.7	...	16.7	...	16.3	15.4	14.9	14.6	14.6	14.6	14.6	14.6	14.5	14.5
13	16.7	...	15.3	...	14.3	13.3	12.5	11.9	11.7	11.5	11.4	11.3	11.2	11.2
14	20.0	...	19.1	...	17.6	16.6	16.0	15.7	15.7	15.7	15.7	15.7	...	...
15	20.0	...	19.1	...	17.6	16.6	16.0	15.8	15.7	15.7	15.7	15.7	15.7	15.6
16	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
17	20.0	...	19.1	...	17.6	16.6	16.0	15.7	15.7	15.7	15.7	15.7	...	...
18	20.0	...	19.1	...	17.6	16.6	16.0	15.8	15.7	15.7	15.7	15.7	15.7	15.6
19	20.0	...	19.1	...	17.6	16.6	16.0	15.8	15.7	15.7	15.7	15.7	15.7	15.6
20	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
21	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
22	20.0	...	19.1	...	17.6	16.6	16.0	15.7	15.7	15.7	15.7	15.7	15.7	15.6
23	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
24	20.0	...	19.1	...	17.6	16.6	16.0	15.7	15.7	15.7	15.7	15.7	15.7	15.6
25	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
26	20.0	...	19.1	...	17.6	16.6	16.0	15.8	15.7	15.7	15.7	15.7	15.7	15.6
27	20.0	...	19.1	...	17.6	16.6	16.0	15.8	15.7	15.7	15.7	15.7	15.7	15.6
28	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
29	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
30	20.0	...	19.1	...	17.6	16.6	16.0	15.7	15.7	15.7	15.7	15.7	15.7	15.6
31	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
32	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
33	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
34	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
35	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
36	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
37	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
38	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
39	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
40	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
41	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
42	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
43	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
44	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
45	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	9.8	9.6	9.4	8.3	6.6	5.2	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
5	11.6	11.3	11.0	9.8	7.7	6.1	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	17.4	17.0	12.4	...	...	...	...	...	...	...	...	...	...	...	...
8	12.9	12.6	12.3	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	18.9	18.6	18.3	18.1	14.7	11.4	8.7	6.5	4.7	3.3	2.2	1.5	...	...	...
11	14.0	13.8	13.6	13.4	13.2	11.4	8.7	6.5	4.7	3.3	2.2	1.5	...	...	...
12	14.4	14.2	14.0	13.7	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
13	11.2	11.2	11.1	11.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	15.5	15.3	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
16	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	15.5	15.3	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
19	15.5	15.3	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
20	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
21	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
22	15.5	15.3	15.1	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
23	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
24	15.5	15.3	15.1	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	(25)
25	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
26	15.5	15.3	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
27	15.5	15.3	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
28	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
29	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
30	15.5	15.3	15.1	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
31	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
32	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
33	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
34	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	(25)
35	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
36	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
37	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
38	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
39	14.1	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	(25)
40	11.4	11.4	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	(25)
41	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
42	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
43	14.1	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	(25)
44	11.4	11.4	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25) 1	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347	S34700	...	...
(25) 2	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347	S34700	...	...
3	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	347	S34700	...	...
(25) 4	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP347	S34700	...	...
5	18Cr-10Ni-Cb	Bar	SA-479	347	S34700	...	...
6	18Cr-10Ni-Cb	Bar	SA-479	347	S34700	...	...
(25) 7	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347	S34700	...	...
8	18Cr-10Ni-Cb	Bar	SA/JIS G4303	SUS347	...	...	...
(25) 9	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	≤5
(25) 10	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	≤5
(25) 11	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H	S34709	...	...
(25) 12	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H	S34709	...	...
(25) 13	18Cr-10Ni-Cb	Plate	SA-240	347H	S34709	...	...
(25) 14	18Cr-10Ni-Cb	Plate	SA-240	347H	S34709	...	...
15	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...
16	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...
(25) 17	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...
(25) 18	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...
(25) 19	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347H	S34709	...	...
(25) 20	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347H	S34709	...	...
(25) 21	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347H	S34709	...	...
(25) 22	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347H	S34709	...	...
(25) 23	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H	S34709	...	...
(25) 24	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H	S34709	...	...
(25) 25	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	347H	S34709	...	...
(25) 26	18Cr-10Ni-Cb	Bar	SA-479	347H	S34709	...	...
(25) 27	18Cr-10Ni-Cb	Bar	SA-479	347H	S34709	...	...
(25) 28	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347H	S34709	...	...
29	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP347H	S34709	...	...
30	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347LN	S34751	...	...
31	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347LN	S34751	...	...
32	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347LN	S34751	...	...
33	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347LN	S34751	...	...
34	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	≤5
35	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	≤5
36	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348	S34800	...	...
37	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348	S34800	...	...
38	18Cr-10Ni-Cb	Plate	SA-240	348	S34800	...	...
39	18Cr-10Ni-Cb	Plate	SA-240	348	S34800	...	...
40	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...
41	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...
(25) 42	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...
(25) 43	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...
44	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348	S34800	...	...
45	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348	S34800	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	(NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T6
2	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7
3	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T6, W12, W14
4	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
5	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, G22, T6
6	8	1	75	30	1500	NP	1500	650	HA-2	G12, G22, T7
7	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
8	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, G22, T6
9	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
10	8	1	75	30	1500	NP	1500	NP	HA-2	T9
11	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
12	8	1	75	30	1500	NP	1500	NP	HA-2	T9
13	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
14	8	1	75	30	1500	NP	1500	NP	HA-2	T9
15	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8, W12, W13
16	8	1	75	30	1500	NP	NP	NP	HA-2	T9, W13
17	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T8
18	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T9
19	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8, W12, W13, W14
20	8	1	75	30	1500	NP	1500	NP	HA-2	T9, W13, W14
21	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T8
22	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T9
23	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
24	8	1	75	30	1500	NP	1500	NP	HA-2	T9
25	8	1	75	30	NP	800	1500	NP	HA-2	G5, T8, W12, W14
26	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8
27	8	1	75	30	1500	NP	NP	NP	HA-2	T9
28	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
29	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
30	8	1	75	30	NP	NP	1100	NP	HA-2	G5, T8
31	8	1	75	30	NP	NP	1100	NP	HA-2	...
32	8	1	75	30	NP	NP	1100	NP	HA-2	G5, T8
33	8	1	75	30	NP	NP	1100	NP	HA-2	...
34	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T6
35	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
36	8	1	75	30	1500	800	1500	NP	HA-2	G5, G12, T6
37	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
38	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T6
39	8	1	75	30	NP	NP	1500	650	HA-2	G12, T7
40	8	1	75	30	1500	NP	NP	NP	HA-2	G12, T7, W13
41	8	1	75	30	1500	800	NP	NP	HA-2	G5, G12, T6, W12, W13
42	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T6
43	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T7
44	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T6, W12, W14
45	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
2	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
3	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
4	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
5	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
6	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
7	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
8	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
9	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
10	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
11	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
12	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
13	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
14	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
15	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
16	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
17	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
18	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
19	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
20	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
21	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
22	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
23	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
24	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
25	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
26	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
27	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
28	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
29	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
30	20.0	...	20.0	...	19.1	17.8	16.9	16.5	16.4	16.3	16.3	16.3	16.3	16.2
31	20.0	...	17.7	...	16.0	14.6	13.6	12.9	12.7	12.6	12.5	12.4	12.4	12.4
32	20.0	...	20.0	...	19.1	17.8	16.9	16.5	16.4	16.3	16.3	16.3	16.3	16.2
33	20.0	...	17.7	...	16.0	14.6	13.6	12.9	12.7	12.6	12.5	12.4	12.4	12.4
34	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
35	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
36	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
37	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
38	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
39	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
40	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
41	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
42	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
43	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
44	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
45	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
2	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
3	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
6	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
9	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
10	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
11	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
12	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
13	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
14	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
15	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
16	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
17	14.1	14.0	13.7	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
18	11.4	11.4	11.4	11.3	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
19	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
20	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
21	14.1	14.0	13.7	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
22	11.4	11.4	11.4	11.3	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
23	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
24	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
25	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
26	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
27	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	16.1	15.8	15.6	13.2	...	...	...	...	...	...	...	...	...	...	...
31	12.4	12.4	12.3	12.2	...	...	...	...	...	...	...	...	...	...	...
32	16.1	15.8	15.6	13.2	...	...	...	...	...	...	...	...	...	...	...
33	12.4	12.4	12.3	12.2	...	...	...	...	...	...	...	...	...	...	...
34	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
35	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
36	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
37	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
38	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
39	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
40	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
41	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
42	14.1	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	...
43	11.4	11.4	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	...
44	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
45	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348	S34800	...	...
2	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348	S34800	...	...
3	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	1	...
4	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348	S34800	...	...
5	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348	S34800	...	...
6	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	348	S34800	...	...
7	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP348	S34800	...	...
8	18Cr-10Ni-Cb	Bar	SA-479	348	S34800	...	...
9	18Cr-10Ni-Cb	Bar	SA-479	348	S34800	...	...
10	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348	S34800	...	...
11	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348	S34800	...	...
12	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	≤5
13	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	≤5
14	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H	S34809	...	...
15	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H	S34809	...	...
16	18Cr-10Ni-Cb	Plate	SA-240	348H	S34809	...	...
17	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...
18	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...
(25) 19	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...
(25) 20	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...
21	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348H	S34809	...	...
22	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348H	S34809	...	...
23	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348H	S34809	...	...
24	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348H	S34809	...	...
25	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	348H	S34809	...	...
26	18Cr-10Ni-Cb	Bar	SA-479	348H	S34809	...	...
27	18Cr-10Ni-Cb	Bar	SA-479	348H	S34809	...	...
28	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348H	S34809	...	...
29	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348H	S34809	...	...
30	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347HFG	S34710	...	...
31	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347HFG	S34710	...	...
32	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	> ³ / ₈
33	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	> ³ / ₈
34	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	> ³ / ₈
35	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	> ³ / ₈
(25) 36	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	> ³ / ₈
(25) 37	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	> ³ / ₈
38	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	> ³ / ₁₆
39	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	> ³ / ₁₆
40	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	> ³ / ₁₆
41	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	> ³ / ₁₆
(25) 42	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	> ³ / ₈
43	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	>5
44	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	>5
(25) 45	18Cr-10Ni-Ti	Forgings	SA-965	F321	S32100	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	(NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T6
2	8	1	75	30	NP	NP	1500	650	HA-2	G12, G24, T7
3	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
4	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, H1, T6
5	8	1	75	30	1500	NP	1500	650	HA-2	G12, H1, T7
6	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, H2, T6, W12, W14
7	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
8	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, G22, H1, T6
9	8	1	75	30	1500	NP	1500	650	HA-2	G12, G22, H1, T7
10	8	1	75	30	NP	800	NP	NP	HA-2	G5, H1, W12
11	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
12	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
13	8	1	75	30	1500	NP	1500	NP	HA-2	T9
14	8	1	75	30	1500	800	1500	NP	HA-2	G5, H2, T8
15	8	1	75	30	1500	NP	1500	NP	HA-2	H2, T9
16	8	1	75	30	NP	800	NP	NP	HA-2	G5, H2
17	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8, W12, W13
18	8	1	75	30	1500	NP	NP	NP	HA-2	T9, W13
19	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T8
20	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T9
21	8	1	75	30	1500	800	1500	NP	HA-2	G5, H2, T8, W12, W14
22	8	1	75	30	1500	NP	1500	NP	HA-2	H2, T9
23	8	1	75	30	NP	NP	1500	NP	HA-2	G5, G24, H2, T8
24	8	1	75	30	NP	NP	1500	NP	HA-2	G24, H2, T9
25	8	1	75	30	NP	800	1500	NP	HA-2	G5, H2, T8, W12, W14
26	8	1	75	30	1500	800	NP	NP	HA-2	G5, H2, T8
27	8	1	75	30	1500	NP	NP	NP	HA-2	H2, T9
28	8	1	75	30	NP	800	NP	NP	HA-2	G5, H2, W12
29	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
30	8	1	80	30	1350	NP	NP	NP	HA-2	G5, T9
31	8	1	80	30	1350	NP	NP	NP	HA-2	T9
32	8	1	70	25	1500	800	1500	NP	HA-2	G5, G12, T7
33	8	1	70	25	1500	NP	1500	NP	HA-2	G12, T7
34	8	1	70	25	1500	800	1500	NP	HA-2	G5, G12, T7, W12, W13, W14
35	8	1	70	25	1500	NP	1500	NP	HA-2	G12, T7, W13, W14
36	8	1	70	25	NP	800	1500	650	HA-2	G5, G12, T7
37	8	1	70	25	NP	NP	1500	650	HA-2	G12, T7
38	8	1	70	25	1500	800	1500	NP	HA-2	G5, T8
39	8	1	70	25	1500	NP	1500	NP	HA-2	T8
40	8	1	70	25	1500	800	1500	NP	HA-2	G5, T8, W12, W13, W14
41	8	1	70	25	1500	NP	1500	NP	HA-2	T8, W13, W14
42	8	1	70	25	NP	800	1500	NP	HA-2	G5, T8
43	8	1	70	30	1500	800	1500	NP	HA-2	G5, G12, T6
44	8	1	70	30	1500	NP	1500	NP	HA-2	G12, T7
45	8	1	70	30	1500	800	1500	650	HA-2	G5, G12, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
2	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
3	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
4	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
5	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
6	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
7	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
8	20.0	...	20.0	...	18.8	17.8	17.2	16.9	16.8	16.8	16.8	16.8	16.8	16.7
9	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
10	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
11	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
12	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
13	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
14	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
15	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
16	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
17	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
18	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
19	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
20	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
21	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
22	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
23	17.0	...	17.0	...	16.0	15.1	14.6	14.3	14.3	14.3	14.3	14.3	14.3	14.2
24	17.0	...	15.6	...	14.6	13.6	12.8	12.2	11.9	11.8	11.6	11.5	11.5	11.4
25	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
26	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	16.8	16.7
27	20.0	...	18.4	...	17.1	16.0	15.0	14.3	14.0	13.8	13.7	13.6	13.5	13.4
28	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
29	20.0	...	20.0	...	18.8	17.8	17.1	16.9	16.8	16.8	16.8	16.8	...	...
30	20.0	...	20.0	...	20.0	19.9	19.3	19.1	19.0	18.9	18.8	18.6	18.3	18.1
31	20.0	...	18.1	...	16.9	15.9	15.2	14.6	14.4	14.1	13.9	13.8	13.6	13.4
32	16.7	16.7	16.7	16.7	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
33	16.7	15.6	15.0	14.4	13.8	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.2
34	16.7	16.7	16.7	16.7	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
35	16.7	15.6	15.0	14.4	13.8	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.2
36	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
37	16.7	...	15.0	...	13.8	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.2
38	16.7	16.7	16.7	16.7	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
39	16.7	15.6	15.0	14.4	13.8	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.2
40	16.7	16.7	16.7	16.7	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
41	16.7	15.6	15.0	14.4	13.8	12.8	11.9	11.3	11.0	10.8	10.6	10.5	10.3	10.2
42	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	13.9	13.8
43	20.0	...	19.0	...	17.8	17.5	17.5	17.5	17.5	17.5	17.2	16.9	16.7	16.5
44	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
45	20.0	...	19.0	...	17.8	17.5	17.5	17.5	17.5	17.5	17.2	16.9	16.7	16.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	14.1	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	...
2	11.4	11.4	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.77	0.68	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
5	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
6	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	16.6	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
9	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
13	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
14	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
15	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
18	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
19	14.1	14.0	13.7	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	(25)
20	11.4	11.4	11.4	11.3	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	(25)
21	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
22	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
23	14.1	14.0	13.7	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
24	11.4	11.4	11.4	11.3	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1	...	...	...
25	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
26	16.6	16.4	16.2	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
27	13.4	13.4	13.4	13.3	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	17.9	17.7	17.5	16.6	12.8	9.7	7.3	5.4	4.0	...	...	...	...	...	...
31	13.3	13.1	13.0	12.8	12.8	9.7	7.3	5.4	4.0	...	...	...	...	...	...
32	13.6	13.5	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
33	10.1	10.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
34	13.6	13.5	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
35	10.1	10.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
36	13.6	13.5	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	(25)
37	10.1	10.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	(25)
38	13.6	13.5	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
39	10.1	10.0	9.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
40	13.6	13.5	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
41	10.1	10.0	9.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
42	13.6	13.5	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	(25)
43	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
44	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
45	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25) 1	18Cr-10Ni-Ti	Forgings	SA-965	F321	S32100	...	...
(25) 2	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	>5
(25) 3	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	>5
(25) 4	18Cr-10Ni-Ti	Forgings	SA-965	F321H	S32109	...	...
(25) 5	18Cr-10Ni-Ti	Forgings	SA-965	F321H	S32109	...	...
6	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi18-10	...	...	≤3
7	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi18-10	...	...	≤3
8	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	≤5
9	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	≤5
10	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	≤5
11	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...	...
12	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...	...
13	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...	...
14	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...	...
15	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...	...
16	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...	...
17	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...
18	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...
(25) 19	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...
(25) 20	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...
21	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	≤ ³ / ₈
22	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	≤ ³ / ₈
23	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	≤ ³ / ₈
24	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	≤ ³ / ₈
(25) 25	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	1	...
(25) 26	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	≤ ³ / ₈
(25) 27	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	≤ ³ / ₈
28	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	≤ ³ / ₈
29	18Cr-10Ni-Ti	Smls. & wld. fittings	SA-403	321	S32100	...	...
30	18Cr-10Ni-Ti	Wld. pipe	SA-409	TP321	S32100	...	...
(25) 31	18Cr-10Ni-Ti	Bar	SA-479	321	S32100	...	...
(25) 32	18Cr-10Ni-Ti	Bar	SA-479	321	S32100	...	...
(25) 33	18Cr-10Ni-Ti	Bar	SA-479	321	S32100	...	...
(25) 34	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321	S32100	...	...
35	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321	S32100	...	...
(25) 36	18Cr-10Ni-Ti	Bar	SA/JIS G4303	SUS321	...	...	...
(25) 37	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	≤5
(25) 38	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	≤5
(25) 39	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H	S32109	...	...
(25) 40	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H	S32109	...	...
(25) 41	18Cr-10Ni-Ti	Plate	SA-240	321H	S32109	...	...
(25) 42	18Cr-10Ni-Ti	Plate	SA-240	321H	S32109	...	...
43	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...
44	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...
(25) 45	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	70	30	1500	NP	1500	650	HA-2	G12, T7
2	8	1	70	30	1500	800	1500	NP	HA-2	G5, T8
3	8	1	70	30	1500	NP	1500	NP	HA-2	T8
4	8	1	70	30	NP	800	1500	NP	HA-2	G5, T8
5	8	1	70	30	NP	NP	1500	NP	HA-2	T8
6	8	1	73	29	NP	NP	1022	650	HA-2	G5, G12, G30, T6
7	8	1	73	29	NP	NP	1022	650	HA-2	G12, G30, T7
8	8	1	75	30	1500	NP	NP	NP	HA-2	G5, G12, T7
9	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7
10	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T6
11	8	1	75	30	1500	NP	NP	NP	HA-2	G5, G12, T7
12	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
13	8	1	75	30	NP	800	1500	NP	HA-2	G5, G12, T6
14	8	1	75	30	1500	NP	NP	NP	HA-2	G5, G12, T7
15	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7
16	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T6
17	8	1	75	30	1500	NP	NP	NP	HA-2	G12, T7, W13
18	8	1	75	30	1500	800	NP	NP	HA-2	G5, G12, T7, W12, W13
19	8	1	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T7
20	8	1	75	30	1500	NP	1500	650	HA-2	G12, G24, T7
21	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T7
22	8	1	75	30	1500	NP	1500	650	HA-2	G12, T7
23	8	1	75	30	1500	800	1500	650	HA-2	G5, G12, T7, W12, W13, W14
24	8	1	75	30	1500	NP	1500	650	HA-2	T7, W13, W14
25	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
26	8	1	75	30	1500	NP	NP	NP	HA-2	G5, G12, T7
27	8	1	75	30	1500	NP	1500	NP	HA-2	G12, T7
28	8	1	75	30	NP	800	1500	NP	HA-2	G5, G12, T6
29	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T6, W12, W14
30	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
31	8	1	75	30	1500	NP	NP	NP	HA-2	G5, G12, T7
32	8	1	75	30	1500	NP	1500	650	HA-2	G12, G22, T7
33	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, G22, T6
34	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
35	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
36	8	1	75	30	NP	800	1500	NP	HA-2	G5, G12, G22, T6
37	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
38	8	1	75	30	1500	NP	1500	NP	HA-2	T8
39	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
40	8	1	75	30	1500	NP	1500	NP	HA-2	T8
41	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
42	8	1	75	30	1500	NP	1500	NP	HA-2	T8
43	8	1	75	30	1500	NP	NP	NP	HA-2	T8, W13
44	8	1	75	30	1500	800	NP	NP	HA-2	G5, T8, W12, W13
45	8	1	75	30	1500	NP	1500	NP	HA-2	G5, G24, T8

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
2	20.0	...	19.0	...	17.8	17.5	17.5	17.5	17.5	17.5	17.2	16.9	16.7	16.5
3	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
4	20.0	...	19.0	...	17.8	17.5	17.5	17.5	17.5	17.5	17.2	16.9	16.7	16.5
5	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
6	19.3	...	19.3	...	19.3	19.3	18.7	17.7	17.2	16.9	16.6	16.4	16.2	16.0
7	19.3	...	17.4	...	16.0	14.8	13.8	13.1	12.8	12.5	12.3	12.1	12.0	11.9
8	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
9	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
10	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
11	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
12	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
13	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
14	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
15	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
16	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
17	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
18	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
19	17.0	...	17.0	...	16.2	15.9	15.9	15.5	15.2	14.9	14.6	14.4	14.2	14.1
20	17.0	...	15.3	...	14.1	13.0	12.2	11.5	11.2	11.0	10.8	10.7	10.5	10.4
21	20.0	20.0	20.0	19.6	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
22	20.0	18.7	18.0	17.2	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
23	20.0	20.0	20.0	19.6	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
24	20.0	18.7	18.0	17.2	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
25	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
26	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
27	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
28	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
29	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
30	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
31	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
32	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
33	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
34	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
35	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
36	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
37	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
38	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
39	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
40	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
41	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
42	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
43	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
44	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
45	17.0	...	17.0	...	16.2	15.9	15.9	15.5	15.2	14.9	14.6	14.4	14.2	14.1

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
2	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
3	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
4	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
5	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
6	15.8	14.9	9.6	...	...	...	...	...	...	...	...	...	...	...	...
7	11.7	11.6	9.6	...	...	...	...	...	...	...	...	...	...	...	...
8	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
9	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
10	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
11	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
12	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
13	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
14	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
15	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
16	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
17	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
18	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
19	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.9	0.68	0.43	0.26	...	...	...
20	10.3	10.2	8.2	5.9	4.3	3.1	2.2	1.4	0.9	0.68	0.43	0.26	...	...	...
21	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
22	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
23	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
24	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
27	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
28	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
29	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
32	12.1	12.0	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
33	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	16.4	14.9	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30	...	...	...
37	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
38	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
39	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
40	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
41	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
42	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
43	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
44	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
45	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
(25)	1 18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...
	2 18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$
	3 18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$
	4 18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$
	5 18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$
(25)	6 18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$\leq \frac{3}{8}$
(25)	7 18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$\leq \frac{3}{8}$
(25)	8 18Cr-10Ni-Ti	Smls. & wld. fittings	SA-403	321H	S32109	...	...
(25)	9 18Cr-10Ni-Ti	Bar	SA-479	321H	S32109	...	...
	10 18Cr-10Ni-Ti	Bar	SA-479	321H	S32109	...	...
(25)	11 18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321H	S32109	...	...
	12 18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321H	S32109	...	...
	13 18Cr-11Ni	Plate	SA-240	305	S30500	...	...
	14 18Cr-12Ni-2Mo	Castings	SA-351	CF3M	J92800	...	...
	15 18Cr-12Ni-2Mo	Castings	SA-351	CF3M	J92800	...	...
	16 18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF3M	J92800	...	...
(25)	17 18Cr-12Ni-2Mo	Castings	SA-351	CF8M	J92900	...	...
(25)	18 18Cr-12Ni-2Mo	Castings	SA-351	CF8M	J92900	...	...
	19 18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF8M	J92900	...	...
	20 18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...	>5
	21 18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...	>5
	22 18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...	≤ 5
	23 18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...	≤ 5
	24 18Cr-13Ni-3Mo	Forgings	SA-182	F317	S31700	...	≤ 5
	25 18Cr-13Ni-3Mo	Forgings	SA-182	F317	S31700	...	≤ 5
	26 18Cr-13Ni-3Mo	Plate	SA-240	317	S31700	...	...
	27 18Cr-13Ni-3Mo	Plate	SA-240	317	S31700	...	...
	28 18Cr-13Ni-3Mo	Plate	SA-240	317L	S31703	...	...
	29 18Cr-13Ni-3Mo	Plate	SA-240	317L	S31703	...	...
	30 18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...
	31 18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...
	32 18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...
	33 18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317L	S31703	...	...
	34 18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317L	S31703	...	...
	35 18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317	S31700	...	...
	36 18Cr-13Ni-3Mo	Smls. pipe	SA-312	TP317	S31700	...	...
	37 18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317	S31700	...	...
	38 18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317	S31700	...	...
	39 18Cr-13Ni-3Mo	Smls. pipe	SA-312	TP317L	S31703	...	...
	40 18Cr-13Ni-3Mo	Smls. pipe	SA-312	TP317L	S31703	...	...
	41 18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317L	S31703	...	...
	42 18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317L	S31703	...	...
	43 18Cr-13Ni-3Mo	Smls. & wld. fittings	SA-403	317	S31700	...	...
	44 18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	CR	...
	45 18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	CR	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	1	75	30	1500	NP	1500	NP	HA-2	G24, T8
2	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
3	8	1	75	30	1500	NP	1500	NP	HA-2	T8
4	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8, W12, W13, W14
5	8	1	75	30	1500	NP	1500	NP	HA-2	T8, W13, W14
6	8	1	75	30	1500	800	1500	NP	HA-2	G5, T8
7	8	1	75	30	1500	NP	1500	NP	HA-2	T8
8	8	1	75	30	NP	800	1500	NP	HA-2	G5, T8, W12, W14
9	8	1	75	30	1500	NP	1500	NP	HA-2	T8
10	8	1	75	30	1500	800	1500	NP	HA-2	G5, H2, T8
11	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
12	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
13	8	1	75	30	NP	800	NP	NP	HA-1	G5
14	8	1	70	30	NP	800	850	650	HA-4	G1, G5, G16, G17, G19
15	8	1	70	30	NP	NP	850	650	HA-4	G1, G19
16	8	1	70	30	NP	800	800	NP	HA-4	G1, G5, G16, G17, G19
17	8	1	70	30	1500	800	1500	650	HA-2	G1, G5, G12, G16, G17, G19, T6
18	8	1	70	30	1500	NP	1500	650	HA-2	G1, G12, G19, T8
19	8	1	70	30	NP	800	800	NP	HA-2	G1, G5, G16, G17, G19
20	8	1	65	25	NP	NP	850	650	HA-4	G5
21	8	1	65	25	NP	NP	850	650	HA-4	...
22	8	1	70	25	NP	NP	850	650	HA-4	G5
23	8	1	70	25	NP	NP	850	650	HA-4	...
24	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, T8
25	8	1	75	30	NP	NP	1500	650	HA-2	G12, T9
26	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, T8
27	8	1	75	30	NP	NP	1500	650	HA-2	G12, T9
28	8	1	75	30	NP	NP	850	650	HA-4	G5
29	8	1	75	30	NP	NP	850	650	HA-4	...
30	8	1	75	30	NP	800	NP	NP	HA-2	G5, W12
31	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T8
32	8	1	75	30	NP	NP	1500	650	HA-2	G12, G24, T9
33	8	1	75	30	NP	NP	850	650	HA-4	G5, G24
34	8	1	75	30	NP	NP	850	650	HA-4	G24
35	8	1	75	30	NP	800	1500	650	HA-2	G5, G12, T8, W12, W14
36	8	1	75	30	NP	NP	1500	650	HA-2	G12, T9
37	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T8
38	8	1	75	30	NP	NP	1500	650	HA-2	G12, G24, T9
39	8	1	75	30	NP	NP	850	650	HA-4	G5
40	8	1	75	30	NP	NP	850	650	HA-4	...
41	8	1	75	30	NP	NP	850	650	HA-4	G5, G24
42	8	1	75	30	NP	NP	850	650	HA-4	G24
43	8	1	75	30	NP	NP	1500	650	HA-2	G5, G12, T8, W14
44	8	1	75	30	NP	NP	850	650	HA-4	G5, G24
45	8	1	75	30	NP	NP	850	650	HA-4	G24

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	15.3	...	14.1	13.0	12.2	11.5	11.2	11.0	10.8	10.7	10.5	10.4
2	20.0	20.0	20.0	19.6	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
3	20.0	18.7	18.0	17.2	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
4	20.0	20.0	20.0	19.6	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
5	20.0	18.7	18.0	17.2	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
6	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
7	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
8	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
9	20.0	...	18.0	...	16.5	15.3	14.3	13.5	13.2	13.0	12.7	12.6	12.4	12.3
10	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	16.7	16.5
11	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
12	20.0	...	20.0	...	19.1	18.7	18.7	18.3	17.9	17.5	17.2	16.9	...	...
13	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
14	20.0	...	20.0	...	19.4	19.2	17.9	17.0	16.6	16.3	16.0	15.8	15.7	...
15	20.0	...	17.2	...	15.5	14.2	13.3	12.6	12.3	12.1	11.9	11.7	11.6	...
16	20.0	...	20.0	...	19.4	19.2	17.9	17.0	16.6	16.3	16.1	15.8	...	...
17	20.0	...	20.0	...	19.4	19.2	17.9	17.0	16.6	16.3	16.0	15.8	15.7	15.5
18	20.0	...	17.2	...	15.5	14.2	13.3	12.6	12.3	12.1	11.9	11.7	11.6	11.5
19	20.0	...	20.0	...	19.4	19.2	17.9	17.0	16.6	16.3	16.0	15.8	...	...
20	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	...
21	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	...
22	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	12.7	...
23	16.7	...	14.2	...	12.7	11.7	10.9	10.4	10.2	10.0	9.8	9.6	9.4	...
24	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
25	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
26	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
27	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
28	20.0	...	20.0	...	19.6	18.9	17.7	16.9	16.5	16.2	15.8	15.5	15.2	...
29	20.0	...	17.0	...	15.2	14.0	13.1	12.5	12.2	12.0	11.7	11.5	11.3	...
30	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
31	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
32	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
33	17.0	...	17.0	...	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...
34	17.0	...	14.5	...	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...
35	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
36	20.0	...	17.3	...	15.6	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
37	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	13.4	13.2
38	17.0	...	14.7	...	13.2	12.1	11.3	10.7	10.5	10.3	10.1	10.0	9.9	9.8
39	20.0	20.0	20.0	20.0	19.6	18.9	17.7	16.9	16.5	16.2	15.8	15.5	15.2	...
40	20.0	18.2	17.0	16.0	15.2	14.0	13.1	12.5	12.2	12.0	11.7	11.5	11.3	...
41	17.0	17.0	17.0	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...	...
42	17.0	15.5	14.5	13.6	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...
43	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	15.7	15.6
44	17.0	...	17.0	...	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...
45	17.0	...	14.5	...	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	10.3	10.2	10.1	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94	...	...	...
2	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
3	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
4	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
5	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
6	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
7	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
8	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
9	12.1	12.0	11.9	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
10	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	15.4	14.9	11.5	8.9	6.9	5.4	4.3	3.4	2.8	2.3	1.9	1.6	...	...	...
18	11.4	11.3	11.2	8.9	6.9	5.4	4.3	3.4	2.8	2.3	1.9	1.6	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
25	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
26	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
27	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1	...	...	...
32	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
36	11.4	11.3	11.2	11.1	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
37	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1	...	...	...
38	9.7	9.6	9.5	9.4	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-S	...
2	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-S	...
3	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-W	...
4	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-W	...
5	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-WU	...
6	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-WU	...
7	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-WX	...
8	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-WX	...
9	18Cr-15Ni-4Si	Forgings	SA-182	...	S30600	Sol. ann.	...
10	18Cr-15Ni-4Si	Forgings	SA-182	...	S30600	Sol. ann.	...
11	18Cr-15Ni-4Si	Plate	SA-240	...	S30600	Sol. ann.	≤2
12	18Cr-15Ni-4Si	Plate	SA-240	...	S30600	Sol. ann.	≤2
13	18Cr-15Ni-4Si	Smls. & wld. pipe	SA-312	...	S30600	Sol. ann.	...
14	18Cr-15Ni-4Si	Smls. & wld. pipe	SA-312	...	S30600	Sol. ann.	...
15	18Cr-15Ni-4Si	Wld. pipe	SA-312	...	S30600	Sol. ann.	...
16	18Cr-15Ni-4Si	Wld. pipe	SA-312	...	S30600	Sol. ann.	...
17	18Cr-15Ni-4Si	Bar	SA-479	...	S30600	Sol. ann.	≤4
18	18Cr-15Ni-4Si	Bar	SA-479	...	S30600	Sol. ann.	≤4
19	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15	S38100	...	...
20	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15	S38100	...	...
21	18Cr-18Ni-2Si	Plate	SA-240	XM-15	S38100	...	...
22	18Cr-18Ni-2Si	Plate	SA-240	XM-15	S38100	...	...
23	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15	S38100	...	...
24	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15	S38100	...	...
25	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15	S38100	...	...
26	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15	S38100	...	...
27	18Cr-20Ni-5.5Si	Smls. tube	SA-213	...	S32615	Sol. ann.	...
28	18Cr-20Ni-5.5Si	Smls. tube	SA-213	...	S32615	Sol. ann.	...
29	18Cr-20Ni-5.5Si	Plate	SA-240	...	S32615	Sol. ann.	...
30	18Cr-20Ni-5.5Si	Plate	SA-240	...	S32615	Sol. ann.	...
31	18Cr-20Ni-5.5Si	Smls. & wld. pipe	SA-312	...	S32615	Sol. ann.	...
32	18Cr-20Ni-5.5Si	Smls. & wld. pipe	SA-312	...	S32615	Sol. ann.	...
33	18Cr-20Ni-5.5Si	Wld. pipe	SA-312	...	S32615	Sol. ann.	...
34	18Cr-20Ni-5.5Si	Wld. pipe	SA-312	...	S32615	Sol. ann.	...
35	18Cr-20Ni-5.5Si	Bar	SA-479	...	S32615	Sol. ann.	...
36	18Cr-20Ni-5.5Si	Bar	SA-479	...	S32615	Sol. ann.	...
37	19Cr-9Ni-1/2Mo	Castings	SA-351	CF10	J92590	...	...
38	19Cr-9Ni-1/2Mo	Castings	SA-351	CF10	J92590	...	...
39	19Cr-9Ni-2Mo	Castings	SA-351	CF10M	...	...	...
40	19Cr-9Ni-2Mo	Castings	SA-351	CF10M	...	...	...
41	19Cr-10Ni-3Mo	Castings	SA-351	CG8M	J93000	...	...
42	19Cr-10Ni-3Mo	Castings	SA-351	CG8M	J93000	...	...
43	19Cr-15Ni-4Mo	Smls. tube	SA-213	...	S31725	...	...
44	19Cr-15Ni-4Mo	Smls. tube	SA-213	...	S31725	...	...
45	19Cr-15Ni-4Mo	Plate	SA-240	...	S31725	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature											
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes	
					(NP = Not Permitted)						
					(SPT = Supports Only)						
					I	III	VIII-1	XII			
1	8	1	75	30	NP	NP	850	650	HA-4	G5	
2	8	1	75	30	NP	NP	850	650	HA-4	...	
3	8	1	75	30	NP	NP	850	650	HA-4	G5, G24	
4	8	1	75	30	NP	NP	850	650	HA-4	G24	
5	8	1	75	30	NP	NP	850	650	HA-4	G5, G24	
6	8	1	75	30	NP	NP	850	650	HA-4	G24	
7	8	1	75	30	NP	NP	850	650	HA-4	G5, G24	
8	8	1	75	30	NP	NP	850	650	HA-4	G24	
9	8	1	78	35	NP	NP	300	NP	HA-2	G5, H6	
10	8	1	78	35	NP	NP	300	NP	HA-2	H6	
11	8	1	78	35	NP	NP	300	NP	HA-2	G5, H6	
12	8	1	78	35	NP	NP	300	NP	HA-2	H6	
13	8	1	78	35	NP	NP	300	NP	HA-2	G5, H6	
14	8	1	78	35	NP	NP	300	NP	HA-2	H6	
15	8	1	78	35	NP	NP	300	NP	HA-2	G5, G24, H6	
16	8	1	78	35	NP	NP	300	NP	HA-2	G24, H6	
17	8	1	78	35	NP	NP	300	NP	HA-2	G5, H6	
18	8	1	78	35	NP	NP	300	NP	HA-2	H6	
19	8	1	75	30	NP	NP	1000	650	HA-2	G5	
20	8	1	75	30	NP	NP	1000	650	HA-2	...	
21	8	1	75	30	NP	NP	1000	650	HA-2	G5	
22	8	1	75	30	NP	NP	1000	650	HA-2	...	
23	8	1	75	30	NP	NP	1000	650	HA-2	G5, G24	
24	8	1	75	30	NP	NP	1000	650	HA-2	G24	
25	8	1	75	30	NP	NP	950	650	HA-2	G5, G24	
26	8	1	75	30	NP	NP	1000	650	HA-2	G24	
27	8	1	80	32	NP	NP	400	NP	HA-2	G5, H6	
28	8	1	80	32	NP	NP	400	NP	HA-2	H6	
29	8	1	80	32	NP	NP	400	NP	HA-2	G5, H6	
30	8	1	80	32	NP	NP	400	NP	HA-2	H6	
31	8	1	80	32	NP	NP	400	NP	HA-2	G5, H6	
32	8	1	80	32	NP	NP	400	NP	HA-2	H6	
33	8	1	80	32	NP	NP	400	NP	HA-2	G5, G24, H6	
34	8	1	80	32	NP	NP	400	NP	HA-2	G24, H6	
35	8	1	80	32	NP	NP	400	NP	HA-2	G5, H6	
36	8	1	80	32	NP	NP	400	NP	HA-2	H6	
37	8	1	70	30	NP	NP	1500	650	HA-1	G1, G5, G19, T6	
38	8	1	70	30	NP	NP	1500	650	HA-1	G1, G19, T7	
39	8	1	70	30	NP	NP	1500	NP	HA-2	G1, G5, G19, T6	
40	8	1	70	30	NP	NP	1500	NP	HA-2	G1, G19, T8	
41	8	1	75	35	NP	NP	1000	650	HA-2	G1, G5, G19	
42	8	1	75	35	NP	NP	1000	650	HA-2	G1, G19	
43	8	4	75	30	NP	NP	400	400	HA-4	G5	
44	8	4	75	30	NP	NP	400	400	HA-4	...	
45	8	4	75	30	NP	NP	400	400	HA-4	G5	

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	19.6	18.9	17.7	16.9	16.5	16.2	15.8	15.5	15.2	...
2	20.0	...	17.0	...	15.2	14.0	13.1	12.5	12.2	12.0	11.7	11.5	11.3	...
3	17.0	...	17.0	...	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...
4	17.0	...	14.5	...	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...
5	17.0	...	17.0	...	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...
6	17.0	...	14.5	...	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...
7	17.0	...	17.0	...	16.7	16.0	15.1	14.3	14.0	13.7	13.5	13.2	12.9	...
8	17.0	...	14.5	...	12.9	11.9	11.2	10.6	10.4	10.2	10.0	9.8	9.6	...
9	22.3	...	21.3	...	19.6	...	...	...	...	...	...	...	...	...
10	22.3	...	17.9	...	16.1	...	...	...	...	...	...	...	...	...
11	22.3	...	21.3	...	19.6	...	...	...	...	...	...	...	...	...
12	22.3	...	17.9	...	16.1	...	...	...	...	...	...	...	...	...
13	22.3	...	21.3	...	19.6	...	...	...	...	...	...	...	...	...
14	22.3	...	17.9	...	16.1	...	...	...	...	...	...	...	...	...
15	19.0	...	18.1	...	16.7	...	...	...	...	...	...	...	...	...
16	19.0	...	15.2	...	13.7	...	...	...	...	...	...	...	...	...
17	22.3	...	21.3	...	19.6	...	...	...	...	...	...	...	...	...
18	22.3	...	17.9	...	16.1	...	...	...	...	...	...	...	...	...
19	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
20	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
21	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	14.9	14.6
22	20.0	...	16.7	...	15.0	13.8	12.9	12.3	12.0	11.7	11.5	11.2	11.0	10.8
23	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
24	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
25	17.0	...	17.0	...	16.1	15.5	14.8	14.1	13.8	13.5	13.2	12.9	12.6	12.4
26	17.0	...	14.2	...	12.7	11.7	11.0	10.4	10.2	10.0	9.8	9.6	9.4	9.2
27	21.3	...	21.3	...	21.3	21.0	...	...	...	...	...	...	...	...
28	21.3	...	17.6	...	16.5	15.4	...	...	...	...	...	...	...	...
29	21.3	...	21.3	...	21.3	21.0	...	...	...	...	...	...	...	...
30	21.3	...	17.6	...	16.5	15.4	...	...	...	...	...	...	...	...
31	21.3	...	21.3	...	21.3	21.0	...	...	...	...	...	...	...	...
32	21.3	...	17.6	...	16.5	15.4	...	...	...	...	...	...	...	...
33	18.1	...	18.1	...	18.1	17.9	...	...	...	...	...	...	...	...
34	18.1	...	15.0	...	14.0	13.1	...	...	...	...	...	...	...	...
35	21.3	...	21.3	...	21.3	21.0	...	...	...	...	...	...	...	...
36	21.3	...	17.6	...	16.5	15.4	...	...	...	...	...	...	...	...
37	20.0	...	19.0	...	17.7	17.2	17.0	16.5	16.2	15.8	15.5	15.2	14.9	14.6
38	20.0	...	16.7	...	15.0	13.8	12.9	12.2	12.0	11.7	11.5	11.3	11.1	10.8
39	20.0	...	20.0	...	19.5	19.3	17.9	17.0	16.6	16.3	16.1	15.9	15.7	15.5
40	20.0	...	17.5	...	15.7	14.3	13.3	12.6	12.3	12.1	11.9	11.8	11.6	11.5
41	21.4	...	20.8	...	19.6	19.1	18.4	17.5	17.1	16.8	16.6	16.4	16.2	16.0
42	21.4	...	18.8	...	16.4	14.7	13.6	12.9	12.7	12.5	12.3	12.1	12.0	11.8
43	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...
44	20.0	...	16.9	...	15.2	14.0	...	...	...	...	...	...	...	...
45	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	14.3	14.0	...	...	...	...	...	...	...	...	...	...	...	...	...
20	10.6	10.4	...	...	...	...	...	...	...	...	...	...	...	...	...
21	14.3	14.0	...	...	...	...	...	...	...	...	...	...	...	...	...
22	10.6	10.4	...	...	...	...	...	...	...	...	...	...	...	...	...
23	12.1	11.9	...	...	...	...	...	...	...	...	...	...	...	...	...
24	9.0	8.8	...	...	...	...	...	...	...	...	...	...	...	...	...
25	12.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	9.0	8.8	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	14.4	12.2	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7	...	...	...
38	10.6	10.4	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7	...	...	...
39	15.3	14.9	11.5	8.9	6.9	5.4	4.3	3.4	2.8	2.3	1.9	1.6	...	...	...
40	11.4	11.3	11.2	8.9	6.9	5.4	4.3	3.4	2.8	2.3	1.9	1.6	...	...	...
41	15.7	12.2	...	...	...	...	...	...	...	...	...	...	...	...	...
42	11.6	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	19Cr-15Ni-4Mo	Plate	SA-240	...	S31725	...	...
2	19Cr-15Ni-4Mo	Wld. tube	SA-249	...	S31725	...	...
3	19Cr-15Ni-4Mo	Wld. tube	SA-249	...	S31725	...	...
4	19Cr-15Ni-4Mo	Smls. pipe	SA-312	...	S31725	...	...
5	19Cr-15Ni-4Mo	Smls. pipe	SA-312	...	S31725	...	...
6	19Cr-15Ni-4Mo	Wld. pipe	SA-312	...	S31725	...	...
7	19Cr-15Ni-4Mo	Wld. pipe	SA-312	...	S31725	...	...
8	19Cr-15Ni-4Mo	Wld. pipe	SA-358	...	S31725	...	...
9	19Cr-15Ni-4Mo	Wld. pipe	SA-358	...	S31725	...	...
10	19Cr-15Ni-4Mo	Smls. pipe	SA-376	...	S31725	...	...
11	19Cr-15Ni-4Mo	Smls. pipe	SA-376	...	S31725	...	...
12	19Cr-15Ni-4Mo	Fittings	SA-403	...	S31725	...	...
13	19Cr-15Ni-4Mo	Wld. pipe	SA-409	...	S31725	...	...
14	19Cr-15Ni-4Mo	Wld. pipe	SA-409	...	S31725	...	...
15	19Cr-15Ni-4Mo	Bar	SA-479	...	S31725	...	...
16	19Cr-15Ni-4Mo	Bar	SA-479	...	S31725	...	...
17	20Cr-3Ni-1.5Mo-N	Plate	SA-240	...	S32003	...	$t > \frac{3}{16}$
18	20Cr-3Ni-1.5Mo-N	Wld. pipe	SA-790	...	S32003	...	...
19	20Cr-3Ni-1.5Mo-N	Sheet	SA-240	...	S32003	...	$t \leq \frac{3}{16}$
20	20Cr-3Ni-1.5Mo-N	Smls. tube	SA-789	...	S32003	...	$t \leq \frac{3}{16}$
21	20Cr-3Ni-1.5Mo-N	Wld. tube	SA-789	...	S32003	...	$t \leq \frac{3}{16}$
22	20Cr-3Ni-1.5Mo-N	Smls. tube	SA-789	...	S32003	...	$t > \frac{3}{16}$
23	20Cr-3Ni-1.5Mo-N	Wld. tube	SA-789	...	S32003	...	$t > \frac{3}{16}$
24	20Cr-10Ni	Bar	SA-479	ER308	S30880	...	...
25	20Cr-18Ni-6Mo	Castings	SA-351	CK3MCuN	J93254	...	...
26	20Cr-18Ni-6Mo	Castings	SA-351	CK3MCuN	J93254	...	...
27	20Cr-18Ni-6Mo	Forgings	SA-182	F44	S31254	...	...
28	20Cr-18Ni-6Mo	Forgings	SA-182	F44	S31254	...	...
29	20Cr-18Ni-6Mo	Fittings	SA-403	...	S31254	...	...
30	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...	$t > 0.187$
31	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...	$t > 0.187$
32	20Cr-18Ni-6Mo	Plate	SA-240	...	S31254	...	$> \frac{3}{16}$
33	20Cr-18Ni-6Mo	Plate	SA-240	...	S31254	...	$> \frac{3}{16}$
34	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...	$t > 0.187$
35	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...	$t > 0.187$
36	20Cr-18Ni-6Mo	Smls. pipe	SA-312	...	S31254	...	$t > 0.187$
37	20Cr-18Ni-6Mo	Smls. pipe	SA-312	...	S31254	...	$t > 0.187$
38	20Cr-18Ni-6Mo	Wld. pipe	SA-312	...	S31254	...	$t > 0.187$
39	20Cr-18Ni-6Mo	Wld. pipe	SA-312	...	S31254	...	$t > 0.187$
40	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...	$t \geq 0.187$
41	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...	$t \geq 0.187$
42	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...	$t \leq 0.187$
43	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...	$t \leq 0.187$
44	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...	$t \leq 0.187$
45	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...	$t \leq 0.187$

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits				External Pressure Chart No.	Notes
					Limits					
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	4	75	30	NP	NP	400	400	HA-4	...
2	8	4	75	30	NP	NP	400	400	HA-4	G5, G24
3	8	4	75	30	NP	NP	400	400	HA-4	G24
4	8	4	75	30	NP	NP	400	NP	HA-4	G5
5	8	4	75	30	NP	NP	400	NP	HA-4	...
6	8	4	75	30	NP	NP	400	NP	HA-4	G5, G24
7	8	4	75	30	NP	NP	400	NP	HA-4	G24
8	8	4	75	30	NP	NP	400	400	HA-4	G5, G24
9	8	4	75	30	NP	NP	400	400	HA-4	G24
10	8	4	75	30	NP	NP	400	400	HA-4	G5
11	8	4	75	30	NP	NP	400	400	HA-4	...
12	8	4	75	30	NP	NP	400	400	HA-4	G5, W14
13	8	4	75	30	NP	NP	400	400	HA-4	G5, G24
14	8	4	75	30	NP	NP	400	400	HA-4	G24
15	8	4	75	30	NP	NP	400	400	HA-4	G5
16	8	4	75	30	NP	NP	400	400	HA-4	...
17	10H	1	95	65	NP	NP	650	NP	HA-5	G19
18	10H	1	95	65	NP	NP	650	NP	HA-5	G19, G24
19	10H	1	100	70	NP	NP	650	NP	HA-5	G19
20	10H	1	100	70	NP	NP	650	NP	HA-5	G19
21	10H	1	100	70	NP	NP	650	NP	HA-5	G19, G24
22	10H	1	95	65	NP	NP	650	NP	HA-5	G19
23	10H	1	95	65	NP	NP	650	NP	HA-5	G19, G24
24	...	...	75	30	NP	800	NP	NP	HA-2	G5
25	8	4	80	38	NP	750	750	650	HA-2	G1, G5
26	8	4	80	38	NP	NP	750	650	HA-2	G1
27	8	4	94	44	NP	750	750	650	HA-2	G5
28	8	4	94	44	NP	NP	750	650	HA-2	...
29	8	4	94	44	NP	750	NP	NP	HA-2	G5, W12
30	8	4	95	45	NP	NP	750	NP	HA-2	G5
31	8	4	95	45	NP	NP	750	NP	HA-2	...
32	8	4	95	45	NP	750	750	650	HA-2	G5
33	8	4	95	45	NP	NP	750	650	HA-2	...
34	8	4	95	45	NP	750	750	650	HA-2	G5, G24
35	8	4	95	45	NP	NP	750	650	HA-2	G24
36	8	4	95	45	NP	750	750	NP	HA-2	G5
37	8	4	95	45	NP	NP	750	NP	HA-2	...
38	8	4	95	45	NP	750	750	NP	HA-2	G5, G24
39	8	4	95	45	NP	NP	750	NP	HA-2	G24
40	8	4	95	45	NP	750	750	650	HA-2	G5, G24
41	8	4	95	45	NP	NP	750	650	HA-2	G24
42	8	4	98	45	NP	NP	750	NP	HA-2	G5
43	8	4	98	45	NP	NP	750	NP	HA-2	...
44	8	4	98	45	NP	750	750	650	HA-2	G5, G24
45	8	4	98	45	NP	NP	750	650	HA-2	G24

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	16.9	...	15.2	14.0	...	...	...	...	...	...	...	...
2	17.0	...	17.0	...	16.6	16.1	...	...	...	...	...	...	...	...
3	17.0	...	14.4	...	12.9	11.9	...	...	...	...	...	...	...	...
4	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...
5	20.0	...	16.9	...	15.2	14.0	...	...	...	...	...	...	...	...
6	17.0	...	17.0	...	16.6	16.1	...	...	...	...	...	...	...	...
7	17.0	...	14.4	...	12.9	11.9	...	...	...	...	...	...	...	...
8	17.0	...	17.0	...	16.6	16.1	...	...	...	...	...	...	...	...
9	17.0	...	14.4	...	12.9	11.9	...	...	...	...	...	...	...	...
10	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...
11	20.0	...	16.9	...	15.2	14.0	...	...	...	...	...	...	...	...
12	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...
13	17.0	...	17.0	...	16.6	16.1	...	...	...	...	...	...	...	...
14	17.0	...	14.4	...	12.9	11.9	...	...	...	...	...	...	...	...
15	20.0	...	20.0	...	19.6	18.9	...	...	...	...	...	...	...	...
16	20.0	...	16.9	...	15.2	14.0	...	...	...	...	...	...	...	...
17	27.1	...	26.3	...	24.8	24.5	24.5	24.5	24.5	...	...	...	...	...
18	23.1	...	22.4	...	21.0	20.8	20.8	20.8	20.8	...	...	...	...	...
19	28.6	...	27.7	...	26.1	25.8	25.8	25.8	25.8	...	...	...	...	...
20	28.6	...	27.7	...	26.1	25.8	25.8	25.8	25.8	...	...	...	...	...
21	24.3	...	23.5	...	22.1	21.9	21.9	21.9	21.9	...	...	...	...	...
22	27.1	...	26.3	...	24.8	24.5	24.5	24.5	24.5	...	...	...	...	...
23	23.1	...	22.4	...	21.0	20.8	20.8	20.8	20.8	...	...	...	...	...
24	20.0	...	20.0	...	18.9	18.3	17.5	16.6	16.2	15.8	15.5	15.2	...	...
25	22.9	...	22.9	...	21.7	20.7	20.0	19.6	19.4	19.3	19.2	...	...	...
26	22.9	...	20.7	...	18.5	17.1	16.1	15.4	15.2	15.1	15.0	...	...	...
27	26.9	...	26.9	...	25.5	24.3	23.5	23.0	22.8	22.7	22.6	...	...	...
28	26.9	...	23.9	...	21.4	19.8	18.6	17.9	17.6	17.4	17.3	...	...	...
29	26.9	...	26.9	...	25.5	24.3	23.5	23.0	22.8	22.7	22.6	...	...	...
30	27.1	...	27.1	...	25.8	24.6	23.7	23.2	23.1	23.0	22.9	...	...	...
31	27.1	...	24.5	...	21.9	20.3	19.1	18.3	18.0	17.9	17.7	...	...	...
32	27.1	...	27.1	...	25.8	24.6	23.7	23.2	23.1	23.0	22.9	...	...	...
33	27.1	...	24.5	...	21.9	20.2	19.1	18.3	18.0	17.8	17.7	...	...	...
34	23.1	...	23.1	...	21.9	20.9	20.2	19.7	19.6	19.5	19.4	...	...	...
35	23.1	...	20.8	...	18.6	17.2	16.2	15.5	15.3	15.2	15.1	...	...	...
36	27.1	...	27.1	...	25.8	24.6	23.7	23.2	23.1	23.0	22.9	...	...	...
37	27.1	...	24.5	...	21.9	20.3	19.1	18.3	18.0	17.9	17.7	...	...	...
38	23.1	...	23.1	...	21.9	20.9	20.2	19.7	19.6	19.5	19.4	...	...	...
39	23.1	...	20.8	...	18.6	17.2	16.2	15.5	15.3	15.2	15.1	...	...	...
40	23.1	...	23.1	...	21.9	20.9	20.2	19.7	19.6	19.5	19.4	...	...	...
41	23.1	...	20.8	...	18.6	17.2	16.2	15.5	15.3	15.2	15.1	...	...	...
42	28.0	...	28.0	...	26.6	25.4	24.5	23.9	23.8	23.7	23.6	...	...	...
43	28.0	...	24.5	...	21.9	20.3	19.1	18.3	18.0	17.9	17.7	...	...	...
44	23.8	...	23.8	...	22.6	21.6	20.8	20.4	20.2	20.1	20.1	...	...	...
45	23.8	...	20.8	...	18.6	17.2	16.2	15.5	15.3	15.2	15.1	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	20Cr-18Ni-6Mo	Smls. pipe	SA-312	...	S31254	...	$t \leq 0.187$
2	20Cr-18Ni-6Mo	Smls. pipe	SA-312	...	S31254	...	$t \leq 0.187$
3	20Cr-18Ni-6Mo	Wld. pipe	SA-312	...	S31254	...	$t \leq 0.187$
4	20Cr-18Ni-6Mo	Wld. pipe	SA-312	...	S31254	...	$t \leq 0.187$
5	20Cr-18Ni-6Mo	Plate	SA-240	...	S31254	...	$\leq \frac{3}{16}$
6	20Cr-18Ni-6Mo	Plate	SA-240	...	S31254	...	$\leq \frac{3}{16}$
7	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...	$t < 0.187$
8	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...	$t < 0.187$
9	20.5Cr-8.8Ni-Mo-N	Plate	SA-240	...	S31655	...	...
10	20.5Cr-8.8Ni-Mo-N	Plate	SA-240	...	S31655	...	...
11	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...	S32101	...	$> \frac{3}{16}$
12	21Cr-5Mn-1.5Ni-Cu-N	Bar	SA-479	...	S32101	...	...
13	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	S32101	...	$> \frac{3}{16}$
14	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	S32101	...	$> \frac{3}{16}$
15	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	S32101	...	$> \frac{3}{16}$
16	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	S32101	...	$> \frac{3}{16}$
17	21Cr-5Mn-1.5Ni-Cu-N	Fittings	SA-815	...	S32101	...	...
18	21Cr-5Mn-1.5Ni-Cu-N	Sheet, strip	SA-240	...	S32101	...	$\leq \frac{3}{16}$
19	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	S32101	...	$\leq \frac{3}{16}$
20	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	S32101	...	$\leq \frac{3}{16}$
21	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	S32101	...	$\leq \frac{3}{16}$
22	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	S32101	...	$\leq \frac{3}{16}$
23	21Cr-6Ni-9Mn	Forgings	SA-182	FXM-11	S21904	...	...
24	21Cr-6Ni-9Mn	Smls. pipe	SA-312	TPXM-11	S21904	...	...
25	21Cr-6Ni-9Mn	Smls. pipe	SA-312	TPXM-11	S21904	...	...
26	21Cr-6Ni-9Mn	Wld. pipe	SA-312	TPXM-11	S21904	...	...
27	21Cr-6Ni-9Mn	Wld. pipe	SA-312	TPXM-11	S21904	...	...
28	21Cr-6Ni-9Mn	Plate	SA-666	XM-11	S21904	...	...
29	21Cr-6Ni-9Mn	Plate	SA-666	XM-11	S21904	...	...
30	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11	S21904	...	...
31	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11	S21904	...	...
32	21Cr-11Ni-N	Forgings	SA-182	F45	S30815	...	...
33	21Cr-11Ni-N	Forgings	SA-182	F45	S30815	...	...
34	21Cr-11Ni-N	Smls. tube	SA-213	...	S30815	...	...
35	21Cr-11Ni-N	Smls. tube	SA-213	...	S30815	...	...
36	21Cr-11Ni-N	Plate	SA-240	...	S30815	...	...
37	21Cr-11Ni-N	Plate	SA-240	...	S30815	...	...
38	21Cr-11Ni-N	Wld. tube	SA-249	...	S30815	...	...
39	21Cr-11Ni-N	Wld. tube	SA-249	...	S30815	...	...
40	21Cr-11Ni-N	Smls. pipe	SA-312	...	S30815	...	...
41	21Cr-11Ni-N	Smls. pipe	SA-312	...	S30815	...	...
42	21Cr-11Ni-N	Wld. pipe	SA-312	...	S30815	...	...
43	21Cr-11Ni-N	Wld. pipe	SA-312	...	S30815	...	...
44	21Cr-11Ni-N	Bar	SA-479	...	S30815	...	...
45	21Cr-11Ni-N	Bar	SA-479	...	S30815	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	4	98	45	NP	750	750	NP	HA-2	G5
2	8	4	98	45	NP		750	NP	HA-2	...
3	8	4	98	45	NP	750	750	NP	HA-2	G5, G24
4	8	4	98	45	NP	NP	750	NP	HA-2	G24
5	8	4	100	45	NP	750	750	650	HA-2	G5
6	8	4	100	45	NP	NP	750	650	HA-2	...
7	8	4	100	45	NP	750	750	650	HA-2	G5
8	8	4	100	45	NP	NP	750	650	HA-2	
9	8	3	92	45	NP	NP	850	NP	HA-2	G5
10	8	3	92	45	NP	NP	850	NP	HA-2	...
11	10H	1	94	65	NP	NP	600	NP	HA-5	G19
12	10H	1	94	65	NP	NP	600	NP	HA-5	G19
13	10H	1	94	65	NP	NP	600	NP	HA-5	G19
14	10H	1	94	65	NP	NP	600	NP	HA-5	G19, G24
15	10H	1	94	65	NP	NP	600	NP	HA-5	G19
16	10H	1	94	65	NP	NP	600	NP	HA-5	G19, G24
17	10H	1	94	65	NP	NP	600	NP	HA-5	G19, W14
18	10H	1	101	77	NP	NP	600	NP	HA-5	G19
19	10H	1	101	77	NP	NP	600	NP	HA-5	G19
20	10H	1	101	77	NP	NP	600	NP	HA-5	G19, G24
21	10H	1	101	77	NP	NP	600	NP	HA-5	G19
22	10H	1	101	77	NP	NP	600	NP	HA-5	G19, G24
23	8	3	90	50	NP	NP	600	600	HA-6	...
24	8	3	90	50	NP	NP	600	600	HA-6	G5
25	8	3	90	50	NP	NP	600	600	HA-6	...
26	8	3	90	50	NP	NP	600	600	HA-6	G5, G24
27	8	3	90	50	NP	NP	600	600	HA-6	G24
28	8	3	90	50	NP	NP	600	600	HA-6	G5
29	8	3	90	50	NP	NP	600	600	HA-6	...
30	8	3	90	50	NP	NP	600	600	HA-6	G5
31	8	3	90	50	NP	NP	600	600	HA-6	...
32	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, T5
33	8	2	87	45	1650	NP	1650	650	HA-6	G6, T6
34	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, T5
35	8	2	87	45	1650	NP	1650	650	HA-6	G6, T6
36	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, T5
37	8	2	87	45	1650	NP	1650	650	HA-6	G6, T6
38	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, G24, T5
39	8	2	87	45	1650	NP	1650	650	HA-6	G6, G24, T6
40	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, T5
41	8	2	87	45	1650	NP	1650	650	HA-6	G6, T6
42	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, G24, T5
43	8	2	87	45	1650	NP	1650	650	HA-6	G6, G24, T6
44	8	2	87	45	1650	NP	1650	650	HA-6	G5, G6, T5
45	8	2	87	45	1650	NP	1650	650	HA-6	G6, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	28.0	...	28.0	...	26.6	25.4	24.5	23.9	23.8	23.7	23.6	...	...	...
2	28.0	...	24.5	...	21.9	20.3	19.1	18.3	18.0	17.9	17.7	...	...	...
3	23.8	...	23.8	...	22.6	21.6	20.8	20.4	20.2	20.1	20.1	...	...	...
4	23.8	...	20.8	...	18.6	17.2	16.2	15.5	15.3	15.2	15.1	...	...	...
5	28.6	...	28.6	...	27.2	25.9	25.0	24.4	24.3	24.1	23.9	...	...	...
6	28.6	...	24.5	...	21.9	20.2	19.1	18.3	18.0	17.8	17.7	...	...	...
7	24.3	...	24.3	...	23.1	22.0	21.3	20.8	20.6	20.5	20.3	...	...	...
8	24.3	...	20.8	...	18.7	17.2	16.2	15.5	15.2	15.2	15.1	...	...	...
9	26.3	...	25.9	...	24.3	23.2	22.5	22.1	21.9	21.7	21.5	21.3	21.0	...
10	26.3	...	23.9	...	21.1	19.3	18.2	17.4	17.1	16.8	16.4	16.1	15.7	...
11	26.9	...	26.9	...	25.6	24.7	24.7	24.7	...	...	...	...	...	...
12	26.9	...	26.9	...	25.6	24.7	24.7	24.7	...	...	...	...	...	...
13	26.9	...	26.9	...	25.6	24.7	24.7	24.7	...	...	...	...	...	...
14	22.8	...	21.1	...	19.8	19.1	19.1	19.1	...	...	...	...	...	...
15	26.9	...	26.9	...	25.6	24.7	24.7	24.7	...	...	...	...	...	...
16	22.8	...	21.1	...	19.8	19.1	19.1	19.1	...	...	...	...	...	...
17	26.9	...	26.9	...	25.6	24.7	24.7	24.7	...	...	...	...	...	...
18	28.9	...	28.9	...	27.5	26.5	26.5	26.5	...	...	...	...	...	...
19	28.9	...	28.9	...	27.5	26.5	26.5	26.5	...	...	...	...	...	...
20	24.5	...	24.5	...	23.4	22.6	22.6	22.6	...	...	...	...	...	...
21	28.9	...	28.9	...	27.5	26.5	26.5	26.5	...	...	...	...	...	...
22	24.5	...	24.5	...	23.4	22.6	22.6	22.6	...	...	...	...	...	...
23	25.7	...	25.7	...	22.0	19.6	18.1	17.1	...	...	...	...	...	...
24	25.7	...	25.7	...	24.0	22.8	22.0	21.5	...	...	...	...	...	...
25	25.7	...	25.7	...	22.0	19.6	18.1	17.1	...	...	...	...	...	...
26	21.9	...	21.9	...	20.4	19.4	18.7	18.3	...	...	...	...	...	...
27	21.9	...	21.9	...	18.7	16.6	15.3	14.6	...	...	...	...	...	...
28	25.7	...	25.7	...	24.0	22.8	22.0	21.5	...	...	...	...	...	...
29	25.7	...	25.7	...	22.0	19.6	18.1	17.1	...	...	...	...	...	...
30	25.7	...	25.7	...	24.0	22.8	22.0	21.5	...	...	...	...	...	...
31	25.7	...	25.7	...	22.0	19.6	18.1	17.1	...	...	...	...	...	...
32	24.9	...	24.7	...	23.3	22.4	21.8	21.4	21.2	21.0	20.8	20.6	20.3	20.0
33	24.9	...	24.7	...	22.0	19.9	18.5	17.7	17.4	17.2	17.0	16.8	16.6	16.4
34	24.9	...	24.7	...	23.3	22.4	21.8	21.4	21.2	21.0	20.8	20.6	20.3	20.0
35	24.9	...	24.7	...	22.0	19.9	18.5	17.7	17.4	17.2	17.0	16.8	16.6	16.4
36	24.9	...	24.7	...	23.3	22.4	21.8	21.4	21.2	21.0	20.8	20.6	20.3	20.0
37	24.9	...	24.7	...	22.0	19.9	18.5	17.7	17.4	17.2	17.0	16.8	16.6	16.4
38	21.1	...	21.0	...	19.8	19.1	18.5	18.2	18.0	17.8	17.7	17.5	17.3	17.0
39	21.1	...	21.0	...	18.7	16.9	15.8	15.0	14.8	14.6	14.5	14.3	14.2	14.0
40	24.9	...	24.7	...	23.3	22.4	21.8	21.4	21.2	21.0	20.8	20.6	20.3	20.0
41	24.9	...	24.7	...	22.0	19.9	18.5	17.7	17.4	17.2	17.0	16.8	16.6	16.4
42	21.1	...	21.0	...	19.8	19.1	18.5	18.2	18.0	17.8	17.7	17.5	17.3	17.0
43	21.1	...	21.0	...	18.7	16.9	15.8	15.0	14.8	14.6	14.5	14.3	14.2	14.0
44	24.9	...	24.7	...	23.3	22.4	21.8	21.4	21.2	21.0	20.8	20.6	20.3	20.0
45	24.9	...	24.7	...	22.0	19.9	18.5	17.7	17.4	17.2	17.0	16.8	16.6	16.4

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	19.1	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
33	16.2	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
34	19.1	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
35	16.2	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
36	19.1	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
37	16.2	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
38	16.3	12.7	9.9	7.7	5.9	4.4	3.4	2.6	2.0	1.6	1.4	1.1	0.85	0.73	0.60
39	13.8	12.7	9.9	7.7	5.9	4.4	3.4	2.6	2.0	1.6	1.4	1.1	0.85	0.73	0.60
40	19.1	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
41	16.2	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
42	16.3	12.7	9.9	7.7	5.9	4.4	3.4	2.6	2.0	1.6	1.4	1.1	0.85	0.73	0.60
43	13.8	12.7	9.9	7.7	5.9	4.4	3.4	2.6	2.0	1.6	1.4	1.1	0.85	0.73	0.60
44	19.1	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71
45	16.2	14.9	11.6	9.0	6.9	5.2	4.0	3.1	2.4	1.9	1.6	1.3	1.0	0.86	0.71

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	22Cr-2Ni-Mo-N	Forgings	SA-182	F66	S32202	...	...
2	22Cr-2Ni-Mo-N	Plate	SA-240	...	S32202	...	...
3	22Cr-2Ni-Mo-N	Bar	SA-479	...	S32202	...	...
4	22Cr-2Ni-Mo-N	Smls. tube	SA-789	...	S32202	...	...
5	22Cr-2Ni-Mo-N	Wld. tube	SA-789	...	S32202	...	...
6	22Cr-2Ni-Mo-N	Smls. pipe	SA-790	...	S32202	...	...
7	22Cr-2Ni-Mo-N	Wld. pipe	SA-790	...	S32202	...	...
8	22Cr-2Ni-Mo-N	Smls. fittings	SA-815	...	S32202	...	...
9	22Cr-2Ni-Mo-N	Wld. fittings	SA-815	...	S32202	...	...
10	22Cr-5Ni-3Mo-N	Castings	SA-995	4A	J92205	...	...
11	22Cr-5Ni-3Mo-N	Forgings	SA-182	F51	S31803	...	...
12	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...	...
13	22Cr-5Ni-3Mo-N	Bar	SA-479	...	S31803	...	...
14	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S31803	...	...
15	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S31803	...	...
16	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S31803	...	...
17	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S31803	...	...
18	22Cr-5Ni-3Mo-N	Smls. fittings	SA-815	...	S31803	...	...
19	22Cr-5Ni-3Mo-N	Wld. fittings	SA-815	...	S31803	...	...
20	22Cr-5Ni-3Mo-N	Smls. & wld. fittings	SA-815	...	S31803	...	...
21	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S32205	...	...
22	22Cr-5Ni-3Mo-N	Bar	SA-479	...	S32205	...	...
23	22Cr-5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...	S32205	...	...
24	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S32205	...	...
25	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S32205	...	...
26	22Cr-5Ni-3Mo-N	Smls. & wld. fittings	SA-815	...	S32205	...	...
27	22Cr-5Ni-3Mo-N	Smls. fittings	SA-815	...	S32205	...	...
28	22Cr-5Ni-3Mo-N	Wld. fittings	SA-815	...	S32205	...	...
29	22Cr-5Ni-3Mo-N	Forgings	SA-182	F60	S32205	...	...
30	22Cr-5Ni-3Mo-N	Smls. & wld. tube	SA-789	...	S32205	...	...
31	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S32205	...	...
32	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S32205	...	...
33	22Cr-13Ni-5Mn	Castings	SA-351	CG6MMN	J93790	...	...
34	22Cr-13Ni-5Mn	Forgings	SA-182	FXM-19	S20910	...	...
35	22Cr-13Ni-5Mn	Smls. tube	SA-213	XM-19	S20910	...	...
36	22Cr-13Ni-5Mn	Plate	SA-240	XM-19	S20910	...	...
37	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...	...
38	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...	...
39	22Cr-13Ni-5Mn	Smls. & wld. pipe	SA-312	TPXM-19	S20910	...	...
40	22Cr-13Ni-5Mn	Smls. pipe	SA-312	TPXM-19	S20910	...	...
41	22Cr-13Ni-5Mn	Wld. pipe	SA-312	TPXM-19	S20910	...	...
42	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	1	...
43	22Cr-13Ni-5Mn	Smls. & wld. fittings	SA-403	XM-19	S20910	...	...
44	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	...	...
45	22Cr-13Ni-5Mn	Wld. pipe	SA-813	TPXM-19	S20910	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted) (SPT = Supports Only)					
					I	III	VIII-1	XII		
1	10H	1	94	65	NP	NP	600	NP	HA-5	G19
2	10H	1	94	65	NP	NP	600	NP	HA-5	G19
3	10H	1	94	65	NP	NP	600	NP	HA-5	G19
4	10H	1	94	65	NP	NP	600	NP	HA-5	G19
5	10H	1	94	65	NP	NP	600	NP	HA-5	G19, G24
6	10H	1	94	65	NP	NP	600	NP	HA-5	G19
7	10H	1	94	65	NP	NP	600	NP	HA-5	G19, G24
8	10H	1	94	65	NP	NP	600	NP	HA-5	G19
9	10H	1	94	65	NP	NP	600	NP	HA-5	G3, G19
10	10H	1	90	60	NP	NP	500	NP	HA-5	G1, G19
11	10H	1	90	65	600	NP	600	600	HA-5	G19
12	10H	1	90	65	600	NP	600	600	HA-5	G19
13	10H	1	90	65	600	NP	600	NP	HA-5	G19
14	10H	1	90	65	600	NP	600	600	HA-5	G19
15	10H	1	90	65	600	NP	600	600	HA-5	G19, G24
16	10H	1	90	65	600	NP	600	600	HA-5	G19
17	10H	1	90	65	600	NP	600	600	HA-5	G19, G24
18	10H	1	90	65	600	NP	NP	NP	HA-5	G19
19	10H	1	90	65	600	NP	NP	NP	HA-5	G19, G24
20	10H	1	90	65	NP	NP	600	600	HA-5	G19, W14
21	10H	1	95	65	NP	600	600	600	HA-5	G19
22	10H	1	95	65	NP	600	600	NP	HA-5	G19
23	10H	1	95	65	NP	600	NP	NP	HA-5	G19, W12
24	10H	1	95	65	NP	NP	600	600	HA-5	G19
25	10H	1	95	65	NP	NP	600	600	HA-5	G19, G24
26	10H	1	95	65	NP	600	NP	NP	HA-5	G19, W12
27	10H	1	95	65	NP	NP	600	600	HA-5	G19
28	10H	1	95	65	NP	NP	600	600	HA-5	G19, G24
29	10H	1	95	70	NP	600	600	600	HA-5	G19
30	10H	1	95	70	NP	600	NP	NP	HA-5	G19, W12
31	10H	1	95	70	NP	NP	600	600	HA-5	G19
32	10H	1	95	70	NP	NP	600	600	HA-5	G19, G24
33	8	3	85	42.5	NP	NP	1050	650	HA-2	G1
34	8	3	100	55	NP	800	1200	650	HA-6	G5, T8
35	8	3	100	55	NP	NP	1200	NP	HA-6	T8
36	8	3	100	55	NP	800	1200	650	HA-6	G5, T8
37	8	3	100	55	NP	800	NP	NP	HA-6	G5, W12
38	8	3	100	55	NP	NP	1200	650	HA-6	G24, T8
39	8	3	100	55	NP	800	NP	NP	HA-6	G5, W12
40	8	3	100	55	NP	NP	1200	650	HA-6	T8
41	8	3	100	55	NP	NP	1200	650	HA-6	G24, T8
42	8	3	100	55	NP	800	NP	NP	HA-6	G5, W12
43	8	3	100	55	NP	800	1200	650	HA-6	G5, T8, W12, W14
44	8	3	100	55	NP	800	1200	650	HA-6	G5, G22, T8
45	8	3	100	55	NP	800	NP	NP	HA-6	G5, W12

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
2	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
3	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
4	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
5	22.8	22.8	22.6	21.7	21.1	21.0	21.0	21.0	...	...	...	...	...	...
6	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
7	22.8	22.8	22.6	21.7	21.1	21.0	21.0	21.0	...	...	...	...	...	...
8	26.9	26.9	26.6	25.5	24.9	24.7	24.7	24.7	...	...	...	...	...	...
9	22.8	22.8	22.6	21.7	21.1	21.0	21.0	21.0	...	...	...	...	...	...
10	25.7	25.7	25.7	25.2	24.6	24.3	24.3	...	...	...	...	...	...	...
11	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
12	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
13	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
14	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
15	21.9	...	21.9	...	21.1	20.3	19.8	19.6	...	...	...	...	...	...
16	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
17	21.9	...	21.9	...	21.1	20.3	19.8	19.6	...	...	...	...	...	...
18	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
19	21.9	...	21.9	...	21.1	20.3	19.8	19.6	...	...	...	...	...	...
20	25.7	...	25.7	...	24.8	23.9	23.3	23.1	...	...	...	...	...	...
21	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
22	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
23	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
24	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
25	23.1	...	23.0	...	22.3	21.4	20.9	20.7	...	...	...	...	...	...
26	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
27	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
28	23.1	...	23.0	...	22.3	21.4	20.9	20.7	...	...	...	...	...	...
29	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
30	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
31	27.1	...	27.1	...	26.2	25.2	24.6	24.3	...	...	...	...	...	...
32	23.1	...	23.0	...	22.3	21.4	20.9	20.7	...	...	...	...	...	...
33	19.4	...	19.3	...	17.8	16.8	16.0	15.4	15.2	14.9	14.7	14.6	14.4	14.2
34	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	23.9	23.6
35	28.6	...	28.4	...	26.9	26.0	25.5	25.0	24.6	24.2	23.9	23.5	23.3	23.0
36	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	23.9	23.6
37	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	...	...
38	24.3	...	24.1	...	22.9	22.1	21.6	21.2	20.9	20.6	20.3	20.0	19.8	19.5
39	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	...	...
40	28.6	...	28.4	...	26.9	26.0	25.5	25.0	24.6	24.2	23.9	23.5	23.3	23.0
41	24.3	...	24.1	...	22.9	22.1	21.6	21.2	20.9	20.6	20.3	20.0	19.8	19.5
42	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	...	...
43	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	23.9	23.6
44	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	23.9	23.6
45	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	14.1	13.9	13.6	...	...	...	...	...	...	...	...	...	...	...	...
34	23.2	22.8	22.3	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
35	22.7	22.5	22.2	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
36	23.2	22.8	22.3	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	19.3	19.1	18.9	17.3	11.1	7.1	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	22.7	22.5	22.2	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
41	19.3	19.1	18.9	17.3	11.1	7.1	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	23.2	22.8	22.3	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
44	23.2	22.8	22.3	20.4	13.0	8.3	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	22Cr-13Ni-5Mn	Wld. pipe	SA-814	TPXM-19	S20910	...	...
2	23Cr-4Ni-Mo-Cu-N	Plate	SA-240	...	S32304	...	...
3	23Cr-4Ni-Mo-Cu-N	Smls. tube	SA-789	...	S32304	...	>1
4	23Cr-4Ni-Mo-Cu-N	Wld. tube	SA-789	...	S32304	...	>1
5	23Cr-4Ni-Mo-Cu-N	Smls. pipe	SA-790	...	S32304	...	...
6	23Cr-4Ni-Mo-Cu-N	Wld. pipe	SA-790	...	S32304	...	...
7	23Cr-4Ni-Mo-Cu-N	Smls. tube	SA-789	...	S32304	...	≤1
8	23Cr-4Ni-Mo-Cu-N	Wld. tube	SA-789	...	S32304	...	≤1
9	23Cr-12Ni	Smls. & wld. fittings	SA-403	309	S30900	...	...
10	23Cr-12Ni	Smls. tube	SA-213	TP309S	S30908	...	...
11	23Cr-12Ni	Smls. tube	SA-213	TP309S	S30908	...	...
12	23Cr-12Ni	Plate	SA-240	309S	S30908	...	...
13	23Cr-12Ni	Plate	SA-240	309S	S30908	...	...
14	23Cr-12Ni	Wld. tube	SA-249	TP309S	S30908	...	...
15	23Cr-12Ni	Wld. tube	SA-249	TP309S	S30908	...	...
16	23Cr-12Ni	Smls. & wld. pipe	SA-312	TP309S	S30908	...	...
17	23Cr-12Ni	Smls. pipe	SA-312	TP309S	S30908	...	...
18	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...
19	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...
(25) 20	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...
(25) 21	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...
22	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	1	...
23	23Cr-12Ni	Bar	SA-479	309S	S30908	...	...
24	23Cr-12Ni	Bar	SA-479	309S	S30908	...	...
25	23Cr-12Ni	Wld. pipe	SA-813	TP309S	S30908	...	...
26	23Cr-12Ni	Wld. pipe	SA-813	TP309S	S30908	...	...
27	23Cr-12Ni	Wld. pipe	SA-814	TP309S	S30908	...	...
28	23Cr-12Ni	Wld. pipe	SA-814	TP309S	S30908	...	...
29	23Cr-12Ni	Smls. tube	SA-213	TP309H	S30909	...	...
30	23Cr-12Ni	Smls. tube	SA-213	TP309H	S30909	...	...
(25) 31	23Cr-12Ni	Plate	SA-240	309H	S30909	...	...
(25) 32	23Cr-12Ni	Plate	SA-240	309H	S30909	...	...
33	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...	...
34	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...	...
35	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...	...
36	23Cr-12Ni	Smls. pipe	SA-312	TP309H	S30909	...	...
37	23Cr-12Ni	Smls. pipe	SA-312	TP309H	S30909	...	...
(25) 38	23Cr-12Ni	Wld. pipe	SA-312	TP309H	S30909	...	...
(25) 39	23Cr-12Ni	Wld. pipe	SA-312	TP309H	S30909	...	...
40	23Cr-12Ni	Bar	SA-479	309H	S30909	...	...
41	23Cr-12Ni	Bar	SA-479	309H	S30909	...	...
42	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb	S30940	...	...
43	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb	S30940	...	...
44	23Cr-12Ni-Cb	Plate	SA-240	309Cb	S30940	...	...
45	23Cr-12Ni-Cb	Plate	SA-240	309Cb	S30940	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	3	100	55	NP	800	NP	NP	HA-6	G5, W12
2	10H	1	87	58	NP	NP	600	600	HA-6	G19
3	10H	1	87	58	NP	NP	600	600	HA-6	G19
4	10H	1	87	58	NP	NP	600	600	HA-6	G19, G24
5	10H	1	87	58	NP	NP	600	600	HA-6	G19
6	10H	1	87	58	NP	NP	600	600	HA-6	G19, G24
7	10H	1	100	65	NP	NP	600	600	HA-5	G19
8	10H	1	100	65	NP	NP	600	600	HA-5	G19, G24
9	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, T5, W12, W14
10	8	2	75	30	1500	NP	1500	650	HA-2	G5, G12, T5
11	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
12	8	2	75	30	1500	800	1500	650	HA-2	G5, G12, T5
13	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
14	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
15	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
16	8	2	75	30	1500	800	1500	650	HA-2	G5, G12, T5, W12, W14
17	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
18	8	2	75	30	1500	NP	NP	NP	HA-2	G5, G12, T5, W13
19	8	2	75	30	1500	NP	NP	NP	HA-2	G12, T6, W13
20	8	2	75	30	1500	NP	1500	650	HA-2	G5, G12, G24, T5
21	8	2	75	30	1500	NP	1500	650	HA-2	G12, G24, T6
22	8	2	75	30	NP	800	NP	NP	HA-2	G5, W12
23	8	2	75	30	1000	NP	1000	650	HA-2	G5, G12, G22, T5
24	8	2	75	30	1000	NP	1000	650	HA-2	G12, G22, T6
25	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
26	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
27	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
28	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
29	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
30	8	2	75	30	1500	NP	1500	NP	HA-2	T7
31	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
32	8	2	75	30	1500	NP	1500	NP	HA-2	T7
33	8	2	75	30	NP	800	NP	NP	HA-2	G5, W12
34	8	2	75	30	NP	NP	1500	NP	HA-2	G5, G24, T6
35	8	2	75	30	NP	NP	1500	NP	HA-2	G24, T7
36	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
37	8	2	75	30	1500	NP	1500	NP	HA-2	T7
38	8	2	75	30	1500	NP	1500	NP	HA-2	G5, G24, T6
39	8	2	75	30	1500	NP	1500	NP	HA-2	G24, T7
40	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
41	8	2	75	30	1500	NP	1500	NP	HA-2	T7
42	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, T5
43	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6
44	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, T5
45	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	28.6	...	28.4	...	26.9	26.0	25.5	25.1	24.9	24.7	24.5	24.2	...	...
2	24.9	...	24.0	...	22.5	21.7	21.3	21.0	...	...	...	...	...	...
3	24.9	...	24.0	...	22.5	21.7	21.3	21.0	...	...	...	...	...	...
4	21.1	...	20.4	...	19.1	18.5	18.1	17.9	...	...	...	...	...	...
5	24.9	...	24.0	...	22.5	21.7	21.3	21.0	...	...	...	...	...	...
6	21.1	...	20.4	...	19.1	18.5	18.1	17.9	...	...	...	...	...	...
7	28.6	...	27.6	...	25.9	25.0	24.6	24.3	...	...	...	...	...	...
8	24.3	...	23.4	...	22.0	21.3	20.9	20.6	...	...	...	...	...	...
9	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
10	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
11	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
12	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
13	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
14	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
15	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
16	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
17	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
18	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
19	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
20	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
21	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
22	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
23	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
24	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
25	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
26	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
27	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
28	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
29	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
30	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
31	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
32	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
33	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
34	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
35	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
36	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
37	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
38	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
39	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
40	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
41	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
42	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
43	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
44	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
45	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
10	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
11	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
12	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
13	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
14	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
15	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
16	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
17	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
18	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
19	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
20	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	(25)
21	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	15.9	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
24	12.5	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
25	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
26	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
27	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
28	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
29	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
30	12.5	12.3	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
31	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	(25)
32	12.5	12.3	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	14.4	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
35	10.6	10.4	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
36	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
37	12.5	12.3	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
38	14.4	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	(25)
39	10.6	10.4	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	(25)
40	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
41	12.5	12.3	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	1.0	0.75	...	...	...
42	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
43	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
44	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
45	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb	S30940	...	...
2	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb	S30940	...	...
3	23Cr-12Ni-Cb	Smls. & wld. pipe	SA-312	TP309Cb	S30940	...	...
4	23Cr-12Ni-Cb	Smls. pipe	SA-312	TP309Cb	S30940	...	...
5	23Cr-12Ni-Cb	Wld. pipe	SA-312	TP309Cb	S30940	...	...
6	23Cr-12Ni-Cb	Wld. pipe	SA-312	TP309Cb	S30940	...	...
7	23Cr-12Ni-Cb	Bar	SA-479	309Cb	S30940	...	...
8	23Cr-12Ni-Cb	Bar	SA-479	309Cb	S30940	...	...
9	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb	S30940	...	...
10	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb	S30940	...	...
11	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb	S30940	...	...
12	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb	S30940	...	...
13	23Cr-25Ni-5.5Mo-N	Forgings	SA-182	...	S32053	...	...
14	23Cr-25Ni-5.5Mo-N	Forgings	SA-182	...	S32053	...	...
15	23Cr-25Ni-5.5Mo-N	Plate	SA-240	...	S32053	...	...
16	23Cr-25Ni-5.5Mo-N	Plate	SA-240	...	S32053	...	...
17	23Cr-25Ni-5.5Mo-N	Wld. tube	SA-249	...	S32053	...	...
18	23Cr-25Ni-5.5Mo-N	Wld. tube	SA-249	...	S32053	...	...
19	23Cr-25Ni-5.5Mo-N	Smls. & wld. pipe	SA-312	...	S32053	...	...
20	23Cr-25Ni-5.5Mo-N	Smls. & wld. pipe	SA-312	...	S32053	...	...
21	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-358	...	S32053	...	...
22	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-358	...	S32053	...	...
23	23Cr-25Ni-5.5Mo-N	Fittings	SA-403	...	S32053	...	...
24	23Cr-25Ni-5.5Mo-N	Fittings	SA-403	...	S32053	...	...
25	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-409	...	S32053	...	...
26	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-409	...	S32053	...	...
27	23Cr-25Ni-5.5Mo-N	Bar	SA-479	...	S32053	...	...
28	23Cr-25Ni-5.5Mo-N	Bar	SA-479	...	S32053	...	...
29	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-813	...	S32053	...	...
30	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-813	...	S32053	...	...
31	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-814	...	S32053	...	...
32	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-814	...	S32053	...	...
33	24Cr-10Ni-4Mo-N	Castings	SA-995	2A	J93345	...	...
34	24Cr-22Ni-6Mo-2W-Cu-N	Forgings	SA-182	F58	S31266	...	...
35	24Cr-22Ni-6Mo-2W-Cu-N	Smls. tube	SA-213	...	S31266	...	...
36	24Cr-22Ni-6Mo-2W-Cu-N	Plate	SA-240	...	S31266	...	...
(25) 37	24Cr-22Ni-6Mo-2W-Cu-N	Wld. tube	SA-249	...	S31266	...	...
38	24Cr-22Ni-6Mo-2W-Cu-N	Smls. pipe	SA-312	...	S31266	...	...
(25) 39	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-312	...	S31266	...	...
(25) 40	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-358	...	S31266	...	...
41	24Cr-22Ni-6Mo-2W-Cu-N	Smls. fittings	SA-403	...	S31266	...	...
42	24Cr-22Ni-6Mo-2W-Cu-N	Wld. fittings	SA-403	...	S31266	...	...
43	24Cr-22Ni-6Mo-2W-Cu-N	Bar, shapes	SA-479	...	S31266	...	...
(25) 44	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-813	...	S31266	...	...
45	25Cr-4Ni-4Mo-Ti	Plate	SA-240	...	S44635	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
2	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
3	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, T5, W12
4	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6
5	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
6	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
7	8	2	75	30	NP	NP	1000	650	HA-2	G5, G12, G22
8	8	2	75	30	NP	NP	1000	650	HA-2	G12, G22
9	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
10	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
11	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G13, G24, T5
12	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
13	8	4	93	43	NP	NP	662	NP	NFN-12	G5
14	8	4	93	43	NP	NP	662	NP	NFN-12	...
15	8	4	93	43	NP	NP	662	NP	NFN-12	G5
16	8	4	93	43	NP	NP	662	NP	NFN-12	...
17	8	4	93	43	NP	NP	662	NP	NFN-12	G5, W12
18	8	4	93	43	NP	NP	662	NP	NFN-12	W12
19	8	4	93	43	NP	NP	662	NP	NFN-12	G5, W12
20	8	4	93	43	NP	NP	662	NP	NFN-12	W12
21	8	4	93	43	NP	NP	662	NP	NFN-12	G5, W12
22	8	4	93	43	NP	NP	662	NP	NFN-12	W12
23	8	4	93	43	NP	NP	662	NP	NFN-12	G5
24	8	4	93	43	NP	NP	662	NP	NFN-12	...
25	8	4	93	43	NP	NP	662	NP	NFN-12	G5, W12
26	8	4	93	43	NP	NP	662	NP	NFN-12	W12
27	8	4	93	43	NP	NP	662	NP	NFN-12	G5
28	8	4	93	43	NP	NP	662	NP	NFN-12	...
29	8	4	93	43	NP	NP	662	NP	NFN-12	G5, G12, W12
30	8	4	93	43	NP	NP	662	NP	NFN-12	G12, W12
31	8	4	93	43	NP	NP	662	NP	NFN-12	G5, G12, W12
32	8	4	93	43	NP	NP	662	NP	NFN-12	G12, W12
33	10H	1	95	65	NP	NP	600	600	HA-5	G1, G19
34	45	...	109	61	NP	NP	800	NP	HA-10	G19
35	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19
36	45	...	109	61	NP	NP	800	NP	HA-10	G19
37	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19, G24
38	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19
39	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19, G24
40	45	...	109	61	NP	NP	800	NP	HA-10	G19, G24
41	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19
42	45	...	109	61	NP	NP	800	NP	HA-10	G3, G5, G19
43	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19
44	45	...	109	61	NP	NP	800	NP	HA-10	G5, G19, G24
45	10I	1	90	75	NP	NP	500	500	HA-5	G19

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
2	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
3	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
4	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
5	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
6	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
7	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	17.5	17.2
8	20.0	...	17.5	...	16.1	15.1	14.4	13.9	13.7	13.5	13.3	13.1	12.9	12.7
9	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
10	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
11	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	14.8	14.6
12	17.0	...	14.9	...	13.7	12.8	12.2	11.8	11.6	11.5	11.3	11.2	11.0	10.8
13	26.5	...	26.5	...	25.1	23.9	23.0	22.3	22.0	21.8	...	...	...	...
14	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
15	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
16	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
17	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
18	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
19	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
20	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
21	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
22	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
23	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
24	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
25	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
26	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
27	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
28	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
29	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
30	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
31	26.5	...	26.5	...	25.1	23.9	23.3	22.3	22.0	21.8	...	...	...	...
32	26.5	...	24.2	...	21.9	20.8	19.3	18.5	18.2	17.9	...	...	...	...
33	27.1	...	27.1	...	25.1	24.2	24.2	24.2	...	...	...	...	...	...
34	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
35	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
36	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
37	26.5	26.5	26.1	25.3	24.6	23.5	22.8	22.4	22.2	22.0	21.8	21.6	...	...
38	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
39	26.5	26.5	26.1	25.3	24.6	23.5	22.8	22.4	22.2	22.0	21.8	21.6	...	...
40	26.5	26.5	26.1	25.3	24.6	23.5	22.8	22.4	22.2	22.0	21.8	21.6	...	...
41	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
42	26.5	26.5	26.1	25.3	24.6	23.5	22.8	22.4	22.2	22.0	21.8	21.6	...	...
43	31.1	31.1	30.8	29.8	28.9	27.7	26.9	26.3	26.1	25.9	25.7	25.4	...	...
44	26.5	26.5	26.1	25.3	24.6	23.5	22.8	22.4	22.2	22.0	21.8	21.6	...	...
45	25.7	...	24.9	...	23.5	22.5	22.0	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
2	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
3	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
4	12.5	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
5	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
6	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
7	15.9	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
8	12.5	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
9	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
10	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
11	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
12	10.6	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	25Cr-4Ni-4Mo-Ti	Wld. tube	SA-268	...	S44635	...	...
2	25Cr-5Ni-3Mo-2Cu	Castings	SA-995	1B	J93372	...	...
3	25Cr-5Ni-3Mo-2Cu	Plate	SA-240	...	S32550	...	...
4	25Cr-5Ni-3Mo-2Cu	Bar	SA-479	...	S32550	...	...
5	25Cr-5Ni-3Mo-2Cu	Smls. tube	SA-789	...	S32550	...	...
6	25Cr-5Ni-3Mo-2Cu	Wld. tube	SA-789	...	S32550	...	...
7	25Cr-5Ni-3Mo-2Cu	Smls. pipe	SA-790	...	S32550	...	...
8	25Cr-5Ni-3Mo-2Cu	Wld. pipe	SA-790	...	S32550	...	...
9	25Cr-6Ni-Mo-N	Forgings	SA-182	...	S32506	...	...
10	25Cr-6Ni-Mo-N	Plate, sheet	SA-240	...	S32506	...	...
11	25Cr-6Ni-Mo-N	Bar	SA-479	...	S32506	...	...
12	25Cr-6Ni-Mo-N	Smls. tube	SA-789	...	S32506	...	...
13	25Cr-6Ni-Mo-N	Wld. tube	SA-789	...	S32506	...	...
14	25Cr-6Ni-Mo-N	Smls. pipe	SA-790	...	S32506	...	...
15	25Cr-6Ni-Mo-N	Wld. pipe	SA-790	...	S32506	...	...
16	25Cr-6Ni-Mo-N	Plate	SA-240	...	S31200	...	...
17	25Cr-6.5Ni-3Mo-N	Smls. tube	SA-789	...	S31260	...	...
18	25Cr-6.5Ni-3Mo-N	Wld. tube	SA-789	...	S31260	...	...
19	25Cr-6.5Ni-3Mo-N	Smls. pipe	SA-790	...	S31260	...	...
20	25Cr-6.5Ni-3Mo-N	Wld. pipe	SA-790	...	S31260	...	...
21	25Cr-6.5Ni-3Mo-N	Plate	SA-240	...	S31260	...	...
22	25Cr-7Ni-3Mo-W-Cu-N	Forgings	SA-182	F54	S39274	...	...
23	25Cr-7Ni-3Mo-W-Cu-N	Smls. tube	SA-789	...	S39274	...	...
24	25Cr-7Ni-3Mo-W-Cu-N	Wld. tube	SA-789	...	S39274	...	...
25	25Cr-7Ni-3Mo-W-Cu-N	Smls. pipe	SA-790	...	S39274	...	...
26	25Cr-7Ni-3Mo-W-Cu-N	Wld. pipe	SA-790	...	S39274	...	...
27	25Cr-7Ni-4Mo-N	Forgings	SA-182	F53	S32750	...	...
28	25Cr-7Ni-4Mo-N	Plate, sheet	SA-240	...	S32750	...	...
29	25Cr-7Ni-4Mo-N	Smls. tube	SA-789	...	S32750	...	...
30	25Cr-7Ni-4Mo-N	Wld. tube	SA-789	...	S32750	...	...
31	25Cr-7Ni-4Mo-N	Smls. pipe	SA-790	...	S32750	...	...
32	25Cr-7Ni-4Mo-N	Wld. pipe	SA-790	...	S32750	...	...
(25) 33	25Cr-7.5Ni-3.5Mo-N-Cu-W	Castings	SA-995	CD3MWCuN	J93380	...	...
(25) 34	25Cr-7.5Ni-3.5Mo-N-Cu-W	Forgings	SA-182	F55	S32760	...	...
35	25Cr-7.5Ni-3.5Mo-N-Cu-W	Plate	SA-240	...	S32760	...	...
36	25Cr-7.5Ni-3.5Mo-N-Cu-W	Bar	SA-479	...	S32760	Annealed	...
37	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. tube	SA-789	...	S32760	...	...
38	25Cr-7.5Ni-3.5Mo-N-Cu-W	Wld. tube	SA-789	...	S32760	...	...
39	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. pipe	SA-790	...	S32760	...	...
40	25Cr-7.5Ni-3.5Mo-N-Cu-W	Wld. pipe	SA-790	...	S32760	...	...
41	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. fittings	SA-815	...	S32760	...	...
42	25Cr-12Ni	Castings	SA-351	CH8	J93400	...	...
43	25Cr-12Ni	Castings	SA-351	CH8	J93400	...	...
44	25Cr-12Ni	Cast pipe	SA-451	CPH8	J93400	...	...
45	25Cr-12Ni	Castings	SA-351	CH20	J93402	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature Limits										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	10I	1	90	75	NP	NP	500	500	HA-5	G19, G24
2	10H	1	100	70	NP	600	NP	NP	HA-5	G19, G29
3	10H	1	110	80	NP	NP	500	500	HA-5	G19
4	10H	1	110	80	NP	NP	500	500	HA-5	G19
5	10H	1	110	80	NP	NP	500	500	HA-5	G19
6	10H	1	110	80	NP	NP	500	500	HA-5	G19, G24
7	10H	1	110	80	NP	NP	500	500	HA-5	G19
8	10H	1	110	80	NP	NP	500	500	HA-5	G19, G24
9	10H	1	90	65	NP	NP	600	NP	HA-5	G19
10	10H	1	90	65	NP	NP	600	NP	HA-5	G19
11	10H	1	90	65	NP	NP	600	NP	HA-5	G19
12	10H	1	90	65	NP	NP	600	NP	HA-5	G19
13	10H	1	90	65	NP	NP	600	NP	HA-5	G19, G24
14	10H	1	90	65	NP	NP	600	NP	HA-5	G19
15	10H	1	90	65	NP	NP	600	NP	HA-5	G19, G24
16	10H	1	100	65	NP	NP	600	600	HA-5	G19
17	10H	1	100	65	NP	NP	650	650	HA-5	G19
18	10H	1	100	65	NP	NP	650	650	HA-5	G19, G24
19	10H	1	100	65	NP	NP	650	650	HA-5	G19
20	10H	1	100	65	NP	NP	650	650	HA-5	G19, G24
21	10H	1	100	70	NP	NP	650	650	HA-5	G19
22	10H	1	116	80	NP	NP	650	650	HA-8	G19
23	10H	1	116	80	NP	NP	650	650	HA-8	G19
24	10H	1	116	80	NP	NP	650	650	HA-8	G19, G24
25	10H	1	116	80	NP	NP	650	650	HA-8	G19
26	10H	1	116	80	NP	NP	650	650	HA-8	G19, G24
27	10H	1	116	80	NP	NP	600	NP	HA-5	G19
28	10H	1	116	80	NP	NP	600	NP	HA-5	G19
29	10H	1	116	80	NP	NP	600	600	HA-5	G19
30	10H	1	116	80	NP	NP	600	600	HA-5	G19, G24
31	10H	1	116	80	NP	NP	600	600	HA-5	G19
32	10H	1	116	80	NP	NP	600	600	HA-5	G19, G24
33	10H	1	100	65	NP	NP	600	NP	HA-5	G19
34	10H	1	109	80	NP	NP	600	NP	HA-9	G19
35	10H	1	109	80	NP	NP	600	NP	HA-9	G19
36	10H	1	109	80	NP	NP	600	NP	HA-9	G19
37	10H	1	109	80	NP	NP	600	NP	HA-9	G19
38	10H	1	109	80	NP	NP	600	NP	HA-9	G19, G24
39	10H	1	109	80	NP	NP	600	NP	HA-9	G19
40	10H	1	109	80	NP	NP	600	NP	HA-9	G19, G24
41	10H	1	109	80	NP	NP	600	NP	HA-9	G19, W14
42	8	2	65	28	NP	800	1500	650	HA-3	G1, G5, G12, G16, G17, G19, T6
43	8	2	65	28	NP	NP	1500	650	HA-3	G1, G12, G19, T7
44	8	2	65	28	NP	800	NP	NP	HA-3	G5, G16, G17, G19
45	8	2	70	30	NP	800	1500	650	HA-2	G1, G5, G12, G16, G17, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	21.9	...	21.2	...	19.9	19.1	18.7	...	...	...	...	...	...	...
2	28.6	...	28.6	...	27.9	27.5	27.5	27.4	...	...	...	...	...	...
3	31.4	...	31.3	...	29.5	28.6	28.2	...	...	...	...	...	...	...
4	31.4	...	31.3	...	29.5	28.6	28.2	...	...	...	...	...	...	...
5	31.4	...	31.3	...	29.5	28.6	28.2	...	...	...	...	...	...	...
6	26.7	...	26.6	...	25.1	24.3	24.0	...	...	...	...	...	...	...
7	31.4	...	31.3	...	29.5	28.6	28.2	...	...	...	...	...	...	...
8	26.7	...	26.6	...	25.1	24.3	24.0	...	...	...	...	...	...	...
9	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
10	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
11	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
12	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
13	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
14	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
15	25.7	...	25.7	...	24.4	24.1	24.1	24.1	...	...	...	...	...	...
16	28.6	...	28.6	...	27.1	26.3	26.1	26.1	...	...	...	...	...	...
17	28.6	...	28.5	...	27.1	26.4	26.3	26.3	26.3	...	...	...	...	...
18	24.3	...	24.3	...	23.0	22.5	22.4	22.4	22.4	...	...	...	...	...
19	28.6	...	28.5	...	27.1	26.4	26.3	26.3	26.3	...	...	...	...	...
20	24.3	...	24.3	...	23.0	22.5	22.4	22.4	22.4	...	...	...	...	...
21	28.6	...	28.5	...	27.1	26.4	26.3	26.3	26.3	...	...	...	...	...
22	33.1	...	33.1	...	31.6	31.4	31.4	31.4	31.4	...	...	...	...	...
23	33.1	...	33.1	...	31.6	31.4	31.4	31.4	31.4	...	...	...	...	...
24	28.2	...	28.2	...	26.8	26.7	26.7	26.7	26.7	...	...	...	...	...
25	33.1	...	33.1	...	31.6	31.4	31.4	31.4	31.4	...	...	...	...	...
26	28.2	...	28.2	...	26.8	26.7	26.7	26.7	26.7	...	...	...	...	...
27	33.1	...	33.0	...	31.2	30.1	29.6	29.4	...	...	...	...	...	...
28	33.1	...	33.0	...	31.2	30.1	29.6	29.4	...	...	...	...	...	...
29	33.1	...	33.0	...	31.2	30.1	29.6	29.4	...	...	...	...	...	...
30	28.2	...	28.0	...	26.5	25.6	25.2	25.0	...	...	...	...	...	...
31	33.1	...	33.0	...	31.2	30.1	29.6	29.4	...	...	...	...	...	...
32	28.2	...	28.0	...	26.5	25.6	25.2	25.0	...	...	...	...	...	...
33	28.6	28.5	28.4	27.7	26.9	26.6	26.6	26.6	...	...	...	...	...	...
34	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
35	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
36	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
37	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
38	26.5	...	25.7	...	24.8	24.8	24.8	24.8	...	...	...	...	...	...
39	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
40	26.5	...	25.7	...	24.8	24.8	24.8	24.8	...	...	...	...	...	...
41	31.1	...	30.2	...	29.2	29.2	29.2	29.2	...	...	...	...	...	...
42	18.6	...	17.0	...	15.8	15.4	15.4	15.4	15.3	15.2	15.0	14.8	14.4	13.9
43	18.6	...	15.3	...	14.1	13.5	13.1	12.7	12.4	12.1	11.8	11.4	11.0	10.7
44	18.6	...	17.0	...	15.8	15.4	15.4	15.4	15.3	15.2	15.0	14.8	...	...
45	20.0	...	18.3	...	17.0	16.6	16.6	16.6	16.5	16.4	16.2	15.9	15.5	14.9

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	13.2	11.1	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80	...	...	...
43	10.3	9.9	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	14.3	11.1	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80	...	...	...

(25)

(25)

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	25Cr-12Ni	Castings	SA-351	CH20	J93402	...	...
2	25Cr-12Ni	Cast pipe	SA-451	CPH20	J93402	...	...
3	25Cr-20Ni	Castings	SA-351	CK20	J94202	...	...
4	25Cr-20Ni	Castings	SA-351	CK20	J94202	...	...
5	25Cr-20Ni	Cast pipe	SA-451	CPK20	J94202	...	...
6	25Cr-20Ni	Forgings	SA-182	F310	S31000	...	>5
7	25Cr-20Ni	Forgings	SA-182	F310	S31000	...	≤5
8	25Cr-20Ni	Forgings	SA-965	F310	S31000	...	...
9	25Cr-20Ni	Smls. tube	SA-213	...	S31002	...	...
10	25Cr-20Ni	Smls. tube	SA-213	...	S31002	...	...
11	25Cr-20Ni	Smls. pipe	SA-312	...	S31002	...	...
12	25Cr-20Ni	Smls. pipe	SA-312	...	S31002	...	...
13	25Cr-20Ni	Smls. tube	SA-213	TP310S	S31008	...	...
14	25Cr-20Ni	Smls. tube	SA-213	TP310S	S31008	...	...
15	25Cr-20Ni	Plate	SA-240	310S	S31008	...	...
16	25Cr-20Ni	Plate	SA-240	310S	S31008	...	...
17	25Cr-20Ni	Wld. tube	SA-249	TP310S	S31008	...	...
18	25Cr-20Ni	Wld. tube	SA-249	TP310S	S31008	...	...
19	25Cr-20Ni	Smls. & wld. pipe	SA-312	TP310S	S31008	...	...
20	25Cr-20Ni	Smls. pipe	SA-312	TP310S	S31008	...	...
(25) 21	25Cr-20Ni	Wld. pipe	SA-312	TP310S	S31008	...	...
(25) 22	25Cr-20Ni	Wld. pipe	SA-312	TP310S	S31008	...	...
23	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	1	...
24	25Cr-20Ni	Smls. & wld. fittings	SA-403	310S	S31008	...	...
25	25Cr-20Ni	Bar	SA-479	310S	S31008	...	...
26	25Cr-20Ni	Bar	SA-479	310S	S31008	...	...
27	25Cr-20Ni	Wld. pipe	SA-813	TP310S	S31008	...	...
28	25Cr-20Ni	Wld. pipe	SA-813	TP310S	S31008	...	...
29	25Cr-20Ni	Wld. pipe	SA-814	TP310S	S31008	...	...
30	25Cr-20Ni	Wld. pipe	SA-814	TP310S	S31008	...	...
31	25Cr-20Ni	Bar	SA/JIS G4303	SUS310S	...	...	...
32	25Cr-20Ni	Smls. tube	SA-213	TP310H	S31009	...	...
33	25Cr-20Ni	Plate	SA-240	310H	S31009	...	...
34	25Cr-20Ni	Plate	SA-240	310H	S31009	...	...
35	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...	...
36	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...	...
37	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...	...
38	25Cr-20Ni	Smls. pipe	SA-312	TP310H	S31009	...	...
39	25Cr-20Ni	Smls. pipe	SA-312	TP310H	S31009	...	...
(25) 40	25Cr-20Ni	Wld. pipe	SA-312	TP310H	S31009	...	...
(25) 41	25Cr-20Ni	Wld. pipe	SA-312	TP310H	S31009	...	...
42	25Cr-20Ni	Bar	SA-479	310H	S31009	...	...
43	25Cr-20Ni	Bar	SA-479	310H	S31009	...	...
44	25Cr-20Ni-Cb	Smls. tube	SA-213	TP310Cb	S31040	...	...
45	25Cr-20Ni-Cb	Smls. tube	SA-213	TP310Cb	S31040	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	2	70	30	NP	NP	1500	650	HA-2	G1, G12, T7
2	8	2	70	30	NP	800	NP	NP	HA-2	G5, G16, G17
3	8	2	65	28	NP	800	1500	650	HA-3	G1, G5, G12, G16, G17, T6
4	8	2	65	28	NP	NP	1500	650	HA-3	G1, G12, T8
5	8	2	65	28	NP	800	NP	NP	HA-3	G5, G16, G17
6	8	2	70	30	NP	800	NP	NP	HA-2	G5
7	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, G14, T5
8	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, T5
9	8	2	73	30	NP	NP	842	NP	HA-2	G5
10	8	2	73	30	NP	NP	842	NP	HA-2	...
11	8	2	73	30	NP	NP	842	NP	HA-2	G5
12	8	2	73	30	NP	NP	842	NP	HA-2	...
13	8	2	75	30	1500	NP	1500	650	HA-2	G5, G12, T5
14	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
15	8	2	75	30	1500	800	1500	650	HA-2	G5, G12, T5
16	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
17	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
18	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
19	8	2	75	30	1500	800	1500	650	HA-2	G5, G12, T5, W12, W14
20	8	2	75	30	1500	NP	1500	650	HA-2	G12, T6
21	8	2	75	30	1500	NP	1500	650	HA-2	G5, G12, G14, G24, T5
22	8	2	75	30	1500	NP	1500	650	HA-2	G12, G14, G24, T6
23	8	2	75	30	NP	800	NP	NP	HA-2	G5, W12
24	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, T5, W12, W14
25	8	2	75	30	1000	NP	1000	650	HA-2	G12, G22, T6
26	8	2	75	30	1000	800	1000	650	HA-2	G5, G12, G22, T5
27	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
28	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
29	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
30	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
31	8	2	75	30	1000	800	1000	NP	HA-2	G5, G12, G22, T5
32	8	2	75	30	1500	800	1500	NP	HA-2	G5, T6
33	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
34	8	2	75	30	1500	NP	1500	NP	HA-2	T7
35	8	2	75	30	NP	800	NP	NP	HA-2	G5, W12
36	8	2	75	30	NP	NP	1500	NP	HA-2	G5, G12, G24, T6
37	8	2	75	30	NP	NP	1500	NP	HA-2	G12, G24, T7
38	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
39	8	2	75	30	1500	NP	1500	NP	HA-2	T7
40	8	2	75	30	1500	NP	1500	NP	HA-2	G5, G24, T6
41	8	2	75	30	1500	NP	1500	NP	HA-2	G24, T7
42	8	2	75	30	1500	NP	1500	NP	HA-2	G5, T6
43	8	2	75	30	1500	NP	1500	NP	HA-2	T7
44	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, T5
45	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	16.3	...	15.1	14.5	14.0	13.6	13.3	12.9	12.6	12.2	11.8	11.4
2	20.0	...	18.3	...	17.0	16.6	16.6	16.6	16.5	16.4	16.2	15.9	...	...
3	18.6	...	17.0	...	15.8	15.4	15.4	15.4	15.3	15.2	15.0	14.8	14.4	13.9
4	18.6	...	15.3	...	14.1	13.5	13.1	12.7	12.4	12.1	11.8	11.4	11.0	10.7
5	18.6	...	17.0	...	15.8	15.4	15.4	15.4	15.3	15.2	15.0	14.8	...	...
6	20.0	...	19.8	...	18.9	18.6	18.5	18.5	18.2	17.9	17.7	17.4	...	...
7	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
8	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
9	20.0	20.0	20.0	20.0	20.0	19.3	18.7	18.3	18.1	17.9	17.4	17.0	16.6	...
10	20.0	18.6	17.9	17.3	16.7	15.7	14.9	14.1	13.7	13.3	12.9	12.6	12.3	...
11	20.0	20.0	20.0	20.0	20.0	19.3	18.7	18.3	18.1	17.9	17.4	17.0	16.6	...
12	20.0	18.6	17.9	17.3	16.7	15.7	14.9	14.1	13.7	13.3	12.9	12.6	12.3	...
13	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
14	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
15	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
16	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
17	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
18	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
19	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
20	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
21	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
22	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
23	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	...	...
24	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
25	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
26	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
27	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
28	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
29	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
30	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
31	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
32	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
33	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
34	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
35	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	...	...
36	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
37	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
38	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
39	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
40	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
41	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
42	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
43	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
44	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
45	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	11.0	10.6	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	13.2	11.3	9.8	8.5	7.3	6.0	4.8	3.5	2.4	1.6	1.1	0.80	...	...	...
4	10.3	9.9	9.5	8.5	7.3	6.0	4.8	3.5	2.4	1.6	1.1	0.80	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
8	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
14	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
15	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
16	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
17	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
18	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
19	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
20	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
21	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
22	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
25	12.3	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
26	15.9	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
27	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
28	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
29	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
30	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
31	15.9	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
32	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
33	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
34	12.3	12.1	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	14.2	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
37	10.5	10.3	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
38	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
39	12.3	12.1	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
40	14.2	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
41	10.5	10.3	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64	...	...	...
42	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
43	12.3	12.1	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75	...	...	...
44	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
45	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	25Cr-20Ni-Cb	Plate	SA-240	310Cb	S31040	...	...
2	25Cr-20Ni-Cb	Plate	SA-240	310Cb	S31040	...	...
3	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb	S31040	...	...
4	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb	S31040	...	...
5	25Cr-20Ni-Cb	Smls. & wld. pipe	SA-312	TP310Cb	S31040	...	...
6	25Cr-20Ni-Cb	Smls. pipe	SA-312	TP310Cb	S31040	...	...
7	25Cr-20Ni-Cb	Wld. pipe	SA-312	TP310Cb	S31040	...	...
8	25Cr-20Ni-Cb	Wld. pipe	SA-312	TP310Cb	S31040	...	...
9	25Cr-20Ni-Cb	Bar	SA-479	310Cb	S31040	...	...
10	25Cr-20Ni-Cb	Bar	SA-479	310Cb	S31040	...	...
11	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb	S31040	...	...
12	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb	S31040	...	...
13	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb	S31040	...	...
14	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb	S31040	...	...
15	25Cr-20Ni-Cb-N	Smls. tube	SA-213	TP310HCbN	S31042	...	...
16	25Cr-20Ni-Cb-N	Smls. tube	SA-213	TP310HCbN	S31042	...	...
17	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN	S31050	...	...
18	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN	S31050	...	...
19	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
20	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
21	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	t > 0.250
22	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	t > 0.250
23	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
24	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
25	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
26	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	0.250 < t ≤ 1.250
27	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	≤0.250, wall
28	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	≤0.250, wall
29	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	t ≤ 0.250
30	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	t ≤ 0.250
31	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	≤0.250, wall
32	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	≤0.250, wall
33	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	≤0.250, wall
34	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	≤0.250, wall
35	26Cr-4Ni-Mo	Plate	SA-240	329	S32900	...	...
36	26Cr-4Ni-Mo	Wld. tube	SA-789	...	S32900	...	...
37	26Cr-4Ni-Mo	Smls. tube	SA-789	...	S32900	...	...
38	26Cr-4Ni-Mo	Wld. pipe	SA-790	...	S32900	...	...
39	26Cr-4Ni-Mo	Smls. pipe	SA-790	...	S32900	...	...
40	26Cr-4Ni-Mo-N	Plate	SA-240	...	S32950	...	...
41	26Cr-4Ni-Mo-N	Wld. tube	SA-789	...	S32950	...	...
42	26Cr-4Ni-Mo-N	Smls. tube	SA-789	...	S32950	...	...
43	26Cr-4Ni-Mo-N	Wld. pipe	SA-790	...	S32950	...	...
44	26Cr-4Ni-Mo-N	Smls. pipe	SA-790	...	S32950	...	...
45	27Cr-7.5Ni-4.5Mo-Co-N	Smls. tube	SA-789	...	S32707	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Applicability and Max. Temperature										
Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Limits				External Pressure Chart No.	Notes
					(NP = Not Permitted)					
					(SPT = Supports Only)					
					I	III	VIII-1	XII		
1	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, T5
2	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6
3	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
4	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
5	8	2	75	30	NP	800	1500	650	HA-2	G5, G12, T5, W12, W14
6	8	2	75	30	NP	NP	1500	650	HA-2	G12, T6
7	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
8	8	2	75	30	NP	NP	1500	650	HA-2	G12, G14, G24, T6
9	8	2	75	30	NP	NP	1000	650	HA-2	G5, G12, G22, T5
10	8	2	75	30	NP	NP	1000	650	HA-2	G12, G22, T6
11	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
12	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
13	8	2	75	30	NP	NP	1500	650	HA-2	G5, G12, G24, T5
14	8	2	75	30	NP	NP	1500	650	HA-2	G12, G24, T6
15	8	3	95	43	1350	NP	NP	NP	HA-2	G5, G12, S4, T8
16	8	3	95	43	1350	NP	NP	NP	HA-2	G12, S4, T9
17	8	2	78	37	NP	NP	600	600	HA-2	G5
18	8	2	78	37	NP	NP	600	600	HA-2	...
19	8	2	78	37	NP	NP	900	650	HA-2	G5
20	8	2	78	37	NP	NP	900	650	HA-2	...
21	8	2	78	37	NP	NP	600	600	HA-2	G5
22	8	2	78	37	NP	NP	600	600	HA-2	...
23	8	2	78	37	NP	NP	900	650	HA-2	G5, G24
24	8	2	78	37	NP	NP	900	650	HA-2	G24
25	8	2	78	37	NP	NP	900	650	HA-2	G5, G24
26	8	2	78	37	NP	NP	900	650	HA-2	G24
27	8	2	84	39	NP	NP	900	650	HA-2	G5
28	8	2	84	39	NP	NP	900	650	HA-2	...
29	8	2	84	39	NP	NP	600	600	HA-2	G5
30	8	2	84	39	NP	NP	600	600	HA-2	...
31	8	2	84	39	NP	NP	900	650	HA-2	G5, G24
32	8	2	84	39	NP	NP	900	650	HA-2	G24
33	8	2	84	39	NP	NP	900	650	HA-2	G5, G24
34	8	2	84	39	NP	NP	900	650	HA-2	G24
35	10H	1	90	70	NP	NP	500	500	HA-5	G19
36	10H	1	90	70	NP	NP	500	500	HA-5	G19, G24
37	10H	1	90	70	NP	NP	500	500	HA-5	G19
38	10H	1	90	70	NP	NP	500	500	HA-5	G19, G24
39	10H	1	90	70	NP	NP	500	500	HA-5	G19
40	10H	1	100	70	NP	NP	600	600	HA-5	G19
41	10H	1	100	70	NP	NP	600	600	HA-5	G19, G24
42	10H	1	100	70	NP	NP	600	600	HA-5	G19
43	10H	1	100	70	NP	NP	600	600	HA-5	G19, G24
44	10H	1	100	70	NP	NP	600	600	HA-5	G19
45	10H	1	133	101	NP	NP	500	NP	HA-5	G19

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
2	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
3	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
4	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
5	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
6	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
7	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
8	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
9	20.0	...	20.0	...	20.0	19.9	19.3	18.5	18.2	17.9	17.7	17.4	17.2	16.9
10	20.0	...	17.6	...	16.1	15.1	14.3	13.7	13.5	13.3	13.1	12.9	12.7	12.5
11	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
12	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
13	17.0	...	17.0	...	17.0	16.9	16.4	15.7	15.5	15.2	15.0	14.8	14.6	14.4
14	17.0	...	15.0	...	13.7	12.8	12.1	11.7	11.5	11.3	11.1	11.0	10.8	10.7
15	27.1	...	26.9	...	25.4	24.6	24.2	24.0	23.9	23.8	23.7	23.6	23.4	23.1
16	27.1	...	24.0	...	21.7	20.2	19.2	18.5	18.3	18.1	17.8	17.6	17.4	17.1
17	22.3	...	22.0	...	20.8	20.0	19.5	19.0	...	...	...	...	...	...
18	22.3	...	21.0	...	19.1	17.8	16.8	15.9	...	...	...	...	...	...
19	22.3	...	22.0	...	20.8	20.0	19.5	19.0	18.8	18.7	18.5	18.4	18.2	17.9
20	22.3	...	21.0	...	19.1	17.8	16.8	15.9	15.5	15.1	14.8	14.4	14.0	13.7
21	22.3	...	22.0	...	20.8	20.0	19.5	19.0	...	...	...	...	...	...
22	22.3	...	21.0	...	19.1	17.8	16.8	15.9	...	...	...	...	...	...
23	18.9	...	18.7	...	17.7	17.0	16.5	16.2	16.0	15.9	15.8	15.6	15.5	15.2
24	18.9	...	17.8	...	16.2	15.1	14.3	13.5	13.2	12.9	12.5	12.2	11.9	11.7
25	18.9	...	18.7	...	17.7	17.0	16.5	16.2	16.0	15.9	15.8	15.6	15.5	15.2
26	18.9	...	17.8	...	16.2	15.1	14.3	13.5	13.2	12.9	12.5	12.2	11.9	11.7
27	24.0	...	23.7	...	22.4	21.6	21.0	20.5	20.3	20.1	20.0	19.8	19.6	19.3
28	24.0	...	22.1	...	20.1	18.7	17.7	16.8	16.4	16.0	15.6	15.2	14.8	14.5
29	24.0	...	23.7	...	22.4	21.6	21.0	20.5	...	...	...	...	...	...
30	24.0	...	22.1	...	20.1	18.7	17.7	16.8	...	...	...	...	...	...
31	20.4	...	20.2	...	19.1	18.3	17.8	17.4	17.3	17.1	17.0	16.8	16.6	16.4
32	20.4	...	18.8	...	17.1	15.9	15.0	14.3	13.9	13.6	13.2	12.9	12.6	12.3
33	20.4	...	20.2	...	19.1	18.3	17.8	17.4	17.3	17.1	17.0	16.8	16.6	16.4
34	20.4	...	18.8	...	17.1	15.9	15.0	14.3	13.9	13.6	13.2	12.9	12.6	12.3
35	25.7	...	25.7	...	24.8	24.3	24.3	...	...	...	...	...	...	...
36	21.9	...	21.9	...	21.0	20.6	20.6	...	...	...	...	...	...	...
37	25.7	...	25.7	...	24.8	24.3	24.3	...	...	...	...	...	...	...
38	21.9	...	21.9	...	21.0	20.6	20.6	...	...	...	...	...	...	...
39	25.7	...	25.7	...	24.8	24.3	24.3	...	...	...	...	...	...	...
40	28.6	...	28.5	...	27.0	26.4	26.4	26.4	...	...	...	...	...	...
41	24.3	...	24.2	...	23.0	22.5	22.5	22.5	...	...	...	...	...	...
42	28.6	...	28.5	...	27.0	26.4	26.4	26.4	...	...	...	...	...	...
43	24.3	...	24.2	...	23.0	22.5	22.5	22.5	...	...	...	...	...	...
44	28.6	...	28.5	...	27.0	26.4	26.4	26.4	...	...	...	...	...	...
45	38.0	38.0	38.0	38.0	37.7	36.9	35.3	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
2	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
3	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
4	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
5	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
6	12.3	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20	...	...	...
7	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
8	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
9	15.9	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	12.3	9.9	...	...	...	...	...	...	...	...	...	...	...	...	...
11	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
12	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
13	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
14	10.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17	...	...	...
15	22.8	22.4	22.0	18.4	13.6	10.1	7.6	5.7	4.3	...	...	...	...	...	...
16	16.9	16.6	16.3	16.1	13.6	10.1	7.6	5.7	4.3	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3;* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.
1	27Cr-7.5Ni-4.5Mo-Co-N	Smls. pipe	SA-790	...	S32707	...	...
2	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	≥0.40
3	29Cr-6.5Ni-2Mo-N	Bar	SA-479	...	S32906	...	...
4	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	≥0.40
5	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	≥0.40
6	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	<0.40
7	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	<0.40
8	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	<0.40

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3;* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	P-No.	Group No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	10H	1	133	101	NP	NP	500	NP	HA-5	G19
2	10H	1	109	80	NP	NP	600	600	HA-5	G19
3	10H	1	109	80	NP	NP	600	600	HA-5	G19
4	10H	1	109	80	NP	NP	600	600	HA-5	G19
5	10H	1	109	80	NP	NP	600	600	HA-5	G19
6	10H	1	116	94	NP	NP	600	600	HA-5	G19
7	10H	1	116	94	NP	NP	600	600	HA-5	G19
8	10H	1	116	94	NP	NP	600	600	HA-5	G19

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3;* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	38.0	38.0	38.0	38.0	37.7	36.9	35.3	...	...	...	...	...	...	...
2	31.1	...	31.1	...	29.6	28.7	28.3	28.3	...	...	...	...	...	...
3	31.1	...	31.1	...	29.6	28.7	28.3	28.3	...	...	...	...	...	...
4	31.1	...	31.1	...	29.6	28.7	28.3	28.3	...	...	...	...	...	...
5	31.1	...	31.1	...	29.6	28.7	28.3	28.3	...	...	...	...	...	...
6	33.1	...	33.1	...	31.5	30.6	30.1	30.1	...	...	...	...	...	...
7	33.1	...	33.1	...	31.5	30.6	30.1	30.1	...	...	...	...	...	...
8	33.1	...	33.1	...	31.5	30.6	30.1	30.1	...	...	...	...	...	...

Table 1A (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3;* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Ferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

NOTES TO TABLE 1A**GENERAL NOTES**

- (25) (a) The following abbreviations are used: N, Normalized; Norm. rld., Normalized rolled; NT, Normalized and tempered; QT, Quenched and tempered; Smls., Seamless; Sol. ann., Solution annealed; and Wld., Welded.
- (b) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (c) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (d) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.
- (e) Stress values for 100°F are applicable for colder temperatures when the toughness requirements of Section III, VIII, or XII are met.
- (f) An alternative typeface is used for stress values obtained from time-dependent properties (see Notes T1 through T12).
- (g) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-516/SA-516M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-516 Grade 70 shall be used when SA-516M Grade 485 is used in construction.

NOTES – GENERAL REQUIREMENTS

- G1 To these stress values a casting quality factor as specified in PG-25 of Section I; UG-24 of Section VIII, Division 1; or TM-190 of Section XII shall be applied.
- G2 These stress values include a joint efficiency factor of 0.60.
- G3 These stress values include a joint efficiency factor of 0.85.
- G4 For Section I applications, these stresses apply when used for boiler, water wall, superheater, and economizer tubes that are enclosed within a setting. A joint efficiency factor of 0.85 is included in values above 850°F.
- G5 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed 66²/₃% but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. For Section III applications, Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G6 Creep-fatigue, thermal ratcheting, and environmental effects are increasingly significant failure modes at temperatures in excess of 1500°F and shall be considered in the design.
- G7 For Section VIII applications, these stress values are based on expected minimum values of 45,000 psi tensile strength and yield strength of 20,000 psi resulting from loss of strength due to thermal treatment required for the glass coating operation. UG-85 does not apply.
- G8 These stress values are established from a consideration of strength only and will be satisfactory for average service. For bolted joints where freedom from leakage over a long period of time without retightening is required, lower stress values may be necessary as determined from the flexibility of the flange and bolts and corresponding relaxation properties.
- G9 For Section III applications, the use of these materials shall be limited to materials for tanks covered in Subsections NC and ND, component supports, and for nonpressure-retaining attachments (NC/ND-2190).
- G10 Upon prolonged exposure to temperatures above 800°F, the carbide phase of carbon steel may be converted to graphite. See Nonmandatory Appendix A, A-201 and A-202.
- G11 Upon prolonged exposure to temperatures above 875°F, the carbide phase of carbon-molybdenum steel may be converted to graphite. See Nonmandatory Appendix A, A-201 and A-202.
- G12 At temperatures above 1000°F, these stress values apply only when the carbon is 0.04% or higher on heat analysis.
- G13 These stress values at 1050°F and above shall be used only when the grain size is ASTM No. 6 or coarser.
- G14 These stress values shall be used when the grain size is not determined or is determined to be finer than ASTM No. 6.
- G15 For Section I applications, use is limited to stays as defined in PG-13 except as permitted by PG-11.
- G16 For Section III Class 3 applications, these S values do not include a casting quality factor. Statically and centrifugally cast products meeting the requirements of NC-2570 shall receive a casting quality factor of 1.00.
- G17 For Section III Class 3 applications, statically and centrifugally cast products meeting the requirements of NC-2571(a) and (b), and cast pipe fittings, pumps, and valves with inlet piping connections of 2 in. nominal pipe size and less, shall receive a casting quality factor of 1.00. Other casting quality factors shall be in accordance with the following:
- (a) for visual examination, 0.80
 - (b) for magnetic particle examination, 0.85
 - (c) for liquid penetrant examination, 0.85
 - (d) for radiography, 1.00
 - (e) for ultrasonic examination, 1.00
 - (f) for magnetic particle or liquid penetrant plus ultrasonic examination or radiography, 1.00
- G18 See Table Y-1 for yield strength values as a function of thickness over this range. Allowable stresses are independent of yield strength in this thickness range.

NOTES TO TABLE 1A (CONT'D)**NOTES – GENERAL REQUIREMENTS (CONT'D)**

- G19 This steel may be expected to develop embrittlement after service at moderately elevated temperature; see Nonmandatory Appendix A, A-207 and A-208.
- G20 These stresses are based on weld metal properties.
- G21 For Section I, use is limited to PEB-5.3. See PG-5.5 for cautionary note.
- G22 For Section I applications, use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.
- G23 For temperatures above the maximum temperature shown on the external pressure chart for this material, Fig. CS-2 may be used for the design using this material.
- G24 A factor of 0.85 has been applied in arriving at the maximum allowable stress values in tension for this material. Divide tabulated values by 0.85 for maximum allowable longitudinal tensile stress.
- G25 For Section III applications, for both Class 2 and Class 3, the completed vessel after final heat treatment shall be examined by the ultrasonic method in accordance with NB-2542 except that angle beam examination in both the circumferential and the axial directions may be performed in lieu of the straight beam examination in the axial direction. The tensile strength shall not exceed 125,000 psi.
- G26 Material that conforms to Class 10, 11, or 12 is not permitted.
- G27 Material that conforms to Class 11 or 12 is not permitted.
- G28 Supplementary Requirement S15 of SA-781, Alternate Mechanical Test Coupons and Specimen Locations for Castings, is mandatory.
- G29 For Section III applications, impact testing in accordance with the requirements of NC-2300 is required for Class 2 components and in accordance with ND-2300 for Class 3 components.
- G30 These stresses apply to all product forms (C, H, and P) as defined in SA/EN 10028-7.

NOTES – HEAT TREATMENT REQUIREMENTS

- H1 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating to the minimum temperature specified in the material specification, but not lower than 1900°F, and quenching in water or rapidly cooling by other means.
- H2 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating to a minimum temperature of 2000°F, and quenching in water or rapidly cooling by other means.
- (25) H3 DELETED
- (25) H4 DELETED
- H5 For Section III applications, if heat treatment is performed after forming or fabrication, it shall be performed at 1500°F to 1850°F for a period of time not to exceed 10 min at temperature, followed by rapid cooling.
- H6 Material shall be solution annealed at 2010°F to 2140°F, followed by a rapid cooling in water or air.

NOTES – SIZE REQUIREMENTS

- S1 For Section I applications, stress values at temperatures of 850°F and above are permissible but, except for tubular products 3 in. O.D. or less enclosed within the boiler setting, use of these materials at these temperatures is not current practice.
- S2 For Section I applications, stress values at temperatures of 900°F and above are permissible but, except for tubular products 3 in. O.D. or less enclosed within the boiler setting, use of these materials at these temperatures is not current practice.
- S3 For Section I applications, stress values at temperatures of 1000°F and above are permissible but, except for tubular products 3 in. O.D. or less enclosed within the boiler setting, use of these materials at these temperatures is not current practice.
- S4 For Section I applications, stress values at temperatures of 1150°F and above are permissible but, except for tubular products 3 in. O.D. or less enclosed within the boiler setting, use of these materials at these temperatures is not current practice.
- S5 Material that conforms to Class 10, 11, or 12 is not permitted when the nominal thickness of the material exceeds $\frac{3}{4}$ in.
- S6 Material that conforms to Class 10, 11, or 12 is not permitted when the nominal thickness of the material exceeds $1\frac{1}{4}$ in.
- S7 The maximum thickness of unheat-treated forgings shall not exceed $3\frac{3}{4}$ in. The maximum thickness as-heat-treated may be 4 in.
- S8 The maximum section thickness shall not exceed 3 in. for double-normalized-and-tempered forgings, or 5 in. for quenched-and-tempered forgings.
- S9 Both NPS 8 and larger, and schedule 140 and heavier.
- S10 The maximum pipe size shall be NPS 4 and the maximum thickness in any pipe size shall be schedule 80.
- S11 Either NPS 8 and larger and less than schedule 140 wall, or less than NPS 8 and all wall thicknesses.

NOTES – TIME-DEPENDENT PROPERTIES [See General Note (f)]

- T1 Allowable stresses for temperatures of 700°F and above are values obtained from time-dependent properties.
- T2 Allowable stresses for temperatures of 750°F and above are values obtained from time-dependent properties.
- T3 Allowable stresses for temperatures of 850°F and above are values obtained from time-dependent properties.
- T4 Allowable stresses for temperatures of 900°F and above are values obtained from time-dependent properties.
- T5 Allowable stresses for temperatures of 950°F and above are values obtained from time-dependent properties.
- T6 Allowable stresses for temperatures of 1000°F and above are values obtained from time-dependent properties.
- T7 Allowable stresses for temperatures of 1050°F and above are values obtained from time-dependent properties.
- T8 Allowable stresses for temperatures of 1100°F and above are values obtained from time-dependent properties.
- T9 Allowable stresses for temperatures of 1150°F and above are values obtained from time-dependent properties.
- T10 Allowable stresses for temperatures of 800°F and above are values obtained from time-dependent properties.
- T11 Allowable stresses for temperatures of 650°F and above are values obtained from time-dependent properties.
- T12 Allowable stresses for temperatures of 1200°F and above are values obtained from time-dependent properties.

NOTES – WELDING REQUIREMENTS

- W1 Not for welded construction.
- W2 Not for welded construction in Section III.

NOTES TO TABLE 1A (CONT'D)**NOTES – WELDING REQUIREMENTS (CONT'D)**

- W3 Welded.
- W4 Nonwelded, or welded if the tensile strength of the Section IX reduced section tension test is not less than 100 ksi.
- W5 Welded, with the tensile strength of the Section IX reduced tension test less than 100 ksi but not less than 95 ksi.
- W6 This material may be welded by the resistance technique.
- W7 In welded construction for temperatures above 850°F, the weld metal shall have a carbon content of greater than 0.05%.
- W8 Welding and oxygen or other thermal cutting processes are not permitted when carbon content exceeds 0.35% by heat analysis.
- W9 For Section I applications, for pressure retaining welds in 2 $\frac{1}{4}$ Cr-1Mo materials, other than circumferential butt welds less than or equal to 3 $\frac{1}{2}$ in. in outside diameter, when the design metal temperatures exceed 850°F, the weld metal shall have a carbon content greater than 0.05%.
- W10 For Section III applications, material that conforms to Class 10, 13, 20, 23, 30, 33, 40, 43, 50, or 53 is not permitted for Class 2 and Class 3 construction when a weld efficiency factor of 1.00 is used in accordance with Note W12.
- W11 For Section VIII applications, Section IX, QW-250 Variables QW-404.12, QW-406.3, QW-407.2, and QW-409.1 shall also apply to this material. These variables shall be applied in accordance with the rules for welding of Part UF.
- W12 These *S* values do not include a longitudinal weld efficiency factor. For Section III applications, for materials welded without filler metal, ultrasonic examination, radiographic examination, or eddy current examination, in accordance with NC-2550, shall provide a longitudinal weld efficiency factor of 1.00. Materials welded with filler metal meeting the requirements of NC-2560 shall receive a longitudinal weld efficiency factor of 1.00. Other longitudinal weld efficiency factors shall be in accordance with the following:
- (a) for single butt weld, with filler metal, 0.80
 - (b) for single or double butt weld, without filler metal, 0.85
 - (c) for double butt weld, with filler metal, 0.90
 - (d) for single or double butt weld, with radiography, 1.00
- W13 For Section I applications, electric resistance and autogenous welded tubing may be used with these stresses, provided the following additional restrictions and requirements are met:
- (a) The tubing shall be used for boiler, waterwall, superheater, and economizer tubes that are enclosed within the setting.
 - (b) The maximum outside diameter shall be 3 $\frac{1}{2}$ in.
 - (c) The weld seam of each tube shall be subjected to an angle beam ultrasonic inspection per SA-450/SA-1016.
 - (d) A complete volumetric inspection of the entire length of each tube shall be performed in accordance with SA-450/SA-1016.
 - (e) Material test reports shall be supplied.
- W14 These *S* values do not include a weld factor. For Section VIII, Division 1 and Section XII applications using welds made without filler metal, the tabulated tensile stress values shall be multiplied by 0.85. For welds made with filler metal, consult UW-12 for Section VIII, Division 1, or TW-130.4 for Section XII, as applicable.
- W15 The Nondestructive Electric Test requirements of SA-53 Type E pipe are required for all sizes. The pipe shall be additionally marked "NDE" and so noted on the material certification.

INTENTIONALLY LEFT BLANK

Table 1B
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Plate, sheet	SB-209	...	Alclad 3003	O
2	...	Plate, sheet	SB-209	...	Alclad 3003	O
3	...	Plate, sheet	SB-209	...	Alclad 3003	H112
4	...	Plate, sheet	SB-209	...	Alclad 3003	H112
5	...	Plate, sheet	SB-209	...	Alclad 3003	H112
6	...	Plate, sheet	SB-209	...	Alclad 3003	H12
7	...	Plate, sheet	SB-209	...	Alclad 3003	H12
8	...	Plate, sheet	SB-209	...	Alclad 3003	H14
9	...	Plate, sheet	SB-209	...	Alclad 3003	H14
10	...	Drawn smls. tube	SB-210	...	Alclad 3003	O
11	...	Drawn smls. tube	SB-210	...	Alclad 3003	H113
12	...	Drawn smls. tube	SB-210	...	Alclad 3003	H14
13	...	Drawn smls. tube	SB-210	...	Alclad 3003	H18
14	...	Cond. & heat exch. tubes	SB-234	...	Alclad 3003	H14
15	...	Cond. & heat exch. tubes	SB-234	...	Alclad 3003	H25
16	...	Smls. extr. tube	SB-241	...	Alclad 3003	O
17	...	Smls. extr. tube	SB-241	...	Alclad 3003	H112
18	...	Plate, sheet	SB-209	...	Alclad 3004	O
19	...	Plate, sheet	SB-209	...	Alclad 3004	O
20	...	Plate, sheet	SB-209	...	Alclad 3004	H112
21	...	Plate, sheet	SB-209	...	Alclad 3004	H112
22	...	Plate, sheet	SB-209	...	Alclad 3004	H32
23	...	Plate, sheet	SB-209	...	Alclad 3004	H32
24	...	Plate, sheet	SB-209	...	Alclad 3004	H34
25	...	Plate, sheet	SB-209	...	Alclad 3004	H34
26	...	Plate, sheet	SB-209	...	Alclad 6061	T4
27	...	Plate, sheet	SB-209	...	Alclad 6061	T451
28	...	Plate, sheet	SB-209	...	Alclad 6061	T451
29	...	Plate, sheet	SB-209	...	Alclad 6061	T4 wld.
30	...	Plate, sheet	SB-209	...	Alclad 6061	T451 wld.
31	...	Plate, sheet	SB-209	...	Alclad 6061	T6
32	...	Plate, sheet	SB-209	...	Alclad 6061	T651
33	...	Plate, sheet	SB-209	...	Alclad 6061	T651
34	...	Plate, sheet	SB-209	...	Alclad 6061	T651
35	...	Plate, sheet	SB-209	...	Alclad 6061	T6 wld.
36	...	Plate, sheet	SB-209	...	Alclad 6061	T651 wld.
37	...	Castings	SB-26	...	A02040	T4
38	...	Castings	SB-108	...	A02040	T4
39	...	Castings	SB-26	...	A03560	T71
40	...	Castings	SB-26	...	A03560	T6
41	...	Castings	SB-108	...	A03560	T6
42	...	Castings	SB/EN 1706	...	AC-42000-S	T6
43	...	Castings	SB-26	...	A24430	F
44	...	Plate, sheet	SB-209	...	A91060	O
45	...	Plate, sheet	SB-209	...	A91060	H112

Table 1B
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	0.006-0.499	21	13	4.5	NP	250 (Cl. 3 only)	400	400	NFA-7	G16
2	0.500-3.000	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-7	G25
3	0.250-0.499	21	16	9	NP	300 (Cl. 3 only)	400	400	NFA-7	G16, W3
4	0.500-2.000	21	15	6	NP	200 (Cl. 3 only)	400	400	NFA-7	G26, W3
5	2.001-3.000	21	14.5	6	NP	200 (Cl. 3 only)	400	400	NFA-7	G26, W3
6	0.017-0.499	21	16	11	NP	300 (Cl. 3 only)	400	400	NFA-7	G16, W3
7	0.500-2.000	21	17	12	NP	300 (Cl. 3 only)	400	400	NFA-7	G25, W3
8	0.009-0.499	21	19	16	NP	250 (Cl. 3 only)	400	400	NFA-7	G16, W3
9	0.500-1.000	21	20	17	NP	250 (Cl. 3 only)	400	400	NFA-7	G25, W3
10	0.010-0.500	21	13	4.5	NP	250 (Cl. 3 only)	400	400	NFA-7	G16
11	0.050-0.500	21	13	4.5	NP	250 (Cl. 3 only)	400	400	NFA-7	G16, W3
12	0.010-0.500	21	19	16	NP	250 (Cl. 3 only)	400	400	NFA-1	G16, W3
13	0.010-0.500	21	26	23	NP	250 (Cl. 3 only)	400	400	NFA-1	G16, W3
14	0.010-0.200	21	19	16	NP	250 (Cl. 3 only)	400	400	NFA-1	G16, W4
15	0.010-0.200	21	21	18	NP	250 (Cl. 3 only)	400	400	NFA-1	G16, W4
16	...	21	13	4.5	NP	250 (Cl. 3 only)	400	400	NFA-7	G16
17	...	21	13	4.5	NP	250 (Cl. 3 only)	400	400	NFA-7	G16, W3
18	0.006-0.499	22	21	8	NP	300 (Cl. 3 only)	400	400	NFA-7	G16
19	0.500-3.000	22	22	8.5	NP	300 (Cl. 3 only)	400	400	NFA-7	G25
20	0.250-0.499	22	22	8.5	NP	300 (Cl. 3 only)	400	400	NFA-7	G16, W3
21	0.500-3.000	22	23	9	NP	300 (Cl. 3 only)	400	400	NFA-7	G25, W3
22	0.017-0.499	22	27	20	NP	250 (Cl. 3 only)	400	400	NFA-7	G16, W3
23	0.500-2.000	22	28	21	NP	250 (Cl. 3 only)	400	400	NFA-7	G25, W3
24	0.009-0.499	22	31	24	NP	250 (Cl. 3 only)	400	400	NFA-7	G16, W3
25	0.500-1.000	22	32	25	NP	250 (Cl. 3 only)	400	400	NFA-7	G25, W3
26	0.010-0.249	23	27	14	NP	400 (Cl. 3 only)	400	400	NFA-12	G16, G24, W4
27	0.250-0.499	23	27	14	NP	400 (Cl. 3 only)	400	400	NFA-12	G16, G24, W4
28	0.500-3.000	23	30	16	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, G25, W4
29	0.010-0.249	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, W7
30	0.250-3.000	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, W7
31	0.010-0.249	23	38	32	NP	400 (Cl. 3 only)	400	400	NFA-12	G16, G24, W4
32	0.250-0.499	23	38	32	NP	400 (Cl. 3 only)	400	400	NFA-12	G16, G24, W4
33	0.500-4.000	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, G25, W4
34	4.001-5.000	23	40	35	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, G26, W4
35	0.010-0.249	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, W7
36	0.250-5.000	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, W7
37	≤2.000	...	45	28	NP	NP	150	150	NFA-12	G15, W4
38	≤2.000	...	48	29	NP	NP	150	150	NFA-12	G15, W4
39	...	...	25	18	NP	350 (Cl. 3 only)	400	400	NFA-1	G15, W4
40	...	...	30	20	NP	250 (Cl. 3 only)	250	250	NFA-12	G15, W4
41	...	...	33	22	NP	NP	250	250	NFA-12	G15, W4
42	...	...	32	26	NP	NP	250	NP	NFA-12	G15, W4
43	...	...	17	6	NP	400 (Cl. 3 only)	400	400	NFA-1	G15, W4
44	0.006-3.000	21	8	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	T3
45	0.250-0.499	21	11	7	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3

Table 1B
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	3.0	2.9	2.8	2.7	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
2	3.3	3.2	3.1	3.0	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
3	4.6	4.5	4.2	3.9	3.3	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
4	4.0	3.9	3.8	3.6	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
5	4.0	3.9	3.8	3.5	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
6	4.6	4.6	4.5	4.2	3.3	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
7	4.9	4.9	4.8	4.5	3.3	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
8	5.4	5.4	5.4	5.2	3.9	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
9	5.7	5.7	5.7	5.5	3.9	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
10	3.0	2.9	2.8	2.7	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
11	3.0	2.9	2.8	2.7	2.2	1.6	1.3	...	...	...	...	...	...	...	...	...	...	...
12	5.4	5.4	5.4	5.2	3.9	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
13	7.4	7.4	7.3	6.9	4.8	3.2	2.3	...	...	...	...	...	...	...	...	...	...	...
14	5.4	5.4	5.4	5.2	3.9	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
15	6.0	6.0	6.0	5.7	3.9	2.7	2.1	...	...	...	...	...	...	...	...	...	...	...
16	3.0	2.9	2.8	2.7	2.2	1.6	1.2	...	...	...	...	...	...	...	...	...	...	...
17	3.0	2.9	2.8	2.7	2.2	1.6	1.2	...	...	...	...	...	...	...	...	...	...	...
18	5.3	5.3	5.3	5.3	4.5	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
19	5.7	5.7	5.7	5.7	4.5	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
20	5.7	5.7	5.7	5.7	4.6	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
21	6.0	6.0	6.0	6.0	4.6	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
22	7.7	7.7	7.7	7.7	5.2	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
23	8.0	8.0	8.0	8.0	5.2	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
24	8.9	8.9	8.9	8.9	5.2	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
25	9.1	9.1	9.1	9.1	5.2	3.4	2.1	...	...	...	...	...	...	...	...	...	...	...
26	7.7	7.7	7.7	7.6	6.2	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
27	7.7	7.7	7.7	7.6	6.2	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
28	8.6	8.6	8.6	8.5	6.2	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
29	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
30	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
31	10.9	10.9	10.9	10.6	7.6	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
32	10.9	10.9	10.9	10.6	7.6	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
33	12.0	12.0	12.0	11.7	7.6	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
34	11.4	11.4	11.4	11.1	7.4	5.7	4.0	...	...	...	...	...	...	...	...	...	...	...
35	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
36	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
37	8.4	7.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	10.3	8.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	7.2	7.2	7.2	6.3	5.4	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
40	8.6	8.6	8.6	6.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	9.5	9.3	8.5	6.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	9.1	9.1	9.1	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	4.0	4.0	4.0	3.8	3.5	3.1	2.8	...	...	...	...	...	...	...	...	...	...	...
44	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
45	3.1	3.0	2.7	2.4	1.8	1.6	1.0	...	...	...	...	...	...	...	...	...	...	...

Table 1B
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Plate, sheet	SB-209	...	A91060	H112
2	...	Plate, sheet	SB-209	...	A91060	H112
3	...	Plate, sheet	SB-209	...	A91060	H12
4	...	Plate, sheet	SB-209	...	A91060	H14
5	...	Drawn smls. tube	SB-210	...	A91060	O
6	...	Drawn smls. tube	SB-210	...	A91060	H14
7	...	Drawn smls. tube	SB-210	...	A91060	H113
8	...	Bar, rod, shapes	SB-221	...	A91060	O
9	...	Bar, rod, shapes	SB-221	...	A91060	H112
10	...	Cond. & heat exch. tubes	SB-234	...	A91060	H14
11	...	Smls. extr. tube	SB-241	...	A91060	O
12	...	Smls. extr. tube	SB-241	...	A91060	H112
13	...	Plate, sheet	SB-209	...	A91100	O
14	...	Plate, sheet	SB-209	...	A91100	H112
15	...	Plate, sheet	SB-209	...	A91100	H112
16	...	Plate, sheet	SB-209	...	A91100	H112
17	...	Plate, sheet	SB-209	...	A91100	H12
18	...	Plate, sheet	SB-209	...	A91100	H14
19	...	Bar, rod, shapes	SB-221	...	A91100	O
20	...	Bar, rod, shapes	SB-221	...	A91100	H112
21	...	Smls. extr. tube	SB-241	...	A91100	O
22	...	Smls. extr. tube	SB-241	...	A91100	H112
23	...	Die forgings	SB-247	...	A92014	T4
24	...	Die forgings	SB-247	...	A92014	T6
25	...	Die forgings	SB-247	...	A92014	T6
26	...	Bar, rod, wire	SB-211	...	A92024	T4
27	...	Bar, rod, wire	SB-211	...	A92024	T4
28	...	Bar, rod, wire	SB-211	...	A92024	T4
29	...	Bar, rod, wire	SB-211	...	A92024	T4
30	...	Bar, rod, shapes	SB-221	...	A92024	T3
31	...	Bar, rod, shapes	SB-221	...	A92024	T3
32	...	Bar, rod, shapes	SB-221	...	A92024	T3
33	...	Bar, rod, shapes	SB-221	...	A92024	T3
34	...	Plate, sheet	SB-209	...	A93003	O
35	...	Plate, sheet	SB-209	...	A93003	H112
36	...	Plate, sheet	SB-209	...	A93003	H112
37	...	Plate, sheet	SB-209	...	A93003	H112
38	...	Plate, sheet	SB-209	...	A93003	H12
39	...	Plate, sheet	SB-209	...	A93003	H14
40	...	Drawn smls. tube	SB-210	...	A93003	O
41	...	Drawn smls. tube	SB-210	...	A93003	H113
42	...	Drawn smls. tube	SB-210	...	A93003	H12
43	...	Drawn smls. tube	SB-210	...	A93003	H14
44	...	Drawn smls. tube	SB-210	...	A93003	H18
45	...	Bar, rod, shapes	SB-221	...	A93003	O

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	0.500-1.000	21	10	5	NP	300 (Cl. 3 only)	400	400	NFA-7	T4, W3
2	1.001-3.000	21	9	4	NP	250 (Cl. 3 only)	400	400	NFA-7	T3, W3
3	0.017-2.000	21	11	9	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3
4	0.009-1.000	21	12	10	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3
5	0.018-0.500	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	T3
6	0.018-0.500	...	12	10	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3
7	0.018-0.500	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3
8	...	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	G13, T3
9	...	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	G13, T3, W3
10	0.010-0.200	21	12	10	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W4
11	...	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	T3
12	...	21	8.5	2.5	NP	300 (Cl. 3 only)	400	400	NFA-7	T3, W3
13	0.006-3.000	21	11	3.5	NP	250 (Cl. 3 only)	400	400	NFA-7	T4
14	0.250-0.499	21	13	7	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
15	0.500-2.000	21	12	5	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
16	2.001-3.000	21	11.5	4	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
17	0.017-2.000	21	14	11	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
18	0.009-1.000	21	16	14	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
19	...	21	11	3	NP	250 (Cl. 3 only)	400	400	NFA-7	T4
20	...	21	11	3	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
21	...	21	11	3	NP	250 (Cl. 3 only)	400	400	NFA-7	T4
22	...	21	11	3	NP	250 (Cl. 3 only)	400	400	NFA-7	T4, W3
23	≤4.000	...	55	30	NP	400 (Cl. 3 only)	400	400	NFA-6	T3, W4
24	≤2.000	...	65	56	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
25	2.001-4.000	...	63	54	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
26	0.125-0.499	...	62	45	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
27	0.500-4.500	...	62	42	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
28	4.501-6.500	...	62	40	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
29	6.501-8.000	...	58	38	NP	400 (Cl. 3 only)	400	400	NFA-6	T2, W4
30	≤0.249	...	57	42	NP	400 (Cl. 3 only)	400	400	NFA-6	G24, T2, W4
31	0.250-0.749	...	60	44	NP	400 (Cl. 3 only)	400	400	NFA-6	G24, T2, W4
32	0.750-1.499	...	65	46	NP	400 (Cl. 3 only)	400	400	NFA-6	G24, T2, W4
33	≥1.500	...	68	48	NP	400 (Cl. 3 only)	400	400	NFA-6	G24, T2, W4
34	0.006-3.000	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3
35	0.250-0.499	21	17	10	NP	300 (Cl. 3 only)	400	400	NFA-1	T4, W3
36	0.500-2.000	21	15	6	NP	200 (Cl. 3 only)	400	400	NFA-1	T3, W3
37	2.001-3.000	21	14.5	6	NP	200 (Cl. 3 only)	400	400	NFA-1	T3, W3
38	0.017-2.000	21	17	12	NP	300 (Cl. 3 only)	400	400	NFA-1	T4, W3
39	0.009-1.000	21	20	17	NP	250 (Cl. 3 only)	400	400	NFA-2	T4, W3
40	0.010-0.500	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3
41	0.010-0.500	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3, W3
42	0.010-0.500	21	17	12	NP	300 (Cl. 3 only)	400	400	NFA-1	T4, W3
43	0.010-0.500	21	20	17	NP	250 (Cl. 3 only)	400	400	NFA-2	T4, W3
44	0.010-0.500	21	27	24	NP	250 (Cl. 3 only)	400	400	NFA-2	T4, W3
45	...	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	2.9	2.7	2.4	2.2	1.7	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
2	2.6	2.4	2.2	1.9	1.5	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
3	3.1	3.1	2.9	2.7	2.1	1.8	1.1	...	...	...	...	...	...	...	...	...	...	...
4	3.4	3.4	3.4	3.4	2.6	1.8	1.2	...	...	...	...	...	...	...	...	...	...	...
5	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
6	3.4	3.4	3.4	3.4	2.6	1.8	1.2	...	...	...	...	...	...	...	...	...	...	...
7	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
8	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
9	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
10	3.4	3.4	3.4	3.4	2.6	1.8	1.2	...	...	...	...	...	...	...	...	...	...	...
11	1.7	1.7	1.6	1.4	1.3	1.1	0.80	...	...	...	...	...	...	...	...	...	...	...
12	1.7	1.7	1.6	1.4	1.2	1.0	0.80	...	...	...	...	...	...	...	...	...	...	...
13	2.3	2.3	2.3	2.3	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
14	3.7	3.7	3.5	3.1	2.4	1.7	1.0	...	...	...	...	...	...	...	...	...	...	...
15	3.3	3.3	3.2	2.9	2.2	1.7	1.0	...	...	...	...	...	...	...	...	...	...	...
16	2.7	2.7	2.6	2.5	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
17	4.0	4.0	4.0	3.6	2.8	2.0	1.2	...	...	...	...	...	...	...	...	...	...	...
18	4.6	4.6	4.6	4.2	2.8	2.0	1.2	...	...	...	...	...	...	...	...	...	...	...
19	2.0	2.0	2.0	2.0	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
20	2.0	2.0	2.0	2.0	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
21	2.0	2.0	2.0	2.0	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
22	2.0	2.0	2.0	2.0	1.8	1.4	1.0	...	...	...	...	...	...	...	...	...	...	...
23	15.7	15.7	13.3	12.5	11.5	6.8	3.9	...	...	...	...	...	...	...	...	...	...	...
24	18.6	18.6	18.6	14.8	11.5	6.8	3.9	...	...	...	...	...	...	...	...	...	...	...
25	18.0	18.0	18.0	14.3	11.5	6.8	3.9	...	...	...	...	...	...	...	...	...	...	...
26	17.7	17.7	17.7	13.7	10.4	6.5	4.5	...	...	...	...	...	...	...	...	...	...	...
27	17.7	17.7	17.7	13.7	10.4	6.5	4.5	...	...	...	...	...	...	...	...	...	...	...
28	17.7	17.7	17.7	13.7	10.4	6.5	4.5	...	...	...	...	...	...	...	...	...	...	...
29	16.6	16.6	16.6	12.8	9.7	6.1	4.2	...	...	...	...	...	...	...	...	...	...	...
30	16.3	16.3	16.3	12.6	9.5	6.0	4.2	...	...	...	...	...	...	...	...	...	...	...
31	17.1	17.1	17.1	13.2	10.0	6.3	4.4	...	...	...	...	...	...	...	...	...	...	...
32	18.6	18.6	18.6	14.3	10.8	6.8	4.7	...	...	...	...	...	...	...	...	...	...	...
33	19.4	19.4	19.4	15.0	11.3	7.1	5.0	...	...	...	...	...	...	...	...	...	...	...
34	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
35	4.9	4.8	4.4	4.1	3.6	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
36	4.0	3.9	3.7	3.6	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
37	4.0	3.9	3.7	3.5	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
38	4.9	4.9	4.8	4.5	3.6	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
39	5.7	5.7	5.7	5.5	4.3	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
40	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
41	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
42	4.9	4.9	4.8	4.5	3.6	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
43	5.7	5.7	5.7	5.5	4.3	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
44	7.7	7.7	7.4	6.9	5.4	3.5	2.5	...	...	...	...	...	...	...	...	...	...	...
45	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Bar, rod, shapes	SB-221	...	A93003	H112
2	...	Cond. & heat exch. tubes	SB-234	...	A93003	H14
3	...	Cond. & heat exch. tubes	SB-234	...	A93003	H25
4	...	Smls. extr. tube	SB-241	...	A93003	O
5	...	Smls. extr. tube	SB-241	...	A93003	H112
6	...	Smls. pipe	SB-241	...	A93003	H112
7	...	Smls. pipe	SB-241	...	A93003	H18
8	...	Die forgings	SB-247	...	A93003	H112
9	...	Die forgings	SB-247	...	A93003	H112 wld.
10	...	Plate, sheet	SB-209	...	A93004	O
11	...	Plate, sheet	SB-209	...	A93004	H112
12	...	Plate, sheet	SB-209	...	A93004	H32
13	...	Plate, sheet	SB-209	...	A93004	H34
14	...	Plate, sheet	SB-209	...	A95052	O
15	...	Plate, sheet	SB-209	...	A95052	H112
16	...	Plate, sheet	SB-209	...	A95052	H112
17	...	Plate, sheet	SB-209	...	A95052	H32
18	...	Plate, sheet	SB-209	...	A95052	H34
19	...	Drawn smls. tube	SB-210	...	A95052	O
20	...	Drawn smls. tube	SB-210	...	A95052	H32
21	...	Drawn smls. tube	SB-210	...	A95052	H34
22	...	Cond. & heat exch. tubes	SB-234	...	A95052	H32
23	...	Cond. & heat exch. tubes	SB-234	...	A95052	H34
24	...	Smls. extr. tube	SB-241	...	A95052	O
25	...	Plate, sheet	SB-209	...	A95083	O
26	...	Plate, sheet	SB-209	...	A95083	O
27	...	Plate, sheet	SB-209	...	A95083	O
28	...	Plate, sheet	SB-209	...	A95083	O
29	...	Plate, sheet	SB-209	...	A95083	O
30	...	Plate, sheet	SB-209	...	A95083	H112
31	...	Plate, sheet	SB-209	...	A95083	H112
32	...	Plate, sheet	SB-209	...	A95083	H32
33	...	Plate, sheet	SB-209	...	A95083	H32
34	...	Bar, rod, shapes	SB-221	...	A95083	O
35	...	Bar, rod, shapes	SB-221	...	A95083	H111
36	...	Bar, rod, shapes	SB-221	...	A95083	H112
37	...	Smls. extr. tube	SB-241	...	A95083	O
38	...	Smls. extr. tube	SB-241	...	A95083	H111
39	...	Smls. extr. tube	SB-241	...	A95083	H112
40	...	Die & hand forgings	SB-247	...	A95083	H111
41	...	Die & hand forgings	SB-247	...	A95083	H112
42	...	Die & hand forgings	SB-247	...	A95083	H111 wld.
43	...	Die & hand forgings	SB-247	...	A95083	H112 wld.
44	...	Plate, sheet	SB-928	...	A95083	H321
45	...	Plate, sheet	SB-928	...	A95083	H321

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3, W3
2	0.010-0.200	21	20	17	NP	250 (Cl. 3 only)	400	400	NFA-2	T4, W4
3	0.010-0.200	21	22	19	NP	250 (Cl. 3 only)	400	400	NFA-2	T4, W4
4	...	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3
5	...	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3, W3
6	≥1.000	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3, W4
7	<1.000	21	27	24	NP	250 (Cl. 3 only)	400	400	NFA-1	T4, W4
8	≤4.000	21	14	5	NP	250 (Cl. 3 only)	400	400	NFA-1	T3
9	≤4.000	21	14	...	NP	250 (Cl. 3 only)	400	400	NFA-1	T3, W7
10	0.006-3.000	22	22	8.5	NP	300 (Cl. 3 only)	400	400	NFA-3	...
11	0.250-3.000	22	23	9	NP	300 (Cl. 3 only)	400	400	NFA-3	W3
12	0.017-2.000	22	28	21	NP	250 (Cl. 3 only)	400	400	NFA-3	W3
13	0.009-1.000	22	32	25	NP	250 (Cl. 3 only)	400	400	NFA-4	W3
14	0.006-3.000	22	25	9.5	NP	250 (Cl. 3 only)	400	400	NFA-8	...
15	0.250-0.499	22	28	16	NP	250 (Cl. 3 only)	400	400	NFA-8	W3
16	0.500-3.000	22	25	9.5	NP	250 (Cl. 3 only)	400	400	NFA-8	W3
17	0.017-2.000	22	31	23	NP	200 (Cl. 3 only)	400	400	NFA-3	W3
18	0.009-1.000	22	34	26	NP	200 (Cl. 3 only)	400	400	NFA-4	W3
19	0.010-0.450	22	25	10	NP	300 (Cl. 3 only)	400	400	NFA-8	...
20	0.010-0.450	22	31	23	NP	200 (Cl. 3 only)	400	400	NFA-8	W4
21	0.010-0.450	22	34	26	NP	200 (Cl. 3 only)	400	400	NFA-8	W4
22	0.010-0.200	22	31	23	NP	200 (Cl. 3 only)	400	400	NFA-8	W4
23	0.010-0.200	22	34	26	NP	200 (Cl. 3 only)	400	400	NFA-8	W4
24	...	22	25	10	NP	250 (Cl. 3 only)	400	400	NFA-8	...
25	0.051-1.500	25	40	18	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
26	1.501-3.000	25	39	17	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
27	3.001-5.000	25	38	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
28	5.001-7.000	25	37	15	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
29	7.001-8.000	25	36	14	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
30	0.250-1.500	25	40	18	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
31	1.501-3.000	25	39	17	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
32	0.125-1.500	25	44	31	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
33	1.501-3.000	25	41	29	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
34	≤5.000	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
35	≤5.000	25	40	24	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
36	≤5.000	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
37	...	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19
38	...	25	40	24	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
39	...	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
40	≤4.000	25	39	20	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W4
41	≤4.000	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W4
42	≤4.000	25	38	...	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W7
43	≤4.000	25	38	...	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W7
44	0.125-1.500	25	44	31	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
45	1.501-3.000	25	41	29	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
2	5.7	5.7	5.7	5.5	4.3	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
3	6.3	6.3	6.3	6.1	4.3	3.0	2.4	...	...	...	...	...	...	...	...	...	...	...
4	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
5	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
6	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
7	7.7	7.7	7.4	6.9	5.4	3.5	2.5	...	...	...	...	...	...	...	...	...	...	...
8	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
9	3.3	3.3	3.3	3.2	2.4	1.8	1.4	...	...	...	...	...	...	...	...	...	...	...
10	5.7	5.7	5.7	5.5	5.0	3.8	2.4	...	...	...	...	...	...	...	...	...	...	...
11	6.0	6.0	6.0	6.0	5.1	3.8	2.4	...	...	...	...	...	...	...	...	...	...	...
12	8.0	8.0	8.0	8.0	5.8	3.8	2.4	...	...	...	...	...	...	...	...	...	...	...
13	9.1	9.1	9.1	9.1	5.8	3.8	2.4	...	...	...	...	...	...	...	...	...	...	...
14	6.3	6.3	6.3	6.3	5.6	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
15	8.0	8.0	8.0	8.0	6.2	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
16	6.3	6.3	6.3	6.3	6.0	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
17	8.9	8.9	8.9	8.9	6.2	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
18	9.7	9.7	9.7	9.7	6.2	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
19	6.7	6.7	6.7	6.7	5.6	4.1	2.3	...	...	...	...	...	...	...	...	...	...	...
20	8.9	8.9	8.9	8.9	6.1	4.1	2.3	...	...	...	...	...	...	...	...	...	...	...
21	9.7	9.7	9.7	9.7	6.1	4.1	2.3	...	...	...	...	...	...	...	...	...	...	...
22	8.9	8.9	8.9	8.9	6.2	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
23	9.7	9.7	9.7	9.7	6.2	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
24	6.7	6.7	6.7	6.7	5.6	4.1	2.3	...	...	...	...	...	...	...	...	...	...	...
25	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	12.6	12.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	12.6	12.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Plate, sheet	SB-209	...	A95086	O
2	...	Plate, sheet	SB-209	...	A95086	H112
3	...	Plate, sheet	SB-209	...	A95086	H112
4	...	Plate, sheet	SB-209	...	A95086	H112
5	...	Plate, sheet	SB-209	...	A95086	H112
6	...	Plate, sheet	SB-209	...	A95086	H32
7	...	Plate, sheet	SB-209	...	A95086	H34
8	...	Bar, rod, shapes	SB-221	...	A95086	H112
9	...	Smls. extr. tube	SB-241	...	A95086	O
10	...	Smls. extr. tube	SB-241	...	A95086	H111
11	...	Smls. extr. tube	SB-241	...	A95086	H112
12	...	Plate, sheet	SB-928	...	A95086	H116
13	...	Plate, sheet	SB-209	...	A95154	O
14	...	Plate, sheet	SB-209	...	A95154	H112
15	...	Plate, sheet	SB-209	...	A95154	H112
16	...	Plate, sheet	SB-209	...	A95154	H32
17	...	Plate, sheet	SB-209	...	A95154	H34
18	...	Drawn smls. tube	SB-210	...	A95154	O
19	...	Drawn smls. tube	SB-210	...	A95154	H34
20	...	Bar, rod, shapes	SB-221	...	A95154	O
21	...	Bar, rod, shapes	SB-221	...	A95154	H112
22	...	Plate, sheet	SB-209	...	A95254	O
23	...	Plate, sheet	SB-209	...	A95254	H112
24	...	Plate, sheet	SB-209	...	A95254	H112
25	...	Plate, sheet	SB-209	...	A95254	H32
26	...	Plate, sheet	SB-209	...	A95254	H34
27	...	Plate, sheet	SB-209	...	A95454	O
28	...	Plate, sheet	SB-209	...	A95454	H112
29	...	Plate, sheet	SB-209	...	A95454	H112
30	...	Plate, sheet	SB-209	...	A95454	H32
31	...	Plate, sheet	SB-209	...	A95454	H34
32	...	Bar, rod, shapes	SB-221	...	A95454	O
33	...	Bar, rod, shapes	SB-221	...	A95454	H111
34	...	Bar, rod, shapes	SB-221	...	A95454	H112
35	...	Cond. & heat exch. tubes	SB-234	...	A95454	H32
36	...	Cond. & heat exch. tubes	SB-234	...	A95454	H34
37	...	Smls. extr. tube	SB-241	...	A95454	O
38	...	Smls. extr. tube	SB-241	...	A95454	H111
39	...	Smls. extr. tube	SB-241	...	A95454	H112
40	...	Plate, sheet	SB-209	...	A95456	O
41	...	Plate, sheet	SB-209	...	A95456	O
42	...	Plate, sheet	SB-209	...	A95456	O
43	...	Plate, sheet	SB-209	...	A95456	O
44	...	Plate, sheet	SB-209	...	A95456	O
45	...	Plate, sheet	SB-209	...	A95456	H112

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	0.020-2.000	25	35	14	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19
2	0.188-0.499	25	36	18	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19, W3
3	0.500-1.000	25	35	16	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19, W3
4	1.001-2.000	25	35	14	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19, W3
5	2.001-3.000	25	34	14	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19
6	0.051-2.000	25	40	28	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
7	0.051-1.000	25	44	34	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
8	≤5.000	25	35	14	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19, W4
9	...	25	35	14	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19
10	...	25	36	21	NP	150 (Cl. 3 only)	150	150	NFA-9	G18, G19, W3
11	...	25	35	14	NP	150 (Cl. 3 only)	150	150	NFA-9	...
12	0.063-2.000	25	40	28	NP	NP	150	150	NFA-11	G18, G19, W3
13	0.020-3.000	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19
14	0.250-0.499	22	32	18	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
15	0.500-3.000	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19, W3
16	0.020-2.000	22	36	26	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
17	0.009-1.000	22	39	29	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
18	0.010-0.450	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19
19	0.010-0.450	22	39	29	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19, W3
20	...	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19
21	...	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19, W3
22	0.051-3.000	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19
23	0.250-0.499	22	32	18	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
24	0.500-3.000	22	30	11	NP	150 (Cl. 3 only)	150	150	NFA-5	G18, G19, W3
25	0.051-2.000	22	36	26	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
26	0.051-1.000	22	39	29	NP	150 (Cl. 3 only)	150	150	NFA-11	G18, G19, W3
27	0.020-3.000	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2
28	0.250-0.499	22	32	18	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
29	0.500-3.000	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
30	0.020-2.000	22	36	26	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
31	0.020-1.000	22	39	29	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
32	≤5.000	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2
33	≤5.000	22	33	19	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
34	≤5.000	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
35	0.010-0.200	22	36	26	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W4
36	0.010-0.200	22	39	29	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W4
37	...	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2
38	...	22	33	19	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
39	...	22	31	12	NP	250 (Cl. 3 only)	400	400	NFA-6	T2, W3
40	0.051-1.500	25	42	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
41	1.501-3.000	25	41	18	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
42	3.001-5.000	25	40	17	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
43	5.001-7.000	25	39	16	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
44	7.001-8.000	25	38	15	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
45	0.250-1.500	25	42	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	10.3	10.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	12.6	12.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	10.3	10.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	9.1	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	10.3	10.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	9.1	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	7.3	7.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	10.3	10.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	11.1	11.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
28	9.1	9.1	9.1	9.1	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
29	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
30	10.3	10.3	10.3	10.3	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
31	11.1	11.1	11.1	10.8	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
32	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
33	9.4	9.4	9.4	9.4	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
34	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
35	10.3	10.3	10.3	10.3	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
36	11.1	11.1	11.1	10.8	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
37	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
38	9.4	9.4	9.4	9.4	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
39	8.0	8.0	8.0	8.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...	...
40	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	11.3	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Plate, sheet	SB-209	...	A95456	H112
2	...	Plate, sheet	SB-209	...	A95456	H32
3	...	Plate, sheet	SB-209	...	A95456	H32
4	...	Plate, sheet	SB-209	...	A95456	H32
5	...	Bar, rod, shapes	SB-221	...	A95456	O
6	...	Bar, rod, shapes	SB-221	...	A95456	H111
7	...	Bar, rod, shapes	SB-221	...	A95456	H112
8	...	Smls. extr. tube	SB-241	...	A95456	O
9	...	Smls. extr. tube	SB-241	...	A95456	H111
10	...	Smls. extr. tube	SB-241	...	A95456	H112
11	...	Plate, sheet	SB-928	...	A95456	H321
12	...	Plate, sheet	SB-928	...	A95456	H321
13	...	Plate, sheet	SB-928	...	A95456	H321
14	...	Plate, sheet	SB-209	...	A95652	O
15	...	Plate, sheet	SB-209	...	A95652	H112
16	...	Plate, sheet	SB-209	...	A95652	H112
17	...	Plate, sheet	SB-209	...	A95652	H32
18	...	Plate, sheet	SB-209	...	A95652	H34
19	...	Plate, sheet	SB-209	...	A96061	T4
20	...	Plate, sheet	SB-209	...	A96061	T451
21	...	Plate, sheet	SB-209	...	A96061	T6
22	...	Plate, sheet	SB-209	...	A96061	T651
23	...	Plate, sheet	SB-209	...	A96061	T651
24	...	Plate, sheet	SB-209	...	A96061	T4 wld.
25	...	Plate, sheet	SB-209	...	A96061	T451 wld.
26	...	Plate, sheet	SB-209	...	A96061	T6 wld.
27	...	Plate, sheet	SB-209	...	A96061	T651 wld.
28	...	Drawn smls. tube	SB-210	...	A96061	T4
29	...	Drawn smls. tube	SB-210	...	A96061	T6
30	...	Drawn smls. tube	SB-210	...	A96061	T4 wld.
31	...	Drawn smls. tube	SB-210	...	A96061	T6 wld.
32	...	Bar, rod, wire	SB-211	...	A96061	T6
33	...	Bar, rod, wire	SB-211	...	A96061	T651
34	...	Bar, rod, wire	SB-211	...	A96061	T6 wld.
35	...	Bar, rod, wire	SB-211	...	A96061	T651 wld.
36	...	Bar, rod, shapes	SB-221	...	A96061	T4
37	...	Bar, rod, shapes	SB-221	...	A96061	T6
38	...	Bar, rod, shapes	SB-221	...	A96061	T4 wld.
39	...	Bar, rod, shapes	SB-221	...	A96061	T6 wld.
40	...	Cond. & heat exch. tubes	SB-234	...	A96061	T4
41	...	Cond. & heat exch. tubes	SB-234	...	A96061	T6
42	...	Cond. & heat exch. tubes	SB-234	...	A96061	T4 wld.
43	...	Cond. & heat exch. tubes	SB-234	...	A96061	T6 wld.
44	...	Smls. extr. tube	SB-241	...	A96061	T4
45	...	Smls. extr. tube	SB-241	...	A96061	T6

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	1.501-3.000	25	41	18	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
2	0.188-0.499	25	46	33	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
3	0.500-1.500	25	44	31	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
4	1.501-3.000	25	41	29	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
5	≤5.000	25	41	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
6	≤5.000	25	42	26	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
7	≤5.000	25	41	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
8	...	25	41	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19
9	...	25	42	26	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
10	...	25	41	19	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
11	0.188-0.499	25	46	33	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
12	0.500-1.500	25	44	31	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
13	1.501-3.000	25	41	29	NP	150 (Cl. 3 only)	150	150	NFA-10	G18, G19, W3
14	0.051-3.000	22	25	9.5	NP	250 (Cl. 3 only)	400	400	NFA-8	T2
15	0.250-0.499	22	28	16	NP	250 (Cl. 3 only)	400	400	NFA-8	T1, W3
16	0.500-3.000	22	25	9.5	NP	250 (Cl. 3 only)	400	400	NFA-8	T2, W3
17	0.051-2.000	22	31	23	NP	200 (Cl. 3 only)	400	400	NFA-3	T1, W3
18	0.051-1.000	22	34	26	NP	200 (Cl. 3 only)	400	400	NFA-4	T1, W3
19	0.006-0.249	23	30	16	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W4
20	0.250-3.000	23	30	16	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W4
21	0.006-0.249	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, T3, W4
22	0.250-4.000	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W4, W9
23	4.001-6.000	23	40	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W4, W9
24	0.006-0.249	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W7
25	0.250-3.000	23	24	...	NP	NP	400	400	NFA-13	G24, T3, W7
26	0.006-0.249	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, T3, W7
27	0.250-6.000	23	24	...	NP	NP	400	400	NFA-12,13	G24, T3, W7, W9
28	0.025-0.500	23	30	16	NP	400 (Cl. 3 only)	400	400	NFA-13	T3, W4
29	0.025-0.500	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
30	0.025-0.500	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-13	T3, W7
31	0.025-0.500	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W7, W9
32	0.125-0.249	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12	G24, T3, W4
33	0.250-8.000	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W4, W9
34	0.125-0.249	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	G13, G24, T3, W7
35	0.250-8.000	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G13, G24, T3, W7, W9
36	...	23	26	16	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W4
37	...	23	38	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W4, W9
38	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W7
39	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G13, G24, T3, W7, W9
40	0.025-0.200	23	30	16	NP	400 (Cl. 3 only)	400	400	NFA-13	T3, W4
41	0.025-0.200	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12	T3, W4
42	0.025-0.200	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-13	T3, W7
43	0.025-0.200	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12	T3, W7
44	...	23	26	16	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W4
45	...	23	38	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W4, W9

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	13.1	13.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	12.6	12.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	13.1	13.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	12.6	12.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	11.7	11.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	6.3	6.3	6.3	6.3	6.1	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
15	8.0	8.0	8.0	7.5	6.1	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
16	6.3	6.3	6.3	6.3	6.1	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
17	8.9	8.9	8.9	7.5	6.1	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
18	9.7	9.7	9.7	7.5	6.1	4.1	2.4	...	...	...	...	...	...	...	...	...	...	...
19	8.6	8.6	8.6	8.5	6.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
20	8.6	8.6	8.6	8.5	6.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
21	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
22	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
23	11.4	11.4	11.4	11.1	8.2	6.3	4.4	...	...	...	...	...	...	...	...	...	...	...
24	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
25	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
26	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
27	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
28	8.6	8.6	8.6	8.5	6.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
29	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
30	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
31	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
32	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
33	12.0	12.0	12.0	11.7	8.4	6.4	4.5	...	...	...	...	...	...	...	...	...	...	...
34	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
35	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
36	7.4	7.4	7.4	7.4	6.0	5.8	4.4	...	...	...	...	...	...	...	...	...	...	...
37	10.9	10.9	10.9	10.6	7.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
38	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
39	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
40	8.6	8.6	8.6	8.5	6.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
41	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
42	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
43	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
44	7.4	7.4	7.4	7.4	6.0	5.8	4.4	...	...	...	...	...	...	...	...	...	...	...
45	10.9	10.9	10.9	10.6	7.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Smls. extr. tube	SB-241	...	A96061	T4 wld.
2	...	Smls. extr. tube	SB-241	...	A96061	T6 wld.
3	...	Smls. pipe	SB-241	...	A96061	T6 drawn
4	...	Smls. pipe	SB-241	...	A96061	T6
5	...	Smls. pipe	SB-241	...	A96061	T6 wld.
6	...	Die forgings	SB-247	...	A96061	T6
7	...	Hand forgings	SB-247	...	A96061	T6
8	...	Hand forgings	SB-247	...	A96061	T6
9	...	Die & hand forgings	SB-247	...	A96061	T6 wld.
10	...	Shapes	SB-308	...	A96061	T6
11	...	Shapes	SB-308	...	A96061	T6 wld.
12	...	Drawn smls. tube	SB-210	...	A96063	T6
13	...	Drawn smls. tube	SB-210	...	A96063	T6 wld.
14	...	Bar, rod, shapes	SB-221	...	A96063	T1
15	...	Bar, rod, shapes	SB-221	...	A96063	T1
16	...	Bar, rod, shapes	SB-221	...	A96063	T5
17	...	Bar, rod, shapes	SB-221	...	A96063	T5
18	...	Bar, rod, shapes	SB-221	...	A96063	T6
19	...	Bar, rod, shapes	SB-221	...	A96063	T5 wld.
20	...	Bar, rod, shapes	SB-221	...	A96063	T6 wld.
21	...	Smls. extr. tube	SB-241	...	A96063	T1
22	...	Smls. extr. tube	SB-241	...	A96063	T1
23	...	Smls. extr. tube	SB-241	...	A96063	T5
24	...	Smls. extr. tube	SB-241	...	A96063	T5
25	...	Smls. extr. tube	SB-241	...	A96063	T6
26	...	Smls. extr. tube	SB-241	...	A96063	T5 wld.
27	...	Smls. extr. tube	SB-241	...	A96063	T6 wld.
28	...	Smls. pipe	SB-241	...	A96063	T6
29	...	Smls. pipe	SB-241	...	A96063	T6 wld.
30	...	Bar, rod	SB-187	...	C10200	O60
31	...	Bar, rod	SB-187	...	C10200	O60
32	...	Smls. tube	SB-75	...	C10200	O50, O60
33	...	Smls. tube	SB-75	...	C10200	O50, O60
34	...	Smls. pipe	SB-42	...	C10200	O61
35	...	Smls. pipe	SB-42	...	C10200	O61
(25) 36	...	Plate, sheet, strip, bar	SB-152	...	C10200	H00
(25) 37	...	Plate, sheet, strip, bar	SB-152	...	C10200	H01
(25) 38	...	Plate, sheet, strip, bar	SB-152	...	C10200	H02
(25) 39	...	Plate, sheet, strip, bar	SB-152	...	C10200	H03
(25) 40	...	Plate, sheet, strip, bar	SB-152	...	C10200	H04
(25) 41	...	Plate, sheet, strip, bar	SB-152	...	C10200	M20, O25
(25) 42	...	Plate, sheet, strip, bar	SB-152	...	C10200	M20, O25
43	...	Smls. pipe	SB-42	...	C10200	H55
44	...	Smls. tube	SB-75	...	C10200	H55
45	...	Smls. cond. tube	SB-111	...	C10200	H55

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-13	G24, T3, W7
2	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G24, T3, W7, W9
3	<1.000	23	42	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
4	≥1.000	23	38	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
5	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W7, W9
6	≤4.000	23	38	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
7	≤4.000	23	37	33	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
8	4.001-8.000	23	35	32	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
9	≤8.000	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W7, W9
10	...	23	38	35	NP	400 (Cl. 3 only)	400	400	NFA-12,13	T3, W4, W9
11	...	23	24	...	NP	400 (Cl. 3 only)	400	400	NFA-12,13	G13, T3, W7, W9
12	0.025-0.500	23	33	28	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W4
13	0.025-0.500	23	17	8	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W7
14	≤0.500	23	17	9	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W4
15	0.501-1.000	23	16	8	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W4
16	≤0.500	23	22	16	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W4
17	0.501-1.000	23	21	15	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W4
18	≤1.000	23	30	25	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W4
19	≤1.000	23	17	8	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W7
20	≤1.000	23	17	8	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W7
21	≤0.500	23	17	9	NP	350 (Cl. 3 only)	NP	NP	NFA-1	T3, W4
22	0.501-1.000	23	16	8	NP	350 (Cl. 3 only)	NP	NP	NFA-1	T3, W4
23	≤0.500	23	22	16	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W4
24	0.501-1.000	23	21	15	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W4
25	≤1.000	23	30	25	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W4
26	≤1.000	23	17	8	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W7
27	≤1.000	23	17	8	NP	350 (Cl. 3 only)	400	400	NFA-1	T3, W7
28	≤1.000	23	30	25	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W4
29	≤1.000	23	17	8	NP	400 (Cl. 3 only)	400	400	NFA-1	T3, W7
30	All	31	28	8	NP	300	400	400	NFC-1	T3
31	All	31	28	8	NP	300	400	400	NFC-1	G5, T3
32	All	31	30	9	400	300 (Cl. 3 only)	400	400	NFC-1	G1, T3
33	All	31	30	9	400	300 (Cl. 3 only)	400	400	NFC-1	G1, G5, T3
34	All	31	30	9	400	300	400	400	NFC-1	G1, T3
35	All	31	30	9	400	300	400	400	NFC-1	G1, G5, T3
36	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	G33, T3, W3
37	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	G33, T3, W3
38	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	G33, T3, W3
39	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	G33, T3, W3
40	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	G33, T3, W3
41	...	31	30	10	NP	300 (Cl. 3 only)	400	400	NFC-1	T3
42	...	31	30	10	NP	250 (Cl. 3 only)	400	400	NFC-1	G5, T2
43	2 < NPS ≤ 12	31	36	30	400	400	400	400	NFC-6	G1, G9, W3
44	All	31	36	30	400	400 (Cl. 3 only)	400	400	NFC-6	G1, G9, W3
45	...	31	36	30	NP	400	400	400	NFC-6	G9, W3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
2	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
3	12.0	12.0	12.0	11.7	8.4	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
4	10.9	10.9	10.9	10.6	7.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
5	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
6	10.9	10.9	10.9	10.6	7.9	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
7	10.6	10.6	10.6	10.5	7.7	6.3	4.5	...	...	...	...	...	...	...	...	...	...	...
8	10.0	10.0	10.0	9.9	7.4	6.1	4.5	...	...	...	...	...	...	...	...	...	...	...
9	6.9	6.9	6.9	6.8	5.5	4.6	3.5	...	...	...	...	...	...	...	...	...	...	...
10	10.9	10.9	10.9	10.6	7.2	5.6	4.0	...	...	...	...	...	...	...	...	...	...	...
11	6.9	6.9	6.9	6.8	5.0	4.2	3.2	...	...	...	...	...	...	...	...	...	...	...
12	9.4	9.4	9.4	8.3	5.5	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
13	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
14	4.9	4.9	4.9	4.9	4.2	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
15	4.6	4.6	4.6	4.6	4.0	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
16	6.3	6.3	6.1	5.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
17	6.0	6.0	5.9	5.6	4.3	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
18	8.6	8.6	8.6	7.5	5.0	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
19	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
20	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
21	4.9	4.9	4.9	4.9	4.2	3.4	...	...	...	...	...	...	...	...	...	...	...	...
22	4.6	4.6	4.6	4.6	4.0	3.4	...	...	...	...	...	...	...	...	...	...	...	...
23	6.3	6.3	6.1	5.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
24	6.0	6.0	5.9	5.6	4.4	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
25	8.6	8.6	8.6	7.5	5.0	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
26	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
27	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
28	8.6	8.6	8.6	7.5	5.0	3.4	2.0	...	...	...	...	...	...	...	...	...	...	...
29	4.9	4.9	4.9	4.9	3.9	3.0	2.0	...	...	...	...	...	...	...	...	...	...	...
30	5.3	4.7	4.7	4.7	4.7	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
31	5.3	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
32	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
33	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
34	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
35	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
36	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
37	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
38	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
39	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
40	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
41	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
42	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
43	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
44	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
45	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	...	Smls. U-bend tube	SB-395	...	C10200	H55
2	...	Smls. pipe	SB-42	...	C10200	H80
3	...	Smls. tube	SB-75	...	C10200	H80
4	...	Smls. cond. tube	SB-111	...	C10200	H80
(25) 5	...	Plate, sheet, strip, bar	SB-152	...	C10400	H00
(25) 6	...	Plate, sheet, strip, bar	SB-152	...	C10400	H01
(25) 7	...	Plate, sheet, strip, bar	SB-152	...	C10400	H02
(25) 8	...	Plate, sheet, strip, bar	SB-152	...	C10400	H03
(25) 9	...	Plate, sheet, strip, bar	SB-152	...	C10400	H04
(25) 10	...	Plate, sheet, strip, bar	SB-152	...	C10400	M20, 025
(25) 11	...	Plate, sheet, strip, bar	SB-152	...	C10400	M20, 025
(25) 12	...	Plate, sheet, strip, bar	SB-152	...	C10500	H00
(25) 13	...	Plate, sheet, strip, bar	SB-152	...	C10500	H01
(25) 14	...	Plate, sheet, strip, bar	SB-152	...	C10500	H02
(25) 15	...	Plate, sheet, strip, bar	SB-152	...	C10500	H03
(25) 16	...	Plate, sheet, strip, bar	SB-152	...	C10500	H04
(25) 17	...	Plate, sheet, strip, bar	SB-152	...	C10500	M20, 025
(25) 18	...	Plate, sheet, strip, bar	SB-152	...	C10500	M20, 025
(25) 19	...	Plate, sheet, strip, bar	SB-152	...	C10700	H00
(25) 20	...	Plate, sheet, strip, bar	SB-152	...	C10700	H01
(25) 21	...	Plate, sheet, strip, bar	SB-152	...	C10700	H02
(25) 22	...	Plate, sheet, strip, bar	SB-152	...	C10700	H03
(25) 23	...	Plate, sheet, strip, bar	SB-152	...	C10700	H04
(25) 24	...	Plate, sheet, strip, bar	SB-152	...	C10700	M20, 025
(25) 25	...	Plate, sheet, strip, bar	SB-152	...	C10700	M20, 025
26	...	Bar	SB-187	...	C11000	H04
27	...	Bar, rod	SB-187	...	C11000	O60
28	...	Bar, rod	SB-187	...	C11000	O60
29	...	Plate, sheet, strip, bar	SB-152	...	C11000	H00
30	...	Plate, sheet, strip, bar	SB-152	...	C11000	H01
31	...	Plate, sheet, strip, bar	SB-152	...	C11000	H02
32	...	Plate, sheet, strip, bar	SB-152	...	C11000	H03
33	...	Plate, sheet, strip, bar	SB-152	...	C11000	H04
34	...	Plate, sheet, strip, bar	SB-152	...	C11000	M20, 025
35	...	Plate, sheet, strip, bar	SB-152	...	C11000	M20, 025
36	...	Smls. tube	SB-75	...	C12000	O50, O60
37	...	Smls. tube	SB-75	...	C12000	O50, O60
38	...	Smls. pipe	SB-42	...	C12000	O61
39	...	Smls. pipe	SB-42	...	C12000	O61
40	...	Smls. pipe	SB-42	...	C12000	H55
41	...	Smls. tube	SB-75	...	C12000	H55
42	...	Smls. cond. tube	SB-111	...	C12000	H55
43	...	Smls. U-bend tube	SB-395	...	C12000	H55
44	...	Smls. pipe	SB-42	...	C12000	H80
45	...	Smls. tube	SB-75	...	C12000	H80

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	31	36	30	NP	400 (Cl. 3 only)	400	400	NFC-6	G9, W3
2	$\frac{1}{8} < \text{NPS} \leq 2$	31	45	40	400	300	400	400	NFC-6	G1, G6, G9, T4, W3
3	<4	31	45	40	400	350	400	400	NFC-6	G1, G6, G9, T4, W3
4	...	31	45	40	NP	300	400	400	NFC-6	G6, G9, T4, W3
5	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
6	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
7	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
8	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
9	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
10	...	31	30	10	NP	300	400	400	NFC-1	T3
11	...	31	30	10	NP	250	400	400	NFC-1	G5, T2
12	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
13	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
14	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
15	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
16	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
17	...	31	30	10	NP	300	400	400	NFC-1	T3
18	...	31	30	10	NP	250	400	400	NFC-1	G5, T2
19	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
20	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
21	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
22	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
23	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
24	...	31	30	10	NP	300	400	400	NFC-1	T3
25	...	31	30	10	NP	250	400	400	NFC-1	G5, T2
26	All	31	28	8	NP	300	400	400	NFC-1	G33, T3
27	All	31	28	8	NP	300	400	400	NFC-1	T3
28	All	31	28	8	NP	300	400	400	NFC-1	G5, T3
29	...	31	30	10	NP	NP	400	400	NFC-1	G33, T3, W3
30	...	31	30	10	NP	NP	400	400	NFC-1	G33, T3, W3
31	...	31	30	10	NP	NP	400	400	NFC-1	G33, T3, W3
32	...	31	30	10	NP	NP	400	400	NFC-1	G33, T3, W3
33	...	31	30	10	NP	NP	400	400	NFC-1	G33, T3, W3
34	...	31	30	10	NP	NP	400	400	NFC-1	T3
35	...	31	30	10	NP	NP	400	400	NFC-1	G5, T2
36	All	31	30	9	400	300 (Cl. 3 only)	400	400	NFC-1	G1, T3
37	All	31	30	9	400	300 (Cl. 3 only)	400	400	NFC-1	G1, G5, T3
38	All	31	30	9	400	300	400	400	NFC-1	G1, T3
39	All	31	30	9	400	300	400	400	NFC-1	G1, G5, T3
40	$2 < \text{NPS} \leq 12$	31	36	30	400	400	400	400	NFC-6	G1, G9, W3
41	All	31	36	30	400	400 (Cl. 3 only)	400	400	NFC-6	G1, G9, W3
42	...	31	36	30	NP	400	400	400	NFC-6	G9, W3
43	...	31	36	30	NP	400 (Cl. 3 only)	400	400	NFC-6	G9, W3
44	$\frac{1}{8} < \text{NPS} \leq 2$	31	45	40	400	300	400	400	NFC-6	G1, G6, G9, T4, W3
45	<4	31	45	40	400	350 (Cl. 3 only)	400	400	NFC-6	G1, G6, G9, T4, W3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
2	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
3	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
4	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
5	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
6	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
7	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
8	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
9	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
10	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
11	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
12	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
13	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
14	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
15	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
16	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
17	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
18	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
19	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
20	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
21	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
22	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
23	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
24	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
25	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
26	5.3	4.7	4.7	4.7	4.7	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
27	5.3	4.7	4.7	4.7	4.7	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
28	5.3	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
29	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
30	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
31	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
32	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
33	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
34	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
35	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
36	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
37	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
38	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
39	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
40	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
41	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
42	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
43	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
44	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
45	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Smls. cond. tube	SB-111	...	C12000	H80
(25) 2	...	Smls. pipe	SB-42	...	C12200	O61
(25) 3	...	Smls. pipe	SB-42	...	C12200	O61
4	...	Smls. tube	SB-75	...	C12200	O50
5	...	Smls. tube	SB-75	...	C12200	O50
6	...	Smls. tube	SB-75	...	C12200	O60
7	...	Smls. tube	SB-75	...	C12200	O60
(25) 8	...	Finned tube	SB-359	...	C12200	O61
(25) 9	...	Finned tube	SB-359	...	C12200	O61
(25) 10	...	Wld. cond. tube	SB-543	...	C12200	W061
(25) 11	...	Wld. cond. tube	SB-543	...	C12200	W061
(25) 12	...	Plate, sheet, strip, bar	SB-152	...	C12200	H00
(25) 13	...	Plate, sheet, strip, bar	SB-152	...	C12200	H01
(25) 14	...	Plate, sheet, strip, bar	SB-152	...	C12200	H02
(25) 15	...	Plate, sheet, strip, bar	SB-152	...	C12200	H03
(25) 16	...	Plate, sheet, strip, bar	SB-152	...	C12200	H04
(25) 17	...	Plate, sheet, strip, bar	SB-152	...	C12200	M20, O25
(25) 18	...	Plate, sheet, strip, bar	SB-152	...	C12200	M20, O25
19	...	Wld. cond. tube	SB-543	...	C12200	WC55
20	...	Smls. pipe	SB-42	...	C12200	H55
21	...	Smls. tube	SB-75	...	C12200	H55
22	...	Smls. cond. tube	SB-111	...	C12200	H55
(25) 23	...	Finned tube	SB-359	...	C12200	H55
24	...	Smls. U-bend tube	SB-395	...	C12200	H55
25	...	Smls. pipe	SB-42	...	C12200	H80
26	...	Smls. cond. tube	SB-75	...	C12200	H80
27	...	Smls. tube	SB-111	...	C12200	H80
(25) 28	...	Finned tube	SB-359	...	C12200	H80
29	...	Plate, sheet, strip, bar	SB-152	...	C12300	H00
30	...	Plate, sheet, strip, bar	SB-152	...	C12300	H01
31	...	Plate, sheet, strip, bar	SB-152	...	C12300	H02
32	...	Plate, sheet, strip, bar	SB-152	...	C12300	H03
33	...	Plate, sheet, strip, bar	SB-152	...	C12300	H04
34	...	Plate, sheet, strip, bar	SB-152	...	C12300	M20, O25
35	...	Plate, sheet, strip, bar	SB-152	...	C12300	M20, O25
(25) 36	...	Plate, sheet, strip, bar	SB-152	...	C14200	M20, O25
(25) 37	...	Plate, sheet, strip, bar	SB-152	...	C14200	M20, O25
38	...	Smls. cond. tube	SB-111	...	C14200	H55
39	...	Smls. U-bend tube	SB-395	...	C14200	H55
40	...	Smls. cond. tube	SB-111	...	C14200	H80
41	...	Smls. cond. tube	SB-111	...	C19200	O61
42	...	Smls. cond. tube	SB-111	...	C19200	O61
43	...	Smls. U-bend tube	SB-395	...	C19200	O61
44	...	Smls. U-bend tube	SB-395	...	C19200	O61
45	...	Wld. cond. tube	SB-543	...	C19400	W061

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	31	45	40	NP	300	400	400	NFC-6	G6, G9, T4, W3
2	All	31	30	9	400	300	400	400	NFC-1	G1, T3
3	All	31	30	9	400	300	400	400	NFC-1	G1, G5, T3
4	All	31	30	9	400	300	400	400	NFC-7	G1, T3
5	All	31	30	9	400	300	400	400	NFC-7	G1, G5, T3
6	All	31	30	9	400	300	400	400	NFC-1	G1, T3
7	All	31	30	9	400	300	400	400	NFC-1	G1, G5, T3
8	...	31	30	9	NP	300 (Cl. 3 only)	400	NP	NFC-1	T3
9	...	31	30	9	NP	300 (Cl. 3 only)	400	NP	NFC-1	G5, T3
10	...	31	30	9	NP	300 (Cl. 3 only)	400	400	NFC-1	G14, T3, W11
11	...	31	30	9	NP	300 (Cl. 3 only)	400	400	NFC-1	G5, G14, T3, W11
12	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
13	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
14	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
15	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
16	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
17	...	31	30	10	NP	300	400	400	NFC-1	T3
18	...	31	30	10	NP	250	400	400	NFC-1	G5, T2
19	...	31	32	15	NP	300 (Cl. 3 only)	400	400	NFC-1	G14, T4, W10
20	2 < NPS ≤ 12	31	36	30	400	400	400	400	NFC-6	G1, G9, W3
21	All	31	36	30	400	400 (Cl. 3 only)	400	400	NFC-6	G1, G9, W3
22	...	31	36	30	NP	400	400	400	NFC-6	G9, W3
23	...	31	36	30	NP	300 (Cl. 3 only)	400	NP	NFC-6	G9, W3
24	...	31	36	30	NP	400 (Cl. 3 only)	400	400	NFC-6	G9, W3
25	1/8 < NPS ≤ 2	31	45	40	400	300	400	400	NFC-6	G1, G6, G9, T4, W3
26	<4	31	45	40	400	350 (Cl. 3 only)	400	400	NFC-6	G1, G6, G9, T4, W3
27	...	31	45	40	NP	300	400	400	NFC-6	G6, G9, T4, W3
28	...	31	45	40	NP	NP	400	NP	NFC-6	G6, G9, T4, W3
29	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
30	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
31	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
32	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
33	...	31	30	10	NP	300	400	400	NFC-1	G33, T3, W3
34	...	31	30	10	NP	300	400	400	NFC-1	T3
35	...	31	30	10	NP	250	400	400	NFC-1	G5, T2
36	...	31	30	10	NP	300 (Cl. 3 only)	NP	NP	NFC-1	...
37	...	31	30	10	NP	250 (Cl. 3 only)	NP	NP	NFC-1	G5
38	...	31	36	30	NP	400	400	400	NFC-6	G9, W3
39	...	31	36	30	NP	400 (Cl. 3 only)	400	400	NFC-6	G9, W3
40	...	31	45	40	NP	300	400	400	NFC-6	G6, G9, T4, W3
41	...	31	38	12	NP	NP	300	300	NFC-1	...
42	...	31	38	12	NP	NP	300	300	NFC-1	G5, T2
43	...	31	38	12	NP	NP	300	300	NFC-1	...
44	...	31	38	12	NP	NP	300	300	NFC-1	G5, T2
45	...	31	45	15	NP	NP	400	400	NFC-5	G14, T4, W11

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
2	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
3	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
4	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
5	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
6	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
7	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
8	6.0	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
9	6.0	6.0	6.0	6.0	6.0	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
10	5.1	4.5	4.5	4.5	4.5	3.8	2.5	...	...	...	...	...	...	...	...	...	...	...
11	5.1	5.1	5.1	5.1	5.1	3.8	2.5	...	...	...	...	...	...	...	...	...	...	...
12	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
13	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
14	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
15	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
16	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
17	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
18	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
19	7.8	7.8	7.8	7.8	7.5	7.3	2.6	...	...	...	...	...	...	...	...	...	...	...
20	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
21	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
22	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
23	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
24	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
25	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
26	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
27	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
28	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
29	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
30	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
31	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
32	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
33	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
34	6.7	5.9	5.9	5.9	5.8	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
35	6.7	6.7	6.7	6.7	6.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...	...
36	6.7	5.9	5.9	5.9	5.8	...	...	...	...	...	...	...	...	...	...	...	...	...
37	6.7	6.7	6.7	6.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
39	10.3	10.3	10.3	10.3	10.0	9.7	9.4	...	...	...	...	...	...	...	...	...	...	...
40	12.9	12.9	12.9	12.9	12.5	11.8	4.3	...	...	...	...	...	...	...	...	...	...	...
41	8.0	7.1	6.7	6.4	6.2	...	...	...	...	...	...	...	...	...	...	...	...	...
42	8.0	8.0	8.0	8.0	6.3	...	...	...	...	...	...	...	...	...	...	...	...	...
43	8.0	7.1	6.7	6.4	6.2	...	...	...	...	...	...	...	...	...	...	...	...	...
44	8.0	8.0	8.0	8.0	6.3	...	...	...	...	...	...	...	...	...	...	...	...	...
45	8.5	8.4	8.3	8.1	7.8	7.6	6.0	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Wld. cond. tube	SB-543	...	C19400	W061
2	...	Wld. cond. tube	SB-543	...	C19400	WC55
(25) 3	...	Smls. pipe	SB-43	...	C23000	061
(25) 4	...	Smls. pipe	SB-43	...	C23000	H58
5	...	Smls. cond. tube	SB-111	...	C23000	061
(25) 6	...	Smls. tube	SB-135	...	C23000	050
(25) 7	...	Smls. red brass tube	SB-135	...	C23000	060
8	...	Smls. tube	SB-395	...	C23000	061
9	...	Wld. cond. tube	SB-543	...	C23000	W061
10	...	Wld. cond. tube	SB-543	...	C23000	WC55
11	...	Smls. tube	SB-111	...	C28000	061
12	...	Plate	SB-171	...	C36500	M10, M20
13	...	Plate	SB-171	...	C36500	020, 025
14	...	Plate	SB-171	...	C36500	M10, M20
15	...	Plate	SB-171	...	C36500	020, 025
(25) 16	...	Plate, sheet	SB-171	...	C36500	M10, M20
(25) 17	...	Plate, sheet	SB-171	...	C36500	020, 025
(25) 18	...	Forgings	SB-283	...	C37700	M10, 020
(25) 19	...	Forgings	SB-283	...	C37700	M10, 020
(25) 20	...	Forgings	SB-283	...	C37700	M10, 020
(25) 21	...	Forgings	SB-283	...	C37700	M10, 020
(25) 22	...	Smls. cond. tube	SB-111	...	C44300	061
(25) 23	...	Plate, sheet	SB-171	...	C44300	M10, M20
(25) 24	...	Plate, sheet	SB-171	...	C44300	020, 025
(25) 25	...	Finned tube	SB-359	...	C44300	061
26	...	Smls. U-bend tube	SB-395	...	C44300	061
27	...	Wld. cond. tube	SB-543	...	C44300	W061
(25) 28	...	Smls. cond. tube	SB-111	...	C44400	061
(25) 29	...	Plate, sheet	SB-171	...	C44400	M10, M20
(25) 30	...	Plate, sheet	SB-171	...	C44400	020, 025
(25) 31	...	Finned tube	SB-359	...	C44400	061
32	...	Smls. U-bend tube	SB-395	...	C44400	061
33	...	Wld. cond. tube	SB-543	...	C44400	W061
(25) 34	...	Smls. cond. tube	SB-111	...	C44500	061
(25) 35	...	Plate, sheet	SB-171	...	C44500	M10, M20
(25) 36	...	Plate, sheet	SB-171	...	C44500	020, 025
(25) 37	...	Finned tube	SB-359	...	C44500	061
38	...	Smls. U-bend tube	SB-395	...	C44500	061
39	...	Wld. cond. tube	SB-543	...	C44500	W061
40	...	Plate	SB-171	...	C46400	M10, M20
41	...	Plate	SB-171	...	C46400	020, 025
(25) 42	...	Plate, sheet	SB-171	...	C46400	M10, M20
(25) 43	...	Plate, sheet	SB-171	...	C46400	020, 025
44	...	Plate	SB-171	...	C46500	M10, M20
45	...	Plate	SB-171	...	C46500	020, 025

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	31	45	15	NP	NP	400	400	NFC-5	G5, G14, T3, W11
2	...	31	45	22	NP	300 (Cl. 3 only)	400	400	NFC-5	G14, T3, W10
3	...	32	40	12	450	300 (Cl. 3 only)	450	450	NFC-1	T3
4	...	32	44	18	450	300 (Cl. 3 only)	450	450	NFC-1	G33, T3, W3
5	...	32	40	12	NP	300 (Cl. 3 only)	450	450	NFC-1	T3
6	...	32	40	12	NP	300 (Cl. 3 only)	NP	NP	NFC-1	...
7	...	32	40	12	NP	300 (Cl. 3 only)	450	450	NFC-1	T3
8	...	32	40	12	NP	300 (Cl. 3 only)	450	450	NFC-1	T3
9	...	32	40	12	NP	300 (Cl. 3 only)	450	450	NFC-1	G14, T3, W11
10	...	32	42	20	NP	300 (Cl. 3 only)	450	450	NFC-2	G14, G33, T3, W10
11	...	32	50	20	400	350 (Cl. 3 only)	400	400	NFC-3	G1, G6, T3
12	$3.5 < t \leq 5$	32	40	12	NP	350 (Cl. 3 only)	400	400	NFC-2	G7, T4
13	$3.5 < t \leq 5$	32	40	12	NP	350 (Cl. 3 only)	400	400	NFC-2	G7, T4
14	$2 < t \leq 3.5$	32	45	15	NP	350 (Cl. 3 only)	400	400	NFC-2	T4
15	$2 < t \leq 3.5$	32	45	15	NP	350 (Cl. 3 only)	400	400	NFC-2	T4
16	≤ 2	32	50	20	NP	350 (Cl. 3 only)	400	400	NFC-2	T3
17	≤ 2	32	50	20	NP	350 (Cl. 3 only)	400	400	NFC-2	T3
18	$> 1\frac{1}{2}$	...	46	15	NP	NP	400	400	NFC-2	G17, T2, W14
19	$> 1\frac{1}{2}$	...	46	15	NP	NP	400	400	NFC-2	G5, G17, T1, W14
20	$\leq 1\frac{1}{2}$	...	50	18	NP	NP	400	400	NFC-2	G17, T1, W14
21	$\leq 1\frac{1}{2}$	...	50	18	NP	NP	400	400	NFC-2	G5, G17, T1, W14
22	...	32	45	15	450	350 (Cl. 3 only)	450	450	NFC-2	G6, T4
23	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
24	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
25	...	32	45	15	NP	350 (Cl. 3 only)	450	NP	NFC-2	G6, T4
26	...	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
27	...	32	45	15	NP	NP	450	450	NFC-2	G7, G14, T4, W11
28	...	32	45	15	450	350 (Cl. 3 only)	450	450	NFC-2	G6, T4
29	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
30	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
31	...	32	45	15	NP	350 (Cl. 3 only)	450	NP	NFC-2	G6, T4
32	...	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
33	...	32	45	15	NP	NP	450	450	NFC-2	G7, G14, T4, W11
34	...	32	45	15	450	350 (Cl. 3 only)	450	450	NFC-2	G6, T4
35	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
36	≤ 4	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
37	...	32	45	15	NP	350 (Cl. 3 only)	450	NP	NFC-2	G6, T4
38	...	32	45	15	NP	350 (Cl. 3 only)	450	450	NFC-2	T4
39	...	32	45	15	NP	NP	450	450	NFC-2	G7, G14, T4, W11
40	$3 < t \leq 5$	32	50	18	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
41	$3 < t \leq 5$	32	50	18	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
42	≤ 3	32	50	20	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
43	≤ 3	32	50	20	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
44	$3 < t \leq 5$	32	50	18	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
45	$3 < t \leq 5$	32	50	18	NP	300 (Cl. 3 only)	400	400	NFC-2	T3

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	8.5	8.5	8.5	8.5	8.5	7.7	6.0	...	...	...	...	...	...	...	...	...	...	...
2	10.9	10.9	10.9	10.6	10.1	7.7	6.0	...	...	...	...	...	...	...	...	...	...	...
3	8.0	8.0	8.0	8.0	8.0	7.0	5.0	2.0	...	...	...	...	...	...	...	...	...	...
4	8.0	8.0	8.0	8.0	8.0	7.0	5.0	2.0	...	...	...	...	...	...	...	...	...	...
5	8.0	8.0	8.0	8.0	8.0	7.0	5.0	2.0	...	...	...	...	...	...	...	...	...	...
6	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...	...	...	...	...	...	...	...
7	8.0	8.0	8.0	8.0	8.0	7.0	5.0	2.0	...	...	...	...	...	...	...	...	...	...
8	8.0	8.0	8.0	8.0	8.0	7.0	5.0	2.0	...	...	...	...	...	...	...	...	...	...
9	6.8	6.8	6.8	6.8	6.8	6.0	4.3	1.7	...	...	...	...	...	...	...	...	...	...
10	6.8	6.8	6.8	6.8	6.8	6.0	4.3	1.7	...	...	...	...	...	...	...	...	...	...
11	13.3	13.3	13.3	13.3	13.3	10.8	5.3	...	...	...	...	...	...	...	...	...	...	...
12	8.0	8.0	8.0	8.0	8.0	8.0	5.3	...	...	...	...	...	...	...	...	...	...	...
13	8.0	8.0	8.0	8.0	8.0	8.0	5.3	...	...	...	...	...	...	...	...	...	...	...
14	10.0	10.0	10.0	10.0	10.0	10.0	5.3	...	...	...	...	...	...	...	...	...	...	...
15	10.0	10.0	10.0	10.0	10.0	10.0	5.3	...	...	...	...	...	...	...	...	...	...	...
16	13.3	13.3	13.3	13.3	13.3	10.8	5.3	...	...	...	...	...	...	...	...	...	...	...
17	13.3	13.3	13.3	13.3	13.3	10.8	5.3	...	...	...	...	...	...	...	...	...	...	...
18	10.0	8.3	8.3	8.3	5.3	3.1	1.8	...	...	...	...	...	...	...	...	...	...	...
19	10.0	10.0	10.0	8.6	5.3	3.1	1.8	...	...	...	...	...	...	...	...	...	...	...
20	12.0	10.0	10.0	8.6	5.3	3.1	1.8	...	...	...	...	...	...	...	...	...	...	...
21	12.0	12.0	12.0	8.6	5.3	3.1	1.8	...	...	...	...	...	...	...	...	...	...	...
22	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
23	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
24	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
25	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
26	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
27	8.5	8.5	8.5	8.5	8.5	8.5	4.5	1.7	...	...	...	...	...	...	...	...	...	...
28	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
29	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
30	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
31	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
32	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
33	8.5	8.5	8.5	8.5	8.5	8.5	4.5	1.7	...	...	...	...	...	...	...	...	...	...
34	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
35	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
36	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
37	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
38	10.0	10.0	10.0	10.0	10.0	10.0	5.3	2.0	...	...	...	...	...	...	...	...	...	...
39	8.5	8.5	8.5	8.5	8.5	8.5	4.5	1.7	...	...	...	...	...	...	...	...	...	...
40	12.0	12.0	12.0	12.0	12.0	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
41	12.0	12.0	12.0	12.0	12.0	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
42	13.3	13.3	13.3	13.3	13.3	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
43	13.3	13.3	13.3	13.3	13.3	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
44	12.0	12.0	12.0	12.0	12.0	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
45	12.0	12.0	12.0	12.0	12.0	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
(25) 1	...	Plate, sheet	SB-171	...	C46500	M10, M20
(25) 2	...	Plate, sheet	SB-171	...	C46500	O20, O25
3	...	Smls. cond. tube	SB-111	...	C60800	O61
4	...	Smls. cond. tube	SB-111	...	C60800	O61
(25) 5	...	Smls. U-bend tube	SB-395	...	C60800	O61
(25) 6	...	Smls. U-bend tube	SB-395	...	C60800	O61
(25) 7	...	Plate	SB-171	...	C61400	M10, M20, O20, O25
(25) 8	...	...	...	...	...	...
(25) 9	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 10	...	Plate	SB-171	...	C61400	M10, M20, O20, O25
(25) 11	...	...	...	...	...	...
(25) 12	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 13	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 14	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
(25) 15	...	...	...	...	...	...
(25) 16	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
(25) 17	...	...	...	...	...	...
(25) 18	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
(25) 19	...	...	...	...	...	...
(25) 20	...	Forgings	SB-283	...	C64200	M10, O20
(25) 21	...	Forgings	SB-283	...	C64200	M10, O20
(25) 22	...	Forgings	SB-283	...	C64200	M10, O20
(25) 23	...	Forgings	SB-283	...	C64200	M10, O20
24	...	Bar, rod	SB-98	...	C65100	O60
25	...	Bar, rod	SB-98	...	C65100	O60
26	...	Bar, rod	SB-98	...	C65100	H02
27	...	Bar, rod	SB-98	...	C65100	H02
(25) 28	...	Smls. pipe & tube	SB-315	...	C65500	O30, O61
(25) 29	...	Smls. pipe & tube	SB-315	...	C65500	O30, O61
(25) 30	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61
(25) 31	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61
32	...	Bar, rod	SB-98	...	C65500	O60
33	...	Bar, rod	SB-98	...	C65500	O60
34	...	Bar, rod	SB-98	...	C65500	H02
35	...	Bar, rod	SB-98	...	C66100	O60
36	...	Bar, rod	SB-98	...	C66100	O60
37	...	Bar, rod	SB-98	...	C66100	H02
38	...	Smls. cond. tube	SB-111	...	C68700	O61
39	...	Smls. cond. tube	SB-111	...	C68700	O61
40	...	Smls. U-bend tube	SB-395	...	C68700	O61
41	...	Smls. U-bend tube	SB-395	...	C68700	O61
42	...	Wld. cond. tube	SB-543	...	C68700	W061
43	...	Wld. cond. tube	SB-543	...	C68700	W061
44	...	Smls. cond. tube	SB-111	...	C70400	O61
45	...	Wld. tube	SB-543	...	C70400	W061

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	≤3	32	50	20	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
2	≤3	32	50	20	NP	300 (Cl. 3 only)	400	400	NFC-2	T3
3	...	35	50	19	NP	300 (Cl. 3 only)	500	500	NFC-2	G6, T3
4	...	35	50	19	NP	300 (Cl. 3 only)	500	500	NFC-2	G5, G6, T3
5	...	35	50	19	NP	300 (Cl. 3 only)	500	500	NFC-2	G6, T3
6	...	35	50	19	NP	300 (Cl. 3 only)	500	500	NFC-2	G5, G6, T3
7	2 < t ≤ 5	35	65	28	NP	500 (Cl. 3 only)	500	500	NFC-8	...
8	...	...	...	...	...	...	...	...	...	...
9	2 < t ≤ 5	35	65	28	NP	500 (Cl. 3 only)	500	500	NFC-8	...
10	≤2	35	70	30	NP	500 (Cl. 3 only)	500	500	NFC-8	...
11	...	...	...	...	...	...	...	...	...	...
12	1/2 < t ≤ 2	35	70	30	NP	500 (Cl. 3 only)	500	500	NFC-8	...
13	≤1/2	35	72	32	NP	450 (Cl. 3 only)	500	500	NFC-8	...
14	3.5 < t ≤ 5	35	80	30	NP	500 (Cl. 3 only)	700	650	NFC-8	T6
15	...	...	...	...	...	...	...	...	...	...
16	2 < t ≤ 3.5	35	85	33	NP	500 (Cl. 3 only)	700	650	NFC-8	T6
17	...	...	...	...	...	...	...	...	...	...
18	≤2	35	90	36	NP	500 (Cl. 3 only)	700	650	NFC-8	T6
19	...	...	...	...	...	...	...	...	...	...
20	>1 1/2	...	68	23	NP	NP	500	500	NFC-3	G10, T4, W14
21	>1 1/2	...	68	23	NP	NP	500	500	NFC-3	G5, G10, T4, W14
22	≤1 1/2	...	70	25	NP	NP	500	500	NFC-3	G10, T4, W14
23	≤1 1/2	...	70	25	NP	NP	500	500	NFC-3	G5, G10, T4, W14
24	All	33	40	12	NP	300	350	350	NFC-1	G17
25	All	33	40	12	NP	300	350	350	NFC-1	G5, G17
26	≤2	33	55	20	NP	300	350	350	NFC-2	G17, W3
27	≤2	33	55	20	NP	300	350	350	NFC-2	G5, G17, W3
28	...	33	50	15	NP	300 (Cl. 3 only)	400	400	NFC-2	G17, T4
29	...	33	50	15	NP	300 (Cl. 3 only)	400	400	NFC-2	G5, G17, T4
30	≤2	33	50	18	NP	300 (Cl. 3 only)	350	350	NFC-2	G17, T3
31	≤2	33	50	18	NP	300 (Cl. 3 only)	350	350	NFC-2	G5, G17, T3
32	All	33	52	15	NP	300	350	350	NFC-2	G17
33	All	33	52	15	NP	300	350	350	NFC-2	G5, G17
34	≤2	33	70	38	NP	300	350	350	NFC-2	G17, W3
35	All	33	52	15	NP	300	350	350	NFC-2	G17
36	All	33	52	15	NP	300	350	350	NFC-2	G5, G17
37	≤2	33	70	38	NP	300	350	350	NFC-2	G17, W3
38	...	32	50	18	NP	300 (Cl. 3 only)	450	450	NFC-2	T3
39	...	32	50	18	NP	300 (Cl. 3 only)	450	450	NFC-2	G5, T3
40	...	32	50	18	NP	300 (Cl. 3 only)	450	450	NFC-2	T3
41	...	32	50	18	NP	300 (Cl. 3 only)	450	450	NFC-2	G5, T3
42	...	32	50	18	NP	NP	450	450	NFC-2	G14, T3, W11
43	...	32	50	18	NP	NP	450	450	NFC-2	G5, G14, T3, W11
44	...	34	38	12	NP	150 (Cl. 3 only)	150	150	NFC-2	...
45	...	34	38	12	NP	NP	150	150	NFC-2	G14, W11

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	13.3	13.3	13.3	13.3	13.3	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
2	13.3	13.3	13.3	13.3	13.3	6.4	2.7	...	...	...	...	...	...	...	...	...	...	...
3	12.7	12.2	12.2	12.2	12.0	10.0	6.0	4.0	2.0	...	...	...	...	...	...	...	...	...
4	12.7	12.7	12.7	12.7	12.7	10.0	6.0	4.0	2.0	...	...	...	...	...	...	...	...	...
5	12.7	12.2	12.2	12.2	12.0	10.0	6.0	4.0	2.0	...	...	...	...	...	...	...	...	...
6	12.7	12.7	12.7	12.7	12.7	10.0	6.0	4.0	2.0	...	...	...	...	...	...	...	...	...
7	18.6	18.6	18.5	18.3	18.2	18.1	17.9	17.5	17.0	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	18.6	18.6	18.5	18.3	18.2	18.1	17.9	17.5	17.0	...	...	...	...	...	...	...	...	...
10	20.0	19.9	19.8	19.7	19.5	19.4	19.2	18.9	18.3	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	20.0	19.9	19.8	19.7	19.5	19.4	19.2	18.9	18.3	...	...	...	...	...	...	...	...	...
13	20.6	20.6	20.6	20.6	20.6	20.6	20.2	19.4	18.8	...	...	...	...	...	...	...	...	...
14	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.7	16.0	12.0	8.6	6.0	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	22.0	22.0	22.0	22.0	22.0	22.0	22.0	21.9	21.7	16.0	12.0	8.6	6.0	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	24.0	24.0	24.0	24.0	24.0	24.0	24.0	23.9	23.6	16.0	12.0	8.6	6.0	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	15.3	14.4	14.2	14.1	14.1	14.1	11.0	7.5	5.2	...	...	...	...	...	...	...	...	...
21	15.3	15.3	15.3	15.3	15.3	15.3	11.0	7.5	5.2	...	...	...	...	...	...	...	...	...
22	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	...	...	...	...	...	...	...	...	...
23	16.7	16.7	16.7	16.7	16.7	16.7	11.0	7.5	5.2	...	...	...	...	...	...	...	...	...
24	8.0	7.9	7.9	7.8	7.8	7.7	...	...	...	...	...	...	...	...	...	...	...	...
25	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...	...	...	...	...	...	...
26	13.3	13.3	13.2	12.9	12.5	12.0	...	...	...	...	...	...	...	...	...	...	...	...
27	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...	...	...	...	...	...	...	...
28	10.0	10.0	9.9	9.9	9.9	9.8	6.8	...	...	...	...	...	...	...	...	...	...	...
29	10.0	10.0	10.0	10.0	10.0	10.0	6.8	...	...	...	...	...	...	...	...	...	...	...
30	12.0	12.0	11.9	11.9	11.9	10.7	...	...	...	...	...	...	...	...	...	...	...	...
31	12.0	12.0	12.0	12.0	12.0	10.7	...	...	...	...	...	...	...	...	...	...	...	...
32	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...	...
33	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...
34	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...
35	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...	...
36	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...
37	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...
38	12.0	11.9	11.8	11.7	11.6	6.5	3.3	1.8	...	...	...	...	...	...	...	...	...	...
39	12.0	12.0	12.0	12.0	12.0	6.5	3.3	1.8	...	...	...	...	...	...	...	...	...	...
40	12.0	11.9	11.8	11.7	11.6	6.5	3.3	1.8	...	...	...	...	...	...	...	...	...	...
41	12.0	12.0	12.0	12.0	12.0	6.5	3.3	1.8	...	...	...	...	...	...	...	...	...	...
42	10.2	10.1	10.0	9.9	9.9	5.5	2.7	1.4	...	...	...	...	...	...	...	...	...	...
43	10.2	10.2	10.2	10.2	10.2	5.5	2.7	1.4	...	...	...	...	...	...	...	...	...	...
44	8.0	8.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	6.8	6.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	...	Smls. cond. tube	SB-111	...	C70400	H55
2	...	Smls. pipe & tube	SB-466	...	C70600	O60
3	...	Smls. pipe & tube	SB-466	...	C70600	O60
4	...	Wld. pipe	SB-467	...	C70600	W061
5	...	Wld. pipe	SB-467	...	C70600	W061
6	...	Bar, rod	SB-151	...	C70600	O60
7	...	Bar, rod	SB-151	...	C70600	O60
8	...	Plate	SB-171	...	C70600	M10, M20
9	...	Plate	SB-171	...	C70600	M10, M20
10	...	Plate, sheet	SB-171	...	C70600	M10, M20
11	...	Plate, sheet	SB-171	...	C70600	M10, M20
12	...	Plate	SB-171	...	C70600	M10, M20
13	...	Plate	SB-171	...	C70600	M10, M20
14	...	Plate	SB-171	...	C70600	O20, O25
15	...	Plate	SB-171	...	C70600	O20, O25
16	...	Plate, sheet	SB-171	...	C70600	O20, O25
17	...	Plate, sheet	SB-171	...	C70600	O20, O25
18	...	Plate	SB-171	...	C70600	O20, O25
19	...	Plate	SB-171	...	C70600	O20, O25
20	...	Smls. cond. tube	SB-111	...	C70600	O61
21	...	Smls. cond. tube	SB-111	...	C70600	O61
22	...	Smls. cond. tube	SB-111	...	C70600	O61
23	...	Smls. cond. tube	SB-111	...	C70600	O61
24	...	Finned tube	SB-359	...	C70600	O61
25	...	Finned tube	SB-359	...	C70600	O61
26	...	Smls. U-bend tube	SB-395	...	C70600	O61
27	...	Smls. U-bend tube	SB-395	...	C70600	O61
28	...	Wld. pipe	SB-467	...	C70600	W061
29	...	Wld. pipe	SB-467	...	C70600	W061
30	...	Wld. tube	SB-543	...	C70600	W061
31	...	Wld. tube	SB-543	...	C70600	W061
32	...	Finned wld. tube	SB-956	...	C70600	W061
33	...	Finned wld. tube	SB-956	...	C70600	W061
34	...	Wld. pipe	SB-467	...	C70600	WM50
35	...	Smls. tube	SB-111	...	C70600	H55
36	...	Smls. pipe & tube	SB-466	...	C70600	H55
37	...	Wld. tube	SB-543	...	C70600	WC55
38	...	Finned wld. tube	SB-956	...	C70600	WC55
39	...	Wld. pipe	SB-467	...	C70600	Wld. fr. cold rld. strip
40	...	Smls. pipe & tube	SB-466	...	C70620	O60
41	...	Smls. pipe & tube	SB-466	...	C70620	O60
42	...	Wld. pipe	SB-467	...	C70620	W061
43	...	Wld. pipe	SB-467	...	C70620	W061
44	...	Bar, rod	SB-151	...	C70620	O60
45	...	Bar, rod	SB-151	...	C70620	O60

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	34	40	30	NP	150 (Cl. 3 only)	150	150	NFC-2	G7, W3
2	...	34	38	13	NP	400	600	600	NFC-3	T6
3	...	34	38	13	NP	400	600	600	NFC-3	G5, T5
4	>4 ¹ / ₂	34	38	13	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T6, W11
5	>4 ¹ / ₂	34	38	13	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
6	All	34	38	15	NP	200	NP	NP	NFC-3	...
7	All	34	38	15	NP	200	NP	NP	NFC-3	G5
8	≤5	34	40	15	NP	400	NP	NP	NFC-3	...
9	≤5	34	40	15	NP	400	NP	NP	NFC-3	G5
10	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	...
11	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	G5
12	≤5	34	40	15	NP	NP	600	600	NFC-3	T5
13	≤5	34	40	15	NP	NP	600	600	NFC-3	G5, T5
14	≤5	34	40	15	NP	400	NP	NP	NFC-3	...
15	≤5	34	40	15	NP	400	NP	NP	NFC-3	G5
16	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	...
17	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	G5
18	≤5	34	40	15	NP	NP	600	600	NFC-3	T5
19	≤5	34	40	15	NP	NP	600	600	NFC-3	G5, T5
20	...	34	40	15	600	400	NP	NP	NFC-3	G1, T5
21	...	34	40	15	600	400	NP	NP	NFC-3	G1, G5, T5
22	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	T5
23	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, T5
24	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G1, T5
25	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G1, G5, T5
26	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	T5
27	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, T5
28	≤4 ¹ / ₂	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T5, W11
29	≤4 ¹ / ₂	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
30	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T5, W11
31	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
32	...	34	40	15	NP	NP	600	NP	NFC-3	G14, G34, T5, W11
33	...	34	40	15	NP	NP	600	NP	NFC-3	G5, G14, G34, T5, W11
34	≤4 ¹ / ₂	34	45	30	NP	NP	600	600	NFC-3	G14, G34, T5, W11
35	...	34	45	35	NP	450 (Cl. 3 only)	600	600	NFC-3	G33, T5, W3
36	...	34	45	35	NP	NP	600	600	NFC-3	G33, T5, W3
37	...	34	45	35	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G33, G34, T5, W10
38	...	34	45	35	NP	NP	600	NP	NFC-3	G14, G33, G34, T5, W10
39	≤4 ¹ / ₂	34	54	45	NP	NP	600	600	NFC-3	G14, G34, T5, W11
40	...	34	38	13	NP	400	600	600	NFC-3	T6
41	...	34	38	13	NP	400	600	600	NFC-3	G5, T5
42	>4 ¹ / ₂	34	38	13	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T6, W11
43	>4 ¹ / ₂	34	38	13	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
44	All	34	38	15	NP	200	NP	NP	NFC-3	...
45	All	34	38	15	NP	200	NP	NP	NFC-3	G5

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	11.4	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	8.7	8.4	8.2	8.0	7.8	7.7	7.5	7.4	7.3	7.0	6.0	...	...	...	...	...	...	...
3	8.7	8.7	8.7	8.7	8.7	8.7	8.7	8.7	8.0	7.0	6.0	...	...	...	...	...	...	...
4	7.4	7.2	7.0	6.8	6.7	6.5	6.4	6.3	6.2	5.7	4.3	...	...	...	...	...	...	...
5	7.4	7.4	7.4	7.4	7.4	7.4	7.4	7.4	6.3	5.7	4.3	...	...	...	...	...	...	...
6	10.0	9.7	9.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	10.0	9.7	9.5	9.3	9.0	8.8	8.7	...	...	...	...	...	...	...	...	...	...	...
9	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
10	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...	...	...	...
11	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...
12	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
13	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
14	10.0	9.7	9.5	9.3	9.0	8.8	8.7	...	...	...	...	...	...	...	...	...	...	...
15	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
16	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...	...	...	...
17	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...
18	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
19	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
20	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
21	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
22	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
23	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
24	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
25	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
26	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
27	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
28	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
29	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
30	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
31	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
32	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
33	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
34	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
35	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
36	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
37	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
38	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
39	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
40	8.7	8.4	8.2	8.0	7.8	7.7	7.5	7.4	7.3	7.0	6.0	...	...	...	...	...	...	...
41	8.7	8.7	8.7	8.7	8.7	8.7	8.7	8.7	8.0	7.0	6.0	...	...	...	...	...	...	...
42	7.4	7.2	7.0	6.8	6.7	6.5	6.4	6.3	6.2	5.7	4.3	...	...	...	...	...	...	...
43	7.4	7.4	7.4	7.4	7.4	7.4	7.4	7.4	6.3	5.7	4.3	...	...	...	...	...	...	...
44	10.0	9.7	9.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	...	Forgings	SB-283	...	C70620	M10
2	...	Forgings	SB-283	...	C70620	M10
3	...	Plate	SB-171	...	C70620	M10, M20
4	...	Plate	SB-171	...	C70620	M10, M20
5	...	Plate, sheet	SB-171	...	C70620	M10, M20
6	...	Plate, sheet	SB-171	...	C70620	M10, M20
7	...	Plate	SB-171	...	C70620	M10, M20
8	...	Plate	SB-171	...	C70620	M10, M20
9	...	Forgings	SB-283	...	C70620	O20
10	...	Forgings	SB-283	...	C70620	O20
11	...	Plate	SB-171	...	C70620	O20, O25
12	...	Plate	SB-171	...	C70620	O20, O25
13	...	Plate, sheet	SB-171	...	C70620	O20, O25
14	...	Plate, sheet	SB-171	...	C70620	O20, O25
15	...	Plate	SB-171	...	C70620	O20, O25
16	...	Plate	SB-171	...	C70620	O20, O25
17	...	Smls. cond. tube	SB-111	...	C70620	O61
18	...	Smls. cond. tube	SB-111	...	C70620	O61
19	...	Smls. cond. tube	SB-111	...	C70620	O61
20	...	Smls. cond. tube	SB-111	...	C70620	O61
21	...	Finned tube	SB-359	...	C70620	O61
22	...	Finned tube	SB-359	...	C70620	O61
23	...	Smls. U-bend tube	SB-395	...	C70620	O61
24	...	Smls. U-bend tube	SB-395	...	C70620	O61
25	...	Wld. pipe	SB-467	...	C70620	W061
26	...	Wld. pipe	SB-467	...	C70620	W061
27	...	Wld. tube	SB-543	...	C70620	W061
28	...	Wld. tube	SB-543	...	C70620	W061
29	...	Finned wld. tube	SB-956	...	C70620	W061
30	...	Finned wld. tube	SB-956	...	C70620	W061
31	...	Forgings	SB-283	...	C70620	M10
32	...	Forgings	SB-283	...	C70620	M10
33	...	Wld. pipe	SB-467	...	C70620	WM50
34	...	Smls. tube	SB-111	...	C70620	H55
35	...	Smls. pipe & tube	SB-466	...	C70620	H55
36	...	Wld. tube	SB-543	...	C70620	WC55
37	...	Finned wld. tube	SB-956	...	C70620	WC55
38	...	Wld. pipe	SB-467	...	C70620	Wld. fr. cold rld. strip
39	...	Smls. tube	SB-466	...	C71000	O60
40	...	Smls. tube	SB-466	...	C71000	O60
41	...	Smls. cond. tube	SB-111	...	C71000	O61
42	...	Smls. cond. tube	SB-111	...	C71000	O61
43	...	Finned tube	SB-359	...	C71000	O61
44	...	Finned tube	SB-359	...	C71000	O61
45	...	Smls. tube	SB-395	...	C71000	O61

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	>6	34	40	15	NP	NP	600	600	NFC-3	T5
2	>6	34	40	15	NP	NP	600	600	NFC-3	G5, T5
3	≤5	34	40	15	NP	400	NP	NP	NFC-3	...
4	≤5	34	40	15	NP	400	NP	NP	NFC-3	G5
5	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	...
6	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	G5
7	≤5	34	40	15	NP	NP	600	600	NFC-3	T5
8	≤5	34	40	15	NP	NP	600	600	NFC-3	G5, T5
9	...	34	40	15	NP	NP	600	600	NFC-3	T5
10	...	34	40	15	NP	NP	600	600	NFC-3	G5, T5
11	≤5	34	40	15	NP	400	NP	NP	NFC-3	...
12	≤5	34	40	15	NP	400	NP	NP	NFC-3	G5
13	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	...
14	≤5	34	40	15	NP	450 (Cl. 3 only)	NP	NP	NFC-3	G5
15	≤5	34	40	15	NP	NP	600	600	NFC-3	T5
16	≤5	34	40	15	NP	NP	600	600	NFC-3	G5, T5
17	...	34	40	15	600	400	NP	NP	NFC-3	G1, T5
18	...	34	40	15	600	400	NP	NP	NFC-3	G1, G5, T5
19	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	T5
20	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, T5
21	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G1, T5
22	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G1, G5, T5
23	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	T5
24	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, T5
25	≤4 ¹ / ₂	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T5, W11
26	≤4 ¹ / ₂	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
27	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G34, T5, W11
28	...	34	40	15	NP	450 (Cl. 3 only)	600	600	NFC-3	G5, G14, G34, T5, W11
29	...	34	40	15	NP	NP	600	NP	NFC-3	G14, G34, T5, W11
30	...	34	40	15	NP	NP	600	NP	NFC-3	G5, G14, G34, T5, W11
31	≤6	34	45	18	NP	NP	600	600	NFC-3	G34, T5
32	≤6	34	45	18	NP	NP	600	600	NFC-3	G5, G34, T5
33	≤4 ¹ / ₂	34	45	30	NP	NP	600	600	NFC-3	G14, G34, T5, W11
34	...	34	45	35	NP	450 (Cl. 3 only)	600	600	NFC-3	G33, T5, W3
35	...	34	45	35	NP	NP	600	600	NFC-3	G33, T5, W3
36	...	34	45	35	NP	450 (Cl. 3 only)	600	600	NFC-3	G14, G33, G34, T5, W10
37	...	34	45	35	NP	NP	600	NP	NFC-3	G14, G33, G34, T5, W10
38	≤4 ¹ / ₂	34	54	45	NP	NP	600	600	NFC-3	G14, G34, T5, W11
39	...	34	45	16	NP	700 (Cl. 3 only)	700	650	NFC-3	T7
40	...	34	45	16	NP	700 (Cl. 3 only)	700	650	NFC-3	G5, T7
41	...	34	45	16	700	700 (Cl. 3 only)	700	650	NFC-3	T7
42	...	34	45	16	700	700 (Cl. 3 only)	700	650	NFC-3	G5, T7
43	...	34	45	16	NP	700 (Cl. 3 only)	700	NP	NFC-3	T7
44	...	34	45	16	NP	700 (Cl. 3 only)	700	NP	NFC-3	G5, T7
45	...	34	45	16	NP	700 (Cl. 3 only)	700	650	NFC-3	T7

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
2	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
3	10.0	9.7	9.5	9.3	9.0	8.8	8.7	...	...	...	...	...	...	...	...	...	...	...
4	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
5	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...	...	...	...
6	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...
7	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
8	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
9	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
10	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
11	10.0	9.7	9.5	9.3	9.0	8.8	8.7	...	...	...	...	...	...	...	...	...	...	...
12	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
13	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...	...	...	...
14	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...
15	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
16	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
17	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
18	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
19	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
20	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
21	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
22	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
23	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
24	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...	...
25	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
26	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
27	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
28	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
29	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
30	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	6.3	5.7	4.3	...	...	...	...	...	...	...
31	12.0	11.7	11.4	11.1	10.9	10.6	10.4	10.2	8.0	7.0	6.0	...	...	...	...	...	...	...
32	12.0	12.0	12.0	12.0	12.0	12.0	12.0	11.8	8.0	7.0	6.0	...	...	...	...	...	...	...
33	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
34	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
35	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	8.0	7.0	6.0	...	...	...	...	...	...	...
36	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
37	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
38	8.5	8.3	8.1	7.9	7.7	7.5	7.4	7.2	6.3	5.7	4.3	...	...	...	...	...	...	...
39	10.7	10.4	10.2	10.0	9.7	9.4	9.2	8.9	8.7	8.5	8.4	7.7	7.0	...	...	...	...	...
40	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	8.4	7.7	7.0	...	...	...	...	...
41	10.7	10.4	10.2	10.0	9.7	9.4	9.2	8.9	8.7	8.5	8.4	7.7	7.0	...	...	...	...	...
42	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	8.4	7.7	7.0	...	...	...	...	...
43	10.7	10.4	10.2	10.0	9.7	9.4	9.2	8.9	8.7	8.5	8.4	7.7	7.0	...	...	...	...	...
44	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	8.4	7.7	7.0	...	...	...	...	...
45	10.7	10.4	10.2	10.0	9.7	9.4	9.2	8.9	8.7	8.5	8.4	7.7	7.0	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	...	Smls. tube	SB-395	...	C71000	O61
2	...	Wld. pipe	SB-467	...	C71500	W061
3	...	Wld. pipe	SB-467	...	C71500	W061
4	...	Plate, sheet	SB-171	...	C71500	M10, M20
5	...	Plate, sheet	SB-171	...	C71500	M10, M20
6	...	Plate, sheet	SB-171	...	C71500	O20, O25
7	...	Plate, sheet	SB-171	...	C71500	O20, O25
8	...	Plate, sheet	SB-171	...	C71500	M10, M20
9	...	Plate, sheet	SB-171	...	C71500	M10, M20
10	...	Plate, sheet	SB-171	...	C71500	O20, O25
11	...	Plate, sheet	SB-171	...	C71500	O20, O25
12	...	Wld. pipe	SB-467	...	C71500	W061
13	...	Wld. pipe	SB-467	...	C71500	W061
14	...	Smls. pipe & tube	SB-466	...	C71500	O60
15	...	Smls. pipe & tube	SB-466	...	C71500	O60
16	...	Smls. cond. tube	SB-111	...	C71500	O61
17	...	Smls. cond. tube	SB-111	...	C71500	O61
18	...	Finned tube	SB-359	...	C71500	O61
19	...	Finned tube	SB-359	...	C71500	O61
20	...	Smls. U-bend tube	SB-395	...	C71500	O61
21	...	Smls. U-bend tube	SB-395	...	C71500	O61
22	...	Wld. cond. tube	SB-543	...	C71500	W061
23	...	Wld. cond. tube	SB-543	...	C71500	W061
24	...	Finned wld. cond. tube	SB-956	...	C71500	W061
25	...	Finned wld. cond. tube	SB-956	...	C71500	W061
26	...	Smls. cond. tube	SB-111	...	C71500	HR50
27	...	Smls. U-bend tube	SB-395	...	C71500	HR50
28	...	Wld. pipe	SB-467	...	C71520	W061
29	...	Wld. pipe	SB-467	...	C71520	W061
30	...	Forgings	SB-283	...	C71520	M10
31	...	Forgings	SB-283	...	C71520	M10
32	...	Plate, sheet	SB-171	...	C71520	M10, M20
33	...	Plate, sheet	SB-171	...	C71520	M10, M20
34	...	Forgings	SB-283	...	C71520	O20
35	...	Forgings	SB-283	...	C71520	O20
36	...	Plate, sheet	SB-171	...	C71520	O20, O25
37	...	Plate, sheet	SB-171	...	C71520	O20, O25
38	...	Forgings	SB-283	...	C71520	M10
39	...	Forgings	SB-283	...	C71520	M10
40	...	Plate, sheet	SB-171	...	C71520	M10, M20
41	...	Plate, sheet	SB-171	...	C71520	M10, M20
42	...	Plate, sheet	SB-171	...	C71520	O20, O25
43	...	Plate, sheet	SB-171	...	C71520	O20, O25
44	...	Wld. pipe	SB-467	...	C71520	W061
45	...	Wld. pipe	SB-467	...	C71520	W061

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	34	45	16	NP	700 (Cl. 3 only)	700	650	NFC-3	G5, T7
2	>4 ¹ / ₂	34	45	15	NP	600 (Cl. 3 only)	NP	NP	NFC-3	G14, W11
3	>4 ¹ / ₂	34	45	15	NP	600 (Cl. 3 only)	NP	NP	NFC-3	G5, G14, W11
4	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	...
5	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	G5
6	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	...
7	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	G5
8	≤2.5	34	50	20	NP	700	700	650	NFC-4	...
9	≤2.5	34	50	20	NP	700	700	650	NFC-4	G5
10	≤2.5	34	50	20	NP	700	700	650	NFC-4	...
11	≤2.5	34	50	20	NP	700	700	650	NFC-4	G5
12	≤4 ¹ / ₂	34	50	20	NP	600 (Cl. 3 only)	NP	NP	NFC-4	G14
13	≤4 ¹ / ₂	34	50	20	NP	600 (Cl. 3 only)	NP	NP	NFC-4	G5, G14
14	...	34	52	18	NP	700	700	650	NFC-4	...
15	...	34	52	18	NP	700	700	650	NFC-4	G5
16	...	34	52	18	700	700	700	650	NFC-4	G1
17	...	34	52	18	700	700	700	650	NFC-4	G1, G5
18	...	34	52	18	NP	700 (Cl. 3 only)	700	NP	NFC-4	G1
19	...	34	52	18	NP	700 (Cl. 3 only)	700	NP	NFC-4	G1, G5
20	...	34	52	18	NP	700 (Cl. 3 only)	700	650	NFC-4	...
21	...	34	52	18	NP	700 (Cl. 3 only)	700	650	NFC-4	G5
22	...	34	52	18	NP	600 (Cl. 3 only)	600	600	NFC-4	G14, W11
23	...	34	52	18	NP	600 (Cl. 3 only)	600	600	NFC-4	G5, G14, W11
24	...	34	52	18	NP	NP	600	NP	NFC-4	G14, W11
25	...	34	52	18	NP	NP	600	NP	NFC-4	G5, G14, W11
26	...	34	72	50	NP	700	800	650	NFC-4	T9, W3
27	...	34	72	50	NP	700	800	650	NFC-8	T9, W3
28	>4 ¹ / ₂	34	45	15	NP	600 (Cl. 3 only)	NP	NP	NFC-3	G14, W11
29	>4 ¹ / ₂	34	45	15	NP	600 (Cl. 3 only)	NP	NP	NFC-3	G5, G14, W11
30	>6	34	45	18	NP	NP	700	650	NFC-4	...
31	>6	34	45	18	NP	NP	700	650	NFC-4	G5
32	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	...
33	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	G5
34	...	34	45	18	NP	NP	700	650	NFC-4	...
35	...	34	45	18	NP	NP	700	650	NFC-4	G5
36	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	...
37	2.5 < t ≤ 5	34	45	18	NP	700	700	650	NFC-4	G5
38	≤6	34	50	20	NP	NP	700	650	NFC-4	...
39	≤6	34	50	20	NP	NP	700	650	NFC-4	G5
40	≤2.5	34	50	20	NP	700	700	650	NFC-4	...
41	≤2.5	34	50	20	NP	700	700	650	NFC-4	G5
42	≤2.5	34	50	20	NP	700	700	650	NFC-4	...
43	≤2.5	34	50	20	NP	700	700	650	NFC-4	G5
44	≤4 ¹ / ₂	34	50	20	NP	600 (Cl. 3 only)	NP	NP	NFC-4	G14
45	≤4 ¹ / ₂	34	50	20	NP	600 (Cl. 3 only)	NP	NP	NFC-4	G5, G14

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	10.7	8.4	7.7	7.0	...	...	...	...	...
2	8.5	8.2	8.0	7.8	7.6	7.5	7.3	7.2	7.0	6.9	6.8	...	...	...	...	...	...	...
3	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	...	...	...	...	...	...	...
4	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
5	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
6	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
7	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
8	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	10.4	...	...	...	...	...
9	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...
10	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	10.4	...	...	...	...	...
11	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...
12	11.3	10.9	10.7	10.4	10.2	10.0	9.7	9.6	9.4	9.2	9.1	...	...	...	...	...	...	...
13	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	...	...	...	...	...	...	...
14	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
15	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
16	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
17	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
18	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
19	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
20	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
21	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
22	10.2	9.8	9.6	9.4	9.2	9.0	8.8	8.6	8.4	8.3	8.2	...	...	...	...	...	...	...
23	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	...	...	...	...	...	...	...
24	10.2	9.8	9.6	9.4	9.2	9.0	8.8	8.6	8.4	8.3	8.2	...	...	...	...	...	...	...
25	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	...	...	...	...	...	...	...
26	20.6	20.6	20.6	20.6	20.6	20.3	20.0	19.7	19.4	19.2	18.9	18.7	18.4	18.0	8.5	...	...	...
27	20.6	20.6	20.6	20.6	20.6	20.3	20.0	19.7	19.4	19.2	18.9	18.7	18.4	18.0	8.5	...	...	...
28	8.5	8.2	8.0	7.8	7.6	7.5	7.3	7.2	7.0	6.9	6.8	...	...	...	...	...	...	...
29	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	8.5	...	...	...	...	...	...	...
30	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
31	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
32	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
33	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
34	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
35	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
36	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
37	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
38	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	10.4	...	...	...	...	...
39	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...
40	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	10.4	...	...	...	...	...
41	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...
42	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	10.4	...	...	...	...	...
43	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...
44	11.3	10.9	10.7	10.4	10.2	10.0	9.7	9.6	9.4	9.2	9.1	...	...	...	...	...	...	...
45	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Smls. pipe & tube	SB-466	...	C71520	O60
2	...	Smls. pipe & tube	SB-466	...	C71520	O60
3	...	Smls. cond. tube	SB-111	...	C71520	O61
4	...	Smls. cond. tube	SB-111	...	C71520	O61
5	...	Finned tube	SB-359	...	C71520	O61
6	...	Finned tube	SB-359	...	C71520	O61
7	...	Smls. U-bend tube	SB-395	...	C71520	O61
8	...	Smls. U-bend tube	SB-395	...	C71520	O61
9	...	Wld. cond. tube	SB-543	...	C71520	W061
10	...	Wld. cond. tube	SB-543	...	C71520	W061
11	...	Finned wld. cond. tube	SB-956	...	C71520	W061
12	...	Finned wld. cond. tube	SB-956	...	C71520	W061
13	...	Smls. cond. tube	SB-111	...	C71520	HR50
14	...	Smls. U-bend tube	SB-395	...	C71520	HR50
15	...	Smls. cond. tube	SB-111	...	C72200	O61
(25) 16	...	Castings	SB-62	...	C83600	M01
(25) 17	...	Castings	SB-62	...	C83600	M01
(25) 18	...	Castings	SB-61	...	C92200	M01
(25) 19	...	Castings	SB-61	...	C92200	M01
(25) 20	...	Castings	SB-584	...	C92200	M01
(25) 21	...	Castings	SB-584	...	C92200	M01
22	...	Castings	SB-584	...	C93700	M01
23	...	Castings	SB-584	...	C93700	M01
24	...	Castings	SB-148	...	C95200	M01
25	...	Castings	SB-271	...	C95200	M02
26	...	Castings	SB-505	...	C95200	M07
27	...	Castings	SB-148	...	C95400	M01
28	...	Castings	SB-271	...	C95400	M02
29	...	Castings	SB-148	...	C95800	M01
30	...	Castings	SB-148	...	C95820	M01
(25) 31	...	Castings	SB-369	...	C96200	M01
32	...	Castings	SB-584	...	C97600	M01
33	...	Castings	SB-584	...	C97600	M01
34	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed
35	99Ni	Smls. & wld. fittings	SB-366	...	N02200	Annealed
36	99Ni	Bar, rod	SB-160	...	N02200	Annealed
37	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed
38	99Ni	Plate, sheet, strip	SB-162	...	N02200	Annealed
39	99Ni	Smls. tube	SB-163	...	N02200	Annealed
40	99Ni	Plate, sheet, strip	SB-162	...	N02200	As rolled
41	99Ni	Bar, rod	SB-160	...	N02200	Hot rolled
42	99Ni	Smls. pipe & tube	SB-161	...	N02200	Stress rel.
43	99Ni	Smls. tube	SB-163	...	N02200	Stress rel.
44	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
45	99Ni-Low C	Smls. & wld. fittings	SB-366	...	N02201	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	34	52	18	NP	700	700	650	NFC-4	...
2	...	34	52	18	NP	700	700	650	NFC-4	G5
3	...	34	52	18	700	700	700	650	NFC-4	G1
4	...	34	52	18	700	700	700	650	NFC-4	G1, G5
5	...	34	52	18	NP	700 (Cl. 3 only)	700	NP	NFC-4	G1
6	...	34	52	18	NP	700 (Cl. 3 only)	700	NP	NFC-4	G1, G5
7	...	34	52	18	NP	700 (Cl. 3 only)	700	650	NFC-4	...
8	...	34	52	18	NP	700 (Cl. 3 only)	700	650	NFC-4	G5
9	...	34	52	18	NP	600 (Cl. 3 only)	600	600	NFC-4	G14, W11
10	...	34	52	18	NP	600 (Cl. 3 only)	600	600	NFC-4	G5, G14, W11
11	...	34	52	18	NP	NP	600	NP	NFC-4	G14, W11
12	...	34	52	18	NP	NP	600	NP	NFC-4	G5, G14, W11
13	...	34	72	50	NP	700	800	650	NFC-4	T9, W3
14	...	34	72	50	NP	700	800	650	NFC-8	T9, W3
15	...	34	45	16	NP	NP	150	150	NFC-3	...
16	...	...	30	14	450	450 (Cl. 3 only)	450	450	NFC-1	G3, G15, W14
17	...	...	30	14	450	450 (Cl. 3 only)	450	450	NFC-1	G3, G5, G15, T19, W14
18	...	...	34	16	550	500 (Cl. 3 only)	550	550	NFC-1	G3, G15, T5, W14
19	...	...	34	16	550	500 (Cl. 3 only)	550	550	NFC-1	G3, G5, G15, T5, W14
20	...	...	34	16	NP	500 (Cl. 3 only)	550	550	NFC-1	G15, T5
21	...	...	34	16	NP	500 (Cl. 3 only)	550	550	NFC-1	G5, G15, T5
22	...	...	30	12	NP	400 (SPT)	400	400	NFC-1	G15, W8
23	...	...	30	12	NP	400 (SPT)	400	400	NFC-1	G5, G15, W8
24	...	35	65	25	550	500 (Cl. 3 only)	600	600	NFC-4	G15, T6
25	...	35	65	25	NP	500 (Cl. 3 only)	600	600	NFC-4	G15, T6
26	...	35	68	26	NP	500 (Cl. 3 only)	NP	NP	NFC-4	G15
27	...	35	75	30	550	400 (Cl. 3 only)	600	600	NFC-4	G15, T19
28	...	35	75	30	NP	400 (Cl. 3 only)	NP	NP	NFC-4	G15
29	...	35	85	35	NP	400 (Cl. 3 only)	NP	400	NFC-4	G15
30	...	35	94	39	NP	NP	400	400	NFC-4	G15
31	...	34	45	25	NP	200 (Cl. 3 only)	NP	NP	NFC-3	G15
32	...	...	40	17	NP	NP	300	300	NFC-1	G15, W8
33	...	...	40	17	NP	NP	300	300	NFC-1	G5, G15, W8
34	>5 O.D.	41	55	12	NP	600 (Cl. 3 only)	600	600	NFN-2	...
35	...	41	55	12	NP	NP	600	600	NFN-2	W12
36	...	41	55	15	NP	600 (Cl. 3 only)	600	600	NFN-2	...
37	≤5 O.D.	41	55	15	NP	600 (Cl. 3 only)	600	600	NFN-2	...
38	...	41	55	15	NP	600 (Cl. 3 only)	600	600	NFN-2	...
39	...	41	55	15	NP	600 (Cl. 3 only)	600	600	NFN-2	...
40	...	41	55	20	NP	600 (Cl. 3 only)	600	600	NFN-2	G20
41	...	41	60	15	NP	600 (Cl. 3 only)	600	600	NFN-2	...
42	...	41	65	40	NP	600 (Cl. 3 only)	600	600	NFN-25	G29
43	...	41	65	40	NP	600 (Cl. 3 only)	600	600	NFN-25	G29
44	>5 O.D.	41	50	10	NP	800 (Cl. 3 only)	1200	650	NFN-1	T10
45	...	41	50	10	800 (Cl. 3 only)	NP	1150	650	NFN-1	T10, W5, W12

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
2	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
3	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
4	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
5	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
6	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
7	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	9.4	...	...	...	...	...
8	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...
9	10.2	9.8	9.6	9.4	9.2	9.0	8.8	8.6	8.4	8.3	8.2	...	...	...	...	...	...	...
10	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	...	...	...	...	...	...	...
11	10.2	9.8	9.6	9.4	9.2	9.0	8.8	8.6	8.4	8.3	8.2	...	...	...	...	...	...	...
12	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	...	...	...	...	...	...	...
13	20.6	20.6	20.6	20.6	20.6	20.3	20.0	19.7	19.4	19.2	18.9	18.7	18.4	18.0	8.5	...	...	...
14	20.6	20.6	20.6	20.6	20.6	20.3	20.0	19.7	19.4	19.2	18.9	18.7	18.4	18.0	8.5	...	...	...
15	10.7	10.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	8.6	8.6	8.4	8.1	7.8	7.6	7.3	7.0	...	...	...	...	...	...	...	...	...	...
17	8.6	8.6	8.6	8.5	8.4	8.2	8.1	7.5	...	...	...	...	...	...	...	...	...	...
18	9.7	9.7	9.6	9.2	9.0	8.9	8.8	8.7	7.4	5.0	...	...	...	...	...	...	...	...
19	9.7	9.7	9.7	9.7	9.7	9.7	9.5	9.1	7.4	5.0	...	...	...	...	...	...	...	...
20	9.7	9.7	9.6	9.2	9.0	8.9	8.8	8.7	7.4	5.0	...	...	...	...	...	...	...	...
21	9.7	9.7	9.7	9.7	9.7	9.7	9.5	9.1	7.4	5.0	...	...	...	...	...	...	...	...
22	8.0	7.4	7.1	7.0	6.8	6.7	6.7	...	...	...	...	...	...	...	...	...	...	...
23	8.0	8.0	8.0	8.0	7.9	7.7	7.4	...	...	...	...	...	...	...	...	...	...	...
24	16.7	15.7	15.2	14.8	14.5	14.3	14.2	14.2	14.2	11.7	7.4	...	...	...	...	...	...	...
25	16.7	15.7	15.2	14.8	14.5	14.3	14.2	14.2	14.2	11.7	7.4	...	...	...	...	...	...	...
26	17.3	16.3	15.8	15.4	15.1	14.9	14.8	14.7	14.7	...	...	...	...	...	...	...	...	...
27	20.0	19.6	19.5	19.4	19.3	19.3	19.3	16.0	13.9	11.0	8.5	...	...	...	...	...	...	...
28	20.0	19.6	19.5	19.4	19.3	19.3	19.3	...	...	...	...	...	...	...	...	...	...	...
29	23.3	23.0	22.9	22.8	22.7	22.4	21.9	...	...	...	...	...	...	...	...	...	...	...
30	26.0	25.6	25.5	25.4	25.3	24.8	24.3	...	...	...	...	...	...	...	...	...	...	...
31	12.9	12.9	12.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	11.3	10.2	9.6	9.1	8.7	...	...	...	...	...	...	...	...	...	...	...	...	...
33	11.3	11.3	11.3	11.1	11.0	...	...	...	...	...	...	...	...	...	...	...	...	...
34	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	...	...	...	...	...	...
35	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	...	...	...	...	...	...
36	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...	...	...	...
37	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...	...	...	...
38	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...	...	...	...
39	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...	...	...	...
40	13.3	...	13.3	...	13.3	...	13.3	...	12.6	...	11.5	...	...	...	...	...	...	...
41	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...	...	...	...
42	18.6	...	18.6	...	18.6	...	18.6	...	18.3	...	17.7	...	...	...	...	...	...	...
43	18.6	...	18.6	...	18.6	...	18.6	...	18.3	...	17.7	...	...	...	...	...	...	...
44	6.7	...	6.4	...	6.3	...	6.2	...	6.2	...	6.2	6.2	6.2	6.1	6.0	5.8	4.5	3.7
45	6.7	...	6.4	...	6.3	...	6.2	...	6.2	...	6.2	6.2	6.2	6.1	6.0	5.8	4.5	3.7

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	
44	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...	...	...	
45	3.0	2.4	2.0	1.5	...	...	...	...	...	...	...	...	...	...	...	...	

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	99Ni-Low C	Bar, rod	SB-160	...	N02201	Hot rolled/ann.
2	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
3	99Ni-Low C	Smls. tube	SB-163	...	N02201	Annealed
4	99Ni-Low C	Plate, sheet, strip	SB-162	...	N02201	Hot rolled/ann.
5	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Stress rel.
6	99Ni-Low C	Smls. pipe & tube	SB-163	...	N02201	Stress rel.
7	67Ni-30Cu	Bar, rod	SB-164	...	N04400	HW or CW ann.
8	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
9	67Ni-30Cu	Forgings	SB-564	...	N04400	Annealed
10	67Ni-30Cu	Plate	SB-127	...	N04400	Annealed
11	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Annealed
12	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
13	67Ni-30Cu	Smls. & wld. fittings	SB-366	...	N04400	Annealed
14	67Ni-30Cu	Hexagons, rings, discs	SB-164	...	N04400	Hot worked
15	67Ni-30Cu	Plate	SB-127	...	N04400	As rolled
16	67Ni-30Cu	Rounds, squares, rectangles	SB-164	...	N04400	Hot worked
17	67Ni-30Cu	Rounds, squares, rectangles	SB-164	...	N04400	Hot worked
18	67Ni-30Cu	Hexagon	SB-164	...	N04400	Hot worked
19	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Stress rel.
20	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Stress rel.
21	67Ni-30Cu-S	Bar	SB-164	...	N04405	Annealed
22	67Ni-30Cu-S	Bar	SB-164	...	N04405	Hot worked
23	47Ni-22Cr-9Mo-18Fe	Plate, sheet, strip	SB-435	...	N06002	Annealed
24	47Ni-22Cr-9Mo-18Fe	Plate, sheet, strip	SB-435	...	N06002	Annealed
25	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...	N06002	Annealed
26	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...	N06002	Annealed
27	47Ni-22Cr-9Mo-18Fe	Smls. & wld. fittings	SB-366	...	N06002	Annealed
28	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.
29	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.
30	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...	N06002	Solution ann.
31	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...	N06002	Solution ann.
32	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.
33	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.
34	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
35	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
36	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
37	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
38	47Ni-22Cr-19Fe-6Mo	Smls. & wld. fittings	SB-366	...	N06007	Annealed
39	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
40	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
41	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
42	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
43	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...	N06007	Solution ann.
44	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...	N06007	Solution ann.
45	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...	N06007	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	41	50	10	NP	800 (Cl. 3 only)	1200	650	NFN-1	T10
2	≤5 O.D.	41	50	12	NP	800 (Cl. 3 only)	1200	650	NFN-1	T9
3	...	41	50	12	NP	800 (Cl. 3 only)	1200	650	NFN-1	T9
4	...	41	50	12	NP	800 (Cl. 3 only)	1200	650	NFN-1	T9
5	...	41	60	30	NP	600 (Cl. 3 only)	600	600	NFN-1	...
6	...	41	60	30	NP	800 (Cl. 3 only)	900	650	NFN-1	...
7	All	42	70	25	NP	800	900	650	NFN-3	T10
8	>5 O.D.	42	70	25	NP	800	900	650	NFN-3	T10
9	...	42	70	25	NP	800	900	650	NFN-3	T10
10	...	42	70	28	NP	800	900	650	NFN-3	T10
11	≤3	42	70	28	NP	800	900	650	NFN-3	T10
12	≤5 O.D.	42	70	28	NP	800	900	650	NFN-3	T10
13	...	42	70	28	NP	800	900	650	NFN-3	T10, W5, W12
14	$2\frac{1}{8} < t \leq 4$	42	75	30	NP	800	900	650	NFN-3	T9
15	...	42	75	40	NP	800	900	650	NFN-3	G12, G20, T9
16	$12 < t \leq 14$	42	75	40	NP	NP	900	650	NFN-3	T9
17	≤12	42	80	40	NP	800 (Cl. 3 only)	900	650	NFN-3	T9
18	≤2 $\frac{1}{8}$	42	80	40	NP	800 (Cl. 3 only)	900	650	NFN-3	T9
19	...	42	85	55	NP	800	800	650	NFN-3	G11, T8
20	...	42	85	55	NP	800	500	500	NFN-3	G5, G21, T8
21	...	42	70	25	NP	800	900	650	NFN-3	T10
22	...	42	75	35	NP	800	900	650	NFN-3	T10
23	...	43	95	35	NP	800	1650	650	NFN-15	G4, G5, T15
24	...	43	95	35	NP	NP	1650	650	NFN-15	G4, T16
25	...	43	95	35	NP	800	1650	650	NFN-15	G4, G5, G13, T15
26	...	43	95	35	NP	NP	1650	650	NFN-15	G4, G13, T16
27	...	43	100	40	NP	800	1650	650	NFN-15	G4, G5, T15, W5, W12
28	...	43	100	40	NP	800	1650	650	NFN-15	G4, G5, G14, T14, W5
29	...	43	100	40	NP	NP	1650	650	NFN-15	G4, G14, T16
30	...	43	100	40	NP	800	1650	650	NFN-15	G4, G5, T14
31	...	43	100	40	NP	NP	1650	650	NFN-15	G4, T16
32	...	43	100	40	NP	800	1650	650	NFN-15	G4, G5, G14, T14, W5
33	...	43	100	40	NP	NP	1650	650	NFN-15	G4, G14, T16
34	> $\frac{3}{4}$	45	85	30	NP	NP	1000	650	NFN-11	...
35	> $\frac{3}{4}$	45	85	30	NP	NP	1000	650	NFN-11	G5
36	> $\frac{3}{4}$	45	85	30	NP	NP	1000	650	NFN-11	...
37	> $\frac{3}{4}$	45	85	30	NP	NP	1000	650	NFN-11	G5
38	...	45	90	35	NP	NP	1000	650	NFN-11	G5, W12
39	≤ $\frac{3}{4}$	45	90	35	NP	NP	1000	650	NFN-11	...
40	≤ $\frac{3}{4}$	45	90	35	NP	NP	1000	650	NFN-11	G5
41	≤ $\frac{3}{4}$	45	90	35	NP	NP	1000	650	NFN-11	...
42	≤ $\frac{3}{4}$	45	90	35	NP	NP	1000	650	NFN-11	G5
43	...	45	90	35	NP	NP	1000	650	NFN-11	G14
44	...	45	90	35	NP	NP	1000	650	NFN-11	G5, G14
45	...	45	90	35	NP	NP	1000	650	NFN-11	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	6.7	...	6.4	...	6.3	...	6.2	...	6.2	...	6.2	6.2	6.2	6.1	6.0	5.8	4.5	3.7
2	8.0	...	7.7	...	7.5	...	7.5	...	7.5	...	7.5	7.5	7.4	7.4	7.2	5.8	4.5	3.7
3	8.0	...	7.7	...	7.5	...	7.5	...	7.5	...	7.5	7.5	7.4	7.4	7.2	5.8	4.5	3.7
4	8.0	...	7.7	...	7.5	...	7.5	...	7.5	...	7.5	7.5	7.4	7.4	7.2	5.8	4.5	3.7
5	17.1	...	17.1	...	17.0	...	17.0	...	16.8	...	16.3	...	...	...	...	...	...	...
6	17.1	...	17.1	...	17.0	...	17.0	...	16.8	...	16.3	14.0	13.4	12.8	12.1	11.7	11.1	...
7	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.0	12.9	12.7	11.0	8.0	...
8	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.0	12.9	12.7	11.0	8.0	...
9	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.0	12.9	12.7	11.0	8.0	...
10	18.7	...	16.4	...	15.2	...	14.7	...	14.7	...	14.7	14.7	14.6	14.5	14.3	11.0	8.0	...
11	18.7	...	16.4	...	15.2	...	14.7	...	14.7	...	14.7	14.7	14.6	14.5	14.3	11.0	8.0	...
12	18.7	...	16.4	...	15.2	...	14.7	...	14.7	...	14.7	14.7	14.6	14.5	14.3	11.0	8.0	...
13	18.7	...	16.4	...	15.2	...	14.7	...	14.7	...	14.7	14.7	14.6	14.5	14.3	11.0	8.0	...
14	20.0	...	19.4	...	18.6	...	17.9	...	17.6	...	17.3	17.2	17.0	16.8	14.5	8.5	4.0	...
15	21.4	...	21.4	...	21.4	...	21.4	...	21.4	...	21.4	21.4	20.7	18.5	14.5	8.5	4.0	...
16	21.4	...	21.4	...	21.4	...	21.4	...	21.4	...	21.4	21.4	20.7	18.5	14.5	8.5	4.0	...
17	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.8	22.0	18.5	14.5	8.5	4.0	...
18	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.8	22.0	18.5	14.5	8.5	4.0	...
19	24.3	...	24.3	...	24.3	...	24.3	...	24.3	...	23.9	23.5	22.8	18.0	12.7	...	...	...
20	24.3	...	24.3	...	24.3	...	24.3	...	24.3	...	23.9	23.5	22.8	18.0	12.7	...	...	...
21	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.0	12.9	12.7	11.0	8.0	...
22	21.4	...	21.4	...	21.4	...	20.9	...	20.5	...	20.2	20.1	19.8	18.5	14.5	8.5	4.0	...
23	23.3	...	23.3	...	23.3	...	23.3	...	22.3	...	21.2	20.7	20.3	20.1	19.9	19.7	19.6	19.5
24	23.3	...	21.0	...	19.2	...	17.7	...	16.5	...	15.7	15.3	15.1	14.9	14.7	14.6	14.5	14.4
25	23.3	...	23.3	...	23.3	...	23.3	...	22.3	...	21.2	20.7	20.3	20.1	19.9	19.7	19.6	19.5
26	23.3	...	21.0	...	19.2	...	17.7	...	16.5	...	15.7	15.3	15.1	14.9	14.7	14.6	14.5	14.4
27	26.7	...	26.7	...	26.7	...	26.7	...	25.5	...	24.2	...	23.3	...	22.7	...	22.4	...
28	22.7	...	22.7	...	22.7	...	22.7	...	21.7	...	20.5	20.1	19.8	19.5	19.3	19.1	19.0	18.9
29	22.7	...	20.4	...	18.7	...	17.2	...	16.1	...	15.2	14.9	14.6	14.4	14.3	14.2	14.1	14.0
30	26.7	...	26.7	...	26.7	...	26.7	...	25.5	...	24.2	23.7	23.3	22.9	22.7	22.5	22.4	22.2
31	26.7	...	24.0	...	22.0	...	20.3	...	18.9	...	17.9	17.5	17.2	17.0	16.8	16.7	16.6	16.5
32	22.7	...	22.7	...	22.7	...	22.7	...	21.7	...	20.5	20.1	19.8	19.5	19.3	19.1	19.0	18.9
33	22.7	...	20.4	...	18.7	...	17.2	...	16.1	...	15.2	14.9	14.6	14.4	14.3	14.2	14.1	14.0
34	20.0	...	18.0	...	16.7	...	15.7	...	14.9	...	14.4	14.2	14.1	14.0	13.9	13.8	13.7	13.6
35	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	19.5	19.2	19.0	18.8	18.7	18.6	18.5	18.4
36	20.0	...	18.0	...	16.7	...	15.7	...	14.9	...	14.4	14.2	14.1	14.0	13.9	13.8	13.7	13.6
37	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	19.5	19.2	19.0	18.8	18.7	18.6	18.5	18.4
38	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.7	...	22.2	...	21.8	...	21.6	...
39	23.3	...	21.0	...	19.5	...	18.3	...	17.4	...	16.8	16.6	16.4	16.3	16.2	16.1	16.0	15.9
40	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.7	22.4	22.2	22.0	21.8	21.7	21.6	21.5
41	23.3	...	21.0	...	19.5	...	18.3	...	17.4	...	16.8	16.6	16.4	16.3	16.2	16.1	16.0	15.9
42	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.7	22.4	22.2	22.0	21.8	21.7	21.6	21.5
43	19.8	...	17.8	...	16.5	...	15.5	...	14.8	...	14.3	14.1	14.0	13.8	13.7	13.7	13.6	13.5
44	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.3	19.1	18.8	18.7	18.5	18.4	18.3	18.3
45	23.3	...	21.0	...	19.5	...	18.3	...	17.4	...	16.8	16.6	16.4	16.3	16.2	16.1	16.0	15.9

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...	...	...	...
2	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...	...	...	...
3	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...	...	...	...
4	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	19.4	19.3	17.5	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
24	14.3	14.3	14.2	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
25	19.4	19.3	17.5	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
26	14.3	14.3	14.2	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
27	22.1	...	17.5	...	11.3	...	7.7	...	4.8	...	3.0	...	1.7	1.2	...	...	...
28	18.8	18.5	14.9	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.4	1.0	...	...	...
29	13.9	13.9	13.8	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.4	1.0	...	...	...
30	22.1	21.7	17.5	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
31	16.4	16.3	16.2	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2	...	...	...
32	18.8	18.5	14.9	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.4	1.0	...	...	...
33	13.9	13.9	13.8	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.4	1.0	...	...	...
34	13.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	18.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	13.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	18.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	21.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	15.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	21.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	15.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	21.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	13.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	18.2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	15.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...	N06007	Solution ann.
2	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...	N06007	Solution ann.
3	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...	N06007	Solution ann.
4	55Ni-21Cr-13.5Mo	Smls. & wld. fittings	SB-366	...	N06022	Solution ann.
5	55Ni-21Cr-13.5Mo	Forgings	SB-462	...	N06022	Solution ann.
6	55Ni-21Cr-13.5Mo	Forgings	SB-462	...	N06022	Solution ann.
7	55Ni-21Cr-13.5Mo	Forgings	SB-564	...	N06022	Solution ann.
8	55Ni-21Cr-13.5Mo	Forgings	SB-564	...	N06022	Solution ann.
9	55Ni-21Cr-13.5Mo	Rod	SB-574	...	N06022	Solution ann.
10	55Ni-21Cr-13.5Mo	Rod	SB-574	...	N06022	Solution ann.
11	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...	N06022	Solution ann.
12	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...	N06022	Solution ann.
13	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...	N06022	Solution ann.
14	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...	N06022	Solution ann.
15	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...	N06022	Solution ann.
16	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...	N06022	Solution ann.
17	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...	N06022	Solution ann.
18	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...	N06022	Solution ann.
19	60Ni-25Cr-9.5Fe-2.1Al	Smls. tube	SB-163	...	N06025	Annealed
20	60Ni-25Cr-9.5Fe-2.1Al	Smls. tube	SB-163	...	N06025	Annealed
21	60Ni-25Cr-9.5Fe-2.1Al	Plate, sheet, strip	SB-168	...	N06025	Annealed
22	60Ni-25Cr-9.5Fe-2.1Al	Plate, sheet, strip	SB-168	...	N06025	Annealed
23	60Ni-25Cr-9.5Fe-2.1Al	Wrought fittings	SB-366	...	N06025	Annealed
24	60Ni-25Cr-9.5Fe-2.1Al	Wrought fittings	SB-366	...	N06025	Annealed
25	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-462	...	N06025	Annealed
26	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-462	...	N06025	Annealed
27	60Ni-25Cr-9.5Fe-2.1Al	Wld. tube	SB-516	...	N06025	Annealed
28	60Ni-25Cr-9.5Fe-2.1Al	Wld. tube	SB-516	...	N06025	Annealed
29	60Ni-25Cr-9.5Fe-2.1Al	Wld. pipe	SB-517	...	N06025	Annealed
30	60Ni-25Cr-9.5Fe-2.1Al	Wld. pipe	SB-517	...	N06025	Annealed
31	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-564	...	N06025	Annealed
32	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-564	...	N06025	Annealed
33	60Ni-25Cr-9.5Fe-2.1Al	Bar	SB-166	...	N06025	HW or CW ann.
34	60Ni-25Cr-9.5Fe-2.1Al	Bar	SB-166	...	N06025	HW or CW ann.
35	60Ni-25Cr-9.5Fe-2.1Al	Smls. pipe & tube	SB-167	...	N06025	HW or CW ann.
36	60Ni-25Cr-9.5Fe-2.1Al	Smls. pipe & tube	SB-167	...	N06025	HW or CW ann.
37	40Ni-29Cr-15Fe-5Mo	Smls. & wld. fittings	SB-366	...	N06030	Solution ann.
38	40Ni-29Cr-15Fe-5Mo	Forgings	SB-462	...	N06030	Solution ann.
39	40Ni-29Cr-15Fe-5Mo	Forgings	SB-462	...	N06030	Solution ann.
40	40Ni-29Cr-15Fe-5Mo	Rod	SB-581	...	N06030	Solution ann.
41	40Ni-29Cr-15Fe-5Mo	Rod	SB-581	...	N06030	Solution ann.
42	40Ni-29Cr-15Fe-5Mo	Plate, sheet, strip	SB-582	...	N06030	Solution ann.
43	40Ni-29Cr-15Fe-5Mo	Plate, sheet, strip	SB-582	...	N06030	Solution ann.
44	40Ni-29Cr-15Fe-5Mo	Wld. pipe	SB-619	...	N06030	Solution ann.
45	40Ni-29Cr-15Fe-5Mo	Wld. pipe	SB-619	...	N06030	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	90	35	NP	NP	1000	650	NFN-11	G5
2	...	45	90	35	NP	NP	1000	650	NFN-11	G14
3	...	45	90	35	NP	NP	1000	650	NFN-11	G5, G14
4	...	43	100	45	1250	800	1250	650	NFN-10	G5, G27, G28, T15, W5, W12
5	...	43	100	45	1250	NP	1250	NP	NFN-10	G5, G27, G28, T15
6	...	43	100	45	1250	NP	1250	NP	NFN-10	G27, G28, T15
7	...	43	100	45	1250	800	1250	650	NFN-10	G5, G27, G28, T15
8	...	43	100	45	1250	NP	1250	650	NFN-10	G27, G28, T15
9	...	43	100	45	1250	800	1250	650	NFN-10	G5, G27, G28, T15
10	...	43	100	45	1250	NP	1250	650	NFN-10	G27, G28, T15
11	...	43	100	45	1250	800	1250	650	NFN-10	G5, G27, G28, T15
12	...	43	100	45	1250	NP	1250	650	NFN-10	G27, G28, T15
13	...	43	100	45	1250	800	1250	650	NFN-10	G5, G14, G27, G28, T15, W6
14	...	43	100	45	1250	NP	1250	650	NFN-10	G14, G27, G28, T15
15	...	43	100	45	1250	800	1250	650	NFN-10	G5, G27, G28, T15
16	...	43	100	45	1250	NP	1250	650	NFN-10	G27, G28, T15
17	...	43	100	45	1250	800	1250	650	NFN-10	G5, G14, G27, G28, T15, W6
18	...	43	100	45	1250	NP	1250	650	NFN-10	G14, G27, G28, T15
19	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
20	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
21	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
22	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
23	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
24	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
25	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
26	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
27	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G14, G30, G31, G32, T12
28	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G14, G30, G31, G32, T13
29	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G14, G30, G31, G32, T12
30	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G14, G30, G31, G32, T13
31	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
32	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
33	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
34	$t \leq 4$	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
35	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G5, G30, G31, G32, T12
36	...	43	98	39	1650	NP	1800	NP	NFN-13	G4, G30, G31, G32, T13
37	...	45	85	35	NP	800	800	650	NFN-19	G5, W5, W12
38	...	45	85	35	NP	NP	800	NP	NFN-19	G5
39	...	45	85	35	NP	NP	800	NP	NFN-19	...
40	...	45	85	35	NP	800	800	650	NFN-19	G5
41	...	45	85	35	NP	NP	800	650	NFN-19	...
42	...	45	85	35	NP	800	800	650	NFN-19	G5
43	...	45	85	35	NP	NP	800	650	NFN-19	...
44	...	45	85	35	NP	800	800	650	NFN-19	G5, G14, W6
45	...	45	85	35	NP	NP	800	650	NFN-19	G14

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.7	22.4	22.2	22.0	21.8	21.7	21.6	21.5
2	19.8	...	17.8	...	16.5	...	15.5	...	14.8	...	14.3	14.1	14.0	13.8	13.7	13.7	13.6	13.5
3	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.3	19.1	18.8	18.7	18.5	18.4	18.3	18.3
4	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
5	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
6	28.6	...	26.7	...	24.6	...	22.9	...	21.5	...	20.4	20.0	19.6	19.3	19.0	18.8	18.6	18.5
7	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
8	28.6	...	26.7	...	24.6	...	22.9	...	21.5	...	20.4	20.0	19.6	19.3	19.0	18.8	18.6	18.5
9	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
10	28.6	...	26.7	...	24.6	...	22.9	...	21.5	...	20.4	20.0	19.6	19.3	19.0	18.8	18.6	18.5
11	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
12	28.6	...	26.7	...	24.6	...	22.9	...	21.5	...	20.4	20.0	19.6	19.3	19.0	18.8	18.6	18.5
13	24.3	...	24.3	...	23.9	...	23.1	...	22.6	...	22.1	21.9	21.8	21.6	21.5	21.3	21.1	21.0
14	24.3	...	22.7	...	20.9	...	19.4	...	18.3	...	17.4	17.0	16.7	16.4	16.2	16.0	15.8	15.7
15	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	26.0	25.8	25.6	25.4	25.3	25.1	24.9	24.7
16	28.6	...	26.7	...	24.6	...	22.9	...	21.5	...	20.4	20.0	19.6	19.3	19.0	18.8	18.6	18.5
17	24.3	...	24.3	...	23.9	...	23.1	...	22.6	...	22.1	21.9	21.8	21.6	21.5	21.3	21.1	21.0
18	24.3	...	22.7	...	20.9	...	19.4	...	18.3	...	17.4	17.0	16.7	16.4	16.2	16.0	15.8	15.7
19	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
20	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
21	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
22	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
23	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
24	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
25	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
26	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
27	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1
28	22.1	22.1	21.9	21.6	21.1	20.3	20.1	19.6	19.1	18.7	18.3	17.9	17.6	17.4	17.2	17.0	16.9	16.8
29	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1	22.1
30	22.1	22.1	21.9	21.6	21.1	20.6	20.1	19.6	19.1	18.7	18.3	17.9	17.6	17.4	17.2	17.0	16.9	16.8
31	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
32	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
33	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
34	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
35	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0	26.0
36	26.0	26.0	25.8	25.4	24.9	24.3	23.7	23.1	22.5	22.0	21.5	21.1	20.7	20.4	20.2	20.0	19.9	19.8
37	23.3	...	23.3	...	23.3	...	22.5	...	21.9	...	21.3	20.9	20.5	20.1	19.7	...	...	...
38	23.3	...	23.3	...	23.3	...	22.5	...	21.9	...	21.3	20.9	20.5	20.1	19.7	...	...	...
39	23.3	...	20.0	...	18.3	...	17.2	...	16.4	...	15.8	15.5	15.2	14.9	14.6	...	...	...
40	23.3	...	23.3	...	23.3	...	22.5	...	21.9	...	21.3	20.9	20.5	20.1	19.7	...	...	...
41	23.3	...	20.0	...	18.3	...	17.2	...	16.4	...	15.8	15.5	15.2	14.9	14.6	...	...	...
42	23.3	...	23.3	...	23.3	...	22.5	...	21.9	...	21.3	20.9	20.5	20.1	19.7	...	...	...
43	23.3	...	20.0	...	18.3	...	17.2	...	16.4	...	15.8	15.5	15.2	14.9	14.6	...	...	...
44	19.8	...	19.8	...	19.8	...	19.1	...	18.6	...	18.1	17.7	17.4	17.1	16.8	...	...	...
45	19.8	...	17.0	...	15.6	...	14.6	...	13.9	...	13.4	13.1	12.9	12.7	12.4	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	21.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	13.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	18.2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
5	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
6	18.3	18.2	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
7	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
8	18.3	18.2	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
9	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
10	18.3	18.2	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
11	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
12	18.3	18.2	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
13	20.7	19.6	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...	...	...	...
14	15.6	15.5	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...	...	...	...
15	24.4	23.0	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
16	18.3	18.2	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...	...	...	...
17	20.7	19.6	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...	...	...	...
18	15.6	15.5	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...	...	...	...
19	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
20	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
21	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
22	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
23	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
24	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
25	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
26	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
27	21.5	16.1	13.3	10.7	8.7	7.0	5.7	4.7	3.4	1.7	1.1	0.92	0.74	0.60	0.48	0.39	0.32
28	16.7	16.1	13.3	10.7	8.7	7.0	5.7	4.7	3.4	1.7	1.1	0.92	0.74	0.60	0.48	0.39	0.32
29	21.5	16.1	13.3	10.7	8.7	7.0	5.7	4.7	3.4	1.7	1.1	0.92	0.74	0.60	0.48	0.39	0.32
30	16.7	16.1	13.3	10.7	8.7	7.0	5.7	4.7	3.4	1.7	1.1	0.92	0.74	0.60	0.48	0.39	0.32
31	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
32	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
33	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
34	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
35	25.3	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
36	19.7	18.9	15.6	12.6	10.2	8.3	6.7	5.5	4.1	2.0	1.3	1.1	0.87	0.70	0.57	0.46	0.37
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	40Ni-29Cr-15Fe-5Mo	Smls. pipe & tube	SB-622	...	N06030	Solution ann.
2	40Ni-29Cr-15Fe-5Mo	Smls. pipe & tube	SB-622	...	N06030	Solution ann.
3	40Ni-29Cr-15Fe-5Mo	Wld. tube	SB-626	...	N06030	Solution ann.
4	40Ni-29Cr-15Fe-5Mo	Wld. tube	SB-626	...	N06030	Solution ann.
5	58Ni-33Cr-8Mo	Smls. & wld. fittings	SB-366	...	N06035	Solution ann.
6	58Ni-33Cr-8Mo	Forgings	SB-462	...	N06035	Solution ann.
7	58Ni-33Cr-8Mo	Forgings	SB-462	...	N06035	Solution ann.
8	58Ni-33Cr-8Mo	Forgings	SB-564	...	N06035	Solution ann.
9	58Ni-33Cr-8Mo	Forgings	SB-564	...	N06035	Solution ann.
10	58Ni-33Cr-8Mo	Rod	SB-574	...	N06035	Solution ann.
11	58Ni-33Cr-8Mo	Rod	SB-574	...	N06035	Solution ann.
12	58Ni-33Cr-8Mo	Plate, sheet, strip	SB-575	...	N06035	Solution ann.
13	58Ni-33Cr-8Mo	Plate, sheet, strip	SB-575	...	N06035	Solution ann.
14	58Ni-33Cr-8Mo	Wld. pipe	SB-619	...	N06035	Solution ann.
15	58Ni-33Cr-8Mo	Wld. pipe	SB-619	...	N06035	Solution ann.
16	58Ni-33Cr-8Mo	Smls. pipe & tube	SB-622	...	N06035	Solution ann.
17	58Ni-33Cr-8Mo	Smls. pipe & tube	SB-622	...	N06035	Solution ann.
18	58Ni-33Cr-8Mo	Wld. tube	SB-626	...	N06035	Solution ann.
19	58Ni-33Cr-8Mo	Wld. tube	SB-626	...	N06035	Solution ann.
20	46Ni-27Cr-23Fe-2.75Si	Rod	SB-166	...	N06045	Solution ann.
21	46Ni-27Cr-23Fe-2.75Si	Rod	SB-166	...	N06045	Solution ann.
22	46Ni-27Cr-23Fe-2.75Si	Smls. pipe & tube	SB-167	...	N06045	Solution ann.
23	46Ni-27Cr-23Fe-2.75Si	Smls. pipe & tube	SB-167	...	N06045	Solution ann.
24	46Ni-27Cr-23Fe-2.75Si	Plate, sheet, strip	SB-168	...	N06045	Solution ann.
25	46Ni-27Cr-23Fe-2.75Si	Plate, sheet, strip	SB-168	...	N06045	Solution ann.
26	46Ni-27Cr-23Fe-2.75Si	Smls. & wld. fittings	SB-366	...	N06045	Solution ann.
27	46Ni-27Cr-23Fe-2.75Si	Forged fittings	SB-462	...	N06045	Solution ann.
28	46Ni-27Cr-23Fe-2.75Si	Forged fittings	SB-462	...	N06045	Solution ann.
29	46Ni-27Cr-23Fe-2.75Si	Wld. tube	SB-516	...	N06045	Solution ann.
30	46Ni-27Cr-23Fe-2.75Si	Wld. tube	SB-516	...	N06045	Solution ann.
31	46Ni-27Cr-23Fe-2.75Si	Wld. pipe	SB-517	...	N06045	Solution ann.
32	46Ni-27Cr-23Fe-2.75Si	Wld. pipe	SB-517	...	N06045	Solution ann.
33	46Ni-27Cr-23Fe-2.75Si	Forgings	SB-564	...	N06045	Solution ann.
34	46Ni-27Cr-23Fe-2.75Si	Forgings	SB-564	...	N06045	Solution ann.
35	59Ni-23Cr-16Mo	Fittings	SB-366	CR5923	N06059	Annealed
36	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923	N06059	Annealed
37	59Ni-23Cr-16Mo	Wld. fittings	SB-366	WP5923W	N06059	Annealed
38	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923WX	N06059	Annealed
39	59Ni-23Cr-16Mo	Forged fittings	SB-462	...	N06059	Solution ann.
40	59Ni-23Cr-16Mo	Forged fittings	SB-462	...	N06059	Solution ann.
41	59Ni-23Cr-16Mo	Forgings	SB-564	...	N06059	Solution ann.
42	59Ni-23Cr-16Mo	Forgings	SB-564	...	N06059	Solution ann.
43	59Ni-23Cr-16Mo	Rod	SB-574	...	N06059	Solution ann.
44	59Ni-23Cr-16Mo	Rod	SB-574	...	N06059	Solution ann.
45	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...	N06059	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	85	35	NP	800	800	650	NFN-19	G5
2	...	45	85	35	NP	NP	800	650	NFN-19	...
3	...	45	85	35	NP	800	800	650	NFN-19	G5, G14, W6
4	...	45	85	35	NP	NP	800	650	NFN-19	G14
5	...	43	85	35	NP	NP	800	NP	NFN-27	G5, W12
6	...	43	85	35	NP	NP	800	NP	NFN-27	G5
7	...	43	85	35	NP	NP	800	NP	NFN-27	...
8	...	43	85	35	NP	NP	800	NP	NFN-27	G5
9	...	43	85	35	NP	NP	800	NP	NFN-27	...
10	...	43	85	35	NP	NP	800	NP	NFN-27	G5
11	...	43	85	35	NP	NP	800	NP	NFN-27	...
12	...	43	85	35	NP	NP	800	NP	NFN-27	G5
13	...	43	85	35	NP	NP	800	NP	NFN-27	...
14	...	43	85	35	NP	NP	800	NP	NFN-27	G5, G14
15	...	43	85	35	NP	NP	800	NP	NFN-27	G14
16	...	43	85	35	NP	NP	800	NP	NFN-27	G5
17	...	43	85	35	NP	NP	800	NP	NFN-27	...
18	...	43	85	35	NP	NP	800	NP	NFN-27	G5, G14
19	...	43	85	35	NP	NP	800	NP	NFN-27	G14
20	...	46	90	35	1500	NP	1500	NP	NFN-8	G1, G5, T11
21	...	46	90	35	1500	NP	1500	NP	NFN-8	T11
22	...	46	90	35	1500	NP	1500	NP	NFN-8	G1, G5, T11
23	...	46	90	35	1500	NP	1500	NP	NFN-8	T11
24	...	46	90	35	1500	NP	1500	NP	NFN-8	G1, G5, T11
25	...	46	90	35	1500	NP	1500	NP	NFN-8	T11
26	...	46	90	35	1500	NP	1500	NP	NFN-8	G5, T11, W12
27	...	46	90	35	1500	NP	1500	NP	NFN-8	G5, T11
28	...	46	90	35	1500	NP	1500	NP	NFN-8	T11
29	...	46	90	35	1500	NP	1500	NP	NFN-8	G5, G14, T11
30	...	46	90	35	1500	NP	1500	NP	NFN-8	G14, T11
31	...	46	90	35	1500	NP	1500	NP	NFN-8	G1, G5, G14, T11
32	...	46	90	35	1500	NP	1500	NP	NFN-8	G14, T11
33	...	46	90	35	1500	NP	1500	NP	NFN-8	G1, G5, T11
34	...	46	90	35	1500	NP	1500	NP	NFN-8	T11
35	...	43	100	45	NP	800	1400	650	NFN-14	G5, G14, G23, T16
36	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
37	...	43	100	45	NP	800	1400	650	NFN-14	G5, G14, G23, T16
38	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
39	...	43	100	45	NP	NP	1400	650	NFN-14	G23, T16
40	...	43	100	45	NP	NP	1400	650	NFN-14	G5, G23, T16
41	...	43	100	45	NP	800	1400	650	NFN-14	G23, T16
42	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
43	...	43	100	45	NP	800	1400	650	NFN-14	G23, T16
44	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
45	...	43	100	45	NP	800	1400	650	NFN-14	G23, T16

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	23.3	...	23.3	...	23.3	...	22.5	...	21.9	...	21.3	20.9	20.5	20.1	19.7	...	...	...
2	23.3	...	20.0	...	18.3	...	17.2	...	16.4	...	15.8	15.5	15.2	14.9	14.6	...	...	...
3	19.8	...	19.8	...	19.8	...	19.1	...	18.6	...	18.1	17.7	17.4	17.1	16.8	...	...	...
4	19.8	...	17.0	...	15.6	...	14.6	...	13.9	...	13.4	13.1	12.9	12.7	12.4	...	...	...
5	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
6	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
7	23.3	...	20.4	...	18.2	...	16.5	...	15.3	...	14.6	14.4	14.2	14.1	13.9	...	...	...
8	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
9	23.3	...	20.4	...	18.2	...	16.5	...	15.3	...	14.6	14.4	14.2	14.1	13.9	...	...	...
10	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
11	23.3	...	20.4	...	18.2	...	16.5	...	15.3	...	14.6	14.4	14.2	14.1	13.9	...	...	...
12	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
13	23.3	...	20.4	...	18.2	...	16.5	...	15.3	...	14.6	14.4	14.2	14.1	13.9	...	...	...
14	19.8	...	19.8	...	19.8	...	18.9	...	17.4	...	16.7	16.5	16.3	16.2	16.0	...	...	...
15	19.8	...	17.3	...	15.5	...	14.0	...	13.0	...	12.4	12.2	12.1	12.0	11.8	...	...	...
16	23.3	...	23.3	...	23.3	...	22.2	...	20.5	...	19.7	19.4	19.2	19.0	18.8	...	...	...
17	23.3	...	20.4	...	18.2	...	16.5	...	15.3	...	14.6	14.4	14.2	14.1	13.9	...	...	...
18	19.8	...	19.8	...	19.8	...	18.9	...	17.4	...	16.7	16.5	16.3	16.2	16.0	...	...	...
19	19.8	...	17.3	...	15.5	...	14.0	...	13.0	...	12.4	12.2	12.1	12.0	11.8	...	...	...
20	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
21	23.3	...	20.9	...	19.3	...	18.1	...	17.4	...	17.0	16.8	16.8	16.7	16.6	16.5	16.0	12.9
22	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
23	23.3	...	20.9	...	19.3	...	18.1	...	17.4	...	17.0	16.8	16.8	16.7	16.6	16.5	16.0	12.9
24	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
25	23.3	...	20.9	...	19.3	...	18.1	...	17.4	...	17.0	16.8	16.8	16.7	16.6	16.5	16.0	12.9
26	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
27	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
28	23.3	...	20.9	...	19.3	...	18.1	...	17.4	...	17.0	16.8	16.8	16.7	16.6	16.5	16.0	12.9
29	19.8	...	19.8	...	19.8	...	19.8	...	19.2	...	18.8	18.6	18.4	18.4	18.2	17.9	13.6	11.0
30	19.8	...	17.8	...	16.4	...	15.4	...	14.8	...	14.5	14.3	14.3	14.2	14.1	14.0	13.6	11.0
31	19.8	...	19.8	...	19.8	...	19.8	...	19.2	...	18.8	18.6	18.4	18.4	18.2	17.9	13.6	11.0
32	19.8	...	17.8	...	16.4	...	15.4	...	14.8	...	14.5	14.3	14.3	14.2	14.1	14.0	13.6	11.0
33	23.3	...	23.3	...	23.3	...	23.3	...	22.6	...	22.1	21.9	21.7	21.6	21.4	21.1	16.0	12.9
34	23.3	...	20.9	...	19.3	...	18.1	...	17.4	...	17.0	16.8	16.8	16.7	16.6	16.5	16.0	12.9
35	24.3	...	24.3	...	24.3	...	23.8	...	23.0	...	22.1	21.8	21.4	21.2	20.9	20.7	20.6	20.1
36	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
37	24.3	...	24.3	...	24.3	...	23.8	...	23.0	...	22.1	21.8	21.4	21.2	20.9	20.7	20.6	20.1
38	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
39	28.6	...	26.9	...	25.2	...	23.8	...	22.6	...	21.4	20.8	20.2	19.6	19.1	18.5	18.0	17.5
40	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
41	28.6	...	26.9	...	25.2	...	23.8	...	22.6	...	21.4	20.8	20.2	19.6	19.1	18.5	18.0	17.5
42	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
43	28.6	...	26.9	...	25.2	...	23.8	...	22.6	...	21.4	20.8	20.2	19.6	19.1	18.5	18.0	17.5
44	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
45	28.6	...	26.9	...	25.2	...	23.8	...	22.6	...	21.4	20.8	20.2	19.6	19.1	18.5	18.0	17.5

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
21	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
22	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
23	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
24	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
25	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
26	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
27	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
28	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
29	8.0	6.0	4.8	3.7	3.0	2.4	1.9	1.5	1.2	0.90	0.70	...	...	...	...	...	...
30	8.0	6.0	4.8	3.7	3.0	2.4	1.9	1.5	1.2	0.90	0.70	...	...	...	...	...	...
31	8.0	6.0	4.8	3.7	3.0	2.4	1.9	1.5	1.2	0.90	0.70	...	...	...	...	...	...
32	8.0	6.0	4.8	3.7	3.0	2.4	1.9	1.5	1.2	0.90	0.70	...	...	...	...	...	...
33	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
34	9.4	7.1	5.6	4.4	3.5	2.8	2.2	1.8	1.4	1.1	0.85	...	...	...	...	...	...
35	19.6	19.2	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
36	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
37	19.6	19.2	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
38	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
39	17.1	16.8	16.5	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
40	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
41	17.1	16.8	16.5	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
42	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
43	17.1	16.8	16.5	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
44	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
45	17.1	16.8	16.5	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...	N06059	Solution ann.
2	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.
3	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.
4	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...	N06059	Solution ann.
5	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...	N06059	Solution ann.
6	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.
7	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.
8	59Ni-23Cr-16Mo-1.6Cu	Smls. & wld. fittings	SB-366	...	N06200	Solution ann.
9	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-462	...	N06200	Solution ann.
10	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-462	...	N06200	Solution ann.
11	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-564	...	N06200	Solution ann.
12	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-564	...	N06200	Solution ann.
13	59Ni-23Cr-16Mo-1.6Cu	Rod	SB-574	...	N06200	Solution ann.
14	59Ni-23Cr-16Mo-1.6Cu	Rod	SB-574	...	N06200	Solution ann.
15	59Ni-23Cr-16Mo-1.6Cu	Plate, sheet, strip	SB-575	...	N06200	Solution ann.
16	59Ni-23Cr-16Mo-1.6Cu	Plate, sheet, strip	SB-575	...	N06200	Solution ann.
17	59Ni-23Cr-16Mo-1.6Cu	Wld. pipe	SB-619	...	N06200	Solution ann.
18	59Ni-23Cr-16Mo-1.6Cu	Wld. pipe	SB-619	...	N06200	Solution ann.
19	59Ni-23Cr-16Mo-1.6Cu	Smls. pipe & tube	SB-622	...	N06200	Solution ann.
20	59Ni-23Cr-16Mo-1.6Cu	Smls. pipe & tube	SB-622	...	N06200	Solution ann.
21	59Ni-23Cr-16Mo-1.6Cu	Wld. tube	SB-626	...	N06200	Solution ann.
22	59Ni-23Cr-16Mo-1.6Cu	Wld. tube	SB-626	...	N06200	Solution ann.
23	60Ni-19Cr-19Mo-1.8Ta	Smls. & wld. fittings	SB-366	...	N06210	Solution ann.
24	60Ni-19Cr-19Mo-1.8Ta	Forgings	SB-564	...	N06210	Solution ann.
25	60Ni-19Cr-19Mo-1.8Ta	Forgings	SB-564	...	N06210	Solution ann.
26	60Ni-19Cr-19Mo-1.8Ta	Rod	SB-574	...	N06210	Solution ann.
27	60Ni-19Cr-19Mo-1.8Ta	Rod	SB-574	...	N06210	Solution ann.
28	60Ni-19Cr-19Mo-1.8Ta	Plate, sheet, strip	SB-575	...	N06210	Solution ann.
29	60Ni-19Cr-19Mo-1.8Ta	Plate, sheet, strip	SB-575	...	N06210	Solution ann.
30	60Ni-19Cr-19Mo-1.8Ta	Wld. pipe	SB-619	...	N06210	Solution ann.
31	60Ni-19Cr-19Mo-1.8Ta	Wld. pipe	SB-619	...	N06210	Solution ann.
32	60Ni-19Cr-19Mo-1.8Ta	Smls. pipe & tube	SB-622	...	N06210	Solution ann.
33	60Ni-19Cr-19Mo-1.8Ta	Smls. pipe & tube	SB-622	...	N06210	Solution ann.
34	60Ni-19Cr-19Mo-1.8Ta	Wld. tube	SB-626	...	N06210	Solution ann.
35	60Ni-19Cr-19Mo-1.8Ta	Wld. tube	SB-626	...	N06210	Solution ann.
36	57Ni-22Cr-14W-2Mo-La	Smls. & wld. fittings	SB-366	...	N06230	Solution ann.
37	57Ni-22Cr-14W-2Mo-La	Plate, sheet, strip	SB-435	...	N06230	Solution ann.
38	57Ni-22Cr-14W-2Mo-La	Plate, sheet, strip	SB-435	...	N06230	Solution ann.
39	57Ni-22Cr-14W-2Mo-La	Forgings	SB-564	...	N06230	Solution ann.
40	57Ni-22Cr-14W-2Mo-La	Forgings	SB-564	...	N06230	Solution ann.
41	57Ni-22Cr-14W-2Mo-La	Bar	SB-572	...	N06230	Solution ann.
42	57Ni-22Cr-14W-2Mo-La	Bar	SB-572	...	N06230	Solution ann.
43	57Ni-22Cr-14W-2Mo-La	Wld. pipe	SB-619	...	N06230	Solution ann.
44	57Ni-22Cr-14W-2Mo-La	Wld. pipe	SB-619	...	N06230	Solution ann.
45	57Ni-22Cr-14W-2Mo-La	Smls. pipe & tube	SB-622	...	N06230	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
2	...	43	100	45	NP	800	1400	650	NFN-14	G14, G23, T16
3	...	43	100	45	NP	800	1400	650	NFN-14	G5, G14, G23, T16
4	...	43	100	45	NP	800	1400	650	NFN-14	G23, T16
5	...	43	100	45	NP	800	1400	650	NFN-14	G5, G23, T16
6	...	43	100	45	NP	800	1400	650	NFN-14	G14, G23, T16
7	...	43	100	45	NP	800	1400	650	NFN-14	G5, G14, G23, T16
8	...	43	100	45	NP	NP	800	NP	NFN-10	G5, W12
9	...	43	100	45	NP	NP	800	NP	NFN-10	...
10	...	43	100	45	NP	NP	800	NP	NFN-10	G5
11	...	43	100	45	NP	NP	800	NP	NFN-10	...
12	...	43	100	45	NP	NP	800	NP	NFN-10	G5
13	...	43	100	45	NP	NP	800	NP	NFN-10	...
14	...	43	100	45	NP	NP	800	NP	NFN-10	G5
15	...	43	100	45	NP	NP	800	NP	NFN-10	...
16	...	43	100	45	NP	NP	800	NP	NFN-10	G5
17	...	43	100	45	NP	NP	800	NP	NFN-10	G14
18	...	43	100	45	NP	NP	800	NP	NFN-10	G5, G14
19	...	43	100	45	NP	NP	800	NP	NFN-10	...
20	...	43	100	45	NP	NP	800	NP	NFN-10	G5
21	...	43	100	45	NP	NP	800	NP	NFN-10	G14
22	...	43	100	45	NP	NP	800	NP	NFN-10	G5, G14
23	...	43	100	45	NP	NP	800	NP	NFN-14	G5, W12
24	...	43	100	45	NP	NP	800	NP	NFN-14	...
25	...	43	100	45	NP	NP	800	NP	NFN-14	G5
26	...	43	100	45	NP	NP	800	NP	NFN-14	...
27	...	43	100	45	NP	NP	800	NP	NFN-14	G5
28	...	43	100	45	NP	NP	800	NP	NFN-14	...
29	...	43	100	45	NP	NP	800	NP	NFN-14	G5
30	...	43	100	45	NP	NP	800	NP	NFN-14	...
31	...	43	100	45	NP	NP	800	NP	NFN-14	G5, G14
32	...	43	100	45	NP	NP	800	NP	NFN-14	...
33	...	43	100	45	NP	NP	800	NP	NFN-14	G5
34	...	43	100	45	NP	NP	800	NP	NFN-14	...
35	...	43	100	45	NP	NP	800	NP	NFN-14	G5, G14
36	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, T15, W12
37	...	43	110	45	1650	NP	1800	650	NFN-24	G4, T16
38	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, T15
39	...	43	110	45	1650	NP	1800	650	NFN-24	G4, T16
40	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, T15
41	...	43	110	45	1650	NP	1800	650	NFN-24	G4, T16
42	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, T15
43	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G14, T16
44	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, G14, T15
45	...	43	110	45	1650	NP	1800	650	NFN-24	G4, T16

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
2	24.3	...	22.9	...	21.4	...	20.2	...	19.2	...	18.2	17.7	17.2	16.7	16.2	15.7	15.3	14.9
3	24.3	...	24.3	...	24.3	...	23.8	...	23.0	...	22.1	21.8	21.4	21.2	20.9	20.7	20.6	20.1
4	28.6	...	26.9	...	25.2	...	23.8	...	22.6	...	21.4	20.8	20.2	19.6	19.1	18.5	18.0	17.5
5	28.6	...	28.6	...	28.6	...	28.0	...	27.0	...	26.0	25.6	25.2	24.9	24.6	24.4	24.2	23.7
6	24.3	...	22.9	...	21.4	...	20.2	...	19.2	...	18.2	17.7	17.2	16.7	16.2	15.7	15.3	14.9
7	24.3	...	24.3	...	24.3	...	23.8	...	23.0	...	22.1	21.8	21.4	21.2	20.9	20.7	20.6	20.1
8	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
9	28.6	...	26.9	...	24.8	...	22.9	...	21.2	...	19.9	19.4	19.1	18.8	18.7	...	...	...
10	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
11	28.6	...	26.9	...	24.8	...	22.9	...	21.2	...	19.9	19.4	19.1	18.8	18.7	...	...	...
12	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
13	28.6	...	26.9	...	24.8	...	22.9	...	21.2	...	19.9	19.4	19.1	18.8	18.7	...	...	...
14	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
15	28.6	...	26.9	...	24.8	...	22.9	...	21.2	...	19.9	19.4	19.1	18.8	18.7	...	...	...
16	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
17	24.3	...	22.9	...	21.1	...	19.4	...	18.0	...	16.9	16.5	16.2	16.0	15.9	...	...	...
18	24.3	...	24.3	...	24.3	...	23.5	...	22.8	...	22.3	22.1	21.9	21.6	21.4	...	...	...
19	28.6	...	26.9	...	24.8	...	22.9	...	21.2	...	19.9	19.4	19.1	18.8	18.7	...	...	...
20	28.6	...	28.6	...	28.6	...	27.6	...	26.8	...	26.2	26.0	25.7	25.4	25.2	...	...	...
21	24.3	...	22.9	...	21.1	...	19.4	...	18.0	...	16.9	16.5	16.2	16.0	15.9	...	...	...
22	24.3	...	24.3	...	24.3	...	23.5	...	22.8	...	22.3	22.1	21.9	21.6	21.4	...	...	...
23	28.6	...	28.6	...	28.5	...	27.6	...	26.9	...	26.3	25.5	24.8	24.1	23.6	...	...	...
24	28.6	...	26.6	...	24.5	...	22.6	...	21.0	...	19.5	18.9	18.4	17.9	17.5	...	...	...
25	28.6	...	28.6	...	28.5	...	27.6	...	26.9	...	26.3	25.5	24.8	24.1	23.6	...	...	...
26	28.6	...	26.6	...	24.5	...	22.6	...	21.0	...	19.5	18.9	18.4	17.9	17.5	...	...	...
27	28.6	...	28.6	...	28.5	...	27.6	...	26.9	...	26.3	25.5	24.8	24.1	23.6	...	...	...
28	28.6	...	26.6	...	24.5	...	22.6	...	21.0	...	19.5	18.9	18.4	17.9	17.5	...	...	...
29	28.6	...	28.6	...	28.5	...	27.6	...	26.9	...	26.3	25.5	24.8	24.1	23.6	...	...	...
30	24.3	...	22.6	...	20.8	...	19.2	...	17.8	...	16.6	16.1	15.6	15.2	14.8	...	...	...
31	24.3	...	24.3	...	24.2	...	23.5	...	22.9	...	22.4	21.7	21.1	20.5	20.0	...	...	...
32	28.6	...	26.6	...	24.5	...	22.6	...	21.0	...	19.5	18.9	18.4	17.9	17.5	...	...	...
33	28.6	...	28.6	...	28.5	...	27.6	...	26.9	...	26.3	25.5	24.8	24.1	23.6	...	...	...
34	24.3	...	22.6	...	20.8	...	19.2	...	17.8	...	16.6	16.1	15.6	15.2	14.8	...	...	...
35	24.3	...	24.3	...	24.2	...	23.5	...	22.9	...	22.4	21.7	21.1	20.5	20.0	...	...	...
36	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.4	29.1	28.7	28.4	28.2	28.2	28.2	28.2
37	30.0	...	28.2	...	26.4	...	24.7	...	23.1	...	22.0	21.5	21.2	21.0	20.9	20.9	20.9	20.9
38	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.4	29.1	28.7	28.4	28.2	28.2	28.2	28.2
39	30.0	...	28.2	...	26.4	...	24.7	...	23.1	...	22.0	21.5	21.2	21.0	20.9	20.9	20.9	20.9
40	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.4	29.1	28.7	28.4	28.2	28.2	28.2	28.2
41	30.0	...	28.2	...	26.4	...	24.7	...	23.1	...	22.0	21.5	21.2	21.0	20.9	20.9	20.9	20.9
42	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.4	29.1	28.7	28.4	28.2	28.2	28.2	28.2
43	25.5	...	24.0	...	22.4	...	21.0	...	19.6	...	18.7	18.3	18.0	17.9	17.8	17.8	17.8	17.8
44	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	25.0	24.7	24.4	24.1	24.0	24.0	24.0	24.0
45	30.0	...	28.2	...	26.4	...	24.7	...	23.1	...	22.0	21.5	21.2	21.0	20.9	20.9	20.9	20.9

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
2	14.5	14.3	14.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
3	19.6	19.2	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
4	17.1	16.8	16.5	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
5	23.1	22.6	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...	...	...	...
6	14.5	14.3	14.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
7	19.6	19.2	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	28.2	28.2	23.2	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
37	20.9	20.9	20.9	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
38	28.2	28.2	23.2	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
39	20.9	20.9	20.9	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
40	28.2	28.2	23.2	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
41	20.9	20.9	20.9	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
42	28.2	28.2	23.2	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
43	17.8	17.8	17.8	16.2	13.3	11.0	9.0	7.2	5.7	4.5	3.5	2.5	1.8	1.3	0.94	0.60	0.38
44	24.0	24.0	19.7	16.2	13.3	11.0	9.0	7.2	5.7	4.5	3.5	2.5	1.8	1.3	0.94	0.60	0.38
45	20.9	20.9	20.9	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	57Ni-22Cr-14W-2Mo-La	Smls. pipe & tube	SB-622	...	N06230	Solution ann.
2	57Ni-22Cr-14W-2Mo-La	Wld. tube	SB-626	...	N06230	Solution ann.
3	57Ni-22Cr-14W-2Mo-La	Wld. tube	SB-626	...	N06230	Solution ann.
4	61Ni-16Mo-16Cr	Smls. & wld. fittings	SB-366	...	N06455	Annealed
5	61Ni-16Mo-16Cr	Rod	SB-574	...	N06455	Solution ann.
6	61Ni-16Mo-16Cr	Rod	SB-574	...	N06455	Solution ann.
7	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...	N06455	Solution ann.
8	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...	N06455	Solution ann.
9	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...	N06455	Solution ann.
10	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...	N06455	Solution ann.
11	61Ni-16Mo-16Cr	Smls. pipe & tube	SB-622	...	N06455	Solution ann.
12	61Ni-16Mo-16Cr	Smls. pipe & tube	SB-622	...	N06455	Solution ann.
13	61Ni-16Mo-16Cr	Wld. tube	SB-626	...	N06455	Solution ann.
14	61Ni-16Mo-16Cr	Wld. tube	SB-626	...	N06455	Solution ann.
15	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
16	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
17	72Ni-15Cr-8Fe	Smls. & wld. fittings	SB-366	...	N06600	Annealed
18	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold drawn/ann.
19	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold drawn/ann.
20	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
21	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
22	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed
23	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed
24	72Ni-15Cr-8Fe	Bar	SB-166	...	N06600	Annealed
25	72Ni-15Cr-8Fe	Bar	SB-166	...	N06600	Annealed
26	72Ni-15Cr-8Fe	Plate	SB-168	...	N06600	Annealed
27	72Ni-15Cr-8Fe	Plate, sheet, strip	SB-168	...	N06600	Annealed
28	72Ni-15Cr-8Fe	Wld. tube	SB-516	...	N06600	Annealed
29	72Ni-15Cr-8Fe	Wld. tube	SB-516	...	N06600	Annealed
30	72Ni-15Cr-8Fe	Forgings	SB-564	...	N06600	...
31	72Ni-15Cr-8Fe	Forgings	SB-564	...	N06600	Annealed
32	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold drawn/ann.
33	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold drawn/ann.
34	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...	N06600	Cold drawn/ann.
35	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...	N06600	Cold drawn/ann.
36	72Ni-15Cr-8Fe	Bar, rod	SB-166	...	N06600	Hot fin.
37	72Ni-15Cr-8Fe	Bar, rod	SB-166	...	N06600	Hot fin.
38	72Ni-15Cr-8Fe	Plate, sheet, strip	SB-168	...	N06600	Hot rolled
39	72Ni-15Cr-8Fe	Plate, sheet, strip	SB-168	...	N06600	Hot rolled
40	60Ni-23Cr-Fe	Smls. tube	SB-163	...	N06601	Annealed
41	60Ni-23Cr-Fe	Smls. tube	SB-163	...	N06601	Annealed
42	60Ni-23Cr-Fe	Bar	SB-166	...	N06601	Annealed
43	60Ni-23Cr-Fe	Bar	SB-166	...	N06601	Annealed
44	60Ni-23Cr-Fe	Smls. pipe & tube	SB-167	...	N06601	Annealed
45	60Ni-23Cr-Fe	Smls. pipe & tube	SB-167	...	N06601	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, T15
2	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G14, T16
3	...	43	110	45	1650	NP	1800	650	NFN-24	G4, G5, G14, T15
4	...	43	100	40	NP	NP	800	650	NFN-14	G5, W12
5	...	43	100	40	NP	NP	800	650	NFN-14	...
6	...	43	100	40	NP	NP	800	650	NFN-14	G5
7	...	43	100	40	NP	NP	800	650	NFN-14	...
8	...	43	100	40	NP	NP	800	650	NFN-14	G5
9	...	43	100	40	NP	NP	800	650	NFN-14	G14
10	...	43	100	40	NP	NP	800	650	NFN-14	G5, G14
11	...	43	100	40	NP	NP	800	650	NFN-14	...
12	...	43	100	40	NP	NP	800	650	NFN-14	G5
13	...	43	100	40	NP	NP	800	650	NFN-14	G14
14	...	43	100	40	NP	NP	800	650	NFN-14	G5, G14
15	>5	43	75	25	NP	800	1200	650	NFN-4	T12
16	>5	43	75	25	NP	800	1200	650	NFN-4	G5, T11
17	...	43	80	30	800	NP	1200	650	NFN-4	G5, T11, W5, W12
18	>5	43	80	30	NP	800 (Cl. 3 only)	1200	650	NFN-4	T12
19	>5	43	80	30	NP	800 (Cl. 3 only)	1200	650	NFN-4	G5, T11
20	≤5	43	80	30	NP	800	1200	650	NFN-4	G5, T11
21	≤5	43	80	30	NP	NP	1200	650	NFN-4	T12
22	≤3	43	80	35	1200	800	1200	650	NFN-4	G5, T11
23	≤3	43	80	35	1200	NP	1200	650	NFN-4	T11
24	...	43	80	35	1200	800	1200	650	NFN-4	G5, T11
25	...	43	80	35	1200	NP	1200	650	NFN-4	T11
26	...	43	80	35	1200	800	1200	650	NFN-4	G5, T11
27	...	43	80	35	1200	NP	1200	650	NFN-4	T11
28	...	43	80	35	NP	NP	1200	650	NFN-4	G14, T11
29	...	43	80	35	NP	NP	1200	650	NFN-4	G5, G14, T11
30	...	43	80	35	NP	800	NP	NP	NFN-4	G5
31	...	43	80	35	NP	NP	1200	650	NFN-4	T11
32	≤5	43	80	35	1200	800 (Cl. 3 only)	1200	650	NFN-4	T11
33	≤5	43	80	35	1200	800	1200	650	NFN-4	G5, T11
34	...	43	80	35	NP	NP	1200	650	NFN-4	G14, T11
35	...	43	80	35	NP	NP	1200	650	NFN-4	G5, G14, T11
36	...	43	85	35	1200	800 (Cl. 3 only)	1200	650	NFN-4	T13
37	...	43	85	35	1200	800 (Cl. 3 only)	1200	650	NFN-4	G5, T12
38	...	43	85	35	1200	800 (Cl. 3 only)	1200	650	NFN-4	G20, T13
39	...	43	85	35	1200	800 (Cl. 3 only)	1200	650	NFN-4	G5, G20, T12
40	≤3 O.D.	43	80	30	1650	NP	1650	NP	NFN-4	G4, T14
41	≤3 O.D.	43	80	30	1650	NP	1650	NP	NFN-4	G4, G5, T13
42	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, T14
43	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, G5, T13
44	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, T14
45	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, G5, T13

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.4	29.1	28.7	28.4	28.2	28.2	28.2	28.2
2	25.5	...	24.0	...	22.4	...	21.0	...	19.6	...	18.7	18.3	18.0	17.9	17.8	17.8	17.8	17.8
3	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	25.0	24.7	24.4	24.1	24.0	24.0	24.0	24.0
4	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.5	...	25.8	...	...	...
5	26.7	...	24.6	...	23.0	...	21.7	...	20.8	...	20.1	19.9	19.6	19.4	19.1	...	...	...
6	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.5	26.1	25.8	...	...	...
7	26.7	...	24.6	...	23.0	...	21.7	...	20.8	...	20.1	19.9	19.6	19.4	19.1	...	...	...
8	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.5	26.1	25.8	...	...	...
9	22.7	...	20.9	...	19.5	...	18.5	...	17.7	...	17.1	16.9	16.7	16.5	16.2	...	...	...
10	22.7	...	22.7	...	22.7	...	22.7	...	22.7	...	22.7	22.7	22.5	22.2	21.9	...	...	...
11	26.7	...	24.6	...	23.0	...	21.7	...	20.8	...	20.1	19.9	19.6	19.4	19.1	...	...	...
12	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.5	26.1	25.8	...	...	...
13	22.7	...	20.9	...	19.5	...	18.5	...	17.7	...	17.1	16.9	16.7	16.5	16.2	...	...	...
14	22.7	...	22.7	...	22.7	...	22.7	...	22.7	...	22.7	22.7	22.5	22.2	21.9	...	...	...
15	16.7	...	15.9	...	15.2	...	14.6	...	14.0	...	13.5	13.3	13.1	12.9	12.7	12.5	12.4	10.6
16	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.7	16.7	16.7	16.7	16.7	16.7	16.0	10.6
17	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	16.0	10.6
18	20.0	...	19.1	...	18.3	...	17.5	...	16.8	...	16.2	15.9	15.7	15.5	15.2	15.1	14.9	10.6
19	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	16.0	10.6
20	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	16.0	10.6
21	20.0	...	19.1	...	18.3	...	17.5	...	16.8	...	16.2	15.9	15.7	15.5	15.2	15.1	14.9	10.6
22	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.4	16.0	10.6
23	22.9	...	21.3	...	20.8	...	20.5	...	20.2	...	19.9	19.8	19.6	19.4	19.1	18.7	16.0	10.6
24	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.4	16.0	10.6
25	22.9	...	21.3	...	20.8	...	20.5	...	20.2	...	19.9	19.8	19.6	19.4	19.1	18.7	16.0	10.6
26	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.4	16.0	10.6
27	22.9	...	21.3	...	20.8	...	20.5	...	20.2	...	19.9	19.8	19.6	19.4	19.1	18.7	16.0	10.6
28	19.4	...	18.1	...	17.7	...	17.4	...	17.2	...	16.9	16.8	16.7	16.5	16.2	15.9	13.6	9.0
29	19.4	...	19.4	...	19.4	...	19.4	...	19.4	...	19.4	19.4	19.4	19.4	19.4	19.0	13.6	9.0
30	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	...	...	...
31	22.9	...	21.3	...	20.8	...	20.5	...	20.2	...	19.9	19.8	19.6	19.4	19.1	18.7	16.0	10.6
32	22.9	...	21.3	...	20.8	...	20.5	...	20.2	...	19.9	19.8	19.6	19.4	19.1	18.7	16.0	10.6
33	22.9	...	22.9	...	22.9	...	22.9	...	22.9	...	22.9	22.9	22.9	22.9	22.9	22.4	16.0	10.6
34	19.4	...	18.1	...	17.7	...	17.4	...	17.2	...	16.9	16.8	16.7	16.5	16.2	15.9	13.6	9.0
35	19.4	...	19.4	...	19.4	...	19.4	...	19.4	...	19.4	19.4	19.4	19.4	19.4	19.0	13.6	9.0
36	23.3	...	22.1	...	21.5	...	21.3	...	21.3	...	21.2	21.1	21.0	20.8	20.5	20.1	19.7	19.3
37	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3	23.3	23.3	20.4
38	23.3	...	22.1	...	21.5	...	21.3	...	21.3	...	21.2	21.1	21.0	20.8	20.5	20.1	19.7	19.3
39	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3	23.3	23.3	20.4
40	20.0	...	17.8	...	16.6	...	15.5	...	14.7	...	14.2	14.0	13.9	13.8	13.8	13.8	13.8	13.7
41	20.0	...	20.0	...	20.0	...	20.0	...	19.9	...	19.2	19.0	18.8	18.7	18.6	18.6	18.6	18.6
42	20.0	...	17.8	...	16.6	...	15.5	...	14.7	...	14.2	14.0	13.9	13.8	13.8	13.8	13.8	13.7
43	20.0	...	20.0	...	20.0	...	20.0	...	19.9	...	19.2	19.0	18.8	18.7	18.6	18.6	18.6	18.6
44	20.0	...	17.8	...	16.6	...	15.5	...	14.7	...	14.2	14.0	13.9	13.8	13.8	13.8	13.8	13.7
45	20.0	...	20.0	...	20.0	...	20.0	...	19.9	...	19.2	19.0	18.8	18.7	18.6	18.6	18.6	18.6

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	28.2	28.2	23.2	19.0	15.6	12.9	10.6	8.5	6.7	5.3	4.1	2.9	2.1	1.5	1.1	0.70	0.45
2	17.8	17.8	17.8	16.2	13.3	11.0	9.0	7.2	5.7	4.5	3.5	2.5	1.8	1.3	0.94	0.60	0.38
3	24.0	24.0	19.7	16.2	13.3	11.0	9.0	7.2	5.7	4.5	3.5	2.5	1.8	1.3	0.94	0.60	0.38
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
16	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
17	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
18	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
19	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
20	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
21	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
22	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
23	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
24	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
25	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
26	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
27	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
28	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...	...	...	...
29	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
32	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
33	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...	...	...	...
34	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...	...	...	...
35	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...	...	...	...
36	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...	...	...	...
37	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...	...	...	...
38	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...	...	...	...
39	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...	...	...	...
40	13.7	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
41	17.6	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
42	13.7	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
43	17.6	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
44	13.7	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
45	17.6	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	
1	60Ni-23Cr-Fe	Plate, sheet, strip	SB-168	...	N06601	Annealed	
2	60Ni-23Cr-Fe	Plate, sheet, strip	SB-168	...	N06601	Annealed	
3	52Ni-22Cr-13Co-9Mo	Bar, rod	SB-166	...	N06617	Annealed	
4	52Ni-22Cr-13Co-9Mo	Bar, rod	SB-166	...	N06617	Annealed	
5	52Ni-22Cr-13Co-9Mo	Smls. pipe & tube	SB-167	...	N06617	Annealed	
6	52Ni-22Cr-13Co-9Mo	Smls. pipe & tube	SB-167	...	N06617	Annealed	
7	52Ni-22Cr-13Co-9Mo	Wld. tube	SB-626	...	N06617	Solution ann.	
8	52Ni-22Cr-13Co-9Mo	Wld. tube	SB-626	...	N06617	Solution ann.	
9	52Ni-22Cr-13Co-9Mo	Plate, sheet, strip	SB-168	...	N06617	Annealed	
10	52Ni-22Cr-13Co-9Mo	Plate, sheet, strip	SB-168	...	N06617	Annealed	
11	52Ni-22Cr-13Co-9Mo	Forgings	SB-564	...	N06617	Annealed	
12	52Ni-22Cr-13Co-9Mo	Forgings	SB-564	...	N06617	Annealed	
13	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet, strip	SB-443	2	N06625	Cold rolled/solution ann.	
14	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	2	N06625	Hot rolled/solution ann.	
15	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe & tube	SB-444	2	N06625	Solution ann.	
16	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe & tube	SB-444	2	N06625	Solution ann.	
17	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	2	N06625	Solution ann.	
18	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	2	N06625	Solution ann.	
19	60Ni-22Cr-9Mo-3.5Cb	Smls. & wld. fittings	SB-366	...	N06625	Annealed	
20	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1	N06625	Annealed	
(25)	21	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1	N06625	Annealed
22	60Ni-22Cr-9Mo-3.5Cb	Plate	SB-443	1	N06625	Cold rolled/ann.	
23	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	1	N06625	Hot rolled/ann.	
24	60Ni-22Cr-9Mo-3.5Cb	Sheet, strip	SB-443	1	N06625	Cold rolled/ann.	
25	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe	SB-444	1	N06625	Annealed	
(25)	26	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1	N06625	Annealed
27	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1	N06625	Annealed	
28	60Ni-22Cr-9Mo-3.5Cb	Wld. tube	SB-704	...	N06625	Annealed	
29	60Ni-22Cr-9Mo-3.5Cb	Wld. pipe	SB-705	1	N06625	Annealed	
30	Ni-Cr-Mo-W	Forged fittings	SB-462	...	N06686	Solution ann.	
31	Ni-Cr-Mo-W	Forged fittings	SB-462	...	N06686	Solution ann.	
32	Ni-Cr-Mo-W	Forgings	SB-564	...	N06686	Solution ann.	
33	Ni-Cr-Mo-W	Forgings	SB-564	...	N06686	Solution ann.	
34	Ni-Cr-Mo-W	Rod	SB-574	...	N06686	Solution ann.	
35	Ni-Cr-Mo-W	Rod	SB-574	...	N06686	Solution ann.	
36	Ni-Cr-Mo-W	Plate, sheet, strip	SB-575	...	N06686	Solution ann.	
37	Ni-Cr-Mo-W	Plate, sheet, strip	SB-575	...	N06686	Solution ann.	
38	Ni-Cr-Mo-W	Wld. pipe	SB-619	...	N06686	Solution ann.	
39	Ni-Cr-Mo-W	Wld. pipe	SB-619	...	N06686	Solution ann.	
40	Ni-Cr-Mo-W	Smls. pipe & tube	SB-622	...	N06686	Solution ann.	
41	Ni-Cr-Mo-W	Smls. pipe & tube	SB-622	...	N06686	Solution ann.	
42	Ni-Cr-Mo-W	Wld. tube	SB-626	...	N06686	Solution ann.	
43	Ni-Cr-Mo-W	Wld. tube	SB-626	...	N06686	Solution ann.	
44	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Annealed	
45	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Annealed	

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, T14
2	...	43	80	30	1650	NP	1650	NP	NFN-4	G4, G5, T13
3	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, T18
4	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G5, T17
5	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, T18
6	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G5, T17
7	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G14, T18
8	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G5, G14, T17
9	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, T18
10	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G5, T17
11	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, T18
12	...	43	95	35	1650	NP	1800	NP	NFN-4	G4, G5, T17
13	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G5, G23, T17, W13
14	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G23, T18, W13
15	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G5, G23, T17, W13
16	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G23, T18, W13
17	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G5, G23, T17, W13
18	...	43	100	40	1100	NP	1600	650	NFN-22	G4, G23, T18, W13
19	...	43	110	50	1100	800	1200	650	NFN-17	G23, T16, W5, W12
20	4 < t ≤ 10	43	110	50	1100	800	1200	650	NFN-17	G23, T16
21	4 < t ≤ 10	43	110	50	1100	800	1200	650	NFN-17	G23, T16
22	≤0.375	43	110	55	1100	800	1200	650	NFN-17	G23, T16
23	≤2.75	43	110	55	1100	800	1200	650	NFN-17	G23, T16
24	...	43	120	60	1100	NP	1200	650	NFN-17	G22, G23, T16
25	...	43	120	60	1100	800	1200	650	NFN-17	G22, G23, T16
26	≤4	43	120	60	1100	800	1200	650	NFN-17	G22, G23, T16
27	≤4	43	120	60	1100	800	1200	650	NFN-17	G22, G23, T16
28	...	43	120	60	1100	800	1200	650	NFN-17	G14, G22, G23, T16
29	...	43	120	60	1100	NP	1200	650	NFN-17	G14, G22, G23, T16
30	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	G5
31	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	...
32	...	43	100	45	NP	NP	800	NP	NFN-10	G5
33	...	43	100	45	NP	NP	800	NP	NFN-10	...
34	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	G5
35	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	...
36	...	43	100	45	NP	NP	800	NP	NFN-10	G5
37	...	43	100	45	NP	NP	800	NP	NFN-10	...
38	≤8	43	100	45	NP	NP	800	NP	NFN-10	G5, G14
39	≤8	43	100	45	NP	NP	800	NP	NFN-10	G14
40	...	43	100	45	NP	NP	800	NP	NFN-10	G5
41	...	43	100	45	NP	NP	800	NP	NFN-10	...
42	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	G5, G14
43	≤3 1/2	43	100	45	NP	NP	800	NP	NFN-10	G14
44	...	43	85	35	NP	NP	850	650	NFN-4	...
45	...	43	85	35	NP	NP	850	650	NFN-4	G5

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	20.0	...	17.8	...	16.6	...	15.5	...	14.7	...	14.2	14.0	13.9	13.8	13.8	13.8	13.8	13.7
2	20.0	...	20.0	...	20.0	...	20.0	...	19.9	...	19.2	19.0	18.8	18.7	18.6	18.6	18.6	18.6
3	23.3	...	20.8	...	19.2	...	18.1	...	17.2	...	16.6	16.4	16.2	16.0	15.9	15.8	15.7	15.6
4	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.5	22.1	21.9	21.7	21.5	21.3	21.2	21.0
5	23.3	...	20.8	...	19.2	...	18.1	...	17.2	...	16.6	16.4	16.2	16.0	15.9	15.8	15.7	15.6
6	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.5	22.1	21.9	21.7	21.5	21.3	21.2	21.0
7	19.8	...	17.7	...	16.3	...	15.4	...	14.6	...	14.1	13.9	13.8	13.6	13.5	13.4	13.3	13.3
8	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.1	18.8	18.6	18.4	18.3	18.1	18.0	17.9
9	23.3	...	20.8	...	19.2	...	18.1	...	17.2	...	16.6	16.4	16.2	16.0	15.9	15.8	15.7	15.6
10	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.5	22.1	21.9	21.7	21.5	21.3	21.2	21.0
11	23.3	...	20.8	...	19.2	...	18.1	...	17.2	...	16.6	16.4	16.2	16.0	15.9	15.8	15.7	15.6
12	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	22.5	22.1	21.9	21.7	21.5	21.3	21.2	21.0
13	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.6
14	26.7	...	24.6	...	23.4	...	22.4	...	21.7	...	21.0	20.8	20.5	20.3	20.1	20.0	19.8	19.7
15	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.6
16	26.7	...	24.6	...	23.4	...	22.4	...	21.7	...	21.0	20.8	20.5	20.3	20.1	20.0	19.8	19.7
17	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.6
18	26.7	...	24.6	...	23.4	...	22.4	...	21.7	...	21.0	20.8	20.5	20.3	20.1	20.0	19.8	19.7
19	31.4	...	31.4	...	31.4	...	30.8	...	30.2	...	29.7	29.4	29.1	28.9	28.6	28.3	28.0	27.7
20	31.4	...	31.4	...	31.4	...	30.8	...	30.2	...	29.7	29.4	29.1	28.9	28.6	28.3	28.0	27.7
21	31.4	...	31.4	...	31.4	...	30.8	...	30.2	...	29.7	29.4	29.1	28.9	28.6	28.3	28.0	27.7
22	31.4	...	31.4	...	31.4	...	30.8	...	30.2	...	29.7	29.4	29.1	28.9	28.6	28.3	28.0	27.7
23	31.4	...	31.4	...	31.4	...	30.8	...	30.2	...	29.7	29.4	29.1	28.9	28.6	28.3	28.0	27.7
24	34.3	...	34.3	...	34.3	...	33.6	...	32.9	...	32.4	32.1	31.8	31.5	31.2	30.9	30.6	30.3
25	34.3	...	34.3	...	34.3	...	33.6	...	32.9	...	32.4	32.1	31.8	31.5	31.2	30.9	30.6	30.3
26	34.3	...	34.3	...	34.3	...	33.6	...	32.9	...	32.4	32.1	31.8	31.5	31.2	30.9	30.6	30.3
27	34.3	...	34.3	...	34.3	...	33.6	...	32.9	...	32.4	32.1	31.8	31.5	31.2	30.9	30.6	30.3
28	29.1	...	29.1	...	29.1	...	28.5	...	28.0	...	27.5	27.3	27.0	26.8	26.5	26.3	26.0	25.7
29	29.1	...	29.1	...	29.1	...	28.5	...	28.0	...	27.5	27.3	27.0	26.8	26.5	26.3	26.0	25.7
30	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	25.9	25.7	25.4	25.2	24.9	...	...	...
31	28.6	...	24.9	...	23.4	...	22.5	...	21.6	...	20.8	20.4	20.1	19.9	19.9	...	...	...
32	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	25.9	25.7	25.4	25.2	24.9	...	...	...
33	28.6	...	24.9	...	23.4	...	22.5	...	21.6	...	20.8	20.4	20.1	19.9	19.9	...	...	...
34	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	25.9	25.7	25.4	25.2	24.9	...	...	...
35	28.6	...	24.9	...	23.4	...	22.5	...	21.6	...	20.8	20.4	20.1	19.9	19.9	...	...	...
36	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	25.9	25.7	25.4	25.2	24.9	...	...	...
37	28.6	...	24.9	...	23.4	...	22.5	...	21.6	...	20.8	20.4	20.1	19.9	19.9	...	...	...
38	24.3	...	24.3	...	24.0	...	23.1	...	22.5	...	22.0	21.8	21.6	21.4	21.2	...	...	...
39	24.3	...	21.2	...	19.9	...	19.1	...	18.4	...	17.7	17.3	17.1	16.9	16.9	...	...	...
40	28.6	...	28.6	...	28.2	...	27.2	...	26.5	...	25.9	25.7	25.4	25.2	24.9	...	...	...
41	28.6	...	24.9	...	23.4	...	22.5	...	21.6	...	20.8	20.4	20.1	19.9	19.9	...	...	...
42	24.3	...	24.3	...	24.0	...	23.1	...	22.5	...	22.0	21.8	21.6	21.4	21.2	...	...	...
43	24.3	...	21.2	...	19.9	...	19.1	...	18.4	...	17.7	17.3	17.1	16.9	16.9	...	...	...
44	23.3	...	21.1	...	19.9	...	19.1	...	18.6	...	18.4	18.4	18.4	18.4	18.4	18.4	...	...
45	23.3	...	23.3	...	23.3	...	23.3	...	23.1	...	22.9	22.9	22.8	22.7	22.6	22.5	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	13.7	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
2	17.6	13.6	10.4	8.0	6.1	4.6	3.6	2.8	2.1	1.7	1.3	1.1	0.87	0.71	...	...	...
3	15.5	15.4	15.4	15.3	15.3	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
4	20.9	20.9	20.8	20.7	18.1	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
5	15.5	15.4	15.4	15.3	15.3	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
6	20.9	20.9	20.8	20.7	18.1	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
7	13.2	13.1	13.1	13.1	13.0	12.3	9.5	7.4	5.6	4.3	3.3	2.6	2.0	1.5	1.2	0.9	0.62
8	17.8	17.8	17.7	17.6	15.4	12.3	9.5	7.4	5.6	4.3	3.3	2.6	2.0	1.5	1.2	0.9	0.62
9	15.5	15.4	15.4	15.3	15.3	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
10	20.9	20.9	20.8	20.7	18.1	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
11	15.5	15.4	15.4	15.3	15.3	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
12	20.9	20.9	20.8	20.7	18.1	14.5	11.2	8.7	6.6	5.1	3.9	3.0	2.3	1.8	1.4	1.1	0.73
13	26.4	26.3	26.2	26.1	20.0	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
14	19.6	19.5	19.4	19.3	19.3	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
15	26.4	26.3	26.2	26.1	20.0	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
16	19.6	19.5	19.4	19.3	19.3	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
17	26.4	26.3	26.2	26.1	20.0	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
18	19.6	19.5	19.4	19.3	19.3	15.0	11.6	8.5	6.7	4.9	3.8	2.6	1.9	...	...	...	...
19	27.4	27.0	26.6	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
20	27.4	27.0	26.6	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
21	27.4	27.0	26.6	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
22	27.4	27.0	26.6	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
23	27.4	27.0	26.6	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
24	29.9	29.5	29.0	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
25	29.9	29.5	29.0	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
26	29.9	29.5	29.0	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
27	29.9	29.5	29.0	21.0	13.2	...	...	...	...	...	...	...	...	...	...	...	...
28	25.4	25.1	24.7	17.9	11.2	...	...	...	...	...	...	...	...	...	...	...	...
29	25.4	25.1	24.7	17.9	11.2	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	58Ni-29Cr-9Fe	Plate, sheet, strip	SB-168	...	N06690	Annealed
2	58Ni-29Cr-9Fe	Plate, sheet, strip	SB-168	...	N06690	Annealed
3	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold drawn/ann.
4	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold drawn/ann.
5	49Ni-25Cr-18Fe-6Mo	Plate, sheet, strip	SB-582	...	N06975	Solution ann.
6	49Ni-25Cr-18Fe-6Mo	Plate, sheet, strip	SB-582	...	N06975	Solution ann.
7	49Ni-25Cr-18Fe-6Mo	Wld. pipe	SB-619	...	N06975	Solution ann.
8	49Ni-25Cr-18Fe-6Mo	Wld. pipe	SB-619	...	N06975	Solution ann.
9	49Ni-25Cr-18Fe-6Mo	Smls. pipe & tube	SB-622	...	N06975	Solution ann.
10	49Ni-25Cr-18Fe-6Mo	Smls. pipe & tube	SB-622	...	N06975	Solution ann.
11	49Ni-25Cr-18Fe-6Mo	Wld. tube	SB-626	...	N06975	Solution ann.
12	49Ni-25Cr-18Fe-6Mo	Wld. tube	SB-626	...	N06975	Solution ann.
13	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
14	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
15	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
16	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
17	47Ni-22Cr-20Fe-7Mo	Smls. & wld. fittings	SB-366	...	N06985	Annealed
18	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
19	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
20	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
21	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
22	47Ni-22Cr-20Fe-7Mo	Wld. pipe	SB-619	...	N06985	Annealed
23	47Ni-22Cr-20Fe-7Mo	Wld. pipe	SB-619	...	N06985	Annealed
24	47Ni-22Cr-20Fe-7Mo	Smls. pipe & tube	SB-622	...	N06985	Annealed
25	47Ni-22Cr-20Fe-7Mo	Smls. pipe & tube	SB-622	...	N06985	Annealed
26	47Ni-22Cr-20Fe-7Mo	Wld. tube	SB-626	...	N06985	Annealed
27	47Ni-22Cr-20Fe-7Mo	Wld. tube	SB-626	...	N06985	Annealed
28	35Ni-35Fe-20Cr-Cb	Forgings	SB-462	...	N08020	Annealed
29	35Ni-35Fe-20Cr-Cb	Forgings	SB-462	...	N08020	Annealed
30	35Ni-35Fe-20Cr-Cb	Plate	SB-463	...	N08020	Annealed
31	35Ni-35Fe-20Cr-Cb	Plate	SB-463	...	N08020	Annealed
32	35Ni-35Fe-20Cr-Cb	Bar	SB-473	...	N08020	Annealed
33	35Ni-35Fe-20Cr-Cb	Bar	SB-473	...	N08020	Annealed
34	35Ni-35Fe-20Cr-Cb	Smls. pipe & tube	SB-729	...	N08020	Annealed
35	35Ni-35Fe-20Cr-Cb	Smls. pipe & tube	SB-729	...	N08020	Annealed
36	35Ni-35Fe-20Cr-Cb	Wld. pipe	SB-464	...	N08020	Wld. ann.
37	35Ni-35Fe-20Cr-Cb	Wld. pipe	SB-464	...	N08020	Wld. ann.
38	35Ni-35Fe-20Cr-Cb	Wld. pipe	SB-464	...	N08020	Wld. ann.
39	35Ni-35Fe-20Cr-Cb	Wld. tube	SB-468	...	N08020	Wld. ann.
40	35Ni-35Fe-20Cr-Cb	Wld. tube	SB-468	...	N08020	Wld. ann.
41	35Ni-35Fe-20Cr-Cb	Wld. tube	SB-468	...	N08020	Wld. ann.
42	35Ni-35Fe-20Cr-Cb	Smls. & wld. fittings	SB-366	...	N08020	Annealed
43	37Ni-33Fe-23Cr-4Mo-Cu	Wld. pipe	SB-464	...	N08024	Wld. ann.
44	37Ni-33Fe-23Cr-4Mo-Cu	Wld. pipe	SB-464	...	N08024	Wld. ann.
45	37Ni-33Fe-23Cr-4Mo-Cu	Wld. tube	SB-468	...	N08024	Wld. ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	43	85	35	NP	NP	850	650	NFN-4	...
2	...	43	85	35	NP	NP	850	650	NFN-4	G5
3	...	43	85	35	1200	NP	850	650	NFN-4	H3, T12
4	...	43	85	35	1200	NP	850	650	NFN-4	G5, H3, T12
5	...	45	85	32	NP	NP	800	650	NFN-11	...
6	...	45	85	32	NP	NP	800	650	NFN-11	G5
7	...	45	85	32	NP	NP	800	650	NFN-11	G14
8	...	45	85	32	NP	NP	800	650	NFN-11	G5, G14
9	...	45	85	32	NP	NP	800	650	NFN-11	...
10	...	45	85	32	NP	NP	800	650	NFN-11	G5
11	...	45	85	32	NP	NP	800	650	NFN-11	G14
12	...	45	85	32	NP	NP	800	650	NFN-11	G5, G14
13	> ³ / ₄	45	85	30	NP	NP	800	650	NFN-19	...
14	> ³ / ₄	45	85	30	NP	NP	800	650	NFN-19	G5
15	> ³ / ₄	45	85	30	NP	NP	800	650	NFN-19	...
16	> ³ / ₄	45	85	30	NP	NP	800	650	NFN-19	G5
17	...	45	90	35	NP	NP	800	650	NFN-18	G5, W12
18	≤ ³ / ₄	45	90	35	NP	NP	800	650	NFN-18	...
19	≤ ³ / ₄	45	90	35	NP	NP	800	650	NFN-18	G5
20	≤ ³ / ₄	45	90	35	NP	NP	800	650	NFN-18	...
21	≤ ³ / ₄	45	90	35	NP	NP	800	650	NFN-18	G5
22	...	45	90	35	NP	NP	800	650	NFN-18	G14
23	...	45	90	35	NP	NP	800	650	NFN-18	G5, G14
24	...	45	90	35	NP	NP	800	650	NFN-18	...
25	...	45	90	35	NP	NP	800	650	NFN-18	G5
26	...	45	90	35	NP	NP	800	650	NFN-18	G14
27	...	45	90	35	NP	NP	800	650	NFN-18	G5, G14
28	...	45	80	35	NP	800	800	650	NFN-12	G5
29	...	45	80	35	NP	NP	800	650	NFN-12	...
30	...	45	80	35	NP	NP	800	650	NFN-12	...
31	...	45	80	35	NP	800	800	650	NFN-12	G5
32	...	45	80	35	NP	800	800	650	NFN-12	G5
33	...	45	80	35	NP	NP	800	650	NFN-12	...
34	...	45	80	35	NP	NP	800	650	NFN-12	...
35	...	45	80	35	NP	NP	800	650	NFN-12	G5
36	...	45	80	35	NP	800	NP	NP	NFN-12	G5, W5
37	...	45	80	35	NP	NP	800	650	NFN-12	G14
38	...	45	80	35	NP	NP	800	650	NFN-12	G5, G14
39	...	45	80	35	NP	800	NP	NP	NFN-12	G5, W5
40	...	45	80	35	NP	NP	800	650	NFN-12	G14
41	...	45	80	35	NP	NP	800	650	NFN-12	G5, G14
42	...	45	85	40	NP	800	800	650	NFN-12	G5, W5, W12
43	...	45	80	35	NP	NP	NP	650	NFN-13	G14
44	...	45	80	35	NP	NP	NP	650	NFN-13	G5, G14
45	...	45	80	35	NP	NP	NP	650	NFN-13	G14

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	23.3	...	21.1	...	19.9	...	19.1	...	18.6	...	18.4	18.4	18.4	18.4	18.4	18.4	...	...
2	23.3	...	23.3	...	23.3	...	23.3	...	23.1	...	22.9	22.9	22.8	22.7	22.6	22.5	...	...
3	23.3	...	21.1	...	19.9	...	19.1	...	18.6	...	18.4	18.4	18.4	18.4	18.4	18.4	18.3	16.5
4	23.3	...	23.3	...	23.3	...	23.3	...	23.1	...	22.9	22.9	22.8	22.7	22.6	22.5	22.2	16.5
5	21.3	...	19.5	...	18.5	...	17.5	...	16.5	...	15.6	15.3	15.0	14.8	14.7	...	...	...
6	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.1	20.6	20.2	20.0	19.8	...	...	...
7	18.1	...	16.6	...	15.7	...	14.9	...	14.0	...	13.3	13.0	12.7	12.6	12.5	...	...	...
8	18.1	...	18.1	...	18.1	...	18.1	...	18.1	...	17.9	17.5	17.2	17.0	16.8	...	...	...
9	21.3	...	19.5	...	18.5	...	17.5	...	16.5	...	15.6	15.3	15.0	14.8	14.7	...	...	...
10	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.1	20.6	20.2	20.0	19.8	...	...	...
11	18.1	...	16.6	...	15.7	...	14.9	...	14.0	...	13.3	13.0	12.7	12.6	12.5	...	...	...
12	18.1	...	18.1	...	18.1	...	18.1	...	18.1	...	17.9	17.5	17.2	17.0	16.8	...	...	...
13	20.0	...	17.8	...	16.2	...	14.9	...	13.9	...	13.1	12.8	12.5	12.3	12.0	...	...	...
14	20.0	...	20.0	...	20.0	...	20.0	...	18.8	...	17.7	17.3	16.9	16.5	16.2	...	...	...
15	20.0	...	17.8	...	16.2	...	14.9	...	13.9	...	13.1	12.8	12.5	12.3	12.0	...	...	...
16	20.0	...	20.0	...	20.0	...	20.0	...	18.8	...	17.7	17.3	16.9	16.5	16.2	...	...	...
17	23.3	...	23.3	...	23.3	...	23.3	...	21.9	...	20.7	20.2	19.7	19.3	18.9	...	...	...
18	23.3	...	20.8	...	18.9	...	17.4	...	16.2	...	15.3	14.9	14.6	14.3	14.0	...	...	...
19	23.3	...	23.3	...	23.3	...	23.3	...	21.9	...	20.7	20.2	19.7	19.3	18.9	...	...	...
20	23.3	...	20.8	...	18.9	...	17.4	...	16.2	...	15.3	14.9	14.6	14.3	14.0	...	...	...
21	23.3	...	23.3	...	23.3	...	23.3	...	21.9	...	20.7	20.2	19.7	19.3	18.9	...	...	...
22	19.8	...	17.7	...	16.1	...	14.8	...	13.8	...	13.0	12.7	12.4	12.1	11.9	...	...	...
23	19.8	...	19.8	...	19.8	...	19.8	...	18.6	...	17.6	17.1	16.8	16.4	16.1	...	...	...
24	23.3	...	20.8	...	18.9	...	17.4	...	16.2	...	15.3	14.9	14.6	14.3	14.0	...	...	...
25	23.3	...	23.3	...	23.3	...	23.3	...	21.9	...	20.7	20.2	19.7	19.3	18.9	...	...	...
26	19.8	...	17.7	...	16.1	...	14.8	...	13.8	...	13.0	12.7	12.4	12.1	11.9	...	...	...
27	19.8	...	19.8	...	19.8	...	19.8	...	18.6	...	17.6	17.1	16.8	16.4	16.1	...	...	...
28	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
29	22.9	...	20.6	...	19.7	...	18.9	...	18.2	...	17.7	17.5	17.4	17.2	16.8	...	...	...
30	22.9	...	20.6	...	19.7	...	18.9	...	18.2	...	17.7	17.5	17.4	17.2	16.8	...	...	...
31	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
32	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
33	22.9	...	20.6	...	19.7	...	18.9	...	18.2	...	17.7	17.5	17.4	17.2	16.8	...	...	...
34	22.9	...	20.6	...	19.7	...	18.9	...	18.2	...	17.7	17.5	17.4	17.2	16.8	...	...	...
35	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
36	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
37	19.4	...	17.5	...	16.7	...	16.1	...	15.5	...	15.0	14.9	14.8	14.6	14.3	...	...	...
38	19.4	...	19.4	...	19.2	...	18.8	...	18.8	...	18.8	18.7	18.6	18.5	18.5	...	...	...
39	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
40	19.4	...	17.5	...	16.7	...	16.1	...	15.5	...	15.0	14.9	14.8	14.6	14.3	...	...	...
41	19.4	...	19.4	...	19.2	...	18.8	...	18.8	...	18.8	18.7	18.6	18.5	18.5	...	...	...
42	22.9	...	22.9	...	22.6	...	22.2	...	22.1	...	22.1	22.0	21.9	21.8	21.8	...	...	...
43	19.4	...	17.5	...	16.3	...	15.4	...	14.5	...	13.6	13.2	12.9	12.6	12.4	...	...	...
44	19.4	...	19.4	...	19.2	...	18.6	...	18.2	...	17.7	17.5	17.3	17.0	16.7	...	...	...
45	19.4	...	17.5	...	16.3	...	15.4	...	14.5	...	13.6	13.2	12.9	12.6	12.4	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	11.6	9.0	6.5	4.5	3.0	...	...	...	...	...	...	...	...	...	...	...	...
4	11.6	9.0	6.5	4.5	3.0	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	37Ni-33Fe-23Cr-4Mo-Cu	Wld. tube	SB-468	...	N08024	Wld. ann.
2	35Ni-30Fe-24Cr-6Mo-Cu	Wld. pipe	SB-464	...	N08026	Wld. ann.
3	35Ni-30Fe-24Cr-6Mo-Cu	Wld. pipe	SB-464	...	N08026	Wld. ann.
4	35Ni-30Fe-24Cr-6Mo-Cu	Wld. tube	SB-468	...	N08026	Wld. ann.
5	35Ni-30Fe-24Cr-6Mo-Cu	Wld. tube	SB-468	...	N08026	Wld. ann.
6	31Ni-31Fe-29Cr-Mo	Smls. tube	SB-668	...	N08028	Annealed
7	31Ni-31Fe-29Cr-Mo	Smls. tube	SB-668	...	N08028	Annealed
8	31Ni-31Fe-29Cr-Mo	Plate, sheet, strip	SB-709	...	N08028	Annealed
9	31Ni-31Fe-29Cr-Mo	Plate, sheet, strip	SB-709	...	N08028	Annealed
10	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. & wld. fittings	SB-366	...	N08031	Solution ann.
11	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forged fittings	SB-462	...	N08031	Solution ann.
12	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forged fittings	SB-462	...	N08031	Solution ann.
13	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forgings	SB-564	...	N08031	Solution ann.
14	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forgings	SB-564	...	N08031	Solution ann.
15	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Rod	SB-581	...	N08031	Solution ann.
16	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Rod	SB-581	...	N08031	Solution ann.
17	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. pipe	SB-619	...	N08031	Solution ann.
18	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. pipe	SB-619	...	N08031	Solution ann.
19	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. pipe & tube	SB-622	...	N08031	Solution ann.
20	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. pipe & tube	SB-622	...	N08031	Solution ann.
21	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08031	Solution ann.
22	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08031	Solution ann.
23	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. tube	SB-626	...	N08031	Solution ann.
24	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. tube	SB-626	...	N08031	Solution ann.
25	37Ni-33Fe-25Cr	Condenser tube	SB-163	...	N08120	Solution ann.
26	37Ni-33Fe-25Cr	Condenser tube	SB-163	...	N08120	Solution ann.
27	37Ni-33Fe-25Cr	Smls. & wld. fittings	SB-366	...	N08120	Solution ann.
28	37Ni-33Fe-25Cr	Smls. pipe & tube	SB-407	...	N08120	Solution ann.
29	37Ni-33Fe-25Cr	Smls. pipe & tube	SB-407	...	N08120	Solution ann.
30	37Ni-33Fe-25Cr	Bar, rod	SB-408	...	N08120	Solution ann.
31	37Ni-33Fe-25Cr	Bar, rod	SB-408	...	N08120	Solution ann.
32	37Ni-33Fe-25Cr	Plate, sheet, strip	SB-409	...	N08120	Solution ann.
33	37Ni-33Fe-25Cr	Plate, sheet, strip	SB-409	...	N08120	Solution ann.
34	37Ni-33Fe-25Cr	Wld. pipe	SB-514	...	N08120	Solution ann.
35	37Ni-33Fe-25Cr	Wld. pipe	SB-514	...	N08120	Solution ann.
36	37Ni-33Fe-25Cr	Wld. tube	SB-515	...	N08120	Solution ann.
37	37Ni-33Fe-25Cr	Wld. tube	SB-515	...	N08120	Solution ann.
38	37Ni-33Fe-25Cr	Forgings	SB-564	...	N08120	Solution ann.
39	37Ni-33Fe-25Cr	Forgings	SB-564	...	N08120	Solution ann.
40	26Ni-43Fe-22Cr-5Mo	Wld. pipe	SB-619	...	N08320	Solution ann.
41	26Ni-43Fe-22Cr-5Mo	Wld. pipe	SB-619	...	N08320	Solution ann.
42	26Ni-43Fe-22Cr-5Mo	Plate, sheet, strip	SB-620	...	N08320	Solution ann.
43	26Ni-43Fe-22Cr-5Mo	Plate, sheet, strip	SB-620	...	N08320	Solution ann.
44	26Ni-43Fe-22Cr-5Mo	Rod	SB-621	...	N08320	Solution ann.
45	26Ni-43Fe-22Cr-5Mo	Rod	SB-621	...	N08320	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	80	35	NP	NP	NP	650	NFN-13	G5, G14
2	...	45	80	35	NP	NP	NP	650	NFN-13	G14
3	...	45	80	35	NP	NP	NP	650	NFN-13	G5, G14
4	...	45	80	35	NP	NP	NP	650	NFN-13	G14
5	...	45	80	35	NP	NP	NP	650	NFN-13	G5, G14
6	...	45	73	31	NP	600	850	650	NFN-13	...
7	...	45	73	31	NP	600	850	650	NFN-13	G5
8	...	45	73	31	NP	NP	850	650	NFN-13	...
9	...	45	73	31	NP	NP	850	650	NFN-13	G5
10	...	45	94	40	NP	NP	800	NP	NFN-11	G5, W12
11	...	45	94	40	NP	NP	800	NP	NFN-11	...
12	...	45	94	40	NP	NP	800	NP	NFN-11	G5
13	...	45	94	40	NP	NP	800	NP	NFN-11	...
14	...	45	94	40	NP	NP	800	NP	NFN-11	G5
15	...	45	94	40	NP	NP	800	NP	NFN-11	...
16	...	45	94	40	NP	NP	800	NP	NFN-11	G5
17	...	45	94	40	NP	NP	800	NP	NFN-11	G14
18	...	45	94	40	NP	NP	800	NP	NFN-11	G5, G14
19	...	45	94	40	NP	NP	800	NP	NFN-11	...
20	...	45	94	40	NP	NP	800	NP	NFN-11	G5
21	...	45	94	40	NP	NP	800	NP	NFN-11	...
22	...	45	94	40	NP	NP	800	NP	NFN-11	G5
23	...	45	94	40	NP	NP	800	NP	NFN-11	G14
24	...	45	94	40	NP	NP	800	NP	NFN-11	G5, G14
25	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G14, T16
26	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, G14, T15
27	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, T15, W12
28	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, T16
29	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, T15
30	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, T16
31	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, T15
32	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, T16
33	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, T15
34	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G14, T16
35	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, G14, T15
36	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G14, T16
37	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, G14, T15
38	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, T16
39	...	45	90	40	NP	NP	1650	NP	NFN-9	G4, G5, T15
40	...	45	75	28	NP	NP	800	650	NFN-13	G14
41	...	45	75	28	NP	NP	800	650	NFN-13	G5, G14
42	...	45	75	28	NP	NP	800	650	NFN-13	...
43	...	45	75	28	NP	NP	800	650	NFN-13	G5
44	...	45	75	28	NP	NP	800	650	NFN-13	...
45	...	45	75	28	NP	NP	800	650	NFN-13	G5

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	19.4	...	19.4	...	19.2	...	18.6	...	18.2	...	17.7	17.5	17.3	17.0	16.7	...	...	...
2	19.4	...	17.6	...	16.1	...	14.9	...	13.8	...	13.0	12.7	12.4	12.1	11.9	...	...	...
3	19.4	...	19.4	...	19.1	...	18.5	...	18.0	...	17.5	17.1	16.7	16.3	16.0	...	...	...
4	19.4	...	17.6	...	16.1	...	14.9	...	13.8	...	13.0	12.7	12.4	12.1	11.9	...	...	...
5	19.4	...	19.4	...	19.1	...	18.5	...	18.0	...	17.5	17.1	16.7	16.3	16.0	...	...	...
6	20.7	...	18.9	...	17.7	...	16.5	...	15.4	...	14.4	14.0	13.6	13.1	12.8	12.4	...	...
7	20.7	...	20.7	...	20.1	...	19.3	...	18.7	...	18.2	18.0	17.8	17.5	17.2	16.7	...	...
8	20.7	...	18.9	...	17.7	...	16.5	...	15.4	...	14.4	14.0	13.6	13.1	12.8	12.4	...	...
9	20.7	...	20.7	...	20.1	...	19.3	...	18.7	...	18.2	18.0	17.8	17.5	17.2	16.7	...	...
10	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
11	26.7	...	22.0	...	19.8	...	18.3	...	17.3	...	16.4	16.1	15.8	15.5	15.2	...	...	...
12	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
13	26.7	...	22.0	...	19.8	...	18.3	...	17.3	...	16.4	16.1	15.8	15.5	15.2	...	...	...
14	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
15	26.7	...	22.0	...	19.8	...	18.3	...	17.3	...	16.4	16.1	15.8	15.5	15.2	...	...	...
16	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
17	22.7	...	18.7	...	16.8	...	15.6	...	14.7	...	13.9	13.7	13.4	13.2	12.9	...	...	...
18	22.7	...	22.7	...	21.9	...	20.8	...	19.8	...	18.9	18.4	18.1	17.8	17.4	...	...	...
19	26.7	...	22.0	...	19.8	...	18.3	...	17.3	...	16.4	16.1	15.8	15.5	15.2	...	...	...
20	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
21	26.7	...	22.0	...	19.8	...	18.3	...	17.3	...	16.4	16.1	15.8	15.5	15.2	...	...	...
22	26.7	...	26.7	...	25.8	...	24.5	...	23.3	...	22.2	21.7	21.3	20.9	20.5	...	...	...
23	22.7	...	18.7	...	16.8	...	15.6	...	14.7	...	13.9	13.7	13.4	13.2	12.9	...	...	...
24	22.7	...	22.7	...	21.9	...	20.8	...	19.8	...	18.9	18.4	18.1	17.8	17.4	...	...	...
25	25.7	...	23.5	...	21.6	...	19.9	...	18.6	...	17.7	17.3	17.0	16.8	16.6	16.5	16.4	16.3
26	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
27	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
28	25.7	...	23.5	...	21.6	...	19.9	...	18.6	...	17.7	17.3	17.0	16.8	16.6	16.5	16.4	16.3
29	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
30	25.7	...	23.5	...	21.6	...	19.9	...	18.6	...	17.7	17.3	17.0	16.8	16.6	16.5	16.4	16.3
31	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
32	25.7	...	23.5	...	21.6	...	19.9	...	18.6	...	17.7	17.3	17.0	16.8	16.6	16.5	16.4	16.3
33	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
34	21.8	...	20.0	...	18.4	...	16.9	...	15.8	...	15.0	14.7	14.5	14.3	14.1	14.0	13.9	13.9
35	21.8	...	21.8	...	21.3	...	20.6	...	20.1	...	20.0	19.9	19.6	19.3	19.0	19.0	18.9	18.8
36	21.8	...	20.0	...	18.4	...	16.9	...	15.8	...	15.0	14.7	14.5	14.3	14.1	14.0	13.9	13.9
37	21.8	...	21.8	...	21.3	...	20.6	...	20.1	...	20.0	19.9	19.6	19.3	19.0	19.0	18.9	18.8
38	25.7	...	23.5	...	21.6	...	19.9	...	18.6	...	17.7	17.3	17.0	16.8	16.6	16.5	16.4	16.3
39	25.7	...	25.7	...	25.0	...	24.2	...	23.7	...	23.5	23.4	23.0	22.7	22.4	22.3	22.2	22.1
40	15.9	...	14.7	...	13.9	...	13.1	...	12.3	...	11.7	11.4	11.2	11.0	10.8	...	...	...
41	15.9	...	15.9	...	15.9	...	15.9	...	15.9	...	15.8	15.4	15.1	14.9	14.6	...	...	...
42	18.7	...	17.3	...	16.3	...	15.4	...	14.5	...	13.8	13.5	13.2	13.0	12.7	...	...	...
43	18.7	...	18.7	...	18.7	...	18.7	...	18.7	...	18.6	18.2	17.8	17.5	17.2	...	...	...
44	18.7	...	17.3	...	16.3	...	15.4	...	14.5	...	13.8	13.5	13.2	13.0	12.7	...	...	...
45	18.7	...	18.7	...	18.7	...	18.7	...	18.7	...	18.6	18.2	17.8	17.5	17.2	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	16.3	16.3	16.2	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
26	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
27	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
28	16.3	16.3	16.2	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
29	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
30	16.3	16.3	16.2	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
31	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
32	16.3	16.3	16.2	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
33	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
34	13.9	13.9	13.8	12.1	10.5	8.0	6.5	5.3	4.3	3.4	2.7	2.2	1.7	1.2	...	...	...
35	18.7	18.6	15.2	12.1	10.5	8.0	6.5	5.3	4.3	3.4	2.7	2.2	1.7	1.2	...	...	...
36	13.9	13.9	13.8	12.1	10.5	8.0	6.5	5.3	4.3	3.4	2.7	2.2	1.7	1.2	...	...	...
37	18.7	18.6	15.2	12.1	10.5	8.0	6.5	5.3	4.3	3.4	2.7	2.2	1.7	1.2	...	...	...
38	16.3	16.3	16.2	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
39	22.0	21.9	17.9	14.2	12.3	9.4	7.6	6.2	5.0	4.0	3.2	2.6	2.0	1.4	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	26Ni-43Fe-22Cr-5Mo	Smls. pipe & tube	SB-622	...	N08320	Solution ann.
2	26Ni-43Fe-22Cr-5Mo	Smls. pipe & tube	SB-622	...	N08320	Solution ann.
3	26Ni-43Fe-22Cr-5Mo	Wld. tube	SB-626	...	N08320	Solution ann.
4	26Ni-43Fe-22Cr-5Mo	Wld. tube	SB-626	...	N08320	Solution ann.
5	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...	N08330	...
6	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...	N08330	...
7	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...	N08330	...
8	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...	N08330	...
9	35Ni-19Cr-1 $\frac{1}{4}$ Si	Pipe	SB-535	...	N08330	...
10	35Ni-19Cr-1 $\frac{1}{4}$ Si	Pipe	SB-535	...	N08330	...
11	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate	SB-536	...	N08330	...
12	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate	SB-536	...	N08330	...
13	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. fittings	SB-366	...	N08330	Annealed
14	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. pipe	SB-535	...	N08330	Annealed
15	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. pipe	SB-535	...	N08330	Annealed
16	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate, sheet, strip	SB-536	...	N08330	Annealed
17	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate, sheet, strip	SB-536	...	N08330	Annealed
18	35Ni-19Cr-1 $\frac{1}{4}$ Si	Wld. pipe	SB-710	...	N08330	Annealed
19	35Ni-19Cr-1 $\frac{1}{4}$ Si	Wld. pipe	SB-710	...	N08330	Annealed
20	35Ni-23Cr-7.5Mo-N	Plate, sheet, strip	SB-625	...	N08354	Solution ann.
21	35Ni-23Cr-7.5Mo-N	Plate, sheet, strip	SB-625	...	N08354	Solution ann.
22	35Ni-23Cr-7.5Mo-N	Bar, wire	SB-649	...	N08354	Solution ann.
23	35Ni-23Cr-7.5Mo-N	Bar, wire	SB-649	...	N08354	Solution ann.
24	35Ni-23Cr-7.5Mo-N	Wld. pipe	SB-673	...	N08354	Solution ann.
25	35Ni-23Cr-7.5Mo-N	Wld. pipe	SB-673	...	N08354	Solution ann.
26	35Ni-23Cr-7.5Mo-N	Wld. tube	SB-674	...	N08354	Solution ann.
27	35Ni-23Cr-7.5Mo-N	Wld. tube	SB-674	...	N08354	Solution ann.
28	35Ni-23Cr-7.5Mo-N	Smls. pipe & tube	SB-677	...	N08354	Solution ann.
29	35Ni-23Cr-7.5Mo-N	Smls. pipe & tube	SB-677	...	N08354	Solution ann.
30	46Fe-24Ni-21Cr-6Mo-N	Smls. & wld. fittings	SB-366	...	N08367	Solution ann.
31	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-462	...	N08367	Solution ann.
32	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-462	...	N08367	Solution ann.
33	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-564	...	N08367	Solution ann.
34	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-564	...	N08367	Solution ann.
35	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
36	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
37	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
38	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
39	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
40	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
41	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
42	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
43	46Fe-24Ni-21Cr-6Mo-N	Bar, rod, wire	SB-691	...	N08367	Solution ann.
44	46Fe-24Ni-21Cr-6Mo-N	Bar, rod, wire	SB-691	...	N08367	Solution ann.
45	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	75	28	NP	NP	800	650	NFN-13	...
2	...	45	75	28	NP	NP	800	650	NFN-13	G5
3	...	45	75	28	NP	NP	800	650	NFN-13	G14
4	...	45	75	28	NP	NP	800	650	NFN-13	G5, G14
5	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, H2, T14
6	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, G5, H2, T12
7	...	46	70	30	NP	NP	1650	650	NFN-13	G4, H1, T14
8	...	46	70	30	NP	NP	1650	650	NFN-13	G4, G5, H1, T12
9	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, H2, T14
10	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, G5, H2, T12
11	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, H2, T14
12	...	46	70	30	1500	NP	NP	NP	NFN-13	G2, G5, H2, T12
13	...	46	70	30	NP	NP	1650	650	NFN-13	G4, G5, T12, W12
14	...	46	70	30	NP	NP	1500	650	NFN-13	H1, T14, W12
15	...	46	70	30	NP	NP	1500	650	NFN-13	G5, H1, T12, W12
16	...	46	70	30	NP	NP	1650	650	NFN-13	G4, H1, T14
17	...	46	70	30	NP	NP	1650	650	NFN-13	G4, G5, H1, T12
18	...	46	70	30	NP	NP	1650	650	NFN-13	G4, G14, H1, T14
19	...	46	70	30	NP	NP	1650	650	NFN-13	G4, G5, G14, H1, T12
20	...	45	93	43	NP	NP	800	NP	HA-6	...
21	...	45	93	43	NP	NP	800	NP	HA-6	G5
22	...	45	93	43	NP	NP	800	NP	HA-6	...
23	...	45	93	43	NP	NP	800	NP	HA-6	G5
24	...	45	93	43	NP	NP	800	NP	HA-6	G14
25	...	45	93	43	NP	NP	800	NP	HA-6	G5, G14
26	...	45	93	43	NP	NP	800	NP	HA-6	G14
27	...	45	93	43	NP	NP	800	NP	HA-6	G5, G14
28	...	45	93	43	NP	NP	800	NP	HA-6	...
29	...	45	93	43	NP	NP	800	NP	HA-6	G5
30	$>3/16$	45	95	45	NP	800	800	NP	NFN-12	G5, W5, W12
31	...	45	95	45	NP	800	800	650	NFN-12	...
32	...	45	95	45	NP	800	800	650	NFN-12	G5
33	...	45	95	45	NP	800	800	650	NFN-12	...
34	...	45	95	45	NP	800	800	650	NFN-12	G5
35	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G14
36	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G5, G14
37	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G14
38	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G5, G14
39	$>3/16$	45	95	45	NP	800	800	650	NFN-12	...
40	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G5
41	$>3/16$	45	95	45	NP	800	800	650	NFN-12	...
42	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G5
43	...	45	95	45	NP	800	800	650	NFN-12	...
44	...	45	95	45	NP	800	800	650	NFN-12	G5
45	$>3/16$	45	95	45	NP	800	800	650	NFN-12	G14

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	18.7	...	17.3	...	16.3	...	15.4	...	14.5	...	13.8	13.5	13.2	13.0	12.7	...	...	...
2	18.7	...	18.7	...	18.7	...	18.7	...	18.7	...	18.6	18.2	17.8	17.5	17.2	...	...	...
3	15.9	...	14.7	...	13.9	...	13.1	...	12.3	...	11.7	11.4	11.2	11.0	10.8	...	...	...
4	15.9	...	15.9	...	15.9	...	15.9	...	15.9	...	15.8	15.4	15.1	14.9	14.6	...	...	...
5	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
6	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
7	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
8	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
9	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
10	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
11	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
12	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
13	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
14	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
15	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
16	20.0	...	17.7	...	16.4	...	15.5	...	14.7	...	14.0	13.7	13.4	13.1	12.9	12.6	12.4	12.1
17	20.0	...	20.0	...	20.0	...	19.6	...	19.4	...	18.9	18.5	18.1	17.7	17.4	17.0	16.7	16.1
18	17.0	...	15.0	...	14.0	...	13.2	...	12.5	...	11.9	11.7	11.4	11.2	10.9	10.7	10.5	10.3
19	17.0	...	17.0	...	17.0	...	16.7	...	16.5	...	16.1	15.7	15.4	15.1	14.8	14.5	14.2	13.7
20	26.5	...	24.3	...	22.1	...	20.5	...	19.6	...	18.9	18.6	18.3	18.0	17.7	...	...	...
21	26.5	...	26.5	...	25.0	...	23.8	...	23.0	...	22.5	22.3	22.1	21.9	21.7	...	...	...
22	26.5	...	24.3	...	22.1	...	20.5	...	19.6	...	18.9	18.6	18.3	18.0	17.7	...	...	...
23	26.5	...	26.5	...	25.0	...	23.8	...	23.0	...	22.5	22.3	22.1	21.9	21.7	...	...	...
24	22.5	...	20.7	...	18.8	...	17.4	...	16.7	...	16.1	15.8	15.6	15.3	15.0	...	...	...
25	22.5	...	22.5	...	21.3	...	20.2	...	19.6	...	19.1	19.0	18.8	18.6	18.4	...	...	...
26	22.5	...	20.7	...	18.8	...	17.4	...	16.7	...	16.1	15.8	15.6	15.3	15.0	...	...	...
27	22.5	...	22.5	...	21.3	...	20.2	...	19.6	...	19.1	19.0	18.8	18.6	18.4	...	...	...
28	26.5	...	24.3	...	22.1	...	20.5	...	19.6	...	18.9	18.6	18.3	18.0	17.7	...	...	...
29	26.5	...	26.5	...	25.0	...	23.8	...	23.0	...	22.5	22.3	22.1	21.9	21.7	...	...	...
30	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
31	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
32	27.1	...	27.1	...	25.7	...	24.6	...	23.8	...	23.3	23.1	22.9	22.8	22.6	...	...	...
33	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
34	27.1	...	27.1	...	25.7	...	24.6	...	23.8	...	23.3	23.1	22.9	22.8	22.6	...	...	...
35	23.1	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...
36	23.1	...	23.1	...	21.8	...	20.9	...	20.2	...	19.8	19.6	19.5	19.4	19.2	...	...	...
37	23.1	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...
38	23.1	...	23.1	...	21.8	...	20.9	...	20.2	...	19.8	19.6	19.5	19.4	19.2	...	...	...
39	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
40	27.1	...	27.1	...	25.7	...	24.6	...	23.8	...	23.3	23.1	22.9	22.8	22.6	...	...	...
41	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
42	27.1	...	27.1	...	25.7	...	24.6	...	23.8	...	23.3	23.1	22.9	22.8	22.6	...	...	...
43	27.1	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
44	27.1	...	27.1	...	25.7	...	24.6	...	23.8	...	23.3	23.1	22.9	22.8	22.6	...	...	...
45	23.1	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
6	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
7	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48	...	...	...
8	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48	...	...	...
9	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
10	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
11	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
12	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
13	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48	...	...	...
14	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
15	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	...	...	...	...	...	...
16	11.9	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48	...	...	...
17	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48	...	...	...
18	10.1	8.5	6.6	5.1	4.0	3.2	2.6	2.0	1.5	1.3	0.94	0.77	0.58	0.41	...	...	...
19	10.8	8.5	6.6	5.1	4.0	3.2	2.6	2.0	1.5	1.3	0.94	0.77	0.58	0.41	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.
2	46Fe-24Ni-21Cr-6Mo-N	Smls. & wld. fittings	SB-366	...	N08367	Solution ann.
3	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
4	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
5	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
6	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
7	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
8	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
9	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
10	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
11	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.
12	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.
13	46Fe-24Ni-21Cr-6Mo-N	Castings	SA-351	CN3MN	J94651	Solution ann.
14	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SB-599	...	N08700	Solution ann.
15	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SB-599	...	N08700	Solution ann.
16	25Ni-47Fe-21Cr-5Mo	Bar, wire	SB-672	...	N08700	Solution ann.
17	32Ni-45Fe-20Cr-Cb	Castings	SA-351	CT15C	...	As cast
18	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08800	Annealed
19	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08800	Annealed
20	33Ni-42Fe-21Cr	Smls. & wld. fittings	SB-366	...	N08800	Annealed
21	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08800	Annealed
22	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08800	Annealed
23	33Ni-42Fe-21Cr	Bar	SB-408	...	N08800	Annealed
24	33Ni-42Fe-21Cr	Bar	SB-408	...	N08800	Annealed
25	33Ni-42Fe-21Cr	Plate	SB-409	...	N08800	Annealed
26	33Ni-42Fe-21Cr	Plate	SB-409	...	N08800	Annealed
27	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08800	Annealed
28	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08800	Annealed
29	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08800	Annealed
30	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08800	Annealed
31	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08800	Annealed
32	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08800	Annealed
33	32Ni-44Fe-21Cr	Smls. tube	SB-163	...	N08801	Ann./stabilized
34	32Ni-44Fe-21Cr	Smls. tube	SB-163	...	N08801	Ann./stabilized
35	32Ni-44Fe-21Cr	Smls. pipe & tube	SB-407	...	N08801	Ann./stabilized
36	32Ni-44Fe-21Cr	Smls. pipe & tube	SB-407	...	N08801	Ann./stabilized
37	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08810	Annealed
38	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08810	Annealed
39	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08810	Annealed
40	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08810	Hot fin./ann.
41	33Ni-42Fe-21Cr	Bar	SB-408	...	N08810	Annealed
42	33Ni-42Fe-21Cr	Bar	SB-408	...	N08810	Annealed
43	33Ni-42Fe-21Cr	Plate	SB-409	...	N08810	Annealed
44	33Ni-42Fe-21Cr	Plate	SB-409	...	N08810	Annealed
45	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08810	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	$\geq \frac{3}{16}$	45	95	45	NP	800	800	650	NFN-12	G5, G14
2	$\leq \frac{3}{16}$	45	100	45	NP	800	800	NP	NFN-12	G5, W5, W12
3	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G14
4	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G5, G14
5	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G14
6	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G5, G14
7	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	...
8	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G5
9	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	...
10	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G5
11	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G14
12	$\leq \frac{3}{16}$	45	100	45	NP	800	800	650	NFN-12	G5, G14
13	...	45	80	38	NP	800	800	650	NFN-12	G15
14	...	45	80	35	NP	NP	650	650	NFN-8	...
15	...	45	80	35	NP	NP	650	650	NFN-8	G5
16	...	45	80	35	NP	NP	650	650	NFN-8	...
17	...	45	63	25	NP	NP	1600	650	NFN-9	G4, G15
18	...	45	75	30	NP	800	1500	NP	NFN-8	G5, T14
19	...	45	75	30	NP	NP	1500	NP	NFN-8	T15
20	...	45	75	30	NP	800	1500	NP	NFN-8	G5, T14, W5, W12
21	...	45	75	30	1500	800	1500	NP	NFN-8	G5, T14
22	...	45	75	30	1500	NP	1500	NP	NFN-8	T15
23	...	45	75	30	1500	800	1500	NP	NFN-8	G5, T14
24	...	45	75	30	1500	NP	1500	NP	NFN-8	T15
25	...	45	75	30	1500	800	1500	NP	NFN-8	G5, T14
26	...	45	75	30	1500	NP	1500	NP	NFN-8	T15
27	...	45	75	30	NP	NP	1500	NP	NFN-8	G14, T15
28	...	45	75	30	NP	NP	1500	NP	NFN-8	G5, G14, T14
29	...	45	75	30	1500	NP	1500	NP	NFN-8	G5, G14, T14
30	...	45	75	30	1500	NP	1500	NP	NFN-8	G14, T15
31	...	45	75	30	1500	800	1500	NP	NFN-8	G5, T14
32	...	45	75	30	1500	NP	1500	NP	NFN-8	T15
33	...	45	65	25	1050	NP	900	NP	NFN-9	H4
34	...	45	65	25	1050	NP	900	NP	NFN-9	G5, H4
35	...	45	65	25	1050	NP	900	NP	NFN-9	H4
36	...	45	65	25	1050	NP	900	NP	NFN-9	G5, H4
37	...	45	65	25	NP	NP	1650	NP	NFN-9	G4, T16
38	...	45	65	25	NP	800	1650	NP	NFN-9	G4, G5, T15
39	...	45	65	25	1500	NP	1800	NP	NFN-9	G4, T16
40	...	45	65	25	1500	800	1800	NP	NFN-9	G4, G5, T15
41	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T16
42	...	45	65	25	1500	800	1650	NP	NFN-9	G4, G5, T15
43	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T16
44	...	45	65	25	1500	800	1650	NP	NFN-9	G4, G5, T15
45	...	45	65	25	NP	NP	1650	NP	NFN-9	G4, G14, T16

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	23.1	...	23.1	...	21.8	...	20.9	...	20.2	...	19.8	19.6	19.5	19.4	19.2	...	...	...
2	28.6	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
3	24.3	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...
4	24.3	...	24.3	...	23.0	...	22.0	...	21.3	...	20.8	20.7	20.5	20.4	20.2	...	...	...
5	24.3	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...
6	24.3	...	24.3	...	23.0	...	22.0	...	21.3	...	20.8	20.7	20.5	20.4	20.2	...	...	...
7	28.6	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
8	28.6	...	28.6	...	27.0	...	25.8	...	25.0	...	24.5	24.3	24.1	24.0	23.8	...	...	...
9	28.6	...	26.2	...	23.8	...	21.9	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...	...
10	28.6	...	28.6	...	27.0	...	25.8	...	25.0	...	24.5	24.3	24.1	24.0	23.8	...	...	...
11	24.3	...	22.2	...	20.2	...	18.7	...	17.4	...	16.5	16.1	15.8	15.5	15.3	...	...	...
12	24.3	...	24.3	...	23.0	...	22.0	...	21.3	...	20.8	20.7	20.5	20.4	20.2	...	...	...
13	22.9	...	21.4	...	18.8	...	16.9	...	15.7	...	14.9	14.7	14.5	14.4	14.2	...	...	...
14	22.9	...	21.0	...	19.0	...	17.7	...	17.1	...	16.5	15.8	...	...	...	...	...	...
15	22.9	...	22.9	...	22.6	...	22.0	...	21.5	...	21.4	21.4	...	...	...	...	...	...
16	22.9	...	21.0	...	19.0	...	17.7	...	17.1	...	16.5	15.8	...	...	...	...	...	...
17	16.7	...	15.7	...	15.3	...	14.9	...	14.6	...	14.2	13.9	13.7	13.5	13.3	13.1	12.9	12.7
18	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
19	20.0	...	18.5	...	17.8	...	17.2	...	16.8	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1	14.9
20	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
21	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
22	20.0	...	18.5	...	17.8	...	17.2	...	16.8	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1	14.9
23	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
24	20.0	...	18.5	...	17.8	...	17.2	...	16.8	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1	14.9
25	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
26	20.0	...	18.5	...	17.8	...	17.2	...	16.8	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1	14.9
27	17.0	...	15.7	...	15.1	...	14.6	...	14.2	...	13.9	13.7	13.5	13.3	13.2	13.0	12.8	12.7
28	17.0	...	17.0	...	17.0	...	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0
29	17.0	...	17.0	...	17.0	...	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0
30	17.0	...	15.7	...	15.1	...	14.6	...	14.2	...	13.9	13.7	13.5	13.3	13.2	13.0	12.8	12.7
31	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
32	20.0	...	18.5	...	17.8	...	17.2	...	16.8	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1	14.9
33	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
34	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
35	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
36	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
37	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
38	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
39	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
40	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
41	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
42	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
43	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
44	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
45	14.2	...	13.1	...	12.3	...	11.6	...	10.9	...	10.4	10.1	9.9	9.7	9.5	9.3	9.1	9.0

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	11.5	10.1	8.9	7.8	6.7	5.7	4.8	4.0	3.3	2.7	2.2	1.8	1.4	...	...	...	...
18	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
19	14.7	14.5	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
20	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
21	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
22	14.7	14.5	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
23	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
24	14.7	14.5	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
25	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
26	14.7	14.5	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
27	12.5	12.3	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...	...	...	...
28	16.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...	...	...	...
29	16.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...	...	...	...
30	12.5	12.3	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...	...	...	...
31	19.9	17.0	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
32	14.7	14.5	13.0	9.8	6.6	4.2	2.0	1.6	1.1	1.0	0.80	...	...	...	...	...	...
33	10.4	10.2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	14.0	13.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	10.4	10.2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	14.0	13.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
38	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
39	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	0.71	0.56	0.44
40	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	0.71	0.56	0.44
41	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
42	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
43	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
44	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
45	8.8	8.7	8.5	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08810	Annealed
2	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08810	Annealed
3	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08810	Annealed
4	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08810	Annealed
5	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08810	Annealed
6	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08811	Annealed
7	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08811	Annealed
8	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08811	Annealed
9	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08811	Annealed
10	33Ni-42Fe-21Cr	Bar	SB-408	...	N08811	Annealed
11	33Ni-42Fe-21Cr	Bar	SB-408	...	N08811	Annealed
12	33Ni-42Fe-21Cr	Plate	SB-409	...	N08811	Annealed
13	33Ni-42Fe-21Cr	Plate	SB-409	...	N08811	Annealed
14	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08811	Annealed
15	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08811	Annealed
16	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08811	Annealed
17	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08811	Annealed
18	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...	N08825	Annealed
19	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...	N08825	Annealed
20	42Ni-21.5Cr-3Mo-2.3Cu	Smls. & wld. fittings	SB-366	...	N08825	Annealed
21	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...	N08825	Cold worked/ann.
22	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...	N08825	Cold worked/ann.
23	42Ni-21.5Cr-3Mo-2.3Cu	Plate	SB-424	...	N08825	Annealed
24	42Ni-21.5Cr-3Mo-2.3Cu	Plate	SB-424	...	N08825	Annealed
25	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...	N08825	Annealed
26	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...	N08825	Annealed
27	42Ni-21.5Cr-3Mo-2.3Cu	Forgings	SB-564	...	N08825	Annealed
28	42Ni-21.5Cr-3Mo-2.3Cu	Forgings	SB-564	...	N08825	Annealed
29	42Ni-21.5Cr-3Mo-2.3Cu	Wld. tube	SB-704	...	N08825	Annealed
30	42Ni-21.5Cr-3Mo-2.3Cu	Wld. tube	SB-704	...	N08825	Annealed
31	42Ni-21.5Cr-3Mo-2.3Cu	Wld. pipe	SB-705	...	N08825	Annealed
32	42Ni-21.5Cr-3Mo-2.3Cu	Wld. pipe	SB-705	...	N08825	Annealed
33	44Fe-25Ni-21Cr-Mo	Forgings	SA-182	...	N08904	Annealed
34	44Fe-25Ni-21Cr-Mo	Smls. tube	SA-213	...	N08904	Annealed
35	44Fe-25Ni-21Cr-Mo	Plate, sheet, strip	SA-240	...	N08904	Annealed
36	44Fe-25Ni-21Cr-Mo	Wld. tube	SA-249	...	N08904	Annealed
37	44Fe-25Ni-21Cr-Mo	Smls. pipe	SA-312	...	N08904	Annealed
38	44Fe-25Ni-21Cr-Mo	Wld. pipe	SA-312	...	N08904	Annealed
39	44Fe-25Ni-21Cr-Mo	Fittings	SA-403	...	N08904	Annealed
40	44Fe-25Ni-21Cr-Mo	Bar	SA-479	...	N08904	Annealed
41	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08925	Annealed
42	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08925	Annealed
43	25Ni-20Cr-6Mo-Cu-N	Bar, wire	SB-649	...	N08925	Annealed
44	25Ni-20Cr-6Mo-Cu-N	Bar, wire	SB-649	...	N08925	Annealed
45	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SB-673	...	N08925	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	65	25	NP	NP	1650	NP	NFN-9	G4, G5, G14, T15
2	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G14, T16
3	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, G14, T15
4	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T16
5	...	45	65	25	1500	800	1650	NP	NFN-9	G4, G5, T15
6	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T17
7	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, T15
8	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T17
9	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, T15
10	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T17
11	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, T15
12	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T17
13	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, T15
14	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G14, T17
15	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, G14, T16
16	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, T17
17	...	45	65	25	1500	NP	1650	NP	NFN-9	G4, G5, T15
18	...	45	85	35	NP	800 (Cl. 3 only)	1000	650	NFN-7	...
19	...	45	85	35	NP	800 (Cl. 3 only)	1000	650	NFN-7	G5
20	...	45	85	35	NP	800 (Cl. 3 only)	1000	650	NFN-7	G5, W5, W12
21	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	...
22	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	G5
23	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	...
24	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	G5
25	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	...
26	...	45	85	35	1000	800 (Cl. 3 only)	1000	650	NFN-7	G5
27	...	45	85	35	NP	NP	1000	NP	NFN-7	...
28	...	45	85	35	NP	NP	1000	NP	NFN-7	G5
29	...	45	85	35	NP	800	1000	650	NFN-7	G14
30	...	45	85	35	NP	NP	1000	650	NFN-7	G5, G14
31	...	45	85	35	NP	NP	1000	650	NFN-7	G14
32	...	45	85	35	NP	NP	1000	650	NFN-7	G5, G14
33	...	45	71	31	NP	700	700	650	NFN-9	W12
34	...	45	71	31	NP	700	700	650	NFN-9	...
35	...	45	71	31	NP	700	700	650	NFN-9	...
36	...	45	71	31	NP	700	700	650	NFN-9	G14
37	...	45	71	31	NP	700	700	650	NFN-9	...
38	...	45	71	31	NP	700	700	650	NFN-9	G14
39	...	45	71	31	NP	700	700	650	NFN-9	W12
40	...	45	71	31	NP	700	700	650	NFN-9	...
41	...	45	87	43	NP	NP	800	650	NFN-12	...
42	...	45	87	43	NP	NP	800	650	NFN-12	G5
43	...	45	87	43	NP	NP	800	650	NFN-12	...
44	...	45	87	43	NP	NP	800	650	NFN-12	G5
45	...	45	87	43	NP	NP	800	650	NFN-12	G14

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	14.2	...	14.2	...	14.2	...	14.2	...	14.2	...	14.0	13.7	13.3	13.0	12.8	12.5	12.3	12.1
2	14.2	...	13.1	...	12.3	...	11.6	...	10.9	...	10.4	10.1	9.9	9.7	9.5	9.3	9.1	9.0
3	14.2	...	14.2	...	14.2	...	14.2	...	14.2	...	14.0	13.7	13.3	13.0	12.8	12.5	12.3	12.1
4	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
5	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
6	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
7	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
8	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
9	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
10	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
11	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
12	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
13	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
14	14.2	...	13.1	...	12.3	...	11.6	...	10.9	...	10.4	10.1	9.9	9.7	9.5	9.3	9.1	9.0
15	14.2	...	14.2	...	14.2	...	14.2	...	14.2	...	14.0	13.7	13.3	13.0	12.8	12.5	12.3	12.1
16	16.7	...	15.4	...	14.4	...	13.6	...	12.9	...	12.2	11.9	11.6	11.4	11.1	10.9	10.7	10.5
17	16.7	...	16.7	...	16.7	...	16.7	...	16.7	...	16.5	16.1	15.7	15.3	15.0	14.7	14.5	14.2
18	23.3	...	21.4	...	20.3	...	19.4	...	18.5	...	17.8	17.5	17.3	17.2	17.0	17.0	16.9	16.8
19	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
20	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
21	23.3	...	21.4	...	20.3	...	19.4	...	18.5	...	17.8	17.5	17.3	17.2	17.0	17.0	16.9	16.8
22	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
23	23.3	...	21.4	...	20.3	...	19.4	...	18.5	...	17.8	17.5	17.3	17.2	17.0	17.0	16.9	16.8
24	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
25	23.3	...	21.4	...	20.3	...	19.4	...	18.5	...	17.8	17.5	17.3	17.2	17.0	17.0	16.9	16.8
26	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
27	23.3	...	21.4	...	20.3	...	19.4	...	18.5	...	17.8	17.5	17.3	17.2	17.0	17.0	16.9	16.8
28	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.2	23.0	22.9	22.8	22.6
29	19.8	...	18.2	...	17.3	...	16.5	...	15.8	...	15.2	14.9	14.7	14.6	14.5	14.4	14.3	14.2
30	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.8	19.8	19.8	19.7	19.6	19.5	19.4	19.2
31	19.8	...	18.2	...	17.3	...	16.5	...	15.8	...	15.2	14.9	14.7	14.6	14.5	14.4	14.3	14.2
32	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.8	19.8	19.8	19.7	19.6	19.5	19.4	19.2
33	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
34	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
35	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
36	17.2	...	14.2	...	12.9	...	11.8	...	10.8	...	10.1	9.9	9.7	...	...	...	...	...
37	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
38	17.2	...	14.2	...	12.9	...	11.8	...	10.8	...	10.1	9.9	9.7	...	...	...	...	...
39	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
40	20.3	...	16.7	...	15.1	...	13.8	...	12.7	...	11.9	11.6	11.4	...	...	...	...	...
41	24.9	...	23.2	...	21.3	...	19.8	...	18.3	...	17.3	17.0	16.9	16.9	16.9	...	...	...
42	24.9	...	24.9	...	23.9	...	23.0	...	22.1	...	21.4	21.1	20.8	20.4	20.1	...	...	...
43	24.9	...	23.2	...	21.3	...	19.8	...	18.3	...	17.3	17.0	16.9	16.9	16.9	...	...	...
44	24.9	...	24.9	...	23.9	...	23.0	...	22.1	...	21.4	21.1	20.8	20.4	20.1	...	...	...
45	21.1	...	19.7	...	18.1	...	16.8	...	15.6	...	14.7	14.4	14.4	14.4	14.4	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73	...	...	...
2	8.8	8.7	8.5	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73	...	...	...
3	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.2	0.94	0.73	...	...	...
4	10.4	10.2	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
5	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.4	1.1	0.86	...	...	...
6	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
7	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
8	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
9	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
10	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
11	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
12	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
13	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
14	8.8	8.7	8.5	8.3	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77	...	...	...
15	11.9	11.7	11.5	8.8	7.1	5.7	4.6	3.7	2.9	2.3	1.9	1.3	1.0	0.77	...	...	...
16	10.4	10.2	10.0	9.8	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
17	14.0	13.8	12.9	10.4	8.3	6.7	5.4	4.3	3.4	2.7	2.2	1.6	1.2	0.91	...	...	...
18	16.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	16.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	16.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	16.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	16.5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	14.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	18.9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	14.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	18.9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SB-673	...	N08925	Annealed
2	25Ni-20Cr-6Mo-Cu-N	Wld. tube	SB-674	...	N08925	Annealed
3	25Ni-20Cr-6Mo-Cu-N	Wld. tube	SB-674	...	N08925	Annealed
4	25Ni-20Cr-6Mo-Cu-N	Smls. pipe & tube	SB-677	...	N08925	Annealed
5	25Ni-20Cr-6Mo-Cu-N	Smls. pipe & tube	SB-677	...	N08925	Annealed
6	62Ni-28Mo-5Fe	Plate	SB-333	...	N10001	Annealed
7	62Ni-28Mo-5Fe	Plate	SB-333	...	N10001	Annealed
8	62Ni-28Mo-5Fe	Smls. & wld. fittings	SB-366	...	N10001	Annealed
9	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...	N10001	Solution ann.
10	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...	N10001	Solution ann.
11	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...	N10001	Solution ann.
12	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...	N10001	Solution ann.
13	62Ni-28Mo-5Fe	Wld. tube	SB-626	...	N10001	Solution ann.
14	62Ni-28Mo-5Fe	Wld. tube	SB-626	...	N10001	Solution ann.
15	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
16	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
17	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
18	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
19	62Ni-28Mo-5Fe	Sheet, strip	SB-333	...	N10001	Annealed
20	62Ni-28Mo-5Fe	Sheet, strip	SB-333	...	N10001	Annealed
21	70Ni-16Mo-7Cr-5Fe	Smls. & wld. fittings	SB-366	...	N10003	Annealed
22	70Ni-16Mo-7Cr-5Fe	Plate, sheet, strip	SB-434	...	N10003	Annealed
23	70Ni-16Mo-7Cr-5Fe	Rod	SB-573	...	N10003	Annealed
24	62Ni-25Mo-8Cr-2Fe	Smls. & wld. fittings	SB-366	...	N10242	Annealed
25	62Ni-25Mo-8Cr-2Fe	Plate, sheet, strip	SB-434	...	N10242	Annealed
26	62Ni-25Mo-8Cr-2Fe	Plate, sheet, strip	SB-434	...	N10242	Annealed
27	62Ni-25Mo-8Cr-2Fe	Forgings	SB-564	...	N10242	Annealed
28	62Ni-25Mo-8Cr-2Fe	Forgings	SB-564	...	N10242	Annealed
29	62Ni-25Mo-8Cr-2Fe	Rod	SB-573	...	N10242	Annealed
30	62Ni-25Mo-8Cr-2Fe	Rod	SB-573	...	N10242	Annealed
31	62Ni-25Mo-8Cr-2Fe	Wld. pipe	SB-619	...	N10242	Solution ann.
32	62Ni-25Mo-8Cr-2Fe	Wld. pipe	SB-619	...	N10242	Solution ann.
33	62Ni-25Mo-8Cr-2Fe	Smls. pipe & tube	SB-622	...	N10242	Solution ann.
34	62Ni-25Mo-8Cr-2Fe	Smls. pipe & tube	SB-622	...	N10242	Solution ann.
35	62Ni-25Mo-8Cr-2Fe	Wld. tube	SB-626	...	N10242	Solution ann.
36	62Ni-25Mo-8Cr-2Fe	Wld. tube	SB-626	...	N10242	Solution ann.
37	54Ni-16Mo-15Cr	Smls. & wld. fittings	SB-366	...	N10276	Solution ann.
38	54Ni-16Mo-15Cr	Forgings	SB-462	...	N10276	Solution ann.
39	54Ni-16Mo-15Cr	Forgings	SB-462	...	N10276	Solution ann.
40	54Ni-16Mo-15Cr	Forgings	SB-564	...	N10276	Solution ann.
41	54Ni-16Mo-15Cr	Forgings	SB-564	...	N10276	Solution ann.
42	54Ni-16Mo-15Cr	Rod	SB-574	...	N10276	Solution ann.
43	54Ni-16Mo-15Cr	Rod	SB-574	...	N10276	Solution ann.
44	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...	N10276	Solution ann.
45	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...	N10276	Solution ann.

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	87	43	NP	NP	800	650	NFN-12	G5, G14
2	...	45	87	43	NP	NP	800	650	NFN-12	G14
3	...	45	87	43	NP	NP	800	650	NFN-12	G5, G14
4	...	45	87	43	NP	NP	800	650	NFN-12	...
5	...	45	87	43	NP	NP	800	650	NFN-12	G5
6	...	44	100	45	NP	800 (Cl. 3 only)	800	650	NFN-5	...
7	...	44	100	45	NP	800 (Cl. 3 only)	800	650	NFN-5	G5
8	...	44	100	45	NP	NP	800	650	NFN-5	G5, W12
9	...	44	100	45	NP	NP	800	650	NFN-5	G14
10	...	44	100	45	NP	NP	800	650	NFN-5	G5, G14
11	...	44	100	45	NP	NP	800	650	NFN-5	...
12	...	44	100	45	NP	NP	800	650	NFN-5	G5
13	...	44	100	45	NP	NP	800	650	NFN-5	G14
14	...	44	100	45	NP	NP	800	650	NFN-5	G5, G14
15	...	44	100	46	NP	800 (Cl. 3 only)	800	650	NFN-5	G13
16	...	44	100	46	NP	800 (Cl. 3 only)	800	650	NFN-5	G5, G13
17	...	44	115	46	NP	800 (Cl. 3 only)	800	650	NFN-5	G13
18	...	44	115	46	NP	800 (Cl. 3 only)	800	650	NFN-5	G5, G13
19	...	44	115	50	NP	800 (Cl. 3 only)	800	650	NFN-5	...
20	...	44	115	50	NP	800 (Cl. 3 only)	800	NP	NFN-5	G5
21	...	44	100	40	NP	NP	1300	650	NFN-6	T15, W12
22	...	44	100	40	NP	NP	1300	650	NFN-6	T15
23	...	44	100	40	NP	NP	1300	650	NFN-6	T15
24	...	44	105	45	NP	NP	1000	NP	NFN-6	G5, W12
25	...	44	105	45	NP	NP	1000	NP	NFN-6	G5
26	...	44	105	45	NP	NP	1000	NP	NFN-6	...
27	...	44	105	45	NP	NP	1000	NP	NFN-6	G5
28	...	44	105	45	NP	NP	1000	NP	NFN-6	...
29	...	44	105	45	NP	NP	1000	NP	NFN-6	G5
30	...	44	105	45	NP	NP	1000	NP	NFN-6	...
31	...	44	105	45	NP	NP	1000	NP	NFN-6	G5, G14
32	...	44	105	45	NP	NP	1000	NP	NFN-6	G14
33	...	44	105	45	NP	NP	1000	NP	NFN-6	G5
34	...	44	105	45	NP	NP	1000	NP	NFN-6	...
35	...	44	105	45	NP	NP	1000	NP	NFN-6	G5, G14
36	...	44	105	45	NP	NP	1000	NP	NFN-6	G14
37	...	43	100	41	1000	800	1250	650	NFN-10	G5, T14, W5, W12
38	...	43	100	41	NP	NP	1250	NP	NFN-10	T15
39	...	43	100	41	NP	NP	1250	NP	NFN-10	G5, T14
40	...	43	100	41	NP	NP	1250	650	NFN-10	T15
41	...	43	100	41	NP	NP	1250	650	NFN-10	G5, T14
42	...	43	100	41	1000	800 (Cl. 3 only)	1250	650	NFN-10	T15
43	...	43	100	41	1000	800	1250	650	NFN-10	G5, T14
44	...	43	100	41	1000	800	1250	650	NFN-10	G5, T14
45	...	43	100	41	1000	800 (Cl. 3 only)	1250	650	NFN-10	T15

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	21.1	...	21.1	...	20.4	...	19.5	...	18.8	...	18.2	17.9	17.7	17.4	17.0	...	...	...
2	21.1	...	19.7	...	18.1	...	16.8	...	15.6	...	14.7	14.4	14.4	14.4	14.4	...	...	...
3	21.1	...	21.1	...	20.4	...	19.5	...	18.8	...	18.2	17.9	17.7	17.4	17.0	...	...	...
4	24.9	...	23.2	...	21.3	...	19.8	...	18.3	...	17.3	17.0	16.9	16.9	16.9	...	...	...
5	24.9	...	24.9	...	23.9	...	23.0	...	22.1	...	21.4	21.1	20.8	20.4	20.1	...	...	...
6	28.6	...	27.2	...	25.7	...	24.6	...	23.7	...	23.0	22.8	22.5	22.3	22.1	...	...	...
7	28.6	...	28.6	...	28.6	...	28.1	...	27.8	...	27.7	27.5	27.4	27.3	27.2	...	...	...
8	28.6	...	28.6	...	28.6	...	28.1	...	27.8	...	27.7	...	27.4	...	27.2	...	...	...
9	24.3	...	23.1	...	21.8	...	20.9	...	20.2	...	19.6	19.3	19.1	18.9	18.8	...	...	...
10	24.3	...	24.3	...	24.3	...	23.9	...	23.7	...	23.5	23.4	23.3	23.2	23.1	...	...	...
11	28.6	...	27.2	...	25.7	...	24.6	...	23.7	...	23.0	22.8	22.5	22.3	22.1	...	...	...
12	28.6	...	28.6	...	28.6	...	28.1	...	27.8	...	27.7	27.5	27.4	27.3	27.2	...	...	...
13	24.3	...	23.1	...	21.8	...	20.9	...	20.2	...	19.6	19.3	19.1	18.9	18.8	...	...	...
14	24.3	...	24.3	...	24.3	...	23.9	...	23.7	...	23.5	23.4	23.3	23.2	23.1	...	...	...
15	28.6	...	27.8	...	26.3	...	25.1	...	24.3	...	23.6	23.3	23.0	22.8	22.6	...	...	...
16	28.6	...	28.6	...	28.6	...	28.1	...	27.8	...	27.7	27.5	27.4	27.3	27.2	...	...	...
17	30.7	...	27.8	...	26.3	...	25.1	...	24.3	...	23.6	23.3	23.0	22.8	22.6	...	...	...
18	30.7	...	30.7	...	30.7	...	30.7	...	30.7	...	30.7	30.7	30.7	30.7	30.5	...	...	...
19	32.9	...	30.2	...	28.6	...	27.3	...	26.4	...	25.6	25.3	25.0	24.8	24.6	...	...	...
20	32.9	...	32.9	...	32.9	...	32.3	...	32.0	...	31.8	31.7	31.5	31.4	31.3	...	...	...
21	26.7	...	24.6	...	22.7	...	21.1	...	20.0	...	19.3	...	18.9	...	18.4	...	17.5	...
22	26.7	...	24.6	...	22.7	...	21.1	...	20.0	...	19.3	19.1	18.9	18.7	18.4	18.1	17.5	16.8
23	26.7	...	24.6	...	22.7	...	21.1	...	20.0	...	19.3	19.1	18.9	18.7	18.4	18.1	17.5	16.8
24	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.8	29.8	29.7	29.6	29.6	29.5	29.5	29.2
25	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.8	29.8	29.7	29.6	29.6	29.5	29.5	29.2
26	30.0	...	28.2	...	26.1	...	24.7	...	23.9	...	23.7	23.6	23.4	23.2	22.9	22.4	22.0	21.6
27	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.8	29.8	29.7	29.6	29.6	29.5	29.5	29.2
28	30.0	...	28.2	...	26.1	...	24.7	...	23.9	...	23.7	23.6	23.4	23.2	22.9	22.4	22.0	21.6
29	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.8	29.8	29.7	29.6	29.6	29.5	29.5	29.2
30	30.0	...	28.2	...	26.1	...	24.7	...	23.9	...	23.7	23.6	23.4	23.2	22.9	22.4	22.0	21.6
31	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	25.4	25.3	25.2	25.2	25.1	25.1	25.1	24.8
32	25.5	...	24.0	...	22.2	...	21.0	...	20.3	...	20.1	20.0	19.9	19.7	19.4	19.1	18.7	18.4
33	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	29.8	29.8	29.7	29.6	29.6	29.5	29.5	29.2
34	30.0	...	28.2	...	26.1	...	24.7	...	23.9	...	23.7	23.6	23.4	23.2	22.9	22.4	22.0	21.6
35	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	25.4	25.3	25.2	25.2	25.1	25.1	25.1	24.8
36	25.5	...	24.0	...	22.2	...	21.0	...	20.3	...	20.1	20.0	19.9	19.7	19.4	19.1	18.7	18.4
37	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
38	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	16.9	16.7	16.6
39	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
40	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	16.9	16.7	16.6
41	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
42	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	16.9	16.7	16.6
43	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
44	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
45	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	16.9	16.7	16.6

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	16.0	...	12.4	...	6.0	...	3.5	...	...	...	...	...	...	...	...	...	...
22	16.0	14.9	12.4	9.3	6.0	4.8	3.5	...	...	...	...	...	...	...	...	...	...
23	16.0	14.9	12.4	9.3	6.0	4.8	3.5	...	...	...	...	...	...	...	...	...	...
24	29.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	29.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	21.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	29.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	21.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	29.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	21.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	24.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	18.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	29.1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	21.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	24.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	18.4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
38	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
39	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
40	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
41	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
42	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
43	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
44	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
45	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
2	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
3	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
4	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
5	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...	N10276	Solution ann.
6	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...	N10276	Solution ann.
7	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
8	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
9	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
10	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
11	62Ni-22Mo-15Cr	Smls. & wld. fittings	SB-366	...	N10362	Solution ann.
12	62Ni-22Mo-15Cr	Forgings	SB-462	...	N10362	Solution ann.
13	62Ni-22Mo-15Cr	Forgings	SB-462	...	N10362	Solution ann.
14	62Ni-22Mo-15Cr	Forgings	SB-564	...	N10362	Solution ann.
15	62Ni-22Mo-15Cr	Forgings	SB-564	...	N10362	Solution ann.
16	62Ni-22Mo-15Cr	Rod	SB-574	...	N10362	Solution ann.
17	62Ni-22Mo-15Cr	Rod	SB-574	...	N10362	Solution ann.
18	62Ni-22Mo-15Cr	Plate, sheet, strip	SB-575	...	N10362	Solution ann.
19	62Ni-22Mo-15Cr	Plate, sheet, strip	SB-575	...	N10362	Solution ann.
20	62Ni-22Mo-15Cr	Wld. pipe	SB-619	...	N10362	Solution ann.
21	62Ni-22Mo-15Cr	Wld. pipe	SB-619	...	N10362	Solution ann.
22	62Ni-22Mo-15Cr	Smls. pipe & tube	SB-622	...	N10362	Solution ann.
23	62Ni-22Mo-15Cr	Smls. pipe & tube	SB-622	...	N10362	Solution ann.
24	62Ni-22Mo-15Cr	Wld. tube	SB-626	...	N10362	Solution ann.
25	62Ni-22Mo-15Cr	Wld. tube	SB-626	...	N10362	Solution ann.
26	Ni-28Mo-3Fe-1.3Cr-0.25Al	Plate, sheet, strip	SB-333	...	N10629	Solution ann.
27	Ni-28Mo-3Fe-1.3Cr-0.25Al	Plate, sheet, strip	SB-333	...	N10629	Solution ann.
28	Ni-28Mo-3Fe-1.3Cr-0.25Al	Rod	SB-335	...	N10629	Solution ann.
29	Ni-28Mo-3Fe-1.3Cr-0.25Al	Rod	SB-335	...	N10629	Solution ann.
30	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. & wld. fittings	SB-366	...	N10629	Solution ann.
31	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forged fittings	SB-462	...	N10629	Solution ann.
32	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forged fittings	SB-462	...	N10629	Solution ann.
33	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forgings	SB-564	...	N10629	Solution ann.
34	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forgings	SB-564	...	N10629	Solution ann.
35	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. pipe	SB-619	...	N10629	Solution ann.
36	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. pipe	SB-619	...	N10629	Solution ann.
37	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. pipe & tube	SB-622	...	N10629	Solution ann.
38	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. pipe & tube	SB-622	...	N10629	Solution ann.
39	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. tube	SB-626	...	N10629	Solution ann.
40	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. tube	SB-626	...	N10629	Solution ann.
41	65Ni-28Mo-2Fe	Smls. & wld. fittings	SB-366	...	N10665	Annealed
42	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Annealed
43	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Annealed
44	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Annealed
45	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	43	100	41	NP	800 (Cl. 3 only)	NP	NP	NFN-10	W5
2	...	43	100	41	NP	800 (Cl. 3 only)	NP	NP	NFN-10	G5, W5
3	...	43	100	41	1000	800	1250	650	NFN-10	G5, G14, T14, W6
4	...	43	100	41	1000	NP	1250	650	NFN-10	G14, T15
5	...	43	100	41	1000	800	1250	650	NFN-10	G5, T14
6	...	43	100	41	1000	800 (Cl. 3 only)	1250	650	NFN-10	T15
7	...	43	100	41	NP	800 (Cl. 3 only)	NP	NP	NFN-10	W5
8	...	43	100	41	NP	800 (Cl. 3 only)	NP	NP	NFN-10	G5, W5
9	...	43	100	41	1000	800	1250	650	NFN-10	G5, G14, T14, W6
10	...	43	100	41	1000	NP	1250	650	NFN-10	G14, T15
11	...	43	105	45	NP	NP	800	NP	NFN-10	G5, W12
12	...	43	105	45	NP	NP	800	NP	NFN-10	...
13	...	43	105	45	NP	NP	800	NP	NFN-10	G5
14	...	43	105	45	NP	NP	800	NP	NFN-10	...
15	...	43	105	45	NP	NP	800	NP	NFN-10	G5
16	...	43	105	45	NP	NP	800	NP	NFN-10	...
17	...	43	105	45	NP	NP	800	NP	NFN-10	G5
18	...	43	105	45	NP	NP	800	NP	NFN-10	...
19	...	43	105	45	NP	NP	800	NP	NFN-10	G5
20	...	43	105	45	NP	NP	800	NP	NFN-10	G14
21	...	43	105	45	NP	NP	800	NP	NFN-10	G5, G14
22	...	43	105	45	NP	NP	800	NP	NFN-10	...
23	...	43	105	45	NP	NP	800	NP	NFN-10	G5
24	...	43	105	45	NP	NP	800	NP	NFN-10	G14
25	...	43	105	45	NP	NP	800	NP	NFN-10	G5, G14
26	...	44	110	51	NP	NP	800	NP	NFN-16	G5
27	...	44	110	51	NP	NP	800	NP	NFN-16	...
28	...	44	110	51	NP	NP	800	NP	NFN-16	G5
29	...	44	110	51	NP	NP	800	NP	NFN-16	...
30	...	44	110	51	NP	NP	800	NP	NFN-16	G5, W12
31	...	44	110	51	NP	NP	800	NP	NFN-16	G5
32	...	44	110	51	NP	NP	800	NP	NFN-16	...
33	...	44	110	51	NP	NP	800	NP	NFN-16	G5
34	...	44	110	51	NP	NP	800	NP	NFN-16	...
35	...	44	110	51	NP	NP	800	NP	NFN-16	G5, G14
36	...	44	110	51	NP	NP	800	NP	NFN-16	G14
37	...	44	110	51	NP	NP	800	NP	NFN-16	G5
38	...	44	110	51	NP	NP	800	NP	NFN-16	...
39	...	44	110	51	NP	NP	800	NP	NFN-16	G5, G14
40	...	44	110	51	NP	NP	800	NP	NFN-16	G14
41	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	G5, W5, W12
42	...	44	110	51	NP	800 (Cl. 3 only)	NP	NP	NFN-16	G5, W5
43	...	44	110	51	NP	800 (Cl. 3 only)	NP	NP	NFN-16	W5
44	...	44	110	51	NP	800 (Cl. 3 only)	NP	NP	NFN-16	G5, W5
45	...	44	110	51	NP	800 (Cl. 3 only)	NP	NP	NFN-16	W5

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	...	...	...
2	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	...	...	...
3	23.2	...	23.2	...	23.2	...	23.2	...	22.8	...	21.5	20.9	20.4	20.0	19.6	19.4	19.2	19.0
4	23.2	...	21.1	...	19.6	...	18.1	...	16.9	...	15.9	15.5	15.1	14.8	14.5	14.3	14.2	14.1
5	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	22.8	22.6	22.4
6	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	16.9	16.7	16.6
7	27.3	...	24.9	...	23.0	...	21.3	...	19.9	...	18.7	18.2	17.8	17.4	17.1	...	...	...
8	27.3	...	27.3	...	27.3	...	27.3	...	26.9	...	25.2	24.6	24.0	23.5	23.1	...	...	...
9	23.2	...	23.2	...	23.2	...	23.2	...	22.8	...	21.5	20.9	20.4	20.0	19.6	19.4	19.2	19.0
10	23.2	...	21.1	...	19.6	...	18.1	...	16.9	...	15.9	15.5	15.1	14.8	14.5	14.3	14.2	14.1
11	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
12	30.0	...	26.7	...	24.5	...	22.7	...	21.4	...	20.5	20.2	20.0	19.8	19.6	...	...	...
13	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
14	30.0	...	26.7	...	24.5	...	22.7	...	21.4	...	20.5	20.2	20.0	19.8	19.6	...	...	...
15	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
16	30.0	...	26.7	...	24.5	...	22.7	...	21.4	...	20.5	20.2	20.0	19.8	19.6	...	...	...
17	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
18	30.0	...	26.7	...	24.5	...	22.7	...	21.4	...	20.5	20.2	20.0	19.8	19.6	...	...	...
19	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
20	25.5	...	22.7	...	20.8	...	19.3	...	18.2	...	17.4	17.2	17.0	16.8	16.7	...	...	...
21	25.5	...	25.5	...	25.5	...	25.2	...	24.5	...	23.5	23.2	23.0	22.7	22.4	...	...	...
22	30.0	...	26.7	...	24.5	...	22.7	...	21.4	...	20.5	20.2	20.0	19.8	19.6	...	...	...
23	30.0	...	30.0	...	30.0	...	29.6	...	28.8	...	27.7	27.3	27.0	26.7	26.4	...	...	...
24	25.5	...	22.7	...	20.8	...	19.3	...	18.2	...	17.4	17.2	17.0	16.8	16.7	...	...	...
25	25.5	...	25.5	...	25.5	...	25.2	...	24.5	...	23.5	23.2	23.0	22.7	22.4	...	...	...
26	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
27	31.4	...	31.4	...	29.6	...	28.1	...	27.0	...	26.1	25.8	25.5	25.3	25.1	...	...	...
28	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
29	31.4	...	31.4	...	29.6	...	28.1	...	27.0	...	26.1	25.8	25.5	25.3	25.1	...	...	...
30	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
31	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
32	31.4	...	31.4	...	29.6	...	28.1	...	27.0	...	26.1	25.8	25.5	25.3	25.1	...	...	...
33	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
34	31.4	...	31.4	...	29.6	...	28.1	...	27.0	...	26.1	25.8	25.5	25.3	25.1	...	...	...
35	26.7	...	26.7	...	26.7	...	26.7	...	26.4	...	26.0	25.8	25.7	25.6	25.4	...	...	...
36	26.7	...	26.7	...	25.2	...	23.9	...	23.0	...	22.2	21.9	21.7	21.5	21.3	...	...	...
37	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
38	31.4	...	31.4	...	29.6	...	28.1	...	27.0	...	26.1	25.8	25.5	25.3	25.1	...	...	...
39	26.7	...	26.7	...	26.7	...	26.7	...	26.4	...	26.0	25.8	25.7	25.6	25.4	...	...	...
40	26.7	...	26.7	...	25.2	...	23.9	...	23.0	...	22.2	21.9	21.7	21.5	21.3	...	...	...
41	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
42	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
43	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
44	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
45	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	19.0	15.7	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...	...	...	...
4	14.0	14.0	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...	...	...	...
5	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
6	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	19.0	15.7	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...	...	...	...
10	14.0	14.0	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	65Ni-28Mo-2Fe	Plate, sheet, strip	SB-333	...	N10665	Solution ann.
2	65Ni-28Mo-2Fe	Plate, sheet, strip	SB-333	...	N10665	Solution ann.
3	65Ni-28Mo-2Fe	Rod	SB-335	...	N10665	Solution ann.
4	65Ni-28Mo-2Fe	Rod	SB-335	...	N10665	Solution ann.
5	65Ni-28Mo-2Fe	Forgings	SB-462	...	N10665	Solution ann.
6	65Ni-28Mo-2Fe	Forgings	SB-462	...	N10665	Solution ann.
7	65Ni-28Mo-2Fe	Forgings	SB-564	...	N10665	Solution ann.
8	65Ni-28Mo-2Fe	Forgings	SB-564	...	N10665	Solution ann.
9	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Solution ann.
10	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Solution ann.
11	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...	N10665	Solution ann.
12	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...	N10665	Solution ann.
13	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Solution ann.
14	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Solution ann.
15	65Ni-29.5Mo-2Fe-2Cr	Plate, sheet, strip	SB-333	...	N10675	Solution ann.
16	65Ni-29.5Mo-2Fe-2Cr	Plate, sheet, strip	SB-333	...	N10675	Solution ann.
17	65Ni-29.5Mo-2Fe-2Cr	Rod	SB-335	...	N10675	Solution ann.
18	65Ni-29.5Mo-2Fe-2Cr	Rod	SB-335	...	N10675	Solution ann.
19	65Ni-29.5Mo-2Fe-2Cr	Smls. & wld. fittings	SB-366	...	N10675	Solution ann.
20	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-462	...	N10675	Solution ann.
21	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-462	...	N10675	Solution ann.
22	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-564	...	N10675	Solution ann.
23	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-564	...	N10675	Solution ann.
24	65Ni-29.5Mo-2Fe-2Cr	Wld. pipe	SB-619	...	N10675	Solution ann.
25	65Ni-29.5Mo-2Fe-2Cr	Wld. pipe	SB-619	...	N10675	Solution ann.
26	65Ni-29.5Mo-2Fe-2Cr	Smls. pipe & tube	SB-622	...	N10675	Solution ann.
27	65Ni-29.5Mo-2Fe-2Cr	Smls. pipe & tube	SB-622	...	N10675	Solution ann.
28	65Ni-29.5Mo-2Fe-2Cr	Wld. tube	SB-626	...	N10675	Solution ann.
29	65Ni-29.5Mo-2Fe-2Cr	Wld. tube	SB-626	...	N10675	Solution ann.
30	37Ni-30Co-28Cr-2.7Si	Smls. & wld. fittings	SB-366	...	N12160	Solution ann.
31	37Ni-30Co-28Cr-2.7Si	Plate, sheet, strip	SB-435	...	N12160	Solution ann.
32	37Ni-30Co-28Cr-2.7Si	Plate, sheet, strip	SB-435	...	N12160	Solution ann.
33	37Ni-30Co-28Cr-2.7Si	Forgings	SB-564	...	N12160	Solution ann.
34	37Ni-30Co-28Cr-2.7Si	Forgings	SB-564	...	N12160	Solution ann.
35	37Ni-30Co-28Cr-2.7Si	Rod	SB-572	...	N12160	Solution ann.
36	37Ni-30Co-28Cr-2.7Si	Rod	SB-572	...	N12160	Solution ann.
37	37Ni-30Co-28Cr-2.7Si	Wld. pipe	SB-619	...	N12160	Solution ann.
38	37Ni-30Co-28Cr-2.7Si	Wld. pipe	SB-619	...	N12160	Solution ann.
39	37Ni-30Co-28Cr-2.7Si	Smls. pipe & tube	SB-622	...	N12160	Solution ann.
40	37Ni-30Co-28Cr-2.7Si	Smls. pipe & tube	SB-622	...	N12160	Solution ann.
41	37Ni-30Co-28Cr-2.7Si	Wld. tube	SB-626	...	N12160	Solution ann.
42	37Ni-30Co-28Cr-2.7Si	Wld. tube	SB-626	...	N12160	Solution ann.
43	59Ni-22Cr-14Mo-4Fe-3W	Castings	SA-494	CX2MW	N26022	Solution ann.
44	53Ni-17Mo-16Cr-6Fe-5W	Castings	SA-494	CW-12MW/C	N30002	Annealed
45	62Ni-28Mo-5Fe	Castings	SA-494	N-12MV/B	N30012	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	...
2	...	44	110	51	NP	800 (Cl. 3 only)	800	NP	NFN-16	G5
3	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	G13
4	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	G5, G13
5	...	44	110	51	NP	NP	800	NP	NFN-16	...
6	...	44	110	51	NP	NP	800	NP	NFN-16	G5
7	...	44	110	51	NP	NP	800	NP	NFN-16	...
8	...	44	110	51	NP	NP	800	NP	NFN-16	G5
9	...	44	110	51	NP	NP	800	650	NFN-16	G14
10	...	44	110	51	NP	NP	800	650	NFN-16	G5, G14
11	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	...
12	...	44	110	51	NP	800 (Cl. 3 only)	800	650	NFN-16	G5
13	...	44	110	51	NP	NP	800	650	NFN-16	G5, G14
14	...	44	110	51	NP	NP	800	650	NFN-16	G14
15	...	44	110	51	NP	NP	800	650	NFN-16	G5
16	...	44	110	51	NP	NP	800	650	NFN-16	...
17	...	44	110	51	NP	NP	800	650	NFN-16	G5
18	...	44	110	51	NP	NP	800	650	NFN-16	...
19	...	44	110	51	NP	NP	800	650	NFN-16	G5, W12
20	...	44	110	51	NP	NP	800	NP	NFN-16	G5
21	...	44	110	51	NP	NP	800	NP	NFN-16	...
22	...	44	110	51	NP	NP	800	650	NFN-16	G5
23	...	44	110	51	NP	NP	800	650	NFN-16	...
24	...	44	110	51	NP	NP	800	650	NFN-16	G5, G14
25	...	44	110	51	NP	NP	800	650	NFN-16	G14
26	...	44	110	51	NP	NP	800	650	NFN-16	G5
27	...	44	110	51	NP	NP	800	650	NFN-16	...
28	...	44	110	51	NP	NP	800	650	NFN-16	G5, G14
29	...	44	110	51	NP	NP	800	650	NFN-16	G14
30	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, T14, W12
31	...	46	90	35	NP	NP	1500	NP	NFN-13	T14
32	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, T14
33	...	46	90	35	NP	NP	1500	NP	NFN-13	T14
34	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, T14
35	...	46	90	35	NP	NP	1500	NP	NFN-13	T14
36	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, T14
37	...	46	90	35	NP	NP	1500	NP	NFN-13	G14, T14
38	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, G14, T14
39	...	46	90	35	NP	NP	1500	NP	NFN-13	T14
40	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, T14
41	...	46	90	35	NP	NP	1500	NP	NFN-13	G14, T14
42	...	46	90	35	NP	NP	1500	NP	NFN-13	G5, G14, T14
43	...	43	80	45	NP	NP	500	500	NFN-10	G15
44	...	...	72	40	NP	NP	1000	650	NFN-10	G15, W1
45	...	...	76	40	NP	NP	1000	650	NFN-10	G15, W1

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
2	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
3	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
4	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
5	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
6	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
7	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
8	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
9	26.7	...	26.7	...	25.7	...	24.6	...	23.7	...	23.1	22.9	22.6	22.3	21.9	...	...	...
10	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.5	26.4	26.3	26.1	26.0	...	...	...
11	31.4	...	31.4	...	30.2	...	28.9	...	27.9	...	27.2	26.9	26.6	26.2	25.8	...	...	...
12	31.4	...	31.4	...	31.4	...	31.4	...	31.4	...	31.2	31.1	30.9	30.7	30.6	...	...	...
13	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.5	26.4	26.3	26.1	26.0	...	...	...
14	26.7	...	26.7	...	25.7	...	24.6	...	23.7	...	23.1	22.9	22.6	22.3	21.9	...	...	...
15	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
16	31.4	...	31.4	...	30.3	...	28.8	...	27.4	...	26.3	25.8	25.4	25.1	24.8	...	...	...
17	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
18	31.4	...	31.4	...	30.3	...	28.8	...	27.4	...	26.3	25.8	25.4	25.1	24.8	...	...	...
19	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
20	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
21	31.4	...	31.4	...	30.3	...	28.8	...	27.4	...	26.3	25.8	25.4	25.1	24.8	...	...	...
22	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
23	31.4	...	31.4	...	30.3	...	28.8	...	27.4	...	26.3	25.8	25.4	25.1	24.8	...	...	...
24	26.7	...	26.7	...	26.7	...	26.7	...	26.4	...	26.0	25.8	25.7	25.6	25.4	...	...	...
25	26.7	...	26.7	...	25.8	...	24.5	...	23.4	...	22.4	21.9	21.6	21.3	21.1	...	...	...
26	31.4	...	31.4	...	31.4	...	31.4	...	31.1	...	30.6	30.4	30.2	30.1	29.9	...	...	...
27	31.4	...	31.4	...	30.3	...	28.8	...	27.4	...	26.3	25.8	25.4	25.1	24.8	...	...	...
28	26.7	...	26.7	...	26.7	...	26.7	...	26.4	...	26.0	25.8	25.7	25.6	25.4	...	...	...
29	26.7	...	26.7	...	25.8	...	24.5	...	23.4	...	22.4	21.9	21.6	21.3	21.1	...	...	...
30	23.3	...	23.3	...	23.3	...	22.2	...	20.3	...	19.0	18.6	18.4	18.3	18.3	18.3	18.3	18.3
31	23.3	...	20.5	...	18.3	...	16.5	...	15.0	...	14.1	13.8	13.6	13.6	13.5	13.5	13.5	13.5
32	23.3	...	23.3	...	23.3	...	22.2	...	20.3	...	19.0	18.6	18.4	18.3	18.3	18.3	18.3	18.3
33	23.3	...	20.5	...	18.3	...	16.5	...	15.0	...	14.1	13.8	13.6	13.6	13.5	13.5	13.5	13.5
34	23.3	...	23.3	...	23.3	...	22.2	...	20.3	...	19.0	18.6	18.4	18.3	18.3	18.3	18.3	18.3
35	23.3	...	20.5	...	18.3	...	16.5	...	15.0	...	14.1	13.8	13.6	13.6	13.5	13.5	13.5	13.5
36	23.3	...	23.3	...	23.3	...	22.2	...	20.3	...	19.0	18.6	18.4	18.3	18.3	18.3	18.3	18.3
37	19.8	...	17.4	...	15.6	...	14.0	...	12.8	...	12.0	11.7	11.6	11.6	11.5	11.5	11.5	11.5
38	19.8	...	19.8	...	19.8	...	18.9	...	17.3	...	16.2	15.8	15.6	15.6	15.6	15.6	15.6	15.6
39	23.3	...	20.5	...	18.3	...	16.5	...	15.0	...	14.1	13.8	13.6	13.6	13.5	13.5	13.5	13.5
40	23.3	...	23.3	...	23.3	...	22.2	...	20.3	...	19.0	18.6	18.4	18.3	18.3	18.3	18.3	18.3
41	19.8	...	17.4	...	15.6	...	14.0	...	12.8	...	12.0	11.7	11.6	11.6	11.5	11.5	11.5	11.5
42	19.8	...	19.8	...	19.8	...	18.9	...	17.3	...	16.2	15.8	15.6	15.6	15.6	15.6	15.6	15.6
43	22.9	...	22.2	...	21.6	...	21.4	...	21.4	...	...	...	...	...	...	...	...	...
44	20.6	...	19.5	...	18.5	...	18.5	...	18.1	...	16.9	16.9	16.9	16.9	16.9	16.9	16.5	16.1
45	21.7	...	20.3	...	20.3	...	20.3	...	20.3	...	18.6	18.3	18.0	17.7	17.3	17.0	16.6	16.2

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	16.6	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
31	13.5	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
32	16.6	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
33	13.5	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
34	16.6	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
35	13.5	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
36	16.6	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
37	11.5	11.5	9.4	7.7	6.4	5.3	4.3	3.7	3.1	2.6	2.1	...	...	...	...	...	...
38	14.1	11.5	9.4	7.7	6.4	5.3	4.3	3.7	3.1	2.6	2.1	...	...	...	...	...	...
39	13.5	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
40	16.6	13.5	11.0	9.1	7.5	6.2	5.1	4.3	3.6	3.0	2.5	...	...	...	...	...	...
41	11.5	11.5	9.4	7.7	6.4	5.3	4.3	3.7	3.1	2.6	2.1	...	...	...	...	...	...
42	14.1	11.5	9.4	7.7	6.4	5.3	4.3	3.7	3.1	2.6	2.1	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	15.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	15.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. & wld. fittings	SB-366	...	R20033	Solution ann.
2	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Forged fittings	SB-462	...	R20033	Solution ann.
3	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Forgings	SB-564	...	R20033	Solution ann.
4	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. pipe	SB-619	...	R20033	Solution ann.
5	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. pipe & tube	SB-622	...	R20033	Solution ann.
6	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Plate, sheet, strip	SB-625	...	R20033	Solution ann.
7	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. tube	SB-626	...	R20033	Solution ann.
8	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Rod	SB-649	...	R20033	Solution ann.
9	21Ni-30Fe-22Cr-18Co-3Mo-3W	Plate, sheet, strip	SB-435	...	R30556	Annealed
10	21Ni-30Fe-22Cr-18Co-3Mo-3W	Plate, sheet, strip	SB-435	...	R30556	Annealed
11	21Ni-30Fe-22Cr-18Co-3Mo-3W	Rod	SB-572	...	R30556	Annealed
12	21Ni-30Fe-22Cr-18Co-3Mo-3W	Rod	SB-572	...	R30556	Annealed
13	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. pipe	SB-619	...	R30556	Annealed
14	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. pipe	SB-619	...	R30556	Annealed
15	21Ni-30Fe-22Cr-18Co-3Mo-3W	Smls. pipe & tube	SB-622	...	R30556	Annealed
16	21Ni-30Fe-22Cr-18Co-3Mo-3W	Smls. pipe & tube	SB-622	...	R30556	Annealed
17	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. tube	SB-626	...	R30556	Annealed
18	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. tube	SB-626	...	R30556	Annealed
19	Co-26Cr-9Ni-5Mo-3Fe-2W	Rod	SB-815	...	R31233	Solution ann.
20	Co-26Cr-9Ni-5Mo-3Fe-2W	Plate, sheet, strip	SB-818	...	R31233	Solution ann.
21	Ti	Plate, sheet, strip	SB-265	1	R50250	Annealed
22	Ti	Smls. tube	SB-338	1	R50250	Annealed
23	Ti	Wld. tube	SB-338	1	R50250	Annealed
24	Ti	Bar, billet	SB-348	1	R50250	Annealed
25	Ti	Smls. & wld. fittings	SB-363	WPT1	R50250	Annealed
26	Ti	Forgings	SB-381	F-1	R50250	Annealed
27	Ti	Smls. pipe	SB-861	1	R50250	Annealed
28	Ti	Wld. pipe	SB-862	1	R50250	Annealed
29	Ti	Castings	SB-367	C-2	R50400	...
30	Ti	Plate, sheet, strip	SB-265	2	R50400	Annealed
31	Ti	Smls. tube	SB-338	2	R50400	Annealed
32	Ti	Wld. tube	SB-338	2	R50400	Annealed
33	Ti	Bar, billet	SB-348	2	R50400	Annealed
34	Ti	Smls. & wld. fittings	SB-363	WPT2	R50400	Annealed
35	Ti	Forgings	SB-381	F-2	R50400	Annealed
36	Ti	Smls. pipe	SB-861	2	R50400	Annealed
37	Ti	Wld. pipe	SB-862	2	R50400	Annealed
38	Ti	Plate, sheet, strip	SB-265	2H	R50400	Annealed
39	Ti	Smls. tube	SB-338	2H	R50400	Annealed
40	Ti	Wld. tube	SB-338	2H	R50400	Annealed
41	Ti	Bar, billet	SB-348	2H	R50400	Annealed
42	Ti	Smls. fittings	SB-363	WPT2H	R50400	Annealed
43	Ti	Wld. fittings	SB-363	WPT2HW	R50400	Annealed
44	Ti	Forgings	SB-381	F-2H	R50400	Annealed
45	Ti	Smls. pipe	SB-861	2H	R50400	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	45	109	55	NP	NP	800	NP	NFN-10	W12
2	...	45	109	55	NP	NP	800	NP	NFN-10	...
3	...	45	109	55	NP	NP	800	NP	NFN-10	...
4	...	45	109	55	NP	NP	800	NP	NFN-10	G14
5	...	45	109	55	NP	NP	800	NP	NFN-10	...
6	...	45	109	55	NP	NP	800	NP	NFN-10	...
7	...	45	109	55	NP	NP	800	NP	NFN-10	G14
8	...	45	109	55	NP	NP	800	NP	NFN-10	...
9	...	45	100	45	NP	NP	1650	650	NFN-15	G4, T17
10	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G5, T16
11	...	45	100	45	NP	NP	1650	650	NFN-15	G4, T17
12	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G5, T16
13	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G14, T16
14	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G5, G14, T15
15	...	45	100	45	NP	NP	1650	650	NFN-15	G4, T17
16	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G5, T16
17	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G14, T16
18	...	45	100	45	NP	NP	1650	650	NFN-15	G4, G5, G14, T15
19	...	49	130	55	NP	NP	800	NP	NFN-15	G8
20	...	49	130	55	NP	NP	800	NP	NFN-15	G8
21	...	51	35	20	600	600	600	NP	NFT-3	...
22	...	51	35	20	600	600	600	NP	NFT-3	...
23	...	51	35	20	600	600	600	NP	NFT-3	G14, W6
24	...	51	35	20	600	600	600	NP	NFT-3	...
25	...	51	35	20	NP	600	600	NP	NFT-3	W5, W12
26	...	51	35	20	NP	600	600	NP	NFT-3	...
27	...	51	35	20	600	600	600	NP	NFT-3	...
28	...	51	35	20	600	600	600	NP	NFT-3	G14, W6
29	...	51	50	40	NP	NP	500	500	NFT-2	G15
30	...	51	50	40	600	600	600	600	NFT-2	...
31	...	51	50	40	600	600	600	600	NFT-2	...
32	...	51	50	40	600	600	600	600	NFT-2	G14, W6
33	...	51	50	40	600	600	600	600	NFT-2	...
34	...	51	50	40	NP	600	600	600	NFT-2	W5, W12
35	...	51	50	40	NP	600	600	600	NFT-2	...
36	...	51	50	40	600	600	600	600	NFT-2	...
37	...	51	50	40	600	600	600	600	NFT-2	G14, W6
38	...	51	58	40	NP	NP	600	NP	NFT-2	...
39	...	51	58	40	NP	NP	600	NP	NFT-2	...
40	...	51	58	40	NP	NP	600	NP	NFT-2	G14, W6
41	...	51	58	40	NP	NP	600	NP	NFT-2	...
42	...	51	58	40	NP	NP	600	NP	NFT-2	...
43	...	51	58	40	NP	NP	600	NP	NFT-2	W12
44	...	51	58	40	NP	NP	600	NP	NFT-2	...
45	...	51	58	40	NP	NP	600	NP	NFT-2	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
 (*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
2	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
3	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
4	26.4	...	26.3	...	23.9	...	22.2	...	21.1	...	20.1	20.0	19.6	19.5	19.2	...	...	...
5	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
6	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
7	26.4	...	26.3	...	23.9	...	22.2	...	21.1	...	20.1	20.0	19.6	19.5	19.2	...	...	...
8	31.1	...	30.9	...	28.1	...	26.1	...	24.8	...	23.6	23.5	23.1	22.9	22.6	...	...	...
9	28.6	...	25.6	...	23.1	...	21.3	...	20.1	...	19.3	18.9	18.7	18.4	18.2	18.0	17.8	17.6
10	28.6	...	28.6	...	28.0	...	27.1	...	26.4	...	26.0	25.6	25.2	24.9	24.6	24.3	24.1	23.8
11	28.6	...	25.6	...	23.1	...	21.3	...	20.1	...	19.3	18.9	18.7	18.4	18.2	18.0	17.8	17.6
12	28.6	...	28.6	...	28.0	...	27.1	...	26.4	...	26.0	25.6	25.2	24.9	24.6	24.3	24.1	23.8
13	24.3	...	21.8	...	19.6	...	18.1	...	17.1	...	16.4	16.1	15.9	15.7	15.5	15.3	15.2	15.0
14	24.3	...	24.3	...	23.8	...	23.0	...	22.5	...	22.1	21.7	21.4	21.1	20.9	20.7	20.5	20.2
15	28.6	...	25.6	...	23.1	...	21.3	...	20.1	...	19.3	18.9	18.7	18.4	18.2	18.0	17.8	17.6
16	28.6	...	28.6	...	28.0	...	27.1	...	26.4	...	26.0	25.6	25.2	24.9	24.6	24.3	24.1	23.8
17	24.3	...	21.8	...	19.6	...	18.1	...	17.1	...	16.4	16.1	15.9	15.7	15.5	15.3	15.2	15.0
18	24.3	...	24.3	...	23.8	...	23.0	...	22.5	...	22.1	21.7	21.4	21.1	20.9	20.7	20.5	20.2
19	34.2	...	32.1	...	28.5	...	25.5	...	23.4	...	22.0	21.5	21.2	20.9	20.5	...	...	...
20	34.2	...	32.1	...	28.5	...	25.5	...	23.4	...	22.0	21.5	21.2	20.9	20.5	...	...	...
21	10.0	9.3	8.3	7.4	6.6	6.0	5.4	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
22	10.0	9.3	8.3	7.4	6.6	6.0	5.5	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
23	8.5	7.9	7.0	6.3	5.6	5.1	4.7	4.1	3.6	3.2	3.0	...	...	...	...	...	...	...
24	10.0	9.3	8.3	7.4	6.6	6.0	5.5	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
25	10.0	9.3	8.3	7.4	6.6	6.0	5.5	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
26	10.0	9.3	8.3	7.4	6.6	6.0	5.5	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
27	10.0	9.3	8.3	7.4	6.6	6.0	5.5	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
28	8.5	7.9	7.0	6.3	5.6	5.1	4.7	4.1	3.6	3.2	3.0	...	...	...	...	...	...	...
29	14.3	13.1	11.8	10.7	9.7	8.9	8.1	7.4	6.8	...	...	...	...	...	...	...	...	...
30	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
31	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
32	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
33	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
34	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
35	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
36	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
37	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
38	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
39	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
40	14.1	13.5	12.3	11.2	10.2	9.4	8.7	8.1	7.5	6.9	6.4	...	...	...	...	...	...	...
41	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
42	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
43	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
44	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
45	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	17.5	17.3	17.1	16.9	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
10	23.6	23.3	21.2	17.0	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
11	17.5	17.3	17.1	16.9	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
12	23.6	23.3	21.2	17.0	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
13	14.8	14.7	14.5	14.4	11.6	9.3	7.5	6.0	4.8	3.8	3.1	2.3	1.8	1.4	...	...	...
14	20.0	19.8	18.0	14.4	11.6	9.3	7.5	6.0	4.8	3.8	3.1	2.3	1.8	1.4	...	...	...
15	17.5	17.3	17.1	16.9	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
16	23.6	23.3	21.2	17.0	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.7	2.1	1.6	...	...	...
17	14.8	14.7	14.5	14.4	11.6	9.3	7.5	6.0	4.8	3.8	3.1	2.3	1.8	1.4	...	...	...
18	20.0	19.8	18.0	14.4	11.6	9.3	7.5	6.0	4.8	3.8	3.1	2.3	1.8	1.4	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
1	Ti	Wld. pipe	SB-862	2H	R50400	Annealed
2	Ti	Castings	SB-367	C-3	R50550	...
3	Ti	Plate, sheet, strip	SB-265	3	R50550	Annealed
4	Ti	Smls. tube	SB-338	3	R50550	Annealed
5	Ti	Wld. tube	SB-338	3	R50550	Annealed
6	Ti	Bar, billet	SB-348	3	R50550	Annealed
7	Ti	Smls. & wld. fittings	SB-363	WPT3	R50550	Annealed
8	Ti	Forgings	SB-381	F-3	R50550	Annealed
9	Ti	Smls. pipe	SB-861	3	R50550	Annealed
10	Ti	Wld. pipe	SB-862	3	R50550	Annealed
11	Ti-Pd	Plate, sheet, strip	SB-265	11	R52250	Annealed
12	Ti-Pd	Plate, sheet, strip	SB-265	17	R52252	Annealed
13	Ti-Ru	Plate, sheet, strip	SB-265	27	R52254	Annealed
14	Ti-Pd	Plate, sheet, strip	SB-265	7	R52400	Annealed
15	Ti-Pd	Smls. tube	SB-338	7	R52400	Annealed
16	Ti-Pd	Wld. tube	SB-338	7	R52400	Annealed
17	Ti-Pd	Bar, billet	SB-348	7	R52400	Annealed
18	Ti-Pd	Smls. fittings	SB-363	WPT7	R52400	Annealed
19	Ti-Pd	Wld. fittings	SB-363	WPT7W	R52400	Annealed
20	Ti-Pd	Castings	SB-367	C-7	R52400	Annealed
21	Ti-Pd	Forgings	SB-381	F-7	R52400	Annealed
22	Ti-Pd	Smls. pipe	SB-861	7	R52400	Annealed
23	Ti-Pd	Wld. pipe	SB-862	7	R52400	Annealed
24	Ti-0.15Pd	Plate, sheet, strip	SB-265	7H	R52400	Annealed
25	Ti-0.15Pd	Smls. tube	SB-338	7H	R52400	Annealed
26	Ti-0.15Pd	Wld. tube	SB-338	7H	R52400	Annealed
27	Ti-0.15Pd	Bar, billet	SB-348	7H	R52400	Annealed
28	Ti-0.15Pd	Smls. fittings	SB-363	WPT7H	R52400	Annealed
29	Ti-0.15Pd	Wld. fittings	SB-363	WPT7HW	R52400	Annealed
30	Ti-0.15Pd	Forgings	SB-381	F-7H	R52400	Annealed
31	Ti-0.15Pd	Smls. pipe	SB-861	7H	R52400	Annealed
32	Ti-0.15Pd	Wld. pipe	SB-862	7H	R52400	Annealed
33	Ti-Pd	Plate, sheet, strip	SB-265	16	R52402	Annealed
34	Ti-Pd	Smls. tube	SB-338	16	R52402	Annealed
35	Ti-Pd	Wld. tube	SB-338	16	R52402	Annealed
36	Ti-Pd	Bar, billet	SB-348	16	R52402	Annealed
37	Ti-Pd	Forgings	SB-381	F-16	R52402	Annealed
38	Ti-0.05Pd	Plate, sheet, strip	SB-265	16H	R52402	Annealed
39	Ti-0.05Pd	Smls. tube	SB-338	16H	R52402	Annealed
40	Ti-0.05Pd	Wld. tube	SB-338	16H	R52402	Annealed
41	Ti-0.05Pd	Bar, billet	SB-348	16H	R52402	Annealed
42	Ti-0.05Pd	Smls. fittings	SB-363	WPT16H	R52402	Annealed
43	Ti-0.05Pd	Wld. fittings	SB-363	WPT16HW	R52402	Annealed
44	Ti-0.05Pd	Forgings	SB-381	F-16H	R52402	Annealed
45	Ti-0.05Pd	Smls. pipe	SB-861	16H	R52402	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	51	58	40	NP	NP	600	NP	NFT-2	W12
2	...	52	65	55	NP	NP	500	NP	NFT-1	G15
3	...	52	65	55	600	600	600	600	NFT-1	...
4	...	52	65	55	600	600	600	600	NFT-1	...
5	...	52	65	55	600	600	600	600	NFT-1	G14, W6
6	...	52	65	55	600	600	600	600	NFT-1	...
7	...	52	65	55	NP	600	600	600	NFT-1	W5, W12
8	...	52	65	55	NP	600	600	600	NFT-1	...
9	...	52	65	55	600	600	600	600	NFT-1	...
10	...	52	65	55	600	600	600	600	NFT-1	G14, W6
11	...	51	35	20	NP	NP	600	NP	NFT-3	...
12	...	51	35	20	NP	NP	600	NP	NFT-3	...
13	...	51	35	20	NP	NP	600	NP	NFT-3	...
14	...	51	50	40	NP	600	600	600	NFT-2	...
15	...	51	50	40	NP	600	600	600	NFT-2	...
16	...	51	50	40	NP	600	600	600	NFT-2	G14, W6
17	...	51	50	40	NP	600	600	600	NFT-2	...
18	...	51	50	40	NP	NP	600	600	NFT-2	...
19	...	51	50	40	NP	NP	600	600	NFT-2	G14
20	...	51	50	40	NP	NP	500	500	NFT-2	G15
21	...	51	50	40	NP	NP	600	600	NFT-2	...
22	...	51	50	40	NP	600	600	600	NFT-2	...
23	...	51	50	40	NP	600	600	600	NFT-2	G14, W6
24	...	51	58	40	NP	NP	600	NP	NFT-2	...
25	...	51	58	40	NP	NP	600	NP	NFT-2	...
26	...	51	58	40	NP	NP	600	NP	NFT-2	G14, W6
27	...	51	58	40	NP	NP	600	NP	NFT-2	...
28	...	51	58	40	NP	NP	600	NP	NFT-2	...
29	...	51	58	40	NP	NP	600	NP	NFT-2	W12
30	...	51	58	40	NP	NP	600	NP	NFT-2	...
31	...	51	58	40	NP	NP	600	NP	NFT-2	...
32	...	51	58	40	NP	NP	600	NP	NFT-2	W12
33	...	51	50	40	NP	NP	600	600	NFT-2	...
34	...	51	50	40	NP	NP	600	600	NFT-2	...
35	...	51	50	40	NP	NP	600	600	NFT-2	G14, W6
36	...	51	50	40	NP	NP	600	600	NFT-2	...
37	...	51	50	40	NP	NP	600	600	NFT-2	...
38	...	51	58	40	NP	NP	600	NP	NFT-2	...
39	...	51	58	40	NP	NP	600	NP	NFT-2	...
40	...	51	58	40	NP	NP	600	NP	NFT-2	G14, W6
41	...	51	58	40	NP	NP	600	NP	NFT-2	...
42	...	51	58	40	NP	NP	600	NP	NFT-2	...
43	...	51	58	40	NP	NP	600	NP	NFT-2	W12
44	...	51	58	40	NP	NP	600	NP	NFT-2	...
45	...	51	58	40	NP	NP	600	NP	NFT-2	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
2	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	...	...	...	...	...	...	...	...	...
3	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
4	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
5	15.8	14.9	13.4	12.1	10.8	9.7	8.8	7.9	7.2	6.7	6.3	...	...	...	...	...	...	...
6	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
7	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
8	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
9	18.6	17.5	15.8	14.2	12.8	11.5	10.3	9.3	8.5	7.9	7.4	...	...	...	...	...	...	...
10	15.8	14.9	13.4	12.1	10.8	9.7	8.8	7.9	7.2	6.7	6.3	...	...	...	...	...	...	...
11	10.0	9.3	8.3	7.4	6.6	6.0	5.4	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
12	10.0	9.3	8.3	7.4	6.6	6.0	5.4	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
13	10.0	9.3	8.3	7.4	6.6	6.0	5.4	4.7	4.2	3.8	3.5	...	...	...	...	...	...	...
14	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
15	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
16	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
17	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
18	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
19	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
20	14.3	13.1	11.8	10.7	9.7	8.9	8.1	7.4	6.8	...	...	...	...	...	...	...	...	...
21	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
22	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
23	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
24	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
25	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
26	14.1	13.5	12.3	11.2	10.2	9.4	8.7	8.1	7.5	6.9	6.4	...	...	...	...	...	...	...
27	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
28	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
29	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
30	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
31	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
32	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
33	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
34	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
35	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
36	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
37	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
38	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
39	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
40	14.1	13.5	12.3	11.2	10.2	9.4	8.7	8.1	7.5	6.9	6.4	...	...	...	...	...	...	...
41	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
42	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
43	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
44	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
45	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	Ti-0.05Pd	Wld. pipe	SB-862	16H	R52402	Annealed
2	Ti-Ru	Plate, sheet, strip	SB-265	26	R52404	Annealed
3	Ti-Ru	Smls. tube	SB-338	26	R52404	Annealed
4	Ti-Ru	Wld. tube	SB-338	26	R52404	Annealed
5	Ti-Ru	Bar, billet	SB-348	26	R52404	Annealed
6	Ti-Ru	Smls. fittings	SB-363	WPT26	R52404	Annealed
7	Ti-Ru	Wld. fittings	SB-363	WPT26W	R52404	Annealed
8	Ti-Ru	Forgings	SB-381	F-26	R52404	Annealed
9	Ti-Ru	Smls. pipe	SB-861	26	R52404	Annealed
10	Ti-Ru	Wld. pipe	SB-862	26	R52404	Annealed
11	Ti-0.10Ru	Plate, sheet, strip	SB-265	26H	R52404	Annealed
12	Ti-0.10Ru	Smls. tube	SB-338	26H	R52404	Annealed
13	Ti-0.10Ru	Wld. tube	SB-338	26H	R52404	Annealed
14	Ti-0.10Ru	Bar, billet	SB-348	26H	R52404	Annealed
15	Ti-0.10Ru	Smls. fittings	SB-363	WPT26H	R52404	Annealed
16	Ti-0.10Ru	Wld. fittings	SB-363	WPT26HW	R52404	Annealed
17	Ti-0.10Ru	Forgings	SB-381	F-26H	R52404	Annealed
18	Ti-0.10Ru	Smls. pipe	SB-861	26H	R52404	Annealed
19	Ti-0.10Ru	Wld. pipe	SB-862	26H	R52404	Annealed
20	Ti-0.3Mo-0.8Ni	Plate, sheet, strip	SB-265	12	R53400	Annealed
21	Ti-0.3Mo-0.8Ni	Smls. tube	SB-338	12	R53400	Annealed
22	Ti-0.3Mo-0.8Ni	Wld. tube	SB-338	12	R53400	Annealed
23	Ti-0.3Mo-0.8Ni	Bar, billet	SB-348	12	R53400	Annealed
24	Ti-0.3Mo-0.8Ni	Smls. fittings	SB-363	WPT12	R53400	Annealed
25	Ti-0.3Mo-0.8Ni	Wld. fittings	SB-363	WPT12W	R53400	Annealed
26	Ti-0.3Mo-0.8Ni	Forgings	SB-381	F-12	R53400	Annealed
27	Ti-0.3Mo-0.8Ni	Smls. pipe	SB-861	12	R53400	Annealed
28	Ti-0.3Mo-0.8Ni	Wld. pipe	SB-862	12	R53400	Annealed
29	Ti-4Al-2.5V-1.5Fe	Plate, sheet, strip	SB-265	38	R54250	Annealed
30	Ti-4Al-2.5V-1.5Fe	Smls. tube	SB-338	38	R54250	Annealed
31	Ti-4Al-2.5V-1.5Fe	Wld. tube	SB-338	38	R54250	Annealed
32	Ti-4Al-2.5V-1.5Fe	Bar, billet	SB-348	38	R54250	Annealed
33	Ti-4Al-2.5V-1.5Fe	Smls. fittings	SB-363	WPT38	R54250	Annealed
34	Ti-4Al-2.5V-1.5Fe	Wld. fittings	SB-363	WPT38W	R54250	Annealed
35	Ti-4Al-2.5V-1.5Fe	Forgings	SB-381	F-38	R54250	Annealed
36	Ti-4Al-2.5V-1.5Fe	Smls. pipe	SB-861	38	R54250	Annealed
37	Ti-4Al-2.5V-1.5Fe	Wld. pipe	SB-862	38	R54250	Annealed
38	Ti-3Al-2.5V	Plate, sheet, strip	SB-265	9	R56320	Annealed
39	Ti-3Al-2.5V	Smls. tube	SB-338	9	R56320	Annealed
40	Ti-3Al-2.5V	Wld. tube	SB-338	9	R56320	Annealed
41	Ti-3Al-2.5V	Bar, billet	SB-348	9	R56320	Annealed
42	Ti-3Al-2.5V	Smls. fittings	SB-363	WPT9	R56320	Annealed
43	Ti-3Al-2.5V	Wld. fittings	SB-363	WPT9W	R56320	Annealed
44	Ti-3Al-2.5V	Forgings	SB-381	F-9	R56320	Annealed
45	Ti-3Al-2.5V	Smls. pipe	SB-861	9	R56320	Annealed

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	51	58	40	NP	NP	600	NP	NFT-2	W12
2	...	51	50	40	NP	NP	600	600	NFT-2	...
3	...	51	50	40	NP	NP	600	600	NFT-2	...
4	...	51	50	40	NP	NP	600	600	NFT-2	G14, W6
5	...	51	50	40	NP	NP	600	600	NFT-2	...
6	...	51	50	40	NP	NP	600	600	NFT-2	...
7	...	51	50	40	NP	NP	600	600	NFT-2	G14
8	...	51	50	40	NP	NP	600	600	NFT-2	...
9	...	51	50	40	NP	NP	600	600	NFT-2	...
10	...	51	50	40	NP	NP	600	600	NFT-2	G14, W6
11	...	51	58	40	NP	NP	600	NP	NFT-2	...
12	...	51	58	40	NP	NP	600	NP	NFT-2	...
13	...	51	58	40	NP	NP	600	NP	NFT-2	G14, W6
14	...	51	58	40	NP	NP	600	NP	NFT-2	...
15	...	51	58	40	NP	NP	600	NP	NFT-2	...
16	...	51	58	40	NP	NP	600	NP	NFT-2	W12
17	...	51	58	40	NP	NP	600	NP	NFT-2	...
18	...	51	58	40	NP	NP	600	NP	NFT-2	...
19	...	51	58	40	NP	NP	600	NP	NFT-2	W12
20	...	52	70	50	NP	NP	600	600	NFT-5	...
21	...	52	70	50	NP	NP	600	600	NFT-5	...
22	...	52	70	50	NP	NP	600	600	NFT-5	G14, W6
23	...	52	70	50	NP	NP	600	600	NFT-5	...
24	...	52	70	50	NP	NP	600	600	NFT-5	...
25	...	52	70	50	NP	NP	600	600	NFT-5	G14
26	...	52	70	50	NP	NP	600	600	NFT-5	...
27	...	52	70	50	NP	NP	600	600	NFT-5	...
28	...	52	70	50	NP	NP	600	600	NFT-5	G14, W6
29	...	54	130	115	NP	NP	650	NP	NFT-6	...
30	...	54	130	115	NP	NP	650	NP	NFT-6	...
31	...	54	130	115	NP	NP	650	NP	NFT-6	G14, W6
32	...	54	130	115	NP	NP	650	NP	NFT-6	...
33	...	54	130	115	NP	NP	650	NP	NFT-6	...
34	...	54	130	115	NP	NP	650	NP	NFT-6	G14, W6
35	...	54	130	115	NP	NP	650	NP	NFT-6	...
36	...	54	130	115	NP	NP	650	NP	NFT-6	...
37	...	54	130	115	NP	NP	650	NP	NFT-6	G14, W6
38	...	53	90	70	NP	600	600	600	NFT-4	...
39	...	53	90	70	NP	600	600	600	NFT-4	...
40	...	53	90	70	NP	600	600	600	NFT-4	G14, W6
41	...	53	90	70	NP	600	NP	NP	NFT-4	...
42	...	53	90	70	NP	600	NP	NP	NFT-4	...
43	...	53	90	70	NP	600	NP	NP	NFT-4	G14, W6
44	...	53	90	70	NP	600	NP	NP	NFT-4	...
45	...	53	90	70	NP	600	600	600	NFT-4	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
2	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
3	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
4	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
5	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
6	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
7	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
8	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
9	14.3	13.7	12.4	11.3	10.3	9.5	8.8	8.2	7.6	7.0	6.5	...	...	...	...	...	...	...
10	12.1	11.7	10.6	9.6	8.8	8.1	7.5	7.0	6.5	6.0	5.5	...	...	...	...	...	...	...
11	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
12	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
13	14.1	13.5	12.3	11.2	10.2	9.4	8.7	8.1	7.5	6.9	6.4	...	...	...	...	...	...	...
14	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
15	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
16	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
17	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
18	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
19	16.6	15.9	14.4	13.1	12.0	11.1	10.2	9.5	8.8	8.2	7.6	...	...	...	...	...	...	...
20	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
21	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
22	17.0	17.0	15.9	14.8	13.8	12.9	12.1	11.5	11.1	10.8	10.5	...	...	...	...	...	...	...
23	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
24	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
25	17.0	17.0	15.9	14.8	13.8	12.9	12.1	11.5	11.1	10.8	10.5	...	...	...	...	...	...	...
26	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
27	20.0	20.0	18.7	17.4	16.2	15.2	14.3	13.6	13.1	12.7	12.3	...	...	...	...	...	...	...
28	17.0	17.0	15.9	14.8	13.8	12.9	12.1	11.5	11.1	10.8	10.5	...	...	...	...	...	...	...
29	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
30	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
31	31.5	31.5	31.4	30.0	28.7	27.5	26.4	25.4	24.7	24.0	23.5	23.2	...	...	...	...	...	...
32	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
33	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
34	31.5	31.5	31.4	30.0	28.7	27.5	26.4	25.4	24.7	24.0	23.5	23.2	...	...	...	...	...	...
35	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
36	37.1	37.1	36.9	35.3	33.8	32.3	31.0	29.9	29.0	28.2	27.7	27.3	...	...	...	...	...	...
37	31.5	31.5	31.4	30.0	28.7	27.5	26.4	25.4	24.7	24.0	23.5	23.2	...	...	...	...	...	...
38	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
39	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
40	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
41	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
42	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
43	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
44	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
45	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	Ti-3Al-2.5V	Wld. pipe	SB-862	9	R56320	Annealed
2	Ti-3Al-2.5V-0.1Ru	Plate, sheet, strip	SB-265	28	R56323	Annealed
3	Ti-3Al-2.5V-0.1Ru	Smls. tube	SB-338	28	R56323	Annealed
4	Ti-3Al-2.5V-0.1Ru	Wld. tube	SB-338	28	R56323	Annealed
5	Ti-3Al-2.5V-0.1Ru	Bar, billet	SB-348	28	R56323	Annealed
6	Ti-3Al-2.5V-0.1Ru	Smls. fittings	SB-363	WPT28	R56323	Annealed
7	Ti-3Al-2.5V-0.1Ru	Wld. fittings	SB-363	WPT28W	R56323	Annealed
8	Ti-3Al-2.5V-0.1Ru	Forgings	SB-381	F-28	R56323	Annealed
9	Ti-3Al-2.5V-0.1Ru	Smls. pipe	SB-861	28	R56323	Annealed
10	Ti-3Al-2.5V-0.1Ru	Wld. pipe	SB-862	28	R56323	Annealed
11	99.2Zr	Forgings	SB-493	...	R60702	Annealed
12	99.2Zr	Smls. tube	SB-523	...	R60702	Annealed
13	99.2Zr	Wld. tube	SB-523	...	R60702	Annealed
14	99.2Zr	Bar, wire	SB-550	...	R60702	Annealed
15	99.2Zr	Plate, sheet, strip	SB-551	...	R60702	Annealed
16	99.2Zr	Smls. fittings	SB-653	PZ-2	R60702	Annealed
17	99.2Zr	Wld. fittings	SB-653	PZ-2W	R60702	Annealed
18	99.2Zr	Smls. & wld. pipe	SB-658	...	R60702	Annealed
19	99.2Zr	Castings	SB-752	702C	R61702	...
20	95.5Zr + 2.5Nb	Forgings	SB-493	...	R60705	Annealed
21	95.5Zr + 2.5Nb	Bar, wire	SB-550	...	R60705	Annealed
22	95.5Zr + 2.5Nb	Plate, sheet, strip	SB-551	...	R60705	Annealed
23	95.5Zr + 2.5Nb	Smls. & wld. pipe	SB-658	...	R60705	Annealed
24	95.5Zr + 2.5Nb	Castings	SB-752	705C	R61705	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)				External Pressure Chart No.	Notes
					I	III	VIII-1	XII		
1	...	53	90	70	NP	600	600	600	NFT-4	G14, W6
2	...	53	90	70	NP	NP	600	NP	NFT-4	...
3	...	53	90	70	NP	NP	600	NP	NFT-4	...
4	...	53	90	70	NP	NP	600	NP	NFT-4	G14, W6
5	...	53	90	70	NP	NP	600	NP	NFT-4	...
6	...	53	90	70	NP	NP	600	NP	NFT-4	...
7	...	53	90	70	NP	NP	600	NP	NFT-4	G14, W6
8	...	53	90	70	NP	NP	600	NP	NFT-4	...
9	...	53	90	70	NP	NP	600	NP	NFT-4	...
10	...	53	90	70	NP	NP	600	NP	NFT-4	G14, W6
11	...	61	55	30	NP	400	700	NP	NFZ-1	...
12	...	61	55	30	NP	400	700	NP	NFZ-1	...
13	...	61	55	30	NP	400	700	NP	NFZ-1	G14, W6
14	...	61	55	30	NP	400	700	NP	NFZ-1	...
15	...	61	55	30	NP	NP	700	NP	NFZ-1	...
16	...	61	55	30	NP	NP	700	NP	NFZ-1	...
17	...	61	55	30	NP	NP	700	NP	NFZ-1	G14, W6
18	...	61	55	30	NP	NP	700	NP	NFZ-1	W12
19	...	61	55	40	NP	NP	600	NP	NFZ-1	G15
20	...	62	70	55	NP	NP	700	NP	NFZ-2	...
21	...	62	80	55	NP	NP	700	NP	NFZ-2	...
22	...	62	80	55	NP	NP	700	NP	NFZ-2	...
23	...	62	80	55	NP	NP	700	NP	NFZ-2	W12
24	...	62	70	50	NP	NP	600	NP	NFZ-1	G15

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900	950
1	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
2	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
3	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
4	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
5	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
6	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
7	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
8	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
9	25.7	25.7	24.7	23.7	22.6	21.4	20.2	19.0	18.1	17.5	17.2	...	...	...	...	...	...	...
10	21.9	21.9	21.0	20.2	19.2	18.2	17.1	16.2	15.4	14.9	14.7	...	...	...	...	...	...	...
11	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
12	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
13	13.4	12.8	11.6	10.5	9.5	8.6	7.7	7.0	6.3	5.6	5.1	4.7	4.5	...	...	...	...	...
14	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
15	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
16	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
17	13.4	12.8	11.6	10.5	9.5	8.6	7.7	7.0	6.3	5.6	5.1	4.7	4.5	...	...	...	...	...
18	15.7	15.1	13.7	12.4	11.2	10.1	9.1	8.3	7.4	6.6	6.0	5.6	5.2	...	...	...	...	...
19	15.7	15.5	14.4	13.1	11.9	10.8	9.6	8.6	7.7	6.9	6.3	...	...	...	...	...	...	...
20	20.0	18.4	16.6	15.1	13.9	13.1	12.4	12.0	11.7	11.5	11.3	11.1	10.8	...	...	...	...	...
21	22.9	21.0	18.9	17.3	15.9	14.9	14.2	13.7	13.4	13.1	12.5	11.9	11.4	...	...	...	...	...
22	22.9	21.0	18.9	17.3	15.9	14.9	14.2	13.7	13.4	13.1	12.5	11.9	11.4	...	...	...	...	...
23	22.9	21.0	18.9	17.3	15.9	14.9	14.2	13.7	13.4	13.1	12.5	11.9	11.4	...	...	...	...	...
24	20.0	19.9	18.5	17.2	16.0	14.8	13.6	12.6	11.7	10.9	10.2	...	...	...	...	...	...	...

Table 1B (Cont'd)
Section I; Section III, Division 1, Classes 2 and 3,* Section VIII, Division 1; and Section XII
Maximum Allowable Stress Values, S, for Nonferrous Materials
(*See Maximum Temperature Limits for Restrictions on Class)

Line	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650	1700	1750	1800
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

NOTES TO TABLE 1B**GENERAL NOTES**

- (a) The following abbreviations are used: ann., annealed; cond., condenser; CW, cold worked; exch., exchanger; extr., extruded; fin., finished; fr., from; HW, Hot worked; rel., relieved; rld., rolled; Smls., Seamless; Sol., Solution; treat., treated; and Wld., Welded.
- (b) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (c) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (d) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.
- (e) An alternative typeface is used for stress values obtained from time-dependent properties (see Notes T1 through T19).
- (f) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SB-407/SB-407M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SB-407 Grade N08800 shall be used when SB-407M Grade N08800 is used in construction.

NOTES - GENERAL REQUIREMENTS

- G1 For steam at 250 psi (406°F), the values given for 400°F may be used.
- G2 At temperatures over 1000°F, these stress values apply only when the carbon is 0.04% or higher.
- G3 In the absence of evidence that the casting is of high quality throughout, values not in excess of 80% of those given in the Table shall be used. This is not intended to apply to valves and fittings made to recognized standards.
- G4 Creep-fatigue, thermal ratcheting, and environmental effects are increasingly significant failure modes at temperatures in excess of 1500°F and shall be considered in the design.
- G5 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed $66\frac{2}{3}\%$ but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. For Section III applications, Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G6 Maximum temperature for external pressure not to exceed 350°F.
- G7 Use 350°F curve for all temperature values below 350°F.
- G8 The stresses for this material are based on 120 ksi minimum tensile strength because of weld metal strength limitations.
- G9 Use Figure NFC-6 up to and including 300°F. Use the 600°F curve of Figure NFC-3 above 300°F up to and including 400°F. Maximum temperature for external pressure not to exceed 400°F.
- G10 Maximum temperature for external pressure not to exceed 450°F.
- G11 Referenced external pressure chart is applicable up to 700°F.
- G12 Referenced external pressure chart is applicable up to 800°F.
- G13 For Section VIII and XII applications, use of external pressure charts for material in the form of bar stock is permitted for stiffener rings only.
- G14 For Section VIII applications, a factor of 0.85 has been applied in arriving at the maximum allowable stress values in tension for this material. Divide tabulated values by 0.85 for maximum allowable longitudinal tensile stress.
- G15 To these stress values a quality factor as specified in ND-3115 of Section III; UG-24 of Section VIII, Division 1; or TM-190 of Section XII shall be applied for castings. This is not intended to apply to valves and fittings made to recognized standards.
- G16 Allowable stress values shown are 90% of those for the corresponding core material.
- G17 C37700 and copper-silicon alloys are not always suitable when exposed to certain media and high temperatures, particularly steam above 212°F. The user should ensure that the alloy selected is satisfactory for the service for which it is to be used.
- G18 Because of the occasionally contingent danger from the failure of pressure vessels by stress corrosion cracking, the following is pertinent. These materials are suitable for engineering use under a wide variety of ordinary corrosive conditions with no particular hazard in respect to stress corrosion.
- G19 Few alloys are completely immune to stress corrosion cracking in all combinations of stress and corrosive environments, and the supplier of the material should be consulted. Reference may also be made to the following sources: (1) Stress Corrosion Cracking Control Measures, B. F. Brown, U.S. National Bureau of Standards (1977), available from NACE, Texas; (2) The Stress Corrosion of Metals, H. L. Logan, John Wiley & Sons, New York, 1966.
- G20 For plate only.
- G21 The maximum operating temperature is arbitrarily set at 500°F because harder temper adversely affects design stress in the creep rupture temperature range.
- G22 The minimum tensile strength of reduced section tension specimens in accordance with QW-462.1 of Section IX shall not be less than 110,000 psi.
- G23 This alloy is subject to severe loss of impact strength at room temperatures after exposure in the range of 1000°F to 1400°F.

NOTES TO TABLE 1B (CONT'D)**NOTES – GENERAL REQUIREMENTS (CONT'D)**

- G24 For stress relieved tempers (T351, T3510, T3511, T451, T4510, T4511, T651, T6510, T6511), stress values for materials in the basic temper shall be used.
- G25 The tension test specimen from plate 0.500 in. and thicker is machined from the core and does not include the cladding alloy; therefore, the allowable stress values for thickness less than 0.500 in. shall be used.
- G26 The tension test specimen from plate 0.500 in. and thicker is machined from the core and does not include the cladding alloy; therefore, the allowable stress values shown are 90% of those for the core material of the same thickness.
- G27 Alloy N06022 in the solution annealed condition is subject to severe loss of impact strength at room temperatures after exposure in the range of 1000°F to 1250°F.
- G28 For external pressure design, the maximum design temperature is limited to 1000°F.
- G29 External pressure chart NFN-2 may be used for temperatures between 400°F and 600°F.
- G30 Alloy N06025 in the solution annealed condition is subject to severe loss of rupture ductility in the approximate temperature range of 1200°F to 1400°F.
- G31 For external pressure design, the maximum design temperature is limited to 1200°F.
- G32 For Section I use, the y values (see Section I, PG-27.4.6) shall be as follows: for 1050°F and below, 0.4; for 1100°F, 0.5; and for 1150°F and above, 0.7.
- G33 Allowable stress values listed are set equal to those of an annealed temper, as data were not provided to justify higher values.
- G34 Time-dependent values are based on creep testing of as-welded product.

NOTES – HEAT TREATMENT REQUIREMENTS

- H1 For temperatures above 1000°F, these stress values may be used only if the material is annealed at a minimum temperature of 1900°F and has a carbon content of 0.04% or higher.
- H2 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating it to a minimum temperature of 1900°F and quenching in water or rapidly cooling by other means.
- H3 For Section I applications, cold drawn pipe and tube shall be annealed at 1900°F minimum.
- H4 The material shall be given a 1725°F to 1825°F stabilizing heat treatment.

NOTES – TIME-DEPENDENT PROPERTIES [See General Note (e)]

- T1 Allowable stresses for temperatures of 250°F and above are values obtained from time-dependent properties.
- T2 Allowable stresses for temperatures of 300°F and above are values obtained from time-dependent properties.
- T3 Allowable stresses for temperatures of 350°F and above are values obtained from time-dependent properties.
- T4 Allowable stresses for temperatures of 400°F and above are values obtained from time-dependent properties.
- T5 Allowable stresses for temperatures of 500°F and above are values obtained from time-dependent properties.
- T6 Allowable stresses for temperatures of 550°F and above are values obtained from time-dependent properties.
- T7 Allowable stresses for temperatures of 600°F and above are values obtained from time-dependent properties.
- T8 Allowable stresses for temperatures of 750°F and above are values obtained from time-dependent properties.
- T9 Allowable stresses for temperatures of 800°F and above are values obtained from time-dependent properties.
- T10 Allowable stresses for temperatures of 850°F and above are values obtained from time-dependent properties.
- T11 Allowable stresses for temperatures of 900°F and above are values obtained from time-dependent properties.
- T12 Allowable stresses for temperatures of 950°F and above are values obtained from time-dependent properties.
- T13 Allowable stresses for temperatures of 1000°F and above are values obtained from time-dependent properties.
- T14 Allowable stresses for temperatures of 1050°F and above are values obtained from time-dependent properties.
- T15 Allowable stresses for temperatures of 1100°F and above are values obtained from time-dependent properties.
- T16 Allowable stresses for temperatures of 1150°F and above are values obtained from time-dependent properties.
- T17 Allowable stresses for temperatures of 1200°F and above are values obtained from time-dependent properties.
- T18 Allowable stresses for temperatures of 1250°F and above are values obtained from time-dependent properties.
- T19 Allowable stresses for temperatures of 450°F and above are values obtained from time-dependent properties.

NOTES – WELDING REQUIREMENTS

- W1 No welding or brazing permitted.
- W2 For Section VIII applications, UNF-56(d) shall apply for welded constructions.
- W3 For welded and brazed constructions, stress values for O (annealed) temper material shall be used.
- W4 The stress values given for this material are not applicable when either welding or thermal cutting is employed.
- W5 These S values do not include a longitudinal weld efficiency factor. For Section III applications, for materials welded without filler metal, ultrasonic examination, radiographic examination, or eddy current examination, in accordance with NC-2550, shall provide a longitudinal weld efficiency factor of 1.00. Materials welded with filler metal meeting the requirements of NC-2560 shall receive a longitudinal weld efficiency factor of 1.00. Other longitudinal weld efficiency factors shall be in accordance with the following:
- (a) for single butt weld, with filler metal, 0.80
 - (b) for single or double butt weld, without filler metal, 0.85
 - (c) for double butt weld, with filler metal, 0.90
 - (d) for single or double butt weld, with radiography or ultrasonic, 1.00
- W6 Filler metal shall not be used in the manufacture of welded pipe or tubing.
- W7 Strength of reduced-section tensile specimen required to qualify welding procedures. See QW-150, Section IX.
- W8 For Section VIII and XII applications, no welding is permitted.

NOTES TO TABLE 1B (CONT'D)

NOTES – WELDING REQUIREMENTS (CONT'D)

- W9 Use NFA-12 when welded with 5356 or 5556 filler metal, all thicknesses, or 4043 or 5554 filler metal, thickness $\leq \frac{3}{8}$ in. Use NFA-13 when welded with 4043 or 5554 filler metal, thickness $> \frac{3}{8}$ in.
- W10 For welded and brazed constructions, stress values for the welded and annealed (W061) temper material shall be used.
- W11 These maximum allowable stress values are to be used in welded or brazed constructions.
- W12 These S values do not include a weld factor. For Section VIII, Division 1 and Section XII applications using welds made without filler metal, the tabulated tensile stress values shall be multiplied by 0.85. For welds made with filler metal, consult UW-12 of Section VIII, Division 1, or TW-130.4 of Section XII, as applicable.
- W13 For service at 1200°F or higher, the deposited weld metal shall be of the same nominal chemistry as the base metal.
- W14 No welding permitted.

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customan

INTENTIONALLY LEFT BLANK

Table 2A
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	Carbon steel	Bar, shapes	SA-675	45	...	...	...	1	1
2	Carbon steel	Plate	SA-285	A	K01700	...	...	1	1
3	Carbon steel	Wld. pipe	SA-672	A45	K01700	...	...	1	1
4	Carbon steel	Wld. pipe	SA-53	E/A	K02504	...	...	1	1
5	Carbon steel	Smls. pipe	SA-53	S/A	K02504	...	...	1	1
6	Carbon steel	Smls. pipe	SA-106	A	K02501	...	...	1	1
7	Carbon steel	Bar, shapes	SA-675	50	...	...	...	1	1
8	Carbon steel	Plate	SA-285	B	K02200	...	≤2	1	1
9	Carbon steel	Wld. pipe	SA-672	A50	K02200	...	...	1	1
10	Carbon steel	Bar, shapes	SA-675	55	...	...	...	1	1
11	Carbon steel	Plate	SA-285	C	K02801	...	≤2	1	1
12	Carbon steel	Wld. pipe	SA-333	1	K03008	...	...	1	1
13	Carbon steel	Smls. pipe	SA-333	1	K03008	...	...	1	1
14	Carbon steel	Wld. tube	SA-334	1	K03008	...	...	1	1
15	Carbon steel	Smls. tube	SA-334	1	K03008	...	...	1	1
16	Carbon steel	Plate	SA-516	55	K01800	...	...	1	1
17	Carbon steel	Smls. pipe	SA-524	II	K02104	...	...	1	1
18	Carbon steel	Wld. pipe	SA-671	CA55	K02801	...	...	1	1
19	Carbon steel	Wld. pipe	SA-671	CE55	K02202	...	...	1	1
20	Carbon steel	Wld. pipe	SA-672	A55	K02801	...	...	1	1
21	Carbon steel	Wld. pipe	SA-672	B55	K02001	...	...	1	1
22	Carbon steel	Wld. pipe	SA-672	C55	K01800	...	...	1	1
23	Carbon steel	Wld. pipe	SA-672	E55	K02202	...	...	1	1
24	Carbon steel	Plate, bar, shapes	SA-36	...	K02600	...	...	1	1
25	Carbon steel	Plate	SA-662	A	K01701	...	...	1	1
26	Carbon steel	Forgings	SA-181	...	K03502	60	...	1	1
27	Carbon steel	Castings	SA-216	WCA	J02502	...	...	1	1
28	Carbon steel	Forgings	SA-266	1	K03506	...	...	1	1
29	Carbon steel	Forgings	SA-350	LF1	K03009	1	...	1	1
30	Carbon steel	Castings	SA-352	LCA	J02504	...	...	1	1
31	Carbon steel	Cast pipe	SA-660	WCA	J02504	...	...	1	1
32	Carbon steel	Bar, shapes	SA-675	60	...	...	...	1	1
33	Carbon steel	Forgings	SA-765	I	K03046	...	...	1	1
34	Carbon steel	Plate	SA-515	60	K02401	...	...	1	1
35	Carbon steel	Plate	SA-516	60	K02100	...	...	1	1
36	Carbon steel	Wld. pipe	SA-671	CB60	K02401	...	...	1	1
37	Carbon steel	Wld. pipe	SA-671	CC60	K02100	...	...	1	1
38	Carbon steel	Wld. pipe	SA-671	CE60	K02402	...	...	1	1
39	Carbon steel	Wld. pipe	SA-672	B60	K02401	...	...	1	1
40	Carbon steel	Wld. pipe	SA-672	C60	K02100	...	...	1	1
41	Carbon steel	Wld. pipe	SA-672	E60	K02402	...	...	1	1
42	Carbon steel	Plate	SA-283	D	K02702	...	...	1	1
43	Carbon steel	Wld. pipe	SA-53	E/B	K03005	...	...	1	1
44	Carbon steel	Smls. pipe	SA-53	S/B	K03005	...	...	1	1
45	Carbon steel	Smls. pipe	SA-106	B	K03006	...	...	1	1

Table 2A
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	45	22.5	NP	700	CS-6	...
2	45	24	700	700	CS-1	...
3	45	24	700	NP	CS-1	G1, G4
4	48	30	700 (SPT)	NP	CS-2	E2
5	48	30	700 (SPT)	NP	CS-2	E2
6	48	30	700	700	CS-2	E2
7	50	25	700 (SPT)	700	CS-1	...
8	50	27	700	700	CS-1	E2
9	50	27	700	NP	CS-1	E2, G1, G4
10	55	27.5	700 (SPT)	700	CS-1	...
11	55	30	700	700	CS-2	...
12	55	30	700	NP	CS-2	...
13	55	30	700	700	CS-2	...
14	55	30	700	NP	CS-2	...
15	55	30	700	700	CS-2	...
16	55	30	700	700	CS-2	...
17	55	30	NP	700	CS-2	...
18	55	30	700	NP	CS-2	G1, G4
19	55	30	700	NP	CS-2	G1, G4
20	55	30	700	NP	CS-2	G1, G4
21	55	30	700	NP	CS-2	G1, G4
22	55	30	700	NP	CS-2	G1, G4
23	55	30	700	NP	CS-2	G1, G4
24	58	36	700 (SPT)	700	CS-2	E2
25	58	40	NP	700	CS-2	E1
26	60	30	700	700	CS-2	...
27	60	30	700	700	CS-2	...
28	60	30	700	700	CS-2	...
29	60	30	700	700	CS-2	...
30	60	30	700	NP	CS-2	...
31	60	30	700	NP	CS-2	...
32	60	30	700 (SPT)	700	CS-2	...
33	60	30	NP	700	CS-2	...
34	60	32	700	700	CS-2	...
35	60	32	700	700	CS-2	...
36	60	32	700	NP	CS-2	G1, G4
37	60	32	700	NP	CS-2	G1, G4
38	60	32	700	NP	CS-2	G1, G4
39	60	32	700	NP	CS-2	G1, G4
40	60	32	700	NP	CS-2	G1, G4
41	60	32	700	NP	CS-2	G1, G4
42	60	33	NP	700	CS-2	E2
43	60	35	700 (SPT)	NP	CS-2	E2
44	60	35	700 (SPT)	NP	CS-2	E2
45	60	35	700	700	CS-2	E2

Table 2A
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	15.0	14.1	13.7	...	13.3	12.8	12.2	11.5	11.1	10.7	...	...	...	...
2	15.0	...	14.7	...	14.2	13.7	13.0	12.3	11.9	11.5	...	...	...	...
3	15.0	...	14.7	...	14.2	13.7	13.0	12.3	11.9	11.5	...	...	...	...
4	16.0	...	16.0	...	16.0	16.0	16.0	15.3	14.6	14.4	...	...	...	...
5	16.0	16.0	16.0	...	16.0	16.0	16.0	15.3	14.6	14.4	...	...	...	...
6	16.0	16.0	16.0	...	16.0	16.0	16.0	15.3	14.6	14.4	...	...	...	...
7	16.7	...	15.3	...	14.7	14.2	13.6	12.8	12.4	11.9	...	...	...	...
8	16.7	16.7	16.5	...	15.9	15.4	14.7	13.8	13.3	13.0	...	...	...	...
9	16.7	16.7	16.5	...	15.9	15.4	14.7	13.8	13.3	13.0	...	...	...	...
10	18.3	...	16.8	...	16.2	15.7	14.9	14.1	13.6	13.1	...	...	...	...
11	18.3	18.3	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
12	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
13	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
14	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
15	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
16	18.3	18.3	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
17	18.3	18.3	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
18	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
19	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
20	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
21	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
22	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
23	18.3	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
24	19.3	...	19.3	...	19.3	19.3	19.3	18.4	17.8	17.3	...	...	...	...
25	19.3	19.3	19.3	...	19.3	19.3	19.3	19.3	19.3	19.2	...	...	...	...
26	20.0	18.8	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
27	20.0	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
28	20.0	18.8	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
29	20.0	18.8	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
30	20.0	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
31	20.0	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
32	20.0	...	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
33	20.0	18.8	18.3	...	17.7	17.1	16.3	15.3	14.8	14.3	...	...	...	...
34	20.0	20.0	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
35	20.0	20.0	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
36	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
37	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
38	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
39	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
40	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
41	20.0	...	19.5	...	18.9	18.2	17.4	16.4	15.8	15.3	...	...	...	...
42	20.0	20.0	20.0	...	19.5	18.8	17.9	16.9	16.3	15.4	...	...	...	...
43	20.0	...	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
44	20.0	...	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
45	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	Carbon steel	Fittings	SA-234	WPB	K03006	...	...	1	1
2	Carbon steel	Wld. fittings	SA-234	WPB	K03006	W	...	1	1
3	Carbon steel	Wld. pipe	SA-333	6	K03006	...	...	1	1
4	Carbon steel	Smls. pipe	SA-333	6	K03006	...	...	1	1
5	Carbon steel	Smls. & wld. tube	SA-334	6	K03006	...	...	1	1
6	Carbon steel	Forgings	SA-372	A	K03002	...	...	1	1
7	Carbon steel	Fittings	SA-420	WPL6	...	...	...	1	1
8	Carbon steel	Wld. fittings	SA-420	WPL6	...	WP-W	...	1	1
9	Carbon steel	Smls. pipe	SA-524	I	K02104	...	...	1	1
10	Carbon steel	Bar	SA-696	B	K03200	...	...	1	1
11	Carbon steel	Forgings	SA-727	...	K02506	...	...	1	1
12	Carbon steel	Wld. tube	SA-178	C	K03503	...	...	1	1
13	Carbon steel	Wld. tube	SA-178	C	K03503	...	...	1	1
14	Carbon steel	Smls. tube	SA-210	A-1	K02707	...	...	1	1
15	Carbon steel	Bar, shapes	SA-675	65	...	...	...	1	1
16	Carbon steel	Castings	SA-352	LCB	J03003	...	...	1	1
17	Carbon steel	Plate	SA-515	65	K02800	...	...	1	1
18	Carbon steel	Plate	SA-516	65	K02403	...	...	1	1
19	Carbon steel	Wld. pipe	SA-671	CB65	K02800	...	...	1	1
20	Carbon steel	Wld. pipe	SA-671	CC65	K02403	...	...	1	1
21	Carbon steel	Wld. pipe	SA-672	B65	K02800	...	...	1	1
22	Carbon steel	Wld. pipe	SA-672	C65	K02403	...	...	1	1
23	Carbon steel	Plate	SA-662	B	K02203	...	...	1	1
24	Carbon steel	Plate	SA-537	...	K12437	1	$2\frac{1}{2} < t \leq 4$	1	2
25	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...	$2\frac{1}{2} < t \leq 4$	1	2
(25)	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$1.4 < t \leq 6.3$	1	2
(25)	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$t \leq 1.4$	1	1
28	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$6 < t \leq 10$	1	2
29	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$4 < t \leq 6$	1	2
30	Carbon steel	Bar, shapes	SA-675	70	...	...	...	1	1
31	Carbon steel	Forgings	SA-105	...	K03504	...	...	1	2
32	Carbon steel	Forgings	SA-181	...	K03502	70	...	1	2
33	Carbon steel	Castings	SA-216	WCB	J03002	...	...	1	2
34	Carbon steel	Forgings	SA-266	2	K03506	...	...	1	2
35	Carbon steel	Forgings	SA-266	4	K03017	...	...	1	2
36	Carbon steel	Forgings	SA-350	LF2	K03011	...	...	1	2
37	Carbon steel	Forgings	SA-508	1	K13502	...	...	1	2
38	Carbon steel	Forgings	SA-508	1A	K13502	...	...	1	2
39	Carbon steel	Forgings	SA-541	1	K03506	...	...	1	2
40	Carbon steel	Forgings	SA-541	1A	K03020	...	...	1	2
41	Carbon steel	Cast pipe	SA-660	WCB	J03003	...	...	1	2
42	Carbon steel	Forgings	SA-765	II	K03047	...	...	1	2
43	Carbon steel	Plate	SA-515	70	K03101	...	...	1	2
44	Carbon steel	Plate	SA-516	70	K02700	...	...	1	2
45	Carbon steel	Wld. pipe	SA-671	CB70	K03101	...	...	1	2

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	60	35	700	700	CS-2	E2
2	60	35	700	NP	CS-2	E2
3	60	35	700	NP	CS-2	E2
4	60	35	700	700	CS-2	E2
5	60	35	700	NP	CS-2	E2
6	60	35	NP	650	CS-2	G19, H5
7	60	35	700	700	CS-2	E2
8	60	35	700	NP	CS-2	E2
9	60	35	NP	700	CS-2	E2
10	60	35	700	NP	CS-2	E2
11	60	36	700 (SPT)	700	CS-2	E2
12	60	37	700	NP	CS-2	E2
13	60	37	NP	700	CS-2	E2, G18
14	60	37	700	700	CS-2	E2
15	65	32.5	NP	700	CS-2	...
16	65	35	700	700	CS-2	...
17	65	35	700	700	CS-2	...
18	65	35	700	700	CS-2	...
19	65	35	700	NP	CS-2	G1, G4
20	65	35	700	NP	CS-2	G1, G4
21	65	35	700	NP	CS-2	G1, G4
22	65	35	700	NP	CS-2	G1, G4
23	65	40	NP	700	CS-2	E2
24	65	45	700	700	CS-2	E2
25	65	45	700	NP	CS-2	E2, G1, G2
26	66.5	37	NP	700	CS-2	E2
27	66.5	40.5	NP	700	CS-2	E2
28	68	40.5	NP	700	CS-2	E2
29	69.5	43	NP	700	CS-2	E2
30	70	35	NP	700	CS-2	...
31	70	36	700	700	CS-2	...
32	70	36	700	700	CS-2	...
33	70	36	700	700	CS-2	...
34	70	36	700	700	CS-2	...
35	70	36	NP	700	CS-2	...
36	70	36	700	700	CS-2	...
37	70	36	700	700	CS-2	...
38	70	36	700	700	CS-2	...
39	70	36	700	700	CS-2	...
40	70	36	700	700	CS-2	...
41	70	36	700	NP	CS-2	...
42	70	36	NP	700	CS-2	...
43	70	38	700	700	CS-2	...
44	70	38	700	700	CS-2	...
45	70	38	700	NP	CS-2	G1, G3

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
2	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
3	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
4	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
5	20.0	...	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
6	20.0	20.0	20.0	20.0	20.0	19.9	19.0	17.9	17.3	...	...	...	...	...
7	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
8	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
9	20.0	20.0	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
10	20.0	...	20.0	...	20.0	19.9	19.0	17.9	17.3	16.8	...	...	...	...
11	20.0	20.0	20.0	...	20.0	20.0	19.6	18.4	17.8	17.3	...	...	...	...
12	20.0	...	20.0	...	20.0	20.0	20.0	18.9	18.3	17.8	...	...	...	...
13	17.0	...	17.0	...	17.0	17.0	17.0	16.1	15.5	15.1	...	...	...	...
14	20.0	20.0	20.0	...	20.0	20.0	20.0	18.9	18.3	17.8	...	...	...	...
15	21.7	20.4	19.8	19.5	19.2	18.5	17.7	16.6	16.1	15.5	...	...	...	...
16	21.7	21.7	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
17	21.7	21.7	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
18	21.7	21.7	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
19	21.7	...	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
20	21.7	...	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
21	21.7	...	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
22	21.7	...	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
23	21.7	21.7	21.7	...	21.7	21.7	21.7	20.4	19.8	19.2	...	...	...	...
24	21.7	...	21.7	...	21.7	21.7	21.7	21.7	20.5	19.6	...	...	...	...
25	21.7	...	21.7	...	21.7	21.7	21.7	21.7	20.5	19.6	...	...	...	...
26	22.2	22.2	22.2	21.9	21.7	20.9	19.9	18.8	18.1	17.5	14.8	12.0	9.3	6.7 (25)
27	22.2	22.2	22.2	22.2	22.2	22.2	21.9	20.6	19.9	19.3	14.8	12.0	9.3	6.7 (25)
28	22.7	22.7	22.7	22.7	22.7	22.7	22.1	20.7	20.1	18.3	14.8	12.0	9.3	6.7
29	23.2	23.2	23.2	23.2	23.2	23.2	23.2	21.9	21.1	18.3	14.8	12.0	9.3	6.7
30	23.3	21.9	21.4	...	20.6	19.9	19.0	17.9	17.3	16.7	...	...	...	...
31	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
32	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
33	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
34	23.3	...	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
35	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
36	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
37	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
38	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
39	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
40	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
41	23.3	...	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
42	23.3	22.6	22.0	...	21.2	20.5	19.6	18.4	17.8	17.2	...	...	...	...
43	23.3	23.3	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...
44	23.3	23.3	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...
45	23.3	...	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	Carbon steel	Wld. pipe	SA-671	CC70	K02700	...	...	1	2
2	Carbon steel	Wld. pipe	SA-672	B70	K03101	...	...	1	2
3	Carbon steel	Wld. pipe	SA-672	C70	K02700	...	...	1	2
4	Carbon steel	Smls. pipe	SA-106	C	K03501	...	...	1	2
5	Carbon steel	Smls. tube	SA-210	C	K03501	...	...	1	2
6	Carbon steel	Castings	SA-216	WCC	K02503	...	...	1	2
7	Carbon steel	Fittings	SA-234	WPC	K03501	...	...	1	2
8	Carbon steel	Wld. fittings	SA-234	WPC	K03501	W	...	1	2
9	Carbon steel	Castings	SA-352	LCC	J02505	...	...	1	2
10	Carbon steel	Castings	SA-487	16	...	A	...	1	2
11	Carbon steel	Plate	SA-537	...	K12437	3	$4 < t \leq 6$	1	3
12	Carbon steel	Cast pipe	SA-660	WCC	J02505	...	...	1	2
13	Carbon steel	Bar	SA-696	C	K03200	...	...	1	2
14	Carbon steel	Plate	SA-662	C	K02007	...	...	1	2
15	Carbon steel	Plate	SA-537	...	K12437	2	$4 < t \leq 6$	1	3
16	Carbon steel	Plate	SA-738	C	...	...	$4 < t \leq 6$	1	3
17	Carbon steel	Plate	SA-537	...	K12437	1	$\leq 2\frac{1}{2}$	1	2
18	Carbon steel	Wld. pipe	SA-671	CD70	K12437	...	$\leq 2\frac{1}{2}$	1	2
19	Carbon steel	Wld. pipe	SA-672	D70	K12437	...	$\leq 2\frac{1}{2}$	1	2
20	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...	$\leq 2\frac{1}{2}$	1	2
21	Carbon steel	Plate	SA-841	A	...	1	$t \leq 4$	1	2
(25) 22	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$2.8 < t \leq 6.3$	1	2
(25) 23	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$1.4 < t \leq 2.8$	1	2
24	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$2.5 < t \leq 4$	1	2
(25) 25	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$2.8 < t \leq 6.3$	1	2
26	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$1.5 < t \leq 2.5$	1	2
27	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$\frac{5}{8} < t \leq 1.5$	1	2
28	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$\leq \frac{5}{8}$	1	2
29	Carbon steel	Forgings	SA-266	3	K05001	...	...	1	2
30	Carbon steel	Plate	SA-299	A	K02803	...	> 1	1	2
31	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...	> 1	1	2
32	Carbon steel	Plate	SA-299	A	K02803	...	≤ 1	1	2
33	Carbon steel	Wld. pipe	SA-671	CK75	K02803	...	≤ 1	1	2
34	Carbon steel	Wld. pipe	SA-672	N75	K02803	...	≤ 1	1	2
35	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...	≤ 1	1	2
36	Carbon steel	Forgings	SA-372	B	K04001	...	...	1	2
37	Carbon steel	Plate	SA-738	A	K12447	N	$\leq 2\frac{1}{2}$	1	2
38	Carbon steel	Plate	SA-738	A	K12447	QT	...	1	2
39	Carbon steel	Plate	SA-537	...	K12437	3	$2\frac{1}{2} < t \leq 4$	1	3
40	Carbon steel	Plate	SA-537	...	K12437	2	$2\frac{1}{2} < t \leq 4$	1	3
41	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...	$2\frac{1}{2} < t \leq 4$	1	3
42	Carbon steel	Plate	SA-738	C	...	...	$2\frac{1}{2} < t \leq 4$	1	3
43	Carbon steel	Plate	SA-299	B	K02803	...	$t > 1$	1	3
44	Carbon steel	Plate	SA-299	B	K02803	...	$t \leq 1$	1	3
45	Carbon steel	Forgings	SA-765	IV	K02009	...	...	1	3

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	70	38	700	NP	CS-2	G1, G4
2	70	38	700	NP	CS-2	G1, G3
3	70	38	700	NP	CS-2	G1, G4
4	70	40	700	700	CS-2	E2
5	70	40	NP	700	CS-2	E2
6	70	40	700	700	CS-2	E2
7	70	40	700	700	CS-2	E2
8	70	40	700	NP	CS-2	E2
9	70	40	700	NP	CS-2	E2
10	70	40	700	NP	CS-2	E2
11	70	40	NP	700	CS-2	E2
12	70	40	700	NP	CS-2	E2
13	70	40	700	NP	CS-2	E2
14	70	43	NP	700	CS-3	E2
15	70	46	700	700	CS-3	E2
16	70	46	NP	650	CS-3	...
17	70	50	700	700	CS-3	E2
18	70	50	700	NP	CS-3	E2, G1, G4
19	70	50	700	NP	CS-3	E2, G1, G4
20	70	50	700	NP	CS-3	E2, G1, G4
21	70	50	NP	650	CS-3	E2
22	71	40.5	NP	700	CS-2	E2
23	74	41.5	NP	700	CS-2	E2
24	71	45.5	NP	700	CS-2	E2
25	74	44	NP	700	CS-2	E2
26	74	48.5	NP	700	CS-2	E2
27	74	50	NP	700	CS-2	E2
28	74	51.5	NP	700	CS-2	E2
29	75	37.5	700	700	CS-2	W6
30	75	40	700	700	CS-2	...
31	75	40	700	NP	CS-2	G1, G4
32	75	42	700	700	CS-2	E2
33	75	42	700	NP	CS-2	E2, G1
34	75	42	700	NP	CS-2	E2, G1
35	75	42	700	NP	CS-2	E2, G1
36	75	45	NP	100	CS-3	G19, H5, W5, W6
37	75	45	NP	700	CS-2	...
38	75	45	NP	700	CS-2	...
39	75	50	NP	700	CS-5	E2
40	75	55	700	700	CS-5	E2
41	75	55	700	NP	CS-5	E2
42	75	55	NP	650	CS-5	...
43	80	45	...	700	CS-3	E2
44	80	47	...	700	CS-3	E2
45	80	50	NP	700	CS-3	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	23.3	...	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...
2	23.3	...	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...
3	23.3	...	23.2	...	22.4	21.6	20.6	19.4	18.8	18.1	...	...	...	...
4	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
5	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
6	23.3	23.3	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
7	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
8	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
9	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
10	23.3	...	23.2	...	21.9	21.1	20.4	19.6	19.1	18.6	...	...	...	...
11	23.3	23.3	23.3	...	23.2	22.2	21.3	20.6	20.2	19.8	...	...	...	...
12	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
13	23.3	...	23.3	...	23.3	22.8	21.7	20.4	19.8	19.2	...	...	...	...
14	23.3	...	23.3	...	23.3	23.3	23.3	22.0	21.2	20.7	...	...	...	...
15	23.3	...	23.3	...	23.3	23.3	23.3	23.1	22.5	20.7	...	...	...	...
16	23.3	...	23.3	...	23.3	23.3	23.3	23.1	22.5	...	...	...	...	...
17	23.3	...	23.3	...	22.8	22.7	22.7	22.4	21.9	21.4	...	...	...	...
18	23.3	...	23.3	...	22.8	22.7	22.7	22.4	21.9	21.4	...	...	...	...
19	23.3	...	23.3	...	22.8	22.7	22.7	22.4	21.9	21.4	...	...	...	...
20	23.3	...	23.3	...	22.8	22.7	22.7	22.4	21.9	21.4	...	...	...	...
21	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	22.8	...	...	...	...	...
22	23.7	23.7	23.7	23.7	23.7	22.9	21.9	20.6	19.9	19.3	14.8	12.0	9.3	6.7 (25)
23	24.7	24.7	24.7	24.4	24.2	23.4	22.3	21.0	20.3	19.6	14.8	12.0	9.3	6.7 (25)
24	23.7	23.7	23.7	23.7	23.7	23.7	23.7	22.5	21.7	18.3	14.8	12.0	9.3	6.7
25	24.7	24.7	24.7	24.7	24.7	24.7	23.9	22.5	21.7	20.0	14.8	12.0	9.3	6.7 (25)
26	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.0	18.3	14.8	12.0	9.3	6.7
27	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.0	18.3	14.8	12.0	9.3	6.7
28	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.7	24.7	18.3	14.8	12.0	9.3	6.7
29	25.0	23.5	22.9	...	22.1	21.4	20.4	19.2	18.5	17.9	...	...	...	...
30	25.0	25.0	24.4	...	23.6	22.8	21.7	20.4	19.8	19.1	...	...	...	...
31	25.0	...	24.4	...	23.6	22.8	21.7	20.4	19.8	19.1	...	...	...	...
32	25.0	25.0	25.0	...	24.8	23.9	22.8	21.5	20.8	20.2	...	...	...	...
33	25.0	25.0	25.0	...	24.8	23.9	22.8	21.5	20.8	20.2	...	...	...	...
34	25.0	25.0	25.0	...	24.8	23.9	22.8	21.5	20.8	20.2	...	...	...	...
35	25.0	...	25.0	...	24.8	23.9	22.8	21.5	20.8	20.2	...	...	...	...
36	25.0	...	...	...	...	...	...	...	...	...	...	...	...	...
37	25.0	...	25.0	...	24.3	22.6	21.2	20.2	19.7	19.3	...	...	...	...
38	25.0	...	25.0	...	25.0	25.0	24.0	23.1	22.7	22.3	...	...	...	...
39	25.0	...	25.0	...	25.0	25.0	25.0	24.8	22.5	21.4	...	...	...	...
40	25.0	...	25.0	...	25.0	25.0	25.0	24.8	24.4	24.3	...	...	...	...
41	25.0	...	25.0	...	25.0	25.0	25.0	24.8	24.4	24.3	...	...	...	...
42	25.0	...	25.0	...	25.0	25.0	25.0	24.8	24.4	...	...	...	...	...
43	26.7	26.7	26.7	26.6	26.5	25.6	24.5	23.0	22.3	19.6	15.7	12.6	9.3	6.7
44	26.7	26.7	26.7	26.6	26.5	25.6	24.5	23.0	22.3	19.6	15.7	12.6	9.3	6.7
45	26.7	...	26.7	...	26.7	26.4	26.4	25.5	25.1	24.7	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	Carbon steel	Plate	SA-537	...	K12437	3	$\leq 2\frac{1}{2}$	1	3
2	Carbon steel	Plate	SA-537	...	K12437	2	$\leq 2\frac{1}{2}$	1	3
3	Carbon steel	Wld. pipe	SA-671	CD80	K12437	...	$\leq 2\frac{1}{2}$	1	3
4	Carbon steel	Wld. pipe	SA-672	D80	K12437	...	$\leq 2\frac{1}{2}$	1	3
5	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...	$\leq 2\frac{1}{2}$	1	3
6	Carbon steel	Plate	SA-738	C	...	...	$\leq 2\frac{1}{2}$	1	3
7	Carbon steel	Plate	SA-841	B	...	2	$t \leq 4$	1	3
8	Carbon steel	Plate	SA-612	...	K02900	N	$\frac{1}{2} < t \leq 1$	10C	1
9	Carbon steel	Plate	SA-612	...	K02900	N	$\leq \frac{1}{2}$	10C	1
10	Carbon steel	Plate	SA-738	B	K12007	...	...	1	3
11	Carbon steel	Forgings	SA-372	C	K04801	...	...	...	...
12	Carbon steel	Plate	SA-724	A	K11831	...	...	1	4
13	Carbon steel	Plate	SA-724	C	K12037	...	...	1	4
14	Carbon steel	Plate	SA-724	B	K12031	...	...	1	4
15	Ductile cast iron	Castings	SA-874	...	...	...	$12 < t < 21$	...	...
16	Ductile cast iron	Castings	SA/JIS G5504	FCD 300 LT	...	...	$12 < t < 21$	...	...
17	C-Mn-Si-Cb	Plate	SA-737	B	K12001	...	...	1	2
18	C-Mn-Si-V	Plate	SA-737	C	K12202	...	...	1	3
19	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1b	K11422	...	...	3	1
20	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1	K11522	...	...	3	1
21	C- $\frac{1}{2}$ Mo	Fittings	SA-234	WP1	K12821	...	...	3	1
22	C- $\frac{1}{2}$ Mo	Wld. fittings	SA-234	WP1	K12821	W	...	3	1
23	C- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P1	K11522	...	...	3	1
24	C- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP1	K11522	...	...	3	1
25	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1a	K12023	...	...	3	1
26	C- $\frac{1}{2}$ Mo	Castings	SA-217	WC1	J12524	...	...	3	1
27	C- $\frac{1}{2}$ Mo	Castings	SA-352	LC1	J12522	...	...	3	1
28	C- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP1	J12521	...	...	3	1
29	C- $\frac{1}{2}$ Mo	Plate	SA-204	A	K11820	...	...	3	1
30	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L65	K11820	...	...	3	1
31	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-65	K11820	...	...	3	1
32	C- $\frac{1}{2}$ Mo	Forgings	SA-182	F1	K12822	...	...	3	2
33	C- $\frac{1}{2}$ Mo	Plate	SA-204	B	K12020	...	...	3	2
34	C- $\frac{1}{2}$ Mo	Forgings	SA-336	F1	K12520	...	...	3	2
35	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L70	K12020	...	...	3	2
36	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-70	K12020	...	...	3	2
37	C- $\frac{1}{2}$ Mo	Plate	SA-204	C	K12320	...	...	3	2
38	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L75	K12320	...	...	3	2
39	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-75	K12320	...	...	3	2
40	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	70	...	...	...
41	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	70	...	...	...
42	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo-V	Plate	SA-517	B	K11630	...	$\leq 1\frac{1}{4}$	11B	4
43	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Forgings	SA-592	A	K11856	...	$2\frac{1}{2} < t \leq 4$	11B	1
44	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Plate	SA-517	A	K11856	...	$\leq 1\frac{1}{4}$	11B	1
45	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Forgings	SA-592	A	K11856	...	$\leq 2\frac{1}{2}$	11B	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	80	55	NP	700	CS-5	E1
2	80	60	700	700	CS-5	E1
3	80	60	700	NP	CS-5	E1, G1, G4
4	80	60	700	NP	CS-5	E1, G1, G4
5	80	60	700	NP	CS-5	E1, G1, G4
6	80	60	NP	650	CS-5	E1
7	80	60	NP	650	CS-3	...
8	81	50	NP	650	CS-3	...
9	83	50	NP	650	CS-3	...
10	85	60	650	600	CS-5	...
11	90	55	NP	100	CS-3	G19, H5, W5, W6
12	90	70	NP	700	CS-5	E1
13	90	70	NP	700	CS-5	E1
14	95	75	NP	700	CS-5	E1
15	43.5	29	650	NP	CD-2	G17, W1
16	43.5	29	650	NP	CD-2	G17, W1
17	70	50	700	700	CS-3	E2
18	80	60	700	700	CS-3	E1
19	53	28	NP	700	CS-1	...
20	55	30	NP	700	CS-2	...
21	55	30	700	700	CS-2	...
22	55	30	700	NP	CS-2	...
23	55	30	700	700	CS-2	...
24	55	30	700	700	CS-2	...
25	60	32	NP	700	CS-2	...
26	65	35	700	700	CS-2	...
27	65	35	700	700	CS-2	...
28	65	35	700	NP	CS-2	...
29	65	37	700	700	CS-2	...
30	65	37	700	NP	CS-2	G1, G2
31	65	37	700	NP	CS-2	G1, G2
32	70	40	700	700	CS-2	...
33	70	40	700	700	CS-2	...
34	70	40	700	700	CS-2	...
35	70	40	700	NP	CS-2	G1, G2
36	70	40	700	NP	CS-2	G1, G2
37	75	43	700	700	CS-2	...
38	75	43	700	NP	CS-2	G1, G2
39	75	43	700	NP	CS-2	G1, G2
40	120	70	NP	100	CS-3	G19, H4, W5, W6
41	120	70	NP	100	CS-3	G19, H4, W5, W6
42	115	100	700 (SPT)	700	HT-1	...
43	105	90	700 (SPT)	NP	CS-5	...
44	115	100	700 (SPT)	700	HT-1	...
45	115	100	NP	700	HT-1	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	24.3	...	...	...	...
2	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	24.3	...	...	...	...
3	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	24.3	...	...	...	...
4	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	24.3	...	...	...	...
5	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	24.3	...	...	...	...
6	26.7	...	26.7	...	26.7	26.7	26.7	26.4	26.0	...	...	...	...	...
7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.6	26.1	...	...	...	...	...
8	27.0	...	27.0	...	26.5	25.0	23.5	22.6	22.0	...	...	...	...	...
9	27.7	...	27.7	...	27.1	25.0	23.5	22.6	22.0	...	...	...	...	...
10	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.1	27.7	...	...	...	...	...
11	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
12	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	26.2	25.9	...	...	...	...
13	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	26.2	25.9	...	...	...	...
14	31.7	31.7	31.7	31.7	31.7	31.7	31.7	31.4	26.2	25.9	...	...	...	...
15	10.9	...	10.8	...	10.3	10.0	9.8	9.6	9.4	...	...	...	...	...
16	10.9	...	10.8	...	10.3	10.0	9.8	9.6	9.4	...	...	...	...	...
17	23.3	23.3	23.3	...	23.3	23.3	23.3	22.6	22.3	22.1	...	...	...	...
18	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.2	25.9	...	...	...	...
19	17.7	...	17.5	...	16.8	16.3	15.8	15.3	15.0	14.7	...	...	...	...
20	18.3	...	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
21	18.3	18.3	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
22	18.3	18.3	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
23	18.3	...	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
24	18.3	...	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
25	20.0	...	20.0	...	19.2	18.6	18.0	17.4	17.1	16.8	...	...	...	...
26	21.7	...	21.7	...	21.0	20.3	19.7	19.1	18.7	18.4	...	...	...	...
27	21.7	...	21.7	...	21.0	20.3	19.7	19.1	18.7	18.4	...	...	...	...
28	21.7	...	21.7	...	21.0	20.3	19.7	19.1	18.7	18.4	...	...	...	...
29	21.7	...	21.7	...	21.7	21.5	20.8	20.2	19.8	19.4	...	...	...	...
30	21.7	...	21.7	...	21.7	21.5	20.8	20.2	19.8	19.4	...	...	...	...
31	21.7	...	21.7	...	21.7	21.5	20.8	20.2	19.8	19.4	...	...	...	...
32	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
33	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
34	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
35	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
36	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
37	25.0	...	25.0	...	25.0	25.0	24.2	23.4	23.0	22.6	...	...	...	...
38	25.0	...	25.0	...	25.0	25.0	24.2	23.4	23.0	22.6	...	...	...	...
39	25.0	...	25.0	...	25.0	25.0	24.2	23.4	23.0	22.6	...	...	...	...
40	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
41	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
42	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...
43	35.0	...	35.0	...	35.0	35.0	35.0	34.8	34.0	33.2	...	...	...	...
44	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...
45	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P2	K11547	...	...	3	1
2	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP2	K11547	...	...	3	1
3	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2	K12143	1	...	3	1
4	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$	K12143	...	...	3	1
5	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T2	K11547	...	...	3	1
6	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP2	J11547	...	...	3	1
7	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F2	K12122	...	...	3	2
8	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2	K12143	2/NT	...	3	2
9	$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	Smls. tube	SA-423	1	K11535	...	...	4	2
10	$\frac{3}{4}\text{Cr}-\frac{3}{4}\text{Ni}-\text{Cu}-\text{Al}$	Smls. pipe	SA-333	4	K11267	...	...	4	2
11	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	70	...	...	...
12	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	70	...	...	...
13	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	70	...	...	...
14	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	G41370	110	...	...	...
15	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	12	K11757	1	...	4	1
16	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	1CR	K11757	22	...	4	1
17	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP12	J11562	...	...	4	1
18	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F12	K11562	1	...	4	1
19	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T12	K11562	...	...	4	1
20	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Fittings	SA-234	WP12	K12062	1	...	4	1
21	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P12	K11562	...	...	4	1
22	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP12	K11562	...	...	4	1
23	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$10 < t \leq 20$	4	1
24	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$6 < t \leq 10$	4	1
25	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$4 < t \leq 6$	4	1
26	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$4 < t \leq 10$	4	1
27	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$2.5 < t \leq 4$	4	1
28	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$2.8 < t \leq 4$	4	1
(25) 29	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$1.4 < t \leq 2.8$	4	1
(25) 30	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$t \leq 1.4$	4	1
31	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$\frac{5}{8} < t \leq 2.5$	4	1
32	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$t \leq \frac{5}{8}$	4	1
33	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	12	K11757	2	...	4	1
34	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	1CR	K11757	42/NT	...	4	1
35	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F12	K11564	2	...	4	1
36	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-336	F12	K11564	...	...	4	1
37	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Castings	SA-217	WC6	J12072	...	...	4	1
38	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP11	J12072	...	...	4	1
39	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Bar	SA-739	B11	K11797	...	...	4	1
40	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Forgings	SA-182	F11	K11597	1	...	4	1
41	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Smls. tube	SA-213	T11	K11597	...	...	4	1
42	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Fittings	SA-234	WP11	...	1	...	4	1
43	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Wld. fittings	SA-234	WP11	...	1/W	...	4	1
44	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Smls. pipe	SA-335	P11	K11597	...	...	4	1
45	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	Forged pipe	SA-369	FP11	K11597	...	...	4	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	55	30	700	700	CS-2	...
2	55	30	700	700	CS-2	...
3	55	33	700	700	CS-2	...
4	55	33	700	NP	CS-2	G1, G2
5	60	30	700	700	CS-2	...
6	60	30	700	NP	CS-2	...
7	70	40	NP	700	CS-2	...
8	70	45	NP	100	CS-3	...
9	60	37	NP	700	CS-2	...
10	60	35	NP	100	CS-2	...
11	120	70	NP	650	CS-5	G19, H4, W5, W6
12	120	70	NP	650	CS-5	G19, H4, W5, W6
13	120	70	NP	650	CS-5	G19, H4, W5, W6
14	135	110	NP	650	HT-1	H4, W5, W6
15	55	33	700	900	CS-2	...
16	55	33	700	NP	CS-2	G15
17	60	30	700	NP	CS-2	...
18	60	32	NP	900	CS-2	...
19	60	32	700	900	CS-2	...
20	60	32	700	900	CS-2	...
21	60	32	700	900	CS-2	...
22	60	32	700	900	CS-2	...
23	61	35	NP	900	CS-2	E4
24	61	35.5	NP	900	CS-2	E4
25	62.5	37	NP	900	CS-2	E4
26	64	38.5	NP	900	CS-2	E4
27	64	39	NP	900	CS-2	E4
28	64	40	NP	900	CS-2	E4
29	64	41.5	NP	900	CS-2	E4
30	64	43	NP	900	CS-2	E4
31	65.5	42	NP	900	CS-2	E4
32	65.5	43.5	NP	900	CS-2	E4
33	65	40	700	900	CS-2	E4
34	65	40	700	NP	CS-2	G16
35	70	40	700	900	CS-2	E4
36	70	40	700	900	CS-2	E4
37	70	40	700	900	CS-2	E4
38	70	40	700	NP	CS-2	...
39	70	45	700	900	CS-3	E4
40	60	30	NP	900	CS-2	...
41	60	30	700	900	CS-2	...
42	60	30	700	900	CS-2	...
43	60	30	700	NP	CS-2	...
44	60	30	700	900	CS-2	...
45	60	30	700	900	CS-2	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	18.3	...	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
2	18.3	...	18.3	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
3	18.3	...	18.3	...	18.3	18.3	18.3	18.0	17.7	17.3	...	...	...	...
4	18.3	...	18.3	...	18.3	18.3	18.3	18.0	17.7	17.3	...	...	...	...
5	20.0	...	18.8	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
6	20.0	...	18.8	...	18.0	17.4	16.9	16.4	16.1	15.7	...	...	...	...
7	23.3	...	23.3	...	23.3	23.2	22.5	21.8	21.4	21.0	...	...	...	...
8	23.3	...	...	...	...	...	...	...	...	...	...	...	...	...
9	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
10	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...
11	40.0	40.0	40.0	...	40.0	40.0	39.4	37.9	36.9	...	...	...	...	...
12	40.0	...	40.0	...	40.0	40.0	39.4	37.9	36.9	...	...	...	...	...
13	40.0	...	40.0	...	40.0	40.0	39.4	37.9	36.9	...	...	...	...	...
14	44.9	...	43.1	...	42.8	42.5	42.1	41.9	40.0	...	...	...	...	...
15	18.3	...	18.0	...	17.6	17.6	17.2	16.8	16.5	16.3	16.0	15.7	15.4	15.0
16	18.3	...	18.0	...	17.6	17.6	17.2	16.8	16.5	16.3	...	...	...	...
17	20.0	...	18.1	...	17.0	16.2	15.7	15.2	15.0	14.8	...	...	...	...
18	20.0	...	19.3	...	18.1	17.3	16.7	16.3	16.0	15.8	15.5	15.3	14.9	14.5
19	20.0	...	19.3	...	18.1	17.3	16.7	16.3	16.0	15.8	15.5	15.3	14.9	14.5
20	20.0	...	19.3	...	18.1	17.3	16.7	16.3	16.0	15.8	15.5	15.3	14.9	14.5
21	20.0	...	19.3	...	18.1	17.3	16.7	16.3	16.0	15.8	15.5	15.3	14.9	14.5
22	20.0	...	19.3	...	18.1	17.3	16.7	16.3	16.0	15.8	15.5	15.3	14.9	14.5
23	20.3	20.2	20.1	19.8	19.5	18.9	18.3	17.7	17.5	17.3	17.0	16.7	16.3	15.8
24	20.3	20.1	19.9	19.8	19.6	19.3	18.6	18.1	17.8	17.5	17.3	16.9	16.5	16.1
25	20.8	20.6	20.4	20.2	20.1	20.0	19.3	18.8	18.5	18.3	17.9	17.6	17.2	16.7
26	21.3	21.1	20.9	20.7	20.5	20.5	20.1	19.6	19.3	19.1	18.7	18.4	17.9	17.5
27	21.3	21.3	21.3	21.3	21.3	21.2	20.5	19.9	19.6	19.3	19.0	18.7	18.3	17.7
28	21.3	21.1	21.0	20.7	20.4	20.3	20.3	20.3	20.1	19.8	19.5	19.1	18.6	18.0
29	21.3	21.1	21.0	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.2	19.8	19.3	18.0 (25)
30	21.3	21.1	21.0	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3	20.3	20.0	18.0 (25)
31	21.8	21.6	21.4	21.2	21.0	20.9	20.9	20.9	20.9	20.8	20.4	20.1	19.6	18.0
32	21.8	21.6	21.4	21.2	21.0	20.9	20.9	20.9	20.9	20.9	20.9	20.7	20.3	18.0
33	21.7	21.7	21.3	...	20.8	20.8	20.8	20.3	20.0	19.7	19.4	19.1	18.6	18.0
34	21.7	...	21.3	...	20.8	20.8	20.8	20.3	20.0	19.7	...	...	...	...
35	23.3	...	22.9	...	22.4	21.7	20.9	20.3	20.0	19.7	19.4	19.1	18.6	18.0
36	23.3	23.3	22.9	...	22.4	21.7	20.9	20.3	20.0	19.7	19.4	19.1	18.6	18.0
37	23.3	...	23.3	...	23.3	22.5	21.7	20.9	20.5	20.1	19.7	19.2	18.7	13.7
38	23.3	...	23.3	...	23.3	22.5	21.7	20.9	20.5	20.1	...	...	...	...
39	23.3	23.3	23.3	...	23.3	23.3	23.3	23.3	23.1	22.6	22.2	21.6	20.2	13.7
40	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
41	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
42	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
43	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	...	...	...	...
44	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6
45	20.0	...	18.5	...	17.6	16.8	16.2	15.7	15.4	15.1	14.8	14.4	14.0	13.6

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	1	...	4	1
2	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	1 $\frac{1}{4}$ CR	K11789	...	...	4	1
3	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11572	2	...	4	1
4	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	2	...	4	1
5	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	4 < t ≤ 10	4	1
6	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	2.25 < t ≤ 4	4	1
7	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	≤ 2.25	4	1
8	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	3	...	4	1
9	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	2	...	4	1
10	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	1 $\frac{1}{4}$ CR	K11789	NT	...	4	1
11	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	2 $\frac{1}{2}$ < t ≤ 4	11B	2
12	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	≤ 2 $\frac{1}{2}$	11B	2
13	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	2 $\frac{1}{2}$ < t ≤ 6	11B	2
14	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	≤ 2 $\frac{1}{2}$	11B	2
15	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	1	...	5A	1
16	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	1	...	5A	1
17	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA-213	T22	K21590	...	...	5A	1
18	2 $\frac{1}{4}$ Cr-1Mo	Fittings	SA-234	WP22	K21590	1	...	5A	1
19	2 $\frac{1}{4}$ Cr-1Mo	Wld. fittings	SA-234	WP22	K21590	1/W	...	5A	1
20	2 $\frac{1}{4}$ Cr-1Mo	Smls. pipe	SA-335	P22	K21590	...	...	5A	1
21	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	1	...	5A	1
22	2 $\frac{1}{4}$ Cr-1Mo	Forged pipe	SA-369	FP22	K21590	...	...	5A	1
23	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	1	...	5A	1
24	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR	K21590	...	...	5A	1
25	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	6 < t ≤ 10	5A	1
26	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	8 < t ≤ 20	5A	1
27	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	4 < t ≤ 6	5A	1
28	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	2.5 < t ≤ 4	5A	1
29	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	1.5 < t ≤ 2.5	5A	1
30	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$\frac{5}{8}$ < t ≤ 1.5	5A	1
31	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	t ≤ $\frac{5}{8}$	5A	1
32	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9	J21890	...	...	5A	1
33	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9	J21890	...	...	5A	1
34	2 $\frac{1}{4}$ Cr-1Mo	Cast pipe	SA-426	CP22	J21890	...	...	5A	1
35	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	3	...	5A	1
36	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	3	...	5A	1
37	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	2	...	5A	1
38	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR	K21590	NT	...	5A	1
39	2 $\frac{1}{4}$ Cr-1Mo	Bar	SA-739	B22	K21390	...	...	5A	1
(25) 40	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	t ≤ 8	5A	1
41	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-487	8	J22091	A	...	5C	1
42	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-508	22	K21590	3	...	5C	1
43	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	3	...	5C	1
44	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-542	B	K21590	4	...	5C	1
45	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	4	≥ $\frac{1}{4}$	5C	4

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	60	35	700	900	CS-2	E4
2	60	35	700	NP	CS-2	G1, G2
3	70	40	700	900	CS-2	E4
4	70	40	NP	900	CS-2	E4
5	71	55	NP	900	CS-3	E4
6	72.5	56.5	NP	900	CS-3	E4
7	74	58	NP	900	CS-3	E4
8	75	45	NP	700	CS-3	...
9	75	45	700	900	CS-3	E3
10	75	45	700	NP	CS-3	G1, G2
11	105	90	700 (SPT)	700	CS-5	S1
12	115	100	NP	700	HT-1	...
13	105	90	700 (Cl. MC & SPT)	700	CS-5	...
14	115	100	700 (Cl. MC & SPT)	700	HT-1	...
15	60	30	700	NP	CS-2	...
16	60	30	NP	700	CS-2	E3, W2
17	60	30	700	900	CS-2	E3, W2
18	60	30	700	900	CS-2	E3, W2
19	60	30	700	NP	CS-2	...
20	60	30	700	900	CS-2	E3, W2
21	60	30	700	900	CS-2	E3, W2
22	60	30	700	900	CS-2	E3, W2
23	60	30	700	900	CS-2	E3, H1, W2
24	60	30	700	NP	CS-2	G1, G2
25	65.5	36.5	NP	900	CS-3	E4, W5
26	65.5	38.5	NP	900	CS-3	E4, W5
27	66.5	37.5	NP	900	CS-3	E4, W5
28	68	40.5	NP	900	CS-3	E4, W5
29	69.5	42	NP	900	CS-3	E4, W5
30	69.5	43.5	NP	900	CS-3	E4, W5
31	69.5	45	NP	900	CS-3	E4, W5
32	70	40	700	900	CS-2	E4, W2
33	70	40	700 (SPT)	NP	CS-2	...
34	70	40	700	NP	CS-2	...
35	75	45	700	900	CS-3	E3, W2
36	75	45	700	900	CS-3	E3, W2
37	75	45	700	900	CS-3	E3, W2
38	75	45	700	NP	CS-3	G1, G2
39	75	45	700	900	CS-3	E3, W2
40	75.5	45	NP	900	CS-3	E3, W5
41	85	55	700	700	CS-3	...
42	85	55	700	850	CS-2	G21
43	85	55	NP	850	CS-2	G21
44	85	55	NP	850	CS-2	G21
45	105	85	700	NP	CS-3	S3, W1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	19.6	18.9	18.3	18.0	17.6	17.2	16.8	16.4	15.0
2	20.0	...	20.0	...	20.0	19.6	18.9	18.3	18.0	17.6	...	...	...	...
3	23.3	...	23.3	...	23.3	22.5	21.7	20.9	20.5	20.1	19.7	19.2	18.7	14.5
4	23.3	...	23.3	...	23.3	22.5	21.7	20.9	20.5	20.1	19.7	19.2	18.7	14.5
5	23.7	23.7	23.7	23.6	23.4	23.4	23.4	23.4	23.4	23.4	23.4	23.1	20.2	13.7
6	24.2	24.2	24.2	24.1	23.9	23.9	23.9	23.9	23.9	23.9	23.9	23.6	20.2	13.7
7	24.7	24.7	24.7	24.5	24.4	24.4	24.4	24.4	24.4	24.4	24.4	24.1	20.2	13.7
8	25.0	25.0	25.0	...	25.0	25.0	24.4	23.5	23.1	22.6	...	...	...	...
9	25.0	...	25.0	...	25.0	25.0	24.4	23.5	23.1	22.6	22.2	21.6	20.2	16.0
10	25.0	...	25.0	...	25.0	25.0	24.4	23.5	23.1	22.6	...	...	...	...
11	35.0	...	35.0	...	35.0	35.0	35.0	35.0	35.0	34.9	...	...	...	...
12	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	38.2	...	...	...	...
13	35.0	...	35.0	...	35.0	35.0	35.0	35.0	35.0	34.9	...	...	...	...
14	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	38.2	...	...	...	...
15	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	...	...	...	...
16	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
17	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
18	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
19	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	...	...	...	...
20	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
21	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
22	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
23	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
24	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	...	...	...	...
25	21.8	21.8	21.8	21.5	21.1	20.5	20.0	19.6	19.4	19.1	18.8	18.5	18.0	15.8
26	21.8	21.8	21.8	21.6	21.3	21.0	20.9	20.8	20.6	20.3	20.0	19.5	19.1	15.8
27	22.2	22.2	22.2	21.9	21.7	21.3	20.8	20.4	20.2	19.9	19.6	19.2	18.7	15.8
28	22.7	22.7	22.7	22.4	22.1	21.9	21.8	21.6	21.5	21.2	20.9	20.5	19.9	15.8
29	23.2	23.2	23.2	22.9	22.6	22.4	22.2	22.1	21.9	21.7	21.4	20.9	20.3	15.8
30	23.2	23.2	23.2	22.9	22.6	22.4	22.2	22.1	21.9	21.7	21.4	20.9	20.3	15.8
31	23.2	23.2	23.2	22.9	22.6	22.4	22.2	22.1	21.9	21.7	21.4	20.9	20.3	15.8
32	23.3	...	23.3	...	23.0	22.6	22.5	22.4	22.2	21.9	21.5	21.0	19.8	16.0
33	23.3	...	23.3	...	23.0	22.6	22.5	22.4	22.2	21.9	...	...	...	...
34	23.3	...	23.3	...	23.0	22.6	22.5	22.4	22.2	21.9	...	...	...	...
35	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	21.9	17.0
36	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	21.9	17.0
37	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	21.9	17.0
38	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	...	...	...	...
39	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	21.9	17.0
40	25.1	25.1	25.1	24.9	24.7	24.3	24.1	24.0	23.9	23.6	23.3	22.7	21.9	15.8 (25)
41	28.3	28.3	28.3	...	27.7	27.4	27.4	27.2	27.0	26.7	...	...	...	...
42	28.3	28.3	28.3	...	27.7	27.4	27.4	27.2	27.0	26.7	26.1	25.4	21.9	...
43	28.3	28.3	28.3	...	27.7	27.4	27.4	27.2	27.0	26.7	26.1	25.4	21.9	...
44	28.3	28.3	28.3	...	27.7	27.4	27.4	27.2	27.0	26.7	26.1	25.4	21.9	...
45	35.0	...	35.0	...	35.0	35.0	34.8	34.3	34.0	33.6	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-182	F22V	K31835	...	...	5C	1
2	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-336	F22V	K31835	...	...	5C	1
3	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-541	22V	K31835	...	...	5C	1
4	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-542	D	K31835	4a	...	5C	1
5	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-832	22V	K31835	...	...	5C	1
6	3Cr-1Mo	Smls. tube	SA-213	T21	K31545	...	...	5A	1
7	3Cr-1Mo	Smls. pipe	SA-335	P21	K31545	...	...	5A	1
8	3Cr-1Mo	Forgings	SA-336	F21	K31545	1	...	5A	1
9	3Cr-1Mo	Forged pipe	SA-369	FP21	K31545	...	...	5A	1
10	3Cr-1Mo	Plate	SA-387	21	K31545	1	...	5A	1
11	3Cr-1Mo	Cast pipe	SA-426	CP21	J31545	...	...	5A	1
12	3Cr-1Mo	Forgings	SA-182	F21	K31545	...	...	5A	1
13	3Cr-1Mo	Forgings	SA-336	F21	K31545	3	...	5A	1
14	3Cr-1Mo	Plate	SA-387	21	K31545	2	...	5A	1
15	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-182	F3V	K31830	...	...	5C	1
16	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-336	F3V	K31830	...	...	5C	1
17	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-508	3V	K31830	...	...	5C	1
18	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-541	3V	K31830	...	...	5C	1
19	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-542	C	K31830	4a	...	5C	1
20	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-832	21V	K31830	...	...	5C	1
21	5Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T5	K41545	...	...	5B	1
22	5Cr- $\frac{1}{2}$ Mo	Fittings	SA-234	WP5	K41545	...	...	5B	1
23	5Cr- $\frac{1}{2}$ Mo	Wld. fittings	SA-234	WP5	K41545	W	...	5B	1
24	5Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P5	K41545	...	...	5B	1
25	5Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP5	K41545	...	...	5B	1
26	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	1	...	5B	1
27	5Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	5CR	K41545	...	...	5B	1
28	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5	K41545	...	...	5B	1
29	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5	K41545	...	...	5B	1
30	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	2	...	5B	1
31	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5A	K42544	...	...	5B	1
32	5Cr- $\frac{1}{2}$ Mo	Castings	SA-217	C5	J42045	NT	...	5B	1
33	5Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP5	J42045	...	...	5B	1
34	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5a	K42544	...	...	5B	1
35	5Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T5b	K51545	...	...	5B	1
36	5Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P5b	K51545	...	...	5B	1
37	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. tube	SA-213	T5c	K41245	...	...	5B	1
38	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. pipe	SA-335	P5c	K41245	...	...	5B	1
39	9Cr-1Mo	Smls. tube	SA-213	T9	K90941	...	...	5B	1
40	9Cr-1Mo	Fittings	SA-234	WP9	K90941	...	...	5B	1
41	9Cr-1Mo	Smls. pipe	SA-335	P9	K90941	...	...	5B	1
42	9Cr-1Mo	Forged pipe	SA-369	FP9	K90941	...	...	5B	1
43	9Cr-1Mo	Forgings	SA-182	F9	K90941	...	...	5B	1
44	9Cr-1Mo	Forgings	SA-336	F9	K90941	...	...	5B	1
45	9Cr-1Mo	Castings	SA-217	C12	J82090	NT	...	5B	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	85	60	NP	900	CS-2	G21
2	85	60	NP	900	CS-2	G21
3	85	60	NP	900	CS-2	G21
4	85	60	NP	900	CS-2	G21
5	85	60	NP	900	CS-2	G21
6	60	30	700	850	CS-2	E3
7	60	30	700	850	CS-2	E3
8	60	30	700	850	CS-2	E3
9	60	30	700	850	CS-2	E3
10	60	30	700	850	CS-2	E3
11	60	30	700	NP	CS-2	...
12	75	45	700	850	CS-3	E3
13	75	45	700	850	CS-3	E3
14	75	45	700	850	CS-3	E3
15	85	60	NP	850	CS-3	G21
16	85	60	NP	850	CS-3	G21
17	85	60	NP	850	CS-3	G21
18	85	60	NP	850	CS-3	G21
19	85	60	NP	850	CS-3	G21
20	85	60	NP	850	CS-3	G21
21	60	30	700	700	CS-2	...
22	60	30	700	700	CS-2	...
23	60	30	700	NP	CS-2	...
24	60	30	700	700	CS-2	...
25	60	30	700	700	CS-2	...
26	60	30	700	700	CS-2	...
27	60	30	700	NP	CS-2	G1, G2
28	60	36	NP	700	CS-2	...
29	70	40	700	700	CS-2	...
30	75	45	700	700	CS-3	...
31	80	50	NP	700	CS-3	...
32	90	60	700	700	CS-3	...
33	90	60	700	NP	CS-3	...
34	90	65	NP	700	CS-5	...
35	60	30	NP	700	CS-2	...
36	60	30	NP	700	CS-2	...
37	60	30	NP	700	CS-2	...
38	60	30	NP	700	CS-2	...
39	60	30	700	700	CS-2	...
40	60	30	NP	700	CS-2	...
41	60	30	700	700	CS-2	...
42	60	30	700	700	CS-2	...
43	85	55	NP	700	CS-3	...
44	85	55	NP	700	CS-3	...
45	90	60	700 (SPT)	700	CS-3	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	28.3	...	28.3	...	28.3	28.3	28.3	27.6	27.1	26.5	25.9	25.2	24.5	23.6
2	28.3	...	28.3	...	28.3	28.3	28.3	27.6	27.1	26.5	25.9	25.2	24.5	23.6
3	28.3	...	28.3	...	28.3	28.3	28.3	27.6	27.1	26.5	25.9	25.2	24.5	23.6
4	28.3	...	28.3	...	28.3	28.3	28.3	27.6	27.1	26.5	25.9	25.2	24.5	23.6
5	28.3	...	28.3	...	28.3	28.3	28.3	27.6	27.1	26.5	25.9	25.2	24.5	23.6
6	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	16.0	...
7	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	16.0	...
8	20.0	19.1	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	16.0	...
9	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	16.0	...
10	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	17.9	17.7	16.0	...
11	20.0	...	18.7	...	18.2	18.0	17.9	17.9	17.9	17.9	...	...	...	...
12	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	19.0	...
13	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	19.0	...
14	25.0	...	25.0	...	24.3	24.1	24.0	23.8	23.6	23.4	23.0	22.5	19.0	...
15	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
16	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
17	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
18	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
19	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
20	28.3	...	28.3	...	27.2	26.4	25.8	25.4	25.2	25.0	24.7	24.3	23.8	...
21	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
22	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
23	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
24	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
25	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
26	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
27	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
28	20.0	...	20.0	...	19.4	19.2	19.2	18.9	18.6	18.2	...	...	...	...
29	23.3	...	23.3	...	22.6	22.4	22.4	22.0	21.7	21.2	...	...	...	...
30	25.0	...	24.9	...	24.2	24.0	24.0	23.6	23.2	22.7	...	...	...	...
31	26.7	...	26.6	...	25.8	25.6	25.6	25.2	24.8	24.3	...	...	...	...
32	30.0	...	29.9	...	29.1	28.8	28.7	28.3	27.9	27.3	...	...	...	...
33	30.0	...	29.9	...	29.1	28.8	28.7	28.3	27.9	27.3	...	...	...	...
34	30.0	...	29.9	...	29.1	28.8	28.7	28.3	27.9	27.3	...	...	...	...
35	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
36	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
37	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
38	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
39	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
40	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
41	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
42	20.0	...	18.1	...	17.4	17.2	17.1	16.8	16.6	16.3	...	...	...	...
43	28.3	...	28.3	...	27.4	27.2	27.1	26.8	26.3	25.8	...	...	...	...
44	28.3	...	28.3	...	27.4	27.2	27.1	26.8	26.3	25.8	...	...	...	...
45	30.0	...	29.9	...	29.1	28.8	28.7	28.3	27.9	27.3	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	9Cr-1Mo	Cast pipe	SA-426	CP9	J82090	...	...	5B	1
2	9Cr-1Mo-V	Smls. tube	SA-213	T91 Type 1	K90901	...	...	15E	1
3	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Type 1	K90901	...	...	15E	1
4	9Cr-1Mo-V	Plate	SA-387	91 Type 1	K90901	2	...	15E	1
5	9Cr-1Mo-V	Forgings	SA-182	F91 Type 1	K90901	...	...	15E	1
6	9Cr-1Mo-V	Forgings	SA-336	F91	K90901	...	...	15E	1
7	12Cr	Bar	SA-479	403	S40300	A	...	6	1
8	12Cr	Bar	SA-479	403	S40300	1	...	6	1
9	12Cr-Al	Plate	SA-240	405	S40500	...	...	7	1
10	12Cr-Al	Bar	SA-479	405	S40500	...	...	7	1
11	12Cr-Al	Bar	SA/JIS G4303	SUS405	...	...	...	7	1
12	12Cr-Al	Smls. tube	SA-268	TP405	S40500	...	...	7	1
13	12 $\frac{1}{2}$ Cr-2Ni	Bar	SA-479	414	S41400	...	...	6	4
14	13Cr	Plate	SA-240	410S	S41008	...	...	7	1
15	13Cr	Smls. tube	SA-268	TP410	S41000	...	...	6	1
16	13Cr	Plate	SA-240	410	S41000	...	...	6	1
17	13Cr	Forgings	SA-182	F6a	S41000	1	...	6	1
18	13Cr	Bar	SA-479	410	S41000	A	...	6	1
19	13Cr	Bar	SA-479	410	S41000	1	...	6	1
20	13Cr	Forgings	SA-182	F6a	S41000	1	...	6	3
21	13Cr	Forgings	SA-182	F6a	S41000	2	...	6	3
22	13Cr	Forgings	SA-336	F6	S41000	...	...	6	3
23	13Cr	Castings	SA-217	CA15	J91150	...	...	6	3
24	13Cr	Cast pipe	SA-426	CPCA15	J91150	...	...	6	3
25	13Cr	Bar	SA/EN 10088-3	X12Cr13	...	QT650	$t \leq 6.25$	...	...
26	13Cr-4Ni	Castings	SA-487	CA6NM	J91540	A	...	6	4
27	13Cr-4Ni	Forgings	SA-182	F6NM	S41500	...	...	6	4
28	13Cr-4Ni	Bar	SA-479	...	S41500	...	...	6	4
29	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	...	...	...	...
30	15Cr	Smls. tube	SA-268	TP429	S42900	...	...	6	2
31	15Cr	Plate	SA-240	429	S42900	...	...	6	2
32	17Cr	Smls. tube	SA-268	TP430	S43000	...	...	7	2
33	17Cr	Plate	SA-240	430	S43000	...	...	7	2
34	17Cr-4Ni-4Cu	Forgings, bar	SA-564	630	S17400	H1150	...	...	...
(25) 35	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1150	...	...	...
(25) 36	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1150	...	...	...
37	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1100	...	...	...
38	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1100	...	...	...
39	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1100	...	...	...
40	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1075	...	...	...
41	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1075	...	...	...
42	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1075	...	...	...
43	26Cr-3Ni-3Mo	Plate	SA-240	26-3-3	S44660	...	$\leq \frac{2}{10}$	10K	1
44	26Cr-3Ni-3Mo	Smls. tube	SA-268	26-3-3	S44660	...	$\leq \frac{2}{10}$	10K	1
45	26Cr-3Ni-3Mo	Wld. tube	SA-268	26-3-3	S44660	...	$\leq \frac{2}{10}$	10K	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	90	60	700	NP	CS-3	...
2	85	60	700	900	CS-3	...
3	85	60	700	900	CS-3	...
4	85	60	700	900	CS-3	...
5	90	60	700	900	CS-3	...
6	85	60	NP	900	CS-3	...
7	70	40	700	NP	...	...
8	70	40	700	NP	...	...
9	60	25	700	800	CS-1	G13
10	60	25	700	NP	CS-1	G13
11	60	25	700	NP	CS-1	G13
12	60	30	NP	800	CS-2	G13
13	115	90	700	NP	CS-3	...
14	60	30	700	800	CS-2	...
15	60	30	NP	800	CS-2	...
16	65	30	NP	800	CS-2	...
17	70	40	700	NP	CS-2	...
18	70	40	700	NP	CS-2	...
19	70	40	700	NP	CS-2	...
20	70	40	NP	800	CS-3	E3
21	85	55	700	800	CS-3	...
22	85	55	NP	800	CS-3	...
23	90	65	700	100	CS-5	...
24	90	65	700	NP	CS-5	...
25	94.5	65.5	700 (SPT)	NP	...	H2, W1
26	110	80	700	NP	CS-5	...
27	115	90	700	NP	CS-3	...
28	115	90	700	NP	CS-3	...
29	150	135	600	NP	HA-7	W1
30	60	35	NP	800	CS-2	G13
31	65	30	NP	800	CS-2	G13
32	60	25	NP	800	CS-2	G13
33	65	30	NP	800	CS-2	G13
34	135	105	650	NP	HT-1	G8, W1
35	135	105	650	600	HT-1	G8, W8
36	135	105	650	600	HT-1	G8, W8
37	140	115	NP	600	HT-1	G8, W1
38	140	115	NP	600	HT-1	G8, W1
39	140	115	NP	600	HT-1	G8, W1
40	145	125	650	NP	HT-1	G8, W1
41	145	125	650	NP	HT-1	G8, W1
42	145	125	650	NP	HT-1	G8, W1
43	85	65	NP	700	HA-5	G13, H6
44	85	65	NP	700	HA-5	G13, H6
45	85	65	NP	700	HA-5	G13, G18, H6

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	30.0	...	29.9	...	29.1	28.8	28.7	28.3	27.9	27.3	...	...	...	...
2	28.3	...	28.3	...	28.3	28.2	28.1	27.7	27.3	26.7	25.9	24.9	23.7	22.3
3	28.3	...	28.3	...	28.3	28.2	28.1	27.7	27.3	26.7	25.9	24.9	23.7	22.3
4	28.3	...	28.3	...	28.3	28.2	28.1	27.7	27.3	26.7	25.9	24.9	23.7	22.3
5	30.0	...	30.0	...	30.0	29.9	29.8	29.3	28.9	28.2	27.4	26.4	25.1	23.6
6	28.3	28.3	28.3	28.3	28.3	28.2	28.1	27.7	27.3	26.7	25.9	24.9	23.7	22.3
7	23.3	...	23.3	...	22.9	22.5	22.1	21.6	21.2	20.6	...	...	...	...
8	23.3	...	23.3	...	22.9	22.5	22.1	21.6	21.2	20.6	...	...	...	...
9	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	13.1	12.6	...	...
10	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	...	...	...	...
11	16.7	...	15.3	...	14.8	14.5	14.3	14.0	13.8	13.5	...	...	...	...
12	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
13	38.3	38.3	38.3	...	37.7	36.8	36.0	35.1	34.5	33.7	...	...	...	...
14	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
15	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
16	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
17	23.3	...	23.3	...	22.9	22.5	22.1	21.6	21.2	20.6	...	...	...	...
18	23.3	...	23.3	...	22.9	22.5	22.1	21.6	21.2	20.6	...	...	...	...
19	23.3	...	23.3	...	22.9	22.5	22.1	21.6	21.2	20.6	...	...	...	...
20	23.3	23.3	23.3	23.1	22.9	22.5	22.1	21.6	21.2	20.6	20.0	19.2	17.2	12.3
21	28.3	...	28.3	...	27.8	27.3	26.9	26.2	25.7	25.1	24.3	23.3	...	...
22	28.3	...	28.3	...	27.8	27.3	26.9	26.2	25.7	25.1	24.3	23.3	...	...
23	30.0	...	30.0	...	29.4	28.9	28.4	27.7	27.2	26.5	...	...	...	...
24	30.0	...	30.0	...	29.4	28.9	28.4	27.7	27.2	26.5	...	...	...	...
25	31.4	31.4	31.4	31.2	30.8	30.2	29.8	29.1	28.5	27.8	...	...	...	...
26	36.7	...	36.7	...	36.0	35.1	34.4	33.6	33.1	32.6	...	...	...	...
27	38.3	...	38.3	...	38.3	37.9	36.5	35.0	34.3	33.4	...	...	...	...
28	38.3	...	38.3	...	38.3	37.9	36.5	35.0	34.3	33.4	...	...	...	...
29	50.0	50.0	50.0	...	50.0	49.3	47.7	45.7	...	...	...	...	...	...
30	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	17.1	16.4	...	...
31	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
32	20.0	...	20.0	...	19.6	19.3	19.0	18.5	18.1	17.7	17.1	16.4	...	...
33	20.0	...	18.4	...	17.8	17.4	17.2	16.8	16.6	16.2	15.7	15.1	...	...
34	45.0	...	45.0	...	45.0	43.7	42.9	42.2	41.8	...	...	...	...	...
35	45.0	...	45.0	...	45.0	43.7	42.9	42.2	41.8	...	...	...	...	...
36	45.0	...	45.0	...	45.0	43.7	42.9	42.2	41.8	...	...	...	...	...
37	46.7	...	46.7	...	46.7	45.4	44.5	43.8	43.4	...	...	...	...	...
38	46.7	...	46.7	...	46.7	45.4	44.5	43.8	43.4	...	...	...	...	...
39	46.7	...	46.7	...	46.7	45.4	44.5	43.8	43.4	...	...	...	...	...
40	48.3	...	48.3	...	48.3	47.0	46.1	45.4	44.9	...	...	...	...	...
41	48.3	...	48.3	...	48.3	47.0	46.1	45.4	44.9	...	...	...	...	...
42	48.3	...	48.3	...	48.3	47.0	46.1	45.4	44.9	...	...	...	...	...
43	28.3	...	28.3	...	28.3	27.9	27.7	27.6	27.5	27.3	...	...	...	...
44	28.3	...	28.3	...	28.3	27.9	27.7	27.6	27.5	27.3	...	...	...	...
45	24.1	...	24.1	...	24.0	23.7	23.6	23.4	23.3	23.2	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	26Cr-3Ni-3Mo	Wld. tube	SA-803	26-3-3	S44660	...	$\leq \frac{2}{10}$	10K	1
2	27Cr-1Mo	Plate	SA-240	XM-27	S44627	...	...	10I	1
3	27Cr-1Mo	Smls. & wld. tube	SA-268	TPXM-27	S44627	...	...	10I	1
4	27Cr-1Mo	Bar	SA-479	XM-27	S44627	...	...	10I	1
5	29Cr-4Mo-Ti	Smls. tube	SA-268	...	S44735	...	...	10J	1
6	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	NT	...	...	...
7	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	QT	...	...	...
8	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2	J13005	A	...	3	3
9	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	A	K12021	...	...	3	2
10	Mn- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	H75	K12021	...	...	3	2
11	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	B	K12022	...	...	3	3
12	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	1	...	3	3
13	Mn- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	H80	K12022	...	...	3	3
14	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	2	...	3	3
15	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	3	...	11A	4
16	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	1	...	3	3
17	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	2	...	3	3
18	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	3	...	11A	4
19	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-302	C	K12039	...	...	3	3
20	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	1	...	3	3
21	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J80	K12539	...	...	3	3
22	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	2	...	3	3
23	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J90	K12539	...	...	3	3
24	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	3	...	11A	4
25	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J100	K12539	...	...	11A	4
26	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-302	D	K12054	...	...	3	3
27	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	1	...	3	3
28	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	1	...	3	3
29	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	2	...	3	3
30	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	3	...	11A	4
31	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	2	...	3	3
(25) 32	...	...	...	...	...	...	...	...	...
33	Mn- $\frac{1}{2}$ Ni-V	Plate	SA/NF A 36-215	P440NJ4	...	...	$\frac{5}{16} \leq t \leq 0.79$	10A	1
34	Mn- $\frac{1}{2}$ Ni-V	Plate	SA-225	C	K12524	...	...	10A	1
35	Mn-V	Castings	SA-487	1	J13002	A/NT	...	10A	1
36	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	A/NT	...	3	3
37	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	1	...	3	3
38	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	2	...	3	3
39	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$2\frac{1}{2} < t \leq 4$	11B	3
40	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Plate	SA-517	F	K11576	...	$\leq 2\frac{1}{2}$	11B	3
41	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$\leq 2\frac{1}{2}$	11B	3
42	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Smls. tube	SA-423	2	K11540	...	...	4	2
43	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	1	...	3	3
44	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	1	...	3	3
45	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	2	...	3	3

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	85	65	NP	600	HA-5	G13, G18, H6
2	65	40	650	NP	HA-2	G13
3	65	40	650	NP	HA-2	G13
4	65	40	650	NP	HA-2	G13
5	75	60	NP	600	HA-6	G13
6	105	65	NP	650	CS-5	G19, W5, W6
7	105	65	NP	650	CS-5	G19, W5, W6
8	85	53	700 (SPT)	NP	CS-3	...
9	75	45	700	700	CS-3	...
10	75	45	700	NP	CS-3	G1, G2
11	80	50	700	700	CS-3	...
12	80	50	700	700	CS-5	...
13	80	50	700	NP	CS-3	G1, G2
14	90	70	700	700	CS-5	...
15	100	83	700	NP	CS-5	...
16	80	50	700	NP	CS-5	...
17	90	70	700	700	CS-5	...
18	100	83	700	700	CS-5	...
19	80	50	700	700	CS-3	...
20	80	50	700	700	CS-5	...
21	80	50	700	NP	CS-5	G1, G2
22	90	70	700	700	CS-5	...
23	90	70	700	NP	CS-5	G1, G2
24	100	83	700	700	CS-5	...
25	100	83	700	NP	CS-5	G1, G2
26	80	50	700	700	CS-3	...
27	80	50	700	700	CS-5	...
28	80	50	NP	700	CS-5	...
29	90	70	700	700	CS-5	...
30	100	83	700	NP	CS-5	...
31	90	70	NP	700	CS-5	...
32	...	...	...	...	...	...
33	91.5	64	NP	150	CS-5	...
34	105	70	NP	700	CS-5	...
35	85	55	700 (SPT)	700	CS-3	...
36	90	60	700	700	CS-3	...
37	80	50	700	700	CS-5	...
38	90	65	700	700	CS-5	...
39	105	90	700 (SPT)	700	CS-5	S1
40	115	100	700 (SPT)	700	HT-1	...
41	115	100	NP	700	HT-1	...
42	60	37	NP	700	CS-2	...
43	80	50	700	700	CS-5	...
44	80	50	700	700	CS-5	...
45	90	65	700	700	CS-5	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	24.1	...	24.1	...	24.0	23.7	23.6	23.4	...	...	...	...	...	...
2	21.7	...	21.7	...	20.9	19.5	18.9	18.7	18.6	...	...	...	...	...
3	21.7	...	21.7	...	20.9	19.5	18.9	18.7	18.6	...	...	...	...	...
4	21.7	...	21.7	...	20.9	19.5	18.9	18.7	18.6	...	...	...	...	...
5	25.0	...	24.6	...	24.2	24.0	23.6	23.3	23.2	23.0	22.7	...	...	...
6	35.0	...	33.3	...	32.8	32.8	32.8	32.8	32.8	...	...	...	...	...
7	35.0	...	33.3	...	32.8	32.8	32.8	32.8	32.8	...	...	...	...	...
8	28.3	...	28.3	...	28.3	28.2	28.2	27.3	27.0	26.5	...	...	...	...
9	25.0	...	25.0	...	25.0	25.0	25.0	25.0	24.9	24.4	...	...	...	...
10	25.0	...	25.0	...	25.0	25.0	25.0	25.0	24.9	24.4	...	...	...	...
11	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
12	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
13	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
14	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
15	33.3	...	33.3	...	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...
16	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
17	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
18	33.3	...	33.3	...	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...
19	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
20	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
21	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
22	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
23	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
24	33.3	...	33.3	...	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...
25	33.3	...	33.3	...	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...
26	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
27	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
28	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
29	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
30	33.3	...	33.3	...	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...
31	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	30.5	30.5	...	...	...	...	...	...	...	...	...	...	...	...
34	35.0	35.0	35.0	...	35.0	35.0	35.0	34.9	34.0	33.3	...	...	...	...
35	28.4	...	26.8	...	26.1	26.1	26.1	25.6	25.1	24.4	...	...	...	...
36	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
37	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
38	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
39	35.0	...	35.0	...	35.0	35.0	35.0	35.0	34.9	34.3	...	...	...	...
40	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...
41	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...
42	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...
43	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
44	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
45	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...

(25)

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	2	...	3	3
2	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	1	...	3	3
3	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	2	...	3	3
4	$\frac{3}{4}$ Ni-1Mo- $\frac{3}{4}$ Cr	Castings	SA-217	WC5	J22000	...	...	4	1
5	1Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC4	J12082	...	...	4	1
6	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$2\frac{1}{2} < t \leq 4$	11B	8
7	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$\leq 2\frac{1}{2}$	11B	8
8	2Ni-1Cu	Forgings	SA-182	FR	K22035	...	...	9A	1
9	2Ni-1Cu	Smls. pipe	SA-333	9	K22035	...	...	9A	1
10	2Ni-1Cu	Smls. pipe	SA-334	9	K22035	...	...	9A	1
11	2Ni-1Cu	Forgings	SA-350	LF9	K22036	...	...	9A	1
12	2Ni-1Cu	Fittings	SA-420	WPL9	K22035	...	...	9A	1
(25) 13	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N	K23550	100	...	...	...
14	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	1	...	...	...
(25) 15	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N	K23550	120	...	...	...
16	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	2	...	...	...
17	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	3	...	...	...
18	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	4	...	...	...
19	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	5	...	...	...
20	$2\frac{1}{2}$ Ni	Plate	SA-203	A	K21703	...	...	9A	1
21	$2\frac{1}{2}$ Ni	Plate	SA-203	B	K22103	...	...	9A	1
22	$2\frac{1}{2}$ Ni	Castings	SA-352	LC2	J22500	...	...	9A	1
23	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	...	3	...	3	3
24	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	...	1	...	11A	5
25	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	...	2	...	11B	10
(25) 26	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-372	P	K34035	100	...	...	...
27	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2	K34035	1	...	...	...
(25) 28	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-372	P	K34035	120	...	...	...
29	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2	K34035	2	...	...	...
30	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2	K34035	3	...	...	...
31	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2	K34035	4	...	...	...
32	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2	K34035	5	...	...	...
33	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B	K42339	3	...	3	3
34	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B	K42339	1	...	11A	5
35	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B	K42339	2	...	11B	10
36	$3\frac{1}{2}$ Ni	Smls. pipe	SA-333	3	K31918	...	...	9B	1
37	$3\frac{1}{2}$ Ni	Smls. tube	SA-334	3	K31918	...	...	9B	1
38	$3\frac{1}{2}$ Ni	Fittings	SA-420	WPL3	...	...	...	9B	1
39	$3\frac{1}{2}$ Ni	Plate	SA-203	D	K31718	...	...	9B	1
40	$3\frac{1}{2}$ Ni	Forgings	SA-350	LF3	K32025	...	...	9B	1
41	$3\frac{1}{2}$ Ni	Forgings	SA-765	III	K32026	...	...	9B	1
42	$3\frac{1}{2}$ Ni	Plate	SA-203	E	K32018	...	...	9B	1
43	$3\frac{1}{2}$ Ni	Plate	SA-203	E	K32018	...	...	9B	1
44	$3\frac{1}{2}$ Ni	Castings	SA-352	LC3	J31550	...	...	9B	1
45	$3\frac{1}{2}$ Ni	Plate	SA-203	F	...	...	>2	9B	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	90	65	700	700	CS-5	...
2	80	50	700	700	CS-5	...
3	90	65	700	700	CS-5	...
4	70	40	700	700	CS-2	...
5	70	40	700 (SPT)	700	CS-2	...
6	105	90	700 (SPT)	700	CS-5	...
7	115	100	700 (SPT)	700	HT-1	...
8	63	46	NP	100	CS-3	...
9	63	46	NP	100	CS-3	...
10	63	46	NP	100	CS-3	...
11	63	46	NP	100	CS-3	...
12	63	46	NP	100	CS-3	...
13	115	100	NP	650	HT-1	W1
14	115	100	700 (SPT)	700	HT-1	G14, G20, W1
15	135	120	NP	650	HT-1	W1
16	135	120	700 (SPT)	700	HT-1	G6, G20, W1
17	155	140	700 (SPT)	NP	HT-1	W1
18	175	160	700 (SPT)	NP	HT-1	W1
19	190	180	700 (SPT)	NP	HT-1	W1
20	65	37	NP	300	CS-2	...
21	70	40	NP	300	CS-2	...
22	70	40	100	100	CS-2	...
23	90	70	NP	650	CS-5	...
24	105	85	NP	650	CS-5	...
25	115	100	NP	650	HT-1	...
26	115	100	NP	650	HT-1	W1
27	115	100	700 (SPT)	700	HT-1	G14, G20, W1
28	135	120	NP	650	HT-1	W1
29	135	120	700 (SPT)	700	HT-1	G6, G20, W1
30	155	140	700 (SPT)	NP	HT-1	W1
31	175	160	700 (SPT)	NP	HT-1	W1
32	190	180	700 (SPT)	NP	HT-1	W1
33	90	70	NP	650	CS-5	...
34	105	85	650	650	CS-5	G5, H3, S4, W3
35	115	100	NP	650	HT-1	...
36	65	35	NP	100	CS-2	...
37	65	35	NP	100	CS-2	...
38	65	35	NP	300	CS-2	...
39	65	37	NP	300	CS-2	...
40	70	37.5	700	300	CS-2	...
41	70	37.5	NP	100	CS-2	...
42	70	40	300 (SPT)	300	CS-2	...
43	70	40	500	NP	CS-2	...
44	70	40	100	100	CS-2	...
45	75	50	NP	100	CS-3	...

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
2	26.7	26.7	26.7	...	26.7	26.7	26.7	26.7	26.7	26.7	...	...	...	...
3	30.0	...	30.0	...	30.0	30.0	30.0	30.0	30.0	30.0	...	...	...	...
4	23.3	...	23.3	...	23.3	23.3	23.0	22.4	22.1	21.7	...	...	...	...
5	23.3	...	23.3	...	23.3	23.3	23.0	22.4	22.1	21.7	...	...	...	...
6	35.0	...	35.0	...	35.0	35.0	35.0	35.0	34.9	34.3	...	...	...	...
7	38.3	...	38.3	...	38.3	38.3	38.3	38.3	38.3	37.5	...	...	...	...
8	21.0	...	...	...	...	...	...	...	...	...	...	...	...	...
9	21.0	...	...	...	...	...	...	...	...	...	...	...	...	...
10	21.0	...	...	...	...	...	...	...	...	...	...	...	...	...
11	21.0	...	...	...	...	...	...	...	...	...	...	...	...	...
12	21.0	...	...	...	...	...	...	...	...	...	...	...	...	...
13	38.3	...	38.3	...	38.3	38.3	38.3	38.3	37.7	...	...	...	...	(25)
14	38.3	...	38.3	...	38.3	38.3	38.3	38.3	37.7	36.8	...	...	...	...
15	45.0	...	45.0	...	45.0	45.0	45.0	45.0	44.3	...	...	...	...	(25)
16	45.0	...	45.0	...	45.0	45.0	45.0	45.0	44.3	43.2	...	...	...	...
17	51.7	...	51.7	...	51.7	51.7	51.7	51.7	50.9	49.7	...	...	...	...
18	58.3	...	58.3	...	58.3	58.3	58.3	58.3	57.4	56.1	...	...	...	...
19	63.3	...	63.3	...	63.3	63.3	63.3	63.3	62.4	60.9	...	...	...	...
20	21.7	...	21.7	...	21.7	...	...	...	...	...	...	...	...	...
21	23.3	...	23.3	...	23.3	...	...	...	...	...	...	...	...	...
22	23.3	...	...	...	...	...	...	...	...	...	...	...	...	...
23	30.0	...	30.0	...	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
24	35.0	...	35.0	...	35.0	34.6	34.4	34.0	33.5	...	...	...	...	...
25	38.3	...	38.3	...	38.3	37.9	37.7	37.2	36.7	...	...	...	...	...
26	38.3	...	38.3	...	38.3	38.3	38.3	38.3	37.7	...	...	...	...	(25)
27	38.3	...	38.3	...	38.3	38.3	38.3	38.3	37.7	36.8	...	...	...	...
28	45.0	...	45.0	...	45.0	45.0	45.0	45.0	44.3	...	...	...	...	(25)
29	45.0	...	45.0	...	45.0	45.0	45.0	45.0	44.3	43.2	...	...	...	...
30	51.7	...	51.7	...	51.7	51.7	51.7	51.7	50.9	49.7	...	...	...	...
31	58.3	...	58.3	...	58.3	58.3	58.3	58.3	57.4	56.1	...	...	...	...
32	63.3	...	63.3	...	63.3	63.3	63.3	63.3	62.4	60.9	...	...	...	...
33	30.0	...	30.0	...	30.0	29.7	29.5	29.1	28.7	...	...	...	...	...
34	35.0	...	35.0	...	35.0	34.6	34.4	34.0	33.5	...	...	...	...	...
35	38.3	...	38.3	...	38.3	37.9	37.7	37.2	36.7	...	...	...	...	...
36	21.7	...	...	...	...	...	...	...	...	...	...	...	...	...
37	21.7	...	...	...	...	...	...	...	...	...	...	...	...	...
38	21.7	...	21.4	...	20.6	...	...	...	...	...	...	...	...	...
39	21.7	...	21.7	...	21.7	...	...	...	...	...	...	...	...	...
40	23.3	...	22.9	...	22.1	21.4	20.3	18.8	17.9	16.9	...	...	...	...
41	23.3	...	...	...	...	...	...	...	...	...	...	...	...	...
42	23.3	...	23.3	...	23.3	...	...	...	...	...	...	...	...	...
43	23.3	...	23.3	...	23.3	22.9	21.6	...	...	...	...	...	...	...
44	23.3	...	...	...	...	...	...	...	...	...	...	...	...	...
45	25.0	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	3 $\frac{1}{2}$ Ni	Plate	SA-203	F	...	...	≤ 2	9B	1
2	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N	K22375	3	...	3	3
3	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N	K22375	1	...	11A	5
4	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N	K22375	2	...	11B	10
5	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3	K44045	1	...	...	...
6	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3	K44045	2	...	...	...
7	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3	K44045	3	...	...	...
8	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3	K44045	4	...	...	...
9	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3	K44045	5	...	...	...
10	5Ni- $\frac{1}{4}$ Mo	Plate	SA-645	...	K41583	...	...	11A	2
11	7Ni	Plate	SA-553	III	K61365	...	≤ 2	11A	1
12	7Ni	Plate	SA-553	III	K61365	...	≤ 2	11A	1
13	8Ni	Plate	SA-553	II	K71340	...	...	11A	1
14	8Ni	Plate	SA-553	II	K71340	...	...	11A	1
15	9Ni	Smls. pipe	SA-333	8	K81340	...	...	11A	1
16	9Ni	Smls. pipe	SA-333	8	K81340	...	...	11A	1
17	9Ni	Smls. tube	SA-334	8	K81340	...	...	11A	1
18	9Ni	Smls. tube	SA-334	8	K81340	...	...	11A	1
19	9Ni	Plate	SA-353	...	K81340	...	...	11A	1
20	9Ni	Plate	SA-353	...	K81340	...	...	11A	1
21	9Ni	Fittings	SA-420	WPL8	K81340	...	...	11A	1
22	9Ni	Fittings	SA-420	WPL8	K81340	...	...	11A	1
23	9Ni	Forgings	SA-522	I	K81340	...	...	11A	1
24	9Ni	Forgings	SA-522	I	K81340	...	...	11A	1
25	9Ni	Plate	SA-553	I	K81340	...	...	11A	1
26	9Ni	Plate	SA-553	I	K81340	...	...	11A	1
27	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660	S66286	...	...	...	...
(25) 28	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10	N08810	...	...	45	...
(25) 29	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H	N08810	...	...	45	...
(25) 30	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...	...	45	...
(25) 31	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H	N08810	...	...	45	...
(25) 32	42Fe-33Ni-21Cr	Bar	SA-276	800H	N08810	...	...	45	...
(25) 33	42Fe-33Ni-21Cr	Smls. pipe	SA-312	800H	N08810	...	...	45	...
(25) 34	42Fe-33Ni-21Cr	Wld. pipe	SA-312	800H	N08810	...	...	45	...
(25) 35	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H	N08810	...	...	45	...
(25) 36	42Fe-33Ni-21Cr	Bar	SA-479	800H	N08810	...	...	45	...
(25) 37	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H	N08810	...	...	45	...
(25) 38	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10	N08810	...	...	45	...
39	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...	8	3
40	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...	8	3
41	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	> 5	8	1
42	16Cr-12Ni-2Mo	Forgings	SA-965	F316L	S31603	...	...	8	1
43	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	≤ 5	8	1
44	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...	...	8	1
45	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	80	55	NP	100	CS-3	...
2	90	70	650	700	CS-5	...
3	105	85	650	700	CS-5	H3, S4, W3
4	115	100	NP	650	HT-1	...
5	115	100	700 (SPT)	700	HT-1	G14, G20, W1
6	135	120	700 (SPT)	700	HT-1	G6, G20, W1
7	155	140	700 (SPT)	NP	HT-1	W1
8	175	160	700 (SPT)	NP	HT-1	W1
9	190	180	700 (SPT)	NP	HT-1	W1
10	95	65	NP	250	CS-3	W4
11	100	85	NP	150	CS-3	W7
12	100	85	NP	150	CS-3	W4
13	100	85	NP	250	CS-3	W7
14	100	85	NP	250	CS-3	W4
15	100	75	NP	250	CS-3	W7
16	100	75	NP	250	CS-3	W4
17	100	75	NP	250	CS-3	W7
18	100	75	NP	250	CS-3	W4
19	100	75	NP	250	CS-3	W7
20	100	75	NP	250	CS-3	W4
21	100	75	NP	250	CS-3	W7
22	100	75	NP	250	CS-3	W4
23	100	75	NP	250	CS-3	G19, S6, W7
24	100	75	NP	250	CS-3	G19, S6, W4
25	100	85	NP	250	CS-3	W7
26	100	85	NP	250	CS-3	W4
27	130	85	700	NP	HA-5	W1
28	65	25	800	800	NFN-9	G7, G22, G23
29	65	25	800	800	NFN-9	G7, G23
30	65	25	800	800	NFN-9	G7, G23
31	65	25	NP	800	NFN-9	G7, G18
32	65	25	800	800	NFN-9	G7, G22, G23
33	65	25	800	800	NFN-9	G7, G23
34	65	25	800	800	NFN-9	G7, G18, G23
35	65	25	800	800	NFN-9	G7, G18, G23
36	65	25	800	800	NFN-9	G7, G22, G23
37	65	25	NP	800	NFN-9	G7, G18
38	65	25	800	800	NFN-9	G7, G22, G23
39	95	45	NP	100	HA-6	...
40	95	45	NP	800	HA-6	G7
41	65	25	800	800	HA-4	G7
42	65	25	800	800	HA-4	G7
43	70	25	800	800	HA-4	G7
44	70	25	800	800	HA-4	G7
45	70	25	800	800	HA-4	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	26.7	...	...	...	...	...	...	...	...	...	...	...	...	...
2	30.0	30.0	30.0	30.0	30.0	29.7	29.5	29.1	28.7	28.2	...	...	...	...
3	35.0	35.0	35.0	35.0	35.0	34.6	34.4	34.0	33.5	32.9	...	...	...	...
4	38.3	38.3	38.3	38.3	38.3	37.9	37.7	37.2	36.7	...	...	...	...	...
5	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	37.7	36.8	...	...	...	...
6	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.3	43.2	...	...	...	...
7	51.7	51.7	51.7	51.7	51.7	51.7	51.7	51.7	50.9	49.7	...	...	...	...
8	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	57.4	56.1	...	...	...	...
9	63.3	63.3	63.3	63.3	63.3	63.3	63.3	63.3	62.4	60.9	...	...	...	...
10	30.1	30.1	28.1	27.7	...	...	...	...	...	...	...	...	...	...
11	33.3	33.3	...	...	...	...	...	...	...	...	...	...	...	...
12	31.7	31.7	...	...	...	...	...	...	...	...	...	...	...	...
13	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
14	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
15	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
16	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
17	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
18	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
19	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
20	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
21	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
22	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
23	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
24	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
25	33.3	33.3	31.1	30.2	...	...	...	...	...	...	...	...	...	...
26	31.7	31.7	29.6	28.7	...	...	...	...	...	...	...	...	...	...
27	43.3	...	43.3	...	43.3	43.3	42.5	41.7	41.3	40.9	...	...	...	...
28	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
29	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
30	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
31	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	...	(25)
32	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
33	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
34	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	...	(25)
35	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	...	(25)
36	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
37	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	...	(25)
38	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	...	(25)
39	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
40	30.0	...	27.6	...	24.7	23.4	23.0	22.9	22.8	22.6	22.3	22.0	21.5	21.0
41	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
42	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
43	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
44	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
45	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...	8	1
2	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...	8	1
3	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...	8	1
4	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	...	...	8	1
5	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...	8	1
6	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	1	...	8	1
7	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	3	...	8	1
8	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	4	...	8	1
9	16Cr-12Ni-2Mo	Fittings	SA-403	316L	S31603	...	...	8	1
10	16Cr-12Ni-2Mo	Fittings	SA-403	316L	S31603	CR	...	8	1
11	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316L	S31603	WP-W	...	8	1
12	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316L	S31603	WP-W	...	8	1
13	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316L	S31603	WP-WX	...	8	1
14	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	...	...	8	1
15	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L	S31603	...	...	8	1
16	16Cr-12Ni-2Mo	Wld. pipe	SA-688	TP316L	S31603	...	...	8	1
17	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316L	S31603	...	...	8	1
18	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316L	S31603	...	...	8	1
19	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316L	...	...	...	8	1
20	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	>5	8	1
21	16Cr-12Ni-2Mo	Forgings	SA-965	F316	S31600	...	...	8	1
22	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	>5	8	1
23	16Cr-12Ni-2Mo	Forgings	SA-965	F316H	S31609	...	...	8	1
24	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	≤5	8	1
25	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...	...	8	1
26	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...	...	8	1
27	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...	8	1
28	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...	8	1
29	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...	8	1
30	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316	S31600	...	...	8	1
31	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...	8	1
32	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	1	...	8	1
33	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	3	...	8	1
34	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	4	...	8	1
35	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316	S31600	...	...	8	1
36	16Cr-12Ni-2Mo	Fittings	SA-403	316	S31600	...	...	8	1
37	16Cr-12Ni-2Mo	Fittings	SA-403	316	S31600	WP-S	...	8	1
38	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316	S31600	WP-W	...	8	1
39	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	...	...	8	1
40	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...	8	1
41	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...	8	1
42	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316	S31600	...	...	8	1
43	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316	S31600	...	...	8	1
44	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316	...	...	...	8	1
45	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	≤5	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	70	25	800	NP	HA-4	G7
2	70	25	NP	800	HA-4	G7, G18
3	70	25	800	NP	HA-4	G7
4	70	25	800	800	HA-4	G7
5	70	25	NP	800	HA-4	G7, G18
6	70	25	800	NP	HA-4	G7
7	70	25	800	NP	HA-4	G7
8	70	25	800	NP	HA-4	G7
9	70	25	800	NP	HA-4	G7
10	70	25	NP	800	HA-4	G7, G18
11	70	25	800	NP	HA-4	G7
12	70	25	NP	800	HA-4	G7, G18
13	70	25	NP	800	HA-4	G7, G18
14	70	25	800	NP	HA-4	G7
15	70	25	800	NP	HA-4	G7
16	70	25	NP	800	HA-4	G7, G18
17	70	25	800	NP	HA-4	G7
18	70	25	800	NP	HA-4	G7
19	70	25	800	NP	HA-4	G7
20	70	30	800	800	HA-2	G7
21	70	30	800	800	HA-2	G7, G9, G10
22	70	30	800	800	HA-2	G7
23	70	30	800	800	HA-2	G7
24	75	30	800	800	HA-2	G7, G9
25	75	30	800	800	HA-2	G7, G9
26	75	30	800	800	HA-2	G7, G9, G10
27	75	30	800	NP	HA-2	G7
28	75	30	NP	800	HA-2	G7, G9, G18
29	75	30	800	NP	HA-2	G7
30	75	30	800	800	HA-2	G7, G9, G10
31	75	30	NP	800	HA-2	G7, G9, G18
32	75	30	800	NP	HA-2	G7
33	75	30	800	NP	HA-2	G7
34	75	30	800	NP	HA-2	G7
35	75	30	800	800	HA-2	G7, G9, G10
36	75	30	800	NP	HA-2	G7
37	75	30	NP	800	HA-2	G7
38	75	30	800	NP	HA-2	G7
39	75	30	800	NP	HA-2	G7
40	75	30	800	NP	HA-2	G7
41	75	30	NP	800	HA-2	G7, G9, G18
42	75	30	800	NP	HA-2	G7
43	75	30	800	NP	HA-2	G7
44	75	30	800	NP	HA-2	G7
45	75	30	800	NP	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
2	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
3	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
4	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
5	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
6	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
7	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
8	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
9	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
10	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
11	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
12	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
13	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
14	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
15	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
16	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.2	11.0	...	...
17	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
18	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
19	16.7	...	16.7	...	16.7	15.7	14.8	14.0	13.7	13.5	13.2	12.9	...	...
20	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
21	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
22	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
23	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
24	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
25	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
26	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
27	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
28	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
29	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
30	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
31	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
32	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
33	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
34	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
35	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
36	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
37	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
38	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
39	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
40	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
41	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
42	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
43	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
44	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
45	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H	S31609	...	...	8	1
2	16Cr-12Ni-2Mo	Plate	SA-240	316H	S31609	...	...	8	1
3	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...	8	1
4	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...	8	1
5	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316H	S31609	...	...	8	1
6	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316H	S31609	...	...	8	1
7	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316H	S31609	...	...	8	1
8	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	1	...	8	1
9	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	3	...	8	1
10	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	4	...	8	1
11	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H	S31609	...	...	8	1
12	16Cr-12Ni-2Mo	Fittings	SA-403	316H	S31609	...	...	8	1
13	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316H	S31609	WP-W	...	8	1
14	16Cr-12Ni-2Mo	Bar	SA-479	316H	S31609	...	...	8	1
15	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316H	S31609	...	...	8	1
16	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316H	S31609	...	...	8	1
17	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2	...	...	≤3	8	1
18	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2	...	...	≤3	8	1
19	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...	>5	8	1
20	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316LN	S31653	...	...	8	1
21	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...	≤5	8	1
22	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316LN	S31653	...	...	8	1
23	16Cr-12Ni-2Mo-N	Plate	SA-240	316LN	S31653	...	...	8	1
24	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316LN	S31653	...	...	8	1
25	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316LN	S31653	...	...	8	1
26	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	1	...	8	1
27	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	3	...	8	1
28	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	4	...	8	1
29	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316LN	S31653	...	...	8	1
30	16Cr-12Ni-2Mo-N	Fittings	SA-403	316LN	S31653	...	...	8	1
31	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316LN	S31653	WP-W	...	8	1
32	16Cr-12Ni-2Mo-N	Bar	SA-479	316LN	S31653	...	...	8	1
33	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316LN	S31653	...	...	8	1
34	16Cr-12Ni-2Mo-N	Wld. pipe	SA-813	TP316LN	S31653	...	...	8	1
35	16Cr-12Ni-2Mo-N	Wld. pipe	SA-814	TP316LN	S31653	...	...	8	1
36	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316N	S31651	...	≤5	8	1
37	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N	S31651	...	≤5	8	1
38	16Cr-12Ni-2Mo-N	Plate	SA-240	316N	S31651	...	≤5	8	1
39	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...	8	1
40	16Cr-12Ni-2Mo-N	Wld. pipe	SA-312	TP316N	S31651	...	≤5	8	1
41	16Cr-12Ni-2Mo-N	Smls. pipe	SA-312	TP316N	S31651	...	≤5	8	1
42	16Cr-12Ni-2Mo-N	Wld. pipe	SA-312	TP316N	S31651	...	...	8	1
43	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	1	≤5	8	1
44	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	3	≤5	8	1
45	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	4	≤5	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	800	800	HA-2	G7
2	75	30	800	NP	HA-2	G7
3	75	30	800	NP	HA-2	G7
4	75	30	NP	800	HA-2	G7, G18
5	75	30	800	NP	HA-2	G7
6	75	30	800	800	HA-2	G7
7	75	30	NP	800	HA-2	G7, G18
8	75	30	800	NP	HA-2	G7
9	75	30	800	NP	HA-2	G7
10	75	30	800	NP	HA-2	G7
11	75	30	800	800	HA-2	G7
12	75	30	800	NP	HA-2	G7
13	75	30	800	NP	HA-2	G7
14	75	30	800	NP	HA-2	G7
15	75	30	800	NP	HA-2	G7
16	75	30	800	NP	HA-2	G7
17	75	32	NP	800	HA-4	G7
18	75	32	NP	800	HA-2	G7
19	70	30	800	NP	HA-2	G7
20	70	30	800	NP	HA-2	G7
21	75	30	800	NP	HA-2	G7
22	75	30	800	NP	HA-2	G7
23	75	30	800	NP	HA-2	G7
24	75	30	800	NP	HA-2	G7
25	75	30	800	NP	HA-2	G7
26	75	30	800	NP	HA-2	G7
27	75	30	800	NP	HA-2	G7
28	75	30	800	NP	HA-2	G7
29	75	30	800	NP	HA-2	G7
30	75	30	800	NP	HA-2	G7
31	75	30	800	NP	HA-2	G7
32	75	30	800	NP	HA-2	G7
33	75	30	800	NP	HA-2	G7
34	75	30	800	NP	HA-2	G7
35	75	30	800	NP	HA-2	G7
36	80	35	800	NP	HA-2	G7
37	80	35	800	800	HA-2	G7
38	80	35	800	800	HA-2	G7
39	80	35	NP	800	HA-2	G7, G18
40	80	35	800	NP	HA-2	G7
41	80	35	800	800	HA-2	G7
42	80	35	NP	800	HA-2	G7, G18
43	80	35	800	NP	HA-2	G7
44	80	35	800	NP	HA-2	G7
45	80	35	800	NP	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
2	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
3	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
4	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
5	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
6	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
7	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
8	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
9	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
10	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
11	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
12	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
13	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
14	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
15	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
16	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
17	21.3	21.3	21.3	21.3	21.3	20.1	18.8	17.9	17.6	17.3	16.9	16.6	...	...
18	21.3	21.3	21.3	21.3	21.3	20.5	19.1	18.1	17.7	17.4	17.2	16.9	...	...
19	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
20	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
21	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
22	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
23	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
24	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
25	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
26	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
27	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
28	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
29	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
30	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
31	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
32	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
33	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
34	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
35	20.0	...	20.0	...	20.0	18.9	17.5	16.5	16.0	15.6	15.2	14.8	...	...
36	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
37	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
38	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
39	19.8	...	19.8	...	19.8	19.8	18.9	17.9	17.4	17.0	16.7	16.3	...	...
40	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
41	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
42	19.8	...	19.8	...	19.8	19.8	18.9	17.9	17.4	17.0	16.7	16.3	...	...
43	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
44	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
45	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N	S31651	...	...	8	1
2	16Cr-12Ni-2Mo-N	Fittings	SA-403	316N	S31651	...	...	8	1
3	16Cr-12Ni-2Mo-N	Fittings	SA-403	316N	S31651	CR	...	8	1
4	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316N	S31651	WP-W	...	8	1
5	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316N	S31651	WP-W	...	8	1
6	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316N	S31651	WP-WX	...	8	1
7	16Cr-12Ni-2Mo-N	Bar	SA-479	316N	S31651	...	...	8	1
8	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316N	S31651	...	...	8	1
9	16Cr-12Ni-2Mo-N	Wld. pipe	SA-813	TP316N	S31651	...	...	8	1
10	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMo17-11-2	...	...	≤3	8	1
11	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMo17-13-3	...	...	≤3	8	1
12	16Cr-12Ni-2Mo-N	Wld. pipe	SA-814	TP316N	S31651	...	...	8	1
13	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N	S31651	...	≤5	8	1
14	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...	S30601	...	...	8	1
15	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	...	8	3
16	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	...	8	3
17	18Cr-5Ni-3Mo	Smls. tube	SA-789	...	S31500	...	...	10H	1
18	18Cr-5Ni-3Mo	Wld. tube	SA-789	...	S31500	...	...	10H	1
19	18Cr-5Ni-3Mo	Smls. pipe	SA-790	...	S31500	...	...	10H	1
20	18Cr-5Ni-3Mo	Wld. pipe	SA-790	...	S31500	...	...	10H	1
21	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	>5	8	1
22	18Cr-8Ni	Forgings	SA-965	F304L	S30403	...	...	8	1
23	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	≤5	8	1
24	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...	...	8	1
25	18Cr-8Ni	Plate	SA-240	304L	S30403	...	...	8	1
26	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...	8	1
27	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...	8	1
28	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...	8	1
29	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	...	...	8	1
30	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...	8	1
31	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	1	...	8	1
32	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	3	...	8	1
33	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	4	...	8	1
34	18Cr-8Ni	Fittings	SA-403	304L	S30403	...	...	8	1
35	18Cr-8Ni	Fittings	SA-403	304L	S30403	WP-S	...	8	1
36	18Cr-8Ni	Wld. fittings	SA-403	304L	S30403	WP-W	...	8	1
37	18Cr-8Ni	Bar	SA-479	304L	S30403	...	...	8	1
38	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...	8	1
39	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...	8	1
40	18Cr-8Ni	Wld. pipe	SA-813	TP304L	S30403	...	...	8	1
41	18Cr-8Ni	Wld. pipe	SA-814	TP304L	S30403	...	...	8	1
42	18Cr-8Ni	Bar	SA/JIS G4303	SUS304L	...	...	...	8	1
43	18Cr-8Ni	Castings	SA-351	CF3	J92500	...	...	8	1
44	18Cr-8Ni	Cast pipe	SA-451	CPF3	J92500	...	...	8	1
45	18Cr-8Ni	Castings	SA-351	CF10	J92590	...	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	80	35	800	800	HA-2	G7
2	80	35	800	NP	HA-2	G7
3	80	35	NP	800	HA-2	G7, G18
4	80	35	800	NP	HA-2	G7
5	80	35	NP	800	HA-2	G7, G18
6	80	35	NP	800	HA-2	G7, G18
7	80	35	800	NP	HA-2	G7
8	80	35	800	NP	HA-2	G7
9	80	35	800	NP	HA-2	G7
10	84	41	NP	800	HA-2	G7
11	84	41	NP	800	HA-2	G7
12	80	35	800	NP	HA-2	G7
13	80	35	800	800	HA-2	G7
14	78	37	NP	500	HA-1	...
15	100	55	NP	800	HA-6	G7
16	100	60	NP	800	HA-6	G7
17	92	64	NP	600	HA-5	G13
18	92	64	NP	600	HA-5	G13, G18
19	92	64	NP	600	HA-5	G13
20	92	64	NP	600	HA-5	G13, G18
21	65	25	800	800	HA-3	G7
22	65	25	NP	800	HA-3	G7
23	70	25	800	800	HA-3	G7
24	70	25	800	800	HA-3	G7
25	70	25	800	800	HA-3	G7
26	70	25	800	NP	HA-3	G7
27	70	25	NP	800	HA-3	G7, G18
28	70	25	800	NP	HA-3	G7
29	70	25	800	800	HA-3	G7
30	70	25	NP	800	HA-3	G7, G18
31	70	25	800	NP	HA-3	G7
32	70	25	800	NP	HA-3	G7
33	70	25	800	NP	HA-3	G7
34	70	25	800	NP	HA-3	G7
35	70	25	NP	800	HA-3	G7
36	70	25	800	NP	HA-3	G7
37	70	25	800	NP	HA-3	G7
38	70	25	800	NP	HA-3	G7
39	70	25	NP	800	HA-3	G7, G18
40	70	25	800	NP	HA-3	G7
41	70	25	800	NP	HA-3	G7
42	70	25	800	NP	HA-3	G7
43	70	30	800	800	HA-3	G7, G13
44	70	30	800	NP	HA-3	G7, G13
45	70	30	NP	800	HA-3	G7, G10, G13

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
2	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
3	19.8	...	19.8	...	19.8	19.8	18.9	17.9	17.4	17.0	16.7	16.3	...	...
4	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
5	19.8	...	19.8	...	19.8	19.8	18.9	17.9	17.4	17.0	16.7	16.3	...	...
6	19.8	...	19.8	...	19.8	19.8	18.9	17.9	17.4	17.0	16.7	16.3	...	...
7	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
8	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
9	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
10	27.3	27.3	27.3	27.2	26.5	25.1	23.8	22.3	21.7	21.2	20.6	20.1	...	...
11	27.3	27.3	27.3	27.2	26.5	25.1	23.8	22.3	21.7	21.2	20.6	20.1	...	...
12	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
13	23.3	...	23.3	...	23.3	23.3	22.3	21.0	20.5	20.0	19.6	19.2	...	...
14	24.7	...	24.7	...	24.4	22.2	20.4	...	...	...	...	...	...	...
15	33.3	...	32.6	...	30.4	29.1	27.2	25.9	25.4	25.0	24.5	24.0	...	...
16	33.3	...	32.6	...	30.4	29.1	28.4	27.8	27.3	26.8	26.2	25.4	...	...
17	30.7	...	29.6	...	28.5	28.3	28.3	28.3	...	...	...	...	...	...
18	26.1	...	25.2	...	24.2	24.0	24.0	24.0	...	...	...	...	...	...
19	30.7	...	29.6	...	28.5	28.3	28.3	28.3	...	...	...	...	...	...
20	26.1	...	25.2	...	24.2	24.0	24.0	24.0	...	...	...	...	...	...
21	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
22	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
23	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
24	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
25	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
26	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
27	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	...	...
28	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
29	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
30	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	...	...
31	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
32	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
33	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
34	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
35	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
36	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
37	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
38	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
39	14.2	...	14.2	...	14.2	13.4	12.5	11.9	11.7	11.4	11.3	11.1	...	...
40	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
41	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
42	16.7	...	16.7	...	16.7	15.8	14.7	14.0	13.7	13.5	13.3	13.0	...	...
43	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
44	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
45	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-8Ni	Castings	SA-351	CF8	J92600	...	...	8	1
2	18Cr-8Ni	Cast pipe	SA-451	CPF8	J92600	...	...	8	1
3	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	>5	8	1
4	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	≥8	8	1
5	18Cr-8Ni	Forgings	SA-965	F304	S30400	...	...	8	1
6	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	>5	8	1
7	18Cr-8Ni	Forgings	SA-965	F304H	S30409	...	...	8	1
8	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9	...	...	≤3	8	1
9	18Cr-8Ni	Plate	SA-240	302	S30200	...	...	8	1
10	18Cr-8Ni	Bar	SA-479	302	S30200	...	...	8	1
11	18Cr-8Ni	Bar	SA/JIS G4303	SUS302	...	...	...	8	1
12	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	≤5	8	1
13	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...	...	8	1
14	18Cr-8Ni	Plate	SA-240	304	S30400	...	...	8	1
15	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...	8	1
16	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...	8	1
17	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...	8	1
18	18Cr-8Ni	Smls. pipe	SA-312	TP304	S30400	...	...	8	1
19	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...	8	1
20	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	1	...	8	1
21	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	3	...	8	1
22	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	4	...	8	1
23	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	<8	8	1
24	18Cr-8Ni	Fittings	SA-403	304	S30400	...	...	8	1
25	18Cr-8Ni	Fittings	SA-403	304	S30400	CR	...	8	1
26	18Cr-8Ni	Fittings	SA-403	304	S30400	WP-S	...	8	1
27	18Cr-8Ni	Wld. fittings	SA-403	304	S30400	WP-W	...	8	1
28	18Cr-8Ni	Wld. fittings	SA-403	304	S30400	WP-W	...	8	1
29	18Cr-8Ni	Wld. fittings	SA-403	304	S30400	WP-WX	...	8	1
30	18Cr-8Ni	Bar	SA-479	304	S30400	...	...	8	1
31	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...	8	1
32	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...	8	1
33	18Cr-8Ni	Wld. tube	SA-813	TP304	S30400	...	...	8	1
34	18Cr-8Ni	Wld. tube	SA-814	TP304	S30400	...	...	8	1
35	18Cr-8Ni	Bar	SA/JIS G4303	SUS304	...	...	...	8	1
36	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	≤5	8	1
37	18Cr-8Ni	Smls. tube	SA-213	TP304H	S30409	...	...	8	1
38	18Cr-8Ni	Plate	SA-240	304H	S30409	...	...	8	1
39	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...	8	1
40	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...	8	1
41	18Cr-8Ni	Wld. pipe	SA-312	TP304H	S30409	...	...	8	1
42	18Cr-8Ni	Smls. pipe	SA-312	TP304H	S30409	...	...	8	1
43	18Cr-8Ni	Wld. pipe	SA-312	TP304H	S30409	...	...	8	1
44	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	1	...	8	1
45	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	3	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	70	30	800	800	HA-1	G7, G9, G10, G13
2	70	30	800	NP	HA-1	G7, G13
3	70	30	800	800	HA-1	G7, G9, G10
4	70	30	800	800	HA-1	G7, G9, G10, S2
5	70	30	800	800	HA-1	G7, G9, G10
6	70	30	800	800	HA-1	G7
7	70	30	800	800	HA-1	G7
8	72.5	29	NP	800	HA-3	G7
9	75	30	NP	800	HA-1	G7, G9
10	75	30	800	NP	HA-1	G7
11	75	30	800	NP	HA-1	G7
12	75	30	800	800	HA-1	G7, G9, G10
13	75	30	800	800	HA-1	G7, G9
14	75	30	800	800	HA-1	G7, G9, G10
15	75	30	800	NP	HA-1	G7
16	75	30	NP	800	HA-1	G7, G9, G18
17	75	30	800	NP	HA-1	G7
18	75	30	800	800	HA-1	G7, G9, G10
19	75	30	NP	800	HA-1	G7, G9, G18
20	75	30	800	NP	HA-1	G7
21	75	30	800	NP	HA-1	G7
22	75	30	800	NP	HA-1	G7
23	75	30	800	800	HA-1	G7, G9, G10, S5
24	75	30	800	NP	HA-1	G7
25	75	30	NP	800	HA-1	G7, G18
26	75	30	NP	800	HA-1	G7
27	75	30	800	NP	HA-1	G7
28	75	30	NP	800	HA-1	G7, G18
29	75	30	NP	800	HA-1	G7, G18
30	75	30	800	NP	HA-1	G7
31	75	30	800	NP	HA-1	G7
32	75	30	NP	800	HA-1	G7, G9, G18
33	75	30	800	NP	HA-1	G7
34	75	30	800	NP	HA-1	G7
35	75	30	800	NP	HA-1	G7
36	75	30	800	800	HA-1	G7
37	75	30	800	800	HA-1	G7
38	75	30	800	NP	HA-1	G7
39	75	30	800	NP	HA-1	G7
40	75	30	NP	800	HA-1	G7, G18
41	75	30	800	NP	HA-1	G7
42	75	30	800	800	HA-1	G7
43	75	30	NP	800	HA-1	G7, G18
44	75	30	800	NP	HA-1	G7
45	75	30	800	NP	HA-1	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
2	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
3	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
4	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
5	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
6	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
7	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
8	19.3	...	19.3	...	19.3	18.3	17.1	16.2	15.9	15.7	15.4	15.1	14.9	14.7
9	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
10	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
11	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
12	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
13	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
14	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
15	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
16	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
17	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
18	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
19	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
20	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
21	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
22	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
23	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
24	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
25	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
26	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
27	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
28	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
29	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
30	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
31	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
32	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
33	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
34	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
35	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
36	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
37	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
38	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
39	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
40	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
41	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
42	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
43	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
44	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
45	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	4	...	8	1
2	18Cr-8Ni	Smls. pipe	SA-376	TP304H	S30409	...	...	8	1
3	18Cr-8Ni	Fittings	SA-403	304H	S30409	...	...	8	1
4	18Cr-8Ni	Fittings	SA-403	304H	S30409	CR	...	8	1
5	18Cr-8Ni	Fittings	SA-403	304H	S30409	WP-S	...	8	1
6	18Cr-8Ni	Wld. fittings	SA-403	304H	S30409	WP-W	...	8	1
7	18Cr-8Ni	Wld. fittings	SA-403	304H	S30409	WP-W	...	8	1
8	18Cr-8Ni	Wld. fittings	SA-403	304H	S30409	WP-WX	...	8	1
9	18Cr-8Ni	Bar	SA-479	304H	S30409	...	...	8	1
10	18Cr-8Ni	Wld. tube	SA-813	TP304H	S30409	...	...	8	1
11	18Cr-8Ni	Wld. tube	SA-814	TP304H	S30409	...	...	8	1
12	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10	...	...	≤3	8	1
13	18Cr-8Ni	Castings	SA-351	CF3A	J92500	...	...	8	1
14	18Cr-8Ni	Cast pipe	SA-451	CPF3A	J92500	...	...	8	1
15	18Cr-8Ni	Castings	SA-351	CF8A	J92600	...	...	8	1
16	18Cr-8Ni	Cast pipe	SA-451	CPF8A	J92600	...	...	8	1
17	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...	>5	8	1
18	18Cr-8Ni-N	Forgings	SA-965	F304LN	S30453	...	...	8	1
19	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...	≤5	8	1
20	18Cr-8Ni-N	Smls. tube	SA-213	TP304LN	S30453	...	...	8	1
21	18Cr-8Ni-N	Plate	SA-240	304LN	S30453	...	...	8	1
22	18Cr-8Ni-N	Wld. tube	SA-249	TP304LN	S30453	...	...	8	1
23	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304LN	S30453	...	...	8	1
24	18Cr-8Ni-N	Wld. pipe	SA-358	304LN	S30453	1	...	8	1
25	18Cr-8Ni-N	Wld. pipe	SA-358	304LN	S30453	3	...	8	1
26	18Cr-8Ni-N	Wld. pipe	SA-358	304LN	S30453	4	...	8	1
27	18Cr-8Ni-N	Smls. pipe	SA-376	TP304LN	S30453	...	...	8	1
28	18Cr-8Ni-N	Fittings	SA-403	304LN	S30453	...	...	8	1
29	18Cr-8Ni-N	Wld. fittings	SA-403	304LN	S30453	WP-W	...	8	1
30	18Cr-8Ni-N	Bar	SA-479	304LN	S30453	...	...	8	1
31	18Cr-8Ni-N	Wld. tube	SA-688	TP304LN	S30453	...	...	8	1
32	18Cr-8Ni-N	Wld. tube	SA-813	TP304LN	S30453	...	...	8	1
33	18Cr-8Ni-N	Wld. tube	SA-814	TP304LN	S30453	...	...	8	1
34	18Cr-8Ni-N	Forgings	SA-182	F304N	S30451	...	...	8	1
35	18Cr-8Ni-N	Smls. tube	SA-213	TP304N	S30451	...	...	8	1
36	18Cr-8Ni-N	Plate	SA-240	304N	S30451	...	...	8	1
37	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...	8	1
38	18Cr-8Ni-N	Wld. pipe	SA-312	TP304N	S30451	...	...	8	1
39	18Cr-8Ni-N	Smls. pipe	SA-312	TP304N	S30451	...	...	8	1
40	18Cr-8Ni-N	Wld. pipe	SA-312	TP304N	S30451	...	...	8	1
41	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	1	...	8	1
42	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	3	...	8	1
43	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	4	...	8	1
44	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N	S30451	...	...	8	1
45	18Cr-8Ni-N	Fittings	SA-403	304N	S30451	...	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	800	NP	HA-1	G7
2	75	30	800	800	HA-1	G7
3	75	30	800	NP	HA-1	G7
4	75	30	NP	800	HA-1	G7, G18
5	75	30	NP	800	HA-1	G7
6	75	30	800	NP	HA-1	G7
7	75	30	NP	800	HA-1	G7, G18
8	75	30	NP	800	HA-1	G7, G18
9	75	30	800	NP	HA-1	G7
10	75	30	800	NP	HA-1	G7
11	75	30	800	NP	HA-1	G7
12	75	31	NP	800	HA-1	G7
13	77	35	700	NP	HA-3	G7, G13
14	77	35	700	NP	HA-3	G7, G13
15	77	35	700	NP	HA-1	G7, G13
16	77	35	700	NP	HA-1	G7, G13
17	70	30	800	NP	HA-1	G7
18	70	30	800	NP	HA-1	G7
19	75	30	800	NP	HA-1	G7
20	75	30	800	NP	HA-1	G7
21	75	30	800	NP	HA-1	G7
22	75	30	800	NP	HA-1	G7
23	75	30	800	NP	HA-1	G7
24	75	30	800	NP	HA-1	G7
25	75	30	800	NP	HA-1	G7
26	75	30	800	NP	HA-1	G7
27	75	30	800	NP	HA-1	G7
28	75	30	800	NP	HA-1	G7
29	75	30	800	NP	HA-1	G7
30	75	30	800	NP	HA-1	G7
31	75	30	800	NP	HA-1	G7
32	75	30	800	NP	HA-1	G7
33	75	30	800	NP	HA-1	G7
34	80	35	800	NP	HA-1	G7
35	80	35	800	800	HA-1	G7
36	80	35	800	800	HA-1	G7
37	80	35	NP	800	HA-1	G7, G18
38	80	35	800	NP	HA-1	G7
39	80	35	800	800	HA-1	G7
40	80	35	NP	800	HA-1	G7, G18
41	80	35	800	NP	HA-1	G7
42	80	35	800	NP	HA-1	G7
43	80	35	800	NP	HA-1	G7
44	80	35	800	800	HA-1	G7
45	80	35	800	NP	HA-1	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
2	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
3	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
4	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
5	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
6	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
7	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
8	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
9	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
10	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
11	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
12	20.7	...	20.7	...	20.5	18.9	17.7	16.8	16.5	16.1	15.8	15.4	...	...
13	23.3	...	23.3	...	22.7	21.7	20.4	19.3	18.9	18.5	...	...	...	...
14	23.3	...	23.3	...	22.7	21.7	20.4	19.3	18.9	18.5	...	...	...	...
15	23.3	...	23.3	...	22.7	21.7	20.4	19.3	18.9	18.5	...	...	...	...
16	23.3	...	23.3	...	22.7	21.7	20.4	19.3	18.9	18.5	...	...	...	...
17	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
18	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
19	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
20	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
21	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
22	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
23	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
24	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
25	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
26	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
27	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
28	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
29	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
30	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
31	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
32	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
33	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
34	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
35	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
36	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
37	19.8	...	19.8	...	19.2	17.3	16.0	15.2	14.9	14.6	14.4	14.1	...	...
38	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
39	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
40	19.8	...	19.8	...	19.2	17.3	16.0	15.2	14.9	14.6	14.4	14.1	...	...
41	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
42	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
43	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
44	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
45	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-8Ni-N	Fittings	SA-403	304N	S30451	CR	...	8	1
2	18Cr-8Ni-N	Wld. fittings	SA-403	304N	S30451	WP-W	...	8	1
3	18Cr-8Ni-N	Wld. fittings	SA-403	304N	S30451	WP-W	...	8	1
4	18Cr-8Ni-N	Wld. fittings	SA-403	304N	S30451	WP-WX	...	8	1
5	18Cr-8Ni-N	Bar	SA-479	304N	S30451	...	...	8	1
6	18Cr-8Ni-N	Wld. tube	SA-688	TP304N	S30451	...	...	8	1
7	18Cr-8Ni-N	Wld. pipe	SA-813	TP304N	S30451	...	...	8	1
8	18Cr-8Ni-N	Wld. pipe	SA-814	TP304N	S30451	...	...	8	1
9	18Cr-8Ni-N	Forgings	SA-965	F304N	S30451	...	...	8	1
10	18Cr-8Ni-N	Plate	SA/EN 10028-7	X2CrNiN18-10	...	...	≤3	8	1
11	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9	...	...	≤3	8	1
12	18Cr-8Ni-4Si-N	Bar	SA-479	...	S21800	...	...	8	3
13	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	...	8	1
14	18Cr-10Ni-Cb	Cast pipe	SA-451	CPF8C	J92710	...	...	8	1
15	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	>5	8	1
16	18Cr-10Ni-Cb	Forgings	SA-965	F347	S34700	...	...	8	1
17	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	>5	8	1
18	18Cr-10Ni-Cb	Forgings	SA-965	F347H	S34709	...	...	8	1
19	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	>5	8	1
20	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	>5	8	1
21	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	≤5	8	1
22	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347	S34700	...	...	8	1
23	18Cr-10Ni-Cb	Plate	SA-240	347	S34700	...	...	8	1
24	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...	8	1
25	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...	8	1
26	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347	S34700	...	...	8	1
27	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347	S34700	...	...	8	1
28	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347	S34700	...	...	8	1
29	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	1	...	8	1
30	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	3	...	8	1
31	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	4	...	8	1
32	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347	S34700	...	...	8	1
33	18Cr-10Ni-Cb	Fittings	SA-403	347	S34700	...	...	8	1
34	18Cr-10Ni-Cb	Fittings	SA-403	347	S34700	CR	...	8	1
35	18Cr-10Ni-Cb	Fittings	SA-403	347	S34700	WP-S	...	8	1
36	18Cr-10Ni-Cb	Wld. fittings	SA-403	347	S34700	WP-W	...	8	1
37	18Cr-10Ni-Cb	Wld. fittings	SA-403	347	S34700	WP-W	...	8	1
38	18Cr-10Ni-Cb	Wld. fittings	SA-403	347	S34700	WP-WX	...	8	1
39	18Cr-10Ni-Cb	Bar	SA-479	347	S34700	...	...	8	1
40	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347	S34700	...	...	8	1
41	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP347	S34700	...	...	8	1
42	18Cr-10Ni-Cb	Bar	SA/JIS G4303	SUS347	...	...	...	8	1
43	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	≤5	8	1
44	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H	S34709	...	...	8	1
45	18Cr-10Ni-Cb	Plate	SA-240	347H	S34709	...	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	80	35	NP	800	HA-1	G7, G18
2	80	35	800	NP	HA-1	G7
3	80	35	NP	800	HA-1	G7, G18
4	80	35	NP	800	HA-1	G7, G18
5	80	35	800	NP	HA-1	G7
6	80	35	800	NP	HA-1	G7
7	80	35	800	NP	HA-1	G7
8	80	35	800	NP	HA-1	G7
9	80	35	800	800	HA-1	G7
10	80	39	NP	800	HA-1	G7
11	80	39	NP	800	HA-1	G7
12	95	50	800	NP	HA-6	...
13	70	30	800	800	HA-2	G7, G9, G13
14	70	30	800	NP	HA-2	G7, G13
15	70	30	800	800	HA-2	G7, G9
16	70	30	800	800	HA-2	G7, G9
17	70	30	800	800	HA-2	G7
18	70	30	800	800	HA-2	G7, G9
19	70	30	NP	800	HA-2	G7, G9
20	70	30	NP	800	HA-2	G7
21	75	30	800	800	HA-2	G7, G9
22	75	30	800	800	HA-2	G7, G9
23	75	30	800	800	HA-2	G7, G9
24	75	30	800	NP	HA-2	G7
25	75	30	NP	800	HA-2	G7, G9, G18
26	75	30	800	NP	HA-2	G7
27	75	30	800	800	HA-2	G7, G9
28	75	30	NP	800	HA-2	G7, G9, G18
29	75	30	800	NP	HA-2	G7
30	75	30	800	NP	HA-2	G7
31	75	30	800	NP	HA-2	G7
32	75	30	800	800	HA-2	G7, G9
33	75	30	800	NP	HA-2	G7
34	75	30	NP	800	HA-2	G7, G18
35	75	30	NP	800	HA-2	G7
36	75	30	800	NP	HA-2	G7
37	75	30	NP	800	HA-2	G7, G18
38	75	30	NP	800	HA-2	G7, G18
39	75	30	800	NP	HA-2	G7
40	75	30	800	NP	HA-2	G7
41	75	30	800	NP	HA-2	G7
42	75	30	800	NP	HA-2	G7
43	75	30	800	800	HA-2	G7
44	75	30	800	800	HA-2	G7
45	75	30	800	800	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	19.8	...	19.8	...	19.2	17.3	16.0	15.2	14.9	14.6	14.4	14.1	...	...
2	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
3	19.8	...	19.8	...	19.2	17.3	16.0	15.2	14.9	14.6	14.4	14.1	...	...
4	19.8	...	19.8	...	19.2	17.3	16.0	15.2	14.9	14.6	14.4	14.1	...	...
5	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
6	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
7	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
8	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
9	23.3	...	23.3	...	22.5	20.3	18.9	17.9	17.5	17.2	16.9	16.6	...	...
10	26.0	25.9	25.1	24.4	23.6	22.7	22.4	21.6	21.2	20.7	20.3	19.8	...	...
11	26.0	26.0	26.0	25.9	25.2	22.8	21.1	20.1	19.6	19.3	18.9	18.6	...	...
12	31.7	...	25.9	...	22.1	19.8	18.4	17.6	17.3	17.1	16.9	16.8	...	...
13	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
14	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
15	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
16	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
17	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
18	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
19	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
20	20.0	...	20.0	...	20.0	19.3	18.7	18.4	18.3	18.3	18.3	18.3	...	...
21	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
22	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
23	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
24	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
25	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
26	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
27	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
28	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
29	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
30	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
31	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
32	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
33	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
34	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
35	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
36	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
37	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
38	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
39	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
40	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
41	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
42	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
43	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
44	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
45	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...

INTENTIONALLY LEFT BLANK

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...	8	1
2	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...	8	1
3	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347H	S34709	...	...	8	1
4	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347H	S34709	...	...	8	1
5	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347H	S34709	...	...	8	1
6	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H	S34709	...	...	8	1
7	18Cr-10Ni-Cb	Fittings	SA-403	347H	S34709	...	...	8	1
8	18Cr-10Ni-Cb	Fittings	SA-403	347H	S34709	CR	...	8	1
9	18Cr-10Ni-Cb	Fittings	SA-403	347H	S34709	WP-S	...	8	1
10	18Cr-10Ni-Cb	Wld. fittings	SA-403	347H	S34709	WP-W	...	8	1
11	18Cr-10Ni-Cb	Wld. fittings	SA-403	347H	S34709	WP-W	...	8	1
12	18Cr-10Ni-Cb	Wld. fittings	SA-403	347H	S34709	WP-WX	...	8	1
13	18Cr-10Ni-Cb	Bar	SA-479	347H	S34709	...	...	8	1
14	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347H	S34709	...	...	8	1
15	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP347H	S34709	...	...	8	1
16	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	≤5	8	1
17	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348	S34800	...	...	8	1
18	18Cr-10Ni-Cb	Plate	SA-240	348	S34800	...	...	8	1
19	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...	8	1
20	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...	8	1
21	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348	S34800	...	...	8	1
22	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348	S34800	...	...	8	1
23	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348	S34800	...	...	8	1
24	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	1	...	8	1
25	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	3	...	8	1
26	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	4	...	8	1
27	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348	S34800	...	...	8	1
28	18Cr-10Ni-Cb	Fittings	SA-403	348	S34800	...	...	8	1
29	18Cr-10Ni-Cb	Fittings	SA-403	348	S34800	CR	...	8	1
30	18Cr-10Ni-Cb	Fittings	SA-403	348	S34800	WP-S	...	8	1
31	18Cr-10Ni-Cb	Wld. fittings	SA-403	348	S34800	WP-W	...	8	1
32	18Cr-10Ni-Cb	Wld. fittings	SA-403	348	S34800	WP-W	...	8	1
33	18Cr-10Ni-Cb	Wld. fittings	SA-403	348	S34800	WP-WX	...	8	1
34	18Cr-10Ni-Cb	Bar	SA-479	348	S34800	...	...	8	1
35	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348	S34800	...	...	8	1
36	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348	S34800	...	...	8	1
37	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	≤5	8	1
38	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H	S34809	...	...	8	1
39	18Cr-10Ni-Cb	Plate	SA-240	348H	S34809	...	...	8	1
40	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...	8	1
41	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...	8	1
42	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348H	S34809	...	...	8	1
43	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348H	S34809	...	...	8	1
44	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348H	S34809	...	...	8	1
45	18Cr-10Ni-Cb	Fittings	SA-403	348H	S34809	...	...	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	800	NP	HA-2	G7
2	75	30	NP	800	HA-2	G7, G18
3	75	30	800	NP	HA-2	G7
4	75	30	800	800	HA-2	G7
5	75	30	NP	800	HA-2	G7, G18
6	75	30	800	800	HA-2	G7
7	75	30	800	NP	HA-2	G7
8	75	30	NP	800	HA-2	G7, G18
9	75	30	NP	800	HA-2	G7
10	75	30	800	NP	HA-2	G7
11	75	30	NP	800	HA-2	G7, G18
12	75	30	NP	800	HA-2	G7, G18
13	75	30	800	NP	HA-2	G7
14	75	30	800	NP	HA-2	G7
15	75	30	800	NP	HA-2	G7
16	75	30	800	800	HA-2	G7, G9
17	75	30	800	800	HA-2	G7, G9
18	75	30	800	800	HA-2	G7, G9
19	75	30	800	NP	HA-2	G7
20	75	30	NP	800	HA-2	G7, G9, G18
21	75	30	800	NP	HA-2	G7
22	75	30	800	800	HA-2	G7, G9
23	75	30	NP	800	HA-2	G7, G9, G18
24	75	30	800	NP	HA-2	G7
25	75	30	800	NP	HA-2	G7
26	75	30	800	NP	HA-2	G7
27	75	30	800	800	HA-2	G7, G9
28	75	30	800	NP	HA-2	G7
29	75	30	NP	800	HA-2	G7, G18
30	75	30	NP	800	HA-2	G7
31	75	30	800	NP	HA-2	G7
32	75	30	NP	800	HA-2	G7, G18
33	75	30	NP	800	HA-2	G7, G18
34	75	30	800	NP	HA-2	G7
35	75	30	800	NP	HA-2	G7
36	75	30	800	NP	HA-2	G7
37	75	30	800	800	HA-2	G7
38	75	30	800	800	HA-2	G7
39	75	30	800	NP	HA-2	G7
40	75	30	800	NP	HA-2	G7
41	75	30	NP	800	HA-2	G7, G18
42	75	30	800	NP	HA-2	G7
43	75	30	800	800	HA-2	G7
44	75	30	NP	800	HA-2	G7, G18
45	75	30	800	NP	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
2	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
3	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
4	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
5	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
6	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
7	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
8	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
9	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
10	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
11	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
12	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
13	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
14	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
15	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
16	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
17	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
18	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
19	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
20	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
21	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
22	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
23	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
24	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
25	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
26	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
27	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
28	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
29	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
30	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
31	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
32	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
33	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
34	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
35	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
36	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
37	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
38	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
39	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
40	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
41	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
42	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
43	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
44	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
45	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-10Ni-Cb	Fittings	SA-403	348H	S34809	CR	...	8	1
2	18Cr-10Ni-Cb	Fittings	SA-403	348H	S34809	WP-S	...	8	1
3	18Cr-10Ni-Cb	Wld. fittings	SA-403	348H	S34809	WP-W	...	8	1
4	18Cr-10Ni-Cb	Wld. fittings	SA-403	348H	S34809	WP-W	...	8	1
5	18Cr-10Ni-Cb	Wld. fittings	SA-403	348H	S34809	WP-WX	...	8	1
6	18Cr-10Ni-Cb	Bar	SA-479	348H	S34809	...	...	8	1
7	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348H	S34809	...	...	8	1
8	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348H	S34809	...	...	8	1
9	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
10	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
11	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$	8	1
12	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$\leq \frac{3}{8}$	8	1
13	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	≤ 5	8	1
14	18Cr-10Ni-Ti	Forgings	SA-965	F321	S32100	...	...	8	1
15	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	≤ 5	8	1
16	18Cr-10Ni-Ti	Forgings	SA-965	F321H	S32109	...	...	8	1
17	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi181-10	...	...	≤ 3	8	1
18	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	≤ 5	8	1
19	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...	...	8	1
20	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...	...	8	1
21	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...	8	1
22	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...	8	1
23	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
24	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
25	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
26	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	1	...	8	1
27	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	3	...	8	1
28	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	4	...	8	1
29	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	$\leq \frac{3}{8}$	8	1
30	18Cr-10Ni-Ti	Fittings	SA-403	321	S32100	...	...	8	1
31	18Cr-10Ni-Ti	Fittings	SA-403	321	S32100	CR	...	8	1
32	18Cr-10Ni-Ti	Fittings	SA-403	321	S32100	WP-S	...	8	1
33	18Cr-10Ni-Ti	Wld. fittings	SA-403	321	S32100	WP-W	...	8	1
34	18Cr-10Ni-Ti	Wld. fittings	SA-403	321	S32100	WP-W	...	8	1
35	18Cr-10Ni-Ti	Wld. fittings	SA-403	321	S32100	WP-WX	...	8	1
36	18Cr-10Ni-Ti	Bar	SA-479	321	S32100	...	...	8	1
37	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321	S32100	...	...	8	1
38	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321	S32100	...	...	8	1
39	18Cr-10Ni-Ti	Bar	SA/JIS G4303	SUS321	...	...	...	8	1
40	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	≤ 5	8	1
41	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H	S32109	...	...	8	1
42	18Cr-10Ni-Ti	Plate	SA-240	321H	S32109	...	...	8	1
43	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...	8	1
44	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...	8	1
45	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$	8	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	NP	800	HA-2	G7, G18
2	75	30	NP	800	HA-2	G7
3	75	30	800	NP	HA-2	G7
4	75	30	NP	800	HA-2	G7, G18
5	75	30	NP	800	HA-2	G7, G18
6	75	30	800	NP	HA-2	G7
7	75	30	800	NP	HA-2	G7
8	75	30	800	NP	HA-2	G7
9	70	25	NP	800	HA-2	G7, G9
10	70	25	800	800	HA-2	G7, G9
11	70	25	NP	800	HA-2	G7
12	70	25	800	800	HA-2	G7
13	70	30	800	800	HA-2	G7, G9
14	70	30	800	800	HA-2	G7, G9
15	70	30	800	800	HA-2	G7
16	70	30	800	800	HA-2	G7, G9
17	73	29	NP	800	HA-2	G7
18	75	30	800	800	HA-2	G7, G9
19	75	30	800	800	HA-2	G7, G9
20	75	30	800	800	HA-2	G7, G9
21	75	30	800	NP	HA-2	G7
22	75	30	NP	800	HA-2	G7, G9, G18
23	75	30	800	NP	HA-2	G7
24	75	30	800	800	HA-2	G7, G9
25	75	30	NP	800	HA-2	G7, G9, G18
26	75	30	800	NP	HA-2	G7
27	75	30	800	NP	HA-2	G7
28	75	30	800	NP	HA-2	G7
29	75	30	800	800	HA-2	G7, G9
30	75	30	800	NP	HA-2	G7
31	75	30	NP	800	HA-2	G7, G18
32	75	30	NP	800	HA-2	G7
33	75	30	800	NP	HA-2	G7
34	75	30	NP	800	HA-2	G7, G18
35	75	30	NP	800	HA-2	G7, G18
36	75	30	800	NP	HA-2	G7
37	75	30	800	NP	HA-2	G7
38	75	30	800	NP	HA-2	G7
39	75	30	800	NP	HA-2	G7
40	75	30	800	800	HA-2	G7
41	75	30	800	800	HA-2	G7
42	75	30	800	800	HA-2	G7
43	75	30	800	NP	HA-2	G7
44	75	30	NP	800	HA-2	G7, G18
45	75	30	800	NP	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
2	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
3	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
4	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
5	17.0	...	17.0	...	17.0	17.0	17.0	16.4	16.1	15.9	15.7	15.6	...	...
6	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
7	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
8	20.0	...	20.0	...	20.0	20.0	20.0	19.3	19.0	18.7	18.5	18.3	...	...
9	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	...	...
10	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	...	...
11	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	...	...
12	16.7	...	16.7	...	16.7	16.7	16.1	15.2	14.9	14.6	14.3	14.1	...	...
13	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
14	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
15	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
16	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
17	19.3	19.3	19.3	19.3	19.3	19.3	18.7	17.6	17.3	16.9	16.7	16.4	...	...
18	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
19	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
20	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
21	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
22	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
23	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
24	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
25	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
26	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
27	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
28	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
29	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
30	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
31	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
32	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
33	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
34	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
35	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
36	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
37	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
38	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
39	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
40	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
41	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
42	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
43	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
44	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
45	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$	8	1
2	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	$\leq \frac{3}{16}$	8	1
3	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$\leq \frac{3}{8}$	8	1
4	18Cr-10Ni-Ti	Fittings	SA-403	321H	S32109	...	...	8	1
5	18Cr-10Ni-Ti	Fittings	SA-403	321H	S32109	CR	...	8	1
6	18Cr-10Ni-Ti	Fittings	SA-403	321H	S32109	WP-S	...	8	1
7	18Cr-10Ni-Ti	Wld. fittings	SA-403	321H	S32109	WP-W	...	8	1
8	18Cr-10Ni-Ti	Wld. fittings	SA-403	321H	S32109	WP-W	...	8	1
9	18Cr-10Ni-Ti	Wld. fittings	SA-403	321H	S32109	WP-WX	...	8	1
10	18Cr-10Ni-Ti	Bar	SA-479	321H	S32109	...	...	8	1
11	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321H	S32109	...	...	8	1
12	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321H	S32109	...	...	8	1
13	18Cr-11Ni	Plate	SA-240	305	S30500	...	...	8	1
14	18Cr-12Ni-2Mo	Castings	SA-351	CF3M	J92800	...	...	8	1
15	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF3M	J92800	...	...	8	1
16	18Cr-12Ni-2Mo	Castings	SA-351	CF8M	J92900	...	...	8	1
17	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF8M	J92900	...	...	8	1
18	18Cr-13Ni-3Mo	Plate	SA-240	317	S31700	...	≤ 5	8	1
19	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...	8	1
20	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...	8	1
21	18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317	S31700	...	...	8	1
22	18Cr-13Ni-3Mo	Smls. pipe	SA-312	TP317	S31700	...	≤ 5	8	1
23	18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317	S31700	...	≤ 5	8	1
24	18Cr-13Ni-3Mo	Fittings	SA-403	317	S31700	WP-S	...	8	1
25	18Cr-13Ni-3Mo	Plate	SA-240	317L	S31703	...	...	8	1
26	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-S	...	8	1
27	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15	S38100	...	≤ 5	8	1
28	18Cr-18Ni-2Si	Plate	SA-240	XM-15	S38100	...	≤ 5	8	1
29	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15	S38100	...	≤ 5	8	1
30	18Cr-18Ni-2Si	Smls. pipe	SA-312	TPXM-15	S38100	...	≤ 5	8	1
31	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15	S38100	...	≤ 5	8	1
32	20Cr-10Ni	Bar	SA-479	ER308	S30880	...	...	8	1
33	21Cr-6Ni-9Mn	Forgings	SA-182	FXM-11	S21904	...	...	8	3
34	21Cr-6Ni-9Mn	Wld. pipe	SA-312	TPXM-11	S21904	...	...	8	3
35	21Cr-6Ni-9Mn	Smls. pipe	SA-312	TPXM-11	S21904	...	...	8	3
36	21Cr-6Ni-9Mn	Wld. pipe	SA-312	TPXM-11	S21904	...	...	8	3
37	21Cr-6Ni-9Mn	Plate	SA-666	XM-11	S21904	...	...	8	3
38	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11	S21904	...	...	8	3
39	22Cr-5Ni-3Mo-N	Forgings	SA-182	F51	S31803	...	...	10H	1
40	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...	...	10H	1
41	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S31803	...	...	10H	1
42	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S31803	...	...	10H	1
43	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S31803	...	...	10H	1
44	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S31803	...	...	10H	1
45	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S32205	...	...	10H	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	800	800	HA-2	G7
2	75	30	NP	800	HA-2	G7, G18
3	75	30	800	800	HA-2	G7
4	75	30	800	NP	HA-2	G7
5	75	30	NP	800	HA-2	G7, G18
6	75	30	NP	800	HA-2	G7
7	75	30	800	NP	HA-2	G7
8	75	30	NP	800	HA-2	G7, G18
9	75	30	NP	800	HA-2	G7, G18
10	75	30	800	NP	HA-2	G7
11	75	30	800	NP	HA-2	G7
12	75	30	800	NP	HA-2	G7
13	75	30	800	NP	HA-1	G7
14	70	30	800	NP	HA-4	G7, G13
15	70	30	800	NP	HA-4	G7, G13
16	70	30	800	800	HA-2	G7, G9, G10, G13
17	70	30	800	NP	HA-2	G7, G13
18	75	30	NP	800	HA-2	G7, G9
19	75	30	800	NP	HA-2	G7
20	75	30	NP	800	HA-2	G7, G9, G18
21	75	30	800	NP	HA-2	G7
22	75	30	NP	800	HA-2	G7, G9
23	75	30	NP	800	HA-2	G7, G9, G18
24	75	30	NP	800	HA-2	G7
25	75	30	NP	800	HA-4	G7
26	75	30	NP	800	HA-4	G7
27	75	30	NP	800	HA-2	G7, G9
28	75	30	NP	800	HA-2	G7, G9
29	75	30	NP	800	HA-2	G7, G9, G18
30	75	30	NP	800	HA-2	G7, G9
31	75	30	NP	800	HA-2	G7, G9, G18
32	75	30	800	NP	HA-2	G7
33	90	50	600	600	HA-6	G7
34	90	50	600	NP	HA-6	G7
35	90	50	600	600	HA-6	G7
36	90	50	NP	600	HA-6	G7, G18
37	90	50	600	600	HA-6	G7
38	90	50	600	600	HA-6	G7
39	90	65	NP	600	HA-5	G13
40	90	65	NP	600	HA-5	G13
41	90	65	NP	600	HA-5	G13
42	90	65	NP	600	HA-5	G13, G18
43	90	65	NP	600	HA-5	G13
44	90	65	NP	600	HA-5	G13, G18
45	95	65	NP	600	HA-5	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
2	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
3	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
4	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
5	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
6	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
7	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
8	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
9	17.0	...	17.0	...	17.0	17.0	16.4	15.5	15.2	14.9	14.6	14.4	...	...
10	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
11	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
12	20.0	...	20.0	...	20.0	20.0	19.3	18.3	17.9	17.5	17.2	16.9	...	...
13	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
14	20.0	...	20.0	...	20.0	19.2	17.9	17.0	16.6	16.3	16.0	15.8	...	...
15	20.0	...	20.0	...	20.0	19.2	17.9	17.0	16.6	16.3	16.0	15.8	...	...
16	20.0	...	20.0	...	20.0	19.2	17.9	17.0	16.6	16.3	16.0	15.8	...	...
17	20.0	...	20.0	...	20.0	19.2	17.9	17.0	16.6	16.3	16.0	15.8	...	...
18	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
19	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
20	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
21	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
22	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
23	17.0	...	17.0	...	17.0	16.4	15.3	14.5	14.1	13.9	13.7	13.5	...	...
24	20.0	...	20.0	...	20.0	19.3	18.0	17.0	16.6	16.3	16.1	15.9	...	...
25	20.0	...	20.0	...	20.0	18.9	17.7	16.9	16.5	16.2	15.8	15.5	...	...
26	20.0	...	20.0	...	20.0	18.9	17.7	16.9	16.5	16.2	15.8	15.5	...	...
27	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
28	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
29	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
30	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
31	17.0	...	17.0	...	17.0	15.8	14.8	14.1	13.8	13.5	13.2	12.9	...	...
32	20.0	...	20.0	...	20.0	18.6	17.5	16.6	16.2	15.8	15.5	15.2	...	...
33	30.0	...	30.0	...	28.0	26.4	24.4	23.1	...	...	...	...	...	...
34	30.0	...	30.0	...	28.0	26.4	24.4	23.1	...	...	...	...	...	...
35	30.0	...	30.0	...	28.0	26.4	24.4	23.1	...	...	...	...	...	...
36	25.5	...	25.5	...	23.8	22.5	20.7	19.7	...	...	...	...	...	...
37	30.0	...	30.0	...	28.0	26.4	24.4	23.1	...	...	...	...	...	...
38	30.0	...	30.0	...	28.0	26.4	24.4	23.1	...	...	...	...	...	...
39	30.0	...	30.0	...	28.9	27.9	27.2	26.9	...	...	...	...	...	...
40	30.0	...	30.0	...	28.9	27.9	27.2	26.9	...	...	...	...	...	...
41	30.0	...	30.0	...	28.9	27.9	27.2	26.9	...	...	...	...	...	...
42	25.5	...	25.5	...	24.6	23.7	23.1	22.9	...	...	...	...	...	...
43	30.0	...	30.0	...	28.9	27.9	27.2	26.9	...	...	...	...	...	...
44	25.5	...	25.5	...	24.6	23.7	23.1	22.9	...	...	...	...	...	...
45	31.7	31.7	31.7	31.1	30.6	29.4	28.7	28.4	28.3	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S32205	...	...	10H	1
2	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S32205	...	...	10H	1
3	22Cr-5Ni-3Mo-N	Forgings	SA-182	F60	S32205	...	...	10H	1
4	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S32205	...	O.D. $\leq$ 8	10H	1
5	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S32205	...	O.D. $\leq$ 8	10H	1
6	22Cr-13Ni-5Mn	Forgings	SA-182	FXM-19	S20910	...	...	8	3
7	22Cr-13Ni-5Mn	Plate	SA-240	XM-19	S20910	...	...	8	3
8	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...	...	8	3
9	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...	...	8	3
10	22Cr-13Ni-5Mn	Wld. pipe	SA-312	TPXM-19	S20910	...	...	8	3
11	22Cr-13Ni-5Mn	Smls. pipe	SA-312	TPXM-19	S20910	...	...	8	3
12	22Cr-13Ni-5Mn	Wld. pipe	SA-312	TPXM-19	S20910	...	...	8	3
13	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	1	...	8	3
14	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	3	...	8	3
15	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	4	...	8	3
16	22Cr-13Ni-5Mn	Fittings	SA-403	XM-19	S20910	...	...	8	3
17	22Cr-13Ni-5Mn	Fittings	SA-403	XM-19	S20910	CR	...	8	3
18	22Cr-13Ni-5Mn	Wld. fittings	SA-403	XM-19	S20910	WP-W	...	8	3
19	22Cr-13Ni-5Mn	Wld. fittings	SA-403	XM-19	S20910	WP-W	...	8	3
20	22Cr-13Ni-5Mn	Wld. fittings	SA-403	XM-19	S20910	WP-WX	...	8	3
21	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	...	...	8	3
22	22Cr-13Ni-5Mn	Wld. pipe	SA-813	TPXM-19	S20910	...	...	8	3
23	22Cr-13Ni-5Mn	Wld. pipe	SA-814	TPXM-19	S20910	...	...	8	3
24	22Cr-13Ni-5Mn	Forgings	SA-965	FXM-19	S20910	...	...	8	3
25	23Cr-4Ni-Mo-Cu	Plate	SA-240	...	S32304	...	...	10H	1
26	23Cr-12Ni	Fittings	SA-403	309	S30900	...	...	8	2
27	23Cr-12Ni	Fittings	SA-403	309	S30900	...	...	8	2
28	23Cr-12Ni	Fittings	SA-403	309	S30900	WP-S	...	8	2
29	23Cr-12Ni	Wld. fittings	SA-403	309	S30900	WP-W	...	8	2
30	23Cr-12Ni	Wld. fittings	SA-403	309	S30900	WP-W	...	8	2
31	23Cr-12Ni	Wld. fittings	SA-403	309	S30900	WP-WX	...	8	2
32	23Cr-12Ni	Smls. tube	SA-213	TP309S	S30908	...	...	8	2
33	23Cr-12Ni	Plate	SA-240	309S	S30908	...	...	8	2
34	23Cr-12Ni	Wld. tube	SA-249	TP309S	S30908	...	...	8	2
35	23Cr-12Ni	Smls. pipe	SA-312	TP309S	S30908	...	...	8	2
36	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...	8	2
37	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	1	...	8	2
38	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	3	...	8	2
39	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	4	...	8	2
40	23Cr-12Ni	Bar	SA-479	309S	S30908	...	...	8	2
41	23Cr-12Ni	Wld. pipe	SA-813	TP309S	S30908	...	...	8	2
42	23Cr-12Ni	Wld. pipe	SA-814	TP309S	S30908	...	...	8	2
43	23Cr-12Ni	Bar	SA/JIS G4303	SUS309S	...	...	...	8	2
44	23Cr-12Ni	Smls. tube	SA-213	TP309H	S30909	...	...	8	2
45	23Cr-12Ni	Plate	SA-240	309H	S30909	...	...	8	2

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	95	65	NP	600	HA-5	G7
2	95	65	NP	600	HA-5	G7
3	95	70	NP	600	HA-5	G7
4	95	70	NP	600	HA-5	G7
5	95	70	NP	600	HA-5	G7
6	100	55	800	800	HA-6	G7
7	100	55	800	800	HA-6	G7
8	100	55	800	NP	HA-6	G7
9	100	55	NP	800	HA-6	G7, G18
10	100	55	800	NP	HA-6	G7
11	100	55	800	800	HA-6	G7
12	100	55	NP	800	HA-6	G7, G18
13	100	55	800	NP	HA-6	G7
14	100	55	800	NP	HA-6	G7
15	100	55	800	NP	HA-6	G7
16	100	55	800	NP	HA-6	G7
17	100	55	NP	800	HA-6	G7, G18
18	100	55	800	NP	HA-6	G7
19	100	55	NP	800	HA-6	G7, G18
20	100	55	NP	800	HA-6	G7, G18
21	100	55	800	800	HA-6	G7
22	100	55	800	NP	HA-6	G7
23	100	55	800	NP	HA-6	G7
24	100	55	800	800	HA-6	G7
25	87	58	NP	600	HA-6	G7, G13
26	75	30	800	NP	HA-2	G7
27	75	30	NP	800	HA-2	G7, G18
28	75	30	NP	800	HA-2	G7
29	75	30	800	NP	HA-2	G7
30	75	30	NP	800	HA-2	G7, G18
31	75	30	NP	800	HA-2	G7, G18
32	75	30	NP	800	HA-2	G7, G9
33	75	30	NP	800	HA-2	G7, G9
34	75	30	NP	800	HA-2	G7, G18
35	75	30	NP	800	HA-2	G7, G9
36	75	30	NP	800	HA-2	G7, G9, G18
37	75	30	800	NP	HA-2	G7
38	75	30	800	NP	HA-2	G7
39	75	30	800	NP	HA-2	G7
40	75	30	800	NP	HA-2	G7
41	75	30	NP	800	HA-2	G7, G9, G18
42	75	30	NP	800	HA-2	G7, G9, G18
43	75	30	800	NP	HA-2	G7
44	75	30	NP	800	HA-2	G7
45	75	30	NP	800	HA-2	G7

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	31.7	31.7	31.7	31.1	30.6	29.4	28.7	28.4	28.3	...	...	...	...	...
2	26.9	26.9	26.9	26.4	26.0	25.0	24.4	24.1	24.1	...	...	...	...	...
3	31.7	31.7	31.7	31.1	30.6	29.4	28.7	28.4	28.3	...	...	...	...	...
4	31.7	31.7	31.7	31.1	30.6	29.4	28.7	28.4	28.3	...	...	...	...	...
5	26.9	26.9	26.9	26.4	26.0	25.0	24.4	24.1	24.1	...	...	...	...	...
6	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
7	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
8	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
9	28.3	...	26.7	...	24.5	23.1	22.0	21.2	20.9	20.6	20.3	20.0	...	...
10	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
11	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
12	28.3	...	28.2	...	26.7	25.8	25.2	24.8	24.7	24.5	24.3	24.0	...	...
13	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
14	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
15	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
16	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
17	28.3	...	28.2	...	26.7	25.8	25.2	24.8	24.7	24.5	24.3	24.0	...	...
18	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
19	28.3	...	28.2	...	26.7	25.8	25.2	24.8	24.7	24.5	24.3	24.0	...	...
20	28.3	...	28.2	...	26.7	25.8	25.2	24.8	24.7	24.5	24.3	24.0	...	...
21	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
22	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
23	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
24	33.3	...	33.1	...	31.4	30.4	29.7	29.2	29.0	28.8	28.5	28.3	...	...
25	29.0	...	28.0	...	26.2	25.3	24.9	24.5	...	...	...	...	...	...
26	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
27	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
28	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
29	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
30	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
31	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
32	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
33	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
34	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
35	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
36	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
37	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
38	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
39	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
40	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
41	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
42	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
43	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
44	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
45	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P-No.	Group No.
1	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...	...	8	2
2	23Cr-12Ni	Smls. pipe	SA-312	TP309H	S30909	...	...	8	2
3	23Cr-12Ni	Wld. pipe	SA-312	TP309H	S30909	...	...	8	2
4	23Cr-12Ni	Bar	SA-479	309H	S30909	...	...	8	2
5	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb	S30940	...	...	8	2
6	23Cr-12Ni-Cb	Plate	SA-240	309Cb	S30940	...	...	8	2
7	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb	S30940	...	...	8	2
8	23Cr-12Ni-Cb	Smls. pipe	SA-312	TP309Cb	S30940	...	...	8	2
9	23Cr-12Ni-Cb	Wld. pipe	SA-312	TP309Cb	S30940	...	...	8	2
10	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb	S30940	...	...	8	2
11	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb	S30940	...	...	8	2
12	24Cr-22Ni-6Mo-2W-Cu-N	Forgings	SA-182	F58	S31266	...	...	45	...
13	24Cr-22Ni-6Mo-2W-Cu-N	Plate	SA-240	...	S31266	...	...	45	...
14	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-358	...	S31266	...	...	45	...
15	25Cr-5Ni-3Mo-2Cu	Plate	SA-240	255	S32550	...	...	10H	1
16	25Cr-6Ni-Mo-N	Plate	SA-240	...	S31200	...	...	10H	1
17	25Cr-12Ni	Castings	SA-351	CH8	J93400	...	...	8	2
18	25Cr-12Ni	Cast pipe	SA-451	CPH8	J93400	...	...	8	2
19	25Cr-12Ni	Castings	SA-351	CH20	J93402	...	...	8	2
20	25Cr-12Ni	Cast pipe	SA-451	CPH20	J93402	...	...	8	2
21	25Cr-20Ni	Castings	SA-351	CK20	J94202	...	...	8	2
22	25Cr-20Ni	Cast pipe	SA-451	CPK20	J94202	...	...	8	2
23	25Cr-20Ni	Forgings	SA-182	F310	S31000	...	≤5	8	2
24	25Cr-20Ni	Forgings	SA-965	F310	S31000	...	...	8	2
25	25Cr-20Ni	Smls. tube	SA-213	TP310S	S31008	...	...	8	2
26	25Cr-20Ni	Plate	SA-240	310S	S31008	...	...	8	2
27	25Cr-20Ni	Wld. tube	SA-249	TP310S	S31008	...	...	8	2
28	25Cr-20Ni	Smls. pipe	SA-312	TP310S	S31008	...	...	8	2
29	25Cr-20Ni	Wld. pipe	SA-312	TP310S	S31008	...	...	8	2
30	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	1	...	8	2
31	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	3	...	8	2
32	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	4	...	8	2
33	25Cr-20Ni	Fittings	SA-403	310S	S31008	...	...	8	2
34	25Cr-20Ni	Fittings	SA-403	310S	S31008	CR	...	8	2
35	25Cr-20Ni	Fittings	SA-403	310S	S31008	WP-S	...	8	2
36	25Cr-20Ni	Wld. fittings	SA-403	310S	S31008	WP-W	...	8	2
37	25Cr-20Ni	Wld. fittings	SA-403	310S	S31008	WP-W	...	8	2
38	25Cr-20Ni	Wld. fittings	SA-403	310S	S31008	WP-WX	...	8	2
39	25Cr-20Ni	Wld. pipe	SA-813	TP310S	S31008	...	...	8	2
40	25Cr-20Ni	Wld. pipe	SA-814	TP310S	S31008	...	...	8	2
41	25Cr-20Ni	Smls. tube	SA-213	TP310H	S31009	...	...	8	2
42	25Cr-20Ni	Plate	SA-240	310H	S31009	...	...	8	2
43	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...	...	8	2
44	25Cr-20Ni	Smls. pipe	SA-312	TP310H	S31009	...	...	8	2
45	25Cr-20Ni	Wld. pipe	SA-312	TP310H	S31009	...	...	8	2

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	NP	800	HA-2	G7, G18
2	75	30	NP	800	HA-2	G7
3	75	30	NP	800	HA-2	G7, G18
4	75	30	NP	800	HA-2	G7
5	75	30	NP	800	HA-2	G7, G9
6	75	30	NP	800	HA-2	G7, G9
7	75	30	NP	800	HA-2	G7, G9, G18
8	75	30	NP	800	HA-2	G7, G9
9	75	30	NP	800	HA-2	G7, G9, G18
10	75	30	NP	800	HA-2	G7, G9, G18
11	75	30	NP	800	HA-2	G7, G9, G18
12	109	61	NP	800	HA-10	G2, G8
13	109	61	NP	800	HA-10	G2, G8
14	109	61	NP	800	HA-10	G2, G8
15	110	80	NP	500	HA-5	G7
16	100	65	NP	600	HA-5	G7, G13
17	65	28	800	800	HA-3	G7, G9, G10, G13
18	65	28	800	NP	HA-3	G7, G13
19	70	30	800	800	HA-2	G7
20	70	30	800	NP	HA-2	G7
21	65	28	800	800	HA-3	G7
22	65	28	800	NP	HA-3	G7
23	75	30	NP	800	HA-2	G7, G9, G11, G12
24	75	30	800	800	HA-2	G7, G9, G11, G12
25	75	30	NP	800	HA-2	G7, G9, G11, G12
26	75	30	NP	800	HA-2	G7, G9, G11, G12
27	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
28	75	30	NP	800	HA-2	G7, G9, G11, G12
29	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
30	75	30	800	NP	HA-2	G7
31	75	30	800	NP	HA-2	G7
32	75	30	800	NP	HA-2	G7
33	75	30	800	NP	HA-2	G7
34	75	30	NP	800	HA-2	G7, G18
35	75	30	NP	800	HA-2	G7
36	75	30	800	NP	HA-2	G7
37	75	30	NP	800	HA-2	G7, G18
38	75	30	NP	800	HA-2	G7, G18
39	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
40	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
41	75	30	NP	800	HA-2	G7
42	75	30	NP	800	HA-2	G7
43	75	30	NP	800	HA-2	G7, G18
44	75	30	NP	800	HA-2	G7
45	75	30	NP	800	HA-2	G7, G18

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
2	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
3	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
4	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
5	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
6	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
7	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
8	20.0	...	20.0	...	20.0	20.0	19.4	18.8	18.5	18.2	18.0	17.7	...	...
9	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
10	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
11	17.0	...	17.0	...	17.0	17.0	16.5	15.9	15.7	15.5	15.3	15.1	...	...
12	36.3	36.2	35.8	34.5	33.3	31.7	30.7	30.2	30.1	29.9	29.8	29.6	...	...
13	36.3	36.2	35.8	34.5	33.3	31.7	30.7	30.2	30.1	29.9	29.8	29.6	...	...
14	30.9	30.8	30.4	29.3	28.3	26.9	26.1	25.7	25.6	25.4	25.3	25.2	...	...
15	36.7	36.6	36.5	35.5	34.5	33.4	32.9	...	...	...	...	...	...	...
16	33.3	...	33.3	...	31.6	30.7	30.5	30.5	...	...	...	...	...	...
17	18.7	...	18.7	...	18.5	18.0	17.7	17.1	16.7	16.3	15.9	15.4	...	...
18	18.7	...	18.7	...	18.5	18.0	17.7	17.1	16.7	16.3	15.9	15.4	...	...
19	20.0	...	20.0	...	19.9	19.4	18.9	18.3	17.9	17.5	17.0	16.5	...	...
20	20.0	...	20.0	...	19.9	19.4	18.9	18.3	17.9	17.5	17.0	16.5	...	...
21	18.7	...	18.7	...	18.5	18.0	17.7	17.1	16.7	16.3	15.9	15.4	...	...
22	18.7	...	18.7	...	18.5	18.0	17.7	17.1	16.7	16.3	15.9	15.4	...	...
23	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
24	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
25	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
26	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
27	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
28	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
29	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
30	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
31	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
32	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
33	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
34	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
35	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
36	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
37	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
38	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
39	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
40	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
41	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
42	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
43	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
44	20.0	...	20.0	...	20.0	20.0	19.3	18.5	18.2	17.9	17.7	17.4	...	...
45	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...

INTENTIONALLY LEFT BLANK

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design/ UNS No.	Class/ Condition/ Temper	Size/Thickness, in.	P-No.	Group No.
1	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb	S31040	...	...	8	2
2	25Cr-20Ni-Cb	Wld. pipe	SA-312	TP310Cb	S31040	...	...	8	2
3	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb	S31040	...	...	8	2
4	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb	S31040	...	...	8	2
5	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN	S31050	...	...	8	2
6	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	$0.250 < t \leq 1.250$	8	2
7	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	$0.250 < t \leq 1.250$	8	2
8	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	$0.250 < t \leq 1.250$	8	2
9	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	...	8	2
10	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	≤ 0.250 , wall	8	2
11	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	≤ 0.250 , wall	8	2
12	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	≤ 0.250 , wall	8	2
13	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	$t \geq 0.40$	10H	1
14	29Cr-6.5Ni-2Mo-N	Bar	SA-479	...	S32906	...	...	10H	1
15	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	$t \geq 0.40$	10H	1
16	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	$t \geq 0.40$	10H	1
17	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	$t < 0.40$	10H	1
18	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	$t < 0.40$	10H	1
19	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	$t < 0.40$	10H	1

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
2	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
3	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
4	75	30	NP	800	HA-2	G7, G9, G11, G12, G18
5	78	37	NP	800	HA-2	G7
6	78	37	NP	800	HA-2	...
7	78	37	NP	800	HA-2	G18
8	78	37	NP	800	HA-2	G18
9	80	35	NP	600	HA-2	...
10	84	39	NP	800	HA-2	...
11	84	39	NP	800	HA-2	G18
12	84	39	NP	800	HA-2	G18
13	109	80	NP	600	HA-5	G8
14	109	80	NP	600	HA-5	G8
15	109	80	NP	600	HA-5	G8
16	109	80	NP	600	HA-5	G8
17	116	94	NP	600	HA-5	G8
18	116	94	NP	600	HA-5	G8
19	116	94	NP	600	HA-5	G8

Table 2A (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Ferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
	100	150	200	250	300	400	500	600	650	700	750	800	850	900
1	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
2	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
3	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
4	17.0	...	17.0	...	17.0	17.0	16.4	15.7	15.5	15.2	15.0	14.8	...	...
5	24.7	...	24.7	...	24.3	23.4	22.7	21.5	21.0	20.4	19.9	19.4	...	...
6	24.7	...	24.7	...	24.3	23.4	22.7	21.5	21.0	20.4	19.9	19.4	...	...
7	21.0	...	21.0	...	20.7	19.9	19.3	18.3	17.8	17.4	16.9	16.5	...	...
8	21.0	...	21.0	...	20.7	19.9	19.3	18.3	17.8	17.4	16.9	16.5	...	...
9	23.3	...	23.3	...	23.3	22.7	21.4	20.3	...	...	...	...	...	...
10	26.0	...	26.0	...	26.0	25.2	23.9	22.7	22.1	21.5	21.0	20.5	...	...
11	22.1	...	22.1	...	22.1	21.4	20.3	19.3	18.8	18.3	17.8	17.4	...	...
12	22.1	...	22.1	...	22.1	21.4	20.3	19.3	18.8	18.3	17.8	17.4	...	...
13	36.3	36.3	36.3	35.4	34.5	33.5	33.0	33.0	...	...	...	...	...	...
14	36.3	36.3	36.3	35.4	34.5	33.5	33.0	33.0	...	...	...	...	...	...
15	36.3	36.3	36.3	35.4	34.5	33.5	33.0	33.0	...	...	...	...	...	...
16	36.3	36.3	36.3	35.4	34.5	33.5	33.0	33.0	...	...	...	...	...	...
17	38.7	38.7	38.6	37.7	36.8	35.6	35.2	35.2	...	...	...	...	...	...
18	38.7	38.7	38.6	37.7	36.8	35.6	35.2	35.2	...	...	...	...	...	...
19	38.7	38.7	38.6	37.7	36.8	35.6	35.2	35.2	...	...	...	...	...	...

NOTES TO TABLE 2A**GENERAL NOTES**

- (25) (a) The following abbreviations are used: N, Normalized; NT, Normalized and tempered; QT, Quenched and tempered; Smls., Seamless; Temp., Temperature; and Wld., Welded.
- (b) An alternative typeface is used for stress values based on successful experience in service (see Notes E1 through E4).
- (c) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-516/SA-516M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-516 Grade 70 shall be used when SA-516M Grade 485 is used in construction.
- (d) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (e) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (f) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES - EXPERIENCE CRITERION

- E1 For values at 650°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E2 For values at 700°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E3 For values at 850°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- (25) E4 For values at 900°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.

NOTES - GENERAL REQUIREMENTS

- G1 Material that conforms to Class 10, 13, 20, 23, 30, 33, 40, 43, 50, or 53 is not permitted.
- G2 Material that conforms to Class 11 or 12 is not permitted.
- G3 Material that conforms to Class 11 or 12 is not permitted when the nominal thickness of the material exceeds $\frac{3}{4}$ in.
- G4 Material that conforms to Class 11 or 12 is not permitted when the nominal thickness of the material exceeds $1\frac{1}{4}$ in.
- G5 For Section III applications, a product analysis is required on this material.
- G6 SA-723 shall not be used for minimum permissible temperature below +40°F.
- G7 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed 66 $\frac{2}{3}$ % but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G8 This material has reduced toughness at room temperature after exposure at high temperature. The degree of embrittlement depends on composition, heat treatment, time, and temperature. The lowest temperature of concern is about 500°F. See Nonmandatory Appendix A, A-207.
- G9 At temperatures over 1000°F, these stress values apply only when the carbon is 0.04% or higher. This note is applicable only when stresses above 1000°F are published.
- G10 For temperatures above 1000°F, these stress values may be used only if the material has been heat treated by heating to a minimum temperature of 1900°F and quenching in water or rapidly cooling by other means. This note is applicable only when stresses above 1000°F are published.
- G11 These stress values at temperatures of 1050°F and above should be used only when assurance is provided that the steel has a predominant grain size not finer than ASTM No. 6. This note is applicable only when stresses above 1000°F are published.
- G12 These stress values shall be considered basic values to be used when no effort is made to control or check the grain size of the steel.
- G13 This steel may be expected to develop embrittlement after service at moderately elevated temperature; see Nonmandatory Appendix A, A-207 and A-208.
- G14 All forgings shall have a maximum tensile strength not in excess of 25 ksi above the specified minimum.
- G15 Fabricated from SA-387 Grade 12 Class 1 plate.
- G16 Fabricated from SA-387 Grade 12 Class 2 plate.
- G17 A factor of 4 was used for tensile strength to obtain the stress value.
- G18 A quality factor of 0.85 has been applied in arriving at the stress values for this material.
- G19 The tensile strength shall not be in excess of 20,000 psi above the specified minimum.
- G20 For Section VIII applications, SA-723 is exempt from the requirement in Section VIII, Division 2, 6.7.6.3(b) that the average of the individual Brinell hardness numbers shall not be more than 10% below or 25% above the number corresponding to the tensile strength.
- G21 See Section VIII, Division 2, 3.4.
- (25) G22 Use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.

NOTES TO TABLE 2A (CONT'D)**NOTES – GENERAL REQUIREMENTS (CONT'D)**

- (25) G23 Stress values for 100°F may be used at temperatures down to -325°F without additional specification requirements.

NOTES – HEAT TREATMENT REQUIREMENTS

H1 Annealed.

H2 Quenched and tempered at 1200°F.

H3 For Section III applications, pieces that are formed (after quenching and tempering) at a temperature lower than 25°F below the final tempering temperature shall be heat treated after forming when the extreme fiber strain from forming exceeds 3%. Heat treatment shall be 1075°F minimum, but not higher than 25°F below the final tempering temperature for a minimum time of 1 hr per inch of thickness. Pieces formed at temperatures within 25°F higher than the original tempering temperature shall be requenched and tempered, either before or after welding into the vessel.

H4 Liquid quenched and tempered.

H5 Normalized, normalized and tempered, or quenched and tempered.

H6 For Section VIII applications involving consideration of heat treatment after forming or welding, see Section VIII, Division 2, Table 6.15 for P-No. 10K, Group No. 1 materials.

NOTES – SIZE REQUIREMENTS

S1 The maximum thickness of forgings shall not exceed $3\frac{3}{4}$ in. (4 in. as heat treated).

S2 Both NPS 8 and larger, and schedule 140 and heavier.

S3 The minimum thickness of pressure-retaining parts shall be $\frac{1}{4}$ in.

S4 For Section III applications, the minimum thickness of shells, heads, and other pressure-retaining parts shall be $\frac{1}{4}$ in. The maximum thickness shall be limited only by the ability to develop the specified mechanical properties.

S5 Either NPS 8 and larger and less than schedule 140 wall, or less than NPS 8 and all wall thicknesses.

S6 The maximum section thickness shall not exceed 3 in. for double-normalized-and-tempered forgings, or 5 in. for quenched-and-tempered forgings.

NOTES – WELDING REQUIREMENTS

W1 Not for welded construction.

W2 In welded construction, for temperatures above 850°F, the weld metal shall have a carbon content of greater than 0.05%.

W3 The following, in addition to the variables in Section IX, QW-250, shall be considered as essential variables requiring requalification of the welding procedure:

(a) An increase in the maximum or a decrease in the minimum specified preheat or interpass temperatures. The specified range of preheat temperatures shall not exceed 150°F.

(b) A change in the thickness T of the welding procedure qualification test plate as follows:

(1) For welded joints that are quenched and tempered after welding, any increase in thickness (the minimum thickness qualified in all cases is $\frac{1}{4}$ in.).

(2) For welded joints that are not quenched and tempered after welding, any change as follows:

(-a) for T less than $\frac{5}{8}$ in., any decrease in thickness (the maximum thickness qualified is $2T$);

(-b) for T equal to $\frac{5}{8}$ in. and over, any departure from the range of $\frac{5}{8}$ in. to $2T$.

W4 Welded, with the tensile strength of the Section IX reduced section tension test less than 100 ksi but not less than 95 ksi.

W5 For Section VIII applications, welding not permitted when carbon content exceeds 0.35% by ladle analysis except for limited types of welding, as allowed in Section VIII, Division 2, Part 6.

W6 For Section VIII applications, Section IX, QW-250 Variables QW-404.12, QW-406.3, QW-407.2, and QW-409.1 shall also apply to this material. These variables shall be applied in accordance with the rules for welding of Section VIII, Division 2, Part 6.

W7 Nonwelded, or welded if the tensile strength of the Section IX reduced section tension test is not less than 100 ksi.

- (25) W8 Not for welded construction in Section III.

INTENTIONALLY LEFT BLANK

Table 2B
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P.No.
1	...	Drawn smls. tube	SB-210	...	Alclad 3003	O	0.010–0.500	21
2	...	Drawn smls. tube	SB-210	...	Alclad 3003	H113	0.050–0.500	21
3	...	Smls. extr. tube	SB-241	...	Alclad 3003	O	...	21
4	...	Smls. extr. tube	SB-241	...	Alclad 3003	H112	...	21
5	...	Plate, sheet	SB-209	...	A93003	O	0.006–3.000	21
6	...	Plate, sheet	SB-209	...	A93003	H112	0.250–0.499	21
7	...	Plate, sheet	SB-209	...	A93003	H112	0.500–2.000	21
8	...	Plate, sheet	SB-209	...	A93003	H112	2.001–3.000	21
9	...	Drawn smls. tube	SB-210	...	A93003	O	0.010–0.500	21
10	...	Drawn smls. tube	SB-210	...	A93003	H113	0.010–0.500	21
11	...	Bar, rod, shapes	SB-221	...	A93003	O	...	21
12	...	Bar, rod, shapes	SB-221	...	A93003	H112	...	21
13	...	Smls. extr. tube	SB-241	...	A93003	O	...	21
14	...	Smls. pipe	SB-241	...	A93003	H112	≥1.000	21
15	...	Smls. extr. tube	SB-241	...	A93003	H112	...	21
16	...	Plate, sheet	SB-209	...	A93004	O	0.006–3.000	22
17	...	Plate, sheet	SB-209	...	A93004	H112	0.250–3.000	22
18	...	Plate, sheet	SB-209	...	A95052	O	0.051–3.000	22
19	...	Plate, sheet	SB-209	...	A95052	H112	0.250–0.499	22
20	...	Plate, sheet	SB-209	...	A95052	H112	0.500–3.000	22
21	...	Plate, sheet	SB-209	...	A95083	O	0.051–1.500	25
22	...	Plate, sheet	SB-209	...	A95083	O	1.501–3.000	25
23	...	Plate, sheet	SB-209	...	A95083	O	3.001–5.000	25
24	...	Plate, sheet	SB-209	...	A95083	O	5.001–7.000	25
25	...	Plate, sheet	SB-209	...	A95083	O	7.001–8.000	25
26	...	Plate, sheet	SB-209	...	A95083	H112	0.250–1.500	25
27	...	Plate, sheet	SB-209	...	A95083	H112	1.501–3.000	25
28	...	Bar, rod, shapes	SB-221	...	A95083	H111	≤5.000	25
29	...	Smls. extr. tube	SB-241	...	A95083	H111	...	25
30	...	Plate, sheet	SB-209	...	A95086	O	0.051–2.000	25
31	...	Plate, sheet	SB-209	...	A95086	H112	0.063–0.499	25
32	...	Plate, sheet	SB-209	...	A95086	H112	0.500–1.000	25
33	...	Plate, sheet	SB-209	...	A95086	H112	1.001–2.000	25
34	...	Plate, sheet	SB-209	...	A95086	H112	2.001–3.000	25
35	...	Plate, sheet	SB-209	...	A95454	O	0.051–3.000	22
36	...	Plate, sheet	SB-209	...	A95454	H112	0.250–0.499	22
37	...	Plate, sheet	SB-209	...	A95454	H112	0.500–3.000	22
38	...	Bar, rod, shapes	SB-221	...	A95454	O	≤5.000	22
39	...	Bar, rod, shapes	SB-221	...	A95454	H112	≤5.000	22
40	...	Smls. extr. tube	SB-241	...	A95454	O	≤5.000	22
41	...	Smls. extr. tube	SB-241	...	A95454	H112	≤5.000	22
42	...	Plate, sheet	SB-209	...	A96061	T4	0.051–0.249	23
43	...	Plate, sheet	SB-209	...	A96061	T451	0.250–3.000	23
44	...	Plate, sheet	SB-209	...	A96061	T6	0.051–0.249	23
45	...	Plate, sheet	SB-209	...	A96061	T651	0.250–4.000	23

Table 2B
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	13	4.5	NP	250	NFA-7	G8
2	13	4.5	NP	250	NFA-7	G8, W2
3	13	4.5	NP	250	NFA-7	G8
4	13	4.5	NP	250	NFA-7	G8, W2
5	14	5	NP	250	NFA-1	G8
6	17	10	NP	250	NFA-1	G8, W2
7	15	6	NP	200	NFA-1	G8, W2
8	14.5	6	NP	200	NFA-1	G8, W2
9	14	5	NP	250	NFA-1	G8
10	14	5	NP	250	NFA-1	G8, W2
11	14	5	NP	250	NFA-1	G2, G8
12	14	5	NP	250	NFA-1	G2, G8, W2
13	14	5	NP	250	NFA-1	G8
14	14	5	NP	250	NFA-1	G8
15	14	5	NP	250	NFA-1	G8, W2
16	22	8.5	NP	250	NFA-3	G8
17	23	9	NP	250	NFA-3	G8, W2
18	25	9.5	NP	200	NFA-8	G8
19	28	16	NP	200	NFA-8	G8, W2
20	25	9.5	NP	200	NFA-8	G8, W2
21	40	18	NP	150	NFA-11	G7, G8
22	39	17	NP	150	NFA-11	G7, G8
23	38	16	NP	150	NFA-11	G7, G8
24	37	15	NP	150	NFA-11	G7, G8
25	36	14	NP	150	NFA-11	G7, G8
26	40	18	NP	150	NFA-11	G7, G8, W2
27	39	17	NP	150	NFA-11	G7, G8, W2
28	40	24	NP	150	NFA-11	G2, G7, G8, W2
29	40	24	NP	150	NFA-11	G7, G8, W2
30	35	14	NP	150	NFA-9	G7, G8
31	36	18	NP	150	NFA-9	G7, G8, W2
32	35	16	NP	150	NFA-9	G7, G8, W2
33	35	14	NP	150	NFA-9	G7, G8, W2
34	34	14	NP	150	NFA-9	G7, G8, W2
35	31	12	NP	250	NFA-6	E2, G8
36	32	18	NP	250	NFA-6	E2, G8, W2
37	31	12	NP	250	NFA-6	E2, G8, W2
38	31	12	NP	250	NFA-6	E2, G2, G8
39	31	12	NP	250	NFA-6	E2, G2, G8, W2
40	31	12	NP	250	NFA-6	E2, G8
41	31	12	NP	250	NFA-6	E2, G8, W2
42	30	16	NP	300	NFA-13	G8, G9, W3
43	30	16	NP	300	NFA-13	G8, G9, W3
44	42	35	NP	300	NFA-12	G8, G9, W3
45	42	35	NP	300	NFA-12,13	G8, G9, W3

Table 2B
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	3.0	3.0	3.0	2.7	...	...	...	...	...	...	...	...	...	...	...
2	3.0	3.0	3.0	2.7	...	...	...	...	...	...	...	...	...	...	...
3	3.0	3.0	3.0	2.7	...	...	...	...	...	...	...	...	...	...	...
4	3.0	3.0	3.0	2.7	...	...	...	...	...	...	...	...	...	...	...
5	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
6	5.7	5.7	5.7	5.3	...	...	...	...	...	...	...	...	...	...	...
7	4.0	4.0	4.0	...	...	...	...	...	...	...	...	...	...	...	...
8	4.0	4.0	4.0	...	...	...	...	...	...	...	...	...	...	...	...
9	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
10	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
11	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
12	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
13	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
14	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
15	3.3	3.3	3.3	3.0	...	...	...	...	...	...	...	...	...	...	...
16	5.7	5.7	5.7	5.5	...	...	...	...	...	...	...	...	...	...	...
17	6.0	6.0	6.0	5.8	...	...	...	...	...	...	...	...	...	...	...
18	6.3	6.3	6.3	...	...	...	...	...	...	...	...	...	...	...	...
19	9.3	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...
20	6.3	6.3	6.3	...	...	...	...	...	...	...	...	...	...	...	...
21	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...
22	11.4	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...
23	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...
24	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...
25	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...
26	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...
27	11.3	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...
28	13.3	13.3	...	...	...	...	...	...	...	...	...	...	...	...	...
29	13.3	13.3	...	...	...	...	...	...	...	...	...	...	...	...	...
30	9.3	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...
31	12.0	11.8	...	...	...	...	...	...	...	...	...	...	...	...	...
32	10.7	10.5	...	...	...	...	...	...	...	...	...	...	...	...	...
33	9.3	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...
34	9.3	9.1	...	...	...	...	...	...	...	...	...	...	...	...	...
35	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
36	10.7	10.7	10.7	7.5	...	...	...	...	...	...	...	...	...	...	...
37	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
38	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
39	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
40	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
41	8.0	8.0	8.0	7.5	...	...	...	...	...	...	...	...	...	...	...
42	10.0	10.0	10.0	8.6	8.1	...	...	...	...	...	...	...	...	...	...
43	10.0	10.0	10.0	8.6	8.1	...	...	...	...	...	...	...	...	...	...
44	14.0	14.0	14.0	13.4	11.3	...	...	...	...	...	...	...	...	...	...
45	14.0	14.0	14.0	13.4	11.3	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P.No.
1	...	Plate, sheet	SB-209	...	A96061	T651	4.001–6.000	23
2	...	Drawn smls. tube	SB-210	...	A96061	T4	0.025–0.500	23
3	...	Drawn smls. tube	SB-210	...	A96061	T6	0.025–0.500	23
4	...	Bar, rod, shapes	SB-221	...	A96061	T4	...	23
5	...	Bar, rod, shapes	SB-221	...	A96061	T6	...	23
6	...	Smls. extr. tube/pipe	SB-241	...	A96061	T4	...	23
7	...	Smls. extr. tube/pipe	SB-241	...	A96061	T6	...	23
8	...	Smls. drawn pipe	SB-241	...	A96061	T6	<1 NPS	23
9	...	Smls. drawn pipe	SB-241	...	A96061	T6	≥1 NPS	23
10	...	Shapes	SB-308	...	A96061	T6	...	23
(25) 11	...	Die forgings	SB-247	...	A96061	T6	≤4.000	23
(25) 12	...	Hand forgings	SB-247	...	A96061	T6	≤4.000	23
(25) 13	...	Hand forgings	SB-247	...	A96061	T6	4.001–8.000	23
(25) 14	...	Die & hand forgings	SB-247	...	A96061	T6 wld.	≤8.000	23
15	...	Drawn smls. tube	SB-210	...	A96063	T6	0.025–0.500	23
16	...	Bar, rod, shapes	SB-221	...	A96063	T5	≤0.500	23
17	...	Bar, rod, shapes	SB-221	...	A96063	T5	0.501–1.000	23
18	...	Bar, rod, shapes	SB-221	...	A96063	T6	≤1.000	23
19	...	Smls. extr. tube	SB-241	...	A96063	T5	≤0.500	23
20	...	Smls. extr. tube	SB-241	...	A96063	T5	0.501–1.000	23
21	...	Smls. extr. tube	SB-241	...	A96063	T6	≤1.000	23
(25) 22	...	Bar, rod	SB-187	...	C10200	O60	All	31
(25) 23	...	Bar, rod	SB-187	...	C10200	O60	All	31
(25) 24	...	Bar, rod	SB-187	...	C11000	O60	All	31
(25) 25	...	Bar, rod	SB-187	...	C11000	O60	All	31
26	...	Smls. tube	SB-111	...	C28000	O61	...	32
(25) 27	...	Smls. tube	SB-111	...	C44300	O61	...	32
(25) 28	...	Smls. tube	SB-111	...	C44400	O61	...	32
(25) 29	...	Smls. tube	SB-111	...	C44500	O61	...	32
30	...	Plate	SB-171	...	C46400	M10, M20, O20, O25	$3 < t \leq 5$	32
(25) 31	...	Plate, sheet	SB-171	...	C46400	M10, M20, O20, O25	≤3	32
(25) 32	...	Smls. tube	SB-111	...	C60800	O61	...	35
(25) 33	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$2 < t \leq 5$	35
(25) 34	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$2 < t \leq 5$	35
(25) 35	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$\frac{1}{2} < t \leq 2$	35
(25) 36	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$\frac{1}{2} < t \leq 2$	35
(25) 37	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$t \leq \frac{1}{2}$	35
(25) 38	...	Plate, sheet, bar	SB-169	...	C61400	O25, O60, M20	$t \leq \frac{1}{2}$	35
(25) 39	...	Bar, rod	SB-98	...	C65100	O60	All	33
(25) 40	...	Bar, rod	SB-98	...	C65100	O60	All	33
(25) 41	...	Bar, rod	SB-98	...	C65100	H02	≤2	33
42	...	Bar, rod	SB-98	...	C65100	H02	≤2	33
(25) 43	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61	≤2	33
(25) 44	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61	≤2	33
45	...	Bar, rod	SB-98	...	C65500	O60	All	33

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	40	35	NP	300	NFA-12,13	G8, G9, W3
2	30	16	NP	300	NFA-13	G8, W3
3	42	35	NP	300	NFA-12,13	G8, W3
4	26	16	NP	300	NFA-13	G2, G8, G9, W3
5	38	35	NP	300	NFA-12,13	G2, G8, G9, W3
6	26	16	NP	300	NFA-13	G8, G9, W3
7	38	35	NP	300	NFA-12,13	G8, G9, W3
8	42	35	NP	300	NFA-12,13	G8, W3
9	38	35	NP	300	NFA-12,13	G8, W3
10	38	35	NP	300	NFA-12,13	G2, G8, W3
11	38	35	NP	300	NFA-12,13	G8, W3
12	37	33	NP	300	NFA-12,13	G8, W3
13	35	32	NP	300	NFA-12,13	G8, W3
14	24	...	NP	300	NFA-12,13	G8
15	33	28	NP	300	NFA-1	G8, W3
16	22	16	NP	300	NFA-1	E2, G2, G8, W3
17	21	15	NP	300	NFA-1	E2, G2, G8, W3
18	30	25	NP	300	NFA-1	G2, G8, W3
19	22	16	NP	300	NFA-1	E2, G8, W3
20	21	15	NP	300	NFA-1	E2, G8, W3
21	30	25	NP	300	NFA-1	G8, W3
22	28	8	NP	300	NFC-1	G4
23	28	8	NP	300	NFC-1	G1, G4
24	28	8	NP	300	NFC-1	G4
25	28	8	NP	300	NFC-1	G1, G4
26	50	20	NP	500	NFC-3	E5, G4, G6
27	45	15	NP	500	NFC-2	E3, G4, G6
28	45	15	NP	500	NFC-2	E3, G4, G6
29	45	15	NP	500	NFC-2	E3, G4, G6
30	50	18	NP	100	NFC-2	G4
31	50	20	NP	100	NFC-2	G4
32	50	19	NP	100	NFC-2	G4, G6
33	65	28	NP	500	NFC-8	G4
34	65	28	NP	500	NFC-8	G1, G4
35	70	30	NP	500	NFC-8	G4
36	70	30	NP	500	NFC-8	G1, G4
37	72	32	NP	500	NFC-8	G4
38	72	32	NP	500	NFC-8	G1, G4
39	40	12	NP	350	NFC-1	G4, G10
40	40	12	NP	350	NFC-1	G1, G4, G10
41	55	20	NP	350	NFC-2	G4, G10, W2
42	55	20	NP	350	NFC-2	G1, G4, G10, W2
43	50	18	NP	300	NFC-2	G4, G10
44	50	18	NP	300	NFC-2	G1, G4, G10
45	52	15	NP	350	NFC-2	G4, G10

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	13.3	13.3	13.3	12.8	10.8	...	...	...	...	...	...	...	...	...	...
2	10.0	10.0	10.0	8.6	8.1	...	...	...	...	...	...	...	...	...	...
3	14.0	14.0	14.0	13.4	11.3	...	...	...	...	...	...	...	...	...	...
4	8.7	8.7	8.7	8.5	8.0	...	...	...	...	...	...	...	...	...	...
5	12.7	12.7	12.7	12.1	10.2	...	...	...	...	...	...	...	...	...	...
6	8.7	8.7	8.7	8.5	8.0	...	...	...	...	...	...	...	...	...	...
7	12.7	12.7	12.7	12.1	10.2	...	...	...	...	...	...	...	...	...	...
8	14.0	14.0	14.0	13.4	11.3	...	...	...	...	...	...	...	...	...	...
9	12.7	12.7	12.7	12.1	10.2	...	...	...	...	...	...	...	...	...	...
10	12.7	12.7	12.7	12.1	10.2	...	...	...	...	...	...	...	...	...	...
11	12.7	12.7	12.7	12.1	10.2	...	...	...	...	...	...	...	...	...	(25)
12	12.3	12.3	12.3	11.8	10.1	...	...	...	...	...	...	...	...	...	(25)
13	11.7	11.7	11.7	11.1	9.6	...	...	...	...	...	...	...	...	...	(25)
14	8.0	8.0	8.0	7.9	7.3	...	...	...	...	...	...	...	...	...	(25)
15	11.0	11.0	11.0	8.7	6.4	...	...	...	...	...	...	...	...	...	...
16	7.3	7.3	7.3	5.1	4.6	...	...	...	...	...	...	...	...	...	...
17	7.0	7.0	7.0	4.9	4.4	...	...	...	...	...	...	...	...	...	...
18	10.0	10.0	10.0	7.9	5.8	...	...	...	...	...	...	...	...	...	...
19	7.3	7.3	7.3	5.1	4.6	...	...	...	...	...	...	...	...	...	...
20	7.0	7.0	7.0	4.9	4.4	...	...	...	...	...	...	...	...	...	...
21	10.0	10.0	10.0	7.9	5.8	...	...	...	...	...	...	...	...	...	...
22	5.3	4.7	4.7	4.7	4.7	...	...	...	...	...	...	...	...	...	(25)
23	5.3	5.3	5.3	5.3	5.3	...	...	...	...	...	...	...	...	...	(25)
24	5.3	4.7	4.7	4.7	4.7	...	...	...	...	...	...	...	...	...	(25)
25	5.3	5.3	5.3	5.3	5.3	...	...	...	...	...	...	...	...	...	(25)
26	13.3	13.3	13.3	13.3	13.3	10.8	5.3	2.0	1.0	...	...	...	...	...	...
27	10.0	10.0	10.0	10.0	10.0	10.0	3.5	2.0	1.0	...	...	...	...	...	(25)
28	10.0	10.0	10.0	10.0	10.0	10.0	3.5	2.0	1.0	...	...	...	...	...	(25)
29	10.0	10.0	10.0	10.0	10.0	10.0	3.5	2.0	1.0	...	...	...	...	...	(25)
30	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	13.3	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	12.7	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	18.7	18.6	18.5	18.3	18.3	18.1	17.9	17.7	17.5	...	...	...	...	...	(25)
34	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	...	...	...	...	...	(25)
35	20.0	19.9	19.8	19.7	19.5	19.4	19.2	19.0	18.8	...	...	...	...	...	(25)
36	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	...	...	...	...	...	(25)
37	21.3	21.3	21.1	20.9	20.9	20.7	20.5	20.3	20.1	...	...	...	...	...	(25)
38	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	...	...	...	...	...	(25)
39	8.0	7.9	7.9	7.8	7.8	7.7	...	...	...	...	...	...	...	...	(25)
40	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...	...	...	(25)
41	13.3	13.3	13.2	12.9	12.5	12.0	...	...	...	...	...	...	...	...	(25)
42	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...	...	...	...	...
43	12.0	12.0	11.9	11.9	11.9	...	...	...	...	...	...	...	...	...	(25)
44	12.0	12.0	12.0	12.0	12.0	...	...	...	...	...	...	...	...	...	(25)
45	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P.No.
1	...	Bar, rod	SB-98	...	C65500	O60	All	33
2	...	Bar, rod	SB-98	...	C65500	H02	≤ 2	33
3	...	Bar, rod	SB-98	...	C66100	O60	All	33
4	...	Bar, rod	SB-98	...	C66100	O60	All	33
5	...	Bar, rod	SB-98	...	C66100	H02	≤ 2	33
6	...	Plate	SB-171	...	C70600	M10, M20, O20, O25	≤ 5	34
7	...	Plate	SB-171	...	C70600	M10, M20, O20, O25	≤ 5	34
8	...	Cond. tube	SB-111	...	C70600	O61	...	34
9	...	Cond. tube	SB-111	...	C70600	O61	...	34
10	...	Smls. U-bend tube	SB-395	...	C70600	O61	...	34
11	...	Smls. U-bend tube	SB-395	...	C70600	O61	...	34
12	...	Plate	SB-171	...	C70620	M10, M20, O20, O25	≤ 5	34
13	...	Plate	SB-171	...	C70620	M10, M20, O20, O25	≤ 5	34
14	...	Cond. tube	SB-111	...	C70620	O61	...	34
15	...	Cond. tube	SB-111	...	C70620	O61	...	34
16	...	Smls. U-bend tube	SB-395	...	C70620	O61	...	34
17	...	Smls. U-bend tube	SB-395	...	C70620	O61	...	34
18	...	Plate	SB-171	...	C71500	M10, M20, O20, O25	$2\frac{1}{2} < t \leq 5$	34
19	...	Plate	SB-171	...	C71500	M10, M20, O20, O25	$2\frac{1}{2} < t \leq 5$	34
20	...	Plate	SB-171	...	C71500	M10, M20, O20, O25	$\leq 2\frac{1}{2}$	34
21	...	Plate	SB-171	...	C71500	M10, M20, O20, O25	$\leq 2\frac{1}{2}$	34
22	...	Cond. tube	SB-111	...	C71500	O61	...	34
23	...	Cond. tube	SB-111	...	C71500	O61	...	34
24	...	Smls. U-bend tube	SB-395	...	C71500	O61	...	34
25	...	Smls. U-bend tube	SB-395	...	C71500	O61	...	34
(25) 26	...	Smls. tube	SB-111	...	C71500	HR50	...	34
27	...	Plate	SB-171	...	C71520	M10, M20, O20, O25	$2\frac{1}{2} < t \leq 5$	34
28	...	Plate	SB-171	...	C71520	M10, M20, O20, O25	$2\frac{1}{2} < t \leq 5$	34
29	...	Plate	SB-171	...	C71520	M10, M20, O20, O25	$\leq 2\frac{1}{2}$	34
30	...	Plate	SB-171	...	C71520	M10, M20, O20, O25	$\leq 2\frac{1}{2}$	34
31	...	Smls. tube	SB-111	...	C71520	O61	...	34
32	...	Smls. tube	SB-111	...	C71520	O61	...	34
33	...	Smls. U-bend tube	SB-395	...	C71520	O61	...	34
34	...	Smls. U-bend tube	SB-395	...	C71520	O61	...	34
35	...	Smls. tube	SB-111	...	C71520	HR50	...	34
(25) 36	...	Castings	SB-584	...	C93700	M01	...	...
(25) 37	...	Castings	SB-584	...	C93700	M01	...	...
38	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed	> 5 O.D.	41
39	99Ni	Bar, rod	SB-160	...	N02200	Annealed	...	41
40	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed	≤ 5 O.D.	41
41	99Ni	Plate, sheet, strip	SB-162	...	N02200	Annealed	...	41
42	99Ni	Smls. tube	SB-163	...	N02200	Annealed	...	41
43	99Ni	Plate, sheet, strip	SB-162	...	N02200	As rolled	...	41
44	99Ni-Low C	Bar, rod	SB-160	...	N02201	Annealed	...	41
45	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed	> 5 O.D.	41

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	52	15	NP	350	NFC-2	G1, G4, G10
2	70	38	NP	350	NFC-2	G4, G10, W2
3	52	15	NP	350	NFC-2	G4, G10
4	52	15	NP	350	NFC-2	G1, G4, G10
5	70	38	NP	350	NFC-2	G4, G10, W2
6	40	15	NP	450	NFC-3	G4
7	40	15	NP	450	NFC-3	G1, G4
8	40	15	NP	450	NFC-3	G4
9	40	15	NP	450	NFC-3	G1, G4
10	40	15	NP	450	NFC-3	G4
11	40	15	NP	450	NFC-3	G1, G4
12	40	15	NP	450	NFC-3	G4
13	40	15	NP	450	NFC-3	G1, G4
14	40	15	NP	450	NFC-3	G4
15	40	15	NP	450	NFC-3	G1, G4
16	40	15	NP	450	NFC-3	G4
17	40	15	NP	450	NFC-3	G1, G4
18	45	18	500	650	NFC-4	G4
19	45	18	500	650	NFC-4	G1, G4
20	50	20	500	650	NFC-4	G4
21	50	20	500	650	NFC-4	G1, G4
22	52	18	500	650	NFC-4	G4
23	52	18	500	650	NFC-4	G1, G4
24	52	18	NP	650	NFC-4	G4
25	52	18	NP	650	NFC-4	G1, G4
26	72	50	500	500	NFC-4	...
27	45	18	500	650	NFC-4	G4
28	45	18	500	650	NFC-4	G1, G4
29	50	20	500	650	NFC-4	G4
30	50	20	500	650	NFC-4	G1, G4
31	52	18	500	650	NFC-4	G4
32	52	18	500	650	NFC-4	G1, G4
33	52	18	NP	650	NFC-4	G4
34	52	18	NP	650	NFC-4	G1, G4
35	72	50	500	500	NFC-4	...
36	30	12	400 (SPT)	NP	NFC-1	...
37	30	12	400 (SPT)	NP	NFC-1	G1
38	55	12	NP	600	NFN-2	G4
39	55	15	NP	600	NFN-2	G2, G4
40	55	15	NP	600	NFN-2	G4
41	55	15	NP	600	NFN-2	G4
42	55	15	NP	600	NFN-2	G4
43	55	20	NP	600	NFN-2	G4
44	50	10	NP	800	NFN-1	G2, G4
45	50	10	NP	800	NFN-1	G4

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...
2	23.3	23.3	23.3	23.3	23.3	23.2	...	...	...	...	...	...	...	...	...
3	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...
4	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...
5	23.3	23.3	23.3	23.3	23.3	23.2	...	...	...	...	...	...	...	...	...
6	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
7	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
8	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
9	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
10	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
11	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
12	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
13	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
14	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
15	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
16	10.0	9.7	9.5	9.3	9.0	8.8	8.7	8.5	...	...	...	...	...	...	...
17	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...
18	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
19	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
20	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	...	...	...
21	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...
22	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
23	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
24	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
25	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
26	24.0	24.0	24.0	24.0	24.0	23.7	23.3	23.0	22.7	...	...	...	...	...	...
27	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
28	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
29	13.3	12.9	12.6	12.3	12.0	11.7	11.5	11.2	11.0	10.8	10.7	10.6	...	...	...
30	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...
31	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
32	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
33	12.0	11.6	11.3	11.0	10.8	10.5	10.3	10.1	9.9	9.8	9.6	9.5	...	...	...
34	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...
35	24.0	24.0	24.0	24.0	24.0	23.7	23.3	23.0	22.7	...	...	...	...	...	...
36	8.0	7.4	7.1	7.0	6.8	6.7	6.7	...	...	...	...	...	...	...	...
37	8.0	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...	...	...
38	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	8.0	...	...	...	...
39	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...
40	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...
41	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...
42	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	10.0	...	...	...	...
43	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.1	12.6	12.0	11.5	...	...	...	...
44	6.7	6.5	6.4	6.3	6.3	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.1	6.0
45	6.7	6.5	6.4	6.3	6.3	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.1	6.0

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P.No.
1	99Ni-Low C	Bar, rod	SB-160	...	N02201	Hot fin.	...	41
2	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed	≤5 O.D.	41
3	99Ni-Low C	Plate, sheet, strip	SB-162	...	N02201	Annealed	...	41
4	99Ni-Low C	Smls. tube	SB-163	...	N02201	Annealed	...	41
5	67Ni-30Cu	Bar, rod	SB-164	...	N04400	HW or CW ann.	All	42
6	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed	>5 O.D.	42
7	67Ni-30Cu	Forgings	SB-564	...	N04400	Annealed	...	42
8	67Ni-30Cu	Plate	SB-127	...	N04400	Annealed	...	42
9	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Annealed	...	42
10	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed	≤5 O.D.	42
11	67Ni-30Cu	Hexagons, rings, discs	SB-164	...	N04400	Hot worked	$2\frac{1}{8} < t \leq 4$	42
12	67Ni-30Cu	Plate	SB-127	...	N04400	As rolled	...	42
13	67Ni-30Cu	Rounds, squares, rectangles	SB-164	...	N04400	Hot worked	$12 < t \leq 14$	42
14	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Stress rel.	...	42
15	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Stress rel.	...	42
16	67Ni-30Cu-S	Bar, rod	SB-164	...	N04405	Annealed	...	42
17	67Ni-30Cu-S	Bar, rod	SB-164	...	N04405	Hot worked	...	42
18	47Ni-22Cr-9Mo-18Fe	Plate	SB-435	...	N06002	Annealed	$\frac{3}{16} < t \leq 2\frac{1}{2}$	43
19	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...	N06002	Annealed	$\frac{1}{16} < t \leq \frac{3}{16}$	43
20	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...	N06002	Solution ann.	$\geq \frac{3}{16}$	43
21	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.	...	43
22	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.	...	43
23	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...	N06002	Solution ann.	...	43
24	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.	...	43
25	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.	...	43
26	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.	$> \frac{3}{4}$	45
27	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.	$> \frac{3}{4}$	45
28	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.	$\frac{5}{16} < t \leq \frac{3}{4}$	45
29	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.	$\frac{3}{16} < t \leq \frac{3}{4}$	45
30	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...	N06007	Solution ann.	...	45
31	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...	N06007	Solution ann.	...	45
32	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...	N06007	Solution ann.	...	45
33	55Ni-21Cr-13.5Mo	Smls. & wld. fittings	SB-366	...	N06022	Solution ann.	...	43
34	55Ni-21Cr-13.5Mo	Forgings	SB-462	...	N06022	Solution ann.	...	43
35	55Ni-21Cr-13.5Mo	Forgings	SB-564	...	N06022	Solution ann.	...	43
36	55Ni-21Cr-13.5Mo	Rod	SB-574	...	N06022	Solution ann.	...	43
37	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...	N06022	Solution ann.	...	43
38	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...	N06022	Solution ann.	...	43
39	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...	N06022	Solution ann.	...	43
40	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...	N06022	Solution ann.	...	43
41	59Ni-23Cr-16Mo	Wld. fittings	SB-366	...	N06059	Solution ann.	...	43
42	59Ni-23Cr-16Mo	Smls. fittings	SB-366	...	N06059	Solution ann.	...	43
43	59Ni-23Cr-16Mo	Wld. fittings	SB-366	...	N06059	Solution ann.	...	43
44	59Ni-23Cr-16Mo	Forged fittings	SB-462	...	N06059	Solution ann.	...	43
45	59Ni-23Cr-16Mo	Forgings	SB-564	...	N06059	Solution ann.	...	43

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	50	10	NP	800	NFN-1	G2, G4
2	50	12	NP	800	NFN-1	E1, G4
3	50	12	NP	800	NFN-1	E1, G4
4	50	12	NP	800	NFN-1	E1, G4
5	70	25	800	800	NFN-3	G1, G2, G4
6	70	25	800	800	NFN-3	G1, G4
7	70	25	800	800	NFN-3	G1, G2, G4
8	70	28	800	800	NFN-3	G1, G4
9	70	28	800	800	NFN-3	G1, G4
10	70	28	800	800	NFN-3	G1, G4
11	75	30	800	NP	NFN-3	E1, G1
12	75	40	800	800	NFN-3	E1, G1, G4
13	75	40	800	NP	NFN-3	E1, G1
14	85	55	500	800	NFN-3	E4, G1, G4, W1
15	85	55	500	NP	NFN-3	G1
16	70	25	800	800	NFN-3	G1, G2, G4
17	75	35	800	NP	NFN-3	G1
18	95	35	800	800	NFN-15	G1, G4
19	95	35	800	800	NFN-15	G1, G4
20	95	35	800	800	NFN-15	G1, G2, G4
21	100	40	800	NP	NFN-15	G1
22	100	40	NP	800	NFN-15	G1, G4, G5
23	100	40	800	800	NFN-15	G1, G4
24	100	40	800	NP	NFN-15	G1
25	100	40	NP	800	NFN-15	G1, G4, G5
26	85	30	NP	800	NFN-11	G1, G2, G4
27	85	30	NP	800	NFN-11	G1, G4
28	90	35	NP	800	NFN-11	G1, G2, G4
29	90	35	NP	800	NFN-11	G1, G4
30	90	35	NP	800	NFN-11	G1, G4, G5
31	90	35	NP	800	NFN-11	G1, G4
32	90	35	NP	800	NFN-11	G1, G4, G5
33	100	45	800	800	NFN-10	G1
34	100	45	800	800	NFN-10	G1
35	100	45	800	800	NFN-10	G1
36	100	45	800	800	NFN-10	G1
37	100	45	800	800	NFN-10	G1
38	100	45	800	800	NFN-10	G1
39	100	45	800	800	NFN-10	G1
40	100	45	800	800	NFN-10	G1
41	100	45	800	NP	NFN-14	G1, G4
42	100	45	800	800	NFN-14	G1, G4
43	100	45	NP	800	NFN-14	G1, G4, G5
44	100	45	800	800	NFN-14	G1, G4
45	100	45	800	800	NFN-14	G1, G4

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	6.7	6.5	6.4	6.3	6.3	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.1	6.0
2	8.0	7.8	7.7	7.6	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.4	7.4	7.2
3	8.0	7.8	7.7	7.6	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.4	7.4	7.2
4	8.0	7.8	7.7	7.6	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.4	7.4	7.2
5	16.7	15.3	14.6	14.0	13.6	13.3	13.2	13.1	13.1	13.1	13.1	13.1	13.0	12.9	12.7
6	16.7	15.3	14.6	14.0	13.6	13.3	13.2	13.1	13.1	13.1	13.1	13.1	13.0	12.9	12.7
7	16.7	15.3	14.6	14.0	13.6	13.3	13.2	13.1	13.1	13.1	13.1	13.1	13.0	12.9	12.7
8	18.7	17.2	16.4	15.7	15.2	14.9	14.7	14.7	14.7	14.7	14.7	14.7	14.6	14.5	14.3
9	18.7	17.2	16.4	15.7	15.2	14.9	14.7	14.7	14.7	14.7	14.7	14.7	14.6	14.5	14.3
10	18.7	17.2	16.4	15.7	15.2	14.9	14.7	14.7	14.7	14.7	14.7	14.7	14.6	14.5	14.3
11	20.0	19.7	19.4	19.0	18.6	18.2	17.9	17.7	17.6	17.5	17.3	17.2	17.0	16.8	15.2
12	25.0	25.0	25.0	25.0	24.8	24.3	23.9	23.7	23.4	23.3	23.1	22.9	22.7	20.9	20.3
13	25.0	25.0	25.0	25.0	24.8	24.3	23.9	23.7	23.4	23.3	23.1	22.9	22.7	20.9	20.3
14	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.2	27.9	27.4	26.6	18.0	12.7
15	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.3	28.3	...	...	...	...	...	...
16	16.7	15.3	14.6	14.0	13.6	13.3	13.2	13.1	13.1	13.1	13.1	13.1	13.0	12.9	12.7
17	23.3	...	20.6	...	19.2	...	18.5	...	18.5	...	18.5	18.5	18.5	18.2	17.6
18	23.3	21.9	21.0	20.1	19.2	18.4	17.7	17.1	16.5	16.1	15.7	15.3	15.1	14.9	14.7
19	23.3	21.9	21.0	20.1	19.2	18.4	17.7	17.1	16.5	16.1	15.7	15.3	15.1	14.9	14.7
20	23.3	21.9	21.0	20.1	19.2	18.4	17.7	17.1	16.5	16.1	15.7	15.3	15.1	14.9	14.7
21	26.7	25.0	24.0	22.9	22.0	21.1	20.3	19.5	18.9	18.4	17.9	17.5	17.2	17.0	16.8
22	22.7	21.3	20.4	19.5	18.7	17.9	17.2	16.6	16.1	15.6	15.2	14.9	14.6	14.4	14.3
23	26.7	25.0	24.0	22.9	22.0	21.1	20.3	19.5	18.9	18.4	17.9	17.5	17.2	17.0	16.8
24	26.7	25.0	24.0	22.9	22.0	21.1	20.3	19.5	18.9	18.4	17.9	17.5	17.2	17.0	16.8
25	22.7	21.3	20.4	19.5	18.7	17.9	17.2	16.6	16.1	15.6	15.2	14.9	14.6	14.4	14.3
26	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.5	19.2	19.0	18.8	18.7
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.5	19.2	19.0	18.8	18.7
28	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8
29	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8
30	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.6	19.3	19.1	18.8	18.7	18.5
31	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8
32	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.6	19.3	19.1	18.8	18.7	18.5
33	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
34	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
35	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
36	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
37	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
38	25.5	...	25.5	...	25.5	...	25.5	...	24.7	...	23.5	23.0	22.5	22.2	21.8
39	30.0	...	30.0	...	30.0	...	30.0	...	29.0	...	27.6	27.0	26.5	26.1	25.7
40	25.5	...	25.5	...	25.5	...	25.5	...	24.7	...	23.5	23.0	22.5	22.2	21.8
41	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
42	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
43	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	24.6	23.9	23.2	22.5	21.8
44	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
45	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P-No.
1	59Ni-23Cr-16Mo	Bar, rod	SB-574	...	N06059	Solution ann.	...	43
2	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...	N06059	Solution ann.	...	43
3	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.	...	43
4	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.	...	43
5	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...	N06059	Solution ann.	...	43
6	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.	...	43
7	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.	...	43
8	61Ni-16Mo-16Cr	Rod	SB-574	...	N06455	Solution ann.	...	43
9	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...	N06455	Solution ann.	...	43
10	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...	N06455	Solution ann.	...	43
11	61Ni-16Mo-16Cr	Wld. pipe & tube	SB-622	...	N06455	Solution ann.	...	43
12	61Ni-16Mo-16Cr	Wld. tube	SB-626	...	N06455	Solution ann.	...	43
13	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin.	>5 O.D.	43
14	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold worked/ann.	>5 O.D.	43
15	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed	...	43
16	72Ni-15Cr-8Fe	Bar, rod	SB-166	...	N06600	Annealed	...	43
17	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold worked/ann.	≤5 O.D.	43
18	72Ni-15Cr-8Fe	Plate	SB-168	...	N06600	Annealed	...	43
19	72Ni-15Cr-8Fe	Forgings	SB-564	...	N06600	Annealed	...	43
20	72Ni-15Cr-8Fe	Wld. tube	SB-516	...	N06600	Cold drawn/ann.	≤4½ O.D.	43
21	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...	N06600	Cold drawn/ann.	≤4½ O.D.	43
22	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed	¼ < O.D. ≤ 7/8	43
23	60Ni-22Cr-9Mo-3.5Cb	Bar, rod	SB-446	...	N06625	Annealed	4 < t ≤ 10	43
24	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	...	N06625	Hot rolled/ann.	≤2.75	43
25	60Ni-22Cr-9Mo-3.5Cb	Plate	SB-443	...	N06625	Cold rolled/ann.	≤0.375	43
26	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe & tube	SB-444	...	N06625	Annealed	...	43
27	60Ni-22Cr-9Mo-3.5Cb	Bar, rod	SB-446	...	N06625	Annealed	≤4	43
28	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Hot worked/ann.	>5 O.D.	43
29	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold worked/ann.	>5 O.D.	43
30	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Hot worked/ann.	≤5 O.D.	43
31	58Ni-29Cr-9Fe	Smls. tube	SB-163	...	N06690	Annealed	...	43
32	58Ni-29Cr-9Fe	Plate	SB-168	...	N06690	Annealed	...	43
33	58Ni-29Cr-9Fe	Forgings	SB-564	...	N06690	Annealed	...	43
34	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Cold worked/ann.	...	43
35	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold worked/ann.	≤5 O.D.	43
36	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Hot worked	...	43
37	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Hot worked/ann.	...	43
38	58Ni-29Cr-9Fe	Smls. tube	SB-163	...	N06690	Annealed	¼ < O.D. ≤ 7/8	43
39	35Ni-19Cr-1¼Si	Bar	SB-511	...	N08330	Annealed	...	46
40	35Ni-19Cr-1¼Si	Smls. & wld. pipe	SB-535	...	N08330	Annealed	...	46
41	35Ni-19Cr-1¼Si	Plate, sheet, strip	SB-536	...	N08330	Annealed	...	46
42	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08800	Annealed	...	45
43	42Fe-33Ni-21Cr	Smls. pipe & tube	SB-407	...	N08800	Annealed	...	45
44	42Fe-33Ni-21Cr	Plate	SB-409	...	N08800	Annealed	...	45
45	42Fe-33Ni-21Cr	Wld. pipe	SB-514	...	N08800	Annealed	...	45

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	100	45	800	800	NFN-14	G1, G4
2	100	45	800	800	NFN-14	G1, G4
3	100	45	800	NP	NFN-14	G1, G4
4	100	45	NP	800	NFN-14	G1, G4, G5
5	100	45	800	800	NFN-14	G1, G4
6	100	45	800	NP	NFN-14	G1, G4
7	100	45	NP	800	NFN-14	G1, G4, G5
8	100	40	NP	800	NFN-14	G1, G2, G4
9	100	40	NP	800	NFN-14	G1, G4
10	100	40	NP	800	NFN-14	G1, G4, G5
11	100	40	NP	800	NFN-14	G1, G4
12	100	40	NP	800	NFN-14	G1, G4, G5
13	75	25	800	NP	NFN-4	G1
14	80	30	800	800	NFN-4	G1, G4
15	80	35	800	800	NFN-4	G1, G4
16	80	35	800	800	NFN-4	G1, G2, G4
17	80	35	800	800	NFN-4	G1, G4
18	80	35	800	800	NFN-4	G1, G4
19	80	35	800	800	NFN-4	G1, G2, G4
20	80	35	NP	800	NFN-4	G1, G4
21	80	35	NP	800	NFN-4	G1, G4
22	80	40	800	NP	NFN-21	G1, G3, S1
23	110	50	800	NP	NFN-17	...
24	110	55	800	NP	NFN-17	...
25	110	55	800	NP	NFN-17	...
26	120	60	800	NP	NFN-17	...
27	120	60	800	NP	NFN-17	...
28	75	25	800	NP	NFN-4	G1
29	85	30	800	NP	NFN-4	G1
30	85	30	800	NP	NFN-4	G1
31	85	35	800	NP	NFN-4	G1
32	85	35	800	NP	NFN-4	G1
33	85	35	800	NP	NFN-4	G1
34	85	35	800	NP	NFN-4	G1
35	85	35	800	NP	NFN-4	G1
36	85	35	800	NP	NFN-4	G1
37	85	35	800	NP	NFN-4	G1
38	85	40	800	NP	NFN-21	G1, G3, S1
39	70	30	NP	800	NFN-13	G1, G2, G4
40	70	30	NP	800	NFN-13	G1, G4, G5
41	70	30	NP	800	NFN-13	G1, G4
42	75	30	800	800	NFN-8	G1, G4
43	75	30	800	800	NFN-8	G1, G4
44	75	30	800	800	NFN-8	G1, G4
45	75	30	NP	800	NFN-8	G1, G4

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
2	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
3	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
4	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	24.6	23.9	23.2	22.5	21.8
5	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
6	30.0	...	30.0	...	30.0	...	30.0	...	30.0	...	28.9	28.1	27.3	26.5	25.7
7	25.5	...	25.5	...	25.5	...	25.5	...	25.5	...	24.6	23.9	23.2	22.5	21.8
8	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8
9	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8
10	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.5	22.2	21.9
11	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8
12	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.5	22.2	21.9
13	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7
14	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
15	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3
16	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3
17	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3
18	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3
19	23.3	...	23.3	...	23.3	...	23.3	...	23.3	...	23.3	23.3	23.3	23.3	23.3
20	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.8	19.8	19.8	19.8	19.8
21	19.8	...	19.8	...	19.8	...	19.8	...	19.8	...	19.8	19.8	19.8	19.8	19.8
22	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.7	26.7	26.7
23	33.3	...	32.1	...	31.2	...	30.3	...	29.4	...	28.6	28.3	27.9	27.6	27.4
24	36.7	...	35.3	...	34.3	...	33.3	...	32.4	...	31.5	31.1	30.7	30.4	30.1
25	36.7	...	35.3	...	34.3	...	33.3	...	32.4	...	31.5	31.1	30.7	30.4	30.1
26	40.0	...	38.5	...	37.4	...	36.3	...	35.3	...	34.4	33.9	33.5	33.2	32.9
27	40.0	...	38.5	...	37.4	...	36.3	...	35.3	...	34.4	33.9	33.5	33.2	32.9
28	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7
29	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
30	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
31	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
32	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
33	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
34	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
35	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
36	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
37	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3
38	26.7	...	26.7	...	26.7	...	26.7	...	26.7	...	26.7	26.7	26.6	26.5	26.4
39	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.4	18.9	18.5	18.1	17.7	17.4
40	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.1	15.7	15.4	15.1	14.8
41	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.4	18.9	18.5	18.1	17.7	17.4
42	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0
43	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0
44	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0
45	17.0	...	17.0	...	17.0	...	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper	Size/Thickness, in.	P.No.
1	42Fe-33Ni-21Cr	Wld. tube	SB-515	...	N08800	Annealed	...	45
2	42Fe-33Ni-21Cr	Forgings	SB-564	...	N08800	Annealed	...	45
3	42Fe-33Ni-21Cr	Bar, rod	SB-408	...	N08800	Hot fin.	...	45
4	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08800	Annealed	$\frac{1}{4} < O.D. \leq \frac{7}{8}$	45
5	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08800	Cold worked	...	45
6	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08810	Annealed	...	45
7	42Fe-33Ni-21Cr	Smls. pipe & tube	SB-407	...	N08810	Annealed	...	45
8	42Fe-33Ni-21Cr	Bar, rod	SB-408	...	N08810	Annealed	...	45
9	42Fe-33Ni-21Cr	Plate	SB-409	...	N08810	Annealed	...	45
10	42Fe-33Ni-21Cr	Wld. pipe	SB-514	...	N08810	Annealed	...	45
11	42Fe-33Ni-21Cr	Wld. tube	SB-515	...	N08810	Annealed	...	45
12	42Fe-33Ni-21Cr	Forgings	SB-564	...	N08810	Annealed	...	45
13	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...	N08825	Annealed	...	45
14	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...	N08825	Annealed	...	45
15	42Ni-21.5Cr-3Mo-2.3Cu	Plate, sheet, strip	SB-424	...	N08825	Annealed	...	45
16	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...	N08825	Annealed	...	45
17	62Ni-28Mo-5Fe	Plate, strip	SB-333	...	N10001	Solution ann.	$\frac{3}{16} \leq t \leq 2\frac{1}{2}$	44
18	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...	N10001	Solution ann.	...	44
19	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...	N10001	Solution ann.	...	44
20	62Ni-28Mo-5Fe	Wld. tube	SB-626	...	N10001	Solution ann.	...	44
21	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Solution ann.	$1\frac{1}{2} < t \leq 3\frac{1}{2}$	44
22	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Solution ann.	$\frac{5}{16} \leq t \leq 1\frac{1}{2}$	44
23	62Ni-28Mo-5Fe	Plate, strip	SB-333	...	N10001	Solution ann.	$< \frac{3}{16}$	44
24	70Ni-16Mo-7Cr-5Fe	Plate, sheet, strip	SB-434	...	N10003	Annealed	$< 2\frac{1}{2}$	44
25	70Ni-16Mo-7Cr-5Fe	Rod	SB-573	...	N10003	Solution ann.	...	44
26	54Ni-16Mo-15Cr	Smls. fittings	SB-366	...	N10276	Solution ann.	...	43
27	54Ni-16Mo-15Cr	Wld. fittings	SB-366	...	N10276	Solution ann.	...	43
28	54Ni-16Mo-15Cr	Forgings	SB-462	...	N10276	Solution ann.	...	43
29	54Ni-16Mo-15Cr	Rod	SB-574	...	N10276	Solution ann.	...	43
30	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...	N10276	Solution ann.	...	43
31	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.	...	43
32	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...	N10276	Solution ann.	...	43
33	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.	...	43
34	65Ni-28Mo-2Fe	Plate, strip	SB-333	...	N10665	Solution ann.	...	44
35	65Ni-28Mo-2Fe	Rod	SB-335	...	N10665	Solution ann.	...	44
36	65Ni-28Mo-2Fe	Smls. fittings	SB-366	...	N10665	Solution ann.	...	44
37	65Ni-28Mo-2Fe	Wld. fittings	SB-366	...	N10665	Solution ann.	...	44
38	65Ni-28Mo-2Fe	Forgings	SB-462	...	N10665	Solution ann.	...	44
39	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Solution ann.	...	44
40	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...	N10665	Solution ann.	...	44
41	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Solution ann.	...	44
42	Ti	Plate, sheet, strip	SB-265	1	R50250	Annealed	...	51
43	Ti	Bar, billet	SB-348	1	R50250	Annealed	...	51
44	Ti	Forgings	SB-381	1	R50250	Annealed	...	51
45	Ti	Smls. tube	SB-338	1	R50250	Smls. ann.	...	51

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	75	30	NP	800	NFN-8	G1, G4
2	75	30	800	800	NFN-8	G1, G2, G4
3	75	30	800	800	NFN-8	G1, G2, G4
4	75	40	800	NP	NFN-8	G1, G3, S1
5	83	47	650	NP	NFN-23	G1
6	65	25	800	800	NFN-9	G1, G4
7	65	25	800	800	NFN-9	G1, G4
8	65	25	800	800	NFN-9	G1, G2, G4
9	65	25	800	800	NFN-9	G1, G4
10	65	25	NP	800	NFN-9	G1, G4, G5
11	65	25	NP	800	NFN-9	G1, G4, G5
12	65	25	800	800	NFN-9	G1, G2, G4
13	85	35	800	800	NFN-7	G1, G4
14	85	35	NP	800	NFN-7	G1, G4
15	85	35	NP	800	NFN-7	G4
16	85	35	800	800	NFN-7	G2, G4
17	100	45	NP	800	NFN-5	G1, G4
18	100	45	NP	800	NFN-5	G1, G4, G5
19	100	45	NP	800	NFN-5	G1, G4
20	100	45	NP	800	NFN-5	G1, G4, G5
21	100	46	NP	800	NFN-5	G1, G2, G4
22	115	46	NP	800	NFN-5	G1, G2, G4
23	115	50	NP	800	NFN-5	G1, G4
24	100	40	NP	800	NFN-6	G4
25	100	40	NP	800	NFN-6	G1, G2, G4
26	100	41	NP	800	NFN-10	G1, G4
27	100	41	NP	800	NFN-10	G1, G4, G5
28	100	41	NP	800	NFN-10	G1, G4
29	100	41	NP	800	NFN-10	G1, G2, G4
30	100	41	NP	800	NFN-10	G1, G4
31	100	41	NP	800	NFN-10	G1, G4, G5
32	100	41	NP	800	NFN-10	G1, G4
33	100	41	NP	800	NFN-10	G1, G4, G5
34	110	51	NP	800	NFN-16	G1, G4
35	110	51	NP	800	NFN-16	G1, G2, G4
36	110	51	NP	800	NFN-16	G1, G4
37	110	51	NP	800	NFN-16	G1, G4, G5
38	110	51	NP	800	NFN-16	G1, G4
39	110	51	NP	800	NFN-16	G1, G4, G5
40	110	51	NP	800	NFN-16	G1, G4
41	110	51	NP	800	NFN-16	G1, G4, G5
42	35	25	NP	600	NFT-3	...
43	35	25	NP	600	NFT-3	...
44	35	25	NP	600	NFT-3	...
45	35	25	NP	600	NFT-3	...

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	17.0	...	17.0	...	17.0	...	17.0	...	17.0	...	17.0	17.0	17.0	17.0	17.0
2	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0
3	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0
4	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	24.9	24.8	24.8	24.7	24.6
5	27.7	...	27.7	...	27.7	...	27.5	...	26.9	...	26.6	26.6	...	...	...
6	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0
7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0
8	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0
9	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0
10	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8
11	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8
12	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0
13	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0
14	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0
15	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0
16	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0
17	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9
18	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4
19	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9
20	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4
21	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.5
22	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.5
23	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.2
24	26.7	25.5	24.6	23.6	22.7	21.8	21.1	20.4	20.0	19.6	19.3	19.1	18.9	18.7	18.4
25	26.7	25.5	24.6	23.6	22.7	21.8	21.1	20.4	20.0	19.6	19.3	19.1	18.9	18.7	18.4
26	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1
27	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6
28	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1
29	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1
30	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1
31	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6
32	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1
33	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6
34	34.0	...	34.0	...	34.0	...	34.0	...	34.0	...	34.0	34.0	34.0	34.0	34.0
35	34.0	...	34.0	...	34.0	...	34.0	...	34.0	...	34.0	34.0	34.0	34.0	34.0
36	34.0	...	34.0	...	34.0	...	34.0	...	34.0	...	34.0	34.0	34.0	34.0	34.0
37	28.9	...	28.9	...	28.9	...	28.9	...	28.9	...	28.9	28.9	28.9	28.9	28.9
38	34.0	...	34.0	...	34.0	...	34.0	...	34.0	...	34.0	34.0	34.0	34.0	34.0
39	28.9	...	28.9	...	28.9	...	28.9	...	28.9	...	28.9	28.9	28.9	28.9	28.9
40	34.0	...	34.0	...	34.0	...	34.0	...	34.0	...	34.0	34.0	34.0	34.0	34.0
41	28.9	...	28.9	...	28.9	...	28.9	...	28.9	...	28.9	28.9	28.9	28.9	28.9
42	11.7	10.9	9.6	8.6	7.7	7.0	6.4	5.9	5.2	4.7	4.2	...	...	...	...
43	11.7	10.9	9.6	8.6	7.7	7.0	6.4	5.9	5.2	4.7	4.2	...	...	...	...
44	11.7	10.9	9.6	8.6	7.7	7.0	6.4	5.9	5.2	4.7	4.2	...	...	...	...
45	11.7	10.9	9.6	8.6	7.7	7.0	6.4	5.9	5.2	4.7	4.2	...	...	...	...

INTENTIONALLY LEFT BLANK

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/ Thickness, in.	P.No.
1	Ti	Smls. pipe	SB-861	1	R50250	Smls. ann.	...	51
2	Ti	Wld. tube	SB-338	1	R50250	Wld. ann.	...	51
3	Ti	Wld. pipe	SB-862	1	R50250	Wld. ann.	...	51
4	Ti	Plate, sheet, strip	SB-265	2	R50400	Annealed	...	51
5	Ti	Bar, billet	SB-348	2	R50400	Annealed	...	51
6	Ti	Forgings	SB-381	2	R50400	Annealed	...	51
7	Ti	Smls. tube	SB-338	2	R50400	Smls. ann.	...	51
8	Ti	Smls. pipe	SB-861	2	R50400	Smls. ann.	...	51
9	Ti	Wld. tube	SB-338	2	R50400	Wld. ann.	...	51
10	Ti	Wld. pipe	SB-862	2	R50400	Wld. ann.	...	51
11	Ti	Plate, sheet, strip	SB-265	3	R50550	Annealed	...	52
12	Ti	Bar, billet	SB-348	3	R50550	Annealed	...	52
13	Ti	Forgings	SB-381	3	R50550	Annealed	...	52
14	Ti	Smls. tube	SB-338	3	R50550	Smls. ann.	...	52
15	Ti	Smls. pipe	SB-861	3	R50550	Smls. ann.	...	52
16	Ti	Wld. tube	SB-338	3	R50550	Wld. ann.	...	52
17	Ti	Wld. pipe	SB-862	3	R50550	Wld. ann.	...	52
18	Ti-Pd	Plate, sheet, strip	SB-265	7	R52400	Annealed	...	51
19	Ti-Pd	Bar, billet	SB-348	7	R52400	Annealed	...	51
20	Ti-Pd	Forgings	SB-381	7	R52400	Annealed	...	51
21	Ti-Pd	Smls. tube	SB-338	7	R52400	Smls. ann.	...	51
22	Ti-Pd	Smls. pipe	SB-861	7	R52400	Smls. ann.	...	51
23	Ti-Pd	Wld. tube	SB-338	7	R52400	Wld. ann.	...	51
24	Ti-Pd	Wld. pipe	SB-862	7	R52400	Wld. ann.	...	51
25	Ti-Pd	Plate, sheet, strip	SB-265	16	R52402	Annealed	...	51
26	Ti-0.3Mo-0.8Ni	Plate, sheet, strip	SB-265	12	R53400	Annealed	...	52
27	Ti-0.3Mo-0.8Ni	Bar, billet	SB-348	12	R53400	Annealed	...	52
28	Ti-0.3Mo-0.8Ni	Forgings	SB-381	F-12	R53400	Annealed	...	52
29	Ti-0.3Mo-0.8Ni	Smls. tube	SB-338	12	R53400	Smls. ann.	...	52
30	Ti-0.3Mo-0.8Ni	Smls. pipe	SB-861	12	R53400	Smls. ann.	...	52
31	Ti-0.3Mo-0.8Ni	Wld. tube	SB-338	12	R53400	Wld. ann.	...	52
32	Ti-0.3Mo-0.8Ni	Wld. pipe	SB-862	12	R53400	Wld. ann.	...	52
33	Ti-3Al-2.5V	Plate, sheet, strip	SB-265	9	R56320	Annealed	...	53
34	Ti-3Al-2.5V	Bar, billet	SB-348	9	R56320	Annealed	...	53
35	Ti-3Al-2.5V	Forgings	SB-381	F-9	R56320	Annealed	...	53
36	Ti-3Al-2.5V	Smls. & wld. tube	SB-338	9	R56320	Smls. ann.	...	53
37	Ti-3Al-2.5V	Wld. fittings	SB-363	9	R56320	Smls. ann.	...	53
38	Ti-3Al-2.5V	Smls. pipe	SB-861	9	R56320	Smls. ann.	...	53
39	Ti-3Al-2.5V	Smls. & wld. tube	SB-338	9	R56320	Wld. ann.	...	53
40	Ti-3Al-2.5V	Wld. fittings	SB-363	9	R56320	Wld. ann.	...	53
41	Ti-3Al-2.5V	Wld. pipe	SB-862	9	R56320	Wld. ann.	...	53

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted) (SPT = Supports Only)		External Pressure Chart No.	Notes
			III	VIII-2		
1	35	25	NP	600	NFT-3	...
2	35	25	NP	600	NFT-3	G5
3	35	25	NP	600	NFT-3	G5
4	50	40	NP	600	NFT-2	...
5	50	40	NP	600	NFT-2	...
6	50	40	NP	600	NFT-2	...
7	50	40	NP	600	NFT-2	...
8	50	40	NP	600	NFT-2	...
9	50	40	NP	600	NFT-2	G5
10	50	40	NP	600	NFT-2	G5
11	65	55	NP	600	NFT-1	...
12	65	55	NP	600	NFT-1	...
13	65	55	NP	600	NFT-1	...
14	65	55	NP	600	NFT-1	...
15	65	55	NP	600	NFT-1	...
16	65	55	NP	600	NFT-1	G5
17	65	55	NP	600	NFT-1	G5
18	50	40	NP	600	NFT-2	...
19	50	40	NP	600	NFT-2	...
20	50	40	NP	600	NFT-2	...
21	50	40	NP	600	NFT-2	...
22	50	40	NP	600	NFT-2	...
23	50	40	NP	600	NFT-2	G5
24	50	40	NP	600	NFT-2	G5
25	50	40	NP	600	NFT-2	...
26	70	50	NP	600	NFT-5	...
27	70	50	NP	600	NFT-5	...
28	70	50	NP	600	NFT-5	...
29	70	50	NP	600	NFT-5	...
30	70	50	NP	600	NFT-5	...
31	70	50	NP	600	NFT-5	G5
32	70	50	NP	600	NFT-5	G5
33	90	70	600	NP	NFT-4	...
34	90	70	600	NP	NFT-4	...
35	90	70	600	NP	NFT-4	...
36	90	70	600	NP	NFT-4	...
37	90	70	600	NP	NFT-4	...
38	90	70	600	NP	NFT-4	...
39	90	70	600	NP	NFT-4	G5
40	90	70	600	NP	NFT-4	G5
41	90	70	600	NP	NFT-4	G5

Table 2B (Cont'd)
Section III, Division 1, Classes 1, MC, and CS; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2, Class 1 Maximum Allowable
Stress Values, S , for Nonferrous Materials

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800
1	11.7	10.9	9.6	8.6	7.7	7.0	6.4	5.9	5.2	4.7	4.2	...	...	...	...
2	9.9	9.2	8.2	7.3	6.5	5.9	5.5	5.0	4.5	4.0	3.5	...	...	...	...
3	9.9	9.2	8.2	7.3	6.5	5.9	5.5	5.0	4.5	4.0	3.5	...	...	...	...
4	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
5	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
6	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
7	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
8	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
9	14.2	13.6	12.3	11.2	10.3	9.4	8.8	8.1	7.5	7.0	6.5	...	...	...	...
10	14.2	13.6	12.3	11.2	10.3	9.4	8.8	8.1	7.5	7.0	6.5	...	...	...	...
11	21.7	20.4	18.4	16.6	14.9	13.4	12.1	10.9	9.9	9.2	8.6	...	...	...	...
12	21.7	20.4	18.4	16.6	14.9	13.4	12.1	10.9	9.9	9.2	8.6	...	...	...	...
13	21.7	20.4	18.4	16.6	14.9	13.4	12.1	10.9	9.9	9.2	8.6	...	...	...	...
14	21.7	20.4	18.4	16.6	14.9	13.4	12.1	10.9	9.9	9.2	8.6	...	...	...	...
15	21.7	20.4	18.4	16.6	14.9	13.4	12.1	10.9	9.9	9.2	8.6	...	...	...	...
16	18.4	17.4	15.6	14.1	12.7	11.4	10.2	9.3	8.4	7.8	7.3	...	...	...	...
17	18.4	17.4	15.6	14.1	12.7	11.4	10.2	9.3	8.4	7.8	7.3	...	...	...	...
18	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
19	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
20	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
21	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
22	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
23	14.2	13.6	12.3	11.2	10.3	9.4	8.8	8.1	7.5	7.0	6.5	...	...	...	...
24	14.2	13.6	12.3	11.2	10.3	9.4	8.8	8.1	7.5	7.0	6.5	...	...	...	...
25	16.7	16.0	14.5	13.2	12.1	11.1	10.3	9.6	8.9	8.2	7.6	...	...	...	...
26	23.3	23.3	21.8	20.3	18.9	17.7	16.7	15.9	15.2	14.8	14.4	...	...	...	...
27	23.3	23.3	21.8	20.3	18.9	17.7	16.7	15.9	15.2	14.8	14.4	...	...	...	...
28	23.3	23.3	21.8	20.3	18.9	17.7	16.7	15.9	15.2	14.8	14.4	...	...	...	...
29	23.3	23.3	21.8	20.3	18.9	17.7	16.7	15.9	15.2	14.8	14.4	...	...	...	...
30	23.3	23.3	21.8	20.3	18.9	17.7	16.7	15.9	15.2	14.8	14.4	...	...	...	...
31	19.8	19.8	18.5	17.3	16.1	15.1	14.2	13.5	12.9	12.6	12.2	...	...	...	...
32	19.8	19.8	18.5	17.3	16.1	15.1	14.2	13.5	12.9	12.6	12.2	...	...	...	...
33	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
34	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
35	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
36	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
37	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
38	30.0	30.0	28.9	27.7	26.4	25.0	23.5	22.2	21.1	20.5	20.1	...	...	...	...
39	25.5	25.5	24.5	23.5	22.4	21.2	20.0	18.9	18.0	17.4	17.1	...	...	...	...
40	25.5	25.5	24.5	23.5	22.4	21.2	20.0	18.9	18.0	17.4	17.1	...	...	...	...
41	25.5	25.5	24.5	23.5	22.4	21.2	20.0	18.9	18.0	17.4	17.1	...	...	...	...

NOTES TO TABLE 2B**GENERAL NOTES**

- (a) The following abbreviations are used: ann., annealed; fin., finished; rel., relieved; Smls., Seamless; and Wld., Welded.
- (b) An alternative typeface is used for stress values based on successful experience in service (see Notes E1 through E4).
- (c) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SB-407/SB-407M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SB-407 Grade N08800 shall be used when SB-407M Grade N08800 is used in construction.
- (d) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (e) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (f) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES – EXPERIENCE CRITERION

- E1 For values at 800°F, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E2 For values at 250°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E3 For values at 400°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E4 For values at 750°F and above, the design stress intensity values or maximum allowable stress values are based on successful experience in service.
- E5 For values at 350°F and above, the design stress intensity values are based on successful experience in service.

NOTES – GENERAL REQUIREMENTS

- G1 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed $66\frac{2}{3}\%$ but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G2 Use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.
- G3 SB-163 Supplementary Requirement S2 shall be met.
- G4 Stress values for 100°F may be used at temperatures down to -325°F without additional specification requirements.
- G5 A joint efficiency factor of 0.85 has been applied in arriving at the stress values for this material.
- G6 Maximum temperature for external pressure design not to exceed 350°F.
- G7 These alloys are occasionally subject to the hazard of stress corrosion cracking. Even though they are suitable for engineering use under a wide variety of corrosive conditions, with no particular hazard with respect to stress corrosion, the supplier of the material should be consulted before applying them.
- G8 Stress values for 100°F may be used at temperatures down to -452°F without additional specification requirements.
- G9 For stress relieved tempers (T451, T4510, T4511, T651, T6510, and T6511), stress values for materials in the basic temper shall be used.
- G10 Copper-silicon alloys are not always suitable when exposed to certain media and high temperature, particularly steam above 212°F. The user should satisfy him/herself that the alloy selected is satisfactory for the service for which it is to be used.

NOTES – SIZE REQUIREMENTS

- S1 Thickness ≤ 0.100 in.

NOTES – WELDING REQUIREMENTS

- W1 Welding except for seal welds is not permitted.
- W2 For welded construction, stress values for material of O temper shall be used.
- W3 The stress values given for this material are not applicable when either welding or thermal cutting is employed.

Table 3
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.
Ferrous Materials							
1	Carbon steel	Bolting	SA-307	A	...	...	$\frac{1}{4} \leq t \leq 4$
2	Carbon steel	Bolting	SA-307	B	...	...	...
3	Carbon steel	Bolting	SA-449	1	K04200	...	$1\frac{1}{2} < t \leq 3$
(25) 4	...	...	...	...	...	...	...
(25) 5	Carbon steel	Bolting	SA-325	1	K02706	...	$1 < t \leq 1\frac{1}{2}$
6	Carbon steel	Bolting	SA-449	1	K04200	...	$1 < t < 1\frac{1}{2}$
7	Carbon steel	Bolting	SA-354	BC	K04100	...	$2\frac{1}{2} < t \leq 4$
8	Carbon steel	Bolting	SA-325	1	K02706	...	$\frac{1}{2} \leq t \leq 1$
9	Carbon steel	Bolting	SA-449	1	K04200	...	≤ 1
10	Carbon steel	Bolting	SA-354	BC	K04100	...	$\frac{1}{4} < t \leq 2\frac{1}{2}$
11	Carbon steel	Bolting	SA-354	BD	K04100	...	$2\frac{1}{2} < t \leq 4$
12	Carbon steel	Bolting	SA-354	BD	K04100	...	$\frac{1}{4} < t \leq 2\frac{1}{2}$
13	C- $\frac{1}{4}$ Mo	Bolting	SA-320	L7A	G40370	...	$\leq 2\frac{1}{2}$
14	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037	G40370	...	$\geq \frac{5}{8}$
15	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042	G40420	...	$\geq \frac{5}{8}$
16	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037	G40370	...	$\leq \frac{1}{2}$
17	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042	G40420	...	$\leq \frac{1}{2}$
18	$\frac{3}{4}$ Cr	Bolting	SA-574	5137M	...	...	$\geq \frac{5}{8}$
19	$\frac{3}{4}$ Cr	Bolting	SA-574	51B37M	...	...	$\geq \frac{5}{8}$
20	$\frac{3}{4}$ Cr	Bolting	SA-574	5137M	...	...	$\leq \frac{1}{2}$
21	$\frac{3}{4}$ Cr	Bolting	SA-574	51B37M	...	...	$\leq \frac{1}{2}$
22	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	5	$2 < t \leq 4$
23	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	5	≤ 2
24	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	4	≤ 4
25	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	3	≤ 4
26	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	2	≤ 3
27	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	H41420	1	$\leq 1\frac{1}{2}$
(25) 28	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-193	B7	G41400	...	$4 < t \leq 7$
29	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-193	B7M	G41400	...	≤ 4
30	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-320	L7M	G41400	...	$\leq 2\frac{1}{2}$
31	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-193	B7	G41400	...	$2\frac{1}{2} < t \leq 4$
32	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-193	B7	G41400	...	$\leq 2\frac{1}{2}$
33	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-320	L7	G41400	...	$\leq 2\frac{1}{2}$
34	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4137	G41370	...	$\geq \frac{5}{8}$
35	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4140	G41400	...	$\geq \frac{5}{8}$
36	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4142	G41420	...	$\geq \frac{5}{8}$
37	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4145	G41450	...	$\geq \frac{5}{8}$
38	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4137	G41370	...	$\leq \frac{1}{2}$
39	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4140	G41400	...	$\leq \frac{1}{2}$
40	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4142	G41420	...	$\leq \frac{1}{2}$
41	1Cr- $\frac{1}{5}$ Mo	Bolting	SA-574	4145	G41450	...	$\leq \frac{1}{2}$
42	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...	$4 < t \leq 8$
43	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...	$2\frac{1}{2} < t \leq 4$
44	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	5	$2 < t \leq 8$
45	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	5	≤ 2

Table 3
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
							Ferrous Materials
1	60	...	NP	450	NP	NP	G12
2	60	...	400	450	NP	450	...
3	90	58	700	650	650	650	...
4	...	...	...	...	...	...	...
5	105	81	650	650	650	650	...
6	105	81	700	700	700	650	...
7	115	99	650	650	650	650	...
8	120	92	NP	650	650	650	...
9	120	92	700	650	650	650	...
10	125	109	650	650	650	650	...
11	140	115	650	650	650	650	...
12	150	130	650	650	650	650	...
13	125	105	NP	650	650	650	W3
14	170	135	550	550	NP	550	G7, G11, W1
15	170	135	550	550	NP	550	G7, G11, W1
16	180	140	550	550	NP	550	G7, G11, W1
17	180	140	550	550	NP	550	G7, G11, W1
18	170	135	550	550	NP	NP	G7, G11, W1
19	170	135	550	550	NP	NP	G7, G11, W1
20	180	140	550	550	NP	NP	G7, G11, W1
21	180	140	550	550	NP	NP	G7, G11, W1
22	115	100	700	NP	NP	NP	...
23	120	105	700	NP	NP	NP	...
24	135	120	700	NP	NP	NP	...
25	145	130	700	700	NP	650	...
26	155	140	700	NP	NP	NP	...
27	165	150	700	NP	NP	NP	...
28	100	75	800	1000	800	650	T5
29	100	80	NP	1000	800	650	T5
30	100	80	NP	1000	800	650	T5
31	115	95	800	1000	800	650	T5
32	125	105	800	1000	800	650	T5
33	125	105	700	800	800	650	...
34	170	135	550	NP	NP	NP	G7, G11, W1
35	170	135	550	550	NP	550	G7, G11, W1
36	170	135	550	NP	NP	NP	G7, G11, W1
37	170	135	550	NP	NP	NP	G7, G11, W1
38	180	140	550	NP	NP	NP	G7, G11, W1
39	180	140	550	NP	NP	NP	G7, G11, W1
40	180	140	550	NP	NP	NP	G7, G11, W1
41	180	140	550	NP	NP	NP	G7, G11, W1
42	100	85	800	1100	800	650	T8
43	110	95	800	1100	800	650	T8
44	115	100	700	700	700	NP	...
45	120	105	700	700	700	NP	...

Table 3
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Ferrous Materials																	
1	7.0	...	7.0	...	7.0	...	7.0	7.0	...	...	...	...	...	...	...	...	...
2	7.0	...	7.0	...	7.0	...	7.0	7.0	...	...	...	...	...	...	...	...	...
3	14.5	14.5	14.5	...	14.5	...	14.5	...	14.5	14.5	14.5	14.5	14.5	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	20.2	20.2	20.2	...	20.2	...	20.2	...	20.2	20.2	20.2	20.2	...	...	...	...	...
6	20.2	...	20.2	...	20.2	...	20.2	...	20.2	...	20.2	20.2	20.2	...	...	...	...
7	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	...	...	...	...	...
8	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	...	...	...	...	...
9	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	23.0	...	...	...	...
10	25.0	25.0	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	...	...	...	...	...
11	28.0	28.0	28.0	...	28.0	...	28.0	...	28.0	...	28.0	28.0	...	...	...	...	...
12	30.0	30.0	30.0	...	30.0	...	30.0	...	30.0	30.0	30.0	30.0	...	...	...	...	...
13	25.0	25.0	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	...	...	...	...	...
14	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
15	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
16	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
17	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
18	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
19	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
20	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
21	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
22	23.0	...	23.0	...	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	...	...	...	...
23	24.0	...	24.0	...	24.0	...	24.0	...	24.0	...	24.0	24.0	24.0	...	...	...	...
24	27.0	...	27.0	...	27.0	...	27.0	...	27.0	...	27.0	27.0	27.0	...	...	...	...
25	29.0	...	29.0	...	29.0	...	29.0	...	29.0	...	29.0	29.0	29.0	...	...	...	...
26	31.0	...	31.0	...	31.0	...	31.0	...	31.0	...	31.0	31.0	31.0	...	...	...	...
27	33.0	...	33.0	...	33.0	...	33.0	...	33.0	...	33.0	33.0	33.0	...	...	...	...
28	18.8	18.8	18.8	...	18.8	...	18.8	...	18.8	18.8	18.8	18.8	18.8	18.8	18.0	16.3	12.5
29	20.0	20.0	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	18.5	16.3	12.5
30	20.0	20.0	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	18.5	16.3	12.5
31	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	23.0	22.2	20.0	16.3	12.5
32	25.0	25.0	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	23.6	21.0	16.3	12.5
33	25.0	25.0	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	23.6	21.0	...	...
34	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
35	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
36	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
37	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
38	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
39	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
40	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
41	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
42	20.0	20.0	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	18.8	16.7	...
43	22.0	22.0	22.0	...	22.0	...	22.0	...	22.0	...	22.0	22.0	22.0	22.0	21.0	18.5	...
44	23.0	...	23.0	...	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	...	...	...	...
45	24.0	...	24.0	...	24.0	...	24.0	...	24.0	...	24.0	24.0	24.0	...	...	...	...

Table 3
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials														
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	8.5	4.5	...	...	...	...	...	...	...	...	...	...	...	...	...
29	8.5	4.5	...	...	...	...	...	...	...	...	...	...	...	...	...
30	8.5	4.5	...	...	...	...	...	...	...	...	...	...	...	...	...
31	8.5	4.5	...	...	...	...	...	...	...	...	...	...	...	...	...
32	8.5	4.5	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	14.3	11.0	6.3	2.8	...	...	...	...	...	...	...	...	...	...	...
43	15.3	11.0	6.3	2.8	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.
Ferrous Materials (Cont'd)							
1	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...	$\leq 2\frac{1}{2}$
2	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	4	≤ 6
3	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	3	≤ 6
4	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	2	≤ 4
5	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	1	≤ 4
6	5Cr- $\frac{1}{2}$ Mo	Bolting	SA-193	B5	K50100	...	≤ 4
7	12Cr-1Mo-V-W	Bolting	SA-437	B4C	K91352	...	...
8	12Cr-1Mo-V-W	Bolting	SA-437	B4B	K91352	...	...
9	13Cr	Bolting	SA-193	B6	S41000	...	≤ 4
10	17Cr-4Ni-4Cu	Bolting	SA-564	630	S17400	H1150	≤ 8
11	17Cr-4Ni-4Cu	Bolting	SA-564	630	S17400	H1100	≤ 8
12	17Cr-4Ni-4Cu	Bolting	SA-705	630	S17400	H1100	≤ 8
13	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	8740	G87400	...	$\geq \frac{5}{8}$
14	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	8740	G87400	...	$\leq \frac{1}{2}$
15	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-320	L43	G43400	...	≤ 4
16	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	4340	G43400	...	$\geq \frac{5}{8}$
17	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	4340	G43400	...	$\leq \frac{1}{2}$
18	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	5	≤ 6
19	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	5	$6 < t \leq 9\frac{1}{2}$
20	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	4	$\leq 9\frac{1}{2}$
21	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	3	$\leq 9\frac{1}{2}$
22	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	2	$\leq 9\frac{1}{2}$
23	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23	H43400	1	≤ 8
24	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	5	≤ 6
25	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	5	$6 < t \leq 9\frac{1}{2}$
26	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	4	$\leq 9\frac{1}{2}$
27	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	3	$\leq 9\frac{1}{2}$
28	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	2	$\leq 9\frac{1}{2}$
29	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24	K24064	1	≤ 8
30	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo-V	Bolting	SA-540	B24V	K24070	3	≤ 11
31	$3\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	5	K42365	2	...
32	25Ni-15Cr-2Ti	Bolting	SA-453	660	S66286	A	...
33	25Ni-15Cr-2Ti	Bolting	SA-453	660	S66286	B	...
34	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	1	...
35	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	1	...
36	16Cr-12Ni-2Mo	Bolting	SA-320	B8MA	S31600	1A	...
37	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B	$2\frac{1}{2} < t \leq 3$
38	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
39	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
40	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B	$2 < t \leq 2\frac{1}{2}$
41	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2	$1 < t \leq 1\frac{1}{4}$
42	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2	$1 < t \leq 1\frac{1}{4}$
43	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B	≤ 2
44	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2	$\frac{3}{4} < t \leq 1$
45	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2	$\frac{3}{4} < t \leq 1$

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
			Ferrous Materials (Cont'd)				
1	125	105	800	1100	800	650	T8
2	135	120	700	700	700	650	...
3	145	130	700	700	700	650	...
4	155	140	700	700	700	650	...
5	165	150	700	700	700	650	...
6	100	80	800	1200	800	650	T5
7	115	85	700	700	700	650	...
8	145	105	700	700	700	650	...
9	110	85	800	900	800	650	T5
10	135	105	NP	650	650	NP	G4
11	140	115	650	650	650	650	G4
12	140	115	650	650	650	650	G4
13	170	135	550	NP	NP	NP	G7, G11, W1
14	180	140	550	NP	NP	NP	G7, G11, W1
15	125	105	400	400	700	400	...
16	170	135	550	550	NP	NP	G7, G11, W1
17	180	140	550	550	NP	NP	G7, G11, W1
18	120	105	700	700	700	650	...
19	115	100	700	700	700	650	...
20	135	120	700	700	700	650	...
21	145	130	700	700	700	650	...
22	155	140	700	700	700	650	...
23	165	150	700	700	700	650	...
24	120	105	700	700	700	650	...
25	115	100	700	700	700	650	...
26	135	120	700	700	700	650	...
27	145	130	700	700	700	650	...
28	155	140	700	700	700	650	...
29	165	150	700	700	700	650	...
30	145	130	700	700	700	650	...
31	115	100	NP	100	100	100	...
32	130	85	800	1000	800	650	...
33	130	85	800	1000	800	650	...
34	75	30	800	1500	800	650	G5, G6, T11
35	75	30	400	800	800	100	...
36	75	30	NP	800	800	100	...
37	80	55	NP	1000	800	650	G8, G9
38	90	50	800	800	NP	650	G8
39	90	50	NP	800	800	100	G8, G9
40	90	65	NP	1000	800	650	G8, G9
41	95	65	800	800	NP	650	G8
42	95	65	NP	800	800	100	G8
43	95	75	NP	1000	800	650	G8, G9
44	100	80	800	800	NP	650	G8
45	100	80	NP	800	800	100	G8

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Ferrous Materials (Cont'd)																	
1	25.0	25.0	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	25.0	25.0	23.5	20.5
2	27.0	...	27.0	...	27.0	...	27.0	...	27.0	...	27.0	27.0	27.0	...	...	...	...
3	29.0	...	29.0	...	29.0	...	29.0	...	29.0	...	29.0	29.0	29.0	...	...	...	...
4	31.0	...	31.0	...	31.0	...	31.0	...	31.0	...	31.0	31.0	31.0	...	...	...	...
5	33.0	...	33.0	...	33.0	...	33.0	...	33.0	...	33.0	33.0	33.0	...	...	...	...
6	20.0	20.0	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	18.5	14.5	10.4
7	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.3	21.3	21.3	...	...	...	...
8	26.2	...	26.2	...	26.2	...	26.2	...	26.2	...	26.2	26.2	26.2	...	...	...	...
9	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.3	21.3	21.3	21.3	21.3	17.2	12.3
10	26.3	...	26.3	...	26.3	...	26.3	...	26.3	...	26.3	26.3	...	...	...	...	...
11	28.0	...	28.0	...	28.0	...	28.0	...	28.0	...	28.0	28.0	...	...	...	...	...
12	28.0	...	28.0	...	28.0	...	28.0	...	28.0	...	28.0	28.0	...	...	...	...	...
13	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
14	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
15	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	...	...	...	...
16	33.8	...	33.8	...	33.8	...	33.8	...	33.8	33.8	...	...	...	...	...	...	...
17	35.0	...	35.0	...	35.0	...	35.0	...	35.0	35.0	...	...	...	...	...	...	...
18	24.0	24.0	24.0	...	24.0	...	24.0	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
19	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	23.0	...	...	...	...
20	27.0	27.0	27.0	...	27.0	...	27.0	...	27.0	27.0	27.0	27.0	27.0	...	...	...	...
21	29.0	29.0	29.0	...	29.0	...	29.0	...	29.0	29.0	29.0	29.0	29.0	...	...	...	...
22	31.0	...	31.0	...	31.0	...	31.0	...	31.0	...	31.0	31.0	31.0	...	...	...	...
23	33.0	...	33.0	...	33.0	...	33.0	...	33.0	...	33.0	33.0	33.0	...	...	...	...
24	24.0	24.0	24.0	...	24.0	...	24.0	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
25	23.0	23.0	23.0	...	23.0	...	23.0	...	23.0	23.0	23.0	23.0	23.0	...	...	...	...
26	27.0	27.0	27.0	...	27.0	...	27.0	...	27.0	27.0	27.0	27.0	27.0	...	...	...	...
27	29.0	29.0	29.0	...	29.0	...	29.0	...	29.0	29.0	29.0	29.0	29.0	...	...	...	...
28	31.0	...	31.0	...	31.0	...	31.0	...	31.0	...	31.0	31.0	31.0	...	...	...	...
29	33.0	...	33.0	...	33.0	...	33.0	...	33.0	...	33.0	33.0	33.0	...	...	...	...
30	29.0	...	29.0	...	29.0	...	29.0	...	29.0	...	29.0	29.0	29.0	...	...	...	...
31	23.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.3	21.3	21.3	21.3	21.3	21.3	21.3
33	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	21.3	21.3	21.3	21.3	21.3	21.3	21.3
34	18.8	...	17.7	...	15.6	...	14.3	...	13.3	...	12.6	12.3	12.1	11.9	11.7	11.6	11.5
35	18.8	...	17.7	...	15.6	...	14.3	...	13.3	...	12.6	12.3	12.1	11.9	11.7	...	...
36	18.8	...	17.7	...	15.6	...	14.3	...	13.3	...	12.6	12.3	12.1	11.9	11.7	...	...
37	18.8	...	17.7	...	15.6	...	14.3	...	13.8	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8
38	18.8	...	17.7	...	15.6	...	14.3	...	13.3	...	12.6	12.5	12.5	12.5	12.5	...	...
39	18.8	...	17.7	...	15.6	...	14.3	...	13.3	...	12.6	12.5	12.5	12.5	12.5	...	...
40	18.8	...	17.7	...	16.3	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3
41	18.8	...	17.7	...	16.3	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	...	...
42	18.8	...	17.7	...	16.3	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	...	...
43	18.8	...	18.8	...	18.8	...	18.8	...	18.8	...	18.8	18.8	18.8	18.8	18.8	18.8	18.8
44	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	...	...
45	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)														
1	16.0	11.0	6.3	2.8	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	7.6	5.6	4.2	3.1	2.0	1.3	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	21.3	21.3	...	...	...	...	...	...	...	...	...	...	...	...	...
33	21.3	21.3	...	...	...	...	...	...	...	...	...	...	...	...	...
34	11.4	11.3	11.2	11.0	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	13.8	13.8	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	16.3	16.3	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	18.8	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness in.
Ferrous Materials (Cont'd)							
1	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2	$\leq \frac{3}{4}$
2	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2	$\leq \frac{3}{4}$
3	16Cr-12Ni-2Mo-N	Bolting	SA-193	B8MNA	S31651	1A	...
4	18Cr-8Ni	Bolting	SA-193	B8	S30400	1	...
5	18Cr-8Ni	Bolting	SA-320	B8	S30400	1	...
6	18Cr-8Ni	Bolting	SA-320	B8A	S30400	1A	...
7	18Cr-8Ni	Bolting	SA-193	B8	S30400	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
8	18Cr-8Ni	Bolting	SA-320	B8	S30400	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
9	18Cr-8Ni	Bolting	SA-193	B8	S30400	2	$1 < t \leq 1\frac{1}{4}$
10	18Cr-8Ni	Bolting	SA-320	B8	S30400	2	$1 < t \leq 1\frac{1}{4}$
11	18Cr-8Ni	Bolting	SA-193	B8	S30400	2	$\frac{3}{4} < t \leq 1$
12	18Cr-8Ni	Bolting	SA-320	B8	S30400	2	$\frac{3}{4} < t \leq 1$
13	18Cr-8Ni	Bolting	SA-193	B8	S30400	2	$\leq \frac{3}{4}$
14	18Cr-8Ni	Bolting	SA-320	B8	S30400	2	$\leq \frac{3}{4}$
15	18Cr-8Ni-N	Bolting	SA-193	B8NA	S30451	1A	...
(25) 16	18Cr-8Ni-S	Bolting	SA-320	B8F	S30300	1	...
(25) 17	18Cr-8Ni-S	Bolting	SA-320	B8FA	S30300	1A	...
18	18Cr-8Ni-Se	Bolting	SA-320	B8F	S30323	1	...
19	18Cr-8Ni-Se	Bolting	SA-320	B8FA	S30323	1A	...
20	18Cr-8Ni-4Si-N	Bolting	SA-193	B8S	S21800	...	...
21	18Cr-8Ni-4Si-N	Bolting	SA-193	B8SA	S21800	...	...
22	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	1	...
23	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	1	...
24	18Cr-10Ni-Cb	Bolting	SA-320	B8CA	S34700	1A	...
25	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
26	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
27	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2	$1 < t \leq 1\frac{1}{4}$
28	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2	$1 < t \leq 1\frac{1}{4}$
29	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2	$\frac{3}{4} < t \leq 1$
30	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2	$\frac{3}{4} < t \leq 1$
31	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2	$\leq \frac{3}{4}$
32	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2	$\leq \frac{3}{4}$
33	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	1	...
34	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	1	...
35	18Cr-10Ni-Ti	Bolting	SA-320	B8TA	S32100	1A	...
36	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
37	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$
38	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2	$1 < t \leq 1\frac{1}{4}$
39	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2	$1 < t \leq 1\frac{1}{4}$
40	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2	$\frac{3}{4} < t \leq 1$
41	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2	$\frac{3}{4} < t \leq 1$
42	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2	$\leq \frac{3}{4}$
43	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2	$\leq \frac{3}{4}$
44	18Cr-11Ni	Bolting	SA-193	B8P	S30500	1	...
45	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
Ferrous Materials (Cont'd)							
1	110	95	800	800	NP	650	G8
2	110	95	NP	800	800	100	G8
3	75	30	800	1000	800	650	G5
4	75	30	800	1500	800	650	G5, G6, T10
5	75	30	400	800	800	100	...
6	75	30	NP	800	800	100	...
7	100	50	NP	1000	800	650	G8, G9
8	100	50	NP	1000	800	100	G8
9	105	65	NP	1000	800	650	G8, G9
10	105	65	NP	1000	800	100	G8
11	115	80	NP	1000	800	650	G8, G9
12	115	80	NP	1000	800	100	G8
13	125	100	NP	1000	800	650	G8, G9
14	125	100	NP	1000	800	100	G8
15	75	30	800	1000	800	650	G5
16	75	30	400	400	400	100	...
17	75	30	NP	400	400	100	...
18	75	30	400	400	400	100	...
19	75	30	NP	400	400	100	...
20	95	50	NP	950	800	650	...
21	95	50	NP	950	800	650	...
22	75	30	800	1500	800	650	G5, G6, T9
23	75	30	400	800	800	100	...
24	75	30	NP	800	800	100	...
25	100	50	NP	100	100	100	G8
26	100	50	NP	100	100	100	G8
27	105	65	NP	100	100	100	G8
28	105	65	NP	100	100	100	G8
29	115	80	NP	100	100	100	G8
30	115	80	NP	100	100	100	G8
31	125	100	NP	100	100	100	G8
32	125	100	NP	100	100	100	G8
33	75	30	800	1500	800	650	G5, G6, T9
34	75	30	400	800	800	100	...
35	75	30	NP	800	800	100	...
36	100	50	NP	1000	800	650	G8
37	100	50	NP	800	800	100	G8
38	105	65	NP	1000	800	650	G8
39	105	65	NP	800	800	100	G8
40	115	80	NP	1000	800	650	G8
41	115	80	NP	800	800	100	G8
42	125	100	NP	1000	800	650	G8
43	125	100	NP	800	800	100	G8
44	75	30	NP	1500	800	650	T10
45	100	50	NP	1000	800	650	G8

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Ferrous Materials (Cont'd)																	
1	22.0	...	22.0	...	22.0	...	22.0	...	22.0	...	22.0	22.0	22.0	22.0	22.0	...	...
2	22.0	...	22.0	...	22.0	...	22.0	...	22.0	...	22.0	22.0	22.0	22.0	22.0	...	...
3	18.8	...	17.8	...	16.3	...	15.2	...	14.2	...	13.4	13.1	12.8	12.5	12.3	12.0	11.8
4	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.1	12.0	11.8	11.5	11.2	11.0	10.8
5	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.1	12.0	11.8	11.5	11.2	...	...
6	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.1	12.0	11.8	11.5	11.2	...	...
7	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5
8	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5
9	18.8	...	16.7	...	16.3	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3
10	18.8	...	16.7	...	16.3	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3
11	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0
12	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0
13	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	25.0	25.0
14	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	25.0	25.0
15	18.8	...	16.5	...	14.4	...	12.9	...	12.0	...	11.4	11.2	11.0	10.8	10.6	10.4	10.2
16	18.8	...	15.0	...	13.6	...	12.6	...	...	...	...	...	...	...	...	...	...
17	18.8	...	15.0	...	13.6	...	12.6	...	...	...	...	...	...	...	...	...	...
18	18.8	...	15.0	...	13.6	...	12.6	...	...	...	...	...	...	...	...	...	...
19	18.8	...	15.0	...	13.6	...	12.6	...	...	...	...	...	...	...	...	...	...
20	23.8	...	23.4	...	21.8	...	19.7	...	18.5	...	17.6	17.3	17.1	16.9	16.7	16.7	16.7
21	23.8	...	23.4	...	21.8	...	19.7	...	18.5	...	17.6	17.3	17.1	16.9	16.7	16.7	16.7
22	18.8	...	17.9	...	16.4	...	15.5	...	15.0	...	14.3	14.1	13.8	13.7	13.6	13.5	13.5
23	18.8	...	17.9	...	16.4	...	15.5	...	15.0	...	14.3	14.1	13.8	13.7	13.6	...	...
24	18.8	...	17.9	...	16.4	...	15.5	...	15.0	...	14.3	14.1	13.8	13.7	13.6	...	...
25	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	25.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	25.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	18.8	...	17.8	...	16.5	...	15.3	...	14.3	...	13.5	13.3	12.9	12.7	12.5	12.4	12.3
34	18.8	...	17.8	...	16.5	...	15.3	...	14.3	...	13.5	13.3	12.9	12.7	12.5	...	...
35	18.8	...	17.8	...	16.5	...	15.3	...	14.3	...	13.5	13.3	12.9	12.7	12.5	...	...
36	18.8	...	17.8	...	16.5	...	15.3	...	14.3	...	13.5	13.3	12.9	12.7	12.5	12.5	12.5
37	18.8	...	17.8	...	16.5	...	15.3	...	14.3	...	13.5	13.3	12.9	12.7	12.5	...	...
38	18.8	...	17.8	...	16.5	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3
39	18.8	...	17.8	...	16.5	...	16.3	...	16.3	...	16.3	16.3	16.3	16.3	16.3	...	...
40	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0
41	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	...	...
42	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	25.0	25.0
43	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	...	...
44	18.8	...	16.7	...	15.0	...	13.8	...	12.9	...	12.1	12.0	11.8	11.5	11.2	11.0	10.8
45	18.8	...	18.8	...	18.8	...	18.8	...	18.8	...	18.8	18.8	18.8	18.8	18.7	18.3	18.0

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)														
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	11.6	11.4	...	...	...	...	...	...	...	...	...	...	...	...	...
4	10.6	10.4	10.1	9.8	7.7	6.0	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	12.5	12.5	...	...	...	...	...	...	...	...	...	...	...	...	...
8	12.5	12.5	...	...	...	...	...	...	...	...	...	...	...	...	...
9	16.3	16.3	...	...	...	...	...	...	...	...	...	...	...	...	...
10	16.3	16.3	...	...	...	...	...	...	...	...	...	...	...	...	...
11	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...
12	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...
13	24.8	24.1	...	...	...	...	...	...	...	...	...	...	...	...	...
14	24.8	24.1	...	...	...	...	...	...	...	...	...	...	...	...	...
15	9.9	9.7	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	16.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	16.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	13.4	13.4	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	12.1	12.0	9.6	6.9	5.0	3.6	2.5	1.7	1.1	0.80	0.50	0.30	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	12.5	12.5	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	16.3	16.3	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	25.0	25.0	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	10.6	10.4	10.1	9.8	7.7	6.0	4.7	3.7	2.9	2.3	1.8	1.4	...	...	...
45	17.7	17.3	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

(25)

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness in.
Ferrous Materials (Cont'd)							
1	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2	$1 < t \leq 1\frac{1}{4}$
2	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2	$\frac{1}{4} < t \leq 1$
3	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2	$\leq \frac{3}{4}$
4	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B	>3
5	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B	>3
6	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B	≤ 3
7	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B	≤ 3
8	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A	>3
9	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A	>3
10	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A	≤ 3
11	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A	≤ 3
12	22Cr-13Ni-5Mn	Bolting	SA-479	XM-19	S20910	Annealed	...
13	22Cr-13Ni-5Mn	Bolting	SA-479	XM-19	S20910	Hot rolled	$3 < t \leq 8$
14	22Cr-13Ni-5Mn	Bolting	SA-479	XM-19	S20910	Hot rolled	$2 < t \leq 3$
15	22Cr-13Ni-5Mn	Bolting	SA-479	XM-19	S20910	Hot rolled	≤ 2
16	23Cr-25Ni-5.5Mo-N	Bolting	SA-193	...	S32053	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
Ferrous Materials (Cont'd)							
1	105	65	NP	1000	800	650	G8
2	115	80	NP	1000	800	650	G8
3	125	100	NP	1000	800	650	G8
4	95	50	800	NP	NP	NP	...
5	95	50	NP	1000	800	650	...
6	95	60	800	NP	NP	NP	...
7	95	60	NP	1000	800	650	...
8	100	60	800	NP	NP	NP	...
9	100	60	NP	1000	800	650	...
10	100	70	800	NP	NP	NP	...
11	100	70	NP	1000	800	650	...
12	100	55	NP	1150	800	650	T9
13	100	60	NP	1150	800	650	T9
14	115	75	NP	1150	800	650	T9
15	135	105	NP	1150	800	650	T9
16	93	43	NP	662	NP	NP	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Ferrous Materials (Cont'd)																	
1	18.8	...	18.8	...	18.8	...	18.8	...	18.8	...	18.8	18.8	18.8	18.8	18.8	18.8	18.8
2	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	20.0	20.0	20.0	20.0	20.0	20.0
3	25.0	...	25.0	...	25.0	...	25.0	...	25.0	...	25.0	25.0	25.0	25.0	25.0	25.0	25.0
4	12.5	...	11.4	...	10.6	...	10.0	...	9.5	...	9.0	8.8	8.6	8.4	8.3	...	...
5	12.5	...	11.5	...	10.7	...	10.0	...	9.5	...	9.0	8.8	8.7	8.5	8.3	8.2	8.0
6	15.0	...	13.7	...	12.7	...	12.0	...	11.5	...	10.9	10.6	10.4	10.1	9.9	...	...
7	15.0	...	13.8	...	12.8	...	12.1	...	11.5	...	10.9	10.6	10.4	10.2	10.0	9.8	9.6
8	15.0	...	13.7	...	12.7	...	12.0	...	11.5	...	10.9	10.6	10.4	10.1	9.9	...	...
9	15.0	...	13.8	...	12.8	...	12.1	...	11.5	...	10.9	10.7	10.4	10.2	10.0	9.8	9.6
10	17.5	...	16.0	...	14.8	...	14.0	...	13.4	...	12.7	12.4	12.1	11.8	11.6	...	...
11	17.5	...	16.1	...	14.9	...	14.1	...	13.4	...	12.7	12.4	12.2	11.9	11.6	11.4	11.2
12	25.0	...	24.9	...	23.6	...	22.7	...	22.3	...	21.9	21.8	21.6	21.4	21.2	20.9	20.6
13	25.0	...	24.9	...	23.6	...	22.7	...	22.3	...	21.9	21.8	21.6	21.4	21.2	20.9	20.6
14	25.0	...	24.9	...	23.6	...	22.7	...	22.3	...	21.9	21.8	21.6	21.4	21.2	20.9	20.6
15	26.2	...	26.2	...	26.2	...	26.2	...	26.2	...	26.2	26.2	26.2	26.2	26.2	26.2	26.2
16	26.5	...	24.2	...	21.9	...	20.8	...	19.3	...	18.5	18.2	17.9	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)														
1	18.8	18.8	...	...	...	...	...	...	...	...	...	...	...	...	...
2	20.0	20.0	...	...	...	...	...	...	...	...	...	...	...	...	...
3	24.8	24.1	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	7.9	7.7	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	9.4	9.2	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	9.4	9.2	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	11.0	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...
12	20.3	19.9	19.0	13.0	8.3	...	...	...	...	...	...	...	...	...	...
13	20.3	19.9	19.0	13.0	8.3	...	...	...	...	...	...	...	...	...	...
14	20.3	19.9	19.0	13.0	8.3	...	...	...	...	...	...	...	...	...	...
15	26.2	26.2	19.0	13.0	8.3	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.
Nonferrous Materials							
1	...	Bolting	SB-211	2014	A92014	T6	0.125–8.000
2	...	Bolting	SB-211	2014	A92014	T651	0.125–8.000
3	...	Bolting	SB-211	2024	A92024	T4	0.125–0.499
4	...	Bolting	SB-211	2024	A92024	T4	0.500–4.500
5	...	Bolting	SB-211	2024	A92024	T4	4.501–6.500
6	...	Bolting	SB-211	2024	A92024	T4	6.501–8.000
7	...	Bolting	SB-211	6061	A96061	T6	0.125–8.000
8	...	Bolting	SB-211	6061	A96061	T651	0.125–8.000
9	...	Bar, rod	SB-187	...	C10200	O60	All
10	...	Bar, rod	SB-187	...	C11000	O60	All
(25) 11	...	Round rod	SB-150	...	C61400	HR50	$2 < t \leq 3$
(25) 12	...	Round rod	SB-150	...	C61400	HR50	$1 < t \leq 2$
(25) 13	...	Round rod	SB-150	...	C61400	HR50	$\frac{1}{2} < t \leq 1$
(25) 14	...	Round rod	SB-150	...	C61400	HR50	$\leq \frac{1}{2}$
15	...	Round rod	SB-150	...	C62300	HR50	> 3
(25) 16	...	Round rod	SB-150	...	C62300	M20, M30	> 3
(25) 17	...	...	...	...	...	...	...
(25) 18	...	Round rod	SB-150	...	C62300	O20, O25, O30	> 3
19	...	Hex/oct rod & bar	SB-150	...	C62300	M20	> 2
20	...	Hex/oct rod & bar	SB-150	...	C62300	HR50	$1 < t \leq 2$
21	...	Hex/oct rod & bar	SB-150	...	C62300	HR50	≤ 1
22	...	Round rod	SB-150	...	C62300	HR50	$2 < t \leq 3$
23	...	Round rod	SB-150	...	C62300	HR50	$1 < t \leq 2$
24	...	Round rod	SB-150	...	C62300	HR50	$\frac{1}{2} < t \leq 1$
25	...	Round rod	SB-150	...	C62300	HR50	$\leq \frac{1}{2}$
26	...	Bar, rod	SB-150	...	C63000	M20, M30	> 4
27	...	Bar, rod	SB-150	...	C63000	O20, O25, O30	> 4
28	...	Bar, rod	SB-150	...	C63000	HR50	> 4
29	...	Bar, rod	SB-150	...	C63000	HR50	$2 < t \leq 4$
30	...	Bar, rod	SB-150	...	C63000	M20, M30	$2 < t \leq 4$
31	...	Bar, rod	SB-150	...	C63000	O20, O25, O30	$2 < t \leq 4$
32	...	Bar, rod	SB-150	...	C63000	HR50	$1 < t \leq 2$
33	...	Bar, rod	SB-150	...	C63000	HR50	$\frac{1}{2} < t \leq 1$
34	...	Bar, rod	SB-150	...	C64200	M10, M20, M30	> 4
(25) 35	...	Bar, rod	SB-150	...	C64200	M10, M20, M30	$3 < t \leq 4$
36	...	Bar, rod	SB-150	...	C64200	HR50	$2 < t \leq 3$
37	...	Bar, rod	SB-150	...	C64200	HR50	$1 < t \leq 2$
38	...	Bar, rod	SB-150	...	C64200	HR50	$\frac{1}{2} < t \leq 1$
39	...	Bar, rod	SB-150	...	C64200	HR50	$\leq \frac{1}{2}$
(25) 40	...	Bar, rod	SB-98	...	C65100	O60	All
41	...	Rod	SB-98	...	C65100	H06	$1 < t \leq 1\frac{1}{2}$
42	...	Rod	SB-98	...	C65100	H06	$\frac{1}{2} < t \leq 1$
43	...	Rod	SB-98	...	C65100	H06	$\leq \frac{1}{2}$
(25) 44	...	Bar, rod	SB-98	...	C65500	O60	All
(25) 45	...	Bar, rod	SB-98	...	C65500	H01	All

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
Nonferrous Materials							
1	65	55	400 (Cl. 3 only)	400	400	400	T1, W4
2	65	55	NP	400	400	400	G10, T1, W4
3	62	45	400 (Cl. 3 only)	400	400	400	T1, W4
4	62	42	400 (Cl. 3 only)	400	400	400	T1, W4
5	62	40	400 (Cl. 3 only)	400	400	400	T2, W4
6	58	38	400 (Cl. 3 only)	400	400	400	T2, W4
7	42	35	400 (Cl. 3 only)	400	400	400	T2, W4
8	42	35	NP	400	400	400	G10, T2, W4
9	28	8	NP	400	400	400	T2
10	28	8	NP	400	400	400	T2
11	70	30	500 (Cl. 3 only)	500	500	500	...
12	70	32	500 (Cl. 3 only)	500	500	500	...
13	75	35	500 (Cl. 3 only)	500	500	500	...
14	80	40	500 (Cl. 3 only)	500	500	500	...
15	75	30	400 (Cl. 3 only)	600	400	600	T3, W1
16	75	30	400 (Cl. 3 only)	600	400	600	T3, W1
17	...	...	...	...	...	...	...
18	75	30	400 (Cl. 3 only)	600	400	600	T3, W1
19	75	30	400 (Cl. 3 only)	600	400	600	T3, W1
20	78	32	400 (Cl. 3 only)	600	400	600	T3, W1
21	80	35	400 (Cl. 3 only)	600	400	600	T3, W1
22	76	37	400 (Cl. 3 only)	600	400	600	T3, W1
23	84	40	400 (Cl. 3 only)	600	400	600	T3, W1
24	88	44	400 (Cl. 3 only)	600	400	600	T3, W1
25	90	50	400 (Cl. 3 only)	600	400	600	T3, W1
26	80	40	700 (Cl. 3 only)	700	500	650	T4, W4
27	80	40	700 (Cl. 3 only)	700	500	650	T4, W4
28	80	40	700 (Cl. 3 only)	700	500	650	T4, W4
29	85	42.5	700 (Cl. 3 only)	700	500	650	T4, W4
30	85	42.5	700 (Cl. 3 only)	700	500	650	T4, W4
31	85	42.5	700 (Cl. 3 only)	700	500	650	T4, W4
32	90	45	700 (Cl. 3 only)	700	500	650	T4, W4
33	100	50	700 (Cl. 3 only)	700	500	650	T4, W4
34	70	25	350 (Cl. 3 only)	600	350	600	T13, W1
35	70	30	350 (Cl. 3 only)	600	350	600	T13, W1
36	75	35	350 (Cl. 3 only)	600	350	600	T13, W1
37	80	42	350 (Cl. 3 only)	600	350	600	T13, W1
38	85	45	350 (Cl. 3 only)	600	350	600	T13, W1
39	90	45	350 (Cl. 3 only)	600	350	600	T13, W1
40	40	12	350 (Cl. 3 only)	350	350	350	G2
41	75	40	350 (Cl. 3 only)	350	350	350	G2, W2
42	75	45	350 (Cl. 3 only)	350	350	350	G2, W2
43	85	55	350 (Cl. 3 only)	350	350	350	G2, W2
44	52	15	350 (Cl. 3 only)	350	350	350	G2
45	55	24	350 (Cl. 3 only)	NP	350	NP	G2, W2

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Nonferrous Materials																	
1	13.0	13.0	13.0	13.0	11.4	6.8	3.9	...	...	...	...	...	...	...	...	...	...
2	13.0	13.0	13.0	13.0	11.4	6.8	3.9	...	...	...	...	...	...	...	...	...	...
3	11.3	11.3	11.3	11.3	10.4	6.5	4.5	...	...	...	...	...	...	...	...	...	...
4	10.5	10.5	10.5	10.5	10.4	6.5	4.5	...	...	...	...	...	...	...	...	...	...
5	10.0	10.0	10.0	10.0	10.0	6.5	4.5	...	...	...	...	...	...	...	...	...	...
6	9.5	9.5	9.5	9.5	9.5	6.1	4.2	...	...	...	...	...	...	...	...	...	...
7	8.4	8.4	8.4	8.4	8.4	6.3	4.4	...	...	...	...	...	...	...	...	...	...
8	8.4	8.4	8.4	8.4	8.4	6.3	4.4	...	...	...	...	...	...	...	...	...	...
9	5.3	4.7	4.7	4.7	4.7	4.4	3.0	...	...	...	...	...	...	...	...	...	...
10	5.3	4.7	4.7	4.7	4.7	4.4	3.0	...	...	...	...	...	...	...	...	...	...
11	17.5	17.5	17.5	17.5	17.5	17.5	17.2	16.6	16.1	...	...	...	...	...	...	...	...
12	17.5	17.5	17.5	17.5	17.5	17.5	17.2	16.6	16.1	...	...	...	...	...	...	...	...
13	17.5	17.5	17.5	17.5	17.5	17.5	17.2	16.6	16.1	...	...	...	...	...	...	...	...
14	17.5	17.5	17.5	17.5	17.5	17.5	17.2	16.6	16.1	...	...	...	...	...	...	...	...
15	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
16	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
19	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
20	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
21	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
22	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
23	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
24	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
25	18.8	18.8	18.8	18.8	18.7	18.1	17.7	16.0	12.5	10.6	9.9	...	...	...	...	...	...
26	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
28	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
29	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
30	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	16.4	12.0	8.5	6.0	...	...	...	...
31	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	21.3	16.4	12.0	8.5	6.0	...	...	...	...
32	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
33	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.4	12.0	8.5	6.0	...	...	...	...
34	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
35	17.5	17.5	17.5	17.5	17.5	17.5	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
36	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
37	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
38	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
39	16.7	16.7	15.6	15.4	15.4	15.4	11.0	7.5	5.2	2.5	1.7	...	...	...	...	...	...
40	8.0	7.9	7.9	7.8	7.8	7.7	...	...	...	...	...	...	...	...	...	...	...
41	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
42	11.3	11.3	11.3	11.3	11.3	11.3	...	...	...	...	...	...	...	...	...	...	...
43	13.8	13.8	13.8	13.8	13.8	13.8	...	...	...	...	...	...	...	...	...	...	...
44	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...
45	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials														
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.
Nonferrous Materials (Cont'd)							
(25) 1	...	Bar, rod	SB-98	...	C65500	H02	≤2
(25) 2	...	Bar, rod	SB-98	...	C66100	O60	All
(25) 3	...	Bar, rod	SB-98	...	C66100	H01	All
(25) 4	...	Bar, rod	SB-98	...	C66100	H02	≤2
5	99Ni	Bolting	SB-160	...	N02200	Annealed	...
6	99Ni	Bolting	SB-160	...	N02200	Hot fin./ann.	...
7	99Ni	Bolting	SB-160	...	N02200	Cold drawn	...
8	99Ni-Low C	Bolting	SB-160	...	N02201	Hot fin./ann.	...
9	67Ni-30Cu	Bolting	SB-164	...	N04400	HW or CW ann.	All
10	67Ni-30Cu	Bolting	SB-164	...	N04400	Hot worked	12 < t ≤ 14
11	67Ni-30Cu	Bolting	SB-164	...	N04400	Hot worked	≤12
12	67Ni-30Cu	Bolting	SB-164	...	N04400	CD-str. rel.	≤12
13	67Ni-30Cu	Bolting	SB-164	...	N04400	Cold worked	≤12
14	67Ni-30Cu	Bolting	SB-164	...	N04400	CD-str. rel.	$\frac{1}{2} < t \leq 3\frac{1}{2}$
15	67Ni-30Cu-S	Bolting	SB-164	...	N04405	Annealed	...
16	67Ni-30Cu-S	Bolting	SB-164	...	N04405	Annealed	...
17	67Ni-30Cu-S	Bolting	SB-164	...	N04405	Hot worked	...
18	67Ni-30Cu-S	Bolting	SB-164	...	N04405	Hot worked	...
19	67Ni-30Cu-S	Bolting	SB-164	...	N04405	Cold worked	...
20	67Ni-28Cu-3Al	Bolting	SF-468	...	N05500	Ann./aged	1.000-1.500
21	67Ni-28Cu-3Al	Bolting	SF-468	...	N05500	Ann./aged	0.250-0.875
22	47Ni-22Cr-9Mo-18Fe	Bolting	SB-572	...	N06002	Annealed	...
23	47Ni-22Cr-19Fe-6Mo	Bolting	SB-581	...	N06007	Solution ann.	$>\frac{3}{4}$
24	47Ni-22Cr-19Fe-6Mo	Bolting	SB-581	...	N06007	Solution ann.	$<\frac{3}{4}$
25	55Ni-21Cr-13.5Mo	Bolting	SB-574	...	N06022	Solution ann.	...
26	40Ni-29Cr-15Fe-5Mo	Bolting	SB-581	...	N06030	Solution ann.	...
27	61Ni-16Mo-16Cr	Bolting	SB-574	...	N06455	Solution ann.	...
28	72Ni-15Cr-8Fe	Bolting	SB-166	...	N06600	Annealed	...
29	72Ni-15Cr-8Fe	Bolting	SB-166	...	N06600	Hot fin.	...
30	72Ni-15Cr-8Fe	Bolting	SB-166	...	N06600	Cold drawn	...
31	72Ni-15Cr-8Fe	Bolting	SB-166	...	N06600	Hot fin.	...
32	72Ni-15Cr-8Fe	Bolting	SB-166	...	N06600	Hot fin.	...
33	60Ni-22Cr-9Mo-3.5Cb	Bolting	SB-446	1	N06625	Annealed	...
34	49Ni-25Cr-18Fe-6Mo	Bolting	SB-581	...	N06975	Solution ann.	...
35	53Ni-19Cr-19Fe-Cb-Mo	Bolting	SB-637	...	N07718	Ann./aged	≤6
36	70Ni-16Cr-7Fe-Ti-Al	Bolting	SB-637	2	N07750	Ann./aged	...
37	26Ni-43Fe-22Cr-5Mo	Bolting	SB-621	...	N08320	Solution ann.	...
38	46Fe-24Ni-21Cr-6Mo-N	Bolting	SB-691	...	N08367	Solution ann.	...
39	33Ni-42Fe-21Cr	Bolting	SB-408	...	N08800	Annealed	...
40	33Ni-42Fe-21Cr	Bolting	SB-408	...	N08810	Annealed	...
41	42Ni-21.5Cr-3Mo-2.3Cu	Bolting	SB-425	...	N08825	Annealed	...
42	62Ni-28Mo-5Fe	Bolting	SB-335	...	N10001	Annealed	$1\frac{1}{2} < t \leq 3\frac{1}{2}$
43	62Ni-28Mo-5Fe	Bolting	SB-335	...	N10001	Annealed	≤1 $\frac{1}{2}$
44	70Ni-16Mo-7Cr-5Fe	Bolting	SB-573	...	N10003	Annealed	...
45	54Ni-16Mo-15Cr	Bolting	SB-574	...	N10276	Solution ann.	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
Nonferrous Materials (Cont'd)							
1	70	38	350 (Cl. 3 only)	NP	350	NP	G2, W2
2	52	15	350 (Cl. 3 only)	350	350	350	G2
3	55	24	350 (Cl. 3 only)	NP	350	NP	G2, W2
4	70	38	350 (Cl. 3 only)	NP	350	NP	G2, W2
5	55	15	600 (Cl. 3 only)	600	600	600	...
6	60	15	600 (Cl. 3 only)	600	600	600	...
7	65	40	600 (Cl. 3 only)	600	600	600	...
8	50	10	600 (Cl. 3 only)	1200	800	650	T5
9	70	25	800	900	800	650	T5
10	75	30	800	900	800	650	T5
11	80	40	800	900	800	650	T5
12	84	50	500	500	500	500	G3
13	85	55	500	500	500	500	G3
14	87	60	NP	500	500	500	G3
15	70	25	800	NP	NP	NP	...
16	70	25	NP	900	800	650	T5
17	75	35	800	NP	NP	NP	...
18	75	35	NP	900	800	650	T5
19	85	50	500	500	500	500	G3
20	130	85	NP	500	NP	NP	...
21	130	90	NP	500	NP	NP	...
22	95	35	NP	1650	800	650	T11
23	85	30	NP	1000	800	650	...
24	90	35	NP	1000	800	650	...
25	100	45	NP	800	800	650	...
26	85	35	NP	800	800	650	...
27	100	40	NP	800	800	650	...
28	80	35	800	1200	800	650	T6
29	85	35	800	1200	800	650	T7
30	90	40	NP	500	500	500	G3, H1
31	90	40	800	NP	NP	NP	...
32	90	40	NP	1200	800	650	T7
33	120	60	NP	1200	800	650	G1, T11
34	85	32	NP	800	800	650	...
35	185	150	800	1150	800	650	W4, W5
36	170	115	800	800	800	650	...
37	75	28	NP	800	800	650	...
38	95	45	800	800	NP	NP	...
39	75	30	NP	1500	800	650	T10
40	65	25	NP	1650	800	650	T11
41	85	35	NP	1000	800	650	...
42	100	46	800	800	800	650	...
43	115	46	800	800	800	650	...
44	100	40	NP	1300	800	650	T10
45	100	41	NP	1250	800	650	T10

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
Nonferrous Materials (Cont'd)																	
1	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...
2	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...
3	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...
4	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...	...	...	...	...	...	...	...	...
5	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
6	10.0	10.0	10.0	10.0	10.0	10.0	10.0	9.8	9.5	8.9	8.3	...	...	...	...	...	...
7	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
8	6.7	6.6	6.4	6.3	6.3	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.2	6.0	5.9	5.8	4.8
9	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.1	12.9	12.7	11.0	8.0
10	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.1	12.9	12.7	11.0	8.0
11	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.0	12.9	12.7	8.5	4.0
12	16.7	...	14.6	...	13.6	...	13.2	...	13.1	...	...	...	...	...	...	...	...
13	16.7	...	14.6	...	13.8	...	13.8	...	13.8	...	...	...	...	...	...	...	...
14	16.7	...	15.0	...	15.0	...	15.0	...	15.0	...	...	...	...	...	...	...	...
15	16.6	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.1	12.9	12.7	...	...
16	16.6	...	14.6	...	13.6	...	13.2	...	13.1	...	13.1	13.1	13.1	13.0	12.7	11.0	8.0
17	18.7	...	18.7	...	18.7	...	18.7	...	18.7	...	18.7	18.4	18.0	16.3	14.5	...	...
18	18.7	...	18.7	...	18.7	...	18.7	...	18.7	...	18.7	18.7	18.0	17.2	14.5	8.5	4.0
19	12.5	...	12.5	...	12.5	...	12.5	...	12.5	...	...	...	...	...	...	...	...
20	21.3	...	21.3	...	21.3	...	21.3	...	21.3	...	...	...	...	...	...	...	...
21	22.5	...	22.5	...	22.5	...	22.5	...	22.5	...	...	...	...	...	...	...	...
22	23.3	...	20.9	...	19.2	...	17.8	...	16.5	...	15.6	15.3	15.0	14.9	14.7	14.6	14.5
23	20.0	...	19.9	...	16.6	...	15.6	...	15.0	...	14.4	14.2	14.0	13.9	13.8	13.7	13.6
24	22.5	...	20.9	...	19.5	...	18.2	...	17.4	...	16.8	16.6	16.4	16.3	16.1	16.0	16.0
25	25.0	...	25.0	...	24.5	...	22.7	...	21.2	...	20.1	19.6	19.2	18.9	18.6	...	...
26	21.3	...	20.0	...	18.3	...	17.2	...	16.4	...	15.8	15.5	15.2	14.9	14.6	...	...
27	25.0	...	24.6	...	23.0	...	21.7	...	20.9	...	20.1	19.8	19.6	19.4	19.1	...	...
28	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	20.0	19.8	19.6	19.4	19.1	18.7	16.0
29	21.2	...	21.2	...	21.2	...	21.2	...	21.2	...	21.2	21.2	21.1	21.0	20.4	20.2	19.5
30	20.0	...	20.0	...	20.0	...	20.0	...	20.0	...	...	...	...	...	...	...	...
31	10.0	...	9.5	...	9.2	...	9.1	...	9.1	...	9.1	9.0	8.9	8.9	8.8	...	...
32	21.2	...	21.2	...	21.2	...	21.2	...	21.2	...	21.2	21.2	21.1	21.0	20.4	20.2	19.5
33	30.0	...	30.0	...	30.0	...	28.2	...	27.0	...	26.4	26.2	26.0	26.0	24.6	24.3	24.0
34	21.3	...	19.6	...	18.4	...	17.6	...	16.5	...	15.6	15.3	15.1	14.9	14.7	...	...
35	37.0	...	36.0	...	35.2	...	34.6	...	34.2	...	33.8	33.7	33.6	33.5	33.3	33.1	32.9
36	28.7	...	28.7	...	28.7	...	28.7	...	28.7	...	28.7	28.7	28.7	28.7	28.7	...	...
37	18.7	...	17.3	...	16.4	...	15.3	...	14.6	...	13.7	13.5	13.2	12.9	12.8	...	...
38	23.8	...	23.8	...	22.4	...	21.5	...	20.5	...	19.4	19.0	18.6	18.3	18.0	...	...
39	18.7	...	18.7	...	17.9	...	17.2	...	16.7	...	16.3	16.1	15.9	15.7	15.5	15.3	15.1
40	16.2	...	15.4	...	14.5	...	13.5	...	12.9	...	12.2	11.9	11.7	11.4	11.1	10.9	10.7
41	21.2	...	21.2	...	20.4	...	19.2	...	18.3	...	17.8	17.6	17.3	17.2	17.1	16.9	16.8
42	25.0	...	25.0	...	25.0	...	24.7	...	24.3	...	23.7	23.4	23.0	22.8	22.5	...	...
43	28.8	...	27.8	...	26.3	...	25.1	...	24.3	...	23.5	23.3	23.0	22.8	22.6	...	...
44	25.0	...	24.0	...	23.0	...	21.0	...	20.0	...	20.0	19.5	19.0	18.5	18.0	17.7	17.5
45	25.0	...	25.0	...	23.0	...	21.2	...	20.0	...	18.8	18.3	17.8	17.4	17.1	16.8	16.6

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3,* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)														
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	3.7	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	14.4	14.3	14.2	14.2	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.3	1.7	1.2
23	13.6	13.5	...	...	...	...	...	...	...	...	...	...	...	...	...
24	15.9	15.8	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	10.6	7.0	4.5	3.0	2.2	2.2	...	...	...	...	...	...	...	...	...
29	19.3	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	19.3	14.5	10.3	7.2	5.8	5.5	...	...	...	...	...	...	...	...	...
33	23.9	23.7	23.6	23.4	21.0	13.2	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	32.6	32.3	32.0	30.7	29.5	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	14.9	14.7	14.5	13.0	9.8	6.6	4.2	2.2	1.6	1.1	1.0	0.80	...	...	...
40	10.5	10.3	10.1	10.0	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	0.98
41	16.7	16.6	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	17.3	17.0	15.5	12.4	9.3	6.6	4.8	3.5	...	...	...	...	...	...	...
45	16.5	16.5	16.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.
	Nonferrous Materials (Cont'd)						
1	65Ni-28Mo-2Fe	Bolting	SB-335	...	N10665	Solution ann.	...
2	21Ni-30Fe-22Cr-18Co-3Mo-3W	Bolting	SB-572	...	R30556	Annealed	...

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)				Notes
			III	VIII-1	VIII-2	XII	
1	110	51	NP	800	800	650	Nonferrous Materials (Cont'd) ...
2	100	45	NP	1650	800	650	T12

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line		Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																
No.		100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
	Nonferrous Materials (Cont'd)																	
1		27.5	...	27.5	...	27.5	...	27.5	...	27.5	...	27.2	26.8	26.6	26.1	25.6	...	...
2		25.0	...	25.0	...	23.1	...	21.3	...	20.1	...	19.3	19.0	18.7	18.5	18.2	18.0	17.8

Table 3 (Cont'd)
Section III, Division 1, Classes 2 and 3;* Section VIII, Divisions 1 and 2;† and Section XII
Maximum Allowable Stress Values, S, for Bolting Materials
 (*See Maximum Temperature Limits for Restrictions on Class)
 (†Use with Part 4.16 of Section VIII, Division 2)

Line No.	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	17.6	17.4	17.2	17.1	16.9	13.6	10.9	8.8	7.0	5.6	4.5	3.6	2.8	2.2	1.8

Nonferrous Materials (Cont'd)

NOTES TO TABLE 3**GENERAL NOTES**

- (a) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (b) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (c) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.
- (d) These stress values are established from a consideration of strength only and will be satisfactory for average service. For bolted joints where freedom from leakage over a long period of time without retightening is required, lower stress values may be necessary as determined from the relative flexibility of the flange and bolts, and corresponding relaxation properties.
- (e) Stress values for 100°F are applicable for colder temperatures when toughness requirements of Section III or Section VIII are met.
- (f) For bolting with a reported hardness exceeding 350 HB, user is cautioned that under certain conditions of temperature and environment or fatigue conditions, stress corrosion cracking of this high hardness bolting shall be considered.
- (g) The following abbreviations are used: Ann., Annealed; ann., annealed; CD, Cold drawn; fin., finished; rel., relieved; str., stress; and wld., welded.
- (h) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-193/SA-193M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-193 Grade B6 shall be used when SA-193M Grade B6 is used in construction.
- (i) An alternative typeface is used for stress values obtained from time-dependent properties (see Notes T1 through T12).

NOTES - GENERAL REQUIREMENTS

- G1 Alloy N06625 in the annealed condition is subject to severe loss of impact strength at room temperatures after exposure in the range of 1000°F to 1400°F.
- G2 Copper-silicon alloys are not always suitable when exposed to certain media and high temperatures, particularly steam above 212°F. The owner, the owner's designated agent, or the user should ensure him/herself that the alloy selected is satisfactory for the service for which it is to be used.
- G3 The maximum operating temperature is arbitrarily set at 500°F because harder temper adversely affects design stress in the creep rupture temperature range.
- G4 This material has reduced toughness at room temperature after exposure for about 5000 hr at 600°F and after shorter exposure above 650°F.
- G5 At temperatures above 1000°F, these stress values apply only when the carbon is 0.04% or higher on heat analysis.
- G6 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating it to a minimum temperature of 1900°F.
- G7 The user is cautioned that under certain conditions of temperature and environment or fatigue conditions, stress corrosion of this material shall be considered.
- G8 For all design temperatures, the maximum hardness shall be Rockwell C35 immediately under thread roots. The hardness shall be taken on a flat area at least $\frac{1}{8}$ in. across, prepared by removing threads; no more material than necessary shall be removed to prepare the flat area. Hardness determinations shall be made at the same frequency as tensile tests.
- G9 For Section VIII, Division 1 applications, use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.
- G10 For stress relieved tempers, stress values for T3 temper can be used for T351, T3510, and T3511; stress values for T4 temper can be used for T451, T4510, and T4511; and stress values for T6 temper can be used for T651, T6510, and T6511.
- G11 The shipping lot testing method of SA-574, 11.3, is prohibited.
- G12 Since these bolts could be used in flanged joints, the maximum permitted temperature and maximum allowable stress are limited to reduce the potential for bolt relaxation and associated flange leakage.

NOTES - HEAT TREATMENT REQUIREMENTS

- H1 Design stresses for the cold drawn temper based on hot rolled properties until required data on cold drawn is submitted.

NOTES - TIME-DEPENDENT PROPERTIES [See General Note (i)]

- T1 Allowable stresses for temperatures of 300°F and above are values obtained from time-dependent properties.
- T2 Allowable stresses for temperatures of 350°F and above are values obtained from time-dependent properties.
- T3 Allowable stresses for temperatures of 450°F and above are values obtained from time-dependent properties.
- T4 Allowable stresses for temperatures of 550°F and above are values obtained from time-dependent properties.
- T5 Allowable stresses for temperatures of 850°F and above are values obtained from time-dependent properties.
- T6 Allowable stresses for temperatures of 900°F and above are values obtained from time-dependent properties.
- T7 Allowable stresses for temperatures of 950°F and above are values obtained from time-dependent properties.
- T8 Allowable stresses for temperatures of 1000°F and above are values obtained from time-dependent properties.
- T9 Allowable stresses for temperatures of 1050°F and above are values obtained from time-dependent properties.
- T10 Allowable stresses for temperatures of 1100°F and above are values obtained from time-dependent properties.

NOTES TO TABLE 3 (CONT'D)

NOTES – TIME-DEPENDENT PROPERTIES [See General Note (i)] (CONT'D)

T11 Allowable stresses for temperatures of 1150°F and above are values obtained from time-dependent properties.

T12 Allowable stresses for temperatures of 1200°F and above are values obtained from time-dependent properties.

T13 Allowable stresses for temperatures of 400°F and above are values obtained from time-dependent properties.

NOTES – WELDING REQUIREMENTS

W1 Welding, brazing, and thermal cutting are not permitted.

W2 If welded, the allowable stress values for the annealed condition shall be used.

W3 This material may be welded by the resistance technique.

W4 The stress values given for this material are not applicable when either welding or thermal cutting is employed.

W5 Except for nonstructural tack welds used as a locking device, welding is prohibited for Section VIII, Division 1 use.

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table 4
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Nominal Composition	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/Condition/ Temper	Size/ Thickness, in.
(25)	Ferrous Materials					
	1 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	5	$2 < t \leq 4$
	2 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	5	≤ 2
	3 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	4	≤ 4
	4 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	3	≤ 4
	5 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	2	≤ 3
	6 1Cr-1Mn- $\frac{1}{4}$ Mo	SA-540	B22	K41420	1	$\leq 1\frac{1}{2}$
	7 1Cr- $\frac{1}{5}$ Mo	SA-193	B7	G41400	...	$4 < t \leq 7$
	8 1Cr- $\frac{1}{5}$ Mo	SA-193	B7M	G41400	...	≤ 4
	9 1Cr- $\frac{1}{5}$ Mo	SA-193	B7	G41400	...	$2\frac{1}{2} < t \leq 4$
	10 1Cr- $\frac{1}{5}$ Mo	SA-193	B7	G41400	...	$\leq 2\frac{1}{2}$
	11 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$4 < t \leq 8$
	12 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$4 < t \leq 8$
	13 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$2\frac{1}{2} < t \leq 4$
	14 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$2\frac{1}{2} < t \leq 4$
	15 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	5	$2 < t \leq 8$
	16 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	5	≤ 2
	17 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$\leq 2\frac{1}{2}$
	18 1Cr- $\frac{1}{2}$ Mo-V	SA-193	B16	K14072	...	$\leq 2\frac{1}{2}$
	19 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	4	≤ 6
	20 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	3	≤ 6
	21 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	2	≤ 4
	22 1Cr- $\frac{1}{2}$ Mo-V	SA-540	B21	K14073	1	≤ 4
	23 12Cr-1Mo-V-W	SA-437	B4C	K91352	...	...
	24 12Cr-1Mo-V-W	SA-437	B4B	K91352	...	...
	25 13Cr	SA-193	B6	S41000	...	≤ 4
	26 17Cr-4Ni-4Cu	SA-564	630	S17400	H1100	≤ 8
	27 17Cr-4Ni-4Cu	SA-705	630	S17400	H1100	≤ 8
	28 $1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-320	L43	G43400	...	≤ 4
	29 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	5	$6 < t \leq 9\frac{1}{2}$
	30 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	5	$6 < t \leq 9\frac{1}{2}$
	31 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	5	≤ 6
	32 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	4	$\leq 9\frac{1}{2}$
	33 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	3	$\leq 9\frac{1}{2}$
	34 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	2	$\leq 9\frac{1}{2}$
	35 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	SA-540	B23	H43400	1	≤ 8
	36 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	5	$6 < t \leq 9\frac{1}{2}$
	37 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	5	$6 < t \leq 9\frac{1}{2}$
	38 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	5	≤ 6
	39 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	4	$\leq 9\frac{1}{2}$
	40 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	3	$\leq 9\frac{1}{2}$
	41 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	2	$\leq 9\frac{1}{2}$
	42 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	SA-540	B24	K24064	1	≤ 8
	43 2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo-V	SA-540	B24V	K24070	3	≤ 11
	44 25Ni-15Cr-2Ti	SA-453	660	S66286	A	...
	45 25Ni-15Cr-2Ti	SA-453	660	S66286	B	...

Table 4
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)		Notes
			III	VIII-2	
Ferrous Materials					
1	115	100	700	700	G4
2	120	105	700	700	G4
3	135	120	700	700	G4
4	145	130	700	700	G3
5	155	140	700	700	G3
6	165	150	600	600	G1
7	100	75	800	800	G4
8	100	80	NP	800	G4
9	115	95	800	800	G4
10	125	105	800	800	G4
11	100	85	800	NP	...
12	100	85	NP	800	...
13	110	95	800	NP	...
14	110	95	NP	800	...
15	115	100	700	700	G4
16	120	105	700	700	G4
17	125	105	800	NP	...
18	125	105	NP	800	...
19	135	120	700	700	G4
20	145	130	700	700	G3
21	155	140	700	700	G3
22	165	150	700	700	G1
23	115	85	700	700	...
24	145	105	700	700	...
25	110	85	700	700	...
26	140	115	650	650	G2
27	140	115	650	650	G2
28	125	105	800	800	G4
29	115	100	700	NP	G4
30	115	100	NP	700	G4
31	120	105	700	700	G4
32	135	120	700	700	G4
33	145	130	700	700	G3
34	155	140	700	700	G3
35	165	150	600	600	G1
36	115	100	700	NP	G4
37	115	100	NP	700	G4
38	120	105	700	700	G4
39	135	120	700	700	G4
40	145	130	700	700	G3
41	155	140	700	700	G3
42	165	150	600	600	G1
43	145	130	700	700	G3
44	130	85	800	800	...
45	130	85	800	800	...

Table 4
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
	100	200	300	400	500	600	650	700	750	800
Ferrous Materials										
1	33.3	31.8	30.9	29.8	28.9	27.6	...	25.9	...	...
2	35.0	33.4	32.4	31.3	30.3	29.0	...	27.2	...	...
3	40.0	38.2	36.9	35.9	34.7	33.1	...	31.1	...	...
4	43.3	41.4	40.2	38.8	37.6	35.9	...	33.7	...	...
5	46.7	44.6	43.1	41.8	40.5	38.7	...	36.3	...	...
6	50.0	47.8	46.2	44.8	43.4	41.4	...	...	...	...
7	25.0	23.3	22.4	21.8	21.1	20.3	19.8	19.2	18.5	17.6
8	26.7	24.9	23.9	23.2	22.5	21.7	21.1	20.5	19.7	18.8
9	31.7	29.5	28.4	27.6	26.7	25.7	25.0	24.3	23.4	22.3
10	35.0	32.6	31.4	30.5	29.5	28.4	27.7	26.9	25.9	24.6
11	28.3	27.4	26.6	25.9	25.2	24.5	...	23.7	...	22.6
12	28.3	27.5	26.9	26.3	25.7	25.0	...	23.8	...	22.4
13	31.7	30.6	29.7	29.0	28.2	27.4	...	26.5	...	25.3
14	31.7	30.7	30.0	29.4	28.8	27.9	...	26.6	...	25.1
15	33.3	32.2	31.3	30.5	29.7	28.8	...	27.9	...	...
16	35.0	33.8	32.8	32.0	31.2	30.3	...	29.3	...	...
17	35.0	33.8	32.8	32.0	31.2	30.3	...	29.3	...	27.9
18	35.0	34.0	33.2	32.5	31.8	30.9	...	29.4	...	27.7
19	40.0	38.7	37.5	36.6	35.6	34.6	...	33.4	...	...
20	43.3	41.9	40.6	39.7	38.6	37.5	...	36.2	...	...
21	46.7	45.1	43.8	42.7	41.5	40.4	...	39.0	...	...
22	50.0	48.4	46.9	45.8	44.5	43.3	...	41.8	...	...
23	28.3	27.2	26.3	25.6	25.0	24.6	24.3	24.0	...	...
24	35.0	33.5	32.4	31.6	30.9	30.2	29.9	29.7	...	...
25	28.3	27.0	26.1	25.3	24.6	23.9	...	23.3	...	...
26	38.3	35.4	33.9	32.7	31.7	30.9	30.5	...	...	...
27	38.3	35.4	33.9	32.7	31.7	30.9	30.5	...	...	...
28	35.0	33.0	31.9	30.6	29.5	28.1	...	26.4	...	24.2
29	33.3	31.8	30.9	29.8	28.9	27.6	...	25.9	...	...
30	33.3	31.8	30.7	29.8	28.9	27.6	...	25.9	...	...
31	35.0	33.4	32.4	31.3	30.3	29.0	...	27.2	...	...
32	40.0	38.2	36.9	35.9	34.7	33.1	...	31.1	...	...
33	43.3	41.4	40.2	38.8	37.6	35.9	...	33.7	...	...
34	46.7	44.6	43.1	41.8	40.5	38.7	...	36.3	...	...
35	50.0	47.8	46.2	44.8	43.4	41.4	...	...	...	...
36	33.3	31.8	30.9	29.8	28.9	27.6	...	25.9	...	...
37	33.3	31.8	30.7	29.8	28.9	27.6	...	25.9	...	...
38	35.0	33.4	32.4	31.3	30.3	29.0	...	27.2	...	...
39	40.0	38.2	36.9	35.9	34.7	33.1	...	31.1	...	...
40	43.3	41.4	40.2	38.8	37.6	35.9	...	33.7	...	...
41	46.7	44.6	43.1	41.8	40.5	38.7	...	36.3	...	...
42	50.0	47.8	46.2	44.8	43.4	41.4	...	...	...	...
43	43.3	41.4	40.2	38.8	37.6	35.9	...	33.7	...	...
44	28.3	27.8	27.3	26.9	26.4	26.0	25.7	25.5	25.2	25.0
45	28.3	27.8	27.3	26.9	26.4	26.0	25.7	25.5	25.2	25.0

INTENTIONALLY LEFT BLANK

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Nominal Composition	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/Condition/ Temper	Size/ Thickness, in.
Ferrous Materials (Cont'd)						
1	16Cr-12Ni-2Mo	SA-193	B8M	S31600	1/Sol. treat.	...
2	16Cr-12Ni-2Mo	SA-193	B8MA	S31600	1A/Sol. treat.	...
3	16Cr-12Ni-2Mo-N	SA-193	B8MNA	S31651	1A/Sol. treat.	...
4	18Cr-8Ni	SA-193	B8	S30400	1/Sol. treat.	...
5	18Cr-8Ni	SA-193	B8A	S30400	1A/Sol. treat.	...
6	18Cr-8Ni-N	SA-193	B8NA	S30451	1A/Sol. treat.	...
7	18Cr-8Ni-4Si-N	SA-193	B8S	S21800	Sol. treat.	...
8	18Cr-8Ni-4Si-N	SA-193	B8SA	S21800	Sol. treat.	...
9	18Cr-10Ni-Cb	SA-193	B8C	S34700	1/Sol. treat.	...
10	18Cr-10Ni-Ti	SA-193	B8T	S32100	1/Sol. treat.	...
11	19Cr-9Ni-Mo-W	SA-453	651	S63198	B	>3
12	19Cr-9Ni-Mo-W	SA-453	651	S63198	B	≤3
13	19Cr-9Ni-Mo-W	SA-453	651	S63198	A	>3
14	19Cr-9Ni-Mo-W	SA-453	651	S63198	A	≤3
15	22Cr-13Ni-5Mn	SA-193	B8R	S20910	1C/Sol. treat.	...
16	22Cr-13Ni-5Mn	SA-193	B8RA	S20910	Sol. treat.	...

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)		Notes
			III	VIII-2	
Ferrous Materials (Cont'd)					
1	75	30	800	800	...
2	75	30	800	800	...
3	75	30	800	800	...
4	75	30	800	800	...
5	75	30	800	800	...
6	75	30	800	800	...
7	95	50	800	800	...
8	95	50	800	800	...
9	75	30	800	800	...
10	75	30	800	800	...
11	95	50	800	800	...
12	95	60	800	800	...
13	100	60	800	800	...
14	100	70	800	800	...
15	100	55	800	800	...
16	100	55	800	800	...

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
	100	200	300	400	500	600	650	700	750	800
Ferrous Materials (Cont'd)										
1	18.8	17.7	15.6	14.3	13.3	12.6	...	12.1	...	11.7
2	10.0	8.6	7.8	7.2	6.7	6.3	...	6.0	...	5.8
3	18.8	17.8	16.3	15.2	14.2	13.4	13.1	12.8	12.5	12.3
4	18.8	16.7	15.0	13.8	12.9	12.1	...	11.8	...	11.2
5	10.0	8.3	7.5	6.9	6.5	6.1	...	5.9	...	5.6
6	18.8	16.5	14.4	12.9	12.0	11.4	11.2	11.0	10.8	10.6
7	23.8	23.4	21.8	19.7	18.5	17.6	17.3	17.1	16.9	16.7
8	23.8	23.4	21.8	19.7	18.5	17.6	17.3	17.1	16.9	16.7
9	18.8	17.9	16.4	15.5	15.0	14.3	...	13.8	...	13.6
10	18.8	17.8	16.5	15.3	14.3	13.5	...	12.9	...	12.5
11	16.7	15.3	14.2	13.3	12.7	12.0	...	11.5	...	11.1
12	20.0	18.3	17.0	16.0	15.1	14.5	...	13.8	...	13.2
13	20.0	18.3	17.0	16.0	15.1	14.5	...	13.8	...	13.2
14	23.3	21.4	19.8	18.7	17.7	16.9	...	16.1	...	15.4
15	18.3	15.7	14.5	13.6	12.9	12.4	12.3	12.1	11.9	11.8
16	18.3	15.7	14.5	13.6	12.9	12.4	12.3	12.1	11.9	11.8

INTENTIONALLY LEFT BLANK

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Nominal Composition	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/Condition/ Temper	Size/ Thickness, in.
Nonferrous Materials						
1	67Ni-30Cu	SB-164	...	N04400	HW or CW ann.	All
2	67Ni-30Cu	SB-164	...	N04400	Hot worked	$12 < t \leq 14$
3	67Ni-30Cu	SB-164	...	N04400	Hot worked	≤ 12
4	67Ni-30Cu	SB-164	...	N04400	CD-str. rel.	$\leq \frac{1}{2}$
5	67Ni-30Cu	SB-164	...	N04400	CD-str. rel.	$3\frac{1}{2} < t \leq 4$
6	67Ni-30Cu	SB-164	...	N04400	As drawn	$\leq \frac{1}{2}$
7	67Ni-30Cu	SB-164	...	N04400	CD-str. rel.	$\frac{1}{2} < t \leq 3\frac{1}{2}$
8	67Ni-30Cu	SB-164	...	N04400	As drawn	$\leq \frac{1}{2}$
9	67Ni-30Cu-S	SB-164	...	N04405	Annealed	...
10	67Ni-30Cu-S	SB-164	...	N04405	Hot worked	...
11	67Ni-30Cu-S	SB-164	...	N04405	As drawn	...
12	53Ni-19Cr-19Fe-Cb-Mo	SB-637	...	N07718	Sol. & precip. harden	≤ 6
13	70Ni-16Cr-7Fe-Ti-Al	SB-637	2	N07750	...	< 4

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Applicability and Max. Temperature Limits (NP = Not Permitted)		Notes
			III	VIII-2	
					Nonferrous Materials
1	70	25	800	800	...
2	75	40	800	800	...
3	80	40	800	800	...
4	84	50	500	500	...
5	84	55	500	500	...
6	85	55	500	500	...
7	87	60	500	500	...
8	110	85	500	500	...
9	70	25	800	800	...
10	75	35	800	800	...
11	85	50	500	500	...
12	185	150	800	800	...
13	170	115	800	800	...

Table 4 (Cont'd)
Section III, Division 1, Classes 1 and MC; Section III, Division 3; and Section III, Division 5
Design Stress Intensity Values, S_m , and Section VIII, Division 2* Maximum Allowable Stress
Values, S , for Bolting Materials
(*Use with Part 5 and Annex 5.F of Section VIII, Division 2)

Line No.	Design Stress Intensity or Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
	100	200	300	400	500	600	650	700	750	800
Nonferrous Materials										
1	16.7	14.6	13.6	13.2	13.1	13.1	13.1	13.1	...	12.7
2	16.7	14.6	13.6	13.2	13.1	13.1	13.1	13.1	...	12.7
3	16.7	14.6	13.6	13.2	13.1	13.1	13.1	13.0	...	12.7
4	16.7	15.8	15.3	15.0	14.9	...	...	...	...	...
5	18.3	17.4	16.8	16.5	16.4	...	...	...	...	...
6	18.3	17.4	16.8	16.5	16.4	...	...	...	...	...
7	20.0	19.0	18.3	18.0	17.9	...	...	...	...	...
8	28.3	26.9	25.9	25.6	25.4	...	...	...	...	...
9	16.6	14.6	13.6	13.2	13.1	13.1	13.1	13.1	...	12.7
10	18.7	18.7	18.7	18.7	18.7	18.7	18.4	18.0	...	14.5
11	16.6	14.6	13.8	13.2	13.2	...	...	...	...	...
12	50.0	48.0	46.9	46.1	45.6	45.1	...	44.8	...	44.4
13	38.3	37.3	36.8	36.3	36.0	35.8	35.7	35.6	35.5	35.4

NOTES TO TABLE 4**GENERAL NOTES**

- (a) The stress values for bolting materials given in this Table do not exceed the lesser of one-third of the specified minimum yield strength or one-third of the yield strength at temperature, with credit granted for the enhancement of properties produced by heat treatment. They are intended for Section VIII, Division 2 use when flanges are designed in accordance with the rules of Part 5 and Annex 5.F when the bolting requirements are determined in accordance with 5.7.1 and 5.7.2. They are intended for Section III use in the design equations. For allowable values of actual preload and service stresses, see Section III, Subsection NB, NB-3230 and Section III Appendices Nonmandatory Appendix E.
- (b) Stress values for 100°F are applicable for colder temperatures when toughness requirements of Section III or Section VIII are met.
- (c) The following abbreviations are used: CD, Cold drawn; precip., precipitation; rel., relieved; Sol., Solution; str., stress; and treat., treated.
- (d) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-193/SA-193M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-193 Grade B6 shall be used when SA-193M Grade B6 is used in construction.
- (e) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (f) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (g) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES - GENERAL REQUIREMENTS

- G1 Stress values may result in relaxation of the bolting materials after prolonged service at temperatures of 500°F and higher, and the designer is to investigate the effect of this relaxation on the application.
- G2 This material has reduced toughness at room temperature after exposure for about 5000 hr at 600°F and after shorter exposure above 650°F.
- G3 Stress values may result in relaxation of the bolting materials after prolonged service at temperatures of 600°F and higher, and the designer is to investigate the effect of this relaxation on the application.
- G4 Stress values may result in relaxation of the bolting materials after prolonged service at temperatures of 700°F and higher, and the designer is to investigate the effect of this relaxation on the application.

Table 5A
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design/ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Bar, shapes	SA-675	45	...	...	...	1	1
2	Carbon steel	Plate	SA-285	A	K01700	...	...	1	1
3	Carbon steel	Smls. pipe	SA-106	A	K02501	...	...	1	1
4	Carbon steel	Bar, shapes	SA-675	50	...	...	...	1	1
5	Carbon steel	Plate	SA-285	B	K02200	...	$t \leq 2$	1	1
6	Carbon steel	Bar, shapes	SA-675	55	...	...	...	1	1
7	Carbon steel	Plate	SA-285	C	K02801	...	$t \leq 2$	1	1
8	Carbon steel	Smls. pipe	SA-333	1	K03008	...	...	1	1
9	Carbon steel	Smls. tube	SA-334	1	K03008	...	...	1	1
10	Carbon steel	Plate	SA-516	55	K01800	...	...	1	1
11	Carbon steel	Smls. pipe	SA-524	II	K02104	...	...	1	1
12	Carbon steel	Plate, bar, shapes	SA-36	...	K02600	...	...	1	1
13	Carbon steel	Plate	SA-662	A	K01701	...	...	1	1
14	Carbon steel	Forgings	SA-181	...	K03502	60	...	1	1
15	Carbon steel	Castings	SA-216	WCA	J02502	...	...	1	1
16	Carbon steel	Forgings	SA-266	1	K03506	...	...	1	1
17	Carbon steel	Forgings	SA-350	LF1	K03009	1	...	1	1
18	Carbon steel	Bar, shapes	SA-675	60	...	...	...	1	1
19	Carbon steel	Forgings	SA-765	I	K03046	...	...	1	1
20	Carbon steel	Plate	SA-515	60	K02401	...	...	1	1
21	Carbon steel	Plate	SA-516	60	K02100	...	...	1	1
22	Carbon steel	Plate	SA-283	D	K02702	...	...	1	1
23	Carbon steel	Smls. pipe	SA-106	B	K03006	...	...	1	1
24	Carbon steel	Fittings	SA-234	WPB	K03006	...	...	1	1
25	Carbon steel	Smls. pipe	SA-333	6	K03006	...	...	1	1
26	Carbon steel	Forgings	SA-372	A	K03002	...	...	1	1
27	Carbon steel	Fittings	SA-420	WPL6	...	...	...	1	1
28	Carbon steel	Smls. pipe	SA-524	I	K02104	...	...	1	1
29	Carbon steel	Forgings	SA-727	...	K02506	...	...	1	1
30	Carbon steel	Wld. tube	SA-178	C	K03503	...	...	1	1
31	Carbon steel	Smls. tube	SA-210	A-1	K02707	...	...	1	1
32	Carbon steel	Bar, shapes	SA-675	65	...	...	...	1	1
33	Carbon steel	Castings	SA-352	LCB	J03003	...	...	1	1
34	Carbon steel	Plate	SA-515	65	K02800	...	...	1	1
35	Carbon steel	Plate	SA-516	65	K02403	...	...	1	1
36	Carbon steel	Plate	SA-662	B	K02203	...	...	1	1
37	Carbon steel	Plate	SA-537	...	K12437	1	$2\frac{1}{2} < t \leq 4$	1	2
(25) 38	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$1.4 < t \leq 6.3$	1	1
(25) 39	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT	$t \leq 1.4$	1	1
40	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$6 < t \leq 10$	1	2
41	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$4 < t \leq 6$	1	2
42	Carbon steel	Bar, shapes	SA-675	70	...	...	...	1	1
43	Carbon steel	Forgings	SA-105	...	K03504	...	...	1	2
44	Carbon steel	Forgings	SA-181	...	K03502	70	...	1	2
45	Carbon steel	Castings	SA-216	WCB	J03002	...	...	1	2

Table 5A
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	45	22.5	900	CS-6	G13, T4
2	45	24	900	CS-1	G13, T3
3	48	30	1000	CS-2	G13, T1
4	50	25	900	CS-1	G13, T3
5	50	27	900	CS-1	G13, T3
6	55	27.5	900	CS-1	G13, T3
7	55	30	1000	CS-2	G13, T3
8	55	30	1000	CS-2	T4
9	55	30	700	CS-2	...
10	55	30	1000	CS-2	G13, T3
11	55	30	1000	CS-2	G13, T3
12	58	36	650	CS-2	G13
13	58	40	700	CS-2	...
14	60	30	1000	CS-2	G13, T4
15	60	30	1000	CS-2	G13, T4
16	60	30	1000	CS-2	G13, T4
17	60	30	700	CS-2	G13
18	60	30	900	CS-2	G13, T4
19	60	30	1000	CS-2	G13, T4
20	60	32	1000	CS-2	G13, T3
21	60	32	1000	CS-2	G13, T3
22	60	33	700	CS-2	...
23	60	35	700	CS-2	G13
24	60	35	1000	CS-2	G13, T3
25	60	35	1000	CS-2	G13, T3
26	60	35	650	CS-2	G9, H2
27	60	35	850	CS-2	G13, T3
28	60	35	1000	CS-2	G13, T3
29	60	36	1000	CS-2	G13, T3
30	60	37	1000	CS-2	G6, G13, T2
31	60	37	1000	CS-2	G13, T3
32	65	32.5	1000	CS-2	G13, T3
33	65	35	650	CS-2	...
34	65	35	1000	CS-2	G13, T3
35	65	35	1000	CS-2	G13, T3
36	65	40	700	CS-2	...
37	65	45	700	CS-2	T2
38	66.5	37	1000	CS-2	G13, T3
39	66.5	40.5	1000	CS-2	G13, T3
40	68	40.5	1000	CS-2	G13, T2
41	69.5	43	1000	CS-2	G13, T2
42	70	35	1000	CS-2	G13, T3
43	70	36	1000	CS-2	G13, T3
44	70	36	1000	CS-2	G13, T3
45	70	36	1000	CS-2	G13, T3

Table 5A
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	15.0	14.1	13.7	13.5	13.3	13.1	12.8	12.5	12.2	11.9	11.5	11.1	10.7	10.4	9.2	7.9	5.9
2	16.0	15.0	14.7	14.4	14.2	13.9	13.7	13.4	13.0	12.7	12.3	11.9	11.5	10.7	9.2	7.9	5.9
3	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.6	14.4	10.7	9.2	7.9	5.9
4	16.7	15.7	15.3	15.0	14.7	14.5	14.2	13.9	13.6	13.2	12.8	12.4	11.9	10.7	9.2	7.9	5.9
5	18.0	16.9	16.5	16.2	15.9	15.7	15.4	15.0	14.7	14.2	13.8	13.3	13.0	10.7	9.2	7.9	5.9
6	18.3	17.2	16.8	16.5	16.2	16.0	15.7	15.3	14.9	14.5	14.1	13.6	13.1	12.7	10.8	8.7	5.9
7	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.0	10.8	8.7	5.9
8	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
9	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	...	...	...	...
10	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.0	10.8	8.7	5.9
11	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.0	10.8	8.7	5.9
12	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	...	...	...	...	...
13	24.2	24.2	24.2	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.3	19.2	...	...	...	...
14	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
15	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
16	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
17	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	...	...	...	...
18	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
19	20.0	18.8	18.3	18.0	17.7	17.4	17.1	16.7	16.3	15.8	15.3	14.8	14.3	13.8	11.4	8.7	5.9
20	21.3	20.0	19.5	19.2	18.9	18.6	18.2	17.8	17.4	16.9	16.4	15.8	15.3	13.9	11.4	8.7	5.9
21	21.3	20.0	19.5	19.2	18.9	18.6	18.2	17.8	17.4	16.9	16.4	15.8	15.3	13.9	11.4	8.7	5.9
22	22.0	20.7	20.2	19.8	19.5	19.1	18.8	18.4	17.9	17.4	16.9	16.3	15.4	...	...	...	...
23	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.8	...	...	...	...
24	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.8	13.9	11.4	8.7	5.9
25	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.8	13.9	11.4	8.7	5.9
26	23.3	22.4	21.4	20.3	19.3	18.4	17.6	16.9	16.5	16.1	15.8	15.6	...	...	...	...	...
27	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.8	13.9	11.4	8.7	...
28	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.8	13.9	11.4	8.7	5.9
29	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.3	13.9	11.4	8.7	5.9
30	21.0	19.7	19.2	18.8	18.5	18.2	17.9	17.5	17.1	16.6	16.1	15.5	14.4	11.8	9.7	7.4	5.0
31	24.7	23.2	22.6	22.2	21.8	21.5	21.1	20.6	20.1	19.5	18.9	18.3	17.8	13.9	11.4	8.7	5.9
32	21.7	20.4	19.8	19.5	19.2	18.9	18.5	18.1	17.7	17.1	16.6	16.1	15.5	13.9	11.4	9.0	6.3
33	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	...	...	...	...	...
34	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.7	13.9	11.4	9.0	6.3
35	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.7	13.9	11.4	9.0	6.3
36	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.2	...	...	...	...
37	27.1	27.1	27.1	27.0	26.5	26.1	25.6	25.0	24.5	23.7	23.0	22.3	16.9	...	...	...	...
38	24.7	23.1	22.5	22.0	21.7	21.3	20.9	...	19.9	19.4	18.8	18.1	17.5	14.8	12.0	9.3	6.7
39	27.1	25.3	24.7	24.2	23.8	23.4	23.0	...	21.9	21.3	20.6	19.9	19.2	14.8	12.0	9.3	6.7
40	27.1	25.3	24.7	24.3	24.0	23.6	23.2	22.6	22.1	21.4	20.7	20.0	18.3	14.8	12.0	9.3	6.7
41	28.5	26.7	26.1	25.6	25.2	24.8	24.4	23.8	23.3	22.6	21.9	21.1	18.3	14.8	12.0	9.3	6.7
42	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	19.0	18.5	17.9	17.3	16.7	14.8	12.0	9.3	6.7
43	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
44	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
45	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7

Table 5A
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	4.0	2.5	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	4.0	2.5	...	...	...	...	...	...	...	...	...	...
8	4.0	2.5	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	4.0	2.5	...	...	...	...	...	...	...	...	...	...
11	4.0	2.5	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...
14	4.0	2.5	...	...	...	...	...	...	...	...	...	...
15	4.0	2.5	...	...	...	...	...	...	...	...	...	...
16	4.0	2.5	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	4.0	2.5	...	...	...	...	...	...	...	...	...	...
20	4.0	2.5	...	...	...	...	...	...	...	...	...	...
21	4.0	2.5	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	4.0	2.5	...	...	...	...	...	...	...	...	...	...
25	4.0	2.5	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	4.0	2.5	...	...	...	...	...	...	...	...	...	...
29	4.0	2.5	...	...	...	...	...	...	...	...	...	...
30	3.4	2.1	...	...	...	...	...	...	...	...	...	...
31	4.0	2.5	...	...	...	...	...	...	...	...	...	...
32	4.0	2.5	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	4.0	2.5	...	...	...	...	...	...	...	...	...	...
35	4.0	2.5	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...
39	4.0	2.5	...	...	...	...	...	...	...	...	...	...
40	4.0	2.5	...	...	...	...	...	...	...	...	...	...
41	4.0	2.5	...	...	...	...	...	...	...	...	...	...
42	4.0	2.5	...	...	...	...	...	...	...	...	...	...
43	4.0	2.5	...	...	...	...	...	...	...	...	...	...
44	4.0	2.5	...	...	...	...	...	...	...	...	...	...
45	4.0	2.5	...	...	...	...	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Forgings	SA-266	2	K03506	...	...	1	2
2	Carbon steel	Forgings	SA-266	4	K03017	...	...	1	2
3	Carbon steel	Forgings	SA-350	LF2	K03011	...	...	1	2
4	Carbon steel	Forgings	SA-508	1	K13502	...	...	1	2
5	Carbon steel	Forgings	SA-508	1A	K13502	...	...	1	2
6	Carbon steel	Forgings	SA-541	1	K03506	...	...	1	2
7	Carbon steel	Forgings	SA-541	1A	K03020	...	...	1	2
8	Carbon steel	Forgings	SA-765	II	K03047	...	...	1	2
9	Carbon steel	Plate	SA-515	70	K03101	...	...	1	2
10	Carbon steel	Plate	SA-516	70	K02700	...	...	1	2
11	Carbon steel	Smls. pipe	SA-106	C	K03501	...	...	1	2
12	Carbon steel	Smls. tube	SA-210	C	K03501	...	...	1	2
13	Carbon steel	Castings	SA-216	WCC	K02503	...	...	1	2
14	Carbon steel	Fittings	SA-234	WPC	K03501	...	...	1	2
15	Carbon steel	Plate	SA-537	...	K12437	3	$4 < t \leq 6$	1	3
16	Carbon steel	Plate	SA-662	C	K02007	...	...	1	2
17	Carbon steel	Plate	SA-537	...	K12437	2	$4 < t \leq 6$	1	3
18	Carbon steel	Plate	SA-738	C	K02008	...	$4 < t \leq 6$	1	3
19	Carbon steel	Plate	SA-537	...	K12437	1	$t \leq 2\frac{1}{2}$	1	2
20	Carbon steel	Plate	SA-841	A	...	1	$t \leq 4$	1	2
(25)	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$2.8 < t \leq 6.3$	1	2
(25)	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$1.4 < t \leq 2.8$	1	2
23	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$2.5 < t \leq 4$	1	2
(25)	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT	$t \leq 1.4$	1	2
25	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$1.5 < t \leq 2.5$	1	2
26	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$\frac{5}{8} < t \leq 1.5$	1	2
27	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...	$\leq \frac{5}{8}$	1	2
28	Carbon steel	Forgings	SA-266	3	K05001	...	...	1	2
29	Carbon steel	Plate	SA-299	A	K02803	...	$t > 1$	1	2
30	Carbon steel	Plate	SA-299	A	K02803	...	$t \leq 1$	1	2
31	Carbon steel	Forgings	SA-372	B	K04001	...	...	1	2
32	Carbon steel	Plate	SA-738	A	K12447	Normalized	$t \leq 2\frac{1}{2}$	1	2
33	Carbon steel	Plate	SA-738	A	K12447	QT	...	1	2
34	Carbon steel	Plate	SA-537	...	K12437	3	$2\frac{1}{2} < t \leq 4$	1	3
35	Carbon steel	Plate	SA-537	...	K12437	2	$2\frac{1}{2} < t \leq 4$	1	3
36	Carbon steel	Plate	SA-738	C	K02008	...	$2\frac{1}{2} < t \leq 4$	1	3
37	Carbon steel	Plate	SA-299	B	K02803	...	$t > 1$	1	3
38	Carbon steel	Plate	SA-299	B	K02803	...	$t \leq 1$	1	3
39	Carbon steel	Forgings	SA-765	IV	K02009	...	...	1	3
40	Carbon steel	Plate	SA-537	...	K12437	3	$t \leq 2\frac{1}{2}$	1	3
41	Carbon steel	Plate	SA-537	...	K12437	2	$t \leq 2\frac{1}{2}$	1	3
42	Carbon steel	Plate	SA-738	C	K02008	...	$t \leq 2\frac{1}{2}$	1	3
43	Carbon steel	Plate	SA-841	B	...	2	$t \leq 4$	1	3
44	Carbon steel	Plate	SA-612	...	K02900	Normalized	$\frac{1}{2} < t \leq 1$	10C	1
45	Carbon steel	Plate	SA-612	...	K02900	Normalized	$t \leq \frac{1}{2}$	10C	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	70	36	1000	CS-2	G13, T3
2	70	36	1000	CS-2	G13, T3
3	70	36	1000	CS-2	G13, T2
4	70	36	1000	CS-2	G13, T3
5	70	36	1000	CS-2	G13, T3
6	70	36	1000	CS-2	G13, T3
7	70	36	1000	CS-2	G13, T3
8	70	36	1000	CS-2	G13, T3
9	70	38	1000	CS-2	G13, T3
10	70	38	1000	CS-2	G13, T3
11	70	40	1000	CS-2	G13, T3
12	70	40	1000	CS-2	G13, T3
13	70	40	1000	CS-2	G13, T3
14	70	40	800	CS-2	G13, T3
15	70	40	700	CS-2	...
16	70	43	700	CS-3	...
17	70	46	650	CS-3	...
18	70	46	650	CS-3	T1
19	70	50	700	CS-3	T2
20	70	50	650	CS-3	...
21	71	40.5	1000	CS-2	G13, T3
22	74	41.5	1000	CS-2	G13, T3
23	71	45.5	1000	CS-2	G13, T2
24	74	44	1000	CS-2	G13, T2
25	74	48.5	1000	CS-2	G13, T2
26	74	50	1000	CS-2	G13, T2
27	74	51.5	1000	CS-2	G13, T2
28	75	37.5	1000	CS-2	G13, T3, W6
29	75	40	1000	CS-2	G13, T3
30	75	42	1000	CS-2	G13, T2
31	75	45	650	CS-3	G9, H2, W2, W6
32	75	45	700	CS-2	...
33	75	45	700	CS-2	...
34	75	50	700	CS-5	T2
35	75	55	650	CS-5	...
36	75	55	650	CS-5	T1
37	80	45	1000	CS-3	G13, T2
38	80	47	1000	CS-3	G13, T2
39	80	50	700	CS-3	T1
40	80	55	700	CS-5	T2
41	80	60	650	CS-5	...
42	80	60	650	CS-5	...
43	80	60	650	CS-3	...
44	81	50	650	CS-3	...
45	83	50	650	CS-3	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
2	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
3	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	16.9	13.9	11.4	8.7	5.9
4	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
5	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
6	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
7	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
8	24.0	22.6	22.0	21.6	21.2	20.9	20.5	20.1	19.6	19.0	18.4	17.8	17.2	14.8	12.0	9.3	6.7
9	25.3	23.8	23.2	22.8	22.4	22.1	21.6	21.2	20.6	20.1	19.4	18.8	18.1	14.8	12.0	9.3	6.7
10	25.3	23.8	23.2	22.8	22.4	22.1	21.6	21.2	20.6	20.1	19.4	18.8	18.1	14.8	12.0	9.3	6.7
11	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.2	14.8	12.0	9.3	6.7
12	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.2	14.8	12.0	9.3	6.7
13	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.2	14.8	12.0	9.3	6.7
14	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.2	14.8	12.0	...	...
15	26.7	24.7	23.5	22.5	21.6	20.8	20.0	19.4	18.9	18.4	18.0	17.6	17.2	...	...	...	...
16	28.7	26.9	26.3	25.8	25.4	25.0	24.5	24.0	23.4	22.7	22.0	21.2	20.7	...	...	...	...
17	29.2	28.4	27.1	25.9	24.8	23.9	23.1	22.4	21.7	21.2	20.7	20.2	...	...	...	...	...
18	29.2	28.8	28.1	27.6	27.1	26.7	26.2	25.6	25.0	24.3	23.5	22.5	...	...	...	...	...
19	29.2	29.2	29.2	28.1	27.0	26.0	25.1	24.3	23.6	23.0	22.5	22.0	18.3	...	...	...	...
20	29.2	29.2	29.2	29.2	29.2	28.6	28.2	...	27.5	27.2	26.8	26.2	...	...	...	...	...
21	27.1	25.3	24.7	24.2	23.8	23.4	23.0	...	21.9	21.3	20.6	19.9	19.2	14.8	12.0	9.3	6.7
22	27.6	25.8	25.1	24.6	24.2	23.8	23.4	...	22.3	21.7	21.0	20.3	19.6	14.8	12.0	9.3	6.7
23	29.6	28.5	27.8	27.3	26.9	26.5	26.1	25.4	24.8	24.1	23.3	22.5	18.3	14.8	12.0	9.3	6.7
24	29.5	27.6	26.9	26.3	25.9	25.5	25.0	...	23.9	23.2	22.5	21.7	20.0	14.8	12.0	9.3	6.7
25	30.8	30.3	29.6	29.1	28.7	28.2	27.7	27.1	26.4	25.6	24.8	24.0	18.3	14.8	12.0	9.3	6.7
26	30.8	30.8	30.5	30.0	29.5	29.1	28.5	27.9	27.2	26.4	25.6	24.7	18.3	14.8	12.0	9.3	6.7
27	30.8	30.8	30.8	30.8	30.4	29.9	29.4	28.7	28.0	27.2	26.3	25.4	18.3	14.8	12.0	9.3	6.7
28	25.0	23.5	22.9	22.5	22.1	21.8	21.4	20.9	20.4	19.8	19.2	18.5	17.9	15.7	12.6	9.3	6.7
29	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.7	21.1	20.4	19.8	19.1	15.7	12.6	9.3	6.7
30	28.0	26.3	25.7	25.2	24.8	24.4	23.9	23.4	22.8	22.2	21.5	20.8	19.6	15.7	12.6	9.3	6.7
31	30.0	28.2	27.5	27.0	26.5	26.1	25.6	25.1	24.4	23.7	23.0	22.2	...	...	...	...	...
32	30.0	27.8	26.5	25.3	24.3	23.4	22.6	21.9	21.2	20.7	20.2	19.7	19.3	...	...	...	...
33	30.0	27.8	26.5	25.3	24.3	23.4	22.6	21.9	21.2	20.7	20.2	19.7	19.3	...	...	...	...
34	31.3	30.9	29.5	28.1	27.0	26.0	25.1	24.3	23.6	23.0	22.5	22.0	18.3	...	...	...	...
35	31.3	31.3	31.3	30.9	29.7	28.6	27.5	26.7	25.9	25.3	24.7	24.2	...	...	...	...	...
36	31.3	31.3	31.3	31.3	31.3	31.2	30.5	29.9	29.3	28.8	28.3	24.4	...	...	...	...	...
37	30.0	28.1	27.5	27.0	26.5	26.1	25.6	...	24.4	23.7	23.0	22.2	19.6	15.7	12.6	9.3	6.7
38	31.3	29.4	28.7	28.2	27.7	27.3	26.8	...	25.5	24.8	24.0	23.2	19.6	15.7	12.6	9.3	6.7
39	33.3	31.3	30.5	30.0	29.5	29.0	28.5	27.9	27.2	26.4	25.6	24.4	19.6	...	...	...	...
40	33.3	33.3	32.4	30.9	29.7	28.6	27.5	26.7	25.9	25.3	24.7	24.2	19.6	...	...	...	...
41	33.3	33.3	33.3	33.3	32.4	31.2	30.1	29.2	28.3	27.6	27.0	26.4	...	...	...	...	...
42	33.3	33.3	33.3	33.3	33.3	33.3	33.3	32.6	32.0	31.4	30.8	26.0	...	...	...	...	...
43	33.3	...	33.3	...	33.3	...	33.3	...	33.0	32.6	32.1	31.4	...	...	...	...	...
44	33.3	31.9	30.6	29.1	27.6	26.2	25.1	24.2	23.5	23.0	22.6	22.3	...	...	...	...	...
45	33.3	31.9	30.6	29.1	27.6	26.2	25.1	24.2	23.5	23.0	22.6	22.3	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	4.0	2.5	...	...	...	...	...	...	...	...	...	...
2	4.0	2.5	...	...	...	...	...	...	...	...	...	...
3	4.0	2.5	...	...	...	...	...	...	...	...	...	...
4	4.0	2.5	...	...	...	...	...	...	...	...	...	...
5	4.0	2.5	...	...	...	...	...	...	...	...	...	...
6	4.0	2.5	...	...	...	...	...	...	...	...	...	...
7	4.0	2.5	...	...	...	...	...	...	...	...	...	...
8	4.0	2.5	...	...	...	...	...	...	...	...	...	...
9	4.0	2.5	...	...	...	...	...	...	...	...	...	...
10	4.0	2.5	...	...	...	...	...	...	...	...	...	...
11	4.0	2.5	...	...	...	...	...	...	...	...	...	...
12	4.0	2.5	...	...	...	...	...	...	...	...	...	...
13	4.0	2.5	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...
21	4.0	2.5	...	...	...	...	...	...	...	...	...	(25)
22	4.0	2.5	...	...	...	...	...	...	...	...	...	(25)
23	4.0	2.5	...	...	...	...	...	...	...	...	...	...
24	4.0	2.5	...	...	...	...	...	...	...	...	...	(25)
25	4.0	2.5	...	...	...	...	...	...	...	...	...	...
26	4.0	2.5	...	...	...	...	...	...	...	...	...	...
27	4.0	2.5	...	...	...	...	...	...	...	...	...	...
28	4.0	2.5	...	...	...	...	...	...	...	...	...	...
29	4.0	2.5	...	...	...	...	...	...	...	...	...	...
30	4.0	2.5	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	4.0	2.5	...	...	...	...	...	...	...	...	...	...
38	4.0	2.5	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design/ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Plate	SA-738	B	K12007	...	...	1	3
2	Carbon steel	Forgings	SA-372	C	K04801	...	...	...	...
3	Carbon steel	Plate	SA-724	A	K11831	...	...	1	4
4	Carbon steel	Plate	SA-724	C	K12037	...	...	1	4
5	Carbon steel	Plate	SA-724	B	K12031	...	...	1	4
6	C-Mn-Si-Cb	Plate	SA-737	B	K12001	...	...	1	2
7	C-Mn-Si-V	Plate	SA-737	C	K12202	...	...	1	3
8	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1b	K11422	...	...	3	1
9	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1	K11522	...	...	3	1
10	C- $\frac{1}{2}$ Mo	Fittings	SA-234	WP1	K12821	...	...	3	1
11	C- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P1	K11522	...	...	3	1
12	C- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP1	K11522	...	...	3	1
13	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1a	K12023	...	...	3	1
14	C- $\frac{1}{2}$ Mo	Castings	SA-217	WC1	J12524	...	...	3	1
15	C- $\frac{1}{2}$ Mo	Castings	SA-352	LC1	J12522	...	...	3	1
16	C- $\frac{1}{2}$ Mo	Plate	SA-204	A	K11820	...	...	3	1
17	C- $\frac{1}{2}$ Mo	Forgings	SA-182	F1	K12822	...	...	3	2
18	C- $\frac{1}{2}$ Mo	Plate	SA-204	B	K12020	...	...	3	2
19	C- $\frac{1}{2}$ Mo	Forgings	SA-336	F1	K12520	...	...	3	2
20	C- $\frac{1}{2}$ Mo	Plate	SA-204	C	K12320	...	...	3	2
21	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	70	...	11B	...
22	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	70	...	11B	...
23	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo-V	Plate	SA-517	B	K11630	...	$t \leq 1\frac{1}{4}$	11B	4
24	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Plate	SA-517	A	K11856	...	$t \leq 1\frac{1}{4}$	11B	1
25	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Forgings	SA-592	A	K11856	...	$t \leq 2\frac{1}{2}$	11B	1
26	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P2	K11547	...	...	3	1
27	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP2	K11547	...	...	3	1
28	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-387	2	K12143	1	...	3	1
29	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T2	K11547	...	...	3	1
30	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F2	K12122	...	...	3	2
31	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-387	2	K12143	2/NT	...	3	2
32	$\frac{3}{4}$ Cr- $\frac{1}{2}$ Ni-Cu	Smls. tube	SA-423	1	K11535	...	...	4	2
33	$\frac{3}{4}$ Cr- $\frac{3}{4}$ Ni-Cu-Al	Smls. pipe	SA-333	4	K11267	...	...	4	2
34	1Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	E	K13047	70	...	11B	1
35	1Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	F	G41350	70	...	11B	1
36	1Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	J	K13548	70	...	11B	1
37	1Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	J	G41370	110	...	11B	1
38	1Cr- $\frac{1}{2}$ Mo	Plate	SA-387	12	K11757	1	...	4	1
39	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12	K11562	1	...	4	1
40	1Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T12	K11562	...	...	4	1
41	1Cr- $\frac{1}{2}$ Mo	Fittings	SA-234	WP12	K12062	1	...	4	1
42	1Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P12	K11562	...	...	4	1
43	1Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP12	K11562	...	...	4	1
44	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$10 < t \leq 20$	4	1
45	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$6 < t \leq 10$	4	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	85	60	650	CS-5	T1
2	90	55	650	CS-3	G9, H2, T1, W2, W6
3	90	70	700	CS-5	...
4	90	70	700	CS-5	...
5	95	75	700	CS-5	...
6	70	50	700	CS-3	...
7	80	60	700	CS-3	...
8	53	28	1000	CS-1	G14, T7
9	55	30	1000	CS-2	G14, T6
10	55	30	1000	CS-2	G14, T6
11	55	30	1000	CS-2	G14, T6
12	55	30	1000	CS-2	G14, T6
13	60	32	1000	CS-2	G14, T6
14	65	35	1000	CS-2	G14, T6
15	65	35	650	CS-2	...
16	65	37	1000	CS-2	G14, T6
17	70	40	1000	CS-2	G14, T6
18	70	40	1000	CS-2	G14, T6
19	70	40	1000	CS-2	G14, T6
20	75	43	1000	CS-2	G14, T6
21	120	70	200	CS-3	G9, H4, W2, W6
22	120	70	200	CS-3	G9, H4, W2, W6
23	115	100	650	HT-1	...
24	115	100	650	HT-1	...
25	115	100	650	HT-1	...
26	55	30	1000	CS-2	T7
27	55	30	1000	CS-2	T7
28	55	33	1000	CS-2	T6
29	60	30	1000	CS-2	T7
30	70	40	1000	CS-2	G14, T6
31	70	45	1000	CS-3	T6
32	60	37	650	CS-2	...
33	60	35	650	CS-2	...
34	120	70	650	CS-5	G9, H4, W2, W6
35	120	70	650	CS-5	G9, H4, W2, W6
36	120	70	650	CS-5	G9, H4, W2, W6
37	135	110	650	HT-1	H4, W2, W6
38	55	33	1200	CS-2	T7
39	60	32	1200	CS-2	T7
40	60	32	1200	CS-2	T7
41	60	32	1200	CS-2	T7
42	60	32	1200	CS-2	T7
43	60	32	1200	CS-2	T7
44	61	35	1200	CS-2	T7
45	61	35.5	1200	CS-2	T7

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	35.4	35.4	35.4	35.4	34.8	34.0	33.3	32.6	32.0	31.4	30.8	24.4	...	...	...	...	...
2	36.7	35.1	33.6	32.0	30.3	28.9	27.6	26.6	25.9	25.3	24.9	24.4	...	...	...	...	...
3	37.5	37.5	37.5	37.5	37.5	36.7	35.2	33.9	32.9	32.2	31.7	26.2	25.9	...	...	...	...
4	37.5	37.5	37.5	37.5	37.5	36.7	35.2	33.9	32.9	32.2	31.7	26.2	25.9	...	...	...	...
5	39.6	39.6	39.6	39.6	39.6	39.4	37.7	36.3	35.3	34.5	33.9	26.2	25.9	...	...	...	...
6	29.2	29.2	29.2	29.1	27.6	26.2	25.1	24.2	23.5	23.0	22.6	22.3	22.1	...	...	...	...
7	33.3	33.3	33.3	33.3	33.1	31.5	30.1	29.1	28.2	27.6	27.1	26.2	25.9	...	...	...	...
8	18.7	18.0	17.5	17.2	16.8	16.5	16.3	16.0	15.8	15.5	15.3	15.0	14.7	14.3	14.0	13.5	13.0
9	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.7
10	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.7
11	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.7
12	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.7
13	21.3	20.5	20.1	19.6	19.2	18.9	18.6	18.3	18.0	17.7	17.4	17.1	16.8	16.4	15.9	15.4	13.7
14	23.3	22.5	21.9	21.5	21.0	20.7	20.3	20.0	19.7	19.4	19.1	18.7	18.4	17.9	17.4	16.9	13.7
15	23.3	22.5	21.9	21.5	21.0	20.7	20.3	20.0	19.7	19.4	19.1	18.7	...	...	...	...	...
16	24.7	23.7	23.2	22.7	22.2	21.8	21.5	21.1	20.8	20.5	20.2	19.8	19.4	19.0	18.4	17.9	13.7
17	26.7	25.7	25.1	24.5	24.0	23.6	23.2	22.9	22.5	22.2	21.8	21.4	21.0	20.5	19.9	19.3	13.7
18	26.7	25.7	25.1	24.5	24.0	23.6	23.2	22.9	22.5	22.2	21.8	21.4	21.0	20.5	19.9	19.3	13.7
19	26.7	25.7	25.1	24.5	24.0	23.6	23.2	22.9	22.5	22.2	21.8	21.4	21.0	20.5	19.9	19.3	13.7
20	28.7	27.6	26.9	26.4	25.9	25.4	25.0	24.6	24.2	23.8	23.4	23.0	22.6	22.0	21.4	20.7	13.7
21	46.7	46.7	46.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	46.7	46.7	46.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
24	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
25	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
26	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.9
27	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.9
28	22.0	21.2	20.7	20.2	19.8	19.5	19.2	18.9	18.6	18.3	18.0	17.7	17.3	16.9	16.4	15.9	14.3
29	20.0	19.2	18.8	18.4	18.0	17.7	17.4	17.1	16.9	16.6	16.4	16.1	15.7	15.4	14.9	14.5	13.9
30	26.7	25.7	25.1	24.5	24.0	23.6	23.2	22.9	22.5	22.2	21.8	21.4	21.0	20.5	19.9	19.3	15.0
31	29.2	28.9	28.2	27.6	27.1	26.6	26.1	25.7	25.3	24.9	24.5	24.1	23.6	23.1	22.4	21.7	14.5
32	24.7	23.3	22.7	22.3	22.0	21.8	21.5	21.3	21.1	20.9	20.6	20.3	...	...	...	...	...
33	23.3	22.1	21.5	21.1	20.8	20.6	20.4	20.2	20.0	19.7	19.5	19.2	...	...	...	...	...
34	46.7	44.5	43.5	42.6	41.9	41.2	40.6	40.0	39.4	38.7	37.9	36.9	...	...	...	...	...
35	46.7	44.5	43.5	42.6	41.9	41.2	40.6	40.0	39.4	38.7	37.9	36.9	...	...	...	...	...
36	46.7	44.5	43.5	42.6	41.9	41.2	40.6	40.0	39.4	38.7	37.9	36.9	...	...	...	...	...
37	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
38	22.0	20.6	19.9	19.2	18.7	18.2	17.9	17.5	17.2	17.0	16.8	16.5	16.3	16.0	15.7	15.4	15.0
39	21.3	20.0	19.3	18.7	18.1	17.7	17.3	17.0	16.7	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
40	21.3	20.0	19.3	18.7	18.1	17.7	17.3	17.0	16.7	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
41	21.3	20.0	19.3	18.7	18.1	17.7	17.3	17.0	16.7	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
42	21.3	20.0	19.3	18.7	18.1	17.7	17.3	17.0	16.7	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
43	21.3	20.0	19.3	18.7	18.1	17.7	17.3	17.0	16.7	16.5	16.3	16.0	15.8	15.5	15.3	14.9	14.5
44	23.2	21.9	21.1	20.4	19.8	19.3	18.9	...	18.2	18.0	17.8	17.5	17.3	17.0	16.6	16.3	15.8
45	23.7	22.2	21.4	20.7	20.2	19.7	19.2	18.9	18.6	18.3	18.1	17.8	17.5	17.3	16.9	16.5	16.1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	8.2	4.8	...	...	...	...	...	...	...	...	...	...
9	8.2	4.8	...	...	...	...	...	...	...	...	...	...
10	8.2	4.8	...	...	...	...	...	...	...	...	...	...
11	8.2	4.8	...	...	...	...	...	...	...	...	...	...
12	8.2	4.8	...	...	...	...	...	...	...	...	...	...
13	8.2	4.8	...	...	...	...	...	...	...	...	...	...
14	8.2	4.8	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	8.2	4.8	...	...	...	...	...	...	...	...	...	...
17	8.2	4.8	...	...	...	...	...	...	...	...	...	...
18	8.2	4.8	...	...	...	...	...	...	...	...	...	...
19	8.2	4.8	...	...	...	...	...	...	...	...	...	...
20	8.2	4.8	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	9.2	5.9	...	...	...	...	...	...	...	...	...	...
27	9.2	5.9	...	...	...	...	...	...	...	...	...	...
28	9.2	5.9	...	...	...	...	...	...	...	...	...	...
29	9.2	5.9	...	...	...	...	...	...	...	...	...	...
30	9.2	5.9	...	...	...	...	...	...	...	...	...	...
31	10.0	6.3	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
39	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
40	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
41	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
42	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
43	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
44	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
45	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$4 < t \leq 6$	4	1
2	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$4 < t \leq 10$	4	1
3	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$2.5 < t \leq 4$	4	1
4	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$2.8 < t \leq 4$	4	1
(25) 5	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$1.4 < t \leq 2.8$	4	1
(25) 6	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT	$t \leq 1.4$	4	1
7	1Cr- $\frac{1}{2}$ Mo	Plate	SA-387	12	K11757	2	...	4	1
8	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$\frac{5}{8} < t \leq 2.5$	4	1
9	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...	$t \leq \frac{5}{8}$	4	1
10	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12	K11564	2	...	4	1
11	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F12	K11564	...	...	4	1
12	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC6	J12072	...	...	4	1
13	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Bar	SA-739	B11	K11797	...	...	4	1
14	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11597	1	...	4	1
15	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T11	K11597	...	...	4	1
16	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Fittings	SA-234	WP11	...	1	...	4	1
17	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P11	K11597	...	...	4	1
18	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forged pipe	SA-369	FP11	K11597	...	...	4	1
19	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	1	...	4	1
20	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11572	2	...	4	1
21	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	2	...	4	1
22	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	$4 < t \leq 10$	4	1
23	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	$2.25 < t \leq 4$	4	1
24	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT	≤ 2.25	4	1
25	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	3	...	4	1
26	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	2	...	4	1
27	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	$2\frac{1}{2} < t \leq 4$	11B	2
28	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...	$t \leq 2\frac{1}{2}$	11B	2
29	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	$2\frac{1}{2} < t \leq 6$	11B	2
30	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...	$t \leq 2\frac{1}{2}$	11B	2
31	$2\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	1	...	5A	1
32	$2\frac{1}{4}$ Cr-1Mo	Smls. tube	SA-213	T22	K21590	...	...	5A	1
33	$2\frac{1}{4}$ Cr-1Mo	Fittings	SA-234	WP22	K21590	1	...	5A	1
34	$2\frac{1}{4}$ Cr-1Mo	Smls. pipe	SA-335	P22	K21590	...	...	5A	1
35	$2\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	1	...	5A	1
36	$2\frac{1}{4}$ Cr-1Mo	Forged pipe	SA-369	FP22	K21590	...	...	5A	1
37	$2\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	1	...	5A	1
38	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$6 < t \leq 10$	5A	1
39	$2\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	$8 < t \leq 20$	5A	1
40	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$4 < t \leq 6$	5A	1
41	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$2.5 < t \leq 4$	5A	1
42	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$1.5 < t \leq 2.5$	5A	1
43	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$\frac{5}{8} < t \leq 1.5$	5A	1
44	$2\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...	$t \leq \frac{5}{8}$	5A	1
45	$2\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9	J21890	...	...	5A	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	62.5	37	1200	CS-2	T7
2	64	38.5	1200	CS-2	T7
3	64	39	1200	CS-2	T7
4	64	40	1200	CS-2	T6
5	64	41.5	1200	CS-2	T6
6	64	43	1200	CS-2	T6
7	65	40	1200	CS-2	T6
8	65.5	42	1200	CS-2	T6
9	65.5	43.5	1200	CS-2	T6
10	70	40	1200	CS-2	T6
11	70	40	1200	CS-2	T6
12	70	40	1100	CS-2	T6
13	70	45	1200	CS-3	T5
14	60	30	1200	CS-2	T7
15	60	30	1200	CS-2	T7
16	60	30	1200	CS-2	T7
17	60	30	1200	CS-2	T7
18	60	30	1200	CS-2	T7
19	60	35	1200	CS-2	T6
20	70	40	1200	CS-2	T7
21	70	40	1200	CS-2	T7
22	71	55	1058	CS-3	G15, T5
23	72.5	56.5	1058	CS-3	G15, T5
24	74	58	1058	CS-3	G15, T5
25	75	45	1200	CS-3	T5
26	75	45	1200	CS-3	T5
27	105	90	650	CS-5	S1
28	115	100	650	HT-1	...
29	105	90	650	CS-5	...
30	115	100	650	HT-1	...
31	60	30	1200	CS-2	T5, W5
32	60	30	1200	CS-2	T5, W5
33	60	30	1200	CS-2	T5, W5
34	60	30	1200	CS-2	T5, W5
35	60	30	1200	CS-2	T5, W5
36	60	30	1200	CS-2	T5, W5
37	60	30	1200	CS-2	H1, T5, W5
38	65.5	36.5	1100	CS-3	T6, W5
39	65.5	38.5	1200	CS-3	T6, W5
40	66.5	37.5	1100	CS-3	T6, W5
41	68	40.5	1100	CS-3	T6, W5
42	69.5	42	1100	CS-3	T6, W5
43	69.5	43.5	1100	CS-3	T6, W5
44	69.5	45	1100	CS-3	T5, W5
45	70	40	1200	CS-2	T7, W5

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	24.7	23.1	22.3	21.6	21.0	20.5	20.0	19.7	19.3	19.1	18.8	18.5	18.3	18.0	17.6	17.2	16.8
2	25.6	24.1	23.3	22.5	21.9	21.3	20.9	...	20.1	19.9	19.6	19.4	19.1	18.8	18.4	17.9	17.5
3	26.1	24.5	23.6	22.9	22.2	21.7	21.2	20.8	20.5	20.2	19.9	19.6	19.3	19.0	18.7	18.2	17.7
4	26.6	25.1	24.2	23.4	22.7	22.1	21.6	...	20.9	20.6	20.4	20.1	19.8	19.5	19.1	18.6	18.0
5	26.6	26.0	25.1	24.2	23.5	22.9	22.4	...	21.7	21.4	21.1	20.8	20.5	20.2	19.8	19.3	18.0
6	26.6	26.6	25.9	25.1	24.4	23.7	23.2	...	22.4	22.1	21.8	21.5	21.2	20.9	20.5	20.0	18.0
7	26.7	25.0	24.1	23.3	22.7	22.1	21.7	21.3	20.9	20.6	20.3	20.0	19.7	19.4	19.1	18.6	18.0
8	27.2	26.3	25.4	24.6	23.9	23.3	22.8	22.4	22.0	21.7	21.4	21.1	20.8	20.4	20.0	19.6	18.0
9	27.2	27.2	26.2	25.4	24.7	24.1	23.6	23.2	22.7	22.4	22.1	21.8	21.5	21.1	20.7	20.2	18.0
10	26.7	25.0	24.1	23.3	22.7	22.1	21.7	21.3	20.9	20.6	20.3	20.0	19.7	19.4	19.1	18.6	18.0
11	26.7	25.0	24.1	23.3	22.7	22.1	21.7	21.3	20.9	20.6	20.3	20.0	19.7	19.4	19.1	18.6	18.0
12	26.7	25.4	24.6	24.0	23.4	22.9	22.5	22.0	21.7	21.3	20.9	20.5	20.1	19.7	19.2	18.7	13.7
13	29.2	28.5	27.7	27.0	26.3	25.8	25.3	24.8	24.4	23.9	23.5	23.1	22.6	22.2	21.6	20.2	13.7
14	20.0	19.0	18.5	18.0	17.6	17.2	16.8	16.5	16.2	16.0	15.7	15.4	15.1	14.8	14.4	14.0	13.6
15	20.0	19.0	18.5	18.0	17.6	17.2	16.8	16.5	16.2	16.0	15.7	15.4	15.1	14.8	14.4	14.0	13.6
16	20.0	19.0	18.5	18.0	17.6	17.2	16.8	16.5	16.2	16.0	15.7	15.4	15.1	14.8	14.4	14.0	13.6
17	20.0	19.0	18.5	18.0	17.6	17.2	16.8	16.5	16.2	16.0	15.7	15.4	15.1	14.8	14.4	14.0	13.6
18	20.0	19.0	18.5	18.0	17.6	17.2	16.8	16.5	16.2	16.0	15.7	15.4	15.1	14.8	14.4	14.0	13.6
19	23.3	22.2	21.5	21.0	20.5	20.0	19.6	19.3	18.9	18.6	18.3	18.0	17.6	17.2	16.8	16.4	13.7
20	26.7	25.4	24.6	24.0	23.4	22.9	22.5	22.0	21.7	21.3	20.9	20.5	20.1	19.7	19.2	18.7	13.7
21	26.7	25.4	24.6	24.0	23.4	22.9	22.5	22.0	21.7	21.3	20.9	20.5	20.1	19.7	19.2	18.7	13.7
22	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.6	29.4	28.7	28.0	20.2	13.7
23	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	30.2	29.5	28.8	20.2	13.7
24	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.8	30.3	29.5	20.2	13.7
25	30.0	28.5	27.7	27.0	26.3	25.8	25.3	24.8	24.4	23.9	23.5	23.1	22.6	22.2	21.6	20.2	13.7
26	30.0	28.5	27.7	27.0	26.3	25.8	25.3	24.8	24.4	23.9	23.5	23.1	22.6	22.2	21.6	20.2	13.7
27	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
28	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
29	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
30	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
31	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
32	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
33	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
34	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
35	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
36	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
37	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	17.1	13.6
38	24.2	22.8	22.1	21.6	21.1	20.8	20.5	20.3	20.0	19.8	19.6	19.4	19.1	18.8	18.4	18.0	15.8
39	25.6	24.2	23.5	22.9	22.4	22.0	21.7	...	21.2	21.0	20.8	20.6	20.3	20.0	19.5	19.0	15.8
40	25.1	23.7	23.0	22.4	22.0	21.6	21.3	21.1	20.8	20.6	20.4	20.2	19.9	19.6	19.2	18.7	15.8
41	27.1	25.5	24.8	24.2	23.7	23.3	22.9	22.7	22.4	22.2	22.0	21.7	21.4	21.1	20.7	20.1	15.8
42	28.0	26.5	25.7	25.0	24.5	24.1	23.8	23.5	23.2	23.0	22.8	22.5	22.2	21.8	21.4	20.9	15.8
43	29.0	27.4	26.6	25.9	25.4	24.9	24.6	24.3	24.0	23.8	23.6	23.3	23.0	22.6	22.1	21.6	15.8
44	29.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.1	23.7	23.3	22.9	21.9	15.8
45	26.7	25.3	24.7	24.2	23.9	23.6	23.4	23.2	23.0	22.7	22.5	22.2	21.9	21.6	21.2	20.7	16.0

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
2	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
3	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
4	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
5	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
6	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
7	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
8	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
9	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
10	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
11	11.3	7.2	4.5	2.8	1.8	1.1	...	...	...	...	...	...
12	9.3	6.3	4.2	2.8	...	...	...	...	...	...	...	...
13	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
14	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
15	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
16	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
17	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
18	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
19	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
20	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
21	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
22	9.3	6.3	4.2	2.8	...	...	...	...	...	...	...	...
23	9.3	6.3	4.2	2.8	...	...	...	...	...	...	...	...
24	9.3	6.3	4.2	2.8	...	...	...	...	...	...	...	...
25	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
26	9.3	6.3	4.2	2.8	1.9	1.2	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
32	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
33	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
34	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
35	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
36	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
37	10.8	8.0	5.7	3.8	2.4	1.4	...	...	...	...	...	...
38	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
39	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
40	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
41	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
42	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
43	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
44	11.4	7.8	5.1	3.2	...	...	...	...	...	...	...	...
45	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
(25)	1 2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	3	...	5A	1
	2 2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	3	...	5A	1
	3 2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	2	...	5A	1
	4 2 $\frac{1}{4}$ Cr-1Mo	Bar	SA-739	B22	K21390	...	...	5A	1
	5 2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT	$t \leq 8$	5A	1
	6 2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-487	8	J22091	A	...	5C	1
	7 2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-508	22	K21590	3	...	5C	1
	8 2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	3	...	5C	1
	9 2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-542	B	K21590	4	...	5C	1
	10 2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-182	F22V	K31835	...	...	5C	1
	11 2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-336	F22V	K31835	...	...	5C	1
	12 2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-541	22V	K31835	...	...	5C	1
	13 2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-542	D	K31835	4a	...	5C	1
	14 2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-832	22V	K31835	...	...	5C	1
	15 3Cr-1Mo	Smls. tube	SA-213	T21	K31545	...	...	5A	1
	16 3Cr-1Mo	Smls. pipe	SA-335	P21	K31545	...	...	5A	1
	17 3Cr-1Mo	Forgings	SA-336	F21	K31545	1	...	5A	1
	18 3Cr-1Mo	Forged pipe	SA-369	FP21	K31545	...	...	5A	1
	19 3Cr-1Mo	Plate	SA-387	21	K31545	1	...	5A	1
	20 3Cr-1Mo	Forgings	SA-182	F21	K31545	...	...	5A	1
	21 3Cr-1Mo	Forgings	SA-336	F21	K31545	3	...	5A	1
	22 3Cr-1Mo	Plate	SA-387	21	K31545	2	...	5A	1
	23 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-182	F3V	K31830	...	...	5C	1
	24 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-336	F3V	K31830	...	...	5C	1
	25 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-508	3V	K31830	...	...	5C	1
	26 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-541	3V	K31830	...	...	5C	1
	27 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-542	C	K31830	4a	...	5C	1
	28 3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-832	21V	K31830	...	...	5C	1
	29 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-182	F3VCb	K31390	...	...	5C	1
	30 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-336	F3VCb	K31390	...	...	5C	1
	31 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-508	3VCb	K31390	...	...	5C	1
	32 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-541	3VCb	K31390	...	...	5C	1
	33 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-542	E	K31390	4a	...	5C	1
	34 3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-832	23V	K31390	...	...	5C	1
	35 5Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T5	K41545	...	...	5B	1
	36 5Cr- $\frac{1}{2}$ Mo	Fittings	SA-234	WP5	K41545	...	...	5B	1
	37 5Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P5	K41545	...	...	5B	1
	38 5Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP5	K41545	...	...	5B	1
	39 5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	1	...	5B	1
	40 5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5	K41545	...	...	5B	1
	41 5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5	K41545	...	...	5B	1
	42 5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	2	...	5B	1
	43 5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5A	K42544	...	...	5B	1
	44 5Cr- $\frac{1}{2}$ Mo	Castings	SA-217	C5	J42045	NT	...	5B	1
	45 5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5a	K42544	...	...	5B	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	75	45	1200	CS-3	T5, W5
2	75	45	1200	CS-3	T5, W5
3	75	45	1200	CS-3	T5, W5
4	75	45	1200	CS-3	T5, W5
5	75.5	45	1200	CS-3	T5, W5
6	85	55	1000	CS-3	T5, W5
7	85	55	850	CS-2	G12, T5
8	85	55	850	CS-2	G12, T5
9	85	55	850	CS-2	G12, T5
10	85	60	900	CS-2	G12, T5
11	85	60	900	CS-2	G12, T5
12	85	60	900	CS-2	G12, T5
13	85	60	900	CS-2	G12, T5
14	85	60	900	CS-2	G12, T5
15	60	30	1200	CS-2	T5
16	60	30	1200	CS-2	T5
17	60	30	1200	CS-2	T5
18	60	30	1200	CS-2	T5
19	60	30	1200	CS-2	T5
20	75	45	1200	CS-3	T6
21	75	45	1200	CS-3	T6
22	75	45	1200	CS-3	T6
23	85	60	900	CS-3	G12, T4
24	85	60	900	CS-3	G12, T4
25	85	60	900	CS-3	G12, T4
26	85	60	900	CS-3	G12, T4
27	85	60	900	CS-3	G12, T4
28	85	60	900	CS-3	G12, T4
29	85	60	900	CS-3	G12, T4
30	85	60	900	CS-3	G12, T4
31	85	60	900	CS-3	G12, T4
32	85	60	900	CS-3	G12, T4
33	85	60	900	CS-3	G12, T4
34	85	60	900	CS-3	G12, T4
35	60	30	1200	CS-2	T5
36	60	30	1200	CS-2	T5
37	60	30	1200	CS-2	T5
38	60	30	1200	CS-2	T5
39	60	30	1200	CS-2	T5
40	60	36	1200	CS-2	T5
41	70	40	1200	CS-2	T5
42	75	45	1200	CS-3	T5
43	80	50	1200	CS-3	T5
44	90	60	1200	CS-3	T5
45	90	65	1200	CS-5	T5

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	21.9	17.0
2	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	21.9	17.0
3	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	21.9	17.0
4	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	21.9	17.0
5	30.0	28.3	27.5	26.8	26.2	25.8	25.4	...	24.8	24.6	24.4	24.1	23.8	23.4	22.9	21.9	15.8
6	35.4	34.7	33.9	33.3	32.8	32.4	32.1	31.9	31.6	31.3	31.0	30.6	30.2	29.7	29.2	21.9	15.8
7	35.4	34.7	33.9	33.3	32.8	32.4	32.1	31.9	31.6	31.3	31.0	30.6	30.2	29.7	29.2	21.9	...
8	35.4	34.7	33.9	33.3	32.8	32.4	32.1	31.9	31.6	31.3	31.0	30.6	30.2	29.7	29.2	21.9	...
9	35.4	34.7	33.9	33.3	32.8	32.4	32.1	31.9	31.6	31.3	31.0	30.6	30.2	29.7	29.2	21.9	...
10	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.9	34.2	33.4	28.9	23.8
11	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.9	34.2	33.4	28.9	23.8
12	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.9	34.2	33.4	28.9	23.8
13	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.9	34.2	33.4	28.9	23.8
14	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.9	34.2	33.4	28.9	23.8
15	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	16.0	12.0
16	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	16.0	12.0
17	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	16.0	12.0
18	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	16.0	12.0
19	20.0	19.1	18.7	18.4	18.2	18.0	18.0	17.9	17.9	17.9	17.9	17.9	17.9	17.9	17.7	16.0	12.0
20	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	19.0	13.1
21	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	19.0	13.1
22	30.0	28.3	27.5	26.8	26.2	25.8	25.4	25.1	24.8	24.6	24.3	24.0	23.7	23.3	22.9	19.0	13.1
23	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
24	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
25	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
26	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
27	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
28	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
29	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
30	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
31	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
32	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
33	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
34	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.1	33.3	31.2	25.8	21.0
35	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
36	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
37	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
38	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
39	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
40	24.0	22.4	21.7	21.2	20.9	20.7	20.6	20.5	20.5	20.4	20.2	19.9	19.6	19.1	18.5	14.3	10.9
41	26.7	24.9	24.1	23.6	23.2	23.0	22.9	22.8	22.7	22.6	22.4	22.1	21.7	21.2	20.5	14.3	10.9
42	30.0	28.0	27.1	26.5	26.1	25.9	25.8	25.7	25.6	25.4	25.2	24.9	24.5	23.9	23.1	14.3	10.9
43	33.3	31.1	30.1	29.5	29.0	28.8	28.6	28.5	28.4	28.3	28.0	27.7	27.2	26.5	25.7	14.3	10.9
44	37.5	37.3	36.2	35.4	34.8	34.5	34.4	34.2	34.1	33.9	33.6	33.2	32.6	31.8	30.8	14.3	10.9
45	37.5	37.5	37.5	37.5	37.5	37.4	37.2	37.1	36.9	36.7	36.4	36.0	35.3	34.5	33.4	14.3	10.9

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
2	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
3	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
4	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
5	11.4	7.8	5.1	3.2	2.0	1.2	...	...	...	...	...	...
6	11.4	7.8	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...
15	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...
16	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...
17	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...
18	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...
19	9.0	7.0	5.5	4.0	2.7	1.5	...	...	...	...	...	...
20	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...
21	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...
22	9.5	6.8	4.9	3.2	2.4	1.3	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
36	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
37	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
38	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
39	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
40	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
41	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
42	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
43	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
44	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
45	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...

(25)

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design/ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	5Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T5b	K51545	...	...	5B	1
2	5Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P5b	K51545	...	...	5B	1
3	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. tube	SA-213	T5c	K41245	...	...	5B	1
4	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. pipe	SA-335	P5c	K41245	...	...	5B	1
5	9Cr-1Mo	Smls. tube	SA-213	T9	K90941	...	...	5B	1
6	9Cr-1Mo	Fittings	SA-234	WP9	K90941	...	...	5B	1
7	9Cr-1Mo	Smls. pipe	SA-335	P9	K90941	...	...	5B	1
8	9Cr-1Mo	Forged pipe	SA-369	FP9	K90941	...	...	5B	1
9	9Cr-1Mo	Forgings	SA-182	F9	K90941	...	...	5B	1
10	9Cr-1Mo	Forgings	SA-336	F9	K90941	...	...	5B	1
11	9Cr-1Mo	Castings	SA-217	C12	J82090	NT	...	5B	1
12	9Cr-1Mo-V	Smls. tube	SA-213	T91 Type 1	K90901	...	...	15E	1
13	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Type 1	K90901	...	...	15E	1
14	9Cr-1Mo-V	Plate	SA-387	91 Type 1	K90901	2	...	15E	1
15	9Cr-1Mo-V	Forgings	SA-182	F91 Type 1	K90901	...	...	15E	1
16	9Cr-1Mo-V	Forgings	SA-336	F91 Type 1	K90901	...	...	15E	1
17	12Cr-Al	Plate	SA-240	405	S40500	...	...	7	1
18	12Cr-Al	Smls. tube	SA-268	TP405	S40500	...	...	7	1
19	13Cr	Plate	SA-240	410S	S41008	...	...	7	1
20	13Cr	Smls. tube	SA-268	TP410	S41000	...	...	6	1
21	13Cr	Plate	SA-240	410	S41000	...	...	6	1
(25) 22	13Cr	Forgings	SA-182	F6a	S41000	1	...	6	3
(25) 23	13Cr	Forgings	SA-182	F6a	S41000	2	...	6	3
24	13Cr	Forgings	SA-336	F6	S41000	...	...	6	3
25	13Cr	Castings	SA-217	CA15	J91150	...	...	6	3
26	15Cr	Smls. tube	SA-268	TP429	S42900	...	...	6	2
27	15Cr	Plate	SA-240	429	S42900	...	...	6	2
28	17Cr	Smls. tube	SA-268	TP430	S43000	...	...	7	2
29	17Cr	Plate	SA-240	430	S43000	...	...	7	2
(25) 30	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1100	...	...	...
(25) 31	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1100	...	...	...
(25) 32	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1100	...	...	...
33	26Cr-3Ni-3Mo	Plate	SA-240	26-3-3	S44660	...	$t \leq \frac{2}{10}$	10K	1
34	26Cr-3Ni-3Mo	Smls. tube	SA-268	26-3-3	S44660	...	$t \leq \frac{2}{10}$	10K	1
35	26Cr-3Ni-3Mo	Wld. tube	SA-268	26-3-3	S44660	...	$t \leq \frac{2}{10}$	10K	1
36	26Cr-3Ni-3Mo	Wld. tube	SA-803	26-3-3	S44660	...	$t \leq \frac{2}{10}$	10K	1
37	29Cr-4Mo-Ti	Smls. tube	SA-268	...	S44735	...	...	10J	1
38	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	QT	...	11A	4
39	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	...	...	11A	4
40	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	A	K12021	...	...	3	2
41	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	B	K12022	...	...	3	3
42	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	1	...	3	3
43	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	2	...	3	3
44	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	2	...	3	3
45	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	3	...	11A	4

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	60	30	1200	CS-2	T5
2	60	30	1200	CS-2	T5
3	60	30	1200	CS-2	T5
4	60	30	1200	CS-2	T5
5	60	30	1200	CS-2	T7
6	60	30	1200	CS-2	T7
7	60	30	1200	CS-2	T7
8	60	30	1200	CS-2	T7
9	85	55	1200	CS-3	T6
10	85	55	1200	CS-3	T6
11	90	60	1200	CS-3	T6
12	85	60	1200	CS-3	T7
13	85	60	1200	CS-3	T7
14	85	60	1200	CS-3	T7
15	90	60	1200	CS-3	T7
16	90	60	1200	CS-3	T7
17	60	25	1000	CS-1	G8, T7
18	60	30	1000	CS-2	G8, T7
19	60	30	1200	CS-2	T6
20	60	30	1200	CS-2	T6
21	65	30	1200	CS-2	T6
22	70	40	1200	CS-3	T5
23	85	55	1200	CS-3	T4
24	85	55	1200	CS-3	T4
25	90	65	1200	CS-5	T4
26	60	35	1200	CS-2	G8, T5
27	65	30	1200	CS-2	G8, T6
28	60	35	1200	CS-2	G8, T5
29	65	30	1200	CS-2	G8, T6
30	140	115	600	HT-1	G8
31	140	115	600	HT-1	G8
32	140	115	600	HT-1	G8
33	85	65	700	HA-5	G8, H3
34	85	65	700	HA-5	G8, H3
35	85	65	700	HA-5	G6, G8, H3
36	85	65	600	HA-5	G6, G8, H3
37	75	60	800	HA-6	G8
38	105	65	650	CS-5	G9, T1, W2, W6
39	105	65	650	CS-5	G9, H2, W2, W6
40	75	45	1000	CS-3	G14, T5
41	80	50	1000	CS-3	G14, T5
42	80	50	1000	CS-5	T5
43	90	70	800	CS-5	...
44	90	70	800	CS-5	...
45	100	83	750	CS-5	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
2	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
3	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
4	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.3	10.9
5	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.8	14.1
6	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.8	14.1
7	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.8	14.1
8	20.0	18.7	18.1	17.7	17.4	17.3	17.2	17.1	17.1	17.0	16.8	16.6	16.3	15.9	15.4	14.8	14.1
9	35.4	34.2	33.1	32.4	31.9	31.7	31.5	31.4	31.3	31.1	30.8	30.4	29.9	29.2	28.2	27.1	16.4
10	35.4	34.2	33.1	32.4	31.9	31.7	31.5	31.4	31.3	31.1	30.8	30.4	29.9	29.2	28.2	27.1	16.4
11	37.5	37.3	36.2	35.4	34.8	34.5	34.4	34.2	34.1	33.9	33.6	33.2	32.6	31.8	30.8	29.6	16.4
12	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.7	33.6	32.3
13	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.7	33.6	32.3
14	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	34.7	33.6	32.3
15	37.5	37.5	37.3	36.8	36.5	36.5	36.5	36.5	36.5	36.5	36.3	36.0	35.4	34.7	33.6	32.3	30.8
16	37.5	37.5	37.3	36.8	36.5	36.5	36.5	36.5	36.5	36.5	36.3	36.0	35.4	34.7	33.6	32.3	30.8
17	16.7	15.8	15.3	15.0	14.8	14.6	14.5	14.4	14.3	14.2	14.0	13.8	13.5	13.1	12.6	12.0	11.3
18	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	13.5
19	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	12.3
20	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	12.3
21	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	12.3
22	26.7	25.2	24.5	24.0	23.7	23.5	23.3	23.1	22.9	22.7	22.5	22.1	21.6	20.9	20.1	17.2	12.3
23	35.4	34.7	33.7	33.1	32.5	32.3	32.0	31.8	31.5	31.2	30.9	30.3	29.7	28.8	24.0	17.2	12.3
24	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	24.0	17.2	12.3
25	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	24.0	17.2	12.3
26	23.3	22.1	21.5	21.0	20.7	20.5	20.3	20.2	20.1	19.9	19.6	19.3	18.9	18.3	17.6	15.7	12.0
27	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	12.0
28	23.3	22.1	21.5	21.0	20.7	20.5	20.3	20.2	20.1	19.9	19.6	19.3	18.9	18.3	17.6	15.7	12.0
29	20.0	18.9	18.4	18.0	17.8	17.6	17.4	17.3	17.2	17.0	16.8	16.6	16.2	15.7	15.1	14.4	12.0
30	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	...	...	...	...	...	...
31	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	...	...	...	...	...	...
32	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	58.3	...	...	...	...	...	...
33	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.2	33.8	33.4	33.2	33.0	32.8	...	...	...	...
34	35.4	35.4	35.4	35.4	35.4	35.4	34.8	34.2	33.8	33.4	33.2	33.0	32.8	...	...	...	...
35	30.1	30.1	30.1	30.1	30.1	30.1	29.6	29.1	28.7	28.4	28.2	28.0	27.9	...	...	...	...
36	30.1	30.1	30.1	30.1	30.1	30.1	29.6	29.1	28.7	28.4	28.2	...	...	...	...	...	...
37	31.3	31.3	31.3	31.3	29.6	28.1	26.8	25.7	24.9	24.3	23.9	23.7	23.6	23.3	22.7	...	...
38	43.3	41.8	41.2	40.4	39.4	38.2	36.9	35.7	34.7	33.9	33.5	24.4	...	...	...	...	...
39	43.3	41.6	40.8	40.0	39.4	38.8	38.3	37.9	37.4	36.9	36.5	35.9	...	...	...	...	...
40	30.0	28.8	28.2	27.7	27.3	26.9	26.5	26.2	25.9	25.6	25.2	24.9	24.4	23.9	23.2	20.0	13.7
41	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	20.0	13.7
42	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	20.0	13.7
43	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.2	36.0	...	...
44	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.2	36.0	...	...
45	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
2	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
3	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
4	8.0	5.8	4.2	2.9	1.8	1.0	...	...	...	...	...	...
5	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
6	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
7	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
8	10.6	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
9	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
10	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
11	11.0	7.4	5.0	3.3	2.2	1.5	...	...	...	...	...	...
12	25.9	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...
13	25.9	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...
14	25.9	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...
15	25.9	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...
16	25.9	16.1	12.2	8.7	5.7	3.5	...	...	...	...	...	...
17	8.4	4.0	...	...	...	...	...	...	...	...	...	...
18	8.4	4.0	...	...	...	...	...	...	...	...	...	...
19	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...
20	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...
21	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...
22	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	(25)
23	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	(25)
24	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...
25	8.8	6.4	4.4	2.9	1.8	1.0	...	...	...	...	...	...
26	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...
27	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...
28	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...
29	9.2	6.5	4.5	3.2	2.4	1.8	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...
40	8.2	4.8	...	...	...	...	...	...	...	...	...	...
41	8.2	4.8	...	...	...	...	...	...	...	...	...	...
42	8.2	4.8	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-302	C	K12039	...	...	3	3
2	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	1	...	3	3
3	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	2	...	3	3
4	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	3	...	11A	4
5	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-302	D	K12054	...	...	3	3
6	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	1	...	3	3
7	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	1	...	3	3
8	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	2	...	3	3
9	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	2	...	3	3
(25) 10	...	...	...	...	...	...	...	...	...
11	Mn- $\frac{1}{2}$ Ni-V	Plate	SA-225	C	K12524	...	...	10A	1
12	Mn-V	Castings	SA-487	1	J13002	A/NT	...	10A	1
13	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	A/NT	...	3	3
14	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	1	...	3	3
15	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	2	...	3	3
16	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$2\frac{1}{2} < t \leq 4$	11B	3
17	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Plate	SA-517	F	K11576	...	$t \leq 2\frac{1}{2}$	11B	3
18	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...	$t \leq 2\frac{1}{2}$	11B	3
19	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Smls. tube	SA-423	2	K11540	...	...	4	2
20	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	1	...	3	3
21	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	1	...	3	3
22	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	2	...	3	3
23	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	2	...	3	3
24	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	1	...	3	3
25	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	2	...	3	3
26	$\frac{3}{4}$ Ni-1Mo- $\frac{3}{4}$ Cr	Castings	SA-217	WC5	J22000	...	...	4	1
27	1Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC4	J12082	...	...	4	1
28	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$2\frac{1}{2} < t \leq 4$	11B	8
29	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...	$t \leq 2\frac{1}{2}$	11B	8
30	2Ni-1Cu	Forgings	SA-182	FR	K22035	...	...	9A	1
31	2Ni-1Cu	Smls. pipe	SA-333	9	K22035	...	...	9A	1
32	2Ni-1Cu	Smls. pipe	SA-334	9	K22035	...	...	9A	1
33	2Ni-1Cu	Forgings	SA-350	LF9	K22036	...	...	9A	1
34	2Ni-1Cu	Fittings	SA-420	WPL9	K22035	...	...	9A	1
(25) 35	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N	K23550	100	...	...	...
36	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	1	...	11B	10
(25) 37	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N	K23550	120	...	...	...
38	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1	K23550	2	...	11B	10
39	$2\frac{1}{2}$ Ni	Plate	SA-203	A	K21703	...	...	9A	1
40	$2\frac{1}{2}$ Ni	Plate	SA-203	B	K22103	...	...	9A	1
41	$2\frac{1}{2}$ Ni	Castings	SA-352	LC2	J22500	...	...	9A	1
42	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	K34035	3	...	3	3
43	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	K34035	1	...	11A	5
44	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C	K34035	2	...	11B	10
(25) 45	$2\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	P	K34035	100	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	80	50	1000	CS-3	G14, T5
2	80	50	800	CS-5	...
3	90	70	800	CS-5	...
4	100	83	800	CS-5	...
5	80	50	1000	CS-3	G14, T5
6	80	50	800	CS-5	...
7	80	50	800	CS-5	...
8	90	70	800	CS-5	...
9	90	70	800	CS-5	...
10	...	...	...	...	...
11	105	70	700	CS-5	T1
12	85	55	650	CS-3	T1
13	90	60	650	CS-3	...
14	80	50	800	CS-5	...
15	90	65	700	CS-5	...
16	105	90	650	CS-5	S1
17	115	100	650	HT-1	...
18	115	100	650	HT-1	...
19	60	37	650	CS-2	...
20	80	50	800	CS-5	...
21	80	50	800	CS-5	...
22	90	65	700	CS-5	...
23	90	65	700	CS-5	...
24	80	50	800	CS-5	...
25	90	65	700	CS-5	...
26	70	40	1100	CS-2	T6
27	70	40	1000	CS-2	T6
28	105	90	650	CS-5	...
29	115	100	650	HT-1	...
30	63	46	100	CS-3	...
31	63	46	100	CS-3	...
32	63	46	100	CS-3	...
33	63	46	100	CS-3	...
34	63	46	100	CS-3	...
35	115	100	650	HT-1	W1
36	115	100	650	HT-1	G10, G11, W1
37	135	120	650	HT-1	W1
38	135	120	650	HT-1	G11, W1
39	65	37	1000	CS-2	T3
40	70	40	1000	CS-2	T2
41	70	40	650	CS-2	...
42	90	70	650	CS-5	...
43	105	85	650	CS-5	...
44	115	100	650	HT-1	...
45	115	100	650	HT-1	W1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	20.0	13.7
2	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
3	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.2	36.0	...	...
4	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	...	...
5	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	20.0	13.7
6	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
7	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
8	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.2	36.0	...	...
9	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.2	36.0	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	43.8	43.3	42.5	42.1	41.6	40.9	39.9	38.6	37.3	36.0	34.9	24.4	19.6	...	...	...	...
12	35.4	35.2	34.5	33.9	33.3	32.9	32.4	32.0	31.6	31.3	30.9	24.4	...	...	...	...	...
13	37.5	37.5	37.5	37.0	36.3	35.8	35.5	35.2	34.6	33.7	32.4	31.0	...	...	...	...	...
14	33.3	32.6	31.7	30.8	30.2	29.9	29.6	29.3	28.9	28.1	27.0	25.8	24.9	24.9	24.9	...	...
15	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	36.5	35.1	33.6	32.3	...	...	...	...
16	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
17	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
18	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
19	24.7	23.3	22.7	22.3	22.0	21.8	21.5	21.3	21.1	20.9	20.6	20.3	...	...	...	...	...
20	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
21	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
22	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.4	36.9	36.5	35.9	35.3	...	...	...	...
23	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.4	36.9	36.5	35.9	35.3	...	...	...	...
24	33.3	32.0	31.4	30.8	30.3	29.9	29.5	29.1	28.8	28.4	28.0	27.6	27.1	26.5	25.7	...	...
25	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.4	36.9	36.5	35.9	35.3	...	...	...	...
26	26.7	25.6	25.1	24.6	24.3	23.9	23.6	23.3	23.0	22.7	22.4	22.1	21.7	21.2	20.6	19.8	16.3
27	26.7	25.6	25.1	24.6	24.3	23.9	23.6	23.3	23.0	22.7	22.4	22.1	21.7	21.2	20.6	19.8	15.0
28	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
29	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
30	26.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	26.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	26.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	26.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	26.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
36	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
37	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
38	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
39	24.7	23.2	22.6	22.2	21.8	21.5	21.1	20.6	20.0	19.3	18.5	17.6	16.6	13.9	11.4	9.0	6.5
40	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.6	20.9	20.0	19.0	16.9	13.9	11.4	9.0	6.5
41	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.6	20.9	20.0	19.0	...	...	...	...	...
42	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	...	...	...	...	...
43	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
44	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
45	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	8.2	4.8	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...
5	8.2	4.8	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	11.0	6.9	4.6	2.8	...	...	...	...	...	...	...	...
27	9.2	5.9	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...
39	4.5	2.5	...	...	...	...	...	...	...	...	...	...
40	4.5	2.5	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	(25)

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design/ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
(25) 1	2 ³ / ₄ Ni-1 ¹ / ₂ Cr- ¹ / ₂ Mo-V	Forgings	SA-723	2	K34035	1	...	11B	10
2	2 ³ / ₄ Ni-1 ¹ / ₂ Cr- ¹ / ₄ Mo-V	Forgings	SA-372	P	K34035	120	...	...	...
3	2 ³ / ₄ Ni-1 ¹ / ₂ Cr- ¹ / ₂ Mo-V	Forgings	SA-723	2	K34035	2	...	11B	10
4	3Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo	Plate	SA-543	B	K42339	3	...	3	3
5	3Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo	Plate	SA-543	B	K42339	1	...	11A	5
6	3Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo	Plate	SA-543	B	K42339	2	...	11B	10
7	3 ¹ / ₂ Ni	Smls. pipe	SA-333	3	K31918	...	...	9B	1
8	3 ¹ / ₂ Ni	Smls. tube	SA-334	3	K31918	...	...	9B	1
9	3 ¹ / ₂ Ni	Fittings	SA-420	WPL3	...	...	...	9B	1
10	3 ¹ / ₂ Ni	Plate	SA-203	D	K31718	...	...	9B	1
11	3 ¹ / ₂ Ni	Forgings	SA-350	LF3	K32025	...	...	9B	1
12	3 ¹ / ₂ Ni	Forgings	SA-765	III	K32026	...	...	9B	1
13	3 ¹ / ₂ Ni	Plate	SA-203	E	K32018	...	...	9B	1
14	3 ¹ / ₂ Ni	Castings	SA-352	LC3	J31550	...	...	9B	1
15	3 ¹ / ₂ Ni	Plate	SA-203	F	...	...	t > 2	9B	1
16	3 ¹ / ₂ Ni	Plate	SA-203	F	...	...	t ≤ 2	9B	1
17	3 ¹ / ₂ Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo-V	Forgings	SA-508	4N	K22375	3	...	3	3
18	3 ¹ / ₂ Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo-V	Forgings	SA-508	4N	K22375	1	...	11A	5
19	3 ¹ / ₂ Ni-1 ³ / ₄ Cr- ¹ / ₂ Mo-V	Forgings	SA-508	4N	K22375	2	...	11B	10
20	4Ni-1 ¹ / ₂ Cr- ¹ / ₂ Mo-V	Forgings	SA-723	3	K44045	1	...	11B	10
21	4Ni-1 ¹ / ₂ Cr- ¹ / ₂ Mo-V	Forgings	SA-723	3	K44045	2	...	11B	10
22	5Ni- ¹ / ₄ Mo	Plate	SA-645	A	K41583	...	...	11A	2
23	7Ni	Plate	SA-553	III	K61365	...	t ≤ 2	11A	1
24	7Ni	Plate	SA-553	III	K61365	...	t ≤ 2	11A	1
25	8Ni	Plate	SA-553	II	K71340	...	...	11A	1
26	8Ni	Plate	SA-553	II	K71340	...	...	11A	1
27	9Ni	Smls. pipe	SA-333	8	K81340	...	...	11A	1
28	9Ni	Smls. pipe	SA-333	8	K81340	...	...	11A	1
29	9Ni	Smls. tube	SA-334	8	K81340	...	...	11A	1
30	9Ni	Smls. tube	SA-334	8	K81340	...	...	11A	1
31	9Ni	Plate	SA-353	...	K81340	...	...	11A	1
32	9Ni	Plate	SA-353	...	K81340	...	...	11A	1
33	9Ni	Fittings	SA-420	WPL8	K81340	...	...	11A	1
34	9Ni	Fittings	SA-420	WPL8	K81340	...	...	11A	1
35	9Ni	Forgings	SA-522	I	K81340	...	...	11A	1
36	9Ni	Forgings	SA-522	I	K81340	...	...	11A	1
37	9Ni	Plate	SA-553	I	K81340	...	...	11A	1
38	9Ni	Plate	SA-553	I	K81340	...	...	11A	1
(25) 39	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10	N08810	...	...	45	...
(25) 40	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H	N08810	...	...	45	...
(25) 41	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...	...	45	...
(25) 42	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H	N08810	...	...	45	...
(25) 43	42Fe-33Ni-21Cr	Bar	SA-276	800H	N08810	...	...	45	...
(25) 44	42Fe-33Ni-21Cr	Smls. pipe	SA-312	800H	N08810	...	...	45	...
(25) 45	42Fe-33Ni-21Cr	Wld. pipe	SA-312	800H	N08810	...	...	45	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	115	100	650	HT-1	G10, G11, W1
2	135	120	650	HT-1	W1
3	135	120	650	HT-1	G11, W1
4	90	70	650	CS-5	...
5	105	85	650	CS-5	W7
6	115	100	650	HT-1	...
7	65	35	650	CS-2	...
8	65	35	650	CS-2	...
9	65	35	650	CS-2	...
10	65	37	1000	CS-2	T3
11	70	37.5	650	CS-2	...
12	70	37.5	650	CS-2	...
13	70	40	1000	CS-2	T3
14	70	40	650	CS-2	...
15	75	50	650	CS-3	T1
16	80	55	650	CS-3	...
17	90	70	650	CS-5	...
18	105	85	650	CS-5	W7
19	115	100	650	HT-1	...
20	115	100	650	HT-1	G10, G11, W1
21	135	120	650	HT-1	G11, W1
22	95	65	250	CS-3	W4
23	100	85	150	CS-3	W3
24	100	85	150	CS-3	W4
25	100	85	250	CS-3	W3
26	100	85	250	CS-3	W4
27	100	75	250	CS-3	W3
28	100	75	250	CS-3	W4
29	100	75	250	CS-3	W3
30	100	75	250	CS-3	W4
31	100	75	250	CS-3	W3
32	100	75	250	CS-3	W4
33	100	75	250	CS-3	W3
34	100	75	250	CS-3	W4
35	100	75	250	CS-3	G9, S2, W3
36	100	75	250	CS-3	G9, S2, W4
37	100	85	250	CS-3	W3
38	100	85	250	CS-3	W4
39	65	25	1650	NFN-9	G2, G17, G18, G19, T10
40	65	25	1650	NFN-9	G2, G18, G19, T10
41	65	25	1650	NFN-9	G2, G18, G19, T10
42	65	25	1650	NFN-9	G2, G6, G18, G19, T10
43	65	25	1650	NFN-9	G2, G17, G18, G19, T10
44	65	25	1650	NFN-9	G2, G18, G19, T10
45	65	25	1650	NFN-9	G2, G6, G18, G19, T10

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
2	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
4	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	...	...	...	...	...
5	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
6	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
7	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	18.9	18.3	17.5	16.7	...	...	...	...	...
8	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	18.9	18.3	17.5	16.7	...	...	...	...	...
9	23.3	21.9	21.4	21.0	20.6	20.3	19.9	19.5	18.9	18.3	17.5	16.7	...	...	...	...	...
10	24.7	23.2	22.6	22.2	21.8	21.5	21.1	20.6	20.0	19.3	18.5	17.6	16.6	13.9	11.4	9.0	6.5
11	25.0	23.5	22.9	22.5	22.1	21.8	21.4	20.9	20.3	19.6	18.8	17.9	...	...	...	...	...
12	25.0	23.5	22.9	22.5	22.1	21.8	21.4	20.9	20.3	19.6	18.8	17.9	...	...	...	...	...
13	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.6	20.9	20.0	19.0	18.0	14.8	12.0	9.3	6.5
14	26.7	25.1	24.4	24.0	23.6	23.2	22.8	22.3	21.6	20.9	20.0	19.0	...	...	...	...	...
15	31.3	31.3	30.5	29.9	29.5	29.0	28.5	27.8	27.1	26.1	25.0	22.5	...	...	...	...	...
16	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	...	...	...	...	...
17	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	37.5	...	...	...	...	...
18	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	43.8	...	...	...	...	...
19	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
20	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	47.9	...	...	...	...	...
21	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	56.3	...	...	...	...	...
22	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
23	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
26	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
27	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
28	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
29	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
30	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
31	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
32	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
33	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
34	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
35	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
36	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
37	41.7	41.7	41.7	41.7	...	...	...	...	...	...	...	...	...	...	...	...	...
38	39.6	39.6	39.6	39.6	...	...	...	...	...	...	...	...	...	...	...	...	...
39	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
40	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
41	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
42	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
43	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
44	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
45	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	4.5	2.5	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	4.5	2.5	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...
39	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
40	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
41	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
42	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6 (25)
43	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
44	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
45	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6 (25)

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
(25) 1	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H	N08810	...	...	45	...
(25) 2	42Fe-33Ni-21Cr	Bar	SA-479	800H	N08810	...	...	45	...
(25) 3	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H	N08810	...	...	45	...
(25) 4	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10	N08810	...	...	45	...
5	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...	8	3
6	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...	...	8	3
7	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	$t > 5$	8	1
8	16Cr-12Ni-2Mo	Forgings	SA-965	F316L	S31603	...	...	8	1
9	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	$t \leq 5$	8	1
10	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...	...	8	1
11	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...	...	8	1
12	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...	8	1
13	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	...	...	8	1
14	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...	8	1
15	16Cr-12Ni-2Mo	Fittings	SA-403	316L	S31603	CR	...	8	1
16	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316L	S31603	WP-W	...	8	1
17	16Cr-12Ni-2Mo	Wld. fittings	SA-403	316L	S31603	WP-WX	...	8	1
18	16Cr-12Ni-2Mo	Wld. pipe	SA-688	TP316L	S31603	...	...	8	1
19	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	$t > 5$	8	1
20	16Cr-12Ni-2Mo	Forgings	SA-965	F316	S31600	...	...	8	1
21	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	$t > 5$	8	1
22	16Cr-12Ni-2Mo	Forgings	SA-965	F316H	S31609	...	...	8	1
23	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	$t \leq 5$	8	1
24	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...	...	8	1
25	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...	...	8	1
26	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...	8	1
27	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316	S31600	...	...	8	1
28	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...	8	1
29	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316	S31600	...	...	8	1
30	16Cr-12Ni-2Mo	Fittings	SA-403	316	S31600	WP-S	...	8	1
31	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...	...	8	1
32	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...	$t \leq 5$	8	1
33	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H	S31609	...	...	8	1
34	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...	...	8	1
35	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316H	S31609	...	...	8	1
36	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316H	S31609	...	...	8	1
37	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H	S31609	...	...	8	1
38	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2	...	...	≤ 3	8	1
39	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2	...	...	≤ 3	8	1
40	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N	S31651	...	$t \leq 5$	8	1
41	16Cr-12Ni-2Mo-N	Plate	SA-240	316N	S31651	...	$t \leq 5$	8	1
42	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...	...	8	1
43	16Cr-12Ni-2Mo-N	Smls. pipe	SA-312	TP316N	S31651	...	$t \leq 5$	8	1
44	16Cr-12Ni-2Mo-N	Wld. pipe	SA-312	TP316N	S31651	...	$t \leq 5$	8	1
45	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N	S31651	...	...	8	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	65	25	1650	NFN-9	G2, G6, G18, G19, T10
2	65	25	1650	NFN-9	G2, G17, G18, G19, T10
3	65	25	1650	NFN-9	G2, G6, G18, G19, T10
4	65	25	1650	NFN-9	G2, G17, G18, G19, T10
5	95	45	800	HA-6	...
6	95	45	800	HA-6	G2
7	65	25	850	HA-4	G2
8	65	25	850	HA-4	G2
9	70	25	850	HA-4	G2
10	70	25	850	HA-4	G2
11	70	25	850	HA-4	G2
12	70	25	850	HA-4	G2, G6
13	70	25	850	HA-4	G2
14	70	25	850	HA-4	G2, G6
15	70	25	850	HA-4	G2, G6
16	70	25	850	HA-4	G2, G6
17	70	25	850	HA-4	G2, G6
18	70	25	850	HA-4	G2, G6
19	70	30	1500	HA-2	G2, T10
20	70	30	1500	HA-2	G2, G3, G4, T10
21	70	30	1500	HA-2	G2, T10
22	70	30	1500	HA-2	G2, T10
23	75	30	1500	HA-2	G2, G3, T10
24	75	30	1500	HA-2	G2, G3, T10
25	75	30	1500	HA-2	G2, G3, G4, T10
26	75	30	1500	HA-2	G2, G3, G6, T10
27	75	30	1500	HA-2	G2, G3, G4, T10
28	75	30	1500	HA-2	G2, G3, G4, G6, T10
29	75	30	1500	HA-2	G2, G3, G4, T10
30	75	30	1500	HA-2	G2, T10
31	75	30	1500	HA-2	G2, G3, G6, T10
32	75	30	1500	HA-2	G2, T10
33	75	30	1500	HA-2	G2, T10
34	75	30	1500	HA-2	G2, G6, T10
35	75	30	1500	HA-2	G2, T10
36	75	30	1500	HA-2	G2, G6, T10
37	75	30	1500	HA-2	G2, G4, T10
38	75	32	850	HA-4	G2, G16
39	75	32	1022	HA-2	G2, G3, G4, G16
40	80	35	1200	HA-2	G2, T9
41	80	35	1200	HA-2	G2, T9
42	80	35	1200	HA-2	G2, G6, T9
43	80	35	1200	HA-2	G2, T9
44	80	35	1200	HA-2	G2, G6, T9
45	80	35	1200	HA-2	G2, G4, T9

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
2	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
3	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
4	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
5	30.0	...	24.2	...	21.9	...	20.7	...	20.0	...	19.1	18.6	18.0	17.3	16.7	...	...
6	30.0	...	30.0	...	29.6	...	28.0	...	27.0	...	25.8	25.1	24.3	23.4	22.6	...	...
7	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
8	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
9	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
10	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
11	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
12	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
13	16.7	16.7	16.7	16.7	16.7	16.4	15.7	15.2	14.8	14.4	14.0	13.7	13.5	13.2	12.9	12.7	...
14	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
15	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
16	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
17	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
18	14.2	14.2	14.2	14.2	14.2	13.9	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.2	11.0	10.8	...
19	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
20	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
21	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
22	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
23	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
24	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
25	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
26	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
27	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
28	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
29	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
30	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
31	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
32	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
33	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
34	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
35	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
36	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
37	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
38	21.3	21.3	21.3	21.3	21.3	20.9	20.1	19.5	18.8	18.3	17.9	17.6	17.2	16.9	16.6	16.2	...
39	21.3	21.3	21.3	21.3	21.3	21.3	20.5	19.8	19.1	18.6	18.1	17.7	17.4	17.2	16.9	16.7	16.6
40	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.0	22.3	21.6	21.0	20.5	20.0	19.6	19.2	18.8	18.5
41	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.0	22.3	21.6	21.0	20.5	20.0	19.6	19.2	18.8	18.5
42	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.5	18.9	18.4	17.9	17.4	17.0	16.7	16.3	16.0	15.7
43	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.0	22.3	21.6	21.0	20.5	20.0	19.6	19.2	18.8	18.5
44	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.5	18.9	18.4	17.9	17.4	17.0	16.7	16.3	16.0	15.7
45	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.0	22.3	21.6	21.0	20.5	20.0	19.6	19.2	18.8	18.5

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6 (25)
2	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
3	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6 (25)
4	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9 (25)
5	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
20	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
21	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
22	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
23	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
24	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
25	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
26	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.6	2.7	2.0	1.5	1.2
27	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
28	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.6	2.7	2.0	1.5	1.2
29	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
30	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
31	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.6	2.7	2.0	1.5	1.2
32	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
33	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
34	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1
35	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
36	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.4	1.1
37	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
38	...	...	...	...	...	...	...	...	...	...	...	...
39	16.4	16.3	16.1	...	...	...	...	...	...	...	...	...
40	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...
41	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...
42	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...
43	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...
44	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...
45	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	16Cr-12Ni-2Mo-N	Fittings	SA-403	316N	S31651	CR	...	8	1
2	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316N	S31651	WP-W	...	8	1
3	16Cr-12Ni-2Mo-N	Wld. fittings	SA-403	316N	S31651	WP-WX	...	8	1
4	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N	S31651	...	...	8	1
5	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-11-2	...	...	≤3	8	1
6	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-13-3	...	...	≤3	8	1
7	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...	S30601	...	...	8	1
8	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	$t > \frac{3}{16}$	8	3
9	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...	$t \leq \frac{3}{16}$	8	3
10	18Cr-5Ni-3Mo	Smls. tube	SA-789	...	S31500	...	...	10H	1
11	18Cr-5Ni-3Mo	Wld. tube	SA-789	...	S31500	...	...	10H	1
12	18Cr-5Ni-3Mo	Smls. pipe	SA-790	...	S31500	...	...	10H	1
13	18Cr-5Ni-3Mo	Wld. pipe	SA-790	...	S31500	...	...	10H	1
14	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	$t > 5$	8	1
15	18Cr-8Ni	Forgings	SA-965	F304L	S30403	...	...	8	1
16	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	$t \leq 5$	8	1
17	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...	...	8	1
18	18Cr-8Ni	Plate	SA-240	304L	S30403	...	...	8	1
19	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...	8	1
20	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	...	...	8	1
21	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...	8	1
22	18Cr-8Ni	Fittings	SA-403	304L	S30403	WP-S	...	8	1
23	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...	...	8	1
24	18Cr-8Ni	Castings	SA-351	CF3	J92500	...	...	8	1
25	18Cr-8Ni	Castings	SA-351	CF10	J92590	...	...	8	1
26	18Cr-8Ni	Castings	SA-351	CF8	J92600	...	...	8	1
27	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	$t > 5$	8	1
28	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	≥8	8	1
29	18Cr-8Ni	Forgings	SA-965	F304	S30400	...	...	8	1
30	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	$t > 5$	8	1
31	18Cr-8Ni	Forgings	SA-965	F304H	S30409	...	...	8	1
32	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9	...	...	≤3	8	1
33	18Cr-8Ni	Plate	SA-240	302	S30200	...	...	8	1
34	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	$t \leq 5$	8	1
35	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...	...	8	1
36	18Cr-8Ni	Plate	SA-240	304	S30400	...	...	8	1
37	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...	8	1
38	18Cr-8Ni	Smls. pipe	SA-312	TP304	S30400	...	...	8	1
39	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...	8	1
40	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...	<8	8	1
41	18Cr-8Ni	Fittings	SA-403	304	S30400	CR	...	8	1
42	18Cr-8Ni	Fittings	SA-403	304	S30400	WP-S	...	8	1
43	18Cr-8Ni	Wld. fittings	SA-403	304	S30400	WP-W	...	8	1
44	18Cr-8Ni	Wld. fittings	SA-403	304	S30400	WP-WX	...	8	1
45	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...	...	8	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	80	35	1200	HA-2	G2, G6, T9
2	80	35	1200	HA-2	G2, G6, T9
3	80	35	1200	HA-2	G2, G6, T9
4	80	35	1200	HA-2	G2, T9
5	84	41	800	HA-2	G2, G16
6	84	41	800	HA-2	G2, G16
7	78	37	400	HA-1	...
8	100	55	800	HA-6	G2
9	100	60	800	HA-6	G2
10	92	64	650	HA-5	G8
11	92	64	650	HA-5	G6, G8
12	92	64	650	HA-5	G8
13	92	64	650	HA-5	G6, G8
14	65	25	1200	HA-3	G2, T9
15	65	25	1200	HA-3	G2, T9
16	70	25	1200	HA-3	G2, T9
17	70	25	1200	HA-3	G2, T9
18	70	25	1200	HA-3	G2, T9
19	70	25	1200	HA-3	G2, G6, T9
20	70	25	1200	HA-3	G2, T9
21	70	25	1200	HA-3	G2, G6, T9
22	70	25	1200	HA-3	G2, T9
23	70	25	1200	HA-3	G2, G6, T9
24	70	30	800	HA-3	G2, G8
25	70	30	1500	HA-3	G2, G4, G8, T8
26	70	30	1500	HA-1	G2, G3, G4, G8, T8
27	70	30	1500	HA-1	G2, G3, G4, T9
28	70	30	1500	HA-1	G2, G3, G4, S3, T9
29	70	30	1500	HA-1	G2, G3, G4, T9
30	70	30	1500	HA-1	G2, T9
31	70	30	1500	HA-1	G2, T9
32	72.5	29	1022	HA-3	G2, G16, T9
33	75	30	750	HA-1	G2, G3
34	75	30	1500	HA-1	G2, G3, G4, T9
35	75	30	1500	HA-1	G2, G3, T9
36	75	30	1500	HA-1	G2, G3, G4, T9
37	75	30	1500	HA-1	G2, G3, G6, T9
38	75	30	1500	HA-1	G2, G3, G4, T9
39	75	30	1500	HA-1	G2, G3, G4, G6, T9
40	75	30	1500	HA-1	G2, G3, G4, S4, T9
41	75	30	1500	HA-1	G2, G6, T9
42	75	30	1500	HA-1	G2, T9
43	75	30	1500	HA-1	G2, G6, T9
44	75	30	1500	HA-1	G2, G6, T9
45	75	30	1500	HA-1	G2, G3, G6, T9

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.5	18.9	18.4	17.9	17.4	17.0	16.7	16.3	16.0	15.7
2	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.5	18.9	18.4	17.9	17.4	17.0	16.7	16.3	16.0	15.7
3	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.5	18.9	18.4	17.9	17.4	17.0	16.7	16.3	16.0	15.7
4	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.0	22.3	21.6	21.0	20.5	20.0	19.6	19.2	18.8	18.5
5	27.1	27.1	27.1	27.1	27.1	26.7	25.6	24.6	23.7	23.0	22.3	21.7	21.1	20.6	20.1	...	...
6	27.1	27.1	27.1	27.1	27.1	26.7	25.6	24.6	23.7	23.0	22.3	21.7	21.1	20.6	20.1	...	...
7	24.7	24.7	24.7	24.7	24.4	23.2	22.2	...	...	...	...	...	...	...	...	...	...
8	36.7	36.7	36.7	36.6	33.8	31.5	29.6	28.2	27.2	26.4	25.9	25.4	25.0	24.5	24.0	...	...
9	40.0	40.0	40.0	39.9	36.8	34.3	32.3	30.8	29.6	28.8	28.2	27.7	27.3	26.8	26.2	...	...
10	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	...	...	...	...	...
11	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	...	...	...	...	...
12	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	38.3	...	...	...	...	...
13	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	32.6	...	...	...	...	...
14	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
15	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
16	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
17	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
18	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
19	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
20	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
21	14.2	14.2	14.2	14.2	14.2	14.0	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.3	11.1	10.9	10.7
22	16.7	16.7	16.7	16.7	16.7	16.5	15.8	15.2	14.7	14.3	14.0	13.7	13.5	13.3	13.0	12.8	12.6
23	14.2	14.2	14.2	14.2	14.2	14.0	13.4	12.9	12.5	12.2	11.9	11.7	11.4	11.3	11.1	10.9	10.7
24	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	...	...
25	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
26	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
27	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
28	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
29	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
30	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
31	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
32	19.3	19.3	19.3	19.3	19.3	19.1	18.3	17.7	17.1	16.6	16.2	15.9	15.6	15.4	15.2	14.9	14.6
33	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	...	...	...
34	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
35	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
36	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
37	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
38	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
39	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
40	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
41	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
42	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
43	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
44	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
45	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...
2	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...
3	15.4	15.1	13.4	10.5	8.3	6.3	...	...	...	...	...	...
4	18.1	17.8	15.8	12.3	9.8	7.4	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...
14	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
15	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
16	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
17	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
18	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
19	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
20	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
21	10.5	10.2	5.4	4.3	3.4	2.7	...	...	...	...	...	...
22	12.3	12.0	6.3	5.1	4.0	3.2	...	...	...	...	...	...
23	10.5	10.2	5.4	4.3	3.4	2.7	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	14.3	12.2	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7
26	14.3	12.2	9.5	7.5	6.0	4.8	3.9	3.3	2.7	2.3	2.0	1.7
27	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
28	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
29	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
30	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
31	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
32	14.3	13.9	6.3	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
35	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
36	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
37	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
38	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
39	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
40	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
41	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
42	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
43	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
44	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
45	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...	$t \leq 5$	8	1
2	18Cr-8Ni	Smls. tube	SA-213	TP304H	S30409	...	...	8	1
3	18Cr-8Ni	Plate	SA-240	304H	S30409	...	...	8	1
4	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...	...	8	1
5	18Cr-8Ni	Smls. pipe	SA-312	TP304H	S30409	...	...	8	1
6	18Cr-8Ni	Wld. pipe	SA-312	TP304H	S30409	...	...	8	1
7	18Cr-8Ni	Smls. pipe	SA-376	TP304H	S30409	...	...	8	1
8	18Cr-8Ni	Fittings	SA-403	304H	S30409	CR	...	8	1
9	18Cr-8Ni	Fittings	SA-403	304H	S30409	WP-S	...	8	1
10	18Cr-8Ni	Wld. fittings	SA-403	304H	S30409	WP-W	...	8	1
11	18Cr-8Ni	Wld. fittings	SA-403	304H	S30409	WP-WX	...	8	1
12	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10	...	...	≤ 3	8	1
13	18Cr-8Ni-N	Smls. tube	SA-213	TP304N	S30451	...	...	8	1
14	18Cr-8Ni-N	Plate	SA-240	304N	S30451	...	...	8	1
15	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...	...	8	1
16	18Cr-8Ni-N	Smls. pipe	SA-312	TP304N	S30451	...	...	8	1
17	18Cr-8Ni-N	Wld. pipe	SA-312	TP304N	S30451	...	...	8	1
18	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N	S30451	...	...	8	1
19	18Cr-8Ni-N	Fittings	SA-403	304N	S30451	CR	...	8	1
20	18Cr-8Ni-N	Wld. fittings	SA-403	304N	S30451	WP-W	...	8	1
21	18Cr-8Ni-N	Wld. fittings	SA-403	304N	S30451	WP-WX	...	8	1
22	18Cr-8Ni-N	Forgings	SA-965	F304N	S30451	...	...	...	...
23	18Cr-8Ni-N	Plate	SA/EN 10028-7	X2CrNiN18-10	...	...	≤ 3	8	1
24	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9	...	...	≤ 3	8	1
25	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	...	8	1
26	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	$t > 5$	8	1
27	18Cr-10Ni-Cb	Forgings	SA-965	F347	S34700	...	...	8	1
28	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	$t > 5$	8	1
29	18Cr-10Ni-Cb	Forgings	SA-965	F347H	S34709	...	...	8	1
30	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	$t > 5$	8	1
31	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	$t > 5$	8	1
32	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...	$t \leq 5$	8	1
33	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347	S34700	...	...	8	1
34	18Cr-10Ni-Cb	Plate	SA-240	347	S34700	...	...	8	1
35	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...	...	8	1
36	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347	S34700	...	...	8	1
37	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347	S34700	...	...	8	1
38	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347	S34700	...	...	8	1
39	18Cr-10Ni-Cb	Fittings	SA-403	347	S34700	CR	...	8	1
40	18Cr-10Ni-Cb	Fittings	SA-403	347	S34700	WP-S	...	8	1
41	18Cr-10Ni-Cb	Wld. fittings	SA-403	347	S34700	WP-W	...	8	1
42	18Cr-10Ni-Cb	Wld. fittings	SA-403	347	S34700	WP-WX	...	8	1
43	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...	$t \leq 5$	8	1
44	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H	S34709	...	...	8	1
45	18Cr-10Ni-Cb	Plate	SA-240	347H	S34709	...	...	8	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	75	30	1500	HA-1	G2, T9
2	75	30	1500	HA-1	G2, T9
3	75	30	1500	HA-1	G2, T9
4	75	30	1500	HA-1	G2, G6, T9
5	75	30	1500	HA-1	G2, T9
6	75	30	1500	HA-1	G2, G6, T9
7	75	30	1500	HA-1	G2, G4, T9
8	75	30	1500	HA-1	G2, G6, T9
9	75	30	1500	HA-1	G2, T9
10	75	30	1500	HA-1	G2, G6, T9
11	75	30	1500	HA-1	G2, G6, T9
12	75	31	1022	HA-1	G2, G3, G4, G16, T9
13	80	35	1200	HA-1	G2, T9
14	80	35	1200	HA-1	G2, T9
15	80	35	1200	HA-1	G2, G6, T9
16	80	35	1200	HA-1	G2, T9
17	80	35	1200	HA-1	G2, G6, T9
18	80	35	1200	HA-1	G2, G4, T9
19	80	35	1200	HA-1	G2, G6, T9
20	80	35	1200	HA-1	G2, G6, T9
21	80	35	1200	HA-1	G2, G6, T9
22	80	35	1200	HA-1	G2, T9
23	80	39	800	HA-1	G2, G16
24	80	39	1022	HA-1	G2, G16, T9
25	70	30	1500	HA-2	G2, G3, G8, T8
26	70	30	1500	HA-2	G2, G3, T8
27	70	30	1500	HA-2	G2, G3, G4, T8
28	70	30	1500	HA-2	G1, G2, T9
29	70	30	1500	HA-2	G1, G2, G3, T9
30	70	30	1500	HA-2	G2, G3, T8
31	70	30	1500	HA-2	G2, T9
32	75	30	1500	HA-2	G2, G3, G4, T8
33	75	30	1500	HA-2	G2, G3, G4, T8
34	75	30	1500	HA-2	G2, G3, T8
35	75	30	1500	HA-2	G2, G3, G6, T8
36	75	30	1500	HA-2	G2, G3, T8
37	75	30	1500	HA-2	G2, G3, G6, T8
38	75	30	1500	HA-2	G2, G3, G4, T8
39	75	30	1500	HA-2	G2, G6, T8
40	75	30	1500	HA-2	G2, T8
41	75	30	1500	HA-2	G2, G6, T8
42	75	30	1500	HA-2	G2, G6, T8
43	75	30	1500	HA-2	G1, G2, T9
44	75	30	1500	HA-2	G1, G2, T9
45	75	30	1500	HA-2	G1, G2, T9

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
2	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
3	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
4	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
5	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
6	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
7	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
8	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
9	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
10	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
11	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
12	20.3	20.3	20.3	20.3	20.3	19.6	18.9	18.3	17.7	17.2	16.8	16.4	16.1	15.7	15.4	15.1	14.8
13	23.3	23.3	23.3	23.3	22.5	21.3	20.3	19.5	18.9	18.3	17.9	17.5	17.2	16.9	16.6	16.3	16.0
14	23.3	23.3	23.3	23.3	22.5	21.3	20.3	19.5	18.9	18.3	17.9	17.5	17.2	16.9	16.6	16.3	16.0
15	19.8	19.8	19.8	19.8	19.2	18.1	17.3	16.6	16.0	15.6	15.2	14.9	14.6	14.4	14.1	13.8	13.6
16	23.3	23.3	23.3	23.3	22.5	21.3	20.3	19.5	18.9	18.3	17.9	17.5	17.2	16.9	16.6	16.3	16.0
17	19.8	19.8	19.8	19.8	19.2	18.1	17.3	16.6	16.0	15.6	15.2	14.9	14.6	14.4	14.1	13.8	13.6
18	23.3	23.3	23.3	23.3	22.5	21.3	20.3	19.5	18.9	18.3	17.9	17.5	17.2	16.9	16.6	16.3	16.0
19	19.8	19.8	19.8	19.8	19.2	18.1	17.3	16.6	16.0	15.6	15.2	14.9	14.6	14.4	14.1	13.8	13.6
20	19.8	19.8	19.8	19.8	19.2	18.1	17.3	16.6	16.0	15.6	15.2	14.9	14.6	14.4	14.1	13.8	13.6
21	19.8	19.8	19.8	19.8	19.2	18.1	17.3	16.6	16.0	15.6	15.2	14.9	14.6	14.4	14.1	13.8	13.6
22	23.3	23.3	23.3	23.3	22.5	21.3	20.3	19.5	18.9	18.3	17.9	17.5	17.2	16.9	16.6	16.3	16.0
23	26.1	26.1	26.1	26.1	26.0	25.2	24.3	23.5	22.8	22.2	21.6	21.1	20.7	20.2	19.8	...	...
24	26.1	26.1	26.1	26.1	25.2	23.9	22.7	21.9	21.1	20.5	20.0	19.6	19.3	18.9	18.6	18.2	17.8
25	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
26	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
28	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
29	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
30	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
31	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
32	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
33	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
34	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
35	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
36	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
37	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
38	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
39	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
40	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
41	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
42	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
43	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
44	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
45	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
2	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
3	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
4	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
5	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
6	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
7	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
8	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
9	14.3	14.0	12.4	9.8	7.7	6.1	4.7	3.7	2.9	2.3	1.8	1.4
10	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
11	12.1	11.9	10.5	8.3	6.6	5.2	4.0	3.1	2.5	2.0	1.6	1.2
12	14.5	14.2	12.4	...	...	...	...	...	...	...	...	...
13	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...
14	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...
15	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...
16	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...
17	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...
18	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...
19	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...
20	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...
21	13.3	13.0	10.5	8.3	6.6	5.2	...	...	...	...	...	...
22	15.6	15.2	12.4	9.8	7.7	6.1	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	17.4	17.0	12.4	...	...	...	...	...	...	...	...	...
25	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
26	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
27	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
28	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
29	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
30	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
31	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
32	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
33	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
34	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
35	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
36	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
37	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
38	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
39	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
40	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
41	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
42	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
43	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
44	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
45	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...	...	8	1
2	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347H	S34709	...	...	8	1
3	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP347H	S34709	...	...	8	1
4	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H	S34709	...	...	8	1
5	18Cr-10Ni-Cb	Fittings	SA-403	347H	S34709	CR	...	8	1
6	18Cr-10Ni-Cb	Fittings	SA-403	347H	S34709	WP-S	...	8	1
7	18Cr-10Ni-Cb	Wld. fittings	SA-403	347H	S34709	WP-W	...	8	1
8	18Cr-10Ni-Cb	Wld. fittings	SA-403	347H	S34709	WP-WX	...	8	1
9	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...	$t \leq 5$	8	1
10	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348	S34800	...	...	8	1
11	18Cr-10Ni-Cb	Plate	SA-240	348	S34800	...	...	8	1
12	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...	...	8	1
13	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348	S34800	...	...	8	1
14	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348	S34800	...	...	8	1
15	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348	S34800	...	...	8	1
16	18Cr-10Ni-Cb	Fittings	SA-403	348	S34800	CR	...	8	1
17	18Cr-10Ni-Cb	Fittings	SA-403	348	S34800	WP-S	...	8	1
18	18Cr-10Ni-Cb	Wld. fittings	SA-403	348	S34800	WP-W	...	8	1
19	18Cr-10Ni-Cb	Wld. fittings	SA-403	348	S34800	WP-WX	...	8	1
20	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...	$t \leq 5$	8	1
21	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H	S34809	...	...	8	1
22	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...	...	8	1
23	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP348H	S34809	...	...	8	1
24	18Cr-10Ni-Cb	Wld. pipe	SA-312	TP348H	S34809	...	...	8	1
25	18Cr-10Ni-Cb	Fittings	SA-403	348H	S34809	CR	...	8	1
26	18Cr-10Ni-Cb	Fittings	SA-403	348H	S34809	WP-S	...	8	1
27	18Cr-10Ni-Cb	Wld. fittings	SA-403	348H	S34809	WP-W	...	8	1
28	18Cr-10Ni-Cb	Wld. fittings	SA-403	348H	S34809	WP-WX	...	8	1
29	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	$t > \frac{3}{8}$	8	1
30	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	$t > \frac{3}{8}$	8	1
31	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$t > \frac{3}{8}$	8	1
32	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$t > \frac{3}{8}$	8	1
33	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	$t > 5$	8	1
34	18Cr-10Ni-Ti	Forgings	SA-965	F321	S32100	...	...	8	1
35	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	$t > 5$	8	1
36	18Cr-10Ni-Ti	Forgings	SA-965	F321H	S32109	...	...	8	1
37	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi18-10	...	...	≤ 3	8	1
38	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...	$t \leq 5$	8	1
39	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...	...	8	1
40	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...	...	8	1
41	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...	...	8	1
42	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321	S32100	...	$t \leq \frac{3}{8}$	8	1
43	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321	S32100	...	...	8	1
44	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...	$t \leq \frac{3}{8}$	8	1
45	18Cr-10Ni-Ti	Fittings	SA-403	321	S32100	CR	...	8	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	75	30	1500	HA-2	G2, G6, T9
2	75	30	1500	HA-2	G1, G2, T9
3	75	30	1500	HA-2	G1, G2, G6, T9
4	75	30	1500	HA-2	G1, G2, T9
5	75	30	1500	HA-2	G1, G2, G6, T9
6	75	30	1500	HA-2	G1, G2, T9
7	75	30	1500	HA-2	G1, G2, G6, T9
8	75	30	1500	HA-2	G1, G2, G6, T9
9	75	30	1500	HA-2	G2, G3, T8
10	75	30	1500	HA-2	G2, G3, T8
11	75	30	1500	HA-2	G2, G3, T8
12	75	30	1500	HA-2	G2, G3, G6, T8
13	75	30	1500	HA-2	G2, G3, T8
14	75	30	1500	HA-2	G2, G3, G6, T8
15	75	30	1500	HA-2	G2, G3, G4, T8
16	75	30	1500	HA-2	G1, G2, G6, T8
17	75	30	1500	HA-2	G1, G2, T8
18	75	30	1500	HA-2	G1, G2, G6, T8
19	75	30	1500	HA-2	G1, G2, G6, T8
20	75	30	1500	HA-2	G2, T9
21	75	30	1500	HA-2	G1, G2, T9
22	75	30	1500	HA-2	G2, G6, T9
23	75	30	1500	HA-2	G1, G2, T9
24	75	30	1500	HA-2	G1, G2, G6, T9
25	75	30	1500	HA-2	G1, G2, G6, T9
26	75	30	1500	HA-2	G1, G2, T9
27	75	30	1500	HA-2	G1, G2, G6, T9
28	75	30	1500	HA-2	G1, G2, G6, T9
29	70	25	1500	HA-2	G2, G3, T9
30	70	25	1500	HA-2	G2, G3, G4, T9
31	70	25	1500	HA-2	G2, T9
32	70	25	1500	HA-2	G1, G2, T9
33	70	30	1500	HA-2	G2, G3, T8
34	70	30	1500	HA-2	G2, G3, T8
35	70	30	1500	HA-2	G1, G2, T9
36	70	30	1500	HA-2	G1, G2, G3, T9
37	73	29	1022	HA-2	G2, G3, G16, T9
38	75	30	1500	HA-2	G2, G3, T8
39	75	30	1500	HA-2	G2, G3, T8
40	75	30	1500	HA-2	G2, G3, T8
41	75	30	1500	HA-2	G2, G3, G6, T8
42	75	30	1500	HA-2	G2, G3, T8
43	75	30	1500	HA-2	G2, G3, G6, T8
44	75	30	1500	HA-2	G2, G3, G4, T8
45	75	30	1500	HA-2	G2, G6, T8

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
2	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
3	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
4	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
5	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
6	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
7	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
8	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
9	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
10	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
11	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
12	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
13	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
14	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
15	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
16	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
17	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
18	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
19	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
20	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
21	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
22	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
23	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
24	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
25	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
26	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	19.0	18.7	18.5	18.3	18.2	18.1
27	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
28	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.1	15.9	15.7	15.6	15.5	15.4
29	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.6	16.1	15.6	15.2	14.9	14.6	14.3	14.1	13.9	13.8
30	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.6	16.1	15.6	15.2	14.9	14.6	14.3	14.1	13.9	13.8
31	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.6	16.1	15.6	15.2	14.9	14.6	14.3	14.1	13.9	13.8
32	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.6	16.1	15.6	15.2	14.9	14.6	14.3	14.1	13.9	13.8
33	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
34	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
35	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
36	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
37	19.3	19.3	19.3	19.3	19.3	19.3	19.3	19.3	18.7	18.1	17.7	17.2	16.9	16.6	16.4	16.2	16.0
38	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
39	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
40	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
41	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
42	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
43	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
44	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
45	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
2	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
3	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
4	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
5	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
6	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
7	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
8	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
9	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
10	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
11	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
12	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
13	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
14	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
15	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
16	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
17	18.1	16.0	12.1	9.1	6.1	4.4	3.3	2.2	1.5	1.2	0.90	0.80
18	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
19	15.4	13.6	10.3	7.8	5.2	3.8	2.8	1.9	1.3	1.0	0.76	0.68
20	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
21	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
22	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
23	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
24	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
25	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
26	18.1	18.1	17.4	14.1	10.5	7.9	5.9	4.4	3.2	2.5	1.8	1.3
27	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
28	15.4	15.4	14.8	12.0	8.9	6.7	5.0	3.7	2.7	2.1	1.6	1.1
29	13.6	13.5	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
30	13.6	13.5	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
31	13.6	13.5	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
32	13.6	13.5	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
33	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
34	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
35	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
36	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
37	15.8	15.7	9.6	...	...	...	...	...	...	...	...	...
38	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
39	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
40	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
41	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.94	0.68	0.43	0.26
42	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
43	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.94	0.68	0.43	0.26
44	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
45	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.94	0.68	0.43	0.26

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	18Cr-10Ni-Ti	Fittings	SA-403	321	S32100	WP-S	...	8	1
2	18Cr-10Ni-Ti	Wld. fittings	SA-403	321	S32100	WP-W	...	8	1
3	18Cr-10Ni-Ti	Wld. fittings	SA-403	321	S32100	WP-WX	...	8	1
4	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...	$t \leq 5$	8	1
5	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H	S32109	...	...	8	1
6	18Cr-10Ni-Ti	Plate	SA-240	321H	S32109	...	...	8	1
7	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...	...	8	1
8	18Cr-10Ni-Ti	Smls. pipe	SA-312	TP321H	S32109	...	$t \leq \frac{3}{8}$	8	1
9	18Cr-10Ni-Ti	Wld. pipe	SA-312	TP321H	S32109	...	$t \leq \frac{3}{8}$	8	1
10	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...	$t \leq \frac{3}{8}$	8	1
11	18Cr-10Ni-Ti	Fittings	SA-403	321H	S32109	CR	...	8	1
12	18Cr-10Ni-Ti	Fittings	SA-403	321H	S32109	WP-S	...	8	1
13	18Cr-10Ni-Ti	Wld. fittings	SA-403	321H	S32109	WP-W	...	8	1
14	18Cr-10Ni-Ti	Wld. fittings	SA-403	321H	S32109	WP-WX	...	8	1
15	18Cr-12Ni-2Mo	Castings	SA-351	CF8M	J92900	...	...	8	1
16	18Cr-13Ni-3Mo	Plate	SA-240	317	S31700	...	$t \leq 5$	8	1
17	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...	...	8	1
18	18Cr-13Ni-3Mo	Smls. pipe	SA-312	TP317	S31700	...	$t \leq 5$	8	1
19	18Cr-13Ni-3Mo	Wld. pipe	SA-312	TP317	S31700	...	$t \leq 5$	8	1
20	18Cr-13Ni-3Mo	Fittings	SA-403	317	S31700	WP-S	...	8	1
21	18Cr-13Ni-3Mo	Plate	SA-240	317L	S31703	...	...	8	1
22	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	WP-S	...	8	1
23	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15	S38100	...	$t \leq 5$	8	1
24	18Cr-18Ni-2Si	Plate	SA-240	XM-15	S38100	...	$t \leq 5$	8	1
25	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15	S38100	...	$t \leq 5$	8	1
26	18Cr-18Ni-2Si	Smls. pipe	SA-312	TPXM-15	S38100	...	$t \leq 5$	8	1
27	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15	S38100	...	$t \leq 5$	8	1
28	21Cr-6Ni-9Mn	Forgings	SA-182	FXM-11	S21904	...	...	8	3
29	21Cr-6Ni-9Mn	Smls. pipe	SA-312	TPXM-11	S21904	...	...	8	3
30	21Cr-6Ni-9Mn	Wld. pipe	SA-312	TPXM-11	S21904	...	...	8	3
31	21Cr-6Ni-9Mn	Plate	SA-666	XM-11	S21904	...	...	8	3
32	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11	S21904	...	...	8	3
(25) 33	22Cr-5Ni-3Mo-N	Forgings	SA-182	F51	S31803	...	...	10H	1
(25) 34	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...	...	10H	1
(25) 35	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S31803	...	...	10H	1
(25) 36	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S31803	...	...	10H	1
(25) 37	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S31803	...	...	10H	1
(25) 38	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S31803	...	...	10H	1
39	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S32205	...	...	10H	1
40	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S32205	...	...	10H	1
41	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S32205	...	...	10H	1
42	22Cr-5Ni-3Mo-N	Forgings	SA-182	F60	S32205	...	...	10H	1
43	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S32205	...	O.D. ≤ 8	10H	1
44	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S32205	...	O.D. ≤ 8	10H	1
45	22Cr-13Ni-5Mn	Forgings	SA-182	FXM-19	S20910	...	...	8	3

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	75	30	1500	HA-2	G2, T8
2	75	30	1500	HA-2	G2, G6, T8
3	75	30	1500	HA-2	G2, G6, T8
4	75	30	1500	HA-2	G1, G2, T9
5	75	30	1500	HA-2	G1, G2, T9
6	75	30	1500	HA-2	G1, G2, T9
7	75	30	1500	HA-2	G2, G6, T9
8	75	30	1500	HA-2	G2, T9
9	75	30	1500	HA-2	G2, G6, T9
10	75	30	1500	HA-2	G1, G2, T9
11	75	30	1500	HA-2	G1, G2, G6, T9
12	75	30	1500	HA-2	G1, G2, T9
13	75	30	1500	HA-2	G1, G2, G6, T9
14	75	30	1500	HA-2	G1, G2, G6, T9
15	70	30	1500	HA-2	G2, G3, G4, G8, T10
16	75	30	1500	HA-2	G2, G3, T10
17	75	30	1500	HA-2	G2, G3, G6, T10
18	75	30	1500	HA-2	G2, G3, T10
19	75	30	1500	HA-2	G2, G3, G6, T10
20	75	30	1500	HA-2	G2, T10
21	75	30	850	HA-4	G2
22	75	30	850	HA-4	G2
23	75	30	1000	HA-2	G2, G3
24	75	30	1000	HA-2	G2, G3
25	75	30	1000	HA-2	G2, G3, G6
26	75	30	1000	HA-2	G2, G3
27	75	30	1000	HA-2	G2, G3, G6
28	90	50	600	HA-6	G2
29	90	50	600	HA-6	G2
30	90	50	600	HA-6	G2, G6
31	90	50	600	HA-6	G2
32	90	50	600	HA-6	G2
33	90	65	600	HA-5	G8
34	90	65	600	HA-5	G8
35	90	65	600	HA-5	G8
36	90	65	600	HA-5	G6, G8
37	90	65	600	HA-5	G8
38	90	65	600	HA-5	G6, G8
39	95	65	400	HA-5	G8
40	95	65	400	HA-5	G8
41	95	65	400	HA-5	G6, G8
42	95	70	400	HA-5	G8
43	95	70	400	HA-5	G8
44	95	70	400	HA-5	G6, G8
45	100	55	1200	HA-6	G2, T10

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
2	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
3	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
4	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
5	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
6	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
7	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
8	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
9	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
10	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
11	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
12	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.8	18.3	17.9	17.5	17.2	16.9	16.7	16.5
13	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
14	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.4	16.0	15.5	15.2	14.9	14.6	14.4	14.2	14.1
15	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
16	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
17	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
18	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
19	17.0	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.5	14.1	13.9	13.7	13.5	13.4	13.2
20	20.0	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.4	17.0	16.6	16.3	16.1	15.9	15.7	15.6
21	20.0	20.0	20.0	20.0	20.0	19.6	18.9	18.2	17.7	17.3	16.9	16.5	16.2	15.8	15.5	15.2	...
22	20.0	20.0	20.0	20.0	20.0	19.6	18.9	18.2	17.7	17.3	16.9	16.5	16.2	15.8	15.5	15.2	...
23	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
24	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
25	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
26	20.0	20.0	20.0	20.0	20.0	19.3	18.6	18.0	17.5	17.0	16.6	16.2	15.8	15.5	15.2	14.9	14.6
27	17.0	17.0	17.0	17.0	17.0	16.4	15.8	15.3	14.8	14.4	14.1	13.8	13.5	13.2	12.9	12.6	12.4
28	33.3	33.3	33.3	32.0	29.7	27.9	26.4	25.3	24.4	23.7	23.1	...	...	...	...	...	...
29	33.3	33.3	33.3	32.0	29.7	27.9	26.4	25.3	24.4	23.7	23.1	...	...	...	...	...	...
30	28.3	28.3	28.3	27.2	25.3	23.7	22.5	21.5	20.7	20.1	19.7	...	...	...	...	...	...
31	33.3	33.3	33.3	32.0	29.7	27.9	26.4	25.3	24.4	23.7	23.1	...	...	...	...	...	...
32	33.3	33.3	33.3	32.0	29.7	27.9	26.4	25.3	24.4	23.7	23.1	...	...	...	...	...	...
33	37.5	37.5	37.5	37.0	35.8	34.9	34.2	33.7	33.2	32.5	31.8	...	...	...	...	...	...
34	37.5	37.5	37.5	37.0	35.8	34.9	34.2	33.7	33.2	32.5	31.8	...	...	...	...	...	...
35	37.5	37.5	37.5	37.0	35.8	34.9	34.2	33.7	33.2	32.5	31.8	...	...	...	...	...	...
36	31.9	31.9	31.9	31.5	30.5	29.7	29.0	28.6	28.2	27.6	27.0	...	...	...	...	...	...
37	37.5	37.5	37.5	37.0	35.8	34.9	34.2	33.7	33.2	32.5	31.8	...	...	...	...	...	...
38	31.9	31.9	31.9	31.5	30.5	29.7	29.0	28.6	28.2	27.6	27.0	...	...	...	...	...	...
39	39.6	...	38.5	...	35.8	...	34.2	...	...	...	...	...	...	...	...	...	...
40	39.6	...	38.5	...	35.8	...	34.2	...	...	...	...	...	...	...	...	...	...
41	33.6	...	32.7	...	30.5	...	29.0	...	...	...	...	...	...	...	...	...	...
42	39.6	...	39.6	...	38.6	...	36.8	...	...	...	...	...	...	...	...	...	...
43	39.6	...	39.6	...	38.6	...	36.8	...	...	...	...	...	...	...	...	...	...
44	33.6	...	33.6	...	32.8	...	31.3	...	...	...	...	...	...	...	...	...	...
45	36.7	36.7	36.7	36.7	36.7	36.7	36.7	35.8	35.0	34.3	33.7	33.1	32.6	32.2	31.8	31.4	31.1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	16.4	16.2	9.6	6.9	5.0	3.6	2.6	1.7	1.1	0.80	0.50	0.30
2	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.94	0.68	0.43	0.26
3	13.9	13.8	8.2	5.9	4.3	3.1	2.2	1.4	0.94	0.68	0.43	0.26
4	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
5	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
6	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
7	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94
8	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
9	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94
10	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
11	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94
12	16.4	16.2	12.3	9.1	6.9	5.4	4.1	3.2	2.5	1.9	1.5	1.1
13	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94
14	13.9	13.8	10.5	7.7	5.9	4.6	3.5	2.7	2.1	1.6	1.3	0.94
15	15.4	15.3	15.1	12.4	9.8	7.4	5.6	4.2	3.2	2.4	1.8	1.4
16	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
17	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1
18	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
19	13.1	13.0	12.9	10.5	8.3	6.3	4.7	3.5	2.6	1.9	1.5	1.1
20	15.4	15.3	15.1	12.4	9.8	7.4	5.5	4.1	3.1	2.3	1.7	1.3
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	14.3	14.0	...	...	...	...	...	...	...	...	...	...
24	14.3	14.0	...	...	...	...	...	...	...	...	...	...
25	12.1	11.9	...	...	...	...	...	...	...	...	...	...
26	14.3	14.0	...	...	...	...	...	...	...	...	...	...
27	12.1	11.9	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	30.7	30.3	29.7	20.4	13.0	8.3	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	22Cr-13Ni-5Mn	Plate	SA-240	XM-19	S20910	...	...	8	3
2	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...	...	8	3
3	22Cr-13Ni-5Mn	Smls. pipe	SA-312	TPXM-19	S20910	...	...	8	3
4	22Cr-13Ni-5Mn	Wld. pipe	SA-312	TPXM-19	S20910	...	...	8	3
5	22Cr-13Ni-5Mn	Fittings	SA-403	XM-19	S20910	CR	...	8	3
6	22Cr-13Ni-5Mn	Wld. fittings	SA-403	XM-19	S20910	WP-W	...	8	3
7	22Cr-13Ni-5Mn	Wld. fittings	SA-403	XM-19	S20910	WP-WX	...	8	3
8	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	...	...	8	3
9	22Cr-13Ni-5Mn	Forgings	SA-965	FXM-19	S20910	...	...	8	3
10	23Cr-4Ni-Mo-Cu-N	Plate	SA-240	...	S32304	...	...	10H	1
11	23Cr-12Ni	Fittings	SA-403	309	S30900	...	...	8	2
12	23Cr-12Ni	Fittings	SA-403	309	S30900	WP-S	...	8	2
13	23Cr-12Ni	Wld. fittings	SA-403	309	S30900	WP-W	...	8	2
14	23Cr-12Ni	Wld. fittings	SA-403	309	S30900	WP-WX	...	8	2
15	23Cr-12Ni	Smls. tube	SA-213	TP309S	S30908	...	...	8	2
16	23Cr-12Ni	Plate	SA-240	309S	S30908	...	...	8	2
17	23Cr-12Ni	Wld. tube	SA-249	TP309S	S30908	...	...	8	2
18	23Cr-12Ni	Smls. pipe	SA-312	TP309S	S30908	...	...	8	2
19	23Cr-12Ni	Wld. pipe	SA-312	TP309S	S30908	...	...	8	2
20	23Cr-12Ni	Wld. pipe	SA-813	TP309S	S30908	...	...	8	2
21	23Cr-12Ni	Wld. pipe	SA-814	TP309S	S30908	...	...	8	2
22	23Cr-12Ni	Smls. tube	SA-213	TP309H	S30909	...	...	8	2
23	23Cr-12Ni	Plate	SA-240	309H	S30909	...	...	8	2
24	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...	...	8	2
25	23Cr-12Ni	Smls. pipe	SA-312	TP309H	S30909	...	...	8	2
26	23Cr-12Ni	Wld. pipe	SA-312	TP309H	S30909	...	...	8	2
27	23Cr-12Ni	Bar	SA-479	309H	S30909	...	...	8	2
28	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb	S30940	...	...	8	2
29	23Cr-12Ni-Cb	Plate	SA-240	309Cb	S30940	...	...	8	2
30	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb	S30940	...	...	8	2
31	23Cr-12Ni-Cb	Smls. pipe	SA-312	TP309Cb	S30940	...	...	8	2
32	23Cr-12Ni-Cb	Wld. pipe	SA-312	TP309Cb	S30940	...	...	8	2
33	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb	S30940	...	...	8	2
34	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb	S30940	...	...	8	2
35	24Cr-22Ni-6Mo-2W-Cu-N	Forgings	SA-182	F58	S31266	...	...	45	...
36	24Cr-22Ni-6Mo-2W-Cu-N	Smls. tube	SA-213	...	S31266	...	...	45	...
37	24Cr-22Ni-6Mo-2W-Cu-N	Plate	SA-240	...	S31266	...	...	45	...
38	24Cr-22Ni-6Mo-2W-Cu-N	Wld. tube	SA-249	...	S31266	...	...	45	...
39	24Cr-22Ni-6Mo-2W-Cu-N	Smls. pipe	SA-312	...	S31266	...	...	45	...
40	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-312	...	S31266	...	...	45	...
41	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-358	...	S31266	...	...	45	...
42	24Cr-22Ni-6Mo-2W-Cu-N	Smls. fittings	SA-403	...	S31266	...	...	45	...
43	24Cr-22Ni-6Mo-2W-Cu-N	Wld. fittings	SA-403	...	S31266	...	...	45	...
44	24Cr-22Ni-6Mo-2W-Cu-N	Bar, shapes	SA-479	...	S31266	...	...	45	...
45	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-813	...	S31266	...	...	45	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	100	55	1200	HA-6	G2, T10
2	100	55	1200	HA-6	G2, G6, T10
3	100	55	1200	HA-6	G2, T10
4	100	55	1200	HA-6	G2, G6, T10
5	100	55	1200	HA-6	G2, G6, T10
6	100	55	1200	HA-6	G2, G6, T10
7	100	55	1200	HA-6	G2, G6, T10
8	100	55	1200	HA-6	G2, T10
9	100	55	1200	HA-6	G2, T10
10	87	58	600	HA-6	G2, G8
11	75	30	1500	HA-2	G2, G6, T7
12	75	30	1500	HA-2	G2, T7
13	75	30	1500	HA-2	G2, G6, T7
14	75	30	1500	HA-2	G2, G6, T7
15	75	30	1500	HA-2	G2, G3, T7
16	75	30	1500	HA-2	G2, G3, T7
17	75	30	1500	HA-2	G2, G6, T7
18	75	30	1500	HA-2	G2, G3, T7
19	75	30	1500	HA-2	G2, G3, G6, T7
20	75	30	1500	HA-2	G2, G3, G6, T7
21	75	30	1500	HA-2	G2, G3, G6, T7
22	75	30	1500	HA-2	G2, T8
23	75	30	1500	HA-2	G2, G4, T8
24	75	30	1500	HA-2	G2, G6, T8
25	75	30	1500	HA-2	G2, T8
26	75	30	1500	HA-2	G2, G6, T8
27	75	30	1500	HA-2	G2, T8
28	75	30	1500	HA-2	G2, G3, T7
29	75	30	1500	HA-2	G2, G3, T7
30	75	30	1500	HA-2	G2, G3, G6, T7
31	75	30	1500	HA-2	G2, G3, T7
32	75	30	1500	HA-2	G2, G3, G6, T7
33	75	30	1500	HA-2	G2, G3, G6, T7
34	75	30	1500	HA-2	G2, G3, G6, T7
35	109	61	800	HA-10	G2, G8
36	109	61	800	HA-10	G2, G8
37	109	61	800	HA-10	G2, G8
38	109	61	800	HA-10	G2, G6, G8
39	109	61	800	HA-10	G2, G8
40	109	61	800	HA-10	G2, G6, G8
41	109	61	800	HA-10	G2, G6, G8
42	109	61	800	HA-10	G2, G8
43	109	61	800	HA-10	G2, G6, G8
44	109	61	800	HA-10	G2, G8
45	109	61	800	HA-10	G2, G6, G8

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	36.7	36.7	36.7	36.7	36.7	36.7	36.7	35.8	35.0	34.3	33.7	33.1	32.6	32.2	31.8	31.4	31.1
2	31.2	31.2	31.2	31.2	31.2	31.2	31.2	30.4	29.7	29.1	28.6	28.2	27.7	27.4	27.0	26.7	26.4
3	36.7	36.7	36.7	36.7	36.7	36.7	36.7	35.8	35.0	34.3	33.7	33.1	32.6	32.2	31.8	31.4	31.1
4	31.2	31.2	31.2	31.2	31.2	31.2	31.2	30.4	29.7	29.1	28.6	28.2	27.7	27.4	27.0	26.7	26.4
5	31.2	31.2	31.2	31.2	31.2	31.2	31.2	30.4	29.7	29.1	28.6	28.2	27.7	27.4	27.0	26.7	26.4
6	31.2	31.2	31.2	31.2	31.2	31.2	31.2	30.4	29.7	29.1	28.6	28.2	27.7	27.4	27.0	26.7	26.4
7	31.2	31.2	31.2	31.2	31.2	31.2	31.2	30.4	29.7	29.1	28.6	28.2	27.7	27.4	27.0	26.7	26.4
8	36.7	36.7	36.7	36.7	36.7	36.7	36.7	35.8	35.0	34.3	33.7	33.1	32.6	32.2	31.8	31.4	31.1
9	36.7	36.7	36.7	36.7	36.7	36.7	36.7	35.8	35.0	34.3	33.7	33.1	32.6	32.2	31.8	31.4	31.1
10	36.3	35.0	33.2	31.9	30.9	30.1	29.6	29.3	28.9	28.5	28.1	...	...	...	...	...	...
11	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
12	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
13	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
14	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
15	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
16	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
17	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
18	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
19	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
20	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
21	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
22	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
23	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
24	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
25	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
26	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
28	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
29	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
30	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
31	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.9	19.4	19.1	18.8	18.5	18.2	18.0	17.7	17.5	17.2
32	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
33	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
34	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.1	14.8	14.6
35	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
36	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
37	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
38	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.5	34.4	34.2	34.1	...	...
39	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
40	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.5	34.4	34.2	34.1	...	...
41	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.5	34.4	34.2	34.1	...	...
42	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
43	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.5	34.4	34.2	34.1	...	...
44	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.7	40.6	40.4	40.3	40.1	...	...
45	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.6	34.5	34.4	34.2	34.1	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	30.7	30.3	29.7	20.4	13.0	8.3	...	...	...	...	...	...
2	26.1	25.7	25.2	17.3	11.1	7.1	...	...	...	...	...	...
3	30.7	30.3	29.7	20.4	13.0	8.3	...	...	...	...	...	...
4	26.1	25.7	25.2	17.3	11.1	7.1	...	...	...	...	...	...
5	26.1	25.7	25.2	17.3	11.1	7.1	...	...	...	...	...	...
6	26.1	25.7	25.2	17.3	11.1	7.1	...	...	...	...	...	...
7	26.1	25.7	25.2	17.3	11.1	7.1	...	...	...	...	...	...
8	30.7	30.3	29.7	20.4	13.0	8.3	...	...	...	...	...	...
9	30.7	30.3	29.7	20.4	13.0	8.3	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...
11	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
12	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
13	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
14	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
15	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
16	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
17	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
18	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
19	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
20	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
21	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
22	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
23	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
24	14.4	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64
25	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
26	14.4	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64
27	16.9	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
28	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
29	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
30	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
31	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
32	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
33	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
34	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./ UNS No.	Class/ Condition/ Temper	Size/ Thickness, in.	P-No.	Group No.
1	25Cr-5Ni-3Mo-2Cu	Plate	SA-240	255	S32550	...	...	10H	1
2	25Cr-6Ni-Mo-N	Plate	SA-240	...	S31200	...	...	10H	1
3	25Cr-12Ni	Castings	SA-351	CH8	J93400	...	...	8	2
4	25Cr-12Ni	Castings	SA-351	CH20	J93402	...	...	8	2
5	25Cr-20Ni	Castings	SA-351	CK20	J94202	...	...	8	2
6	25Cr-20Ni	Forgings	SA-182	F310	S31000	...	$t \leq 5$	8	2
7	25Cr-20Ni	Forgings	SA-965	F310	S31000	...	...	8	2
8	25Cr-20Ni	Smls. tube	SA-213	TP310S	S31008	...	...	8	2
9	25Cr-20Ni	Plate	SA-240	310S	S31008	...	...	8	2
10	25Cr-20Ni	Wld. tube	SA-249	TP310S	S31008	...	...	8	2
11	25Cr-20Ni	Smls. pipe	SA-312	TP310S	S31008	...	...	8	2
12	25Cr-20Ni	Wld. pipe	SA-312	TP310S	S31008	...	...	8	2
13	25Cr-20Ni	Fittings	SA-403	310S	S31008	CR	...	8	2
14	25Cr-20Ni	Fittings	SA-403	310S	S31008	WP-S	...	8	2
15	25Cr-20Ni	Wld. fittings	SA-403	310S	S31008	WP-W	...	8	2
16	25Cr-20Ni	Wld. fittings	SA-403	310S	S31008	WP-WX	...	8	2
17	25Cr-20Ni	Wld. pipe	SA-813	TP310S	S31008	...	...	8	2
18	25Cr-20Ni	Wld. pipe	SA-814	TP310S	S31008	...	...	8	2
19	25Cr-20Ni	Smls. tube	SA-213	TP310H	S31009	...	...	8	2
20	25Cr-20Ni	Plate	SA-240	310H	S31009	...	...	8	2
21	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...	...	8	2
22	25Cr-20Ni	Smls. pipe	SA-312	TP310H	S31009	...	...	8	2
23	25Cr-20Ni	Wld. pipe	SA-312	TP310H	S31009	...	...	8	2
24	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb	S31040	...	...	8	2
25	25Cr-20Ni-Cb	Wld. pipe	SA-312	TP310Cb	S31040	...	...	8	2
26	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb	S31040	...	...	8	2
27	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb	S31040	...	...	8	2
28	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN	S31050	...	...	8	2
29	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	$0.25 < t \leq 1.25$	8	2
30	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	$0.25 < t \leq 1.25$	8	2
31	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	$0.25 < t \leq 1.25$	8	2
32	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...	...	8	2
33	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...	$t \leq 0.25$	8	2
34	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...	$t \leq 0.25$	8	2
35	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...	$t \leq 0.25$	8	2
36	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	$t \geq 0.40$	10H	1
37	29Cr-6.5Ni-2Mo-N	Bar	SA-479	...	S32906	...	...	10H	1
38	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	$t \geq 0.40$	10H	1
39	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	$t \geq 0.40$	10H	1
40	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...	$t < 0.40$	10H	1
41	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...	$t < 0.40$	10H	1
42	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...	$t < 0.40$	10H	1

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	110	80	500	HA-5	G8
2	100	65	650	HA-5	G2, G8
3	65	28	1500	HA-3	G2, G3, G4, G8, T8
4	70	30	1500	HA-2	G2, T8
5	65	28	1500	HA-3	G2, T8
6	75	30	1500	HA-2	G2, G3, G5, G7, T7
7	75	30	1500	HA-2	G2, G3, G5, G7, T7
8	75	30	1500	HA-2	G2, G3, G5, G7, T7
9	75	30	1500	HA-2	G2, G3, G5, G7, T7
10	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
11	75	30	1500	HA-2	G2, G3, G5, G7, T7
12	75	30	100	HA-2	G2, G3, G5, G6, G7
13	75	30	1500	HA-2	G2, G6, T7
14	75	30	1500	HA-2	G2, T7
15	75	30	1500	HA-2	G2, G6, T7
16	75	30	1500	HA-2	G2, G6, T7
17	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
18	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
19	75	30	1500	HA-2	G2, T8
20	75	30	1500	HA-2	G2, T8
21	75	30	1500	HA-2	G2, G6, T8
22	75	30	1500	HA-2	G2, T8
23	75	30	1500	HA-2	G2, G6, T8
24	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
25	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
26	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
27	75	30	1500	HA-2	G2, G3, G5, G6, G7, T7
28	78	37	900	HA-2	...
29	78	37	900	HA-2	...
30	78	37	900	HA-2	G6
31	78	37	900	HA-2	G6
32	80	35	600	HA-2	...
33	84	39	900	HA-2	...
34	84	39	900	HA-2	G6
35	84	39	900	HA-2	G6
36	109	80	600	HA-5	G8
37	109	80	600	HA-5	G8
38	109	80	600	HA-5	G8
39	109	80	600	HA-5	G8
40	116	94	600	HA-5	G8
41	116	94	600	HA-5	G8
42	116	94	600	HA-5	G8

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	45.8	45.8	45.8	44.7	42.9	41.4	40.3	39.6	39.1	...	...	...	...	...	...	...	...
2	41.7	41.7	41.7	41.7	41.7	41.7	41.7	41.7	40.9	40.1	39.2	38.0	...	...	...	...	...
3	18.7	18.7	18.7	18.7	18.7	18.6	18.2	17.9	17.7	17.4	17.1	16.7	16.3	15.9	15.4	14.9	14.4
4	20.0	20.0	20.0	20.0	20.0	19.9	19.5	19.2	18.9	18.6	18.3	17.9	17.5	17.0	16.5	16.0	15.4
5	18.7	18.7	18.7	18.7	18.7	18.6	18.2	17.9	17.7	17.4	17.1	16.7	16.3	15.9	15.4	14.9	14.4
6	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
7	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
8	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
9	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
10	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
11	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
12	17.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
14	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
15	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
16	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
17	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
18	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
19	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
20	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
21	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
22	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.3	18.9	18.5	18.2	17.9	17.7	17.4	17.2	16.9
23	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
24	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
25	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
26	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
27	17.0	17.0	17.0	17.0	17.0	17.0	17.0	16.8	16.4	16.0	15.7	15.5	15.2	15.0	14.8	14.6	14.4
28	24.7	24.7	24.7	24.7	24.7	24.7	24.0	23.3	22.7	22.1	21.5	21.0	20.4	19.9	19.4	18.9	18.5
29	24.7	24.7	24.7	24.7	24.7	24.7	24.0	23.3	22.7	22.1	21.5	21.0	20.4	19.9	19.4	18.9	18.5
30	21.0	21.0	21.0	21.0	21.0	21.0	20.4	19.8	19.3	18.8	18.3	17.8	17.4	16.9	16.5	16.1	15.7
31	21.0	21.0	21.0	21.0	21.0	21.0	20.4	19.8	19.3	18.8	18.3	17.8	17.4	16.9	16.5	16.1	15.7
32	23.3	23.3	23.3	23.3	23.3	23.3	22.7	22.0	21.4	20.9	20.3	...	...	...	...	...	...
33	26.0	26.0	26.0	26.0	26.0	26.0	25.3	24.5	23.9	23.3	22.7	22.1	21.5	21.0	20.5	20.0	19.5
34	22.1	22.1	22.1	22.1	22.1	22.1	21.5	20.9	20.3	19.8	19.3	18.8	18.3	17.8	17.4	17.0	16.6
35	22.1	22.1	22.1	22.1	22.1	22.1	21.5	20.9	20.3	19.8	19.3	18.8	18.3	17.8	17.4	17.0	16.6
36	45.4	45.4	45.4	43.5	41.6	40.6	40.0	...	37.9	36.8	36.8	...	...	...	...	...	...
37	45.4	45.4	45.4	43.5	41.6	40.6	40.0	...	37.9	36.8	36.8	...	...	...	...	...	...
38	45.4	45.4	45.4	43.5	41.6	40.6	40.0	...	37.9	36.8	36.8	...	...	...	...	...	...
39	45.4	45.4	45.4	43.5	41.6	40.6	40.0	...	37.9	36.8	36.8	...	...	...	...	...	...
40	48.3	48.3	48.3	48.3	48.3	47.7	47.0	...	44.6	43.3	43.3	...	...	...	...	...	...
41	48.3	48.3	48.3	48.3	48.3	47.7	47.0	...	44.6	43.3	43.3	...	...	...	...	...	...
42	48.3	48.3	48.3	48.3	48.3	47.7	47.0	...	44.6	43.3	43.3	...	...	...	...	...	...

Table 5A (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Ferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500
1	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	13.9	11.1	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80
4	14.9	11.1	8.5	6.5	5.0	3.8	2.9	2.3	1.8	1.3	0.90	0.80
5	13.9	11.3	9.8	8.5	7.3	6.0	4.8	3.5	2.4	1.6	1.1	0.80
6	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
7	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
8	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
9	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
10	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
11	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
12	...	...	...	...	...	...	...	...	...	...	...	...
13	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
14	15.9	9.9	7.1	5.0	3.6	2.5	1.5	0.80	0.50	0.40	0.30	0.20
15	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
16	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
17	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
18	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
19	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
20	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
21	14.2	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64
22	16.7	13.8	10.3	7.6	5.5	4.0	3.0	2.2	1.7	1.3	0.97	0.75
23	14.2	11.7	8.8	6.5	4.7	3.4	2.6	1.9	1.4	1.1	0.82	0.64
24	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
25	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
26	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
27	13.5	8.4	6.0	4.3	3.1	2.1	1.3	0.68	0.43	0.34	0.26	0.17
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...

NOTES TO TABLE 5A**GENERAL NOTES**

- (25) (a) The following abbreviations are used: N, Normalized; NT, Normalized and tempered; QT, Quenched and tempered; Smls., Seamless; Temp., Temperature; and Wld., Welded.
- (b) An alternative typeface is used for stress values obtained from time-dependent properties (see Notes T1 through T10).
- (c) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-516/SA-516M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-516 Grade 70 shall be used when SA-516M Grade 485 is used in construction.
- (d) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (e) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (f) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES - GENERAL REQUIREMENTS

- G1 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating to a minimum temperature of 2000°F, and quenching in water or rapidly cooling by other means.
- G2 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed 66²/₃% but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G3 At temperatures over 1000°F, these stress values apply only when the carbon is 0.04% or higher. This note is applicable only when stresses above 1000°F are published.
- G4 For temperatures above 1000°F, these stress values may be used only if the material has been heat treated by heating to a minimum temperature of 1900°F and quenching in water or rapidly cooling by other means. This note is applicable only when stresses above 1000°F are published.
- G5 These stress values at temperatures of 1050°F and above should be used only when assurance is provided that the steel has a predominant grain size not finer than ASTM No. 6. This note is applicable only when stresses above 1000°F are published.
- G6 A quality factor of 0.85 has been applied in arriving at the maximum allowable stress values for this material.
- G7 These stress values shall be considered basic values to be used when no effort is made to control or check the grain size of the steel.
- G8 This steel may be expected to develop embrittlement after service at moderately elevated temperature; see Nonmandatory Appendix A, A-207 and A-208.
- G9 The tensile strength shall not be in excess of 20,000 psi above the specified minimum.
- G10 All forgings shall have a maximum tensile strength not in excess of 25 ksi above the specified minimum.
- G11 SA-723 is exempt from the requirement in Section VIII, Division 2, 6.7.6.3(b) that the average of the individual Brinell hardness numbers shall not be more than 10% below or 25% above the number corresponding to the tensile strength.
- G12 See Section VIII, Division 2, 3.4.
- G13 Upon prolonged exposure to temperatures above 800°F, the carbide phase of carbon steel may be converted to graphite. See Nonmandatory Appendix A, A-201 and A-202.
- G14 Upon prolonged exposure to temperatures above 875°F, the carbide phase of carbon-molybdenum steel may be converted to graphite. See Nonmandatory Appendix A, A-201 and A-202.
- G15 This material may be susceptible to temper embrittlement. See Nonmandatory Appendix A, A-203.
- G16 These stresses apply to all product forms (C, H, and P) as defined in SA/EN 10028-7.
- (25) G17 Use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.
- (25) G18 Maximum allowable stress values for 100°F may be used at temperatures down to -325°F without additional specification requirements.
- (25) G19 Creep-fatigue, thermal ratcheting, and environmental effects are increasingly significant failure modes at temperatures in excess of 1,500°F and shall be considered in the design.

NOTES - HEAT TREATMENT REQUIREMENTS

- H1 Annealed.
- H2 Normalized, normalized and tempered, or quenched and tempered.
- H3 For applications involving consideration of heat treatment after forming or welding, see Section VIII, Division 2, Table 6.15 for P-No. 10K, Group No. 1 materials.
- H4 Liquid quenched and tempered.

NOTES - SIZE REQUIREMENTS

- S1 The maximum thickness of forgings shall not exceed 3³/₄ in. (4 in. as heat treated).

NOTES TO TABLE 5A (CONT'D)**NOTES – SIZE REQUIREMENTS (CONT'D)**

S2 The maximum section thickness shall not exceed 3 in. for double-normalized-and-tempered forgings, or 5 in. for quenched-and-tempered forgings.

S3 Both NPS 8 and larger, and schedule 140 and heavier.

S4 Either NPS 8 and larger and less than schedule 140 wall, or less than NPS 8 and all wall thicknesses.

NOTES – TIME-DEPENDENT PROPERTIES

T1 Allowable stresses for temperatures of 650°F and above are values obtained from time-dependent properties.

T2 Allowable stresses for temperatures of 700°F and above are values obtained from time-dependent properties.

T3 Allowable stresses for temperatures of 750°F and above are values obtained from time-dependent properties.

T4 Allowable stresses for temperatures of 800°F and above are values obtained from time-dependent properties.

T5 Allowable stresses for temperatures of 850°F and above are values obtained from time-dependent properties.

T6 Allowable stresses for temperatures of 900°F and above are values obtained from time-dependent properties.

T7 Allowable stresses for temperatures of 950°F and above are values obtained from time-dependent properties.

T8 Allowable stresses for temperatures of 1000°F and above are values obtained from time-dependent properties.

T9 Allowable stresses for temperatures of 1050°F and above are values obtained from time-dependent properties.

T10 Allowable stresses for temperatures of 1100°F and above are values obtained from time-dependent properties.

NOTES – WELDING REQUIREMENTS

W1 Not for welded construction.

W2 Welding is not permitted when carbon content exceeds 0.35% by ladle analysis except for limited types of welding, as allowed in Section VIII, Division 2, Part 6.

W3 Nonwelded, or welded if the tensile strength of the Section IX reduced section tension test is not less than 100 ksi.

W4 Welded, with the tensile strength of the Section IX reduced section tension test less than 100 ksi but not less than 95 ksi.

W5 In welded construction, for temperatures above 850°F, the weld metal shall have a carbon content of greater than 0.05%.

W6 Section IX, QW-250 Variables QW-404.12, QW-406.3, QW-407.2, and QW-409.1 shall also apply to this material. These variables shall be applied in accordance with the rules for welding of Section VIII, Division 2, Part 6.

W7 The following, in addition to the variables in Section IX, QW-250, shall be considered as essential variables requiring requalification of the welding procedure:

(a) An increase in the maximum or a decrease in the minimum specified preheat or interpass temperatures. The specified range of preheat temperatures shall not exceed 150°F.

(b) A change in the thickness T of the welding procedure qualification test plate as follows:

(1) For welded joints that are quenched and tempered after welding, any increase in thickness (the minimum thickness qualified in all cases is $\frac{1}{4}$ in.).

(2) For welded joints that are not quenched and tempered after welding, any change as follows:

(-a) for T less than $\frac{5}{8}$ in., any decrease in thickness (the maximum thickness qualified is $2T$);

(-b) for T equal to $\frac{5}{8}$ in. and over, any departure from the range of $\frac{5}{8}$ in. to $2T$.

Table 5B
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper
1	...	Drawn smls. tube	SB-210	...	Alclad 3003	O
2	...	Drawn smls. tube	SB-210	...	Alclad 3003	H113
3	...	Smls. extr. tube	SB-241	...	Alclad 3003	O
4	...	Smls. extr. tube	SB-241	...	Alclad 3003	H112
5	...	Plate, sheet	SB-209	...	A93003	O
6	...	Plate, sheet	SB-209	...	A93003	H112
7	...	Plate, sheet	SB-209	...	A93003	H112
8	...	Plate, sheet	SB-209	...	A93003	H112
9	...	Drawn smls. tube	SB-210	...	A93003	O
10	...	Drawn smls. tube	SB-210	...	A93003	H113
11	...	Bar, rod, shapes	SB-221	...	A93003	O
12	...	Bar, rod, shapes	SB-221	...	A93003	H112
13	...	Smls. extr. tube	SB-241	...	A93003	O
14	...	Smls. pipe	SB-241	...	A93003	H112
15	...	Smls. extr. tube	SB-241	...	A93003	H112
16	...	Plate, sheet	SB-209	...	A93004	O
17	...	Plate, sheet	SB-209	...	A93004	H112
18	...	Plate, sheet	SB-209	...	A95052	O
19	...	Plate, sheet	SB-209	...	A95052	H112
20	...	Plate, sheet	SB-209	...	A95052	H112
21	...	Plate, sheet	SB-209	...	A95083	O
22	...	Plate, sheet	SB-209	...	A95083	O
23	...	Plate, sheet	SB-209	...	A95083	O
24	...	Plate, sheet	SB-209	...	A95083	O
25	...	Plate, sheet	SB-209	...	A95083	O
26	...	Plate, sheet	SB-209	...	A95083	H112
27	...	Plate, sheet	SB-209	...	A95083	H112
28	...	Bar, rod, shapes	SB-221	...	A95083	H111
29	...	Smls. extr. tube	SB-241	...	A95083	H111
30	...	Plate, sheet	SB-209	...	A95086	O
31	...	Plate, sheet	SB-209	...	A95086	H112
32	...	Plate, sheet	SB-209	...	A95086	H112
33	...	Plate, sheet	SB-209	...	A95086	H112
34	...	Plate, sheet	SB-209	...	A95086	H112
35	...	Plate, sheet	SB-209	...	A95454	O
36	...	Plate, sheet	SB-209	...	A95454	H112
37	...	Plate, sheet	SB-209	...	A95454	H112
38	...	Bar, rod, shapes	SB-221	...	A95454	O
39	...	Bar, rod, shapes	SB-221	...	A95454	H112
40	...	Smls. extr. tube	SB-241	...	A95454	O
41	...	Smls. extr. tube	SB-241	...	A95454	H112
42	...	Plate, sheet	SB-209	...	A96061	T4
43	...	Plate, sheet	SB-209	...	A96061	T451
44	...	Plate, sheet	SB-209	...	A96061	T6
45	...	Plate, sheet	SB-209	...	A96061	T651

Table 5B
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	$0.010 \leq t \leq 0.5$	21	13	4.5	400	NFA-7	G4, T3
2	$0.050 \leq t \leq 0.5$	21	13	4.5	400	NFA-7	G4, T3, W2
3	...	21	13	4.5	400	NFA-7	G4, T3
4	...	21	13	4.5	400	NFA-7	G4, T3, W2
5	$0.006 \leq t \leq 3$	21	14	5	400	NFA-1	G4, T4
6	$0.250 \leq t < 0.5$	21	17	10	400	NFA-1	G4, T2, W2
7	$0.5 \leq t \leq 2$	21	15	6	400	NFA-1	G4, T2, W2
8	$2 < t \leq 3$	21	14.5	6	400	NFA-1	G4, T2, W2
9	$0.010 \leq t \leq 0.5$	21	14	5	400	NFA-1	G4, T2
10	$0.010 \leq t \leq 0.5$	21	14	5	400	NFA-1	G4, T2, W2
11	...	21	14	5	400	NFA-1	G2, G4, T2
12	...	21	14	5	400	NFA-1	G2, G4, T2, W2
13	...	21	14	5	400	NFA-1	G4, T2
14	$t \geq 1$	21	14	5	400	NFA-1	G4, T2
15	...	21	14	5	400	NFA-1	G4, T2, W2
16	$0.006 \leq t \leq 3$	22	22	8.5	400	NFA-3	G4, T3
17	$0.250 \leq t \leq 3$	22	23	9	400	NFA-3	G4, T2, W2
18	$0.051 \leq t \leq 3$	22	25	9.5	400	NFA-8	G4, T2
19	$0.25 \leq t < 0.5$	22	28	16	400	NFA-8	G4, T2, W2
20	$0.5 \leq t \leq 3$	22	25	9.5	400	NFA-8	G4, T2, W2
21	$0.051 \leq t \leq 1.5$	25	40	18	150	NFA-11	G4, G6
22	$1.5 < t \leq 3$	25	39	17	150	NFA-11	G4, G6
23	$3 < t \leq 5$	25	38	16	150	NFA-11	G4, G6
24	$5 < t \leq 7$	25	37	15	150	NFA-11	G4, G6
25	$7 < t \leq 8$	25	36	14	150	NFA-11	G4, G6
26	$0.25 \leq t \leq 1.5$	25	40	18	150	NFA-11	G4, G6, W2
27	$1.5 < t \leq 3$	25	39	17	150	NFA-11	G4, G6, W2
28	$t \leq 5$	25	40	24	150	NFA-11	G2, G4, G6, W2
29	...	25	40	24	150	NFA-11	G4, G6, W2
30	$0.051 \leq t \leq 2$	25	35	14	150	NFA-9	G4, G6
31	$0.063 \leq t < 0.5$	25	36	18	150	NFA-9	G4, G6, W2
32	$0.5 \leq t < 1$	25	35	16	150	NFA-9	G4, G6, W2
33	$1 < t \leq 2$	25	35	14	150	NFA-9	G4, G6, W2
34	$2 < t \leq 3$	25	34	14	150	NFA-9	G4, G6, W2
35	$0.051 \leq t \leq 3$	22	31	12	400	NFA-6	G4, T1
36	$0.250 \leq t < 0.5$	22	32	18	400	NFA-6	G4, T2, W2
37	$0.5 \leq t \leq 3$	22	31	12	400	NFA-6	G4, T1, W2
38	$t \leq 5$	22	31	12	400	NFA-6	G2, G4, T1
39	$t \leq 5$	22	31	12	400	NFA-6	G2, G4, T1, W2
40	$t \leq 5$	22	31	12	400	NFA-6	G4, T1
41	$t \leq 5$	22	31	12	400	NFA-6	G4, T1, W2
42	$0.051 \leq t < 0.25$	23	30	16	400	NFA-13	G4, G8, T4, W3
43	$0.25 \leq t \leq 3$	23	30	16	400	NFA-13	G4, G8, T4, W3
44	$0.051 \leq t < 0.25$	23	42	35	400	NFA-12	G4, G8, T2, W3
45	$0.25 \leq t \leq 4$	23	42	35	400	NFA-12,13	G4, G8, T2, W3, W4

Table 5B
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	3.0	2.9	2.8	2.7	2.5	1.9	1.5	...	...	...	...	...	...	...	...	...	...
2	3.0	2.9	2.8	2.7	2.5	1.9	1.5	...	...	...	...	...	...	...	...	...	...
3	3.0	2.9	2.8	2.7	2.5	1.9	1.5	...	...	...	...	...	...	...	...	...	...
4	3.0	2.9	2.8	2.7	2.5	1.9	1.5	...	...	...	...	...	...	...	...	...	...
5	3.3	3.2	3.1	3.0	2.8	2.6	2.3	...	...	...	...	...	...	...	...	...	...
6	6.7	6.4	6.3	6.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
7	4.0	3.9	3.8	3.6	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
8	4.0	3.8	3.8	3.6	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
9	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
10	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
11	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
12	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
13	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
14	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
15	3.3	3.2	3.1	3.0	2.7	1.9	1.5	...	...	...	...	...	...	...	...	...	...
16	5.7	5.7	5.7	5.7	5.7	3.8	2.3	...	...	...	...	...	...	...	...	...	...
17	6.0	6.0	6.0	6.0	5.7	3.8	2.3	...	...	...	...	...	...	...	...	...	...
18	6.3	6.3	6.3	6.3	6.1	4.1	2.3	...	...	...	...	...	...	...	...	...	...
19	10.7	10.7	10.7	10.7	6.1	4.1	2.3	...	...	...	...	...	...	...	...	...	...
20	6.3	6.3	6.3	6.3	6.1	4.1	2.3	...	...	...	...	...	...	...	...	...	...
21	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	11.3	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	11.3	11.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	16.0	16.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	16.0	16.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	12.0	12.0	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	10.7	10.7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	9.3	9.3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
36	12.0	12.0	12.0	12.0	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
37	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
38	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
39	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
40	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
41	8.0	8.0	8.0	7.5	5.5	4.1	3.0	...	...	...	...	...	...	...	...	...	...
42	10.7	10.5	10.4	10.2	10.2	10.2	5.2	...	...	...	...	...	...	...	...	...	...
43	10.7	10.5	10.4	10.2	10.2	10.2	5.2	...	...	...	...	...	...	...	...	...	...
44	17.5	17.5	17.5	17.5	16.7	10.7	5.2	...	...	...	...	...	...	...	...	...	...
45	17.5	17.5	17.5	17.5	16.7	10.7	5.2	...	...	...	...	...	...	...	...	...	...

Table 5B
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
1	...	Plate, sheet	SB-209	...	A96061	T651
2	...	Plate, sheet	SB-209	...	A96061	T6 wld.
3	...	Drawn smls. tube	SB-210	...	A96061	T4
4	...	Drawn smls. tube	SB-210	...	A96061	T6
5	...	Drawn smls. tube	SB-210	...	A96061	T6 wld.
6	...	Bar, rod, shapes	SB-221	...	A96061	T4
7	...	Bar, rod, shapes	SB-221	...	A96061	T6
8	...	Bar, rod, shapes	SB-221	...	A96061	T6 wld.
9	...	Smls. extr. tube/pipe	SB-241	...	A96061	T4
10	...	Smls. extr. tube/pipe	SB-241	...	A96061	T6
11	...	Smls. drawn pipe	SB-241	...	A96061	T6
12	...	Smls. drawn pipe	SB-241	...	A96061	T6
13	...	Smls. extr. tube/pipe	SB-241	...	A96061	T6 wld.
14	...	Smls. drawn pipe	SB-241	...	A96061	T6 wld.
15	...	Shapes	SB-308	...	A96061	T6
16	...	Shapes	SB-308	...	A96061	T6 wld.
(25) 17	...	Die forgings	SB-247	...	A96061	T6
(25) 18	...	Hand forgings	SB-247	...	A96061	T6
(25) 19	...	Hand forgings	SB-247	...	A96061	T6
(25) 20	...	Die & hand forgings	SB-247	...	A96061	T6 wld.
21	...	Drawn smls. tube	SB-210	...	A96063	T6
22	...	Bar, rod, shapes	SB-221	...	A96063	T5
23	...	Bar, rod, shapes	SB-221	...	A96063	T5
24	...	Bar, rod, shapes	SB-221	...	A96063	T6
25	...	Smls. extr. tube	SB-241	...	A96063	T5
26	...	Smls. extr. tube	SB-241	...	A96063	T5
27	...	Smls. extr. tube	SB-241	...	A96063	T6
28	...	Bar, rod	SB-187	...	C10200	O60
29	...	Bar, rod	SB-187	...	C11000	O60
30	...	Smls. tube	SB-111	...	C28000	O61
31	...	Smls. tube	SB-111	...	C44300	O61
32	...	Smls. tube	SB-111	...	C44400	O61
33	...	Smls. tube	SB-111	...	C44500	O61
(25) 34	...	Plate	SB-171	...	C46400	M10, M20, O20, O25
(25) 35	...	Plate, sheet	SB-171	...	C46400	M10, M20, O20, O25
(25) 36	...	Smls. tube	SB-111	...	C60800	O61
(25) 37	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 38	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 39	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
40	...	Bar, rod	SB-98	...	C65100	O60
41	...	Bar, rod	SB-98	...	C65100	H02
(25) 42	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61
43	...	Bar, rod	SB-98	...	C65500	O60
44	...	Bar, rod	SB-98	...	C65500	H02
45	...	Bar, rod	SB-98	...	C66100	O60

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	$4 < t \leq 6$	23	40	35	400	NFA-12,13	G4, G8, T3, W3, W4
2	...	23	24	...	400	NFA-12	G4, G8, T4
3	$0.025 \leq t \leq 0.5$	23	30	16	400	NFA-13	G4, T4, W3
4	$0.025 \leq t \leq 0.5$	23	42	35	400	NFA-12,13	G4, T2, W3, W4
5	...	23	24	...	400	NFA-13	G4, T4, W4
6	...	23	26	16	400	NFA-13	G2, G4, G8, T4, W3
7	...	23	38	35	400	NFA-12,13	G2, G4, G8, T3, W3, W4
8	...	23	24	...	400	NFA-12,13	G2, G4, G8, T4, W4
9	...	23	26	16	400	NFA-13	G4, G8, T4, W3
10	...	23	38	35	400	NFA-12,13	G4, G8, T3, W3, W4
11	NPS < 1	23	42	35	400	NFA-12,13	G4, T2, W3, W4
12	NPS ≥ 1	23	38	35	400	NFA-12,13	G4, T3, W3, W4
13	...	23	24	...	400	NFA-12,13	G4, T4, W4
14	...	23	24	...	400	NFA-12,13	G4, T4, W4
15	...	23	38	35	400	NFA-12,13	G2, G4, T3, W3, W4
16	...	23	24	...	400	NFA-12,13	G2, G4, T4, W4
17	≤ 4.000	23	38	35	300	NFA-12,13	G4, W4
18	≤ 4.000	23	37	33	300	NFA-12,13	G4, W4
19	4.001–8.000	23	35	32	300	NFA-12,13	G4, W4
20	≤ 8.000	23	24	...	300	NFA-12,13	G4, W4
21	$0.025 \leq t \leq 0.5$	23	33	28	400	NFA-1	G4, T1, W3
22	$t \leq 0.5$	23	22	16	400	NFA-1	G2, G4, T1, W3
23	$0.501 \leq t \leq 1$	23	21	15	400	NFA-1	G2, G4, T1, W3
24	$t \leq 1$	23	30	25	400	NFA-1	G2, G4, T1, W3
25	$t \leq 0.5$	23	22	16	400	NFA-1	G4, T1, W3
26	$0.501 \leq t \leq 1$	23	21	15	400	NFA-1	G4, T1, W3
27	$t \leq 1$	23	30	25	400	NFA-1	G4, T1, W3
28	All	31	28	8	400	NFC-1	G1, G3, T3
29	All	31	28	8	400	NFC-1	G1, G3, T3
30	...	32	50	20	400	NFC-3	G3, G5, T3
31	...	32	45	15	400	NFC-2	G3, G5, T4
32	...	32	45	15	400	NFC-2	G3, G5, T4
33	...	32	45	15	400	NFC-2	G3, G5, T4
34	$3 < t \leq 5$	32	50	18	400	NFC-2	G3, T3
35	$t \leq 3$	32	50	20	400	NFC-2	G3, T3
36	...	35	50	19	500	NFC-2	G1, G3, G5, T3
37	$2 < t \leq 5$	35	65	28	500	NFC-8	G3
38	$\frac{1}{2} < t \leq 2$	35	70	30	500	NFC-8	G3
39	$t \leq \frac{1}{2}$	35	72	32	500	NFC-8	G3
40	All	33	40	12	350	NFC-1	G1, G3, G9
41	≤ 2	33	55	20	350	NFC-2	G1, G3, G9, W2
42	≤ 2	33	50	18	350	NFC-2	G1, G3, G9, T3
43	All	33	52	15	350	NFC-2	G1, G3, G9
44	≤ 2	33	70	38	350	NFC-2	G1, G3, G9, W2
45	All	33	52	15	350	NFC-2	G1, G3, G9

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	16.7	16.7	16.7	16.7	16.7	10.7	5.2	...	...	...	...	...	...	...	...	...	...
2	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
3	10.7	10.5	10.4	10.2	10.2	10.2	5.2	...	...	...	...	...	...	...	...	...	...
4	17.5	17.5	17.5	17.5	16.7	10.7	5.2	...	...	...	...	...	...	...	...	...	...
5	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
6	10.7	10.6	10.2	10.2	10.2	10.2	5.2	...	...	...	...	...	...	...	...	...	...
7	15.8	15.8	15.8	15.8	15.8	10.7	5.2	...	...	...	...	...	...	...	...	...	...
8	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
9	10.7	10.6	10.2	10.2	10.2	10.2	5.2	...	...	...	...	...	...	...	...	...	...
10	15.8	15.8	15.8	15.8	15.8	10.7	5.2	...	...	...	...	...	...	...	...	...	...
11	17.5	17.5	17.5	17.5	16.7	10.7	5.2	...	...	...	...	...	...	...	...	...	...
12	15.8	15.8	15.8	15.8	15.8	10.7	5.2	...	...	...	...	...	...	...	...	...	...
13	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
14	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
15	15.8	15.8	15.8	15.8	15.8	10.7	5.2	...	...	...	...	...	...	...	...	...	...
16	10.0	10.0	10.0	10.0	10.0	10.0	5.2	...	...	...	...	...	...	...	...	...	...
17	15.8	15.8	15.8	15.8	15.8	...	...	...	...	...	...	...	...	...	...	...	...
18	15.4	15.4	15.4	15.4	15.4	...	...	...	...	...	...	...	...	...	...	...	...
19	14.6	14.6	14.6	14.6	14.6	...	...	...	...	...	...	...	...	...	...	...	...
20	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...	...
21	13.8	13.8	13.8	9.6	7.3	3.8	2.0	...	...	...	...	...	...	...	...	...	...
22	9.2	9.2	9.2	8.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...
23	8.8	8.8	8.8	8.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...
24	12.5	12.5	12.5	9.6	7.3	3.8	2.0	...	...	...	...	...	...	...	...	...	...
25	9.2	9.2	9.2	8.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...
26	8.8	8.8	8.8	8.8	4.6	3.4	2.0	...	...	...	...	...	...	...	...	...	...
27	12.5	12.5	12.5	9.6	7.3	3.8	2.0	...	...	...	...	...	...	...	...	...	...
28	5.3	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...
29	5.3	5.3	5.3	5.3	5.3	4.4	3.0	...	...	...	...	...	...	...	...	...	...
30	13.3	13.3	13.3	13.3	13.3	10.8	5.3	...	...	...	...	...	...	...	...	...	...
31	10.0	10.0	10.0	10.0	10.0	10.0	5.3	...	...	...	...	...	...	...	...	...	...
32	10.0	10.0	10.0	10.0	10.0	10.0	5.3	...	...	...	...	...	...	...	...	...	...
33	10.0	10.0	10.0	10.0	10.0	10.0	5.3	...	...	...	...	...	...	...	...	...	...
34	12.0	12.0	12.0	12.0	12.0	6.4	2.7	...	...	...	...	...	...	...	...	...	...
35	13.3	13.3	13.3	13.3	13.3	6.4	2.7	...	...	...	...	...	...	...	...	...	...
36	12.7	12.7	12.7	12.7	12.7	10.0	6.0	4.0	2.0	...	...	...	...	...	...	...	...
37	18.7	18.6	18.5	18.4	18.2	18.1	17.9	17.7	17.6	...	...	...	...	...	...	...	...
38	20.0	19.9	19.8	19.7	19.5	19.4	19.2	19.0	18.8	...	...	...	...	...	...	...	...
39	21.3	21.3	21.1	20.9	20.9	20.7	20.5	20.3	20.1	...	...	...	...	...	...	...	...
40	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...	...	...	...	...	...
41	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...	...	...	...	...	...	...
42	12.0	12.0	12.0	12.0	12.0	10.7	...	...	...	...	...	...	...	...	...	...	...
43	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...
44	25.3	25.3	25.3	25.3	25.3	25.3	...	...	...	...	...	...	...	...	...	...	...
45	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper
1	...	Bar, rod	SB-98	...	C66100	H02
2	...	Plate	SB-171	...	C70600	M10, M20, O20, O25
3	...	Condenser tubes	SB-111	...	C70600	O61
4	...	Smls. U-bend tube	SB-395	...	C70600	O61
5	...	Plate	SB-171	...	C70620	M10, M20, O20, O25
6	...	Condenser tubes	SB-111	...	C70620	O61
7	...	Smls. U-bend tube	SB-395	...	C70620	O61
8	...	Plate	SB-171	...	C71500	M10, M20, O20, O25
9	...	Plate	SB-171	...	C71500	M10, M20, O20, O25
10	...	Condenser tubes	SB-111	...	C71500	O61
11	...	Smls. U-bend tube	SB-395	...	C71500	O61
12	...	Plate	SB-171	...	C71520	M10, M20, O20, O25
13	...	Plate	SB-171	...	C71520	M10, M20, O20, O25
14	...	Condenser tubes	SB-111	...	C71520	O61
15	...	Smls. U-bend tube	SB-395	...	C71520	O61
16	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed
17	99Ni	Bar, rod	SB-160	...	N02200	Annealed
18	99Ni	Smls. pipe & tube	SB-161	...	N02200	Annealed
19	99Ni	Plate, sheet, strip	SB-162	...	N02200	Annealed
20	99Ni	Smls. tube	SB-163	...	N02200	Annealed
21	99Ni	Plate, sheet, strip	SB-162	...	N02200	As rolled
22	99Ni-Low C	Bar, rod	SB-160	...	N02201	Annealed
23	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
24	99Ni-Low C	Bar, rod	SB-160	...	N02201	Hot fin.
25	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
26	99Ni-Low C	Plate, sheet, strip	SB-162	...	N02201	Annealed
27	99Ni-Low C	Smls. tube	SB-163	...	N02201	Annealed
28	67Ni-30Cu	Bar, rod	SB-164	...	N04400	Annealed
29	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
30	67Ni-30Cu	Forgings	SB-564	...	N04400	Annealed
31	67Ni-30Cu	Plate	SB-127	...	N04400	Annealed
32	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Annealed
33	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
34	67Ni-30Cu	Plate	SB-127	...	N04400	As rolled
35	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Stress rel.
36	67Ni-30Cu-S	Bar, rod	SB-164	...	N04405	Annealed
37	47Ni-22Cr-9Mo-18Fe	Plate	SB-435	...	N06002	Annealed
38	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...	N06002	Annealed
39	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...	N06002	Solution ann.
40	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.
41	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...	N06002	Solution ann.
42	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.
43	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
44	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
45	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	≤ 2	33	70	38	350	NFC-2	G1, G3, G9, W2
2	$t \leq 5$	34	40	15	600	NFC-3	G1, G3, T5
3	...	34	40	15	600	NFC-3	G1, G3, T5
4	...	34	40	15	600	NFC-3	G1, G3, T5
5	$t \leq 5$	34	40	15	600	NFC-3	G1, G3, T5
6	...	34	40	15	600	NFC-3	G1, G3, T5
7	...	34	40	15	600	NFC-3	G1, G3, T5
8	$2\frac{1}{2} < t \leq 5$	34	45	18	700	NFC-4	G1, G3
9	$t \leq 2\frac{1}{2}$	34	50	20	700	NFC-4	G1, G3
10	...	34	52	18	700	NFC-4	G1, G3
11	...	34	52	18	700	NFC-4	G1, G3
12	$2\frac{1}{2} < t \leq 5$	34	45	18	700	NFC-4	G1, G3
13	$t \leq 2\frac{1}{2}$	34	50	20	700	NFC-4	G1, G3
14	...	34	52	18	700	NFC-4	G1, G3
15	...	34	52	18	700	NFC-4	G1, G3
16	O.D. > 5	41	55	12	600	NFN-2	G3
17	...	41	55	15	600	NFN-2	G2, G3
18	O.D. ≤ 5	41	55	15	600	NFN-2	G3
19	...	41	55	15	600	NFN-2	G3
20	...	41	55	15	600	NFN-2	G3
21	...	41	55	20	600	NFN-2	G3
22	...	41	50	10	600	NFN-1	G2, G3
23	O.D. > 5	41	50	10	1200	NFN-1	G3, T9
24	...	41	50	10	600	NFN-1	G2, G3
25	O.D. ≤ 5	41	50	12	1200	NFN-1	G3, T8
26	...	41	50	12	600	NFN-1	G3
27	...	41	50	12	1200	NFN-1	G3, T8
28	...	42	70	25	900	NFN-3	G1, G2, G3, T8
29	O.D. > 5	42	70	25	900	NFN-3	G1, G3, T8
30	...	42	70	25	900	NFN-3	G1, G2, G3, T8
31	...	42	70	28	900	NFN-3	G1, G3, T8
32	...	42	70	28	900	NFN-3	G1, G3, T8
33	O.D. ≤ 5	42	70	28	900	NFN-3	G1, G3, T8
34	...	42	75	40	900	NFN-3	G1, G3, T7
35	...	42	85	55	800	NFN-3	G1, G3, T7, W1
36	...	42	70	25	900	NFN-3	G1, G2, G3, T8
37	$\frac{3}{16} < t \leq 2\frac{1}{2}$	43	95	35	900	NFN-15	G1, G3, G13
38	$\frac{1}{16} < t \leq \frac{3}{16}$	43	95	35	900	NFN-15	G1, G3, G13
39	$t > \frac{3}{16}$	43	95	35	900	NFN-15	G1, G2, G3, G13
40	...	43	100	40	1650	NFN-15	G1, G3, G7, G13, T10
41	...	43	100	40	1650	NFN-15	G1, G3, G13, T10
42	...	43	100	40	1650	NFN-15	G1, G3, G7, G13, T10
43	$t > \frac{3}{4}$	45	85	30	1000	NFN-11	G1, G2, G3
44	$t > \frac{3}{4}$	45	85	30	1000	NFN-11	G1, G3
45	$\frac{5}{16} < t \leq \frac{3}{4}$	45	90	35	1000	NFN-11	G1, G2, G3, T10

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	25.3	25.3	25.3	25.3	25.3	25.3	...	...	...	...	...	...	...	...	...	...	...
2	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
3	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
4	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
5	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
6	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
7	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	8.0	7.0	6.0	...	...	...	...	...	...
8	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
9	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...
10	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
11	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
12	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
13	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...
14	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
15	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	...	...	...	...
16	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...
17	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
18	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
19	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
20	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	...	...	...	...	...	...
21	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	13.3	...	...	...	...	...	...
22	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	...	...	...	...	...	...
23	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	5.8	4.5
24	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	6.7	...	...	...	...	...	...
25	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	7.2	5.8	4.5
26	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	...	...	...	...	...	...
27	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	7.2	5.8	4.5
28	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	15.0	11.0	8.0
29	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	15.0	11.0	8.0
30	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	15.0	11.0	8.0
31	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	15.0	11.0	8.0
32	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	15.0	11.0	8.0
33	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	18.7	15.0	11.0	8.0
34	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	20.9	14.5	4.0
35	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	35.4	18.0	12.7	...
36	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	15.0	11.0	8.0
37	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.3	21.7	21.2	20.7	20.3	20.1	19.9	19.7	19.6
38	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.3	21.7	21.2	20.7	20.3	20.1	19.9	19.7	19.6
39	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.3	21.7	21.2	20.7	20.3	20.1	19.9	19.7	19.6
40	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.4	21.7	21.1	20.5	20.1	19.8	19.5	19.3	19.1	16.7
41	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.4	25.5	24.8	24.2	23.7	23.3	22.9	22.7	22.5	19.6
42	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.4	21.7	21.1	20.5	20.1	19.8	19.5	19.3	19.1	16.7
43	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.5	19.2	19.0	18.8	18.7	18.6	18.5
44	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.5	19.2	19.0	18.8	18.7	18.6	18.5
45	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8	21.7	20.0

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	3.7	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	3.7	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	3.7	3.0	2.4	2.0	1.5	1.2	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	16.6	16.4	16.4	14.9	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.6	1.3
41	19.5	19.3	19.3	17.5	14.1	11.3	9.3	7.7	6.1	4.8	3.8	3.0	2.4	1.9	1.5
42	16.6	16.4	16.4	14.9	12.0	9.6	7.9	6.5	5.2	4.1	3.2	2.6	2.0	1.6	1.3
43	18.4	18.3	...	...	...	...	...	...	...	...	...	...	...	...	...
44	18.4	18.3	...	...	...	...	...	...	...	...	...	...	...	...	...
45	19.5	18.9	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper
1	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
2	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...	N06007	Solution ann.
3	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...	N06007	Solution ann.
4	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...	N06007	Solution ann.
5	55Ni-21Cr-13.5Mo	Smls. & wld. fittings	SB-366	...	N06022	Solution ann.
6	55Ni-21Cr-13.5Mo	Forgings	SB-462	...	N06022	Solution ann.
7	55Ni-21Cr-13.5Mo	Forgings	SB-564	...	N06022	Solution ann.
8	55Ni-21Cr-13.5Mo	Rod	SB-574	...	N06022	Solution ann.
9	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...	N06022	Solution ann.
10	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...	N06022	Solution ann.
11	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...	N06022	Solution ann.
12	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...	N06022	Solution ann.
13	59Ni-23Cr-16Mo	Wld. fittings	SB-366	...	N06059	Solution ann.
14	59Ni-23Cr-16Mo	Smls. fittings	SB-366	...	N06059	Solution ann.
15	59Ni-23Cr-16Mo	Forged fittings	SB-462	...	N06059	Solution ann.
16	59Ni-23Cr-16Mo	Forgings	SB-564	...	N06059	Solution ann.
17	59Ni-23Cr-16Mo	Bar, rod	SB-574	...	N06059	Solution ann.
18	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...	N06059	Solution ann.
19	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.
20	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...	N06059	Solution ann.
21	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.
22	61Ni-16Mo-16Cr	Rod	SB-574	...	N06455	Solution ann.
23	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...	N06455	Solution ann.
24	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...	N06455	Solution ann.
25	61Ni-16Mo-16Cr	Smls. pipe & tube	SB-622	...	N06455	Solution ann.
26	61Ni-16Mo-16Cr	Wld. tube	SB-626	...	N06455	Solution ann.
27	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold worked/ann.
28	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed
29	72Ni-15Cr-8Fe	Bar, rod	SB-166	...	N06600	Annealed
30	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold worked/ann.
31	72Ni-15Cr-8Fe	Plate	SB-168	...	N06600	Annealed
32	72Ni-15Cr-8Fe	Forgings	SB-564	...	N06600	Annealed
33	72Ni-15Cr-8Fe	Wld. tube	SB-516	...	N06600	Cold drawn/ann.
34	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...	N06600	Cold drawn/ann.
35	35Ni-19Cr-1.25Si	Bar	SB-511	...	N08330	Annealed
36	35Ni-19Cr-1.25Si	Smls. & wld. pipe	SB-535	...	N08330	Annealed
37	35Ni-19Cr-1.25Si	Plate, sheet, strip	SB-536	...	N08330	Annealed
38	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08800	Annealed
39	42Fe-33Ni-21Cr	Smls. pipe & tube	SB-407	...	N08800	Annealed
40	42Fe-33Ni-21Cr	Plate	SB-409	...	N08800	Annealed
41	42Fe-33Ni-21Cr	Wld. pipe	SB-514	...	N08800	Annealed
42	42Fe-33Ni-21Cr	Wld. tube	SB-515	...	N08800	Annealed
43	42Fe-33Ni-21Cr	Forgings	SB-564	...	N08800	Annealed
44	42Fe-33Ni-21Cr	Bar, rod	SB-408	...	N08800	Hot fin.
45	42Fe-33Ni-21Cr	Smls. tube	SB-163	...	N08810	Annealed

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	$\frac{3}{16} < t \leq \frac{3}{4}$	45	90	35	1000	NFN-11	G1, G3, T10
2	...	45	90	35	1000	NFN-11	G1, G3, G7, T10
3	...	45	90	35	1000	NFN-11	G1, G3, T10
4	...	45	90	35	1000	NFN-11	G1, G3, G7, T10
5	...	43	100	45	1250	NFN-10	G1, G12, T13
6	...	43	100	45	1250	NFN-10	G1, G12, T13
7	...	43	100	45	1250	NFN-10	G1, G12, T13
8	...	43	100	45	1250	NFN-10	G1, G12, T13
9	...	43	100	45	1250	NFN-10	G1, G12, T13
10	...	43	100	45	1250	NFN-10	G1, G7, G12, T13
11	...	43	100	45	1250	NFN-10	G1, G12, T13
12	...	43	100	45	1250	NFN-10	G1, G7, G12, T13
13	...	43	100	45	1400	NFN-14	G1, G3, G7, G11, T14
14	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
15	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
16	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
17	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
18	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
19	...	43	100	45	1400	NFN-14	G1, G3, G7, G11, T14
20	...	43	100	45	1400	NFN-14	G1, G3, G11, T14
21	...	43	100	45	1400	NFN-14	G1, G3, G7, G11, T14
22	...	43	100	40	800	NFN-14	G1, G2, G3
23	...	43	100	40	800	NFN-14	G1, G3
24	...	43	100	40	800	NFN-14	G1, G3, G7
25	...	43	100	40	800	NFN-14	G1, G3
26	...	43	100	40	800	NFN-14	G1, G3, G7
27	O.D. > 5	43	80	30	1200	NFN-4	G1, G3, T10
28	...	43	80	35	1200	NFN-4	G1, G3, T10
29	...	43	80	35	1200	NFN-4	G1, G2, G3, T10
30	O.D. ≤ 5	43	80	35	1200	NFN-4	G1, G3, T10
31	...	43	80	35	1200	NFN-4	G1, G3, T10
32	...	43	80	35	1200	NFN-4	G1, G2, G3, T10
33	O.D. ≤ 4½	43	80	35	1200	NFN-4	G1, G3, G7, T10
34	O.D. ≤ 4½	43	80	35	1200	NFN-4	G1, G3, G7, T10
35	...	46	70	30	1650	NFN-13	G1, G2, G3, G13, H1, T11
36	...	46	70	30	1650	NFN-13	G1, G3, G7, G10, H2, T11
37	...	46	70	30	1650	NFN-13	G1, G3, G10, H2, T11
38	...	45	75	30	1500	NFN-8	G1, G3, T12
39	...	45	75	30	1500	NFN-8	G1, G3, T12
40	...	45	75	30	1500	NFN-8	G1, G3, T12
41	...	45	75	30	1500	NFN-8	G1, G3, G7, T12
42	...	45	75	30	1500	NFN-8	G1, G3, G7, T12
43	...	45	75	30	1500	NFN-8	G1, G2, G3, T12
44	...	45	75	30	1500	NFN-8	G1, G2, G3, T12
45	...	45	65	25	1650	NFN-9	G1, G3, G13, T14

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8	21.7	20.0
2	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.6	19.3	19.1	18.8	18.7	18.5	18.4	17.0
3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.1	22.7	22.4	22.2	22.0	21.8	21.7	20.0
4	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.6	19.3	19.1	18.8	18.7	18.5	18.4	17.0
5	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
6	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
7	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
8	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
9	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
10	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4	24.7	24.0	23.4	22.9	22.5	22.2	21.8	21.6	21.4
11	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	29.0	28.2	27.6	27.0	26.5	26.1	25.7	25.4	25.1
12	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4	24.7	24.0	23.4	22.9	22.5	22.2	21.8	21.6	21.4
13	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.2	24.6	23.9	23.3	22.8	22.2	21.7	21.2	20.8
14	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
15	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
16	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
17	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
18	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
19	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.2	24.6	23.9	23.3	22.8	22.2	21.7	21.2	20.8
20	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.7	28.9	28.2	27.5	26.8	26.1	25.5	25.0	24.5
21	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.2	24.6	23.9	23.3	22.8	22.2	21.7	21.2	20.8
22	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8	...	...
23	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8	...	...
24	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.5	22.2	21.9	...	...
25	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8	...	...
26	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	22.7	...	...
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	16.0
28	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	16.0
29	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	16.0
30	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	16.0
31	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	16.0
32	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	16.0
33	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	13.6
34	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	19.8	13.6
35	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.4	18.9	18.5	18.1	17.7	17.4	17.0	16.7
36	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.4	18.9	18.5	18.1	17.7	17.4	17.0	16.7
37	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	19.4	18.9	18.5	18.1	17.7	17.4	17.0	16.7
38	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
39	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
40	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
41	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0
42	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0
43	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
44	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0
45	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	19.5	18.9	...	...	...	...	...	...	...	...	...	...	...	...	...
2	16.6	16.1	...	...	...	...	...	...	...	...	...	...	...	...	...
3	19.5	18.9	...	...	...	...	...	...	...	...	...	...	...	...	...
4	16.6	16.1	...	...	...	...	...	...	...	...	...	...	...	...	...
5	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
6	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
7	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
8	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
9	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
10	21.2	21.0	20.5	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...
11	24.9	24.7	24.1	17.5	12.7	9.6	7.6	...	...	...	...	...	...	...	...
12	21.2	21.0	20.5	14.9	10.8	8.2	6.5	...	...	...	...	...	...	...	...
13	20.5	20.4	20.4	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...
14	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
15	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
16	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
17	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
18	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
19	20.5	20.4	20.4	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...
20	24.2	24.0	24.0	18.8	14.6	11.6	9.4	7.4	5.9	4.8	...	...	...	...	...
21	20.5	20.4	20.4	16.0	12.4	9.9	8.0	6.3	5.0	4.1	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
28	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
29	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
30	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
31	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
32	10.6	7.0	4.5	3.0	2.2	2.0	...	...	...	...	...	...	...	...	...
33	9.0	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...
34	9.0	6.0	3.8	2.6	1.9	1.7	...	...	...	...	...	...	...	...	...
35	16.1	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48
36	16.1	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48
37	16.1	12.7	10.0	7.8	6.0	4.7	3.8	3.1	2.4	1.8	1.5	1.1	0.90	0.68	0.48
38	20.0	18.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...
39	20.0	18.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...
40	20.0	18.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...
41	17.0	16.1	12.3	9.4	7.1	4.8	3.1	1.4	1.2	0.80	0.72	0.58	...	...	...
42	17.0	16.1	12.3	9.4	7.1	4.8	3.1	1.4	1.2	0.80	0.72	0.58	...	...	...
43	20.0	18.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...
44	20.0	18.9	14.5	11.1	8.3	5.6	3.6	1.7	1.4	0.94	0.85	0.68	...	...	...
45	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	1.0

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/Temper
1	42Fe-33Ni-21Cr	Smls. pipe & tube	SB-407	...	N08810	Annealed
2	42Fe-33Ni-21Cr	Bar, rod	SB-408	...	N08810	Annealed
3	42Fe-33Ni-21Cr	Plate	SB-409	...	N08810	Annealed
4	42Fe-33Ni-21Cr	Wld. pipe	SB-514	...	N08810	Annealed
5	42Fe-33Ni-21Cr	Wld. tube	SB-515	...	N08810	Annealed
6	42Fe-33Ni-21Cr	Forgings	SB-564	...	N08810	Annealed
7	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...	N08825	Annealed
8	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...	N08825	Annealed
9	42Ni-21.5Cr-3Mo-2.3Cu	Plate, sheet, strip	SB-424	...	N08825	Annealed
10	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...	N08825	Annealed
11	42Ni-21.5Cr-3Mo-2.3Cu	Forgings	SB-564	...	N08825	Annealed
12	62Ni-28Mo-5Fe	Plate	SB-333	...	N10001	Solution ann.
13	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...	N10001	Solution ann.
14	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...	N10001	Solution ann.
15	62Ni-28Mo-5Fe	Wld. tube	SB-626	...	N10001	Solution ann.
16	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Solution ann.
17	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Solution ann.
18	62Ni-28Mo-5Fe	Sheet, strip	SB-333	...	N10001	Solution ann.
19	70Ni-16Mo-7Cr-5Fe	Plate, sheet, strip	SB-434	...	N10003	Annealed
20	70Ni-16Mo-7Cr-5Fe	Rod	SB-573	...	N10003	Solution ann.
21	54Ni-16Mo-15Cr	Smls. fittings	SB-366	...	N10276	Solution ann.
22	54Ni-16Mo-15Cr	Wld. fittings	SB-366	...	N10276	Solution ann.
23	54Ni-16Mo-15Cr	Forgings	SB-462	...	N10276	Solution ann.
24	54Ni-16Mo-15Cr	Rod	SB-574	...	N10276	Solution ann.
25	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...	N10276	Solution ann.
26	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
27	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...	N10276	Solution ann.
28	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
29	65Ni-28Mo-2Fe	Plate, sheet, strip	SB-333	...	N10665	Solution ann.
30	65Ni-28Mo-2Fe	Rod	SB-335	...	N10665	Solution ann.
31	65Ni-28Mo-2Fe	Smls. fittings	SB-366	...	N10665	Solution ann.
32	65Ni-28Mo-2Fe	Wld. fittings	SB-366	...	N10665	Solution ann.
33	65Ni-28Mo-2Fe	Forgings	SB-462	...	N10665	Solution ann.
34	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Solution ann.
35	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...	N10665	Solution ann.
36	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Solution ann.
37	Ti	Plate, sheet, strip	SB-265	1	R50250	Annealed
38	Ti	Bar, billet	SB-348	1	R50250	Annealed
39	Ti	Forgings	SB-381	1	R50250	Annealed
40	Ti	Smls. tube	SB-338	1	R50250	Smls. ann.
41	Ti	Smls. pipe	SB-861	1	R50250	Smls. ann.
42	Ti	Wld. tube	SB-338	1	R50250	Wld. ann.
43	Ti	Wld. pipe	SB-862	1	R50250	Wld. ann.
44	Ti	Plate, sheet, strip	SB-265	2	R50400	Annealed
45	Ti	Bar, billet	SB-348	2	R50400	Annealed

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	...	45	65	25	1650	NFN-9	G1, G3, G13, T14
2	...	45	65	25	1650	NFN-9	G1, G2, G3, G13, T14
3	...	45	65	25	1650	NFN-9	G1, G3, G13, T14
4	...	45	65	25	1650	NFN-9	G1, G3, G7, G13, T14
5	...	45	65	25	1650	NFN-9	G1, G3, G7, G13, T14
6	...	45	65	25	1650	NFN-9	G1, G2, G3, G13, T14
7	...	45	85	35	1000	NFN-7	G1, G3
8	...	45	85	35	1000	NFN-7	G1, G3
9	...	45	85	35	1000	NFN-7	G1, G3
10	...	45	85	35	1000	NFN-7	G1, G2, G3
11	...	45	85	35	1000	NFN-7	G1, G3
12	$\frac{3}{16} \leq t \leq 2\frac{1}{2}$	44	100	45	800	NFN-5	G1, G3
13	...	44	100	45	800	NFN-5	G1, G3, G7
14	...	44	100	45	800	NFN-5	G1, G3
15	...	44	100	45	800	NFN-5	G1, G3, G7
16	$1\frac{1}{2} < t \leq 3\frac{1}{2}$	44	100	46	800	NFN-5	G1, G2, G3
17	$\frac{5}{16} \leq t \leq 1\frac{1}{2}$	44	115	46	800	NFN-5	G1, G2, G3
18	$t < \frac{3}{16}$	44	115	50	800	NFN-5	G1, G3
19	$t < 2\frac{1}{2}$	44	100	40	800	NFN-6	G3
20	...	44	100	40	800	NFN-6	G1, G2, G3
21	...	43	100	41	800	NFN-10	G1, G3
22	...	43	100	41	800	NFN-10	G1, G3, G7
23	...	43	100	41	800	NFN-10	G1, G3
24	...	43	100	41	1250	NFN-10	G1, G2, G3, T13
25	...	43	100	41	1250	NFN-10	G1, G3, T13
26	...	43	100	41	1250	NFN-10	G1, G3, G7, T13
27	...	43	100	41	1250	NFN-10	G1, G3, T13
28	...	43	100	41	1250	NFN-10	G1, G3, G7, T13
29	...	44	110	51	800	NFN-16	G1, G3
30	...	44	110	51	800	NFN-16	G1, G2, G3
31	...	44	110	51	800	NFN-16	G1, G3
32	...	44	110	51	800	NFN-16	G1, G3, G7
33	...	44	110	51	800	NFN-16	G1, G3
34	...	44	110	51	800	NFN-16	G1, G3, G7
35	...	44	110	51	800	NFN-16	G1, G3
36	...	44	110	51	800	NFN-16	G1, G3, G7
37	...	51	35	25	600	NFT-3	...
38	...	51	35	25	600	NFT-3	...
39	...	51	35	25	600	NFT-3	...
40	...	51	35	25	600	NFT-3	...
41	...	51	35	25	600	NFT-3	...
42	...	51	35	25	600	NFT-3	G7
43	...	51	35	25	600	NFT-3	G7
44	...	51	50	40	600	NFT-2	...
45	...	51	50	40	600	NFT-2	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
2	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
3	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
4	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
5	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.2	14.0	13.7	13.3	13.0	12.8	12.5	12.3
6	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.7	16.5	16.1	15.7	15.3	15.0	14.7	14.5
7	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0	22.9	22.8
8	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0	22.9	22.8
9	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0	22.9	22.8
10	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0	22.9	22.8
11	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.3	23.2	23.0	22.9	22.8
12	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	...	...
13	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4	...	...
14	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.9	...	...
15	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.5	25.4	...	...
16	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.5	...	...
17	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.7	30.5	...	...
18	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.3	33.2	...	...
19	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8	25.5	25.3	24.9	...	...
20	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.7	26.5	26.1	25.8	25.5	25.3	24.9	...	...
21	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1	...	...
22	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6	...	...
23	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1	...	...
24	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1	22.8	22.6
25	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1	22.8	22.6
26	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6	19.4	19.2
27	27.3	27.3	27.3	27.3	27.3	27.3	27.3	27.3	26.9	26.0	25.2	24.6	24.0	23.5	23.1	22.8	22.6
28	23.2	23.2	23.2	23.2	23.2	23.2	23.2	23.2	22.8	22.1	21.5	20.9	20.4	20.0	19.6	19.4	19.2
29	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	...	...
30	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	...	...
31	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	...	...
32	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	...	...
33	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	...	...
34	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	...	...
35	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	34.0	...	...
36	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	28.9	...	...
37	14.6	13.4	11.7	10.2	9.0	7.8	6.8	5.9	5.2	4.7	4.4	...	...	...	...	...	...
38	14.6	13.4	11.7	10.2	9.0	7.8	6.8	5.9	5.2	4.7	4.4	...	...	...	...	...	...
39	14.6	13.4	11.7	10.2	9.0	7.8	6.8	5.9	5.2	4.7	4.4	...	...	...	...	...	...
40	14.6	13.4	11.7	10.2	9.0	7.8	6.8	5.9	5.2	4.7	4.4	...	...	...	...	...	...
41	14.6	13.4	11.7	10.2	9.0	7.8	6.8	5.9	5.2	4.7	4.4	...	...	...	...	...	...
42	12.4	11.4	9.9	8.7	7.6	6.7	5.8	5.1	4.5	4.0	3.8	...	...	...	...	...	...
43	12.4	11.4	9.9	8.7	7.6	6.7	5.8	5.1	4.5	4.0	3.8	...	...	...	...	...	...
44	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
45	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	1.0
2	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	1.0
3	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	1.0
4	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.3	1.0	0.83
5	12.1	11.9	11.7	9.9	7.9	6.3	5.0	4.0	3.2	2.6	2.0	1.6	1.3	1.0	0.83
6	14.2	14.0	13.8	11.6	9.3	7.4	5.9	4.7	3.8	3.0	2.4	1.9	1.5	1.2	1.0
7	22.6	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...
8	22.6	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...
9	22.6	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...
10	22.6	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...
11	22.6	22.3	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	22.4	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...
25	22.4	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...
26	19.0	19.0	15.7	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...
27	22.4	22.3	18.5	15.0	12.2	9.8	7.8	...	...	...	...	...	...	...	...
28	19.0	19.0	15.7	12.8	10.4	8.3	6.6	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/Temper
1	Ti	Forgings	SB-381	2	R50400	Annealed
2	Ti	Smls. tube	SB-338	2	R50400	Smls. ann.
3	Ti	Smls. pipe	SB-861	2	R50400	Smls. ann.
4	Ti	Wld. tube	SB-338	2	R50400	Wld. ann.
5	Ti	Wld. pipe	SB-862	2	R50400	Wld. ann.
6	Ti	Plate, sheet, strip	SB-265	3	R50550	Annealed
7	Ti	Bar, billet	SB-348	3	R50550	Annealed
8	Ti	Forgings	SB-381	3	R50550	Annealed
9	Ti	Smls. tube	SB-338	3	R50550	Smls. ann.
10	Ti	Smls. pipe	SB-861	3	R50550	Smls. ann.
11	Ti	Wld. tube	SB-338	3	R50550	Wld. ann.
12	Ti	Wld. pipe	SB-862	3	R50550	Wld. ann.
13	Ti-Pd	Plate, sheet, strip	SB-265	7	R52400	Annealed
14	Ti-Pd	Bar, billet	SB-348	7	R52400	Annealed
15	Ti-Pd	Forgings	SB-381	F-7	R52400	Annealed
16	Ti-Pd	Smls. tube	SB-338	7	R52400	Smls. ann.
17	Ti-Pd	Smls. pipe	SB-861	7	R52400	Smls. ann.
18	Ti-Pd	Wld. tube	SB-338	7	R52400	Wld. ann.
19	Ti-Pd	Wld. pipe	SB-862	7	R52400	Wld. ann.
20	Ti-Pd	Plate, sheet, strip	SB-265	16	R52402	Annealed
21	Ti-Pd	Smls. tube	SB-338	16	R52402	Annealed
22	Ti-Pd	Wld. tube	SB-338	16	R52402	Annealed
23	Ti-Pd	Bar, billet	SB-348	16	R52402	Annealed
24	Ti-Pd	Forgings	SB-381	F-16	R52402	Annealed
25	Ti-0.3Mo-0.8Ni	Plate, sheet, strip	SB-265	12	R53400	Annealed
26	Ti-0.3Mo-0.8Ni	Bar, billet	SB-348	12	R53400	Annealed
27	Ti-0.3Mo-0.8Ni	Forgings	SB-381	F-12	R53400	Annealed
28	Ti-0.3Mo-0.8Ni	Smls. tube	SB-338	12	R53400	Smls. ann.
29	Ti-0.3Mo-0.8Ni	Smls. pipe	SB-861	12	R53400	Smls. ann.
30	Ti-0.3Mo-0.8Ni	Wld. tube	SB-338	12	R53400	Wld. ann.
31	Ti-0.3Mo-0.8Ni	Wld. pipe	SB-862	12	R53400	Wld. ann.

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Size/ Thickness, in.	P-No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Maximum Use Temperature, °F	External Pressure Chart No.	Notes
1	...	51	50	40	600	NFT-2	...
2	...	51	50	40	600	NFT-2	...
3	...	51	50	40	600	NFT-2	...
4	...	51	50	40	600	NFT-2	G7
5	...	51	50	40	600	NFT-2	G7
6	...	52	65	55	600	NFT-1	...
7	...	52	65	55	600	NFT-1	...
8	...	52	65	55	600	NFT-1	...
9	...	52	65	55	600	NFT-1	...
10	...	52	65	55	600	NFT-1	...
11	...	52	65	55	600	NFT-1	G7
12	...	52	65	55	600	NFT-1	G7
13	...	51	50	40	600	NFT-2	...
14	...	51	50	40	600	NFT-2	...
15	...	51	50	40	600	NFT-2	...
16	...	51	50	40	600	NFT-2	...
17	...	51	50	40	600	NFT-2	...
18	...	51	50	40	600	NFT-2	G7
19	...	51	50	40	600	NFT-2	G7
20	...	51	50	40	600	NFT-2	...
21	...	51	50	40	600	NFT-2	...
22	...	51	50	40	600	NFT-2	...
23	...	51	50	40	600	NFT-2	...
24	...	51	50	40	600	NFT-2	...
25	...	52	70	50	600	NFT-5	...
26	...	52	70	50	600	NFT-5	...
27	...	52	70	50	600	NFT-5	...
28	...	52	70	50	600	NFT-5	...
29	...	52	70	50	600	NFT-5	...
30	...	52	70	50	600	NFT-5	G7
31	...	52	70	50	600	NFT-5	G7

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding																	
Line No.	100	150	200	250	300	350	400	450	500	550	600	650	700	750	800	850	900
1	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
2	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
3	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
4	17.7	17.7	17.7	16.2	14.5	12.8	11.1	9.6	8.4	7.4	6.8	...	...	...	...	...	...
5	17.7	17.7	17.7	16.2	14.5	12.8	11.1	9.6	8.4	7.4	6.8	...	...	...	...	...	...
6	27.1	27.1	27.1	26.5	23.8	21.3	19.1	17.0	15.0	13.2	11.4	...	...	...	...	...	...
7	27.1	27.1	27.1	26.5	23.8	21.3	19.1	17.0	15.0	13.2	11.4	...	...	...	...	...	...
8	27.1	27.1	27.1	26.5	23.8	21.3	19.1	17.0	15.0	13.2	11.4	...	...	...	...	...	...
9	27.1	27.1	27.1	26.5	23.8	21.3	19.1	17.0	15.0	13.2	11.4	...	...	...	...	...	...
10	27.1	27.1	27.1	26.5	23.8	21.3	19.1	17.0	15.0	13.2	11.4	...	...	...	...	...	...
11	23.0	23.0	23.0	22.5	20.3	18.1	16.2	14.4	12.8	11.2	9.7	...	...	...	...	...	...
12	23.0	23.0	23.0	22.5	20.3	18.1	16.2	14.4	12.8	11.2	9.7	...	...	...	...	...	...
13	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
14	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
15	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
16	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
17	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
18	17.7	17.7	17.7	16.2	14.5	12.8	11.1	9.6	8.4	7.4	6.8	...	...	...	...	...	...
19	17.7	17.7	17.7	16.2	14.5	12.8	11.1	9.6	8.4	7.4	6.8	...	...	...	...	...	...
20	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
21	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
22	17.7	17.7	17.7	16.2	14.5	12.8	11.1	9.6	8.4	7.4	6.8	...	...	...	...	...	...
23	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
24	20.8	20.8	20.8	19.1	17.1	15.1	13.1	11.3	9.8	8.7	8.0	...	...	...	...	...	...
25	29.2	29.2	27.8	25.3	23.1	21.3	19.8	18.5	17.3	16.4	16.1	...	...	...	...	...	...
26	29.2	29.2	27.8	25.3	23.1	21.3	19.8	18.5	17.3	16.4	16.1	...	...	...	...	...	...
27	29.2	29.2	27.8	25.3	23.1	21.3	19.8	18.5	17.3	16.4	16.1	...	...	...	...	...	...
28	29.2	29.2	27.8	25.3	23.1	21.3	19.8	18.5	17.3	16.4	16.1	...	...	...	...	...	...
29	29.2	29.2	27.8	25.3	23.1	21.3	19.8	18.5	17.3	16.4	16.1	...	...	...	...	...	...
30	24.8	24.8	23.7	21.5	19.7	18.1	16.9	15.7	14.7	13.9	13.6	...	...	...	...	...	...
31	24.8	24.8	23.7	21.5	19.7	18.1	16.9	15.7	14.7	13.9	13.6	...	...	...	...	...	...

Table 5B (Cont'd)
Section VIII, Division 2, Class 2
Maximum Allowable Stress Values, S, for Nonferrous Materials

Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding															
Line No.	950	1000	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
1	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...

NOTES TO TABLE 5B**GENERAL NOTES**

- (a) The following abbreviations are used: ann., annealed; extr., extruded; fin., finished; rel., relieved; Smls., Seamless; and Wld., Welded.
- (b) An alternative typeface is used for stress values obtained from time-dependent properties (see Notes T1 through T14).
- (c) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SB-407/SB-407M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SB-407 Grade N08800 shall be used when SB-407M Grade N08800 is used in construction.
- (d) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (e) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (f) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES - GENERAL REQUIREMENTS

- G1 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed $66\frac{2}{3}\%$ but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction. Table Y-2 lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give allowable stress values that will result in lower levels of permanent strain.
- G2 Use of external pressure charts for material in the form of bar stock is permitted for stiffening rings only.
- G3 Maximum allowable stress values for 100°F may be used at temperatures down to -325°F without additional specification requirements.
- G4 Maximum allowable stress values for 100°F may be used at temperatures down to -452°F without additional specification requirements.
- G5 Maximum temperature for external pressure design not to exceed 350°F.
- G6 These alloys are occasionally subject to the hazard of stress corrosion cracking. Even though they are suitable for engineering use under a wide variety of corrosive conditions, with no particular hazard with respect to stress corrosion, the supplier of the material should be consulted before applying them.
- G7 A joint efficiency factor of 0.85 has been applied in arriving at the maximum allowable stress values for this material.
- G8 For stress relieved tempers (T451, T4510, T4511, T651, T6510, T6511), stress values for materials in the basic temper shall be used.
- G9 Copper-silicon alloys are not always suitable when exposed to certain media and high temperature, particularly steam above 212°F. The user should satisfy him/herself that the alloy selected is satisfactory for the service for which it is to be used.
- G10 At temperatures over 1000°F, these stress values apply only when the carbon is 0.04% or higher.
- G11 This alloy is subject to severe loss of impact strength at room temperatures after exposure in the range of 1000°F to 1400°F.
- G12 Alloy N06022 in the solution annealed condition is subject to severe loss of impact strength at room temperatures after exposure in the range of 1000°F to 1250°F.
- G13 Creep-fatigue, thermal ratcheting, and environmental effects are increasingly significant failure modes at temperatures in excess of 1500°F and shall be considered in the design.

NOTES - HEAT TREATMENT REQUIREMENTS

- H1 For temperatures above 1000°F, these stress values may be used only if the material is annealed at a minimum temperature of 1900°F and has a carbon content of 0.04% or higher.
- H2 For temperatures above 1000°F, these stress values may be used only if the material is heat treated by heating it to a minimum temperature of 1900°F and quenching in water or rapidly cooling by other means.

NOTES - TIME-DEPENDENT PROPERTIES

- T1 Allowable stresses for temperatures of 250°F and above are values obtained from time-dependent properties.
- T2 Allowable stresses for temperatures of 300°F and above are values obtained from time-dependent properties.
- T3 Allowable stresses for temperatures of 350°F and above are values obtained from time-dependent properties.
- T4 Allowable stresses for temperatures of 400°F and above are values obtained from time-dependent properties.
- T5 Allowable stresses for temperatures of 500°F and above are values obtained from time-dependent properties.
- T6 Allowable stresses for temperatures of 700°F and above are values obtained from time-dependent properties.
- T7 Allowable stresses for temperatures of 750°F and above are values obtained from time-dependent properties.
- T8 Allowable stresses for temperatures of 800°F and above are values obtained from time-dependent properties.
- T9 Allowable stresses for temperatures of 850°F and above are values obtained from time-dependent properties.
- T10 Allowable stresses for temperatures of 900°F and above are values obtained from time-dependent properties.
- T11 Allowable stresses for temperatures of 950°F and above are values obtained from time-dependent properties.
- T12 Allowable stresses for temperatures of 1000°F and above are values obtained from time-dependent properties.
- T13 Allowable stresses for temperatures of 1050°F and above are values obtained from time-dependent properties.

NOTES TO TABLE 5B (CONT'D)

NOTES – TIME-DEPENDENT PROPERTIES (CONT'D)

T14 Allowable stresses for temperatures of 1100°F and above are values obtained from time-dependent properties.

NOTES – WELDING REQUIREMENTS

W1 Welding except for seal welds is not permitted.

W2 For welded construction, stress values for material at 0 temper shall be used.

W3 The stress values given for this material are not applicable when either welding or thermal cutting is employed.

W4 Use NFA-12 when welded with 5356 or 5556 filler metal, all thicknesses, or 4043 or 5554 filler metal, thickness $\leq \frac{3}{8}$ in. Use NFA-13 when welded with 4043 or 5554 filler metal, thickness $> \frac{3}{8}$ in.

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table 6A
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Bar, stay	SA-675	45	...	...	...	1	1
2	Carbon steel	Plate	SA-285	A	K01700	...	...	1	1
3	Carbon steel	Sheet	SA-414	A	K01501	...	...	1	1
4	Carbon steel	Wld. pipe & tube	SA-178	A	K01200	...	...	1	1
5	Carbon steel	Smls. pipe & tube	SA-192	...	K01201	...	...	1	1
6	Carbon steel	Smls. pipe & tube	SA-53	A	K02504	...	...	1	1
7	Carbon steel	Wld. pipe & tube	SA-53	A	K02504	...	...	1	1
8	Carbon steel	Butt-wld. pipe	SA-53	F	...	...	...	1	1
9	Carbon steel	Smls. pipe & tube	SA-106	A	K02501	...	...	1	1
10	Carbon steel	Wld. pipe & tube	SA-135	A	...	...	...	1	1
11	Carbon steel	Bar, stay	SA-675	50	...	...	...	1	1
12	Carbon steel	Plate	SA-285	B	K02200	...	...	1	1
13	Carbon steel	Sheet	SA-414	B	K02201	...	...	1	1
14	Carbon steel	Plate	SA/EN 10025-2	S235JR	...	...	$t \leq 4$	1	1
15	Carbon steel	Wld. pipe & tube	SA/EN 10217-1	P235TR2	...	...	$t \leq 1\frac{9}{16}$	1	1
16	Carbon steel	Bar, stay	SA-675	55	...	...	...	1	1
17	Carbon steel	Plate	SA-285	C	K02801	...	...	1	1
18	Carbon steel	Plate	SA-516	55	K01800	...	...	1	1
19	Carbon steel	Sheet	SA-414	C	K02503	...	...	1	1
20	Carbon steel	Plate	SA-36	...	K02600	...	...	1	1
21	Carbon steel	Bar, stay	SA-36	...	K02600	...	...	1	1
22	Carbon steel	Forgings	SA-181	...	K03502	60	...	1	1
23	Carbon steel	Castings	SA-216	WCA	J02502	...	...	1	1
24	Carbon steel	Forgings	SA-266	1	K03506	...	...	1	1
25	Carbon steel	Bar, stay	SA-675	60	...	...	...	1	1
26	Carbon steel	Plate	SA-515	60	K02401	...	...	1	1
27	Carbon steel	Plate	SA-516	60	K02100	...	...	1	1
28	Carbon steel	Smls. pipe & tube	SA-53	B	K03005	...	...	1	1
29	Carbon steel	Wld. pipe & tube	SA-53	B	K03005	...	...	1	1
30	Carbon steel	Smls. pipe & tube	SA-106	B	K03006	...	...	1	1
31	Carbon steel	Wld. pipe & tube	SA-135	B	...	...	...	1	1
(25) 32	Carbon steel	Smls. & wld. ftgs.	SA-234	WPB	K03506	...	...	1	1
33	Carbon steel	Sheet	SA-414	D	K02505	...	...	1	1
34	Carbon steel	Wld. pipe & tube	SA-178	C	K03503	...	...	1	1
35	Carbon steel	Smls. pipe & tube	SA-210	A-1	K02707	...	...	1	1
36	Carbon steel	Bolting	SA-307	B	...	...	...	...	...
37	Carbon steel	Bar, stay	SA-675	65	...	...	...	1	1
38	Carbon steel	Plate	SA-515	65	K02800	...	...	1	1
39	Carbon steel	Plate	SA-516	65	K02403	...	...	1	1
40	Carbon steel	Sheet	SA-414	E	K02704	...	...	1	1
41	Carbon steel	Plate	SA/CSA-G40.21	44W	...	...	...	1	1
42	Carbon steel	Plate	SA/CSA-G40.21	50W	...	...	...	1	1
43	Carbon steel	Bolting	SA-311	1018	...	A	...	...	...
44	Carbon steel	Plate	SA-455	...	K03300	...	$0.58 < t \leq \frac{3}{4}$	1	2
45	Carbon steel	Bar, stay	SA-675	70	...	...	...	1	2

Table 6A
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
					100	150	200	250	300	350	400	450	500	
1	45	22.5	...	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	
2	45	24	CS-1	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	
3	45	25	CS-1	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	
4	47	26	CS-2	G3, G4	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	8.0	
5	47	26	CS-1	G3	9.4	9.4	9.4	9.4	9.4	9.4	9.4	9.4	9.4	
6	48	30	CS-2	G4	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	
7	48	30	CS-2	...	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	
8	48	30	CS-2	G5	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	
9	48	30	CS-2	...	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	
10	48	30	CS-2	G4	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	8.2	
11	50	25	...	...	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	
12	50	27	CS-1	...	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	
13	50	30	CS-2	...	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	
14	52	31	CS-2	...	10.4	...	10.4	...	10.4	...	10.4	...	10.4	
15	52	33	CS-2	G4	8.8	...	8.8	...	8.8	...	8.8	...	8.8	
16	55	27.5	...	...	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	
17	55	30	CS-2	...	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	
18	55	30	CS-2	...	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	
19	55	33	CS-2	...	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	11.0	
20	58	36	CS-2	G1, G2	11.6	11.6	11.6	11.6	11.6	11.6	11.6	11.6	11.6	
21	58	36	...	G1	11.6	11.6	11.6	11.6	11.6	11.6	11.6	11.6	11.6	
22	60	30	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
23	60	30	CS-2	G6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	
24	60	30	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
25	60	30	...	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
26	60	32	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
27	60	32	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
28	60	35	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
29	60	35	CS-2	G4	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	
30	60	35	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
31	60	35	CS-2	G4	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	
32	60	35	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
33	60	35	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
34	60	37	CS-1	...	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	
35	60	37	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	
36	60	...	...	G7	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	7.0	
37	65	32.5	...	...	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	
38	65	35	CS-2	...	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	
39	65	35	CS-2	...	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	
40	65	38	CS-2	...	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	
41	65	44	CS-2	...	13.0	...	13.0	...	13.0	...	13.0	...	13.0	
42	65	50	CS-2	...	13.0	...	13.0	...	13.0	...	13.0	...	13.0	
43	65	55	...	G8, W1, W3	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	13.0	
44	70	35	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
45	70	35	...	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Cond./Temper	Size/Thickness, in.	P-No.	Group No.
1	Carbon steel	Forgings	SA-105	...	K03504	...	...	1	2
2	Carbon steel	Forgings	SA-181	...	K03502	70	...	1	2
3	Carbon steel	Castings	SA-216	WCB	J03002	...	...	1	2
4	Carbon steel	Forgings	SA-266	2	K03506	...	...	1	2
5	Carbon steel	Plate	SA-515	70	K03101	...	...	1	2
6	Carbon steel	Plate	SA-516	70	K02700	...	...	1	2
7	Carbon steel	Smls. pipe & tube	SA-106	C	K03501	...	...	1	2
8	Carbon steel	Sheet	SA-414	F	K03102	...	...	1	2
9	Carbon steel	Bolting	SA-311	1018	...	A	...	...	...
10	Carbon steel	Plate	SA-455	...	K03300	...	$\frac{3}{8} < t \leq 0.58$	1	2
11	Carbon steel	Forgings	SA-266	3	K05001	...	...	1	2
12	Carbon steel	Plate	SA-455	...	K03300	...	$t \leq \frac{3}{8}$	1	2
13	Carbon steel	Sheet	SA-414	G	K03103	...	...	1	2
14	Carbon steel	Bolting	SA-311	1035	...	A	...	...	...
15	Carbon steel	Bolting	SA-311	1035	...	A	...	...	...
16	Carbon steel	Bolting	SA-311	1045	...	A	...	...	...
17	Carbon steel	Bolting	SA-311	1045	...	A	...	...	...
18	Carbon steel	Bolting	SA-311	1050	...	A	...	...	...
19	Carbon steel	Bolting	SA-311	1050	...	A	...	...	...
(25) 20	Carbon steel	Bolting	SA-325	1	...	...	$1 < t \leq 1\frac{1}{2}$	...	...
21	Carbon steel	Bolting	SA-311	1045	...	B	...	...	...
(25) 22	Carbon steel	Bolting	SA-325	1	...	...	$\frac{1}{2} \leq t \leq 1$	...	...
23	Carbon steel	Bolting	SA-354	BC	...	...	...	...	...
24	Carbon steel	Bolting	SA-354	BD	...	...	...	...	...
(25) 25	...	...	...	...	...	...	...	...	...
26	1Cr-0.2Mo	Bolting	SA-193	B7	G41400	...	...	...	...
27	1Cr-0.2Mo	Bolting	SA-320	L7	...	...	...	...	...
28	5Cr- $\frac{1}{2}$ Mo	Bolting	SA-193	B5	K50100	...	...	...	...
29	18Cr-2Mo	Plate	SA-240	...	S44400	...	$t \leq \frac{3}{8}$	7	2
30	18Cr-2Mo	Tube	SA-268	...	S44400	...	$t \leq \frac{3}{8}$	7	2
(25) 31	18Cr-2Mo	Bar	SA-479	CS-2	S44400	...	$t \leq \frac{3}{8}$	7	2
(25) 32	18Cr-Ti	Plate	SA-240	439	S43035	...	$t \leq \frac{3}{8}$	7	2
(25) 33	18Cr-Ti	Plate	SA-240	...	S43932	...	$t \leq \frac{3}{8}$	7	2
(25) 34	18Cr-Ti	Tube	SA-268	TP439	S43035	...	$t \leq \frac{3}{8}$	7	2
(25) 35	18Cr-Ti	Bar	SA-479	439	S43035	...	$t \leq \frac{3}{8}$	7	2
36	29Cr-4Mo	Smls. tube	SA-268	29-4	S44700	...	...	10J	1
37	29Cr-4Mo	Wld. tube	SA-268	29-4	S44700	...	...	10J	1
38	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-320	L43	G43400	...	$t \leq 4$	...	...
39	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...	...	8	1
40	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...	...	8	1
41	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...	...	8	1
42	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...	...	8	1
43	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	...	...	8	1
44	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	...	...	8	1
45	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	...	...	8	1

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
					100	150	200	250	300	350	400	450	500	
1	70	36	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
2	70	36	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
3	70	36	CS-2	G6	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	11.2	
4	70	36	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
5	70	38	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
6	70	38	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
7	70	40	CS-2	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
8	70	42	CS-3	...	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
9	70	60	...	G8, W1, W2	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	
10	73	37	CS-2	...	14.6	14.6	14.6	14.6	14.6	14.6	14.6	14.6	14.6	
11	75	37.5	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	
12	75	38	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	
13	75	45	CS-3	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	
14	80	70	...	G8, W1, W3	16.0	16.0	16.0	16.0	16.0	16.0	16.0	16.0	16.0	
15	85	75	...	G8, W1, W2	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	
16	90	80	...	G8, W1, W3	18.0	18.0	18.0	18.0	18.0	18.0	18.0	18.0	18.0	
17	95	85	...	G8, W1, W2	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	
18	95	85	...	G8, W1, W3	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	19.0	
19	100	90	...	G8, W1, W2	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	
20	105	81	...	G7	20.2	20.2	20.2	20.2	20.2	20.2	20.2	20.2	20.2	
21	115	100	...	G8, W1, W2	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0	
22	120	92	...	G7	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0	23.0	
23	125	109	...	G7	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	
24	150	130	...	G7	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	30.0	
25	...	...	...	...	...	...	...	...	...	...	...	...	...	
26	100	75	...	G7	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8	
27	125	105	...	G7	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	
28	100	80	...	G7	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	20.0	
29	60	40	CS-2	...	12.0	12.0	12.0	11.8	11.6	11.5	11.4	11.2	11.1	
30	60	40	CS-2	...	12.0	12.0	12.0	11.8	11.6	11.5	11.4	11.2	11.1	
31	60	45	...	...	12.0	12.0	12.0	11.8	11.6	11.5	11.4	11.2	11.1	
32	60	30	...	...	12.0	12.0	12.0	11.8	11.6	11.4	11.3	11.2	11.0	
33	60	30	CS-2	...	12.0	12.0	12.0	11.8	11.6	11.4	11.3	11.2	11.0	
34	60	30	CS-2	...	12.0	12.0	12.0	11.8	11.6	11.4	11.3	11.2	11.0	
35	70	40	CS-2	...	14.0	14.0	14.0	13.8	13.5	13.3	13.2	13.0	12.9	
36	80	60	HA-6	G12	15.0	15.0	15.0	14.7	14.5	14.4	14.4	14.4	14.4	
37	80	60	HA-6	G4, G12	12.8	12.8	12.7	12.5	12.3	12.2	12.2	12.2	12.2	
38	125	105	...	G7	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	25.0	
39	70	25	HA-4	G9, G11	14.0	14.0	13.6	13.1	12.7	12.1	11.7	11.3	10.9	
40	70	25	HA-4	G9, G10, G11	14.0	14.0	13.6	13.1	12.7	12.1	11.7	11.3	10.9	
41	70	25	HA-4	G9	14.0	14.0	13.6	13.1	12.7	12.1	11.7	11.3	10.9	
42	70	25	HA-4	G4, G9, G10, G11	11.9	11.9	11.6	11.2	10.8	10.3	9.9	9.6	9.3	
43	70	25	HA-4	G9, G11	14.0	14.0	13.6	13.1	12.7	12.1	11.7	11.3	10.9	
44	70	25	HA-4	G4, G9, G11	11.9	11.9	11.6	11.2	10.8	10.3	9.9	9.6	9.3	
45	70	25	HA-4	G9, G10	14.0	14.0	13.6	13.1	12.7	12.1	11.7	11.3	10.9	

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Cond./Temper	Size/Thickness, in.	P-No.	Group No.
1	16Cr-12Ni-2Mo	Castings	SA-351	CF3M	J92800	...	$t \geq 0.10$	8	1
2	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...	...	8	1
3	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...	...	8	1
4	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...	...	8	1
5	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...	...	8	1
6	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316	S31600	...	...	8	1
7	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	...	...	8	1
8	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	...	...	8	1
9	16Cr-12Ni-2Mo-Ti	Smls. tube	SA-213	TP316Ti	S31635	...	...	8	1
10	16Cr-12Ni-2Mo-Ti	Plate	SA-240	316Ti	S31635	...	...	8	1
11	16Cr-12Ni-2Mo-Ti	Smls. pipe	SA-312	TP316Ti	S31635	...	...	8	1
12	16Cr-12Ni-2Mo-Ti	Wld. pipe	SA-312	TP316Ti	S31635	...	...	8	1
(25) 13	16Cr-12Ni-2Mo-Ti	Plate	SA/EN 10088-2	X6CrNiMoTi17-12-2	...	...	$t \leq \frac{5}{16}$	8	1
14	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...	$t \leq 5$	8	1
15	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...	...	8	1
16	18Cr-8Ni	Plate	SA-240	304L	S30403	...	...	8	1
17	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...	...	8	1
18	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	...	...	8	1
19	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	...	...	8	1
20	18Cr-8Ni	Bar	SA-479	304L	S30403	...	...	8	1
21	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	$t \leq 5$	8	1
22	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...	...	8	1
23	18Cr-8Ni	Plate	SA-240	304	S30400	...	...	8	1
24	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...	...	8	1
25	18Cr-8Ni	Smls. pipe	SA-312	TP304	S30400	...	...	8	1
26	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	...	...	8	1
27	18Cr-8Ni	Bar	SA-479	304	S30400	...	...	8	1
28	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...	$t \geq 0.10$	8	1
(25) 29	...	...	...	...	...	...	...	...	...
30	20Cr-10Ni	Bar	SA-479	ER308	S30880	...	...	...	...
31	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...	S32101	...	$t > \frac{3}{16}$	10H	1
32	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	S32101	...	$t > \frac{3}{16}$	10H	1
33	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	S32101	...	$t > \frac{3}{16}$	10H	1
34	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	S32101	...	$t > \frac{3}{16}$	10H	1
35	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	S32101	...	$t > \frac{3}{16}$	10H	1
36	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...	S32101	...	$t \leq \frac{3}{16}$	10H	1
37	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	S32101	...	$t \leq \frac{3}{16}$	10H	1
38	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	S32101	...	$t \leq \frac{3}{16}$	10H	1
39	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	S32101	...	$t \leq \frac{3}{16}$	10H	1
40	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	S32101	...	$t \leq \frac{3}{16}$	10H	1
41	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...	...	10H	1
42	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S31803	...	...	10H	1
43	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S31803	...	...	10H	1
44	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S31803	...	...	10H	1
45	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S31803	...	...	10H	1

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
					100	150	200	250	300	350	400	450	500	
1	70	30	...	G6, G9	11.2	11.2	11.2	11.0	10.9	10.8	10.8	10.7	10.7	
2	75	30	HA-2	G9, G11	15.0	15.0	15.0	14.8	14.6	14.4	14.3	13.8	13.3	
3	75	30	HA-2	G9, G10, G11	15.0	15.0	15.0	14.8	14.6	14.4	14.3	13.8	13.3	
4	75	30	HA-2	G9	15.0	15.0	15.0	14.8	14.6	14.4	14.3	13.8	13.3	
5	75	30	HA-2	G4, G9, G10, G11	12.8	12.8	12.8	12.6	12.4	12.3	12.1	11.7	11.3	
6	75	30	HA-2	G9, G11	15.0	15.0	15.0	14.8	14.6	14.4	14.3	13.8	13.3	
7	75	30	HA-2	G4, G9, G11	12.8	12.8	12.8	12.6	12.4	12.3	12.1	11.7	11.3	
8	75	30	HA-2	G7, G9, G13	15.0	15.0	15.0	14.8	14.6	14.4	14.3	13.8	13.3	
9	75	30	HA-2	G9	15.0	14.8	14.0	13.3	12.7	12.3	12.1	11.9	11.8	
10	75	30	HA-2	G9	15.0	14.8	14.0	13.3	12.7	12.3	12.1	11.9	11.8	
11	75	30	HA-2	G9	15.0	14.8	14.0	13.3	12.7	12.3	12.1	11.9	11.8	
12	75	30	HA-2	G4, G9	12.7	12.6	11.9	11.3	10.8	10.5	10.3	10.1	10.0	
13	78.5	35	HA-2	G9, G14	15.0	14.8	14.0	13.3	12.7	12.3	12.1	11.9	11.8	
14	70	25	HA-3	G9, G11	14.0	13.9	13.2	12.7	12.2	12.0	11.7	11.3	10.9	
15	70	25	HA-3	G9, G10, G11	14.0	13.9	13.2	12.7	12.2	12.0	11.7	11.3	10.9	
16	70	25	HA-3	G9	14.0	13.9	13.2	12.7	12.2	12.0	11.7	11.3	10.9	
17	70	25	HA-3	G4, G9, G10, G11	11.9	11.8	11.2	10.8	10.4	10.2	9.9	9.6	9.3	
18	70	25	HA-3	G9, G11	14.0	13.9	13.2	12.7	12.2	12.0	11.7	11.3	10.9	
19	70	25	HA-3	G4, G9, G11	11.9	11.8	11.2	10.8	10.4	10.2	9.9	9.6	9.3	
20	70	25	HA-3	G9, G10	14.0	13.9	13.2	12.7	12.2	12.0	11.7	11.3	10.9	
21	75	30	HA-1	G9, G11	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
22	75	30	HA-1	G9, G10, G11	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
23	75	30	HA-1	G9	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
24	75	30	HA-1	G4, G9, G10, G11	12.8	12.7	12.1	11.6	11.3	11.0	10.9	10.8	10.8	
25	75	30	HA-1	G9, G11	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
26	75	30	HA-1	G4, G9, G11	12.8	12.7	12.1	11.6	11.3	11.0	10.9	10.8	10.8	
27	75	30	HA-1	G7, G9, G13	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
28	70	30	...	G6, G9	11.2	11.2	10.7	10.2	9.8	9.5	9.3	9.1	9.0	
29	...	...	...	...	...	...	...	...	...	...	...	...	...	
30	75	30	HA-2	G7, G9, G13	15.0	15.0	14.2	13.6	13.2	13.0	12.8	12.7	12.7	
31	94	65	HA-5	...	18.8	18.8	18.8	18.5	17.9	17.5	17.3	17.2	17.2	
32	94	65	HA-5	...	18.8	18.8	18.8	18.5	17.9	17.5	17.3	17.2	17.2	
33	94	65	HA-5	...	16.0	16.0	16.0	15.7	15.2	14.9	14.7	14.6	14.6	
34	94	65	HA-5	...	18.8	18.8	18.8	18.5	17.9	17.5	17.3	17.2	17.2	
35	94	65	HA-5	...	16.0	16.0	16.0	15.7	15.2	14.9	14.7	14.6	14.6	
36	101	77	HA-5	...	20.2	20.2	20.2	19.8	19.3	18.8	18.6	18.5	18.5	
37	101	77	HA-5	...	20.2	20.2	20.2	19.8	19.3	18.8	18.6	18.5	18.5	
38	101	77	HA-5	...	17.2	17.2	17.2	16.9	16.4	16.0	15.8	15.7	15.7	
39	101	77	HA-5	...	20.2	20.2	20.2	19.8	19.3	18.8	18.6	18.5	18.5	
40	101	77	HA-5	...	17.2	17.2	17.2	16.9	16.4	16.0	15.8	15.7	15.7	
41	90	65	HA-5	...	18.0	18.0	18.0	...	17.4	...	16.7	...	16.3	
42	90	65	HA-5	...	18.0	18.0	18.0	...	17.4	...	16.7	...	16.3	
43	90	65	HA-5	...	15.3	15.3	15.3	...	14.8	...	14.2	...	13.9	
44	90	65	HA-5	...	18.0	18.0	18.0	...	17.4	...	16.7	...	16.3	
45	90	65	HA-5	...	15.3	15.3	15.3	...	14.8	...	14.2	...	13.9	

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line					Alloy	Class/	Size/		Group
No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Design./ UNS No.	Cond./ Temper	Thickness, in.	P-No.	No.
(25)	1	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S32205	...	10H	1
(25)	2	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S32205	...	10H	1
(25)	3	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S32205	...	10H	1
(25)	4	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S32205	...	10H	1
(25)	5	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S32205	...	10H	1
	6	23Cr-12Ni	Bar	SA-479	309S	S30908	...	8	2
	7	23Cr-12Ni	Bar	SA-479	309H	S30909	...	8	2
	8	25Cr-20Ni	Bar	SA-479	310S	S31008	...	8	2
	9	44Fe-25Ni-21Cr-Mo	Plate	SA-240	904L	N08904	...	45	...
(25)	10	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...	45	...

Table 6A (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Ferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
					100	150	200	250	300	350	400	450	500	
1	95	65	HA-5	...	19.0	19.0	19.0	18.7	18.3	18.0	17.6	17.4	17.2	
2	95	65	HA-5	...	19.0	19.0	19.0	18.7	18.3	18.0	17.6	17.4	17.2	
3	95	65	HA-5	G4	16.2	16.2	16.2	15.9	15.6	15.3	15.0	14.8	14.6	
4	95	70	HA-5	...	19.0	19.0	19.0	18.7	18.3	18.0	17.6	17.4	17.2	
5	95	70	HA-5	G4	16.2	16.2	16.2	15.9	15.6	15.3	15.0	14.8	14.6	
6	75	30	HA-2	G7, G9, G13	15.0	15.0	15.0	15.0	14.9	14.8	14.6	14.5	14.3	
7	75	30	HA-2	G7, G9, G13	15.0	15.0	15.0	15.0	14.9	14.8	14.6	14.5	14.3	
8	75	30	HA-2	G7, G9, G13	15.0	15.0	15.0	15.0	14.9	14.8	14.6	14.5	14.3	
9	71	31	NFN-9	...	14.2	14.2	14.2	13.9	13.6	13.3	13.1	12.9	12.7	
10	65	25	NFN-9	G9	13.0	13.0	13.0	13.0	13.0	13.0	12.9	12.8	12.8	

NOTES TO TABLE 6A**GENERAL NOTES**

- (a) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (b) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.
- (c) The following abbreviations are used: Smls., Seamless; and Wld., Welded.

NOTES – GENERAL REQUIREMENTS

- G1 These allowable stress values also apply to structural shapes.
- G2 SA/CSA-G40.21 as specified in ASME BPVC, Section II, Part A, grade 38W, may be used in lieu of SA-36 for plates and bars not exceeding $\frac{3}{4}$ in.
- G3 Tensile value is expected minimum.
- G4 The stress value includes a joint factor of 0.85.
- G5 The stress value includes a joint factor of 0.60.
- G6 The stress value includes a casting quality factor of 0.80. Increased casting quality factors as a result of material examination beyond the requirements of the material specifications shall not be permitted.
- G7 The stress value is established from a consideration of strength only and will be satisfactory for average service. For bolted joints, where freedom from leakage over a long period of time without retightening is required, lower stress values may be necessary, as determined from the relative flexibility of the flange and bolts, and corresponding relaxation properties.
- G8 For tie-rods and draw bolts on cast-iron sectional boilers subject to system pressure.
- G9 The water temperature shall not exceed 210°F.
- G10 Tubing material shall be fully annealed.
- G11 The limitations of ASME BPVC, Section IV, HF-204.2 and HF-204.3 apply.
- G12 Heat treatment after forming or fabrication is neither required nor prohibited.
- G13 For arc or resistance welded studs only.
- G14 For cold-rolled strips only.

NOTES – WELDING REQUIREMENTS

- W1 Welding or brazing is not permitted.
- W2 For tie-rods and draw bolts up to $\frac{7}{8}$ in. diameter subject to system pressure, welding is not permitted.
- W3 For tie-rods and draw bolts over $\frac{7}{8}$ in. diameter up to $1\frac{1}{4}$ in. diameter subject to system pressure, welding is not permitted.

INTENTIONALLY LEFT BLANK

Table 6B
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.
1	...	Castings	SB-26	...	A13560	T6	...	...
2	...	Smls. extr. tube	SB-241	...	A91100	O	...	21
3	...	Drawn smls. tube	SB-210	...	A93003	O	...	21
4	...	Plate, sheet	SB-209	...	A95052	H32 wld.	...	22
(25) 5	...	Drawn smls. tube	SB-210	...	A95052	O	...	22
6	...	Drawn smls. tube	SB-210	...	A95052	H32 wld.	...	22
7	...	Smls. extr. tube	SB-241	...	A95052	H32 wld.	...	22
8	...	Plate, sheet	SB-209	...	A96061	T6 wld.	...	23
9	...	Plate, sheet	SB-209	...	A96061	T651 wld.	...	23
10	...	Drawn smls. tube	SB-210	...	A96061	T6	...	23
11	...	Drawn smls. tube	SB-210	...	A96061	T6 wld.	...	23
12	...	Bar, rod, wire	SB-211	...	A96061	T6 wld.	...	23
13	...	Bar, rod, wire	SB-211	...	A96061	T651 wld.	...	23
14	...	Bar, rod, shapes	SB-221	...	A96061	T6 wld.	...	23
15	...	Smls. extr. tube	SB-241	...	A96061	T6 wld.	...	23
16	...	Smls. extr. tube	SB-241	...	A96063	O	...	23
(25) 17	...	Smls. extr. tube	SB-241	...	A96063	T1	0.501-1.000	23
(25) 18	...	Smls. extr. tube	SB-241	...	A96063	T1	≤0.500	23
19	...	Bar, rod, shapes	SB-221	...	A96063	T5	$t > \frac{1}{2}$	23
20	...	Bar, rod, shapes	SB-221	...	A96063	T5	$t \leq \frac{1}{2}$	23
21	...	Bar, rod, shapes	SB-221	...	A96063	T6	...	23
22	...	Castings	SB/EN 1706	...	AC-42000	F	...	...
23	...	Castings	SB/EN 1706	...	AC-43000	F	...	...
24	...	Castings	SB/EN 1706	...	AC-44300	F	...	...
(25) 25	...	Smls. tube	SB-75	...	C10200	O50	All	31
(25) 26	...	Smls. tube	SB-75	...	C10200	O60	All	31
(25) 27	...	Smls. pipe	SB-42	...	C10200	O61	All	31
(25) 28	...	Plate, sheet, strip, bar	SB-152	...	C10200	O25	...	31
(25) 29	...	Smls. pipe	SB-42	...	C10200	H55	$2 < \text{NPS} \leq 12$	31
(25) 30	...	Smls. tube	SB-75	...	C10200	H55	All	31
(25) 31	...	Smls. cond. tube	SB-111	...	C10200	H55	...	31
(25) 32	...	Smls. U-bend tube	SB-395	...	C10200	H55	...	31
(25) 33	...	Smls. pipe	SB-42	...	C10200	H80	$\frac{1}{8} < \text{NPS} \leq 2$	31
(25) 34	...	Smls. tube	SB-75	...	C10200	H80	$t < 4$	31
(25) 35	...	Smls. cond. tube	SB-111	...	C10200	H80	...	31
(25) 36	...	Plate, sheet, strip, bar	SB-152	...	C10400	O25	...	31
(25) 37	...	Plate, sheet, strip, bar	SB-152	...	C10500	O25	...	31
(25) 38	...	Plate, sheet, strip, bar	SB-152	...	C10700	O25	...	31
(25) 39	...	Plate, sheet, strip, bar	SB-152	...	C11000	O25	...	31
(25) 40	...	Smls. tube	SB-75	...	C12000	O50	All	31
(25) 41	...	Smls. tube	SB-75	...	C12000	O60	All	31
(25) 42	...	Smls. pipe	SB-42	...	C12000	O61	All	31
(25) 43	...	Smls. pipe	SB-42	...	C12000	H55	$2 < \text{NPS} \leq 12$	31
(25) 44	...	Smls. tube	SB-75	...	C12000	H55	All	31
(25) 45	...	Smls. cond. tube	SB-111	...	C12000	H55	...	31

Table 6B
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	34	24	...	G6, W1	5.4	5.4	5.4	5.4	...	...	...	...	...
2	11	3	NFA-7	...	2.0	2.0	2.0	1.9	1.6	...	...	...	...
3	14	5	NFA-1	...	2.8	2.8	2.6	2.3	2.1	...	...	...	...
4	25	9.5	NFA-8	...	5.0	5.0	5.0	5.0	4.8	...	...	...	...
5	25	10	NFA-8	...	5.0	5.0	5.0	5.0	4.8	...	...	...	...
6	25	10	NFA-12	...	5.0	5.0	5.0	5.0	4.8	...	...	...	...
7	25	10	NFA-8	...	5.0	5.0	5.0	5.0	4.8	...	...	...	...
8	24	11	NFA-12	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
9	24	11	NFA-12,13	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
10	42	35	NFA-12,13	W1	8.4	8.4	8.4	8.2	7.0	...	...	...	...
11	24	11	NFA-12,13	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
12	24	11	NFA-12	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
13	24	11	NFA-12,13	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
14	24	11	NFA-12,13	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
15	24	11	NFA-12,13	...	4.8	4.8	4.8	4.7	4.5	...	...	...	...
16	16	5	NFA-1	...	3.2	3.2	3.2	3.0	2.8	...	...	...	...
17	16	8	NFA-1	W1	3.2	3.2	3.2	3.2	3.2	...	...	...	...
18	17	9	NFA-1	W1	3.4	3.4	3.4	3.4	3.4	...	...	...	...
19	21	15	NFA-1	W1	4.2	4.2	4.1	3.9	3.5	...	...	...	...
20	22	16	NFA-1	W1	4.4	4.4	4.3	4.1	3.6	...	...	...	...
21	30	25	NFA-1	...	6.0	6.0	6.0	5.3	4.1	...	...	...	...
22	20.3	11.6	...	G9	1.6	1.6	1.6	1.6	1.5	...	...	...	...
23	21.8	11.6	...	G6	3.5	3.5	3.5	3.5	3.5	...	...	...	...
24	34.8	18.9	...	G8, W1	3.5	3.5	3.1	3.1	3.1	...	...	...	...
25	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
26	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
27	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
28	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
29	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
30	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
31	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
32	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
33	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
34	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
35	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
36	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
37	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
38	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
39	30	10	NFC-1	G1	6.0	5.9	5.9	5.7	5.4	...	...	...	...
40	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
41	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
42	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
43	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
44	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
45	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...

Table 6B (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.
(25) 1	...	Smls. U-bend tube	SB-395	...	C12000	H55	...	31
(25) 2	...	Smls. pipe	SB-42	...	C12000	H80	$\frac{1}{8} < \text{NPS} \leq 2$	31
(25) 3	...	Smls. tube	SB-75	...	C12000	H80	$t < 4$	31
(25) 4	...	Smls. cond. tube	SB-111	...	C12000	H80	...	31
(25) 5	...	Finned tube	SB-359	...	C12200	O62	...	31
(25) 6	...	Smls. tube	SB-75	...	C12200	O60	All	31
(25) 7	...	Smls. tube	SB-75	...	C12200	O50	All	31
(25) 8	...	Smls. pipe	SB-42	...	C12200	O61	All	31
(25) 9	...	Finned tube	SB-359	...	C12200	O61	...	31
(25) 10	...	Plate, sheet, strip, bar	SB-152	...	C12200	O25	...	31
(25) 11	...	Smls. pipe	SB-42	...	C12200	H55	$2 < \text{NPS} \leq 12$	31
(25) 12	...	Smls. tube	SB-75	...	C12200	H55	All	31
(25) 13	...	Smls. cond. tube	SB-111	...	C12200	H55	...	31
(25) 14	...	Finned tube	SB-359	...	C12200	H55	...	31
(25) 15	...	Smls. U-bend tube	SB-395	...	C12200	H55	...	31
(25) 16	...	Smls. pipe	SB-42	...	C12200	H80	$\frac{1}{8} < \text{NPS} \leq 2$	31
(25) 17	...	Smls. tube	SB-75	...	C12200	H80	$t < 4$	31
(25) 18	...	Smls. cond. tube	SB-111	...	C12200	H80	...	31
(25) 19	...	Finned tube	SB-359	...	C12200	H80	...	31
(25) 20	...	Plate, sheet, strip, bar	SB-152	...	C12300	O25	...	31
(25) 21	...	Plate, sheet, strip, bar	SB-152	...	C14200	O25	...	31
(25) 22	...	Smls. cond. tube	SB-111	...	C14200	H55	...	31
(25) 23	...	Smls. U-bend tube	SB-395	...	C14200	H55	...	31
(25) 24	...	Smls. cond. tube	SB-111	...	C14200	H80	...	31
(25) 25	...	Smls. tube	SB-43	...	C23000	O61	...	32
(25) 26	...	Smls. cond. tube	SB-111	...	C23000	O61	...	32
(25) 27	...	Smls. U-bend tube	SB-395	...	C23000	O61	...	32
(25) 28	...	Forgings	SB-283	...	C37700	M10	$t > 1\frac{1}{2}$	...
(25) 29	...	Forgings	SB-283	...	C37700	M10	$\leq 1\frac{1}{2}$	...
(25) 30	...	Plate, sheet	SB-171	...	C44300	M20, O25	$t \leq 4$	32
(25) 31	...	Finned tube	SB-359	...	C44300	O61	...	32
(25) 32	...	Smls. U-bend tube	SB-395	...	C44300	O61	...	32
(25) 33	...	Plate, sheet	SB-171	...	C44400	M20, O25	$t \leq 4$	32
(25) 34	...	Finned tube	SB-359	...	C44400	O61	...	32
(25) 35	...	Smls. U-bend tube	SB-395	...	C44400	O61	...	32
(25) 36	...	Plate, sheet	SB-171	...	C44500	M20, O25	$t \leq 4$	32
(25) 37	...	Finned tube	SB-359	...	C44500	O61	...	32
(25) 38	...	Smls. U-bend tube	SB-395	...	C44500	O61	...	32
(25) 39	...	Plate, sheet	SB-171	...	C46400	M20, O25	$t \leq 3$	32
(25) 40	...	Smls. cond. tube	SB-111	...	C60800	O61	...	35
(25) 41	...	Bar, rod	SB-98	...	C65100	O60	All	33
(25) 42	...	Bar, rod	SB-98	...	C65100	H02	$t \leq 2$	33
(25) 43	...	Smls. pipe & tube	SB-315	...	C65500	O61	...	33
(25) 44	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61	$t \leq 2$	33
(25) 45	...	Bar, rod	SB-98	...	C65500	O60	All	33

Table 6B (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
2	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
3	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
4	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
5	30	6.5	NFC-1	...	4.3	3.8	3.8	3.8	3.8	...	...	...	...
6	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
7	30	9	NFC-7	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
8	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
9	30	9	NFC-1	...	6.0	5.3	5.3	5.3	5.3	...	...	...	...
10	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
11	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
12	36	30	NFC-3	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
13	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
14	36	30	NFC-6	G2	7.2	7.2	7.2	7.1	7.0	6.8	6.6	...	...
15	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
16	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
17	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
18	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
19	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
20	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
21	30	10	NFC-1	...	6.0	5.9	5.9	5.7	5.4	...	...	...	...
22	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
23	36	30	NFC-6	G2	7.2	7.2	7.2	7.2	7.0	6.8	6.6	...	...
24	45	40	NFC-4	G2	9.0	9.0	9.0	9.0	8.8	8.3	...	...	...
25	40	12	NFC-2	...	8.0	8.0	8.0	8.0	8.0	...	...	...	...
26	40	12	NFC-2	...	8.0	8.0	8.0	8.0	8.0	...	...	...	...
27	40	12	NFC-2	...	8.0	8.0	8.0	8.0	8.0	...	...	...	...
28	46	15	...	G3, W1	9.2	8.3	8.3	...	...	...	...	...	...
29	50	18	...	G3, W1	10.0	10.0	9.8	...	...	...	...	...	...
30	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
31	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
32	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
33	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
34	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
35	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
36	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
37	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
38	45	15	NFC-2	...	9.0	9.0	9.0	8.9	8.8	8.6	...	...	...
39	50	20	NFC-2	...	10.0	10.0	10.0	10.0	10.0	...	...	...	...
40	50	19	NFC-2	...	10.0	10.0	10.0	10.0	10.0	9.9	...	...	...
41	40	12	...	G4	8.0	7.9	7.9	7.8	7.8	7.7	...	...	...
42	55	20	...	G2, G4	11.0	11.0	11.0	11.0	11.0	11.0	...	...	...
43	50	15	NFC-2	G4	10.0	10.0	9.9	9.9	9.9	9.8	...	...	...
44	50	18	NFC-2	G4	10.0	10.0	10.0	10.0	10.0	9.8	...	...	...
45	52	15	...	G4	10.4	10.4	10.4	10.4	10.4	10.2	...	...	...

Table 6B (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.	
(25)	1	...	Bar, rod	SB-98	...	C65500	H01	...	33
	2	...	Smls. pipe & tube	SB-466	...	C70600	O60	...	34
	3	...	Plate	SB-171	...	C70600	M20, O25	$t \leq 5$	34
	4	...	Smls. cond. tube	SB-111	...	C70600	O61	...	34
	5	...	Finned tube	SB-359	...	C70600	O61	...	34
	6	...	Smls. U-bend tube	SB-395	...	C70600	O61	...	34
	7	...	Wld. tube	SB-543	...	C70600	W061	...	34
	8	...	Smls. pipe & tube	SB-466	...	C70620	O60	...	34
	9	...	Plate	SB-171	...	C70620	M20, O25	$t \leq 5$	34
	10	...	Smls. cond. tube	SB-111	...	C70620	O61	...	34
	11	...	Finned tube	SB-359	...	C70620	O61	...	34
	12	...	Smls. U-bend tube	SB-395	...	C70620	O61	...	34
	13	...	Wld. tube	SB-543	...	C70620	W061	...	34
	14	...	Smls. tube	SB-466	...	C71000	O60	...	34
	15	...	Smls. cond. tube	SB-111	...	C71000	O61	...	34
	16	...	Smls. U-bend tube	SB-395	...	C71000	O61	...	34
	17	...	Plate	SB-171	...	C71500	M20, O25	$t \leq 2\frac{1}{2}$	34
	18	...	Smls. pipe & tube	SB-466	...	C71500	O60	...	34
	19	...	Smls. cond. tube	SB-111	...	C71500	O61	...	34
	20	...	Smls. U-bend tube	SB-395	...	C71500	O61	...	34
	21	...	Plate	SB-171	...	C71520	M20, O25	$t \leq 2\frac{1}{2}$	34
	22	...	Smls. pipe & tube	SB-466	...	C71520	O60	...	34
	23	...	Smls. cond. tube	SB-111	...	C71520	O61	...	34
	24	...	Smls. U-bend tube	SB-395	...	C71520	O61	...	34
(25)	25	...	Castings	SB-62	...	C83600	M01	...	...
(25)	26	...	Castings	SB-584	...	C84400	M01	...	...
(25)	27	...	Castings	SB-584	...	C90300	M01	...	...
(25)	28	...	Castings	SB-61	...	C92200	M01	...	...
	29	67Ni-30Cu	Bar	SB-164	...	N04400	Annealed	...	42
	30	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed	>5 O.D.	42
	31	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed	≤5 O.D.	42
	32	67Ni-30Cu	Rod	SB-164	...	N04400	Hot worked	...	42
	33	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Stress rel.	...	42
	34	57Ni-22Cr-14W-2Mo-La	Smls. & wld. fittings	SB-366	...	N06230	Solution ann.	...	43
	35	57Ni-22Cr-14W-2Mo-La	Plate, sheet, strip	SB-435	...	N06230	Solution ann.	...	43
	36	57Ni-22Cr-14W-2Mo-La	Forgings	SB-564	...	N06230	Solution ann.	...	43
	37	57Ni-22Cr-14W-2Mo-La	Bar	SB-572	...	N06230	Solution ann.	...	43
	38	57Ni-22Cr-14W-2Mo-La	Wld. pipe	SB-619	...	N06230	Solution ann.	...	43
	39	57Ni-22Cr-14W-2Mo-La	Smls. pipe & tube	SB-622	...	N06230	Solution ann.	...	43
	40	57Ni-22Cr-14W-2Mo-La	Wld. tube	SB-626	...	N06230	Solution ann.	...	43
	41	33Ni-42Fe-21Cr	Plate	SB-409	...	N08800	Annealed	...	45
	42	33Ni-42Fe-21Cr	Plate	SB-409	...	N08810	Annealed	...	45

Table 6B (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Nonferrous Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	55	24	...	G2, G4	11.0	11.0	11.0	11.0	11.0	11.0	...	...	...
2	38	13	NFC-3	...	7.6	7.6	7.6	7.6	7.6	7.5	7.2	7.0	6.8
3	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
4	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
5	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
6	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
7	40	15	NFC-3	...	6.8	6.8	6.8	6.8	6.8	6.7	6.4	6.3	6.1
8	38	13	NFC-3	...	7.6	7.6	7.6	7.6	7.6	7.5	7.2	7.0	6.8
9	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
10	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
11	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
12	40	15	NFC-3	...	8.0	8.0	8.0	8.0	8.0	7.8	7.6	7.4	7.2
13	40	15	NFC-3	...	6.8	6.8	6.8	6.8	6.8	6.7	6.4	6.3	6.1
14	45	16	NFC-3	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0
15	45	16	NFC-3	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0
16	45	16	NFC-3	...	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0	9.0
17	50	20	NFC-4	...	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
18	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
19	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
20	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
21	50	20	NFC-4	...	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
22	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
23	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
24	52	18	NFC-4	...	10.4	10.4	10.4	10.4	10.4	10.4	10.3	10.1	9.9
25	30	14	NFC-1	G6	4.8	4.8	4.8	4.8	4.8	4.6	4.6	4.5	4.4
26	29	13	...	G6	4.6	4.6	4.6	4.5	4.3	4.1	4.0	...	...
27	40	18	...	G6	6.4	6.4	6.4	6.4	6.4	6.4	6.4	...	...
28	34	16	NFC-1	G6	5.4	5.4	5.4	5.4	5.4	5.4	4.7	...	...
29	70	25	NFN-3	G5	14.0	14.0	14.0	14.0	13.6	13.3	13.2	13.1	13.1
30	70	25	NFN-3	G5	14.0	14.0	14.0	14.0	13.6	13.3	13.2	13.1	13.1
31	70	28	NFN-3	G5	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0	14.0
32	80	40	NFN-3	G5	16.0	16.0	16.0	16.0	16.0	16.0	16.0	16.0	16.0
33	85	55	NFN-3	G5	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0	17.0
34	110	45	NFN-24	...	22.0	22.0	22.0	22.0	22.0	21.9	21.5	21.2	21.0
35	110	45	NFN-24	...	22.0	22.0	22.0	22.0	22.0	21.9	21.5	21.2	21.0
36	110	45	NFN-24	...	22.0	22.0	22.0	22.0	22.0	21.9	21.5	21.2	21.0
37	110	45	NFN-24	...	22.0	22.0	22.0	22.0	22.0	21.9	21.5	21.2	21.0
38	110	45	NFN-24	...	18.7	18.7	18.7	18.7	18.7	18.6	18.3	18.0	17.9
39	110	45	NFN-24	...	22.0	22.0	22.0	22.0	22.0	21.9	21.5	21.2	21.0
40	110	45	NFN-24	...	18.7	18.7	18.7	18.7	18.7	18.6	18.3	18.0	17.9
41	75	30	NFN-8	G7	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	14.9
42	65	25	NFN-9	G7	13.0	13.0	13.0	13.0	13.0	13.0	12.9	12.8	12.8

NOTES TO TABLE 6B**GENERAL NOTES**

- (a) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (b) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.
- (c) The following abbreviations are used: cond., condenser; extr., extruded; Smls., Seamless; and Wld., Welded.

NOTES – GENERAL REQUIREMENTS

- G1 When material is to be welded, the phosphorous deoxidized types should be specified.
- G2 When nonferrous materials conforming to Section II specifications are used in welded or brazed construction, the maximum allowable working stresses shall not exceed the values given herein for the material in the annealed condition.
- G3 For use in ASME BPVC, Section IV, eq. HG-307.2(b)(2), the maximum allowable stress at room temperature (100°F max.) shall be 10.0 ksi through 1½ in. thickness and 9.2 ksi over 1½ in. thickness.
- G4 Copper-silicon alloys are not always suitable when exposed to certain median and high temperatures, particularly steam above 212°F. Therefore, this material is limited to the construction of hot water boilers to be operated at a temperature not to exceed 200°F.
- G5 To be used for HLW connections only.
- G6 The stress value includes a casting quality factor of 0.8. Increased casting quality factors as a result of material examination beyond the requirement of the material specification shall not be permitted. This is not intended to apply to valves and fittings made to recognized standards.
- G7 The maximum water temperature shall not exceed 210°F.
- G8 The castings shall not be repaired.
- G9 When proof testing is required to establish design pressure, that testing shall comply with ASME BPVC, Section IV, HG-501 and HG-502.3, except that in the equation in HG-502.3, the design factor shall be 10 in lieu of 5.

NOTES – WELDING REQUIREMENTS

- W1 Welding or brazing is not permitted.

INTENTIONALLY LEFT BLANK

Table 6C
Section IV Maximum Allowable Stress Values, S, for Lined Water Heater Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Castings	SA-278	20	...	...	...	...	...
2	Carbon steel	Castings	SA-278	25	...	...	...	...	...
3	Carbon steel	Castings	SA-278	30	...	...	...	...	...
4	Carbon steel	Castings	SA-278	35	...	...	...	...	...
5	Carbon steel	Castings	SA-278	40	...	...	...	...	...
6	Carbon steel	Wld. tube	SA-513	1008	...	...	...	1	1
7	Carbon steel	Bar	SA-675	45	...	...	...	1	1
8	Carbon steel	Plate	SA-285	A	K01700	...	...	1	1
9	Carbon steel	Plate	SA-285 AISI C-1012	...	...	...	...	1	1
10	Carbon steel	Sheet	SA-414	A	K01501	...	...	1	1
11	Carbon steel	Sheet	SA-414 AISI C-1012	...	...	...	...	1	1
12	Carbon steel	Wld. tube	SA-513	1010	...	...	...	1	1
13	Carbon steel	Wld. tube	SA-178	E/A	K01200	...	...	1	1
14	Carbon steel	Smls. pipe	SA-53	A	K02504	...	...	1	1
15	Carbon steel	Wld. pipe	SA-53	E/A	K02504	...	...	1	1
16	Carbon steel	Smls. pipe	SA-106	A	K02501	...	...	1	1
17	Carbon steel	Wld. pipe	SA-135	E/A	...	...	...	1	1
18	Carbon steel	Wld. tube	SA-513	1015	...	...	...	1	1
19	Carbon steel	Bar	SA-675	50	...	...	...	1	1
20	Carbon steel	Plate	SA-285	B	K02200	...	...	1	1
21	Carbon steel	Plate	SA-285 AISI C-1015d	...	...	...	...	1	1
22	Carbon steel	Sheet	SA-414	B	K02201	...	...	1	1
23	Carbon steel	Sheet	SA-414 AISI C-1015d	...	...	...	...	1	1
24	Carbon steel	Bar	SA-675	55	...	...	...	1	1
25	Carbon steel	Plate	SA-285	C	K02801	...	...	1	1
26	Carbon steel	Plate	SA-516	55	K01800	...	...	1	1
27	Carbon steel	Plate	SA-285 AISI C-1023	...	...	...	...	1	1
28	Carbon steel	Sheet	SA-414	C	K02503	...	...	1	1
29	Carbon steel	Sheet	SA-414 AISI C-1023	...	...	...	...	1	1
30	Carbon steel	Plate	SA-36	...	K02600	...	...	1	1
31	Carbon steel	Bar, shapes	SA-36	...	K02600	...	...	1	1
32	Carbon steel	Forgings	SA-181	...	K03502	60	...	1	1
33	Carbon steel	Bar	SA-675	60	...	...	...	1	1
34	Carbon steel	Plate	SA-515	60	K02401	...	...	1	1
35	Carbon steel	Plate	SA-516	60	K02100	...	...	1	1
36	Carbon steel	Smls. pipe	SA-53	B	K03005	...	...	1	1
37	Carbon steel	Wld. pipe	SA-53	E/B	K03005	...	...	1	1
38	Carbon steel	Smls. pipe	SA-106	B	K03006	...	...	1	1
39	Carbon steel	Wld. pipe	SA-135	E/B	...	...	...	1	1
40	Carbon steel	Sheet	SA-414	D	K02505	...	...	1	1
41	Carbon steel	Plate	SA/CSA-G40.21	38W	...	...	...	1	1
42	Carbon steel	Wld. tube	SA-178	E/C	K03503	...	...	1	1
43	Carbon steel	Bar	SA-675	65	...	...	...	1	1
44	Carbon steel	Plate	SA-515	65	K02800	...	...	1	1
45	Carbon steel	Plate	SA-516	65	K02403	...	...	1	1

Table 6C
Section IV Maximum Allowable Stress Values, S, for Lined Water Heater Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	20	18	CI-1	W1	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0	5.0
2	25	23	CI-1	W1	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3	6.3
3	30	27	CI-1	W1	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5	7.5
4	35	32	CI-1	W1	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8	8.8
5	40	36	CI-1	W1	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
6	42	30	...	G1, G2	8.9	8.9	8.9	8.9	8.9	8.9	8.9	8.9	8.9
7	45	23	CS-6	...	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3
8	45	24	CS-1	...	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3
9	45	25	...	...	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3
10	45	25	CS-1	...	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3
11	45	25	...	...	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3	11.3
12	45	32	...	G1, G2	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6	9.6
13	47	26	...	G1, G2	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0	10.0
14	48	30	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0
15	48	30	CS-2	G1	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0
16	48	30	CS-2	...	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0
17	48	30	CS-2	G1	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0	12.0
18	48	35	...	G1, G2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2	10.2
19	50	25	CS-1	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
20	50	27	CS-1	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
21	50	30	...	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
22	50	30	CS-2	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
23	50	30	...	...	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
24	55	28	CS-1	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
25	55	30	CS-2	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
26	55	30	CS-2	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
27	55	33	...	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
28	55	33	CS-2	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
29	55	33	...	...	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8	13.8
30	58	36	CS-2	...	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5
31	58	36	...	...	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5
32	60	30	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
33	60	30	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
34	60	32	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
35	60	32	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
36	60	35	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
37	60	35	CS-2	G1	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
38	60	35	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
39	60	35	CS-2	G1	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
40	60	35	CS-2	...	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
41	60	36	CS-2	...	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5	14.5
42	60	37	...	G1	12.8	12.8	12.8	12.8	12.8	12.8	12.8	12.8	12.8
43	65	33	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3
44	65	35	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3
45	65	35	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3

Table 6C (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Lined Water Heater Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Class/ Cond./ Temper	Size/ Thickness, in.	P-No.	Group No.
1	Carbon steel	Sheet	SA-414	E	K02704	...	...	1	1
2	Carbon steel	Plate	SA/CSA-G40.21	44W	...	...	$t \leq 8$	1	1
3	Carbon steel	Plate	SA/CSA-G40.21	50W	...	...	$t \leq 6$	1	1
4	Carbon steel	Plate	SA-455	...	K03300	...	$0.58 < t \leq \frac{3}{4}$	1	2
5	Carbon steel	Bar	SA-675	70	...	...	...	1	2
6	Carbon steel	Forgings	SA-105	...	K03504	...	...	1	2
7	Carbon steel	Forgings	SA-181	...	K03502	70	...	1	2
8	Carbon steel	Plate	SA-515	70	K03101	...	...	1	2
9	Carbon steel	Plate	SA-516	70	K02700	...	...	1	2
10	Carbon steel	Smls. pipe	SA-106	C	K03501	...	...	1	2
11	Carbon steel	Sheet	SA-414	F	K03102	...	...	1	2
12	Carbon steel	Plate	SA-455	...	K03300	...	$\frac{3}{8} < t \leq 0.58$	1	2
13	Carbon steel	Plate	SA-455	...	K03300	...	$t \leq \frac{3}{8}$	1	2
14	Carbon steel	Sheet	SA-414	G	K03103	...	...	1	2

Table 6C (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Lined Water Heater Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	65	38	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3
2	65	44	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3
3	65	50	CS-2	...	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3	16.3
4	70	35	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
5	70	35	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
6	70	36	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
7	70	36	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
8	70	38	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
9	70	38	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
10	70	40	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
11	70	42	CS-2	...	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5	17.5
12	73	37	CS-2	...	18.3	18.3	18.3	18.3	18.3	18.3	18.3	18.3	18.3
13	75	38	CS-2	...	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8
14	75	45	CS-3	...	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8	18.8

NOTES TO TABLE 6C**GENERAL NOTES**

- (a) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (b) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES - GENERAL REQUIREMENTS

G1 The stress value includes a joint factor of 0.85.

G2 Tensile value is expected minimum.

NOTES - WELDING REQUIREMENTS

W1 Welding or brazing is not permitted.

INTENTIONALLY LEFT BLANK

Table 6D
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Size/ Thickness, in.	P-No.	Group No.
1	18Cr-2Mo	Plate	SA-240	...	S44400	$t \leq \frac{3}{8}$	7	2
2	18Cr-2Mo	Smls. tube	SA-268	...	S44400	$t \leq \frac{3}{8}$	7	2
3	18Cr-2Mo	Wld. tube	SA-268	...	S44400	$t \leq \frac{3}{8}$	7	2
4	18Cr-2Mo	Bar	SA-479	...	S44400	$t \leq \frac{3}{8}$	7	2
5	18Cr-Ti	Plate	SA-240	439	S43035	$t \leq \frac{3}{8}$	7	2
6	18Cr-Ti	Smls. tube	SA-268	TP439	S43035	$t \leq \frac{3}{8}$	7	2
7	18Cr-Ti	Bar	SA-479	439	S43035	$t \leq \frac{3}{8}$	7	2
8	29Cr-4Mo	Smls. tube	SA-268	29-4	S44700	...	10	1
9	29Cr-4Mo	Wld. tube	SA-268	29-4	S44700	...	10	1
10	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	$t \leq \frac{1}{2}$	8	1
11	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	$t \leq \frac{1}{2}$	8	1
12	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
13	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
14	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	$t \leq \frac{1}{2}$	8	1
15	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	$t \leq \frac{1}{2}$	8	1
16	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
17	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
18	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
19	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
20	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
21	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316L	S31603	$t \leq \frac{1}{2}$	8	1
22	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	$t \leq \frac{1}{2}$	8	1
23	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	$t \leq \frac{1}{2}$	8	1
24	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	$t \leq \frac{1}{2}$	8	1
25	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	$t \leq \frac{1}{2}$	8	1
26	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	$t \leq \frac{1}{2}$	8	1
27	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	$t \leq \frac{1}{2}$	8	1
28	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	$t \leq \frac{1}{2}$	8	1
29	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	$t \leq \frac{1}{2}$	8	1
30	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	$t \leq \frac{1}{2}$	8	1
31	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	$t \leq \frac{1}{2}$	8	1
32	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316	S31600	$t \leq \frac{1}{2}$	8	1
33	16Cr-12Ni-2Mo	Smls. pipe	SA-312	TP316	S31600	$t \leq \frac{1}{2}$	8	1
34	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	$t \leq \frac{1}{2}$	8	1
35	16Cr-12Ni-2Mo	Wld. pipe	SA-312	TP316	S31600	$t \leq \frac{1}{2}$	8	1
36	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	$t \leq \frac{1}{2}$	8	1
37	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	$t \leq \frac{1}{2}$	8	1
38	18Cr-8Ni	Forgings	SA-182	F304L	S30403	$t \leq \frac{1}{2}$	8	1
39	18Cr-8Ni	Forgings	SA-182	F304L	S30403	$t \leq \frac{1}{2}$	8	1
40	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
41	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
42	18Cr-8Ni	Plate	SA-240	304L	S30403	$t \leq \frac{1}{2}$	8	1
43	18Cr-8Ni	Plate	SA-240	304L	S30403	$t \leq \frac{1}{2}$	8	1
44	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
45	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	$t \leq \frac{1}{2}$	8	1

Table 6D
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	60	40	CS-2	...	15.0	15.0	15.0	14.8	14.6	14.4	14.2	14.0	13.9
2	60	40	CS-2	...	15.0	15.0	15.0	14.8	14.6	14.4	14.2	14.0	13.9
3	60	40	CS-2	G1	12.8	12.8	12.8	12.6	12.4	12.2	12.1	11.9	11.8
4	60	...	CS-2	...	15.0	15.0	15.0	15.0	14.6	14.6	14.5	14.3	13.9
5	60	30	CS-2	...	15.0	15.0	15.0	14.7	14.5	14.3	14.1	14.0	13.8
6	60	30	CS-2	...	15.0	15.0	15.0	14.7	14.5	14.3	14.1	14.0	13.8
7	70	40	CS-2	...	17.5	17.5	17.5	17.2	16.9	16.7	16.5	16.3	16.1
8	80	60	HA-6	G2	20.0	20.0	20.0	19.6	19.3	19.3	19.2	19.2	19.2
9	80	60	HA-6	G1, G2	17.0	17.0	17.0	16.7	16.4	16.4	16.3	16.3	16.3
10	70	25	HA-4	...	16.7	15.1	14.2	13.4	12.7	12.2	11.7	11.3	10.9
11	70	25	HA-4	G3	17.5	17.3	17.0	16.5	16.0	15.8	15.6	15.3	14.8
12	70	25	HA-4	...	16.7	15.1	14.2	13.4	12.7	12.2	11.7	11.3	10.9
13	70	25	HA-4	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
14	70	25	HA-4	...	16.7	15.1	14.2	13.4	12.7	12.2	11.7	11.3	10.9
15	70	25	HA-4	G3	17.5	17.3	17.0	16.5	16.0	15.8	15.6	15.3	14.8
16	70	25	HA-4	G1	14.2	12.9	12.1	11.4	10.8	10.3	9.9	9.6	9.3
17	70	25	HA-4	G1, G3	14.9	14.7	14.5	14.0	13.6	13.4	13.2	13.0	12.5
18	70	25	HA-4	...	16.7	15.1	14.2	13.4	12.7	12.2	11.7	11.3	10.9
19	70	25	HA-4	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
20	70	25	HA-4	G1	14.2	12.9	12.1	11.4	10.8	10.3	9.9	9.6	9.3
21	70	25	HA-4	G1, G3	14.9	14.5	14.0	13.5	13.0	12.7	12.5	12.3	12.2
22	70	25	HA-4	...	16.7	15.1	14.2	13.4	12.7	12.2	11.7	11.3	10.9
23	70	25	HA-4	G3	17.5	17.3	17.0	16.5	16.0	15.8	15.6	15.3	14.8
24	75	30	HA-2	...	18.8	18.3	17.3	16.4	15.6	14.9	14.3	13.8	13.3
25	75	30	HA-2	G3	18.8	18.8	18.8	18.5	18.2	18.1	18.0	18.0	18.0
26	75	30	HA-2	...	18.8	18.3	17.3	16.4	15.6	14.9	14.3	13.8	13.3
27	75	30	HA-2	G3	18.8	18.8	18.8	18.5	18.2	18.1	18.0	18.0	18.0
28	75	30	HA-2	...	18.8	18.3	17.3	16.4	15.6	14.9	14.3	13.8	13.3
29	75	30	HA-2	G3	18.8	18.8	18.8	18.5	18.2	18.1	18.0	18.0	18.0
30	75	30	HA-2	G1	15.9	15.5	14.7	13.9	13.3	12.7	12.1	11.7	11.3
31	75	30	HA-2	G1, G3	15.9	15.9	15.9	15.7	15.5	15.4	15.3	15.3	15.3
32	75	30	HA-2	...	18.8	18.3	17.3	16.4	15.6	14.9	14.3	13.8	13.3
33	75	30	HA-2	G3	18.8	18.8	18.8	18.5	18.2	18.1	18.0	18.0	18.0
34	75	30	HA-2	G1	15.9	15.5	14.7	13.9	13.3	12.7	12.1	11.7	11.3
35	75	30	HA-2	G1, G3	15.9	15.9	15.9	15.7	15.5	15.4	15.3	15.3	15.3
36	75	30	HA-2	...	18.8	18.3	17.3	16.4	15.6	14.9	14.3	13.8	13.3
37	75	30	HA-2	G3	18.8	18.8	18.8	18.5	18.2	18.1	18.0	18.0	18.0
38	70	25	HA-3	...	16.7	15.1	14.3	13.5	12.8	12.2	11.7	11.3	10.9
39	70	25	HA-3	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
40	70	25	HA-3	...	16.7	15.1	14.3	13.5	12.8	12.2	11.7	11.3	10.9
41	70	25	HA-3	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
42	70	25	HA-3	...	16.7	15.1	14.3	13.5	12.8	12.2	11.7	11.3	10.9
43	70	25	HA-3	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
44	70	25	HA-3	G1	14.2	12.9	12.1	11.4	10.9	10.4	9.9	9.6	9.3
45	70	25	HA-3	G1, G3	14.9	14.5	14.0	13.5	13.0	12.7	12.5	12.3	12.2

Table 6D (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Size/ Thickness, in.	P-No.	Group No.
1	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
2	18Cr-8Ni	Smls. pipe	SA-312	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
3	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
4	18Cr-8Ni	Wld. pipe	SA-312	TP304L	S30403	$t \leq \frac{1}{2}$	8	1
5	18Cr-8Ni	Bar	SA-479	304L	S30403	$t \leq \frac{1}{2}$	8	1
6	18Cr-8Ni	Bar	SA-479	304L	S30403	$t \leq \frac{1}{2}$	8	1
7	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	8	1
8	18Cr-8Ni	Forgings	SA-182	F304	S30400	...	8	1
9	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	$t \leq \frac{1}{2}$	8	1
10	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	$t \leq \frac{1}{2}$	8	1
11	18Cr-8Ni	Plate	SA-240	304	S30400	$t \leq \frac{1}{2}$	8	1
12	18Cr-8Ni	Plate	SA-240	304	S30400	$t \leq \frac{1}{2}$	8	1
13	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	$t \leq \frac{1}{2}$	8	1
14	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	$t \leq \frac{1}{2}$	8	1
15	18Cr-8Ni	Smls. pipe	SA-312	TP304	S30400	$t \leq \frac{1}{2}$	8	1
16	18Cr-8Ni	Smls. pipe	SA-312	TP304	S30400	$t \leq \frac{1}{2}$	8	1
17	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	$t \leq \frac{1}{2}$	8	1
18	18Cr-8Ni	Wld. pipe	SA-312	TP304	S30400	$t \leq \frac{1}{2}$	8	1
19	18Cr-8Ni	Bar	SA-479	304	S30400	$t \leq \frac{1}{2}$	8	1
20	18Cr-8Ni	Bar	SA-479	304	S30400	$t \leq \frac{1}{2}$	8	1
(25)	21	20Cr-3Ni-1.5Mo-N	Plate	SA-240	...	$t > \frac{3}{16}$	10H	1
(25)	22	20Cr-3Ni-1.5Mo-N	Smls. tube	SA-789	...	$t > \frac{3}{16}$	10H	1
(25)	23	20Cr-3Ni-1.5Mo-N	Wld. tube	SA-789	...	$t > \frac{3}{16}$	10H	1
(25)	24	20Cr-3Ni-1.5Mo-N	Smls. pipe	SA-790	...	$t > \frac{3}{16}$	10H	1
(25)	25	20Cr-3Ni-1.5Mo-N	Wld. pipe	SA-790	...	$t > \frac{3}{16}$	10H	1
(25)	26	20Cr-3Ni-1.5Mo-N	Sheet, strip	SA-240	...	$t \leq \frac{3}{16}$	10H	1
(25)	27	20Cr-3Ni-1.5Mo-N	Smls. tube	SA-789	...	$t \leq \frac{3}{16}$	10H	1
(25)	28	20Cr-3Ni-1.5Mo-N	Wld. tube	SA-789	...	$t \leq \frac{3}{16}$	10H	1
(25)	29	20Cr-3Ni-1.5Mo-N	Smls. pipe	SA-790	...	$t \leq \frac{3}{16}$	10H	1
(25)	30	20Cr-3Ni-1.5Mo-N	Wld. pipe	SA-790	...	$t \leq \frac{3}{16}$	10H	1
(25)	31	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...	$t > \frac{3}{16}$	10H	1
(25)	32	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	$t > \frac{3}{16}$	10H	1
(25)	33	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	$t > \frac{3}{16}$	10H	1
(25)	34	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	$t > \frac{3}{16}$	10H	1
(25)	35	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	$t > \frac{3}{16}$	10H	1
(25)	36	21Cr-5Mn-1.5Ni-Cu-N	Sheet, strip	SA-240	...	$t \leq \frac{3}{16}$	10H	1
(25)	37	21Cr-5Mn-1.5Ni-Cu-N	Smls. tube	SA-789	...	$t \leq \frac{3}{16}$	10H	1
(25)	38	21Cr-5Mn-1.5Ni-Cu-N	Wld. tube	SA-789	...	$t \leq \frac{3}{16}$	10H	1
(25)	39	21Cr-5Mn-1.5Ni-Cu-N	Smls. pipe	SA-790	...	$t \leq \frac{3}{16}$	10H	1
(25)	40	21Cr-5Mn-1.5Ni-Cu-N	Wld. pipe	SA-790	...	$t \leq \frac{3}{16}$	10H	1
41	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...	10H	1
42	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S31803	...	10H	1
43	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S31803	...	10H	1
44	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S31803	...	10H	1
45	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S31803	...	10H	1

Table 6D (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	70	25	HA-3	...	16.7	15.1	14.3	13.5	12.8	12.2	11.7	11.3	10.9
2	70	25	HA-3	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
3	70	25	HA-3	G1	14.2	12.9	12.1	11.4	10.9	10.4	9.9	9.6	9.3
4	70	25	HA-3	G1, G3	14.9	14.5	14.0	13.5	13.0	12.7	12.5	12.3	12.2
5	70	25	HA-3	...	16.7	15.1	14.3	13.5	12.8	12.2	11.7	11.3	10.9
6	70	25	HA-3	G3	17.5	17.0	16.5	15.9	15.3	15.0	14.7	14.5	14.4
7	75	30	HA-1	...	18.8	18.3	16.7	15.8	14.9	14.4	13.8	13.4	12.9
8	75	30	HA-1	G3	18.8	18.3	17.8	17.2	16.6	16.3	16.0	15.9	15.9
9	75	30	HA-1	...	18.8	18.3	16.7	15.7	14.9	14.4	13.8	13.4	12.9
10	75	30	HA-1	G3	18.8	18.3	17.8	17.2	16.6	16.3	16.0	15.9	15.9
11	75	30	HA-1	...	18.8	18.3	16.7	15.8	14.9	14.4	13.8	13.4	12.9
12	75	30	HA-1	G3	18.8	18.3	17.8	17.2	16.6	16.3	16.0	15.9	15.9
13	75	30	HA-1	G1	15.9	15.5	14.2	13.4	12.7	12.2	11.7	11.4	11.0
14	75	30	HA-1	G1, G3	15.9	15.5	15.1	14.6	14.1	13.8	13.6	13.5	13.5
15	75	30	HA-1	...	18.8	18.3	16.7	15.8	14.9	14.4	13.8	13.4	12.9
16	75	30	HA-1	G3	18.8	18.3	17.8	17.2	16.6	16.3	16.0	15.9	15.9
17	75	30	HA-1	G1	15.9	15.5	14.2	13.4	12.7	12.2	11.7	11.4	11.0
18	75	30	HA-1	G1, G3	15.9	15.5	15.1	14.6	14.1	13.8	13.6	13.5	13.5
19	75	30	HA-1	...	18.8	18.3	16.7	15.8	14.9	14.4	13.8	13.4	12.9
20	75	30	HA-1	G3	18.8	18.3	17.8	17.2	16.6	16.3	16.0	15.9	15.9
21	95	65	HA-5	...	23.8	23.4	23.0	22.4	21.7	21.6	21.5	21.5	21.5
22	95	65	HA-5	...	23.8	23.4	23.0	22.4	21.7	21.6	21.5	21.5	21.5
23	95	65	HA-5	G1	20.2	19.9	19.6	19.0	18.4	18.3	18.2	18.2	18.2
24	95	65	HA-5	...	23.8	23.4	23.0	22.4	21.7	21.6	21.5	21.5	21.5
25	95	65	HA-5	G1	20.2	19.9	19.6	19.0	18.4	18.3	18.2	18.2	18.2
26	100	70	HA-5	...	25.0	24.6	24.3	23.5	22.8	22.7	22.6	22.6	22.6
27	100	70	HA-5	...	25.0	24.6	24.3	23.5	22.8	22.7	22.6	22.6	22.6
28	100	70	HA-5	G1	21.3	20.9	20.6	20.0	19.4	19.3	19.2	19.2	19.2
29	100	70	HA-5	...	25.0	24.6	24.3	23.5	22.8	22.7	22.6	22.6	22.6
30	100	70	HA-5	G1	21.3	20.9	20.6	20.0	19.4	19.3	19.2	19.2	19.2
31	94	65	HA-5	...	23.5	23.5	23.5	23.0	22.4	22.0	21.6	21.6	21.6
32	94	65	HA-5	...	23.5	23.5	23.5	23.0	22.4	22.0	21.6	21.6	21.6
33	94	65	HA-5	G1	20.0	20.0	20.0	19.5	19.0	18.7	18.4	18.4	18.3
34	94	65	HA-5	...	23.5	23.5	23.5	23.0	22.4	22.0	21.6	21.6	21.6
35	94	65	HA-5	G1	20.0	20.0	20.0	19.5	19.0	18.7	18.4	18.4	18.3
36	101	77	HA-5	...	25.3	25.3	25.3	24.7	24.1	23.7	23.2	23.2	23.2
37	101	77	HA-5	...	25.3	25.3	25.3	24.7	24.1	23.7	23.2	23.2	23.2
38	101	77	HA-5	G1	21.5	21.5	21.5	21.0	20.4	20.1	19.7	19.7	19.7
39	101	77	HA-5	...	25.3	25.3	25.3	24.7	24.1	23.7	23.2	23.2	23.2
40	101	77	HA-5	G1	21.5	21.5	21.5	21.0	20.4	20.1	19.7	19.7	19.7
41	90	65	HA-5	...	22.5	22.5	22.5	22.1	21.7	21.3	20.9	20.6	20.4
42	90	65	HA-5	...	22.5	22.5	22.5	22.1	21.7	21.3	20.9	20.6	20.4
43	90	65	HA-5	G1	19.1	19.1	19.1	18.8	18.4	18.1	17.8	17.5	17.3
44	90	65	HA-5	...	22.5	22.5	22.5	22.1	21.7	21.3	20.9	20.6	20.4
45	90	65	HA-5	G1	19.1	19.1	19.1	18.8	18.4	18.1	17.8	17.5	17.3

Table 6D (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

	Line No.	Nominal Composition	Product Form	Spec. No.	Type/ Grade	Alloy Desig./ UNS No.	Size/ Thickness, in.	P-No.	Group No.
(25)	1	22Cr-5Ni-3Mo-N	Plate, sheet, strip	SA-240	...	S32205	...	10H	1
(25)	2	22Cr-5Ni-3Mo-N	Smls. pipe	SA-790	...	S32205	...	10H	1
(25)	3	22Cr-5Ni-3Mo-N	Wld. pipe	SA-790	...	S32205	...	10H	1
(25)	4	22Cr-5Ni-3Mo-N	Smls. tube	SA-789	...	S32205	...	10H	1
(25)	5	22Cr-5Ni-3Mo-N	Wld. tube	SA-789	...	S32205	...	10H	1

Table 6D (Cont'd)
Section IV Maximum Allowable Stress Values, S, for Unlined Water Heater Materials

Line No.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	External Pressure Chart No.	Notes	Maximum Allowable Stress, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding								
					100	150	200	250	300	350	400	450	500
1	95	65	HA-5	...	23.8	23.8	23.8	23.4	22.9	22.5	22.1	21.8	21.5
2	95	65	HA-5	...	23.8	23.8	23.8	23.4	22.9	22.5	22.1	21.8	21.5
3	95	65	HA-5	G1	20.2	20.2	20.2	19.8	19.5	19.1	18.7	18.5	18.3
4	95	70	HA-5	...	23.8	23.8	23.8	23.4	22.9	22.5	22.1	21.8	21.5
5	95	70	HA-5	G1	20.2	20.2	20.2	19.8	19.5	19.1	18.7	18.5	18.3

NOTES TO TABLE 6D**GENERAL NOTES**

- (a) The following abbreviations are used: Smls., Seamless; and Wld., Welded.
- (b) The stress values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (c) The properties of steels are influenced by the processing history, heat treatment, melting practice, and level of residual elements. See Nonmandatory Appendix A for more information.
- (d) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTES – GENERAL REQUIREMENTS

- G1 The stress value includes a joint factor of 0.85.
- G2 Heat treatment after forming or fabrication is neither required nor prohibited.
- G3 Due to the relatively low yield strength of these materials, these higher stress values were established at temperatures where the short-time tensile properties govern to permit the use of these alloys where slightly greater deformation is acceptable. The stress values in this range exceed $66\frac{2}{3}\%$ but do not exceed 90% of the yield strength at temperature. Use of these stresses may result in dimensional changes due to permanent strain. These stress values are not recommended for the flanges of gasketed joints or other applications where slight amounts of distortion can cause leakage or malfunction.

INTENTIONALLY LEFT BLANK

Table U
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials				
(25) 1	Carbon steel	Castings	SA-278	20
(25) 2	Carbon steel	Castings	SA-278	25
(25) 3	Carbon steel	Castings	SA-278	30
(25) 4	Carbon steel	Castings	SA-278	35
(25) 5	Carbon steel	Castings	SA-278	40
6	Carbon steel	Sheet	SA-1008	CS-A
7	Carbon steel	Sheet	SA-1008	CS-B
(25) 8	Carbon steel	Wld. tube	SA-513	1/1008
9	Carbon steel	Bar	SA-675	45
10	Carbon steel	Wld. pipe	SA-134	A283A
11	Carbon steel	Plate	SA-285	A
12	Carbon steel	Wld. pipe	SA-672	A45
13	Carbon steel	Sheet	SA-414	A
(25) 14	Carbon steel	Wld. tube	SA-513	1/1010
15	Carbon steel	Wld. tube	SA-178	A
16	Carbon steel	Smls. tube	SA-179	...
17	Carbon steel	Smls. tube	SA-192	...
18	Carbon steel	Wld. tube	SA-214	...
19	Carbon steel	Smls. tube	SA-556	A2
(25) 20	...	...	...	...
21	Carbon steel	Wld. pipe	SA-53	E/A
(25) 22	Carbon steel	Butt-wld. pipe	SA-53	F/A
23	Carbon steel	Smls. pipe	SA-53	S/A
24	Carbon steel	Smls. pipe	SA-106	A
25	Carbon steel	Wld. pipe	SA-135	A
26	Carbon steel	Forged pipe	SA-369	FPA
27	Carbon steel	Wld. pipe	SA-587	...
(25) 28	Carbon steel	Wld. tube	SA-513	1/1015
29	Carbon steel	Bar	SA-675	50
30	Carbon steel	Wld. pipe	SA-134	A283B
31	Carbon steel	Plate	SA-285	B
32	Carbon steel	Wld. pipe	SA-672	A50
33	Carbon steel	Sheet	SA-414	B
34	Carbon steel	Plate	SA/EN 10028-3	P275NH
(25) 35	Carbon steel	Plate	SA/EN 10025-2	S235JR
36	Carbon steel	Plate	SA/EN 10028-2	P235GH
37	Carbon steel	Plate	SA/EN 10028-3	P275NH
38	Carbon steel	Smls. tube	SA/EN 10216-2	P235GH
(25) 39	Carbon steel	Wld. pipe & tube	SA/EN 10217-1	P235TR2
40	Carbon steel	Sheet, strip	SA-1011	36
41	Carbon steel	Plate	SA/EN 10028-3	P275NH
42	Carbon steel	Bar	SA-675	55
43	Carbon steel	Wld. pipe	SA-134	A283C
44	Carbon steel	Plate	SA-283	C
45	Carbon steel	Plate	SA-285	C

Table U
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
				Ferrous Materials
1	...	...	...	20
2	...	...	...	25
3	...	...	...	30
4	...	...	...	35
5	...	...	...	40
6	...	...	...	40
7	...	...	...	40
8	...	...	...	42
9	...	...	...	45
10	...	...	...	45
11	K01700	...	...	45
12	K01700	...	...	45
13	K01501	...	...	45
14	...	...	...	45
15	K01200	...	...	47
16	K01200	...	...	47
17	K01201	...	...	47
18	K01807	...	...	47
19	K01807	...	...	47
20	...	...	...	...
21	K02504	...	...	48
22	...	...	...	48
23	K02504	...	...	48
24	K02501	...	...	48
25	...	...	...	48
26	K02501	...	...	48
27	K11500	...	...	48
28	...	...	...	48
29	...	...	...	50
30	...	...	...	50
31	K02200	...	...	50
32	K02200	...	...	50
33	K02201	...	...	50
34	...	...	$6 < t \leq 10$	51
35	...	...	$t \leq 4$	52
36	...	...	$\leq 2\frac{1}{4}$	52
37	...	...	$4 < t \leq 6$	52
38	...	...	$t \leq 2\frac{1}{2}$	52
39	...	...	$t \leq 1\frac{9}{16}$	52
40	SS	Type 1	$t \leq 0.23$	53
41	...	...	$2\frac{1}{4} < t \leq 4$	53.5
42	...	...	...	55
43	K02401	...	...	55
44	K02401	...	...	55
45	K02801	...	...	55

Table U
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials														
1	20.0	20.0	20.0	20.0	...	...	...	...	...	...	...	...	...	...
2	25.0	25.0	25.0	25.0	...	...	...	...	...	...	...	...	...	...
3	30.0	30.0	30.0	30.0	...	...	...	...	...	...	...	...	...	...
4	35.0	35.0	35.0	35.0	...	...	...	...	...	...	...	...	...	...
5	40.0	40.0	40.0	40.0	40.0	40.0	40.0	...	...	...	...	...	...	...
6	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0	39.5	36.8	33.5	29.9	26.2	23.1
7	40.0	40.0	40.0	40.0	40.0	40.0	40.0	40.0	39.5	36.8	33.5	29.9	26.2	23.1
8	42.0	42.0	42.0	42.0	42.0	42.0	42.0	42.0	41.5	38.6	35.1	31.4	27.5	24.2
9	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.3	37.7	33.6	29.5	25.9
10	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.3	37.7	33.6	29.5	25.9
11	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.3	37.7	33.6	29.5	25.9
12	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.3	37.7	33.6	29.5	25.9
13	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.3	37.7	33.6	29.5	25.9
14	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.4	41.4	37.6	33.6	29.5	25.9
15	47.0	47.0	47.0	47.0	47.0	47.0	47.0	47.0	46.4	43.2	39.3	35.1	30.8	27.1
16	47.0	47.0	47.0	47.0	47.0	47.0	47.0	47.0	46.4	43.2	39.3	35.1	30.8	27.1
17	47.0	47.0	47.0	47.0	47.0	47.0	47.0	47.0	46.4	43.2	39.3	35.1	30.8	27.1
18	47.0	47.0	47.0	47.0	47.0	47.0	47.0	47.0	46.4	43.2	39.3	35.1	30.8	27.1
19	47.0	47.0	47.0	47.0	47.0	47.0	47.0	47.0	46.4	43.2	39.3	35.1	30.8	27.1
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
22	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
23	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
24	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
25	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
26	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
27	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.2	35.8	31.5	27.7
28	48.0	48.0	48.0	48.0	48.0	48.0	48.0	48.0	47.4	44.1	40.1	35.8	31.5	27.7
29	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.4	45.9	41.8	37.3	32.8	28.8
30	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.4	45.9	41.8	37.3	32.8	28.8
31	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.4	45.9	41.8	37.3	32.8	28.8
32	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.4	45.9	41.8	37.3	32.8	28.8
33	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.4	45.9	41.8	37.3	32.8	28.8
34	51.0	51.0	51.0	51.0	51.0	51.0	51.0	51.0	50.3	46.8	42.6	38.0	33.3	29.1
35	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	51.4	47.8	43.5	38.8	34.1	29.9
36	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	51.4	47.8	43.5	38.8	34.1	30.0
37	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	51.7	48.1	43.9	39.1	34.3	29.9
38	52.2	52.2	52.2	52.2	52.2	52.2	52.2	52.2	51.6	48.0	43.7	39.0	34.3	30.1
39	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	51.3	47.7	43.5	38.8	34.1	30.0
40	53.0	53.0	53.0	53.0	53.0	52.9	...	...	...	...	...	...	...	...
41	53.5	53.5	53.5	53.5	53.5	53.5	53.5	53.5	53.1	49.5	45.1	40.2	35.2	30.8
42	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
43	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
44	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
45	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

[illegible]

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	Carbon steel	Smls. & wld. pipe	SA-333	1
2	Carbon steel	Smls. & wld. tube	SA-334	1
3	Carbon steel	Plate	SA-516	55
4	Carbon steel	Smls. pipe	SA-524	II
5	Carbon steel	Wld. pipe	SA-671	CA55
6	Carbon steel	Wld. pipe	SA-671	CE55
7	Carbon steel	Wld. pipe	SA-672	A55
8	Carbon steel	Wld. pipe	SA-672	B55
9	Carbon steel	Wld. pipe	SA-672	C55
10	Carbon steel	Wld. pipe	SA-672	E55
11	Carbon steel	Sheet	SA-414	C
12	Carbon steel	Sheet, strip	SA-1011	40
13	Carbon steel	Sheet, strip	SA-1011	45
14	Carbon steel	Plate	SA/EN 10028-3	P275NH
15	Carbon steel	Plate, sheet, bar	SA-36	...
16	Carbon steel	Plate, sheet	SA-662	A
17	Carbon steel	Sheet, strip	SA-1011	36
18	Carbon steel	Plate	SA/EN 10028-2	P265GH
19	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH
20	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A
21	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR
22	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0
23	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C
24	Carbon steel	Forgings	SA-181	...
25	Carbon steel	Castings	SA-216	WCA
26	Carbon steel	Forgings	SA-266	1
27	Carbon steel	Bolting	SA-307	A
28	Carbon steel	Bolting	SA-307	B
29	Carbon steel	Forgings	SA-350	LF1
30	Carbon steel	Castings	SA-352	LCA
31	Carbon steel	Cast pipe	SA-660	WCA
32	Carbon steel	Bar	SA-675	60
33	Carbon steel	Forgings	SA-765	I
34	Carbon steel	Plate	SA-515	60
35	Carbon steel	Plate	SA-516	60
36	Carbon steel	Wld. pipe	SA-671	CB60
37	Carbon steel	Wld. pipe	SA-671	CC60
38	Carbon steel	Wld. pipe	SA-671	CE60
39	Carbon steel	Wld. pipe	SA-672	B60
40	Carbon steel	Wld. pipe	SA-672	C60
41	Carbon steel	Wld. pipe	SA-672	E60
42	Carbon steel	Wld. pipe	SA-134	A283D
43	Carbon steel	Plate	SA-283	D
44	Carbon steel	Wld. pipe	SA-53	E/B
45	Carbon steel	Smls. pipe	SA-53	S/B

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Design./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K03008	...	...	55
2	K03008	...	...	55
3	K01800	...	...	55
4	K02104	...	...	55
5	K02801	...	...	55
6	K02202	...	...	55
7	K02801	...	...	55
8	K02001	...	...	55
9	K01800	...	...	55
10	K02202	...	...	55
11	K02503	...	...	55
12	SS	...	$t \leq 0.23$	55
13	HSLAS	2	...	55
14	...	...	$\leq 2\frac{1}{4}$	56.5
15	K02600	...	...	58
16	K01701	...	...	58
17	SS	Type 2	$t \leq 0.23$	58
18	...	...	$\leq 2\frac{1}{4}$	59.5
19	...	...	$t \leq 2\frac{1}{2}$	59.5
20	...	...	...	59.5
21	...	...	...	59.5
22	...	...	...	59.5
23	...	...	...	59.5
24	K03502	60	...	60
25	J02502	...	...	60
26	K03506	...	...	60
27	...	...	$\frac{1}{4} \leq t \leq 4$	60
28	...	...	...	60
29	K03009	1	...	60
30	J02504	...	...	60
31	J02504	...	...	60
32	...	...	...	60
33	K03046	...	...	60
34	K02401	...	...	60
35	K02100	...	...	60
36	K02401	...	...	60
37	K02100	...	...	60
38	K02402	...	...	60
39	K02401	...	...	60
40	K02100	...	...	60
41	K02402	...	...	60
42	K02702	...	...	60
43	K02702	...	...	60
44	K03005	...	...	60
45	K03005	...	...	60

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
2	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
3	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
4	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
5	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
6	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
7	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
8	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
9	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
10	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
11	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	54.3	50.5	46.0	41.1	36.1	31.7
12	55.0	55.0	55.0	55.0	55.0	54.9	...	...	...	...	...	...	...	...
13	55.0	55.0	55.0	55.0	55.0	54.9	...	...	...	...	...	...	...	...
14	56.5	56.5	56.5	56.5	56.5	56.5	56.5	56.5	56.0	52.1	47.5	42.4	37.1	32.4
15	58.0	58.0	58.0	58.0	58.0	58.0	58.0	58.0	57.3	53.3	48.5	43.3	38.0	33.4
16	58.0	58.0	58.0	58.0	58.0	58.0	58.0	58.0	57.3	53.3	48.5	43.3	38.0	33.4
17	58.0	58.0	58.0	58.0	58.0	58.0	...	...	...	...	...	...	...	...
18	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	58.8	54.7	49.8	44.4	39.0	34.3
19	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	58.7	54.6	49.8	44.4	39.0	34.3
20	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	...	...	...	...	...	...
21	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	...	...	...	...	...	...
22	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	...	...	...	...	...	...
23	59.5	59.5	59.5	59.5	59.5	59.5	59.5	59.5	...	...	...	...	...	...
24	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
25	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
26	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
27	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
28	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
29	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
30	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
31	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
32	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
33	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
34	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
35	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
36	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
37	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
38	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
39	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
40	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
41	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
42	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
43	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
44	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
45	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	Carbon steel	Smls. pipe	SA-106	B
2	Carbon steel	Wld. pipe	SA-135	B
3	Carbon steel	Smls. & wld. ftgs.	SA-234	WPB
4	Carbon steel	Smls. & wld. pipe	SA-333	6
5	Carbon steel	Smls. & wld. tube	SA-334	6
6	Carbon steel	Forged pipe	SA-369	FPB
7	Carbon steel	Forgings	SA-372	A
8	Carbon steel	Sheet	SA-414	D
9	Carbon steel	Smls. & wld. ftgs.	SA-420	WPL6
10	Carbon steel	Smls. pipe	SA-524	I
11	Carbon steel	Bar	SA-696	B
12	Carbon steel	Forgings	SA-727	...
13	Carbon steel	Wld. tube	SA-178	C
14	Carbon steel	Smls. tube	SA-210	A-1
15	Carbon steel	Smls. tube	SA-556	B2
(25) 16	...	...	...	...
17	Carbon steel	Plate, bar	SA/CSA-G40.21	38W
18	Carbon steel	Plate, sheet, bar	SA-572	42
19	Carbon steel	Sheet, strip	SA-1011	45
20	Carbon steel	Sheet, strip	SA-1011	45
21	Carbon steel	Sheet, strip	SA-1011	50
22	Carbon steel	Plate	SA/AS 1548	PT430
23	Carbon steel	Plate	SA/EN 10028-2	P295GH
24	Carbon steel	Plate	SA/EN 10028-2	P295GH
25	Carbon steel	Bar	SA-675	65
26	Carbon steel	Castings	SA-352	LCB
27	Carbon steel	Plate	SA-515	65
28	Carbon steel	Plate	SA-516	65
29	Carbon steel	Wld. pipe	SA-671	CB65
30	Carbon steel	Wld. pipe	SA-671	CC65
31	Carbon steel	Wld. pipe	SA-672	B65
32	Carbon steel	Wld. pipe	SA-672	C65
33	Carbon steel	Sheet	SA-414	E
34	Carbon steel	Plate	SA-662	B
35	Carbon steel	Plate	SA-537	...
36	Carbon steel	Wld. pipe	SA-691	CMSH-70
37	Carbon steel	Plate, bar	SA/CSA-G40.21	44W
38	Carbon steel	Plate, bar	SA/CSA-G40.21	50W
39	Carbon steel	Plate, sheet, bar	SA-572	50
40	Carbon steel	Round bar	SA-572	50
41	Carbon steel	Sheet, strip	SA-1011	50
42	Carbon steel	Sheet, strip	SA-1011	50
(25) 43	Carbon steel	Bolting	SA-311	1018
44	Carbon steel	Sheet, strip	SA-1011	55
45	Carbon steel	Plate	SA/AS 1548	PT460

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K03006	...	...	60
2	...	...	...	60
3	K03006	...	...	60
4	K03006	...	...	60
5	K03006	...	...	60
6	K03006	...	...	60
7	K03002	...	...	60
8	K02505	...	...	60
9	...	...	...	60
10	K02104	...	...	60
11	K03200	...	...	60
12	K02506	...	...	60
13	K03503	...	...	60
14	K02707	...	...	60
15	K02707	...	...	60
16	...	...	...	...
17	...	...	...	60
18	...	...	$t \leq 6$	60
19	HSLAS	1	...	60
20	SS	...	$t \leq 0.23$	60
21	HSLAS	2	...	60
22	...	...	≤ 6	62.5
23	...	...	$6 < t \leq 10$	62.5
24	...	...	$4 < t \leq 6$	64
25	...	...	...	65
26	J03003	...	...	65
27	K02800	...	...	65
28	K02403	...	...	65
29	K02800	...	...	65
30	K02403	...	...	65
31	K02800	...	...	65
32	K02403	...	...	65
33	K02704	...	...	65
34	K02203	...	...	65
35	K12437	1	$2\frac{1}{2} < t \leq 4$	65
36	K12437	...	$2\frac{1}{2} < t \leq 4$	65
37	...	...	$t \leq 8$	65
38	...	...	$t \leq 6$	65
39	...	...	$t \leq 4$	65
40	...	...	$t \leq 11$	65
41	SS	...	$t \leq 0.23$	65
42	HSLAS	1	...	65
43	G10180	A	$\frac{7}{8} < t \leq 1\frac{1}{4}$	65
44	HSLAS	2	...	65
45	...	...	≤ 6	66.5

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
2	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
3	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
4	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
5	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
6	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
7	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
8	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
9	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
10	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
11	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
12	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
13	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
14	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
15	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	59.3	55.1	50.2	44.8	39.4	34.6
16	...	...	...	...	...	...	...	...	...	...	...	...	...	...
17	60.0	58.0	58.0	58.0	58.0	58.0	58.0	58.0	57.3	53.3	48.5	43.3	38.0	33.4
18	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...	...
19	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...	...
20	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...	...
21	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...	...
22	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	61.7	57.4	52.3	46.7	41.0	36.0
23	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	61.7	57.4	52.3	46.7	41.0	36.0
24	64.0	64.0	64.0	64.0	64.0	64.0	64.0	64.0	63.2	58.8	53.5	47.5	42.0	36.9
25	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
26	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
27	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
28	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
29	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
30	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
31	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
32	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
33	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
34	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
35	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
36	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.6	37.5
37	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.8	54.5	48.6	42.7	37.4
38	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.8	54.5	48.6	42.7	37.4
39	65.0	65.0	65.0	65.0	65.0	65.0	...	...	...	...	...	...	...	...
40	65.0	65.0	65.0	65.0	65.0	65.0	...	...	...	...	...	...	...	...
41	65.0	65.0	65.0	65.0	65.0	65.0	...	...	...	...	...	...	...	...
42	65.0	65.0	65.0	65.0	65.0	65.0	...	...	...	...	...	...	...	...
43	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	64.2	59.7	54.4	48.5	42.7	37.5
44	65.0	65.0	65.0	65.0	65.0	65.0	...	...	...	...	...	...	...	...
45	66.5	66.5	66.5	66.5	66.5	66.5	66.5	66.5	65.7	61.1	55.6	49.6	43.6	38.3

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	Carbon steel	Plate	SA/EN 10028-2	P295GH
2	Carbon steel	Forgings	SA/EN 10222-2	P280GH
3	Carbon steel	Plate	SA/EN 10028-2	P355GH
4	Carbon steel	Plate	SA/GB 713	Q345R
5	Carbon steel	Plate	SA/EN 10025-2	S355J2+N
6	Carbon steel	Plate	SA/EN 10028-2	P355GH
7	Carbon steel	Plate	SA/GB 713	Q345R
8	Carbon steel	Plate	SA-455	...
9	Carbon steel	Bar	SA-675	70
10	Carbon steel	Forgings	SA-105	...
11	Carbon steel	Forgings	SA-181	...
12	Carbon steel	Castings	SA-216	WCB
13	Carbon steel	Forgings	SA-266	2
14	Carbon steel	Forgings	SA-266	4
15	Carbon steel	Forgings	SA-350	LF2
16	Carbon steel	Forgings	SA-508	1
17	Carbon steel	Forgings	SA-508	1A
18	Carbon steel	Forgings	SA-541	1
19	Carbon steel	Forgings	SA-541	1A
20	Carbon steel	Cast pipe	SA-660	WCB
21	Carbon steel	Forgings	SA-765	II
22	Carbon steel	Plate	SA-515	70
23	Carbon steel	Plate	SA-516	70
24	Carbon steel	Wld. pipe	SA-671	CB70
25	Carbon steel	Wld. pipe	SA-671	CC70
26	Carbon steel	Wld. pipe	SA-672	B70
27	Carbon steel	Wld. pipe	SA-672	C70
28	Carbon steel	Smls. pipe	SA-106	C
29	Carbon steel	Wld. tube	SA-178	D
30	Carbon steel	Smls. tube	SA-210	C
31	Carbon steel	Castings	SA-216	WCC
32	Carbon steel	Smls. & wld. ftgs.	SA-234	WPC
33	Carbon steel	Castings	SA-352	LCC
34	Carbon steel	Castings	SA-487	16
35	Carbon steel	Plate	SA-537	...
36	Carbon steel	Smls. tube	SA-556	C2
37	...	...	...	...
38	Carbon steel	Cast pipe	SA-660	WCC
39	Carbon steel	Bar	SA-696	C
40	Carbon steel	Sheet	SA-414	F
41	Carbon steel	Plate	SA-662	C
42	Carbon steel	Plate	SA-537	...
43	Carbon steel	Plate	SA-738	C
44	Carbon steel	Plate	SA-537	...
45	Carbon steel	Wld. pipe	SA-671	CD70

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	...	...	≤ 4	66.5
2	...	N, NT, or QT	$t \leq 6.3$	66.5
3	...	...	$6 < t \leq 10$	68
4	...	...	$6 < t \leq 10$	68
5	...	...	$0.12 < t \leq 3.15$	68
6	...	...	$4 < t \leq 6$	69.5
7	...	...	$4 < t \leq 6$	69.5
8	K03300	...	$0.58 < t \leq \frac{3}{4}$	70
9	...	...	...	70
10	K03504	...	...	70
11	K03502	70	...	70
12	J03002	...	...	70
13	K03506	...	...	70
14	K03017	...	...	70
15	K03011	...	...	70
16	K13502	...	...	70
17	K13502	...	...	70
18	K03506	...	...	70
19	K03020	...	...	70
20	J03003	...	...	70
21	K03047	...	...	70
22	K03101	...	...	70
23	K02700	...	...	70
24	K03101	...	...	70
25	K02700	...	...	70
26	K03101	...	...	70
27	K02700	...	...	70
28	K03501	...	...	70
29	...	...	...	70
30	K03501	...	...	70
31	J02503	...	...	70
32	K03501	...	...	70
33	J02505	...	...	70
34	...	A	...	70
35	K12437	3	$4 < t \leq 6$	70
36	K03006	...	...	70
37	...	...	...	...
38	J02505	...	...	70
39	K03200	...	...	70
40	K03102	...	...	70
41	K02007	...	...	70
42	K12437	2	$4 < t \leq 6$	70
43	K02008	...	$4 < t \leq 6$	70
44	K12437	1	$\leq 2\frac{1}{2}$	70
45	K12437	...	$\leq 2\frac{1}{2}$	70

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	66.5	66.5	66.5	66.5	66.5	66.5	66.5	66.5	65.7	61.1	55.6	49.6	43.6	38.3
2	66.7	66.7	66.7	66.7	66.7	66.7	66.7	66.7	65.7	61.2	55.8	49.8	43.6	38.1
3	68.0	68.0	68.0	68.0	68.0	68.0	68.0	68.0	65.5	62.2	57.5	51.7	45.0	37.7
4	68.2	68.2	68.2	68.2	68.2	68.2	68.2	68.2	67.3	62.5	56.9	50.7	44.5	39.4
5	68.2	...	...	...	...	...	...	...	...	...	...	...	...	...
6	69.5	69.5	69.5	69.5	69.5	69.5	69.5	69.5	66.9	63.5	58.8	52.8	45.9	38.5
7	69.6	69.6	69.6	69.6	69.6	69.6	69.6	69.6	68.7	63.9	58.1	51.7	45.5	40.2
8	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
9	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
10	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
11	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
12	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
13	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
14	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
15	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
16	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
17	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
18	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
19	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
20	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
21	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
22	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
23	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
24	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
25	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
26	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
27	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
28	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
29	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
30	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
31	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
32	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
33	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
34	70.0	69.5	65.7	63.3	62.6	62.6	62.6	62.6	62.3	59.2	...	...	...	...
35	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
36	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
37	...	...	...	...	...	...	...	...	...	...	...	...	...	...
38	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
39	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
40	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
41	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.1	64.3	58.6	52.3	45.9	40.4
42	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
43	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
44	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
45	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	Carbon steel	Wld. pipe	SA-672	D70
2	Carbon steel	Wld. pipe	SA-691	CMSH-70
3	Carbon steel	Plate	SA-841	A
4	Carbon steel	Plate, sheet, bar	SA-572	55
5	Carbon steel	Round bar	SA-572	55
6	Carbon steel	Sheet, strip	SA-1011	55
(25) 7	Carbon steel	Bolting	SA-311	1018
8	Carbon steel	Sheet, strip	SA-1011	60
(25) 9	Carbon steel	Forgings	SA/EN 10222-2	P305GH
10	Carbon steel	Plate	SA/EN 10028-2	P355GH
11	Carbon steel	Plate	SA/GB 713	Q345R
12	Carbon steel	Plate	SA/GB 713	Q345R
13	Carbon steel	Plate	SA-455	...
(25) 14	Carbon steel	Forgings	SA/EN 10222-2	P305GH
15	Carbon steel	Plate	SA/EN 10028-2	P355GH
16	Carbon steel	Plate	SA/GB 713	Q345R
17	Carbon steel	Plate	SA/EN 10025-2	S355J2+N
18	Carbon steel	Forgings	SA-266	3
19	Carbon steel	Plate	SA-455	...
20	Carbon steel	Plate	SA-299	A
21	Carbon steel	Wld. pipe	SA-671	CK75
22	Carbon steel	Wld. pipe	SA-672	N75
23	Carbon steel	Wld. pipe	SA-691	CMS-75
24	Carbon steel	Plate	SA-299	A
25	Carbon steel	Wld. pipe	SA-691	CMS-75
26	Carbon steel	Forgings	SA-372	B
27	Carbon steel	Sheet	SA-414	G
28	Carbon steel	Plate	SA-738	A
29	Carbon steel	Plate	SA-537	...
30	Carbon steel	Plate	SA-537	...
31	Carbon steel	Wld. pipe	SA-691	CMSH-80
32	Carbon steel	Plate	SA-738	C
33	Carbon steel	Plate, sheet, bar	SA-572	60
34	Carbon steel	Round bar	SA-572	60
35	Carbon steel	Sheet, strip	SA-1011	60
36	Carbon steel	Plate	SA-299	B
37	Carbon steel	Plate	SA-299	B
38	Carbon steel	Forgings	SA-765	IV
39	Carbon steel	Plate	SA-537	...
40	Carbon steel	Plate	SA-537	...
41	Carbon steel	Wld. pipe	SA-671	CD80
42	Carbon steel	Wld. pipe	SA-672	D80
43	Carbon steel	Wld. pipe	SA-691	CMSH-80
44	Carbon steel	Plate	SA-738	C
45	Carbon steel	Plate	SA-841	B

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K12437	...	$\leq 2\frac{1}{2}$	70
2	K12437	...	$\leq 2\frac{1}{2}$	70
3	...	1	≤ 4	70
4	...	...	$t \leq 2$	70
5	...	...	$t \leq 3\frac{1}{2}$	70
6	HSLAS	1	...	70
7	G10180	A	$t \leq \frac{7}{8}$	70
8	HSLAS	2	...	70
9	...	N, NT, or QT	$2.8 < t \leq 6.3$	71
10	...	...	$2.5 < t \leq 4$	71
11	...	...	$1.5 < t \leq 4$	71
12	...	...	$\frac{5}{8} < t \leq 1.5$	72.5
13	K03300	...	$\frac{3}{8} < t \leq \frac{5}{8}$	73
14	...	N, NT, or QT	$t \leq 2.8$	74
15	...	...	≤ 2.5	74
16	...	...	$\frac{1}{8} \leq t \leq \frac{5}{8}$	74
17	...	...	$t < 0.12$	74
18	K05001	...	...	75
19	K03300	...	$\leq \frac{3}{8}$	75
20	K02803	...	> 1	75
21	K02803	...	> 1	75
22	K02803	...	> 1	75
23	K02803	...	> 1	75
24	K02803	...	≤ 1	75
25	K02803	...	≤ 1	75
26	K04001	...	...	75
27	K03103	...	...	75
28	K12447	...	...	75
29	K12437	3	$2\frac{1}{2} < t \leq 4$	75
30	K12437	2	$2\frac{1}{2} < t \leq 4$	75
31	K12437	...	$2\frac{1}{2} < t \leq 4$	75
32	K02008	...	$2\frac{1}{2} < t \leq 4$	75
33	...	...	$t \leq 1\frac{1}{4}$	75
34	...	...	$t \leq 3\frac{1}{2}$	75
35	HSLAS	1	...	75
36	K02803	...	> 1	80
37	K02803	...	≤ 1	80
38	K02009	...	...	80
39	K12437	3	$\leq 2\frac{1}{2}$	80
40	K12437	2	$\leq 2\frac{1}{2}$	80
41	K12437	...	$\leq 2\frac{1}{2}$	80
42	K12437	...	$\leq 2\frac{1}{2}$	80
43	K12437	...	$\leq 2\frac{1}{2}$	80
44	K02008	...	$\leq 2\frac{1}{2}$	80
45	...	2	≤ 4	80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
2	70.0	70.0	69.1	68.4	68.4	68.4	68.4	68.4	67.7	65.4	...	...	...	...
3	70.0	70.0	70.0	70.0	70.0	69.9	68.4	...	...	...	...	...	...	...
4	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...
5	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...
6	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...
7	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.2	64.3	58.6	52.3	46.0	40.4
8	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...
9	71.1	71.1	71.1	71.1	71.1	71.1	71.1	71.1	70.0	65.2	59.4	53.0	46.5	40.6
10	71.0	71.0	71.0	71.0	71.0	71.0	71.0	71.0	68.3	64.8	60.0	53.9	46.9	39.3
11	71.1	71.1	71.1	71.1	71.1	71.1	71.1	71.1	70.1	65.2	59.3	52.8	46.4	41.0
12	72.5	72.5	72.5	72.5	72.5	72.5	72.5	72.5	71.6	66.5	60.5	53.9	47.4	41.9
13	73.0	73.0	73.0	73.0	73.0	73.0	73.0	73.0	72.1	67.1	61.1	54.5	47.9	42.1
14	74.0	74.0	74.0	74.0	74.0	74.0	74.0	74.0	72.9	67.9	61.8	55.2	48.4	42.2
15	74.0	74.0	74.0	74.0	74.0	74.0	74.0	74.0	71.1	67.5	62.4	56.1	48.8	40.9
16	74.0	74.0	74.0	74.0	74.0	74.0	74.0	74.0	73.0	67.9	61.7	55.0	48.3	42.7
17	74.0	...	...	...	...	...	...	...	...	...	...	...	...	...
18	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
19	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
20	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
21	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
22	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
23	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
24	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
25	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
26	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
27	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
28	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.1	68.9	62.8	56.0	49.2	43.2
29	75.0	75.0	74.0	73.3	73.2	73.2	73.2	73.2	72.5	70.1	...	...	...	...
30	75.0	75.0	74.0	73.3	73.2	73.2	73.2	73.2	72.5	70.1	...	...	...	...
31	75.0	75.0	74.0	73.3	73.2	73.2	73.2	73.2	72.5	70.1	...	...	...	...
32	75.0	75.0	74.0	73.3	73.2	73.2	73.2	73.2	72.5	70.1	...	...	...	...
33	75.0	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...
34	75.0	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...
35	75.0	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...
36	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.0	73.5	66.9	59.7	52.5	46.1
37	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.0	73.5	66.9	59.7	52.5	46.1
38	80.0	80.0	80.0	79.1	79.1	79.1	78.8	77.7	...	...	...	...	...	...
39	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
40	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
41	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
42	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
43	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
44	80.0	80.0	78.9	78.2	78.1	78.1	78.1	78.1	77.4	74.8	...	...	...	...
45	80.0	80.0	80.0	80.0	80.0	79.9	78.2	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
	1 Carbon steel	Plate, sheet, bar	SA-572	65
(25)	2 Carbon steel	Bolting	SA-311	1035
	3 Carbon steel	Plate	SA-612	...
	4 Carbon steel	Plate	SA-841	F
	5 Carbon steel	Plate	SA-612	...
	6 Carbon steel	Plate	SA-738	B
(25)	7 Carbon steel	Bolting	SA-311	1035
	8 Carbon steel	Plate	SA-841	F
	9 Carbon steel	Forgings	SA-372	C
	10 Carbon steel	Bolting	SA-449	...
	11 Carbon steel	Plate	SA-724	A
	12 Carbon steel	Plate	SA-724	C
(25)	13 Carbon steel	Bolting	SA-311	1045
	14 Carbon steel	Plate	SA-724	B
(25)	15 Carbon steel	Bolting	SA-311	1045
(25)	16 Carbon steel	Bolting	SA-311	1050
(25)	17 Carbon steel	Bolting	SA-311	1050
(25)	18 ...	...	...	...
(25)	19 Carbon steel	Bolting	SA-325	1
	20 Carbon steel	Bolting	SA-449	...
	21 Carbon steel	Bolting	SA-354	BC
(25)	22 Carbon steel	Bolting	SA-311	1045
	23 Carbon steel	Bolting	SA-325	1
	24 Carbon steel	Bolting	SA-449	...
	25 Carbon steel	Bolting	SA-354	BC
	26 Carbon steel	Bolting	SA-354	BD
	27 Carbon steel	Bolting	SA-354	BD
(25)	28 Carbon steel	Flat wire	SA-905	...
(25)	29 Carbon steel	Flat wire	SA-905	...
(25)	30 Carbon steel	Flat wire	SA-905	...
(25)	31 Carbon steel	Flat wire	SA-905	...
(25)	32 Carbon steel	Flat wire	SA-905	...
(25)	33 Carbon steel	Flat wire	SA-905	...
(25)	34 Carbon steel	Flat wire	SA-905	...
(25)	35 Carbon steel	Flat wire	SA-905	...
(25)	36 Carbon steel	Flat wire	SA-905	...
(25)	37 Carbon steel	Flat wire	SA-905	...
	38 Ductile cast iron	Castings	SA-874	...
	39 Ductile cast iron	Castings	SA/JIS G5504	FCD 300 LT
	40 C-Mn-Si-Cb	Plate	SA-737	B
	41 C-Mn-Si-Cb	Plate	SA/AS 1548	PT490
	42 C-Mn-Si-Cb	Plate	SA/GB 713	Q370R
	43 C-Mn-Si-Cb	Plate	SA/GB 713	Q370R
	44 C-Mn-Si-Cb	Plate	SA/GB 713	Q370R
	45 C-Mn-Si-V	Plate	SA-737	C

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	...	...	$t \leq 1\frac{1}{4}$	80
2	G10350	A	$\frac{7}{8} < t \leq 1\frac{1}{4}$	80
3	K02900	...	$\frac{1}{2} < t \leq 1$	81
4	...	6	$t \leq 1.25$	82
5	K02900	...	$\leq \frac{1}{2}$	83
6	K12007	...	...	85
7	G10350	A	$t \leq \frac{7}{8}$	85
8	...	7	$t \leq 1$	86
9	K04801	...	...	90
10	K04200	...	$1\frac{1}{2} < t \leq 3$	90
11	K11831	...	...	90
12	K12037	...	...	90
13	G10450	A	$\frac{7}{8} < t \leq 1\frac{1}{4}$	90
14	K12031	...	...	95
15	G10450	A	$t \leq \frac{7}{8}$	95
16	G10500	A	$\frac{7}{8} < t \leq 1\frac{1}{4}$	95
17	G10500	A	$t \leq \frac{7}{8}$	100
18	...	...	...	...
19	K02706	...	$1 < t \leq 1\frac{1}{2}$	105
20	K04200	...	$1 < t < 1\frac{1}{2}$	105
21	K04100	...	$2\frac{1}{2} < t \leq 4$	115
22	G10450	B	$t \leq 3$	115
23	K02706	...	$\frac{1}{2} \leq t \leq 1$	120
24	K04200	...	≤ 1	120
25	K04100	...	$\frac{1}{4} < t \leq 2\frac{1}{2}$	125
26	K04100	...	$2\frac{1}{2} < t \leq 4$	140
27	K04100	...	$\frac{1}{4} < t \leq 2\frac{1}{2}$	150
28	...	2	0.059	246
29	...	2	0.051	250
30	...	2	0.040	256
31	...	2	0.030	262
32	...	2	0.020	268
33	...	1	0.059	275
34	...	1	0.051	280
35	...	1	0.040	285
36	...	1	0.030	290
37	...	1	0.020	296
38	...	...	$12 < t < 21$	43.5
39	...	...	$12 < t < 21$	43.5
40	K12001	...	...	70
41	...	...	≤ 6	71
42	...	Normalized	$2.5 < t \leq 4$	74
43	...	Normalized	$1.5 < t \leq 2.5$	75.5
44	...	Normalized	$0.4 < t \leq 1.5$	77
45	K12202	...	...	80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	80.0	80.0	80.0	80.0	80.0	79.9	...	...	...	...	...	...	...	...
2	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	73.5	66.9	59.7	52.5	46.1
3	81.0	81.0	79.4	79.4	79.4	79.4	79.4	79.4	...	...	...	...	...	...
4	82.0	82.0	82.0	82.0	82.0	81.8	80.2	...	...	...	...	...	...	...
5	83.0	83.0	81.3	81.3	81.3	81.3	81.3	81.3	...	...	...	...	...	...
6	85.0	85.0	85.0	85.0	85.0	84.2	83.0	81.0	78.3	74.6	...	...	...	...
7	85.0	85.0	85.0	85.0	85.0	85.0	85.0	85.0	84.0	78.1	71.1	63.5	55.8	49.0
8	86.0	86.0	86.0	86.0	86.0	85.8	84.2	...	...	...	...	...	...	...
9	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	88.9	82.7	75.3	67.2	59.0	51.9
10	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	88.9	82.7	75.3	67.2	59.0	51.9
11	90.0	90.0	88.8	87.9	87.9	87.9	87.9	87.9	87.0	84.1	...	...	...	...
12	90.0	90.0	88.8	87.9	87.9	87.9	87.9	87.9	87.0	84.1	...	...	...	...
13	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	89.0	82.7	75.3	67.2	59.1	51.9
14	95.0	95.0	93.7	92.8	92.8	92.8	92.8	92.8	91.9	88.8	...	...	...	...
15	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	93.9	87.2	79.5	70.9	62.4	54.8
16	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	93.9	87.2	79.5	70.9	62.4	54.8
17	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	98.8	91.8	83.7	74.7	65.7	57.7
18	...	...	...	...	...	...	...	...	...	...	...	...	...	...
19	105.0	105.0	103.6	102.6	102.5	102.5	102.5	102.5	101.5	98.1	91.5	80.3	62.5	35.8
20	105.0	105.0	103.6	102.6	102.5	102.5	102.5	102.5	101.5	98.1	91.5	80.3	62.5	35.8
21	115.0	115.0	115.0	115.0	115.0	115.0	115.0	113.6	105.7	96.2	85.8	75.4	66.3	...
22	115.0	115.0	115.0	115.0	115.0	115.0	115.0	115.0	113.7	105.6	96.2	85.9	75.5	66.3
23	120.0	120.0	118.4	117.3	117.2	117.2	117.2	117.2	116.1	112.1	104.6	91.8	71.5	41.0
24	120.0	120.0	118.4	117.3	117.2	117.2	117.2	117.2	116.1	112.1	104.6	91.8	71.5	41.0
25	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	123.5	114.8	104.6	93.3	82.0	72.1
26	140.0	140.0	140.0	140.0	140.0	140.0	140.0	140.0	138.3	128.6	117.1	104.5	91.8	80.7
27	150.0	150.0	150.0	150.0	150.0	150.0	150.0	150.0	147.8	137.3	124.9	111.3	97.6	85.5
28	246.0	...	...	...	...	...	...	...	...	...	...	...	...	...
29	250.0	...	...	...	...	...	...	...	...	...	...	...	...	...
30	256.0	...	...	...	...	...	...	...	...	...	...	...	...	...
31	262.0	...	...	...	...	...	...	...	...	...	...	...	...	...
32	268.0	...	...	...	...	...	...	...	...	...	...	...	...	...
33	275.0	257.7	...	...	...	...	...	...	...	...	...	...	...	...
34	280.0	262.7	...	...	...	...	...	...	...	...	...	...	...	...
35	285.0	266.8	...	...	...	...	...	...	...	...	...	...	...	...
36	290.0	271.8	...	...	...	...	...	...	...	...	...	...	...	...
37	296.0	277.8	...	...	...	...	...	...	...	...	...	...	...	...
38	43.5	43.4	41.3	39.9	39.1	38.4	37.6	...	...	...	...	...	...	...
39	43.5	43.4	41.3	39.9	39.1	38.4	37.6	...	...	...	...	...	...	...
40	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.4	66.7	63.0	58.2	52.7	47.0	...
41	71.0	71.0	71.0	71.0	71.0	71.0	71.0	70.4	67.7	63.9	59.1	53.5	47.6	42.2
42	74.0	74.0	74.0	74.0	74.0	74.0	74.0	74.0	70.9	66.4	61.1	55.4	49.6	44.0
43	75.4	75.4	75.4	75.4	75.4	75.4	75.4	75.4	72.3	67.7	62.3	56.5	50.6	45.0
44	76.9	76.9	76.9	76.9	76.9	76.9	76.9	76.9	73.7	69.0	63.5	57.6	51.5	45.9
45	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.4	76.3	72.0	66.5	60.3	53.7	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	C-Mn-Si-V-Cb	Plate	SA-656	T3
2	C-Mn-Si-V-Cb	Plate	SA-656	T7
3	C-Mn-Si-V-Cb	Plate	SA-656	T3
4	C-Mn-Si-V-Cb	Plate	SA-656	T7
5	C-Mn-Si-V-Cb	Plate	SA-656	T3
6	C-Mn-Si-V-Cb	Plate	SA-656	T7
7	C-Mn-Si-V-Cb	Plate	SA-656	T3
8	C-Mn-Si-V-Cb	Plate	SA-656	T7
9	C-Mn-Ti	Plate, sheet	SA-562	...
10	C-Si-Ti	Forgings	SA-836	...
11	C- $\frac{1}{4}$ Mo	Bolting	SA-320	L7A
(25) 12	Alloy steel	Bolting	SA/ISO 898-1	8.8
(25) 13	Alloy steel	Bolting	SA/ISO 898-1	8.8
14	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037
15	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042
16	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4140
17	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037
18	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042
19	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3
20	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1b
21	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1b
22	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1
23	C- $\frac{1}{2}$ Mo	Smls. & wld. ftgs.	SA-234	WP1
24	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1
25	C- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P1
26	C- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP1
27	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1a
28	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1a
29	C- $\frac{1}{2}$ Mo	Castings	SA-217	WC1
30	C- $\frac{1}{2}$ Mo	Castings	SA-352	LC1
31	C- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP1
32	C- $\frac{1}{2}$ Mo	Plate	SA-204	A
33	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L65
34	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-65
35	C- $\frac{1}{2}$ Mo	Forgings	SA-182	F1
36	C- $\frac{1}{2}$ Mo	Plate	SA-204	B
37	C- $\frac{1}{2}$ Mo	Forgings	SA-336	F1
38	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L70
39	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-70
40	C- $\frac{1}{2}$ Mo	Plate	SA-204	C
41	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L75
42	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-75
43	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G
44	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H
45	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	...	...	≤ 2	60
2	...	...	≤ 2	60
3	...	...	$\leq 1\frac{1}{2}$	70
4	...	...	$\leq 1\frac{1}{2}$	70
5	...	...	≤ 1	80
6	...	...	≤ 1	80
7	...	...	$\leq \frac{3}{4}$	90
8	...	...	$\leq \frac{3}{4}$	90
9	K11224	...	...	55
10	...	1	...	55
11	G40370	...	$\leq 2\frac{1}{2}$	125
12	...	...	$d \leq \frac{5}{8}$	116
13	...	...	$d > \frac{5}{8}$	120
14	G40370	...	$\geq \frac{5}{8}$	170
15	G40420	...	$\geq \frac{5}{8}$	170
16	G41400	...	$\geq \frac{5}{8}$	170
17	G40370	...	$\leq \frac{1}{2}$	180
18	G40420	...	$\leq \frac{1}{2}$	180
19	...	...	$t \leq 2\frac{1}{2}$	65.5
20	K11422	...	...	53
21	K11422	...	...	53
22	K11522	...	...	55
23	K12821	...	...	55
24	K11522	...	...	55
25	K11522	...	...	55
26	K11522	...	...	55
27	K12023	...	...	60
28	K12023	...	...	60
29	J12524	...	...	65
30	J12522	...	...	65
31	J12521	...	...	65
32	K11820	...	...	65
33	K11820	...	...	65
34	K11820	...	...	65
35	K12822	...	...	70
36	K12020	...	...	70
37	K12520	...	...	70
38	K12020	...	...	70
39	K12020	...	...	70
40	K12320	...	...	75
41	K12320	...	...	75
42	K12320	...	...	75
43	K13049	55	...	85
44	K13547	55	...	85
45	K13049	65	...	105

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	60.0	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...
2	60.0	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...	...	...	...	...
3	70.0	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...
4	70.0	70.0	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...
5	80.0	80.0	80.0	80.0	80.0	80.0	80.0	...	...	...	...	...	...	...
6	80.0	80.0	80.0	80.0	80.0	80.0	80.0	...	...	...	...	...	...	...
7	90.0	90.0	90.0	90.0	90.0	90.0	90.0	...	...	...	...	...	...	...
8	90.0	90.0	90.0	90.0	90.0	90.0	90.0	...	...	...	...	...	...	...
9	55.0	44.4	41.5	39.5	38.1	36.9	36.3	35.6	34.8	...	...	...	...	...
10	55.0	54.3	50.7	48.3	46.6	45.1	44.3	43.5	42.5	...	...	...	...	...
11	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	123.5	114.8	104.6	93.3	82.0	72.1
12	116.0	116.0	116.0	...	...	...	...	...	...	...	...	...	...	...
13	120.0	120.0	120.0	...	...	...	...	...	...	...	...	...	...	...
14	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	166.0	158.1	148.4	137.2
15	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	166.0	158.1	148.4	137.2
16	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	170.0	166.0	158.1	148.4	137.2
17	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	175.8	167.4	157.2	145.3
18	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	180.0	175.8	167.4	157.2	145.3
19	65.3	65.3	65.3	65.3	65.3	65.3	65.3	65.3	65.3	65.3	63.7	60.7	57.0	52.7
20	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	51.8	49.3	46.3	42.8
21	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	53.0	51.8	49.3	46.3	42.8
22	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
23	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
24	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
25	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
26	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
27	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.6	55.8	52.4	48.4
28	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.6	55.8	52.4	48.4
29	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
30	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
31	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
32	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
33	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
34	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	65.0	63.5	60.4	56.8	52.5
35	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
36	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
37	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
38	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
39	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
40	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	73.2	69.7	65.5	60.5
41	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	73.2	69.7	65.5	60.5
42	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	73.2	69.7	65.5	60.5
43	85.0	85.0	85.0	85.0	85.0	85.0	85.0	82.2	78.2	73.8	68.9	63.8	58.7	53.6
44	85.0	85.0	85.0	85.0	85.0	85.0	85.0	82.2	78.2	73.8	68.9	63.8	58.7	53.6
45	105.0	105.0	105.0	105.0	105.0	105.0	105.0	102.0	96.6	91.1	85.2	78.9	72.5	66.3

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)
(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	H
2	$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	G
3	$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	H
4	$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}-\text{V}$	Plate	SA-517	B
5	$\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{Si}$	Plate	SA-517	A
6	$\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{Si}$	Forgings	SA-592	A
7	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P2
8	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP2
9	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2
10	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$
11	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T2
12	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP2
13	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F2
14	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2
15	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$
16	$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	Wld. tube	SA-423	1
17	$\frac{3}{4}\text{Cr}-\frac{3}{4}\text{Ni}-\text{Cu}-\text{Al}$	Pipe	SA-333	4
(25) 18	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 19	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 20	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 21	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 22	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 23	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 24	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 25	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 26	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 27	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 28	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 29	0.7Cr-1.5Si	Wire	SA-401	9254
(25) 30	0.7Cr-1.5Si	Wire	SA-401	9254
31	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	E
32	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	F
33	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	J
34	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7
(25) 35	Alloy steel	Bolting	SA/ISO 898-1	9.8
(25) 36	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7M
37	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-320	L7M
38	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	F
39	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7
40	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	E
41	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	F
42	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	J
43	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7
44	1Cr- $\frac{1}{5}\text{Mo}$	Bolting	SA-320	L7
45	1Cr- $\frac{1}{5}\text{Mo}$	Forgings	SA-372	J

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K13547	65	...	105
2	K13547	70	...	120
3	K13547	70	...	120
4	K11630	...	$\leq 1\frac{1}{4}$	115
5	K11856	...	$\leq 1\frac{1}{4}$	115
6	K11856	...	$\leq 2\frac{1}{2}$	115
7	K11547	...	...	55
8	K11547	...	...	55
9	K12143	1	...	55
10	K12143	...	...	55
11	K11547	...	...	60
12	J11547	...	...	60
13	K12122	...	...	70
14	K12143	2	...	70
15	K12143	...	...	70
16	K11535	...	...	60
17	K11267	...	...	60
18	G92540	QT	0.25	250
19	G92540	QT	0.219	255
20	G92540	QT	0.192	260
21	G92540	QT	0.177	260
22	G92540	QT	0.162	265
23	G92540	QT	0.135	270
24	G92540	QT	0.12	275
25	G92540	QT	0.092	280
26	G92540	QT	0.08	285
27	G92540	QT	0.062	290
28	G92540	QT	0.054	292
29	G92540	QT	0.041	298
30	G92540	QT	0.032	300
31	K13047	55	...	85
32	G41350	55	...	85
33	K13548	55	...	85
34	G41400	...	$4 < t \leq 7$	100
35	...	...	$d \leq \frac{5}{8}$	130.5
36	G41400	...	≤ 4	100
37	G41400	...	$\leq 2\frac{1}{2}$	100
38	G41350	65	...	105
39	G41400	...	$2\frac{1}{2} < t \leq 4$	115
40	K13047	70	...	120
41	G41350	70	...	120
42	K13548	70	...	120
43	G41400	...	$\leq 2\frac{1}{2}$	125
44	G41400	...	$\leq 2\frac{1}{2}$	125
45	G41370	110	...	135

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	105.0	105.0	105.0	105.0	105.0	105.0	105.0	102.0	96.6	91.1	85.2	78.9	72.5	66.3
2	120.0	120.0	120.0	120.0	120.0	120.0	119.2	115.2	110.3	104.4	97.7	90.4	82.9	75.5
3	120.0	120.0	120.0	120.0	120.0	120.0	119.2	115.2	110.3	104.4	97.7	90.4	82.9	75.5
4	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
5	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
6	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
7	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
8	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
9	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
10	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	53.7	51.1	48.0	44.4
11	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.6	55.8	52.4	48.4
12	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.6	55.8	52.4	48.4
13	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
14	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
15	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.4	65.1	61.1	56.5
16	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...
17	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	...	...	...
18	250	...	...	...	...	...	...	...	...	...	...	...	...	...
19	255	...	...	...	...	...	...	...	...	...	...	...	...	...
20	260	...	...	...	...	...	...	...	...	...	...	...	...	...
21	260	...	...	...	...	...	...	...	...	...	...	...	...	...
22	265	...	...	...	...	...	...	...	...	...	...	...	...	...
23	270	...	...	...	...	...	...	...	...	...	...	...	...	...
24	275	...	...	...	...	...	...	...	...	...	...	...	...	...
25	280	...	...	...	...	...	...	...	...	...	...	...	...	...
26	285	...	...	...	...	...	...	...	...	...	...	...	...	...
27	290	...	...	...	...	...	...	...	...	...	...	...	...	...
28	292	...	...	...	...	...	...	...	...	...	...	...	...	...
29	298	...	...	...	...	...	...	...	...	...	...	...	...	...
30	300	...	...	...	...	...	...	...	...	...	...	...	...	...
31	85.0	85.0	85.0	85.0	85.0	85.0	85.0	82.2	78.2	73.8	68.9	63.8	58.7	53.6
32	85.0	85.0	85.0	85.0	85.0	85.0	85.0	82.2	78.2	73.8	68.9	63.8	58.7	53.6
33	85.0	85.0	85.0	85.0	85.0	85.0	85.0	82.2	78.2	73.8	68.9	63.8	58.7	53.6
34	100.0	100.0	100.0	100.0	100.0	100.0	100.0	95.7	91.4	86.7	81.4	75.7	69.4	62.7
35	130.5	130.5	130.5	...	...	...	...	...	...	...	...	...	...	...
36	100.0	100.0	100.0	100.0	100.0	100.0	100.0	95.7	91.4	86.7	81.4	75.7	69.4	62.7
37	100.0	100.0	100.0	100.0	100.0	100.0	100.0	95.7	91.4	86.7	81.4	75.7	69.4	62.7
38	105.0	105.0	105.0	105.0	105.0	105.0	105.0	102.0	96.6	91.1	85.2	78.9	72.5	66.3
39	115.0	115.0	115.0	115.0	115.0	115.0	114.5	110.1	105.1	99.7	93.6	87.0	79.8	72.1
40	120.0	120.0	120.0	120.0	120.0	120.0	119.2	115.2	110.3	104.4	97.7	90.4	82.9	75.5
41	120.0	120.0	120.0	120.0	120.0	120.0	119.2	115.2	110.3	104.4	97.7	90.4	82.9	75.5
42	120.0	120.0	120.0	120.0	120.0	120.0	119.2	115.2	110.3	104.4	97.7	90.4	82.9	75.5
43	125.0	125.0	125.0	125.0	125.0	125.0	124.4	119.6	114.3	108.4	101.8	94.6	86.8	78.4
44	125.0	125.0	125.0	125.0	125.0	125.0	124.4	119.6	114.3	108.4	101.8	94.6	86.8	78.4
45	135.0	135.0	135.0	135.0	135.0	135.0	134.1	129.7	124.0	117.4	109.9	101.7	93.3	85.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
(25) 1	1Cr- $\frac{1}{5}$ Mo-B	Forgings	SA-372	R
2	1Cr- $\frac{1}{2}$ Mo	Plate	SA-387	12
3	1Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	1CR
4	1Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP12
5	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12
6	1Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T12
7	1Cr- $\frac{1}{2}$ Mo	Smls. & wld. ftgs.	SA-234	WP12
8	1Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P12
9	1Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP12
10	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5
11	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5
12	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5
13	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5
14	1Cr- $\frac{1}{2}$ Mo	Smls. tube	SA/EN 10216-2	13CrMo4-5
15	1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR
16	1Cr- $\frac{1}{2}$ Mo	Forgings	SA/EN 10222-2	13CrMo4-5
17	1Cr- $\frac{1}{2}$ Mo	Plate	SA-387	12
18	1Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	1CR
19	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5
20	1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR
21	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12
22	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F12
23	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16
24	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16
25	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
26	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
27	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16
28	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
29	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
30	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
31	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21
32	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
33	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
34	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
35	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
36	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
37	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
38	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
39	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
40	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
41	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
42	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
43	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
44	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
45	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	G41371	110	...	135
2	K11757	1	...	55
3	K11757	...	...	55
4	J11562	...	...	60
5	K11562	1	...	60
6	K11562	...	...	60
7	K12062	1	...	60
8	K11562	...	...	60
9	K11562	...	...	60
10	...	NT or QT	$10 < t \leq 20$	61
11	...	...	$6 < t \leq 10$	61
12	...	...	$4 < t \leq 6$	62.5
13	...	...	$2.5 < t \leq 4$	64
14	...	...	$t \leq 2\frac{1}{2}$	64
15	...	...	$4 < t \leq 8$	64
16	...	NT or QT	$t \leq 10$	64
17	K11757	2	...	65
18	K11757	...	...	65
19	...	...	$t \leq 2.5$	65.5
20	...	...	$0.25 \leq t \leq 4$	65.5
21	K11564	2	...	70
22	K11564	...	...	70
23	K14072	...	$4 < t \leq 8$	100
24	K14072	...	$2\frac{1}{2} < t \leq 4$	110
25	K14073	5	$2 < t \leq 8$	115
26	K14073	5	≤ 2	120
27	K14072	...	$\leq 2\frac{1}{2}$	125
28	K14073	4	≤ 6	135
29	K14073	3	≤ 6	145
30	K14073	2	≤ 4	155
31	K14073	1	≤ 4	165
32	...	Oil	0.020	300
33	...	Oil	0.020	300
34	...	Oil	0.032	290
35	...	Oil	0.032	290
36	...	Oil	0.041	280
37	...	Oil	0.041	280
38	...	Oil	0.054	270
39	...	Oil	0.054	270
40	...	Oil	0.062	265
41	...	Oil	0.062	265
42	...	Oil	0.080	255
43	...	Oil	0.080	255
44	...	Oil	0.105	245
45	...	Oil	0.105	245

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	135.0	135.0	135.0	135.0	135.0	135.0	134.1	129.7	124.0	117.4	109.9	101.7	93.3	85.0
2	55.0	54.0	52.9	52.9	52.9	52.9	52.9	52.9	52.9	52.9	52.9	51.4	48.9	45.8
3	55.0	54.0	52.9	52.9	52.9	52.9	52.9	52.9	52.9	52.9	52.9	51.4	48.9	45.8
4	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
5	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
6	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
7	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
8	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
9	60.0	58.9	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	57.7	56.1	53.3	50.0
10	60.9	60.2	58.5	58.1	58.1	58.1	58.1	58.1	58.1	58.1	57.8	56.5	54.1	50.2
11	60.9	59.8	58.8	58.6	58.6	58.5	58.5	58.5	58.5	58.5	58.3	57.0	54.5	49.9
12	62.4	61.2	60.2	60.0	59.9	59.9	59.9	59.9	59.9	59.9	59.6	58.4	55.8	51.1
13	63.8	62.7	61.6	61.4	61.3	61.3	61.3	61.3	61.3	61.3	61.0	59.7	57.1	52.3
14	63.8	63.8	63.8	63.8	63.8	63.8	63.8	63.8	63.8	63.8	62.0	59.3	55.9	51.9
15	63.8	62.7	61.6	61.4	61.3	61.3	61.3	61.3	61.3	61.3	61.0	59.7	57.1	52.3
16	63.8	63.0	61.3	60.8	60.8	60.8	60.8	60.8	60.8	60.8	60.5	59.2	56.7	52.6
17	65.0	63.8	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	60.8	57.8	54.2
18	65.0	63.8	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	62.5	60.8	57.8	54.2
19	65.3	64.1	63.0	62.8	62.7	62.7	62.7	62.7	62.7	62.7	62.4	61.1	58.4	53.5
20	65.3	64.1	63.0	62.8	62.7	62.7	62.7	62.7	62.7	62.7	62.4	61.1	58.4	53.5
21	70.0	68.7	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	65.5	62.2	58.3
22	70.0	68.7	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	67.3	65.5	62.2	58.3
23	100.0	100.0	100.0	100.0	100.0	100.0	98.7	95.8	92.5	88.8	84.7	80.2	75.5	70.4
24	110.0	110.0	110.0	110.0	110.0	110.0	108.5	105.4	101.8	97.7	93.1	88.2	83.0	77.4
25	115.0	115.0	115.0	115.0	115.0	115.0	113.9	109.8	106.3	101.8	97.2	91.7	87.0	81.6
26	120.0	120.0	120.0	120.0	120.0	120.0	118.8	114.6	110.9	106.3	101.4	95.7	90.8	85.1
27	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	125.0	99.7	94.6	88.7
28	135.0	135.0	135.0	135.0	135.0	135.0	135.0	135.0	124.7	119.5	114.0	107.7	102.2	95.8
29	145.0	145.0	145.0	145.0	145.0	145.0	143.6	138.4	134.0	128.4	122.5	115.6	109.7	102.9
30	155.0	155.0	155.0	155.0	155.0	155.0	153.5	148.0	143.2	137.3	130.9	123.6	117.3	110.0
31	165.0	165.0	165.0	165.0	165.0	165.0	163.4	157.5	152.5	146.1	139.4	131.6	124.9	117.1
32	300	...	...	...	...	...	...	...	...	...	...	...	...	...
33	300	...	...	...	...	...	...	...	...	...	...	...	...	...
34	290	...	...	...	...	...	...	...	...	...	...	...	...	...
35	290	...	...	...	...	...	...	...	...	...	...	...	...	...
36	280	...	...	...	...	...	...	...	...	...	...	...	...	...
37	280	...	...	...	...	...	...	...	...	...	...	...	...	...
38	270	...	...	...	...	...	...	...	...	...	...	...	...	...
39	270	...	...	...	...	...	...	...	...	...	...	...	...	...
40	265	...	...	...	...	...	...	...	...	...	...	...	...	...
41	265	...	...	...	...	...	...	...	...	...	...	...	...	...
42	255	...	...	...	...	...	...	...	...	...	...	...	...	...
43	255	...	...	...	...	...	...	...	...	...	...	...	...	...
44	245	...	...	...	...	...	...	...	...	...	...	...	...	...
45	245	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	
3	...	...	...	...	...	...	...	...	...	...	...	...	
4	...	...	...	...	...	...	...	...	...	...	...	...	
5	...	...	...	...	...	...	...	...	...	...	...	...	
6	...	...	...	...	...	...	...	...	...	...	...	...	
7	...	...	...	...	...	...	...	...	...	...	...	...	
8	...	...	...	...	...	...	...	...	...	...	...	...	
9	...	...	...	...	...	...	...	...	...	...	...	...	
10	...	...	...	...	...	...	...	...	...	...	...	...	
11	...	...	...	...	...	...	...	...	...	...	...	...	
12	...	...	...	...	...	...	...	...	...	...	...	...	
13	...	...	...	...	...	...	...	...	...	...	...	...	
14	...	...	...	...	...	...	...	...	...	...	...	...	
15	...	...	...	...	...	...	...	...	...	...	...	...	
16	...	...	...	...	...	...	...	...	...	...	...	...	
17	...	...	...	...	...	...	...	...	...	...	...	...	
18	...	...	...	...	...	...	...	...	...	...	...	...	
19	...	...	...	...	...	...	...	...	...	...	...	...	
20	...	...	...	...	...	...	...	...	...	...	...	...	
21	...	...	...	...	...	...	...	...	...	...	...	...	
22	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	
29	...	...	...	...	...	...	...	...	...	...	...	...	
30	...	...	...	...	...	...	...	...	...	...	...	...	
31	...	...	...	...	...	...	...	...	...	...	...	...	
32	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	
45	...	...	...	...	...	...	...	...	...	...	...	...	

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
2	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
3	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
4	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
5	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
6	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
7	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
8	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
9	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
10	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
11	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
12	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
13	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
14	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
15	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
16	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
17	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-231	...
18	1Cr- $\frac{1}{4}$ Si-V	Wire	SA-232	...
19	1Cr-V	Smls. tube	SA-213	T17
20	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC6
21	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP11
22	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Bar	SA-739	B11
23	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11
24	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T11
25	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. & wld. ftgs.	SA-234	WP11
26	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P11
27	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11
28	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forged pipe	SA-369	FP11
29	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11
30	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	$1\frac{1}{4}$ CR
31	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11
32	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11
33	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5
34	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5
35	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5
36	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11
37	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11
38	$1\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	$1\frac{1}{4}$ CR
39	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E
40	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E
41	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E
42	$1\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E
43	$2\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22
44	$2\frac{1}{4}$ Cr-1Mo	Smls. tube	SA-213	T22
45	$2\frac{1}{4}$ Cr-1Mo	Smls. & wld. ftgs.	SA-234	WP22

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	...	Oil	0.135	235
2	...	Oil	0.135	235
3	...	Oil	0.162	225
4	...	Oil	0.162	225
5	...	Oil	0.192	220
6	...	Oil	0.192	220
7	...	Oil	0.244	210
8	...	Oil	0.244	210
9	...	Oil	0.283	205
10	...	Oil	0.283	205
11	...	Oil	0.312	203
12	...	Oil	0.312	203
13	...	Oil	0.375	200
14	...	Oil	0.375	200
15	...	Oil	0.438	195
16	...	Oil	0.438	195
17	...	Oil	0.500	190
18	...	Oil	0.500	190
19	K12047	...	...	60
20	J12072	...	...	70
21	J12072	...	...	70
22	K11797	...	...	70
23	K11597	1	...	60
24	K11597	...	...	60
25	...	1	...	60
26	K11597	...	...	60
27	K11597	1	...	60
28	K11597	...	...	60
29	K11789	1	...	60
30	K11789	...	...	60
31	K11572	2	...	70
32	K11572	2	...	70
33	...	QT	$4 < t \leq 10$	71
34	...	QT	$2.25 < t \leq 4$	72.5
35	...	QT	≤ 2.25	74
36	K11572	3	...	75
37	K11789	2	...	75
38	K11789	...	...	75
39	K11695	...	$2\frac{1}{2} < t \leq 4$	105
40	K11695	...	$\leq 2\frac{1}{2}$	115
41	K21604	...	$2\frac{1}{2} < t \leq 6$	105
42	K21604	...	$\leq 2\frac{1}{2}$	115
43	K21590	1	...	60
44	K21590	...	...	60
45	K21590	1	...	60

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	235	...	...	...	...	...	...	...	...	...	...	...	...	...
2	235	...	...	...	...	...	...	...	...	...	...	...	...	...
3	225	...	...	...	...	...	...	...	...	...	...	...	...	...
4	225	...	...	...	...	...	...	...	...	...	...	...	...	...
5	220	...	...	...	...	...	...	...	...	...	...	...	...	...
6	220	...	...	...	...	...	...	...	...	...	...	...	...	...
7	210	...	...	...	...	...	...	...	...	...	...	...	...	...
8	210	...	...	...	...	...	...	...	...	...	...	...	...	...
9	205	...	...	...	...	...	...	...	...	...	...	...	...	...
10	205	...	...	...	...	...	...	...	...	...	...	...	...	...
11	203	...	...	...	...	...	...	...	...	...	...	...	...	...
12	203	...	...	...	...	...	...	...	...	...	...	...	...	...
13	200	...	...	...	...	...	...	...	...	...	...	...	...	...
14	200	...	...	...	...	...	...	...	...	...	...	...	...	...
15	195	...	...	...	...	...	...	...	...	...	...	...	...	...
16	195	...	...	...	...	...	...	...	...	...	...	...	...	...
17	190	...	...	...	...	...	...	...	...	...	...	...	...	...
18	190	...	...	...	...	...	...	...	...	...	...	...	...	...
19	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
20	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.0	65.1	61.4	56.9
21	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.0	65.1	61.4	56.9
22	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.0	65.1	61.4	56.9
23	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
24	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
25	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
26	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
27	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
28	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
29	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
30	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	58.3	55.8	52.6	48.8
31	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.0	65.1	61.4	56.9
32	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	68.0	65.1	61.4	56.9
33	71.1	71.1	70.3	70.3	70.3	70.3	70.3	70.3	70.3	69.3	66.9	63.9	60.4	56.2
34	72.5	72.5	71.8	71.8	71.8	71.8	71.8	71.8	71.8	70.8	68.3	65.3	61.6	57.4
35	74.0	74.0	73.2	73.2	73.2	73.2	73.2	73.2	73.2	72.2	69.7	66.6	62.8	58.5
36	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	72.8	69.7	65.7	61.0
37	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	72.8	69.7	65.7	61.0
38	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	72.8	69.7	65.7	61.0
39	105.0	105.0	105.0	105.0	105.0	105.0	105.0	104.6	102.7	100.4	97.7	94.8	91.5	88.1
40	115.0	115.0	115.0	115.0	115.0	115.0	115.0	114.6	112.5	110.0	107.0	103.8	100.2	96.5
41	105.0	105.0	105.0	105.0	105.0	105.0	105.0	104.6	102.7	100.4	97.7	94.8	91.5	88.1
42	115.0	115.0	115.0	115.0	115.0	115.0	115.0	114.6	112.5	110.0	107.0	103.8	100.2	96.5
43	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
44	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
45	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	2 $\frac{1}{4}$ Cr-1Mo	Smls. pipe	SA-335	P22
2	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22
3	2 $\frac{1}{4}$ Cr-1Mo	Forged pipe	SA-369	FP22
4	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22
5	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR
6	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10
7	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10
8	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10
9	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10
10	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10
11	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA/EN 10216-2	10CrMo9-10
12	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9
13	2 $\frac{1}{4}$ Cr-1Mo	Cast pipe	SA-426	CP22
14	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22
15	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22
16	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22
17	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR
18	2 $\frac{1}{4}$ Cr-1Mo	Bar	SA-739	B22
19	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10
20	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-487	8
21	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-508	22
22	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22
23	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-542	B
24	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22
25	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-182	F22V
26	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-336	F22V
27	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-541	22V
28	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-542	D
29	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-832	22V
30	3Cr-1Mo	Smls. tube	SA-213	T21
31	3Cr-1Mo	Smls. pipe	SA-335	P21
32	3Cr-1Mo	Forgings	SA-336	F21
33	3Cr-1Mo	Forged pipe	SA-369	FP21
34	3Cr-1Mo	Plate	SA-387	21
35	3Cr-1Mo	Cast pipe	SA-426	CP21
36	3Cr-1Mo	Forgings	SA-182	F21
37	3Cr-1Mo	Forgings	SA-336	F21
38	3Cr-1Mo	Plate	SA-387	21
39	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-182	F3V
40	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-336	F3V
41	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-508	3V
42	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-541	3V
43	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-542	C
44	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-832	21V
45	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-182	F3VCb

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K21590	...	...	60
2	K21590	1	...	60
3	K21590	...	...	60
4	K21590	1	...	60
5	K21590	...	...	60
6	...	...	$6 < t \leq 10$	65.5
7	...	NT or QT	$8 < t \leq 20$	65.5
8	...	...	$4 < t \leq 6$	66.5
9	...	...	$2.5 < t \leq 4$	68
10	...	...	$t \leq 2.5$	69.5
11	...	...	$t \leq 2\frac{1}{2}$	69.5
12	J21890	...	...	70
13	J21890	...	...	70
14	K21590	3	...	75
15	K21590	3	...	75
16	K21590	2	...	75
17	K21590	...	...	75
18	K21390	...	...	75
19	...	NT or QT	$t \leq 8$	75.5
20	J22091	A	...	85
21	K21590	3	...	85
22	K21390	3	...	85
23	K21590	4	...	85
24	K21390	4	...	105
25	K31835	...	...	85
26	K31835	...	...	85
27	K31835	...	...	85
28	K31835	4a	...	85
29	K31835	...	...	85
30	K31545	...	...	60
31	K31545	...	...	60
32	K31545	1	...	60
33	K31545	...	...	60
34	K31545	1	...	60
35	J31545	...	...	60
36	K31545	...	...	75
37	K31545	3	...	75
38	K31545	2	...	75
39	K31830	...	...	85
40	K31830	...	...	85
41	K31830	...	...	85
42	K31830	...	...	85
43	K31830	4a	...	85
44	K31830	...	...	85
45	...	...	...	85

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
2	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
3	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
4	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
5	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
6	65.3	65.3	63.5	62.9	62.6	62.1	61.6	61.0	60.0	58.8	57.1	54.8	51.9	48.2
7	65.3	65.3	64.0	63.0	62.7	62.4	62.0	61.4	60.4	59.0	57.2	54.9	52.1	48.8
8	66.7	66.7	65.0	64.3	64.0	63.5	63.0	62.3	61.4	60.1	58.3	56.1	53.1	49.3
9	68.2	68.2	66.4	65.7	65.4	64.9	64.4	63.7	62.7	61.4	59.6	57.3	54.2	50.4
10	69.6	69.6	67.8	67.1	66.7	66.2	65.8	65.0	64.1	62.7	60.9	58.5	55.4	51.4
11	69.6	69.6	67.8	67.1	66.7	66.2	65.7	65.0	64.0	62.7	60.9	58.5	55.4	51.5
12	70.0	70.0	69.0	67.9	67.6	67.3	66.8	66.0	64.6	62.7	60.1	56.9	52.8	48.1
13	70.0	70.0	69.0	67.9	67.6	67.3	66.8	66.0	64.6	62.7	60.1	56.9	52.8	48.1
14	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
15	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
16	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
17	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
18	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
19	75.4	75.4	74.0	72.8	72.4	72.1	71.6	70.9	69.8	68.2	66.1	63.4	60.2	56.4
20	85.0	85.0	83.0	82.2	82.1	81.7	81.1	80.0	78.4	76.1	73.0	69.0	64.1	58.2
21	85.0	85.0	84.9	84.9	83.5	81.7	81.0	80.3	79.1	76.5	71.4	...	...	...
22	85.0	85.0	84.9	84.9	83.5	81.7	81.0	80.3	79.1	76.5	71.4	...	...	...
23	85.0	85.0	84.9	84.9	83.5	81.7	81.0	80.3	79.1	76.5	71.4	...	...	...
24	105.0	105.0	105.0	105.0	104.3	103.0	102.1	100.9	99.4	97.5	95.0	92.1	88.5	84.4
25	85.0	85.0	85.0	85.0	85.0	82.8	81.3	79.6	77.7	75.6	73.4	71.0	...	...
26	85.0	85.0	85.0	85.0	85.0	82.8	81.3	79.6	77.7	75.6	73.4	71.0	...	...
27	85.0	85.0	85.0	85.0	85.0	82.8	81.3	79.6	77.7	75.6	73.4	71.0	...	...
28	85.0	85.0	85.0	85.0	85.0	82.8	81.3	79.6	77.7	75.6	73.4	71.0	...	...
29	85.0	85.0	85.0	85.0	85.0	82.8	81.3	79.6	77.7	75.6	73.4	71.0	...	...
30	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
31	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
32	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
33	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
34	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
35	60.0	59.9	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	58.2	57.5	53.9
36	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
37	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
38	75.0	75.0	73.0	72.2	71.9	71.4	70.8	70.1	69.0	67.5	65.6	63.0	59.7	55.4
39	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
40	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
41	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
42	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
43	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
44	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
45	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-336	F3VCb
2	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-508	3VCb
3	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-541	3VCb
4	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-542	E
5	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-832	23V
6	5Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T5
7	5Cr- $\frac{1}{2}$ Mo	Smls. & wld. ftgs.	SA-234	WP5
8	5Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P5
9	5Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP5
10	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5
11	5Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	5CR
12	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5
13	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5
14	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5
15	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5A
16	5Cr- $\frac{1}{2}$ Mo	Castings	SA-217	C5
17	5Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP5
18	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5a
19	5Cr- $\frac{1}{2}$ Mo	Bolting	SA-193	B5
20	5Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T5b
21	5Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P5b
22	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. tube	SA-213	T5c
23	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. pipe	SA-335	P5c
24	9Cr-1Mo	Smls. tube	SA-213	T9
25	9Cr-1Mo	Fittings	SA-234	WP9
26	9Cr-1Mo	Smls. pipe	SA-335	P9
27	9Cr-1Mo	Forged pipe	SA-369	FP9
28	9Cr-1Mo	Forgings	SA-182	F9
29	9Cr-1Mo	Forgings	SA-336	F9
30	9Cr-1Mo	Castings	SA-217	C12
31	9Cr-1Mo	Cast pipe	SA-426	CP9
32	9Cr-1Mo-V	Smls. tube	SA-213	T91 Types 1 & 2
33	9Cr-1Mo-V	Fittings	SA-234	WP91 Types 1 & 2
34	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Types 1 & 2
35	9Cr-1Mo-V	Forged pipe	SA-369	FP91 Types 1 & 2
36	9Cr-1Mo-V	Plate	SA-387	91 Types 1 & 2
37	9Cr-1Mo-V	Forgings	SA-182	F91 Types 1 & 2
38	9Cr-1Mo-V	Forgings	SA-336	F91 Types 1 & 2
39	11Cr-Ti	Plate	SA-240	...
40	11Cr-Ti	Plate	SA-240	...
41	11Cr-Ti	Plate	SA-240	...
42	11Cr-Ti	Smls. & wld. tube	SA-268	TP409
43	12Cr	Plate	SA-1010	40
44	12Cr	Bar	SA-479	403
45	12Cr	Bar	SA-479	403

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	...	...	...	85
2	...	...	...	85
3	...	...	...	85
4	...	4a	...	85
5	...	...	...	85
6	K41545	...	...	60
7	K41545	...	...	60
8	K41545	...	...	60
9	K41545	...	...	60
10	K41545	1	...	60
11	K41545	...	...	60
12	K41545	...	...	60
13	K41545	...	...	70
14	K41545	2	...	75
15	K42544	...	...	80
16	J42045	...	...	90
17	J42045	...	...	90
18	K42544	...	...	90
19	K50100	...	≤4	100
20	K51545	...	...	60
21	K51545	...	...	60
22	K41245	...	...	60
23	K41245	...	...	60
24	K90941	...	...	60
25	K90941	...	...	60
26	K90941	...	...	60
27	K90941	...	...	60
28	K90941	...	...	85
29	K90941	...	...	85
30	J82090	...	...	90
31	J82090	...	...	90
32	K90901	...	...	85
33	K90901	...	...	90
34	K90901	...	...	85
35	K90901	...	...	85
36	K90901	2	...	85
37	K90901	...	...	90
38	K90901	...	...	90
39	S40910	...	...	55
40	S40920	...	...	55
41	S40930	...	...	55
42	S40900	...	...	55
43	S41003	...	≤ ³ / ₄	66
44	S40300	A	...	70
45	S40300	1	...	70

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
2	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
3	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
4	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
5	85.0	85.0	81.5	79.0	77.5	76.4	75.7	75.0	74.1	72.9	71.4	69.8	...	...
6	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
7	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
8	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
9	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
10	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
11	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
12	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
13	70.0	69.9	67.8	67.3	67.1	66.1	65.1	63.7	61.8	59.4	56.5	53.2	49.5	45.5
14	75.0	74.8	72.7	72.1	71.9	70.8	69.7	68.2	66.2	63.6	60.6	57.0	53.1	48.7
15	80.0	79.8	77.5	76.9	76.7	75.5	74.4	72.8	70.6	67.9	64.6	60.9	56.6	52.0
16	90.0	89.8	87.2	86.5	86.2	85.0	83.7	81.9	79.4	76.4	72.7	68.5	63.7	58.5
17	90.0	89.8	87.2	86.5	86.2	85.0	83.7	81.9	79.4	76.4	72.7	68.5	63.7	58.5
18	90.0	89.8	87.2	86.5	86.2	85.0	83.7	81.9	79.4	76.4	72.7	68.5	63.7	58.5
19	100.0	99.6	96.8	95.7	95.5	94.1	92.6	91.1	88.0	85.3	81.2	76.5	71.7	66.0
20	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
21	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
22	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
23	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
24	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
25	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
26	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
27	60.0	59.9	58.1	57.7	57.5	56.7	55.8	54.6	52.9	50.9	48.5	45.6	42.5	39.0
28	85.0	84.8	82.3	81.7	81.4	80.3	79.0	77.3	75.0	72.1	68.7	64.7	60.1	55.2
29	85.0	84.8	82.3	81.7	81.4	80.3	79.0	77.3	75.0	72.1	68.7	64.7	60.1	55.2
30	90.0	89.8	87.2	86.5	86.2	85.0	83.7	81.9	79.4	76.4	72.7	68.5	63.7	58.5
31	90.0	89.8	87.2	86.5	86.2	85.0	83.7	81.9	79.4	76.4	72.7	68.5	63.7	58.5
32	85.0	85.0	85.0	84.7	84.4	83.1	81.8	80.0	77.6	74.7	71.1	66.9	62.2	57.0
33	90.0	90.0	90.0	89.7	89.4	88.0	86.6	84.7	82.2	79.1	75.3	70.8	65.9	60.4
34	85.0	85.0	85.0	84.7	84.4	83.1	81.8	80.0	77.6	74.7	71.1	66.9	62.2	57.0
35	85.0	85.0	85.0	84.7	84.4	83.1	81.8	80.0	77.6	74.7	71.1	66.9	62.2	57.0
36	85.0	85.0	85.0	84.7	84.4	83.1	81.8	80.0	77.6	74.7	71.1	66.9	62.2	57.0
37	90.0	90.0	90.0	89.7	89.4	88.0	86.6	84.7	82.2	79.1	75.3	70.8	65.9	60.4
38	90.0	90.0	90.0	89.7	89.4	88.0	86.6	84.7	82.2	79.1	75.3	70.8	65.9	60.4
39	55.0	55.0	53.9	53.0	52.1	50.9	49.9	48.6	47.1	45.2	42.9	40.3	37.4	34.1
40	55.0	55.0	53.9	53.0	52.1	50.9	49.9	48.6	47.1	45.2	42.9	40.3	37.4	34.1
41	55.0	55.0	53.9	53.0	52.1	50.9	49.9	48.6	47.1	45.2	42.9	40.3	37.4	34.1
42	55.0	55.0	53.9	53.0	52.1	50.9	49.9	48.6	47.1	45.2	42.9	40.3	37.4	34.1
43	66.0	66.0	66.0	64.3	62.1	59.8	58.5	56.9	55.0	52.6	49.7	46.1	41.8	36.7
44	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
45	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	12Cr	Plate	SA-1010	50
2	12Cr-Al	Plate	SA-240	405
3	12Cr-Al	Smls. & wld. tube	SA-268	TP405
4	12Cr-Al	Bar	SA-479	405
5	12Cr-Al	Bar	SA/JIS G4303	SUS405
6	12Cr-Ti	Smls. & wld. tube	SA-268	...
7	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16
8	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16
9	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16
10	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16
11	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16
12	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16
13	13Cr	Plate	SA-240	410S
14	13Cr	Smls. & wld. tube	SA-268	TP410
15	13Cr	Plate	SA-240	410
16	13Cr	Forgings	SA-182	F6a
17	13Cr	Bar	SA-479	410
18	13Cr	Bar	SA-479	410
19	13Cr	Bar	SA-479	410
20	13Cr	Forgings	SA-182	F6a
21	13Cr	Castings	SA-217	CA15
22	13Cr	Cast pipe	SA-426	CPCA15
23	13Cr	Bar	SA/EN 10088-3	X12Cr13
24	13Cr	Bolting	SA-193	B6
25	13Cr-4Ni	Castings	SA-487	CA6NM
26	13Cr-4Ni	Forgings	SA-182	F6NM
27	13Cr-4Ni	Bar	SA-479	...
28	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
29	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
30	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
31	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
32	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
33	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
34	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
35	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
36	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
37	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
38	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
39	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
40	13Cr-8Ni-2Mo	Bar	SA-564	XM-13
41	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13
42	15Cr	Smls. & wld. tube	SA-268	TP429
43	15Cr	Plate	SA-240	429
(25) 44	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 45	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S41003	...	$\leq \frac{3}{4}$	70
2	S40500	...	...	60
3	S40500	...	...	60
4	S40500	...	...	60
5	...	...	...	60
6	S40800	...	...	55
7	S45500	H1000	...	205
8	S45500	H1000	$t \geq \frac{1}{2}$	205
9	S45500	H950	...	220
10	S45500	H950	$t \geq \frac{1}{2}$	220
11	S45500	H900	...	235
12	S45500	H900	$t \geq \frac{1}{2}$	235
13	S41008	...	...	60
14	S41000	...	...	60
15	S41000	...	...	65
16	S41000	1	...	70
17	S41000	...	...	70
18	S41000	A	...	70
19	S41000	1	...	70
20	S41000	2	...	85
21	J91150	...	...	90
22	J91150	...	...	90
23	...	QT650	$t \leq 6.25$	94.5
24	S41000	...	≤ 4	110
25	J91540	A	...	110
26	S41500	...	...	115
27	S41500	...	...	115
28	S13800	H1150M	...	125
29	S13800	H1150M	...	125
30	S13800	H1150	...	135
31	S13800	H1150	...	135
32	S13800	H1100	...	150
33	S13800	H1100	...	150
34	S13800	H1050	...	175
35	S13800	H1050	...	175
36	S13800	H1025	...	185
37	S13800	H1025	...	185
38	S13800	H1000	...	205
39	S13800	H1000	...	205
40	S13800	H950	...	220
41	S13800	H950	...	220
42	S42900	...	...	60
43	S42900	...	...	65
44	S15500	H1150M	...	115
45	S15500	H1150M	...	115

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	70.0	70.0	70.0	68.2	65.8	63.4	62.0	60.4	58.3	55.8	52.7	48.9	44.3	38.9
2	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
3	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
4	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
5	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
6	55.0	55.0	53.9	53.0	52.1	50.9	49.9	48.6	47.1	45.2	42.9	40.3	37.4	34.1
7	205.0	...	...	...	...	...	...	...	...	...	...	...	...	...
8	205.0	...	...	...	...	...	...	...	...	...	...	...	...	...
9	220.0	...	...	...	...	...	...	...	...	...	...	...	...	...
10	220.0	...	...	...	...	...	...	...	...	...	...	...	...	...
11	235.0	...	...	...	...	...	...	...	...	...	...	...	...	...
12	235.0	...	...	...	...	...	...	...	...	...	...	...	...	...
13	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
14	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
15	65.0	65.0	63.7	62.6	61.6	60.1	59.0	57.5	55.6	53.4	50.7	47.7	44.2	40.3
16	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
17	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
18	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
19	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
20	85.0	85.0	83.3	81.8	80.6	78.6	77.1	75.2	72.8	69.8	66.3	62.3	57.8	52.8
21	90.0	90.0	88.2	86.7	85.3	83.2	81.6	79.6	77.0	73.9	70.2	66.0	61.2	55.9
22	90.0	90.0	88.2	86.7	85.3	83.2	81.6	79.6	77.0	73.9	70.2	66.0	61.2	55.9
23	94.3	94.3	92.3	90.7	89.3	87.2	85.6	83.4	80.7	77.4	73.5	69.0	64.1	58.7
24	110.0	110.0	109.0	107.0	105.0	102.0	100.0	97.7	94.6	90.9	86.4	81.1	75.1	68.4
25	110.0	110.0	108.0	105.3	103.1	100.7	99.4	97.8	95.9	93.5	90.5	86.7	81.7	75.4
26	115.0	115.0	115.0	113.7	109.5	105.1	102.8	100.3	97.6	94.7	91.4	...	...	...
27	115.0	115.0	115.0	113.7	109.5	105.1	102.8	100.3	97.6	94.7	91.4	...	...	...
28	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
29	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
30	135.0	...	...	...	...	...	...	...	...	...	...	...	...	...
31	135.0	...	...	...	...	...	...	...	...	...	...	...	...	...
32	150.0	...	...	...	...	...	...	...	...	...	...	...	...	...
33	150.0	...	...	...	...	...	...	...	...	...	...	...	...	...
34	175.0	...	...	...	...	...	...	...	...	...	...	...	...	...
35	175.0	...	...	...	...	...	...	...	...	...	...	...	...	...
36	185.0	...	...	...	...	...	...	...	...	...	...	...	...	...
37	185.0	...	...	...	...	...	...	...	...	...	...	...	...	...
38	205.0	...	...	...	...	...	...	...	...	...	...	...	...	...
39	205.0	...	...	...	...	...	...	...	...	...	...	...	...	...
40	220.0	...	...	...	...	...	...	...	...	...	...	...	...	...
41	220.0	...	...	...	...	...	...	...	...	...	...	...	...	...
42	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
43	65.0	65.0	63.7	62.6	61.6	60.1	59.0	57.5	55.6	53.4	50.7	47.7	44.2	40.3
44	115.0	115.0	114.5	111.3	108.6	106.5	104.7	103.1	103.5	100.6	96.8	91.6	84.8	76.4
45	115.0	115.0	114.5	111.3	108.6	106.5	104.7	103.1	103.5	100.6	96.8	91.6	84.8	76.4

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

(25)

(25)
(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
(25) 1	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 2	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
(25) 3	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 4	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
(25) 5	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 6	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
(25) 7	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 8	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
(25) 9	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 10	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
(25) 11	15Cr-5Ni-3Cu	Bar	SA-564	XM-12
(25) 12	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12
13	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
14	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
15	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
16	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
17	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
18	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
19	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
20	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
21	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
22	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
23	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
24	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
25	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25
26	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25
27	17Cr	Smls. & wld. tube	SA-268	TP430
28	17Cr	Plate	SA-240	430
29	17Cr	Bar	SA-479	430
(25) 30	17Cr-4Ni-4Cu	Bar	SA-564	630
(25) 31	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 32	17Cr-4Ni-4Cu	Bar	SA-564	630
(25) 33	17Cr-4Ni-4Cu	Plate	SA-693	630
(25) 34	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 35	17Cr-4Ni-4Cu	Bar	SA-564	630
(25) 36	17Cr-4Ni-4Cu	Plate	SA-693	630
(25) 37	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 38	17Cr-4Ni-4Cu	Bar	SA-564	630
(25) 39	17Cr-4Ni-4Cu	Plate	SA-693	630
(25) 40	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 41	17Cr-4Ni-4Cu	Bar	SA-564	630
(25) 42	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 43	17Cr-4Ni-4Cu	Forgings	SA-705	630
(25) 44	17Cr-4Ni-4Cu	Forgings	SA-705	630
45	17Cr-7Ni-1Al	Forgings	SA-705	631

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S15500	H1150	...	135
2	S15500	H1150	...	135
3	S15500	H1100	...	140
4	S15500	H1100	...	140
5	S15500	H1075	...	145
6	S15500	H1075	...	145
7	S15500	H1025	...	155
8	S15500	H1025	...	155
9	S15500	H925	...	170
10	S15500	H925	...	170
11	S15500	H900	...	190
12	S15500	H900	...	190
13	S45000	H1150	...	125
14	S45000	H1150	$t \geq \frac{1}{2}$	125
15	S45000	H1100	...	130
16	S45000	H1100	$t \geq \frac{1}{2}$	130
17	S45000	H1050	...	145
18	S45000	H1050	$t \geq \frac{1}{2}$	145
19	S45000	H1025	...	150
20	S45000	H1025	$t \geq \frac{1}{2}$	150
21	S45000	H1000	...	160
22	S45000	H1000	$t \geq \frac{1}{2}$	160
23	S45000	H950	...	170
24	S45000	H950	$t \geq \frac{1}{2}$	170
25	S45000	H900	...	180
26	S45000	H900	$t \geq \frac{1}{2}$	180
27	S43000	...	...	60
28	S43000	...	...	65
29	S43000	...	...	70
30	S17400	H1150M	...	115
31	S17400	H1150M	...	115
32	S17400	H1150	...	135
33	S17400	H1150	...	135
34	S17400	H1150	...	135
35	S17400	H1100	...	140
36	S17400	H1100	...	140
37	S17400	H1100	...	140
38	S17400	H1075	...	145
39	S17400	H1075	...	145
40	S17400	H1075	...	145
41	S17400	H1025	...	155
42	S17400	H1025	...	155
43	S17400	H925	...	170
44	S17400	H900	...	190
45	S17700	TH1050	...	170

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	135.0	135.0	134.4	130.6	127.5	125.0	122.9	121.1	121.5	118.1	113.6	107.5	99.6	89.7
2	135.0	135.0	134.4	130.6	127.5	125.0	122.9	121.1	121.5	118.1	113.6	107.5	99.6	89.7
3	140.0	140.0	139.4	135.5	132.2	129.7	127.5	125.6	126.0	122.5	117.8	111.5	103.3	93.0
4	140.0	140.0	139.4	135.5	132.2	129.7	127.5	125.6	126.0	122.5	117.8	111.5	103.3	93.0
5	145.0	145.0	144.4	140.3	137.0	134.3	132.0	130.1	130.5	126.9	122.0	115.5	107.0	96.3
6	145.0	145.0	144.4	140.3	137.0	134.3	132.0	130.1	130.5	126.9	122.0	115.5	107.0	96.3
7	155.0	155.0	154.4	150.0	146.4	143.6	141.2	139.0	139.5	135.6	130.4	123.4	114.4	103.0
8	155.0	155.0	154.4	150.0	146.4	143.6	141.2	139.0	139.5	135.6	130.4	123.4	114.4	103.0
9	170.0	170.0	169.3	164.5	160.6	157.4	154.8	152.5	153.0	148.7	143.1	135.4	125.4	112.9
10	170.0	170.0	169.3	164.5	160.6	157.4	154.8	152.5	153.0	148.7	143.1	135.4	125.4	112.9
11	190.0	190.0	189.2	183.8	179.5	176.0	173.0	170.4	171.0	166.2	159.9	151.3	140.2	126.2
12	190.0	190.0	189.2	183.8	179.5	176.0	173.0	170.4	171.0	166.2	159.9	151.3	140.2	126.2
13	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
14	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
15	130.0	...	...	...	...	...	...	...	...	...	...	...	...	...
16	130.0	...	...	...	...	...	...	...	...	...	...	...	...	...
17	145.0	...	...	...	...	...	...	...	...	...	...	...	...	...
18	145.0	...	...	...	...	...	...	...	...	...	...	...	...	...
19	150.0	...	...	...	...	...	...	...	...	...	...	...	...	...
20	150.0	...	...	...	...	...	...	...	...	...	...	...	...	...
21	160.0	...	...	...	...	...	...	...	...	...	...	...	...	...
22	160.0	...	...	...	...	...	...	...	...	...	...	...	...	...
23	170.0	...	...	...	...	...	...	...	...	...	...	...	...	...
24	170.0	...	...	...	...	...	...	...	...	...	...	...	...	...
25	180.0	...	...	...	...	...	...	...	...	...	...	...	...	...
26	180.0	...	...	...	...	...	...	...	...	...	...	...	...	...
27	60.0	60.0	58.8	57.8	56.9	55.5	54.4	53.1	51.4	49.3	46.8	44.0	40.8	37.2
28	65.0	65.0	63.7	62.6	61.6	60.1	59.0	57.5	55.6	53.4	50.7	47.7	44.2	40.3
29	70.0	70.0	68.6	67.4	66.4	64.7	63.5	61.9	59.9	57.5	54.6	51.3	47.6	43.5
30	115.0	115.0	114.5	111.3	108.6	106.5	104.7	103.1	103.5	100.6	96.8	91.6	84.8	76.4
31	115.0	115.0	114.5	111.3	108.6	106.5	104.7	103.1	103.5	100.6	96.8	91.6	84.8	76.4
32	135.0	135.0	134.4	130.6	127.5	125.0	122.9	121.1	121.5	118.1	113.6	107.5	99.6	89.7
33	135.0	135.0	134.4	130.6	127.5	125.0	122.9	121.1	121.5	118.1	113.6	107.5	99.6	89.7
34	135.0	135.0	134.4	130.6	127.5	125.0	122.9	121.1	121.5	118.1	113.6	107.5	99.6	89.7
35	140.0	140.0	139.4	135.5	132.2	129.7	127.5	125.6	126.0	122.5	117.8	111.5	103.3	93.0
36	140.0	140.0	139.4	135.5	132.2	129.7	127.5	125.6	126.0	122.5	117.8	111.5	103.3	93.0
37	140.0	140.0	139.4	135.5	132.2	129.7	127.5	125.6	126.0	122.5	117.8	111.5	103.3	93.0
38	145.0	145.0	144.4	140.3	137.0	134.3	132.0	130.1	130.5	126.9	122.0	115.5	107.0	96.3
39	145.0	145.0	144.4	140.3	137.0	134.3	132.0	130.1	130.5	126.9	122.0	115.5	107.0	96.3
40	145.0	145.0	144.4	140.3	137.0	134.3	132.0	130.1	130.5	126.9	122.0	115.5	107.0	96.3
41	155.0	155.0	154.4	150.0	146.4	143.6	141.2	139.0	139.5	135.6	130.4	123.4	114.4	103.0
42	155.0	155.0	154.4	150.0	146.4	143.6	141.2	139.0	139.5	135.6	130.4	123.4	114.4	103.0
43	170.0	170.0	169.3	164.5	160.6	157.4	154.8	152.5	153.0	148.7	143.1	135.4	125.4	112.9
44	190.0	190.0	189.2	183.8	179.5	176.0	173.0	170.4	171.0	166.2	159.9	151.3	140.2	126.2
45	170.0	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	
14	...	...	...	...	...	...	...	...	...	...	...	...	
15	...	...	...	...	...	...	...	...	...	...	...	...	
16	...	...	...	...	...	...	...	...	...	...	...	...	
17	...	...	...	...	...	...	...	...	...	...	...	...	
18	...	...	...	...	...	...	...	...	...	...	...	...	
19	...	...	...	...	...	...	...	...	...	...	...	...	
20	...	...	...	...	...	...	...	...	...	...	...	...	
21	...	...	...	...	...	...	...	...	...	...	...	...	
22	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	
29	...	...	...	...	...	...	...	...	...	...	...	...	
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	17Cr-7Ni-1Al	Forgings	SA-705	631
2	18Cr-2Mo	Plate	SA-240	...
3	18Cr-2Mo	Smls. & wld. tube	SA-268	...
(25) 4	18Cr-2Mo	Bar	SA-479	...
5	18Cr-Ti	Plate	SA-240	...
(25) 6	18Cr-Ti	Plate	SA-240	439
7	18Cr-Ti	Smls. & wld. tube	SA-268	TP439
8	18Cr-Ti	Wld. tube	SA-803	TP439
(25) 9	...	...	...	...
10	18Cr-Ti	Smls. & wld. tube	SA-268	TP430 Ti
11	18Cr-Ti	Bar	SA-479	439
12	26Cr-3Ni-3Mo	Plate	SA-240	26-3-3
13	26Cr-3Ni-3Mo	Smls. & wld. tube	SA-268	26-3-3
14	26Cr-3Ni-3Mo	Wld. tube	SA-803	26-3-3
15	27Cr	Smls. tube	SA-268	TP446-1
16	27Cr-1Mo	Forgings	SA-182	FXM-27Cb
17	27Cr-1Mo	Plate	SA-240	XM-27
18	27Cr-1Mo	Smls. & wld. tube	SA-268	TPXM-27
19	27Cr-1Mo	Bar	SA-479	XM-27
(25) 20	...	...	...	...
(25) 21	...	...	...	...
22	27Cr-1Mo-Ti	Plate	SA-240	XM-33
23	27Cr-1Mo-Ti	Smls. & wld. tube	SA-268	TPXM-33
24	29Cr-4Mo	Bar	SA-479	...
25	29Cr-4Mo	Plate	SA-240	...
26	29Cr-4Mo	Smls. & wld. tube	SA-268	29-4
27	29Cr-4Mo-2Ni	Bar	SA-479	...
28	29Cr-4Mo-2Ni	Plate	SA-240	...
29	29Cr-4Mo-2Ni	Smls. & wld. tube	SA-268	29-4-2
30	29Cr-4Mo-Ti	Smls. & wld. tube	SA-268	...
31	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D
32	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2
33	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2
34	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	A
35	Mn- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	H75
36	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	B
37	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A
38	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A
39	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A
40	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D
41	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D
42	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D
43	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-302	C
44	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B
45	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	H80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S17700	RH950	...	185
2	S44400	...	...	60
3	S44400	...	...	60
4	S44400	...	$t \leq \frac{3}{8}$	60
5	S43932	...	...	60
6	S43035	...	...	60
7	S43035	...	...	60
8	S43035	...	...	60
9	...	...	...	...
10	S43036	...	...	60
11	S43035	...	...	70
12	S44660	...	$\leq \frac{2}{10}$	85
13	S44660	...	$\leq \frac{2}{10}$	85
14	S44660	...	$\leq \frac{2}{10}$	85
15	S44600	...	...	70
16	S44627	...	...	60
17	S44627	...	...	65
18	S44627	...	...	65
19	S44627	...	...	65
20	...	...	...	...
21	...	...	...	...
22	S44626	...	...	68
23	S44626	...	...	68
24	S44700	...	...	70
25	S44700	...	...	80
26	S44700	...	...	80
27	S44800	...	...	70
28	S44800	...	...	80
29	S44800	...	...	80
30	S44735	...	...	75
31	K14508	...	...	105
32	J13005	A	...	85
33	J13005	B	...	90
34	K12021	...	...	75
35	K12021	...	...	75
36	K12022	...	...	80
37	K12521	1	...	80
38	K12521	2	...	90
39	K12521	3	...	100
40	K12529	1	...	80
41	K12529	2	...	90
42	K12529	3	...	100
43	K12039	...	...	80
44	K12539	1	...	80
45	K12039	...	...	80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	185.0	...	...	...	...	...	...	...	...	...	...	...	...	...
2	60.0	60.0	58.2	56.8	55.5	53.9	52.9	51.8	50.4	48.9	47.1	44.9	42.2	38.9
3	60.0	60.0	58.2	56.8	55.5	53.9	52.9	51.8	50.4	48.9	47.1	44.9	42.2	38.9
4	60.0	60.0	58.2	56.8	55.5	53.9	52.9	51.8	50.4	48.9	47.1	44.9	42.2	38.9
5	60.0	60.0	57.9	56.4	55.2	53.8	53.0	51.9	50.7	49.2	47.3	45.0	42.3	39.0
6	60.0	60.0	57.9	56.4	55.2	53.8	53.0	51.9	50.7	49.2	47.3	45.0	42.3	39.0
7	60.0	60.0	57.9	56.4	55.2	53.8	53.0	51.9	50.7	49.2	47.3	45.0	42.3	39.0
8	60.0	60.0	57.9	56.4	55.2	53.8	53.0	51.9	50.7	49.2	47.3	45.0	42.3	39.0
9	...	...	...	...	...	...	...	...	...	...	...	...	...	...
10	60.0	60.0	57.9	56.4	55.2	53.8	53.0	51.9	50.7	49.2	47.3	45.0	42.3	39.0
11	70.0	70.0	67.6	65.8	64.4	62.8	61.8	60.6	59.1	57.3	55.2	52.5	49.3	45.4
12	85.0	85.0	84.8	83.7	83.2	82.8	82.4	81.8	...	...	...	...	...	...
13	85.0	85.0	84.8	83.7	83.2	82.8	82.4	81.8	...	...	...	...	...	...
14	85.0	85.0	84.8	83.7	83.2	82.8	82.4	81.8	...	...	...	...	...	...
15	70.0	70.0	67.6	65.8	64.4	62.8	61.8	60.6	59.1	57.3	55.2	52.5	49.3	45.4
16	60.0	60.0	58.1	56.5	56.5	56.5	56.5	...	...	...	...	...	...	...
17	65.0	65.0	64.0	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5
18	65.0	65.0	64.0	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5
19	65.0	65.0	64.0	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5	63.5
20	...	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...	...
22	68.0	68.0	67.6	66.5	65.8	64.5	63.5	62.0	59.9	57.0	...	...	...	...
23	68.0	68.0	67.6	66.5	65.8	64.5	63.5	62.0	59.9	57.0	...	...	...	...
24	70.0	69.8	67.6	67.2	67.2	67.2	67.2	67.2	67.2	...	...	...	...	...
25	80.0	79.8	77.2	76.8	76.8	76.8	76.8	76.8	76.8	...	...	...	...	...
26	80.0	79.8	77.2	76.8	76.8	76.8	76.8	76.8	76.8	...	...	...	...	...
27	70.0	68.7	67.6	67.1	66.2	65.3	64.8	64.3	63.5	...	...	...	...	...
28	80.0	78.6	77.3	76.7	75.7	74.6	74.1	73.5	72.6	...	...	...	...	...
29	80.0	78.6	77.3	76.7	75.7	74.6	74.1	73.5	72.6	...	...	...	...	...
30	75.0	73.7	72.5	71.9	70.9	69.9	69.5	68.9	68.0	...	...	...	...	...
31	105.0	105.0	105.0	105.0	105.0	105.0	105.0	105.0	102.7	95.5	87.3	79.1	72.3	68.7
32	85.0	85.0	85.0	84.6	84.6	84.6	84.5	84.5	...	...	...	...	...	...
33	90.0	90.0	90.0	89.5	89.5	89.5	89.5	89.5	...	...	...	...	...	...
34	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	72.4	68.6	63.7	57.9
35	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	72.4	68.6	63.7	57.9
36	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
37	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
38	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
39	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	96.6	91.4	84.9	77.1
40	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
41	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
42	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	96.6	91.4	84.9	77.1
43	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
44	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
45	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J80
2	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B
3	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J90
4	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B
5	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J100
6	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-302	D
7	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C
8	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E
9	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C
10	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E
11	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C
12	Mn- $\frac{1}{2}$ Ni-V	Plate	SA-225	C
13	Mn-V	Castings	SA-487	1
14	Mn-V	Castings	SA-487	1
15	$1\frac{1}{2}$ Si- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P15
16	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4
17	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4
18	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4
19	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3
20	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3
21	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F
22	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Plate	SA-517	F
23	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F
24	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Smls. & wld. tube	SA-423	2
25	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2
26	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2
27	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2
28	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2
29	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3
30	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3
(25) 31	$\frac{3}{4}$ Ni-1Cu- $\frac{3}{4}$ Cr	Plate	SA-736	A
(25) 32	$\frac{3}{4}$ Ni-1Cu- $\frac{3}{4}$ Cr	Plate	SA-736	A
33	$\frac{3}{4}$ Ni-1Mo- $\frac{3}{4}$ Cr	Castings	SA-217	WC5
34	1Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC4
35	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P
36	$1\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P
37	$1\frac{1}{2}$ Ni	Forgings	SA-350	LF5
38	$1\frac{1}{2}$ Ni	Forgings	SA-350	LF5
(25) 39	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-320	L43
40	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Forgings	SA-372	L
41	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	4340
42	$1\frac{3}{4}$ Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-574	4340
43	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23
44	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23
45	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K12539	...	...	80
2	K12539	2	...	90
3	K12539	...	...	90
4	K12539	3	...	100
5	K12539	...	...	100
6	K12054	...	...	80
7	K12554	1	...	80
8	K12554	1	...	80
9	K12554	2	...	90
10	K12554	2	...	90
11	K12554	3	...	100
12	K12524	...	...	105
13	J13002	A	...	85
14	J13002	B	...	90
15	K11578	...	...	60
16	J13047	A	...	90
17	J13047	B	...	105
18	J13047	E	...	115
19	K12045	1	...	80
20	K12045	2	...	90
21	K11576	...	$2\frac{1}{2} < t \leq 4$	105
22	K11576	...	$\leq 2\frac{1}{2}$	115
23	K11576	...	$\leq 2\frac{1}{2}$	115
24	K11540	...	...	60
25	K12766	1	...	80
26	K12765	1	...	80
27	K12766	2	...	90
28	K12765	2	...	90
29	K12042	1	...	80
30	K12042	2	...	90
31	...	3	$2 < t \leq 4$	75
32	...	3	≤ 2	85
33	J22000	...	...	70
34	J12082	...	...	70
35	K21650	...	$2\frac{1}{2} < t \leq 4$	105
36	K21650	...	$\leq 2\frac{1}{2}$	115
37	K13050	1	...	60
38	K13050	2	...	70
39	G43400	...	≤ 4	125
40	K24055	...	...	155
41	G43400	...	$\geq \frac{5}{8}$	170
42	G43400	...	$\leq \frac{1}{2}$	180
43	H43400	5	$6 < t \leq 9\frac{1}{2}$	115
44	H43400	5	≤ 6	120
45	H43400	4	$\leq 9\frac{1}{2}$	135

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
2	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
3	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
4	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	96.6	91.4	84.9	77.1
5	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	96.6	91.4	84.9	77.1
6	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
7	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
8	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
9	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
10	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
11	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	96.6	91.4	84.9	77.1
12	105.0	105.0	105.0	105.0	105.0	105.0	105.0	105.0	104.3	96.2	...	...	...	...
13	85.0	...	...	...	...	...	...	...	...	...	...	...	...	...
14	90.0	...	...	...	...	...	...	...	...	...	...	...	...	...
15	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	60.0	57.9	54.9	51.0	46.3
16	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	...	...	...	...	...	...
17	105.0	105.0	105.0	105.0	105.0	105.0	105.0	105.0	...	...	...	...	...	...
18	115.0	115.0	115.0	115.0	115.0	115.0	115.0	115.0	...	...	...	...	...	...
19	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
20	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	88.7	86.3	82.9	78.5	73.0	66.4
21	105.0	105.0	105.0	105.0	105.0	105.0	104.8	102.8	100.1	96.8	92.8	88.2	82.9	77.0
22	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
23	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
24	60.0	...	...	...	...	...	...	...	...	...	...	...	...	...
25	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
26	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
27	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
28	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
29	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	77.3	73.1	68.0	61.7
30	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	86.9	82.3	76.4	69.4
31	75.0	75.0	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...
32	85.0	85.0	85.0	85.0	85.0	85.0	85.0	...	...	...	...	...	...	...
33	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	67.6	64.0	59.5	54.0
34	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	70.0	67.6	64.0	59.5	54.0
35	105.0	105.0	105.0	105.0	105.0	105.0	104.8	102.8	100.1	96.8	92.8	88.2	82.9	77.0
36	115.0	115.0	115.0	115.0	115.0	115.0	114.8	112.6	109.6	106.0	101.6	96.6	90.8	84.4
37	60.0	...	...	...	...	...	...	...	...	...	...	...	...	...
38	70.0	...	...	...	...	...	...	...	...	...	...	...	...	...
39	125.0	125.0	125.0	125.0	125.0	125.0	123.1	120.1	116.5	112.3	107.9	103.9	101.0	100.0
40	155.0	155.0	155.0	155.0	155.0	155.0	155.0	155.0	155.0	153.1	147.1	141.7	137.7	136.4
41	170.0	170.0	170.0	170.0	170.0	170.0	167.4	163.4	158.4	152.7	146.8	141.3	137.3	136.0
42	180.0	180.0	180.0	180.0	180.0	180.0	177.3	173.0	167.7	161.7	155.4	149.7	145.4	144.0
43	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	99.3	95.6	92.9	92.0
44	120.0	120.0	120.0	120.0	120.0	120.0	118.2	115.3	111.8	107.8	103.6	99.8	96.9	96.0
45	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	116.6	112.2	109.0	108.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
(25) 1	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23
(25) 2	Alloy steel	Bolting	SA/ISO 898-1	10.9
(25) 3	Alloy steel	Bolting	SA/ISO 898-1	12.9
4	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23
5	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{4}$ Mo	Bolting	SA-540	B23
6	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
7	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
8	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
9	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
10	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
11	2Ni- $\frac{3}{4}$ Cr- $\frac{1}{3}$ Mo	Bolting	SA-540	B24
12	2Ni-1Cu	Forgings	SA-182	FR
13	2Ni-1Cu	Fittings	SA-234	WPR
14	2Ni-1Cu	Smls. & wld. pipe	SA-333	9
15	2Ni-1Cu	Tube	SA-334	9
16	2Ni-1Cu	Forgings	SA-350	LF9
17	2Ni-1Cu	Smls. & wld. ftgs.	SA-420	WPL9
(25) 18	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N
19	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
(25) 20	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-372	N
21	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
22	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
23	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
24	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
25	2Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Forgings	SA-723	1
26	2 $\frac{1}{2}$ Ni	Pipe	SA-333	7
27	2 $\frac{1}{2}$ Ni	Tube	SA-334	7
28	2 $\frac{1}{2}$ Ni	Plate	SA-203	A
29	2 $\frac{1}{2}$ Ni	Plate	SA-203	B
30	2 $\frac{1}{2}$ Ni	Castings	SA-352	LC2
31	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C
32	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C
33	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	C
(25) 34	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-372	P
35	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
(25) 36	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-372	P
37	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
38	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
39	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
40	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
41	2 $\frac{3}{4}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	2
42	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B
43	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Forgings	SA-372	M
44	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B
45	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-543	B

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	H43400	3	$\leq 9\frac{1}{2}$	145
2	...	...	...	151
3	...	...	...	177
4	H43400	2	$\leq 9\frac{1}{2}$	155
5	H43400	1	≤ 8	165
6	K24064	5	$6 < t \leq 9\frac{1}{2}$	115
7	K24064	5	≤ 6	120
8	K24064	4	$\leq 9\frac{1}{2}$	135
9	K24064	3	$\leq 9\frac{1}{2}$	145
10	K24064	2	$\leq 9\frac{1}{2}$	155
11	K24064	1	≤ 8	165
12	K22035	...	...	63
13	K22035	...	...	63
14	K22035	...	...	63
15	K22035	...	...	63
16	K22036	...	...	63
17	K22035	...	...	63
18	K23550	100	...	115
19	K23550	1	...	115
20	K23550	120	...	135
21	K23550	2	...	135
22	K23550	2a	...	145
23	K23550	3	...	155
24	K23550	4	...	175
25	K23550	5	...	190
26	K21903	...	...	65
27	K21903	...	...	65
28	K21703	...	...	65
29	K22103	...	...	70
30	J22500	...	...	70
31	...	3	...	90
32	...	1	...	105
33	...	2	...	115
34	K34035	100	...	115
35	K34035	1	...	115
36	K34035	120	...	135
37	K34035	2	...	135
38	K34035	2a	...	145
39	K34035	3	...	155
40	K34035	4	...	175
41	K34035	5	...	190
42	K42339	3	...	90
43	K42365	85	...	105
44	K42339	1	...	105
45	K42339	2	...	115

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	145.0	145.0	145.0	145.0	145.0	145.0	142.8	139.3	135.1	130.3	125.2	120.6	117.1	116.0
2	150.8	150.8	150.8	...	...	...	...	...	...	...	...	...	...	...
3	176.9	176.9	176.9	...	...	...	...	...	...	...	...	...	...	...
4	155.0	155.0	155.0	155.0	155.0	155.0	152.6	149.0	144.4	139.2	133.9	128.9	125.2	124.0
5	165.0	165.0	165.0	165.0	165.0	165.0	165.0	158.6	153.7	148.2	142.5	137.2	133.3	132.0
6	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	99.3	95.6	92.9	92.0
7	120.0	120.0	120.0	120.0	120.0	120.0	118.2	115.3	111.8	107.8	103.6	99.8	96.9	96.0
8	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	116.6	112.2	109.0	108.0
9	145.0	145.0	145.0	145.0	145.0	145.0	142.8	139.3	135.1	130.3	125.2	120.6	117.1	116.0
10	155.0	155.0	155.0	155.0	155.0	155.0	152.6	149.0	144.4	139.2	133.9	128.9	125.2	124.0
11	165.0	165.0	165.0	165.0	165.0	165.0	165.0	158.6	153.7	148.2	142.5	137.2	133.3	132.0
12	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
13	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
14	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
15	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
16	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
17	63.0	...	...	...	...	...	...	...	...	...	...	...	...	...
18	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	...	...	...	...
19	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	...	...	...	...
20	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	...	...	...	...
21	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	...	...	...	...
22	145.0	145.0	145.0	145.0	145.0	145.0	142.7	139.3	135.1	130.3	...	...	...	...
23	155.0	155.0	155.0	155.0	155.0	155.0	152.6	149.0	144.4	139.2	...	...	...	...
24	175.0	175.0	175.0	175.0	175.0	175.0	172.3	168.2	163.1	157.2	...	...	...	...
25	190.0	190.0	190.0	190.0	190.0	190.0	187.1	182.6	177.0	170.7	...	...	...	...
26	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
27	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
28	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
29	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
30	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
31	90.0	90.0	90.0	89.1	88.5	87.3	86.2	84.7	82.6	79.9	76.5	72.5	67.7	62.1
32	105.0	105.0	105.0	103.9	103.3	101.9	100.6	98.8	96.4	93.2	89.3	84.5	78.9	72.5
33	115.0	115.0	115.0	113.8	113.1	111.6	110.2	108.2	105.5	102.1	97.8	92.6	86.5	79.4
34	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	...	...	...	...
35	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	...	...	...	...
36	135.0	135.0	135.0	135.5	135.0	135.0	132.9	129.7	125.8	121.3	...	...	...	...
37	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	...	...	...	...
38	145.0	145.0	145.0	145.0	145.0	145.0	142.7	139.3	135.1	130.3	...	...	...	...
39	155.0	155.0	155.0	155.0	155.0	155.0	152.6	149.0	144.4	139.2	...	...	...	...
40	175.0	175.0	175.0	175.0	175.0	175.0	172.3	168.2	163.1	157.2	...	...	...	...
41	190.0	190.0	190.0	190.0	190.0	190.0	187.1	182.6	177.0	170.7	...	...	...	...
42	90.0	90.0	90.0	89.1	88.5	87.3	86.2	84.7	82.6	79.9	76.5	72.5	67.7	62.1
43	105.0	105.0	105.0	103.9	103.3	101.9	100.6	98.8	96.4	93.2	89.3	84.5	78.9	72.5
44	105.0	105.0	105.0	103.9	103.3	101.9	100.6	98.8	96.4	93.2	89.3	84.5	78.9	72.5
45	115.0	115.0	115.0	113.8	113.1	111.6	110.2	108.2	105.5	102.1	97.8	92.6	86.5	79.4

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	3Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo	Forgings	SA-372	M
2	3 $\frac{1}{2}$ Ni	Pipe	SA-333	3
3	3 $\frac{1}{2}$ Ni	Tube	SA-334	3
4	3 $\frac{1}{2}$ Ni	Fittings	SA-420	WPL3
5	3 $\frac{1}{2}$ Ni	Plate	SA-203	D
6	3 $\frac{1}{2}$ Ni	Forgings	SA-350	LF3
7	3 $\frac{1}{2}$ Ni	Forgings	SA-765	III
8	3 $\frac{1}{2}$ Ni	Plate	SA-203	E
9	3 $\frac{1}{2}$ Ni	Castings	SA-352	LC3
10	3 $\frac{1}{2}$ Ni	Plate	SA-203	F
11	3 $\frac{1}{2}$ Ni	Plate	SA-203	F
(25) 12	3 $\frac{1}{2}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Mn	Castings	SA-487	17
(25) 13	3 $\frac{1}{2}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Mn	Castings	SA-487	17
(25) 14	3 $\frac{1}{2}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Mn	Castings	SA-487	17
(25) 15	3 $\frac{1}{2}$ Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Mn	Castings	SA-487	17
16	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N
(25) 17	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-541	4N
18	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N
(25) 19	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-541	5
20	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-508	4N
(25) 21	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-541	4N
(25) 22	3 $\frac{1}{2}$ Ni-1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-541	5
23	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
24	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
25	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
26	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
27	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
28	4Ni-1 $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-723	3
29	5Ni- $\frac{1}{4}$ Mo	Plate	SA-645	A
30	7Ni	Plate	SA-553	III
31	8Ni	Forgings	SA-522	II
32	8Ni	Plate	SA-553	II
33	9Ni	Plate	SA/EN 10028-4	X8Ni9
34	9Ni	Plate	SA/EN 10028-4	X8Ni9
35	9Ni	Plate	SA/EN 10028-4	X7Ni9
36	9Ni	Plate	SA/EN 10028-4	X8Ni9
37	9Ni	Smls. & wld. pipe	SA-333	8
38	9Ni	Smls. & wld. tube	SA-334	8
39	9Ni	Plate	SA-353	...
40	9Ni	Smls. & wld. ftgs.	SA-420	WPL8
41	9Ni	Forgings	SA-522	I
42	9Ni	Plate	SA-553	I
(25) 43	46Fe-24Ni-21Cr-6Mo-N	Smls. & wld. fittings	SA-403	...
(25) 44	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-182	F62
(25) 45	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-965	F62

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	K42365	100	...	120
2	K31918	...	...	65
3	K31918	...	...	65
4	...	...	...	65
5	K31718	...	...	65
6	K32025	...	...	70
7	K32026	...	...	70
8	K32018	...	...	70
9	J31550	...	...	70
10	...	...	>2	75
11	...	...	≤2	80
12	...	A	12 < t ≤ 14	102
13	...	A	8 < t ≤ 12	106
14	...	A	6 < t ≤ 8	110
15	...	A	≤6	113
16	K22375	3	...	90
17	K42343	3	...	90
18	K22375	1	...	105
19	K42348	1	...	105
20	K22375	2	...	115
21	K42343	2	...	115
22	K42348	2	...	115
23	K44045	1	...	115
24	K44045	2	...	135
25	K44045	3	...	155
26	K44045	2a	...	145
27	K44045	4	...	175
28	K44045	5	...	190
29	K41583	...	...	95
30	K61365	...	≤2	100
31	K71340	...	...	100
32	K71340	...	...	100
33	...	NNT640	≤2	93
34	...	QT640	≤2	93
35	...	QT	≤2	98.5
36	...	QT680	≤2	98.5
37	K81340	...	...	100
38	K81340	...	...	100
39	K81340	...	...	100
40	K81340	...	...	100
41	K81340	...	...	100
42	K81340	...	...	100
43	N08367	...	...	95
44	N08367	...	...	95
45	N08367	...	...	95

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	120.0	120.0	120.0	118.8	118.0	116.4	115.0	112.9	110.1	106.5	102.0	96.6	90.2	82.8
2	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
3	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
4	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
5	65.0	65.0	65.0	65.0	65.0	65.0	65.0	61.7	57.6	53.7	50.1	46.5	42.2	36.3
6	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
7	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
8	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
9	70.0	70.0	70.0	70.0	70.0	70.0	70.0	66.5	62.0	57.9	54.0	50.1	45.5	39.1
10	75.0	75.0	75.0	75.0	75.0	75.0	75.0	71.2	66.5	62.0	57.9	53.7	48.7	41.9
11	80.0	80.0	80.0	80.0	80.0	80.0	80.0	76.0	70.9	66.1	61.7	57.2	52.0	44.7
12	102	...	...	...	...	...	...	...	...	...	...	...	...	...
13	106	...	...	...	...	...	...	...	...	...	...	...	...	...
14	110	...	...	...	...	...	...	...	...	...	...	...	...	...
15	113	...	...	...	...	...	...	...	...	...	...	...	...	...
16	90.0	90.0	90.0	89.1	88.5	87.3	86.2	84.7	82.6	79.9	76.5	72.5	67.7	62.1
17	90.0	90.0	90.0	89.1	88.5	87.3	86.2	84.7	82.6	79.9	76.5	72.5	67.7	62.1
18	105.0	105.0	105.0	103.9	103.3	101.9	100.6	98.8	96.4	93.2	89.3	84.5	78.9	72.5
19	105.0	105.0	105.0	103.9	103.3	101.9	100.6	98.8	96.4	93.2	89.3	84.5	78.9	72.5
20	115.0	115.0	115.0	113.8	113.1	111.6	110.2	108.2	105.5	102.1	97.8	92.6	86.5	79.4
21	115.0	115.0	115.0	113.8	113.1	111.6	110.2	108.2	105.5	102.1	97.8	92.6	86.5	79.4
22	115.0	115.0	115.0	113.8	113.1	111.6	110.2	108.2	105.5	102.1	97.8	92.6	86.5	79.4
23	115.0	115.0	115.0	115.0	115.0	115.0	113.2	110.5	107.1	103.3	...	...	...	...
24	135.0	135.0	135.0	135.0	135.0	135.0	132.9	129.7	125.8	121.3	...	...	...	...
25	155.0	155.0	155.0	155.0	155.0	155.0	152.6	149.0	144.4	139.2	...	...	...	...
26	145.0	145.0	145.0	145.0	145.0	145.0	142.7	139.3	135.1	130.3	...	...	...	...
27	175.0	175.0	175.0	175.0	175.0	175.0	172.3	168.2	163.1	157.2	...	...	...	...
28	190.0	190.0	190.0	190.0	190.0	190.0	187.1	182.6	177.0	170.7	...	...	...	...
29	95.0	...	...	...	...	...	...	...	...	...	...	...	...	...
30	100.0	90.2	...	...	...	...	...	...	...	...	...	...	...	...
31	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
32	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
33	92.8	92.8	92.4	...	...	...	...	...	...	...	...	...	...	...
34	92.8	92.8	92.4	...	...	...	...	...	...	...	...	...	...	...
35	98.6	98.6	98.2	...	...	...	...	...	...	...	...	...	...	...
36	98.6	98.6	98.2	...	...	...	...	...	...	...	...	...	...	...
37	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
38	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
39	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
40	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
41	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
42	100.0	100.0	99.5	...	...	...	...	...	...	...	...	...	...	...
43	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
44	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
45	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
(25) 1	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...
(25) 2	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...
(25) 3	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...
(25) 4	46Fe-24Ni-21Cr-6Mo-N	Plate	SA-240	...
(25) 5	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...
(25) 6	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-276	...
(25) 7	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-479	...
(25) 8	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...
(25) 9	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...
(25) 10	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...
(25) 11	46Fe-24Ni-21Cr-6Mo-N	Sheet, strip	SA-240	...
(25) 12	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...
13	25Ni-15Cr-2Ti	Bolting	SA-453	660
14	25Ni-15Cr-2Ti	Bolting	SA-453	660
15	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660
16	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660
(25) 17	25Ni-47Fe-21Cr-5Mo	Forgings	SA-182	F700
(25) 18	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SA-240	...
(25) 19	25Ni-47Fe-21Cr-5Mo	Bar	SA-276	...
(25) 20	25Ni-47Fe-21Cr-5Mo	Wld. pipe	SA-358	...
(25) 21	25Ni-47Fe-21Cr-5Mo	Fittings	SA-403	700
(25) 22	25Ni-47Fe-21Cr-5Mo	Bar	SA-479	...
(25) 23	25Ni-47Fe-21Cr-5Mo	Forgings	SA-965	F700
24	27Ni-22Cr-7Mo-Mn-Cu-N	Forgings	SA-182	...
25	27Ni-22Cr-7Mo-Mn-Cu-N	Smls. tube	SA-213	...
26	27Ni-22Cr-7Mo-Mn-Cu-N	Plate	SA-240	...
27	27Ni-22Cr-7Mo-Mn-Cu-N	Wld. tube	SA-249	...
28	29Ni-20Cr-3Cu-2Mo	Castings	SA-351	CN7M
(25) 29	35Ni-35Fe-20Cr-Cb	Forgings	SA-182	F20
(25) 30	35Ni-35Fe-20Cr-Cb	Forgings	SA-965	F20
(25) 31	35Ni-35Fe-20Cr-Cb	Plate	SA-240	...
(25) 32	35Ni-35Fe-20Cr-Cb	Bar	SA-276	Alloy 20
(25) 33	35Ni-35Fe-20Cr-Cb	Bar	SA-479	Alloy 20
(25) 34	35Ni-35Fe-20Cr-Cb	Smls. pipe	SA-312	Alloy 20
(25) 35	35Ni-35Fe-20Cr-Cb	Wld. pipe	SA-312	Alloy 20
(25) 36	35Ni-35Fe-20Cr-Cb	Smls. tube	SA-213	Alloy 20
(25) 37	35Ni-35Fe-20Cr-Cb	Wld. tube	SA-249	Alloy 20
(25) 38	35Ni-35Fe-20Cr-Cb	Smls. & wld. ftgs.	SA-403	...
(25) 39	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC11
(25) 40	42Fe-33Ni-21Cr	Smls. tube	SA-213	...
(25) 41	42Fe-33Ni-21Cr	Plate	SA-240	...
(25) 42	42Fe-33Ni-21Cr	Wld. tube	SA-249	...
(25) 43	42Fe-33Ni-21Cr	Bar	SA-276	...
(25) 44	42Fe-33Ni-21Cr	Smls. pipe	SA-312	...
(25) 45	42Fe-33Ni-21Cr	Bar	SA-479	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	N08367	...	$> \frac{3}{16}$	95
2	N08367	...	$> \frac{3}{16}$	95
3	N08367	...	$> \frac{3}{16}$	95
4	N08367	...	$\geq \frac{3}{16}$	95
5	N08367	...	$> \frac{3}{16}$	95
6	N08367	...	...	95
7	N08367	...	...	95
8	N08367	...	$\leq \frac{3}{16}$	100
9	N08367	...	$\leq \frac{3}{16}$	100
10	N08367	...	$\leq \frac{3}{16}$	100
11	N08367	...	$< \frac{3}{16}$	100
12	N08367	...	$\leq \frac{3}{16}$	100
13	S66286	A	...	130
14	S66286	B	...	130
15	S66286	1	...	130
16	S66286	2	...	130
17	N08700	...	...	80
18	N08700	...	...	80
19	N08700	...	...	80
20	N08700	...	...	80
21	N08700	...	...	80
22	N08700	...	...	80
23	N08700	...	...	80
24	S31277	...	...	112
25	S31277	...	...	112
26	S31277	...	...	112
27	S31277	...	...	112
28	J95150	...	...	62
29	N08020	...	...	80
30	N08020	...	...	80
31	N08020	...	...	80
32	N08020	...	...	80
33	N08020	...	...	80
34	N08020	...	...	80
35	N08020	...	...	80
36	N08020	...	...	80
37	N08020	...	...	80
38	N08020	...	...	85
39	N08811	...	...	65
40	N08811	...	...	65
41	N08811	...	...	65
42	N08811	...	...	65
43	N08811	...	...	65
44	N08811	...	...	65
45	N08811	...	...	65

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
2	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
3	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
4	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
5	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
6	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
7	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
8	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
9	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
10	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
11	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
12	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
13	130.0	130.0	130.0	129.7	127.1	124.8	123.7	122.6	121.3	119.8	118.3	116.4	114.4	112.1
14	130.0	130.0	130.0	129.7	127.1	124.8	123.7	122.6	121.3	119.8	118.3	116.4	114.4	112.1
15	130.0	130.0	130.0	130.0	127.6	125.2	124.0	122.7	121.3	119.8	118.1	116.3	114.4	112.1
16	130.0	130.0	130.0	130.0	127.6	125.2	124.0	122.7	121.3	119.8	118.1	116.3	114.4	112.1
17	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
18	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
19	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
20	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
21	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
22	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
23	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
24	112.0	103.3	97.6	93.4	90.3	87.6	86.3	85.2	84.2	83.6	...	...	...	...
25	112.0	103.3	97.6	93.4	90.3	87.6	86.3	85.2	84.2	83.6	...	...	...	...
26	112.0	103.3	97.6	93.4	90.3	87.6	86.3	85.2	84.2	83.6	...	...	...	...
27	112.0	103.3	97.6	93.4	90.3	87.6	86.3	85.2	84.2	83.6	...	...	...	...
28	62.0	52.4	47.7	44.6	42.4	40.6	39.9	39.2	...	...	...	...	...	...
29	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
30	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
31	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
32	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
33	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
34	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
35	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
36	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
37	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
38	85.0	85.0	84.1	82.4	82.2	82.1	81.9	81.5	81.1	81.1	...	...	...	...
39	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
40	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
41	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
42	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
43	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
44	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
45	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	
14	...	...	...	...	...	...	...	...	...	...	...	...	
15	...	...	...	...	...	...	...	...	...	...	...	...	
16	...	...	...	...	...	...	...	...	...	...	...	...	
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
40	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
41	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
42	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
43	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
44	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
45	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
	Ferrous Materials (Cont'd)			
(25) 1	42Fe-33Ni-21Cr	Wld. tube	SA-688	...
(25) 2	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC11
3	14Cr-16Ni-6Si-Cu-Mo	Smls. tube	SA-213	...
4	14Cr-16Ni-6Si-Cu-Mo	Plate	SA-240	...
5	14Cr-16Ni-6Si-Cu-Mo	Wld. tube	SA-249	...
6	14Cr-16Ni-6Si-Cu-Mo	Wld. pipe	SA-312	...
7	14Cr-16Ni-6Si-Cu-Mo	Smls. & wld. fittings	SA-403	...
8	14Cr-16Ni-6Si-Cu-Mo	Bar	SA-479	...
9	16Cr-4Ni-6Mn	Plate	SA-240	201LN
10	16Cr-9Mn-2Ni-N	Plate	SA-240	204
11	16Cr-12Ni-2Mo	Forgings	SA-182	F316L
12	16Cr-12Ni-2Mo	Forgings	SA-965	F316L
13	16Cr-12Ni-2Mo	Forgings	SA-182	F316L
14	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L
15	16Cr-12Ni-2Mo	Plate	SA-240	316L
16	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L
17	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316L
18	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L
19	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L
20	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L
21	16Cr-12Ni-2Mo	Smls. & wld. ftgs.	SA-403	316L
22	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316L
23	16Cr-12Ni-2Mo	Bar	SA-479	316L
24	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L
25	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316L
26	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316L
27	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316L
28	16Cr-12Ni-2Mo	Forgings	SA-182	F316
29	16Cr-12Ni-2Mo	Forgings	SA-965	F316
30	16Cr-12Ni-2Mo	Forgings	SA-182	F316H
31	16Cr-12Ni-2Mo	Forgings	SA-965	F316H
32	16Cr-12Ni-2Mo	Forgings	SA-182	F316
33	16Cr-12Ni-2Mo	Bolting	SA-193	B8M
34	16Cr-12Ni-2Mo	Bolting	SA-193	B8MA
35	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316
36	16Cr-12Ni-2Mo	Plate	SA-240	316
37	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316
38	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316
39	16Cr-12Ni-2Mo	Bolting	SA-320	B8M
40	16Cr-12Ni-2Mo	Bolting	SA-320	B8MA
41	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316
42	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316
43	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316
44	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316
45	16Cr-12Ni-2Mo	Smls. & wld. ftgs.	SA-403	316

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	N08811	...	...	65
2	N08811	...	...	65
3	S38815	...	...	78
4	S38815	...	...	78
5	S38815	...	...	78
6	S38815	...	...	78
7	S38815	...	...	78
8	S38815	...	...	78
9	S20153	...	...	95
10	S20400	...	...	95
11	S31603	...	>5	65
12	S31603	...	...	65
13	S31603	...	≤5	70
14	S31603	...	...	70
15	S31603	...	...	70
16	S31603	...	...	70
17	S31603	...	...	70
18	S31603	1	...	70
19	S31603	3	...	70
20	S31603	4	...	70
21	S31603	...	...	70
22	S31603	...	...	70
23	S31603	Annealed	...	70
24	S31603	...	...	70
25	S31603	...	...	70
26	S31603	...	...	70
27	...	...	...	70
28	S31600	...	>5	70
29	S31600	...	...	70
30	S31609	...	>5	70
31	S31609	...	...	70
32	S31600	...	≤5	75
33	S31600	1	...	75
34	S31600	1A	...	75
35	S31600	...	...	75
36	S31600	...	...	75
37	S31600	...	...	75
38	S31600	...	...	75
39	S31600	1	...	75
40	S31600	1A	...	75
41	S31600	1	...	75
42	S31600	3	...	75
43	S31600	4	...	75
44	S31600	...	...	75
45	S31600	...	...	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
2	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
3	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
4	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
5	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
6	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
7	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
8	78.0	78.0	77.8	75.3	73.5	72.4	72.2	72.1	72.0	71.9	...	...	...	...
9	95.0	82.9	74.2	70.3	69.1	68.7	68.4	67.9	67.0	65.9	64.5	63.0	61.7	60.9
10	95.0	82.6	72.2	66.2	63.5	62.7	62.6	62.6	62.3	61.8	60.8	59.2	56.8	53.4
11	65.0	63.2	59.5	57.8	57.3	57.3	57.2	57.1	56.7	56.2	55.4	54.4	53.0	51.4
12	65.0	63.2	59.5	57.8	57.3	57.3	57.2	57.1	56.7	56.2	55.4	54.4	53.0	51.4
13	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
14	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
15	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
16	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
17	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
18	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
19	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
20	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
21	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
22	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
23	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
24	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
25	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
26	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
27	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
28	70.0	70.0	68.0	67.1	67.0	67.0	67.0	67.0	66.7	66.1	65.1	63.8	62.1	60.0
29	70.0	70.0	68.0	67.1	67.0	67.0	67.0	67.0	66.7	66.1	65.1	63.8	62.1	60.0
30	70.0	70.0	68.0	67.1	67.0	67.0	67.0	67.0	66.7	66.1	65.1	63.8	62.1	60.0
31	70.0	70.0	68.0	67.1	67.0	67.0	67.0	67.0	66.7	66.1	65.1	63.8	62.1	60.0
32	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
33	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
34	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
35	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
36	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
37	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
38	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
39	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
40	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
41	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
42	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
43	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
44	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
45	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
2	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	50.1	48.6	46.7	44.6	...	...	...	...	...	...	...	...	...
12	50.1	48.6	46.7	44.6	...	...	...	...	...	...	...	...	...
13	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
14	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
15	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
16	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
17	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
18	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
19	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
20	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
21	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
22	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
23	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
24	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
25	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
26	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	56.3	52.2	48.3	44.5	40.9	37.4	34.0	30.8	27.8	24.9	...	...	...
29	56.3	52.2	48.3	44.5	40.9	37.4	34.0	30.8	27.8	24.9	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
33	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
34	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
35	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
36	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
37	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
38	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
39	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
40	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
41	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
42	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
43	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
44	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
45	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316
2	16Cr-12Ni-2Mo	Bar	SA-479	316
3	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316
4	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316
5	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316
6	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316
7	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2
8	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2
9	16Cr-12Ni-2Mo	Forgings	SA-182	F316H
10	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H
11	16Cr-12Ni-2Mo	Plate	SA-240	316H
12	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H
13	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316H
14	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H
15	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H
16	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H
17	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H
18	16Cr-12Ni-2Mo	Smls. & wld. ftgs.	SA-403	316H
19	16Cr-12Ni-2Mo	Bar	SA-479	316H
20	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316H
21	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316H
22	16Cr-12Ni-2Mo	Bar	SA-276	316
23	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2
24	16Cr-12Ni-2Mo	Bolting	SA-193	B8M
25	16Cr-12Ni-2Mo	Bolting	SA-320	B8M
26	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2
27	16Cr-12Ni-2Mo	Bar	SA-276	316
28	16Cr-12Ni-2Mo	Bar	SA-276	316
29	16Cr-12Ni-2Mo	Bolting	SA-193	B8M
30	16Cr-12Ni-2Mo	Bolting	SA-320	B8M
31	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2
32	16Cr-12Ni-2Mo	Bar	SA-276	316
33	16Cr-12Ni-2Mo	Bar	SA-276	316
34	16Cr-12Ni-2Mo	Bolting	SA-193	B8M
35	16Cr-12Ni-2Mo	Bolting	SA-320	B8M
36	16Cr-12Ni-2Mo	Bar	SA-276	316
37	16Cr-12Ni-2Mo	Bolting	SA-193	B8M
38	16Cr-12Ni-2Mo	Bolting	SA-320	B8M
39	16Cr-12Ni-2Mo	Bar	SA-276	316
40	16Cr-12Ni-2Mo	Bar	SA-276	316
41	16Cr-12Ni-2Mo-Cb	Plate	SA-240	316Cb
42	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN
43	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316LN
44	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN
45	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316LN

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S31600	...	...	75
2	S31600	Annealed	...	75
3	S31600	...	...	75
4	S31600	...	...	75
5	S31600	...	...	75
6	...	...	...	75
7	...	...	≤ 3	75
8	...	...	≤ 3	75
9	S31609	...	≤ 5	75
10	S31609	...	...	75
11	S31609	...	...	75
12	S31609	...	...	75
13	S31609	...	...	75
14	S31609	1	...	75
15	S31609	3	...	75
16	S31609	4	...	75
17	S31609	...	...	75
18	S31609	...	...	75
19	S31609	...	...	75
20	S31609	...	...	75
21	S31609	...	...	75
22	S31600	S	$2\frac{1}{2} < t \leq 3$	80
23	S31600	2B	$2\frac{1}{2} < t \leq 3$	80
24	S31600	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	90
25	S31600	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	90
26	S31600	2B	$2 < t \leq 2\frac{1}{2}$	90
27	S31600	S	$2 < t \leq 2\frac{1}{2}$	90
28	S31600	B	$1\frac{1}{2} < t \leq 1\frac{3}{4}$	95
29	S31600	2	$1 < t \leq 1\frac{1}{4}$	95
30	S31600	2	$1 < t \leq 1\frac{1}{4}$	95
31	S31600	2B	≤ 2	95
32	S31600	S	$t \leq 2$	95
33	S31600	B	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100
34	S31600	2	$\frac{3}{4} < t \leq 1$	100
35	S31600	2	$\frac{3}{4} < t \leq 1$	100
36	S31600	B	$1 < t \leq 1\frac{1}{4}$	105
37	S31600	2	$\leq \frac{3}{4}$	110
38	S31600	2	$\leq \frac{3}{4}$	110
39	S31600	B	$\frac{3}{4} < t \leq 1$	115
40	S31600	B	$t \leq \frac{1}{4}$	125
41	S31640	...	...	75
42	S31653	...	> 5	70
43	S31653	...	...	70
44	S31653	...	≤ 5	75
45	S31653	...	...	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
2	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
3	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
4	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
5	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
6	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
7	75.4	72.9	69.5	67.1	66.2	66.2	66.2	66.2	66.0	65.3	64.3	62.9	61.4	59.8
8	75.4	75.1	73.5	72.4	72.0	72.0	72.0	72.0	71.9	71.2	70.1	68.7	66.8	64.7
9	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
10	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
11	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
12	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
13	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
14	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
15	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
16	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
17	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
18	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
19	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
20	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
21	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
22	80.0	80.0	77.8	76.7	76.6	76.6	...	...	...	...	...	...	...	...
23	80.0	80.0	77.2	74.4	74.4	74.4	74.4	74.4	73.9	73.5	72.2	70.4	68.6	66.9
24	90.0	90.0	86.8	83.7	83.7	83.7	83.7	83.7	83.2	82.7	81.2	79.2	77.2	75.2
25	90.0	90.0	86.8	83.7	83.7	83.7	83.7	83.7	83.2	82.7	81.2	79.2	77.2	75.2
26	90.0	90.0	86.8	83.7	83.7	83.7	83.7	83.7	83.2	82.7	81.2	79.2	77.2	75.2
27	90.0	90.0	87.5	86.3	86.2	86.2	...	...	...	...	...	...	...	...
28	95.0	95.0	92.3	91.1	90.9	90.9	...	...	...	...	...	...	...	...
29	95.0	95.0	91.6	88.3	88.3	88.3	88.3	88.3	87.8	87.3	85.7	83.6	81.5	79.4
30	95.0	95.0	91.6	88.3	88.3	88.3	88.3	88.3	87.8	87.3	85.7	83.6	81.5	79.4
31	95.0	95.0	91.6	88.3	88.3	88.3	88.3	88.3	87.8	87.3	85.7	83.6	81.5	79.4
32	95.0	95.0	92.3	91.1	90.9	90.9	...	...	...	...	...	...	...	...
33	100.0	100.0	97.2	95.9	95.7	95.7	...	...	...	...	...	...	...	...
34	100.0	100.0	98.6	96.3	95.7	95.7	95.7	95.7	95.3	94.4	93.0	91.1	88.7	85.7
35	100.0	100.0	98.6	96.3	95.7	95.7	95.7	95.7	95.3	94.4	93.0	91.1	88.7	85.7
36	105.0	105.0	102.1	100.7	100.5	100.5	...	...	...	...	...	...	...	...
37	110.0	110.0	108.4	105.9	105.3	105.3	105.3	105.3	104.8	103.8	102.3	100.2	97.6	94.3
38	110.0	110.0	108.4	105.9	105.3	105.3	105.3	105.3	104.8	103.8	102.3	100.2	97.6	94.3
39	115.0	115.0	111.8	110.2	110.1	110.1	...	...	...	...	...	...	...	...
40	125.0	125.0	121.5	119.8	119.7	119.7	...	...	...	...	...	...	...	...
41	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	...	...	...
42	70.0	70.0	66.0	62.6	60.3	59.0	58.6	58.3	57.9	57.6	57.1	56.4	55.6	54.6
43	70.0	70.0	66.0	62.6	60.3	59.0	58.6	58.3	57.9	57.6	57.1	56.4	55.6	54.6
44	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
45	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
											Ferrous Materials (Cont'd)		
1	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
2	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
3	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
4	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
5	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	16Cr-12Ni-2Mo-N	Plate	SA-240	316LN
2	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316LN
3	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316LN
4	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN
5	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN
6	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN
7	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316LN
8	16Cr-12Ni-2Mo-N	Fittings	SA-403	316LN
9	16Cr-12Ni-2Mo-N	Bar	SA-479	316LN
10	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316LN
11	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316N
12	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N
13	16Cr-12Ni-2Mo-N	Plate	SA-240	316N
14	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N
15	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316N
16	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N
17	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N
18	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N
19	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N
20	16Cr-12Ni-2Mo-N	Smls. & wld. ftgs.	SA-403	316N
21	16Cr-12Ni-2Mo-N	Bar	SA-479	316N
22	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316N
23	16Cr-12Ni-2Mo-N	Wld. pipe	SA-813	TP316N
24	16Cr-12Ni-2Mo-N	Wld. pipe	SA-814	TP316N
25	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N
26	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-11-2
27	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-13-3
28	16Cr-12Ni-2Mo-Ti	Smls. tube	SA-213	TP316Ti
29	16Cr-12Ni-2Mo-Ti	Plate	SA-240	316Ti
30	16Cr-12Ni-2Mo-Ti	Smls. & wld. pipe	SA-312	TP316Ti
(25) 31	...	Plate	SA/EN 10088-2	X6CrNiMoTi17-12-2
32	17Cr-4Ni-6Mn	Plate	SA-240	201-1
33	17Cr-4Ni-6Mn	Plate	SA-666	201-1
34	17Cr-4Ni-6Mn	Plate	SA-240	201-2
35	17Cr-4Ni-6Mn	Plate	SA-666	201-2
36	17Cr-7Ni	Plate, sheet, strip	SA-240	301
37	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...
38	18Cr-3Ni-12Mn	Plate	SA-240	XM-29
39	18Cr-3Ni-12Mn	Wld. tube	SA-249	XM-29
40	18Cr-3Ni-12Mn	Wld. pipe	SA-312	XM-29
41	18Cr-3Ni-12Mn	Bar	SA-479	XM-29
42	18Cr-3Ni-12Mn	Wld. tube	SA-688	TPXM-29
43	18Cr-5Ni-3Mo	Smls. & wld. tube	SA-789	...
44	18Cr-5Ni-3Mo	Smls. & wld. pipe	SA-790	...
45	18Cr-8Ni	Forgings	SA-182	F304L

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S31653	...	...	75
2	S31653	...	...	75
3	S31653	...	...	75
4	S31653	1	...	75
5	S31653	3	...	75
6	S31653	4	...	75
7	S31653	...	...	75
8	S31653	...	...	75
9	S31653	...	...	75
10	S31653	...	...	75
11	S31651	...	...	80
12	S31651	...	...	80
13	S31651	...	...	80
14	S31651	...	...	80
15	S31651	...	...	80
16	S31651	1	...	80
17	S31651	3	...	80
18	S31651	4	...	80
19	S31651	...	...	80
20	S31651	...	...	80
21	S31651	...	...	80
22	S31651	...	...	80
23	S31651	...	...	80
24	S31651	...	...	80
25	S31651	...	...	80
26	...	...	≤3	84
27	...	...	≤3	84
28	S31635	...	...	75
29	S31635	...	...	75
30	S31635	...	...	75
31	...	...	$t \leq \frac{5}{16}$	78.5
32	S20100	...	...	75
33	S20100	...	...	75
34	S20100	...	...	95
35	S20100	...	...	95
36	S30100	...	...	75
37	S30601	Solution ann.	...	78
38	S24000	...	...	100
39	S24000	...	...	100
40	S24000	...	...	100
41	S24000	...	...	100
42	S24000	...	...	100
43	S31500	...	...	92
44	S31500	...	...	92
45	S30403	...	>5	65

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
2	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
3	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
4	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
5	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
6	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
7	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
8	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
9	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
10	75.0	75.0	70.7	67.1	64.6	63.3	62.8	62.4	62.1	61.7	61.1	60.4	59.6	58.4
11	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
12	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
13	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
14	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
15	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
16	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
17	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
18	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
19	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
20	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
21	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
22	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
23	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
24	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
25	80.0	80.0	77.0	75.1	74.4	74.3	74.3	74.3	74.2	73.9	73.3	72.4	71.1	69.3
26	84.1	83.5	79.5	75.4	72.5	70.9	70.4	70.0	69.7	69.2	68.6	67.8	66.7	65.6
27	84.1	83.5	79.5	75.4	72.5	70.9	70.4	70.0	69.7	69.2	68.6	67.8	66.7	65.6
28	75.0	69.8	63.7	60.3	58.8	58.5	58.5	58.5	58.5	58.5	58.5	58.3	57.6	56.6
29	75.0	69.8	63.7	60.3	58.8	58.5	58.5	58.5	58.5	58.5	58.5	58.3	57.6	56.6
30	75.0	69.8	63.7	60.3	58.8	58.5	58.5	58.5	58.5	58.5	58.5	58.3	57.6	56.6
31	78.5	75.2	69.0	65.0	62.8	61.8	61.6	61.5	61.5	61.5	61.4	61.2	60.9	60.2
32	75.0	65.6	60.3	58.4	...	...	...	...	...	...	...	...	...	...
33	75.0	65.6	60.3	58.4	...	...	...	...	...	...	...	...	...	...
34	95.0	83.1	76.4	74.0	...	...	...	...	...	...	...	...	...	...
35	95.0	83.1	76.4	74.0	...	...	...	...	...	...	...	...	...	...
36	75.0	61.1	55.1	53.9	53.9	53.9	53.9	53.7	52.5	51.2	49.9	49.2	...	...
37	78.0	78.0	74.0	70.0	66.0	...	...	...	...	...	...	...	...	...
38	100.0	97.7	91.1	87.3	85.1	83.3	82.0	80.5	78.5	76.3	73.8	71.4	69.4	68.3
39	100.0	97.7	91.1	87.3	85.1	83.3	82.0	80.5	78.5	76.3	73.8	71.4	69.4	68.3
40	100.0	97.7	91.1	87.3	85.1	83.3	82.0	80.5	78.5	76.3	73.8	71.4	69.4	68.3
41	100.0	97.7	91.1	87.3	85.1	83.3	82.0	80.5	78.5	76.3	73.8	71.4	69.4	68.3
42	100.0	97.7	91.1	87.3	85.1	83.3	82.0	80.5	78.5	76.3	73.8	71.4	69.4	68.3
43	92.0	88.8	85.4	84.8	84.8	84.8	84.8	84.8	84.8	...	...	...	...	...
44	92.0	88.8	85.4	84.8	84.8	84.8	84.8	84.8	84.8	...	...	...	...	...
45	65.0	61.3	56.9	54.5	53.4	52.9	52.6	52.4	52.0	51.4	50.7	49.8	48.6	47.1

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	55.3	53.6	51.4	48.9	46.1	42.8	39.3	35.6	31.8	27.9	...	...	...
29	55.3	53.6	51.4	48.9	46.1	42.8	39.3	35.6	31.8	27.9	...	...	...
30	55.3	53.6	51.4	48.9	46.1	42.8	39.3	35.6	31.8	27.9	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	
45	46.6	45.6	44.7	43.7	...	...	...	...	...	...	...	...	...

(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-8Ni	Forgings	SA-965	F304L
2	18Cr-8Ni	Forgings	SA-182	F304L
3	18Cr-8Ni	Smls. tube	SA-213	TP304L
4	18Cr-8Ni	Plate	SA-240	304L
5	18Cr-8Ni	Wld. tube	SA-249	TP304L
6	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304L
7	18Cr-8Ni	Wld. pipe	SA-358	304L
8	18Cr-8Ni	Wld. pipe	SA-358	304L
9	18Cr-8Ni	Wld. pipe	SA-358	304L
10	18Cr-8Ni	Smls. & wld. ftgs.	SA-403	304L
11	18Cr-8Ni	Wld. pipe	SA-409	TP304L
12	18Cr-8Ni	Bar	SA-479	304L
13	18Cr-8Ni	Wld. tube	SA-688	TP304L
14	18Cr-8Ni	Wld. pipe	SA-813	TP304L
15	18Cr-8Ni	Wld. pipe	SA-814	TP304L
16	18Cr-8Ni	Bar	SA/JIS G4303	SUS304L
17	18Cr-8Ni	Forgings	SA-182	F304
18	18Cr-8Ni	Forgings	SA-182	F304H
19	18Cr-8Ni	Castings	SA-351	CF3
20	18Cr-8Ni	Castings	SA-351	CF8
21	18Cr-8Ni	Smls. pipe	SA-376	TP304
22	18Cr-8Ni	Cast pipe	SA-451	CPF3
23	18Cr-8Ni	Cast pipe	SA-451	CPF8
24	18Cr-8Ni	Forgings	SA-965	F304
25	18Cr-8Ni	Forgings	SA-965	F304H
26	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9
27	18Cr-8Ni	Forgings	SA-182	F304
28	18Cr-8Ni	Forgings	SA-182	F304H
29	18Cr-8Ni	Bolting	SA-193	B8
30	18Cr-8Ni	Bolting	SA-193	B8A
31	18Cr-8Ni	Smls. tube	SA-213	TP304
32	18Cr-8Ni	Smls. tube	SA-213	TP304H
33	18Cr-8Ni	Plate	SA-240	302
34	18Cr-8Ni	Plate	SA-240	304
35	18Cr-8Ni	Plate	SA-240	304H
36	18Cr-8Ni	Wld. tube	SA-249	TP304
37	18Cr-8Ni	Wld. tube	SA-249	TP304H
38	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304
39	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304H
40	18Cr-8Ni	Bolting	SA-320	B8
41	18Cr-8Ni	Bolting	SA-320	B8A
42	18Cr-8Ni	Wld. pipe	SA-358	304
43	18Cr-8Ni	Wld. pipe	SA-358	304
44	18Cr-8Ni	Wld. pipe	SA-358	304
45	18Cr-8Ni	Wld. pipe	SA-358	304H

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S30403	...	...	65
2	S30403	...	≤5	70
3	S30403	...	...	70
4	S30403	...	...	70
5	S30403	...	...	70
6	S30403	...	...	70
7	S30403	1	...	70
8	S30403	3	...	70
9	S30403	4	...	70
10	S30403	...	...	70
11	S30403	...	...	70
12	S30403	Annealed	...	70
13	S30403	...	...	70
14	S30403	...	...	70
15	S30403	...	...	70
16	...	...	...	70
17	S30400	...	>5	70
18	S30409	...	>5	70
19	J92500	...	...	70
20	J92600	...	...	70
21	S30400	...	≥8	70
22	J92500	...	...	70
23	J92600	...	...	70
24	S30400	...	...	70
25	S30409	...	...	70
26	...	...	≤3	72.5
27	S30400	...	≤5	75
28	S30409	...	≤5	75
29	S30400	1	...	75
30	S30400	1A	...	75
31	S30400	...	...	75
32	S30409	...	...	75
33	S30200	...	...	75
34	S30400	...	...	75
35	S30409	...	...	75
36	S30400	...	...	75
37	S30409	...	...	75
38	S30400	...	...	75
39	S30409	...	...	75
40	S30400	1	...	75
41	S30400	1A	...	75
42	S30400	1	...	75
43	S30400	3	...	75
44	S30400	4	...	75
45	S30409	1	...	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	65.0	61.3	56.9	54.5	53.4	52.9	52.6	52.4	52.0	51.4	50.7	49.8	48.6	47.1
2	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
3	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
4	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
5	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
6	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
7	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
8	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
9	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
10	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
11	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
12	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
13	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
14	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
15	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
16	70.0	66.1	61.2	58.7	57.5	56.9	56.7	56.4	56.0	55.4	54.6	53.6	52.3	50.7
17	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
18	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
19	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
20	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
21	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
22	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
23	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
24	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
25	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
26	72.5	68.1	63.9	60.8	59.3	58.8	58.7	58.5	58.1	57.5	56.6	55.4	54.0	52.7
27	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
28	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
29	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
30	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
31	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
32	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
33	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
34	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
35	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
36	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
37	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
38	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
39	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
40	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
41	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
42	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
43	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
44	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
45	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	46.6	45.6	44.7	43.7	...	...	...	...	...	...	...	...	...
2	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
3	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
4	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
5	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
6	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
7	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
8	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
9	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
10	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
11	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
12	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
13	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
14	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
15	50.2	49.1	48.1	47.0	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	52.4	50.1	47.4	44.2	40.6	36.7	32.7	28.8	25.3	22.4	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	52.4	50.1	47.4	44.2	40.6	36.7	32.7	28.8	25.3	22.4	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	52.4	50.1	47.4	44.2	40.6	36.7	32.7	28.8	25.3	22.4	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
30	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
31	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
41	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
42	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
43	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
44	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-8Ni	Wld. pipe	SA-358	304H
2	18Cr-8Ni	Wld. pipe	SA-358	304H
3	18Cr-8Ni	Wld. pipe	SA-358	304LN
4	18Cr-8Ni	Wld. pipe	SA-358	304LN
5	18Cr-8Ni	Wld. pipe	SA-358	304LN
6	18Cr-8Ni	Smls. pipe	SA-376	TP304
7	18Cr-8Ni	Smls. pipe	SA-376	TP304H
8	18Cr-8Ni	Smls. & wld. ftgs.	SA-403	304
9	18Cr-8Ni	Smls. & wld. ftgs.	SA-403	304H
10	18Cr-8Ni	Wld. pipe	SA-409	TP304
11	18Cr-8Ni	Bar	SA-479	302
12	18Cr-8Ni	Bar	SA-479	304
13	18Cr-8Ni	Bar	SA-479	304H
14	18Cr-8Ni	Wld. tube	SA-688	TP304
15	18Cr-8Ni	Wld. pipe	SA-813	TP304
16	18Cr-8Ni	Wld. pipe	SA-813	TP304H
17	18Cr-8Ni	Wld. pipe	SA-814	TP304
18	18Cr-8Ni	Wld. pipe	SA-814	TP304H
19	18Cr-8Ni	Bar	SA/JIS G4303	SUS302
20	18Cr-8Ni	Bar	SA/JIS G4303	SUS304
21	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10
22	18Cr-8Ni	Castings	SA-351	CF3A
23	18Cr-8Ni	Castings	SA-351	CF8A
24	18Cr-8Ni	Cast pipe	SA-451	CPF3A
25	18Cr-8Ni	Cast pipe	SA-451	CPF8A
26	18Cr-8Ni	Bolting	SA-320	B8
27	18Cr-8Ni	Bolting	SA-320	B8
28	18Cr-8Ni	Bolting	SA-320	B8
29	18Cr-8Ni	Bolting	SA-320	B8
30	18Cr-8Ni-N	Forgings	SA-182	F304LN
31	18Cr-8Ni-N	Forgings	SA-965	F304LN
32	18Cr-8Ni-N	Forgings	SA-182	F304LN
33	18Cr-8Ni-N	Bolting	SA-193	B8NA
34	18Cr-8Ni-N	Smls. tube	SA-213	TP304LN
35	18Cr-8Ni-N	Plate	SA-240	304LN
36	18Cr-8Ni-N	Wld. tube	SA-249	TP304LN
37	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304LN
38	18Cr-8Ni-N	Smls. pipe	SA-376	TP304LN
39	18Cr-8Ni-N	Smls. & wld. ftgs.	SA-403	304LN
40	18Cr-8Ni-N	Bar	SA-479	304LN
41	18Cr-8Ni-N	Wld. tube	SA-688	TP304LN
42	18Cr-8Ni-N	Wld. pipe	SA-813	TP304LN
43	18Cr-8Ni-N	Wld. pipe	SA-814	TP304LN
44	18Cr-8Ni-N	Forgings	SA-182	F304N
45	18Cr-8Ni-N	Smls. tube	SA-213	TP304N

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S30409	3	...	75
2	S30409	4	...	75
3	S30453	1	...	75
4	S30453	3	...	75
5	S30453	4	...	75
6	S30400	...	<8	75
7	S30409	...	...	75
8	S30400	...	...	75
9	S30409	...	...	75
10	S30400	...	...	75
11	S30200	...	...	75
12	S30400	Annealed	...	75
13	S30409	...	...	75
14	S30400	...	...	75
15	S30400	...	...	75
16	S30409	...	...	75
17	S30400	...	...	75
18	S30409	...	...	75
19	...	...	...	75
20	...	...	...	75
21	...	...	≤3	75
22	J92500	...	...	77
23	J92600	...	...	77
24	J92500	...	...	77
25	J92600	...	...	77
26	S30400	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100
27	S30400	2	$1 < t \leq 1\frac{1}{4}$	105
28	S30400	2	$\frac{3}{4} < t \leq 1$	115
29	S30400	2	$t \leq \frac{3}{4}$	125
30	S30453	...	>5	70
31	S30453	...	...	70
32	S30453	...	≤5	75
33	S30451	1A	...	75
34	S30453	...	...	75
35	S30453	...	...	75
36	S30453	...	...	75
37	S30453	...	...	75
38	S30453	...	...	75
39	S30453	WP	...	75
40	S30453	...	...	75
41	S30453	...	...	75
42	S30453	...	...	75
43	S30453	...	...	75
44	S30451	...	...	80
45	S30451	...	...	80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
2	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
3	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
4	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
5	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
6	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
7	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
8	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
9	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
10	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
11	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
12	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
13	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
14	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
15	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
16	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
17	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
18	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
19	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
20	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
21	75.4	71.1	67.0	64.4	63.5	63.5	63.5	63.5	63.5	63.2	62.3	61.1	59.5	57.8
22	77.0	72.9	68.0	65.7	65.1	65.1	65.1	65.1	65.0	64.5	63.6	62.5	60.9	58.9
23	77.0	72.9	68.0	65.7	65.1	65.1	65.1	65.1	65.0	64.5	63.6	62.5	60.9	58.9
24	77.0	72.9	68.0	65.7	65.1	65.1	65.1	65.1	65.0	64.5	63.6	62.5	60.9	58.9
25	77.0	72.9	68.0	65.7	65.1	65.1	65.1	65.1	65.0	64.5	63.6	62.5	60.9	58.9
26	100.0	...	...	...	...	...	...	...	...	...	...	...	...	...
27	105.0	...	...	...	...	...	...	...	...	...	...	...	...	...
28	115.0	...	...	...	...	...	...	...	...	...	...	...	...	...
29	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
30	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
31	70.0	66.3	61.8	59.7	59.2	59.2	59.2	59.2	59.0	58.6	57.9	56.8	55.4	53.6
32	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
33	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
34	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
35	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
36	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
37	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
38	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
39	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
40	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
41	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
42	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
43	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
44	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
45	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
15	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	56.1	53.7	50.8	47.3	43.5	39.3	35.0	30.9	27.1	24.0	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-8Ni-N	Plate	SA-240	304N
2	18Cr-8Ni-N	Wld. tube	SA-249	TP304N
3	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304N
4	18Cr-8Ni-N	Wld. pipe	SA-358	304N
5	18Cr-8Ni-N	Wld. pipe	SA-358	304N
6	18Cr-8Ni-N	Wld. pipe	SA-358	304N
7	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N
8	18Cr-8Ni-N	Smls. & wld. ftgs.	SA-403	304N
9	18Cr-8Ni-N	Bar	SA-479	304N
10	18Cr-8Ni-N	Wld. tube	SA-688	TP304N
11	18Cr-8Ni-N	Wld. pipe	SA-813	TP304N
12	18Cr-8Ni-N	Wld. pipe	SA-814	TP304N
13	18Cr-8Ni-N	Forgings	SA-965	F304N
14	18Cr-8Ni-N	Plate	SA/EN 10028-7	X2CrNiN18-10
15	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9
(25) 16	18Cr-8Ni-S	Bolting	SA-320	B8F
(25) 17	18Cr-8Ni-S	Bolting	SA-320	B8FA
18	18Cr-8Ni-Se	Bolting	SA-320	B8F
19	18Cr-8Ni-Se	Bolting	SA-320	B8FA
20	18Cr-8Ni-4Si-N	Bar	SA-479	...
21	18Cr-9Ni-3Cu-Cb-N	Smls. tube	SA-213	...
22	18Cr-10Ni-Cb	Forgings	SA-965	F348H
23	18Cr-10Ni-Cb	Castings	SA-351	CF8C
24	18Cr-10Ni-Cb	Cast pipe	SA-451	CPF8C
25	18Cr-10Ni-Cb	Forgings	SA-182	F347
26	18Cr-10Ni-Cb	Forgings	SA-965	F347
27	18Cr-10Ni-Cb	Forgings	SA-182	F347H
28	18Cr-10Ni-Cb	Forgings	SA-965	F347H
29	18Cr-10Ni-Cb	Forgings	SA-182	F348
30	18Cr-10Ni-Cb	Forgings	SA-965	F348
31	18Cr-10Ni-Cb	Forgings	SA-182	F348H
32	18Cr-10Ni-Cb	Forgings	SA-182	F347
33	18Cr-10Ni-Cb	Bolting	SA-193	B8C
34	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347
35	18Cr-10Ni-Cb	Plate	SA-240	347
36	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347
37	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347
38	18Cr-10Ni-Cb	Bolting	SA-320	B8C
39	18Cr-10Ni-Cb	Bolting	SA-320	B8CA
40	18Cr-10Ni-Cb	Wld. pipe	SA-358	347
41	18Cr-10Ni-Cb	Wld. pipe	SA-358	347
42	18Cr-10Ni-Cb	Wld. pipe	SA-358	347
43	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347
44	18Cr-10Ni-Cb	Smls. & wld. ftgs.	SA-403	347
45	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP347

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S30451	...	...	80
2	S30451	...	...	80
3	S30451	...	...	80
4	S30451	1	...	80
5	S30451	3	...	80
6	S30451	4	...	80
7	S30451	...	...	80
8	S30451	...	...	80
9	S30451	...	...	80
10	S30451	...	...	80
11	S30451	...	...	80
12	S30451	...	...	80
13	S30451	...	...	80
14	...	...	≤3	80
15	...	...	≤3	80
16	S30300	1	...	75
17	S30300	1A	...	75
18	S30323	1	...	75
19	S30323	1A	...	75
20	S21800	...	...	95
21	S30432	...	...	86
22	S34809	...	...	65
23	J92710	...	...	70
24	J92710	...	...	70
25	S34700	...	>5	70
26	S34700	...	...	70
27	S34709	...	>5	70
28	S34709	...	...	70
29	S34800	...	>5	70
30	S34800	...	...	70
31	S34809	...	>5	70
32	S34700	...	≤5	75
33	S34700	1	...	75
34	S34700	...	...	75
35	S34700	...	...	75
36	S34700	...	...	75
37	S34700	...	...	75
38	S34700	1	...	75
39	S34700	1A	...	75
40	S34700	1	...	75
41	S34700	3	...	75
42	S34700	4	...	75
43	S34700	...	...	75
44	S34700	...	...	75
45	S34700	...	...	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
2	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
3	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
4	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
5	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
6	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
7	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
8	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
9	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
10	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
11	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
12	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
13	80.0	80.0	76.1	73.2	71.2	69.7	69.1	68.6	67.9	67.3	66.5	65.5	64.4	63.0
14	79.8	75.3	70.9	68.1	67.1	67.1	67.1	67.1	67.1	66.9	65.9	64.6	62.9	61.2
15	79.8	79.2	76.2	73.1	70.8	69.4	68.9	68.4	67.8	67.1	66.3	65.3	64.1	62.9
16	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
17	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
18	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
19	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
20	95.0	93.9	87.0	82.1	79.3	77.9	77.5	77.1	76.7	76.2	75.5	74.7	73.6	72.5
21	86.0	85.8	82.1	80.2	79.5	79.1	79.0	78.7	78.3	77.7	76.8	75.7	74.3	71.9
22	65.0	62.2	57.1	53.9	52.0	51.2	51.0	51.0	51.0	51.0	50.9	50.7	50.4	49.8
23	70.0	66.9	61.5	58.0	56.0	55.1	55.0	54.9	54.9	54.9	54.8	54.6	54.2	53.6
24	70.0	67.0	61.5	58.0	56.0	55.1	54.9	54.9	54.9	54.9	54.8	54.6	54.3	53.7
25	70.0	66.9	61.5	58.0	56.0	55.1	55.0	54.9	54.9	54.9	54.8	54.6	54.2	53.6
26	70.0	66.9	61.5	58.0	56.0	55.1	55.0	54.9	54.9	54.9	54.8	54.6	54.2	53.6
27	70.0	67.0	61.5	58.0	56.0	55.1	54.9	54.9	54.9	54.9	54.8	54.6	54.3	53.7
28	70.0	67.0	61.5	58.0	56.0	55.1	54.9	54.9	54.9	54.9	54.8	54.6	54.3	53.7
29	70.0	66.9	61.5	58.0	56.0	55.1	55.0	54.9	54.9	54.9	54.8	54.6	54.2	53.6
30	70.0	66.9	61.5	58.0	56.0	55.1	55.0	54.9	54.9	54.9	54.8	54.6	54.2	53.6
31	70.0	67.0	61.5	58.0	56.0	55.1	54.9	54.9	54.9	54.9	54.8	54.6	54.3	53.7
32	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
33	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
34	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
35	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
36	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
37	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
38	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
39	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
40	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
41	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
42	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
43	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
44	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
45	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	52.2	49.7	46.8	43.7	40.3	36.8	33.2	29.7	26.2	22.8	...	...	...
26	52.2	49.7	46.8	43.7	40.3	36.8	33.2	29.7	26.2	22.8	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	52.2	49.7	46.8	43.7	40.3	36.8	33.2	29.7	26.2	22.8	...	...	...
30	52.2	49.7	46.8	43.7	40.3	36.8	33.2	29.7	26.2	22.8	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
33	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
34	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
35	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
36	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
37	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
38	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
39	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
40	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
41	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
42	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
43	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
44	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
45	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-10Ni-Cb	Bar	SA-479	347
2	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347
3	18Cr-10Ni-Cb	Bar	SA/JIS G4303	SUS347
4	18Cr-10Ni-Cb	Forgings	SA-182	F347H
5	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H
6	18Cr-10Ni-Cb	Plate	SA-240	347H
7	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H
8	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347H
9	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H
10	18Cr-10Ni-Cb	Smls. & wld. ftgs.	SA-403	347H
11	18Cr-10Ni-Cb	Bar	SA-479	347H
12	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347H
13	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP347H
14	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347LN
15	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347LN
16	18Cr-10Ni-Cb	Forgings	SA-182	F348
17	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348
18	18Cr-10Ni-Cb	Plate	SA-240	348
19	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348
20	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348
21	18Cr-10Ni-Cb	Wld. pipe	SA-358	348
22	18Cr-10Ni-Cb	Wld. pipe	SA-358	348
23	18Cr-10Ni-Cb	Wld. pipe	SA-358	348
24	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348
25	18Cr-10Ni-Cb	Smls. & wld. ftgs.	SA-403	348
26	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP348
27	18Cr-10Ni-Cb	Bar	SA-479	348
28	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348
29	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348
30	18Cr-10Ni-Cb	Forgings	SA-182	F348H
31	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H
32	18Cr-10Ni-Cb	Plate	SA-240	348H
33	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H
34	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348H
35	18Cr-10Ni-Cb	Smls. & wld. ftgs.	SA-403	348H
36	18Cr-10Ni-Cb	Bar	SA-479	348H
37	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348H
38	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348H
39	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347HFG
40	18Cr-10Ni-Cb	Bolting	SA-320	B8C
41	18Cr-10Ni-Cb	Bolting	SA-320	B8C
42	18Cr-10Ni-Cb	Bolting	SA-320	B8C
43	18Cr-10Ni-Cb	Bolting	SA-320	B8C
44	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321
45	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S34700	...	...	75
2	S34700	...	...	75
3	...	...	...	75
4	S34709	...	≤5	75
5	S34709	...	...	75
6	S34709	...	...	75
7	S34709	...	...	75
8	S34709	...	...	75
9	S34709	...	...	75
10	S34709	...	...	75
11	S34709	...	...	75
12	S34709	...	...	75
13	S34709	...	...	75
14	S34751	...	...	75
15	S34751	...	...	75
16	S34800	...	≤5	75
17	S34800	...	...	75
18	S34800	...	...	75
19	S34800	...	...	75
20	S34800	...	...	75
21	S34800	1	...	75
22	S34800	3	...	75
23	S34800	4	...	75
24	S34800	...	...	75
25	S34800	...	...	75
26	S34800	...	...	75
27	S34800	...	...	75
28	S34800	...	...	75
29	S34800	...	...	75
30	S34809	...	≤5	75
31	S34809	...	...	75
32	S34809	...	...	75
33	S34809	...	...	75
34	S34809	...	...	75
35	S34809	...	...	75
36	S34809	...	...	75
37	S34809	...	...	75
38	S34809	...	...	75
39	S34710	...	...	80
40	S34700	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100
41	S34700	2	$1 < t \leq 1\frac{1}{4}$	105
42	S34700	2	$\frac{3}{4} < t \leq 1$	115
43	S34700	2	$t \leq \frac{3}{4}$	125
44	S32100	...	$> \frac{3}{8}$	70
45	S32100	...	$> \frac{3}{8}$	70

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
2	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
3	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
4	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
5	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
6	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
7	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
8	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
9	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
10	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
11	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
12	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
13	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
14	75.0	73.1	66.9	62.3	59.3	57.7	57.4	57.2	57.1	57.0	56.9	56.6	56.2	55.4
15	75.0	73.1	66.9	62.3	59.3	57.7	57.4	57.2	57.1	57.0	56.9	56.6	56.2	55.4
16	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
17	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
18	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
19	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
20	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
21	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
22	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
23	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
24	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
25	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
26	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
27	75.0	71.7	65.9	62.1	60.0	59.1	58.9	58.8	58.8	58.8	58.7	58.5	58.1	57.5
28	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
29	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
30	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
31	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
32	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
33	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
34	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
35	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
36	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
37	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
38	75.0	71.8	65.9	62.1	60.0	59.0	58.9	58.8	58.8	58.8	58.7	58.5	58.2	57.5
39	80.0	77.7	72.8	69.6	67.7	66.7	66.4	66.2	66.0	65.8	65.4	64.9	64.3	63.3
40	100.0	...	...	...	...	...	...	...	...	...	...	...	...	...
41	105.0	...	...	...	...	...	...	...	...	...	...	...	...	...
42	115.0	...	...	...	...	...	...	...	...	...	...	...	...	...
43	125.0	...	...	...	...	...	...	...	...	...	...	...	...	...
44	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
45	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
2	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
17	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
18	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
19	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
20	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
21	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
22	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
23	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
24	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
25	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
26	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
27	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
28	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
29	55.9	53.2	50.1	46.8	43.2	39.4	35.6	31.8	28.1	24.5	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	57.6	55.6	53.1	50.4	47.4	44.2	40.8	37.3	33.8	30.2	...	...	...
45	57.6	55.6	53.1	50.4	47.4	44.2	40.8	37.3	33.8	30.2	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321H
2	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H
3	18Cr-10Ni-Ti	Forgings	SA-182	F321
4	18Cr-10Ni-Ti	Forgings	SA-965	F321
5	18Cr-10Ni-Ti	Forgings	SA-182	F321H
6	18Cr-10Ni-Ti	Forgings	SA-965	F321H
7	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi18-10
8	18Cr-10Ni-Ti	Forgings	SA-182	F321
9	18Cr-10Ni-Ti	Bolting	SA-193	B8T
10	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321
11	18Cr-10Ni-Ti	Plate	SA-240	321
12	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321
13	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321
14	18Cr-10Ni-Ti	Bolting	SA-320	B8T
15	18Cr-10Ni-Ti	Bolting	SA-320	B8TA
16	18Cr-10Ni-Ti	Wld. pipe	SA-358	321
17	18Cr-10Ni-Ti	Wld. pipe	SA-358	321
18	18Cr-10Ni-Ti	Wld. pipe	SA-358	321
19	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321
20	18Cr-10Ni-Ti	Smls. & wld. ftgs.	SA-403	321
21	18Cr-10Ni-Ti	Wld. pipe	SA-409	TP321
22	18Cr-10Ni-Ti	Bar	SA-479	321
23	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321
24	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321
25	18Cr-10Ni-Ti	Bar	SA/JIS G4303	SUS321
26	18Cr-10Ni-Ti	Forgings	SA-182	F321H
27	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H
28	18Cr-10Ni-Ti	Plate	SA-240	321H
29	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H
30	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321H
31	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H
32	18Cr-10Ni-Ti	Smls. & wld. ftgs.	SA-403	321H
33	18Cr-10Ni-Ti	Bar	SA-479	321H
34	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321H
35	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321H
36	18Cr-10Ni-Ti	Bolting	SA-320	B8T
37	18Cr-10Ni-Ti	Bolting	SA-320	B8T
38	18Cr-10Ni-Ti	Bolting	SA-320	B8T
39	18Cr-10Ni-Ti	Bolting	SA-320	B8T
40	18Cr-11Ni	Plate	SA-240	305
41	18Cr-12Ni-2Mo	Castings	SA-351	CF3M
42	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF3M
43	18Cr-12Ni-2Mo	Castings	SA-351	CF8M
44	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF8M
45	18Cr-13Ni-3Mo	Forgings	SA-182	F317L

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S32109	...	$> \frac{3}{16}$	70
2	S32109	...	$> \frac{3}{8}$	70
3	S32100	...	> 5	70
4	S32100	...	...	70
5	S32109	...	> 5	70
6	S32109	...	...	70
7	...	...	≤ 3	73
8	S32100	...	≤ 5	75
9	S32100	1	...	75
10	S32100	...	...	75
11	S32100	...	...	75
12	S32100	...	...	75
13	S32100	...	$\leq \frac{3}{8}$	75
14	S32100	1	...	75
15	S32100	1A	...	75
16	S32100	1	...	75
17	S32100	3	...	75
18	S32100	4	...	75
19	S32100	...	$\leq \frac{3}{8}$	75
20	S32100	...	...	75
21	S32100	...	...	75
22	S32100	...	...	75
23	S32100	...	...	75
24	S32100	...	...	75
25	...	...	...	75
26	S32109	...	≤ 5	75
27	S32109	...	...	75
28	S32109	...	...	75
29	S32109	...	...	75
30	S32109	...	$\leq \frac{3}{16}$	75
31	S32109	...	$\leq \frac{3}{8}$	75
32	S32109	...	...	75
33	S32109	...	...	75
34	S32109	...	...	75
35	S32109	...	...	75
36	S32100	2	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100
37	S32100	2	$1 < t \leq 1\frac{1}{4}$	105
38	S32100	2	$\frac{3}{4} < t \leq 1$	115
39	S32100	2	$t \leq \frac{3}{4}$	125
40	S30500	...	...	75
41	J92800	...	...	70
42	J92800	...	...	70
43	J92900	...	...	70
44	J92900	...	...	70
45	S31703	...	> 5	65

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
2	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
3	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
4	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
5	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
6	70.0	66.4	62.4	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	61.1	59.6
7	72.5	68.5	65.4	63.5	62.8	62.8	62.8	62.8	62.8	62.8	62.8	62.8	62.6	62.1
8	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
9	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
10	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
11	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
12	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
13	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
14	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
15	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
16	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
17	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
18	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
19	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
20	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
21	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
22	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
23	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
24	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
25	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
26	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
27	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
28	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
29	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
30	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
31	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
32	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
33	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
34	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
35	75.0	71.1	66.9	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	65.5	63.8
36	50.0	...	...	...	...	...	...	...	...	...	...	...	...	...
37	65.0	...	...	...	...	...	...	...	...	...	...	...	...	...
38	80.0	...	...	...	...	...	...	...	...	...	...	...	...	...
39	100.0	...	...	...	...	...	...	...	...	...	...	...	...	...
40	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
41	70.0	70.0	68.0	67.2	67.2	67.2	67.2	67.2	66.8	66.2	65.2	63.9	62.3	60.2
42	70.0	70.0	68.0	67.2	67.2	67.2	67.2	67.2	66.8	66.2	65.2	63.9	62.3	60.2
43	70.0	70.0	68.0	67.2	67.2	67.2	67.2	67.2	66.8	66.2	65.2	63.9	62.3	60.2
44	70.0	70.0	68.0	67.2	67.2	67.2	67.2	67.2	66.8	66.2	65.2	63.9	62.3	60.2
45	65.0	63.2	59.5	57.8	57.3	57.3	57.2	57.1	56.7	56.2	55.4	54.4	53.0	51.4

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	57.6	55.6	53.1	50.4	47.4	44.2	40.8	37.3	33.8	30.2	...	...	...
4	57.6	55.6	53.1	50.4	47.4	44.2	40.8	37.3	33.8	30.2	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
9	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
10	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
11	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
12	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
13	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
14	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
15	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
16	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
17	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
18	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
19	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
20	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
21	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
22	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
23	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
24	61.8	59.5	56.9	54.0	50.8	47.4	43.7	40.0	36.2	32.4	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	50.1	48.6	46.7	44.6	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	18Cr-13Ni-3Mo	Forgings	SA-182	F317L
2	18Cr-13Ni-3Mo	Forgings	SA-182	F317
3	18Cr-13Ni-3Mo	Plate	SA-240	317
4	18Cr-13Ni-3Mo	Plate	SA-240	317L
5	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317
6	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317L
7	18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317
8	18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317L
9	18Cr-13Ni-3Mo	Smls. & wld. ftgs.	SA-403	317
10	18Cr-13Ni-3Mo	Fittings	SA-403	317L
11	18Cr-15Ni-4Si	Forgings	SA-182	...
12	18Cr-15Ni-4Si	Plate	SA-240	...
13	18Cr-15Ni-4Si	Smls. & wld. pipe	SA-312	...
14	18Cr-15Ni-4Si	Bar	SA-479	...
15	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15
16	18Cr-18Ni-2Si	Plate	SA-240	XM-15
17	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15
18	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15
19	18Cr-20Ni-5.5Si	Smls. tube	SA-213	...
20	18Cr-20Ni-5.5Si	Plate	SA-240	...
21	18Cr-20Ni-5.5Si	Smls. & wld. pipe	SA-312	...
22	18Cr-20Ni-5.5Si	Bar	SA-479	...
23	19Cr-9Ni- $\frac{1}{2}$ Mo	Castings	SA-351	CF10
24	19Cr-9Ni-Mo-W	Bolting	SA-453	651
25	19Cr-9Ni-Mo-W	Bolting	SA-453	651
26	19Cr-9Ni-2Mo	Castings	SA-351	CF10M
27	19Cr-10Ni-3Mo	Castings	SA-351	CG8M
28	19Cr-15Ni-4Mo	Smls. tube	SA-213	...
29	19Cr-15Ni-4Mo	Plate	SA-240	...
30	19Cr-15Ni-4Mo	Wld. tube	SA-249	...
31	19Cr-15Ni-4Mo	Smls. & wld. pipe	SA-312	...
32	19Cr-15Ni-4Mo	Wld. pipe	SA-358	...
33	19Cr-15Ni-4Mo	Smls. pipe	SA-376	...
34	19Cr-15Ni-4Mo	Wld. pipe	SA-409	...
35	19Cr-15Ni-4Mo	Bar	SA-479	...
36	20Cr-3Ni-1.5Mo-N	Plate	SA-240	...
37	20Cr-3Ni-1.5Mo-N	Wld. pipe	SA-790	...
38	20Cr-3Ni-1.5Mo-N	Sheet	SA-240	...
39	20Cr-3Ni-1.5Mo-N	Smls. & wld. tube	SA-789	...
40	20Cr-10Ni	Bar	SA-479	ER308
41	20Cr-18Ni-6Mo	Castings	SA-351	CK3MCuN
42	20Cr-18Ni-6Mo	Forgings	SA-182	F44
43	20Cr-18Ni-6Mo	Smls. tube	SA-213	...
44	20Cr-18Ni-6Mo	Wld. tube	SA-249	...
45	20Cr-18Ni-6Mo	Smls. & wld. pipe	SA-312	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S31703	...	≤5	70
2	S31700	...	≤5	75
3	S31700	...	...	75
4	S31703	...	...	75
5	S31700	...	...	75
6	S31703	...	...	75
7	S31700	...	...	75
8	S31703	...	...	75
9	S31700	...	...	75
10	S31703	...	...	75
11	S30600	Solution ann.	...	78
12	S30600	Solution ann.	≤2	78
13	S30600	Solution ann.	...	78
14	S30600	Solution ann.	≤4	78
15	S38100	...	...	75
16	S38100	...	...	75
17	S38100	...	...	75
18	S38100	...	...	75
19	S32615	Solution ann.	...	80
20	S32615	Solution ann.	...	80
21	S32615	Solution ann.	...	80
22	S32615	Solution ann.	...	80
23	J92590	...	...	70
24	S63198	B	...	95
25	S63198	A	...	100
26	...	...	...	70
27	J93000	...	...	75
28	S31725	...	...	75
29	S31725	...	...	75
30	S31725	...	...	75
31	S31725	...	...	75
32	S31725	...	...	75
33	S31725	...	...	75
34	S31725	...	...	75
35	S31725	...	...	75
36	S32003	...	$>^{3/16}$	95
37	S32003	...	...	95
38	S32003	...	$≤^{3/16}$	100
39	S32003	...	...	100
40	S30880	...	...	75
41	J93254	...	...	80
42	S31254	...	...	94
43	S31254	...	$t > 0.187$	95
44	S31254	...	$t > 0.187$	95
45	S31254	...	$t > 0.187$	95

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	70.0	68.1	64.0	62.2	61.8	61.7	61.6	61.5	61.1	60.5	59.7	58.6	57.1	55.4
2	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
3	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
4	75.0	72.9	68.6	66.7	66.2	66.1	66.1	65.9	65.5	64.9	64.0	62.7	61.2	59.3
5	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
6	75.0	72.9	68.6	66.7	66.2	66.1	66.1	65.9	65.5	64.9	64.0	62.7	61.2	59.3
7	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
8	75.0	72.9	68.6	66.7	66.2	66.1	66.1	65.9	65.5	64.9	64.0	62.7	61.2	59.3
9	75.0	75.0	72.9	71.9	71.8	71.8	71.8	71.8	71.5	70.8	69.7	68.3	66.5	64.3
10	75.0	72.9	68.6	66.7	66.2	66.1	66.1	65.9	65.5	64.9	64.0	62.7	61.2	59.3
11	78.0	74.6	68.6	...	...	...	...	...	...	...	...	...	...	...
12	78.0	74.6	68.6	...	...	...	...	...	...	...	...	...	...	...
13	78.0	74.6	68.6	...	...	...	...	...	...	...	...	...	...	...
14	78.0	74.6	68.6	...	...	...	...	...	...	...	...	...	...	...
15	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
16	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
17	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
18	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
19	80.0	79.6	76.0	73.6	...	...	...	...	...	...	...	...	...	...
20	80.0	79.6	76.0	73.6	...	...	...	...	...	...	...	...	...	...
21	80.0	79.6	76.0	73.6	...	...	...	...	...	...	...	...	...	...
22	80.0	79.6	76.0	73.6	...	...	...	...	...	...	...	...	...	...
23	70.0	66.4	62.1	60.1	59.4	59.3	59.2	59.1	58.8	58.4	57.7	56.8	55.6	54.0
24	95.0	93.7	88.4	85.1	83.2	82.2	81.8	81.3	80.7	79.9	78.8	77.3	75.4	73.0
25	100.0	98.6	93.0	89.6	87.6	86.5	86.1	85.6	84.9	84.1	82.9	81.4	79.4	76.8
26	70.0	69.9	68.2	67.7	67.4	66.6	66.0	65.3	64.5	63.7	62.8	61.9	61.0	60.0
27	75.0	72.8	68.8	66.8	66.1	66.0	66.0	66.0	65.9	65.5	65.0	64.0	62.7	60.8
28	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
29	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
30	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
31	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
32	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
33	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
34	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
35	75.0	72.7	68.5	66.6	66.1	66.1	66.1	65.9	65.6	64.9	64.0	62.8	61.2	59.2
36	95.0	92.1	86.6	85.8	85.8	85.8	85.8	85.8	85.8	85.8	85.8	...	...	...
37	95.0	92.1	86.6	85.8	85.8	85.8	85.8	85.8	85.8	85.8	85.8	...	...	...
38	100.0	97.0	91.2	90.3	90.3	90.3	90.3	90.3	90.3	90.3	90.3	...	...	...
39	100.0	97.0	91.2	90.3	90.3	90.3	90.3	90.3	90.3	90.3	90.3	...	...	...
40	75.0	71.0	66.2	64.0	63.4	63.4	63.4	63.4	63.3	62.8	62.0	60.8	59.3	57.4
41	80.0	80.0	76.0	72.5	70.0	68.4	68.0	67.7	67.4	67.0	66.4	...	...	...
42	94.0	94.0	89.4	85.2	82.2	80.4	79.9	79.5	79.2	78.7	78.0	...	...	...
43	95.0	95.0	90.4	86.1	83.1	81.3	80.8	80.3	80.0	79.5	78.8	...	...	...
44	95.0	95.0	90.4	86.1	83.1	81.3	80.8	80.3	80.0	79.5	78.8	...	...	...
45	95.0	95.0	90.4	86.1	83.1	81.3	80.8	80.3	80.0	79.5	78.8	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	54.0	52.3	50.3	48.0	...	...	...	...	...	...	...	...	...
2	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
3	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
4	57.8	56.1	53.9	51.4	...	...	...	...	...	...	...	...	...
5	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
6	57.8	56.1	53.9	51.4	...	...	...	...	...	...	...	...	...
7	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
8	57.8	56.1	53.9	51.4	...	...	...	...	...	...	...	...	...
9	60.3	55.9	51.7	47.7	43.8	40.0	36.5	33.1	29.8	26.7	...	...	...
10	57.8	56.1	53.9	51.4	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...
2	20Cr-18Ni-6Mo	Smls. tube	SA-213	...
3	20Cr-18Ni-6Mo	Wld. tube	SA-249	...
4	20Cr-18Ni-6Mo	Smls. & wld. pipe	SA-312	...
5	20Cr-18Ni-6Mo	Plate	SA-240	...
6	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...
7	20.5Cr-8.8Ni-Mo-N	Plate	SA-240	...
8	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...
9	21Cr-5Mn-1.5Ni-Cu-N	Bar	SA-479	...
10	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. tube	SA-789	...
11	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. pipe	SA-790	...
12	21Cr-5Mn-1.5Ni-Cu-N	Fittings	SA-815	...
13	21Cr-5Mn-1.5Ni-Cu-N	Sheet, strip	SA-240	...
14	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. tube	SA-789	...
15	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. pipe	SA-790	...
16	21Cr-6Ni-9Mn	Forgings	SA-182	FXM-11
17	21Cr-6Ni-9Mn	Smls. & wld. pipe	SA-312	TPXM-11
18	21Cr-6Ni-9Mn	Plate	SA-666	XM-11
19	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11
20	21Cr-11Ni-N	Forgings	SA-182	F45
21	21Cr-11Ni-N	Smls. tube	SA-213	...
22	21Cr-11Ni-N	Plate	SA-240	...
23	21Cr-11Ni-N	Wld. tube	SA-249	...
24	21Cr-11Ni-N	Smls. & wld. pipe	SA-312	...
25	21Cr-11Ni-N	Bar	SA-479	...
26	22Cr-2Ni-Mo-N	Forgings	SA-182	F66
27	22Cr-2Ni-Mo-N	Plate	SA-240	...
28	22Cr-2Ni-Mo-N	Bar	SA-479	...
29	22Cr-2Ni-Mo-N	Smls. & wld. tube	SA-789	...
30	22Cr-2Ni-Mo-N	Smls. & wld. pipe	SA-790	...
31	22Cr-2Ni-Mo-N	Smls. & wld. ftgs.	SA-815	...
32	22Cr-5Ni-3Mo-N	Castings	SA-995	4A
33	22Cr-5Ni-3Mo-N	Forgings	SA-182	F51
34	22Cr-5Ni-3Mo-N	Plate	SA-240	...
35	22Cr-5Ni-3Mo-N	Bar	SA-479	...
36	22Cr-5Ni-3Mo-N	Smls. & wld. tube	SA-789	...
37	22Cr-5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...
38	22Cr-5Ni-3Mo-N	Smls. & wld. ftgs.	SA-815	...
39	22Cr-5Ni-3Mo-N	Forgings	SA-182	F60
40	22Cr-5Ni-3Mo-N	Plate	SA-240	...
41	22Cr-5Ni-3Mo-N	Bar	SA-479	...
42	22Cr-5Ni-3Mo-N	Smls. & wld. tube	SA-789	...
43	22Cr-5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...
44	22Cr-5Ni-3Mo-N	Smls. & wld. ftgs.	SA-815	...
45	22Cr-13Ni-5Mn	Castings	SA-351	CG6MMN

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S31254	...	$t \geq 0.187$	95
2	S31254	...	$t \leq 0.187$	98
3	S31254	...	$t \leq 0.187$	98
4	S31254	...	$t \leq 0.187$	98
5	S31254	...	$t \leq 0.187$	100
6	S31254	...	$t < 0.187$	100
7	S31655	...	...	92
8	S32101	...	$> \frac{3}{16}$	94
9	S32101	...	...	94
10	S32101	...	> 0.187	94
11	S32101	...	> 0.187	94
12	S32101	...	...	94
13	S32101	...	$\leq \frac{3}{16}$	101
14	S32101	...	≤ 0.187	101
15	S32101	...	≤ 0.187	101
16	S21904	...	...	90
17	S21904	...	...	90
18	S21904	...	...	90
19	S21904	...	...	90
20	S30815	...	...	87
21	S30815	...	...	87
22	S30815	...	...	87
23	S30815	...	...	87
24	S30815	...	...	87
25	S30815	...	...	87
26	S32202	...	...	94
27	S32202	...	...	94
28	S32202	...	...	94
29	S32202	...	...	94
30	S32202	...	...	94
31	S32202	...	...	94
32	J92205	...	...	90
33	S31803	...	...	90
34	S31803	...	...	90
35	S31803	...	...	90
36	S31803	...	...	90
37	S31803	...	...	90
38	S31803	...	...	90
39	S32205	...	...	95
40	S32205	...	...	95
41	S32205	...	...	95
42	S32205	...	...	95
43	S32205	...	...	95
44	S32205	...	...	95
45	J93790	...	...	85

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	95.0	95.0	90.4	86.1	83.1	81.3	80.8	80.3	80.0	79.5	78.8	...	...	...
2	98.0	98.0	93.2	88.8	85.7	83.8	83.3	82.9	82.6	82.0	81.3	...	...	...
3	98.0	98.0	93.2	88.8	85.7	83.8	83.3	82.9	82.6	82.0	81.3	...	...	...
4	98.0	98.0	93.2	88.8	85.7	83.8	83.3	82.9	82.6	82.0	81.3	...	...	...
5	100.0	100.0	95.1	90.6	87.5	85.6	85.0	84.6	84.2	83.3	83.0	...	...	...
6	100.0	100.0	95.1	90.6	87.5	85.6	85.0	84.6	84.2	83.3	83.0	...	...	...
7	92.1	90.8	85.1	81.3	78.5	77.3	76.6	76.1	75.4	74.6	73.6	...	...	...
8	94.0	94.0	89.5	86.5	86.3	86.3	86.3	...	...	...	...	...	...	...
9	94.0	94.0	89.5	86.5	86.3	86.3	86.3	...	...	...	...	...	...	...
10	94.0	94.0	89.5	86.5	86.3	86.3	86.3	...	...	...	...	...	...	...
11	94.0	94.0	89.5	86.5	86.3	86.3	86.3	...	...	...	...	...	...	...
12	94.0	94.0	89.5	86.5	86.3	86.3	86.3	...	...	...	...	...	...	...
13	101.0	101.0	96.2	92.9	92.7	92.7	92.7	...	...	...	...	...	...	...
14	101.0	101.0	96.2	92.9	92.7	92.7	92.7	...	...	...	...	...	...	...
15	101.0	101.0	96.2	92.9	92.7	92.7	92.7	...	...	...	...	...	...	...
16	90.0	90.0	84.1	79.7	76.9	75.3	74.6	74.0	73.2	72.3	71.1	69.6	67.8	65.7
17	90.0	90.0	84.1	79.7	76.9	75.3	74.6	74.0	73.2	72.3	71.1	69.6	67.8	65.7
18	90.0	90.0	84.1	79.7	76.9	75.3	74.6	74.0	73.2	72.3	71.1	69.6	67.8	65.7
19	90.0	90.0	84.1	79.7	76.9	75.3	74.6	74.0	73.2	72.3	71.1	69.6	67.8	65.7
20	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
21	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
22	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
23	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
24	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
25	87.0	86.4	81.6	78.5	76.4	74.8	74.1	73.5	72.8	72.0	71.1	70.1	68.9	67.5
26	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
27	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
28	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
29	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
30	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
31	94.0	93.2	87.0	86.3	86.3	86.3	...	...	...	...	...	...	...	...
32	90.0	90.0	86.2	85.2	85.2	...	...	...	...	...	...	...	...	...
33	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
34	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
35	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
36	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
37	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
38	90.0	90.0	86.8	83.5	81.6	80.7	80.5	...	...	...	...	...	...	...
39	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
40	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
41	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
42	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
43	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
44	95.0	95.0	91.7	88.2	86.1	85.2	85.0	...	...	...	...	...	...	...
45	85.0	84.6	80.1	77.3	75.6	74.5	74.0	73.5	72.9	72.1	71.2	70.1	68.7	67.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	22Cr-13Ni-5Mn	Forgings	SA-182	FXM-19
2	22Cr-13Ni-5Mn	Bolting	SA-193	B8R
3	22Cr-13Ni-5Mn	Bolting	SA-193	B8RA
4	22Cr-13Ni-5Mn	Smls. tube	SA-213	XM-19
5	22Cr-13Ni-5Mn	Plate	SA-240	XM-19
6	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19
7	22Cr-13Ni-5Mn	Smls. & wld. pipe	SA-312	TPXM-19
8	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19
9	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19
10	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19
11	22Cr-13Ni-5Mn	Smls. & wld. ftgs.	SA-403	XM-19
12	22Cr-13Ni-5Mn	Bar	SA-479	XM-19
13	22Cr-13Ni-5Mn	Bar	SA-479	XM-19
14	22Cr-13Ni-5Mn	Wld. pipe	SA-813	TPXM-19
15	22Cr-13Ni-5Mn	Wld. pipe	SA-814	TPXM-19
16	22Cr-13Ni-5Mn	Forgings	SA-965	FXM-19
17	22Cr-13Ni-5Mn	Bar	SA-479	XM-19
18	22Cr-13Ni-5Mn	Bar	SA-479	XM-19
19	23Cr-4Ni-Mo-Cu-N	Plate	SA-240	...
20	23Cr-4Ni-Mo-Cu-N	Smls. & wld. tube	SA-789	...
21	23Cr-4Ni-Mo-Cu-N	Smls. & wld. pipe	SA-790	...
22	23Cr-4Ni-Mo-Cu-N	Smls. & wld. tube	SA-789	...
23	23Cr-12Ni	Smls. & wld. ftgs.	SA-403	309
24	23Cr-12Ni	Smls. tube	SA-213	TP309S
25	23Cr-12Ni	Plate	SA-240	309S
26	23Cr-12Ni	Wld. tube	SA-249	TP309S
27	23Cr-12Ni	Smls. & wld. pipe	SA-312	TP309S
28	23Cr-12Ni	Wld. pipe	SA-358	309S
29	23Cr-12Ni	Wld. pipe	SA-358	309S
30	23Cr-12Ni	Wld. pipe	SA-358	309S
31	23Cr-12Ni	Bar	SA-479	309S
32	23Cr-12Ni	Wld. pipe	SA-813	TP309S
33	23Cr-12Ni	Wld. pipe	SA-814	TP309S
34	23Cr-12Ni	Bar	SA/JIS G4303	SUS309S
35	23Cr-12Ni	Smls. tube	SA-213	TP309H
36	23Cr-12Ni	Plate	SA-240	309H
37	23Cr-12Ni	Wld. tube	SA-249	TP309H
38	23Cr-12Ni	Smls. & wld. pipe	SA-312	TP309H
39	23Cr-12Ni	Bar	SA-479	309H
40	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb
41	23Cr-12Ni-Cb	Plate	SA-240	309Cb
42	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb
43	23Cr-12Ni-Cb	Smls. & wld. pipe	SA-312	TP309Cb
44	23Cr-12Ni-Cb	Bar	SA-479	309Cb
45	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S20910	...	...	100
2	S20910	Annealed	...	100
3	S20910	Annealed	...	100
4	S20910	...	...	100
5	S20910	...	...	100
6	S20910	...	...	100
7	S20910	...	...	100
8	S20910	1	...	100
9	S20910	3	...	100
10	S20910	4	...	100
11	S20910	...	...	100
12	S20910	Annealed	...	100
13	S20910	Hot rolled	$3 < t \leq 8$	100
14	S20910	...	...	100
15	S20910	...	...	100
16	S20910	...	...	100
17	S20910	Hot rolled	$2 < t \leq 3$	115
18	S20910	Hot rolled	≤ 2	135
19	S32304	...	...	87
20	S32304	...	> 1	87
21	S32304	...	...	87
22	S32304	...	≤ 1	100
23	S30900	...	...	75
24	S30908	...	...	75
25	S30908	...	...	75
26	S30908	...	...	75
27	S30908	...	...	75
28	S30908	1	...	75
29	S30908	3	...	75
30	S30908	4	...	75
31	S30908	...	...	75
32	S30908	...	...	75
33	S30908	...	...	75
34	...	...	...	75
35	S30909	...	...	75
36	S30909	...	...	75
37	S30909	...	...	75
38	S30909	...	...	75
39	S30909	...	...	75
40	S30940	...	...	75
41	S30940	...	...	75
42	S30940	...	...	75
43	S30940	...	...	75
44	S30940	...	...	75
45	S30940	...	...	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
2	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
3	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
4	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
5	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
6	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
7	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
8	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
9	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
10	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
11	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
12	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
13	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
14	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
15	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
16	100.0	99.4	94.2	91.1	89.1	87.7	87.0	86.4	85.6	84.8	83.8	82.6	81.3	79.7
17	115.0	114.3	108.4	104.7	102.5	100.8	100.1	99.3	98.4	97.5	96.3	95.0	93.5	91.7
18	135.0	134.1	127.2	123.0	120.3	118.4	117.5	116.6	115.6	114.4	113.1	111.5	109.7	107.6
19	87.0	83.9	78.7	76.0	74.6	73.5	72.9	72.1	71.2	70.3	...	...	...	...
20	87.0	83.9	78.7	76.0	74.6	73.5	72.9	72.1	71.2	70.3	...	...	...	...
21	87.0	83.9	78.7	76.0	74.6	73.5	72.9	72.1	71.2	70.3	...	...	...	...
22	100.0	96.5	90.6	87.6	86.1	84.9	84.2	83.4	...	...	...	...	...	...
23	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
24	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
25	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
26	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
27	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
28	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
29	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
30	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
31	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
32	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
33	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
34	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
35	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
36	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
37	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
38	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
39	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
40	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
41	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
42	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
43	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
44	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
45	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
2	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
3	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
4	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
5	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
6	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
7	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
8	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
9	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
10	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
11	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
12	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
13	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
14	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
15	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
16	77.3	75.6	73.5	71.0	...	...	...	...	...	...	...	...	...
17	88.9	86.9	84.5	81.7	...	...	...	...	...	...	...	...	...
18	104.4	102.0	99.2	95.9	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
25	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
26	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
27	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
28	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
29	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
30	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
31	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
32	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
33	55.2	52.2	49.1	45.7	42.3	38.8	35.2	31.6	28.0	24.5	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb
2	23Cr-25Ni-5.5Mo-N	Forgings	SA-182	...
3	23Cr-25Ni-5.5Mo-N	Bolting	SA-193	...
4	23Cr-25Ni-5.5Mo-N	Plate	SA-240	...
5	23Cr-25Ni-5.5Mo-N	Wld. tube	SA-249	...
6	23Cr-25Ni-5.5Mo-N	Smls. & wld. pipe	SA-312	...
7	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-358	...
8	23Cr-25Ni-5.5Mo-N	Fittings	SA-403	...
9	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-409	...
10	23Cr-25Ni-5.5Mo-N	Bar	SA-479	...
11	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-813	...
12	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-814	...
13	24Cr-10Ni-4Mo-N	Castings	SA-995	2A
14	24Cr-22Ni-6Mo-2W-Cu-N	Forgings	SA-182	F58
15	24Cr-22Ni-6Mo-2W-Cu-N	Smls. tube	SA-213	...
16	24Cr-22Ni-6Mo-2W-Cu-N	Plate	SA-240	...
17	24Cr-22Ni-6Mo-2W-Cu-N	Wld. tube	SA-249	...
18	24Cr-22Ni-6Mo-2W-Cu-N	Smls. & wld. pipe	SA-312	...
19	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-358	...
20	24Cr-22Ni-6Mo-2W-Cu-N	Smls. & wld. fittings	SA-403	...
21	24Cr-22Ni-6Mo-2W-Cu-N	Bar, shapes	SA-479	...
22	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-813	...
23	25Cr-4Ni-4Mo-Ti	Plate	SA-240	...
24	25Cr-4Ni-4Mo-Ti	Wld. tube	SA-268	...
25	25Cr-5Ni-3Mo-2Cu	Castings	SA-995	1B
26	25Cr-5Ni-3Mo-2Cu	Plate	SA-240	...
27	25Cr-5Ni-3Mo-2Cu	Bar	SA-479	...
28	25Cr-5Ni-3Mo-2Cu	Smls. & wld. tube	SA-789	...
29	25Cr-5Ni-3Mo-2Cu	Smls. & wld. pipe	SA-790	...
30	25Cr-6Ni-Mo-N	Forgings	SA-182	...
31	25Cr-6Ni-Mo-N	Plate, sheet	SA-240	...
32	25Cr-6Ni-Mo-N	Bar	SA-479	...
33	25Cr-6Ni-Mo-N	Smls. tube	SA-789	...
34	25Cr-6Ni-Mo-N	Wld. tube	SA-789	...
35	25Cr-6Ni-Mo-N	Smls. pipe	SA-790	...
36	25Cr-6Ni-Mo-N	Wld. pipe	SA-790	...
37	25Cr-6Ni-Mo-N	Plate	SA-240	...
38	25Cr-6.5Ni-3Mo-N	Smls. & wld. tube	SA-789	...
39	25Cr-6.5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...
40	25Cr-6.5Ni-3Mo-N	Plate	SA-240	...
41	25Cr-7Ni-3Mo-W-Cu-N	Forgings	SA-182	F54
42	25Cr-7Ni-3Mo-W-Cu-N	Smls. & wld. tube	SA-789	...
43	25Cr-7Ni-3Mo-W-Cu-N	Smls. & wld. pipe	SA-790	...
44	25Cr-7Ni-4Mo-N	Forgings	SA-182	F53
45	25Cr-7Ni-4Mo-N	Plate	SA-240	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S30940	...	...	75
2	S32053	...	...	93
3	S32053	...	...	93
4	S32053	...	...	93
5	S32053	...	...	93
6	S32053	...	...	93
7	S32053	...	...	93
8	S32053	...	...	93
9	S32053	...	...	93
10	S32053	...	...	93
11	S32053	...	...	93
12	S32053	...	...	93
13	J93345	...	...	95
14	S31266	...	...	109
15	S31266	...	...	109
16	S31266	...	...	109
17	S31266	...	...	109
18	S31266	...	...	109
19	S31266	...	...	109
20	S31266	...	...	109
21	S31266	...	...	109
22	S31266	...	...	109
23	S44635	...	...	90
24	S44635	...	...	90
25	J93372	...	...	100
26	S32550	...	...	110
27	S32550	...	...	110
28	S32550	...	...	110
29	S32550	...	...	110
30	S32506	...	...	90
31	S32506	...	...	90
32	S32506	...	...	90
33	S32506	...	...	90
34	S32506	...	...	90
35	S32506	...	...	90
36	S32506	...	...	90
37	S31200	...	...	100
38	S31260	...	...	100
39	S31260	...	...	100
40	S31260	...	...	100
41	S39274	...	...	116
42	S39274	...	...	116
43	S39274	...	...	116
44	S32750	...	...	116
45	S32750	...	...	116

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	75.0	75.0	74.7	73.0	71.6	70.2	69.3	68.3	67.2	65.8	64.2	62.5	60.4	58.2
2	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
3	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
4	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
5	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
6	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
7	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
8	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
9	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
10	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
11	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
12	93.0	93.0	87.8	83.7	80.5	78.1	77.2	76.5	...	...	...	...	...	...
13	95.0	94.9	87.8	84.6	84.6	84.6	84.6	81.3	...	...	...	...	...	...
14	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
15	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
16	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
17	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
18	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
19	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
20	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
21	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
22	109.0	107.7	101.3	96.9	94.0	92.1	91.3	90.6	89.8	88.9	...	...	...	...
23	90.0	87.1	82.1	78.8	77.0	76.3	75.7	...	...	...	...	...	...	...
24	90.0	87.1	82.1	78.8	77.0	76.3	75.7	...	...	...	...	...	...	...
25	100.0	...	...	...	...	...	...	...	...	...	...	...	...	...
26	110.0	109.6	103.4	100.1	98.7	...	...	...	...	...	...	...	...	...
27	110.0	109.6	103.4	100.1	98.7	...	...	...	...	...	...	...	...	...
28	110.0	109.6	103.4	100.1	98.7	...	...	...	...	...	...	...	...	...
29	110.0	109.6	103.4	100.1	98.7	...	...	...	...	...	...	...	...	...
30	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
31	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
32	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
33	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
34	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
35	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
36	90.0	89.8	85.3	84.4	84.4	84.4	...	...	...	...	...	...	...	...
37	100.0	100.0	94.8	92.0	91.5	91.5	...	...	...	...	...	...	...	...
38	100.0	99.9	94.9	92.5	92.2	92.2	92.2	...	...	...	...	...	...	...
39	100.0	99.9	94.9	92.5	92.2	92.2	92.2	...	...	...	...	...	...	...
40	100.0	99.9	94.9	92.5	92.2	92.2	92.2	...	...	...	...	...	...	...
41	116.0	116.0	110.5	109.9	109.9	109.9	109.9	109.9	109.9	...	...	...	...	...
42	116.0	116.0	110.5	109.9	109.9	109.9	109.9	109.9	109.9	...	...	...	...	...
43	116.0	116.0	110.5	109.9	109.9	109.9	109.9	109.9	109.9	...	...	...	...	...
44	116.0	115.5	109.1	105.4	103.6	103.0	...	...	...	...	...	...	...	...
45	116.0	115.5	109.1	105.4	103.6	103.0	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	25Cr-7Ni-4Mo-N	Smls. & wld. tube	SA-789	...
2	25Cr-7Ni-4Mo-N	Smls. & wld. pipe	SA-790	...
3	25Cr-7.5Ni-3.5Mo-N-Cu-W	Castings	SA-995	CD3MWCuN
4	25Cr-7.5Ni-3.5Mo-N-Cu-W	Forgings	SA-182	F55
5	25Cr-7.5Ni-3.5Mo-N-Cu-W	Plate	SA-240	...
6	25Cr-7.5Ni-3.5Mo-N-Cu-W	Bar	SA-479	...
7	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. tube	SA-789	...
8	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. pipe	SA-790	...
9	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. ftgs.	SA-815	...
10	25Cr-12Ni	Castings	SA-351	CH8
11	25Cr-12Ni	Cast pipe	SA-451	CPH8
12	25Cr-12Ni	Castings	SA-351	CH20
13	25Cr-12Ni	Cast pipe	SA-451	CPH20
14	25Cr-20Ni	Castings	SA-351	CK20
15	25Cr-20Ni	Cast pipe	SA-451	CPK20
16	25Cr-20Ni	Forgings	SA-182	F310
17	25Cr-20Ni	Forgings	SA-965	F310
18	25Cr-20Ni	Smls. tube	SA-213	...
19	25Cr-20Ni	Smls. pipe	SA-312	...
20	25Cr-20Ni	Smls. tube	SA-213	TP310S
21	25Cr-20Ni	Plate	SA-240	310S
22	25Cr-20Ni	Wld. tube	SA-249	TP310S
23	25Cr-20Ni	Smls. & wld. pipe	SA-312	TP310S
24	25Cr-20Ni	Wld. pipe	SA-358	310S
25	25Cr-20Ni	Wld. pipe	SA-358	310S
26	25Cr-20Ni	Wld. pipe	SA-358	310S
27	25Cr-20Ni	Smls. & wld. ftgs.	SA-403	310S
28	25Cr-20Ni	Bar	SA-479	310S
29	25Cr-20Ni	Wld. pipe	SA-813	TP310S
30	25Cr-20Ni	Wld. pipe	SA-814	TP310S
31	25Cr-20Ni	Bar	SA/JIS G4303	SUS310S
32	25Cr-20Ni	Smls. tube	SA-213	TP310H
33	25Cr-20Ni	Plate	SA-240	310H
34	25Cr-20Ni	Wld. tube	SA-249	TP310H
35	25Cr-20Ni	Smls. & wld. pipe	SA-312	TP310H
36	25Cr-20Ni	Bar	SA-479	310H
37	25Cr-20Ni-Cb	Smls. tube	SA-213	TP310Cb
38	25Cr-20Ni-Cb	Plate	SA-240	310Cb
39	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb
40	25Cr-20Ni-Cb	Smls. & wld. pipe	SA-312	TP310Cb
41	25Cr-20Ni-Cb	Bar	SA-479	310Cb
42	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb
43	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb
44	25Cr-20Ni-Cb-N	Smls. tube	SA-213	TP310HCbN
45	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S32750	...	...	116
2	S32750	...	...	116
3	J93380	...	...	100
4	S32760	...	...	109
5	S32760	...	...	109
6	S32760	Annealed	...	109
7	S32760	...	...	109
8	S32760	...	...	109
9	S32760	...	...	109
10	J93400	...	...	65
11	J93400	...	...	65
12	J93402	...	...	70
13	J93402	...	...	70
14	J94202	...	...	65
15	J94202	...	...	65
16	S31000	...	≤ 5	75
17	S31000	...	...	75
18	S31002	...	...	73
19	S31002	...	...	73
20	S31008	...	...	75
21	S31008	...	...	75
22	S31008	...	...	75
23	S31008	...	...	75
24	S31008	1	...	75
25	S31008	3	...	75
26	S31008	4	...	75
27	S31008	...	...	75
28	S31008	...	...	75
29	S31008	...	...	75
30	S31008	...	...	75
31	...	...	...	75
32	S31009	...	...	75
33	S31009	...	...	75
34	S31009	...	...	75
35	S31009	...	...	75
36	S31009	...	...	75
37	S31040	...	...	75
38	S31040	...	...	75
39	S31040	...	...	75
40	S31040	...	...	75
41	S31040	...	...	75
42	S31040	...	...	75
43	S31040	...	...	75
44	S31042	...	...	95
45	S31050	...	...	78

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)														
1	116.0	115.5	109.1	105.4	103.6	103.0	...	...	...	...	...	...	...	...
2	116.0	115.5	109.1	105.4	103.6	103.0	...	...	...	...	...	...	...	...
3	100.0	99.5	94.3	93.1	93.1	93.1	...	...	...	...	...	...	...	...
4	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
5	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
6	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
7	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
8	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
9	109.0	96.1	92.9	92.9	92.9	92.9	...	...	...	...	...	...	...	...
10	65.0	59.5	55.4	53.9	53.8	53.8	53.7	53.3	52.6	51.6	50.2	48.5	46.3	43.8
11	65.0	59.5	55.4	53.9	53.8	53.8	53.7	53.3	52.6	51.6	50.2	48.5	46.3	43.8
12	70.0	64.0	59.6	58.1	57.9	57.9	57.8	57.4	56.7	55.6	54.1	52.2	49.9	47.2
13	70.0	64.0	59.6	58.1	57.9	57.9	57.8	57.4	56.7	55.6	54.1	52.2	49.9	47.2
14	65.0	59.5	55.4	53.9	53.8	53.8	53.7	53.3	52.6	51.6	50.2	48.5	46.3	43.8
15	65.0	59.5	55.4	53.9	53.8	53.8	53.7	53.3	52.6	51.6	50.2	48.5	46.3	43.8
16	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
17	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
18	73.0	73.0	71.1	67.6	65.5	64.1	63.5	62.7	61.9	61.0	60.3	60.1	...	...
19	73.0	73.0	71.1	67.6	65.5	64.1	63.5	62.7	61.9	61.0	60.3	60.1	...	...
20	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
21	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
22	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
23	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
24	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
25	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
26	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
27	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
28	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
29	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
30	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
31	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
32	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
33	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
34	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
35	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
36	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
37	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
38	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
39	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
40	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
41	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
42	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
43	75.0	74.2	70.8	69.6	69.5	69.5	69.5	69.3	68.8	68.0	66.9	65.5	63.8	61.6
44	95.0	94.0	89.0	86.0	84.5	83.8	83.6	83.4	83.0	82.6	82.0	81.1	80.0	78.6
45	78.0	77.0	72.9	70.1	68.1	66.6	66.0	65.4	64.9	64.3	63.6	62.8	61.5	59.7

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
21	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
22	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
23	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
24	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
25	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
26	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
27	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
28	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
29	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
30	58.2	55.2	51.7	48.0	43.9	39.7	35.3	30.8	26.5	22.3	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Ferrous Materials (Cont'd)				
1	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN
2	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN
3	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN
4	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN
5	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN
6	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN
7	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN
8	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN
9	26Cr-4Ni-Mo	Plate	SA-240	329
10	26Cr-4Ni-Mo	Smls. & wld. tube	SA-789	...
11	26Cr-4Ni-Mo	Smls. & wld. pipe	SA-790	...
12	26Cr-4Ni-Mo-N	Plate	SA-240	...
13	26Cr-4Ni-Mo-N	Smls. & wld. tube	SA-789	...
14	26Cr-4Ni-Mo-N	Smls. & wld. pipe	SA-790	...
15	27Cr-7.5Ni-4.5Mo-Co-N	Smls. tube	SA-789	...
16	27Cr-7.5Ni-4.5Mo-Co-N	Smls. pipe	SA-790	...
17	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...
18	29Cr-6.5Ni-2Mo-N	Bar	SA-479	...
19	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...
20	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...
21	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...
22	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...
23	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Ferrous Materials (Cont'd)				
1	S31050	...	$0.250 < t \leq 1.250$	78
2	S31050	...	$t > 0.250$	78
3	S31050	...	$0.250 < t \leq 1.250$	78
4	S31050	...	$0.250 < t \leq 1.250$	78
5	S31050	...	≤ 0.250 , wall	84
6	S31050	...	$t \leq 0.250$	84
7	S31050	...	≤ 0.250 , wall	84
8	S31050	...	≤ 0.250 , wall	84
9	S32900	...	...	90
10	S32900	...	...	90
11	S32900	...	...	90
12	S32950	...	...	100
13	S32950	...	...	100
14	S32950	...	...	100
15	S32707	...	...	133
16	S32707	...	...	133
17	S32906	...	≥ 0.40	109
18	S32906	...	...	109
19	S32906	...	≥ 0.40	109
20	S32906	...	≥ 0.40	109
21	S32906	...	< 0.40	116
22	S32906	...	< 0.40	116
23	S32906	...	< 0.40	116

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)													
1	78.0	77.0	72.9	70.1	68.1	66.6	66.0	65.4	64.9	64.3	63.6	62.8	61.5	59.7
2	78.0	77.0	72.9	70.1	68.1	66.6	66.0	65.4	64.9	64.3	63.6	62.8	61.5	59.7
3	78.0	77.0	72.9	70.1	68.1	66.6	66.0	65.4	64.9	64.3	63.6	62.8	61.5	59.7
4	78.0	77.0	72.9	70.1	68.1	66.6	66.0	65.4	64.9	64.3	63.6	62.8	61.5	59.7
5	84.0	83.0	78.5	75.5	73.3	71.7	71.0	70.4	69.9	69.3	68.5	67.6	66.2	64.3
6	84.0	83.0	78.5	75.5	73.3	71.7	71.0	70.4	69.9	69.3	68.5	67.6	66.2	64.3
7	84.0	83.0	78.5	75.5	73.3	71.7	71.0	70.4	69.9	69.3	68.5	67.6	66.2	64.3
8	84.0	83.0	78.5	75.5	73.3	71.7	71.0	70.4	69.9	69.3	68.5	67.6	66.2	64.3
9	90.0	90.0	86.7	84.9	84.9	84.9	84.9	84.9	...	...	...	...	...	...
10	90.0	90.0	86.7	84.9	84.9	84.9	84.9	84.9	...	...	...	...	...	...
11	90.0	90.0	86.7	84.9	84.9	84.9	84.9	84.9	...	...	...	...	...	...
12	100.0	99.7	94.6	92.5	92.5	92.5	92.5	92.5	...	...	...	...	...	...
13	100.0	99.7	94.6	92.5	92.5	92.5	92.5	92.5	...	...	...	...	...	...
14	100.0	99.7	94.6	92.5	92.5	92.5	92.5	92.5	...	...	...	...	...	...
15	133.0	133.0	132.1	129.2	123.7	...	...	...	...	...	...	...	...	...
16	133.0	133.0	132.1	129.2	123.7	...	...	...	...	...	...	...	...	...
17	109.0	108.9	103.6	100.5	99.1	99.1	...	...	...	...	...	...	...	...
18	109.0	108.9	103.6	100.5	99.1	99.1	...	...	...	...	...	...	...	...
19	109.0	108.9	103.6	100.5	99.1	99.1	...	...	...	...	...	...	...	...
20	109.0	108.9	103.6	100.5	99.1	99.1	...	...	...	...	...	...	...	...
21	116.0	115.9	110.3	106.9	105.5	105.5	...	...	...	...	...	...	...	...
22	116.0	115.9	110.3	106.9	105.5	105.5	...	...	...	...	...	...	...	...
23	116.0	115.9	110.3	106.9	105.5	105.5	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials				
1	...	Plate, sheet	SB-209	...
2	...	Plate, sheet	SB-209	...
3	...	Plate, sheet	SB-209	...
4	...	Plate, sheet	SB-209	...
5	...	Plate, sheet	SB-209	...
6	...	Plate, sheet	SB-209	...
7	...	Plate, sheet	SB-209	...
8	...	Plate, sheet	SB-209	...
9	...	Plate, sheet	SB-209	...
10	...	Drawn smls. tube	SB-210	...
11	...	Drawn smls. tube	SB-210	...
12	...	Drawn smls. tube	SB-210	...
13	...	Drawn smls. tube	SB-210	...
14	...	Cond. & heat exch. tubes	SB-234	...
15	...	Cond. & heat exch. tubes	SB-234	...
16	...	Smls. extr. tube	SB-241	...
17	...	Smls. extr. tube	SB-241	...
18	...	Plate, sheet	SB-209	...
19	...	Plate, sheet	SB-209	...
20	...	Plate, sheet	SB-209	...
21	...	Plate, sheet	SB-209	...
22	...	Plate, sheet	SB-209	...
23	...	Plate, sheet	SB-209	...
24	...	Plate, sheet	SB-209	...
25	...	Plate, sheet	SB-209	...
26	...	Plate, sheet	SB-209	...
27	...	Plate, sheet	SB-209	...
28	...	Plate, sheet	SB-209	...
29	...	Plate, sheet	SB-209	...
30	...	Plate, sheet	SB-209	...
31	...	Plate, sheet	SB-209	...
32	...	Plate, sheet	SB-209	...
33	...	Plate, sheet	SB-209	...
34	...	Plate, sheet	SB-209	...
35	...	Plate, sheet	SB-209	...
36	...	Plate, sheet	SB-209	...
37	...	Castings	SB/EN 1706	...
38	...	Plate, sheet	SB-209	...
39	...	Plate, sheet	SB-209	...
40	...	Plate, sheet	SB-209	...
41	...	Plate, sheet	SB-209	...
42	...	Plate, sheet	SB-209	...
43	...	Plate, sheet	SB-209	...
44	...	Drawn smls. tube	SB-210	...
45	...	Drawn smls. tube	SB-210	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials				
1	Alclad 3003	O	0.006–0.499	13
2	Alclad 3003	O	0.500–3.000	14
3	Alclad 3003	H112	0.250–0.499	16
4	Alclad 3003	H112	0.500–2.000	15
5	Alclad 3003	H112	2.001–3.000	14.5
6	Alclad 3003	H12	0.017–0.499	16
7	Alclad 3003	H12	0.500–2.000	17
8	Alclad 3003	H14	0.009–0.499	19
9	Alclad 3003	H14	0.500–1.000	20
10	Alclad 3003	O	0.010–0.500	13
11	Alclad 3003	H113	0.050–0.500	13
12	Alclad 3003	H14	0.010–0.500	19
13	Alclad 3003	H18	0.010–0.500	26
14	Alclad 3003	H14	0.010–0.200	19
15	Alclad 3003	H25	0.010–0.200	21
16	Alclad 3003	O	...	13
17	Alclad 3003	H112	...	13
18	Alclad 3004	O	0.006–0.499	21
19	Alclad 3004	O	0.500–3.000	22
20	Alclad 3004	H112	0.250–0.499	22
21	Alclad 3004	H112	0.500–3.000	23
22	Alclad 3004	H32	0.017–0.499	27
23	Alclad 3004	H32	0.500–2.000	28
24	Alclad 3004	H34	0.009–0.499	31
25	Alclad 3004	H34	0.500–1.000	32
26	Alclad 6061	T4	0.010–0.249	27
27	Alclad 6061	T451	0.250–0.499	27
28	Alclad 6061	T451	0.500–3.000	30
29	Alclad 6061	T4 wld.	0.010–0.249	24
30	Alclad 6061	T451 wld.	0.250–3.000	24
31	Alclad 6061	T6	0.010–0.249	38
32	Alclad 6061	T651	0.250–0.499	38
33	Alclad 6061	T651	0.500–4.000	42
34	Alclad 6061	T651	4.001–5.000	40
35	Alclad 6061	T6 wld.	0.010–0.249	24
36	Alclad 6061	T651 wld.	0.250–5.000	24
37	AC-42000-S	T6	...	32
38	A91060	O	0.006–3.000	8
39	A91060	H112	0.250–0.499	11
40	A91060	H112	0.500–1.000	10
41	A91060	H112	1.001–3.000	9
42	A91060	H12	0.017–2.000	11
43	A91060	H14	0.009–1.000	12
44	A91060	O	0.018–0.500	8.5
45	A91060	H14	0.018–0.500	12

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials														
1	13.0	12.0	9.7	7.5	...	...	...	...	...	...	...	...	...	...
2	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
3	16.0	14.6	12.2	9.3	...	...	...	...	...	...	...	...	...	...
4	15.0	13.8	11.3	8.6	...	...	...	...	...	...	...	...	...	...
5	14.5	13.4	10.8	8.3	...	...	...	...	...	...	...	...	...	...
6	16.0	15.8	13.6	11.0	...	...	...	...	...	...	...	...	...	...
7	17.0	16.8	14.5	11.7	...	...	...	...	...	...	...	...	...	...
8	19.0	19.0	16.7	12.9	...	...	...	...	...	...	...	...	...	...
9	20.0	20.0	17.5	13.5	...	...	...	...	...	...	...	...	...	...
10	13.0	12.0	9.7	7.5	...	...	...	...	...	...	...	...	...	...
11	13.0	12.0	9.7	7.5	...	...	...	...	...	...	...	...	...	...
12	19.0	19.0	16.7	12.9	...	...	...	...	...	...	...	...	...	...
13	26.0	25.6	22.2	14.7	...	...	...	...	...	...	...	...	...	...
14	19.0	19.0	16.7	12.9	...	...	...	...	...	...	...	...	...	...
15	21.0	21.0	18.3	13.4	...	...	...	...	...	...	...	...	...	...
16	13.0	12.0	9.7	7.5	...	...	...	...	...	...	...	...	...	...
17	13.0	12.0	9.7	7.5	...	...	...	...	...	...	...	...	...	...
18	21.0	21.0	19.2	11.9	...	...	...	...	...	...	...	...	...	...
19	22.0	22.0	20.1	12.4	...	...	...	...	...	...	...	...	...	...
20	22.0	22.0	20.1	12.4	...	...	...	...	...	...	...	...	...	...
21	23.0	23.0	20.6	13.9	...	...	...	...	...	...	...	...	...	...
22	27.0	27.0	24.7	18.2	...	...	...	...	...	...	...	...	...	...
23	28.0	28.0	25.6	18.9	...	...	...	...	...	...	...	...	...	...
24	31.0	31.0	27.9	20.1	...	...	...	...	...	...	...	...	...	...
25	32.0	32.0	28.8	20.8	...	...	...	...	...	...	...	...	...	...
26	27.0	27.0	25.5	16.0	...	...	...	...	...	...	...	...	...	...
27	27.0	27.0	25.5	16.0	...	...	...	...	...	...	...	...	...	...
28	30.0	30.0	28.3	17.8	...	...	...	...	...	...	...	...	...	...
29	24.0	24.0	23.0	15.0	...	...	...	...	...	...	...	...	...	...
30	24.0	24.0	23.0	15.0	...	...	...	...	...	...	...	...	...	...
31	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
32	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
33	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
34	40.0	40.0	33.4	18.4	...	...	...	...	...	...	...	...	...	...
35	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
36	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
37	32.0	32.0	29.3	...	...	...	...	...	...	...	...	...	...	...
38	8.0	6.8	5.3	3.8	...	...	...	...	...	...	...	...	...	...
39	11.0	9.4	7.2	5.3	...	...	...	...	...	...	...	...	...	...
40	10.0	8.5	6.6	4.8	...	...	...	...	...	...	...	...	...	...
41	9.0	7.7	5.9	4.4	...	...	...	...	...	...	...	...	...	...
42	11.0	10.3	8.2	6.0	...	...	...	...	...	...	...	...	...	...
43	12.0	12.0	10.3	6.9	...	...	...	...	...	...	...	...	...	...
44	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
45	12.0	12.0	10.3	6.9	...	...	...	...	...	...	...	...	...	...

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Nonferrous Materials

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Drawn smls. tube	SB-210	...
2	...	Bar, rod, shapes	SB-221	...
3	...	Bar, rod, shapes	SB-221	...
4	...	Cond. & heat exch. tubes	SB-234	...
5	...	Smls. extr. tube	SB-241	...
6	...	Smls. extr. tube	SB-241	...
7	...	Plate, sheet	SB-209	...
8	...	Plate, sheet	SB-209	...
9	...	Plate, sheet	SB-209	...
10	...	Plate, sheet	SB-209	...
11	...	Plate, sheet	SB-209	...
12	...	Plate, sheet	SB-209	...
13	...	Bar, rod, shapes	SB-221	...
14	...	Bar, rod, shapes	SB-221	...
15	...	Smls. extr. tube	SB-241	...
16	...	Smls. extr. tube	SB-241	...
17	...	Plate, sheet	SB-209	...
18	...	Plate, sheet	SB-209	...
19	...	Plate, sheet	SB-209	...
20	...	Plate, sheet	SB-209	...
21	...	Plate, sheet	SB-209	...
22	...	Plate, sheet	SB-209	...
23	...	Drawn smls. tube	SB-210	...
24	...	Drawn smls. tube	SB-210	...
25	...	Drawn smls. tube	SB-210	...
26	...	Drawn smls. tube	SB-210	...
27	...	Drawn smls. tube	SB-210	...
28	...	Bar, rod, shapes	SB-221	...
29	...	Bar, rod, shapes	SB-221	...
30	...	Cond. & heat exch. tubes	SB-234	...
31	...	Cond. & heat exch. tubes	SB-234	...
32	...	Smls. extr. tube	SB-241	...
33	...	Smls. extr. tube	SB-241	...
34	...	Smls. pipe	SB-241	...
35	...	Smls. pipe	SB-241	...
36	...	Die forgings	SB-247	...
37	...	Die forgings	SB-247	...
38	...	Plate, sheet	SB-209	...
39	...	Plate, sheet	SB-209	...
40	...	Plate, sheet	SB-209	...
41	...	Plate, sheet	SB-209	...
42	...	Plate, sheet	SB-209	...
43	...	Plate, sheet	SB-209	...
44	...	Plate, sheet	SB-209	...
45	...	Plate, sheet	SB-209	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	A91060	H113	0.018-0.500	8.5
2	A91060	O	...	8.5
3	A91060	H112	...	8.5
4	A91060	H14	0.010-0.200	12
5	A91060	O	...	8.5
6	A91060	H112	...	8.5
7	A91100	O	0.006-3.000	11
8	A91100	H112	0.250-0.499	13
9	A91100	H112	0.500-2.000	12
10	A91100	H112	2.001-3.000	11.5
11	A91100	H12	0.017-2.000	14
12	A91100	H14	0.009-1.000	16
13	A91100	O	...	11
14	A91100	H112	...	11
15	A91100	O	...	11
16	A91100	H112	...	11
17	A93003	O	0.006-3.000	14
18	A93003	H112	0.250-0.499	17
19	A93003	H112	0.500-2.000	15
20	A93003	H112	2.001-3.000	14.5
21	A93003	H12	0.017-2.000	17
22	A93003	H14	0.009-1.000	20
23	A93003	O	0.010-0.500	14
24	A93003	H113	0.010-0.500	14
25	A93003	H12	0.010-0.500	17
26	A93003	H14	0.010-0.500	20
27	A93003	H18	0.010-0.500	27
28	A93003	O	...	14
29	A93003	H112	...	14
30	A93003	H14	0.010-0.200	20
31	A93003	H25	0.010-0.200	22
32	A93003	O	...	14
33	A93003	H112	...	14
34	A93003	H112	≥1.000	14
35	A93003	H18	<1.000	27
36	A93003	H112	≤4.000	14
37	A93003	H112 wld.	≤4.000	14
38	A93004	O	0.006-3.000	22
39	A93004	H112	0.250-3.000	23
40	A93004	H32	0.017-2.000	28
41	A93004	H34	0.009-1.000	32
42	A95052	O	0.006-3.000	25
43	A95052	H112	0.250-0.499	28
44	A95052	H112	0.500-3.000	25
45	A95052	H32	0.017-2.000	31

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
2	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
3	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
4	12.0	12.0	10.3	6.9	...	...	...	...	...	...	...	...	...	...
5	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
6	8.5	7.2	5.6	4.1	...	...	...	...	...	...	...	...	...	...
7	11.0	10.2	8.0	5.3	...	...	...	...	...	...	...	...	...	...
8	13.0	12.1	9.5	6.6	...	...	...	...	...	...	...	...	...	...
9	12.0	11.2	8.8	6.0	...	...	...	...	...	...	...	...	...	...
10	11.5	10.7	8.4	5.9	...	...	...	...	...	...	...	...	...	...
11	14.0	13.9	11.7	9.1	...	...	...	...	...	...	...	...	...	...
12	16.0	16.0	13.2	9.7	...	...	...	...	...	...	...	...	...	...
13	11.0	10.2	8.0	5.3	...	...	...	...	...	...	...	...	...	...
14	11.0	10.2	8.0	5.3	...	...	...	...	...	...	...	...	...	...
15	11.0	10.2	8.0	5.3	...	...	...	...	...	...	...	...	...	...
16	11.0	10.2	8.0	5.3	...	...	...	...	...	...	...	...	...	...
17	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
18	17.0	15.5	13.0	9.9	...	...	...	...	...	...	...	...	...	...
19	15.0	13.8	11.3	8.6	...	...	...	...	...	...	...	...	...	...
20	14.5	13.3	10.9	8.3	...	...	...	...	...	...	...	...	...	...
21	17.0	16.8	14.5	11.7	...	...	...	...	...	...	...	...	...	...
22	20.0	20.0	17.5	13.5	...	...	...	...	...	...	...	...	...	...
23	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
24	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
25	17.0	16.8	14.5	11.7	...	...	...	...	...	...	...	...	...	...
26	20.0	20.0	17.5	13.5	...	...	...	...	...	...	...	...	...	...
27	27.0	26.5	23.0	15.3	...	...	...	...	...	...	...	...	...	...
28	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
29	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
30	20.0	20.0	17.5	13.5	...	...	...	...	...	...	...	...	...	...
31	22.0	22.0	19.1	14.1	...	...	...	...	...	...	...	...	...	...
32	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
33	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
34	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
35	27.0	26.5	23.0	15.3	...	...	...	...	...	...	...	...	...	...
36	14.0	12.9	10.5	8.0	...	...	...	...	...	...	...	...	...	...
37	14.0	13.0	10.6	8.4	...	...	...	...	...	...	...	...	...	...
38	22.0	22.0	20.1	12.4	...	...	...	...	...	...	...	...	...	...
39	23.0	23.0	20.6	13.9	...	...	...	...	...	...	...	...	...	...
40	28.0	28.0	25.6	18.9	...	...	...	...	...	...	...	...	...	...
41	32.0	32.0	28.8	20.8	...	...	...	...	...	...	...	...	...	...
42	25.0	25.0	23.9	17.3	...	...	...	...	...	...	...	...	...	...
43	28.0	28.0	26.7	19.4	...	...	...	...	...	...	...	...	...	...
44	25.0	25.0	23.9	17.3	...	...	...	...	...	...	...	...	...	...
45	31.0	31.0	28.0	21.2	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Plate, sheet	SB-209	...
2	...	Drawn smls. tube	SB-210	...
3	...	Drawn smls. tube	SB-210	...
4	...	Drawn smls. tube	SB-210	...
5	...	Cond. & heat exch. tubes	SB-234	...
6	...	Cond. & heat exch. tubes	SB-234	...
7	...	Smls. extr. tube	SB-241	...
8	...	Plate, sheet	SB-209	...
9	...	Plate, sheet	SB-209	...
10	...	Plate, sheet	SB-209	...
11	...	Plate, sheet	SB-209	...
12	...	Plate, sheet	SB-209	...
13	...	Plate, sheet	SB-209	...
14	...	Plate, sheet	SB-209	...
15	...	Plate, sheet	SB-209	...
16	...	Plate, sheet	SB-209	...
17	...	Bar, rod, shapes	SB-221	...
18	...	Bar, rod, shapes	SB-221	...
19	...	Bar, rod, shapes	SB-221	...
20	...	Smls. extr. tube	SB-241	...
21	...	Smls. extr. tube	SB-241	...
22	...	Smls. extr. tube	SB-241	...
23	...	Die & hand forgings	SB-247	...
24	...	Die & hand forgings	SB-247	...
25	...	Die & hand forgings	SB-247	...
26	...	Die & hand forgings	SB-247	...
27	...	Plate, sheet	SB-928	...
28	...	Plate, sheet	SB-928	...
29	...	Plate, sheet	SB-209	...
30	...	Plate, sheet	SB-209	...
31	...	Plate, sheet	SB-209	...
32	...	Plate, sheet	SB-209	...
33	...	Plate, sheet	SB-209	...
34	...	Plate, sheet	SB-209	...
35	...	Bar, rod, shapes	SB-221	...
36	...	Smls. extr. tube	SB-241	...
37	...	Smls. extr. tube	SB-241	...
38	...	Smls. extr. tube	SB-241	...
39	...	Plate, sheet	SB-928	...
40	...	Plate, sheet	SB-209	...
41	...	Plate, sheet	SB-209	...
42	...	Plate, sheet	SB-209	...
43	...	Plate, sheet	SB-209	...
44	...	Plate, sheet	SB-209	...
45	...	Drawn smls. tube	SB-210	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	A95052	H34	0.009-1.000	34
2	A95052	O	0.010-0.450	25
3	A95052	H32	0.010-0.450	31
4	A95052	H34	0.010-0.450	34
5	A95052	H32	0.010-0.200	31
6	A95052	H34	0.010-0.200	34
7	A95052	O	...	25
8	A95083	O	0.051-1.500	40
9	A95083	O	1.501-3.000	39
10	A95083	O	3.001-5.000	38
11	A95083	O	5.001-7.000	37
12	A95083	O	7.001-8.000	36
13	A95083	H112	0.250-1.500	40
14	A95083	H112	1.501-3.000	39
15	A95083	H32	0.125-1.500	44
16	A95083	H32	1.501-3.000	41
17	A95083	O	≤5.000	39
18	A95083	H111	≤5.000	40
19	A95083	H112	≤5.000	39
20	A95083	O	...	39
21	A95083	H111	...	40
22	A95083	H112	...	39
23	A95083	H111	≤4.000	39
24	A95083	H112	≤4.000	39
25	A95083	H111 wld.	≤4.000	38
26	A95083	H112 wld.	≤4.000	38
27	A95083	H321	0.125-1.500	44
28	A95083	H321	1.501-3.000	41
29	A95086	O	0.020-2.000	35
30	A95086	H112	0.188-0.499	36
31	A95086	H112	0.500-2.000	35
32	A95086	H112	2.001-3.000	34
33	A95086	H32	0.020-2.000	40
34	A95086	H34	0.009-1.000	44
35	A95086	H112	≤5.000	35
36	A95086	O	...	35
37	A95086	H111	...	36
38	A95086	H112	...	35
39	A95086	H116	0.063-2.000	40
40	A95154	O	0.020-3.000	30
41	A95154	H112	0.250-0.499	32
42	A95154	H112	0.500-3.000	30
43	A95154	H32	0.020-2.000	36
44	A95154	H34	0.009-1.000	39
45	A95154	O	0.010-0.450	30

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	34.0	34.0	33.1	25.4	...	...	...	...	...	...	...	...	...	...
2	25.0	25.0	23.9	17.3	...	...	...	...	...	...	...	...	...	...
3	31.0	31.0	28.0	21.2	...	...	...	...	...	...	...	...	...	...
4	34.0	34.0	33.1	25.4	...	...	...	...	...	...	...	...	...	...
5	31.0	31.0	28.0	21.2	...	...	...	...	...	...	...	...	...	...
6	34.0	34.0	33.1	25.4	...	...	...	...	...	...	...	...	...	...
7	25.0	25.0	23.9	17.3	...	...	...	...	...	...	...	...	...	...
8	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
9	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
10	38.0	...	...	...	...	...	...	...	...	...	...	...	...	...
11	37.0	...	...	...	...	...	...	...	...	...	...	...	...	...
12	36.0	...	...	...	...	...	...	...	...	...	...	...	...	...
13	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
14	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
15	44.0	...	...	...	...	...	...	...	...	...	...	...	...	...
16	41.0	...	...	...	...	...	...	...	...	...	...	...	...	...
17	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
18	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
19	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
20	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
21	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
22	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
23	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
24	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
25	38.0	...	...	...	...	...	...	...	...	...	...	...	...	...
26	38.0	...	...	...	...	...	...	...	...	...	...	...	...	...
27	44.0	...	...	...	...	...	...	...	...	...	...	...	...	...
28	41.0	...	...	...	...	...	...	...	...	...	...	...	...	...
29	35.0	...	...	...	...	...	...	...	...	...	...	...	...	...
30	36.0	...	...	...	...	...	...	...	...	...	...	...	...	...
31	35.0	...	...	...	...	...	...	...	...	...	...	...	...	...
32	34.0	...	...	...	...	...	...	...	...	...	...	...	...	...
33	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
34	44.0	...	...	...	...	...	...	...	...	...	...	...	...	...
35	35.0	...	...	...	...	...	...	...	...	...	...	...	...	...
36	35.0	...	...	...	...	...	...	...	...	...	...	...	...	...
37	36.0	...	...	...	...	...	...	...	...	...	...	...	...	...
38	35.0	...	...	...	...	...	...	...	...	...	...	...	...	...
39	40.0	...	...	...	...	...	...	...	...	...	...	...	...	...
40	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
41	32.0	...	...	...	...	...	...	...	...	...	...	...	...	...
42	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
43	36.0	...	...	...	...	...	...	...	...	...	...	...	...	...
44	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
45	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Drawn smls. tube	SB-210	...
2	...	Bar, rod, shapes	SB-221	...
3	...	Bar, rod, shapes	SB-221	...
4	...	Plate, sheet	SB-209	...
5	...	Plate, sheet	SB-209	...
6	...	Plate, sheet	SB-209	...
7	...	Plate, sheet	SB-209	...
8	...	Plate, sheet	SB-209	...
9	...	Plate, sheet	SB-209	...
10	...	Plate, sheet	SB-209	...
11	...	Plate, sheet	SB-209	...
12	...	Plate, sheet	SB-209	...
13	...	Plate, sheet	SB-209	...
14	...	Bar, rod, shapes	SB-221	...
15	...	Bar, rod, shapes	SB-221	...
16	...	Bar, rod, shapes	SB-221	...
17	...	Cond. & heat exch. tubes	SB-234	...
18	...	Cond. & heat exch. tubes	SB-234	...
19	...	Smls. extr. tube	SB-241	...
20	...	Smls. extr. tube	SB-241	...
21	...	Smls. extr. tube	SB-241	...
22	...	Plate, sheet	SB-209	...
23	...	Plate, sheet	SB-209	...
24	...	Plate, sheet	SB-209	...
25	...	Plate, sheet	SB-209	...
26	...	Plate, sheet	SB-209	...
27	...	Plate, sheet	SB-209	...
28	...	Plate, sheet	SB-209	...
29	...	Plate, sheet	SB-209	...
30	...	Plate, sheet	SB-209	...
31	...	Plate, sheet	SB-209	...
32	...	Bar, rod, shapes	SB-221	...
33	...	Bar, rod, shapes	SB-221	...
34	...	Bar, rod, shapes	SB-221	...
35	...	Smls. extr. tube	SB-241	...
36	...	Smls. extr. tube	SB-241	...
37	...	Smls. extr. tube	SB-241	...
38	...	Plate, sheet	SB-928	...
39	...	Plate, sheet	SB-928	...
40	...	Plate, sheet	SB-928	...
41	...	Plate, sheet	SB-209	...
42	...	Plate, sheet	SB-209	...
43	...	Plate, sheet	SB-209	...
44	...	Plate, sheet	SB-209	...
45	...	Plate, sheet	SB-209	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	A95154	H34	0.010-0.450	39
2	A95154	O	...	30
3	A95154	H112	...	30
4	A95254	O	0.051-3.000	30
5	A95254	H112	0.250-0.499	32
6	A95254	H112	0.500-3.000	30
7	A95254	H32	0.051-2.000	36
8	A95254	H34	0.051-1.000	39
9	A95454	O	0.020-3.000	31
10	A95454	H112	0.250-0.499	32
11	A95454	H112	0.500-3.000	31
12	A95454	H32	0.020-2.000	36
13	A95454	H34	0.020-1.000	39
14	A95454	O	≤5.000	31
15	A95454	H111	≤5.000	33
16	A95454	H112	≤5.000	31
17	A95454	H32	0.010-0.200	36
18	A95454	H34	0.010-0.200	39
19	A95454	O	...	31
20	A95454	H111	...	33
21	A95454	H112	...	31
22	A95456	O	0.051-1.500	42
23	A95456	O	1.501-3.000	41
24	A95456	O	3.001-5.000	40
25	A95456	O	5.001-7.000	39
26	A95456	O	7.001-8.000	38
27	A95456	H112	0.250-1.500	42
28	A95456	H112	1.501-3.000	41
29	A95456	H32	0.188-0.499	46
30	A95456	H32	0.500-1.500	44
31	A95456	H32	1.501-3.000	41
32	A95456	O	≤5.000	41
33	A95456	H111	≤5.000	42
34	A95456	H112	≤5.000	41
35	A95456	O	...	41
36	A95456	H111	...	42
37	A95456	H112	...	41
38	A95456	H321	0.188-0.499	46
39	A95456	H321	0.500-1.500	44
40	A95456	H321	1.501-3.000	41
41	A96061	T4	0.006-0.249	30
42	A96061	T451	0.250-3.000	30
43	A96061	T6	0.006-0.249	42
44	A96061	T651	0.250-4.000	42
45	A96061	T651	4.001-6.000	40

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
2	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
3	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
4	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
5	32.0	...	...	...	...	...	...	...	...	...	...	...	...	...
6	30.0	...	...	...	...	...	...	...	...	...	...	...	...	...
7	36.0	...	...	...	...	...	...	...	...	...	...	...	...	...
8	39.0	...	...	...	...	...	...	...	...	...	...	...	...	...
9	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
10	32.0	32.0	29.0	22.2	...	...	...	...	...	...	...	...	...	...
11	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
12	36.0	36.0	32.1	24.3	...	...	...	...	...	...	...	...	...	...
13	39.0	39.0	33.8	24.3	...	...	...	...	...	...	...	...	...	...
14	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
15	33.0	33.0	29.9	23.0	...	...	...	...	...	...	...	...	...	...
16	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
17	36.0	36.0	32.1	24.3	...	...	...	...	...	...	...	...	...	...
18	39.0	39.0	33.8	24.3	...	...	...	...	...	...	...	...	...	...
19	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
20	33.0	33.0	29.9	23.0	...	...	...	...	...	...	...	...	...	...
21	31.0	31.0	28.1	21.6	...	...	...	...	...	...	...	...	...	...
22	42.0	42.0	...	...	...	...	...	...	...	...	...	...	...	...
23	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
24	40.0	40.0	...	...	...	...	...	...	...	...	...	...	...	...
25	39.0	39.0	...	...	...	...	...	...	...	...	...	...	...	...
26	38.0	38.0	...	...	...	...	...	...	...	...	...	...	...	...
27	42.0	42.0	...	...	...	...	...	...	...	...	...	...	...	...
28	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
29	46.0	46.0	...	...	...	...	...	...	...	...	...	...	...	...
30	44.0	44.0	...	...	...	...	...	...	...	...	...	...	...	...
31	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
32	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
33	42.0	42.0	...	...	...	...	...	...	...	...	...	...	...	...
34	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
35	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
36	42.0	42.0	...	...	...	...	...	...	...	...	...	...	...	...
37	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
38	46.0	46.0	...	...	...	...	...	...	...	...	...	...	...	...
39	44.0	44.0	...	...	...	...	...	...	...	...	...	...	...	...
40	41.0	41.0	...	...	...	...	...	...	...	...	...	...	...	...
41	30.0	30.0	28.3	17.7	...	...	...	...	...	...	...	...	...	...
42	30.0	30.0	28.3	17.7	...	...	...	...	...	...	...	...	...	...
43	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
44	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
45	40.0	40.0	33.4	18.4	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Plate, sheet	SB-209	...
2	...	Plate, sheet	SB-209	...
3	...	Plate, sheet	SB-209	...
4	...	Plate, sheet	SB-209	...
5	...	Drawn smls. tube	SB-210	...
6	...	Drawn smls. tube	SB-210	...
7	...	Drawn smls. tube	SB-210	...
8	...	Drawn smls. tube	SB-210	...
9	...	Bar, rod, wire	SB-211	...
10	...	Bar, rod, wire	SB-211	...
11	...	Bar, rod, wire	SB-211	...
12	...	Bar, rod, wire	SB-211	...
13	...	Bar, rod, shapes	SB-221	...
14	...	Bar, rod, shapes	SB-221	...
15	...	Bar, rod, shapes	SB-221	...
16	...	Bar, rod, shapes	SB-221	...
17	...	Cond. & heat exch. tubes	SB-234	...
18	...	Cond. & heat exch. tubes	SB-234	...
19	...	Cond. & heat exch. tubes	SB-234	...
20	...	Cond. & heat exch. tubes	SB-234	...
21	...	Smls. extr. tube	SB-241	...
22	...	Smls. extr. tube	SB-241	...
23	...	Smls. extr. tube	SB-241	...
24	...	Smls. extr. tube	SB-241	...
25	...	Smls. pipe	SB-241	...
26	...	Smls. pipe	SB-241	...
27	...	Smls. pipe	SB-241	...
28	...	Die forgings	SB-247	...
29	...	Hand forgings	SB-247	...
30	...	Hand forgings	SB-247	...
31	...	Die & hand forgings	SB-247	...
32	...	Shapes	SB-308	...
33	...	Shapes	SB-308	...
34	...	Drawn smls. tube	SB-210	...
35	...	Drawn smls. tube	SB-210	...
(25) 36	...	Bar, rod, shapes	SB-221	...
37	...	Bar, rod, shapes	SB-221	...
38	...	Bar, rod, shapes	SB-221	...
39	...	Bar, rod, shapes	SB-221	...
40	...	Bar, rod, shapes	SB-221	...
41	...	Bar, rod, shapes	SB-221	...
42	...	Smls. extr. tube	SB-241	...
43	...	Smls. extr. tube	SB-241	...
44	...	Smls. extr. tube	SB-241	...
45	...	Smls. extr. tube	SB-241	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	A96061	T4 wld.	0.006–0.249	24
2	A96061	T451 wld.	0.250–3.000	24
3	A96061	T6 wld.	0.006–0.249	24
4	A96061	T651 wld.	0.250–6.000	24
5	A96061	T4	0.025–0.500	30
6	A96061	T6	0.025–0.500	42
7	A96061	T4 wld.	0.025–0.500	24
8	A96061	T6 wld.	0.025–0.500	24
9	A96061	T6	0.125–8.000	42
10	A96061	T651	0.125–8.000	42
11	A96061	T6 wld.	0.125–8.000	24
12	A96061	T651 wld.	0.125–8.000	24
13	A96061	T4	...	26
14	A96061	T6	...	38
15	A96061	T4 wld.	...	24
16	A96061	T6 wld.	...	24
17	A96061	T4	0.025–0.200	30
18	A96061	T6	0.025–0.200	42
19	A96061	T4 wld.	0.025–0.200	24
20	A96061	T6 wld.	0.025–0.200	24
21	A96061	T4	...	26
22	A96061	T6	...	38
23	A96061	T4 wld.	...	24
24	A96061	T6 wld.	...	24
25	A96061	T6 drawn	<1.000	42
26	A96061	T6	≥1.000	38
27	A96061	T6 wld.	...	24
28	A96061	T6	≤4.000	38
29	A96061	T6	≤4.000	37
30	A96061	T6	4.001–8.000	35
31	A96061	T6 wld.	≤8.000	24
32	A96061	T6	...	38
33	A96061	T6 wld.	...	24
34	A96063	T6	0.025–0.500	33
35	A96063	T6 wld.	0.025–0.500	17
36	A96063	T1	≤0.500	17
37	A96063	T1	0.501–1.000	16
38	A96063	T5	≤0.500	22
39	A96063	T5	0.501–1.000	21
40	A96063	T6	≤1.000	30
41	A96063	T6 wld.	≤1.000	17
42	A96063	O	...	16
43	A96063	T1	≤0.500	17
44	A96063	T1	0.501–1.000	16
45	A96063	T5	≤0.500	22

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
2	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
3	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
4	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
5	30.0	30.0	28.3	17.7	...	...	...	...	...	...	...	...	...	...
6	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
7	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
8	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
9	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
10	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
11	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
12	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
13	26.0	26.0	24.6	15.4	...	...	...	...	...	...	...	...	...	...
14	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
15	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
16	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
17	30.0	30.0	28.3	17.7	...	...	...	...	...	...	...	...	...	...
18	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
19	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
20	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
21	26.0	26.0	24.6	15.4	...	...	...	...	...	...	...	...	...	...
22	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
23	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
24	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
25	42.0	42.0	35.1	19.3	...	...	...	...	...	...	...	...	...	...
26	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
27	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
28	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
29	37.0	37.0	33.0	18.5	...	...	...	...	...	...	...	...	...	...
30	35.0	35.0	33.1	20.7	...	...	...	...	...	...	...	...	...	...
31	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
32	38.0	38.0	31.7	17.5	...	...	...	...	...	...	...	...	...	...
33	24.0	24.0	23.2	15.5	...	...	...	...	...	...	...	...	...	...
34	33.0	33.0	22.2	9.6	...	...	...	...	...	...	...	...	...	...
35	17.0	17.0	15.4	3.9	...	...	...	...	...	...	...	...	...	...
36	17.0	17.0	17.0	8.7	...	...	...	...	...	...	...	...	...	...
37	16.0	16.0	16.0	8.7	...	...	...	...	...	...	...	...	...	...
38	22.0	21.4	18.2	8.7	...	...	...	...	...	...	...	...	...	...
39	21.0	20.5	17.3	8.7	...	...	...	...	...	...	...	...	...	...
40	30.0	29.9	20.4	9.0	...	...	...	...	...	...	...	...	...	...
41	17.0	17.0	15.4	3.9	...	...	...	...	...	...	...	...	...	...
42	16.0	16.0	16.0	...	...	...	...	...	...	...	...	...	...	...
43	17.0	17.0	17.0	...	...	...	...	...	...	...	...	...	...	...
44	16.0	16.0	16.0	...	...	...	...	...	...	...	...	...	...	...
45	22.0	21.4	18.2	8.7	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Smls. extr. tube	SB-241	...
2	...	Smls. extr. tube/pipe	SB-241	...
3	...	Smls. extr. tube	SB-241	...
4	...	Smls. extr. tube/pipe	SB-241	...
5	...	Smls. pipe	SB-241	...
6	...	Castings	SB/EN 1706	AlSi7Mg
7	...	Castings	SB/EN 1706	...
8	...	Bar, rod	SB-187	...
9	...	Smls. tube	SB-75	...
10	...	Smls. pipe	SB-42	...
(25) 11	...	Plate, sheet, strip, bar	SB-152	...
(25) 12	...	Plate, sheet, strip, bar	SB-152	...
(25) 13	...	Plate, sheet, strip, bar	SB-152	...
(25) 14	...	Plate, sheet, strip, bar	SB-152	...
(25) 15	...	Plate, sheet, strip, bar	SB-152	...
(25) 16	...	Plate, sheet, strip, bar	SB-152	...
17	...	Smls. pipe	SB-42	...
18	...	Smls. tube	SB-75	...
19	...	Smls. cond. tube	SB-111	...
20	...	Smls. U-bend tube	SB-395	...
21	...	Smls. pipe	SB-42	...
22	...	Smls. tube	SB-75	...
23	...	Smls. cond. tube	SB-111	...
(25) 24	...	Plate, sheet, strip, bar	SB-152	...
(25) 25	...	Plate, sheet, strip, bar	SB-152	...
(25) 26	...	Plate, sheet, strip, bar	SB-152	...
(25) 27	...	Plate, sheet, strip, bar	SB-152	...
(25) 28	...	Plate, sheet, strip, bar	SB-152	...
(25) 29	...	Plate, sheet, strip, bar	SB-152	...
(25) 30	...	Plate, sheet, strip, bar	SB-152	...
(25) 31	...	Plate, sheet, strip, bar	SB-152	...
(25) 32	...	Plate, sheet, strip, bar	SB-152	...
(25) 33	...	Plate, sheet, strip, bar	SB-152	...
(25) 34	...	Plate, sheet, strip, bar	SB-152	...
(25) 35	...	Plate, sheet, strip, bar	SB-152	...
(25) 36	...	Plate, sheet, strip, bar	SB-152	...
(25) 37	...	Plate, sheet, strip, bar	SB-152	...
(25) 38	...	Plate, sheet, strip, bar	SB-152	...
(25) 39	...	Plate, sheet, strip, bar	SB-152	...
(25) 40	...	Plate, sheet, strip, bar	SB-152	...
(25) 41	...	Plate, sheet, strip, bar	SB-152	...
42	...	Bar	SB-187	...
43	...	Bar, rod	SB-187	...
44	...	Plate, sheet, strip, bar	SB-152	...
45	...	Plate, sheet, strip, bar	SB-152	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	A96063	T5	0.501-1.000	21
2	A96063	T6	≤1.000	30
3	A96063	T5 wld.	≤1.000	17
4	A96063	T6 wld.	≤1.000	17
5	A96063	O	...	16
6	AC-42000	...	...	20
7	AC-44300	F	...	35
8	C10200	O60	All	28
9	C10200	O60	All	30
10	C10200	O61	All	30
11	C10200	H00	...	30
12	C10200	H01	...	30
13	C10200	H02	...	30
14	C10200	H03	...	30
15	C10200	H04	...	30
16	C10200	M20, O25	...	30
17	C10200	H55	2 < NPS ≤ 12	36
18	C10200	H55	All	36
19	C10200	H55	...	36
20	C10200	H55	...	36
21	C10200	H80	$\frac{1}{8}$ < NPS ≤ 2	45
22	C10200	H80	<4	45
23	C10200	H80	...	45
24	C10400	H00	...	30
25	C10400	H01	...	30
26	C10400	H02	...	30
27	C10400	H03	...	30
28	C10400	H04	...	30
29	C10400	M20, O25	...	30
30	C10500	H00	...	30
31	C10500	H01	...	30
32	C10500	H02	...	30
33	C10500	H03	...	30
34	C10500	H04	...	30
35	C10500	M20, O25	...	30
36	C10700	H00	...	30
37	C10700	H01	...	30
38	C10700	H02	...	30
39	C10700	H03	...	30
40	C10700	H04	...	30
41	C10700	M20, O25	...	30
42	C11000	H04	All	28
43	C11000	O60	All	28
44	C11000	H00	...	30
45	C11000	H01	...	30

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	21.0	20.5	17.3	8.7	...	...	...	...	...	...	...	...	...	...
2	30.0	30.0	20.2	8.7	...	...	...	...	...	...	...	...	...	...
3	17.0	17.0	15.4	3.9	...	...	...	...	...	...	...	...	...	...
4	17.0	17.0	15.4	3.9	...	...	...	...	...	...	...	...	...	...
5	16.0	16.0	16.0	...	...	...	...	...	...	...	...	...	...	...
6	20.3	19.7	19.0	...	...	...	...	...	...	...	...	...	...	...
7	34.8	30.5	30.5	...	...	...	...	...	...	...	...	...	...	...
8	28.0	27.4	25.4	23.3	...	...	...	...	...	...	...	...	...	...
9	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
10	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
11	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
12	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
13	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
14	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
15	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
16	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
17	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
18	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
19	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
20	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
21	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
22	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
23	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
24	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
25	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
26	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
27	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
28	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
29	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
30	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
31	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
32	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
33	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
34	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
35	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
36	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
37	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
38	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
39	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
40	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
41	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
42	28.0	27.4	25.4	23.3	...	...	...	...	...	...	...	...	...	...
43	28.0	27.4	25.4	23.3	...	...	...	...	...	...	...	...	...	...
44	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
45	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Plate, sheet, strip, bar	SB-152	...
2	...	Plate, sheet, strip, bar	SB-152	...
3	...	Plate, sheet, strip, bar	SB-152	...
4	...	Plate, sheet, strip, bar	SB-152	...
5	...	Smls. tube	SB-75	...
6	...	Smls. tube	SB-75	...
7	...	Smls. pipe	SB-42	...
8	...	Smls. pipe	SB-42	...
9	...	Smls. tube	SB-75	...
10	...	Smls. cond. tube	SB-111	...
11	...	Smls. U-bend tube	SB-395	...
12	...	Smls. pipe	SB-42	...
13	...	Smls. tube	SB-75	...
14	...	Smls. cond. tube	SB-111	...
15	...	Smls. tube	SB-75	...
16	...	Smls. tube	SB-75	...
17	...	Smls. pipe	SB-42	...
18	...	Finned tube	SB-359	...
19	...	Wld. cond. tube	SB-543	...
20	...	Finned tube	SB-359	...
(25) 21	...	Plate, sheet, strip, bar	SB-152	...
(25) 22	...	Plate, sheet, strip, bar	SB-152	...
(25) 23	...	Plate, sheet, strip, bar	SB-152	...
(25) 24	...	Plate, sheet, strip, bar	SB-152	...
(25) 25	...	Plate, sheet, strip, bar	SB-152	...
(25) 26	...	Plate, sheet, strip, bar	SB-152	...
27	...	Wld. cond. tube	SB-543	...
28	...	Smls. pipe	SB-42	...
29	...	Smls. tube	SB-75	...
30	...	Smls. cond. tube	SB-111	...
31	...	Finned tube	SB-359	...
32	...	Smls. U-bend tube	SB-395	...
33	...	Smls. pipe	SB-42	...
34	...	Smls. cond. tube	SB-75	...
35	...	Smls. tube	SB-111	...
(25) 36	...	Finned tube	SB-359	...
37	...	Plate, sheet, strip, bar	SB-152	...
38	...	Plate, sheet, strip, bar	SB-152	...
39	...	Plate, sheet, strip, bar	SB-152	...
40	...	Plate, sheet, strip, bar	SB-152	...
41	...	Plate, sheet, strip, bar	SB-152	...
42	...	Plate, sheet, strip, bar	SB-152	...
(25) 43	...	Plate, sheet, strip, bar	SB-152	...
44	...	Smls. cond. tube	SB-111	...
45	...	Smls. U-bend tube	SB-395	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	C11000	H02	...	30
2	C11000	H03	...	30
3	C11000	H04	...	30
4	C11000	M20, O25	...	30
5	C12000	O50	All	30
6	C12000	O60	All	30
7	C12000	O61	All	30
8	C12000	H55	2 < NPS ≤ 12	36
9	C12000	H55	All	36
10	C12000	H55	...	36
11	C12000	H55	...	36
12	C12000	H80	$\frac{1}{8} < \text{NPS} \leq 2$	45
13	C12000	H80	<4	45
14	C12000	H80	...	45
15	C12200	O50	All	30
16	C12200	O60	All	30
17	C12200	O61	All	30
18	C12200	O61	...	30
19	C12200	W061	...	30
20	C12200	O62	...	30
21	C12200	H00	...	30
22	C12200	H01	...	30
23	C12200	H02	...	30
24	C12200	H03	...	30
25	C12200	H04	...	30
26	C12200	M20, O25	...	30
27	C12200	WC55	...	32
28	C12200	H55	2 < NPS ≤ 12	36
29	C12200	H55	All	36
30	C12200	H55	...	36
31	C12200	H55	...	36
32	C12200	H55	...	36
33	C12200	H80	$\frac{1}{8} < \text{NPS} \leq 2$	45
34	C12200	H80	<4	45
35	C12200	H80	...	45
36	C12200	H80	...	45
37	C12300	H00	...	30
38	C12300	H01	...	30
39	C12300	H02	...	30
40	C12300	H03	...	30
41	C12300	H04	...	30
42	C12300	M20, O25	...	30
43	C14200	M20, O25	...	30
44	C14200	H55	...	36
45	C14200	H55	...	36

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
2	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
3	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
4	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
5	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
6	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
7	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
8	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
9	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
10	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
11	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
12	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
13	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
14	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
15	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
16	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
17	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
18	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
19	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
20	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
21	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
22	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
23	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
24	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
25	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
26	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
27	32.0	32.0	31.0	29.3	...	...	...	...	...	...	...	...	...	...
28	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
29	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
30	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
31	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
32	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
33	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
34	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
35	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
36	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
37	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
38	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
39	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
40	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
41	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
42	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
43	30.0	29.4	27.2	25.0	...	...	...	...	...	...	...	...	...	...
44	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...
45	36.0	36.0	34.9	32.9	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Smls. cond. tube	SB-111	...
2	...	Smls. cond. tube	SB-111	...
3	...	Smls. U-bend tube	SB-395	...
4	...	Wld. cond. tube	SB-543	...
5	...	Wld. cond. tube	SB-543	...
6	...	Smls. pipe	SB-43	...
7	...	Smls. cond. tube	SB-111	...
8	...	Smls. tube	SB-135	...
9	...	Smls. U-bend tube	SB-395	...
10	...	Wld. cond. tube	SB-543	...
11	...	Smls. tube	SB-111	...
12	...	Plate	SB-171	...
13	...	Plate	SB-171	...
(25) 14	...	Plate, sheet	SB-171	...
(25) 15	...	Forgings	SB-283	...
(25) 16	...	Forgings	SB-283	...
(25) 17	...	Plate, sheet	SB-171	...
(25) 18	...	Plate, sheet	SB-171	...
19	...	Smls. cond. tube	SB-111	...
20	...	Finned tube	SB-359	...
21	...	Smls. U-bend tube	SB-395	...
22	...	Wld. cond. tube	SB-543	...
(25) 23	...	Plate, sheet	SB-171	...
(25) 24	...	Plate, sheet	SB-171	...
25	...	Smls. cond. tube	SB-111	...
26	...	Finned tube	SB-359	...
27	...	Smls. U-bend tube	SB-395	...
28	...	Wld. cond. tube	SB-543	...
(25) 29	...	Plate, sheet	SB-171	...
(25) 30	...	Plate, sheet	SB-171	...
31	...	Smls. cond. tube	SB-111	...
32	...	Finned tube	SB-359	...
33	...	Smls. U-bend tube	SB-395	...
34	...	Wld. cond. tube	SB-543	...
(25) 35	...	Plate, sheet	SB-171	...
(25) 36	...	Plate, sheet	SB-171	...
37	...	Smls. cond. tube	SB-111	...
38	...	Smls. U-bend tube	SB-395	...
(25) 39	...	Plate, sheet, bar	SB-169	...
40	...	Plate	SB-171	...
(25) 41	...	Plate, sheet, bar	SB-169	...
42	...	Plate	SB-171	...
(25) 43	...	Plate, sheet, bar	SB-169	...
44	...	Plate	SB-171	...
45	...	Bar, rod	SB-150	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	C14200	H80	...	45
2	C19200	O61	...	38
3	C19200	O61	...	38
4	C19400	W061	...	45
5	C19400	WC55	...	45
6	C23000	O61 and H58	...	40
7	C23000	O61	...	40
8	C23000	O50 and O60	...	40
9	C23000	O61	...	40
10	C23000	W061 and WC55	...	40
11	C28000	O25	...	50
12	C36500	O25 and M20	>3.5 to ≤ 5	40
13	C36500	O25 and M20	>2 to ≤ 3.5	45
14	C36500	O25 and M20	≤ 2	50
15	C37700	M10, O20	$>1\frac{1}{2}$	46
16	C37700	M10, O20	$\leq 1\frac{1}{2}$	50
17	C44300	M10, M20	≤ 4	45
18	C44300	O20, O25	≤ 4	45
19	C44300	O61	...	45
20	C44300	O61	...	45
21	C44300	O61	...	45
22	C44300	W061	...	45
23	C44400	M10, M20	≤ 4	45
24	C44400	O20, O25	≤ 4	45
25	C44400	O61	...	45
26	C44400	O61	...	45
27	C44400	O61	...	45
28	C44400	W061	...	45
29	C44500	M10, M20	≤ 4	45
30	C44500	O20, O25	≤ 4	45
31	C44500	O61	...	45
32	C44500	O61	...	45
33	C44500	O61	...	45
34	C44500	W061	...	45
35	C46400	M10, M20, O20, O25	≤ 5	50
36	C46500	M10, M20, O20, O25	≤ 5	50
37	C60800	O61	...	50
38	C60800	O61	...	50
39	C61400	M20, O25, O60	$2 < t \leq 5$	65
40	C61400	M10, M20, O20, O25	$2 < t \leq 5$	65
41	C61400	M20, O25, O60	$\frac{1}{2} < t \leq 2$	70
42	C61400	M10, M20, O20, O25	≤ 2	70
43	C61400	M20, O25, O60	$\leq \frac{1}{2}$	72
44	C63000	M10, M20, O20, O25	$3.5 < t \leq 5$	80
45	C63000	M20, M30	>4	80

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	45.0	45.0	43.9	38.2	...	...	...	...	...	...	...	...	...	...
2	38.0	35.9	32.6	29.7	...	...	...	...	...	...	...	...	...	...
3	38.0	35.9	32.6	29.7	...	...	...	...	...	...	...	...	...	...
4	45.0	45.0	41.7	38.6	...	...	...	...	...	...	...	...	...	...
5	45.0	45.0	41.7	38.6	...	...	...	...	...	...	...	...	...	...
6	40.0	40.0	40.0	39.6	36.4	...	...	...	...	...	...	...	...	...
7	40.0	40.0	40.0	39.6	36.4	...	...	...	...	...	...	...	...	...
8	40.0	40.0	40.0	39.6	36.4	...	...	...	...	...	...	...	...	...
9	40.0	40.0	40.0	39.6	36.4	...	...	...	...	...	...	...	...	...
10	40.0	40.0	40.0	39.6	36.4	...	...	...	...	...	...	...	...	...
11	50.0	50.0	50.0	48.9	...	...	...	...	...	...	...	...	...	...
12	40.0	40.0	40.0	39.1	...	...	...	...	...	...	...	...	...	...
13	45.0	45.0	45.0	44.0	...	...	...	...	...	...	...	...	...	...
14	50.0	50.0	50.0	48.9	...	...	...	...	...	...	...	...	...	...
15	46.0	45.2	42.5	36.8	29.1	...	...	...	...	...	...	...	...	...
16	50.0	49.1	46.2	40.0	31.7	...	...	...	...	...	...	...	...	...
17	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
18	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
19	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
20	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
21	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
22	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
23	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
24	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
25	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
26	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
27	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
28	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
29	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
30	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
31	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
32	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
33	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
34	45.0	44.8	43.8	42.1	...	...	...	...	...	...	...	...	...	...
35	50.0	50.0	50.0	47.7	43.4	...	...	...	...	...	...	...	...	...
36	50.0	50.0	50.0	47.7	43.4	...	...	...	...	...	...	...	...	...
37	50.0	50.0	50.0	47.3	38.5	...	...	...	...	...	...	...	...	...
38	50.0	50.0	50.0	47.3	38.5	...	...	...	...	...	...	...	...	...
39	65.0	65.0	65.0	63.7	59.4	...	...	...	...	...	...	...	...	...
40	65.0	65.0	65.0	63.7	59.4	...	...	...	...	...	...	...	...	...
41	70.0	70.0	70.0	68.6	63.9	...	...	...	...	...	...	...	...	...
42	70.0	70.0	70.0	68.6	63.9	...	...	...	...	...	...	...	...	...
43	72.0	72.0	72.0	70.6	65.8	...	...	...	...	...	...	...	...	...
44	80.0	80.0	80.0	80.0	80.0	70.1	60.5	48.8	...	...	...	...	...	...
45	80.0	80.0	80.0	80.0	80.0	70.1	60.5	48.8	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	(25)
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Bar, rod	SB-150	...
2	...	Bar, rod	SB-150	...
3	...	Plate	SB-171	...
4	...	Bar, rod	SB-150	...
5	...	Bar, rod	SB-150	...
6	...	Bar, rod	SB-150	...
(25) 7	...	Plate	SB-171	...
8	...	Bar, rod	SB-150	...
9	...	Bar, rod	SB-150	...
(25) 10	...	Forgings	SB-283	...
(25) 11	...	Forgings	SB-283	...
12	...	Bar, rod	SB-150	...
13	...	Bar, rod	SB-150	...
14	...	Bar, rod	SB-150	...
15	...	Bar, rod	SB-150	...
16	...	Bar, rod	SB-150	...
17	...	Bar, rod	SB-150	...
18	...	Bar, rod	SB-98	...
19	...	Bar, rod	SB-98	...
20	...	Rod	SB-98	...
21	...	Rod	SB-98	...
(25) 22	...	Plate, sheet, strip, bar	SB-96	...
(25) 23	...	Smls. pipe & tube	SB-315	...
24	...	Bar, rod	SB-98	...
(25) 25	...	Bar, rod	SB-98	...
26	...	Bar, rod	SB-98	...
(25) 27	...	Bar, rod	SB-98	...
(25) 28	...	Bar, rod	SB-98	...
(25) 29	...	Bar, rod	SB-98	...
30	...	Smls. cond. tube	SB-111	...
31	...	Smls. U-bend tube	SB-395	...
32	...	Wld. cond. tube	SB-543	...
33	...	Smls. cond. tube	SB-111	...
34	...	Wld. tube	SB-543	...
35	...	Smls. cond. tube	SB-111	...
36	...	Smls. pipe & tube	SB-466	...
37	...	Wld. pipe	SB-467	...
38	...	Bar, rod	SB-151	...
39	...	Plate, sheet	SB-171	...
40	...	Plate, sheet	SB-171	...
41	...	Smls. cond. tube	SB-111	...
42	...	Finned tube	SB-359	...
43	...	Smls. U-bend tube	SB-395	...
44	...	Wld. pipe	SB-467	...
45	...	Wld. tube	SB-543	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	C63000	O20, O25, O30	>4	80
2	C63000	HR50	>4	80
3	C63000	M10, M20, O20, O25	$2 < t \leq 3.5$	85
4	C63000	HR50	$2 < t \leq 4$	85
5	C63000	M20, M30	$2 < t \leq 4$	85
6	C63000	O20, O25, O30	$2 < t \leq 4$	85
7	C63000	M10, M20, O20, O25	≤ 2	90
8	C63000	HR50	$1 < t \leq 2$	90
9	C63000	HR50	$\frac{1}{2} < t \leq 1$	100
10	C64200	M10, O20	$>1\frac{1}{2}$	68
11	C64200	M10, O20	$\leq 1\frac{1}{2}$	70
12	C64200	M10, M20, M30	>4	70
13	C64200	M10, M20, M30	$3 < t \leq 4$	70
14	C64200	HR50	$2 < t \leq 3$	75
15	C64200	HR50	$1 < t \leq 2$	80
16	C64200	HR50	$\frac{1}{2} < t \leq 1$	85
17	C64200	HR50	$\leq \frac{1}{2}$	90
18	C65100	O60	All	40
19	C65100	H02	≤ 2	55
20	C65100	H06	$\frac{1}{2} < t \leq 1\frac{1}{2}$	75
21	C65100	H06	$t \leq \frac{1}{2}$	85
22	C65500	O61	≤ 2	50
23	C65500	O30, O61	...	50
24	C65500	O60	All	52
25	C65500	H01	All	55
26	C65500	H02	≤ 2	70
27	C66100	O60	All	52
28	C66100	H01	All	55
29	C66100	H02	≤ 2	70
30	C68700	O61	...	50
31	C68700	O61	...	50
32	C68700	W061	...	50
33	C70400	O61	...	38
34	C70400	W061	...	38
35	C70400	H55	...	40
36	C70600	O60	...	38
37	C70600	W061	$>4\frac{1}{2}$	38
38	C70600	O60	All	38
39	C70600	M10, M20	≤ 5	40
40	C70600	O20, O25	≤ 5	40
41	C70600	O61	...	40
42	C70600	O61	...	40
43	C70600	O61	...	40
44	C70600	W061	$\leq 4\frac{1}{2}$	40
45	C70600	W061	...	40

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	80.0	80.0	80.0	80.0	80.0	70.1	60.5	48.8	...	...	...	...	...	...
2	80.0	80.0	80.0	80.0	80.0	70.1	60.5	48.8	...	...	...	...	...	...
3	85.0	85.0	85.0	85.0	85.0	74.5	64.3	51.9	...	...	...	...	...	...
4	85.0	85.0	85.0	85.0	85.0	74.5	64.3	51.9	...	...	...	...	...	...
5	85.0	85.0	85.0	85.0	85.0	74.5	64.3	51.9	...	...	...	...	...	...
6	85.0	85.0	85.0	85.0	85.0	74.5	64.3	51.9	...	...	...	...	...	...
7	90.0	90.0	90.0	90.0	90.0	78.9	68.1	54.9	...	...	...	...	...	...
8	90.0	90.0	90.0	90.0	90.0	78.9	68.1	54.9	...	...	...	...	...	...
9	100.0	100.0	100.0	100.0	100.0	87.6	75.6	61.0	...	...	...	...	...	...
10	68.0	68.0	68.0	68.0	68.0	...	...	...	...	...	...	...	...	...
11	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...	...
12	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...	...
13	70.0	70.0	70.0	70.0	70.0	...	...	...	...	...	...	...	...	...
14	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...	...
15	80.0	80.0	80.0	80.0	80.0	...	...	...	...	...	...	...	...	...
16	85.0	85.0	85.0	85.0	85.0	...	...	...	...	...	...	...	...	...
17	90.0	90.0	90.0	90.0	90.0	...	...	...	...	...	...	...	...	...
18	40.0	40.0	40.0	40.0	36.8	...	...	...	...	...	...	...	...	...
19	55.0	55.0	55.0	52.1	45.0	...	...	...	...	...	...	...	...	...
20	75.0	75.0	75.0	71.1	66.0	...	...	...	...	...	...	...	...	...
21	85.0	85.0	85.0	80.6	74.8	...	...	...	...	...	...	...	...	...
22	50.0	50.0	50.0	47.5	42.9	...	...	...	...	...	...	...	...	...
23	50.0	50.0	50.0	47.5	42.9	...	...	...	...	...	...	...	...	...
24	52.0	52.0	52.0	49.4	44.6	...	...	...	...	...	...	...	...	...
25	55.0	55.0	55.0	54.9	50.2	...	...	...	...	...	...	...	...	...
26	70.0	70.0	70.0	70.0	67.1	...	...	...	...	...	...	...	...	...
27	52.0	52.0	52.0	49.4	44.6	...	...	...	...	...	...	...	...	...
28	55.0	55.0	55.0	54.9	50.2	...	...	...	...	...	...	...	...	...
29	70.0	70.0	70.0	70.0	67.1	...	...	...	...	...	...	...	...	...
30	50.0	50.0	50.0	50.0	49.7	46.8	...	...	...	...	...	...	...	...
31	50.0	50.0	50.0	50.0	49.7	46.8	...	...	...	...	...	...	...	...
32	50.0	50.0	50.0	50.0	49.7	46.8	...	...	...	...	...	...	...	...
33	38.0	38.0	36.7	34.9	33.7	32.9	...	...	...	...	...	...	...	...
34	38.0	38.0	36.7	34.9	33.7	32.9	...	...	...	...	...	...	...	...
35	40.0	40.0	38.6	36.8	35.5	34.7	...	...	...	...	...	...	...	...
36	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
37	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
38	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
39	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
40	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
41	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
42	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
43	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
44	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
45	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	(25)
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	(25)
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Finned wld. tube	SB-956	...
2	...	Wld. pipe	SB-467	...
3	...	Smls. tube	SB-111	...
4	...	Smls. pipe & tube	SB-466	...
5	...	Wld. tube	SB-543	...
6	...	Finned wld. tube	SB-956	...
7	...	Wld. pipe	SB-467	...
8	...	Smls. pipe & tube	SB-466	...
9	...	Wld. pipe	SB-467	...
10	...	Bar, rod	SB-151	...
11	...	Forgings	SB-283	...
12	...	Plate, sheet	SB-171	...
13	...	Forgings	SB-283	...
14	...	Plate, sheet	SB-171	...
15	...	Smls. cond. tube	SB-111	...
16	...	Finned tube	SB-359	...
17	...	Smls. U-bend tube	SB-395	...
18	...	Wld. pipe	SB-467	...
19	...	Wld. tube	SB-543	...
20	...	Finned wld. tube	SB-956	...
21	...	Forgings	SB-283	...
22	...	Wld. pipe	SB-467	...
23	...	Smls. tube	SB-111	...
24	...	Smls. pipe & tube	SB-466	...
25	...	Wld. tube	SB-543	...
26	...	Finned wld. tube	SB-956	...
27	...	Wld. pipe	SB-467	...
28	...	Smls. tube	SB-466	...
29	...	Smls. cond. tube	SB-111	...
30	...	Finned tube	SB-359	...
31	...	Smls. tube	SB-395	...
32	...	Wld. pipe	SB-467	...
33	...	Plate, sheet	SB-171	...
34	...	Plate, sheet	SB-171	...
35	...	Wld. pipe	SB-467	...
36	...	Smls. pipe & tube	SB-466	...
37	...	Smls. cond. tube	SB-111	...
38	...	Finned tube	SB-359	...
39	...	Smls. U-bend tube	SB-395	...
40	...	Wld. tube	SB-543	...
41	...	Finned wld. tube	SB-956	...
42	...	Smls. cond. tube	SB-111	...
43	...	Smls. U-bend tube	SB-395	...
44	...	Wld. pipe	SB-467	...
45	...	Forgings	SB-283	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	C70600	W061	...	40
2	C70600	WM50	$\leq 4\frac{1}{2}$	45
3	C70600	H55	...	45
4	C70600	H55	...	45
5	C70600	WC55	...	45
6	C70600	WC55	...	45
7	C70600	Wld. fr. cold rld. strip	$\leq 4\frac{1}{2}$	54
8	C70620	O60	...	38
9	C70620	W061	$> 4\frac{1}{2}$	38
10	C70620	O60	All	38
11	C70620	M10	> 6	40
12	C70620	M20	≤ 5	40
13	C70620	O20	...	40
14	C70620	O25	≤ 5	40
15	C70620	O61	...	40
16	C70620	O61	...	40
17	C70620	O61	...	40
18	C70620	W061	$\leq 4\frac{1}{2}$	40
19	C70620	W061	...	40
20	C70620	W061	...	40
21	C70620	M10	≤ 6	45
22	C70620	W061	$\leq 4\frac{1}{2}$	45
23	C70620	H55	...	45
24	C70620	H55	...	45
25	C70620	WC55	...	45
26	C70620	WC55	...	45
27	C70620	Wld. fr. cold rld. strip	$\leq 4\frac{1}{2}$	54
28	C71000	O60	...	45
29	C71000	O61	...	45
30	C71000	O61	...	45
31	C71000	O61	...	45
32	C71500	W061	$> 4\frac{1}{2}$	45
33	C71500	M10, M20, O20, O25	$2.5 < t \leq 5$	45
34	C71500	M10, M20, O20, O25	≤ 2.5	50
35	C71500	W061	$\leq 4\frac{1}{2}$	50
36	C71500	O60	...	52
37	C71500	O61	...	52
38	C71500	O61	...	52
39	C71500	O61	...	52
40	C71500	W061	...	52
41	C71500	W061	...	52
42	C71500	HR50	...	72
43	C71500	HR50	...	72
44	C71520	W061	$> 4\frac{1}{2}$	45
45	C71520	M10	> 6	45

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
2	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
3	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
4	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
5	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
6	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
7	54.0	53.4	49.3	46.3	44.6	44.0	...	...	...	...	...	...	...	...
8	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
9	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
10	38.0	37.6	34.7	32.6	31.4	30.9	...	...	...	...	...	...	...	...
11	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
12	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
13	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
14	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
15	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
16	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
17	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
18	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
19	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
20	40.0	39.6	36.5	34.3	33.0	32.6	...	...	...	...	...	...	...	...
21	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
22	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
23	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
24	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
25	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
26	45.0	44.5	41.1	38.6	37.1	36.6	...	...	...	...	...	...	...	...
27	54.0	53.4	49.3	46.3	44.6	44.0	...	...	...	...	...	...	...	...
28	45.0	45.0	43.8	42.5	41.4	40.0	39.2	38.2	37.0	35.5	...	...	...	...
29	45.0	45.0	43.8	42.5	41.4	40.0	39.2	38.2	37.0	35.5	...	...	...	...
30	45.0	45.0	43.8	42.5	41.4	40.0	39.2	38.2	37.0	35.5	...	...	...	...
31	45.0	45.0	43.8	42.5	41.4	40.0	39.2	38.2	37.0	35.5	...	...	...	...
32	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...
33	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...
34	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	...	...	...	...	...	...
35	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	...	...	...	...	...	...
36	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
37	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
38	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
39	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
40	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
41	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
42	72.0	72.0	72.0	70.0	68.0	66.3	65.4	64.4	63.0	...	...	...	...	...
43	72.0	72.0	72.0	70.0	68.0	66.3	65.4	64.4	63.0	...	...	...	...	...
44	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...
45	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	...	Forgings	SB-283	...
2	...	Plate, sheet	SB-171	...
3	...	Forgings	SB-283	...
4	...	Plate, sheet	SB-171	...
5	...	Wld. pipe	SB-467	...
6	...	Smls. pipe & tube	SB-466	...
7	...	Smls. cond. tube	SB-111	...
8	...	Finned tube	SB-359	...
9	...	Smls. pipe & tube	SB-395	...
10	...	Wld. tube	SB-543	...
11	...	Finned wld. tube	SB-956	...
12	...	Smls. cond. tube	SB-111	...
13	...	Smls. U-bend tube	SB-395	...
14	...	Smls. cond. tube	SB-111	...
15	...	Castings	SB-62	...
16	...	Castings	SB-61	...
17	...	Castings	SB-584	...
18	...	Castings	SB-584	...
19	...	Castings	SB-148	...
20	...	Castings	SB-271	...
21	...	Castings	SB-505	...
22	...	Castings	SB-148	...
23	...	Castings	SB-271	...
24	...	Castings	SB-148	...
25	...	Castings	SB-148	...
26	...	Castings	SB-369	...
27	...	Castings	SB-584	...
28	99Ni	Plate, sheet, strip	SB-162	...
29	99Ni	Smls. pipe & tube	SB-161	...
30	99Ni	Smls. tube	SB-163	...
31	99Ni-Low C	Smls. pipe & tube	SB-161	...
32	99Ni-Low C	Smls. & wld. ftgs.	SB-366	...
33	99Ni-Low C	Bar, rod	SB-160	...
34	99Ni-Low C	Smls. pipe & tube	SB-161	...
35	99Ni-Low C	Smls. tube	SB-163	...
36	99Ni-Low C	Plate, sheet, strip	SB-162	...
37	67Ni-30Cu	Bar	SB-164	...
38	67Ni-30Cu	Smls. pipe & tube	SB-165	...
39	67Ni-30Cu	Forgings	SB-564	...
40	67Ni-30Cu	Plate	SB-127	...
41	67Ni-30Cu	Smls. tube	SB-163	...
42	67Ni-30Cu	Smls. pipe & tube	SB-165	...
43	67Ni-30Cu	Smls. & wld. ftgs.	SB-366	...
44	67Ni-30Cu	Plate	SB-127	...
45	67Ni-30Cu	Rounds	SB-164	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	C71520	O20	...	45
2	C71520	O25	$2.5 < t \leq 5$	45
3	C71520	M10	≤ 6	50
4	C71520	O25	≤ 2.5	50
5	C71520	W061	$\leq 4\frac{1}{2}$	50
6	C71520	O60	...	52
7	C71520	O61	...	52
8	C71520	O61	...	52
9	C71520	O61	...	52
10	C71520	W061	...	52
11	C71520	W061	...	52
12	C71520	HR50	...	72
13	C71520	HR50	...	72
14	C72200	O61	...	45
15	C83600	M01	...	30
16	C92200	M01	...	34
17	C92200	M01	...	34
18	C93700	M01	...	30
19	C95200	M01	...	65
20	C95200	M02	...	65
21	C95200	M07	...	68
22	C95400	M01	...	75
23	C95400	M02	...	75
24	C95800	M01	...	85
25	C95820	M01	...	94
26	C96200	M01	...	45
27	C97600	M01	...	40
28	N02200	As rolled	...	55
29	N02200	Stress rel.	...	65
30	N02200	Stress rel.	...	65
31	N02201	Annealed	>5 O.D.	50
32	N02201	Annealed	...	50
33	N02201	Hot rolled/ann.	...	50
34	N02201	Annealed	≤ 5 O.D.	50
35	N02201	Annealed	...	50
36	N02201	Hot rolled/ann.	...	50
37	N04400	Annealed	...	70
38	N04400	Annealed	>5 O.D.	70
39	N04400	Annealed	...	70
40	N04400	Annealed	...	70
41	N04400	Annealed	≤ 3	70
42	N04400	Annealed	≤ 5 O.D.	70
43	N04400	Annealed	...	70
44	N04400	As rolled	...	75
45	N04400	Hot worked	$12 < t \leq 14$	75

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...
2	45.0	45.0	45.0	45.0	45.0	45.0	45.0	45.0	...	...	...	...	...	...
3	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	...	...	...	...	...	...
4	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	...	...	...	...	...	...
5	50.0	50.0	50.0	50.0	50.0	50.0	50.0	50.0	...	...	...	...	...	...
6	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
7	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
8	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
9	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
10	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
11	52.0	52.0	52.0	52.0	52.0	52.0	52.0	52.0	...	...	...	...	...	...
12	72.0	72.0	72.0	70.0	68.0	66.3	65.4	64.4	63.0	...	...	...	...	...
13	72.0	72.0	72.0	70.0	68.0	66.3	65.4	64.4	63.0	...	...	...	...	...
14	45.0	43.7	41.7	38.4	37.2	...	...	...	...	...	...	...	...	...
15	30.0	30.0	29.3	28.3	27.7	27.5	...	...	...	...	...	...	...	...
16	34.0	34.0	34.0	33.1	29.5	20.5	...	...	...	...	...	...	...	...
17	34.0	34.0	34.0	33.1	29.5	20.5	...	...	...	...	...	...	...	...
18	30.0	29.6	27.7	26.0	24.5	20.5	...	...	...	...	...	...	...	...
19	65.0	65.0	65.0	62.1	56.5	48.6	...	...	...	...	...	...	...	...
20	65.0	65.0	65.0	62.1	56.5	48.6	...	...	...	...	...	...	...	...
21	68.0	68.0	68.0	65.0	59.2	50.9	...	...	...	...	...	...	...	...
22	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...	...
23	75.0	75.0	75.0	75.0	75.0	...	...	...	...	...	...	...	...	...
24	85.0	84.8	80.2	76.8	...	...	...	...	...	...	...	...	...	...
25	94.0	93.7	88.7	84.9	81.7	...	...	...	...	...	...	...	...	...
26	45.0	44.8	41.0	38.8	37.3	...	...	...	...	...	...	...	...	...
27	40.0	39.5	38.5	...	...	...	...	...	...	...	...	...	...	...
28	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	55.0	...	...	...
29	65.0	65.0	65.0	65.0	64.1	61.8	59.8	...	...	...	...	...	...	...
30	65.0	65.0	65.0	65.0	64.1	61.8	59.8	...	...	...	...	...	...	...
31	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
32	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
33	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
34	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
35	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
36	50.0	50.0	50.0	49.8	47.8	45.6	44.4	43.2	42.2	40.8	38.4	35.9	33.3	30.7
37	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
38	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
39	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
40	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
41	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
42	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
43	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
44	75.0	75.0	75.0	75.0	75.0	75.0	74.9	72.3	69.0	65.1	60.8	56.6	53.1	50.8
45	75.0	75.0	75.0	75.0	75.0	75.0	74.9	72.3	69.0	65.1	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
32	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
33	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
34	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
35	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
36	28.3	26.0	24.1	22.7	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	67Ni-30Cu	Rounds	SB-164	...
2	67Ni-30Cu	Rounds	SB-164	...
3	67Ni-30Cu	Rounds	SB-164	...
4	67Ni-30Cu	Smls. tube	SB-163	...
5	67Ni-30Cu	Smls. pipe & tube	SB-165	...
6	67Ni-30Cu	Rounds	SB-164	...
7	67Ni-30Cu	Rounds	SB-164	...
8	67Ni-30Cu-S	Bar	SB-164	...
9	67Ni-30Cu-S	Bar	SB-164	...
10	67Ni-28Cu-3Al	Bolting	SF-468	...
11	47Ni-22Cr-9Mo-18Fe	Plate	SB-435	...
12	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...
13	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...
14	47Ni-22Cr-9Mo-18Fe	Smls. & wld. ftgs.	SB-366	...
15	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...
16	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...
17	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...
18	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...
19	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...
20	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...
21	47Ni-22Cr-19Fe-6Mo	Smls. & wld. ftgs.	SB-366	...
22	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...
23	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...
24	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...
25	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...
26	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...
27	55Ni-21Cr-13.5Mo	Smls. & wld. ftgs.	SB-366	...
28	55Ni-21Cr-13.5Mo	Forgings	SB-462	...
29	55Ni-21Cr-13.5Mo	Forgings	SB-564	...
30	55Ni-21Cr-13.5Mo	Rod	SB-574	...
31	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...
32	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...
33	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...
34	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...
35	60Ni-25Cr-9.5Fe-2.1Al	Smls. tube	SB-163	...
36	60Ni-25Cr-9.5Fe-2.1Al	Plate, sheet, strip	SB-168	...
37	60Ni-25Cr-9.5Fe-2.1Al	Wrought fittings	SB-366	...
38	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-462	...
39	60Ni-25Cr-9.5Fe-2.1Al	Wld. tube	SB-516	...
40	60Ni-25Cr-9.5Fe-2.1Al	Wld. pipe	SB-517	...
41	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-564	...
42	60Ni-25Cr-9.5Fe-2.1Al	Bar	SB-166	...
43	60Ni-25Cr-9.5Fe-2.1Al	Smls. pipe & tube	SB-167	...
44	40Ni-29Cr-15Fe-5Mo	Smls. & wld. ftgs.	SB-366	...
45	40Ni-29Cr-15Fe-5Mo	Forgings	SB-462	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N04400	Hot worked	$t \leq 12$	80
2	N04400	CW & SR	$t < \frac{1}{2}$	84
3	N04400	CW & SR	$3\frac{1}{2} < t \leq 4$	84
4	N04400	Stress rel.	...	85
5	N04400	Stress rel.	...	85
6	N04400	CW & SR	$\frac{1}{2} \leq t \leq 3\frac{1}{2}$	87
7	N04400	Cold worked	$t < \frac{1}{2}$	110
8	N04405	Annealed	...	70
9	N04405	Hot worked	...	75
10	N05500	Ann./aged	0.250–1.500	130
11	N06002	Annealed	$> \frac{3}{16}$	95
12	N06002	Solution ann.	$\leq \frac{3}{16}$	95
13	N06002	Annealed	...	95
14	N06002	Annealed	...	100
15	N06002	Annealed	$\frac{1}{16} < t \leq \frac{3}{16}$	100
16	N06002	Solution ann.	...	100
17	N06002	Solution ann.	...	100
18	N06002	Solution ann.	...	100
19	N06007	Solution ann.	$> \frac{3}{4}$	85
20	N06007	Solution ann.	$> \frac{3}{4}$	85
21	N06007	Annealed	...	90
22	N06007	Solution ann.	$\leq \frac{3}{4}$	90
23	N06007	Solution ann.	$\leq \frac{3}{4}$	90
24	N06007	Solution ann.	...	90
25	N06007	Solution ann.	...	90
26	N06007	Solution ann.	...	90
27	N06022	Solution ann.	...	100
28	N06022	Solution ann.	...	100
29	N06022	Solution ann.	...	100
30	N06022	Solution ann.	...	100
31	N06022	Solution ann.	...	100
32	N06022	Solution ann.	...	100
33	N06022	Solution ann.	...	100
34	N06022	Solution ann.	...	100
35	N06025	Annealed	...	98
36	N06025	Annealed	...	98
37	N06025	Annealed	...	98
38	N06025	Annealed	$t \leq 4$	98
39	N06025	Annealed	...	98
40	N06025	Annealed	...	98
41	N06025	Annealed	$t \leq 4$	98
42	N06025	HW or CW ann.	$t \leq 4$	98
43	N06025	HW or CW ann.	...	98
44	N06030	Solution ann.	...	85
45	N06030	Solution ann.	...	85

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	80.0	80.0	80.0	80.0	79.9	78.7	77.3	75.3	72.4	68.6	...	...	...	...
2	84.0	84.0	84.0	84.0	83.9	82.6	81.2	79.0	76.0	72.0	...	...	...	...
3	84.0	84.0	84.0	84.0	83.9	82.6	81.2	79.0	76.0	72.0	...	...	...	...
4	85.0	85.0	85.0	84.9	84.9	83.7	82.2	79.9	76.8	72.9	68.6	64.2	60.2	57.5
5	85.0	85.0	85.0	84.9	84.9	83.7	82.2	79.9	76.8	72.9	68.6	64.2	60.2	57.5
6	87.0	87.0	87.0	87.0	86.9	85.6	84.1	81.9	78.7	74.6	...	...	...	...
7	110.0	110.0	110.0	110.0	109.9	108.2	106.3	103.5	99.6	94.3	...	...	...	...
8	70.0	70.0	70.0	70.0	70.0	70.0	70.0	69.7	67.3	64.1	60.3	56.4	52.9	50.5
9	75.0	75.0	75.0	75.0	75.0	75.0	74.9	72.3	69.0	65.1	60.8	56.6	53.1	50.8
10	130.0	130.0	130.0	130.0	130.0	129.7	128.1	126.3	...	...	...	...	...	...
11	95.0	95.0	93.8	91.4	89.0	86.4	85.1	83.7	82.5	81.3	80.2	79.3	78.6	78.1
12	95.0	95.0	93.8	91.4	89.0	86.4	85.1	83.7	82.5	81.3	80.2	79.3	78.6	78.1
13	95.0	95.0	93.8	91.4	89.0	86.4	85.1	83.7	82.5	81.3	80.2	79.3	78.6	78.1
14	100.0	100.0	98.8	96.3	93.7	91.0	89.6	88.2	86.8	85.6	84.5	83.5	82.8	82.2
15	100.0	100.0	98.8	96.3	93.7	91.0	89.6	88.2	86.8	85.6	84.5	83.5	82.8	82.2
16	100.0	100.0	98.8	96.3	93.7	91.0	89.6	88.2	86.8	85.6	84.5	83.5	82.8	82.2
17	100.0	100.0	98.8	96.3	93.7	91.0	89.6	88.2	86.8	85.6	84.5	83.5	82.8	82.2
18	100.0	100.0	98.8	96.3	93.7	91.0	89.6	88.2	86.8	85.6	84.5	83.5	82.8	82.2
19	85.0	85.0	83.7	82.7	81.4	79.8	79.0	78.3	77.7	77.2	76.5	75.7	74.1	71.5
20	85.0	85.0	83.7	82.7	81.4	79.8	79.0	78.3	77.7	77.2	76.5	75.7	74.1	71.5
21	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
22	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
23	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
24	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
25	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
26	90.0	90.0	88.6	87.6	86.2	84.5	83.7	82.9	82.3	81.7	81.1	80.1	78.5	75.7
27	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
28	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
29	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
30	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
31	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
32	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
33	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
34	100.0	100.0	98.5	95.3	92.9	91.1	90.4	89.7	89.1	88.4	87.8	87.1	86.3	85.4
35	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
36	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
37	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
38	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
39	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
40	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
41	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
42	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
43	98.0	98.0	98.0	97.9	97.9	97.9	97.9	97.9	97.9	97.9	97.3	96.0	94.3	92.1
44	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
45	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	75.1	73.1	70.6	67.7	64.3	60.4	56.1	51.4	46.3	41.1	35.8	30.6	25.6
12	75.1	73.1	70.6	67.7	64.3	60.4	56.1	51.4	46.3	41.1	35.8	30.6	25.6
13	75.1	73.1	70.6	67.7	64.3	60.4	56.1	51.4	46.3	41.1	35.8	30.6	25.6
14	79.0	76.9	74.3	71.2	67.6	63.6	59.0	54.1	48.8	43.3	37.7	32.2	27.0
15	79.0	76.9	74.3	71.2	67.6	63.6	59.0	54.1	48.8	43.3	37.7	32.2	27.0
16	79.0	76.9	74.3	71.2	67.6	63.6	59.0	54.1	48.8	43.3	37.7	32.2	27.0
17	79.0	76.9	74.3	71.2	67.6	63.6	59.0	54.1	48.8	43.3	37.7	32.2	27.0
18	79.0	76.9	74.3	71.2	67.6	63.6	59.0	54.1	48.8	43.3	37.7	32.2	27.0
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
28	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
29	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
30	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
31	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
32	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
33	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
34	83.4	82.3	81.1	79.7	78.2	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	40Ni-29Cr-15Fe-5Mo	Rod	SB-581	...
2	40Ni-29Cr-15Fe-5Mo	Plate, sheet, strip	SB-582	...
3	40Ni-29Cr-15Fe-5Mo	Wld. pipe	SB-619	...
4	40Ni-29Cr-15Fe-5Mo	Smls. pipe & tube	SB-622	...
5	40Ni-29Cr-15Fe-5Mo	Wld. tube	SB-626	...
6	58Ni-33Cr-8Mo	Smls. & wld. ftgs.	SB-366	...
7	58Ni-33Cr-8Mo	Forgings	SB-462	...
8	58Ni-33Cr-8Mo	Forgings	SB-564	...
9	58Ni-33Cr-8Mo	Rod	SB-574	...
10	58Ni-33Cr-8Mo	Plate, sheet, strip	SB-575	...
11	58Ni-33Cr-8Mo	Wld. pipe	SB-619	...
12	58Ni-33Cr-8Mo	Smls. pipe & tube	SB-622	...
13	58Ni-33Cr-8Mo	Wld. tube	SB-626	...
14	46Ni-27Cr-23Fe-2.75Si	Rod	SB-166	...
15	46Ni-27Cr-23Fe-2.75Si	Smls. pipe & tube	SB-167	...
16	46Ni-27Cr-23Fe-2.75Si	Plate, sheet, strip	SB-168	...
17	46Ni-27Cr-23Fe-2.75Si	Smls. & wld. ftgs.	SB-366	...
18	46Ni-27Cr-23Fe-2.75Si	Wld. tube	SB-516	...
19	46Ni-27Cr-23Fe-2.75Si	Wld. pipe	SB-517	...
20	46Ni-27Cr-23Fe-2.75Si	Forgings	SB-564	...
21	59Ni-23Cr-16Mo	Fittings	SB-366	CR5923
22	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923
23	59Ni-23Cr-16Mo	Wld. fittings	SB-366	WP5923W
24	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923WX
25	59Ni-23Cr-16Mo	Forged fittings	SB-462	...
26	59Ni-23Cr-16Mo	Forgings	SB-564	...
27	59Ni-23Cr-16Mo	Rod	SB-574	...
28	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...
29	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...
30	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...
31	59Ni-23Cr-16Mo	Wld. tube	SB-626	...
32	59Ni-23Cr-16Mo-1.6Cu	Fittings	SB-366	...
33	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-462	...
34	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-564	...
35	59Ni-23Cr-16Mo-1.6Cu	Rod	SB-574	...
36	59Ni-23Cr-16Mo-1.6Cu	Plate, sheet, strip	SB-575	...
37	59Ni-23Cr-16Mo-1.6Cu	Wld. pipe	SB-619	...
38	59Ni-23Cr-16Mo-1.6Cu	Smls. pipe & tube	SB-622	...
39	59Ni-23Cr-16Mo-1.6Cu	Wld. tube	SB-626	...
40	60Ni-19Cr-19Mo-1.8Ta	Smls. & wld. ftgs.	SB-366	...
41	60Ni-19Cr-19Mo-1.8Ta	Forgings	SB-564	...
42	60Ni-19Cr-19Mo-1.8Ta	Rod	SB-574	...
43	60Ni-19Cr-19Mo-1.8Ta	Plate, sheet, strip	SB-575	...
44	60Ni-19Cr-19Mo-1.8Ta	Wld. pipe	SB-619	...
45	60Ni-19Cr-19Mo-1.8Ta	Smls. pipe & tube	SB-622	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N06030	Solution ann.	...	85
2	N06030	Solution ann.	...	85
3	N06030	Solution ann.	...	85
4	N06030	Solution ann.	...	85
5	N06030	Solution ann.	...	85
6	N06035	Solution ann.	...	85
7	N06035	Solution ann.	...	85
8	N06035	Solution ann.	...	85
9	N06035	Solution ann.	...	85
10	N06035	Solution ann.	...	85
11	N06035	Solution ann.	...	85
12	N06035	Solution ann.	...	85
13	N06035	Solution ann.	...	85
14	N06045	...	...	90
15	N06045	...	...	90
16	N06045	...	...	90
17	N06045	...	...	90
18	N06045	...	...	90
19	N06045	...	...	90
20	N06045	...	...	90
21	N06059	Annealed	...	100
22	N06059	Annealed	...	100
23	N06059	Annealed	...	100
24	N06059	Annealed	...	100
25	N06059	Solution ann.	...	100
26	N06059	Solution ann.	...	100
27	N06059	Solution ann.	...	100
28	N06059	Solution ann.	...	100
29	N06059	Solution ann.	...	100
30	N06059	Solution ann.	...	100
31	N06059	Solution ann.	...	100
32	N06200	Solution ann.	...	100
33	N06200	Solution ann.	...	100
34	N06200	Solution ann.	...	100
35	N06200	Solution ann.	...	100
36	N06200	Solution ann.	...	100
37	N06200	Solution ann.	...	100
38	N06200	Solution ann.	...	100
39	N06200	Solution ann.	...	100
40	N06210	Solution ann.	...	100
41	N06210	Solution ann.	...	100
42	N06210	Solution ann.	...	100
43	N06210	Solution ann.	...	100
44	N06210	Solution ann.	...	100
45	N06210	Solution ann.	...	100

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
2	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
3	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
4	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
5	85.0	85.0	81.5	78.8	76.7	75.0	74.3	73.6	73.0	72.4	71.7	70.9	69.9	68.5
6	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
7	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
8	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
9	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
10	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
11	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
12	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
13	85.0	85.0	83.7	79.6	76.7	74.8	74.0	73.3	72.6	71.8	70.9	69.8	68.6	67.2
14	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
15	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
16	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
17	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
18	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
19	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
20	90.0	90.0	87.1	82.3	79.1	77.2	76.6	76.0	75.4	74.8	74.0	72.9	71.6	70.1
21	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
22	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
23	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
24	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
25	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
26	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
27	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
28	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
29	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
30	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
31	100.0	100.0	100.0	97.9	94.4	91.2	89.7	88.3	87.1	86.1	85.3	84.7	84.2	83.8
32	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
33	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
34	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
35	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
36	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
37	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
38	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
39	100.0	100.0	100.0	96.7	93.7	91.7	91.0	90.2	89.3	88.3	87.2	86.0	84.9	84.1
40	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
41	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
42	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
43	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
44	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
45	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	60Ni-19Cr-19Mo-1.8Ta	Wld. tube	SB-626	...
2	57Ni-22Cr-14W-2Mo-La	Plate, sheet, strip	SB-435	...
3	57Ni-22Cr-14W-2Mo-La	Forgings	SB-564	...
4	57Ni-22Cr-14W-2Mo-La	Bar	SB-572	...
5	57Ni-22Cr-14W-2Mo-La	Wld. pipe	SB-619	...
6	57Ni-22Cr-14W-2Mo-La	Smls. pipe & tube	SB-622	...
7	57Ni-22Cr-14W-2Mo-La	Wld. tube	SB-626	...
8	61Ni-16Mo-16Cr	Smls. & wld. ftgs.	SB-366	...
9	61Ni-16Mo-16Cr	Rod	SB-574	...
10	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...
11	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...
12	61Ni-16Mo-16Cr	Smls. pipe & tube	SB-622	...
13	61Ni-16Mo-16Cr	Wld. tube	SB-626	...
14	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...
15	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...
16	72Ni-15Cr-8Fe	Smls. & wld. ftgs.	SB-366	...
17	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...
18	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...
19	72Ni-15Cr-8Fe	Smls. tube	SB-163	...
20	72Ni-15Cr-8Fe	Bar	SB-166	...
21	72Ni-15Cr-8Fe	Plate	SB-168	...
22	72Ni-15Cr-8Fe	Wld. tube	SB-516	...
23	72Ni-15Cr-8Fe	Forgings	SB-564	...
24	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...
25	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...
26	72Ni-15Cr-8Fe	Bar, rod	SB-166	...
27	72Ni-15Cr-8Fe	Plate, sheet, strip	SB-168	...
28	72Ni-15Cr-8Fe	Rounds	SB-166	...
29	72Ni-15Cr-8Fe	Rounds	SB-166	...
30	72Ni-15Cr-8Fe	Rounds	SB-166	...
31	60Ni-23Cr-Fe	Smls. tube	SB-163	...
32	60Ni-23Cr-Fe	Bar	SB-166	...
33	60Ni-23Cr-Fe	Smls. pipe & tube	SB-167	...
34	60Ni-23Cr-Fe	Plate, sheet, strip	SB-168	...
35	52Ni-22Cr-13Co-9Mo	Bar, rod	SB-166	...
36	52Ni-22Cr-13Co-9Mo	Smls. pipe & tube	SB-167	...
37	52Ni-22Cr-13Co-9Mo	Plate, sheet, strip	SB-168	...
38	52Ni-22Cr-13Co-9Mo	Forgings	SB-564	...
39	52Ni-22Cr-13Co-9Mo	Wld. tube	SB-626	...
40	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet, strip	SB-443	2
41	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe & tube	SB-444	2
42	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	2
43	60Ni-22Cr-9Mo-3.5Cb	Smls. & wld. ftgs.	SB-366	...
44	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1
45	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N06210	Solution ann.	...	100
2	N06230	Solution ann.	...	110
3	N06230	Solution ann.	...	110
4	N06230	Solution ann.	...	110
5	N06230	Solution ann.	...	110
6	N06230	Solution ann.	...	110
7	N06230	Solution ann.	...	110
8	N06455	Annealed	...	100
9	N06455	Solution ann.	...	100
10	N06455	Solution ann.	...	100
11	N06455	Solution ann.	...	100
12	N06455	Solution ann.	...	100
13	N06455	Solution ann.	...	100
14	N06600	Hot fin./ann.	>5	75
15	N06600	Hot fin./ann.	>5	80
16	N06600	Annealed	...	80
17	N06600	Cold drawn/ann.	>5	80
18	N06600	Hot fin./ann.	≤5	80
19	N06600	Annealed	≤3	80
20	N06600	Annealed	...	80
21	N06600	Annealed	...	80
22	N06600	Annealed	...	80
23	N06600	...	...	80
24	N06600	Cold drawn/ann.	≤5	80
25	N06600	Cold drawn/ann.	...	80
26	N06600	Hot fin.	...	85
27	N06600	Hot rolled	...	85
28	N06600	Hot worked	$t > 3$	85
29	N06600	Hot worked	$\frac{1}{2} < t \leq 3$	90
30	N06600	Hot worked	$\frac{1}{4} \leq t \leq \frac{1}{2}$	95
31	N06601	Annealed	≤3 O.D.	80
32	N06601	Annealed	...	80
33	N06601	Annealed	...	80
34	N06601	Annealed	...	80
35	N06617	Annealed	...	95
36	N06617	Annealed	...	95
37	N06617	Annealed	...	95
38	N06617	Annealed	...	95
39	N06617	Solution ann.	...	95
40	N06625	Solution ann.	...	100
41	N06625	Solution ann.	...	100
42	N06625	Solution ann.	...	100
43	N06625	Annealed	...	110
44	N06625	Annealed	$4 < t \leq 10$	110
45	N06625	Annealed	$4 < t \leq 10$	110

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	100.0	100.0	99.8	96.7	94.2	92.2	91.4	90.7	90.0	89.4	88.9	88.4	87.8	87.3
2	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
3	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
4	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
5	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
6	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
7	110.0	110.0	110.0	107.7	104.8	102.9	102.3	101.9	101.5	101.3	101.0	100.7	100.4	99.8
8	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
9	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
10	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
11	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
12	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
13	100.0	100.0	100.0	100.0	98.9	97.7	97.1	96.3	95.4	94.5	93.5	92.6	92.0	92.0
14	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	75.0	74.2	72.2	69.8
15	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	78.3	79.1	77.1
16	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1	74.5
17	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	78.3	79.1	77.1
18	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
19	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
20	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
21	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
22	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
23	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
24	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.1	77.1
25	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	80.0	75.3	77.1
26	85.0	85.0	85.0	85.0	85.0	85.0	85.0	85.0	85.0	85.0	85.0	...	85.0	83.0
27	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	...	85.0	83.0
28	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	...	...	...
29	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	90.0	...	...	...
30	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	95.0	...	...	...
31	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.7	79.2	78.6	77.8	76.7	75.5	73.9
32	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.7	79.2	78.6	77.8	76.7	75.5	73.9
33	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.7	79.2	78.6	77.8	76.7	75.5	73.9
34	80.0	80.0	80.0	80.0	80.0	80.0	80.0	79.7	79.2	78.6	77.8	76.7	75.5	73.9
35	95.0	95.0	95.0	95.0	95.0	93.2	92.3	91.4	90.6	89.9	89.2	88.5	87.8	87.1
36	95.0	95.0	95.0	95.0	95.0	93.2	92.3	91.4	90.6	89.9	89.2	88.5	87.8	87.1
37	95.0	95.0	95.0	95.0	95.0	93.2	92.3	91.4	90.6	89.9	89.2	88.5	87.8	87.1
38	95.0	95.0	95.0	95.0	95.0	93.2	92.3	91.4	90.6	89.9	89.2	88.5	87.8	87.1
39	95.0	95.0	95.0	95.0	95.0	93.2	92.3	91.4	90.6	89.9	89.2	88.5	87.8	87.1
40	100.0	100.0	100.0	100.0	99.5	99.3	99.3	99.3	99.3	99.3	99.3	99.2	98.5	97.3
41	100.0	100.0	100.0	100.0	99.5	99.3	99.3	99.3	99.3	99.3	99.3	99.2	98.5	97.3
42	100.0	100.0	100.0	100.0	99.5	99.3	99.3	99.3	99.3	99.3	99.3	99.2	98.5	97.3
43	110.0	110.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	107.0	106.0
44	110.0	110.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	107.0	106.0
45	110.0	110.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	107.0	106.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	67.0	63.6	59.8	55.5	...	...	...	...	...	...	...	...	...
15	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
16	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
17	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
18	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
19	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
20	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
21	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
22	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
23	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
24	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
25	71.4	67.9	63.8	59.2	...	...	...	...	...	...	...	...	...
26	76.0	71.6	66.5	61.0	...	...	...	...	...	...	...	...	...
27	76.0	71.6	66.5	61.0	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	95.5	93.2	90.3	86.6	82.3	77.3	71.6	65.4	58.6	51.4	44.0	...	...
41	95.5	93.2	90.3	86.6	82.3	77.3	71.6	65.4	58.6	51.4	44.0	...	...
42	95.5	93.2	90.3	86.6	82.3	77.3	71.6	65.4	58.6	51.4	44.0	...	...
43	104.0	102.0	98.4	94.1	89.1	83.2	76.5	69.1	61.1	52.7	44.0	...	...
44	104.0	102.0	98.4	94.1	89.1	83.2	76.5	69.1	61.1	52.7	44.0	...	...
45	104.0	102.0	98.4	94.1	89.1	83.2	76.5	69.1	61.1	52.7	44.0	...	...

(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	60Ni-22Cr-9Mo-3.5Cb	Plate	SB-443	1
2	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	1
3	60Ni-22Cr-9Mo-3.5Cb	Sheet, strip	SB-443	1
4	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe	SB-444	1
5	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1
(25) 6	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1
7	60Ni-22Cr-9Mo-3.5Cb	Wld. tube	SB-704	...
8	60Ni-22Cr-9Mo-3.5Cb	Wld. pipe	SB-705	...
9	Ni-Cr-Mo-W	Forgings	SB-564	...
10	Ni-Cr-Mo-W	Rod	SB-574	...
11	Ni-Cr-Mo-W	Plate, sheet, strip	SB-575	...
12	Ni-Cr-Mo-W	Wld. pipe	SB-619	...
13	Ni-Cr-Mo-W	Smls. pipe & tube	SB-622	...
14	Ni-Cr-Mo-W	Wld. tube	SB-626	...
15	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...
16	58Ni-29Cr-9Fe	Smls. tube	SB-163	...
17	58Ni-29Cr-9Fe	Bar, rod	SB-166	...
18	58Ni-29Cr-9Fe	Plate, sheet, strip	SB-168	...
19	58Ni-29Cr-9Fe	Forgings	SB-564	...
20	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...
21	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...
22	49Ni-25Cr-18Fe-6Mo	Plate, sheet, strip	SB-582	...
23	49Ni-25Cr-18Fe-6Mo	Wld. pipe	SB-619	...
24	49Ni-25Cr-18Fe-6Mo	Smls. pipe & tube	SB-622	...
25	49Ni-25Cr-18Fe-6Mo	Wld. tube	SB-626	...
26	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...
27	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...
28	47Ni-22Cr-20Fe-7Mo	Smls. & wld. ftgs.	SB-366	...
29	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...
30	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...
31	47Ni-22Cr-20Fe-7Mo	Wld. pipe	SB-619	...
32	47Ni-22Cr-20Fe-7Mo	Smls. pipe & tube	SB-622	...
33	47Ni-22Cr-20Fe-7Mo	Wld. tube	SB-626	...
34	35Ni-35Fe-20Cr-Cb	Forgings	SB-462	...
35	35Ni-35Fe-20Cr-Cb	Plate	SB-463	...
36	35Ni-35Fe-20Cr-Cb	Bar	SB-473	...
37	35Ni-35Fe-20Cr-Cb	Smls. pipe & tube	SB-729	...
38	35Ni-35Fe-20Cr-Cb	Wld. pipe	SB-464	...
39	35Ni-35Fe-20Cr-Cb	Wld. tube	SB-468	...
40	35Ni-35Fe-20Cr-Cb	Smls. & wld. ftgs.	SB-366	...
41	37Ni-33Fe-23Cr-4Mo-Cu	Wld. pipe	SB-464	...
42	37Ni-33Fe-23Cr-4Mo-Cu	Wld. tube	SB-468	...
43	35Ni-30Fe-24Cr-6Mo-Cu	Wld. pipe	SB-464	...
44	35Ni-30Fe-24Cr-6Mo-Cu	Wld. tube	SB-468	...
45	31Ni-31Fe-29Cr-Mo	Smls. tube	SB-668	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N06625	Cold rolled/ann.	≤0.375	110
2	N06625	Hot rolled/ann.	≤2.75	110
3	N06625	Cold rolled/ann.	...	120
4	N06625	Annealed	...	120
5	N06625	Annealed	≤4	120
6	N06625	Annealed	≤4	120
7	N06625	Annealed	...	120
8	N06625	Annealed	...	120
9	N06686	Solution ann.	...	100
10	N06686	Solution ann.	...	100
11	N06686	Solution ann.	...	100
12	N06686	Solution ann.	...	100
13	N06686	Solution ann.	...	100
14	N06686	Solution ann.	...	100
15	N06690	Hot worked/ann.	>5 O.D.	75
16	N06690	Annealed	...	85
17	N06690	Annealed	...	85
18	N06690	Annealed	...	85
19	N06690	Annealed	...	85
20	N06690	Cold worked/ann.	...	85
21	N06690	Hot worked/ann.	≤5 O.D.	85
22	N06975	Solution ann.	...	85
23	N06975	Solution ann.	...	85
24	N06975	Solution ann.	...	85
25	N06975	Solution ann.	...	85
26	N06985	Annealed	> ³ / ₄	85
27	N06985	Annealed	> ³ / ₄	85
28	N06985	Annealed	...	90
29	N06985	Annealed	≤ ³ / ₄	90
30	N06985	Annealed	≤ ³ / ₄	90
31	N06985	Annealed	...	90
32	N06985	Annealed	...	90
33	N06985	Annealed	...	90
34	N08020	Annealed	...	80
35	N08020	Annealed	...	80
36	N08020	Annealed	...	80
37	N08020	Annealed	...	80
38	N08020	Wld. ann.	...	80
39	N08020	Wld. ann.	...	80
40	N08020	Annealed	...	85
41	N08024	Wld. ann.	...	80
42	N08024	Wld. ann.	...	80
43	N08026	Wld. ann.	...	80
44	N08026	Wld. ann.	...	80
45	N08028	Annealed	...	73

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	110	110	110	108	106	104	103	102	101	100	99.2	98.2	97.1	95.9
2	110.0	110.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	108.0	107.0	106.0
3	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
4	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
5	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
6	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
7	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
8	120.0	120.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	118.0	117.0	116.0
9	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
10	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
11	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
12	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
13	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
14	100.0	100.0	98.8	95.3	92.7	90.8	89.9	89.1	88.2	87.1	85.9	84.5	82.8	80.9
15	75.0	75.0	73.8	72.5	71.4	70.7	70.5	70.3	70.2	69.9	69.5	68.9	67.9	66.4
16	85.0	85.0	84.0	82.0	80.8	80.2	80.0	79.8	79.6	79.3	78.7	78.0	76.9	75.3
17	85.0	85.0	84.0	82.0	80.8	80.2	80.0	79.8	79.6	79.3	78.7	78.0	76.9	75.3
18	85.0	85.0	84.0	82.0	80.8	80.2	80.0	79.8	79.6	79.3	78.7	78.0	76.9	75.3
19	85.0	85.0	84.0	82.0	80.8	80.2	80.0	79.8	79.6	79.3	78.7	78.0	76.9	75.3
20	85.0	84.9	83.7	82.2	81.0	80.2	79.9	79.7	79.5	79.2	78.8	78.1	76.9	75.2
21	85.0	84.9	83.7	82.2	81.0	80.2	79.9	79.7	79.5	79.2	78.8	78.1	76.9	75.2
22	85.0	85.0	85.0	83.5	81.7	80.3	79.7	79.1	78.5	78.0	77.3	76.6	75.7	74.4
23	85.0	85.0	85.0	83.5	81.7	80.3	79.7	79.1	78.5	78.0	77.3	76.6	75.7	74.4
24	85.0	85.0	85.0	83.5	81.7	80.3	79.7	79.1	78.5	78.0	77.3	76.6	75.7	74.4
25	85.0	85.0	85.0	83.5	81.7	80.3	79.7	79.1	78.5	78.0	77.3	76.6	75.7	74.4
26	85.0	85.0	83.8	80.4	77.9	76.2	75.6	75.0	74.4	73.8	73.0	72.1	70.9	69.5
27	85.0	85.0	83.8	80.4	77.9	76.2	75.6	75.0	74.4	73.8	73.0	72.1	70.9	69.5
28	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
29	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
30	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
31	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
32	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
33	90.0	90.0	88.7	85.1	82.5	80.7	80.0	79.4	78.8	78.1	77.3	76.3	75.1	73.6
34	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
35	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
36	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
37	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
38	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
39	80.0	80.0	79.2	77.6	77.3	77.3	77.0	76.7	76.3	76.3	...	...	...	...
40	85.0	85.0	84.1	82.4	82.2	82.1	81.9	81.5	81.1	81.1	...	...	...	...
41	80.0	80.0	79.0	76.8	74.8	72.9	72.1	71.4	70.8	70.3	69.9	69.5	69.2	68.6
42	80.0	80.0	79.0	76.8	74.8	72.9	72.1	71.4	70.8	70.3	69.9	69.5	69.2	68.6
43	80.0	80.0	78.6	76.2	74.1	72.1	71.1	70.1	69.1	68.1	67.2	66.4	65.7	65.0
44	80.0	80.0	78.6	76.2	74.1	72.1	71.1	70.1	69.1	68.1	67.2	66.4	65.7	65.0
45	73.0	73.0	70.4	67.6	65.4	63.6	62.9	62.1	61.4	60.7	59.9	59.0	58.1	57.1

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	104.0	102.0	98.4	94.1	89.1	83.2	76.5	69.1	61.1	52.7	44.0	...	...
3	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
4	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
5	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
6	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
7	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
8	114.0	111.0	107.0	103.0	97.2	90.7	83.4	75.4	66.7	57.5	48.0	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	31Ni-31Fe-29Cr-Mo	Plate, sheet, strip	SB-709	...
2	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. & wld. ftgs.	SB-366	...
3	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forgings	SB-564	...
4	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Rod	SB-581	...
5	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. pipe	SB-619	...
6	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. pipe & tube	SB-622	...
7	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Plate, sheet, strip	SB-625	...
8	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. tube	SB-626	...
9	37Ni-33Fe-25Cr	Condenser tube	SB-163	...
10	37Ni-33Fe-25Cr	Smls. & wld. ftgs.	SB-366	...
11	37Ni-33Fe-25Cr	Smls. pipe & tube	SB-407	...
12	37Ni-33Fe-25Cr	Bar, rod	SB-408	...
13	37Ni-33Fe-25Cr	Plate, sheet, strip	SB-409	...
14	37Ni-33Fe-25Cr	Wld. pipe	SB-514	...
15	37Ni-33Fe-25Cr	Wld. tube	SB-515	...
16	37Ni-33Fe-25Cr	Forgings	SB-564	...
17	26Ni-43Fe-22Cr-5Mo	Wld. pipe	SB-619	...
18	26Ni-43Fe-22Cr-5Mo	Plate, sheet, strip	SB-620	...
19	26Ni-43Fe-22Cr-5Mo	Rod	SB-621	...
20	26Ni-43Fe-22Cr-5Mo	Smls. pipe & tube	SB-622	...
21	26Ni-43Fe-22Cr-5Mo	Wld. tube	SB-626	...
22	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...
23	35Ni-19Cr-1 $\frac{1}{4}$ Si	Pipe	SB-535	...
24	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate	SB-536	...
25	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. ftgs.	SB-366	...
26	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. pipe	SB-535	...
27	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate, sheet, strip	SB-536	...
28	35Ni-19Cr-1 $\frac{1}{4}$ Si	Wld. pipe	SB-710	...
29	35Ni-23Cr-7.5Mo-N	Plate, sheet, strip	SB-625	...
30	35Ni-23Cr-7.5Mo-N	Bar, wire	SB-649	...
31	35Ni-23Cr-7.5Mo-N	Wld. pipe	SB-673	...
32	35Ni-23Cr-7.5Mo-N	Wld. tube	SB-674	...
33	35Ni-23Cr-7.5Mo-N	Smls. pipe & tube	SB-677	...
34	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-462	...
35	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-564	...
36	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...
37	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...
38	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...
39	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...
40	46Fe-24Ni-21Cr-6Mo-N	Bar, rod, wire	SB-691	...
41	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...
42	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...
43	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...
44	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...
45	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N08028	Annealed	...	73
2	N08031	...	...	94
3	N08031	...	...	94
4	N08031	...	...	94
5	N08031	...	...	94
6	N08031	...	...	94
7	N08031	...	...	94
8	N08031	...	...	94
9	N08120	Solution ann.	...	90
10	N08120	Solution ann.	...	90
11	N08120	Solution ann.	...	90
12	N08120	Solution ann.	...	90
13	N08120	Solution ann.	...	90
14	N08120	Solution ann.	...	90
15	N08120	Solution ann.	...	90
16	N08120	Solution ann.	...	90
17	N08320	Solution ann.	...	75
18	N08320	Solution ann.	...	75
19	N08320	Solution ann.	...	75
20	N08320	Solution ann.	...	75
21	N08320	Solution ann.	...	75
22	N08330	...	...	70
23	N08330	...	...	70
24	N08330	...	...	70
25	N08330	Annealed	...	70
26	N08330	Annealed	...	70
27	N08330	Annealed	...	70
28	N08330	Annealed	...	70
29	N08354	Solution ann.	...	95
30	N08354	Solution ann.	...	95
31	N08354	Solution ann.	...	95
32	N08354	Solution ann.	...	95
33	N08354	Solution ann.	...	95
34	N08367	Solution ann.	...	95
35	N08367	Solution ann.	...	95
36	N08367	Solution ann.	$> \frac{3}{16}$	95
37	N08367	Solution ann.	$> \frac{3}{16}$	95
38	N08367	Solution ann.	$> \frac{3}{16}$	95
39	N08367	Solution ann.	$> \frac{3}{16}$	95
40	N08367	Solution ann.	...	95
41	N08367	Solution ann.	$> \frac{3}{16}$	95
42	N08367	Solution ann.	$\leq \frac{3}{16}$	100
43	N08367	Solution ann.	$\leq \frac{3}{16}$	100
44	N08367	Solution ann.	$\leq \frac{3}{16}$	100
45	N08367	Solution ann.	$\leq \frac{3}{16}$	100

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	73.0	73.0	70.4	67.6	65.4	63.6	62.9	62.1	61.4	60.7	59.9	59.0	58.1	57.1
2	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
3	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
4	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
5	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
6	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
7	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
8	94.0	94.0	90.5	85.8	81.6	78.1	76.7	75.6	74.7	74.0	73.2	72.2	...	...
9	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
10	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
11	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
12	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
13	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
14	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
15	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
16	90.0	90.0	87.5	84.7	83.1	82.2	82.0	81.8	81.6	81.3	80.9	80.3	79.5	78.3
17	75.0	75.0	74.2	71.7	70.4	70.0	69.9	69.9	69.8	69.5	...	...	...	...
18	75.0	75.0	74.2	71.7	70.4	70.0	69.9	69.9	69.8	69.5	...	...	...	...
19	75.0	75.0	74.2	71.7	70.4	70.0	69.9	69.9	69.8	69.5	...	...	...	...
20	75.0	75.0	74.2	71.7	70.4	70.0	69.9	69.9	69.8	69.5	...	...	...	...
21	75.0	75.0	74.2	71.7	70.4	70.0	69.9	69.9	69.8	69.5	...	...	...	...
22	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
23	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
24	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
25	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
26	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
27	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
28	70.0	70.0	70.0	68.6	68.0	68.0	68.0	68.0	68.0	68.0	68.0	67.9	66.7	64.9
29	92.8	92.8	87.5	83.4	80.6	78.8	78.1	77.4	76.7	76.0	...	...	...	...
30	92.8	92.8	87.5	83.4	80.6	78.8	78.1	77.4	76.7	76.0	...	...	...	...
31	92.8	92.8	87.5	83.4	80.6	78.8	78.1	77.4	76.7	76.0	...	...	...	...
32	92.8	92.8	87.5	83.4	80.6	78.8	78.1	77.4	76.7	76.0	...	...	...	...
33	92.8	92.8	87.5	83.4	80.6	78.8	78.1	77.4	76.7	76.0	...	...	...	...
34	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
35	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
36	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
37	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
38	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
39	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
40	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
41	95.0	95.0	89.8	85.9	83.3	81.5	80.8	80.2	79.7	79.2	78.7	78.0	...	...
42	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
43	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
44	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
45	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
23	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
24	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
25	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
26	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
27	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
28	62.2	59.5	56.4	52.9	49.1	44.9	40.5	35.9	31.3	26.9	22.7	19.0	16.1
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...
2	46Fe-24Ni-21Cr-6Mo-N	Castings	SA-351	CN3MN
3	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SB-599	...
4	25Ni-47Fe-21Cr-5Mo	Bar, wire	SB-672	...
5	32Ni-45Fe-20Cr-Cb	Castings	SA-351	CT15C
6	33Ni-42Fe-21Cr	Smls. tube	SB-163	...
7	33Ni-42Fe-21Cr	Smls. & wld. ftgs.	SB-366	...
8	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...
9	33Ni-42Fe-21Cr	Bar	SB-408	...
10	33Ni-42Fe-21Cr	Plate	SB-409	...
11	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...
12	33Ni-42Fe-21Cr	Wld. tube	SB-515	...
13	33Ni-42Fe-21Cr	Forgings	SB-564	...
14	33Ni-42Fe-21Cr	Smls. tube	SB-163	...
15	32Ni-44Fe-21Cr	Smls. tube	SB-163	...
16	32Ni-44Fe-21Cr	Smls. pipe & tube	SB-407	...
17	33Ni-42Fe-21Cr	Smls. tube	SB-163	...
18	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...
19	33Ni-42Fe-21Cr	Bar	SB-408	...
20	33Ni-42Fe-21Cr	Plate	SB-409	...
21	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...
22	33Ni-42Fe-21Cr	Wld. tube	SB-515	...
23	33Ni-42Fe-21Cr	Forgings	SB-564	...
(25) 24	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10
(25) 25	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H
(25) 26	42Fe-33Ni-21Cr	Plate	SA-240	800H
(25) 27	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H
(25) 28	42Fe-33Ni-21Cr	Bar	SA-276	800H
(25) 29	42Fe-33Ni-21Cr	Smls. pipe	SA-312	800H
(25) 30	42Fe-33Ni-21Cr	Wld. pipe	SA-312	800H
(25) 31	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H
(25) 32	42Fe-33Ni-21Cr	Bar	SA-479	800H
(25) 33	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H
(25) 34	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10
35	33Ni-42Fe-21Cr	Smls. tube	SB-163	...
36	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...
37	33Ni-42Fe-21Cr	Bar	SB-408	...
38	32Ni-44Fe-21Cr	Plate	SB-409	...
39	33Ni-42Fe-21Cr	Wld. tube	SB-515	...
40	33Ni-42Fe-21Cr	Forgings	SB-564	...
41	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...
42	42Ni-21.5Cr-3Mo-2.3Cu	Smls. & wld. ftgs.	SB-366	...
43	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...
44	42Ni-21.5Cr-3Mo-2.3Cu	Plate	SB-424	...
45	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N08367	Solution ann.	$\leq 3/16$	100
2	J94651	Solution ann.	...	80
3	N08700	Solution ann.	...	80
4	N08700	Solution ann.	...	80
5	...	As cast	...	63
6	N08800	Annealed	...	75
7	N08800	Annealed	...	75
8	N08800	Annealed	...	75
9	N08800	Annealed	...	75
10	N08800	Annealed	...	75
11	N08800	Annealed	...	75
12	N08800	Annealed	...	75
13	N08800	Annealed	...	75
14	N08800	Cold worked	...	83
15	N08801	Ann./stabilized	...	65
16	N08801	Ann./stabilized	...	65
17	N08810	Annealed	...	65
18	N08810	Annealed	...	65
19	N08810	Annealed	...	65
20	N08810	Annealed	...	65
21	N08810	Annealed	...	65
22	N08810	Annealed	...	65
23	N08810	Annealed	...	65
24	N08810	...	...	65
25	N08810	...	...	65
26	N08810	...	...	65
27	N08810	...	...	65
28	N08810	...	...	65
29	N08810	...	...	65
30	N08810	...	...	65
31	N08810	...	...	65
32	N08810	...	...	65
33	N08810	...	...	65
34	N08810	...	...	65
35	N08811	Annealed	...	65
36	N08811	Annealed	...	65
37	N08811	Annealed	...	65
38	N08811	Annealed	...	65
39	N08811	Annealed	...	65
40	N08811	Annealed	...	65
41	N08825	Annealed	...	85
42	N08825	Annealed	...	85
43	N08825	Cold worked/ann.	...	85
44	N08825	Annealed	...	85
45	N08825	Annealed	...	85

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	100.0	100.0	94.5	90.5	87.7	85.8	85.1	84.4	83.9	83.4	82.8	82.2	...	...
2	80.0	75.5	69.6	65.7	63.0	60.8	59.8	58.9	58.0	57.2	56.5	55.9	55.3	54.8
3	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
4	80.0	80.0	79.2	77.2	75.2	75.0	74.8	...	...	...	...	...	...	...
5	63.0	63.0	63.0	63.0	63.0	63.0	63.0	63.0	63.0	63.0	63.0	...	...	...
6	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
7	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
8	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
9	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
10	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
11	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
12	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
13	75.0	75.0	75.0	75.0	74.7	74.6	74.6	74.5	74.2	73.9	73.3	72.5	71.4	70.0
14	83.0	83.0	83.0	82.5	80.7	80.0	79.9	...	...	...	...	...	...	...
15	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
16	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
17	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
18	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
19	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
20	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
21	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
22	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
23	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
24	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
25	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
26	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
27	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
28	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
29	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
30	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
31	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
32	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
33	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
34	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
35	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
36	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
37	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
38	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
39	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
40	65.0	65.0	65.0	64.6	64.0	63.8	63.8	63.8	63.8	63.8	63.8	63.6	63.1	62.3
41	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
42	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
43	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
44	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
45	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
7	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
8	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
9	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
10	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
11	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
12	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
13	66.0	62.3	57.9	53.0	47.7	42.3	36.9	32.0	28.1	25.6	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
18	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
19	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
20	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
21	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
22	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
23	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
24	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
25	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
26	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
27	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
28	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
29	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
30	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
31	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
32	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
33	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
34	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0 (25)
35	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
36	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
37	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
38	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
39	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
40	60.0	57.7	55.1	52.2	49.0	45.5	41.8	38.0	34.1	30.2	26.3	22.5	19.0
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	42Ni-21.5Cr-3Mo-2.3Cu	Forgings	SB-564	...
2	42Ni-21.5Cr-3Mo-2.3Cu	Wld. tube	SB-704	...
3	42Ni-21.5Cr-3Mo-2.3Cu	Wld. pipe	SB-705	...
4	44Fe-25Ni-21Cr-Mo	Forgings	SA-182	...
5	44Fe-25Ni-21Cr-Mo	Plate, sheet, strip	SA-240	...
6	44Fe-25Ni-21Cr-Mo	Wld. tube	SA-249	...
7	44Fe-25Ni-21Cr-Mo	Smls. & wld. pipe	SA-312	...
8	44Fe-25Ni-21Cr-Mo	Smls. tube	SA-213	...
9	44Fe-25Ni-21Cr-Mo	Fittings	SA-403	...
10	44Fe-25Ni-21Cr-Mo	Bar	SA-479	...
11	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SB-625	...
12	25Ni-20Cr-6Mo-Cu-N	Bar, wire	SB-649	...
13	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SB-673	...
14	25Ni-20Cr-6Mo-Cu-N	Wld. tube	SB-674	...
15	25Ni-20Cr-6Mo-Cu-N	Smls. pipe & tube	SB-677	...
(25) 16	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SA-240	...
(25) 17	25Ni-20Cr-6Mo-Cu-N	Bar	SA-276	...
(25) 18	25Ni-20Cr-6Mo-Cu-N	Bar	SA-479	...
(25) 19	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SA-312	...
(25) 20	25Ni-20Cr-6Mo-Cu-N	Smls. pipe	SA-312	...
(25) 21	25Ni-20Cr-6Mo-Cu-N	Smls. tube	SA-213	...
22	62Ni-28Mo-5Fe	Plate	SB-333	...
23	62Ni-28Mo-5Fe	Smls. & wld. ftgs.	SB-366	...
24	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...
25	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...
26	62Ni-28Mo-5Fe	Wld. tube	SB-626	...
27	62Ni-28Mo-5Fe	Rod	SB-335	...
28	62Ni-28Mo-5Fe	Sheet, strip	SB-333	...
29	70Ni-16Mo-7Cr-5Fe	Smls. & wld. ftgs.	SB-366	...
30	70Ni-16Mo-7Cr-5Fe	Plate, sheet, strip	SB-434	...
31	70Ni-16Mo-7Cr-5Fe	Rod	SB-573	...
32	62Ni-25Mo-8Cr-2Fe	Smls. & wld. ftgs.	SB-366	...
33	62Ni-25Mo-8Cr-2Fe	Plate, sheet, strip	SB-434	...
34	62Ni-25Mo-8Cr-2Fe	Forgings	SB-564	...
35	62Ni-25Mo-8Cr-2Fe	Rod	SB-573	...
36	62Ni-25Mo-8Cr-2Fe	Wld. pipe	SB-619	...
37	62Ni-25Mo-8Cr-2Fe	Smls. pipe & tube	SB-622	...
38	62Ni-25Mo-8Cr-2Fe	Wld. tube	SB-626	...
39	54Ni-16Mo-15Cr	Smls. & wld. ftgs.	SB-366	...
40	54Ni-16Mo-15Cr	Forgings	SB-462	...
41	54Ni-16Mo-15Cr	Forgings	SB-564	...
42	54Ni-16Mo-15Cr	Rod	SB-574	...
43	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...
44	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...
45	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N08825	Annealed	...	85
2	N08825	Annealed	...	85
3	N08825	Annealed	...	85
4	N08904	Annealed	...	71
5	N08904	Annealed	...	71
6	N08904	Annealed	...	71
7	N08904	Annealed	...	71
8	N08904	Annealed	...	71
9	N08904	Annealed	...	71
10	N08904	Annealed	...	71
11	N08925	Annealed	...	87
12	N08925	Annealed	...	87
13	N08925	Annealed	...	87
14	N08925	Annealed	...	87
15	N08925	Annealed	...	87
16	N08925	...	...	87
17	N08925	...	...	87
18	N08925	...	...	87
19	N08925	...	...	87
20	N08925	...	...	87
21	N08925	...	...	87
22	N10001	Annealed	...	100
23	N10001	Annealed	...	100
24	N10001	Solution ann.	...	100
25	N10001	Solution ann.	...	100
26	N10001	Solution ann.	...	100
27	N10001	Annealed	...	100
28	N10001	Annealed	...	115
29	N10003	Annealed	...	100
30	N10003	Annealed	...	100
31	N10003	Annealed	...	100
32	N10242	Annealed	...	105
33	N10242	Annealed	...	105
34	N10242	Annealed	...	105
35	N10242	Annealed	...	105
36	N10242	Solution ann.	...	105
37	N10242	Solution ann.	...	105
38	N10242	Solution ann.	...	105
39	N10276	Solution ann.	...	100
40	N10276	Solution ann.	...	100
41	N10276	Solution ann.	...	100
42	N10276	Solution ann.	...	100
43	N10276	Solution ann.	...	100
44	N10276	Solution ann.	...	100
45	N10276	Solution ann.	...	100

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
2	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
3	85.0	85.0	85.0	85.0	85.0	85.0	84.6	84.2	83.7	83.1	82.4	81.5	80.4	79.0
4	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
5	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
6	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
7	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
8	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
9	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
10	71.0	71.0	67.8	65.4	63.6	62.2	61.6	61.0	60.5	...	...	...	...	...
11	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
12	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
13	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
14	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
15	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
16	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
17	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
18	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
19	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
20	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
21	87.0	87.0	83.8	80.4	77.4	74.9	73.8	72.7	71.5	70.2	...	...	...	...
22	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
23	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
24	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
25	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
26	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
27	100.0	100.0	100.0	98.4	97.4	96.8	96.4	96.0	95.6	95.2	...	...	...	...
28	115.0	115.0	115.0	113.1	112.0	111.3	110.9	110.4	109.9	109.5	...	...	...	...
29	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	99.7	98.0	96.0	93.6
30	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	99.7	98.0	96.0	93.6
31	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	100.0	99.7	98.0	96.0	93.6
32	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
33	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
34	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
35	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
36	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
37	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
38	105.0	105.0	105.0	105.0	105.0	104.4	104.2	103.9	103.7	103.5	103.3	103.2	103.1	103.1
39	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
40	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
41	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
42	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
43	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
44	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
45	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	90.9	87.8	84.3	80.5	76.4	...	...	...	...	...	...	...	...
30	90.9	87.8	84.3	80.5	76.4	...	...	...	...	...	...	...	...
31	90.9	87.8	84.3	80.5	76.4	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
40	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
41	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
42	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
43	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
44	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
45	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	54Ni-16Mo-15Cr	Wld. tube	SB-626	...
2	62Ni-22Mo-15Cr	Smls. & wld. ftgs.	SB-366	...
3	62Ni-22Mo-15Cr	Forgings	SB-462	...
4	62Ni-22Mo-15Cr	Forgings	SB-564	...
5	62Ni-22Mo-15Cr	Rod	SB-574	...
6	62Ni-22Mo-15Cr	Plate, sheet, strip	SB-575	...
7	62Ni-22Mo-15Cr	Wld. pipe	SB-619	...
8	62Ni-22Mo-15Cr	Smls. pipe & tube	SB-622	...
9	62Ni-22Mo-15Cr	Wld. tube	SB-626	...
10	Ni-28Mo-3Fe-1.3Cr-0.25Al	Plate, sheet, strip	SB-333	...
11	Ni-28Mo-3Fe-1.3Cr-0.25Al	Rod	SB-335	...
12	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. & wld. ftgs.	SB-366	...
13	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forgings	SB-564	...
14	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. pipe	SB-619	...
15	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. pipe & tube	SB-622	...
16	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. tube	SB-626	...
17	65Ni-28Mo-2Fe	Smls. & wld. ftgs.	SB-366	...
18	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...
19	65Ni-28Mo-2Fe	Wld. tube	SB-626	...
20	65Ni-28Mo-2Fe	Plate, sheet, strip	SB-333	...
21	65Ni-28Mo-2Fe	Rod	SB-335	...
22	65Ni-28Mo-2Fe	Forgings	SB-462	...
23	65Ni-28Mo-2Fe	Forgings	SB-564	...
24	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...
25	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...
26	65Ni-28Mo-2Fe	Wld. tube	SB-626	...
27	65Ni-29.5Mo-2Fe-2Cr	Plate, sheet, strip	SB-333	...
28	65Ni-29.5Mo-2Fe-2Cr	Rod	SB-335	...
29	65Ni-29.5Mo-2Fe-2Cr	Smls. & wld. ftgs.	SB-366	...
30	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-462	...
31	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-564	...
32	65Ni-29.5Mo-2Fe-2Cr	Wld. pipe	SB-619	...
33	65Ni-29.5Mo-2Fe-2Cr	Smls. pipe & tube	SB-622	...
34	65Ni-29.5Mo-2Fe-2Cr	Wld. tube	SB-626	...
35	37Ni-30Co-28Cr-2.7Si	Plate, sheet, strip	SB-435	...
36	37Ni-30Co-28Cr-2.7Si	Forgings	SB-564	...
37	37Ni-30Co-28Cr-2.7Si	Rod	SB-572	...
38	37Ni-30Co-28Cr-2.7Si	Wld. pipe	SB-619	...
39	37Ni-30Co-28Cr-2.7Si	Smls. pipe & tube	SB-622	...
40	37Ni-30Co-28Cr-2.7Si	Wld. tube	SB-626	...
41	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. & wld. ftgs.	SB-366	...
42	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Forgings	SB-564	...
43	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. pipe	SB-619	...
44	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. pipe & tube	SB-622	...
45	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Plate, sheet, strip	SB-625	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	N10276	Solution ann.	...	100
2	N10362	Solution ann.	...	105
3	N10362	Solution ann.	...	105
4	N10362	Solution ann.	...	105
5	N10362	Solution ann.	...	105
6	N10362	Solution ann.	...	105
7	N10362	Solution ann.	...	105
8	N10362	Solution ann.	...	105
9	N10362	Solution ann.	...	105
10	N10629	...	...	110
11	N10629	...	...	110
12	N10629	...	...	110
13	N10629	...	...	110
14	N10629	...	...	110
15	N10629	...	...	110
16	N10629	...	...	110
17	N10665	Annealed	...	110
18	N10665	Annealed	...	110
19	N10665	Annealed	...	110
20	N10665	Solution ann.	...	110
21	N10665	Solution ann.	...	110
22	N10665	Solution ann.	...	110
23	N10665	Solution ann.	...	110
24	N10665	Solution ann.	...	110
25	N10665	Solution ann.	...	110
26	N10665	Solution ann.	...	110
27	N10675	Solution ann.	...	110
28	N10675	Solution ann.	...	110
29	N10675	Solution ann.	...	110
30	N10675	Solution ann.	...	110
31	N10675	Solution ann.	...	110
32	N10675	Solution ann.	...	110
33	N10675	Solution ann.	...	110
34	N10675	Solution ann.	...	110
35	N12160	Solution ann.	...	90
36	N12160	Solution ann.	...	90
37	N12160	Solution ann.	...	90
38	N12160	Solution ann.	...	90
39	N12160	Solution ann.	...	90
40	N12160	Solution ann.	...	90
41	R20033	...	...	109
42	R20033	...	...	109
43	R20033	...	...	109
44	R20033	...	...	109
45	R20033	...	...	109

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	100.0	100.0	100.0	97.7	95.7	93.9	93.1	92.4	91.7	90.9	90.2	89.4	88.5	87.6
2	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
3	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
4	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
5	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
6	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
7	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
8	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
9	105.0	105.0	105.0	103.0	101.0	99.5	99.2	99.0	98.7	98.3	...	...	...	...
10	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
11	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
12	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
13	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
14	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
15	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
16	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.0	...
17	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
18	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
19	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
20	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
21	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
22	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
23	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
24	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
25	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
26	110.0	110.0	110.0	110.0	110.0	109.2	108.7	108.1	107.6	107.0	106.5	105.9	105.5	105.3
27	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
28	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
29	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
30	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
31	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
32	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
33	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
34	110.0	110.0	110.0	110.0	108.7	107.1	106.4	105.8	105.2	104.7	104.2	103.8	103.3	102.8
35	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
36	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
37	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
38	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
39	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
40	90.0	90.0	90.0	87.8	85.5	83.3	82.2	81.1	80.0	78.9	77.8	76.6	75.4	74.1
41	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
42	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
43	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
44	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
45	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	86.2	84.7	82.9	80.9	78.6	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. tube	SB-626	...
2	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Rod	SB-649	...
3	21Ni-30Fe-22Cr-18Co-3Mo-3W	Plate, sheet, strip	SB-435	...
4	21Ni-30Fe-22Cr-18Co-3Mo-3W	Rod	SB-572	...
5	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. pipe	SB-619	...
6	21Ni-30Fe-22Cr-18Co-3Mo-3W	Smls. pipe & tube	SB-622	...
7	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. tube	SB-626	...
8	Co-26Cr-9Ni-5Mo-3Fe-2W	Rod	SB-815	...
9	Co-26Cr-9Ni-5Mo-3Fe-2W	Plate, sheet, strip	SB-818	...
10	Ti	Plate, sheet, strip	SB-265	1
11	Ti	Smls. & wld. tube	SB-338	1
12	Ti	Bar, billet	SB-348	1
13	Ti	Smls. & wld. ftgs.	SB-363	WPT1
14	Ti	Forgings	SB-381	F-1
15	Ti	Smls. pipe	SB-861	1
16	Ti	Wld. pipe	SB-862	1
17	Ti	Castings	SB-367	C-2
18	Ti	Forgings	SB-381	F-2
19	Ti	Plate, sheet, strip	SB-265	2H
20	Ti	Smls. & wld. tube	SB-338	2H
21	Ti	Bar, billet	SB-348	2H
22	Ti	Smls. fittings	SB-363	WPT2H
23	Ti	Wld. fittings	SB-363	WPT2HW
24	Ti	Forgings	SB-381	F-2H
25	Ti	Smls. pipe	SB-861	2H
26	Ti	Wld. pipe	SB-862	2H
27	Ti	Castings	SB-367	C-3
28	Ti	Plate, sheet, strip	SB-265	3
29	Ti	Smls. & wld. tube	SB-338	3
30	Ti	Bar, billet	SB-348	3
31	Ti	Smls. & wld. ftgs.	SB-363	WPT3
32	Ti	Forgings	SB-381	F-3
33	Ti	Smls. pipe	SB-861	3
34	Ti	Wld. pipe	SB-862	3
35	Ti-Pd	Plate, sheet, strip	SB-265	11
36	Ti-Pd	Plate, sheet, strip	SB-265	17
37	Ti-Ru	Plate, sheet, strip	SB-265	27
38	Ti-Pd	Plate, sheet, strip	SB-265	7
39	Ti-0.15Pd	Plate, sheet, strip	SB-265	7H
40	Ti-0.15Pd	Smls. & wld. tube	SB-338	7H
41	Ti-0.15Pd	Bar, billet	SB-348	7H
42	Ti-0.15Pd	Smls. fittings	SB-363	WPT7H
43	Ti-0.15Pd	Wld. fittings	SB-363	WPT7HW
44	Ti-0.15Pd	Forgings	SB-381	F-7H
45	Ti-0.15Pd	Smls. pipe	SB-861	7H

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	R20033	...	...	109
2	R20033	...	...	109
3	R30556	Annealed	...	100
4	R30556	Annealed	...	100
5	R30556	Annealed	...	100
6	R30556	Annealed	...	100
7	R30556	Annealed	...	100
8	R31233	Solution ann.	...	130
9	R31233	Solution ann.	...	130
10	R50250	Annealed	...	35
11	R50250	Annealed	...	35
12	R50250	Annealed	...	35
13	R50250	Annealed	...	35
14	R50250	Annealed	...	35
15	R50250	Annealed	...	35
16	R50250	Annealed	...	35
17	R50400	...	...	50
18	R50400	Annealed	...	50
19	R50400	Annealed	...	58
20	R50400	Annealed	...	58
21	R50400	Annealed	...	58
22	R50400	Annealed	...	58
23	R50400	Annealed	...	58
24	R50400	Annealed	...	58
25	R50400	Annealed	...	58
26	R50400	Annealed	...	58
27	R50550	...	...	65
28	R50550	Annealed	...	65
29	R50550	Annealed	...	65
30	R50550	Annealed	...	65
31	R50550	Annealed	...	65
32	R50550	Annealed	...	65
33	R50550	Annealed	...	65
34	R50550	Annealed	...	65
35	R52250	Annealed	...	35
36	R52252	Annealed	...	35
37	R52254	Annealed	...	35
38	R52400	Annealed	...	50
39	R52400	Annealed	...	58
40	R52400	Annealed	...	58
41	R52400	Annealed	...	58
42	R52400	Annealed	...	58
43	R52400	Annealed	...	58
44	R52400	Annealed	...	58
45	R52400	Annealed	...	58

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
2	109.0	109.0	103.2	97.8	93.7	90.6	89.3	88.2	87.1	86.0	84.9	83.5	...	...
3	100.0	100.0	97.9	94.7	92.5	91.1	90.5	90.1	89.7	89.3	88.8	88.2	87.5	86.6
4	100.0	100.0	97.9	94.7	92.5	91.1	90.5	90.1	89.7	89.3	88.8	88.2	87.5	86.6
5	100.0	100.0	97.9	94.7	92.5	91.1	90.5	90.1	89.7	89.3	88.8	88.2	87.5	86.6
6	100.0	100.0	97.9	94.7	92.5	91.1	90.5	90.1	89.7	89.3	88.8	88.2	87.5	86.6
7	100.0	100.0	97.9	94.7	92.5	91.1	90.5	90.1	89.7	89.3	88.8	88.2	87.5	86.6
8	130.0	130.0	130.0	130.0	130.0	130.0	130.0	128.3	126.6	125.2	124.1	123.0	121.9	120.4
9	130.0	130.0	130.0	130.0	130.0	130.0	130.0	128.3	126.6	125.2	124.1	123.0	121.9	120.4
10	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
11	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
12	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
13	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
14	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
15	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
16	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
17	50.0	41.3	34.1	28.4	23.8	...	...	...	...	...	...	...	...	...
18	50.0	43.6	36.2	30.9	26.6	22.8	...	...	...	...	...	...	...	...
19	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
20	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
21	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
22	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
23	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
24	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
25	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
26	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
27	65.0	55.2	44.6	36.2	29.8	...	...	...	...	...	...	...	...	...
28	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
29	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
30	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
31	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
32	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
33	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
34	65.0	55.2	44.6	36.2	29.8	25.8	...	...	...	...	...	...	...	...
35	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
36	35.0	29.2	23.2	19.2	16.4	12.4	...	...	...	...	...	...	...	...
37	35.0	28.9	23.1	19.3	16.3	12.5	...	...	...	...	...	...	...	...
38	50.0	43.6	36.2	30.9	26.6	22.8	...	...	...	...	...	...	...	...
39	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
40	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
41	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
42	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
43	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
44	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
45	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	Ti-0.15Pd	Wld. pipe	SB-862	7H
2	Ti-Pd	Plate, sheet, strip	SB-265	16
3	Ti-Pd	Bar, billet	SB-348	16
4	Ti-Pd	Forgings	SB-381	F-16
5	Ti-0.05Pd	Plate, sheet, strip	SB-265	16H
6	Ti-0.05Pd	Smls. & wld. tube	SB-338	16H
7	Ti-0.05Pd	Bar, billet	SB-348	16H
8	Ti-0.05Pd	Smls. fittings	SB-363	WPT16H
9	Ti-0.05Pd	Wld. fittings	SB-363	WPT16HW
10	Ti-0.05Pd	Forgings	SB-381	F-16H
11	Ti-0.05Pd	Smls. pipe	SB-861	16H
12	Ti-0.05Pd	Wld. pipe	SB-862	16H
13	Ti-Ru	Plate, sheet, strip	SB-265	26
14	Ti-Ru	Smls. & wld. tube	SB-338	26
15	Ti-Ru	Bar, billet	SB-348	26
16	Ti-Ru	Smls. fittings	SB-363	WPT26
17	Ti-Ru	Wld. fittings	SB-363	WPT26W
18	Ti-Ru	Forgings	SB-381	F-26
19	Ti-Ru	Smls. pipe	SB-861	26
20	Ti-Ru	Wld. pipe	SB-862	26
21	Ti-0.10Ru	Plate, sheet, strip	SB-265	26H
22	Ti-0.10Ru	Smls. & wld. tube	SB-338	26H
23	Ti-0.10Ru	Bar, billet	SB-348	26H
24	Ti-0.10Ru	Smls. fittings	SB-363	WPT26H
25	Ti-0.10Ru	Wld. fittings	SB-363	WPT26HW
26	Ti-0.10Ru	Forgings	SB-381	F-26H
27	Ti-0.10Ru	Smls. pipe	SB-861	26H
28	Ti-0.10Ru	Wld. pipe	SB-862	26H
29	Ti-0.3Mo-0.8Ni	Forgings	SB-381	F-12
30	Ti-4Al-2.5V-1.5Fe	Plate, sheet, strip	SB-265	38
31	Ti-4Al-2.5V-1.5Fe	Smls. tube	SB-338	38
32	Ti-4Al-2.5V-1.5Fe	Wld. tube	SB-338	38
33	Ti-4Al-2.5V-1.5Fe	Bar, billet	SB-348	38
34	Ti-4Al-2.5V-1.5Fe	Smls. fittings	SB-363	WPT38
35	Ti-4Al-2.5V-1.5Fe	Wld. fittings	SB-363	WPT38W
36	Ti-4Al-2.5V-1.5Fe	Forgings	SB-381	F-38
37	Ti-4Al-2.5V-1.5Fe	Smls. pipe	SB-861	38
38	Ti-4Al-2.5V-1.5Fe	Wld. pipe	SB-862	38
39	Ti-3Al-2.5V	Plate, sheet, strip	SB-265	9
40	Ti-3Al-2.5V	Smls. & wld. tube	SB-338	9
41	Ti-3Al-2.5V	Bar, billet	SB-348	9
42	Ti-3Al-2.5V	Smls. fittings	SB-363	WPT9
43	Ti-3Al-2.5V	Wld. fittings	SB-363	WPT9W
44	Ti-3Al-2.5V	Forgings	SB-381	F-9
45	Ti-3Al-2.5V	Smls. pipe	SB-861	9

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	R52400	Annealed	...	58
2	R52402	Annealed	...	50
3	R52402	Annealed	...	50
4	R52402	Annealed	...	50
5	R52402	Annealed	...	58
6	R52402	Annealed	...	58
7	R52402	Annealed	...	58
8	R52402	Annealed	...	58
9	R52402	Annealed	...	58
10	R52402	Annealed	...	58
11	R52402	Annealed	...	58
12	R52402	Annealed	...	58
13	R52404	Annealed	...	50
14	R52404	Annealed	...	50
15	R52404	Annealed	...	50
16	R52404	Annealed	...	50
17	R52404	Annealed	...	50
18	R52404	Annealed	...	50
19	R52404	Annealed	...	50
20	R52404	Annealed	...	50
21	R52404	Annealed	...	58
22	R52404	Annealed	...	58
23	R52404	Annealed	...	58
24	R52404	Annealed	...	58
25	R52404	Annealed	...	58
26	R52404	Annealed	...	58
27	R52404	Annealed	...	58
28	R52404	Annealed	...	58
29	R53400	Annealed	...	70
30	R54250	Annealed	...	130
31	R54250	Annealed	...	130
32	R54250	Annealed	...	130
33	R54250	Annealed	...	130
34	R54250	Annealed	...	130
35	R54250	Annealed	...	130
36	R54250	Annealed	...	130
37	R54250	Annealed	...	130
38	R54250	Annealed	...	130
39	R56320	Annealed	...	90
40	R56320	Annealed	...	90
41	R56320	Annealed	...	90
42	R56320	Annealed	...	90
43	R56320	Annealed	...	90
44	R56320	Annealed	...	90
45	R56320	Annealed	...	90

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)														
1	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
2	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
3	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
4	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
5	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
6	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
7	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
8	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
9	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
10	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
11	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
12	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
13	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
14	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
15	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
16	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
17	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
18	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
19	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
20	50.0	43.6	36.0	30.8	26.4	22.8	...	...	...	...	...	...	...	...
21	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
22	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
23	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
24	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
25	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
26	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
27	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
28	58.0	50.5	42.0	35.8	30.9	26.5	...	...	...	...	...	...	...	...
29	70.0	65.4	56.8	50.0	45.7	43.2	...	...	...	...	...	...	...	...
30	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
31	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
32	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
33	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
34	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
35	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
36	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
37	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
38	130.0	129.1	118.1	108.6	101.4	96.9	95.4	...	...	...	...	...	...	...
39	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
40	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
41	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
42	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
43	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
44	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
45	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade
Nonferrous Materials (Cont'd)				
1	Ti-3Al-2.5V	Wld. pipe	SB-862	9
2	Ti-3Al-2.5V-0.1Ru	Plate, sheet, strip	SB-265	28
3	Ti-3Al-2.5V-0.1Ru	Smls. & wld. tube	SB-338	28
4	Ti-3Al-2.5V-0.1Ru	Bar, billet	SB-348	28
5	Ti-3Al-2.5V-0.1Ru	Smls. fittings	SB-363	WPT28
6	Ti-3Al-2.5V-0.1Ru	Wld. fittings	SB-363	WPT28W
7	Ti-3Al-2.5V-0.1Ru	Forgings	SB-381	F-28
8	Ti-3Al-2.5V-0.1Ru	Smls. pipe	SB-861	28
9	Ti-3Al-2.5V-0.1Ru	Wld. pipe	SB-862	28
10	99.2Zr	Forgings	SB-493	...
11	99.2Zr	Smls. & wld. tube	SB-523	...
12	99.2Zr	Bar, wire	SB-550	...
13	99.2Zr	Plate, sheet, strip	SB-551	...
14	99.2Zr	Smls. fittings	SB-653	PZ-2
15	99.2Zr	Wld. fittings	SB-653	PZ-2W
16	99.2Zr	Smls. & wld. pipe	SB-658	...
(25) 17	99.2Zr	Castings	SB-752	...
18	95.5Zr + 2.5Nb	Forgings	SB-493	...
19	95.5Zr + 2.5Nb	Smls. & wld. tube	SB-523	...
20	95.5Zr + 2.5Nb	Bar, wire	SB-550	...
21	95.5Zr + 2.5Nb	Plate, sheet, strip	SB-551	...
22	95.5Zr + 2.5Nb	Smls. fittings	SB-653	PZ-5
23	95.5Zr + 2.5Nb	Wld. fittings	SB-653	PZ-5W
24	95.5Zr + 2.5Nb	Smls. & wld. pipe	SB-658	...
(25) 25	95.5Zr + 2.5Nb	Castings	SB-752	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Line No.	Alloy Desig./UNS No.	Class/Condition/ Temper	Size/Thickness, in.	Min. Tensile Strength, ksi
Nonferrous Materials (Cont'd)				
1	R56320	Annealed	...	90
2	R56323	Annealed	...	90
3	R56323	Annealed	...	90
4	R56323	Annealed	...	90
5	R56323	Annealed	...	90
6	R56323	Annealed	...	90
7	R56323	Annealed	...	90
8	R56323	Annealed	...	90
9	R56323	Annealed	...	90
10	R60702	Annealed	...	55
11	R60702	Annealed	...	55
12	R60702	Annealed	...	55
13	R60702	Annealed	...	55
14	R60702	Annealed	...	55
15	R60702	Annealed	...	55
16	R60702	Annealed	...	55
17	R61702	...	...	55
18	R60705	Annealed	...	70
19	R60705	Annealed	...	80
20	R60705	Annealed	...	80
21	R60705	Annealed	...	80
22	R60705	Annealed	...	80
23	R60705	Annealed	...	80
24	R60705	Annealed	...	80
25	R61705	...	...	70

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding														
Line No.	100	200	300	400	500	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)													
1	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
2	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
3	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
4	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
5	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
6	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
7	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
8	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
9	90.0	86.6	79.1	70.5	63.4	60.3	...	...	...	...	...	...	...	...
10	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
11	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
12	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
13	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
14	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
15	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
16	55.0	47.9	39.0	31.9	26.6	23.1	21.8	20.8	19.9	19.2	...	...	...	...
17	55.0	50.1	41.0	33.4	27.2	22.3	...	...	...	...	...	...	...	...
18	70.0	58.0	48.8	43.5	40.9	39.6	38.9	37.8	35.9	33.0	...	...	...	...
19	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
20	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
21	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
22	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
23	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
24	80.0	66.3	55.8	49.7	46.8	45.3	44.5	43.2	41.1	37.7	...	...	...	...
25	70.0	64.1	55.1	47.1	40.4	35.5	...	...	...	...	...	...	...	...

Table U (Cont'd)
Tensile Strength Values, S_u , for Ferrous and Nonferrous Materials

Tensile Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...

NOTES TO TABLE U**GENERAL NOTES**

- (a) The following abbreviations are used: ann., annealed; cond., condenser; CW, cold worked; fin., finished; fr., from; ftgs., fittings; HW, Hot worked; N, Normalized; NT, Normalized and tempered; QT, Quenched and tempered; rel., relieved; rld., rolled; Smls., Seamless; Sol., Solution; SR, stress relieved; Str., Strength; treat., treated; and Wld., Welded.
- (b) The tabulated values of tensile strength are those which the Committee believes are suitable for use in design calculations. At temperatures above room temperature, the values of tensile strength tend toward an average or expected value which may be as much as 10% above the tensile strength trend curve adjusted to the minimum specified room temperature tensile strength. The tensile strength values do not correspond exactly to "average" as this term is applied to a statistical treatment of a homogeneous set of data. Neither the ASME Material Specifications nor the rules of Sections I, III, VIII, or XII require elevated temperature testing for tensile strengths of production material for use in Code components. It is not intended that results of such tests, if performed, be compared with these tabulated tensile strength values for ASME Code acceptance/rejection purposes for materials. If some elevated temperature test results on production material appear lower than the tabulated values by a large amount (more than the typical variability of material and suggesting the possibility of some error), further investigation by retest or other means should be considered.
- (c) Notes limiting applications of these materials appear in Tables 1A, 1B, 2A, 2B, 3, 4, 5A, and 5B.
- (d) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-516/SA-516M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-516 Grade 70 shall be used when SA-516M Grade 485 is used in construction.
- (e) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (f) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

INTENTIONALLY LEFT BLANK

Table Y-1
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials						
(25)	1 Carbon steel	Sheet	SA-1008	CS-A	...	...
	2 Carbon steel	Sheet	SA-1008	CS-B	...	...
	3 Carbon steel	Wld. tube	SA-513	1/1008	...	...
	4 Carbon steel	Bar	SA-675	45	...	...
	5 Carbon steel	Wld. pipe	SA-134	A283A	...	...
(25)	6 Carbon steel	Plate	SA-285	A	K01700	...
	7 Carbon steel	Wld. pipe	SA-672	A45	K01700	...
	8 Carbon steel	Sheet	SA-414	A	K01501	...
	9 Carbon steel	Wld. tube	SA-513	1/1010	...	...
	10 Carbon steel	Wld. tube	SA-178	A	K01200	...
(25)	11 Carbon steel	Smls. tube	SA-179	...	K01200	...
	12 Carbon steel	Smls. tube	SA-192	...	K01201	...
	13 Carbon steel	Wld. tube	SA-214	...	K01807	...
	14 Carbon steel	Smls. tube	SA-556	A2	K01807	...
	15 ...	...	...	...	...	...
(25)	16 Carbon steel	Wld. pipe	SA-53	E/A	K02504	...
	17 Carbon steel	Butt-wld. pipe	SA-53	F/A	...	...
	18 Carbon steel	Smls. pipe	SA-53	S/A	K02504	...
	19 Carbon steel	Smls. pipe	SA-106	A	K02501	...
	20 Carbon steel	Wld. pipe	SA-135	A	...	...
(25)	21 Carbon steel	Forged pipe	SA-369	FPA	K02501	...
	22 Carbon steel	Wld. pipe	SA-587	...	K11500	...
	23 Carbon steel	Wld. tube	SA-513	1/1015	...	...
	24 Carbon steel	Bar	SA-675	50	...	...
	25 Carbon steel	Wld. pipe	SA-134	A283B	...	...
(25)	26 Carbon steel	Plate	SA-285	B	K02200	...
	27 Carbon steel	Wld. pipe	SA-672	A50	K02200	...
	28 Carbon steel	Sheet	SA-414	B	K02201	...
	29 Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
	30 Carbon steel	Plate	SA/EN 10025-2	S235JR	...	...
(25)	31 Carbon steel	Plate	SA/EN 10028-2	P235GH	...	...
	32 Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...
	33 Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
	34 Carbon steel	Wld. pipe & tube	SA/EN 10217-1	P235TR2	...	...
	35 Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...
(25)	36 Carbon steel	Smls. tube	SA/EN 10216-2	P235GH	...	...
	37 Carbon steel	Sheet, strip	SA-1011	36	SS	Type 1
	38 Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
	39 Carbon steel	Bar	SA-675	55	...	...
	40 Carbon steel	Wld. pipe	SA-134	A283C	K02401	...
(25)	41 Carbon steel	Plate	SA-283	C	K02401	...
	42 Carbon steel	Plate	SA-285	C	K02801	...
	43 Carbon steel	Smls. & wld. pipe	SA-333	1	K03008	...
	44 Carbon steel	Smls. & wld. tube	SA-334	1	K03008	...
	45 Carbon steel	Plate	SA-516	55	K01800	...

Table Y-1
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials				
1	...	40	20	...
2	...	40	20	...
3	...	42	30	...
4	...	45	22.5	...
5	...	45	24	...
6	...	45	24	...
7	...	45	24	...
8	...	45	25	...
9	...	45	32	...
10	...	47	26	...
11	...	47	26	...
12	...	47	26	...
13	...	47	26	...
14	...	47	26	...
15	...	...	...	...
16	...	48	30	...
17	...	48	30	...
18	...	48	30	...
19	...	48	30	...
20	...	48	30	...
21	...	48	30	...
22	...	48	30	...
23	...	48	35	...
24	...	50	25	...
25	...	50	27	...
26	...	50	27	...
27	...	50	27	...
28	...	50	30	...
29	$6 < t \leq 10$	51	31	...
30	$t \leq 4$	52	31	...
31	$\leq 2\frac{1}{4}$	52	31	...
32	$1\frac{5}{8} < t \leq 2\frac{1}{2}$	52	31	...
33	$4 < t \leq 6$	52	32.5	...
34	$t \leq 1\frac{9}{16}$	52	33	...
35	$\frac{5}{8} < t \leq 1\frac{5}{8}$	52	32.5	...
36	$t \leq \frac{5}{8}$	52	34	...
37	$t \leq 0.23$	53	36	...
38	$2\frac{1}{4} < t \leq 4$	53.5	34	...
39	...	55	27.5	...
40	...	55	30	...
41	...	55	30	...
42	...	55	30	...
43	...	55	30	...
44	...	55	30	...
45	...	55	30	...

Table Y-1
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials									
1	20.0	18.8	18.3	18.0	17.7	...	17.1	...	16.3
2	20.0	18.8	18.3	18.0	17.7	...	17.1	...	16.3
3	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.5
4	22.5	21.1	20.6	20.2	19.9	...	19.2	...	18.3
5	24.0	22.6	22.0	21.6	21.2	...	20.5	...	19.6
6	24.0	22.6	22.0	21.6	21.2	...	20.5	...	19.6
7	24.0	22.6	22.0	21.6	21.2	...	20.5	...	19.6
8	25.0	23.5	22.9	22.5	22.1	...	21.4	...	20.4
9	32.0	30.0	29.3	28.8	28.3	...	27.3	...	26.1
10	26.0	24.4	23.8	23.4	23.0	...	22.2	...	21.2
11	26.0	24.4	23.8	23.4	23.0	...	22.2	...	21.2
12	26.0	24.4	23.8	23.4	23.0	...	22.2	...	21.2
13	26.0	24.4	23.8	23.4	23.0	...	22.2	...	21.2
14	26.0	24.4	23.8	23.4	23.0	...	22.2	...	21.2
15	...	...	...	...	...	...	...	...	...
16	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
17	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
18	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
19	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
20	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
21	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
22	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
23	35.0	32.8	32.0	31.5	31.0	...	29.9	...	28.5
24	25.0	23.5	22.9	22.5	22.1	...	21.4	...	20.4
25	27.0	25.4	24.7	24.3	23.9	...	23.1	...	22.0
26	27.0	25.4	24.7	24.3	23.9	...	23.1	...	22.0
27	27.0	25.4	24.7	24.3	23.9	...	23.1	...	22.0
28	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
29	31.0	29.3	28.6	...	27.6	...	26.6	...	25.4
30	31.0	29.1	28.4	27.9	27.4	...	26.5	...	25.3
31	31.0	...	28.4	...	27.4	...	26.5	...	25.3
32	31.2	29.3	28.6	28.0	27.6	27.1	26.6	26.1	25.4
33	32.5	30.7	29.9	...	28.9	...	27.9	...	26.6
34	33.0	31.0	30.2	29.7	29.2	28.7	28.2	27.6	26.8
35	32.6	30.7	29.9	29.3	28.9	28.4	27.9	27.3	26.6
36	34.1	32.0	31.2	30.6	30.2	29.7	29.1	28.5	27.8
37	36.0	33.8	33.1	32.4	31.6	31.2	30.8	30.2	29.3
38	34.0	32.0	31.1	...	30.1	...	29.1	...	...
39	27.5	25.8	25.2	24.7	24.3	...	23.5	...	22.4
40	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
41	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
42	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
43	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
44	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
45	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4

Table Y-1
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
										Ferrous Materials
1	...	15.3	14.8	14.3	13.8	13.4	13.0	12.6	12.3	11.9
2	...	15.3	14.8	14.3	13.8	13.4	13.0	12.6	12.3	11.9
3	...	23.0	22.3	21.5	20.8	20.1	19.5	18.9	18.5	17.9
4	...	17.2	16.7	16.1	15.6	15.1	14.6	14.2	13.8	13.4
5	...	18.4	17.8	17.2	16.6	16.1	15.6	15.2	14.7	14.3
6	...	18.4	17.8	17.2	16.6	16.1	15.6	15.2	14.7	14.3
7	...	18.4	17.8	17.2	16.6	16.1	15.6	15.2	14.7	14.3
8	...	19.2	18.5	17.9	17.3	16.8	16.3	15.8	15.4	14.9
9	...	24.5	23.8	22.9	22.2	21.4	20.8	20.2	19.7	19.1
10	...	19.9	19.3	18.6	18.0	17.4	16.9	16.4	16.0	15.5
11	...	19.9	19.3	18.6	18.0	17.4	16.9	16.4	16.0	15.5
12	...	19.9	19.3	18.6	18.0	17.4	16.9	16.4	16.0	15.5
13	...	19.9	19.3	18.6	18.0	17.4	16.9	16.4	16.0	15.5
14	...	19.9	19.3	18.6	18.0	17.4	16.9	16.4	16.0	15.5
15	...	...	...	...	...	...	...	...	...	...
16	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
17	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
18	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
19	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
20	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
21	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
22	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
23	...	26.8	26.0	25.0	24.2	23.4	22.8	22.1	21.5	20.9
24	...	19.2	18.5	17.9	17.3	16.8	16.3	15.8	15.4	14.9
25	...	20.7	20.0	19.3	18.7	18.1	17.6	17.1	16.6	16.0
26	...	20.7	20.0	19.3	18.7	18.1	17.6	17.1	16.6	16.0
27	...	20.7	20.0	19.3	18.7	18.1	17.6	17.1	16.6	16.0
28	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
29	...	23.9	23.1	22.3	21.6	20.9	20.3	19.7	19.2	18.5
30	...	23.7	23	22.2	21.5	20.7	20.2	19.6	19	18.4
31	...	23.8	...	22.2	21.5	20.8	20.2	19.6	19.0	18.4
32	24.7	23.9	23.1	22.3	21.6	20.9	20.3	19.7	19.2	18.5
33	...	25.0	24.2	23.4	22.6	21.9	21.2	20.6	20.0	19.4
34	26.1	25.3	24.4	23.6	22.8	22.1	21.5	20.9	20.2	19.6
35	25.8	25.0	24.2	23.4	22.6	21.9	21.2	20.6	20.0	19.4
36	27.0	26.1	25.3	24.4	23.6	22.8	22.2	21.5	20.9	20.3
37	28.3	27.7	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	21.1	20.4	19.7	19.0	18.4	17.9	17.4	16.9	16.3
40	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
41	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
42	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
43	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
44	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
45	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8

Table Y-1
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	(25)
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Carbon steel	Smls. pipe	SA-524	II	K02104	...
2	Carbon steel	Wld. pipe	SA-671	CA55	K02801	...
3	Carbon steel	Wld. pipe	SA-671	CE55	K02202	...
4	Carbon steel	Wld. pipe	SA-672	A55	K02801	...
5	Carbon steel	Wld. pipe	SA-672	B55	K02001	...
6	Carbon steel	Wld. pipe	SA-672	C55	K01800	...
7	Carbon steel	Wld. pipe	SA-672	E55	K02202	...
8	Carbon steel	Sheet	SA-414	C	K02503	...
9	Carbon steel	Sheet, strip	SA-1011	40	SS	...
10	Carbon steel	Sheet, strip	SA-1011	45	HSLAS	2
11	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
12	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
13	Carbon steel	Plate	SA/EN 10028-3	P275NH	...	...
14	Carbon steel	Plate, sheet, bar	SA-36	...	K02600	...
15	Carbon steel	Plate, sheet	SA-662	A	K01701	...
16	Carbon steel	Sheet, strip	SA-1011	36	SS	Type 2
17	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...
18	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...
19	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...
20	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...
21	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...
22	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...
23	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...
24	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...
25	Carbon steel	Plate	SA/EN 10028-2	P265GH	...	...
26	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...
27	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250A	...	...
28	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250BR	...	...
29	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250 B0	...	...
30	Carbon steel	Plate, bar, shapes	SA/IS 2062	E250C	...	...
31	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...
32	Carbon steel	Smls. tube	SA/EN 10216-2	P265GH	...	...
33	Carbon steel	Forgings	SA-181	...	K03502	60
34	Carbon steel	Castings	SA-216	WCA	J02502	...
35	Carbon steel	Forgings	SA-266	1	K03506	...
36	Carbon steel	Forgings	SA-350	LF1	K03009	1
37	Carbon steel	Castings	SA-352	LCA	J02504	...
38	Carbon steel	Cast pipe	SA-660	WCA	J02504	...
39	Carbon steel	Bar	SA-675	60	...	...
40	Carbon steel	Forgings	SA-765	I	K03046	...
41	Carbon steel	Plate	SA-515	60	K02401	...
42	Carbon steel	Plate	SA-516	60	K02100	...
43	Carbon steel	Wld. pipe	SA-671	CB60	K02401	...
44	Carbon steel	Wld. pipe	SA-671	CC60	K02100	...
45	Carbon steel	Wld. pipe	SA-671	CE60	K02402	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	55	30	...
2	...	55	30	...
3	...	55	30	...
4	...	55	30	...
5	...	55	30	...
6	...	55	30	...
7	...	55	30	...
8	...	55	33	...
9	$t \leq 0.23$	55	40	...
10	...	55	45	...
11	$1\frac{1}{2} < t \leq 2\frac{1}{4}$	56.5	37	...
12	$\frac{5}{8} < t \leq 1\frac{1}{2}$	56.5	38.5	...
13	$\leq \frac{5}{8}$	56.5	40	...
14	...	58	36	...
15	...	58	40	...
16	$t \leq 0.23$	58	36	...
17	$t > 1\frac{1}{2}$	59.5	33.4	...
18	$t > 1\frac{1}{2}$	59.5	33.4	...
19	$t > 1\frac{1}{2}$	59.5	33.4	...
20	$t > 1\frac{1}{2}$	59.5	33.4	...
21	$\frac{3}{4} < t \leq 1\frac{1}{2}$	59.5	34.8	...
22	$\frac{3}{4} < t \leq 1\frac{1}{2}$	59.5	34.8	...
23	$\frac{3}{4} < t \leq 1\frac{1}{2}$	59.5	34.8	...
24	$\frac{3}{4} < t \leq 1\frac{1}{2}$	59.5	34.8	...
25	$\leq 2\frac{1}{4}$	59.5	35.5	...
26	$1\frac{5}{8} < t \leq 2\frac{1}{2}$	59.5	35.5	...
27	$\leq \frac{3}{4}$	59.5	36.3	...
28	$\leq \frac{3}{4}$	59.5	36.3	...
29	$\leq \frac{3}{4}$	59.5	36.3	...
30	$\leq \frac{3}{4}$	59.5	36.3	...
31	$\frac{5}{8} < t \leq 1\frac{5}{8}$	59.5	37	...
32	$t \leq \frac{5}{8}$	59.5	38.5	...
33	...	60	30	...
34	...	60	30	...
35	...	60	30	...
36	...	60	30	...
37	...	60	30	...
38	...	60	30	...
39	...	60	30	...
40	...	60	30	...
41	...	60	32	...
42	...	60	32	...
43	...	60	32	...
44	...	60	32	...
45	...	60	32	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
2	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
3	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
4	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
5	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
6	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
7	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
8	33.0	31.0	30.2	29.7	29.2	...	28.2	...	26.9
9	40.0	37.6	36.6	36.0	35.4	34.6	34.2	33.6	32.6
10	45.0	42.3	41.4	40.4	39.5	38.9	38.5	37.7	36.7
11	37.0	34.7	33.9	...	32.7	...	31.6	...	30.1
12	38.5	36.2	35.3	...	34.1	...	32.9	...	31.3
13	40.0	37.4	36.5	...	35.3	...	34.1	...	32.5
14	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
15	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
16	36.0	33.8	33.1	32.4	31.6	31.2	30.8	30.2	29.3
17	33.4	...	30.5	...	29.5	...	28.5	...	27.2
18	33.4	...	30.5	...	29.5	...	28.5	...	27.2
19	33.4	...	30.5	...	29.5	...	28.5	...	27.2
20	33.4	...	30.5	...	29.5	...	28.5	...	27.2
21	34.8	...	31.8	...	30.8	...	29.8	...	28.4
22	34.8	...	31.8	...	30.8	...	29.8	...	28.4
23	34.8	...	31.8	...	30.8	...	29.8	...	28.4
24	34.8	...	31.8	...	30.8	...	29.8	...	28.4
25	35.5	...	32.5	...	31.4	...	30.3	...	28.9
26	35.5	33.4	32.6	31.9	31.4	30.9	30.4	29.7	29.0
27	36.3	...	33.1	...	32.1	...	31.0	...	29.6
28	36.3	...	33.1	...	32.1	...	31.0	...	29.6
29	36.3	...	33.1	...	32.1	...	31.0	...	29.6
30	36.3	...	33.1	...	32.1	...	31.0	...	29.6
31	37.0	34.8	33.9	33.3	32.7	32.2	31.6	30.9	30.1
32	38.4	36.1	35.2	34.6	34.0	33.5	32.8	32.1	31.3
33	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
34	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
35	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
36	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
37	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
38	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
39	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
40	30.0	28.2	27.5	27.0	26.5	...	25.6	...	24.4
41	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
42	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
43	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
44	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
45	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
2	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
3	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
4	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
5	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
6	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
7	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
8	...	25.3	24.5	23.6	22.8	22.1	21.5	20.9	20.3	19.6
9	31.4	30.7	...	...	...	...	...	...	...	...
10	35.4	34.6	...	...	...	...	...	...	...	...
11	...	28.3	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
12	...	29.5	28.5	27.5	26.6	25.8	25.0	24.3	23.6	22.9
13	...	30.6	29.6	28.6	27.6	26.7	25.9	25.2	24.5	23.7
14	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
15	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
16	28.3	27.7	...	...	...	...	...	...	...	...
17	...	25.6	24.7	23.8	...	...	...	...	...	...
18	...	25.6	24.7	23.8	...	...	...	...	...	...
19	...	25.6	24.7	23.8	...	...	...	...	...	...
20	...	25.6	24.7	23.8	...	...	...	...	...	...
21	...	26.7	25.8	24.9	...	...	...	...	...	...
22	...	26.7	25.8	24.9	...	...	...	...	...	...
23	...	26.7	25.8	24.9	...	...	...	...	...	...
24	...	26.7	25.8	24.9	...	...	...	...	...	...
25	...	27.2	26.3	25.4	24.6	23.8	23.1	22.4	21.8	21.1
26	28.1	27.2	26.3	25.4	24.6	23.8	23.1	22.5	21.8	21.1
27	...	27.8	26.8	25.9	...	...	...	...	...	...
28	...	27.8	26.8	25.9	...	...	...	...	...	...
29	...	27.8	26.8	25.9	...	...	...	...	...	...
30	...	27.8	26.8	25.9	...	...	...	...	...	...
31	29.3	28.4	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
32	30.4	29.5	28.5	27.5	26.6	25.8	25.0	24.3	23.6	22.8
33	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
34	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
35	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
36	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
37	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
38	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
39	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
40	...	23.0	22.2	21.5	20.8	20.1	19.5	19.0	18.4	17.8
41	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
42	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
43	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
44	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
45	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Carbon steel	Wld. pipe	SA-672	B60	K02401	...
2	Carbon steel	Wld. pipe	SA-672	C60	K02100	...
3	Carbon steel	Wld. pipe	SA-672	E60	K02402	...
4	Carbon steel	Wld. pipe	SA-134	A283D	K02702	...
5	Carbon steel	Plate	SA-283	D	K02702	...
6	Carbon steel	Wld. pipe	SA-53	E/B	K03005	...
7	Carbon steel	Smls. pipe	SA-53	S/B	K03005	...
8	Carbon steel	Smls. pipe	SA-106	B	K03006	...
9	Carbon steel	Wld. pipe	SA-135	B	...	...
10	Carbon steel	Smls. & wld. fittings	SA-234	WPB	K03006	...
11	Carbon steel	Smls. & wld. pipe	SA-333	6	K03006	...
12	Carbon steel	Smls. & wld. tube	SA-334	6	K03006	...
13	Carbon steel	Forged pipe	SA-369	FPB	K03006	...
14	Carbon steel	Forgings	SA-372	A	K03002	...
15	Carbon steel	Sheet	SA-414	D	K02505	...
16	Carbon steel	Smls. & wld. fittings	SA-420	WPL6	...	...
17	Carbon steel	Smls. pipe	SA-524	I	K02104	...
18	Carbon steel	Bar	SA-696	B	K03200	...
19	Carbon steel	Bolting	SA-307	A	...	...
20	Carbon steel	Bolting	SA-307	B	...	...
21	Carbon steel	Forgings	SA-727	...	K02506	...
22	Carbon steel	Wld. tube	SA-178	C	K03503	...
23	Carbon steel	Smls. tube	SA-210	A-1	K02707	...
24	Carbon steel	Smls. tube	SA-556	B2	K02707	...
(25)	...	...	...	...	...	...
26	Carbon steel	Plate, bar	SA/CSA-G40.21	38W	...	...
27	Carbon steel	Plate, sheet, bar	SA-572	42	...	...
28	Carbon steel	Sheet, strip	SA-1011	45	HSLAS	1
29	Carbon steel	Sheet, strip	SA-1011	45	SS	...
30	Carbon steel	Sheet, strip	SA-1011	50	HSLAS	2
31	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
32	Carbon steel	Plate	SA/AS 1548	PT430	...	...
33	Carbon steel	Plate	SA/AS 1548	PT430	...	...
34	Carbon steel	Plate	SA/AS 1548	PT430	...	...
35	Carbon steel	Plate	SA/AS 1548	PT430	...	...
36	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
37	Carbon steel	Bar	SA-675	65	...	...
38	Carbon steel	Castings	SA-352	LCB	J03003	...
39	Carbon steel	Plate	SA-515	65	K02800	...
40	Carbon steel	Plate	SA-516	65	K02403	...
41	Carbon steel	Wld. pipe	SA-671	CB65	K02800	...
42	Carbon steel	Wld. pipe	SA-671	CC65	K02403	...
43	Carbon steel	Wld. pipe	SA-672	B65	K02800	...
44	Carbon steel	Wld. pipe	SA-672	C65	K02403	...
45	Carbon steel	Sheet	SA-414	E	K02704	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	60	32	...
2	...	60	32	...
3	...	60	32	...
4	...	60	33	...
5	...	60	33	...
6	...	60	35	...
7	...	60	35	...
8	...	60	35	...
9	...	60	35	...
10	...	60	35	...
11	...	60	35	...
12	...	60	35	...
13	...	60	35	...
14	...	60	35	...
15	...	60	35	...
16	...	60	35	...
17	...	60	35	...
18	...	60	35	...
19	$\frac{1}{4} \leq t \leq 4$	60	36	...
20	...	60	36	...
21	...	60	36	...
22	...	60	37	...
23	...	60	37	...
24	...	60	37	...
25	...	...	...	...
26	...	60	38	...
27	$t \leq 6$	60	42	...
28	...	60	45	...
29	$t \leq 0.23$	60	45	...
30	...	60	50	...
31	$6 < t \leq 10$	62.5	32	...
32	$3\frac{1}{4} < t \leq 6$	62.5	36.5	...
33	$1\frac{1}{2} < t \leq 3\frac{1}{4}$	62.5	39	...
34	$\frac{5}{8} < t \leq 1\frac{1}{2}$	62.5	40.5	...
35	$\leq \frac{5}{8}$	62.5	43.5	...
36	$4 < t \leq 6$	64	34	...
37	...	65	32.5	...
38	...	65	35	...
39	...	65	35	...
40	...	65	35	...
41	...	65	35	...
42	...	65	35	...
43	...	65	35	...
44	...	65	35	...
45	...	65	38	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
2	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
3	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
4	33.0	31.0	30.2	29.7	29.2	...	28.2	...	26.9
5	33.0	31.0	30.2	29.7	29.2	...	28.2	...	26.9
6	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
7	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
8	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
9	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
10	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
11	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
12	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
13	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
14	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
15	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
16	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
17	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
18	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
19	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
20	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
21	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
22	37.0	34.8	33.9	33.3	32.7	...	31.6	...	30.2
23	37.0	34.8	33.9	33.3	32.7	...	31.6	...	30.2
24	37.0	34.8	33.9	33.3	32.7	...	31.6	...	30.2
25	...	...	...	...	...	...	...	...	...
26	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
27	42.0	39.5	38.5	37.8	37.2	36.4	35.9	35.2	34.2
28	45.0	42.3	41.3	40.5	39.9	39.0	38.5	37.8	36.7
29	45.0	42.3	41.3	40.5	39.9	39.0	38.5	37.8	36.7
30	50.0	46.3	44.2	42.2	40.5	39.1	37.6	36.5	35.4
31	32.0	30.1	29.3	28.8	28.3	...	27.3	...	26.1
32	36.5	...	33.4	...	32.3	...	31.2	...	29.7
33	39.0	...	35.7	...	34.5	...	33.3	...	31.8
34	40.5	...	37.1	...	35.8	...	34.6	...	33.0
35	43.5	...	39.9	...	38.5	...	37.2	...	35.4
36	34.0	32.0	31.1	30.6	30.1	...	29.1	...	27.7
37	32.5	30.5	29.8	29.2	28.8	...	27.8	...	26.5
38	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
39	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
40	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
41	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
42	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
43	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
44	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
45	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
2	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
3	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
4	...	25.3	24.5	23.6	22.8	22.1	21.5	20.9	20.3	19.6
5	...	25.3	24.5	23.6	22.8	22.1	21.5	20.9	20.3	19.6
6	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
7	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
8	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
9	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
10	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
11	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
12	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
13	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
14	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
15	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
16	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
17	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
18	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
19	...	27.6	26.7	25.8	...	...	...	...	...	...
20	...	27.6	26.7	25.8	...	...	...	...	...	...
21	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
22	...	28.4	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
23	...	28.4	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
24	...	28.4	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
25	...	...	...	...	...	...	...	...	...	...
26	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	21.4
27	33.0	32.2	...	...	...	...	...	...	...	...
28	35.4	34.5	...	...	...	...	...	...	...	...
29	35.4	34.5	...	...	...	...	...	...	...	...
30	34.6	33.7	...	...	...	...	...	...	...	...
31	...	24.5	23.7	22.9	22.2	21.5	20.8	20.2	19.7	19.0
32	...	28.0	27.1	26.1	25.3	24.5	23.7	23.1	22.4	21.7
33	...	29.9	28.9	27.9	27.0	26.1	25.4	24.7	24.0	23.2
34	...	31.0	30.0	29.0	28.0	27.1	26.3	25.6	24.9	24.1
35	...	33.3	32.2	31.1	30.1	29.2	28.3	27.5	26.7	25.9
36	...	26.1	25.2	24.3	23.5	22.8	22.1	21.5	20.9	20.2
37	...	24.9	24.1	23.3	22.5	21.8	21.1	20.5	20.0	19.3
38	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
39	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
40	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
41	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
42	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
43	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
44	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
45	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Carbon steel	Plate	SA-662	B	K02203	...
2	Carbon steel	Plate, bar	SA/CSA-G40.21	44W	...	...
3	Carbon steel	Plate, bar	SA/CSA-G40.21	44W	...	...
4	Carbon steel	Plate	SA-537	...	K12437	1
5	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...
6	Carbon steel	Plate, bar	SA/CSA-G40.21	50W	...	...
7	Carbon steel	Plate, bar	SA/CSA-G40.21	50W	...	...
8	Carbon steel	Plate, sheet, bar	SA-572	50	...	...
9	Carbon steel	Round bar	SA-572	50	...	...
10	Carbon steel	Sheet, strip	SA-1011	50	SS	...
11	Carbon steel	Sheet, strip	SA-1011	50	HSLAS	1
(25) 12	Carbon steel	Bolting	SA-311	1018	G10180	A
13	Carbon steel	Sheet, strip	SA-1011	55	HSLAS	2
(25) 14	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT
15	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
16	Carbon steel	Plate	SA/AS 1548	PT460	...	...
17	Carbon steel	Plate	SA/AS 1548	PT460	...	...
(25) 18	Carbon steel	Forgings	SA/EN 10222-2	P280GH	...	N, NT, or QT
19	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
20	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
21	Carbon steel	Plate	SA/AS 1548	PT460	...	...
22	Carbon steel	Plate	SA/EN 10028-2	P295GH	...	...
23	Carbon steel	Plate	SA/AS 1548	PT460	...	...
24	Carbon steel	Plate	SA/GB 713	Q345R	...	...
25	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...
26	Carbon steel	Plate	SA/EN 10025-2	S355J2+N	...	...
27	Carbon steel	Plate	SA/EN 10025-2	S355J2+N	...	...
28	Carbon steel	Plate	SA/EN 10025-2	S355J2+N	...	...
29	Carbon steel	Plate	SA/EN 10025-2	S355J2+N	...	...
30	Carbon steel	Plate	SA/GB 713	Q345R	...	...
31	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...
32	Carbon steel	Plate	SA-455	...	K03300	...
33	Carbon steel	Bar	SA-675	70	...	...
34	Carbon steel	Forgings	SA-105	...	K03504	...
35	Carbon steel	Forgings	SA-181	...	K03502	70
36	Carbon steel	Castings	SA-216	WCB	J03002	...
37	Carbon steel	Forgings	SA-266	2	K03506	...
38	Carbon steel	Forgings	SA-266	4	K03017	...
39	Carbon steel	Forgings	SA-350	LF2	K03011	...
40	Carbon steel	Forgings	SA-508	1	K13502	...
41	Carbon steel	Forgings	SA-508	1A	K13502	...
42	Carbon steel	Forgings	SA-541	1	K03506	...
43	Carbon steel	Forgings	SA-541	1A	K03020	...
44	Carbon steel	Cast pipe	SA-660	WCB	J03003	...
45	Carbon steel	Forgings	SA-765	II	K03047	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	65	40	...
2	$2\frac{1}{2} < t \leq 8$	65	40	...
3	$t \leq 2\frac{1}{2}$	65	44	...
4	$2\frac{1}{2} < t \leq 4$	65	45	...
5	$2\frac{1}{2} < t \leq 4$	65	45	...
6	$2\frac{1}{2} < t \leq 6$	65	46	...
7	$t \leq 2\frac{1}{2}$	65	50	...
8	$t \leq 4$	65	50	...
9	$t \leq 11$	65	50	...
10	$t \leq 0.23$	65	50	...
11	...	65	50	...
12	$\frac{7}{8} < t \leq 1\frac{1}{4}$	65	55	...
13	...	65	55	...
14	$1.4 < t \leq 6.3$	66.5	37	...
15	$2\frac{1}{4} < t \leq 4$	66.5	37.5	...
16	$3\frac{1}{4} < t \leq 6$	66.5	38.5	...
17	$1\frac{1}{2} < t \leq 3\frac{1}{4}$	66.5	40	...
18	$t \leq 1.4$	66.5	40.5	...
19	$1\frac{1}{2} < t \leq 2\frac{1}{4}$	66.5	41.5	...
20	$\frac{5}{8} < t \leq 1\frac{1}{2}$	66.5	42	...
21	$\frac{5}{8} < t \leq 1\frac{1}{2}$	66.5	43	...
22	$\leq \frac{5}{8}$	66.5	43	...
23	$\leq \frac{5}{8}$	66.5	44	...
24	$6 < t \leq 10$	68	38.5	...
25	$6 < t \leq 10$	68	40.5	...
26	$2.48 < t \leq 3.15$	68	47	...
27	$1.57 < t \leq 2.48$	68	48.5	...
28	$0.63 < t \leq 1.57$	68	50	...
29	$0.12 \leq t \leq 0.63$	68	51.5	...
30	$4 < t \leq 6$	69.5	41.5	...
31	$4 < t \leq 6$	69.5	43	...
32	$0.58 < t \leq \frac{3}{4}$	70	35	...
33	...	70	35	...
34	...	70	36	...
35	...	70	36	...
36	...	70	36	...
37	...	70	36	...
38	...	70	36	...
39	...	70	36	...
40	...	70	36	...
41	...	70	36	...
42	...	70	36	...
43	...	70	36	...
44	...	70	36	...
45	...	70	36	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
2	40.0	37.8	36.8	36.1	35.4	34.8	34.1	...	32.5
3	44.0	41.6	40.5	39.7	39.0	38.2	37.5	...	35.8
4	45.0	42.3	41.2	40.5	39.8	...	38.4	...	36.7
5	45.0	42.3	41.2	40.5	39.8	...	38.4	...	36.7
6	46.0	43.4	42.4	41.5	40.7	40.0	39.2	...	37.4
7	50.0	47.2	46.0	45.1	44.3	43.5	42.6	...	40.6
8	50.0	46.3	44.2	42.2	40.5	39.1	37.6	36.5	35.4
9	50.0	46.3	44.2	42.2	40.5	39.1	37.6	36.5	35.4
10	50.0	46.3	44.2	42.2	40.5	39.1	37.6	36.5	35.4
11	50.0	46.3	44.2	42.2	40.5	39.1	37.6	36.5	35.4
12	55.0	51.6	50.4	49.5	48.6	...	47.1	...	44.8
13	55.0	51.0	48.6	46.4	44.5	42.8	41.3	40.2	38.9
14	37.0	34.6	33.7	33.0	32.5	32.0	31.4	...	29.9
15	37.5	35.2	34.4	33.7	33.2	...	32.0	...	30.6
16	38.5	...	35.3	...	34.1	...	32.9	...	31.4
17	40.0	...	36.6	...	35.4	...	34.2	...	32.6
18	40.6	38.0	37.0	36.3	35.7	35.1	34.4	...	32.9
19	41.5	39.0	38.0	37.3	36.7	...	35.5	...	33.8
20	42.0	39.5	38.5	37.8	37.2	...	35.9	...	34.2
21	43.0	...	39.4	...	38.0	...	36.7	...	35.0
22	43.0	40.4	39.4	38.7	38.0	...	36.7	...	35.0
23	44.0	...	40.3	...	38.9	...	37.6	...	35.9
24	38.4	36.1	35.2	34.6	34.1	33.5	32.9	...	31.4
25	40.6	...	37.1	...	35.9	...	34.7	...	33.1
26	47.1	...	...	...	...	...	...	...	...
27	48.6	...	...	...	...	...	...	...	...
28	50.0	...	...	...	...	...	...	...	...
29	51.5	...	...	...	...	...	...	...	...
30	41.3	38.8	37.9	37.2	36.6	36.0	35.4	34.5	33.7
31	42.8	...	39.1	...	37.9	...	36.6	...	34.9
32	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
33	35.0	32.9	32.1	31.5	31.0	...	29.9	...	28.5
34	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
35	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
36	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
37	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
38	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
39	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
40	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
41	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
42	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
43	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
44	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3
45	36.0	33.8	33.0	32.4	31.8	...	30.8	...	29.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
2	31.6	30.7	29.7	28.7	27.7	26.8	26.0	25.2	24.5	23.8
3	34.8	33.7	32.7	31.6	30.5	29.5	28.6	27.7	26.9	26.2
4	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
5	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
6	36.4	35.3	34.1	33.0	31.9	30.9	29.9	29.0	28.2	27.4
7	39.5	38.3	37.1	35.9	34.7	33.5	32.5	31.5	30.6	29.8
8	34.6	33.7	...	...	...	...	...	...	...	...
9	34.6	33.7	...	...	...	...	...	...	...	...
10	34.6	33.7	...	...	...	...	...	...	...	...
11	34.6	33.7	...	...	...	...	...	...	...	...
12	...	42.2	40.8	39.4	...	...	...	...	...	...
13	37.8	37.1	...	...	...	...	...	...	...	...
14	29.1	28.2	27.2	26.3	25.4	24.6	23.8	23.2	22.5	21.9
15	...	28.7	27.8	26.9	26.0	25.1	24.4	23.7	23.0	22.3
16	...	29.5	28.5	27.6	26.7	25.8	25.0	24.3	23.6	22.9
17	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
18	31.9	30.9	29.9	28.9	27.9	27.0	26.2	25.4	24.8	24.1
19	...	31.8	30.8	29.7	28.7	27.8	27.0	26.2	25.5	24.7
20	...	32.2	31.1	30.1	29.1	28.2	27.3	26.5	25.8	25.0
21	...	33.0	31.9	30.8	29.8	28.8	28.0	27.2	26.4	25.6
22	...	33.0	31.9	30.8	29.8	28.8	28.0	27.2	26.4	25.6
23	...	33.7	32.6	31.5	30.5	29.5	28.6	27.8	27.0	26.2
24	30.5	29.5	28.5	27.5	26.6	25.8	25.0	24.3	23.6	22.8
25	...	31.1	30.1	29.0	28.1	27.2	26.4	25.7	25.0	24.2
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	32.7	31.7	30.7	29.6	28.6	27.7	26.9	26.1	25.3	24.5
31	...	32.8	31.7	30.6	29.6	28.6	27.8	27.0	26.3	25.5
32	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
33	...	26.8	25.9	25.1	24.2	23.5	22.8	22.1	21.5	20.8
34	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
35	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
36	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
37	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
38	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
39	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
40	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
41	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
42	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
43	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
44	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4
45	...	27.6	26.7	25.8	24.9	24.1	23.4	22.8	22.1	21.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Carbon steel	Plate	SA-515	70	K03101	...
2	Carbon steel	Plate	SA-516	70	K02700	...
3	Carbon steel	Wld. pipe	SA-671	CB70	K03101	...
4	Carbon steel	Wld. pipe	SA-671	CC70	K02700	...
5	Carbon steel	Wld. pipe	SA-672	B70	K03101	...
6	Carbon steel	Wld. pipe	SA-672	C70	K02700	...
7	Carbon steel	Smls. pipe	SA-106	C	K03501	...
8	Carbon steel	Wld. tube	SA-178	D	...	...
9	Carbon steel	Smls. tube	SA-210	C	K03501	...
10	Carbon steel	Castings	SA-216	WCC	J02503	...
11	Carbon steel	Smls. & wld. fittings	SA-234	WPC	K03501	...
12	Carbon steel	Castings	SA-352	LCC	J02505	...
13	Carbon steel	Castings	SA-487	16	...	A
14	Carbon steel	Plate	SA-537	...	K12437	3
15	Carbon steel	Smls. tube	SA-556	C2	K03006	...
(25) 16	...	...	...	...	...	...
17	Carbon steel	Cast pipe	SA-660	WCC	J02505	...
18	Carbon steel	Bar	SA-696	C	K03200	...
19	Carbon steel	Sheet	SA-414	F	K03102	...
20	Carbon steel	Plate	SA-662	C	K02007	...
21	Carbon steel	Plate	SA-537	...	K12437	2
22	Carbon steel	Plate	SA-738	C	K02008	...
23	Carbon steel	Plate	SA-537	...	K12437	1
24	Carbon steel	Wld. pipe	SA-671	CD70	K12437	...
25	Carbon steel	Wld. pipe	SA-672	D70	K12437	...
26	Carbon steel	Wld. pipe	SA-691	CMSH-70	K12437	...
27	Carbon steel	Plate	SA-841	A	...	1
28	Carbon steel	Plate, sheet, bar	SA-572	55	...	...
29	Carbon steel	Round bar	SA-572	55	...	...
30	Carbon steel	Sheet, strip	SA-1011	55	HSLAS	1
(25) 31	Carbon steel	Bolting	SA-311	1018	G10180	A
32	Carbon steel	Sheet, strip	SA-1011	60	HSLAS	2
(25) 33	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT
(25) 34	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT
35	Carbon steel	Plate	SA/GB 713	Q345R	...	...
36	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...
37	Carbon steel	Plate	SA/GB 713	Q345R	...	...
38	Carbon steel	Plate	SA/GB 713	Q345R	...	...
39	Carbon steel	Plate	SA-455	...	K03300	...
(25) 40	Carbon steel	Forgings	SA/EN 10222-2	P305GH	...	N, NT, or QT
41	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...
42	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...
43	Carbon steel	Plate	SA/GB 713	Q345R	...	...
44	Carbon steel	Plate	SA/EN 10025-2	S355J2+N	...	...
45	Carbon steel	Plate	SA/EN 10028-2	P355GH	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	70	38	...
2	...	70	38	...
3	...	70	38	...
4	...	70	38	...
5	...	70	38	...
6	...	70	38	...
7	...	70	40	...
8	...	70	40	...
9	...	70	40	...
10	...	70	40	...
11	...	70	40	...
12	...	70	40	...
13	...	70	40	...
14	$4 < t \leq 6$	70	40	...
15	...	70	40	...
16	...	...	...	...
17	...	70	40	...
18	...	70	40	...
19	...	70	42	...
20	...	70	43	...
21	$4 < t \leq 6$	70	46	...
22	$4 < t \leq 6$	70	46	...
23	$\leq 2\frac{1}{2}$	70	50	...
24	$\leq 2\frac{1}{2}$	70	50	...
25	$\leq 2\frac{1}{2}$	70	50	...
26	$\leq 2\frac{1}{2}$	70	50	...
27	≤ 4	70	50	...
28	$t \leq 2$	70	55	...
29	$t \leq 3\frac{1}{2}$	70	55	...
30	...	70	55	...
31	$t \leq \frac{7}{8}$	70	60	...
32	...	70	60	...
33	$2.8 < t \leq 6.3$	71	40.5	...
34	$1.4 < t \leq 2.8$	74	41.5	...
35	$2\frac{1}{4} < t \leq 4$	71	44	...
36	$2.5 < t \leq 4$	71	45.5	...
37	$1.5 < t \leq 2\frac{1}{4}$	71	45.5	...
38	$\frac{5}{8} < t \leq 1.5$	72.5	47	...
39	$\frac{3}{8} < t \leq \frac{5}{8}$	73	37	...
40	$t \leq 1.4$	74	44	...
41	$1.5 < t \leq 2.5$	74	48.5	...
42	$\frac{5}{8} < t \leq 1.5$	74	50	...
43	$\frac{1}{8} \leq t \leq \frac{5}{8}$	74	50	...
44	$t < 0.12$	74	51.5	...
45	$\leq \frac{5}{8}$	74	51.5	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
2	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
3	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
4	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
5	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
6	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
7	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
8	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
9	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
10	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
11	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
12	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
13	40.0	37.2	35.7	34.4	33.4	...	31.8	...	30.5
14	40.0	37.1	35.3	33.8	32.4	...	30.0	...	28.3
15	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
16	...	...	...	...	...	...	...	...	...
17	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
18	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
19	42.0	39.5	38.5	37.8	37.2	...	35.9	...	34.2
20	43.0	40.4	39.4	38.7	38.0	...	36.7	...	35.0
21	46.0	42.6	40.6	38.8	37.2	...	34.6	...	32.5
22	46.0	42.6	40.6	38.8	37.2	...	34.6	...	32.5
23	50.0	46.3	44.2	42.2	40.5	...	37.6	...	35.4
24	50.0	46.3	44.2	42.2	40.5	...	37.6	...	35.4
25	50.0	46.3	44.2	42.2	40.5	...	37.6	...	35.4
26	50.0	46.3	44.2	42.2	40.5	...	37.6	...	35.4
27	50.0	...	46.1	...	43.8	...	42.3	...	41.3
28	55.0	51.0	48.6	46.4	44.5	42.8	41.3	40.2	38.9
29	55.0	51.0	48.6	46.4	44.5	42.8	41.3	40.2	38.9
30	55.0	51.0	48.6	46.4	44.5	42.8	41.3	40.2	38.9
31	60.0	56.3	55.0	54.0	53.0	...	51.3	...	48.8
32	60.0	55.8	53.0	50.7	48.6	46.6	45.1	43.9	42.4
33	40.6	38.0	37.0	36.3	35.7	35.1	34.4	...	32.9
34	41.3	38.7	37.7	36.9	36.3	35.7	35.1	...	33.4
35	44.2	41.5	40.6	39.8	39.2	38.6	37.8	37.0	36.1
36	45.7	...	41.7	...	40.4	...	39.1	...	37.3
37	45.7	42.9	41.9	41.1	40.5	39.8	39.1	38.2	37.3
38	47.1	44.3	43.2	42.4	41.8	41.1	40.3	39.4	38.5
39	37.0	34.8	33.9	33.3	32.7	...	31.6	...	30.2
40	44.2	41.4	40.3	39.5	38.9	38.2	37.5	...	35.8
41	48.6	...	44.4	...	43.0	...	41.6	...	39.6
42	50.0	...	45.7	...	44.3	...	42.8	...	40.8
43	50.0	47.0	45.9	45.0	44.3	43.6	42.8	41.9	40.8
44	51.5	...	...	...	...	...	...	...	...
45	51.5	...	47.0	...	45.6	...	44.1	...	42.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
2	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
3	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
4	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
5	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
6	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
7	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
8	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
9	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
10	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
11	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
12	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
13	...	29.3	28.7	28.0	27.1	26.2	...	...	...	...
14	...	27.0	26.4	25.8	25.2	24.4	...	...	...	...
15	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
16	...	...	...	...	...	...	...	...	...	...
17	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
18	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
19	...	32.2	31.1	30.1	29.1	28.2	27.3	26.5	25.8	25.0
20	...	33.0	31.9	30.8	29.8	28.8	28.0	27.2	26.4	25.6
21	...	31.0	30.3	29.7	28.9	28.1	...	...	...	...
22	...	31.0	30.3	29.7	28.9	28.1	...	...	...	...
23	...	33.7	33.0	32.3	31.5	30.5	...	...	...	...
24	...	33.7	33.0	32.3	31.5	30.5	...	...	...	...
25	...	33.7	33.0	32.3	31.5	30.5	...	...	...	...
26	...	33.7	33.0	32.3	31.5	30.5	...	...	...	...
27	...	40.1	39.3	38.1	36.7	34.9	...	...	...	...
28	37.8	37.1	...	...	...	...	...	...	...	...
29	37.8	37.1	...	...	...	...	...	...	...	...
30	37.8	37.1	...	...	...	...	...	...	...	...
31	...	46.0	44.5	43.0	...	...	...	...	...	...
32	41.2	40.5	...	...	...	...	...	...	...	...
33	31.9	30.9	29.9	28.9	27.9	27.0	26.2	25.4	24.8	24.1
34	32.5	31.5	30.4	29.4	28.4	27.5	26.6	25.9	25.2	24.5
35	35.0	33.9	32.8	31.7	30.6	29.7	28.8	27.9	27.1	26.2
36	...	35.0	33.8	32.7	31.6	30.6	29.7	28.9	28.1	27.2
37	36.2	35.1	33.9	32.7	31.6	30.6	29.7	28.8	28.0	27.1
38	37.3	36.2	35.0	33.8	32.6	31.6	30.6	29.8	28.9	28.0
39	...	28.4	27.4	26.5	25.6	24.8	24.1	23.4	22.7	22.0
40	34.8	33.7	32.6	31.4	30.4	29.4	28.5	27.7	27.0	26.2
41	...	37.2	36.0	34.7	33.6	32.5	31.6	30.7	29.9	28.9
42	...	38.3	37.0	35.8	34.6	33.5	32.5	31.6	30.8	29.8
43	39.6	38.4	37.1	35.9	34.7	33.5	32.5	31.6	30.7	29.7
44	...	...	...	...	...	...	...	...	...	...
45	...	39.4	38.1	36.8	35.6	34.5	33.5	32.5	31.6	30.6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Carbon steel	Forgings	SA-266	3	K05001	...
2	Carbon steel	Plate	SA-455	...	K03300	...
3	Carbon steel	Plate	SA-299	A	K02803	...
4	Carbon steel	Wld. pipe	SA-671	CK75	K02803	...
5	Carbon steel	Wld. pipe	SA-672	N75	K02803	...
6	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...
7	Carbon steel	Plate	SA-299	A	K02803	...
8	Carbon steel	Wld. pipe	SA-691	CMS-75	K02803	...
9	Carbon steel	Forgings	SA-372	B	K04001	...
10	Carbon steel	Sheet	SA-414	G	K03103	...
11	Carbon steel	Plate	SA-738	A	K12447	...
12	Carbon steel	Plate	SA-537	...	K12437	3
13	Carbon steel	Plate	SA-537	...	K12437	2
14	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...
15	Carbon steel	Plate	SA-738	C	K02008	...
16	Carbon steel	Plate, sheet, bar	SA-572	60	...	...
17	Carbon steel	Round bar	SA-572	60	...	...
18	Carbon steel	Sheet, strip	SA-1011	60	HSLAS	1
19	Carbon steel	Plate	SA-299	B	K02803	...
20	Carbon steel	Plate	SA-299	B	K02803	...
21	Carbon steel	Forgings	SA-765	IV	K02009	...
22	Carbon steel	Plate	SA-537	...	K12437	3
23	Carbon steel	Plate	SA-537	...	K12437	2
24	Carbon steel	Wld. pipe	SA-671	CD80	K12437	...
25	Carbon steel	Wld. pipe	SA-672	D80	K12437	...
26	Carbon steel	Wld. pipe	SA-691	CMSH-80	K12437	...
27	Carbon steel	Plate	SA-738	C	K02008	...
28	Carbon steel	Plate	SA-841	B	...	2
29	Carbon steel	Plate, sheet, bar	SA-572	65	...	...
(25) 30	Carbon steel	Bolting	SA-311	1035	G10350	A
31	Carbon steel	Plate	SA-612	...	K02900	...
32	Carbon steel	Plate	SA-841	F	...	6
33	Carbon steel	Plate	SA-612	...	K02900	...
34	Carbon steel	Plate	SA-738	B	K12007	...
(25) 35	Carbon steel	Bolting	SA-311	1035	G10350	A
36	Carbon steel	Plate	SA-841	F	...	7
37	Carbon steel	Forgings	SA-372	C	K04801	...
38	Carbon steel	Bolting	SA-449	...	K04200	...
39	Carbon steel	Plate	SA-724	A	K11831	...
40	Carbon steel	Plate	SA-724	C	K12037	...
(25) 41	Carbon steel	Bolting	SA-311	1045	G10450	A
42	Carbon steel	Plate	SA-724	B	K12031	...
(25) 43	Carbon steel	Bolting	SA-311	1045	G10450	A
(25) 44	Carbon steel	Bolting	SA-311	1050	G10500	A
(25) 45	Carbon steel	Bolting	SA-311	1050	G10500	A

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	75	37.5	...
2	$\leq \frac{3}{8}$	75	38	...
3	>1	75	40	...
4	>1	75	40	...
5	>1	75	40	...
6	>1	75	40	...
7	≤ 1	75	42	...
8	≤ 1	75	42	...
9	...	75	45	...
10	...	75	45	...
11	...	75	45	...
12	$2\frac{1}{2} < t \leq 4$	75	50	...
13	$2\frac{1}{2} < t \leq 4$	75	55	...
14	$2\frac{1}{2} < t \leq 4$	75	55	...
15	$2\frac{1}{2} < t \leq 4$	75	55	...
16	$t \leq 1\frac{1}{4}$	75	60	...
17	$t \leq 3\frac{1}{2}$	75	60	...
18	...	75	60	...
19	>1	80	45	...
20	≤ 1	80	47	...
21	...	80	50	...
22	$\leq 2\frac{1}{2}$	80	55	...
23	$\leq 2\frac{1}{2}$	80	60	...
24	$\leq 2\frac{1}{2}$	80	60	...
25	$\leq 2\frac{1}{2}$	80	60	...
26	$\leq 2\frac{1}{2}$	80	60	...
27	$\leq 2\frac{1}{2}$	80	60	...
28	≤ 4	80	60	...
29	$t \leq 1\frac{1}{4}$	80	65	...
30	$\frac{7}{8} < t \leq 1\frac{1}{4}$	80	70	...
31	$\frac{1}{2} < t \leq 1$	81	50	...
32	$t \leq 1.25$	82	70	...
33	$\leq \frac{1}{2}$	83	50	...
34	...	85	60	...
35	$t \leq \frac{7}{8}$	85	75	...
36	$t \leq 1$	86	75	...
37	...	90	55	...
38	$1\frac{1}{2} < t \leq 3$	90	58	...
39	...	90	70	...
40	...	90	70	...
41	$\frac{7}{8} < t \leq 1\frac{1}{4}$	90	80	...
42	...	95	75	...
43	$t \leq \frac{7}{8}$	95	85	...
44	$\frac{7}{8} < t \leq 1\frac{1}{4}$	95	85	...
45	$t \leq \frac{7}{8}$	100	90	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	37.5	35.2	34.4	33.7	33.2	...	32.0	...	30.6
2	38.0	35.7	34.8	34.2	33.6	...	32.5	...	31.0
3	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
4	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
5	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
6	40.0	37.6	36.6	36.0	35.4	...	34.2	...	32.6
7	42.0	39.5	38.5	37.8	37.2	...	35.9	...	34.2
8	42.0	39.5	38.5	37.8	37.2	...	35.9	...	34.2
9	45.0	42.3	41.2	40.5	39.8	...	38.4	...	36.7
10	45.0	42.3	41.2	40.5	39.8	...	38.4	...	36.7
11	45.0	42.3	41.2	40.5	39.8	...	38.4	...	36.7
12	50.0	46.3	44.2	42.2	40.5	...	37.6	...	35.4
13	55.0	51.0	48.6	46.4	44.5	...	41.3	...	38.9
14	55.0	51.0	48.6	46.4	44.5	...	41.3	...	38.9
15	55.0	51.0	48.6	46.4	44.5	...	41.3	...	38.9
16	60.0	55.8	53.0	50.7	48.6	46.6	45.1	43.9	42.4
17	60.0	55.8	53.0	50.7	48.6	46.6	45.1	43.9	42.4
18	60.0	55.8	53.0	50.7	48.6	46.6	45.1	43.9	42.4
19	45.0	...	41.2	...	39.8	...	38.4	...	36.7
20	47.0	...	43.1	...	41.6	...	40.2	...	38.3
21	50.0	47.6	45.8	44.5	43.5	...	41.4	...	39.7
22	55.0	51.0	48.6	46.4	44.5	...	41.3	...	38.9
23	60.0	55.6	53.0	50.7	48.6	...	45.1	...	42.4
24	60.0	55.6	53.0	50.7	48.6	...	45.1	...	42.4
25	60.0	55.6	53.0	50.7	48.6	...	45.1	...	42.4
26	60.0	55.6	53.0	50.7	48.6	...	45.1	...	42.4
27	60.0	55.6	53.0	50.7	48.6	...	45.1	...	42.4
28	60.0	...	55.3	...	52.8	...	50.7	...	49.6
29	65.0	60.4	57.4	54.9	52.6	50.5	48.8	47.5	45.9
30	70.0	65.7	64.2	63	61.8	...	59.9	...	57
31	50.0	...	44.1	...	40.6	...	37.5	...	35.3
32	70.0	67.1	64.8	...	61.2	...	59.3	...	58.0
33	50.0	...	44.1	...	40.6	...	37.5	...	35.3
34	60.0	56.9	55.2	53.6	52.3	...	49.9	...	48.0
35	75.0	70.4	68.8	67.5	66.3	...	64.2	...	61
36	75.0	71.9	69.5	...	65.6	...	63.5	...	62.1
37	55.0	51.7	50.4	49.4	48.7	...	47.0	...	44.8
38	58.0	...	53.1	...	51.3	...	49.6	...	47.3
39	70.0	64.9	61.8	59.1	56.7	...	52.6	...	49.5
40	70.0	64.9	61.8	59.1	56.7	...	52.6	...	49.5
41	80.0	75.1	73.3	72	70.7	...	68.4	...	65.1
42	75.0	69.5	66.3	63.3	60.7	...	56.3	...	53.1
43	85.0	79.8	77.9	76.5	75.1	...	72.7	...	69.2
44	85.0	79.8	77.9	76.5	75.1	...	72.7	...	69.2
45	90.0	84.5	82.5	81	79.5	...	77	...	73.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	28.7	27.8	26.9	26.0	25.1	24.4	23.7	23.0	22.3
2	...	29.1	28.2	27.2	26.3	25.5	24.7	24.0	23.3	22.6
3	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
4	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
5	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
6	...	30.7	29.6	28.6	27.7	26.8	26.0	25.3	24.6	23.8
7	...	32.2	31.1	30.1	29.1	28.2	27.3	26.5	25.8	25.0
8	...	32.2	31.1	30.1	29.1	28.2	27.3	26.5	25.8	25.0
9	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
10	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
11	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
12	...	33.7	33.0	32.3	31.5	30.5	...	...	...	...
13	...	37.1	36.3	35.5	34.6	33.5	...	...	...	...
14	...	37.1	36.3	35.5	34.6	33.5	...	...	...	...
15	...	37.1	36.3	35.5	34.6	33.5	...	...	...	...
16	41.2	40.5	...	...	...	...	...	...	...	...
17	41.2	40.5	...	...	...	...	...	...	...	...
18	41.2	40.5	...	...	...	...	...	...	...	...
19	...	34.5	33.4	32.2	31.2	30.2	29.3	28.4	27.6	26.7
20	...	36.0	34.8	33.7	32.5	31.5	30.6	29.7	28.9	27.9
21	...	38.2	37.7	37.1	...	...	...	...	...	...
22	...	37.1	36.3	35.5	34.6	33.5	...	...	...	...
23	...	40.5	39.6	38.7	37.7	36.6	...	...	...	...
24	...	40.5	39.6	38.7	37.7	36.6	...	...	...	...
25	...	40.5	39.6	38.7	37.7	36.6	...	...	...	...
26	...	40.5	39.6	38.7	37.7	36.6	...	...	...	...
27	...	40.5	39.6	38.7	37.7	36.6	...	...	...	...
28	...	48.2	47.1	45.7	44.0	41.9	...	...	...	...
29	44.7	43.9	...	...	...	...	...	...	...	...
30	...	53.7	51.9	50.2	...	...	...	...	...	...
31	...	33.9	33.0	32.1	...	...	...	...	...	...
32	...	56.1	55.0	...	...	...	...	...	...	...
33	...	33.9	33.0	32.1	...	...	...	...	...	...
34	...	46.3	45.4	44.5	43.5	42.4	...	...	...	...
35	...	57.5	55.6	53.8	...	...	...	...	...	...
36	...	60.1	58.9	...	...	...	...	...	...	...
37	...	42.2	40.8	39.4	38.1	36.9	35.8	34.8	33.8	32.7
38	...	44.5	43.0	41.5	40.2	38.9	37.7	36.7	...	...
39	...	47.2	46.2	45.2	44.0	42.7	...	...	...	...
40	...	47.2	46.2	45.2	44.0	42.7	...	...	...	...
41	...	61.3	59.3	57.3	...	...	...	...	...	...
42	...	50.6	49.5	48.4	47.2	45.7	...	...	...	...
43	...	65.2	63	60.9	...	...	...	...	...	...
44	...	65.2	63	60.9	...	...	...	...	...	...
45	...	69	66.8	64.5	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
(25) 1	...	...	...	...	...	...
(25) 2	Carbon steel	Bolting	SA-325	1	K02706	...
3	Carbon steel	Bolting	SA-449	...	K04200	...
4	Carbon steel	Bolting	SA-354	BC	K04100	...
(25) 5	Carbon steel	Bolting	SA-311	1045	G10450	B
6	Carbon steel	Bolting	SA-325	1	K02706	...
7	Carbon steel	Bolting	SA-449	...	K04200	...
8	Carbon steel	Bolting	SA-354	BC	K04100	...
9	Carbon steel	Bolting	SA-354	BD	K04100	...
10	Carbon steel	Bolting	SA-354	BD	K04100	...
11	Carbon steel	Flat wire	SA-905	...	...	2
12	Carbon steel	Flat wire	SA-905	...	...	2
13	Carbon steel	Flat wire	SA-905	...	...	2
14	Carbon steel	Flat wire	SA-905	...	...	2
15	Carbon steel	Flat wire	SA-905	...	...	2
16	Carbon steel	Flat wire	SA-905	...	...	1
17	Carbon steel	Flat wire	SA-905	...	...	1
18	Carbon steel	Flat wire	SA-905	...	...	1
19	Carbon steel	Flat wire	SA-905	...	...	1
20	Carbon steel	Flat wire	SA-905	...	...	1
21	Ductile cast iron	Castings	SA-874	...	...	...
22	Ductile cast iron	Castings	SA/JIS G5504	FCD 300 LT	...	...
23	C-Mn-Si-Cb	Plate	SA-737	B	K12001	...
24	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490	...	...
25	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490	...	...
26	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490	...	...
27	C-Mn-Si-Cb	Plate	SA/AS 1548	PT490	...	...
28	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized
29	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized
30	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized
31	C-Mn-Si-Cb	Plate	SA/GB 713	Q370R	...	Normalized
32	C-Mn-Si-V	Plate	SA-737	C	K12202	...
33	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...
34	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...
35	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...
36	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...
37	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...
38	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...
39	C-Mn-Si-V-Cb	Plate	SA-656	T3	...	...
40	C-Mn-Si-V-Cb	Plate	SA-656	T7	...	...
41	C-Mn-Ti	Plate, sheet	SA-562	...	K11224	...
42	C-Si-Ti	Forgings	SA-836	...	...	1
43	C-1/2Mo	Bolting	SA-320	L7A	G40370	...
(25) 44	Alloy steel	Bolting	SA/ISO 898-1	8.8	...	...
(25) 45	Alloy steel	Bolting	SA/ISO 898-1	8.8	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	...	...	...
2	$1 < t \leq 1\frac{1}{2}$	105	81	...
3	$1 < t < 1\frac{1}{2}$	105	81	...
4	$2\frac{1}{2} < t \leq 4$	115	99	...
5	$t \leq 3$	115	100	...
6	$\frac{1}{2} \leq t \leq 1$	120	92	...
7	≤ 1	120	92	...
8	$\frac{1}{4} < t \leq 2\frac{1}{2}$	125	109	...
9	$2\frac{1}{2} < t \leq 4$	140	115	...
10	$\frac{1}{4} < t \leq 2\frac{1}{2}$	150	130	...
11	0.059	246	210	(1)
12	0.051	250	214	(1)
13	0.040	256	221	(1)
14	0.030	262	226	(1)
15	0.020	268	232	(1)
16	0.059	275	239	(1)
17	0.051	280	243	(1)
18	0.040	285	250	(1)
19	0.030	290	255	(1)
20	0.020	296	260	(1)
21	$12 < t < 21$	43.5	29	...
22	$12 < t < 21$	43.5	29	...
23	...	70	50	...
24	$3\frac{1}{4} < t \leq 6$	71	46.5	...
25	$1\frac{1}{2} < t \leq 3\frac{1}{4}$	71	48	...
26	$\frac{5}{8} < t \leq 1\frac{1}{2}$	71	49.5	...
27	$\leq \frac{5}{8}$	71	52	...
28	$2.5 < t \leq 4$	74	48	...
29	$1.5 < t \leq 2.5$	75.5	49.5	...
30	$0.6 < t \leq 1.5$	77	52	...
31	$0.4 \leq t \leq 0.6$	77	53.5	...
32	...	80	60	...
33	≤ 2	60	50	...
34	≤ 2	60	50	...
35	$\leq 1\frac{1}{2}$	70	60	...
36	$\leq 1\frac{1}{2}$	70	60	...
37	≤ 1	80	70	...
38	≤ 1	80	70	...
39	$\leq \frac{3}{4}$	90	80	...
40	$\leq \frac{3}{4}$	90	80	...
41	...	55	30	...
42	...	55	25	...
43	$\leq 2\frac{1}{2}$	125	105	...
44	$d \leq \frac{5}{8}$	116	93	...
45	$d > \frac{5}{8}$	120	95.5	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...
2	81.0	...	71.6	...	65.6	...	60.8	...	57.3
3	81.0	...	71.6	...	65.6	...	60.8	...	57.3
4	99.0	...	90.7	...	87.6	...	84.6	...	80.7
5	100.0	93.9	91.7	90	88.3	...	85.6	...	81.4
6	92.0	...	81.3	...	74.5	...	69.1	...	65.1
7	92.0	...	81.3	...	74.5	...	69.1	...	65.1
8	109.0	...	99.9	...	96.4	...	93.1	...	88.8
9	115.0	...	105.4	...	101.7	...	98.3	...	93.7
10	130.0	...	119.1	...	115.0	...	111.0	...	105.9
11	210.0	...	...	...	...	...	...	...	...
12	214.0	...	...	...	...	...	...	...	...
13	221.0	...	...	...	...	...	...	...	...
14	226.0	...	...	...	...	...	...	...	...
15	232.0	...	...	...	...	...	...	...	...
16	239.0	...	224.0	...	...	...	...	...	...
17	243.0	...	228.0	...	...	...	...	...	...
18	250.0	...	234.0	...	...	...	...	...	...
19	255.0	...	239.0	...	...	...	...	...	...
20	260.0	...	244.0	...	...	...	...	...	...
21	29.0	...	25.4	...	24.1	...	23.5	...	23.1
22	29.0	...	25.4	...	24.1	...	23.5	...	23.1
23	50.0	47.9	45.8	43.6	41.4	...	37.7	...	35.3
24	46.5	...	42.6	...	38.5	...	35.0	...	32.8
25	48.0	...	44.0	...	39.7	...	36.2	...	33.9
26	49.5	...	45.4	...	41.0	...	37.3	...	34.9
27	52.0	...	47.7	...	43.0	...	39.2	...	36.7
28	47.9	46.2	44.0	41.7	39.5	37.6	36.0	...	33.8
29	49.3	47.4	45.3	43.0	40.7	38.7	37.1	...	34.8
30	52.2	50.2	48.0	45.5	43.1	41.0	39.3	...	36.9
31	53.7	51.6	49.3	46.8	44.3	42.1	40.3	...	37.9
32	60.0	57.5	55.0	52.3	49.7	...	45.2	...	42.3
33	50.0	...	45.8	...	41.4	...	37.7	...	35.3
34	50.0	...	45.8	...	41.4	...	37.7	...	35.3
35	60.0	...	55.0	...	49.7	...	45.2	...	42.3
36	60.0	...	55.0	...	49.7	...	45.2	...	42.3
37	70.0	...	64.2	...	57.9	...	52.7	...	49.4
38	70.0	...	64.2	...	57.9	...	52.7	...	49.4
39	80.0	...	73.4	...	66.2	...	60.3	...	56.5
40	80.0	...	73.4	...	66.2	...	60.3	...	56.5
41	30.0	27.3	25.8	24.7	24.0	...	23.4	...	23.4
42	25.0	22.7	21.5	20.6	20.0	...	19.5	...	19.5
43	105.0	...	96.2	...	92.9	...	89.7	...	85.6
44	92.8	...	86.6	...	83.1	...	...	...	...
45	95.7	...	89.3	...	85.7	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	54.6	53.4	52.3	51.0	49.4	47.4	44.8	41.4	36.9
3	...	54.6	53.4	52.3	51.0	49.4	47.4	44.8	41.4	36.9
4	...	75.9	73.4	70.9	68.5	66.4	64.4	62.6	60.8	58.8
5	...	76.7	74.2	71.7	...	...	...	...	...	...
6	...	62.0	60.7	59.3	57.9	56.1	53.9	50.9	47.0	41.9
7	...	62.0	60.7	59.3	57.9	56.1	53.9	50.9	47.0	41.9
8	...	83.6	80.8	78.1	75.5	73.1	70.9	68.9	66.9	64.8
9	...	88.2	85.2	82.3	79.6	77.1	74.8	72.7	70.6	68.4
10	...	99.6	96.2	93.0	89.8	87.0	84.3	81.9	79.5	76.9
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	22.5	22.1	...	...	...	...	...	...	...
22	...	22.5	22.1	...	...	...	...	...	...	...
23	...	33.9	33.4	32.9	32.2	31.2	29.9	28.1	25.9	25.9
24	...	31.6	31.1	30.6	29.9	29.0	27.8	26.1	24.1	21.6
25	...	32.6	32.1	31.6	30.9	30.0	28.7	27.0	24.8	22.3
26	...	33.6	33.1	32.6	31.9	30.9	29.6	27.8	25.6	22.0
27	...	35.3	34.8	34.2	33.5	32.5	31.1	29.2	26.9	24.1
28	33.1	32.6	32.1	31.5	30.7	29.7	28.5	27.0	25.3	23.7
29	34.1	33.6	33.1	32.5	31.7	30.6	29.3	27.8	26.1	24.6
30	36.1	35.6	35.0	34.4	33.5	32.4	31.0	29.4	27.7	26.0
31	37.1	36.5	36.0	35.3	34.5	33.3	31.9	30.2	28.4	26.7
32	...	40.7	40.1	39.5	38.6	37.5	35.9	33.7	31.0	31.0
33	...	33.9	33.4	...	...	...	...	...	...	...
34	...	33.9	33.4	...	...	...	...	...	...	...
35	...	40.7	40.1	...	...	...	...	...	...	...
36	...	40.7	40.1	...	...	...	...	...	...	...
37	...	47.5	46.8	...	...	...	...	...	...	...
38	...	47.5	46.8	...	...	...	...	...	...	...
39	...	54.3	53.5	...	...	...	...	...	...	...
40	...	54.3	53.5	...	...	...	...	...	...	...
41	...	23.4	23.4	23.3	22.9	...	...	...	...	...
42	...	19.5	19.5	19.4	19.1	...	...	...	...	...
43	...	80.5	77.8	75.2	72.7	70.4	68.3	66.4	64.5	62.4
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037	G40370	...
2	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042	G40420	...
3	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4140	G41400	...
4	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4037	G40370	...
5	C- $\frac{1}{4}$ Mo	Bolting	SA-574	4042	G40420	...
6	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...
7	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...
8	C-0.3Mo	Smls. tube	SA/EN 10216-2	16Mo3	...	...
9	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1b	K11422	...
10	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1b	K11422	...
11	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1	K11522	...
12	C- $\frac{1}{2}$ Mo	Smls. & wld. fittings	SA-234	WP1	K12821	...
13	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1	K11522	...
14	C- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P1	K11522	...
15	C- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP1	K11522	...
16	C- $\frac{1}{2}$ Mo	Smls. tube	SA-209	T1a	K12023	...
17	C- $\frac{1}{2}$ Mo	Wld. tube	SA-250	T1a	K12023	...
18	C- $\frac{1}{2}$ Mo	Castings	SA-217	WC1	J12524	...
19	C- $\frac{1}{2}$ Mo	Castings	SA-352	LC1	J12522	...
20	C- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP1	J12521	...
21	C- $\frac{1}{2}$ Mo	Plate	SA-204	A	K11820	...
22	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L65	K11820	...
23	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-65	K11820	...
24	C- $\frac{1}{2}$ Mo	Forgings	SA-182	F1	K12822	...
25	C- $\frac{1}{2}$ Mo	Plate	SA-204	B	K12020	...
26	C- $\frac{1}{2}$ Mo	Forgings	SA-336	F1	K12520	...
27	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L70	K12020	...
28	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-70	K12020	...
29	C- $\frac{1}{2}$ Mo	Plate	SA-204	C	K12320	...
30	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	L75	K12320	...
31	C- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	CM-75	K12320	...
32	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	55
33	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	55
34	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	65
35	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	65
36	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	G	K13049	70
37	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo	Forgings	SA-372	H	K13547	70
38	$\frac{1}{2}$ Cr- $\frac{1}{5}$ Mo-V	Plate	SA-517	B	K11630	...
39	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Plate	SA-517	A	K11856	...
40	$\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-Si	Forgings	SA-592	A	K11856	...
41	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P2	K11547	...
42	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP2	K11547	...
43	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Plate	SA-387	2	K12143	1
44	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	$\frac{1}{2}$ CR	K12143	...
45	$\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T2	K11547	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	$\geq \frac{5}{8}$	170	135	...
2	$\geq \frac{5}{8}$	170	135	...
3	$\geq \frac{5}{8}$	170	135	...
4	$\leq \frac{1}{2}$	180	140	...
5	$\leq \frac{1}{2}$	180	140	...
6	$1\frac{5}{8} < t \leq 2\frac{1}{2}$	65.5	37.5	...
7	$\frac{5}{8} < t \leq 1\frac{5}{8}$	65.5	39	...
8	$t \leq \frac{5}{8}$	65.5	40.5	...
9	...	53	28	...
10	...	53	28	...
11	...	55	30	...
12	...	55	30	...
13	...	55	30	...
14	...	55	30	...
15	...	55	30	...
16	...	60	32	...
17	...	60	32	...
18	...	65	35	...
19	...	65	35	...
20	...	65	35	...
21	...	65	37	...
22	...	65	37	...
23	...	65	37	...
24	...	70	40	...
25	...	70	40	...
26	...	70	40	...
27	...	70	40	...
28	...	70	40	...
29	...	75	43	...
30	...	75	43	...
31	...	75	43	...
32	...	85	55	...
33	...	85	55	...
34	...	105	65	...
35	...	105	65	...
36	...	120	70	...
37	...	120	70	...
38	$\leq 1\frac{1}{4}$	115	100	...
39	$\leq 1\frac{1}{4}$	115	100	...
40	$\leq 2\frac{1}{2}$	115	100	...
41	...	55	30	...
42	...	55	30	...
43	...	55	33	...
44	...	55	33	...
45	...	60	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	135.0	...	126.9	...	121.7	...	117.6	...	114.0
2	135.0	...	126.9	...	121.7	...	117.6	...	114.0
3	135.0	...	126.9	...	121.7	...	117.6	...	114.0
4	140.0	...	131.6	...	126.2	...	121.9	...	118.2
5	140.0	...	131.6	...	126.2	...	121.9	...	118.2
6	37.7	36.3	35.4	34.7	34.0	33.4	32.8	32.3	31.8
7	39.2	37.7	36.8	36.0	35.3	34.7	34.1	33.6	33.1
8	40.6	39.1	38.2	37.4	36.6	36.0	35.4	34.8	34.3
9	28.0	26.9	26.3	25.8	25.2	...	24.4	...	23.6
10	28.0	26.9	26.3	25.8	25.2	...	24.4	...	23.6
11	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
12	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
13	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
14	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
15	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
16	32.0	30.8	30.1	29.4	28.9	...	27.9	...	27.0
17	32.0	30.8	30.1	29.4	28.9	...	27.9	...	27.0
18	35.0	33.7	32.9	32.2	31.6	...	30.5	...	29.5
19	35.0	33.7	32.9	32.2	31.6	...	30.5	...	29.5
20	35.0	33.7	32.9	32.2	31.6	...	30.5	...	29.5
21	37.0	35.6	34.8	34.0	33.4	...	32.2	...	31.2
22	37.0	35.6	34.8	34.0	33.4	...	32.2	...	31.2
23	37.0	35.6	34.8	34.0	33.4	...	32.2	...	31.2
24	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
25	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
26	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
27	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
28	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
29	43.0	41.4	40.4	39.6	38.8	...	37.4	...	36.3
30	43.0	41.4	40.4	39.6	38.8	...	37.4	...	36.3
31	43.0	41.4	40.4	39.6	38.8	...	37.4	...	36.3
32	55.0	52.7	51.4	50.3	49.4	...	47.8	...	46.3
33	55.0	52.7	51.4	50.3	49.4	...	47.8	...	46.3
34	65.0	62.3	60.8	59.5	58.4	...	56.5	...	54.8
35	65.0	62.3	60.8	59.5	58.4	...	56.5	...	54.8
36	70.0	66.9	65.2	63.9	62.8	...	60.9	...	59.1
37	70.0	66.9	65.2	63.9	62.8	...	60.9	...	59.1
38	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
39	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
40	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
41	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
42	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
43	33.0	31.8	31.0	30.4	29.8	...	28.7	...	27.9
44	33.0	31.8	31.0	30.4	29.8	...	28.7	...	27.9
45	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	110.4	108.4	106.2	103.7	100.9	97.7	94.1	90.0	85.5
2	...	110.4	108.4	106.2	103.7	100.9	97.7	94.1	90.0	85.5
3	...	110.4	108.4	106.2	103.7	100.9	97.7	94.1	90.0	85.5
4	...	114.5	112.4	110.1	107.6	104.6	101.3	97.5	93.3	88.6
5	...	114.5	112.4	110.1	107.6	104.6	101.3	97.5	93.3	88.6
6	31.3	30.8	30.3	29.7	29.0	28.2	27.3	26.3	25.1	23.9
7	32.5	32.0	31.4	30.8	30.1	29.3	28.3	27.3	26.1	24.8
8	33.8	33.2	32.6	31.9	31.2	30.4	29.4	28.3	27.1	25.7
9	...	22.9	22.5	22.0	21.5	20.9	20.3	19.5	18.7	17.7
10	...	22.9	22.5	22.0	21.5	20.9	20.3	19.5	18.7	17.7
11	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
12	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
13	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
14	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
15	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
16	...	26.2	25.7	25.2	24.6	23.9	23.2	22.3	21.3	20.3
17	...	26.2	25.7	25.2	24.6	23.9	23.2	22.3	21.3	20.3
18	...	28.6	28.1	27.5	26.9	26.2	25.3	24.4	23.3	22.2
19	...	28.6	28.1	27.5	26.9	26.2	25.3	24.4	23.3	22.2
20	...	28.6	28.1	27.5	26.9	26.2	25.3	24.4	23.3	22.2
21	...	30.2	29.7	29.1	28.4	27.7	26.8	25.8	24.7	23.4
22	...	30.2	29.7	29.1	28.4	27.7	26.8	25.8	24.7	23.4
23	...	30.2	29.7	29.1	28.4	27.7	26.8	25.8	24.7	23.4
24	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
25	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
26	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
27	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
28	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
29	...	35.2	34.5	33.8	33.0	32.1	31.1	30.0	28.7	27.2
30	...	35.2	34.5	33.8	33.0	32.1	31.1	30.0	28.7	27.2
31	...	35.2	34.5	33.8	33.0	32.1	31.1	30.0	28.7	27.2
32	...	44.7	43.6	42.2	40.6	38.7	36.3	33.6	30.4	26.7
33	...	44.7	43.6	42.2	40.6	38.7	36.3	33.6	30.4	26.7
34	...	52.8	51.5	49.9	48.0	45.7	43.0	39.7	35.9	31.5
35	...	52.8	51.5	49.9	48.0	45.7	43.0	39.7	35.9	31.5
36	...	56.8	55.4	53.7	51.7	49.2	46.3	42.8	38.7	33.9
37	...	56.8	55.4	53.7	51.7	49.2	46.3	42.8	38.7	33.9
38	...	85.5	84.3	83.0	81.4	79.5	77.1	74.2	70.5	66.1
39	...	85.5	84.3	83.0	81.4	79.5	77.1	74.2	70.5	66.1
40	...	85.5	84.3	83.0	81.4	79.5	77.1	74.2	70.5	66.1
41	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
42	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
43	...	27.0	26.5	26.0	25.4	24.7	23.9	23.0	22.0	20.9
44	...	27.0	26.5	26.0	25.4	24.7	23.9	23.0	22.0	20.9
45	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP2	J11547	...
2	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F2	K12122	...
3	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	2	K12143	2
4	$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	$\frac{1}{2}\text{CR}$	K12143	...
5	$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	Wld. tube	SA-423	1	K11535	...
6	$\frac{3}{4}\text{Cr}-\frac{3}{4}\text{Ni}-\text{Cu}-\text{Al}$	Pipe	SA-333	4	K11267	...
7	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	55
8	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	55
9	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	55
10	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7	G41400	...
(25) 11	Alloy steel	Bolting	SA/ISO 898-1	9.8	...	...
12	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7M	G41400	...
13	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-320	L7M	G41400	...
14	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	65
15	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7	G41400	...
16	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	E	K13047	70
17	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	F	G41350	70
18	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	K13548	70
19	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-193	B7	G41400	...
20	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-320	L7	G41400	...
21	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Forgings	SA-372	J	G41370	110
22	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-574	4137	G41370	...
23	$1\text{Cr}-\frac{1}{5}\text{Mo}$	Bolting	SA-574	4137	G41370	...
(25) 24	$1\text{Cr}-\frac{1}{5}\text{Mo}-\text{B}$	Forgings	SA-372	R	G41371	110
25	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	12	K11757	1
26	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	1CR	K11757	...
27	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Cast pipe	SA-426	CP12	J11562	...
28	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-182	F12	K11562	1
29	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA-213	T12	K11562	...
30	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. & wld. fittings	SA-234	WP12	K12062	1
31	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. pipe	SA-335	P12	K11562	...
32	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forged pipe	SA-369	FP12	K11562	...
33	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT
34	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...
35	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...
36	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/GB 713	15CrMoR	...	NT
37	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT
38	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA/EN 10028-2	13CrMo4-5	...	...
39	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT
40	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA/EN 10216-2	13CrMo4-5	...	...
(25) 41	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT
42	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Smls. tube	SA/EN 10216-2	13CrMo4-5	...	...
(25) 43	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA/EN 10222-2	13CrMo4-5	...	NT or QT
44	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-387	12	K11757	2
45	$1\text{Cr}-\frac{1}{2}\text{Mo}$	Wld. pipe	SA-691	1CR	K11757	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	60	30	...
2	...	70	40	...
3	...	70	45	...
4	...	70	45	...
5	...	60	37	...
6	...	60	35	...
7	...	85	55	...
8	...	85	55	...
9	...	85	55	...
10	$4 < t \leq 7$	100	75	...
11	$d \leq \frac{5}{8}$	130.5	104.5	...
12	$\leq 2\frac{1}{2}$	100	80	...
13	$\leq 2\frac{1}{2}$	100	80	...
14	...	105	65	...
15	$2\frac{1}{2} < t \leq 4$	115	95	...
16	...	120	70	...
17	...	120	70	...
18	...	120	70	...
19	$\leq 2\frac{1}{2}$	125	105	...
20	$\leq 2\frac{1}{2}$	125	105	...
21	...	135	110	...
22	$\geq \frac{5}{8}$	170	135	...
23	$\leq \frac{1}{2}$	180	140	...
24	...	135	110	...
25	...	55	33	...
26	...	55	33	...
27	...	60	30	...
28	...	60	32	...
29	...	60	32	...
30	...	60	32	...
31	...	60	32	...
32	...	60	32	...
33	$10 < t \leq 20$	61	35	...
34	$6 < t \leq 10$	61	35.5	...
35	$4 < t \leq 6$	62.5	37	...
36	$4 < t \leq 8$	64	37	...
37	$4 < t \leq 10$	64	38.5	...
38	$2.5 < t \leq 4$	64	39	...
39	$2.8 < t \leq 4$	64	40	...
40	$1\frac{5}{8} < t \leq 2\frac{1}{2}$	64	40.5	...
41	$1.4 < t \leq 2.8$	64	41.5	...
42	$t \leq 1\frac{5}{8}$	64	42	...
43	$t \leq 1.4$	64	43	...
44	...	65	40	...
45	...	65	40	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.9	28.2	27.6	27.1	...	26.1	...	25.3
2	40.0	38.5	37.6	36.8	36.1	...	34.8	...	33.8
3	45.0	43.3	42.3	41.4	40.6	...	39.2	...	38.0
4	45.0	43.3	42.3	41.4	40.6	...	39.2	...	38.0
5	37.0	35.0	34.1	33.5	33.0	...	32.3	...	31.6
6	35.0	33.1	32.3	31.7	31.3	...	30.6	...	29.9
7	55.0	52.7	51.4	50.3	49.4	...	47.8	...	46.3
8	55.0	52.7	51.4	50.3	49.4	...	47.8	...	46.3
9	55.0	52.7	51.4	50.3	49.4	...	47.8	...	46.3
10	75.0	...	69.9	...	67.2	...	65.3	...	63.2
11	104.4	...	95.6	...	92.4	...	...	...	...
12	80.0	...	74.6	...	71.7	...	69.7	...	67.4
13	80.0	...	74.6	...	71.7	...	69.7	...	67.4
14	65.0	62.3	60.8	59.5	58.4	...	56.5	...	54.8
15	95.0	...	88.5	...	85.1	...	82.7	...	80.1
16	70.0	66.9	65.2	63.9	62.8	...	60.9	...	59.1
17	70.0	66.9	65.2	63.9	62.8	...	60.9	...	59.1
18	70.0	66.9	65.2	63.9	62.8	...	60.9	...	59.1
19	105.0	...	98.0	...	94.1	...	91.5	...	88.5
20	105.0	...	98.0	...	94.1	...	91.5	...	88.5
21	110.0	105.1	102.5	100.4	98.6	...	95.6	...	92.8
22	135.0	129.0	125.8	123.2	121.0	...	117.3	...	113.9
23	140.0	133.8	130.5	127.8	125.5	...	121.7	...	118.1
24	110.0	105.1	102.5	100.4	98.6	...	95.6	...	92.8
25	33.0	31.0	29.8	28.9	28.1	...	26.8	...	25.9
26	33.0	31.0	29.8	28.9	28.1	...	26.8	...	25.9
27	30.0	28.1	27.1	26.2	25.5	...	24.4	...	23.5
28	32.0	30.0	28.9	28.0	27.2	...	26.0	...	25.1
29	32.0	30.0	28.9	28.0	27.2	...	26.0	...	25.1
30	32.0	30.0	28.9	28.0	27.2	...	26.0	...	25.1
31	32.0	30.0	28.9	28.0	27.2	...	26.0	...	25.1
32	32.0	30.0	28.9	28.0	27.2	...	26.0	...	25.1
33	34.8	32.8	31.6	30.6	29.7	29.0	28.3	...	27.4
34	35.5	33.3	32.1	31.1	30.2	29.5	28.9	28.4	27.9
35	37.0	34.7	33.5	32.4	31.5	30.7	30.0	29.5	29.0
36	32.6	30.6	29.5	28.6	27.8	27.1	26.5	...	25.6
37	38.4	36.2	34.9	33.8	32.8	32.0	31.3	...	30.2
38	39.2	36.7	35.4	34.3	33.3	32.5	31.8	31.3	30.7
39	39.9	37.6	36.3	35.1	34.1	33.2	32.5	...	31.4
40	40.6	38.6	37.5	36.5	35.6	34.9	34.2	33.6	33.0
41	41.3	38.9	37.6	36.4	35.3	34.4	33.6	...	32.5
42	42.1	40.0	38.8	37.8	36.9	36.1	35.4	34.8	34.2
43	42.8	40.3	38.9	37.6	36.5	35.6	34.8	...	33.6
44	40.0	37.5	36.2	35.0	34.0	...	32.5	...	31.4
45	40.0	37.5	36.2	35.0	34.0	...	32.5	...	31.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	24.5	24.1	23.6	23.1	22.4	21.7	20.9	20.0	19.0
2	...	32.7	32.1	31.5	30.7	29.9	28.9	27.9	26.7	25.3
3	...	36.8	36.1	35.4	34.6	33.6	32.6	31.4	30.0	28.5
4	...	36.8	36.1	35.4	34.6	33.6	32.6	31.4	30.0	28.5
5	...	30.9	30.5	30.0	29.5	28.8	28.0	27.0	25.6	23.7
6	...	29.2	28.8	28.4	27.9	27.3	26.5	25.5	24.2	22.4
7	...	44.7	43.6	42.2	40.6	38.7	36.3	33.6	30.4	26.7
8	...	44.7	43.6	42.2	40.6	38.7	36.3	33.6	30.4	26.7
9	...	44.7	43.6	42.2	40.6	38.7	36.3	33.6	30.4	26.7
10	...	60.9	59.3	57.6	55.4	52.8	49.7	45.8	41.5	36.4
11	...	...	...	...	...	...	...	...	...	...
12	...	65.0	63.2	61.4	59.1	56.3	53.0	48.8	44.2	38.8
13	...	65.0	63.2	61.4	59.1	56.3	53.0	48.8	44.2	38.8
14	...	52.8	51.5	49.9	48.0	45.7	43.0	39.7	35.9	31.5
15	...	77.1	75.1	73.0	70.2	66.9	62.9	58.0	52.5	46.1
16	...	56.8	55.4	53.7	51.7	49.2	46.3	42.8	38.7	33.9
17	...	56.8	55.4	53.7	51.7	49.2	46.3	42.8	38.7	33.9
18	...	56.8	55.4	53.7	51.7	49.2	46.3	42.8	38.7	33.9
19	...	85.3	83.0	80.6	77.6	73.9	69.5	64.1	58.1	50.9
20	...	85.3	83.0	80.6	77.6	73.9	69.5	64.1	58.1	50.9
21	...	89.3	87.1	84.4	81.2	77.4	72.7	67.3	60.8	53.3
22	...	109.6	106.9	103.6	99.7	95.0	89.2	82.6	74.6	65.4
23	...	113.7	110.9	107.4	103.3	98.5	92.5	85.7	77.4	67.8
24	...	89.3	87.1	84.4	81.2	77.4	72.7	67.3	60.8	53.3
25	...	25.1	24.8	24.4	24.0	23.6	23.1	22.5	21.7	20.9
26	...	25.1	24.8	24.4	24.0	23.6	23.1	22.5	21.7	20.9
27	...	22.9	22.5	22.2	21.9	21.4	21.0	20.4	19.8	19.0
28	...	24.4	24.0	23.7	23.3	22.9	22.4	21.8	21.1	20.2
29	...	24.4	24.0	23.7	23.3	22.9	22.4	21.8	21.1	20.2
30	...	24.4	24.0	23.7	23.3	22.9	22.4	21.8	21.1	20.2
31	...	24.4	24.0	23.7	23.3	22.9	22.4	21.8	21.1	20.2
32	...	24.4	24.0	23.7	23.3	22.9	22.4	21.8	21.1	20.2
33	27.0	26.6	26.3	25.9	25.5	25.0	24.4	23.7	23.0	22.2
34	27.5	27.1	26.7	26.3	25.9	25.4	24.8	24.2	23.4	22.5
35	28.6	28.2	27.8	27.4	26.9	26.4	25.8	25.1	24.3	23.4
36	25.2	24.9	24.5	24.2	23.8	23.3	22.8	22.2	21.5	20.7
37	29.8	29.4	29.0	28.6	28.1	27.6	26.9	26.2	25.4	24.5
38	30.3	29.8	29.4	29.0	28.5	28.0	27.4	26.6	25.8	24.8
39	30.9	30.5	30.1	29.7	29.2	28.6	27.9	27.2	26.3	25.5
40	32.4	31.8	31.3	30.7	30.0	29.3	28.5	27.6	26.6	25.4
41	32.1	31.6	31.2	30.8	30.3	29.7	29.0	28.2	27.3	26.4
42	33.6	33.0	32.4	31.8	31.1	30.3	29.5	28.6	27.5	26.3
43	33.2	32.7	32.3	31.8	31.3	30.7	30.0	29.2	28.3	27.3
44	...	30.5	30.1	29.6	29.1	28.6	28.0	27.2	26.3	25.3
45	...	30.5	30.1	29.6	29.1	28.6	28.0	27.2	26.3	25.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR	...	NT
2	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...
3	1Cr- $\frac{1}{2}$ Mo	Plate	SA/GB 713	15CrMoR	...	NT
4	1Cr- $\frac{1}{2}$ Mo	Plate	SA/EN 10028-2	13CrMo4-5	...	...
5	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F12	K11564	2
6	1Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F12	K11564	...
7	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...
8	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...
9	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	5
10	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	5
11	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-193	B16	K14072	...
12	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	4
13	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	3
14	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	2
15	1Cr- $\frac{1}{2}$ Mo-V	Bolting	SA-540	B21	K14073	1
16	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	5
17	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	5
18	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	4
19	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	3
20	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	2
21	1Cr-1Mn- $\frac{1}{4}$ Mo	Bolting	SA-540	B22	K41420	1
22	1Cr-V	Smls. tube	SA-213	T17	K12047	...
23	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC6	J12072	...
24	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP11	J12072	...
25	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo	Bar	SA-739	B11	K11797	...
26	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11597	1
27	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T11	K11597	...
28	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. & wld. fittings	SA-234	WP11	...	1
29	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P11	K11597	...
30	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11597	1
31	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forged pipe	SA-369	FP11	K11597	...
32	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	1
33	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	1 $\frac{1}{4}$ CR	K11789	...
34	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-182	F11	K11572	2
35	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	2
36	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT
37	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT
38	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA/EN 10028-2	13CrMoSi5-5	...	QT
39	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Forgings	SA-336	F11	K11572	3
40	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Plate	SA-387	11	K11789	2
41	1 $\frac{1}{4}$ Cr- $\frac{1}{2}$ Mo-Si	Wld. pipe	SA-691	1 $\frac{1}{4}$ CR	K11789	...
42	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...
43	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Cu	Forgings	SA-592	E	K11695	...
44	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...
45	1 $\frac{3}{4}$ Cr- $\frac{1}{2}$ Mo-Ti	Plate	SA-517	E	K21604	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	$2.5 < t \leq 4$	65.5	40	...
2	$\frac{5}{8} < t \leq 2.5$	65.5	42	...
3	$0.25 \leq t \leq 2.5$	65.5	43	...
4	$t \leq \frac{5}{8}$	65.5	43.5	...
5	...	70	40	...
6	...	70	40	...
7	$4 < t \leq 8$	100	85	...
8	$2\frac{1}{2} < t \leq 4$	110	95	...
9	$2 < t \leq 8$	115	100	...
10	≤ 2	120	105	...
11	$\leq 2\frac{1}{2}$	125	105	...
12	≤ 6	135	120	...
13	≤ 6	145	130	...
14	≤ 4	155	140	...
15	≤ 4	165	150	...
16	$2 < t \leq 4$	115	100	...
17	≤ 2	120	105	...
18	≤ 4	135	120	...
19	≤ 4	145	130	...
20	≤ 3	155	140	...
21	$\leq 1\frac{1}{2}$	165	150	...
22	...	60	30	...
23	...	70	40	...
24	...	70	40	...
25	...	70	45	...
26	...	60	30	...
27	...	60	30	...
28	...	60	30	...
29	...	60	30	...
30	...	60	30	...
31	...	60	30	...
32	...	60	35	...
33	...	60	35	...
34	...	70	40	...
35	...	70	40	...
36	$4 < t \leq 10$	71	55	...
37	$2.25 < t \leq 4$	72.5	56.5	...
38	≤ 2.25	74	58	...
39	...	75	45	...
40	...	75	45	...
41	...	75	45	...
42	$2\frac{1}{2} < t \leq 4$	105	90	...
43	$\leq 2\frac{1}{2}$	115	100	...
44	$2\frac{1}{2} < t \leq 6$	105	90	...
45	$\leq 2\frac{1}{2}$	115	100	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	39.9	37.4	36.1	34.9	33.9	33.1	32.4	...	31.3
2	42.1	39.4	38.0	36.8	35.8	34.9	34.2	33.6	33.0
3	42.8	40.1	38.7	37.5	36.4	35.5	34.7	...	33.6
4	43.5	40.8	39.4	38.1	37.0	36.1	35.3	34.7	34.1
5	40.0	37.5	36.2	35.0	34.0	...	32.5	...	31.4
6	40.0	37.5	36.2	35.0	34.0	...	32.5	...	31.4
7	85.0	...	82.0	...	79.9	...	77.8	...	75.7
8	95.0	...	91.7	...	89.3	...	86.9	...	84.6
9	100.0	...	96.7	...	93.8	...	91.5	...	89.0
10	105.0	...	101.3	...	98.7	...	96.1	...	93.5
11	105.0	...	101.3	...	98.7	...	96.1	...	93.5
12	120.0	...	116.0	...	112.6	...	109.8	...	106.8
13	130.0	...	125.7	...	121.9	...	119.0	...	115.7
14	140.0	...	135.4	...	131.3	...	128.1	...	124.6
15	150.0	...	145.1	...	140.7	...	137.3	...	133.5
16	100.0	...	95.4	...	92.7	...	89.4	...	86.7
17	105.0	...	100.2	...	97.2	...	93.9	...	90.9
18	120.0	...	114.6	...	110.7	...	107.7	...	104.1
19	130.0	...	124.1	...	120.5	...	116.4	...	112.9
20	140.0	...	133.8	...	129.3	...	125.4	...	121.5
21	150.0	...	143.4	...	138.6	...	134.4	...	130.2
22	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
23	40.0	38.0	36.9	36.0	35.1	...	33.7	...	32.5
24	40.0	38.0	36.9	36.0	35.1	...	33.7	...	32.5
25	45.0	42.8	41.5	40.5	39.5	...	37.9	...	36.5
26	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
27	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
28	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
29	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
30	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
31	30.0	28.5	27.7	27.0	26.3	...	25.3	...	24.4
32	35.0	33.3	32.3	31.5	30.7	...	29.5	...	28.4
33	35.0	33.3	32.3	31.5	30.7	...	29.5	...	28.4
34	40.0	38.0	36.9	36.0	35.1	...	33.7	...	32.5
35	40.0	38.0	36.9	36.0	35.1	...	33.7	...	32.5
36	55.0	53.8	53.0	52.2	51.3	50.5	49.6	48.7	47.8
37	56.5	55.3	54.5	53.6	52.7	51.8	50.9	50.0	49.1
38	58.0	56.7	55.9	55.1	54.2	53.2	52.3	51.3	50.4
39	45.0	42.8	41.5	40.5	39.5	...	37.9	...	36.5
40	45.0	42.8	41.5	40.5	39.5	...	37.9	...	36.5
41	45.0	42.8	41.5	40.5	39.5	...	37.9	...	36.5
42	90.0	87.5	86.0	84.5	83.2	...	81.0	...	79.2
43	100.0	97.2	95.5	93.9	92.5	...	90.0	...	88.0
44	90.0	87.5	86.0	84.5	83.2	...	81.0	...	79.2
45	100.0	97.2	95.5	93.9	92.5	...	90.0	...	88.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	30.8	30.4	30.0	29.5	29.1	28.5	27.9	27.1	26.3	25.3
2	32.5	32.1	31.6	31.2	30.6	30.1	29.4	28.6	27.7	26.6
3	33.1	32.6	32.2	31.7	31.2	30.6	29.9	29.1	28.2	27.1
4	33.6	33.2	32.7	32.2	31.7	31.1	30.4	29.6	28.6	27.6
5	...	30.5	30.1	29.6	29.1	28.6	28.0	27.2	26.3	25.3
6	...	30.5	30.1	29.6	29.1	28.6	28.0	27.2	26.3	25.3
7	...	73.5	72.3	71.0	69.6	67.9	65.9	63.6	60.8	57.4
8	...	82.1	80.8	79.4	77.7	75.9	73.7	71.1	68.0	64.2
9	...	86.5	85.2	83.6	81.9	79.8	77.4	74.7	71.6	67.8
10	...	90.8	89.3	87.7	85.9	83.9	81.5	78.6	75.2	71.0
11	...	90.8	89.3	87.7	85.9	83.9	81.5	78.6	75.2	71.0
12	...	103.8	102.2	100.3	98.3	95.8	92.9	89.6	85.9	81.4
13	...	112.5	110.8	108.7	106.5	103.7	100.6	97.1	93.1	88.1
14	...	121.1	119.3	117.0	114.7	111.7	108.4	104.6	100.2	94.9
15	...	129.8	127.8	125.4	122.9	119.7	116.1	112.1	107.4	101.7
16	...	82.8	80.2	77.7	...	...	...	...	...	...
17	...	87.0	84.3	81.6	...	...	...	...	...	...
18	...	99.3	96.3	93.3	...	...	...	...	...	...
19	...	107.8	104.1	101.1	...	...	...	...	...	...
20	...	116.1	112.1	108.9	...	...	...	...	...	...
21	...	124.2	118.2	114.0	...	...	...	...	...	...
22	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
23	...	31.4	30.8	30.2	29.6	28.8	28.1	27.2	26.2	25.0
24	...	31.4	30.8	30.2	29.6	28.8	28.1	27.2	26.2	25.0
25	...	35.3	34.6	34.0	33.2	32.5	31.6	30.6	29.4	28.2
26	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
27	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
28	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
29	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
30	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
31	...	23.5	23.1	22.6	22.2	21.6	21.0	20.4	19.6	18.8
32	...	27.4	26.9	26.4	25.9	25.2	24.5	23.8	22.9	21.9
33	...	27.4	26.9	26.4	25.9	25.2	24.5	23.8	22.9	21.9
34	...	31.4	30.8	30.2	29.6	28.8	28.1	27.2	26.2	25.0
35	...	31.4	30.8	30.2	29.6	28.8	28.1	27.2	26.2	25.0
36	46.9	45.9	45.0	44.0	43.0	42.0	40.8	39.6	38.2	36.6
37	48.1	47.2	46.2	45.2	44.2	43.1	41.9	40.7	39.2	37.6
38	49.4	48.5	47.5	46.5	45.4	44.3	43.1	41.7	40.3	38.6
39	...	35.3	34.6	34.0	33.2	32.5	31.6	30.6	29.4	28.2
40	...	35.3	34.6	34.0	33.2	32.5	31.6	30.6	29.4	28.2
41	...	35.3	34.6	34.0	33.2	32.5	31.6	30.6	29.4	28.2
42	...	77.7	77.0	76.3	75.6	74.7	73.7	72.5	71.0	69.2
43	...	86.3	85.6	84.8	84.0	83.0	81.9	80.5	78.9	76.8
44	...	77.7	77.0	76.3	75.6	74.7	73.7	72.5	71.0	69.2
45	...	86.3	85.6	84.8	84.0	83.0	81.9	80.5	78.9	76.8

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	1
2	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA-213	T22	K21590	...
3	2 $\frac{1}{4}$ Cr-1Mo	Smls. & wld. fittings	SA-234	WP22	K21590	1
4	2 $\frac{1}{4}$ Cr-1Mo	Smls. pipe	SA-335	P22	K21590	...
5	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	1
6	2 $\frac{1}{4}$ Cr-1Mo	Forged pipe	SA-369	FP22	K21590	...
7	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	1
8	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR	K21590	...
9	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
10	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT
11	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
12	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
13	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA/EN 10216-2	10CrMo9-10	...	...
14	2 $\frac{1}{4}$ Cr-1Mo	Smls. tube	SA/EN 10216-2	10CrMo9-10	...	...
15	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
16	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
17	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA/EN 10028-2	10CrMo9-10	...	...
18	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-217	WC9	J21890	...
19	2 $\frac{1}{4}$ Cr-1Mo	Cast pipe	SA-426	CP22	J21890	...
20	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-182	F22	K21590	3
21	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-336	F22	K21590	3
22	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-387	22	K21590	2
23	2 $\frac{1}{4}$ Cr-1Mo	Wld. pipe	SA-691	2 $\frac{1}{4}$ CR	K21590	...
24	2 $\frac{1}{4}$ Cr-1Mo	Bar	SA-739	B22	K21390	...
(25) 25	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA/EN 10222-2	11CrMo9-10	...	NT or QT
26	2 $\frac{1}{4}$ Cr-1Mo	Castings	SA-487	8	J22091	A
27	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-508	22	K21590	3
28	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	3
29	2 $\frac{1}{4}$ Cr-1Mo	Plate	SA-542	B	K21590	4
30	2 $\frac{1}{4}$ Cr-1Mo	Forgings	SA-541	22	K21390	4
31	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-182	F22V	K31835	...
32	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-336	F22V	K31835	...
33	2 $\frac{1}{4}$ Cr-1Mo-V	Forgings	SA-541	22V	K31835	...
34	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-542	D	K31835	4a
35	2 $\frac{1}{4}$ Cr-1Mo-V	Plate	SA-832	22V	K31835	...
36	3Cr-1Mo	Smls. tube	SA-213	T21	K31545	...
37	3Cr-1Mo	Smls. pipe	SA-335	P21	K31545	...
38	3Cr-1Mo	Forgings	SA-336	F21	K31545	1
39	3Cr-1Mo	Forged pipe	SA-369	FP21	K31545	...
40	3Cr-1Mo	Plate	SA-387	21	K31545	1
41	3Cr-1Mo	Cast pipe	SA-426	CP21	J31545	...
42	3Cr-1Mo	Forgings	SA-182	F21	K31545	...
43	3Cr-1Mo	Forgings	SA-336	F21	K31545	3
44	3Cr-1Mo	Plate	SA-387	21	K31545	2
45	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-182	F3V	K31830	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	60	30	...
2	...	60	30	...
3	...	60	30	...
4	...	60	30	...
5	...	60	30	...
6	...	60	30	...
7	...	60	30	...
8	...	60	30	...
9	$6 < t \leq 10$	65.5	36.5	...
10	$8 < t \leq 20$	65.5	38.5	...
11	$4 < t \leq 6$	66.5	37.5	...
12	$2.5 < t \leq 4$	68	40.5	...
13	$1\frac{5}{8} < t \leq 2\frac{1}{2}$	69.5	39	...
14	$t \leq 1\frac{5}{8}$	69.5	40.5	...
15	$1.5 < t \leq 2.5$	69.5	42	...
16	$\frac{5}{8} < t \leq 1.5$	69.5	43.5	...
17	$t \leq \frac{5}{8}$	69.5	45	...
18	...	70	40	...
19	...	70	40	...
20	...	75	45	...
21	...	75	45	...
22	...	75	45	...
23	...	75	45	...
24	...	75	45	...
25	$t \leq 8$	75.5	45	...
26	...	85	55	...
27	...	85	55	...
28	...	85	55	...
29	...	85	55	...
30	...	105	85	...
31	...	85	60	...
32	...	85	60	...
33	...	85	60	...
34	...	85	60	...
35	...	85	60	...
36	...	60	30	...
37	...	60	30	...
38	...	60	30	...
39	...	60	30	...
40	...	60	30	...
41	...	60	30	...
42	...	75	45	...
43	...	75	45	...
44	...	75	45	...
45	...	85	60	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
2	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
3	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
4	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
5	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
6	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
7	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
8	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
9	36.3	34.2	33.2	32.4	31.7	31.2	30.7	30.4	30.0
10	38.4	36.3	35.3	34.4	33.6	33.0	32.5	...	31.8
11	37.7	35.6	34.5	33.7	33.0	32.4	31.9	31.6	31.2
12	40.6	38.3	37.2	36.3	35.5	34.9	34.4	34.0	33.6
13	39.2	37.0	35.9	35.0	34.3	33.7	33.2	32.8	32.4
14	40.6	38.4	37.2	36.3	35.5	34.9	34.4	34.0	33.6
15	42.1	39.7	38.5	37.6	36.8	36.1	35.6	35.2	34.8
16	43.5	41.1	39.8	38.9	38.0	37.4	36.9	36.5	36.1
17	45.0	42.4	41.2	40.1	39.3	38.6	38.1	37.7	37.3
18	40.0	37.9	37.0	36.3	35.8	...	35.1	...	34.4
19	40.0	37.9	37.0	36.3	35.8	...	35.1	...	34.4
20	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
21	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
22	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
23	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
24	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
25	45.0	42.5	41.3	40.2	39.3	38.6	38.1	...	37.2
26	55.0	52.1	50.8	49.9	49.2	...	48.2	...	47.4
27	55.0	...	53.1	...	51.8	...	50.6	...	49.5
28	55.0	...	53.1	...	51.8	...	50.6	...	49.5
29	55.0	...	53.1	...	51.8	...	50.6	...	49.5
30	85.0	...	81.6	...	79.6	...	78.0	...	76.7
31	60.0	...	59.5	...	58.6	...	57.4	...	56.0
32	60.0	...	59.5	...	58.6	...	57.4	...	56.0
33	60.0	...	59.5	...	58.6	...	57.4	...	56.0
34	60.0	...	59.5	...	58.6	...	57.4	...	56.0
35	60.0	...	59.5	...	58.6	...	57.4	...	56.0
36	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
37	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
38	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
39	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
40	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
41	30.0	28.6	28.0	27.6	27.2	...	26.9	...	26.9
42	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
43	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
44	45.0	42.5	41.2	40.2	39.4	...	38.1	...	37.3
45	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
2	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
3	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
4	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
5	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
6	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
7	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
8	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
9	29.7	29.4	29.1	28.7	28.2	27.7	27.0	26.1	25.1	24.0
10	31.5	31.2	30.9	30.5	30.0	29.3	28.6	27.7	26.6	25.5
11	30.9	30.6	30.3	29.9	29.4	28.8	28.0	27.2	26.1	25.0
12	33.3	33.0	32.6	32.2	31.6	31.0	30.2	29.3	28.2	26.9
13	32.1	31.7	31.4	30.9	30.4	29.8	29.1	28.2	27.1	25.8
14	33.3	32.9	32.5	32.1	31.6	30.9	30.2	29.3	28.2	26.8
15	34.5	34.2	33.8	33.3	32.8	32.1	31.3	30.3	29.2	27.8
16	35.7	35.3	34.9	34.5	33.9	33.2	32.4	31.4	30.2	28.8
17	36.9	36.5	36.1	35.6	35.0	34.3	33.4	32.4	31.2	29.8
18	...	33.7	33.3	32.9	32.4	31.8	31.1	30.2	29.1	27.6
19	...	33.7	33.3	32.9	32.4	31.8	31.1	30.2	29.1	27.6
20	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
21	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
22	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
23	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
24	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
25	36.9	36.5	36.1	35.6	35.0	34.3	33.4	32.4	31.2	29.8
26	...	46.4	45.9	45.3	44.6	43.8	42.8	41.6	40.0	38.0
27	...	48.2	47.5	46.8	46.0	45.2	44.2	...	...	...
28	...	48.2	47.5	46.8	46.0	45.2	44.2	...	...	...
29	...	48.2	47.5	46.8	46.0	45.2	44.2	...	...	...
30	...	75.2	74.4	73.4	72.3	71.0	69.4	67.6	65.4	63.0
31	...	54.2	53.3	52.3	51.2	50.1	49.0	47.8	...	...
32	...	54.2	53.3	52.3	51.2	50.1	49.0	47.8	...	...
33	...	54.2	53.3	52.3	51.2	50.1	49.0	47.8	...	...
34	...	54.2	53.3	52.3	51.2	50.1	49.0	47.8	...	...
35	...	54.2	53.3	52.3	51.2	50.1	49.0	47.8	...	...
36	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
37	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
38	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
39	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
40	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
41	...	26.9	26.9	26.9	26.8	26.6	26.2	25.6	24.8	23.7
42	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
43	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
44	...	36.5	36.1	35.6	35.0	34.3	33.5	32.4	31.2	29.7
45	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-336	F3V	K31830	...
2	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-508	3V	K31830	...
3	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Forgings	SA-541	3V	K31830	...
4	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-542	C	K31830	4a
5	3Cr-1Mo- $\frac{1}{4}$ V-Ti-B	Plate	SA-832	21V	K31830	...
6	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-182	F3VCb	...	...
7	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-336	F3VCb	...	...
8	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-508	3VCb	...	...
9	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Forgings	SA-541	3VCb	...	...
10	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-542	E	...	4a
11	3Cr-1Mo- $\frac{1}{4}$ V-Cb-Ca	Plate	SA-832	23V	...	...
12	5Cr- $\frac{1}{2}$ Mo	Smls. tube	SA-213	T5	K41545	...
13	5Cr- $\frac{1}{2}$ Mo	Smls. & wld. fittings	SA-234	WP5	K41545	...
14	5Cr- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P5	K41545	...
15	5Cr- $\frac{1}{2}$ Mo	Forged pipe	SA-369	FP5	K41545	...
16	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	1
17	5Cr- $\frac{1}{2}$ Mo	Wld. pipe	SA-691	5CR	K41545	...
18	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5	K41545	...
19	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5	K41545	...
20	5Cr- $\frac{1}{2}$ Mo	Plate	SA-387	5	K41545	2
21	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-336	F5A	K42544	...
22	5Cr- $\frac{1}{2}$ Mo	Castings	SA-217	C5	J42045	...
23	5Cr- $\frac{1}{2}$ Mo	Cast pipe	SA-426	CP5	J42045	...
24	5Cr- $\frac{1}{2}$ Mo	Forgings	SA-182	F5a	K42544	...
25	5Cr- $\frac{1}{2}$ Mo	Bolting	SA-193	B5	K50100	...
26	5Cr- $\frac{1}{2}$ Mo-Si	Smls. tube	SA-213	T5b	K51545	...
27	5Cr- $\frac{1}{2}$ Mo-Si	Smls. pipe	SA-335	P5b	K51545	...
28	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. tube	SA-213	T5c	K41245	...
29	5Cr- $\frac{1}{2}$ Mo-Ti	Smls. pipe	SA-335	P5c	K41245	...
30	9Cr-1Mo	Smls. tube	SA-213	T9	K90941	...
31	9Cr-1Mo	Fittings	SA-234	WP9	K90941	...
32	9Cr-1Mo	Smls. pipe	SA-335	P9	K90941	...
33	9Cr-1Mo	Forged pipe	SA-369	FP9	K90941	...
34	9Cr-1Mo	Forgings	SA-182	F9	K90941	...
35	9Cr-1Mo	Forgings	SA-336	F9	K90941	...
36	9Cr-1Mo	Castings	SA-217	C12	J82090	...
37	9Cr-1Mo	Cast pipe	SA-426	CP9	J82090	...
38	9Cr-1Mo-V	Smls. tube	SA-213	T91 Types 1 & 2	K90901	...
39	9Cr-1Mo-V	Fittings	SA-234	WP91 Types 1 & 2	K90901	...
40	9Cr-1Mo-V	Smls. pipe	SA-335	P91 Types 1 & 2	K90901	...
41	9Cr-1Mo-V	Forged pipe	SA-369	FP91 Types 1 & 2	K90901	...
42	9Cr-1Mo-V	Plate	SA-387	91 Types 1 & 2	K90901	2
43	9Cr-1Mo-V	Forgings	SA-182	F91 Types 1 & 2	K90901	...
44	9Cr-1Mo-V	Forgings	SA-336	F91 Types 1 & 2	K90901	...
45	11Cr-Ti	Plate	SA-240	...	S40910	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	85	60	...
2	...	90	60	...
3	...	85	60	...
4	...	85	60	...
5	...	85	60	...
6	...	85	60	...
7	...	85	60	...
8	...	85	60	...
9	...	85	60	...
10	...	85	60	...
11	...	85	60	...
12	...	60	30	...
13	...	60	30	...
14	...	60	30	...
15	...	60	30	...
16	...	60	30	...
17	...	60	30	...
18	...	60	36	...
19	...	70	40	...
20	...	75	45	...
21	...	80	50	...
22	...	90	60	...
23	...	90	60	...
24	...	90	65	...
25	≤4	100	80	...
26	...	60	30	...
27	...	60	30	...
28	...	60	30	...
29	...	60	30	...
30	...	60	30	...
31	...	60	30	...
32	...	60	30	...
33	...	60	30	...
34	...	85	55	...
35	...	85	55	...
36	...	90	60	...
37	...	90	60	...
38	...	85	60	...
39	...	90	60	...
40	...	85	60	...
41	...	85	60	...
42	...	85	60	...
43	...	90	60	...
44	...	90	60	...
45	...	55	25	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
2	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
3	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
4	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
5	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
6	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
7	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
8	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
9	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
10	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
11	60.0	57.4	56.0	54.8	53.8	...	52.6	...	52.0
12	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
13	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
14	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
15	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
16	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
17	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
18	36.0	33.6	32.5	31.8	31.4	...	30.9	...	30.7
19	40.0	37.3	36.2	35.4	34.8	...	34.4	...	34.1
20	45.0	42.0	40.7	39.8	39.2	...	38.7	...	38.4
21	50.0	46.7	45.2	44.2	43.6	...	42.9	...	42.6
22	60.0	56.0	54.2	53.0	52.3	...	51.5	...	51.2
23	60.0	56.0	54.2	53.0	52.3	...	51.5	...	51.2
24	65.0	60.7	58.8	57.5	56.6	...	55.8	...	55.4
25	80.0	...	71.1	...	68.9	...	68.7	...	68.7
26	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
27	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
28	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
29	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
30	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
31	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
32	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
33	30.0	28.0	27.1	26.5	26.1	...	25.8	...	25.6
34	55.0	51.3	49.7	48.6	47.9	...	47.2	...	46.9
35	55.0	51.3	49.7	48.6	47.9	...	47.2	...	46.9
36	60.0	56.0	54.2	53.0	52.3	...	51.5	...	51.2
37	60.0	56.0	54.2	53.0	52.3	...	51.5	...	51.2
38	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
39	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
40	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
41	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
42	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
43	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
44	60.0	57.1	55.9	55.2	54.8	...	54.7	...	54.7
45	25.0	23.0	21.7	20.6	19.6	...	18.1	...	17.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
2	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
3	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
4	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
5	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
6	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
7	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
8	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
9	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
10	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
11	...	51.7	51.4	51.2	50.8	50.3	49.5	48.5	...	...
12	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
13	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
14	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
15	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
16	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
17	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
18	...	30.3	29.9	29.3	28.6	27.7	26.6	25.3	23.8	22.2
19	...	33.6	33.2	32.6	31.8	30.8	29.6	28.1	26.5	24.6
20	...	37.8	37.4	36.7	35.8	34.6	33.3	31.6	29.8	27.7
21	...	42.0	41.5	40.8	39.8	38.5	36.9	35.1	33.1	30.8
22	...	50.5	49.8	48.9	47.7	46.2	44.3	42.2	39.7	36.9
23	...	50.5	49.8	48.9	47.7	46.2	44.3	42.2	39.7	36.9
24	...	54.7	54.0	53.0	51.7	50.0	48.0	45.7	43.0	40.0
25	...	68.6	67.9	66.7	65.1	62.9	60.3	57.1	53.6	49.7
26	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
27	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
28	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
29	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
30	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
31	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
32	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
33	...	25.2	24.9	24.5	23.9	23.1	22.2	21.1	19.8	18.5
34	...	46.2	45.7	44.8	43.7	42.3	40.6	38.6	36.4	33.9
35	...	46.2	45.7	44.8	43.7	42.3	40.6	38.6	36.4	33.9
36	...	50.5	49.8	48.9	47.7	46.2	44.3	42.2	39.7	36.9
37	...	50.5	49.8	48.9	47.7	46.2	44.3	42.2	39.7	36.9
38	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
39	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
40	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
41	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
42	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
43	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
44	...	54.5	54.0	53.2	52.0	50.4	48.5	46.1	43.4	40.2
45	...	17.0	16.9	16.9	16.8	16.6	16.3	15.9	15.3	14.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	11Cr-Ti	Plate	SA-240	...	S40920	...
2	11Cr-Ti	Plate	SA-240	...	S40930	...
3	11Cr-Ti	Smls. & wld. tube	SA-268	TP409	S40900	...
4	12Cr	Plate	SA-1010	40	S41003	...
5	12Cr	Bar	SA-479	403	S40300	A
6	12Cr	Bar	SA-479	403	S40300	1
7	12Cr	Plate	SA-1010	50	S41003	...
8	12Cr-Al	Plate	SA-240	405	S40500	...
9	12Cr-Al	Bar	SA-479	405	S40500	...
10	12Cr-Al	Bar	SA/JIS G4303	SUS405	...	...
11	12Cr-Al	Smls. & wld. tube	SA-268	TP405	S40500	...
12	12Cr-1Mo-V-W	Bolting	SA-437	B4C	K91352	...
13	12Cr-1Mo-V-W	Bolting	SA-437	B4B	K91352	...
14	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16	S45500	H1000
15	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16	S45500	H1000
16	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16	S45500	H950
17	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16	S45500	H950
18	12Cr-9Ni-2Cu-1Ti	Bar	SA-564	XM-16	S45500	H900
19	12Cr-9Ni-2Cu-1Ti	Forgings	SA-705	XM-16	S45500	H900
20	12Cr-Ti	Smls. & wld. tube	SA-268	...	S40800	...
21	13Cr	Plate	SA-240	410S	S41008	...
22	13Cr	Smls. & wld. tube	SA-268	TP410	S41000	...
23	13Cr	Plate	SA-240	410	S41000	...
24	13Cr	Forgings	SA-182	F6a	S41000	1
25	13Cr	Bar	SA-479	410	S41000	...
26	13Cr	Bar	SA-479	410	S41000	A
27	13Cr	Bar	SA-479	410	S41000	1
28	13Cr	Forgings	SA-182	F6a	S41000	2
29	13Cr	Castings	SA-217	CA15	J91150	...
30	13Cr	Cast pipe	SA-426	CPCA15	J91150	...
31	13Cr	Bar	SA/EN 10088-3	X12Cr13	...	QT650
32	13Cr	Bolting	SA-193	B6	S41000	...
33	13Cr-4Ni	Castings	SA-487	CA6NM	J91540	A
34	13Cr-4Ni	Forgings	SA-182	F6NM	S41500	...
35	13Cr-4Ni	Bar	SA-479	...	S41500	...
36	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1150M
37	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1150M
38	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1150
39	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1150
40	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1100
41	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1100
42	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1050
43	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1050
44	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1025
45	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1025

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	55	25	...
2	...	55	25	...
3	...	55	25	...
4	$\leq \frac{3}{4}$	66	40	...
5	...	70	40	...
6	...	70	40	...
7	$\leq \frac{3}{4}$	70	50	...
8	...	60	25	...
9	...	60	25	...
10	...	60	25	...
11	...	60	30	...
12	...	115	85	...
13	...	145	105	...
14	...	205	185	...
15	$\geq \frac{1}{2}$	205	185	...
16	...	220	205	...
17	$\geq \frac{1}{2}$	220	205	...
18	...	235	220	...
19	$\geq \frac{1}{2}$	235	220	...
20	...	55	30	...
21	...	60	30	...
22	...	60	30	...
23	...	65	30	...
24	...	70	40	...
25	...	70	40	...
26	...	70	40	...
27	...	70	40	...
28	...	85	55	...
29	...	90	65	...
30	...	90	65	...
31	$t \leq 6.25$	94.5	65.5	...
32	≤ 4	110	85	...
33	...	110	80	...
34	...	115	90	...
35	...	115	90	...
36	...	125	85	...
37	...	125	85	...
38	...	135	90	...
39	...	135	90	...
40	...	150	135	...
41	...	150	135	...
42	...	175	165	...
43	...	175	165	...
44	...	185	175	...
45	...	185	175	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Ferrous Materials (Cont'd)								
1	25.0	23.0	21.7	20.6	19.6	...	18.1	...	17.3
2	25.0	23.0	21.7	20.6	19.6	...	18.1	...	17.3
3	25.0	23.0	21.7	20.6	19.6	...	18.1	...	17.3
4	40.0	...	40.0	...	36.7	...	33.9	...	32.3
5	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
6	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
7	50.0	...	50.0	...	45.9	...	42.4	...	40.3
8	25.0	23.6	23.0	22.5	22.2	...	21.8	...	21.5
9	25.0	23.6	23.0	22.5	22.2	...	21.8	...	21.5
10	25.0	23.6	23.0	22.5	22.2	...	21.8	...	21.5
11	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
12	85.0	...	81.6	...	78.9	...	76.8	...	75.0
13	105.0	...	100.5	...	97.2	...	94.8	...	92.7
14	185.0	...	...	...	...	...	...	...	...
15	185.0	...	...	...	...	...	...	...	...
16	205.0	...	...	...	...	...	...	...	...
17	205.0	...	...	...	...	...	...	...	...
18	220.0	...	...	...	...	...	...	...	...
19	220.0	...	...	...	...	...	...	...	...
20	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
21	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
22	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
23	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
24	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
25	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
26	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
27	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
28	55.0	52.0	50.6	49.6	48.8	...	48.0	...	47.3
29	65.0	61.4	59.8	58.6	57.7	...	56.7	...	55.9
30	65.0	61.4	59.8	58.6	57.7	...	56.7	...	55.9
31	65.3	62.0	60.4	59.1	58.1	57.3	56.8	...	56.0
32	85.0	...	78.0	...	75.0	...	73.6	...	72.8
33	80.0	76.9	75.3	73.9	72.9	...	71.3	...	70.3
34	90.0	87.7	86.5	85.5	84.6	...	82.8	...	80.8
35	90.0	87.7	86.5	85.5	84.6	...	82.8	...	80.8
36	85.0	...	...	...	...	...	...	...	...
37	85.0	...	...	...	...	...	...	...	...
38	90.0	...	...	...	...	...	...	...	...
39	90.0	...	...	...	...	...	...	...	...
40	135.0	...	...	...	...	...	...	...	...
41	135.0	...	...	...	...	...	...	...	...
42	165.0	...	...	...	...	...	...	...	...
43	165.0	...	...	...	...	...	...	...	...
44	175.0	...	...	...	...	...	...	...	...
45	175.0	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	17.0	16.9	16.9	16.8	16.6	16.3	15.9	15.3	14.5
2	...	17.0	16.9	16.9	16.8	16.6	16.3	15.9	15.3	14.5
3	...	17.0	16.9	16.9	16.8	16.6	16.3	15.9	15.3	14.5
4	...	31.1	30.4	29.4	28.1	26.5	24.7	22.9	21.5	21.2
5	...	33.7	33.1	32.4	31.4	30.2	28.8	27.1	25.2	23.0
6	...	33.7	33.1	32.4	31.4	30.2	28.8	27.1	25.2	23.0
7	...	38.9	38.0	36.8	35.1	33.1	30.9	28.6	26.9	26.5
8	...	21.0	20.7	20.2	19.6	18.9	18.0	16.9	15.7	14.4
9	...	21.0	20.7	20.2	19.6	18.9	18.0	16.9	15.7	14.4
10	...	21.0	20.7	20.2	19.6	18.9	18.0	16.9	15.7	14.4
11	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
12	...	73.8	72.9	72.0	...	...	...	...	...	...
13	...	90.6	89.7	89.1	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
21	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
22	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
23	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
24	...	33.7	33.1	32.4	31.4	30.2	28.8	27.1	25.2	23.0
25	...	33.7	33.1	32.4	31.4	30.2	28.8	27.1	25.2	23.0
26	...	33.7	33.1	32.4	...	...	...	...	...	...
27	...	33.7	33.1	32.4	...	...	...	...	...	...
28	...	46.3	45.5	44.5	43.2	41.6	39.6	37.3	34.6	31.6
29	...	54.7	53.8	52.6	51.0	49.1	46.8	44.0	40.9	37.3
30	...	54.7	53.8	52.6	...	...	...	...	...	...
31	55.6	55.0	54.2	53.0	51.4	49.4	47.0	44.2	41.0	37.7
32	...	71.7	70.7	69.4	67.6	65.2	62.3	58.7	54.6	49.9
33	...	69.1	68.2	67.0	65.4	63.4	...	...	...	...
34	...	78.5	77.2	75.7	...	...	...	...	...	...
35	...	78.5	77.2	75.7	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H1000
2	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H1000
3	13Cr-8Ni-2Mo	Bar	SA-564	XM-13	S13800	H950
4	13Cr-8Ni-2Mo	Forgings	SA-705	XM-13	S13800	H950
5	15Cr	Smls. & wld. tube	SA-268	TP429	S42900	...
6	15Cr	Plate	SA-240	429	S42900	...
(25) 7	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H1150M
(25) 8	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H1150M
(25) 9	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H1150
(25) 10	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H1150
(25) 11	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H1100
(25) 12	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H1100
(25) 13	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H1075
(25) 14	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H1075
(25) 15	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H1025
(25) 16	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H1025
(25) 17	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H925
(25) 18	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H925
(25) 19	15Cr-5Ni-3Cu	Bar	SA-564	XM-12	S15500	H900
(25) 20	15Cr-5Ni-3Cu	Forgings	SA-705	XM-12	S15500	H900
21	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H1150
22	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H1150
23	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H1100
24	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H1100
25	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H1050
26	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H1050
27	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H1025
28	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H1025
29	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H1000
30	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H1000
31	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H950
32	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H950
33	15Cr-6Ni-Cu-Mo	Bar	SA-564	XM-25	S45000	H900
34	15Cr-6Ni-Cu-Mo	Forgings	SA-705	XM-25	S45000	H900
35	17Cr	Smls. & wld. tube	SA-268	TP430	S43000	...
36	17Cr	Plate	SA-240	430	S43000	...
37	17Cr	Bar	SA-479	430	S43000	...
(25) 38	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1150M
(25) 39	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1150M
(25) 40	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1150
(25) 41	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1150
(25) 42	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1150
(25) 43	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1100
(25) 44	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1100
(25) 45	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1100

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	205	190	...
2	...	205	190	...
3	...	220	205	...
4	...	220	205	...
5	...	60	35	...
6	...	65	30	...
7	...	115	75	...
8	...	115	75	...
9	...	135	105	...
10	...	135	105	...
11	...	140	115	...
12	...	140	115	...
13	...	145	125	...
14	...	145	125	...
15	...	155	145	...
16	...	155	145	...
17	...	170	155	...
18	...	170	155	...
19	...	190	170	...
20	...	190	170	...
21	...	125	75	...
22	$\geq \frac{1}{2}$	125	75	...
23	...	130	105	...
24	$\geq \frac{1}{2}$	130	105	...
25	...	145	135	...
26	$\geq \frac{1}{2}$	145	135	...
27	...	150	140	...
28	$\geq \frac{1}{2}$	150	140	...
29	...	160	150	...
30	$\geq \frac{1}{2}$	160	150	...
31	...	170	160	...
32	$\geq \frac{1}{2}$	170	160	...
33	...	180	170	...
34	$\geq \frac{1}{2}$	180	170	...
35	...	60	35	...
36	...	65	30	...
37	...	70	40	...
38	...	115	75	...
39	...	115	75	...
40	...	135	105	...
41	...	135	105	...
42	...	135	105	...
43	...	140	115	...
44	...	140	115	...
45	...	140	115	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	190.0	...	...	...	...	...	...	...	...
2	190.0	...	...	...	...	...	...	...	...
3	205.0	...	...	...	...	...	...	...	...
4	205.0	...	...	...	...	...	...	...	...
5	35.0	33.1	32.2	31.5	31.1	...	30.5	...	30.1
6	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
7	75.0	71.3	69.6	68.1	66.9	66.4	64.8	64.8	63.0
8	75.0	71.3	69.6	68.1	66.9	66.4	64.8	64.8	63.0
9	105.0	99.9	97.4	95.4	93.6	93.0	90.7	90.7	88.3
10	105.0	99.9	97.4	95.4	93.6	93.0	90.7	90.7	88.3
11	115.0	109.4	106.7	104.5	102.6	101.8	99.4	99.3	96.7
12	115.0	109.4	106.7	104.5	102.6	101.8	99.4	99.3	96.7
13	125.0	118.9	116.0	113.5	111.5	110.7	108.0	107.9	105.1
14	125.0	118.9	116.0	113.5	111.5	110.7	108.0	107.9	105.1
15	145.0	137.9	134.5	131.7	129.3	128.4	125.3	125.2	121.9
16	145.0	137.9	134.5	131.7	129.3	128.4	125.3	125.2	121.9
17	155.0	147.4	143.8	140.8	138.2	137.2	134.0	133.8	130.3
18	155.0	147.4	143.8	140.8	138.2	137.2	134.0	133.8	130.3
19	170.0	161.7	157.7	154.4	151.6	150.5	146.9	146.8	142.9
20	170.0	161.7	157.7	154.4	151.6	150.5	146.9	146.8	142.9
21	75.0	...	...	...	...	...	...	...	...
22	75.0	...	...	...	...	...	...	...	...
23	105.0	...	...	...	...	...	...	...	...
24	105.0	...	...	...	...	...	...	...	...
25	135.0	...	...	...	...	...	...	...	...
26	135.0	...	...	...	...	...	...	...	...
27	140.0	...	...	...	...	...	...	...	...
28	140.0	...	...	...	...	...	...	...	...
29	150.0	...	...	...	...	...	...	...	...
30	150.0	...	...	...	...	...	...	...	...
31	160.0	...	...	...	...	...	...	...	...
32	160.0	...	...	...	...	...	...	...	...
33	170.0	...	...	...	...	...	...	...	...
34	170.0	...	...	...	...	...	...	...	...
35	35.0	33.1	32.2	31.5	31.1	...	30.5	...	30.1
36	30.0	28.4	27.6	27.0	26.6	...	26.2	...	25.8
37	40.0	37.8	36.8	36.0	35.5	...	34.9	...	34.4
38	75.0	71.3	69.6	68.1	66.9	66.4	64.8	64.8	63.0
39	75.0	71.3	69.6	68.1	66.9	66.4	64.8	64.8	63.0
40	105.0	99.9	97.4	95.4	93.6	93.0	90.7	90.7	88.3
41	105.0	99.9	97.4	95.4	93.6	93.0	90.7	90.7	88.3
42	105.0	99.9	97.4	95.4	93.6	93.0	90.7	90.7	88.3
43	115.0	109.4	106.7	104.5	102.6	101.8	99.4	99.3	96.7
44	115.0	109.4	106.7	104.5	102.6	101.8	99.4	99.3	96.7
45	115.0	109.4	106.7	104.5	102.6	101.8	99.4	99.3	96.7

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	29.5	29.0	28.3	27.5	26.4	25.2	23.7	22.0	20.1
6	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
7	62.2	61.4	60.3	59.4	58.0	56.7	54.9	52.3	48.5	43.0
8	62.2	61.4	60.3	59.4	58.0	56.7	54.9	52.3	48.5	43.0
9	87.1	85.9	84.4	83.2	81.1	79.4	76.9	73.2	67.9	60.2
10	87.1	85.9	84.4	83.2	81.1	79.4	76.9	73.2	67.9	60.2
11	95.4	94.1	92.5	91.1	88.9	86.9	84.2	80.2	74.4	66.0
12	95.4	94.1	92.5	91.1	88.9	86.9	84.2	80.2	74.4	66.0
13	103.6	102.3	100.5	99.0	96.6	94.5	91.5	87.2	80.8	71.7
14	103.6	102.3	100.5	99.0	96.6	94.5	91.5	87.2	80.8	71.7
15	120.2	118.6	116.6	114.8	112.0	109.6	106.2	101.1	93.8	83.2
16	120.2	118.6	116.6	114.8	112.0	109.6	106.2	101.1	93.8	83.2
17	128.5	126.8	124.6	122.8	119.8	117.2	113.5	108.1	100.2	88.9
18	128.5	126.8	124.6	122.8	119.8	117.2	113.5	108.1	100.2	88.9
19	141.0	139.1	136.7	134.6	131.4	128.5	124.5	118.6	109.9	97.5
20	141.0	139.1	136.7	134.6	131.4	128.5	124.5	118.6	109.9	97.5
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	29.5	29.0	28.3	27.5	26.4	25.2	23.7	22.0	20.1
36	...	25.3	24.8	24.3	23.6	22.7	21.6	20.3	18.9	17.2
37	...	33.7	33.1	32.4	31.4	30.2	28.8	27.1	25.2	23.0
38	62.2	61.4	60.3	59.4	58.0	56.7	54.9	52.3	48.5	43.0
39	62.2	61.4	60.3	59.4	58.0	56.7	54.9	52.3	48.5	43.0
40	87.1	85.9	84.4	83.2	81.1	79.4	76.9	73.2	67.9	60.2
41	87.1	85.9	84.4	83.2	81.1	79.4	76.9	73.2	67.9	60.2
42	87.1	85.9	84.4	83.2	81.1	79.4	76.9	73.2	67.9	60.2
43	95.4	94.1	92.5	91.1	88.9	86.9	84.2	80.2	74.4	66.0
44	95.4	94.1	92.5	91.1	88.9	86.9	84.2	80.2	74.4	66.0
45	95.4	94.1	92.5	91.1	88.9	86.9	84.2	80.2	74.4	66.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
(25) 1	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1075
(25) 2	17Cr-4Ni-4Cu	Plate	SA-693	630	S17400	H1075
(25) 3	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1075
(25) 4	17Cr-4Ni-4Cu	Bar	SA-564	630	S17400	H1025
(25) 5	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H1025
(25) 6	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H925
(25) 7	17Cr-4Ni-4Cu	Forgings	SA-705	630	S17400	H900
8	17Cr-7Ni-1Al	Forgings	SA-705	631	S17700	TH1050
9	17Cr-7Ni-1Al	Forgings	SA-705	631	S17700	RH950
10	18Cr-2Mo	Plate	SA-240	...	S44400	...
11	18Cr-2Mo	Smls. & wld. tube	SA-268	...	S44400	...
(25) 12	18Cr-2Mo	Bar	SA-479	...	S44400	...
13	18Cr-Ti	Plate	SA-240	...	S43932	...
(25) 14	18Cr-Ti	Plate	SA-240	439	S43035	...
15	18Cr-Ti	Smls. & wld. tube	SA-268	TP439	S43035	...
16	18Cr-Ti	Wld. tube	SA-803	TP439	S43035	...
(25) 17	...	...	...	...	...	...
18	18Cr-Ti	Smls. & wld. tube	SA-268	TP430 Ti	S43036	...
19	18Cr-Ti	Bar	SA-479	439	S43035	...
20	26Cr-3Ni-3Mo	Plate	SA-240	26-3-3	S44660	...
21	26Cr-3Ni-3Mo	Smls. & wld. tube	SA-268	26-3-3	S44660	...
22	26Cr-3Ni-3Mo	Wld. tube	SA-803	26-3-3	S44660	...
23	27Cr	Smls. tube	SA-268	TP446-1	S44600	...
24	27Cr-1Mo	Forgings	SA-182	FXM-27Cb	S44627	...
25	27Cr-1Mo	Plate	SA-240	XM-27	S44627	...
26	27Cr-1Mo	Smls. & wld. tube	SA-268	TPXM-27	S44627	...
(25) 27	27Cr-1Mo	Bar	SA-479	XM-27	S44627	...
(25) 28	...	...	...	...	...	...
29	...	...	...	...	...	...
30	27Cr-1Mo-Ti	Plate	SA-240	XM-33	S44626	...
31	27Cr-1Mo-Ti	Smls. & wld. tube	SA-268	TPXM-33	S44626	...
32	29Cr-4Mo	Bar	SA-479	...	S44700	...
33	29Cr-4Mo	Plate	SA-240	...	S44700	...
34	29Cr-4Mo	Smls. & wld. tube	SA-268	29-4	S44700	...
35	29Cr-4Mo-2Ni	Bar	SA-479	...	S44800	...
36	29Cr-4Mo-2Ni	Plate	SA-240	...	S44800	...
37	29Cr-4Mo-2Ni	Smls. & wld. tube	SA-268	29-4-2	S44800	...
38	29Cr-4Mo-Ti	Smls. & wld. tube	SA-268	...	S44735	...
39	Mn- $\frac{1}{4}$ Mo	Forgings	SA-372	D	K14508	...
40	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2	J13005	A
41	Mn- $\frac{1}{4}$ Mo-V	Castings	SA-487	2	J13005	B
42	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	A	K12021	...
43	Mn- $\frac{1}{2}$ Mo	Wld. pipe	SA-672	H75	K12021	...
44	Mn- $\frac{1}{2}$ Mo	Plate	SA-302	B	K12022	...
45	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	145	125	...
2	...	145	125	...
3	...	145	125	...
4	...	155	145	...
5	...	155	145	...
6	...	170	155	...
7	...	190	170	...
8	...	170	140	...
9	...	185	150	...
10	...	60	40	...
11	...	60	40	...
12	$t \leq \frac{3}{8}$	60	45	...
13	...	60	30	...
14	...	60	30	...
15	...	60	30	...
16	...	60	30	...
17	...	...	...	...
18	...	60	35	...
19	...	70	40	...
20	$\leq \frac{2}{10}$	85	65	...
21	$\leq \frac{2}{10}$	85	65	...
22	$\leq \frac{2}{10}$	85	65	...
23	...	70	40	...
24	...	60	35	...
25	...	65	40	...
26	...	65	40	...
27	...	65	40	...
28	...	...	...	...
29	...	...	...	...
30	...	68	45	...
31	...	68	45	...
32	...	70	55	...
33	...	80	60	...
34	...	80	60	...
35	...	70	55	...
36	...	80	60	...
37	...	80	60	...
38	...	75	60	...
39	...	105	65	...
40	...	85	53	...
41	...	90	65	...
42	...	75	45	...
43	...	75	45	...
44	...	80	50	...
45	...	80	50	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	125.0	118.9	116.0	113.5	111.5	110.7	108.0	107.9	105.1
2	125.0	118.9	116.0	113.5	111.5	110.7	108.0	107.9	105.1
3	125.0	118.9	116.0	113.5	111.5	110.7	108.0	107.9	105.1
4	145.0	137.9	134.5	131.7	129.3	128.4	125.3	125.2	121.9
5	145.0	137.9	134.5	131.7	129.3	128.4	125.3	125.2	121.9
6	155.0	147.4	143.8	140.8	138.2	137.2	134.0	133.8	130.3
7	170.0	161.7	157.7	154.4	151.6	150.5	146.9	146.8	142.9
8	140.0	...	...	...	...	...	...	...	...
9	150.0	...	...	...	...	...	...	...	...
10	40.0	36.5	34.8	33.5	32.4	...	30.8	...	29.4
11	40.0	36.5	34.8	33.5	32.4	...	30.8	...	29.4
12	45.0	41.1	39.2	37.7	36.5	...	34.7	...	33.1
13	30.0	27.4	25.9	24.6	23.5	...	21.9	...	20.9
14	30.0	27.4	25.9	24.6	23.5	...	21.9	...	20.9
15	30.0	27.4	25.9	24.6	23.5	...	21.9	...	20.9
16	30.0	27.4	25.9	24.6	23.5	...	21.9	...	20.9
17	...	...	...	...	...	...	...	...	...
18	35.0	...	30.2	...	27.4	...	25.5	...	24.4
19	40.0	36.5	34.6	32.8	31.3	...	29.1	...	27.9
20	65.0	60.6	58.3	56.4	54.7	...	52.3	...	50.6
21	65.0	60.6	58.3	56.4	54.7	...	52.3	...	50.6
22	65.0	60.6	58.3	56.4	54.7	...	52.3	...	50.6
23	40.0	36.5	34.6	32.8	31.3	...	29.1	...	27.9
24	35.0	32.1	30.3	28.8	27.6	...	25.7	...	24.8
25	40.0	36.6	34.5	32.8	31.3	...	29.3	...	28.3
26	40.0	36.6	34.5	32.8	31.3	...	29.3	...	28.3
27	40.0	36.6	34.5	32.8	31.3	...	29.3	...	28.3
28	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...
30	45.0	41.5	39.5	37.6	35.9	...	33.1	...	31.1
31	45.0	41.5	39.5	37.6	35.9	...	33.1	...	31.1
32	55.0	50.8	48.4	46.4	44.7	...	42.6	...	41.6
33	60.0	55.4	52.8	50.6	48.8	...	46.4	...	45.4
34	60.0	55.4	52.8	50.6	48.8	...	46.4	...	45.4
35	55.0	49.0	45.8	43.0	40.7	...	36.9	...	34.3
36	60.0	53.4	49.9	47.0	44.4	...	40.2	...	37.4
37	60.0	53.4	49.9	47.0	44.4	...	40.2	...	37.4
38	60.0	53.4	49.9	47.0	44.4	...	40.2	...	37.4
39	65.0	62.8	61.5	60.4	59.6	...	58.6	...	58.2
40	53.0	51.2	50.4	49.4	48.2	...	45.2	...	42.4
41	65.0	62.8	61.8	60.6	59.1	...	55.4	...	52.0
42	45.0	43.3	42.3	41.6	40.9	...	39.8	...	38.8
43	45.0	43.3	42.3	41.6	40.9	...	39.8	...	38.8
44	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
45	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	103.6	102.3	100.5	99.0	96.6	94.5	91.5	87.2	80.8	71.7
2	103.6	102.3	100.5	99.0	96.6	94.5	91.5	87.2	80.8	71.7
3	103.6	102.3	100.5	99.0	96.6	94.5	91.5	87.2	80.8	71.7
4	120.2	118.6	116.6	114.8	112.0	109.6	106.2	101.1	93.8	83.2
5	120.2	118.6	116.6	114.8	112.0	109.6	106.2	101.1	93.8	83.2
6	128.5	126.8	124.6	122.8	119.8	117.2	113.5	108.1	100.2	88.9
7	141.0	139.1	136.7	134.6	131.4	128.5	124.5	118.6	109.9	97.5
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	28.0	27.3	26.6	25.9	25.1	24.2	23.2	22.1	20.7
11	...	28.0	27.3	26.6	25.9	25.1	24.2	23.2	22.1	20.7
12	...	31.5	30.7	29.9	29.1	28.2	27.2	26.1	24.9	23.3
13	...	20.5	20.3	20.2	20.1	19.8	19.4	18.8	17.9	16.6
14	...	20.5	20.3	20.2	20.1	19.8	19.4	18.8	17.9	16.6
15	...	20.5	20.3	20.2	20.1	19.8	19.4	18.8	17.9	16.6
16	...	20.5	20.3	20.2	20.1	19.8	19.4	18.8	17.9	16.6
17	...	...	...	...	...	...	...	...	...	...
18	...	23.9	23.7	23.6	23.4	23.1	22.6	21.9	20.9	...
19	...	27.3	27.1	26.9	26.7	26.4	25.9	25.0	23.8	22.2
20	...	49.7	49.5	49.3	...	...	...	...	...	...
21	...	49.7	49.5	49.3	...	...	...	...	...	...
22	...	49.7	49.5	49.3	...	...	...	...	...	...
23	...	27.3	27.1	26.9	26.7	26.4	25.9	25.0	23.8	22.2
24	...	24.6	24.6	...	...	...	...	...	...	...
25	...	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0
26	...	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0
27	...	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0	28.0
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	30.0	29.7	29.6	...	...	...	...	...	...
31	...	30.0	29.7	29.6	...	...	...	...	...	...
32	...	41.3	41.1	40.6	39.7	...	...	...	...	...
33	...	45.0	44.8	44.3	43.3	...	...	...	...	...
34	...	45.0	44.8	44.3	43.3	...	...	...	...	...
35	...	32.9	32.6	32.4	32.1	...	...	...	...	...
36	...	35.9	35.6	35.3	35.0	...	...	...	...	...
37	...	35.9	35.6	35.3	35.0	...	...	...	...	...
38	...	35.9	35.6	35.3	35.0	...	...	...	...	...
39	...	57.6	57.0	56.0	54.7	53.0	50.9	48.5	45.8	43.1
40	...	40.9	40.5	39.8	...	...	...	...	...	...
41	...	50.2	49.7	48.8	...	...	...	...	...	...
42	...	37.9	37.3	36.7	35.8	34.8	33.3	31.4	28.9	25.5
43	...	37.9	37.3	36.7	35.8	34.8	33.3	31.4	28.9	25.5
44	...	42.1	41.5	40.7	39.8	38.6	37.0	34.9	32.1	28.4
45	...	42.1	41.5	40.7	39.8	38.6	37.0	34.9	32.1	28.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	
9	...	...	...	...	...	...	...	...	...	...	...	...	
10	...	...	...	...	...	...	...	...	...	...	...	...	
11	...	...	...	...	...	...	...	...	...	...	...	...	
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	
16	...	...	...	...	...	...	...	...	...	...	...	...	
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	
19	...	...	...	...	...	...	...	...	...	...	...	...	
20	...	...	...	...	...	...	...	...	...	...	...	...	
21	...	...	...	...	...	...	...	...	...	...	...	...	
22	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	
31	...	...	...	...	...	...	...	...	...	...	...	...	
32	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	
45	...	...	...	...	...	...	...	...	...	...	...	...	

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	2
2	Mn- $\frac{1}{2}$ Mo	Plate	SA-533	A	K12521	3
3	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	1
4	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	2
5	Mn- $\frac{1}{2}$ Mo- $\frac{1}{4}$ Ni	Plate	SA-533	D	K12529	3
6	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-302	C	K12039	...
7	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	1
8	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	H80	K12039	...
9	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J80	K12539	...
10	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	2
11	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J90	K12539	...
12	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Plate	SA-533	B	K12539	3
13	Mn- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ni	Wld. pipe	SA-672	J100	K12539	...
14	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-302	D	K12054	...
15	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	1
16	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	1
17	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	2
18	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	E	K12554	2
19	Mn- $\frac{1}{2}$ Mo- $\frac{3}{4}$ Ni	Plate	SA-533	C	K12554	3
20	Mn- $\frac{1}{2}$ Ni-V	Plate	SA-225	C	K12524	...
21	Mn-V	Castings	SA-487	1	J13002	A
22	Mn-V	Castings	SA-487	1	J13002	B
23	$\frac{1}{2}$ Si- $\frac{1}{2}$ Mo	Smls. pipe	SA-335	P15	K11578	...
24	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	A
25	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	B
26	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{4}$ Mo-V	Castings	SA-487	4	J13047	E
27	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	1
28	$\frac{1}{2}$ Ni- $\frac{1}{2}$ Mo-V	Forgings	SA-541	3	K12045	2
29	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...
30	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Plate	SA-517	F	K11576	...
31	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo-V	Forgings	SA-592	F	K11576	...
32	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Cu-Mo	Smls. & wld. tube	SA-423	2	K11540	...
33	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	1
34	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	1
35	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-508	2	K12766	2
36	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo- $\frac{1}{3}$ Cr-V	Forgings	SA-541	2	K12765	2
37	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	1
38	$\frac{3}{4}$ Ni- $\frac{1}{2}$ Mo-Cr-V	Forgings	SA-508	3	K12042	2
39	$\frac{3}{4}$ Ni-1Cu- $\frac{3}{4}$ Cr	Plate	SA-736	A	K12042	3
40	$\frac{3}{4}$ Ni-1Cu- $\frac{3}{4}$ Cr	Plate	SA-736	A	K12042	3
41	$\frac{3}{4}$ Ni-1Mo- $\frac{3}{4}$ Cr	Castings	SA-217	WC5	J22000	...
42	1Ni- $\frac{1}{2}$ Cr- $\frac{1}{2}$ Mo	Castings	SA-217	WC4	J12082	...
43	$\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...
44	$\frac{1}{4}$ Ni-1Cr- $\frac{1}{2}$ Mo	Plate	SA-517	P	K21650	...
45	$\frac{1}{2}$ Ni	Forgings	SA-350	LF5	K13050	1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	90	70	...
2	...	100	83	...
3	...	80	50	...
4	...	90	70	...
5	...	100	83	...
6	...	80	50	...
7	...	80	50	...
8	...	80	50	...
9	...	80	50	...
10	...	90	70	...
11	...	90	70	...
12	...	100	83	...
13	...	100	83	...
14	...	80	50	...
15	...	80	50	...
16	...	80	50	...
17	...	90	70	...
18	...	90	70	...
19	...	100	83	...
20	...	105	70	...
21	...	85	55	...
22	...	90	65	...
23	...	60	30	...
24	...	90	60	...
25	...	105	85	...
26	...	115	95	...
27	...	80	50	...
28	...	90	65	...
29	$2\frac{1}{2} < t \leq 4$	105	90	...
30	$\leq 2\frac{1}{2}$	115	100	...
31	$\leq 2\frac{1}{2}$	115	100	...
32	...	60	37	...
33	...	80	50	...
34	...	80	50	...
35	...	90	65	...
36	...	90	65	...
37	...	80	50	...
38	...	90	65	...
39	$2 < t \leq 4$	75	65	...
40	≤ 2	85	75	...
41	...	70	40	...
42	...	70	40	...
43	$2\frac{1}{2} < t \leq 4$	105	90	...
44	$\leq 2\frac{1}{2}$	115	100	...
45	...	60	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Ferrous Materials (Cont'd)								
1	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
2	83.0	79.8	78.1	76.7	75.5	...	73.4	...	71.6
3	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
4	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
5	83.0	79.8	78.1	76.7	75.5	...	73.4	...	71.6
6	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
7	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
8	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
9	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
10	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
11	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
12	83.0	79.8	78.1	76.7	75.5	...	73.4	...	71.6
13	83.0	79.8	78.1	76.7	75.5	...	73.4	...	71.6
14	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
15	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
16	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
17	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
18	70.0	67.3	65.9	64.7	63.7	...	61.9	...	60.4
19	83.0	79.8	78.1	76.7	75.5	...	73.4	...	71.6
20	70.0	64.9	63.7	63.1	62.4	...	59.8	...	56.0
21	55.0	...	...	...	...	...	...	...	...
22	65.0	...	...	...	...	...	...	...	...
23	30.0	28.8	28.2	27.7	27.3	...	26.5	...	25.9
24	60.0	58.7	57.0	55.5	54.4	...	53.3	...	51.9
25	85.0	83.1	80.7	78.6	77.1	...	75.5	...	73.6
26	95.0	92.9	90.2	87.9	86.2	...	84.4	...	82.2
27	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
28	65.0	63.0	61.9	60.9	60.2	...	58.9	...	58.0
29	90.0	87.5	86.0	84.5	83.2	...	80.9	...	78.9
30	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
31	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
32	37.0	...	...	...	...	...	...	...	...
33	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
34	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
35	65.0	62.5	61.2	60.1	59.1	...	57.5	...	56.1
36	65.0	62.5	61.2	60.1	59.1	...	57.5	...	56.1
37	50.0	48.1	47.0	46.2	45.5	...	44.2	...	43.2
38	65.0	62.5	61.2	60.1	59.1	...	57.5	...	56.1
39	65.0	...	61.1	...	58.6	...	56.8	...	54.9
40	75.0	...	70.6	...	67.6	...	65.6	...	63.4
41	40.0	38.4	37.6	37.0	36.4	...	35.4	...	34.5
42	40.0	38.4	37.6	37.0	36.4	...	35.4	...	34.5
43	90.0	87.5	86.0	84.5	83.2	...	80.9	...	78.9
44	100.0	97.2	95.5	93.9	92.4	...	89.9	...	87.6
45	30.0	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	$1\frac{1}{2}\text{Ni}$	Forgings	SA-350	LF5	K13050	2
2	$1\frac{3}{4}\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-320	L43	G43400	...
3	$1\frac{3}{4}\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Forgings	SA-372	L	K24055	...
4	$1\frac{3}{4}\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-574	4340	G43400	...
5	$1\frac{3}{4}\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-574	4340	G43400	...
6	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	5
7	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	5
8	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	4
9	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	3
(25) 10	Alloy steel	Bolting	SA/ISO 898-1	10.9	...	...
(25) 11	Alloy steel	Bolting	SA/ISO 898-1	12.9	...	...
12	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	2
13	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$	Bolting	SA-540	B23	H43400	1
14	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	5
15	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	5
16	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	4
17	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	3
18	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	2
19	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$	Bolting	SA-540	B24	K24064	1
20	$2\text{Ni}-1\text{Cu}$	Forgings	SA-182	FR	K22035	...
21	$2\text{Ni}-1\text{Cu}$	Fittings	SA-234	WPR	K22035	...
22	$2\text{Ni}-1\text{Cu}$	Smls. & wld. pipe	SA-333	9	K22035	...
23	$2\text{Ni}-1\text{Cu}$	Tube	SA-334	9	K22035	...
24	$2\text{Ni}-1\text{Cu}$	Forgings	SA-350	LF9	K22036	...
25	$2\text{Ni}-1\text{Cu}$	Smls. & wld. fittings	SA-420	WPL9	K22035	...
(25) 26	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-372	N	K23550	100
27	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	1
(25) 28	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-372	N	K23550	120
29	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	2
30	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	2a
31	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	3
32	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	4
33	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	Forgings	SA-723	1	K23550	5
34	$2\frac{1}{2}\text{Ni}$	Pipe	SA-333	7	K21903	...
35	$2\frac{1}{2}\text{Ni}$	Tube	SA-334	7	K21903	...
36	$2\frac{1}{2}\text{Ni}$	Plate	SA-203	A	K21703	...
37	$2\frac{1}{2}\text{Ni}$	Plate	SA-203	B	K22103	...
38	$2\frac{1}{2}\text{Ni}$	Castings	SA-352	LC2	J22500	...
39	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	C	...	3
40	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	C	...	1
41	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	C	...	2
(25) 42	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-372	P	K34035	100
43	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	1
(25) 44	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-372	P	K34035	120
45	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	2

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	70	37.5	...
2	≤ 4	125	105	...
3	...	155	135	...
4	$\geq \frac{5}{8}$	170	135	...
5	$\leq \frac{1}{2}$	180	140	...
6	$6 < t \leq 9\frac{1}{2}$	115	100	...
7	≤ 6	120	105	...
8	$\leq 9\frac{1}{2}$	135	120	...
9	$\leq 9\frac{1}{2}$	145	130	...
10	...	151	136.5	...
11	...	177	159.5	...
12	$\leq 9\frac{1}{2}$	155	140	...
13	≤ 8	165	150	...
14	$6 < t \leq 9\frac{1}{2}$	115	100	...
15	≤ 6	120	105	...
16	$\leq 9\frac{1}{2}$	135	120	...
17	$\leq 9\frac{1}{2}$	145	130	...
18	$\leq 9\frac{1}{2}$	155	140	...
19	≤ 8	165	150	...
20	...	63	46	...
21	...	63	46	...
22	...	63	46	...
23	...	63	46	...
24	...	63	46	...
25	...	63	46	...
26	...	115	100	...
27	...	115	100	...
28	...	135	120	...
29	...	135	120	...
30	...	145	130	...
31	...	155	140	...
32	...	175	160	...
33	...	190	180	...
34	...	65	35	...
35	...	65	35	...
36	...	65	37	...
37	...	70	40	...
38	...	70	40	...
39	...	90	70	...
40	...	105	85	...
41	...	115	100	...
42	...	115	100	...
43	...	115	100	...
44	...	135	120	...
45	...	135	120	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	37.5	...	...	...	...	...	...	...	...
2	105.0	...	99.0	...	95.7	...	91.8	...	88.5
3	135.0	132.1	129.7	127.7	126.2	125.0	124.0	123.2	122.4
4	135.0	...	129.6	...	126.3	...	124.1	...	122.4
5	140.0	...	134.4	...	131.0	...	128.7	...	126.9
6	100.0	...	96.0	...	93.5	...	91.9	...	90.6
7	105.0	...	100.8	...	98.2	...	96.5	...	95.2
8	120.0	...	115.2	...	112.2	...	110.3	...	108.8
9	130.0	...	124.8	...	121.6	...	119.5	...	117.8
10	136.3	...	130.8	...	127.4	...	...	...	...
11	159.5	...	153.1	...	149.1	...	...	...	...
12	140.0	...	134.4	...	131.0	...	128.7	...	126.9
13	150.0	...	144.0	...	140.3	...	137.9	...	136.0
14	100.0	...	96.0	...	93.5	...	91.9	...	90.6
15	105.0	...	100.8	...	98.2	...	96.5	...	95.2
16	120.0	...	115.2	...	112.2	...	110.3	...	108.8
17	130.0	...	124.8	...	121.6	...	119.5	...	117.8
18	140.0	...	134.4	...	131.0	...	128.7	...	126.9
19	150.0	...	144.0	...	140.3	...	137.9	...	136.0
20	46.0	...	...	...	...	...	...	...	...
21	46.0	...	...	...	...	...	...	...	...
22	46.0	...	...	...	...	...	...	...	...
23	46.0	...	...	...	...	...	...	...	...
24	46.0	...	...	...	...	...	...	...	...
25	46.0	...	...	...	...	...	...	...	...
26	100.0	97.5	96.0	94.6	93.5	...	91.9	...	90.6
27	100.0	97.5	96.0	94.6	93.5	...	91.9	...	90.6
28	120.0	117.0	115.2	113.6	112.2	...	110.3	...	108.8
29	120.0	117.0	115.2	113.6	112.2	...	110.3	...	108.8
30	130.0	...	125.0	...	122.0	...	120.0	...	118.0
31	140.0	136.5	134.4	132.5	131.0	...	128.7	...	126.9
32	160.0	156.0	153.6	151.4	149.7	...	147.1	...	145.0
33	180.0	175.5	172.8	170.4	168.4	...	165.5	...	163.2
34	35.0	32.9	32.1	31.4	30.9	...	29.9	...	28.4
35	35.0	32.9	32.1	31.4	30.9	...	29.9	...	28.4
36	37.0	34.8	33.9	33.2	32.7	...	31.6	...	30.0
37	40.0	37.6	36.6	35.9	35.4	...	34.2	...	32.5
38	40.0	37.6	36.6	35.9	35.4	...	34.2	...	32.5
39	70.0	67.3	65.9	64.8	63.9	...	62.5	...	61.4
40	85.0	81.8	80.1	78.7	77.5	...	75.8	...	74.5
41	100.0	96.2	94.2	92.5	91.2	...	89.2	...	87.7
42	100.0	97.5	96.0	94.6	93.5	...	91.9	...	90.6
43	100.0	97.5	96.0	94.6	93.5	...	91.9	...	90.6
44	120.0	117.0	115.2	113.6	112.2	...	110.3	...	108.8
45	120.0	117.0	115.2	113.6	112.2	...	110.3	...	108.8

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	...	...	...	...	...	...	...	...	...
2	...	84.3	82.1	79.2	...	...	...	...	...	...
3	121.4	120.0	118.3	116.1	113.3	110.1	106.4	102.5	98.7	95.2
4	...	120.0	118.3	116.1	113.4	110.1	106.4	102.5	98.6	95.2
5	...	124.5	122.7	120.4	117.6	114.2	110.4	106.3	102.3	98.7
6	...	88.9	87.6	86.0	84.0	81.6	78.8	75.9	73.1	70.5
7	...	93.4	92.0	90.3	88.2	85.6	82.8	79.7	76.7	74.0
8	...	106.7	105.2	103.2	100.8	97.9	94.6	91.1	87.7	84.6
9	...	115.6	113.9	111.8	109.2	106.0	102.5	98.7	95.0	91.6
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	124.5	122.7	120.4	117.6	114.2	110.4	106.3	102.3	98.7
13	...	133.4	131.4	129.0	126.0	122.3	118.3	113.9	109.6	105.7
14	...	88.9	87.6	86.0	84.0	81.6	78.8	75.9	73.1	70.5
15	...	93.4	92.0	90.3	88.2	85.6	82.8	79.7	76.7	74.0
16	...	106.7	105.2	103.2	100.8	97.9	94.6	91.1	87.7	84.6
17	...	115.6	113.9	111.8	109.2	106.0	102.5	98.7	95.0	91.6
18	...	124.5	122.7	120.4	117.6	114.2	110.4	106.3	102.3	98.7
19	...	133.4	131.4	129.0	126.0	122.3	118.3	113.9	109.6	105.7
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	88.9	87.6	86.0	84.0	81.6	80.9	79.4	77.8	...
27	...	88.9	87.6	86.0	84.0	81.6	80.9	79.4	77.8	...
28	...	106.7	105.2	103.2	100.8	97.9	97.1	95.2	93.4	...
29	...	106.7	105.2	103.2	100.8	97.9	97.1	95.2	93.4	...
30	...	116.0	114.0	112.0	109.0	106.0	...	...	...	...
31	...	124.5	122.7	120.4	117.6	114.2	113.3	111.1	108.9	...
32	...	142.2	140.2	137.6	134.3	130.5	129.5	127.0	124.5	...
33	...	160.0	157.7	154.8	151.1	146.8	145.6	142.8	140.0	...
34	...	26.3	25.0	23.6	22.1	20.5	19.0	17.5	16.0	14.6
35	...	26.3	25.0	23.6	22.1	20.5	19.0	17.5	16.0	14.6
36	...	27.8	26.4	24.9	23.4	21.7	20.1	18.4	16.9	15.4
37	...	30.0	28.6	27.0	25.3	23.5	21.7	19.9	18.3	16.7
38	...	30.0	28.6	27.0	25.3	23.5	21.7	19.9	18.3	16.7
39	...	60.2	59.5	58.7	57.6	56.2	54.6	52.6	50.2	47.3
40	...	73.1	72.3	71.2	69.9	68.3	66.3	63.9	60.9	57.5
41	...	86.0	85.0	83.8	82.2	80.3	78.0	75.1	71.7	67.6
42	...	88.9	87.6	86.0	84.0	81.6	80.9	79.4	77.8	...
43	...	88.9	87.6	86.0	84.0	81.6	80.9	79.4	77.8	...
44	...	106.7	105.2	103.2	100.8	97.9	97.1	95.2	93.4	...
45	...	106.7	105.2	103.2	100.8	97.9	97.1	95.2	93.4	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	2a
2	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	3
3	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	4
4	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	2	K34035	5
5	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	B	K42339	3
6	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-372	M	K42365	85
7	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	B	K42339	1
8	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-508	5	K42365	2
9	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Plate	SA-543	B	K42339	2
10	$3\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	Forgings	SA-372	M	K42365	100
11	$3\frac{1}{2}\text{Ni}$	Pipe	SA-333	3	K31918	...
12	$3\frac{1}{2}\text{Ni}$	Tube	SA-334	3	K31918	...
13	$3\frac{1}{2}\text{Ni}$	Fittings	SA-420	WPL3	...	...
14	$3\frac{1}{2}\text{Ni}$	Plate	SA-203	D	K31718	...
15	$3\frac{1}{2}\text{Ni}$	Forgings	SA-350	LF3	K32025	...
16	$3\frac{1}{2}\text{Ni}$	Forgings	SA-765	III	K32026	...
17	$3\frac{1}{2}\text{Ni}$	Plate	SA-203	E	K32018	...
18	$3\frac{1}{2}\text{Ni}$	Castings	SA-352	LC3	J31550	...
19	$3\frac{1}{2}\text{Ni}$	Plate	SA-203	F	...	...
20	$3\frac{1}{2}\text{Ni}$	Plate	SA-203	F	...	...
(25) 21	$3\frac{1}{2}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Mn}$	Castings	SA-487	17	...	A
(25) 22	$3\frac{1}{2}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Mn}$	Castings	SA-487	17	...	A
(25) 23	$3\frac{1}{2}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Mn}$	Castings	SA-487	17	...	A
(25) 24	$3\frac{1}{2}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Mn}$	Castings	SA-487	17	...	A
25	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-508	4N	K22375	3
26	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-541	4N	K42343	3
27	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-508	4N	K22375	1
28	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-541	5	K42348	1
29	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-508	4N	K22375	2
30	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-541	4N	K42343	2
31	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-541	5	K42348	2
32	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	1
33	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	2
34	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	2a
35	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	3
36	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	4
37	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	Forgings	SA-723	3	K44045	5
38	$5\text{Ni}-\frac{1}{4}\text{Mo}$	Plate	SA-645	A	K41583	...
39	7Ni	Plate	SA-553	III	K61365	...
40	8Ni	Forgings	SA-522	II	K71340	...
41	8Ni	Plate	SA-553	II	K71340	...
42	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	NNT640
43	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	QT640
44	9Ni	Plate	SA/EN 10028-4	X7Ni9	...	QT
45	9Ni	Plate	SA/EN 10028-4	X8Ni9	...	QT680

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	145	130	...
2	...	155	140	...
3	...	175	160	...
4	...	190	180	...
5	...	90	70	...
6	...	105	85	...
7	...	105	85	...
8	...	115	100	...
9	...	115	100	...
10	...	120	100	...
11	...	65	35	...
12	...	65	35	...
13	...	65	35	...
14	...	65	37	...
15	...	70	37.5	...
16	...	70	37.5	...
17	...	70	40	...
18	...	70	40	...
19	>2	75	50	...
20	≤2	80	55	...
21	12 < t ≤ 14	102	88	...
22	8 < t ≤ 12	106	91	...
23	6 < t ≤ 8	110	94	...
24	≤6	113	97	...
25	...	90	70	...
26	...	90	70	...
27	...	105	85	...
28	...	105	85	...
29	...	115	100	...
30	...	115	100	...
31	...	115	100	...
32	...	115	100	...
33	...	135	120	...
34	...	145	130	...
35	...	155	140	...
36	...	175	160	...
37	...	190	180	...
38	...	95	65	...
39	≤2	100	85	...
40	...	100	75	...
41	...	100	85	...
42	≤2	93	69.5	...
43	≤2	93	69.5	...
44	≤2	98.5	83.5	...
45	≤2	98.5	83.5	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	130.0	...	125.0	...	122.0	...	120.0	...	118.0
2	140.0	136.5	134.4	132.5	131.0	...	128.7	...	126.9
3	160.0	156.0	153.6	151.4	149.7	...	147.1	...	145.0
4	180.0	175.5	172.8	170.4	168.4	...	165.5	...	163.2
5	70.0	67.3	65.9	64.8	63.9	...	62.5	...	61.4
6	85.0	81.8	80.1	78.7	77.5	76.6	75.8	75.2	74.5
7	85.0	81.8	80.1	78.7	77.5	...	75.8	...	74.5
8	100.0	96.2	94.2	92.6	91.2	90.1	89.2	88.5	87.6
9	100.0	96.2	94.2	92.5	91.2	...	89.2	...	87.7
10	100.0	96.2	94.2	92.5	91.2	90.1	89.2	88.4	87.7
11	35.0	32.9	32.1	31.4	30.9	...	29.9	...	28.4
12	35.0	32.9	32.1	31.4	30.9	...	29.9	...	28.4
13	35.0	32.9	32.1	31.4	30.9	...	29.9	...	28.4
14	37.0	34.8	33.9	33.2	32.7	...	31.6	...	30.0
15	37.5	35.3	34.3	33.7	33.2	...	32.0	...	30.4
16	37.5	35.3	34.3	33.7	33.2	...	32.0	...	30.4
17	40.0	37.6	36.6	35.9	35.4	...	34.2	...	32.5
18	40.0	37.6	36.6	35.9	35.4	...	34.2	...	32.5
19	50.0	47.0	45.8	44.9	44.2	...	42.7	...	40.6
20	55.0	51.7	50.4	49.4	48.6	...	47.0	...	44.6
21	88	...	...	...	...	...	...	...	...
22	91	...	...	...	...	...	...	...	...
23	94	...	...	...	...	...	...	...	...
24	97	...	...	...	...	...	...	...	...
25	70.0	67.3	65.9	64.8	63.9	...	62.5	...	61.4
26	70.0	...	65.9	...	63.9	...	62.5	...	61.4
27	85.0	81.8	80.1	78.7	77.5	...	75.8	...	74.5
28	85.0	...	80.1	...	77.5	...	75.8	...	74.5
29	100.0	96.2	94.2	92.5	91.2	...	89.2	...	87.7
30	100.0	...	94.2	...	91.2	...	89.2	...	87.7
31	100.0	...	94.2	...	91.2	...	89.2	...	87.7
32	100.0	97.5	96.0	94.6	93.5	...	91.9	...	90.6
33	120.0	117.0	115.2	113.6	112.2	...	110.3	...	108.8
34	130.0	...	125.0	...	122.0	...	120.0	...	118.0
35	140.0	136.5	134.4	132.5	131.0	...	128.7	...	126.9
36	160.0	156.0	153.6	151.4	149.7	...	147.1	...	145.0
37	180.0	175.5	172.8	170.4	168.4	...	165.5	...	163.2
38	65.0	...	...	...	...	...	...	...	...
39	85.0	80.9	...	...	...	...	...	...	...
40	75.0	72.8	72.0	70.5	67.0	...	...	...	...
41	85.0	82.5	81.6	79.9	75.9	...	...	...	...
42	69.6	67.6	66.9	65.4	62.1	...	...	...	...
43	69.6	67.6	66.9	65.4	62.1	...	...	...	...
44	83.4	81.0	80.1	78.4	74.4	...	...	...	...
45	83.4	81.0	80.1	78.4	74.4	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	116.0	114.0	112.0	109.0	106.0	...	...	...	...
2	...	124.5	122.7	120.4	117.6	114.2	113.3	111.1	108.9	...
3	...	142.2	140.2	137.6	134.3	130.5	129.5	127.0	124.5	...
4	...	160.0	157.7	154.8	151.1	146.8	145.6	142.8	140.0	...
5	...	60.2	59.5	58.7	57.6	56.2	54.6	52.6	50.2	47.3
6	73.9	73.1	72.3	71.2	69.9	68.3	66.3	63.9	60.9	57.5
7	...	73.1	72.3	71.2	69.9	68.3	66.3	63.9	60.9	57.5
8	86.9	86.0	85.1	83.8	82.2	80.4	78.0	75.2	71.6	67.6
9	...	86.0	85.0	83.8	82.2	80.3	78.0	75.1	71.7	67.6
10	86.9	86.0	85.0	83.8	82.2	80.3	78.0	75.1	71.7	67.6
11	...	26.3	25.0	23.6	22.1	20.5	19.0	17.5	16.0	14.6
12	...	26.3	25.0	23.6	22.1	20.5	19.0	17.5	16.0	14.6
13	...	26.3	25.0	23.6	22.1	20.5	19.0	17.5	16.0	14.6
14	...	27.8	26.4	24.9	23.4	21.7	20.1	18.4	16.9	15.4
15	...	28.2	26.8	25.3	23.7	22.0	20.3	18.7	17.1	15.6
16	...	28.2	26.8	25.3	23.7	22.0	20.3	18.7	17.1	15.6
17	...	30.0	28.6	27.0	25.3	23.5	21.7	19.9	18.3	16.7
18	...	30.0	28.6	27.0	25.3	23.5	21.7	19.9	18.3	16.7
19	...	37.5	35.7	33.7	31.6	29.4	27.1	24.9	22.8	20.8
20	...	41.3	39.3	37.1	34.7	32.3	29.8	27.4	25.1	22.9
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	60.2	59.5	58.7	57.6	56.2	54.6	52.6	50.2	47.3
26	...	60.2	59.5	58.7	...	...	...	...	...	...
27	...	73.1	72.3	71.2	69.9	68.3	66.3	63.9	60.9	57.5
28	...	73.1	72.3	71.2	...	...	...	...	...	...
29	...	86.0	85.0	83.8	82.2	80.3	78.0	75.1	71.7	67.6
30	...	86.0	85.0	83.9	...	...	...	...	...	...
31	...	86.0	85.0	83.9	...	...	...	...	...	...
32	...	88.9	87.6	86.0	84.0	81.6	80.9	79.4	77.8	...
33	...	106.7	105.2	103.2	100.8	97.9	97.1	95.2	93.4	...
34	...	116.0	114.0	112.0	109.0	106.0	...	...	...	...
35	...	124.5	122.7	120.4	117.6	114.2	113.3	111.1	108.9	...
36	...	142.2	140.2	137.6	134.3	130.5	129.5	127.0	124.5	...
37	...	160.0	157.7	154.8	151.1	146.8	145.6	142.8	140.0	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)
(25)
(25)
(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	9Ni	Smls. & wld. pipe	SA-333	8	K81340	...
2	9Ni	Smls. & wld. tube	SA-334	8	K81340	...
3	9Ni	Plate	SA-353	...	K81340	...
4	9Ni	Smls. & wld. fittings	SA-420	WPL8	K81340	...
5	9Ni	Forgings	SA-522	I	K81340	...
6	9Ni	Plate	SA-553	I	K81340	...
(25) 7	46Fe-24Ni-21Cr-6Mo-N	Smls. & wld. fittings	SA-403	...	N08367	...
(25) 8	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-182	F62	N08367	...
(25) 9	46Fe-24Ni-21Cr-6Mo-N	Forgings	SA-965	F62	N08367	...
(25) 10	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...
(25) 11	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...
(25) 12	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...
(25) 13	46Fe-24Ni-21Cr-6Mo-N	Plate	SA-240	...	N08367	...
(25) 14	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...
(25) 15	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-276	...	N08367	...
(25) 16	46Fe-24Ni-21Cr-6Mo-N	Bar	SA-479	...	N08367	...
(25) 17	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SA-312	...	N08367	...
(25) 18	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-688	...	N08367	...
(25) 19	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SA-249	...	N08367	...
(25) 20	46Fe-24Ni-21Cr-6Mo-N	Sheet, strip	SA-240	...	N08367	...
(25) 21	46Fe-24Ni-21Cr-6Mo-N	Smls. tube	SA-213	...	N08367	...
22	25Ni-15Cr-2Ti	Bolting	SA-453	660	S66286	A
23	25Ni-15Cr-2Ti	Bolting	SA-453	660	S66286	B
24	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660	S66286	1
25	25Ni-15Cr-2Ti	Forgings, bar	SA-638	660	S66286	2
(25) 26	25Ni-47Fe-21Cr-5Mo	Forgings	SA-182	F700	N08700	...
(25) 27	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SA-240	...	N08700	...
(25) 28	25Ni-47Fe-21Cr-5Mo	Bar	SA-276	...	N08700	...
(25) 29	25Ni-47Fe-21Cr-5Mo	Wld. pipe	SA-358	...	N08700	...
(25) 30	25Ni-47Fe-21Cr-5Mo	Fittings	SA-403	700	N08700	...
(25) 31	25Ni-47Fe-21Cr-5Mo	Bar	SA-479	...	N08700	...
(25) 32	25Ni-47Fe-21Cr-5Mo	Forgings	SA-965	F700	N08700	...
33	27Ni-22Cr-7Mo-Mn-Cu-N	Forgings	SA-182	...	S31277	...
34	27Ni-22Cr-7Mo-Mn-Cu-N	Smls. tube	SA-213	...	S31277	...
35	27Ni-22Cr-7Mo-Mn-Cu-N	Plate	SA-240	...	S31277	...
36	27Ni-22Cr-7Mo-Mn-Cu-N	Wld. tube	SA-249	...	S31277	...
37	29Ni-20Cr-3Cu-2Mo	Castings	SA-351	CN7M	J95150	...
(25) 38	35Ni-35Fe-20Cr-Cb	Forgings	SA-182	F20	N08020	...
(25) 39	35Ni-35Fe-20Cr-Cb	Forgings	SA-965	F20	N08020	...
(25) 40	35Ni-35Fe-20Cr-Cb	Plate	SA-240	...	N08020	...
(25) 41	35Ni-35Fe-20Cr-Cb	Bar	SA-276	Alloy 20	N08020	...
(25) 42	35Ni-35Fe-20Cr-Cb	Bar	SA-479	Alloy 20	N08020	...
(25) 43	35Ni-35Fe-20Cr-Cb	Smls. pipe	SA-312	Alloy 20	N08020	...
(25) 44	35Ni-35Fe-20Cr-Cb	Wld. pipe	SA-312	Alloy 20	N08020	...
(25) 45	35Ni-35Fe-20Cr-Cb	Smls. tube	SA-213	Alloy 20	N08020	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	100	75	...
2	...	100	75	...
3	...	100	75	...
4	...	100	75	...
5	...	100	75	...
6	...	100	85	...
7	...	95	45	...
8	...	95	45	...
9	...	95	45	...
10	$> \frac{3}{16}$	95	45	...
11	$> \frac{3}{16}$	95	45	...
12	$> \frac{3}{16}$	95	45	...
13	$\geq \frac{3}{16}$	95	45	...
14	$> \frac{3}{16}$	95	45	...
15	...	95	45	...
16	...	95	45	...
17	$\leq \frac{3}{16}$	100	45	...
18	$\leq \frac{3}{16}$	100	45	...
19	$\leq \frac{3}{16}$	100	45	...
20	$< \frac{3}{16}$	100	45	...
21	$\leq \frac{3}{16}$	100	45	...
22	...	130	85	...
23	...	130	85	...
24	...	130	85	...
25	...	130	85	...
26	...	80	35	...
27	...	80	35	...
28	...	80	35	...
29	...	80	35	...
30	...	80	35	...
31	...	80	35	...
32	...	80	35	...
33	...	112	52	...
34	...	112	52	...
35	...	112	52	...
36	...	112	52	...
37	...	62	25	...
38	...	80	35	...
39	...	80	35	...
40	...	80	35	...
41	...	80	35	...
42	...	80	35	...
43	...	80	35	...
44	...	80	35	...
45	...	80	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	75.0	72.8	72.0	70.5	67.0	...	...	...	...
2	75.0	72.8	72.0	70.5	67.0	...	...	...	...
3	75.0	72.8	72.0	70.5	67.0	...	...	...	...
4	75.0	72.8	72.0	70.5	67.0	...	...	...	...
5	75.0	72.8	72.0	70.5	67.0	...	...	...	...
6	85.0	82.5	81.6	79.9	75.9	...	...	...	...
7	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
8	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
9	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
10	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
11	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
12	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
13	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
14	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
15	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
16	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
17	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
18	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
19	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
20	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
21	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
22	85.0	...	83.3	...	82.0	...	80.8	...	79.3
23	85.0	...	83.3	...	82.0	...	80.8	...	79.3
24	85.0	...	83.3	...	82.0	...	80.7	...	79.4
25	85.0	...	83.3	...	82.0	...	80.7	...	79.4
26	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
27	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
28	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
29	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
30	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
31	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
32	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
33	52.0	50.5	48.2	45.6	43.2	41.2	39.7	38.8	38.3
34	52.0	50.5	48.2	45.6	43.2	41.2	39.7	38.8	38.3
35	52.0	50.5	48.2	45.6	43.2	41.2	39.7	38.8	38.3
36	52.0	50.5	48.2	45.6	43.2	41.2	39.7	38.8	38.3
37	25.0	...	21.6	...	19.4	...	17.6	...	16.2
38	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
39	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
40	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
41	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
42	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
43	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
44	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
45	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
8	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
9	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
10	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
11	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
12	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
13	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
14	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
15	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
16	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
17	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
18	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
19	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
20	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
21	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
22	...	77.9	77.2	76.4	75.7	74.9	74.0	73.2	72.3	71.5
23	...	77.9	77.2	76.4	75.7	74.9	74.0	73.2	72.3	71.5
24	...	77.9	77.2	76.4	75.7	74.9	74.0	73.2	...	...
25	...	77.9	77.2	76.4	75.7	74.9	74.0	73.2	...	...
26	25.3	24.7	23.8	...	...	...	...	...	...	...
27	25.3	24.7	23.8	...	...	...	...	...	...	...
28	25.3	24.7	23.8	...	...	...	...	...	...	...
29	25.3	24.7	23.8	...	...	...	...	...	...	...
30	25.3	24.7	23.8	...	...	...	...	...	...	...
31	25.3	24.7	23.8	...	...	...	...	...	...	...
32	25.3	24.7	23.8	...	...	...	...	...	...	...
33	38.1	38.1	38.0	37.9	37.7	37.4	...	...	...	...
34	38.1	38.1	38.0	37.9	37.7	37.4	...	...	...	...
35	38.1	38.1	38.0	37.9	37.7	37.4	...	...	...	...
36	38.1	38.1	38.0	37.9	37.7	37.4	...	...	...	...
37	...	15.0	14.5	14.0	...	...	...	...	...	...
38	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
39	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
40	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
41	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
42	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
43	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
44	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
45	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	(25)
19	...	...	...	...	...	...	...	...	...	...	...	...	(25)
20	...	...	...	...	...	...	...	...	...	...	...	...	(25)
21	...	...	...	...	...	...	...	...	...	...	...	...	(25)
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	(25)
27	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	(25)
41	...	...	...	...	...	...	...	...	...	...	...	...	(25)
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/Temper
Ferrous Materials (Cont'd)						
(25) 1	35Ni-35Fe-20Cr-Cb	Wld. tube	SA-249	Alloy 20	N08020	...
(25) 2	35Ni-35Fe-20Cr-Cb	Smls. & wld. ftgs.	SA-403	...	N08020	...
(25) 3	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC11	N08811	...
(25) 4	42Fe-33Ni-21Cr	Smls. tube	SA-213	...	N08811	...
(25) 5	42Fe-33Ni-21Cr	Plate	SA-240	...	N08811	...
(25) 6	42Fe-33Ni-21Cr	Wld. tube	SA-249	...	N08811	...
(25) 7	42Fe-33Ni-21Cr	Bar	SA-276	...	N08811	...
(25) 8	42Fe-33Ni-21Cr	Smls. pipe	SA-312	...	N08811	...
(25) 9	42Fe-33Ni-21Cr	Bar	SA-479	...	N08811	...
(25) 10	42Fe-33Ni-21Cr	Wld. tube	SA-688	...	N08811	...
(25) 11	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC11	N08811	...
12	14Cr-16Ni-6Si-Cu-Mo	Smls. tube	SA-213	...	S38815	...
13	14Cr-16Ni-6Si-Cu-Mo	Plate	SA-240	...	S38815	...
14	14Cr-16Ni-6Si-Cu-Mo	Wld. tube	SA-249	...	S38815	...
15	14Cr-16Ni-6Si-Cu-Mo	Wld. pipe	SA-312	...	S38815	...
16	14Cr-16Ni-6Si-Cu-Mo	Smls. & wld. fittings	SA-403	...	S38815	...
17	14Cr-16Ni-6Si-Cu-Mo	Bar	SA-479	...	S38815	...
18	16Cr-4Ni-6Mn	Plate	SA-240	201LN	S20153	...
19	16Cr-9Mn-2Ni-N	Plate	SA-240	204	S20400	...
20	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...
21	16Cr-12Ni-2Mo	Forgings	SA-965	F316L	S31603	...
22	16Cr-12Ni-2Mo	Forgings	SA-182	F316L	S31603	...
23	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316L	S31603	...
24	16Cr-12Ni-2Mo	Plate	SA-240	316L	S31603	...
25	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316L	S31603	...
26	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316L	S31603	...
27	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	1
28	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	3
29	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316L	S31603	4
30	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316L	S31603	...
31	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316L	S31603	...
32	16Cr-12Ni-2Mo	Bar	SA-479	316L	S31603	Annealed
33	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316L	S31603	...
34	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316L	S31603	...
35	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316L	S31603	...
36	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316L	...	...
37	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...
38	16Cr-12Ni-2Mo	Forgings	SA-965	F316	S31600	...
39	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...
40	16Cr-12Ni-2Mo	Forgings	SA-965	F316H	S31609	...
41	16Cr-12Ni-2Mo	Forgings	SA-182	F316	S31600	...
42	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	1
43	16Cr-12Ni-2Mo	Bolting	SA-193	B8MA	S31600	1A
44	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316	S31600	...
45	16Cr-12Ni-2Mo	Plate	SA-240	316	S31600	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	80	35	...
2	...	85	40	...
3	...	65	25	...
4	...	65	25	...
5	...	65	25	...
6	...	65	25	...
7	...	65	25	...
8	...	65	25	...
9	...	65	25	...
10	...	65	25	...
11	...	65	25	...
12	...	78	37	...
13	...	78	37	...
14	...	78	37	...
15	...	78	37	...
16	...	78	37	...
17	...	78	37	...
18	...	95	45	...
19	...	95	48	...
20	>5	65	25	...
21	...	65	25	...
22	≤5	70	25	...
23	...	70	25	...
24	...	70	25	...
25	...	70	25	...
26	...	70	25	...
27	...	70	25	...
28	...	70	25	...
29	...	70	25	...
30	...	70	25	...
31	...	70	25	...
32	...	70	25	...
33	...	70	25	...
34	...	70	25	...
35	...	70	25	...
36	...	70	25	...
37	>5	70	30	...
38	...	70	30	...
39	>5	70	30	...
40	...	70	30	...
41	≤5	75	30	...
42	...	75	30	...
43	...	75	30	...
44	...	75	30	...
45	...	75	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
2	40.0	36.6	35.4	34.5	33.8	33.1	32.5	31.8	31.2
3	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
4	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
5	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
6	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
7	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
8	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
9	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
10	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
11	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
12	37.0	...	31.2	...	27.8	...	25.6	...	24.4
13	37.0	...	31.2	...	27.8	...	25.6	...	24.4
14	37.0	...	31.2	...	27.8	...	25.6	...	24.4
15	37.0	...	31.2	...	27.8	...	25.6	...	24.4
16	37.0	...	31.2	...	27.8	...	25.6	...	24.4
17	37.0	...	31.2	...	27.8	...	25.6	...	24.4
18	45.0	...	36.3	...	32.9	...	31.1	...	30.0
19	48.0	40.3	36.4	33.1	30.5	...	26.8	...	24.8
20	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
21	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
22	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
23	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
24	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
25	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
26	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
27	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
28	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
29	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
30	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
31	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
32	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
33	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
34	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
35	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
36	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
37	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
38	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
39	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
40	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
41	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
42	30.0	...	25.9	...	23.4	...	21.4	...	20.0
43	30.0	...	25.9	...	23.4	...	21.4	...	20.0
44	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
45	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
2	30.7	30.3	30.0	29.8	29.4	28.8	...	...	...	...
3	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
4	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
5	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
6	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
7	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
8	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
9	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
10	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
11	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
12	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
13	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
14	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
15	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
16	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
17	...	24.0	24.0	24.0	24.0	24.0	...	...	...	...
18	...	28.7	27.9	27.0	26.0	25.1	24.2	23.6	23.6	23.6
19	...	23.8	23.5	23.2	23.0	22.7	22.2	21.5	20.5	19.1
20	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
21	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
22	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
23	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
24	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
25	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
26	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
27	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
28	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
29	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
30	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
31	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
32	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
33	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
34	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
35	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
36	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
37	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
38	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
39	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
40	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
41	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
42	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
43	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
44	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
45	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
4	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
5	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
6	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
7	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
8	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
9	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
10	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
11	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
21	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
22	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
23	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
24	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
25	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
26	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
27	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
28	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
29	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
30	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
31	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
32	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
33	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
34	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
35	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
38	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
42	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
43	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
44	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
45	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316	S31600	...
2	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316	S31600	...
3	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	1
4	16Cr-12Ni-2Mo	Bolting	SA-320	B8MA	S31600	1A
5	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	1
6	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	3
7	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316	S31600	4
8	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316	S31600	...
9	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316	S31600	...
10	16Cr-12Ni-2Mo	Wld. pipe	SA-409	TP316	S31600	...
11	16Cr-12Ni-2Mo	Bar	SA-479	316	S31600	Annealed
12	16Cr-12Ni-2Mo	Wld. tube	SA-688	TP316	S31600	...
13	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316	S31600	...
14	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316	S31600	...
15	16Cr-12Ni-2Mo	Bar	SA/JIS G4303	SUS316	...	...
16	16Cr-12Ni-2Mo	Forgings	SA-182	F316H	S31609	...
17	16Cr-12Ni-2Mo	Smls. tube	SA-213	TP316H	S31609	...
18	16Cr-12Ni-2Mo	Plate	SA-240	316H	S31609	...
19	16Cr-12Ni-2Mo	Wld. tube	SA-249	TP316H	S31609	...
20	16Cr-12Ni-2Mo	Smls. & wld. pipe	SA-312	TP316H	S31609	...
21	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	1
22	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	3
23	16Cr-12Ni-2Mo	Wld. pipe	SA-358	316H	S31609	4
24	16Cr-12Ni-2Mo	Smls. pipe	SA-376	TP316H	S31609	...
25	16Cr-12Ni-2Mo	Smls. & wld. fittings	SA-403	316H	S31609	...
26	16Cr-12Ni-2Mo	Bar	SA-479	316H	S31609	...
27	16Cr-12Ni-2Mo	Wld. pipe	SA-813	TP316H	S31609	...
28	16Cr-12Ni-2Mo	Wld. pipe	SA-814	TP316H	S31609	...
29	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X2CrNiMo17-12-2	...	...
30	16Cr-12Ni-2Mo	Plate	SA/EN 10028-7	X5CrNiMo17-12-2	...	...
31	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B
32	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	S
33	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2
34	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2
35	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B
36	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	S
37	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	B
38	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2
39	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2
40	16Cr-12Ni-2Mo	Bolting	SA-193	B8M2	S31600	2B
41	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	S
42	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	B
43	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2
44	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2
45	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	B

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	75	30	...
2	...	75	30	...
3	...	75	30	...
4	...	75	30	...
5	...	75	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	≤5	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	75	30	...
22	...	75	30	...
23	...	75	30	...
24	...	75	30	...
25	...	75	30	...
26	...	75	30	...
27	...	75	30	...
28	...	75	30	...
29	≤3	75	32	...
30	≤3	75	32	...
31	$2\frac{1}{2} < t \leq 3$	80	55	...
32	$2\frac{1}{2} < t \leq 3$	80	55	...
33	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	90	50	...
34	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	90	50	...
35	$2 < t \leq 2\frac{1}{2}$	90	65	...
36	$2 < t \leq 2\frac{1}{2}$	90	65	...
37	$1\frac{1}{2} < t \leq 1\frac{3}{4}$	95	45	...
38	$1 < t \leq 1\frac{1}{4}$	95	65	...
39	$1 < t \leq 1\frac{1}{4}$	95	65	...
40	≤2	95	75	...
41	≤2	95	75	...
42	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
43	$\frac{3}{4} < t \leq 1$	100	80	...
44	$\frac{3}{4} < t \leq 1$	100	80	...
45	$1 < t \leq 1\frac{1}{4}$	105	65	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
2	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
3	30.0	...	25.9	...	23.4	...	21.4	...	20.0
4	30.0	...	25.9	...	23.4	...	21.4	...	20.0
5	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
6	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
7	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
8	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
9	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
10	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
11	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
12	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
13	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
14	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
15	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
16	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
17	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
18	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
19	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
20	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
21	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
22	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
23	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
24	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
25	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
26	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
27	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
28	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
29	31.9	28.9	27.2	25.7	24.4	...	22.3	...	20.9
30	31.9	29.1	27.6	26.2	24.9	...	22.8	...	21.2
31	55.0	...	51.7	...	48.8	...	46.5	...	45.3
32	55.0	...	51.7	...	48.8	...	46.5	...	45.3
33	50.0	...	47.0	...	44.4	...	42.3	...	41.2
34	50.0	...	47.0	...	44.4	...	42.3	...	41.2
35	65.0	...	61.1	...	57.7	...	54.9	...	53.5
36	65.0	...	61.1	...	57.7	...	54.9	...	53.5
37	45.0	...	42.3	...	39.9	...	38.0	...	37.0
38	65.0	...	61.1	...	57.7	...	54.9	...	53.5
39	65.0	...	61.1	...	57.7	...	54.9	...	53.5
40	75.0	...	70.5	...	66.5	...	63.4	...	61.7
41	75.0	...	70.5	...	66.5	...	63.4	...	61.7
42	50.0	...	47.0	...	44.4	...	42.3	...	41.2
43	80.0	...	69.1	...	65.5	...	59.6	...	55.0
44	80.0	...	69.1	...	65.5	...	59.6	...	55.0
45	65.0	...	61.1	...	57.7	...	54.9	...	53.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
2	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
3	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
4	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
5	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
6	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
7	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
8	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
9	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
10	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
11	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
12	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
13	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
14	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
15	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
16	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
17	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
18	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
19	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
20	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
21	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
22	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
23	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
24	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
25	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
26	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
27	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
28	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
29	...	19.9	19.5	19.2	18.8	18.4	18.0	17.6	17.2	16.9
30	...	20.1	19.7	19.3	19.1	18.8	18.6	18.4	18.2	18.1
31	...	44.4	43.9	43.2	42.7	42.1	41.5	40.9	40.3	39.6
32	...	44.4	...	...	...	...	...	...	...	...
33	...	40.4	39.9	39.3	38.8	38.3	37.7	37.2	36.7	36.0
34	...	40.4	39.9	39.3	38.8	38.3	37.7	37.2	36.7	36.0
35	...	52.5	51.8	51.0	50.4	49.7	49.0	48.4	47.6	46.8
36	...	52.5	...	...	...	...	...	...	...	...
37	...	36.3	...	...	...	...	...	...	...	...
38	...	52.5	51.8	51.0	50.4	49.7	49.0	48.4	47.6	46.8
39	...	52.5	51.8	51.0	50.4	49.7	49.0	48.4	47.6	46.8
40	...	60.5	59.8	58.9	58.1	57.4	56.6	55.8	55.0	54.0
41	...	60.5	...	...	...	...	...	...	...	...
42	...	40.4	...	...	...	...	...	...	...	...
43	...	51.7	49.3	48.4	47.7	47.1	46.6	46.1	45.7	45.3
44	...	51.7	49.3	48.4	47.7	47.1	46.6	46.1	45.7	45.3
45	...	52.5	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600 1650
	Ferrous Materials (Cont'd)											
1	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
2	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
3	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
4	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
5	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
6	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
7	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
8	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
9	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
10	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
11	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
12	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
13	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
14	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	16Cr-12Ni-2Mo	Bolting	SA-193	B8M	S31600	2
2	16Cr-12Ni-2Mo	Bolting	SA-320	B8M	S31600	2
3	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	B
4	16Cr-12Ni-2Mo	Bar	SA-276	316	S31600	B
5	16Cr-12Ni-2Mo-Cb	Plate	SA-240	316Cb	S31640	...
6	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...
7	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316LN	S31653	...
8	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316LN	S31653	...
9	16Cr-12Ni-2Mo-N	Bolting	SA-193	B8MNA	S31651	1A
10	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316LN	S31653	...
11	16Cr-12Ni-2Mo-N	Plate	SA-240	316LN	S31653	...
12	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316LN	S31653	...
13	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316LN	S31653	...
14	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	1
15	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	3
16	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316LN	S31653	4
17	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316LN	S31653	...
18	16Cr-12Ni-2Mo-N	Fittings	SA-403	316LN	S31653	...
19	16Cr-12Ni-2Mo-N	Bar	SA-479	316LN	S31653	...
20	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316LN	S31653	...
21	16Cr-12Ni-2Mo-N	Forgings	SA-182	F316N	S31651	...
22	16Cr-12Ni-2Mo-N	Smls. tube	SA-213	TP316N	S31651	...
23	16Cr-12Ni-2Mo-N	Plate	SA-240	316N	S31651	...
24	16Cr-12Ni-2Mo-N	Wld. tube	SA-249	TP316N	S31651	...
25	16Cr-12Ni-2Mo-N	Smls. & wld. pipe	SA-312	TP316N	S31651	...
26	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	1
27	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	3
28	16Cr-12Ni-2Mo-N	Wld. pipe	SA-358	316N	S31651	4
29	16Cr-12Ni-2Mo-N	Smls. pipe	SA-376	TP316N	S31651	...
30	16Cr-12Ni-2Mo-N	Smls. & wld. fittings	SA-403	316N	S31651	...
31	16Cr-12Ni-2Mo-N	Bar	SA-479	316N	S31651	...
32	16Cr-12Ni-2Mo-N	Wld. tube	SA-688	TP316N	S31651	...
33	16Cr-12Ni-2Mo-N	Wld. pipe	SA-813	TP316N	S31651	...
34	16Cr-12Ni-2Mo-N	Wld. pipe	SA-814	TP316N	S31651	...
35	16Cr-12Ni-2Mo-N	Forgings	SA-965	F316N	S31651	...
36	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-11-2	...	...
37	16Cr-12Ni-2Mo-N	Plate	SA/EN 10028-7	X2CrNiMoN17-13-3	...	...
38	16Cr-12Ni-2Mo-Ti	Smls. tube	SA-214	TP316Ti	S31635	...
39	16Cr-12Ni-2Mo-Ti	Plate	SA-240	316Ti	S31635	...
40	16Cr-12Ni-2Mo-Ti	Smls. & wld. pipe	SA-312	TP316Ti	S31635	...
(25) 41	...	Plate	SA/EN 10088-2	X6CrNiMoTi17-12-2	...	...
42	17Cr-4Ni-6Mn	Plate	SA-240	201-1	S20100	...
43	17Cr-4Ni-6Mn	Plate	SA-666	201-1	S20100	...
44	17Cr-4Ni-6Mn	Plate	SA-240	201-2	S20100	...
45	17Cr-4Ni-6Mn	Plate	SA-666	201-2	S20100	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	$\leq \frac{3}{4}$	110	95	...
2	$\leq \frac{3}{4}$	110	95	...
3	$\frac{3}{4} < t \leq 1$	115	80	...
4	$\leq \frac{3}{4}$	125	100	...
5	...	75	30	...
6	> 5	70	30	...
7	...	70	30	...
8	≤ 5	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	...	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	80	35	...
22	...	80	35	...
23	...	80	35	...
24	...	80	35	...
25	...	80	35	...
26	...	80	35	...
27	...	80	35	...
28	...	80	35	...
29	...	80	35	...
30	...	80	35	...
31	...	80	35	...
32	...	80	35	...
33	...	80	35	...
34	...	80	35	...
35	...	80	35	...
36	≤ 3	84	41	...
37	≤ 3	84	41	...
38	...	70	30	...
39	...	75	30	...
40	...	70	30	...
41	$t \leq \frac{5}{16}$	78.5	35	...
42	...	75	38	...
43	...	75	38	...
44	...	95	45	...
45	...	95	45	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	95.0	...	79.2	...	71.1	...	65.5	...	61.5
2	95.0	...	79.2	...	71.1	...	65.5	...	61.5
3	80.0	...	75.2	...	71.0	...	67.6	...	65.8
4	100.0	...	94.0	...	88.7	...	84.5	...	82.3
5	30.0	28.0	26.5	25.1	23.8	...	21.5	...	19.8
6	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
7	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
8	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
9	30.0	27.9	26.6	25.5	24.4	...	22.6	...	21.2
10	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
11	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
12	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
13	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
14	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
15	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
16	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
17	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
18	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
19	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
20	30.0	27.1	25.5	24.1	22.9	...	21.0	...	19.5
21	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
22	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
23	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
24	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
25	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
26	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
27	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
28	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
29	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
30	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
31	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
32	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
33	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
34	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
35	35.0	32.5	31.0	29.7	28.5	...	26.4	...	24.7
36	40.6	37.6	34.5	32.8	31.0	...	28.4	...	26.4
37	40.6	37.6	34.5	32.8	31.0	...	28.4	...	26.4
38	30.0	28.0	26.5	25.1	23.8	22.7	21.5	20.7	19.8
39	30.0	28.0	26.5	25.1	23.8	22.7	21.5	20.7	19.8
40	30.0	28.0	26.5	25.1	23.8	22.7	21.5	20.7	19.8
41	35.0	33.4	32.2	31.0	30.0	...	28.0	...	26.4
42	38.0	31.8	28.9	26.6	25.0	...	22.7	...	...
43	38.0	31.8	28.9	26.6	25.0	...	22.7	...	...
44	45.0	37.7	34.2	31.5	29.6	...	26.9	...	...
45	45.0	37.7	34.2	31.5	29.6	...	26.9	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	58.3	57.0	55.7	54.5	53.4	52.3	51.3	50.2	49.2
2	...	58.3	57.0	55.7	54.5	53.4	52.3	51.3	50.2	49.2
3	...	64.6	...	...	...	...	...	...	...	...
4	...	80.7	...	...	...	...	...	...	...	...
5	...	18.7	18.3	18.0	17.8	17.6	17.5	17.4	17.3	17.1
6	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
7	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
8	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
9	...	20.1	19.5	19.1	18.7	18.3	17.9	17.6	17.2	17.0
10	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
11	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
12	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
13	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
14	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
15	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
16	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
17	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
18	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
19	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
20	...	18.3	17.8	17.3	16.9	16.5	16.1	15.8	15.5	15.3
21	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
22	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
23	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
24	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
25	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
26	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
27	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
28	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
29	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
30	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
31	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
32	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
33	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
34	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
35	...	23.4	22.8	22.3	21.8	21.3	20.9	20.5	20.1	19.8
36	...	24.8	24.1	23.5	22.9	22.3	...	...	...	...
37	...	24.8	24.1	23.5	22.9	22.3	...	...	...	...
38	...	18.7	18.3	18.0	17.8	17.6	17.5	17.4	17.3	17.1
39	...	18.7	18.3	18.0	17.8	17.6	17.5	17.4	17.3	17.1
40	...	18.7	18.3	18.0	17.8	17.6	17.5	17.4	17.3	17.1
41	...	25.1	24.6	24.2	23.9	23.7	23.6	23.6	23.5	23.5
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
39	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
40	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	17Cr-7Ni	Plate, sheet, strip	SA-240	301	S30100	...
2	17.5Cr-17.5Ni-5.3Si	Plate	SA-240	...	S30601	Solution ann.
3	18Cr-3Ni-12Mn	Plate	SA-240	XM-29	S24000	...
4	18Cr-3Ni-12Mn	Wld. tube	SA-249	XM-29	S24000	...
5	18Cr-3Ni-12Mn	Wld. pipe	SA-312	XM-29	S24000	...
6	18Cr-3Ni-12Mn	Bar	SA-479	XM-29	S24000	...
7	18Cr-3Ni-12Mn	Wld. tube	SA-688	TPXM-29	S24000	...
8	18Cr-5Ni-3Mo	Smls. & wld. tube	SA-789	...	S31500	...
9	18Cr-5Ni-3Mo	Smls. & wld. pipe	SA-790	...	S31500	...
10	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...
11	18Cr-8Ni	Forgings	SA-965	F304L	S30403	...
12	18Cr-8Ni	Forgings	SA-182	F304L	S30403	...
13	18Cr-8Ni	Smls. tube	SA-213	TP304L	S30403	...
14	18Cr-8Ni	Plate	SA-240	304L	S30403	...
15	18Cr-8Ni	Wld. tube	SA-249	TP304L	S30403	...
16	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304L	S30403	...
17	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	1
18	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	3
19	18Cr-8Ni	Wld. pipe	SA-358	304L	S30403	4
20	18Cr-8Ni	Smls. & wld. fittings	SA-403	304L	S30403	...
21	18Cr-8Ni	Wld. pipe	SA-409	TP304L	S30403	...
22	18Cr-8Ni	Bar	SA-479	304L	S30403	Annealed
23	18Cr-8Ni	Wld. tube	SA-688	TP304L	S30403	...
24	18Cr-8Ni	Wld. pipe	SA-813	TP304L	S30403	...
25	18Cr-8Ni	Wld. pipe	SA-814	TP304L	S30403	...
26	18Cr-8Ni	Bar	SA/JIS G4303	SUS304L	...	...
27	18Cr-8Ni	Forgings	SA-182	F304	S30400	...
28	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...
29	18Cr-8Ni	Castings	SA-351	CF3	J92500	...
30	18Cr-8Ni	Castings	SA-351	CF8	J92600	...
31	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...
32	18Cr-8Ni	Cast pipe	SA-451	CPF3	J92500	...
33	18Cr-8Ni	Cast pipe	SA-451	CPF8	J92600	...
34	18Cr-8Ni	Forgings	SA-965	F304	S30400	...
35	18Cr-8Ni	Forgings	SA-965	F304H	S30409	...
36	18Cr-8Ni	Plate	SA/EN 10028-7	X2CrNi18-9	...	...
37	18Cr-8Ni	Forgings	SA-182	F304	S30400	...
38	18Cr-8Ni	Forgings	SA-182	F304H	S30409	...
39	18Cr-8Ni	Bolting	SA-193	B8	S30400	1
40	18Cr-8Ni	Bolting	SA-193	B8A	S30400	1A
41	18Cr-8Ni	Smls. tube	SA-213	TP304	S30400	...
42	18Cr-8Ni	Smls. tube	SA-213	TP304H	S30409	...
43	18Cr-8Ni	Plate	SA-240	302	S30200	...
44	18Cr-8Ni	Plate	SA-240	304	S30400	...
45	18Cr-8Ni	Plate	SA-240	304H	S30409	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	75	30	...
2	...	78	37	...
3	...	100	55	...
4	...	100	55	...
5	...	100	55	...
6	...	100	55	...
7	...	100	55	...
8	...	92	64	...
9	...	92	64	...
10	>5	65	25	...
11	...	65	25	...
12	≤5	70	25	...
13	...	70	25	...
14	...	70	25	...
15	...	70	25	...
16	...	70	25	...
17	...	70	25	...
18	...	70	25	...
19	...	70	25	...
20	...	70	25	...
21	...	70	25	...
22	...	70	25	...
23	...	70	25	...
24	...	70	25	...
25	...	70	25	...
26	...	70	25	...
27	>5	70	30	...
28	>5	70	30	...
29	...	70	30	...
30	...	70	30	...
31	≥8	70	30	...
32	...	70	30	...
33	...	70	30	...
34	...	70	30	...
35	...	70	30	...
36	≤3	72.5	29	...
37	≤5	75	30	...
38	≤5	75	30	...
39	...	75	30	...
40	...	75	30	...
41	...	75	30	...
42	...	75	30	...
43	...	75	30	...
44	...	75	30	...
45	...	75	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	...	24.2	...	21.6	...	20.2	...	19.5
2	37.0	...	30.4	...	27.1	...	24.7	...	22.7
3	55.0	48.3	44.2	40.6	37.5	...	32.9	...	30.2
4	55.0	48.3	44.2	40.6	37.5	...	32.9	...	30.2
5	55.0	48.3	44.2	40.6	37.5	...	32.9	...	30.2
6	55.0	48.3	44.2	40.6	37.5	...	32.9	...	30.2
7	55.0	48.3	44.2	40.6	37.5	...	32.9	...	30.2
8	64.0	55.6	52.3	50.2	49.0	...	47.7	...	46.6
9	64.0	55.6	52.3	50.2	49.0	...	47.7	...	46.6
10	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
11	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
12	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
13	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
14	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
15	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
16	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
17	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
18	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
19	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
20	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
21	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
22	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
23	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
24	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
25	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
26	25.0	22.7	21.4	20.2	19.2	...	17.5	...	16.4
27	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
28	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
29	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
30	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
31	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
32	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
33	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
34	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
35	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
36	29.0	...	24.8	...	22.3	...	20.3	...	19.0
37	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
38	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
39	30.0	...	25.0	...	22.4	...	20.7	...	19.4
40	30.0	...	25.0	...	22.4	...	20.7	...	19.4
41	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
42	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
43	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
44	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
45	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	18.8	18.3	17.8	17.3	16.7	16.2	15.8	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	28.7	28.2	27.8	27.3	26.6	25.9	25.1	24.2	23.4
4	...	28.7	28.2	27.8	27.3	26.6	25.9	25.1	24.2	23.4
5	...	28.7	28.2	27.8	27.3	26.6	25.9	25.1	24.2	23.4
6	...	28.7	28.2	27.8	27.3	26.6	25.9	25.1	24.2	23.4
7	...	28.7	28.2	27.8	27.3	26.6	25.9	25.1	24.2	23.4
8	...	45.2	44.4	43.6	42.8	42.3	...	...	...	...
9	...	45.2	44.4	43.6	42.8	42.3	...	...	...	...
10	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
11	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
12	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
13	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
14	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
15	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
16	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
17	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
18	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
19	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
20	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
21	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
22	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
23	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
24	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
25	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
26	...	15.5	15.2	15.0	14.7	14.5	14.3	14.0	13.7	13.3
27	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
28	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
29	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
30	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
31	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
32	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
33	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
34	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
35	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
36	...	18.0	17.7	17.4	17.1	16.8	16.6	16.3	15.9	15.4
37	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
38	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
39	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
40	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
41	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
42	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
43	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
44	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
45	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
11	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
12	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
13	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
14	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
15	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
16	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
17	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
18	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
19	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
20	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
21	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
22	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
23	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
24	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
25	13.2	12.3	12.0	11.6	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
40	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
41	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-8Ni	Wld. tube	SA-249	TP304	S30400	...
2	18Cr-8Ni	Wld. tube	SA-249	TP304H	S30409	...
3	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304	S30400	...
4	18Cr-8Ni	Smls. & wld. pipe	SA-312	TP304H	S30409	...
5	18Cr-8Ni	Bolting	SA-320	B8	S30400	1
6	18Cr-8Ni	Bolting	SA-320	B8A	S30400	1A
7	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	1
8	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	3
9	18Cr-8Ni	Wld. pipe	SA-358	304	S30400	4
10	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	1
11	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	3
12	18Cr-8Ni	Wld. pipe	SA-358	304H	S30409	4
13	18Cr-8Ni	Wld. pipe	SA-358	304LN	S30453	1
14	18Cr-8Ni	Wld. pipe	SA-358	304LN	S30453	3
15	18Cr-8Ni	Wld. pipe	SA-358	304LN	S30453	4
16	18Cr-8Ni	Smls. pipe	SA-376	TP304	S30400	...
17	18Cr-8Ni	Smls. pipe	SA-376	TP304H	S30409	...
18	18Cr-8Ni	Smls. & wld. fittings	SA-403	304	S30400	...
19	18Cr-8Ni	Smls. & wld. fittings	SA-403	304H	S30409	...
20	18Cr-8Ni	Wld. pipe	SA-409	TP304	S30400	...
21	18Cr-8Ni	Bar	SA-479	302	S30200	...
22	18Cr-8Ni	Bar	SA-479	304	S30400	Annealed
23	18Cr-8Ni	Bar	SA-479	304H	S30409	...
24	18Cr-8Ni	Wld. tube	SA-688	TP304	S30400	...
25	18Cr-8Ni	Wld. pipe	SA-813	TP304	S30400	...
26	18Cr-8Ni	Wld. pipe	SA-813	TP304H	S30409	...
27	18Cr-8Ni	Wld. pipe	SA-814	TP304	S30400	...
28	18Cr-8Ni	Wld. pipe	SA-814	TP304H	S30409	...
29	18Cr-8Ni	Bar	SA/JIS G4303	SUS302	...	...
30	18Cr-8Ni	Bar	SA/JIS G4303	SUS304	...	...
31	18Cr-8Ni	Plate	SA/EN 10028-7	X5CrNi18-10	...	...
32	18Cr-8Ni	Castings	SA-351	CF3A	J92500	...
33	18Cr-8Ni	Castings	SA-351	CF8A	J92600	...
34	18Cr-8Ni	Cast pipe	SA-451	CPF3A	J92500	...
35	18Cr-8Ni	Cast pipe	SA-451	CPF8A	J92600	...
36	18Cr-8Ni	Bolting	SA-193	B8	S30400	2
37	18Cr-8Ni	Bolting	SA-320	B8	S30400	2
38	18Cr-8Ni	Bolting	SA-193	B8	S30400	2
39	18Cr-8Ni	Bolting	SA-320	B8	S30400	2
40	18Cr-8Ni	Bolting	SA-193	B8	S30400	2
41	18Cr-8Ni	Bolting	SA-320	B8	S30400	2
42	18Cr-8Ni	Bolting	SA-193	B8	S30400	2
43	18Cr-8Ni	Bolting	SA-320	B8	S30400	2
44	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...
45	18Cr-8Ni-N	Forgings	SA-965	F304LN	S30453	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	75	30	...
2	...	75	30	...
3	...	75	30	...
4	...	75	30	...
5	...	75	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	<8	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	75	30	...
22	...	75	30	...
23	...	75	30	...
24	...	75	30	...
25	...	75	30	...
26	...	75	30	...
27	...	75	30	...
28	...	75	30	...
29	...	75	30	...
30	...	75	30	...
31	≤3	75	31	...
32	...	77	35	...
33	...	77	35	...
34	...	77	35	...
35	...	77	35	...
36	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
37	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
38	$1 < t \leq 1\frac{1}{4}$	105	65	...
39	$1 < t \leq 1\frac{1}{4}$	105	65	...
40	$\frac{3}{4} < t \leq 1$	115	80	...
41	$\frac{3}{4} < t \leq 1$	115	80	...
42	$\leq \frac{3}{4}$	125	100	...
43	$\leq \frac{3}{4}$	125	100	...
44	>5	70	30	...
45	...	70	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
2	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
3	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
4	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
5	30.0	...	25.0	...	22.4	...	20.7	...	19.4
6	30.0	...	25.0	...	22.4	...	20.7	...	19.4
7	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
8	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
9	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
10	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
11	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
12	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
13	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
14	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
15	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
16	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
17	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
18	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
19	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
20	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
21	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
22	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
23	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
24	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
25	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
26	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
27	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
28	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
29	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
30	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
31	30.5	...	25.4	...	22.8	...	21.0	...	19.7
32	35.0	31.2	29.2	27.5	26.2	...	24.1	...	22.6
33	35.0	31.2	29.2	27.5	26.2	...	24.1	...	22.6
34	35.0	31.2	29.2	27.5	26.2	...	24.1	...	22.6
35	35.0	31.2	29.2	27.5	26.2	...	24.1	...	22.6
36	50.0	44.5	41.7	39.3	37.3	...	34.5	...	32.3
37	50.0	44.5	41.7	39.3	37.3	...	34.5	...	32.3
38	65.0	57.9	54.2	51.1	48.5	...	44.9	...	42.0
39	65.0	57.9	54.2	51.1	48.5	...	44.9	...	42.0
40	80.0	71.2	66.7	62.9	59.7	...	55.2	...	51.7
41	80.0	71.2	66.7	62.9	59.7	...	55.2	...	51.7
42	100.0	89.0	83.3	78.7	74.7	...	69.0	...	64.7
43	100.0	89.0	83.3	78.7	74.7	...	69.0	...	64.7
44	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
45	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
2	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
3	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
4	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
5	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
6	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
7	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
8	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
9	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
10	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
11	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
12	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
13	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
14	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
15	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
16	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
17	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
18	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
19	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
20	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
21	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
22	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
23	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
24	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
25	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
26	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
27	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
28	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
29	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
30	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
31	...	18.7	18.3	17.9	17.5	17.1	16.8	16.4	16.1	15.8
32	...	21.5	21.0	20.5	20.1	19.7	19.3	18.9	18.5	18.1
33	...	21.5	21.0	20.5	20.1	19.7	19.3	18.9	18.5	18.1
34	...	21.5	21.0	20.5	20.1	19.7	19.3	18.9	18.5	18.1
35	...	21.5	21.0	20.5	20.1	19.7	19.3	18.9	18.5	18.1
36	...	30.7	30.0	29.3	28.7	28.2	27.5	27.0	26.5	25.8
37	...	30.7	30.0	29.3	28.7	28.2	27.5	27.0	26.5	25.8
38	...	39.9	39.0	38.1	37.3	36.6	35.8	35.1	34.5	33.6
39	...	39.9	39.0	38.1	37.3	36.6	35.8	35.1	34.5	33.6
40	...	49.1	48.0	46.9	45.9	45.1	44.0	43.2	42.4	41.3
41	...	49.1	48.0	46.9	45.9	45.1	44.0	43.2	42.4	41.3
42	...	61.3	60.0	58.7	57.3	56.3	55.0	54.0	53.0	51.7
43	...	61.3	60.0	58.7	57.3	56.3	55.0	54.0	53.0	51.7
44	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
45	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
6	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
7	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
8	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
9	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
25	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	15.2	14.9	14.5	14.0	13.5	12.9	12.3	11.5	10.7	9.7	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-8Ni-N	Forgings	SA-182	F304LN	S30453	...
2	18Cr-8Ni-N	Bolting	SA-193	B8NA	S30451	1A
3	18Cr-8Ni-N	Smls. tube	SA-213	TP304LN	S30453	...
4	18Cr-8Ni-N	Plate	SA-240	304LN	S30453	...
5	18Cr-8Ni-N	Wld. tube	SA-249	TP304LN	S30453	...
6	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304LN	S30453	...
7	18Cr-8Ni-N	Smls. pipe	SA-376	TP304LN	S30453	...
8	18Cr-8Ni-N	Smls. & wld. fittings	SA-403	304LN	S30453	WP
9	18Cr-8Ni-N	Bar	SA-479	304LN	S30453	...
10	18Cr-8Ni-N	Wld. tube	SA-688	TP304LN	S30453	...
11	18Cr-8Ni-N	Wld. pipe	SA-813	TP304LN	S30453	...
12	18Cr-8Ni-N	Wld. pipe	SA-814	TP304LN	S30453	...
13	18Cr-8Ni-N	Forgings	SA-182	F304N	S30451	...
14	18Cr-8Ni-N	Smls. tube	SA-213	TP304N	S30451	...
15	18Cr-8Ni-N	Plate	SA-240	304N	S30451	...
16	18Cr-8Ni-N	Wld. tube	SA-249	TP304N	S30451	...
17	18Cr-8Ni-N	Smls. & wld. pipe	SA-312	TP304N	S30451	...
18	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	1
19	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	3
20	18Cr-8Ni-N	Wld. pipe	SA-358	304N	S30451	4
21	18Cr-8Ni-N	Smls. pipe	SA-376	TP304N	S30451	...
22	18Cr-8Ni-N	Smls. & wld. fittings	SA-403	304N	S30451	...
23	18Cr-8Ni-N	Bar	SA-479	304N	S30451	...
24	18Cr-8Ni-N	Wld. tube	SA-688	TP304N	S30451	...
25	18Cr-8Ni-N	Wld. pipe	SA-813	TP304N	S30451	...
26	18Cr-8Ni-N	Wld. pipe	SA-814	TP304N	S30451	...
27	18Cr-8Ni-N	Forgings	SA-965	F304N	S30451	...
28	18Cr-8Ni-N	Plate	SA/EN 10028-7	X2CrNiN18-10	...	...
29	18Cr-8Ni-N	Plate	SA/EN 10028-7	X5CrNiN19-9	...	...
(25) 30	18Cr-8Ni-S	Bolting	SA-320	B8F	S30300	1
(25) 31	18Cr-8Ni-S	Bolting	SA-320	B8FA	S30300	1A
32	18Cr-8Ni-Se	Bolting	SA-320	B8F	S30323	1
33	18Cr-8Ni-Se	Bolting	SA-320	B8FA	S30323	1A
34	18Cr-8Ni-4Si-N	Bolting	SA-193	B8S	S21800	...
35	18Cr-8Ni-4Si-N	Bolting	SA-193	B8SA	S21800	...
36	18Cr-8Ni-4Si-N	Bar	SA-479	...	S21800	...
37	18Cr-9Ni-3Cu-Cb-N	Smls. tube	SA-213	...	S30432	...
38	18Cr-10Ni-Cb	Forgings	SA-965	F348H	S34809	...
39	18Cr-10Ni-Cb	Castings	SA-351	CF8C	J92710	...
40	18Cr-10Ni-Cb	Cast pipe	SA-451	CPF8C	J92710	...
41	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...
42	18Cr-10Ni-Cb	Forgings	SA-965	F347	S34700	...
43	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...
44	18Cr-10Ni-Cb	Forgings	SA-965	F347H	S34709	...
45	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	≤5	75	30	...
2	...	75	30	...
3	...	75	30	...
4	...	75	30	...
5	...	75	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	80	35	...
14	...	80	35	...
15	...	80	35	...
16	...	80	35	...
17	...	80	35	...
18	...	80	35	...
19	...	80	35	...
20	...	80	35	...
21	...	80	35	...
22	...	80	35	...
23	...	80	35	...
24	...	80	35	...
25	...	80	35	...
26	...	80	35	...
27	...	80	35	...
28	≤3	80	39	...
29	≤3	80	39	...
30	...	75	30	...
31	...	75	30	...
32	...	75	30	...
33	...	75	30	...
34	...	95	50	...
35	...	95	50	...
36	...	95	50	...
37	...	86	34	...
38	...	65	25	...
39	...	70	30	...
40	...	70	30	...
41	>5	70	30	...
42	...	70	30	...
43	>5	70	30	...
44	...	70	30	...
45	>5	70	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
2	30.0	...	25.0	...	22.4	...	20.7	...	19.4
3	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
4	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
5	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
6	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
7	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
8	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
9	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
10	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
11	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
12	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
13	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
14	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
15	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
16	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
17	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
18	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
19	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
20	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
21	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
22	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
23	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
24	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
25	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
26	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
27	35.0	30.9	28.6	26.7	25.0	...	22.6	...	21.0
28	39.2	35.9	32.6	31.0	29.3	...	27.0	...	25.3
29	39.2	34.5	32.0	29.9	28.0	...	25.3	...	23.4
30	30.0	...	25.0	...	22.4	...	20.7	...	19.4
31	30.0	...	25.0	...	22.4	...	20.7	...	19.4
32	30.0	...	25.0	...	22.4	...	20.7	...	19.4
33	30.0	...	25.0	...	22.4	...	20.7	...	19.4
34	50.0	42.6	38.8	35.7	33.2	...	29.7	...	27.6
35	50.0	42.6	38.8	35.7	33.2	...	29.7	...	27.6
36	50.0	42.6	38.8	35.7	33.2	...	29.7	...	27.6
37	34.0	...	29.7	...	27.4	...	25.7	...	24.4
38	25.0	23.8	23.0	22.2	21.4	...	20.0	...	18.8
39	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
40	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
41	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
42	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
43	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
44	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
45	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
2	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
3	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
4	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
5	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
6	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
7	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
8	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
9	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
10	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
11	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
12	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
13	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
14	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
15	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
16	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
17	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
18	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
19	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
20	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
21	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
22	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
23	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
24	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
25	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
26	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
27	...	19.9	19.5	19.1	18.8	18.5	18.1	17.7	17.3	16.9
28	...	24.0	23.5	23.0	22.5	22.0	...	...	...	...
29	...	22.3	21.8	21.4	21.0	20.7	20.2	19.8	19.4	18.9
30	...	18.4	18.0	17.6	17.2	16.9	...	...	...	...
31	...	18.4	18.0	17.6	17.2	16.9	...	...	...	...
32	...	18.4	18.0	17.6	17.2	16.9	...	...	...	...
33	...	18.4	18.0	17.6	17.2	16.9	...	...	...	...
34	...	26.4	25.9	25.6	25.4	25.2	25.0	24.9	24.9	24.9
35	...	26.4	25.9	25.6	25.4	25.2	25.0	24.9	24.9	24.9
36	...	26.4	25.9	25.6	25.4	25.2	25.0	24.9	24.9	24.9
37	...	23.4	23.0	22.6	22.3	21.9	21.6	21.3	21.0	20.7
38	...	17.9	17.6	17.3	17.1	17.0	16.9	16.8	16.8	16.7
39	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
40	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
41	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
42	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
43	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
44	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
45	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...	...
42	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...	...

(25)

(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-10Ni-Cb	Forgings	SA-965	F348	S34800	...
2	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...
3	18Cr-10Ni-Cb	Forgings	SA-182	F347	S34700	...
4	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	1
5	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347	S34700	...
6	18Cr-10Ni-Cb	Plate	SA-240	347	S34700	...
7	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347	S34700	...
8	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347	S34700	...
9	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	1
10	18Cr-10Ni-Cb	Bolting	SA-320	B8CA	S34700	1A
11	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	1
12	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	3
13	18Cr-10Ni-Cb	Wld. pipe	SA-358	347	S34700	4
14	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347	S34700	...
15	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	347	S34700	...
16	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP347	S34700	...
17	18Cr-10Ni-Cb	Bar	SA-479	347	S34700	...
18	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347	S34700	...
19	18Cr-10Ni-Cb	Bar	SA/JIS G4303	SUS347	...	...
20	18Cr-10Ni-Cb	Forgings	SA-182	F347H	S34709	...
21	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347H	S34709	...
22	18Cr-10Ni-Cb	Plate	SA-240	347H	S34709	...
23	18Cr-10Ni-Cb	Wld. tube	SA-249	TP347H	S34709	...
24	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP347H	S34709	...
25	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP347H	S34709	...
26	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	347H	S34709	...
27	18Cr-10Ni-Cb	Bar	SA-479	347H	S34709	...
28	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP347H	S34709	...
29	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP347H	S34709	...
30	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347LN	S34751	...
31	18Cr-10Ni-Cb	Smls. pipe	SA-312	TP347LN	S34751	...
32	18Cr-10Ni-Cb	Forgings	SA-182	F348	S34800	...
33	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348	S34800	...
34	18Cr-10Ni-Cb	Plate	SA-240	348	S34800	...
35	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348	S34800	...
36	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348	S34800	...
37	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	1
38	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	3
39	18Cr-10Ni-Cb	Wld. pipe	SA-358	348	S34800	4
40	18Cr-10Ni-Cb	Smls. pipe	SA-376	TP348	S34800	...
41	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	348	S34800	...
42	18Cr-10Ni-Cb	Wld. pipe	SA-409	TP348	S34800	...
43	18Cr-10Ni-Cb	Bar	SA-479	348	S34800	...
44	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348	S34800	...
45	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348	S34800	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	70	30	...
2	>5	70	30	...
3	≤5	75	30	...
4	...	75	30	...
5	...	75	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	...	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	≤5	75	30	...
21	...	75	30	...
22	...	75	30	...
23	...	75	30	...
24	...	75	30	...
25	...	75	30	...
26	...	75	30	...
27	...	75	30	...
28	...	75	30	...
29	...	75	30	...
30	...	75	30	...
31	...	75	30	...
32	≤5	75	30	...
33	...	75	30	...
34	...	75	30	...
35	...	75	30	...
36	...	75	30	...
37	...	75	30	...
38	...	75	30	...
39	...	75	30	...
40	...	75	30	...
41	...	75	30	...
42	...	75	30	...
43	...	75	30	...
44	...	75	30	...
45	...	75	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
2	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
3	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
4	30.0	...	27.6	...	25.7	...	24.0	...	22.5
5	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
6	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
7	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
8	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
9	30.0	...	27.6	...	25.7	...	24.0	...	22.5
10	30.0	...	27.6	...	25.7	...	24.0	...	22.5
11	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
12	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
13	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
14	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
15	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
16	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
17	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
18	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
19	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
20	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
21	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
22	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
23	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
24	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
25	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
26	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
27	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
28	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
29	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
30	30.0	...	26.5	...	24.0	...	21.9	...	20.4
31	30.0	...	26.5	...	24.0	...	21.9	...	20.4
32	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
33	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
34	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
35	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
36	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
37	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
38	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
39	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
40	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
41	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
42	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
43	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
44	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
45	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
2	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
3	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
4	...	21.5	21.1	20.7	20.5	20.4	20.3	20.2	20.1	20.1
5	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
6	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
7	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
8	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
9	...	21.5	21.1	20.7	20.5	20.4	20.3	20.2	20.1	20.1
10	...	21.5	21.1	20.7	20.5	20.4	20.3	20.2	20.1	20.1
11	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
12	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
13	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
14	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
15	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
16	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
17	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
18	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
19	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
20	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
21	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
22	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
23	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
24	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
25	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
26	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
27	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
28	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
29	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
30	...	19.4	19.1	18.9	18.7	18.7	18.6	18.6	18.6	18.6
31	...	19.4	19.1	18.9	18.7	18.7	18.6	18.6	18.6	18.6
32	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
33	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
34	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
35	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
36	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
37	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
38	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
39	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
40	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
41	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
42	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
43	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
44	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
45	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding												
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600 1650
Ferrous Materials (Cont'd)												
1	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...
3	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
4	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
5	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
6	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
7	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
8	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
9	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
10	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
11	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
12	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
13	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
14	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
15	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
16	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
17	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
18	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...
32	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
33	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
34	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
35	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
36	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
37	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
38	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
39	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
40	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
41	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
42	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
43	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
44	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...
45	19.7	19.4	19.0	18.5	17.8	17.0	15.9	14.7	13.3	11.7	...	...

INTENTIONALLY LEFT BLANK

NORMDOC.COM : Click to view the full PDF of ASME BPVC.II.D.C (ASME BPVC Section 2 Part D Customary Units)

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-10Ni-Cb	Forgings	SA-182	F348H	S34809	...
2	18Cr-10Ni-Cb	Smls. tube	SA-213	TP348H	S34809	...
3	18Cr-10Ni-Cb	Plate	SA-240	348H	S34809	...
4	18Cr-10Ni-Cb	Wld. tube	SA-249	TP348H	S34809	...
5	18Cr-10Ni-Cb	Smls. & wld. pipe	SA-312	TP348H	S34809	...
6	18Cr-10Ni-Cb	Smls. & wld. fittings	SA-403	348H	S34809	...
7	18Cr-10Ni-Cb	Bar	SA-479	348H	S34809	...
8	18Cr-10Ni-Cb	Wld. pipe	SA-813	TP348H	S34809	...
9	18Cr-10Ni-Cb	Wld. pipe	SA-814	TP348H	S34809	...
10	18Cr-10Ni-Cb	Smls. tube	SA-213	TP347HFG	S34710	...
11	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2
12	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2
13	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2
14	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2
15	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2
16	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2
17	18Cr-10Ni-Cb	Bolting	SA-193	B8C	S34700	2
18	18Cr-10Ni-Cb	Bolting	SA-320	B8C	S34700	2
19	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321	S32100	...
20	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...
21	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321H	S32109	...
22	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...
23	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...
24	18Cr-10Ni-Ti	Forgings	SA-965	F321	S32100	...
25	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...
26	18Cr-10Ni-Ti	Forgings	SA-965	F321H	S32109	...
27	18Cr-10Ni-Ti	Plate	SA/EN 10028-7	X6CrNiTi18-10	...	...
28	18Cr-10Ni-Ti	Forgings	SA-182	F321	S32100	...
29	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	1
30	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321	S32100	...
31	18Cr-10Ni-Ti	Plate	SA-240	321	S32100	...
32	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321	S32100	...
33	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321	S32100	...
34	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	1
35	18Cr-10Ni-Ti	Bolting	SA-320	B8TA	S32100	1A
36	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	1
37	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	3
38	18Cr-10Ni-Ti	Wld. pipe	SA-358	321	S32100	4
39	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321	S32100	...
40	18Cr-10Ni-Ti	Smls. & wld. fittings	SA-403	321	S32100	...
41	18Cr-10Ni-Ti	Wld. pipe	SA-409	TP321	S32100	...
42	18Cr-10Ni-Ti	Bar	SA-479	321	S32100	...
43	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321	S32100	...
44	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321	S32100	...
45	18Cr-10Ni-Ti	Bar	SA/JIS G4303	SUS321	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	≤ 5	75	30	...
2	...	75	30	...
3	...	75	30	...
4	...	75	30	...
5	...	75	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	80	30	...
11	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
12	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
13	$1 < t \leq 1\frac{1}{4}$	105	65	...
14	$1 < t \leq 1\frac{1}{4}$	105	65	...
15	$\frac{3}{4} < t \leq 1$	115	80	...
16	$\frac{3}{4} < t \leq 1$	115	80	...
17	$\leq \frac{3}{4}$	125	100	...
18	$\leq \frac{3}{4}$	125	100	...
19	$> \frac{3}{8}$	70	25	...
20	$> \frac{3}{8}$	70	25	...
21	$> \frac{3}{16}$	70	25	...
22	$> \frac{3}{8}$	70	25	...
23	> 5	70	30	...
24	...	70	30	...
25	> 5	70	30	...
26	...	70	30	...
27	≤ 3	73	29	...
28	≤ 5	75	30	...
29	...	75	30	...
30	...	75	30	...
31	...	75	30	...
32	...	75	30	...
33	$\leq \frac{3}{8}$	75	30	...
34	...	75	30	...
35	...	75	30	...
36	...	75	30	...
37	...	75	30	...
38	...	75	30	...
39	$\leq \frac{3}{8}$	75	30	...
40	...	75	30	...
41	...	75	30	...
42	...	75	30	...
43	...	75	30	...
44	...	75	30	...
45	...	75	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
2	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
3	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
4	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
5	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
6	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
7	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
8	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
9	30.0	28.6	27.6	26.6	25.7	...	24.0	...	22.6
10	30.0	...	27.1	...	25.3	...	23.9	...	22.8
11	50.0	...	46.0	...	42.8	...	40.0	...	37.7
12	50.0	...	46.0	...	42.8	...	40.0	...	37.7
13	65.0	...	59.8	...	55.7	...	52.0	...	49.0
14	65.0	...	59.8	...	55.7	...	52.0	...	49.0
15	80.0	...	73.6	...	68.5	...	64.0	...	60.3
16	80.0	...	73.6	...	68.5	...	64.0	...	60.3
17	100.0	...	92.0	...	85.7	...	80.0	...	75.3
18	100.0	...	92.0	...	85.7	...	80.0	...	75.3
19	25.0	23.4	22.5	21.5	20.7	...	19.2	...	17.9
20	25.0	23.4	22.5	21.5	20.7	...	19.2	...	17.9
21	25.0	23.4	22.5	21.5	20.7	...	19.2	...	17.9
22	25.0	23.4	22.5	21.5	20.7	...	19.2	...	17.9
23	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
24	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
25	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
26	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
27	29.0	27.2	26.1	25.0	24.0	...	22.2	...	20.8
28	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
29	30.0	...	27.0	...	24.8	...	23.0	...	21.5
30	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
31	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
32	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
33	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
34	30.0	...	27.0	...	24.8	...	23.0	...	21.5
35	30.0	...	27.0	...	24.8	...	23.0	...	21.5
36	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
37	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
38	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
39	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
40	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
41	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
42	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
43	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
44	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
45	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
2	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
3	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
4	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
5	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
6	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
7	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
8	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
9	...	21.5	21.1	20.7	20.5	20.3	20.2	20.2	20.1	20.1
10	...	21.9	21.5	21.2	20.9	20.6	20.4	20.2	19.9	19.7
11	...	35.8	35.2	34.5	34.2	33.8	33.7	33.7	33.5	33.5
12	...	35.8	35.2	34.5	34.2	33.8	33.7	33.7	33.5	33.5
13	...	46.6	45.7	44.9	44.4	44.0	43.8	43.8	43.6	43.6
14	...	46.6	45.7	44.9	44.4	44.0	43.8	43.8	43.6	43.6
15	...	57.3	56.3	55.2	54.7	54.1	53.9	53.9	53.6	53.6
16	...	57.3	56.3	55.2	54.7	54.1	53.9	53.9	53.6	53.6
17	...	71.7	70.3	69.0	68.3	67.7	67.3	67.3	67.0	67.0
18	...	71.7	70.3	69.0	68.3	67.7	67.3	67.3	67.0	67.0
19	...	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.2	15.0
20	...	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.2	15.0
21	...	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.2	15.0
22	...	16.9	16.5	16.2	15.9	15.7	15.5	15.3	15.2	15.0
23	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
24	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
25	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
26	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
27	...	19.6	19.2	18.8	18.5	18.2	18.0	17.8	17.6	17.4
28	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
29	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
30	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
31	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
32	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
33	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
34	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
35	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
36	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
37	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
38	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
39	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
40	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
41	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
42	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
43	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
44	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
45	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	14.8	14.6	14.2	13.9	13.5	13.0	12.5	11.9	11.2	10.4	...	...	...
20	14.8	14.6	14.2	13.9	13.5	13.0	12.5	11.9	11.2	10.4	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
24	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
29	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
30	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
31	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
32	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
33	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
34	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
35	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
36	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
37	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
38	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
39	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
40	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
41	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
42	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
43	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
44	17.8	17.5	17.1	16.7	16.2	15.6	15.0	14.3	13.4	12.5	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-10Ni-Ti	Forgings	SA-182	F321H	S32109	...
2	18Cr-10Ni-Ti	Smls. tube	SA-213	TP321H	S32109	...
3	18Cr-10Ni-Ti	Plate	SA-240	321H	S32109	...
4	18Cr-10Ni-Ti	Wld. tube	SA-249	TP321H	S32109	...
5	18Cr-10Ni-Ti	Smls. & wld. pipe	SA-312	TP321H	S32109	...
6	18Cr-10Ni-Ti	Smls. pipe	SA-376	TP321H	S32109	...
7	18Cr-10Ni-Ti	Smls. & wld. fittings	SA-403	321H	S32109	...
8	18Cr-10Ni-Ti	Bar	SA-479	321H	S32109	...
9	18Cr-10Ni-Ti	Wld. pipe	SA-813	TP321H	S32109	...
10	18Cr-10Ni-Ti	Wld. pipe	SA-814	TP321H	S32109	...
11	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2
12	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2
13	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2
14	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2
15	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2
16	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2
17	18Cr-10Ni-Ti	Bolting	SA-193	B8T	S32100	2
18	18Cr-10Ni-Ti	Bolting	SA-320	B8T	S32100	2
19	18Cr-11Ni	Bolting	SA-193	B8P	S30500	1
20	18Cr-11Ni	Plate	SA-240	305	S30500	...
21	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2
22	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2
23	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2
24	18Cr-11Ni	Bolting	SA-193	B8P	S30500	2
25	18Cr-12Ni-2Mo	Castings	SA-351	CF3M	J92800	...
26	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF3M	J92800	...
27	18Cr-12Ni-2Mo	Castings	SA-351	CF8M	J92900	...
28	18Cr-12Ni-2Mo	Cast pipe	SA-451	CPF8M	J92900	...
29	18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...
30	18Cr-13Ni-3Mo	Forgings	SA-182	F317L	S31703	...
31	18Cr-13Ni-3Mo	Forgings	SA-182	F317	S31700	...
32	18Cr-13Ni-3Mo	Plate	SA-240	317	S31700	...
33	18Cr-13Ni-3Mo	Plate	SA-240	317L	S31703	...
34	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317	S31700	...
35	18Cr-13Ni-3Mo	Wld. tube	SA-249	TP317L	S31703	...
36	18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317	S31700	...
37	18Cr-13Ni-3Mo	Smls. & wld. pipe	SA-312	TP317L	S31703	...
38	18Cr-13Ni-3Mo	Smls. & wld. fittings	SA-403	317	S31700	...
39	18Cr-13Ni-3Mo	Fittings	SA-403	317L	S31703	...
40	18Cr-15Ni-4Si	Forgings	SA-182	...	S30600	Solution ann.
41	18Cr-15Ni-4Si	Plate	SA-240	...	S30600	Solution ann.
42	18Cr-15Ni-4Si	Smls. & wld. pipe	SA-312	...	S30600	Solution ann.
43	18Cr-15Ni-4Si	Bar	SA-479	...	S30600	Solution ann.
44	18Cr-18Ni-2Si	Smls. tube	SA-213	XM-15	S38100	...
45	18Cr-18Ni-2Si	Plate	SA-240	XM-15	S38100	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	≤ 5	75	30	...
2	...	75	30	...
3	...	75	30	...
4	...	75	30	...
5	$\leq \frac{3}{16}$	75	30	...
6	$\leq \frac{3}{8}$	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
12	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
13	$1 < t \leq 1\frac{1}{4}$	105	65	...
14	$1 < t \leq 1\frac{1}{4}$	105	65	...
15	$\frac{3}{4} < t \leq 1$	115	80	...
16	$\frac{3}{4} < t \leq 1$	115	80	...
17	$\leq \frac{3}{4}$	125	100	...
18	$\leq \frac{3}{4}$	125	100	...
19	...	75	30	...
20	...	75	30	...
21	$1\frac{1}{4} < t \leq 1\frac{1}{2}$	100	50	...
22	$1 < t \leq 1\frac{1}{4}$	105	65	...
23	$\frac{3}{4} < t \leq 1$	115	80	...
24	$\leq \frac{3}{4}$	125	100	...
25	...	70	30	...
26	...	70	30	...
27	...	70	30	...
28	...	70	30	...
29	> 5	65	25	...
30	≤ 5	70	25	...
31	≤ 5	75	30	...
32	...	75	30	...
33	...	75	30	...
34	...	75	30	...
35	...	75	30	...
36	...	75	30	...
37	...	75	30	...
38	...	75	30	...
39	...	75	30	...
40	...	78	35	...
41	≤ 2	78	35	...
42	...	78	35	...
43	≤ 4	78	35	...
44	...	75	30	...
45	...	75	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
2	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
3	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
4	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
5	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
6	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
7	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
8	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
9	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
10	30.0	28.1	27.0	25.8	24.8	...	23.0	...	21.5
11	50.0	...	45.0	...	41.3	...	38.3	...	35.8
12	50.0	...	45.0	...	41.3	...	38.3	...	35.8
13	65.0	...	58.5	...	53.7	...	49.8	...	46.6
14	65.0	...	58.5	...	53.7	...	49.8	...	46.6
15	80.0	...	72.0	...	66.1	...	61.3	...	57.3
16	80.0	...	72.0	...	66.1	...	61.3	...	57.3
17	100.0	...	90.0	...	82.7	...	76.7	...	71.7
18	100.0	...	90.0	...	82.7	...	76.7	...	71.7
19	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
20	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
21	50.0	44.5	41.7	39.3	37.3	...	34.5	...	32.3
22	65.0	57.9	54.2	51.1	48.5	...	44.9	...	42.0
23	80.0	71.2	66.7	62.9	59.7	...	55.2	...	51.7
24	100.0	89.0	83.3	78.7	74.7	...	69.0	...	64.7
25	30.0	27.3	25.8	24.5	23.3	...	21.4	...	19.9
26	30.0	27.3	25.8	24.5	23.3	...	21.4	...	19.9
27	30.0	27.3	25.8	24.5	23.3	...	21.4	...	19.9
28	30.0	27.3	25.8	24.5	23.3	...	21.4	...	19.9
29	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
30	25.0	22.7	21.3	20.1	19.0	...	17.5	...	16.4
31	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
32	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
33	30.0	27.3	25.5	24.1	22.8	...	21.0	...	19.7
34	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
35	30.0	27.3	25.5	24.1	22.8	...	21.0	...	19.7
36	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
37	30.0	27.3	25.5	24.1	22.8	...	21.0	...	19.7
38	30.0	27.4	25.9	24.6	23.4	...	21.4	...	20.0
39	30.0	27.3	25.5	24.1	22.8	...	21.0	...	19.7
40	35.0	...	26.9	...	24.2	...	...	...	...
41	35.0	...	26.9	...	24.2	...	...	...	...
42	35.0	...	26.9	...	24.2	...	...	...	...
43	35.0	...	26.9	...	24.2	...	...	...	...
44	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
45	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Ferrous Materials (Cont'd)										
1	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
2	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
3	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
4	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
5	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
6	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
7	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
8	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
9	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
10	...	20.3	19.8	19.4	19.1	18.8	18.6	18.4	18.2	18.0
11	...	33.8	33.0	32.3	31.8	31.3	31.0	30.7	30.3	30.0
12	...	33.8	33.0	32.3	31.8	31.3	31.0	30.7	30.3	30.0
13	...	44.0	42.9	42.0	41.4	40.7	40.3	39.9	39.4	39.0
14	...	44.0	42.9	42.0	41.4	40.7	40.3	39.9	39.4	39.0
15	...	54.1	52.8	51.7	50.9	50.1	49.6	49.1	48.5	48.0
16	...	54.1	52.8	51.7	50.9	50.1	49.6	49.1	48.5	48.0
17	...	67.7	66.0	64.7	63.7	62.7	62.0	61.3	60.7	60.0
18	...	67.7	66.0	64.7	63.7	62.7	62.0	61.3	60.7	60.0
19	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
20	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
21	...	30.7	30.0	29.3	28.7	28.2	27.5	27.0	26.5	25.8
22	...	39.9	39.0	38.1	37.3	36.6	35.8	35.1	34.5	33.6
23	...	49.1	48.0	46.9	45.9	45.1	44.0	43.2	42.4	41.3
24	...	61.3	60.0	58.7	57.3	56.3	55.0	54.0	53.0	51.7
25	...	18.8	18.4	18.1	17.8	17.6	17.4	17.3	17.1	17.0
26	...	18.8	18.4	18.1	17.8	17.6	17.4	17.3	17.1	17.0
27	...	18.8	18.4	18.1	17.8	17.6	17.4	17.3	17.1	17.0
28	...	18.8	18.4	18.1	17.8	17.6	17.4	17.3	17.1	17.0
29	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
30	...	15.6	15.3	15.0	14.7	14.4	14.1	13.8	13.5	13.2
31	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
32	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
33	...	18.7	18.3	18.0	17.6	17.2	16.9	16.5	16.1	15.8
34	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
35	...	18.7	18.3	18.0	17.6	17.2	16.9	16.5	16.1	15.8
36	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
37	...	18.7	18.3	18.0	17.6	17.2	16.9	16.5	16.1	15.8
38	...	18.9	18.5	18.2	17.9	17.7	17.5	17.3	17.1	17.0
39	...	18.7	18.3	18.0	17.6	17.2	16.9	16.5	16.1	15.8
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
45	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
30	13.1	13.0	12.8	12.5	...	...	...	...	...	...	...	...	...
31	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
32	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
33	15.7	15.6	15.3	15.1	...	...	...	...	...	...	...	...	...
34	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
35	15.7	15.6	15.3	15.1	...	...	...	...	...	...	...	...	...
36	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
37	15.7	15.6	15.3	15.1	...	...	...	...	...	...	...	...	...
38	16.5	16.3	16.1	15.9	15.7	15.5	15.3	15.0	14.6	14.3	...	...	...
39	15.7	15.6	15.3	15.1	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	18Cr-18Ni-2Si	Wld. tube	SA-249	TPXM-15	S38100	...
2	18Cr-18Ni-2Si	Wld. pipe	SA-312	TPXM-15	S38100	...
3	18Cr-20Ni-5.5Si	Smls. tube	SA-213	...	S32615	Solution ann.
4	18Cr-20Ni-5.5Si	Plate	SA-240	...	S32615	Solution ann.
5	18Cr-20Ni-5.5Si	Smls. & wld. pipe	SA-312	...	S32615	Solution ann.
6	18Cr-20Ni-5.5Si	Bar	SA-479	...	S32615	Solution ann.
7	19Cr-9Ni- $\frac{1}{2}$ Mo	Castings	SA-351	CF10	J92590	...
8	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B
9	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	B
10	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A
11	19Cr-9Ni-Mo-W	Bolting	SA-453	651	S63198	A
12	19Cr-9Ni-2Mo	Castings	SA-351	CF10M	...	...
13	19Cr-10Ni-3Mo	Castings	SA-351	CG8M	J93000	...
14	19Cr-15Ni-4Mo	Smls. tube	SA-213	...	S31725	...
15	19Cr-15Ni-4Mo	Plate	SA-240	...	S31725	...
16	19Cr-15Ni-4Mo	Wld. tube	SA-249	...	S31725	...
17	19Cr-15Ni-4Mo	Smls. & wld. pipe	SA-312	...	S31725	...
18	19Cr-15Ni-4Mo	Wld. pipe	SA-358	...	S31725	...
19	19Cr-15Ni-4Mo	Smls. pipe	SA-376	...	S31725	...
20	19Cr-15Ni-4Mo	Wld. pipe	SA-409	...	S31725	...
21	19Cr-15Ni-4Mo	Bar	SA-479	...	S31725	...
22	20Cr-3Ni-1.5Mo-N	Plate	SA-240	...	S32003	...
23	20Cr-3Ni-1.5Mo-N	Wld. pipe	SA-790	...	S32003	...
24	20Cr-3Ni-1.5Mo-N	Sheet	SA-240	...	S32003	...
25	20Cr-3Ni-1.5Mo-N	Smls. & wld. tube	SA-789	...	S32003	...
26	20Cr-10Ni	Bar	SA-479	ER308	S30880	...
27	20Cr-18Ni-6Mo	Castings	SA-351	CK3MCuN	J93254	...
28	20Cr-18Ni-6Mo	Forgings	SA-182	F44	S31254	...
29	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...
30	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...
31	20Cr-18Ni-6Mo	Smls. & wld. pipe	SA-312	...	S31254	...
32	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...
33	20Cr-18Ni-6Mo	Smls. tube	SA-213	...	S31254	...
34	20Cr-18Ni-6Mo	Wld. tube	SA-249	...	S31254	...
35	20Cr-18Ni-6Mo	Smls. & wld. pipe	SA-312	...	S31254	...
36	20Cr-18Ni-6Mo	Plate	SA-240	...	S31254	...
37	20Cr-18Ni-6Mo	Wld. pipe	SA-358	...	S31254	...
38	20.5Cr-8.8Ni-Mo-N	Plate	SA-240	...	S31655	...
39	21Cr-5Mn-1.5Ni-Cu-N	Plate	SA-240	...	S32101	...
40	21Cr-5Mn-1.5Ni-Cu-N	Bar	SA-479	...	S32101	...
41	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. tube	SA-789	...	S32101	...
42	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. pipe	SA-790	...	S32101	...
43	21Cr-5Mn-1.5Ni-Cu-N	Fittings	SA-815	...	S32101	...
44	21Cr-5Mn-1.5Ni-Cu-N	Sheet, strip	SA-240	...	S32101	...
45	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. tube	SA-789	...	S32101	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	75	30	...
2	...	75	30	...
3	...	80	32	...
4	...	80	32	...
5	...	80	32	...
6	...	80	32	...
7	...	70	30	...
8	>3	95	50	...
9	≤ 3	95	60	...
10	>3	100	60	...
11	≤ 3	100	70	...
12	...	70	30	...
13	...	75	35	...
14	...	75	30	...
15	...	75	30	...
16	...	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	75	30	...
22	$>3/16$	95	65	...
23	...	95	65	...
24	$\leq 3/16$	100	70	...
25	...	100	70	...
26	...	75	30	...
27	...	80	38	...
28	...	94	44	...
29	$t > 0.187$	95	45	...
30	$t > 0.187$	95	45	...
31	$t > 0.187$	95	45	...
32	$t \geq 0.187$	95	45	...
33	$t \leq 0.187$	98	45	...
34	$t \leq 0.187$	98	45	...
35	$t \leq 0.187$	98	45	...
36	$t \leq 0.187$	100	45	...
37	$t < 0.187$	100	45	...
38	...	92	45	...
39	$>3/16$	94	65	...
40	...	94	65	...
41	$>3/16$	94	65	...
42	$>3/16$	94	65	...
43	...	94	65	...
44	$\leq 3/16$	101	77	...
45	$\leq 3/16$	101	77	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
2	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
3	32.0	...	26.4	...	24.8	...	23.1	...	...
4	32.0	...	26.4	...	24.8	...	23.1	...	...
5	32.0	...	26.4	...	24.8	...	23.1	...	...
6	32.0	...	26.4	...	24.8	...	23.1	...	...
7	30.0	26.7	25.0	23.6	22.4	...	20.6	...	19.3
8	50.0	...	46.4	...	44.3	...	42.5	...	41.1
9	60.0	...	55.7	...	53.1	...	51.1	...	49.4
10	60.0	...	55.7	...	53.1	...	51.1	...	49.4
11	70.0	...	65.0	...	62.0	...	59.6	...	57.6
12	30.0	27.7	26.2	24.8	23.5	...	21.4	...	19.9
13	35.0	30.5	28.1	26.2	24.5	...	22.1	...	20.5
14	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
15	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
16	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
17	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
18	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
19	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
20	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
21	30.0	27.0	25.3	24.0	22.8	...	21.0	...	19.7
22	65.0	...	55.8	...	50.6	...	47.6	...	46.0
23	65.0	...	55.8	...	50.6	...	47.6	...	46.0
24	70.0	...	60.1	...	54.5	...	51.3	...	49.5
25	70.0	...	60.1	...	54.5	...	51.3	...	49.5
26	30.0	26.7	25.0	23.6	22.4	...	20.7	...	19.4
27	38.0	33.3	31.0	29.2	27.8	...	25.6	...	24.2
28	44.0	38.5	35.9	33.8	32.1	...	29.7	...	28.0
29	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
30	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
31	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
32	45.0	39.4	36.7	34.6	32.9	...	30.4	...	28.6
33	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
34	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
35	45.0	39.4	36.7	34.6	32.8	...	30.4	...	28.6
36	45.0	39.4	36.7	34.6	32.9	...	30.4	...	28.6
37	45.0	39.4	36.7	34.6	32.9	...	30.4	...	28.6
38	45.0	...	35.9	...	31.7	...	29.0	...	27.3
39	65.0	...	57.6	...	51.4	...	49.4	...	48.4
40	65.0	...	57.6	...	51.4	...	49.4	...	48.4
41	65.0	...	57.6	...	51.4	...	49.4	...	48.4
42	65.0	...	57.6	...	51.4	...	49.4	...	48.4
43	65.0	...	57.6	...	51.4	...	49.4	...	48.4
44	77.0	...	68.2	...	60.9	...	58.5	...	57.3
45	77.0	...	68.2	...	60.9	...	58.5	...	57.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
2	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	18.4	17.9	17.6	17.2	16.9	16.6	16.3	15.9	15.6
8	...	39.9	39.4	38.9	38.3	37.8	37.3	36.7	36.0	35.4
9	...	47.9	47.3	46.6	46.0	45.4	44.7	44.0	43.3	42.4
10	...	47.9	47.3	46.6	46.0	45.4	44.7	44.0	43.3	42.4
11	...	55.9	55.1	54.4	53.7	52.9	52.2	51.3	50.5	49.5
12	...	18.8	18.5	18.1	17.9	17.6	17.4	17.2	17.0	16.9
13	...	19.4	19.0	18.7	18.4	18.2	18.0	17.7	17.4	17.0
14	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
15	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
16	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
17	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
18	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
19	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
20	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
21	...	18.7	18.3	18.0	17.6	17.3	16.9	16.6	16.2	15.9
22	...	44.6	43.6	42.6	41.6	40.9	40.9	...	...	...
23	...	44.6	43.6	42.6	41.6	40.9	40.9	...	...	...
24	...	48.0	47.0	45.9	44.8	44.0	44.0	...	...	...
25	...	48.0	47.0	45.9	44.8	44.0	44.0	...	...	...
26	...	18.4	18.0	17.6	17.2	16.9	16.5	16.2	15.9	15.5
27	...	23.2	22.8	22.6	22.4	22.3	22.1	...	...	...
28	...	26.8	26.4	26.2	26.0	25.8	25.6	...	...	...
29	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
30	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
31	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
32	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
33	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
34	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
35	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
36	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
37	...	27.4	27.0	26.8	26.6	26.4	26.2	...	...	...
38	...	26.1	25.6	25.1	24.6	24.1	23.6	...	...	...
39	...	46.0	45.5	...	...	...	...	...	...	...
40	...	46.0	45.5	...	...	...	...	...	...	...
41	...	46.0	45.5	...	...	...	...	...	...	...
42	...	46.0	45.5	...	...	...	...	...	...	...
43	...	46.0	45.5	...	...	...	...	...	...	...
44	...	54.5	53.9	...	...	...	...	...	...	...
45	...	54.5	53.9	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	21Cr-5Mn-1.5Ni-Cu-N	Smls. & wld. pipe	SA-790	...	S32101	...
2	21Cr-6Ni-9Mn	Forgings	SA-182	FXM-11	S21904	...
3	21Cr-6Ni-9Mn	Smls. & wld. pipe	SA-312	TPXM-11	S21904	...
4	21Cr-6Ni-9Mn	Plate	SA-666	XM-11	S21904	...
5	21Cr-6Ni-9Mn	Forgings	SA-965	FXM-11	S21904	...
6	21Cr-11Ni-N	Forgings	SA-182	F45	S30815	...
7	21Cr-11Ni-N	Smls. tube	SA-213	...	S30815	...
8	21Cr-11Ni-N	Plate	SA-240	...	S30815	...
9	21Cr-11Ni-N	Wld. tube	SA-249	...	S30815	...
10	21Cr-11Ni-N	Smls. & wld. pipe	SA-312	...	S30815	...
11	21Cr-11Ni-N	Bar	SA-479	...	S30815	...
12	22Cr-2Ni-Mo-N	Forgings	SA-182	F66	S32202	...
13	22Cr-2Ni-Mo-N	Plate	SA-240	...	S32202	...
14	22Cr-2Ni-Mo-N	Bar	SA-479	...	S32202	...
15	22Cr-2Ni-Mo-N	Smls. & wld. tube	SA-789	...	S32202	...
16	22Cr-2Ni-Mo-N	Smls. & wld. pipe	SA-790	...	S32202	...
17	22Cr-2Ni-Mo-N	Smls. & wld. fittings	SA-815	...	S32202	...
18	22Cr-5Ni-3Mo-N	Castings	SA-995	4A	J92205	...
19	22Cr-5Ni-3Mo-N	Forgings	SA-182	F51	S31803	...
20	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S31803	...
21	22Cr-5Ni-3Mo-N	Bar	SA-479	...	S31803	...
22	22Cr-5Ni-3Mo-N	Smls. & wld. tube	SA-789	...	S31803	...
23	22Cr-5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...	S31803	...
24	22Cr-5Ni-3Mo-N	Smls. & wld. fittings	SA-815	...	S31803	...
25	22Cr-5Ni-3Mo-N	Plate	SA-240	...	S32205	...
26	22Cr-5Ni-3Mo-N	Bar	SA-479	...	S32205	...
27	22Cr-5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...	S32205	...
28	22Cr-5Ni-3Mo-N	Smls. & wld. fittings	SA-815	...	S32205	...
29	22Cr-5Ni-3Mo-N	Forgings	SA-182	F60	S32205	...
30	22Cr-5Ni-3Mo-N	Smls. & wld. tube	SA-789	...	S32205	...
31	22Cr-13Ni-5Mn	Castings	SA-351	CG6MMN	J93790	...
32	22Cr-13Ni-5Mn	Forgings	SA-182	FXM-19	S20910	...
33	22Cr-13Ni-5Mn	Bolting	SA-193	B8R	S20910	Annealed
34	22Cr-13Ni-5Mn	Bolting	SA-193	B8RA	S20910	Annealed
35	22Cr-13Ni-5Mn	Smls. tube	SA-213	XM-19	S20910	...
36	22Cr-13Ni-5Mn	Plate	SA-240	XM-19	S20910	...
37	22Cr-13Ni-5Mn	Wld. tube	SA-249	TPXM-19	S20910	...
38	22Cr-13Ni-5Mn	Smls. & wld. pipe	SA-312	TPXM-19	S20910	...
39	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	1
40	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	3
41	22Cr-13Ni-5Mn	Wld. pipe	SA-358	XM-19	S20910	4
42	22Cr-13Ni-5Mn	Smls. & wld. fittings	SA-403	XM-19	S20910	...
43	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	Annealed
44	22Cr-13Ni-5Mn	Wld. pipe	SA-813	TPXM-19	S20910	...
45	22Cr-13Ni-5Mn	Wld. pipe	SA-814	TPXM-19	S20910	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	$\leq 3/16$	101	77	...
2	...	90	50	...
3	...	90	50	...
4	...	90	50	...
5	...	90	50	...
6	...	87	45	...
7	...	87	45	...
8	...	87	45	...
9	...	87	45	...
10	...	87	45	...
11	...	87	45	...
12	...	94	65	...
13	...	94	65	...
14	...	94	65	...
15	...	94	65	...
16	...	94	65	...
17	...	94	65	...
18	...	90	60	...
19	...	90	65	...
20	...	90	65	...
21	...	90	65	...
22	...	90	65	...
23	...	90	65	...
24	...	90	65	...
25	...	95	65	...
26	...	95	65	...
27	...	95	65	...
28	...	95	65	...
29	...	95	70	...
30	...	95	70	...
31	...	85	42.5	...
32	...	100	55	...
33	...	100	55	...
34	...	100	55	...
35	...	100	55	...
36	...	100	55	...
37	...	100	55	...
38	...	100	55	...
39	...	100	55	...
40	...	100	55	...
41	...	100	55	...
42	...	100	55	...
43	...	100	55	...
44	...	100	55	...
45	...	100	55	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Ferrous Materials (Cont'd)								
1	77.0	...	68.2	...	60.9	...	58.5	...	57.3
2	50.0	42.5	38.6	35.5	33.0	...	29.4	...	27.1
3	50.0	42.5	38.6	35.5	33.0	...	29.4	...	27.1
4	50.0	42.5	38.6	35.5	33.0	...	29.4	...	27.1
5	50.0	42.5	38.6	35.5	33.0	...	29.4	...	27.1
6	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
7	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
8	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
9	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
10	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
11	45.0	40.2	37.5	35.1	33.0	...	29.9	...	27.8
12	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
13	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
14	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
15	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
16	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
17	65.0	59.6	55.5	52.0	49.3	47.5	46.5	45.9	45.5
18	60.0	60.0	53.9	...	47.9	...	44.5	...	42.3
19	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
20	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
21	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
22	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
23	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
24	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
25	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
26	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
27	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
28	65.0	60.5	57.8	55.5	53.7	...	51.2	...	49.6
29	70.0	65.1	62.2	59.8	57.9	...	55.2	...	53.4
30	70.0	65.1	62.2	59.8	57.9	...	55.2	...	53.4
31	42.5	38.4	36.4	34.8	33.4	...	31.5	...	30.0
32	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
33	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
34	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
35	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
36	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
37	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
38	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
39	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
40	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
41	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
42	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
43	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
44	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
45	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	54.5	53.9	...	...	...	...	...	...	...
2	...	25.7	25.3	25.0	24.8	24.6	24.4	24.1	23.5	22.6
3	...	25.7	25.3	25.0	24.8	24.6	24.4	24.1	23.5	22.6
4	...	25.7	25.3	25.0	24.8	24.6	24.4	24.1	23.5	22.6
5	...	25.7	25.3	25.0	24.8	24.6	24.4	24.1	23.5	22.6
6	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
7	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
8	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
9	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
10	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
11	...	26.5	26.1	25.8	25.5	25.2	25.0	24.7	24.3	23.9
12	44.9	43.9	42.5	...	...	...	...	...	...	...
13	44.9	43.9	42.5	...	...	...	...	...	...	...
14	44.9	43.9	42.5	...	...	...	...	...	...	...
15	44.9	43.9	42.5	...	...	...	...	...	...	...
16	44.9	43.9	42.5	...	...	...	...	...	...	...
17	44.9	43.9	42.5	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	47.9	46.9	...	...	...	...	...	...	...
20	...	47.9	46.9	...	...	...	...	...	...	...
21	...	47.9	46.9	...	...	...	...	...	...	...
22	...	47.9	46.9	...	...	...	...	...	...	...
23	...	47.9	46.9	...	...	...	...	...	...	...
24	...	47.9	46.9	...	...	...	...	...	...	...
25	...	47.9	46.9	...	...	...	...	...	...	...
26	...	47.9	46.9	...	...	...	...	...	...	...
27	...	47.9	46.9	...	...	...	...	...	...	...
28	...	47.9	46.9	...	...	...	...	...	...	...
29	...	51.6	50.5	...	...	...	...	...	...	...
30	...	51.6	50.5	...	...	...	...	...	...	...
31	...	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.4	26.0
32	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
33	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
34	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
35	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
36	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
37	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
38	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
39	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
40	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
41	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
42	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
43	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
44	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
45	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
33	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
34	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
35	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
36	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
37	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
38	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
39	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
40	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
41	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
42	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
43	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
44	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
45	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	22Cr-13Ni-5Mn	Forgings	SA-965	FXM-19	S20910	...
2	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	Hot rolled
3	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	Hot rolled
4	22Cr-13Ni-5Mn	Bar	SA-479	XM-19	S20910	Hot rolled
5	23Cr-4Ni-Mo-Cu-N	Plate	SA-240	...	S32304	...
6	23Cr-4Ni-Mo-Cu-N	Smls. & wld. tube	SA-789	...	S32304	...
7	23Cr-4Ni-Mo-Cu-N	Smls. & wld. pipe	SA-790	...	S32304	...
8	23Cr-4Ni-Mo-Cu-N	Smls. & wld. tube	SA-789	...	S32304	...
9	23Cr-12Ni	Smls. & wld. fittings	SA-403	309	S30900	...
10	23Cr-12Ni	Smls. tube	SA-213	TP309S	S30908	...
11	23Cr-12Ni	Plate	SA-240	309S	S30908	...
12	23Cr-12Ni	Wld. tube	SA-249	TP309S	S30908	...
13	23Cr-12Ni	Smls. & wld. pipe	SA-312	TP309S	S30908	...
14	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	1
15	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	3
16	23Cr-12Ni	Wld. pipe	SA-358	309S	S30908	4
17	23Cr-12Ni	Bar	SA-479	309S	S30908	...
18	23Cr-12Ni	Wld. pipe	SA-813	TP309S	S30908	...
19	23Cr-12Ni	Wld. pipe	SA-814	TP309S	S30908	...
20	23Cr-12Ni	Bar	SA/JIS G4303	SUS309S	...	...
21	23Cr-12Ni	Smls. tube	SA-213	TP309H	S30909	...
22	23Cr-12Ni	Plate	SA-240	309H	S30909	...
23	23Cr-12Ni	Wld. tube	SA-249	TP309H	S30909	...
24	23Cr-12Ni	Smls. & wld. pipe	SA-312	TP309H	S30909	...
25	23Cr-12Ni	Bar	SA-479	309H	S30909	...
26	23Cr-12Ni-Cb	Smls. tube	SA-213	TP309Cb	S30940	...
27	23Cr-12Ni-Cb	Plate	SA-240	309Cb	S30940	...
28	23Cr-12Ni-Cb	Wld. tube	SA-249	TP309Cb	S30940	...
29	23Cr-12Ni-Cb	Smls. & wld. pipe	SA-312	TP309Cb	S30940	...
30	23Cr-12Ni-Cb	Bar	SA-479	309Cb	S30940	...
31	23Cr-12Ni-Cb	Wld. pipe	SA-813	TP309Cb	S30940	...
32	23Cr-12Ni-Cb	Wld. pipe	SA-814	TP309Cb	S30940	...
33	23Cr-25Ni-5.5Mo-N	Forgings	SA-182	...	S32053	...
34	23Cr-25Ni-5.5Mo-N	Bolting	SA-193	...	S32053	...
35	23Cr-25Ni-5.5Mo-N	Plate	SA-240	...	S32053	...
36	23Cr-25Ni-5.5Mo-N	Wld. tube	SA-249	...	S32053	...
37	23Cr-25Ni-5.5Mo-N	Smls. & wld. pipe	SA-312	...	S32053	...
38	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-358	...	S32053	...
39	23Cr-25Ni-5.5Mo-N	Fittings	SA-403	...	S32053	...
40	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-409	...	S32053	...
41	23Cr-25Ni-5.5Mo-N	Bar	SA-479	...	S32053	...
42	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-813	...	S32053	...
43	23Cr-25Ni-5.5Mo-N	Wld. pipe	SA-814	...	S32053	...
44	24Cr-10Ni-4Mo-N	Castings	SA-995	2A	J93345	...
45	24Cr-22Ni-6Mo-2W-Cu-N	Forgings	SA-182	F58	S31266	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	100	55	...
2	$3 < t \leq 8$	100	60	...
3	$2 < t \leq 3$	115	75	...
4	≤ 2	135	105	...
5	...	87	58	...
6	> 1	87	58	...
7	...	87	58	...
8	≤ 1	100	65	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	...	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	75	30	...
22	...	75	30	...
23	...	75	30	...
24	...	75	30	...
25	...	75	30	...
26	...	75	30	...
27	...	75	30	...
28	...	75	30	...
29	...	75	30	...
30	...	75	30	...
31	...	75	30	...
32	...	75	30	...
33	...	93	43	...
34	...	93	43	...
35	...	93	43	...
36	...	93	43	...
37	...	93	43	...
38	...	93	43	...
39	...	93	43	...
40	...	93	43	...
41	...	93	43	...
42	...	93	43	...
43	...	93	43	...
44	...	95	65	...
45	...	109	61	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	55.0	49.8	47.1	45.0	43.3	...	40.7	...	38.8
2	60.0	...	51.4	...	47.2	...	44.4	...	42.4
3	75.0	...	64.2	...	59.0	...	55.5	...	53.0
4	105.0	...	89.9	...	82.6	...	77.8	...	74.2
5	58.0	52.6	49.8	47.8	46.3	...	44.5	...	43.4
6	58.0	52.6	49.8	47.8	46.3	...	44.5	...	43.4
7	58.0	52.6	49.8	47.8	46.3	...	44.5	...	43.4
8	65.0	58.9	55.9	53.6	51.9	...	49.6	...	48.6
9	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
10	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
11	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
12	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
13	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
14	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
15	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
16	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
17	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
18	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
19	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
20	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
21	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
22	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
23	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
24	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
25	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
26	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
27	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
28	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
29	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
30	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
31	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
32	30.0	27.6	26.3	25.1	24.2	...	22.7	...	21.6
33	43.0	...	36.3	...	32.8	...	30.5	...	29.0
34	43.0	...	36.3	...	32.8	...	30.5	...	29.0
35	43.0	...	36.3	...	32.8	...	30.5	...	29.0
36	43.0	...	36.3	...	32.8	...	30.5	...	29.0
37	43.0	...	36.3	...	32.8	...	30.5	...	29.0
38	43.0	...	36.3	...	32.8	...	30.5	...	29.0
39	43.0	...	36.3	...	32.8	...	30.5	...	29.0
40	43.0	...	36.3	...	32.8	...	30.5	...	29.0
41	43.0	...	36.3	...	32.8	...	30.5	...	29.0
42	43.0	...	36.3	...	32.8	...	30.5	...	29.0
43	43.0	...	36.3	...	32.8	...	30.5	...	29.0
44	65.0	56.6	52.4	49.2	46.8	...	43.9	...	42.5
45	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
									Ferrous Materials (Cont'd)	
1	...	37.4	36.8	36.3	35.8	35.3	34.9	34.5	34.1	33.7
2	...	40.8	40.1	39.5	39.0	38.5	38.1	37.7	37.2	36.7
3	...	51.0	50.2	49.4	48.8	48.2	47.6	47.1	46.6	45.9
4	...	71.4	70.3	69.2	68.3	67.5	66.7	66.0	65.2	64.2
5	...	42.1	41.3	40.4	39.4	38.6	...	...	...	...
6	...	42.1	41.3	40.4	39.4	38.6	...	...	...	...
7	...	42.1	41.3	40.4	39.4	38.6	...	...	...	...
8	...	47.2	46.3	45.3	...	...	...	...	...	...
9	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
10	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
11	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
12	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
13	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
14	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
15	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
16	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
17	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
18	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
19	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
20	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
21	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
22	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
23	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
24	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
25	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
26	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
27	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
28	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
29	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
30	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
31	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
32	...	20.8	20.5	20.2	20.0	19.7	19.4	19.1	18.8	18.4
33	...	27.8	27.3	26.9	...	...	...	...	...	...
34	...	27.8	27.3	26.9	...	...	...	...	...	...
35	...	27.8	27.3	26.9	...	...	...	...	...	...
36	...	27.8	27.3	26.9	...	...	...	...	...	...
37	...	27.8	27.3	26.9	...	...	...	...	...	...
38	...	27.8	27.3	26.9	...	...	...	...	...	...
39	...	27.8	27.3	26.9	...	...	...	...	...	...
40	...	27.8	27.3	26.9	...	...	...	...	...	...
41	...	27.8	27.3	26.9	...	...	...	...	...	...
42	...	27.8	27.3	26.9	...	...	...	...	...	...
43	...	27.8	27.3	26.9	...	...	...	...	...	...
44	...	41.4	40.6	39.3	...	...	...	...	...	...
45	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	32.9	32.4	31.7	30.9	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
11	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
12	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
13	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
14	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
15	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
16	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
17	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
18	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
19	17.6	17.2	16.7	16.2	15.6	15.0	14.3	13.5	12.5	11.5	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	24Cr-22Ni-6Mo-2W-Cu-N	Smls. tube	SA-213	...	S31266	...
2	24Cr-22Ni-6Mo-2W-Cu-N	Plate	SA-240	...	S31266	...
3	24Cr-22Ni-6Mo-2W-Cu-N	Wld. tube	SA-249	...	S31266	...
4	24Cr-22Ni-6Mo-2W-Cu-N	Smls. & wld. pipe	SA-312	...	S31266	...
5	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-358	...	S31266	...
6	24Cr-22Ni-6Mo-2W-Cu-N	Smls. & wld. fittings	SA-403	...	S31266	...
7	24Cr-22Ni-6Mo-2W-Cu-N	Bar, shapes	SA-479	...	S31266	...
8	24Cr-22Ni-6Mo-2W-Cu-N	Wld. pipe	SA-813	...	S31266	...
9	25Cr-4Ni-4Mo-Ti	Plate	SA-240	...	S44635	...
10	25Cr-4Ni-4Mo-Ti	Wld. tube	SA-268	...	S44635	...
11	25Cr-5Ni-3Mo-2Cu	Castings	SA-995	1B	J93372	...
12	25Cr-5Ni-3Mo-2Cu	Plate	SA-240	...	S32550	...
13	25Cr-5Ni-3Mo-2Cu	Bar	SA-479	...	S32550	...
14	25Cr-5Ni-3Mo-2Cu	Smls. & wld. tube	SA-789	...	S32550	...
15	25Cr-5Ni-3Mo-2Cu	Smls. & wld. pipe	SA-790	...	S32550	...
16	25Cr-6Ni-Mo-N	Forgings	SA-182	...	S32506	...
17	25Cr-6Ni-Mo-N	Plate, sheet	SA-240	...	S32506	...
18	25Cr-6Ni-Mo-N	Bar	SA-479	...	S32506	...
19	25Cr-6Ni-Mo-N	Smls. tube	SA-789	...	S32506	...
20	25Cr-6Ni-Mo-N	Wld. tube	SA-789	...	S32506	...
21	25Cr-6Ni-Mo-N	Smls. pipe	SA-790	...	S32506	...
22	25Cr-6Ni-Mo-N	Wld. pipe	SA-790	...	S32506	...
23	25Cr-6Ni-Mo-N	Plate	SA-240	...	S31200	...
24	25Cr-6.5Ni-3Mo-N	Smls. & wld. tube	SA-789	...	S31260	...
25	25Cr-6.5Ni-3Mo-N	Smls. & wld. pipe	SA-790	...	S31260	...
26	25Cr-6.5Ni-3Mo-N	Plate	SA-240	...	S31260	...
27	25Cr-7Ni-3Mo-W-Cu-N	Forgings	SA-182	F54	S39274	...
28	25Cr-7Ni-3Mo-W-Cu-N	Smls. & wld. tube	SA-789	...	S39274	...
29	25Cr-7Ni-3Mo-W-Cu-N	Smls. & wld. pipe	SA-790	...	S39274	...
30	25Cr-7Ni-4Mo-N	Forgings	SA-182	F53	S32750	...
31	25Cr-7Ni-4Mo-N	Plate	SA-240	...	S32750	...
32	25Cr-7Ni-4Mo-N	Smls. & wld. tube	SA-789	...	S32750	...
33	25Cr-7Ni-4Mo-N	Smls. & wld. pipe	SA-790	...	S32750	...
34	25Cr-7.5Ni-3.5Mo-N-Cu-W	Castings	SA-995	CD3MWCuN	J93380	...
35	25Cr-7.5Ni-3.5Mo-N-Cu-W	Forgings	SA-182	F55	S32760	...
36	25Cr-7.5Ni-3.5Mo-N-Cu-W	Plate	SA-240	...	S32760	...
37	25Cr-7.5Ni-3.5Mo-N-Cu-W	Bar	SA-479	...	S32760	Annealed
38	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. tube	SA-789	...	S32760	...
39	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. pipe	SA-790	...	S32760	...
40	25Cr-7.5Ni-3.5Mo-N-Cu-W	Smls. & wld. fittings	SA-815	...	S32760	...
41	25Cr-12Ni	Castings	SA-351	CH8	J93400	...
42	25Cr-12Ni	Cast pipe	SA-451	CPH8	J93400	...
43	25Cr-12Ni	Castings	SA-351	CH20	J93402	...
44	25Cr-12Ni	Cast pipe	SA-451	CPH20	J93402	...
45	25Cr-20Ni	Castings	SA-351	CK20	J94202	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	109	61	...
2	...	109	61	...
3	...	109	61	...
4	...	109	61	...
5	...	109	61	...
6	...	109	61	...
7	...	109	61	...
8	...	109	61	...
9	...	90	75	...
10	...	90	75	...
11	...	100	70	...
12	...	110	80	...
13	...	110	80	...
14	...	110	80	...
15	...	110	80	...
16	...	90	65	...
17	...	90	65	...
18	...	90	65	...
19	...	90	65	...
20	...	90	65	...
21	...	90	65	...
22	...	90	65	...
23	...	100	65	...
24	...	100	65	...
25	...	100	65	...
26	...	100	70	...
27	...	116	80	...
28	...	116	80	...
29	...	116	80	...
30	...	116	80	...
31	...	116	80	...
32	...	116	80	...
33	...	116	80	...
34	...	100	65	...
35	...	109	80	...
36	...	109	80	...
37	...	109	80	...
38	...	109	80	...
39	...	109	80	...
40	...	109	80	...
41	...	65	28	...
42	...	65	28	...
43	...	70	30	...
44	...	70	30	...
45	...	65	28	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
2	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
3	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
4	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
5	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
6	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
7	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
8	61.0	56.2	53.7	51.7	50.0	48.7	47.6	46.8	46.1
9	75.0	66.1	62.0	58.7	55.8	...	51.0	...	47.5
10	75.0	66.1	62.0	58.7	55.8	...	51.0	...	47.5
11	70.0	...	...	...	...	...	...	...	...
12	80.0	73.8	70.2	67.0	64.3	...	60.5	...	58.7
13	80.0	73.8	70.2	67.0	64.3	...	60.5	...	58.7
14	80.0	73.8	70.2	67.0	64.3	...	60.5	...	58.7
15	80.0	73.8	70.2	67.0	64.3	...	60.5	...	58.7
16	65.0	...	57.4	...	52.8	...	50.1	...	49.0
17	65.0	...	57.4	...	52.8	...	50.1	...	49.0
18	65.0	...	57.4	...	52.8	...	50.1	...	49.0
19	65.0	...	57.4	...	52.8	...	50.1	...	49.0
20	65.0	...	57.4	...	52.8	...	50.1	...	49.0
21	65.0	...	57.4	...	52.8	...	50.1	...	49.0
22	65.0	...	57.4	...	52.8	...	50.1	...	49.0
23	65.0	58.6	55.3	52.6	50.4	...	47.5	...	45.5
24	65.0	59.5	56.6	54.2	52.3	...	49.5	...	47.9
25	65.0	59.5	56.6	54.2	52.3	...	49.5	...	47.9
26	70.0	64.1	61.0	58.4	56.3	...	53.3	...	51.5
27	80.0	70.6	66.9	64.2	62.1	...	59.3	...	58.2
28	80.0	70.6	66.9	64.2	62.1	...	59.3	...	58.2
29	80.0	70.6	66.9	64.2	62.1	...	59.3	...	58.2
30	80.0	74.0	70.5	67.4	64.7	...	60.7	...	58.3
31	80.0	74.0	70.5	67.4	64.7	...	60.7	...	58.3
32	80.0	74.0	70.5	67.4	64.7	...	60.7	...	58.3
33	80.0	74.0	70.5	67.4	64.7	...	60.7	...	58.3
34	65.0	57.9	54.1	52.2	50.2	49.4	48.5	48.1	47.7
35	80.0	...	64.6	...	59.9	...	58.7	...	58.2
36	80.0	...	64.6	...	59.9	...	58.7	...	58.2
37	80.0	...	64.6	...	59.9	...	58.7	...	58.2
38	80.0	...	64.6	...	59.9	...	58.7	...	58.2
39	80.0	...	64.6	...	59.9	...	58.7	...	58.2
40	80.0	...	64.6	...	59.9	...	58.7	...	58.2
41	28.0	24.4	22.9	21.8	21.1	...	20.2	...	19.6
42	28.0	24.4	22.9	21.8	21.1	...	20.2	...	19.6
43	30.0	26.1	24.5	23.4	22.6	...	21.7	...	21.0
44	30.0	26.1	24.5	23.4	22.6	...	21.7	...	21.0
45	28.0	24.4	22.9	21.8	21.1	...	20.2	...	19.6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
2	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
3	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
4	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
5	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
6	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
7	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
8	45.7	45.3	45.1	44.9	44.7	44.5	...	...	...	...
9	...	45.0	43.5	...	...	...	...	...	...	...
10	...	45.0	43.5	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	58.4	58.2	57.4	55.4	51.5	...	...	...	...
13	...	58.4	58.2	57.4	55.4	51.5	...	...	...	...
14	...	58.4	58.2	57.4	55.4	51.5	...	...	...	...
15	...	58.4	58.2	57.4	55.4	51.5	...	...	...	...
16	...	48.4	...	...	...	...	...	...	...	...
17	...	48.4	...	...	...	...	...	...	...	...
18	...	48.4	...	...	...	...	...	...	...	...
19	...	48.4	...	...	...	...	...	...	...	...
20	...	48.4	...	...	...	...	...	...	...	...
21	...	48.4	...	...	...	...	...	...	...	...
22	...	48.4	...	...	...	...	...	...	...	...
23	...	43.6	42.2	...	...	...	...	...	...	...
24	...	46.8	46.3	45.8	45.2	...	...	...	...	...
25	...	46.8	46.3	45.8	45.2	...	...	...	...	...
26	...	50.4	49.9	49.4	48.7	...	...	...	...	...
27	...	58.2	58.2	58.2	58.2	...	...	...	...	...
28	...	58.2	58.2	58.2	58.2	...	...	...	...	...
29	...	58.2	58.2	58.2	58.2	...	...	...	...	...
30	...	57.2	57.0	57.0	57.0	...	...	...	...	...
31	...	57.2	57.0	57.0	57.0	...	...	...	...	...
32	...	57.2	57.0	57.0	57.0	...	...	...	...	...
33	...	57.2	57.0	57.0	57.0	...	...	...	...	...
34	47.3	47.0	...	...	...	...	...	...	...	...
35	...	56.0	...	...	...	...	...	...	...	...
36	...	56.0	...	...	...	...	...	...	...	...
37	...	56.0	...	...	...	...	...	...	...	...
38	...	56.0	...	...	...	...	...	...	...	...
39	...	56.0	...	...	...	...	...	...	...	...
40	...	56.0	...	...	...	...	...	...	...	...
41	...	19.0	18.6	18.1	17.6	17.1	16.6	16.0	15.4	14.8
42	...	19.0	18.6	18.1	17.6	17.1	16.6	16.0	15.4	14.8
43	...	20.3	19.9	19.4	18.9	18.3	17.7	17.1	16.5	15.9
44	...	20.3	19.9	19.4	18.9	18.3	17.7	17.1	16.5	15.9
45	...	19.0	18.6	18.1	17.6	17.1	16.6	16.0	15.4	14.8

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	25Cr-20Ni	Cast pipe	SA-451	CPK20	J94202	...
2	25Cr-20Ni	Forgings	SA-182	F310	S31000	...
3	25Cr-20Ni	Forgings	SA-965	F310	S31000	...
4	25Cr-20Ni	Smls. tube	SA-213	...	S31002	...
5	25Cr-20Ni	Smls. pipe	SA-312	...	S31002	...
6	25Cr-20Ni	Smls. tube	SA-213	TP310S	S31008	...
7	25Cr-20Ni	Plate	SA-240	310S	S31008	...
8	25Cr-20Ni	Wld. tube	SA-249	TP310S	S31008	...
9	25Cr-20Ni	Smls. & wld. pipe	SA-312	TP310S	S31008	...
10	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	1
11	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	3
12	25Cr-20Ni	Wld. pipe	SA-358	310S	S31008	4
13	25Cr-20Ni	Smls. & wld. fittings	SA-403	310S	S31008	...
14	25Cr-20Ni	Bar	SA-479	310S	S31008	...
15	25Cr-20Ni	Wld. pipe	SA-813	TP310S	S31008	...
16	25Cr-20Ni	Wld. pipe	SA-814	TP310S	S31008	...
17	25Cr-20Ni	Bar	SA/JIS G4303	SUS310S	...	...
18	25Cr-20Ni	Smls. tube	SA-213	TP310H	S31009	...
19	25Cr-20Ni	Plate	SA-240	310H	S31009	...
20	25Cr-20Ni	Wld. tube	SA-249	TP310H	S31009	...
21	25Cr-20Ni	Smls. & wld. pipe	SA-312	TP310H	S31009	...
22	25Cr-20Ni	Bar	SA-479	310H	S31009	...
23	25Cr-20Ni-Cb	Smls. tube	SA-213	TP310Cb	S31040	...
24	25Cr-20Ni-Cb	Plate	SA-240	310Cb	S31040	...
25	25Cr-20Ni-Cb	Wld. tube	SA-249	TP310Cb	S31040	...
26	25Cr-20Ni-Cb	Smls. & wld. pipe	SA-312	TP310Cb	S31040	...
27	25Cr-20Ni-Cb	Bar	SA-479	310Cb	S31040	...
28	25Cr-20Ni-Cb	Wld. pipe	SA-813	TP310Cb	S31040	...
29	25Cr-20Ni-Cb	Wld. pipe	SA-814	TP310Cb	S31040	...
30	25Cr-20Ni-Cb-N	Smls. tube	SA-213	TP310HCbN	S31042	...
31	25Cr-22Ni-2Mo-N	Forgings	SA-182	F310MoLN	S31050	...
32	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...
33	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...
34	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...
35	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...
36	25Cr-22Ni-2Mo-N	Smls. tube	SA-213	TP310MoLN	S31050	...
37	25Cr-22Ni-2Mo-N	Plate	SA-240	310MoLN	S31050	...
38	25Cr-22Ni-2Mo-N	Wld. tube	SA-249	TP310MoLN	S31050	...
39	25Cr-22Ni-2Mo-N	Wld. pipe	SA-312	TP310MoLN	S31050	...
40	26Cr-4Ni-Mo	Plate	SA-240	329	S32900	...
41	26Cr-4Ni-Mo	Smls. & wld. tube	SA-789	...	S32900	...
42	26Cr-4Ni-Mo	Smls. & wld. pipe	SA-790	...	S32900	...
43	26Cr-4Ni-Mo-N	Plate	SA-240	...	S32950	...
44	26Cr-4Ni-Mo-N	Smls. & wld. tube	SA-789	...	S32950	...
45	26Cr-4Ni-Mo-N	Smls. & wld. pipe	SA-790	...	S32950	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	65	28	...
2	≤5	75	30	...
3	...	75	30	...
4	...	73	30	...
5	...	73	30	...
6	...	75	30	...
7	...	75	30	...
8	...	75	30	...
9	...	75	30	...
10	...	75	30	...
11	...	75	30	...
12	...	75	30	...
13	...	75	30	...
14	...	75	30	...
15	...	75	30	...
16	...	75	30	...
17	...	75	30	...
18	...	75	30	...
19	...	75	30	...
20	...	75	30	...
21	...	75	30	...
22	...	75	30	...
23	...	75	30	...
24	...	75	30	...
25	...	75	30	...
26	...	75	30	...
27	...	75	30	...
28	...	75	30	...
29	...	75	30	...
30	...	95	43	...
31	...	78	37	...
32	0.250 < t ≤ 1.250	78	37	...
33	t > 0.250	78	37	...
34	0.250 < t ≤ 1.250	78	37	...
35	0.250 < t ≤ 1.250	78	37	...
36	≤0.250, wall	84	39	...
37	t ≤ 0.250	84	39	...
38	≤0.250, wall	84	39	...
39	≤0.250, wall	84	39	...
40	...	90	70	...
41	...	90	70	...
42	...	90	70	...
43	...	100	70	...
44	...	100	70	...
45	...	100	70	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Ferrous Materials (Cont'd)									
1	28.0	24.4	22.9	21.8	21.1	...	20.2	...	19.6
2	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
3	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
4	30.0	27.9	26.8	25.9	25.0	24.3	23.6	23.0	22.3
5	30.0	27.9	26.8	25.9	25.0	24.3	23.6	23.0	22.3
6	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
7	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
8	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
9	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
10	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
11	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
12	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
13	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
14	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
15	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
16	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
17	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
18	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
19	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
20	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
21	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
22	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
23	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
24	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
25	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
26	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
27	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
28	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
29	30.0	27.9	26.5	25.3	24.2	...	22.6	...	21.4
30	43.0	...	36.0	...	32.5	...	30.2	...	28.8
31	37.0	33.4	31.5	29.9	28.6	...	26.7	...	25.2
32	37.0	33.4	31.5	29.9	28.6	...	26.7	...	25.2
33	37.0	33.4	31.5	29.9	28.6	...	26.7	...	25.2
34	37.0	33.4	31.5	29.9	28.6	...	26.7	...	25.2
35	37.0	33.4	31.5	29.9	28.6	...	26.7	...	25.2
36	39.0	35.2	33.2	31.5	30.2	...	28.1	...	26.5
37	39.0	35.2	33.2	31.5	30.2	...	28.1	...	26.5
38	39.0	35.2	33.2	31.5	30.2	...	28.1	...	26.5
39	39.0	35.2	33.2	31.5	30.2	...	28.1	...	26.5
40	70.0	65.3	62.4	59.8	57.6	...	53.9	...	51.3
41	70.0	65.3	62.4	59.8	57.6	...	53.9	...	51.3
42	70.0	65.3	62.4	59.8	57.6	...	53.9	...	51.3
43	70.0	64.9	62.0	59.5	57.3	...	53.8	...	51.3
44	70.0	64.9	62.0	59.5	57.3	...	53.8	...	51.3
45	70.0	64.9	62.0	59.5	57.3	...	53.8	...	51.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	19.0	18.6	18.1	17.6	17.1	16.6	16.0	15.4	14.8
2	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
3	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
4	21.7	21.1	20.5	19.9	19.3	18.8	18.5	18.3	...	...
5	21.7	21.1	20.5	19.9	19.3	18.8	18.5	18.3	...	...
6	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
7	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
8	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
9	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
10	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
11	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
12	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
13	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
14	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
15	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
16	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
17	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
18	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
19	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
20	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
21	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
22	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
23	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
24	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
25	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
26	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
27	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
28	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
29	...	20.6	20.2	19.9	19.6	19.4	19.1	18.8	18.5	18.2
30	...	27.8	27.4	27.1	26.8	26.4	26.1	25.7	25.3	24.9
31	...	23.9	23.3	22.7	22.1	21.6	21.0	20.6	20.2	19.9
32	...	23.9	23.3	22.7	22.1	21.6	21.0	20.6	20.2	19.9
33	...	23.9	23.3	22.7	22.1	21.6	21.0	20.6	20.2	19.9
34	...	23.9	23.3	22.7	22.1	21.6	21.0	20.6	20.2	19.9
35	...	23.9	23.3	22.7	22.1	21.6	21.0	20.6	20.2	19.9
36	...	25.2	24.6	23.9	23.3	22.7	22.2	21.7	21.3	21.0
37	...	25.2	24.6	23.9	23.3	22.7	22.2	21.7	21.3	21.0
38	...	25.2	24.6	23.9	23.3	22.7	22.2	21.7	21.3	21.0
39	...	25.2	24.6	23.9	23.3	22.7	22.2	21.7	21.3	21.0
40	...	49.6	49.1	48.8	...	...	...	...	...	...
41	...	49.6	49.1	48.8	...	...	...	...	...	...
42	...	49.6	49.1	48.8	...	...	...	...	...	...
43	...	49.6	49.1	48.6	...	...	...	...	...	...
44	...	49.6	49.1	48.6	...	...	...	...	...	...
45	...	49.6	49.1	48.6	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Ferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
7	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
8	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
9	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
10	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
11	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
12	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
13	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
14	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
15	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
16	17.6	17.0	16.3	15.4	14.5	13.4	12.1	10.7	9.2	7.4	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Ferrous Materials (Cont'd)						
1	27Cr-7.5Ni-4.5Mo-Co-N	Smls. tube	SA-789	...	S32707	...
2	27Cr-7.5Ni-4.5Mo-Co-N	Smls. pipe	SA-790	...	S32707	...
3	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...
4	29Cr-6.5Ni-2Mo-N	Bar	SA-479	...	S32906	...
5	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...
6	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...
7	29Cr-6.5Ni-2Mo-N	Plate, sheet, strip	SA-240	...	S32906	...
8	29Cr-6.5Ni-2Mo-N	Smls. tube	SA-789	...	S32906	...
9	29Cr-6.5Ni-2Mo-N	Smls. pipe	SA-790	...	S32906	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Ferrous Materials (Cont'd)				
1	...	133	101	...
2	...	133	101	...
3	≥ 0.40	109	80	...
4	...	109	80	...
5	≥ 0.40	109	80	...
6	≥ 0.40	109	80	...
7	< 0.40	116	94	...
8	< 0.40	116	94	...
9	< 0.40	116	94	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Ferrous Materials (Cont'd)								
1	101.0	93.7	87.1	82.5	80.1	79.2	78.3	76.7	74.6
2	101.0	93.7	87.1	82.5	80.1	79.2	78.3	76.7	74.6
3	80.0	...	68.9	...	63.2	...	59.4	...	57.1
4	80.0	...	68.9	...	63.2	...	59.4	...	57.1
5	80.0	...	68.9	...	63.2	...	59.4	...	57.1
6	80.0	...	68.9	...	63.2	...	59.4	...	57.1
7	94.0	...	81.0	...	74.3	...	69.8	...	67.1
8	94.0	...	81.0	...	74.3	...	69.8	...	67.1
9	94.0	...	81.0	...	74.3	...	69.8	...	67.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Ferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	55.9	...	...	...	...	...	...	...	...
4	...	55.9	...	...	...	...	...	...	...	...
5	...	55.9	...	...	...	...	...	...	...	...
6	...	55.9	...	...	...	...	...	...	...	...
7	...	65.7	...	...	...	...	...	...	...	...
8	...	65.7	...	...	...	...	...	...	...	...
9	...	65.7	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Ferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials						
1	...	Plate, sheet	SB-209	...	Alclad 3003	O
2	...	Plate, sheet	SB-209	...	Alclad 3003	O
3	...	Plate, sheet	SB-209	...	Alclad 3003	H112
4	...	Plate, sheet	SB-209	...	Alclad 3003	H112
5	...	Plate, sheet	SB-209	...	Alclad 3003	H112
6	...	Plate, sheet	SB-209	...	Alclad 3003	H12
7	...	Plate, sheet	SB-209	...	Alclad 3003	H12
8	...	Plate, sheet	SB-209	...	Alclad 3003	H14
9	...	Plate, sheet	SB-209	...	Alclad 3003	H14
10	...	Drawn smls. tube	SB-210	...	Alclad 3003	O
11	...	Drawn smls. tube	SB-210	...	Alclad 3003	H113
12	...	Drawn smls. tube	SB-210	...	Alclad 3003	H14
13	...	Drawn smls. tube	SB-210	...	Alclad 3003	H18
14	...	Cond. & heat exch. tubes	SB-234	...	Alclad 3003	H14
15	...	Cond. & heat exch. tubes	SB-234	...	Alclad 3003	H25
16	...	Smls. extr. tube	SB-241	...	Alclad 3003	O
17	...	Smls. extr. tube	SB-241	...	Alclad 3003	H112
18	...	Plate, sheet	SB-209	...	Alclad 3004	O
19	...	Plate, sheet	SB-209	...	Alclad 3004	O
20	...	Plate, sheet	SB-209	...	Alclad 3004	H112
21	...	Plate, sheet	SB-209	...	Alclad 3004	H112
22	...	Plate, sheet	SB-209	...	Alclad 3004	H32
23	...	Plate, sheet	SB-209	...	Alclad 3004	H32
24	...	Plate, sheet	SB-209	...	Alclad 3004	H34
25	...	Plate, sheet	SB-209	...	Alclad 3004	H34
26	...	Plate, sheet	SB-209	...	Alclad 6061	T4
27	...	Plate, sheet	SB-209	...	Alclad 6061	T451
28	...	Plate, sheet	SB-209	...	Alclad 6061	T451
29	...	Plate, sheet	SB-209	...	Alclad 6061	T6
30	...	Plate, sheet	SB-209	...	Alclad 6061	T651
31	...	Plate, sheet	SB-209	...	Alclad 6061	T651
32	...	Plate, sheet	SB-209	...	Alclad 6061	T651
33	...	Castings	SB/EN 1706	...	AC-42000-S	T6
34	...	Plate, sheet	SB-209	...	A91060	O
35	...	Plate, sheet	SB-209	...	A91060	H112
36	...	Plate, sheet	SB-209	...	A91060	H112
37	...	Plate, sheet	SB-209	...	A91060	H112
38	...	Plate, sheet	SB-209	...	A91060	H12
39	...	Plate, sheet	SB-209	...	A91060	H14
40	...	Drawn smls. tube	SB-210	...	A91060	O
41	...	Drawn smls. tube	SB-210	...	A91060	H14
42	...	Drawn smls. tube	SB-210	...	A91060	H113
43	...	Bar, rod, shapes	SB-221	...	A91060	O
44	...	Bar, rod, shapes	SB-221	...	A91060	H112
45	...	Cond. & heat exch. tubes	SB-234	...	A91060	H14

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials				
1	0.006–0.499	13	4.5	...
2	0.500–3.000	14	5	...
3	0.250–0.499	16	9	...
4	0.500–2.000	15	6	...
5	2.001–3.000	14.5	6	...
6	0.017–0.499	16	11	...
7	0.500–2.000	17	12	...
8	0.009–0.499	19	16	...
9	0.500–1.000	20	17	...
10	0.010–0.500	13	4.5	...
11	0.050–0.500	13	4.5	...
12	0.010–0.500	19	16	...
13	0.010–0.500	26	23	...
14	0.010–0.200	19	16	...
15	0.010–0.200	21	18	...
16	...	13	4.5	...
17	...	13	4.5	...
18	0.006–0.499	21	8	...
19	0.500–3.000	22	8.5	...
20	0.250–0.499	22	8.5	...
21	0.500–3.000	23	9	...
22	0.017–0.499	27	20	...
23	0.500–2.000	28	21	...
24	0.009–0.499	31	24	...
25	0.500–1.000	32	25	...
26	0.010–0.249	27	14	...
27	0.250–0.499	27	14	...
28	0.500–3.000	30	16	...
29	0.010–0.249	38	32	...
30	0.250–0.499	38	32	...
31	0.500–4.000	42	35	...
32	4.001–5.000	40	35	...
33	...	32	26	...
34	0.006–3.000	8	2.5	...
35	0.250–0.499	11	7	...
36	0.500–1.000	10	5	...
37	1.001–3.000	9	4	...
38	0.017–2.000	11	9	...
39	0.009–1.000	12	10	...
40	0.018–0.500	8.5	2.5	...
41	0.018–0.500	12	10	...
42	0.018–0.500	8.5	2.5	...
43	...	8.5	2.5	...
44	...	8.5	2.5	...
45	0.010–0.200	12	10	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Nonferrous Materials								
1	4.5	4.3	4.2	4.0	3.8	3.5	3.2	...	...
2	5.0	4.8	4.7	4.5	4.2	3.9	3.6	...	...
3	9.0	8.7	8.4	8.0	7.5	7.0	6.5	...	...
4	6.0	5.8	5.6	5.4	5.0	4.7	4.3	...	...
5	6.0	5.8	5.6	5.4	5.0	4.7	4.3	...	...
6	11.0	10.9	10.3	9.1	7.9	6.8	5.4	...	...
7	12.0	11.9	11.2	9.9	8.6	7.4	5.9	...	...
8	16.0	15.4	14.5	13.1	11.3	9.2	7.2	...	...
9	17.0	16.4	15.4	13.9	12.0	9.8	7.6	...	...
10	4.5	4.3	4.2	4.0	3.8	3.5	3.2	...	...
11	4.5	4.3	4.2	4.0	3.8	3.5	3.2	...	...
12	16.0	15.4	14.5	13.1	11.3	9.2	7.2	...	...
13	23.0	20.6	18.3	16.0	13.4	10.4	7.5	...	...
14	16.0	15.4	14.5	13.1	11.3	9.2	7.2	...	...
15	18.0	17.0	15.6	13.9	11.9	9.6	7.3	...	...
16	4.5	4.3	4.2	4.0	3.8	3.5	3.2	...	...
17	4.5	4.3	4.2	4.0	3.8	3.5	3.2	...	...
18	8.0	8.0	8.0	8.0	8.0	8.0	7.6	...	...
19	8.5	8.5	8.5	8.5	8.5	8.5	8.1	...	...
20	8.5	8.5	8.5	8.5	8.5	8.5	8.1	...	...
21	9.0	9.0	9.0	9.0	9.0	8.9	8.5	...	...
22	20.0	20.0	20.0	19.7	18.5	16.1	12.2	...	...
23	21.0	21.0	21.0	20.7	19.4	16.9	12.8	...	...
24	24.0	24.0	24.0	23.5	21.1	16.6	12.3	...	...
25	25.0	25.0	25.0	24.5	22.0	17.3	12.8	...	...
26	14.0	13.7	13.6	13.3	13.3	13.3	10.2	...	...
27	14.0	13.7	13.6	13.3	13.3	13.3	10.2	...	...
28	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
29	32.0	31.5	31.3	29.8	25.3	18.2	12.2	...	...
30	32.0	31.5	31.3	29.8	25.3	18.2	12.2	...	...
31	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
32	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
33	26.2	25.8	24.4	24.4	...	...	...	...	...
34	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
35	7.0	7.0	6.8	6.0	5.3	4.9	4.6	...	...
36	5.0	5.0	4.8	4.4	3.8	3.5	3.2	...	...
37	4.0	4.0	3.8	3.5	3.0	2.8	2.6	...	...
38	9.0	8.3	7.7	7.0	6.2	5.4	4.3	...	...
39	10.0	9.6	9.3	8.6	7.5	6.2	4.5	...	...
40	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
41	10.0	9.6	9.3	8.6	7.5	6.2	4.5	...	...
42	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
43	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
44	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
45	10.0	9.6	9.3	8.6	7.5	6.2	4.5	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Smls. extr. tube	SB-241	...	A91060	O
2	...	Smls. extr. tube	SB-241	...	A91060	H112
3	...	Plate, sheet	SB-209	...	A91100	O
4	...	Plate, sheet	SB-209	...	A91100	H112
5	...	Plate, sheet	SB-209	...	A91100	H112
6	...	Plate, sheet	SB-209	...	A91100	H112
7	...	Plate, sheet	SB-209	...	A91100	H12
8	...	Plate, sheet	SB-209	...	A91100	H14
9	...	Bar, rod, shapes	SB-221	...	A91100	O
10	...	Bar, rod, shapes	SB-221	...	A91100	H112
11	...	Smls. extr. tube	SB-241	...	A91100	O
12	...	Smls. extr. tube	SB-241	...	A91100	H112
13	...	Plate, sheet	SB-209	...	A93003	O
14	...	Plate, sheet	SB-209	...	A93003	H112
15	...	Plate, sheet	SB-209	...	A93003	H112
16	...	Plate, sheet	SB-209	...	A93003	H112
17	...	Plate, sheet	SB-209	...	A93003	H12
18	...	Plate, sheet	SB-209	...	A93003	H14
19	...	Drawn smls. tube	SB-210	...	A93003	O
20	...	Drawn smls. tube	SB-210	...	A93003	H113
21	...	Drawn smls. tube	SB-210	...	A93003	H12
22	...	Drawn smls. tube	SB-210	...	A93003	H14
23	...	Drawn smls. tube	SB-210	...	A93003	H18
24	...	Bar, rod, shapes	SB-221	...	A93003	O
25	...	Bar, rod, shapes	SB-221	...	A93003	H112
26	...	Cond. & heat exch. tubes	SB-234	...	A93003	H14
27	...	Cond. & heat exch. tubes	SB-234	...	A93003	H25
28	...	Smls. extr. tube	SB-241	...	A93003	O
29	...	Smls. extr. tube	SB-241	...	A93003	H112
30	...	Smls. pipe	SB-241	...	A93003	H112
31	...	Smls. pipe	SB-241	...	A93003	H18
32	...	Die forgings	SB-247	...	A93003	H112
33	...	Plate, sheet	SB-209	...	A93004	O
34	...	Plate, sheet	SB-209	...	A93004	H112
35	...	Plate, sheet	SB-209	...	A93004	H32
36	...	Plate, sheet	SB-209	...	A93004	H34
37	...	Plate, sheet	SB-209	...	A95052	O
38	...	Plate, sheet	SB-209	...	A95052	H112
39	...	Plate, sheet	SB-209	...	A95052	H112
40	...	Plate, sheet	SB-209	...	A95052	H32
41	...	Plate, sheet	SB-209	...	A95052	H34
42	...	Drawn smls. tube	SB-210	...	A95052	O
43	...	Drawn smls. tube	SB-210	...	A95052	H32
44	...	Drawn smls. tube	SB-210	...	A95052	H34
45	...	Cond. & heat exch. tubes	SB-234	...	A95052	H32

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	8.5	2.5	...
2	...	8.5	2.5	...
3	0.006-3.000	11	3.5	...
4	0.250-0.499	13	7	...
5	0.500-2.000	12	5	...
6	2.001-3.000	11.5	4	...
7	0.017-2.000	14	11	...
8	0.009-1.000	16	14	...
9	...	11	3	...
10	...	11	3	...
11	...	11	3	...
12	...	11	3	...
13	0.006-3.000	14	5	...
14	0.250-0.499	17	10	...
15	0.500-2.000	15	6	...
16	2.001-3.000	14.5	6	...
17	0.017-2.000	17	12	...
18	0.009-1.000	20	17	...
19	0.010-0.500	14	5	...
20	0.010-0.500	14	5	...
21	0.010-0.500	17	12	...
22	0.010-0.500	20	17	...
23	0.010-0.500	27	24	...
24	...	14	5	...
25	...	14	5	...
26	0.010-0.200	20	17	...
27	0.010-0.200	22	19	...
28	...	14	5	...
29	...	14	5	...
30	≥1.000	14	5	...
31	<1.000	27	24	...
32	≤4.000	14	5	...
33	0.006-3.000	22	8.5	...
34	0.250-3.000	23	9	...
35	0.017-2.000	28	21	...
36	0.009-1.000	32	25	...
37	0.006-3.000	25	9.5	...
38	0.250-0.499	28	16	...
39	0.500-3.000	25	9.5	...
40	0.017-2.000	31	23	...
41	0.009-1.000	34	26	...
42	0.010-0.450	25	10	...
43	0.010-0.450	31	23	...
44	0.010-0.450	34	26	...
45	0.010-0.200	31	23	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Nonferrous Materials (Cont'd)								
1	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
2	2.5	2.5	2.4	2.2	1.9	1.8	1.6	...	...
3	3.5	3.5	3.5	3.4	3.2	2.8	2.4	...	...
4	7.0	7.0	7.0	6.8	6.3	5.6	4.8	...	...
5	5.0	5.0	5.0	4.9	4.6	4.0	3.4	...	...
6	4.0	4.0	4.0	3.9	3.6	3.2	2.7	...	...
7	11.0	10.7	10.2	9.4	8.2	6.9	5.5	...	...
8	14.0	13.5	12.7	11.4	9.9	8.0	6.1	...	...
9	3.0	3.0	3.0	2.9	2.7	2.4	2.1	...	...
10	3.0	3.0	3.0	2.9	2.7	2.4	2.1	...	...
11	3.0	3.0	3.0	2.9	2.7	2.4	2.1	...	...
12	3.0	3.0	3.0	2.9	2.7	2.4	2.1	...	...
13	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
14	10.0	9.7	9.4	8.9	8.4	7.8	7.2	...	...
15	6.0	5.8	5.6	5.4	5.0	4.7	4.3	...	...
16	6.0	5.8	5.6	5.4	5.0	4.7	4.3	...	...
17	12.0	11.9	11.2	9.9	8.6	7.4	5.9	...	...
18	17.0	16.4	15.4	13.9	12.0	9.8	7.6	...	...
19	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
20	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
21	12.0	11.9	11.2	9.9	8.6	7.4	5.9	...	...
22	17.0	16.4	15.4	13.9	12.0	9.8	7.6	...	...
23	24.0	21.5	19.1	16.6	14.0	10.8	7.8	...	...
24	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
25	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
26	17.0	16.4	15.4	13.9	12.0	9.8	7.6	...	...
27	19.0	17.9	16.5	14.7	12.6	10.1	7.7	...	...
28	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
29	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
30	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
31	24.0	21.5	19.1	16.6	14.0	10.8	7.8	...	...
32	5.0	5.0	5.0	4.9	4.6	4.3	3.7	...	...
33	8.5	8.5	8.5	8.5	8.5	8.5	8.1	...	...
34	9.0	9.0	9.0	9.0	9.0	8.9	8.5	...	...
35	21.0	21.0	21.0	20.7	19.4	16.9	12.8	...	...
36	25.0	25.0	25.0	24.5	22.0	17.3	12.8	...	...
37	9.5	9.5	9.5	9.5	9.5	9.4	8.6	...	...
38	16.0	16.0	16.0	16.0	16.0	15.8	14.5	...	...
39	9.5	9.5	9.5	9.5	9.5	9.4	8.6	...	...
40	23.0	23.0	22.8	22.0	20.0	16.6	12.2	...	...
41	26.0	26.0	25.8	25.1	22.5	17.6	12.2	...	...
42	10.0	10.0	10.0	10.0	10.0	9.9	9.1	...	...
43	23.0	23.0	22.8	22.0	20.0	16.6	12.2	...	...
44	26.0	26.0	25.8	25.1	22.5	17.6	12.2	...	...
45	23.0	23.0	22.8	22.0	20.0	16.6	12.2	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Cond. & heat exch. tubes	SB-234	...	A95052	H34
2	...	Smls. extr. tube	SB-241	...	A95052	O
3	...	Plate, sheet	SB-209	...	A95083	O
4	...	Plate, sheet	SB-209	...	A95083	O
5	...	Plate, sheet	SB-209	...	A95083	O
6	...	Plate, sheet	SB-209	...	A95083	O
7	...	Plate, sheet	SB-209	...	A95083	O
8	...	Plate, sheet	SB-209	...	A95083	H112
9	...	Plate, sheet	SB-209	...	A95083	H112
10	...	Plate, sheet	SB-209	...	A95083	H32
11	...	Plate, sheet	SB-209	...	A95083	H32
12	...	Bar, rod, shapes	SB-221	...	A95083	O
13	...	Bar, rod, shapes	SB-221	...	A95083	H111
14	...	Bar, rod, shapes	SB-221	...	A95083	H112
15	...	Smls. extr. tube	SB-241	...	A95083	O
16	...	Smls. extr. tube	SB-241	...	A95083	H111
17	...	Smls. extr. tube	SB-241	...	A95083	H112
18	...	Die & hand forgings	SB-247	...	A95083	H111
19	...	Die & hand forgings	SB-247	...	A95083	H112
20	...	Plate, sheet	SB-928	...	A95083	H321
21	...	Plate, sheet	SB-928	...	A95083	H321
22	...	Plate, sheet	SB-209	...	A95086	O
23	...	Plate, sheet	SB-209	...	A95086	H112
24	...	Plate, sheet	SB-209	...	A95086	H112
25	...	Plate, sheet	SB-209	...	A95086	H112
26	...	Plate, sheet	SB-209	...	A95086	H112
27	...	Plate, sheet	SB-209	...	A95086	H32
28	...	Plate, sheet	SB-209	...	A95086	H34
29	...	Bar, rod, shapes	SB-221	...	A95086	H112
30	...	Smls. extr. tube	SB-241	...	A95086	O
31	...	Smls. extr. tube	SB-241	...	A95086	H111
32	...	Smls. extr. tube	SB-241	...	A95086	H112
33	...	Plate, sheet	SB-928	...	A95086	H116
34	...	Plate, sheet	SB-209	...	A95154	O
35	...	Plate, sheet	SB-209	...	A95154	H112
36	...	Plate, sheet	SB-209	...	A95154	H112
37	...	Plate, sheet	SB-209	...	A95154	H32
38	...	Plate, sheet	SB-209	...	A95154	H34
39	...	Drawn smls. tube	SB-210	...	A95154	O
40	...	Drawn smls. tube	SB-210	...	A95154	H34
41	...	Bar, rod, shapes	SB-221	...	A95154	O
42	...	Bar, rod, shapes	SB-221	...	A95154	H112
43	...	Plate, sheet	SB-209	...	A95254	O
44	...	Plate, sheet	SB-209	...	A95254	H112
45	...	Plate, sheet	SB-209	...	A95254	H112

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	0.010-0.200	34	26	...
2	...	25	10	...
3	0.051-1.500	40	18	...
4	1.501-3.000	39	17	...
5	3.001-5.000	38	16	...
6	5.001-7.000	37	15	...
7	7.001-8.000	36	14	...
8	0.250-1.500	40	18	...
9	1.501-3.000	39	17	...
10	0.125-1.500	44	31	...
11	1.501-3.000	41	29	...
12	≤5.000	39	16	...
13	≤5.000	40	24	...
14	≤5.000	39	16	...
15	...	39	16	...
16	...	40	24	...
17	...	39	16	...
18	≤4.000	39	20	...
19	≤4.000	39	16	...
20	0.125-1.500	44	31	...
21	1.501-3.000	41	29	...
22	0.020-2.000	35	14	...
23	0.188-0.499	36	18	...
24	0.500-1.000	35	16	...
25	1.001-2.000	35	14	...
26	2.001-3.000	34	14	...
27	0.020-2.000	40	28	...
28	0.009-1.000	44	34	...
29	≤5.000	35	14	...
30	...	35	14	...
31	...	36	21	...
32	...	35	14	...
33	0.063-2.000	40	28	...
34	0.020-3.000	30	11	...
35	0.250-0.499	32	18	...
36	0.500-3.000	30	11	...
37	0.020-2.000	36	26	...
38	0.009-1.000	39	29	...
39	0.010-0.450	30	11	...
40	0.010-0.450	39	29	...
41	...	30	11	...
42	...	30	11	...
43	0.051-3.000	30	11	...
44	0.250-0.499	32	18	...
45	0.500-3.000	30	11	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	100	150	200	250	300	350	400	450	500
	Nonferrous Materials (Cont'd)								
1	26.0	26.0	25.8	25.1	22.5	17.6	12.2	...	...
2	10.0	10.0	10.0	10.0	10.0	9.9	9.1	...	...
3	18.0	18.0	...	...	...	...	...	...	...
4	17.0	17.0	...	...	...	...	...	...	...
5	16.0	16.0	...	...	...	...	...	...	...
6	15.0	15.0	...	...	...	...	...	...	...
7	14.0	14.0	...	...	...	...	...	...	...
8	18.0	18.0	...	...	...	...	...	...	...
9	17.0	17.0	...	...	...	...	...	...	...
10	31.0	31.0	...	...	...	...	...	...	...
11	29.0	29.0	...	...	...	...	...	...	...
12	16.0	16.0	...	...	...	...	...	...	...
13	24.0	24.0	...	...	...	...	...	...	...
14	16.0	16.0	...	...	...	...	...	...	...
15	16.0	16.0	...	...	...	...	...	...	...
16	24.0	24.0	...	...	...	...	...	...	...
17	16.0	16.0	...	...	...	...	...	...	...
18	20.0	20.0	...	...	...	...	...	...	...
19	16.0	16.0	...	...	...	...	...	...	...
20	31.0	31.0	...	...	...	...	...	...	...
21	29.0	29.0	...	...	...	...	...	...	...
22	14.0	14.0	...	...	...	...	...	...	...
23	18.0	18.0	...	...	...	...	...	...	...
24	16.0	16.0	...	...	...	...	...	...	...
25	14.0	14.0	...	...	...	...	...	...	...
26	14.0	14.0	...	...	...	...	...	...	...
27	28.0	28.0	...	...	...	...	...	...	...
28	34.0	34.0	...	...	...	...	...	...	...
29	14.0	14.0	...	...	...	...	...	...	...
30	14.0	14.0	...	...	...	...	...	...	...
31	21.0	21.0	...	...	...	...	...	...	...
32	14.0	14.0	...	...	...	...	...	...	...
33	28.0	28.0	...	...	...	...	...	...	...
34	11.0	11.0	...	...	...	...	...	...	...
35	18.0	18.0	...	...	...	...	...	...	...
36	11.0	11.0	...	...	...	...	...	...	...
37	26.0	26.0	...	...	...	...	...	...	...
38	29.0	29.0	...	...	...	...	...	...	...
39	11.0	11.0	...	...	...	...	...	...	...
40	29.0	29.0	...	...	...	...	...	...	...
41	11.0	11.0	...	...	...	...	...	...	...
42	11.0	11.0	...	...	...	...	...	...	...
43	11.0	11.0	...	...	...	...	...	...	...
44	18.0	18.0	...	...	...	...	...	...	...
45	11.0	11.0	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Plate, sheet	SB-209	...	A95254	H32
2	...	Plate, sheet	SB-209	...	A95254	H34
3	...	Plate, sheet	SB-209	...	A95454	O
4	...	Plate, sheet	SB-209	...	A95454	H112
5	...	Plate, sheet	SB-209	...	A95454	H112
6	...	Plate, sheet	SB-209	...	A95454	H32
7	...	Plate, sheet	SB-209	...	A95454	H34
8	...	Bar, rod, shapes	SB-221	...	A95454	O
9	...	Bar, rod, shapes	SB-221	...	A95454	H111
10	...	Bar, rod, shapes	SB-221	...	A95454	H112
11	...	Cond. & heat exch. tubes	SB-234	...	A95454	H32
12	...	Cond. & heat exch. tubes	SB-234	...	A95454	H34
13	...	Smls. extr. tube	SB-241	...	A95454	O
14	...	Smls. extr. tube	SB-241	...	A95454	H111
15	...	Smls. extr. tube	SB-241	...	A95454	H112
16	...	Plate, sheet	SB-209	...	A95456	O
17	...	Plate, sheet	SB-209	...	A95456	O
18	...	Plate, sheet	SB-209	...	A95456	O
19	...	Plate, sheet	SB-209	...	A95456	O
20	...	Plate, sheet	SB-209	...	A95456	O
21	...	Plate, sheet	SB-209	...	A95456	H112
22	...	Plate, sheet	SB-209	...	A95456	H112
23	...	Plate, sheet	SB-209	...	A95456	H32
24	...	Plate, sheet	SB-209	...	A95456	H32
25	...	Plate, sheet	SB-209	...	A95456	H32
26	...	Bar, rod, shapes	SB-221	...	A95456	O
27	...	Bar, rod, shapes	SB-221	...	A95456	H111
28	...	Bar, rod, shapes	SB-221	...	A95456	H112
29	...	Smls. extr. tube	SB-241	...	A95456	O
30	...	Smls. extr. tube	SB-241	...	A95456	H111
31	...	Smls. extr. tube	SB-241	...	A95456	H112
32	...	Plate, sheet	SB-928	...	A95456	H321
33	...	Plate, sheet	SB-928	...	A95456	H321
34	...	Plate, sheet	SB-928	...	A95456	H321
35	...	Plate, sheet	SB-209	...	A96061	T4
36	...	Plate, sheet	SB-209	...	A96061	T451
37	...	Plate, sheet	SB-209	...	A96061	T6
38	...	Plate, sheet	SB-209	...	A96061	T651
39	...	Plate, sheet	SB-209	...	A96061	T651
40	...	Drawn smls. tube	SB-210	...	A96061	T4
41	...	Drawn smls. tube	SB-210	...	A96061	T6
42	...	Bar, rod, wire	SB-211	...	A96061	T6
43	...	Bar, rod, wire	SB-211	...	A96061	T651
44	...	Bar, rod, shapes	SB-221	...	A96061	T4
45	...	Bar, rod, shapes	SB-221	...	A96061	T6

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	0.051–2.000	36	26	...
2	0.051–1.000	39	29	...
3	0.020–3.000	31	12	...
4	0.250–0.499	32	18	...
5	0.500–3.000	31	12	...
6	0.020–2.000	36	26	...
7	0.020–1.000	39	29	...
8	≤5.000	31	12	...
9	≤5.000	33	19	...
10	≤5.000	31	12	...
11	0.010–0.200	36	26	...
12	0.010–0.200	39	29	...
13	...	31	12	...
14	...	33	19	...
15	...	31	12	...
16	0.051–1.500	42	19	...
17	1.501–3.000	41	18	...
18	3.001–5.000	40	17	...
19	5.001–7.000	39	16	...
20	7.001–8.000	38	15	...
21	0.250–1.500	42	19	...
22	1.501–3.000	41	18	...
23	0.188–0.499	46	33	...
24	0.500–1.500	44	31	...
25	1.501–3.000	41	29	...
26	≤5.000	41	19	...
27	≤5.000	42	26	...
28	≤5.000	41	19	...
29	...	41	19	...
30	...	42	26	...
31	...	41	19	...
32	0.188–0.499	46	33	...
33	0.500–1.500	44	31	...
34	1.501–3.000	41	29	...
35	0.006–0.249	30	16	...
36	0.250–3.000	30	16	...
37	0.006–0.249	42	35	...
38	0.250–4.000	42	35	...
39	4.001–6.000	40	35	...
40	0.025–0.500	30	16	...
41	0.025–0.500	42	35	...
42	$\frac{1}{8} < t \leq 8$	42	35	...
43	$\frac{1}{8} < t \leq 8$	42	35	...
44	...	26	16	...
45	...	38	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	26.0	26.0	...	...	...	...	...	...	...
2	29.0	29.0	...	...	...	...	...	...	...
3	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
4	18.0	18.0	18.0	18.0	17.8	17.2	15.9	...	...
5	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
6	26.0	25.9	25.7	25.0	23.7	21.4	18.1	...	...
7	29.0	28.6	27.5	25.9	23.9	21.4	18.1	...	...
8	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
9	19.0	19.0	19.0	19.0	18.8	18.2	16.8	...	...
10	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
11	26.0	25.9	25.7	25.0	23.7	21.4	18.1	...	...
12	29.0	28.6	27.5	25.9	23.9	21.4	18.1	...	...
13	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
14	19.0	19.0	19.0	19.0	18.8	18.2	16.8	...	...
15	12.0	12.0	12.0	12.0	11.9	11.5	10.6	...	...
16	19.0	19.0	...	...	...	...	...	...	...
17	18.0	18.0	...	...	...	...	...	...	...
18	17.0	17.0	...	...	...	...	...	...	...
19	16.0	16.0	...	...	...	...	...	...	...
20	15.0	15.0	...	...	...	...	...	...	...
21	19.0	19.0	...	...	...	...	...	...	...
22	18.0	18.0	...	...	...	...	...	...	...
23	33.0	33.0	...	...	...	...	...	...	...
24	31.0	31.0	...	...	...	...	...	...	...
25	29.0	29.0	...	...	...	...	...	...	...
26	19.0	19.0	...	...	...	...	...	...	...
27	26.0	26.0	...	...	...	...	...	...	...
28	19.0	19.0	...	...	...	...	...	...	...
29	19.0	19.0	...	...	...	...	...	...	...
30	26.0	26.0	...	...	...	...	...	...	...
31	19.0	19.0	...	...	...	...	...	...	...
32	33.0	33.0	...	...	...	...	...	...	...
33	31.0	31.0	...	...	...	...	...	...	...
34	29.0	29.0	...	...	...	...	...	...	...
35	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
36	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
37	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
38	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
39	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
40	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
41	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
42	35.0	34.6	33.7	32.4	27.4	20.0	13.3	...	...
43	35.0	34.6	33.7	32.4	27.4	20.0	13.3	...	...
44	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
45	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Cond. & heat exch. tubes	SB-234	...	A96061	T4
2	...	Cond. & heat exch. tubes	SB-234	...	A96061	T6
3	...	Smls. extr. tube	SB-241	...	A96061	T4
4	...	Smls. extr. tube	SB-241	...	A96061	T6
5	...	Smls. pipe	SB-241	...	A96061	T6 drawn
6	...	Smls. pipe	SB-241	...	A96061	T6
7	...	Die forgings	SB-247	...	A96061	T6
8	...	Hand forgings	SB-247	...	A96061	T6
9	...	Hand forgings	SB-247	...	A96061	T6
10	...	Shapes	SB-308	...	A96061	T6
11	...	Drawn smls. tube	SB-210	...	A96063	T6
12	...	Bar, rod, shapes	SB-221	...	A96063	T1
13	...	Bar, rod, shapes	SB-221	...	A96063	T1
14	...	Bar, rod, shapes	SB-221	...	A96063	T5
15	...	Bar, rod, shapes	SB-221	...	A96063	T5
16	...	Bar, rod, shapes	SB-221	...	A96063	T6
17	...	Smls. extr. tube	SB-241	...	A96063	O
18	...	Smls. extr. tube	SB-241	...	A96063	T1
19	...	Smls. extr. tube	SB-241	...	A96063	T1
20	...	Smls. extr. tube	SB-241	...	A96063	T5
21	...	Smls. extr. tube	SB-241	...	A96063	T5
22	...	Smls. extr. tube	SB-241	...	A96063	T6
23	...	Smls. pipe	SB-241	...	A96063	O
24	...	Castings	SB/EN 1706	AlSi7Mg	AC-42000	...
25	...	Castings	SB/EN 1706	...	AC-44300	F
26	...	Bar, rod	SB-187	...	C10200	O60
27	...	Smls. pipe	SB-42	...	C10200	O61
28	...	Smls. tube	SB-75	...	C10200	O60
(25) 29	...	Plate, sheet, strip, bar	SB-152	...	C10200	H00
(25) 30	...	Plate, sheet, strip, bar	SB-152	...	C10200	H01
(25) 31	...	Plate, sheet, strip, bar	SB-152	...	C10200	H02
(25) 32	...	Plate, sheet, strip, bar	SB-152	...	C10200	H03
(25) 33	...	Plate, sheet, strip, bar	SB-152	...	C10200	H04
(25) 34	...	Plate, sheet, strip, bar	SB-152	...	C10200	M20, O25
35	...	Smls. pipe	SB-42	...	C10200	H55
36	...	Smls. tube	SB-75	...	C10200	H55
37	...	Smls. cond. tube	SB-111	...	C10200	H55
38	...	Smls. U-bend tube	SB-395	...	C10200	H55
39	...	Smls. pipe	SB-42	...	C10200	H80
40	...	Smls. tube	SB-75	...	C10200	H80
41	...	Smls. cond. tube	SB-111	...	C10200	H80
(25) 42	...	Plate, sheet, strip, bar	SB-152	...	C10400	H00
(25) 43	...	Plate, sheet, strip, bar	SB-152	...	C10400	H01
(25) 44	...	Plate, sheet, strip, bar	SB-152	...	C10400	H02
(25) 45	...	Plate, sheet, strip, bar	SB-152	...	C10400	H03

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	0.025–0.200	30	16	...
2	0.025–0.200	42	35	...
3	...	26	16	...
4	...	38	35	...
5	<1.000	42	35	...
6	≥1.000	38	35	...
7	≤4.000	38	35	...
8	≤4.000	37	33	...
9	4.001–8.000	35	32	...
10	...	38	35	...
11	0.025–0.500	33	28	...
12	≤0.500	17	9	...
13	0.501–1.000	16	8	...
14	≤0.500	22	16	...
15	0.501–1.000	21	15	...
16	≤1.000	30	25	...
17	...	16	5	...
18	≤0.500	17	9	...
19	0.501–1.000	16	8	...
20	≤0.500	22	16	...
21	0.501–1.000	21	15	...
22	≤1.000	30	25	...
23	...	16	5	...
24	...	20	12	...
25	...	35	19	...
26	All	28	8	...
27	All	30	9	...
28	All	30	9	...
29	...	30	10	...
30	...	30	10	...
31	...	30	10	...
32	...	30	10	...
33	...	30	10	...
34	...	30	10	...
35	2 < NPS ≤ 12	36	30	...
36	All	36	30	...
37	...	36	30	...
38	...	36	30	...
39	1/8 < NPS ≤ 2	45	40	...
40	<4	45	40	...
41	...	45	40	...
42	...	30	10	...
43	...	30	10	...
44	...	30	10	...
45	...	30	10	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
2	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
3	16.0	15.7	15.5	15.2	15.2	15.2	11.6	...	...
4	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
5	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
6	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
7	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
8	33.0	32.5	32.2	30.6	26.1	18.7	12.6	...	...
9	32.0	31.4	31.1	30.5	30.5	30.5	23.2	...	...
10	35.0	34.4	34.2	32.5	27.7	19.9	13.3	...	...
11	28.0	26.9	26.4	24.2	18.4	9.8	5.7	...	...
12	9.0	9.0	9.0	8.9	8.9	8.9	5.1	...	...
13	8.0	8.0	8.0	7.9	7.9	7.9	5.1	...	...
14	16.0	15.5	15.1	15.0	13.2	8.9	5.1	...	...
15	15.0	14.5	14.2	14.0	12.5	8.9	5.1	...	...
16	25.0	24.1	23.5	21.5	16.3	8.7	5.1	...	...
17	5.0	4.9	4.8	4.5	4.2	3.7	...	...	...
18	9.0	9.0	9.0	8.9	8.9	8.9	...	...	...
19	8.0	8.0	8.0	7.9	7.9	7.9	...	...	...
20	16.0	15.5	15.1	15.0	13.2	8.9	5.1	...	...
21	15.0	14.5	14.2	14.0	12.5	8.9	5.1	...	...
22	25.0	24.0	23.5	21.6	16.4	8.7	5.1	...	...
23	5.0	4.9	4.8	4.5	4.2	3.7	...	...	...
24	11.6	11.6	11.6	11.6	11.6	11.6	...	...	...
25	18.9	15.5	13.2	12.5	12.5	...	...	...	...
26	8.0	7.0	7.0	7.0	7.0	6.8	6.5	6.1	...
27	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
28	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
29	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
30	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
31	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
32	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
33	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
34	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
35	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
36	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
37	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
38	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
39	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
40	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
41	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
42	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
43	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
44	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
45	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	(25)
34	...	...	...	...	...	...	...	...	...	...	...	...	(25)
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	(25)

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
(25) 1	...	Plate, sheet, strip, bar	SB-152	...	C10400	H04
(25) 2	...	Plate, sheet, strip, bar	SB-152	...	C10400	M20, O25
(25) 3	...	Plate, sheet, strip, bar	SB-152	...	C10500	H00
(25) 4	...	Plate, sheet, strip, bar	SB-152	...	C10500	H01
(25) 5	...	Plate, sheet, strip, bar	SB-152	...	C10500	H02
(25) 6	...	Plate, sheet, strip, bar	SB-152	...	C10500	H03
(25) 7	...	Plate, sheet, strip, bar	SB-152	...	C10500	H04
(25) 8	...	Plate, sheet, strip, bar	SB-152	...	C10500	M20, O25
(25) 9	...	Plate, sheet, strip, bar	SB-152	...	C10700	H00
(25) 10	...	Plate, sheet, strip, bar	SB-152	...	C10700	H01
(25) 11	...	Plate, sheet, strip, bar	SB-152	...	C10700	H02
(25) 12	...	Plate, sheet, strip, bar	SB-152	...	C10700	H03
(25) 13	...	Plate, sheet, strip, bar	SB-152	...	C10700	H04
(25) 14	...	Plate, sheet, strip, bar	SB-152	...	C10700	M20, O25
15	...	Bar	SB-187	...	C11000	H04
16	...	Bar, rod	SB-187	...	C11000	O60
17	...	Plate, sheet, strip, bar	SB-152	...	C11000	M20, O25
18	...	Smls. tube	SB-75	...	C12000	O50
19	...	Smls. tube	SB-75	...	C12000	O60
20	...	Smls. pipe	SB-42	...	C12000	O61
21	...	Smls. pipe	SB-42	...	C12000	H55
22	...	Smls. tube	SB-75	...	C12000	H55
23	...	Smls. cond. tube	SB-111	...	C12000	H55
24	...	Smls. U-bend tube	SB-395	...	C12000	H55
25	...	Smls. pipe	SB-42	...	C12000	H80
26	...	Smls. tube	SB-75	...	C12000	H80
27	...	Smls. cond. tube	SB-111	...	C12000	H80
28	...	Finned tube	SB-359	...	C12200	O62
29	...	Smls. tube	SB-75	...	C12200	O50
30	...	Smls. tube	SB-75	...	C12200	O60
31	...	Smls. pipe	SB-42	...	C12200	O61
32	...	Finned tube	SB-359	...	C12200	O61
33	...	Wld. cond. tube	SB-543	...	C12200	W061
34	...	Plate, sheet, strip	SB-152	...	C12200	H00
(25) 35	...	Plate, sheet, strip, bar	SB-152	...	C12200	H01
(25) 36	...	Plate, sheet, strip, bar	SB-152	...	C12200	H02
(25) 37	...	Plate, sheet, strip, bar	SB-152	...	C12200	H03
(25) 38	...	Plate, sheet, strip, bar	SB-152	...	C12200	H04
(25) 39	...	Plate, sheet, strip, bar	SB-152	...	C12200	M20, O25
40	...	Wld. cond. tube	SB-543	...	C12200	WC55
41	...	Smls. pipe	SB-42	...	C12200	H55
42	...	Smls. tube	SB-75	...	C12200	H55
43	...	Smls. cond. tube	SB-111	...	C12200	H55
44	...	Finned tube	SB-359	...	C12200	H55
45	...	Smls. U-bend tube	SB-395	...	C12200	H55

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	30	10	...
2	...	30	10	...
3	...	30	10	...
4	...	30	10	...
5	...	30	10	...
6	...	30	10	...
7	...	30	10	...
8	...	30	10	...
9	...	30	10	...
10	...	30	10	...
11	...	30	10	...
12	...	30	10	...
13	...	30	10	...
14	...	30	10	...
15	All	28	8	...
16	All	28	8	...
17	...	30	10	...
18	All	30	9	...
19	All	30	9	...
20	All	30	9	...
21	$2 < \text{NPS} \leq 12$	36	30	...
22	All	36	30	...
23	...	36	30	...
24	...	36	30	...
25	$\frac{1}{8} < \text{NPS} \leq 2$	45	40	...
26	< 4	45	40	...
27	...	45	40	...
28	...	30	6.5	...
29	All	30	9	...
30	All	30	9	...
31	All	30	9	...
32	...	30	9	...
33	...	30	9	...
34	...	30	10	...
35	...	30	10	...
36	...	30	10	...
37	...	30	10	...
38	...	30	10	...
39	...	30	10	...
40	...	32	15	...
41	$2 < \text{NPS} \leq 12$	36	30	...
42	All	36	30	...
43	...	36	30	...
44	...	36	30	...
45	...	36	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
2	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
3	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
4	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
5	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
6	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
7	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
8	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
9	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
10	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
11	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
12	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
13	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
14	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
15	8.0	6.8	6.5	6.4	6.3	6.1	5.8	5.6	...
16	8.0	7.0	7.0	7.0	7.0	6.8	6.5	6.1	...
17	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
18	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
19	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
20	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
21	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
22	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
23	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
24	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
25	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
26	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
27	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
28	6.5	5.7	5.7	5.7	5.7	5.5	5.3	5.0	...
29	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
30	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
31	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
32	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
33	9.0	7.9	7.9	7.9	7.9	7.6	7.3	6.9	...
34	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
35	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
36	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
37	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
38	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
39	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
40	15.0	14.8	14.5	14.1	13.5	12.9	12.2	11.5	...
41	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
42	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
43	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
44	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
45	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	(25)
8	...	...	...	...	...	...	...	...	...	...	...	...	(25)
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	(25)
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	(25)
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	
16	...	...	...	...	...	...	...	...	...	...	...	...	
17	...	...	...	...	...	...	...	...	...	...	...	...	
18	...	...	...	...	...	...	...	...	...	...	...	...	
19	...	...	...	...	...	...	...	...	...	...	...	...	
20	...	...	...	...	...	...	...	...	...	...	...	...	
21	...	...	...	...	...	...	...	...	...	...	...	...	
22	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	...	...	...	...	...	...	...	...	...	...	...	...	
26	...	...	...	...	...	...	...	...	...	...	...	...	
27	...	...	...	...	...	...	...	...	...	...	...	...	
28	...	...	...	...	...	...	...	...	...	...	...	...	
29	...	...	...	...	...	...	...	...	...	...	...	...	
30	...	...	...	...	...	...	...	...	...	...	...	...	
31	...	...	...	...	...	...	...	...	...	...	...	...	
32	...	...	...	...	...	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	(25)
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	(25)
39	...	...	...	...	...	...	...	...	...	...	...	...	(25)
40	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	
45	...	...	...	...	...	...	...	...	...	...	...	...	

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Smls. pipe	SB-42	...	C12200	H80
2	...	Smls. cond. tube	SB-75	...	C12200	H80
3	...	Smls. tube	SB-111	...	C12200	H80
(25) 4	...	Finned tube	SB-359	...	C12200	H80
5	...	Plate, sheet, strip, bar	SB-152	...	C12300	H00
6	...	Plate, sheet, strip, bar	SB-152	...	C12300	H01
7	...	Plate, sheet, strip, bar	SB-152	...	C12300	H02
8	...	Plate, sheet, strip, bar	SB-152	...	C12300	H03
9	...	Plate, sheet, strip, bar	SB-152	...	C12300	H04
10	...	Plate, sheet, strip, bar	SB-152	...	C12300	M20, O25
(25) 11	...	Plate, sheet, strip, bar	SB-152	...	C14200	M20, O25
12	...	Smls. cond. tube	SB-111	...	C14200	H55
13	...	Smls. U-bend tube	SB-395	...	C14200	H55
14	...	Smls. cond. tube	SB-111	...	C14200	H80
15	...	Smls. cond. tube	SB-111	...	C19200	O61
16	...	Smls. U-bend tube	SB-395	...	C19200	O61
17	...	Wld. cond. tube	SB-543	...	C19400	W061
18	...	Wld. cond. tube	SB-543	...	C19400	WC55
19	...	Smls. pipe	SB-43	...	C23000	O61 and H58
20	...	Smls. cond. tube	SB-111	...	C23000	O61
21	...	Smls. tube	SB-135	...	C23000	O50 and O60
22	...	Smls. U-bend tube	SB-395	...	C23000	O61
23	...	Wld. cond. tube	SB-543	...	C23000	W061 and WC55
24	...	Smls. tube	SB-111	...	C28000	O25
25	...	Plate	SB-171	...	C36500	O25 and M20
26	...	Plate	SB-171	...	C36500	O25 and M20
(25) 27	...	Plate, sheet	SB-171	...	C36500	O25 and M20
(25) 28	...	Forgings	SB-283	...	C37700	M10, O20
(25) 29	...	Forgings	SB-283	...	C37700	M10, O20
(25) 30	...	Plate, sheet	SB-171	...	C44300	M10, M20
(25) 31	...	Plate, sheet	SB-171	...	C44300	O20, O25
32	...	Smls. cond. tube	SB-111	...	C44300	O61
33	...	Finned tube	SB-359	...	C44300	O61
34	...	Smls. U-bend tube	SB-395	...	C44300	O61
35	...	Wld. cond. tube	SB-543	...	C44300	W061
(25) 36	...	Plate, sheet	SB-171	...	C44400	M10, M20
(25) 37	...	Plate, sheet	SB-171	...	C44400	O20, O25
38	...	Smls. cond. tube	SB-111	...	C44400	O61
39	...	Finned tube	SB-359	...	C44400	O61
40	...	Smls. U-bend tube	SB-395	...	C44400	O61
41	...	Wld. cond. tube	SB-543	...	C44400	W061
(25) 42	...	Plate, sheet	SB-171	...	C44500	M10, M20
(25) 43	...	Plate, sheet	SB-171	...	C44500	O20, O25
44	...	Smls. cond. tube	SB-111	...	C44500	O61
45	...	Finned tube	SB-359	...	C44500	O61

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	$\frac{1}{8} < \text{NPS} \leq 3$	45	40	...
2	< 4	45	40	...
3	...	45	40	...
4	...	45	40	...
5	...	30	10	...
6	...	30	10	...
7	...	30	10	...
8	...	30	10	...
9	...	30	10	...
10	...	30	10	...
11	...	30	10	...
12	...	36	30	...
13	...	36	30	...
14	...	45	40	...
15	...	38	12	...
16	...	38	12	...
17	...	45	15	...
18	...	45	22	...
19	...	40	12	...
20	...	40	12	...
21	...	40	12	...
22	...	40	12	...
23	...	40	12	...
24	...	50	20	...
25	$> 3.5 \text{ to } \leq 5$	40	12	...
26	$> 2 \text{ to } \leq 3.5$	45	15	...
27	≤ 2	50	20	...
28	$> 1\frac{1}{2}$	46	15	...
29	$\leq 1\frac{1}{2}$	50	18	...
30	≤ 4	45	15	...
31	≤ 4	45	15	...
32	...	45	15	...
33	...	45	15	...
34	...	45	15	...
35	...	45	15	...
36	≤ 4	45	15	...
37	≤ 4	45	15	...
38	...	45	15	...
39	...	45	15	...
40	...	45	15	...
41	...	45	15	...
42	≤ 4	45	15	...
43	≤ 4	45	15	...
44	...	45	15	...
45	...	45	15	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
2	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
3	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
4	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
5	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
6	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
7	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
8	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
9	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
10	10.0	8.8	8.8	8.8	8.8	8.5	8.1	7.7	...
11	10.0	8.5	8.1	8.0	7.8	7.6	7.3	7.0	...
12	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
13	30.0	29.7	29.0	28.1	27.0	25.7	24.4	23.0	...
14	40.0	38.3	37.6	36.9	35.7	33.7	30.5	25.5	...
15	12.0	10.7	10.1	9.6	9.3	9.0	8.8	8.5	...
16	12.0	10.7	10.1	9.6	9.3	9.0	8.8	8.5	...
17	15.0	14.8	14.6	14.3	13.8	13.4	12.8	12.3	...
18	22.0	21.8	21.4	20.9	20.3	19.6	18.8	18.0	...
19	12.0	12.0	12.0	12.0	12.0	12.0	11.9	11.6	11.0
20	12.0	12.0	12.0	12.0	12.0	12.0	11.9	11.6	11.0
21	12.0	12.0	12.0	12.0	12.0	12.0	11.9	11.6	11.0
22	12.0	12.0	12.0	12.0	12.0	12.0	11.9	11.6	11.0
23	12.0	12.0	12.0	12.0	12.0	12.0	11.9	11.6	11.0
24	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	...
25	12.0	12.0	12.0	12.0	12.0	12.0	12.0	11.9	...
26	15.0	15.0	15.0	15.0	15.0	15.0	15.0	14.8	...
27	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.8	...
28	15.0	12.5	12.5	12.5	12.5	12.5	12.5	12.5	12.5
29	18.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
30	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
31	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
32	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
33	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
34	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
35	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
36	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
37	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
38	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
39	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
40	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
41	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
42	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
43	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
44	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
45	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	(25)
28	...	...	...	...	...	...	...	...	...	...	...	...	(25)
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	(25)
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	(25)
37	...	...	...	...	...	...	...	...	...	...	...	...	(25)
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	(25)
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Smls. U-bend tube	SB-395	...	C44500	O61
2	...	Wld. cond. tube	SB-543	...	C44500	W061
3	...	Plate	SB-171	...	C46400	M10, M20
(25) 4	...	Plate, sheet	SB-171	...	C46400	O20, O25
5	...	Plate	SB-171	...	C46500	M10, M20
(25) 6	...	Plate, sheet	SB-171	...	C46500	O20, O25
7	...	Smls. cond. tube	SB-111	...	C60800	O61
8	...	Smls. U-bend tube	SB-395	...	C60800	O61
(25) 9	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
10	...	Plate	SB-171	...	C61400	M10, M20, O20, O25
(25) 11	...	Round rod	SB-150	...	C61400	HR50
(25) 12	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
13	...	Plate	SB-171	...	C61400	M10, M20, O20, O25
(25) 14	...	Round rod	SB-150	...	C61400	HR50
(25) 15	...	Plate, sheet, bar	SB-169	...	C61400	M20, O25, O60
(25) 16	...	Round rod	SB-150	...	C61400	HR50
(25) 17	...	Round rod	SB-150	...	C61400	HR50
18	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
19	...	Bar, rod	SB-150	...	C63000	M20, M30
20	...	Bar, rod	SB-150	...	C63000	O20, O25, O30
21	...	Bar, rod	SB-150	...	C63000	HR50
22	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
23	...	Bar, rod	SB-150	...	C63000	HR50
24	...	Bar, rod	SB-150	...	C63000	M20, M30
25	...	Bar, rod	SB-150	...	C63000	O20, O25, O30
26	...	Plate	SB-171	...	C63000	M10, M20, O20, O25
27	...	Bar, rod	SB-150	...	C63000	HR50
28	...	Bar, rod	SB-150	...	C63000	HR50
(25) 29	...	Forgings	SB-283	...	C64200	M10, O20
(25) 30	...	Forgings	SB-283	...	C64200	M10, O20
31	...	Bar, rod	SB-150	...	C64200	M10, M20, M30
(25) 32	...	...	...	...	...	...
33	...	Bar, rod	SB-150	...	C64200	M10, M20, M30
34	...	Bar, rod	SB-150	...	C64200	HR50
35	...	Bar, rod	SB-150	...	C64200	HR50
36	...	Bar, rod	SB-150	...	C64200	HR50
37	...	Bar, rod	SB-150	...	C64200	HR50
38	...	Bar, rod	SB-98	...	C65100	O60
39	...	Bar, rod	SB-98	...	C65100	H02
40	...	Rod	SB-98	...	C65100	H06
41	...	Rod	SB-98	...	C65100	H06
42	...	Rod	SB-98	...	C65100	H06
(25) 43	...	Smls. pipe & tube	SB-315	...	C65500	O30, O61
(25) 44	...	Plate, sheet, strip, bar	SB-96	...	C65500	O61
45	...	Bar, rod	SB-98	...	C65500	O60

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	45	15	...
2	...	45	15	...
3	$3 < t \leq 5$	50	18	...
4	≤ 3	50	20	...
5	$3 < t \leq 5$	50	18	...
6	≤ 3	50	20	...
7	...	50	19	...
8	...	50	19	...
9	$2 < t \leq 5$	65	28	...
10	$2 < t \leq 5$	65	28	...
11	$2 < t \leq 3$	70	30	...
12	$\frac{1}{2} < t \leq 2$	70	30	...
13	≤ 2	70	30	...
14	$1 < t \leq 2$	70	32	...
15	$\leq \frac{1}{2}$	72	32	...
16	$\frac{1}{2} < t \leq 1$	75	35	...
17	$\leq \frac{1}{2}$	80	40	...
18	$3.5 < t \leq 5$	80	30	...
19	> 4	80	40	...
20	> 4	80	40	...
21	> 4	80	40	...
22	$2 < t \leq 3.5$	85	33	...
23	$2 < t \leq 4$	85	42.5	...
24	$2 < t \leq 4$	85	42.5	...
25	$2 < t \leq 4$	85	42.5	...
26	≤ 2	90	36	...
27	$1 < t \leq 2$	90	45	...
28	$\frac{1}{2} < t \leq 1$	100	50	...
29	$> 1\frac{1}{2}$	68	23	...
30	$\leq 1\frac{1}{2}$	70	25	...
31	> 4	70	25	...
32	...	...	...	...
33	$3 < t \leq 4$	70	30	...
34	$2 < t \leq 3$	75	35	...
35	$1 < t \leq 2$	80	42	...
36	$\frac{1}{2} < t \leq 1$	85	45	...
37	$\leq \frac{1}{2}$	90	45	...
38	All	40	12	...
39	≤ 2	55	20	...
40	$1 < t \leq 1\frac{1}{2}$	75	40	...
41	$\frac{1}{2} < t \leq 1$	75	45	...
42	$t \leq \frac{1}{2}$	85	55	...
43	...	50	15	...
44	≤ 2	50	18	...
45	All	52	15	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
2	15.0	15.0	15.0	15.0	15.0	15.0	14.9	14.7	...
3	18.0	18.0	18.0	18.0	18.0	18.0	17.7	17.3	16.6
4	20.0	20.0	20.0	20.0	20.0	20.0	19.7	19.2	18.4
5	18.0	18.0	18.0	18.0	18.0	18.0	17.7	17.3	16.6
6	20.0	20.0	20.0	20.0	20.0	20.0	19.7	19.2	18.4
7	19.0	18.3	18.3	18.3	18.0	17.5	17.0	16.5	16.0
8	19.0	18.3	18.3	18.3	18.0	17.5	17.0	16.5	16.0
9	28.0	27.9	27.7	27.5	27.4	27.2	26.9	26.6	26.3
10	28.0	27.9	27.7	27.5	27.4	27.2	26.9	26.6	26.3
11	30.0	29.9	29.7	29.5	29.3	29.1	28.8	28.5	28.2
12	30.0	29.9	29.7	29.5	29.3	29.1	28.8	28.5	28.2
13	30.0	29.9	29.7	29.5	29.3	29.1	28.8	28.5	28.2
14	32.0	31.9	31.7	31.5	31.3	31.0	30.7	30.4	30.1
15	32.0	31.9	31.7	31.4	31.3	31.1	30.8	30.4	30.1
16	35.0	34.9	34.7	34.4	34.2	34.0	33.6	33.3	32.9
17	40.0	39.9	39.6	39.3	39.1	38.8	38.4	38.0	37.6
18	30.0	30.0	30.0	30.0	30.0	30.0	30.0	29.8	29.5
19	40.0	40.0	40.0	40.0	40.0	40.0	40.0	39.8	39.4
20	40.0	40.0	40.0	40.0	40.0	40.0	40.0	39.8	39.4
21	40.0	40.0	40.0	40.0	40.0	40.0	40.0	39.8	39.4
22	33.0	33.0	33.0	33.0	33.0	33.0	33.0	32.8	32.5
23	42.5	42.5	42.5	42.5	42.5	42.5	42.5	42.2	41.8
24	42.5	42.5	42.5	42.5	42.5	42.5	42.5	42.2	41.8
25	42.5	42.5	42.5	42.5	42.5	42.5	42.5	42.2	41.8
26	36.0	36.0	36.0	36.0	36.0	36.0	36.0	35.8	35.4
27	45.0	45.0	45.0	45.0	45.0	45.0	45.0	44.7	44.3
28	50.0	50.0	50.0	50.0	50.0	50.0	50.0	49.7	49.2
29	23.0	21.6	21.2	21.2	21.2	21.2	21.2	21.2	21.2
30	25.0	23.5	23.1	23.0	23.0	23.0	23.0	23.0	23.0
31	25.0	23.5	23.1	23.0	23.0	23.0	23.0	23.0	23.0
32	...	...	...	...	...	...	...	...	...
33	30.0	28.2	27.7	27.6	27.6	27.6	27.6	27.6	27.6
34	35.0	32.9	32.3	32.2	32.2	32.2	32.2	32.2	32.2
35	42.0	39.4	38.8	38.7	38.7	38.7	38.7	38.7	38.7
36	45.0	42.3	41.6	41.4	41.4	41.4	41.4	41.4	41.4
37	45.0	42.3	41.6	41.4	41.4	41.4	41.4	41.4	41.4
38	12.0	11.9	11.8	11.8	11.7	11.5	11.4	11.2	10.9
39	20.0	20.0	19.8	19.4	18.8	18.0	17.2	16.2	15.3
40	40.0	39.3	38.4	37.5	36.3	35.0	33.5	31.7	29.4
41	45.0	44.2	43.2	42.1	40.9	39.4	37.7	35.6	33.1
42	55.0	54.0	52.8	51.5	50.0	48.2	46.1	43.5	40.5
43	15.0	15.0	14.9	14.9	14.8	14.7	14.6	14.5	14.2
44	18.0	18.0	17.9	17.9	17.8	17.7	17.6	17.3	17.0
45	15.0	15.0	14.9	14.9	14.8	14.7	14.6	14.5	14.2

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...
18	29.0	27.9	26.1	23.1	...	...	...	...	...	...
19	38.7	37.2	34.7	30.8	...	...	...	...	...	...
20	38.7	37.2	34.7	30.8	...	...	...	...	...	...
21	38.7	37.2	34.7	30.8	...	...	...	...	...	...
22	31.9	30.7	28.7	25.4	...	...	...	...	...	...
23	41.1	39.6	36.9	32.7	...	...	...	...	...	...
24	41.1	39.6	36.9	32.7	...	...	...	...	...	...
25	41.1	39.6	36.9	32.7	...	...	...	...	...	...
26	34.8	33.5	31.3	27.7	...	...	...	...	...	...
27	43.5	41.9	39.1	34.6	...	...	...	...	...	...
28	48.3	46.5	43.4	38.5	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	(25)
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	(25)
12	...	...	...	...	...	...	...	...	...	...	...	...	(25)
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	(25)
15	...	...	...	...	...	...	...	...	...	...	...	...	(25)
16	...	...	...	...	...	...	...	...	...	...	...	...	(25)
17	...	...	...	...	...	...	...	...	...	...	...	...	(25)
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	(25)
30	...	...	...	...	...	...	...	...	...	...	...	...	(25)
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	(25)
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	(25)
44	...	...	...	...	...	...	...	...	...	...	...	...	(25)
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
(25) 1	...	Bar, rod	SB-98	...	C65500	H01
2	...	Bar, rod	SB-98	...	C65500	H02
(25) 3	...	Bar, rod	SB-98	...	C66100	O60
(25) 4	...	Bar, rod	SB-98	...	C66100	H01
(25) 5	...	Bar, rod	SB-98	...	C66100	H02
6	...	Smls. cond. tube	SB-111	...	C68700	O61
7	...	Smls. U-bend tube	SB-395	...	C68700	O61
8	...	Wld. cond. tube	SB-543	...	C68700	W061
9	...	Smls. cond. tube	SB-111	...	C70400	O61
10	...	Wld. tube	SB-543	...	C70400	W061
11	...	Smls. cond. tube	SB-111	...	C70400	H55
12	...	Smls. pipe & tube	SB-466	...	C70600	O60
13	...	Wld. pipe	SB-467	...	C70600	W061
14	...	Bar, rod	SB-151	...	C70600	O60
15	...	Plate, sheet	SB-171	...	C70600	M10, M20
16	...	Plate, sheet	SB-171	...	C70600	O20, O25
17	...	Smls. cond. tube	SB-111	...	C70600	O61
18	...	Finned tube	SB-359	...	C70600	O61
19	...	Smls. U-bend tube	SB-395	...	C70600	O61
20	...	Wld. pipe	SB-467	...	C70600	W061
21	...	Wld. tube	SB-543	...	C70600	W061
22	...	Finned wld. tube	SB-956	...	C70600	W061
23	...	Wld. pipe	SB-467	...	C70600	WM50
24	...	Smls. tube	SB-111	...	C70600	H55
25	...	Smls. pipe & tube	SB-466	...	C70600	H55
26	...	Wld. tube	SB-543	...	C70600	WC55
27	...	Finned wld. tube	SB-956	...	C70600	WC55
28	...	Wld. pipe	SB-467	...	C70600	Wld. fr. cold rld. strip
29	...	Smls. pipe & tube	SB-466	...	C70620	O60
30	...	Wld. pipe	SB-467	...	C70620	W061
31	...	Bar, rod	SB-151	...	C70620	O60
32	...	Forgings	SB-283	...	C70620	M10
33	...	Plate, sheet	SB-171	...	C70620	M10, M20
34	...	Forgings	SB-283	...	C70620	O20
35	...	Plate, sheet	SB-171	...	C70620	O20, O25
36	...	Smls. cond. tube	SB-111	...	C70620	O61
37	...	Finned tube	SB-359	...	C70620	O61
38	...	Smls. U-bend tube	SB-395	...	C70620	O61
39	...	Wld. pipe	SB-467	...	C70620	W061
40	...	Wld. tube	SB-543	...	C70620	W061
41	...	Finned wld. tube	SB-956	...	C70620	W061
42	...	Forgings	SB-283	...	C70620	M10
43	...	Wld. pipe	SB-467	...	C70620	WM50
44	...	Smls. tube	SB-111	...	C70620	H55
45	...	Smls. pipe & tube	SB-466	...	C70620	H55

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	All	55	24	...
2	≤ 2	70	38	...
3	All	52	15	...
4	All	55	24	...
5	≤ 2	70	38	...
6	...	50	18	...
7	...	50	18	...
8	...	50	18	...
9	...	38	12	...
10	...	38	12	...
11	...	40	30	...
12	...	38	13	...
13	$> 4^{1/2}$	38	13	...
14	All	38	15	...
15	≤ 5	40	15	...
16	≤ 5	40	15	...
17	...	40	15	...
18	...	40	15	...
19	...	40	15	...
20	$\leq 4^{1/2}$	40	15	...
21	...	40	15	...
22	...	40	15	...
23	$\leq 4^{1/2}$	45	30	...
24	...	45	35	...
25	...	45	35	...
26	...	45	35	...
27	...	45	35	...
28	$\leq 4^{1/2}$	54	45	...
29	...	38	13	...
30	$> 4^{1/2}$	38	13	...
31	All	38	15	...
32	> 6	40	15	...
33	≤ 5	40	15	...
34	...	40	15	...
35	≤ 5	40	15	...
36	...	40	15	...
37	...	40	15	...
38	...	40	15	...
39	$\leq 4^{1/2}$	40	15	...
40	...	40	15	...
41	...	40	15	...
42	≤ 6	45	18	...
43	$\leq 4^{1/2}$	45	30	...
44	...	45	35	...
45	...	45	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	24.0	23.5	23.0	22.5	22.0	21.5	21.0	20.6	20.1
2	38.0	37.6	37.2	36.6	35.8	34.5	32.6	29.9	26.4
3	15.0	15.0	14.9	14.9	14.8	14.7	14.6	14.5	14.2
4	24.0	23.5	23.0	22.5	22.0	21.5	21.0	20.6	20.1
5	38.0	37.6	37.2	36.6	35.8	34.5	32.6	29.9	26.4
6	18.0	17.8	17.7	17.6	17.4	17.3	17.1	16.8	...
7	18.0	17.8	17.7	17.6	17.4	17.3	17.1	16.8	...
8	18.0	17.8	17.7	17.6	17.4	17.3	17.1	16.8	...
9	12.0	11.6	11.3	11.1	11.0	10.9	...	...	...
10	12.0	11.6	11.3	11.1	11.0	10.9	...	...	...
11	30.0	28.9	28.3	27.8	27.5	27.3	...	...	...
12	13.0	12.6	12.3	12.0	11.7	11.5	11.3	11.1	10.9
13	13.0	12.6	12.3	12.0	11.7	11.5	11.3	11.1	10.9
14	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
15	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
16	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
17	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
18	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
19	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
20	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
21	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
22	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
23	30.0	29.1	28.5	27.8	27.1	26.5	26.0	25.6	25.3
24	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
25	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
26	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
27	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
28	45.0	43.7	42.7	41.6	40.7	39.8	39.0	38.4	37.9
29	13.0	12.6	12.3	12.0	11.7	11.5	11.3	11.1	10.9
30	13.0	12.6	12.3	12.0	11.7	11.5	11.3	11.1	10.9
31	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
32	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
33	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
34	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
35	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
36	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
37	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
38	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
39	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
40	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
41	15.0	14.6	14.2	13.9	13.6	13.3	13.0	12.8	12.6
42	18.0	17.5	17.0	16.7	16.3	16.0	15.6	15.4	15.1
43	30.0	29.1	28.5	27.8	27.1	26.5	26.0	25.6	25.3
44	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
45	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...
12	10.8	10.8	...	...	...	...	...	...	...	...
13	10.8	10.8	...	...	...	...	...	...	...	...
14	12.5	12.4	...	...	...	...	...	...	...	...
15	12.5	12.4	...	...	...	...	...	...	...	...
16	12.5	12.4	...	...	...	...	...	...	...	...
17	12.5	12.4	...	...	...	...	...	...	...	...
18	12.5	12.4	...	...	...	...	...	...	...	...
19	12.5	12.4	...	...	...	...	...	...	...	...
20	12.5	12.4	...	...	...	...	...	...	...	...
21	12.5	12.4	...	...	...	...	...	...	...	...
22	12.5	12.4	...	...	...	...	...	...	...	...
23	25.0	24.9	...	...	...	...	...	...	...	...
24	29.2	29.0	...	...	...	...	...	...	...	...
25	29.2	29.0	...	...	...	...	...	...	...	...
26	29.2	29.0	...	...	...	...	...	...	...	...
27	29.2	29.0	...	...	...	...	...	...	...	...
28	37.5	37.3	...	...	...	...	...	...	...	...
29	10.8	10.8	...	...	...	...	...	...	...	...
30	10.8	10.8	...	...	...	...	...	...	...	...
31	12.5	12.4	...	...	...	...	...	...	...	...
32	12.5	12.4	...	...	...	...	...	...	...	...
33	12.5	12.4	...	...	...	...	...	...	...	...
34	12.5	12.4	...	...	...	...	...	...	...	...
35	12.5	12.4	...	...	...	...	...	...	...	...
36	12.5	12.4	...	...	...	...	...	...	...	...
37	12.5	12.4	...	...	...	...	...	...	...	...
38	12.5	12.4	...	...	...	...	...	...	...	...
39	12.5	12.4	...	...	...	...	...	...	...	...
40	12.5	12.4	...	...	...	...	...	...	...	...
41	12.5	12.4	...	...	...	...	...	...	...	...
42	15.0	14.9	...	...	...	...	...	...	...	...
43	25.0	24.9	...	...	...	...	...	...	...	...
44	29.2	29.0	...	...	...	...	...	...	...	...
45	29.2	29.0	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Wld. tube	SB-543	...	C70620	WC55
2	...	Finned wld. tube	SB-956	...	C70620	WC55
3	...	Wld. pipe	SB-467	...	C70620	Wld. fr. cold rld. strip
4	...	Smls. tube	SB-466	...	C71000	O60
5	...	Smls. cond. tube	SB-111	...	C71000	O61
6	...	Finned tube	SB-359	...	C71000	O61
7	...	Smls. tube	SB-395	...	C71000	O61
8	...	Wld. pipe	SB-467	...	C71500	W061
9	...	Plate, sheet	SB-171	...	C71500	M10, M20, O20, O25
10	...	Plate, sheet	SB-171	...	C71500	M10, M20, O20, O25
11	...	Wld. pipe	SB-467	...	C71500	W061
12	...	Smls. pipe & tube	SB-466	...	C71500	O60
13	...	Smls. cond. tube	SB-111	...	C71500	O61
14	...	Finned tube	SB-359	...	C71500	O61
15	...	Smls. U-bend tube	SB-395	...	C71500	O61
16	...	Wld. tube	SB-543	...	C71500	W061
17	...	Finned wld. tube	SB-956	...	C71500	W061
18	...	Smls. cond. tube	SB-111	...	C71500	HR50
19	...	Smls. U-bend tube	SB-395	...	C71500	HR50
20	...	Wld. pipe	SB-467	...	C71520	W061
21	...	Forgings	SB-283	...	C71520	M10
22	...	Forgings	SB-283	...	C71520	O20
23	...	Plate, sheet	SB-171	...	C71520	O25
24	...	Forgings	SB-283	...	C71520	M10
25	...	Plate, sheet	SB-171	...	C71520	O25
26	...	Wld. pipe	SB-467	...	C71520	W061
27	...	Smls. pipe & tube	SB-466	...	C71520	O60
28	...	Smls. cond. tube	SB-111	...	C71520	O61
29	...	Finned tube	SB-359	...	C71520	O61
30	...	Smls. U-bend tube	SB-395	...	C71520	O61
31	...	Wld. tube	SB-543	...	C71520	W061
32	...	Finned wld. tube	SB-956	...	C71520	W061
33	...	Smls. cond. tube	SB-111	...	C71520	HR50
34	...	Smls. U-bend tube	SB-395	...	C71520	HR50
35	...	Smls. cond. tube	SB-111	...	C72200	O61
36	...	Castings	SB-62	...	C83600	M01
37	...	Castings	SB-61	...	C92200	M01
38	...	Castings	SB-584	...	C92200	M01
39	...	Castings	SB-584	...	C93700	M01
40	...	Castings	SB-148	...	C95200	M01
41	...	Castings	SB-271	...	C95200	M02
42	...	Castings	SB-505	...	C95200	M07
43	...	Castings	SB-148	...	C95400	M01
44	...	Castings	SB-271	...	C95400	M02
45	...	Castings	SB-148	...	C95800	M01

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	45	35	...
2	...	45	35	...
3	$\leq 4\frac{1}{2}$	54	45	...
4	...	45	16	...
5	...	45	16	...
6	...	45	16	...
7	...	45	16	...
8	$> 4\frac{1}{2}$	45	15	...
9	$2.5 < t \leq 5$	45	18	...
10	≤ 2.5	50	20	...
11	$\leq 4\frac{1}{2}$	50	20	...
12	...	52	18	...
13	...	52	18	...
14	...	52	18	...
15	...	52	18	...
16	...	52	18	...
17	...	52	18	...
18	...	72	50	...
19	...	72	50	...
20	$> 4\frac{1}{2}$	45	15	...
21	> 6	45	18	...
22	...	45	18	...
23	$2.5 < t \leq 5$	45	18	...
24	≤ 6	50	20	...
25	≤ 2.5	50	20	...
26	$\leq 4\frac{1}{2}$	50	20	...
27	...	52	18	...
28	...	52	18	...
29	...	52	18	...
30	...	52	18	...
31	...	52	18	...
32	...	52	18	...
33	...	72	50	...
34	...	72	50	...
35	...	45	16	...
36	...	30	14	...
37	...	34	16	...
38	...	34	16	...
39	...	30	12	...
40	...	65	25	...
41	...	65	25	...
42	...	68	26	...
43	...	75	30	...
44	...	75	30	...
45	...	85	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
2	35.0	34.0	33.2	32.4	31.6	30.9	30.3	29.8	29.5
3	45.0	43.7	42.7	41.6	40.7	39.8	39.0	38.4	37.9
4	16.0	15.6	15.3	14.9	14.5	14.1	13.8	13.4	13.0
5	16.0	15.6	15.3	14.9	14.5	14.1	13.8	13.4	13.0
6	16.0	15.6	15.3	14.9	14.5	14.1	13.8	13.4	13.0
7	16.0	15.6	15.3	14.9	14.5	14.1	13.8	13.4	13.0
8	15.0	14.5	14.1	13.8	13.5	13.2	12.9	12.6	12.4
9	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
10	20.0	19.3	18.8	18.4	18.0	17.6	17.2	16.9	16.5
11	20.0	19.3	18.8	18.4	18.0	17.6	17.2	16.9	16.5
12	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
13	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
14	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
15	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
16	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
17	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
18	50.0	48.2	47.5	46.8	46.2	45.6	45.0	44.4	43.9
19	50.0	48.2	47.5	46.8	46.2	45.6	45.0	44.4	43.9
20	15.0	14.5	14.1	13.8	13.5	13.2	12.9	12.6	12.2
21	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
22	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
23	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
24	20.0	19.3	18.8	18.4	18.0	17.6	17.2	16.9	16.5
25	20.0	19.3	18.8	18.4	18.0	17.6	17.2	16.9	16.5
26	20.0	19.3	18.8	18.4	18.0	17.6	17.2	16.9	16.5
27	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
28	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
29	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
30	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
31	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
32	18.0	17.4	17.0	16.6	16.2	15.8	15.5	15.2	14.9
33	50.0	48.2	47.5	46.8	46.2	45.6	45.0	44.4	43.9
34	50.0	48.2	47.5	46.8	46.2	45.6	45.0	44.4	43.9
35	16.0	15.6	15.2	14.8	14.5	14.2	13.9	13.7	...
36	14.0	13.1	12.6	12.1	11.7	11.3	10.9	10.5	10.1
37	16.0	15.0	14.3	13.8	13.5	13.3	13.2	13.1	13.0
38	16.0	15.0	14.3	13.8	13.5	13.3	13.2	13.1	13.0
39	12.0	11.1	10.7	10.4	10.3	10.1	10.0	9.9	9.8
40	25.0	23.5	22.8	22.2	21.7	21.4	21.3	21.2	21.2
41	25.0	23.5	22.8	22.2	21.7	21.4	21.3	21.2	21.2
42	26.0	24.5	23.7	23.0	22.6	22.3	22.1	22.1	22.1
43	30.0	29.5	29.3	29.1	28.9	28.9	28.9	28.9	28.9
44	30.0	29.5	29.3	29.1	28.9	28.9	28.9	28.9	28.9
45	35.0	34.5	34.3	34.2	34.0	33.9	33.8	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	29.2	29.0	...	...	...	...	...	...	...	...
2	29.2	29.0	...	...	...	...	...	...	...	...
3	37.5	37.3	...	...	...	...	...	...	...	...
4	12.7	12.5	12.2	12.0	...	...	...	...	...	...
5	12.7	12.5	12.2	12.0	...	...	...	...	...	...
6	12.7	12.5	12.2	12.0	...	...	...	...	...	...
7	12.7	12.5	12.2	12.0	...	...	...	...	...	...
8	12.2	12.0	11.9	11.7	...	...	...	...	...	...
9	14.6	14.4	14.2	14.1	...	...	...	...	...	...
10	16.3	16.0	15.8	15.7	...	...	...	...	...	...
11	16.3	16.0	15.8	15.7	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...
13	14.6	14.4	14.2	14.1	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...
16	14.6	14.4	14.2	14.1	...	...	...	...	...	...
17	14.6	14.4	14.2	14.1	...	...	...	...	...	...
18	43.5	43.2	42.9	42.6	...	...	...	...	...	...
19	43.5	43.2	42.9	42.6	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	14.6	14.4	14.2	14.1	...	...	...	...	...	...
22	14.6	14.4	14.2	14.1	...	...	...	...	...	...
23	14.6	14.4	14.2	14.1	...	...	...	...	...	...
24	16.3	16.0	15.8	15.7	...	...	...	...	...	...
25	16.3	16.0	15.8	15.7	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...
28	14.6	14.4	14.2	14.1	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...
31	14.6	14.4	14.2	14.1	...	...	...	...	...	...
32	14.6	14.4	14.2	14.1	...	...	...	...	...	...
33	43.5	43.2	42.9	42.6	...	...	...	...	...	...
34	43.5	43.2	42.9	42.6	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...
37	12.8	12.8	...	...	...	...	...	...	...	...
38	12.8	12.8	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...
40	21.2	21.2	...	...	...	...	...	...	...	...
41	21.2	21.2	...	...	...	...	...	...	...	...
42	22.1	22.1	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	...	Castings	SB-148	...	C95820	M01
2	...	Castings	SB-369	...	C96200	M01
3	...	Castings	SB-584	...	C97600	M01
4	99Ni	Bolting	SB-160	...	N02200	Annealed
5	99Ni	Plate, sheet, strip	SB-162	...	N02200	As rolled
6	99Ni	Bolting	SB-160	...	N02200	Hot fin./ann.
7	99Ni	Bolting	SB-160	...	N02200	Cold drawn
8	99Ni	Smls. pipe & tube	SB-161	...	N02200	Stress rel.
9	99Ni	Smls. tube	SB-163	...	N02200	Stress rel.
10	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
11	99Ni-Low C	Smls. & wld. fittings	SB-366	...	N02201	Annealed
12	99Ni-Low C	Bar, rod	SB-160	...	N02201	Hot rolled/ann.
13	99Ni-Low C	Smls. pipe & tube	SB-161	...	N02201	Annealed
14	99Ni-Low C	Smls. tube	SB-163	...	N02201	Annealed
15	99Ni-Low C	Plate, sheet, strip	SB-162	...	N02201	Hot rolled/ann.
16	67Ni-30Cu	Bar	SB-164	...	N04400	Annealed
17	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
18	67Ni-30Cu	Forgings	SB-564	...	N04400	Annealed
19	67Ni-30Cu	Plate	SB-127	...	N04400	Annealed
20	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Annealed
21	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Annealed
22	67Ni-30Cu	Smls. & wld. fittings	SB-366	...	N04400	Annealed
23	67Ni-30Cu	Plate	SB-127	...	N04400	As rolled
24	67Ni-30Cu	Rounds	SB-164	...	N04400	Hot worked
25	67Ni-30Cu	Rounds	SB-164	...	N04400	Hot worked
26	67Ni-30Cu	Rounds	SB-164	...	N04400	CW & SR
27	67Ni-30Cu	Rounds	SB-164	...	N04400	CW & SR
28	67Ni-30Cu	Smls. tube	SB-163	...	N04400	Stress rel.
29	67Ni-30Cu	Smls. pipe & tube	SB-165	...	N04400	Stress rel.
30	67Ni-30Cu	Rounds	SB-164	...	N04400	CW & SR
31	67Ni-30Cu	Rounds	SB-164	...	N04400	Cold worked
32	67Ni-30Cu-S	Bar	SB-164	...	N04405	Annealed
33	67Ni-30Cu-S	Bar	SB-164	...	N04405	Hot worked
34	67Ni-28Cu-3Al	Bolting	SF-468	...	N05500	Ann./aged
35	67Ni-28Cu-3Al	Bolting	SF-468	...	N05500	Ann./aged
36	47Ni-22Cr-9Mo-18Fe	Plate	SB-435	...	N06002	Annealed
37	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...	N06002	Solution ann.
38	47Ni-22Cr-9Mo-18Fe	Rod	SB-572	...	N06002	Annealed
39	47Ni-22Cr-9Mo-18Fe	Smls. & wld. fittings	SB-366	...	N06002	Annealed
40	47Ni-22Cr-9Mo-18Fe	Sheet	SB-435	...	N06002	Annealed
41	47Ni-22Cr-9Mo-18Fe	Wld. pipe	SB-619	...	N06002	Solution ann.
42	47Ni-22Cr-9Mo-18Fe	Smls. pipe & tube	SB-622	...	N06002	Solution ann.
43	47Ni-22Cr-9Mo-18Fe	Wld. tube	SB-626	...	N06002	Solution ann.
44	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
45	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	94	39	...
2	...	45	25	...
3	...	40	17	...
4	...	55	15	...
5	...	55	20	...
6	...	60	15	...
7	...	65	40	...
8	...	65	40	...
9	...	65	40	...
10	>5 O.D.	50	10	...
11	...	50	10	...
12	...	50	10	...
13	≤5 O.D.	50	12	...
14	...	50	12	...
15	...	50	12	...
16	...	70	25	...
17	>5 O.D.	70	25	...
18	...	70	25	...
19	...	70	28	...
20	≤3	70	28	...
21	≤5 O.D.	70	28	...
22	...	70	28	...
23	...	75	40	...
24	12 < t ≤ 14	75	40	...
25	≤12	80	40	...
26	<1/2	84	50	...
27	3 1/2 < t ≤ 4	84	55	...
28	...	85	55	...
29	...	85	55	...
30	1/2 ≤ t ≤ 3 1/2	87	60	...
31	<1/2	110	85	...
32	...	70	25	...
33	...	75	35	...
34	1.000–1.500	130	85	...
35	0.250–0.875	130	90	...
36	>3/16	95	35	...
37	≤3/16	95	35	...
38	...	95	35	...
39	...	100	40	...
40	1/16 < t ≤ 3/16	100	40	...
41	...	100	40	...
42	...	100	40	...
43	...	100	40	...
44	>3/4	85	30	...
45	>3/4	85	30	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	39.0	38.5	38.2	38.1	37.9	37.8	37.6	37.5	37.2
2	25.0	24.3	23.7	23.0	22.5	22.1	21.7	21.4	21.0
3	17.0	15.3	14.3	13.6	13.1	12.8	12.6	12.4	12.3
4	15.0	15.0	15.0	15.0	15.0	15.0	15.0	14.7	14.2
5	20.0	20.0	20.0	20.0	20.0	20.0	20.0	19.6	18.9
6	15.0	15.0	15.0	15.0	15.0	15.0	15.0	14.7	14.2
7	40.0	38.7	38.4	38.3	38.3	38.3	38.2	37.9	37.5
8	40.0	38.7	38.4	38.3	38.3	38.3	38.2	37.9	37.5
9	40.0	38.7	38.4	38.3	38.3	38.3	38.2	37.9	37.5
10	10.0	9.7	9.6	9.5	9.4	9.4	9.4	9.4	9.4
11	10.0	9.7	9.6	9.5	9.4	9.4	9.4	9.4	9.4
12	10.0	9.7	9.6	9.5	9.4	9.4	9.4	9.4	9.4
13	12.0	11.7	11.5	11.4	11.3	11.2	11.2	11.2	11.2
14	12.0	11.7	11.5	11.4	11.3	11.2	11.2	11.2	11.2
15	12.0	11.7	11.5	11.4	11.3	11.2	11.2	11.2	11.2
16	25.0	23.0	21.9	21.0	20.4	20.0	19.7	19.7	19.7
17	25.0	23.0	21.9	21.0	20.4	20.0	19.7	19.7	19.7
18	25.0	23.0	21.9	21.0	20.4	20.0	19.7	19.7	19.7
19	28.0	25.8	24.5	23.6	22.8	22.4	22.1	22.0	22.0
20	28.0	25.8	24.5	23.6	22.8	22.4	22.1	22.0	22.0
21	28.0	25.8	24.5	23.6	22.8	22.4	22.1	22.0	22.0
22	28.0	25.8	24.5	23.6	22.8	22.4	22.1	22.0	22.0
23	40.0	39.5	38.8	37.9	37.1	36.4	35.9	35.5	35.2
24	40.0	...	38.8	...	37.1	...	35.9	...	35.2
25	40.0	...	38.8	...	37.1	...	35.9	...	35.2
26	50.0	...	47.2	...	45.8	...	45.0	...	45.0
27	55.0	...	51.8	...	50.4	...	49.7	...	49.2
28	55.0	52.9	51.8	51.0	50.4	50.0	49.7	49.5	49.2
29	55.0	52.9	51.8	51.0	50.4	50.0	49.7	49.5	49.2
30	60.0	...	56.6	...	54.9	...	54.0	...	54.0
31	85.0	...	80.2	...	77.8	...	76.5	...	76.5
32	25.0	23.0	21.9	21.0	20.4	20.0	19.7	19.7	19.7
33	35.0	34.6	33.9	33.2	32.5	31.9	31.4	31.0	30.8
34	85.0	...	81.2	...	79.4	...	78.2	...	77.5
35	90.0	...	86.0	...	84.0	...	82.8	...	82.1
36	35.0	32.9	31.5	30.1	28.8	27.7	26.6	25.7	24.8
37	35.0	32.9	31.5	30.1	28.8	27.7	26.6	25.7	24.8
38	35.0	32.9	31.5	30.1	28.8	27.7	26.6	25.7	24.8
39	40.0	37.5	35.9	34.4	33.0	31.6	30.4	29.3	28.4
40	40.0	37.5	35.9	34.4	33.0	31.6	30.4	29.3	28.4
41	40.0	37.5	35.9	34.4	33.0	31.6	30.4	29.3	28.4
42	40.0	37.5	35.9	34.4	33.0	31.6	30.4	29.3	28.4
43	40.0	37.5	35.9	34.4	33.0	31.6	30.4	29.3	28.4
44	30.0	28.1	27.0	25.9	25.0	24.2	23.5	22.9	22.4
45	30.0	28.1	27.0	25.9	25.0	24.2	23.5	22.9	22.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)										
1	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...
4	13.6	12.9	...	...	...	...	...	...	...	...
5	18.1	17.2	...	...	...	...	...	...	...	...
6	13.6	12.9	...	...	...	...	...	...	...	...
7	37.0	36.4	35.7	...	...	...	...	...	...	...
8	37.0	36.4	35.7	...	...	...	...	...	...	...
9	37.0	36.4	35.7	...	...	...	...	...	...	...
10	9.4	9.4	9.3	9.3	9.2	9.0	8.8	8.6	8.2	7.9
11	9.4	9.4	9.3	9.3	9.2	9.0	8.8	8.6	8.2	7.9
12	9.4	9.4	9.3	9.3	9.2	9.0	8.8	8.6	8.2	7.9
13	11.2	11.2	11.2	11.1	11.0	10.8	10.6	10.3	9.9	9.4
14	11.2	11.2	11.2	11.1	11.0	10.8	10.6	10.3	9.9	9.4
15	11.2	11.2	11.2	11.1	11.0	10.8	10.6	10.3	9.9	9.4
16	19.7	19.7	19.7	19.6	19.4	19.1	18.9	18.8	...	...
17	19.7	19.7	19.7	19.6	19.4	19.1	18.9	18.8	...	...
18	19.7	19.7	19.7	19.6	19.4	19.1	18.9	18.8	...	...
19	22.0	22.0	22.0	21.9	21.7	21.4	21.2	21.1	...	...
20	22.0	22.0	22.0	21.9	21.7	21.4	21.2	21.1	...	...
21	22.0	22.0	22.0	21.9	21.7	21.4	21.2	21.1	...	...
22	22.0	22.0	22.0	21.9	21.7	21.4	21.2	21.1	...	...
23	34.9	34.7	34.4	34.0	33.5	32.9	32.3	31.6	...	...
24	...	34.7	34.4	34.0	33.5	32.9	...	...	...	...
25	...	34.7	34.4	34.0	33.5	32.9	...	...	...	...
26	...	44.2	42.1	42.1	41.8	40.4	...	...	...	...
27	...	48.1	47.3	46.3	45.3	44.4	...	...	...	...
28	48.7	48.1	47.3	46.3	45.3	44.4	...	...	...	...
29	48.7	48.1	47.3	46.3	45.3	44.4	...	...	...	...
30	...	53.0	50.5	50.5	50.1	48.5	...	...	...	...
31	...	75.1	71.6	71.6	71.0	68.7	...	...	...	...
32	19.7	19.7	19.7	19.6	19.4	19.1	18.9	18.8	...	...
33	30.6	30.3	30.1	29.8	29.3	28.8	28.2	27.7	...	...
34	...	77.1	76.9	76.7	...	...	...	...	...	...
35	...	81.6	81.4	81.2	...	...	...	...	...	...
36	24.1	23.5	23.0	22.6	22.3	22.1	21.9	21.7	21.6	21.5
37	24.1	23.5	23.0	22.6	22.3	22.1	21.9	21.7	21.6	21.5
38	24.1	23.5	23.0	22.6	22.3	22.1	21.9	21.7	21.6	21.5
39	27.5	26.9	26.3	25.8	25.5	25.2	25.0	24.9	24.7	24.6
40	27.5	26.9	26.3	25.8	25.5	25.2	25.0	24.9	24.7	24.6
41	27.5	26.9	26.3	25.8	25.5	25.2	25.0	24.9	24.7	24.6
42	27.5	26.9	26.3	25.8	25.5	25.2	25.0	24.9	24.7	24.6
43	27.5	26.9	26.3	25.8	25.5	25.2	25.0	24.9	24.7	24.6
44	22.0	21.6	21.3	21.1	20.9	20.8	20.7	20.6	20.5	20.4
45	22.0	21.6	21.3	21.1	20.9	20.8	20.7	20.6	20.5	20.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	7.3	7.0	6.7	6.4	...	...	...	...	...	...	...	...	...
11	7.3	7.0	6.7	6.4	...	...	...	...	...	...	...	...	...
12	7.3	7.0	6.7	6.4	...	...	...	...	...	...	...	...	...
13	8.8	8.4	8.0	7.7	...	...	...	...	...	...	...	...	...
14	8.8	8.4	8.0	7.7	...	...	...	...	...	...	...	...	...
15	8.8	8.4	8.0	7.7	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	21.4	21.3	21.1	20.8	20.5	20.1	19.7	19.1	18.4	17.6	16.7	15.6	14.4
37	21.4	21.3	21.1	20.8	20.5	20.1	19.7	19.1	18.4	17.6	16.7	15.6	14.4
38	21.4	21.3	21.1	20.8	20.5	20.1	19.7	19.1	18.4	17.6	16.7	15.6	14.4
39	24.5	24.3	24.1	23.8	23.4	23.0	22.5	21.8	21.1	20.1	19.1	17.8	16.4
40	24.5	24.3	24.1	23.8	23.4	23.0	22.5	21.8	21.1	20.1	19.1	17.8	16.4
41	24.5	24.3	24.1	23.8	23.4	23.0	22.5	21.8	21.1	20.1	19.1	17.8	16.4
42	24.5	24.3	24.1	23.8	23.4	23.0	22.5	21.8	21.1	20.1	19.1	17.8	16.4
43	24.5	24.3	24.1	23.8	23.4	23.0	22.5	21.8	21.1	20.1	19.1	17.8	16.4
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	47Ni-22Cr-19Fe-6Mo	Smls. & wld. fittings	SB-366	...	N06007	Annealed
2	47Ni-22Cr-19Fe-6Mo	Rod	SB-581	...	N06007	Solution ann.
3	47Ni-22Cr-19Fe-6Mo	Plate, sheet, strip	SB-582	...	N06007	Solution ann.
4	47Ni-22Cr-19Fe-6Mo	Wld. pipe	SB-619	...	N06007	Solution ann.
5	47Ni-22Cr-19Fe-6Mo	Smls. pipe & tube	SB-622	...	N06007	Solution ann.
6	47Ni-22Cr-19Fe-6Mo	Wld. tube	SB-626	...	N06007	Solution ann.
7	55Ni-21Cr-13.5Mo	Smls. & wld. fittings	SB-366	...	N06022	Solution ann.
8	55Ni-21Cr-13.5Mo	Forgings	SB-462	...	N06022	Solution ann.
9	55Ni-21Cr-13.5Mo	Forgings	SB-564	...	N06022	Solution ann.
10	55Ni-21Cr-13.5Mo	Rod	SB-574	...	N06022	Solution ann.
11	55Ni-21Cr-13.5Mo	Plate, sheet, strip	SB-575	...	N06022	Solution ann.
12	55Ni-21Cr-13.5Mo	Wld. pipe	SB-619	...	N06022	Solution ann.
13	55Ni-21Cr-13.5Mo	Smls. pipe & tube	SB-622	...	N06022	Solution ann.
14	55Ni-21Cr-13.5Mo	Wld. tube	SB-626	...	N06022	Solution ann.
15	60Ni-25Cr-9.5Fe-2.1Al	Smls. tube	SB-163	...	N06025	Annealed
16	60Ni-25Cr-9.5Fe-2.1Al	Plate, sheet, strip	SB-168	...	N06025	Annealed
17	60Ni-25Cr-9.5Fe-2.1Al	Wrought fittings	SB-366	...	N06025	Annealed
18	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-462	...	N06025	Annealed
19	60Ni-25Cr-9.5Fe-2.1Al	Wld. tube	SB-516	...	N06025	Annealed
20	60Ni-25Cr-9.5Fe-2.1Al	Wld. pipe	SB-517	...	N06025	Annealed
21	60Ni-25Cr-9.5Fe-2.1Al	Forgings	SB-564	...	N06025	Annealed
22	60Ni-25Cr-9.5Fe-2.1Al	Bar	SB-166	...	N06025	HW or CW ann.
23	60Ni-25Cr-9.5Fe-2.1Al	Smls. pipe & tube	SB-167	...	N06025	HW or CW ann.
24	40Ni-29Cr-15Fe-5Mo	Smls. & wld. fittings	SB-366	...	N06030	Solution ann.
25	40Ni-29Cr-15Fe-5Mo	Forgings	SB-462	...	N06030	Solution ann.
26	40Ni-29Cr-15Fe-5Mo	Rod	SB-581	...	N06030	Solution ann.
27	40Ni-29Cr-15Fe-5Mo	Plate, sheet, strip	SB-582	...	N06030	Solution ann.
28	40Ni-29Cr-15Fe-5Mo	Wld. pipe	SB-619	...	N06030	Solution ann.
29	40Ni-29Cr-15Fe-5Mo	Smls. pipe & tube	SB-622	...	N06030	Solution ann.
30	40Ni-29Cr-15Fe-5Mo	Wld. tube	SB-626	...	N06030	Solution ann.
31	58Ni-33Cr-8Mo	Smls. & wld. fittings	SB-366	...	N06035	Solution ann.
32	58Ni-33Cr-8Mo	Forgings	SB-462	...	N06035	Solution ann.
33	58Ni-33Cr-8Mo	Forgings	SB-564	...	N06035	Solution ann.
34	58Ni-33Cr-8Mo	Rod	SB-574	...	N06035	Solution ann.
35	58Ni-33Cr-8Mo	Plate, sheet, strip	SB-575	...	N06035	Solution ann.
36	58Ni-33Cr-8Mo	Wld. pipe	SB-619	...	N06035	Solution ann.
37	58Ni-33Cr-8Mo	Smls. pipe & tube	SB-622	...	N06035	Solution ann.
38	58Ni-33Cr-8Mo	Wld. tube	SB-626	...	N06035	Solution ann.
39	46Ni-27Cr-23Fe-2.75Si	Rod	SB-166	...	N06045	Solution ann.
40	46Ni-27Cr-23Fe-2.75Si	Smls. pipe & tube	SB-167	...	N06045	Solution ann.
41	46Ni-27Cr-23Fe-2.75Si	Plate, sheet, strip	SB-168	...	N06045	Solution ann.
42	46Ni-27Cr-23Fe-2.75Si	Smls. & wld. fittings	SB-366	...	N06045	Solution ann.
43	46Ni-27Cr-23Fe-2.75Si	Wld. tube	SB-516	...	N06045	Solution ann.
44	46Ni-27Cr-23Fe-2.75Si	Wld. pipe	SB-517	...	N06045	Solution ann.
45	46Ni-27Cr-23Fe-2.75Si	Forgings	SB-564	...	N06045	Solution ann.

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	90	35	...
2	$\leq 3/4$	90	35	...
3	$\leq 3/4$	90	35	...
4	...	90	35	...
5	...	90	35	...
6	...	90	35	...
7	...	100	45	...
8	...	100	45	...
9	...	100	45	...
10	...	100	45	...
11	...	100	45	...
12	...	100	45	...
13	...	100	45	...
14	...	100	45	...
15	...	98	39	...
16	...	98	39	...
17	...	98	39	...
18	$t \leq 4$	98	39	...
19	...	98	39	...
20	...	98	39	...
21	$t \leq 4$	98	39	...
22	$t \leq 4$	98	39	...
23	...	98	39	...
24	...	85	35	...
25	...	85	35	...
26	...	85	35	...
27	...	85	35	...
28	...	85	35	...
29	...	85	35	...
30	...	85	35	...
31	...	85	35	...
32	...	85	35	...
33	...	85	35	...
34	...	85	35	...
35	...	85	35	...
36	...	85	35	...
37	...	85	35	...
38	...	85	35	...
39	...	90	35	...
40	...	90	35	...
41	...	90	35	...
42	...	90	35	...
43	...	90	35	...
44	...	90	35	...
45	...	90	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
2	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
3	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
4	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
5	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
6	35.0	32.8	31.4	30.2	29.2	28.2	27.4	26.7	26.1
7	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
8	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
9	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
10	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
11	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
12	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
13	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
14	45.0	42.0	40.1	38.4	36.9	35.5	34.3	33.2	32.2
15	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
16	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
17	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
18	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
19	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
20	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
21	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
22	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
23	39.0	39.0	38.7	38.1	37.3	36.4	35.5	...	33.7
24	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
25	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
26	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
27	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
28	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
29	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
30	35.0	31.7	30.0	28.6	27.5	26.6	25.8	25.1	24.6
31	35.0	...	30.6	...	27.3	...	24.7	...	22.9
32	35.0	...	30.6	...	27.3	...	24.7	...	22.9
33	35.0	...	30.6	...	27.3	...	24.7	...	22.9
34	35.0	...	30.6	...	27.3	...	24.7	...	22.9
35	35.0	...	30.6	...	27.3	...	24.7	...	22.9
36	35.0	...	30.6	...	27.3	...	24.7	...	22.9
37	35.0	...	30.6	...	27.3	...	24.7	...	22.9
38	35.0	...	30.6	...	27.3	...	24.7	...	22.9
39	35.0	...	31.4	...	28.9	...	27.1	...	26.0
40	35.0	...	31.4	...	28.9	...	27.1	...	26.0
41	35.0	...	31.4	...	28.9	...	27.1	...	26.0
42	35.0	...	31.4	...	28.9	...	27.1	...	26.0
43	35.0	...	31.4	...	28.9	...	27.1	...	26.0
44	35.0	...	31.4	...	28.9	...	27.1	...	26.0
45	35.0	...	31.4	...	28.9	...	27.1	...	26.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
2	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
3	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
4	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
5	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
6	25.6	25.2	24.9	24.6	24.4	24.2	24.1	24.0	23.9	23.8
7	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
8	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
9	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
10	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
11	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
12	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
13	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
14	31.4	30.6	30.0	29.4	29.0	28.6	28.2	27.9	27.7	27.5
15	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
16	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
17	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
18	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
19	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
20	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
21	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
22	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
23	32.9	32.2	31.6	31.1	30.7	30.3	30.1	29.9	29.7	29.5
24	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
25	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
26	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
27	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
28	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
29	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
30	24.1	23.6	23.2	22.8	22.3	21.9	21.5	21.1	20.9	20.7
31	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
32	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
33	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
34	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
35	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
36	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
37	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
38	...	21.9	21.6	21.3	21.1	20.8	20.6	20.2	19.8	19.3
39	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
40	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
41	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
42	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
43	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
44	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9
45	...	25.4	25.3	25.1	25.0	24.9	24.7	24.5	24.3	23.9

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
8	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
9	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
10	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
11	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
12	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
13	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
14	27.0	26.8	26.6	26.4	26.2	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	59Ni-23Cr-16Mo	Fittings	SB-366	CR5923	N06059	Annealed
2	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923	N06059	Annealed
3	59Ni-23Cr-16Mo	Wld. fittings	SB-366	WP5923W	N06059	Annealed
4	59Ni-23Cr-16Mo	Fittings	SB-366	WP5923WX	N06059	Annealed
5	59Ni-23Cr-16Mo	Forged fittings	SB-462	...	N06059	Solution ann.
6	59Ni-23Cr-16Mo	Forgings	SB-564	...	N06059	Solution ann.
7	59Ni-23Cr-16Mo	Rod	SB-574	...	N06059	Solution ann.
8	59Ni-23Cr-16Mo	Plate, sheet, strip	SB-575	...	N06059	Solution ann.
9	59Ni-23Cr-16Mo	Wld. pipe	SB-619	...	N06059	Solution ann.
10	59Ni-23Cr-16Mo	Smls. pipe & tube	SB-622	...	N06059	Solution ann.
11	59Ni-23Cr-16Mo	Wld. tube	SB-626	...	N06059	Solution ann.
12	59Ni-23Cr-16Mo-1.6Cu	Fittings	SB-366	...	N06200	Solution ann.
13	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-462	...	N06200	Solution ann.
14	59Ni-23Cr-16Mo-1.6Cu	Forgings	SB-564	...	N06200	Solution ann.
15	59Ni-23Cr-16Mo-1.6Cu	Rod	SB-574	...	N06200	Solution ann.
16	59Ni-23Cr-16Mo-1.6Cu	Plate, sheet, strip	SB-575	...	N06200	Solution ann.
17	59Ni-23Cr-16Mo-1.6Cu	Wld. pipe	SB-619	...	N06200	Solution ann.
18	59Ni-23Cr-16Mo-1.6Cu	Smls. pipe & tube	SB-622	...	N06200	Solution ann.
19	59Ni-23Cr-16Mo-1.6Cu	Wld. tube	SB-626	...	N06200	Solution ann.
20	60Ni-19Cr-19Mo-1.8Ta	Smls. & wld. fittings	SB-366	...	N06210	Solution ann.
21	60Ni-19Cr-19Mo-1.8Ta	Forgings	SB-564	...	N06210	Solution ann.
22	60Ni-19Cr-19Mo-1.8Ta	Rod	SB-574	...	N06210	Solution ann.
23	60Ni-19Cr-19Mo-1.8Ta	Plate, sheet, strip	SB-575	...	N06210	Solution ann.
24	60Ni-19Cr-19Mo-1.8Ta	Wld. pipe	SB-619	...	N06210	Solution ann.
25	60Ni-19Cr-19Mo-1.8Ta	Smls. pipe & tube	SB-622	...	N06210	Solution ann.
26	60Ni-19Cr-19Mo-1.8Ta	Wld. tube	SB-626	...	N06210	Solution ann.
27	57Ni-22Cr-14W-2Mo-La	Plate, sheet, strip	SB-435	...	N06230	Solution ann.
28	57Ni-22Cr-14W-2Mo-La	Forgings	SB-564	...	N06230	Solution ann.
29	57Ni-22Cr-14W-2Mo-La	Bar	SB-572	...	N06230	Solution ann.
30	57Ni-22Cr-14W-2Mo-La	Wld. pipe	SB-619	...	N06230	Solution ann.
31	57Ni-22Cr-14W-2Mo-La	Smls. pipe & tube	SB-622	...	N06230	Solution ann.
32	57Ni-22Cr-14W-2Mo-La	Wld. tube	SB-626	...	N06230	Solution ann.
33	61Ni-16Mo-16Cr	Smls. & wld. fittings	SB-366	...	N06455	Annealed
34	61Ni-16Mo-16Cr	Rod	SB-574	...	N06455	Solution ann.
35	61Ni-16Mo-16Cr	Plate, sheet, strip	SB-575	...	N06455	Solution ann.
36	61Ni-16Mo-16Cr	Wld. pipe	SB-619	...	N06455	Solution ann.
37	61Ni-16Mo-16Cr	Smls. pipe & tube	SB-622	...	N06455	Solution ann.
38	61Ni-16Mo-16Cr	Wld. tube	SB-626	...	N06455	Solution ann.
39	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
40	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
41	72Ni-15Cr-8Fe	Smls. & wld. fittings	SB-366	...	N06600	Annealed
42	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Cold drawn/ann.
43	72Ni-15Cr-8Fe	Smls. pipe & tube	SB-167	...	N06600	Hot fin./ann.
44	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	Annealed
45	72Ni-15Cr-8Fe	Bar	SB-166	...	N06600	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	100	45	...
2	...	100	45	...
3	...	100	45	...
4	...	100	45	...
5	...	100	45	...
6	...	100	45	...
7	...	100	45	...
8	...	100	45	...
9	...	100	45	...
10	...	100	45	...
11	...	100	45	...
12	...	100	45	...
13	...	100	45	...
14	...	100	45	...
15	...	100	45	...
16	...	100	45	...
17	...	100	45	...
18	...	100	45	...
19	...	100	45	...
20	...	100	45	...
21	...	100	45	...
22	...	100	45	...
23	...	100	45	...
24	...	100	45	...
25	...	100	45	...
26	...	100	45	...
27	...	110	45	...
28	...	110	45	...
29	...	110	45	...
30	...	110	45	...
31	...	110	45	...
32	...	110	45	...
33	...	100	40	...
34	...	100	40	...
35	...	100	40	...
36	...	100	40	...
37	...	100	40	...
38	...	100	40	...
39	>5	75	25	...
40	>5	80	30	...
41	...	80	30	...
42	>5	80	30	...
43	≤5	80	30	...
44	≤3	80	35	...
45	...	80	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
2	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
3	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
4	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
5	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
6	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
7	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
8	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
9	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
10	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
11	45.0	42.8	40.4	39.1	37.8	36.9	35.8	34.8	33.9
12	45.0	...	40.4	...	37.2	...	34.3	...	31.8
13	45.0	...	40.4	...	37.2	...	34.3	...	31.8
14	45.0	...	40.4	...	37.2	...	34.3	...	31.8
15	45.0	...	40.4	...	37.2	...	34.3	...	31.8
16	45.0	...	40.4	...	37.2	...	34.3	...	31.8
17	45.0	...	40.4	...	37.2	...	34.3	...	31.8
18	45.0	...	40.4	...	37.2	...	34.3	...	31.8
19	45.0	...	40.4	...	37.2	...	34.3	...	31.8
20	45.0	...	40.0	...	36.8	...	33.9	...	31.4
21	45.0	...	40.0	...	36.8	...	33.9	...	31.4
22	45.0	...	40.0	...	36.8	...	33.9	...	31.4
23	45.0	...	40.0	...	36.8	...	33.9	...	31.4
24	45.0	...	40.0	...	36.8	...	33.9	...	31.4
25	45.0	...	40.0	...	36.8	...	33.9	...	31.4
26	45.0	...	40.0	...	36.8	...	33.9	...	31.4
27	45.0	...	42.3	...	39.6	...	37.0	...	34.7
28	45.0	...	42.3	...	39.6	...	37.0	...	34.7
29	45.0	...	42.3	...	39.6	...	37.0	...	34.7
30	45.0	...	42.3	...	39.6	...	37.0	...	34.7
31	45.0	...	42.3	...	39.6	...	37.0	...	34.7
32	45.0	...	42.3	...	39.6	...	37.0	...	34.7
33	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
34	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
35	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
36	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
37	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
38	40.0	38.2	36.9	35.6	34.5	33.5	32.6	31.8	31.2
39	25.0	24.3	23.8	23.3	22.8	22.3	21.9	21.4	21.0
40	30.0	29.2	28.6	28.0	27.4	26.8	26.2	25.7	25.2
41	30.0	29.2	28.6	28.0	27.4	26.8	26.2	25.7	25.2
42	30.0	29.2	28.6	28.0	27.4	26.8	26.2	25.7	25.2
43	30.0	29.2	28.6	28.0	27.4	26.8	26.2	25.7	25.2
44	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
45	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
2	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
3	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
4	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
5	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
6	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
7	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
8	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
9	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
10	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
11	33.0	32.1	31.2	30.3	29.4	28.6	27.8	27.0	26.3	25.7
12	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
13	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
14	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
15	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
16	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
17	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
18	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
19	...	29.8	29.1	28.6	28.2	28.0	27.8	27.6	27.2	26.4
20	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
21	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
22	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
23	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
24	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
25	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
26	...	29.3	28.4	27.5	26.8	26.2	25.7	25.2	24.9	24.7
27	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
28	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
29	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
30	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
31	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
32	...	32.9	32.3	31.9	31.6	31.4	31.3	31.3	31.3	31.3
33	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
34	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
35	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
36	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
37	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
38	30.6	30.2	29.8	29.4	29.0	28.7	28.3	27.9	27.6	27.3
39	20.6	20.3	19.9	19.6	19.3	19.1	18.8	18.6	18.5	18.3
40	24.7	24.3	23.9	23.5	23.2	22.9	22.6	22.3	22.2	21.9
41	24.7	24.3	23.9	23.5	23.2	22.9	22.6	22.3	22.2	21.9
42	24.7	24.3	23.9	23.5	23.2	22.9	22.6	22.3	22.2	21.9
43	24.7	24.3	23.9	23.5	23.2	22.9	22.6	22.3	22.2	21.9
44	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
45	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	18.0	17.6	17.2	16.7	...	...	...	...	...	...	...	...	...
40	21.6	21.1	20.6	20.1	...	...	...	...	...	...	...	...	...
41	21.6	21.1	20.6	20.1	...	...	...	...	...	...	...	...	...
42	21.6	21.1	20.6	20.1	...	...	...	...	...	...	...	...	...
43	21.6	21.1	20.6	20.1	...	...	...	...	...	...	...	...	...
44	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
45	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper	
Nonferrous Materials (Cont'd)							
1	72Ni-15Cr-8Fe	Plate	SB-168	...	N06600	Annealed	
2	72Ni-15Cr-8Fe	Wld. tube	SB-516	...	N06600	Annealed	
3	72Ni-15Cr-8Fe	Forgings	SB-564	...	N06600	...	
4	72Ni-15Cr-8Fe	Pipe, tube	SB-167	...	N06600	Cold drawn/ann.	
5	72Ni-15Cr-8Fe	Wld. pipe	SB-517	...	N06600	Cold drawn/ann.	
6	72Ni-15Cr-8Fe	Smls. tube	SB-163	...	N06600	...	
7	72Ni-15Cr-8Fe	Bar, rod	SB-166	...	N06600	Hot worked	
8	72Ni-15Cr-8Fe	Plate, sheet, strip	SB-168	...	N06600	Hot rolled	
9	72Ni-15Cr-8Fe	Rounds	SB-166	...	N06600	Hot worked	
10	72Ni-15Cr-8Fe	Rounds	SB-166	...	N06600	Hot worked	
11	60Ni-23Cr-Fe	Smls. tube	SB-163	...	N06601	Annealed	
12	60Ni-23Cr-Fe	Bar	SB-166	...	N06601	Annealed	
13	60Ni-23Cr-Fe	Smls. pipe & tube	SB-167	...	N06601	Annealed	
14	60Ni-23Cr-Fe	Plate, sheet, strip	SB-168	...	N06601	Annealed	
15	52Ni-22Cr-13Co-9Mo	Bar, rod	SB-166	...	N06617	Annealed	
16	52Ni-22Cr-13Co-9Mo	Smls. pipe & tube	SB-167	...	N06617	Annealed	
17	52Ni-22Cr-13Co-9Mo	Plate, sheet, strip	SB-168	...	N06617	Annealed	
18	52Ni-22Cr-13Co-9Mo	Forgings	SB-564	...	N06617	Annealed	
19	52Ni-22Cr-13Co-9Mo	Wld. tube	SB-626	...	N06617	Solution ann.	
20	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet, strip	SB-443	2	N06625	Solution ann.	
21	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	2	N06625	Hot rolled/sol. ann.	
22	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe & tube	SB-444	2	N06625	Solution ann.	
23	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	2	N06625	Solution ann.	
24	60Ni-22Cr-9Mo-3.5Cb	Smls. & wld. fittings	SB-366	...	N06625	Annealed	
25	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1	N06625	Annealed	
(25)	26	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1	N06625	Annealed
	27	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet, strip	SB-443	1	N06625	Annealed
	28	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet	SB-443	1	N06625	Hot rolled/ann.
	29	60Ni-22Cr-9Mo-3.5Cb	Plate, sheet, strip	SB-443	1	N06625	Annealed
	30	60Ni-22Cr-9Mo-3.5Cb	Smls. pipe	SB-444	1	N06625	Annealed
(25)	31	60Ni-22Cr-9Mo-3.5Cb	Bar	SB-446	1	N06625	Annealed
	32	60Ni-22Cr-9Mo-3.5Cb	Forgings	SB-564	1	N06625	Annealed
	33	60Ni-22Cr-9Mo-3.5Cb	Wld. tube	SB-704	...	N06625	Annealed
	34	60Ni-22Cr-9Mo-3.5Cb	Wld. pipe	SB-705	...	N06625	Annealed
	35	Ni-Cr-Mo-W	Forgings	SB-564	...	N06686	Solution ann.
	36	Ni-Cr-Mo-W	Rod	SB-574	...	N06686	Solution ann.
	37	Ni-Cr-Mo-W	Plate, sheet, strip	SB-575	...	N06686	Solution ann.
	38	Ni-Cr-Mo-W	Wld. pipe	SB-619	...	N06686	Solution ann.
	39	Ni-Cr-Mo-W	Smls. pipe & tube	SB-622	...	N06686	Solution ann.
	40	Ni-Cr-Mo-W	Wld. tube	SB-626	...	N06686	Solution ann.
	41	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Hot worked/ann.
	42	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold worked/ann.
	43	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Hot worked/ann.
	44	58Ni-29Cr-9Fe	Smls. tube	SB-163	...	N06690	Annealed
	45	58Ni-29Cr-9Fe	Bar, rod	SB-166	...	N06690	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	80	35	...
2	...	80	35	...
3	...	80	35	...
4	≤ 5	80	35	...
5	...	80	35	...
6	...	80	40	...
7	> 3	85	35	...
8	...	85	35	...
9	$\frac{1}{2} < t \leq 3$	90	40	...
10	$\frac{1}{4} \leq t \leq \frac{1}{2}$	95	45	...
11	≤ 3 O.D.	80	30	...
12	...	80	30	...
13	...	80	30	...
14	...	80	30	...
15	...	95	35	...
16	...	95	35	...
17	...	95	35	...
18	...	95	35	...
19	...	95	35	...
20	...	100	40	...
21	...	100	40	...
22	...	100	40	...
23	...	100	40	...
24	...	110	50	...
25	$4 < t \leq 10$	110	50	...
26	$4 < t \leq 10$	110	50	...
27	...	110	55	...
28	≤ 2.75	110	55	...
29	...	120	60	...
30	...	120	60	...
31	≤ 4	120	60	...
32	≤ 4	120	60	...
33	...	120	60	...
34	...	120	60	...
35	...	100	45	...
36	...	100	45	...
37	...	100	45	...
38	≤ 8	100	45	...
39	...	100	45	...
40	$\leq 3\frac{1}{2}$	100	45	...
41	> 5 O.D.	75	25	...
42	> 5 O.D.	85	30	...
43	≤ 5 O.D.	85	30	...
44	...	85	35	...
45	...	85	35	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
2	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
3	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
4	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
5	35.0	32.8	32.0	31.5	31.2	30.9	30.7	30.5	30.3
6	40.0	...	36.6	...	35.6	...	35.1	...	34.7
7	35.0	33.8	33.2	32.7	32.3	32.1	31.9	31.9	31.9
8	35.0	33.8	33.2	32.7	32.3	32.1	31.9	31.9	31.9
9	40.0	...	38.0	...	37.0	...	36.4	...	36.4
10	45.0	...	42.8	...	41.7	...	41.0	...	40.9
11	30.0	27.8	26.8	25.8	24.9	24.0	23.3	22.7	22.1
12	30.0	27.8	26.8	25.8	24.9	24.0	23.3	22.7	22.1
13	30.0	27.8	26.8	25.8	24.9	24.0	23.3	22.7	22.1
14	30.0	27.8	26.8	25.8	24.9	24.0	23.3	22.7	22.1
15	35.0	...	31.1	...	28.9	...	27.1	...	25.9
16	35.0	...	31.1	...	28.9	...	27.1	...	25.9
17	35.0	...	31.1	...	28.9	...	27.1	...	25.9
18	35.0	...	31.1	...	28.9	...	27.1	...	25.9
19	35.0	...	31.1	...	28.9	...	27.1	...	25.9
20	40.0	37.7	36.4	35.2	34.2	33.2	32.4	31.7	31.1
21	40.0	38.0	36.9	36.0	35.1	34.3	33.7	33.0	32.5
22	40.0	37.7	36.4	35.2	34.2	33.2	32.4	31.7	31.1
23	40.0	37.7	36.4	35.2	34.2	33.2	32.4	31.7	31.1
24	50.0	45.6	43.3	41.3	39.7	38.3	37.3	36.4	35.8
25	50.0	45.6	43.3	41.3	39.7	38.3	37.3	36.4	35.8
26	50.0	45.6	43.3	41.3	39.7	38.3	37.3	36.4	35.8
27	55.0	50.1	47.6	45.5	43.7	42.2	41.0	40.1	39.4
28	55.0	53.8	53.0	52.2	51.4	50.7	49.9	49.2	48.5
29	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
30	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
31	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
32	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
33	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
34	60.0	54.7	51.9	49.6	47.6	46.0	44.7	43.7	43.0
35	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
36	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
37	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
38	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
39	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
40	45.0	39.5	37.3	36.0	35.1	34.3	33.7	33.1	32.5
41	25.0	23.6	22.7	22.0	21.3	20.8	20.4	20.1	19.9
42	30.0	28.3	27.3	26.4	25.6	25.0	24.5	24.1	23.9
43	30.0	28.3	27.3	26.4	25.6	25.0	24.5	24.1	23.9
44	35.0	32.9	31.7	30.7	29.8	29.1	28.6	28.2	27.9
45	35.0	32.9	31.7	30.7	29.8	29.1	28.6	28.2	27.9

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
2	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
3	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
4	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
5	30.1	29.9	29.7	29.4	29.1	28.7	28.1	27.3	26.1	25.3
6	...	34.2	33.9	33.6	33.2	32.8	...	...	...	...
7	31.9	31.8	31.7	31.5	31.2	30.7	30.1	29.5	28.9	28.1
8	31.9	31.8	31.7	31.5	31.2	30.7	30.1	29.5	28.9	28.1
9	...	36.4	36.1	35.9	35.4	34.8	...	...	...	...
10	...	40.9	40.6	40.4	39.8	39.1	...	...	...	...
11	21.7	21.3	21.1	20.9	20.8	20.7	20.6	20.6	20.6	20.6
12	21.7	21.3	21.1	20.9	20.8	20.7	20.6	20.6	20.6	20.6
13	21.7	21.3	21.1	20.9	20.8	20.7	20.6	20.6	20.6	20.6
14	21.7	21.3	21.1	20.9	20.8	20.7	20.6	20.6	20.6	20.6
15	...	25.0	24.6	24.3	24.1	23.8	23.7	23.5	23.4	23.3
16	...	25.0	24.6	24.3	24.1	23.8	23.7	23.5	23.4	23.3
17	...	25.0	24.6	24.3	24.1	23.8	23.7	23.5	23.4	23.3
18	...	25.0	24.6	24.3	24.1	23.8	23.7	23.5	23.4	23.3
19	...	25.0	24.6	24.3	24.1	23.8	23.7	23.5	23.4	23.3
20	30.5	30.1	29.7	29.4	29.2	29.1	29.0	28.9	28.8	28.8
21	32.0	31.5	31.2	30.8	30.5	30.2	30.0	29.7	29.6	29.4
22	30.5	30.1	29.7	29.4	29.2	29.1	29.0	28.9	28.8	28.8
23	30.5	30.1	29.7	29.4	29.2	29.1	29.0	28.9	28.8	28.8
24	35.4	35.1	35.0	35.0	35.0	35.0	35.0	35.0	35.0	35.0
25	35.4	35.1	35.0	35.0	35.0	35.0	35.0	35.0	35.0	35.0
26	35.4	35.1	35.0	35.0	35.0	35.0	35.0	35.0	35.0	35.0
27	38.9	38.6	38.5	38.5	38.5	38.5	38.5	38.5	38.5	38.5
28	47.9	47.2	46.6	46.1	45.6	45.2	44.8	44.5	44.2	43.9
29	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
30	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
31	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
32	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
33	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
34	42.5	42.2	42.1	42.1	42.1	42.1	42.1	42.1	42.1	42.1
35	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
36	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
37	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
38	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
39	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
40	31.8	31.2	30.6	30.2	29.9	29.8	29.8	29.8	29.8	29.4
41	19.8	19.7	19.7	19.7	19.7	19.7	19.6	19.6	19.5	19.4
42	23.7	23.6	23.6	23.6	23.6	23.6	23.6	23.5	23.4	23.3
43	23.7	23.6	23.6	23.6	23.6	23.6	23.6	23.5	23.4	23.3
44	27.7	27.6	27.5	27.5	27.5	27.5	27.5	27.5	27.4	27.1
45	27.7	27.6	27.5	27.5	27.5	27.5	27.5	27.5	27.4	27.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
2	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
3	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
4	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
5	24.3	23.2	21.9	20.5	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	27.4	26.6	25.6	24.4	...	...	...	...	...	...	...	...	...
8	27.4	26.6	25.6	24.4	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	28.7	28.7	28.6	28.5	28.3	28.1	27.8	27.4	26.8	26.1	25.3	24.3	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	28.7	28.7	28.6	28.5	28.3	28.1	27.8	27.4	26.8	26.1	25.3	24.3	...
23	28.7	28.7	28.6	28.5	28.3	28.1	27.8	27.4	26.8	26.1	25.3	24.3	...
24	35.0	35.0	35.0	35.0	35.0	35.0	35.0	34.5	33.5	32.2	30.6	28.6	...
25	35.0	35.0	35.0	35.0	35.0	35.0	35.0	34.5	33.5	32.2	30.6	28.6	...
26	35.0	35.0	35.0	35.0	35.0	35.0	35.0	34.5	33.5	32.2	30.6	28.6	...
27	38.5	38.5	38.5	38.5	38.5	38.5	38.5	38.0	36.8	35.4	33.6	31.5	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
30	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
31	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
32	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
33	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
34	42.1	42.1	42.1	42.1	42.1	42.1	42.1	41.4	40.2	38.6	36.7	34.4	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	58Ni-29Cr-9Fe	Plate, sheet, strip	SB-168	...	N06690	Annealed
2	58Ni-29Cr-9Fe	Forgings	SB-564	...	N06690	Annealed
3	58Ni-29Cr-9Fe	Smls. pipe & tube	SB-167	...	N06690	Cold worked/ann.
4	58Ni-29Cr-9Fe	Smls. tube	SB-163	...	N06690	Annealed
5	49Ni-25Cr-18Fe-6Mo	Bolting	SB-581	...	N06975	Solution ann.
6	49Ni-25Cr-18Fe-6Mo	Plate, sheet, strip	SB-582	...	N06975	Solution ann.
7	49Ni-25Cr-18Fe-6Mo	Wld. pipe	SB-619	...	N06975	Solution ann.
8	49Ni-25Cr-18Fe-6Mo	Smls. pipe & tube	SB-622	...	N06975	Solution ann.
9	49Ni-25Cr-18Fe-6Mo	Wld. tube	SB-626	...	N06975	Solution ann.
10	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
11	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
12	47Ni-22Cr-20Fe-7Mo	Smls. & wld. fittings	SB-366	...	N06985	Annealed
13	47Ni-22Cr-20Fe-7Mo	Rod	SB-581	...	N06985	Annealed
14	47Ni-22Cr-20Fe-7Mo	Plate, sheet, strip	SB-582	...	N06985	Annealed
15	47Ni-22Cr-20Fe-7Mo	Wld. pipe	SB-619	...	N06985	Annealed
16	47Ni-22Cr-20Fe-7Mo	Smls. pipe & tube	SB-622	...	N06985	Annealed
17	47Ni-22Cr-20Fe-7Mo	Wld. tube	SB-626	...	N06985	Annealed
18	35Ni-35Fe-20Cr-Cb	Forgings	SB-462	...	N08020	Annealed
19	35Ni-35Fe-20Cr-Cb	Plate	SB-463	...	N08020	Annealed
20	35Ni-35Fe-20Cr-Cb	Bar	SB-473	...	N08020	Annealed
21	35Ni-35Fe-20Cr-Cb	Smls. pipe & tube	SB-729	...	N08020	Annealed
22	35Ni-35Fe-20Cr-Cb	Wld. pipe	SB-464	...	N08020	Wld. ann.
23	35Ni-35Fe-20Cr-Cb	Wld. tube	SB-468	...	N08020	Wld. ann.
24	35Ni-35Fe-20Cr-Cb	Smls. & wld. fittings	SB-366	...	N08020	Annealed
25	37Ni-33Fe-23Cr-4Mo-Cu	Wld. pipe	SB-464	...	N08024	Wld. ann.
26	37Ni-33Fe-23Cr-4Mo-Cu	Wld. tube	SB-468	...	N08024	Wld. ann.
27	35Ni-30Fe-24Cr-6Mo-Cu	Wld. pipe	SB-464	...	N08026	Wld. ann.
28	35Ni-30Fe-24Cr-6Mo-Cu	Wld. tube	SB-468	...	N08026	Wld. ann.
29	31Ni-31Fe-29Cr-Mo	Smls. tube	SB-668	...	N08028	Annealed
30	31Ni-31Fe-29Cr-Mo	Plate, sheet, strip	SB-709	...	N08028	Annealed
31	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. & wld. fittings	SB-366	...	N08031	Solution ann.
32	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Forgings	SB-564	...	N08031	Solution ann.
33	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Rod	SB-581	...	N08031	Solution ann.
34	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. pipe	SB-619	...	N08031	Solution ann.
35	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Smls. pipe & tube	SB-622	...	N08031	Solution ann.
36	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08031	Solution ann.
37	31Ni-33Fe-27Cr-6.5Mo-Cu-N	Wld. tube	SB-626	...	N08031	Solution ann.
38	37Ni-33Fe-25Cr	Condenser tube	SB-163	...	N08120	Solution ann.
39	37Ni-33Fe-25Cr	Smls. & wld. fittings	SB-366	...	N08120	Solution ann.
40	37Ni-33Fe-25Cr	Smls. pipe & tube	SB-407	...	N08120	Solution ann.
41	37Ni-33Fe-25Cr	Bar, rod	SB-408	...	N08120	Solution ann.
42	37Ni-33Fe-25Cr	Plate, sheet, strip	SB-409	...	N08120	Solution ann.
43	37Ni-33Fe-25Cr	Wld. pipe	SB-514	...	N08120	Solution ann.
44	37Ni-33Fe-25Cr	Wld. tube	SB-515	...	N08120	Solution ann.
45	37Ni-33Fe-25Cr	Forgings	SB-564	...	N08120	Solution ann.

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	85	35	...
2	...	85	35	...
3	≤5 O.D.	85	35	...
4	...	85	40	...
5	...	85	32	...
6	...	85	32	...
7	...	85	32	...
8	...	85	32	...
9	...	85	32	...
10	> ³ / ₄	85	30	...
11	> ³ / ₄	85	30	...
12	...	90	35	...
13	≤ ³ / ₄	90	35	...
14	≤ ³ / ₄	90	35	...
15	...	90	35	...
16	...	90	35	...
17	...	90	35	...
18	...	80	35	...
19	...	80	35	...
20	...	80	35	...
21	...	80	35	...
22	...	80	35	...
23	...	80	35	...
24	...	85	40	...
25	...	80	35	...
26	...	80	35	...
27	...	80	35	...
28	...	80	35	...
29	...	73	31	...
30	...	73	31	...
31	...	94	40	...
32	...	94	40	...
33	...	94	40	...
34	...	94	40	...
35	...	94	40	...
36	...	94	40	...
37	...	94	40	...
38	...	90	40	...
39	...	90	40	...
40	...	90	40	...
41	...	90	40	...
42	...	90	40	...
43	...	90	40	...
44	...	90	40	...
45	...	90	40	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	35.0	32.9	31.7	30.7	29.8	29.1	28.6	28.2	27.9
2	35.0	32.9	31.7	30.7	29.8	29.1	28.6	28.2	27.9
3	35.0	33.0	31.8	30.8	29.9	29.1	28.5	28.1	27.8
4	40.0	...	36.2	...	34.1	...	32.7	...	31.9
5	32.0	30.2	29.3	28.5	27.7	27.0	26.2	25.5	24.8
6	32.0	30.2	29.3	28.5	27.7	27.0	26.2	25.5	24.8
7	32.0	30.2	29.3	28.5	27.7	27.0	26.2	25.5	24.8
8	32.0	30.2	29.3	28.5	27.7	27.0	26.2	25.5	24.8
9	32.0	30.2	29.3	28.5	27.7	27.0	26.2	25.5	24.8
10	30.0	28.0	26.7	25.5	24.3	23.3	22.4	21.5	20.8
11	30.0	28.0	26.7	25.5	24.3	23.3	22.4	21.5	20.8
12	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
13	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
14	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
15	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
16	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
17	35.0	32.7	31.2	29.7	28.4	27.2	26.1	25.1	24.3
18	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
19	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
20	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
21	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
22	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
23	35.0	32.0	30.9	30.2	29.6	29.0	28.4	27.8	27.3
24	40.0	36.6	35.4	34.5	33.8	33.1	32.5	31.8	31.2
25	35.0	32.2	30.9	29.8	28.8	28.0	27.2	26.3	25.5
26	35.0	32.2	30.9	29.8	28.8	28.0	27.2	26.3	25.5
27	35.0	32.6	31.1	29.7	28.4	27.3	26.3	25.3	24.4
28	35.0	32.6	31.1	29.7	28.4	27.3	26.3	25.3	24.4
29	31.0	29.4	28.4	27.4	26.5	25.6	24.8	23.9	23.2
30	31.0	29.4	28.4	27.4	26.5	25.6	24.8	23.9	23.2
31	40.0	...	33.0	...	29.7	...	27.4	...	25.9
32	40.0	...	33.0	...	29.7	...	27.4	...	25.9
33	40.0	...	33.0	...	29.7	...	27.4	...	25.9
34	40.0	...	33.0	...	29.7	...	27.4	...	25.9
35	40.0	...	33.0	...	29.7	...	27.4	...	25.9
36	40.0	...	33.0	...	29.7	...	27.4	...	25.9
37	40.0	...	33.0	...	29.7	...	27.4	...	25.9
38	40.0	...	35.3	...	32.3	...	29.9	...	27.9
39	40.0	...	35.3	...	32.3	...	29.9	...	27.9
40	40.0	...	35.3	...	32.3	...	29.9	...	27.9
41	40.0	...	35.3	...	32.3	...	29.9	...	27.9
42	40.0	...	35.3	...	32.3	...	29.9	...	27.9
43	40.0	...	35.3	...	32.3	...	29.9	...	27.9
44	40.0	...	35.3	...	32.3	...	29.9	...	27.9
45	40.0	...	35.3	...	32.3	...	29.9	...	27.9

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	27.7	27.6	27.5	27.5	27.5	27.5	27.5	27.5	27.4	27.1
2	27.7	27.6	27.5	27.5	27.5	27.5	27.5	27.5	27.4	27.1
3	27.7	27.6	27.5	27.5	27.5	27.5	27.5	27.4	27.3	27.2
4	...	31.5	31.5	31.5	31.5	31.5	...	...	...	...
5	24.1	23.4	22.9	22.5	22.2	22.0	21.9	21.9	21.9	21.9
6	24.1	23.4	22.9	22.5	22.2	22.0	21.9	21.9	21.9	21.9
7	24.1	23.4	22.9	22.5	22.2	22.0	21.9	21.9	21.9	21.9
8	24.1	23.4	22.9	22.5	22.2	22.0	21.9	21.9	21.9	21.9
9	24.1	23.4	22.9	22.5	22.2	22.0	21.9	21.9	21.9	21.9
10	20.2	19.7	19.2	18.8	18.4	18.0	17.6	17.3	17.0	16.7
11	20.2	19.7	19.2	18.8	18.4	18.0	17.6	17.3	17.0	16.7
12	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
13	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
14	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
15	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
16	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
17	23.6	23.0	22.4	21.9	21.4	21.0	20.6	20.2	19.8	19.5
18	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
19	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
20	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
21	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
22	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
23	26.8	26.5	26.2	26.0	25.8	25.2	...	...	...	...
24	30.7	30.3	30.0	29.8	29.4	28.8	...	...	...	...
25	24.8	24.0	23.3	22.7	22.2	21.8	21.5	21.3	21.0	20.7
26	24.8	24.0	23.3	22.7	22.2	21.8	21.5	21.3	21.0	20.7
27	23.7	23.0	22.3	21.8	21.3	20.9	20.6	20.3	20.1	19.9
28	23.7	23.0	22.3	21.8	21.3	20.9	20.6	20.3	20.1	19.9
29	22.4	21.7	21.0	20.3	19.7	19.1	18.6	18.1	17.6	17.2
30	22.4	21.7	21.0	20.3	19.7	19.1	18.6	18.1	17.6	17.2
31	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
32	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
33	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
34	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
35	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
36	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
37	...	24.7	24.1	23.6	23.2	22.8	22.4	22.2	...	...
38	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
39	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
40	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
41	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
42	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
43	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
44	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4
45	...	26.5	26.0	25.5	25.2	24.9	24.7	24.6	24.5	24.4

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	26Ni-43Fe-22Cr-5Mo	Wld. pipe	SB-619	...	N08320	Solution ann.
2	26Ni-43Fe-22Cr-5Mo	Plate, sheet, strip	SB-620	...	N08320	Solution ann.
3	26Ni-43Fe-22Cr-5Mo	Rod	SB-621	...	N08320	Solution ann.
4	26Ni-43Fe-22Cr-5Mo	Smls. pipe & tube	SB-622	...	N08320	Solution ann.
5	26Ni-43Fe-22Cr-5Mo	Wld. tube	SB-626	...	N08320	Solution ann.
6	35Ni-19Cr-1 $\frac{1}{4}$ Si	Bar	SB-511	...	N08330	...
7	35Ni-19Cr-1 $\frac{1}{4}$ Si	Pipe	SB-535	...	N08330	...
8	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate	SB-536	...	N08330	...
9	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. fittings	SB-366	...	N08330	Annealed
10	35Ni-19Cr-1 $\frac{1}{4}$ Si	Smls. & wld. pipe	SB-535	...	N08330	Annealed
11	35Ni-19Cr-1 $\frac{1}{4}$ Si	Plate, sheet, strip	SB-536	...	N08330	Annealed
12	35Ni-19Cr-1 $\frac{1}{4}$ Si	Wld. pipe	SB-710	...	N08330	Annealed
13	35Ni-23Cr-7.5Mo-N	Plate, sheet, strip	SB-625	...	N08354	Solution ann.
14	35Ni-23Cr-7.5Mo-N	Bar, wire	SB-649	...	N08354	Solution ann.
15	35Ni-23Cr-7.5Mo-N	Wld. pipe	SB-673	...	N08354	Solution ann.
16	35Ni-23Cr-7.5Mo-N	Wld. tube	SB-674	...	N08354	Solution ann.
17	35Ni-23Cr-7.5Mo-N	Smls. pipe & tube	SB-677	...	N08354	Solution ann.
18	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-462	...	N08367	Solution ann.
19	46Fe-24Ni-21Cr-6Mo-N	Forgings	SB-564	...	N08367	Solution ann.
20	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
21	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
22	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
23	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
24	46Fe-24Ni-21Cr-6Mo-N	Bar, rod, wire	SB-691	...	N08367	Solution ann.
25	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.
26	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-675	...	N08367	Solution ann.
27	46Fe-24Ni-21Cr-6Mo-N	Wld. tube	SB-676	...	N08367	Solution ann.
28	46Fe-24Ni-21Cr-6Mo-N	Plate, sheet, strip	SB-688	...	N08367	Solution ann.
29	46Fe-24Ni-21Cr-6Mo-N	Smls. pipe & tube	SB-690	...	N08367	Solution ann.
30	46Fe-24Ni-21Cr-6Mo-N	Wld. pipe	SB-804	...	N08367	Solution ann.
31	46Fe-24Ni-21Cr-6Mo-N	Castings	SA-351	CN3MN	J94651	Solution ann.
32	25Ni-47Fe-21Cr-5Mo	Plate, sheet, strip	SB-599	...	N08700	Solution ann.
33	25Ni-47Fe-21Cr-5Mo	Bar, wire	SB-672	...	N08700	Solution ann.
34	32Ni-45Fe-20Cr-Cb	Castings	SA-351	CT15C	...	As cast
35	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08800	Annealed
36	33Ni-42Fe-21Cr	Smls. & wld. fittings	SB-366	...	N08800	Annealed
37	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08800	Annealed
38	33Ni-42Fe-21Cr	Bar	SB-408	...	N08800	Annealed
39	33Ni-42Fe-21Cr	Plate	SB-409	...	N08800	Annealed
40	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08800	Annealed
41	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08800	Annealed
42	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08800	Annealed
43	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08800	Annealed
44	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08800	Cold worked
45	32Ni-44Fe-21Cr	Smls. tube	SB-163	...	N08801	Ann./stabilized

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	75	28	...
2	...	75	28	...
3	...	75	28	...
4	...	75	28	...
5	...	75	28	...
6	...	70	30	...
7	...	70	30	...
8	...	70	30	...
9	...	70	30	...
10	...	70	30	...
11	...	70	30	...
12	...	70	30	...
13	...	93	43	...
14	...	93	43	...
15	...	93	43	...
16	...	93	43	...
17	...	93	43	...
18	...	95	45	...
19	...	95	45	...
20	$> \frac{3}{16}$	95	45	...
21	$> \frac{3}{16}$	95	45	...
22	$> \frac{3}{16}$	95	45	...
23	$> \frac{3}{16}$	95	45	...
24	...	95	45	...
25	$> \frac{3}{16}$	95	45	...
26	$\leq \frac{3}{16}$	100	45	...
27	$\leq \frac{3}{16}$	100	45	...
28	$\leq \frac{3}{16}$	100	45	...
29	$\leq \frac{3}{16}$	100	45	...
30	$\leq \frac{3}{16}$	100	45	...
31	...	80	38	...
32	...	80	35	...
33	...	80	35	...
34	...	63	25	...
35	...	75	30	...
36	...	75	30	...
37	...	75	30	...
38	...	75	30	...
39	...	75	30	...
40	...	75	30	...
41	...	75	30	...
42	...	75	30	...
43	...	75	40	...
44	...	83	47	...
45	...	65	25	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	28.0	26.7	25.9	25.2	24.5	23.8	23.1	22.4	21.8
2	28.0	26.7	25.9	25.2	24.5	23.8	23.1	22.4	21.8
3	28.0	26.7	25.9	25.2	24.5	23.8	23.1	22.4	21.8
4	28.0	26.7	25.9	25.2	24.5	23.8	23.1	22.4	21.8
5	28.0	26.7	25.9	25.2	24.5	23.8	23.1	22.4	21.8
6	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
7	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
8	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
9	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
10	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
11	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
12	30.0	27.7	26.5	25.5	24.7	23.9	23.2	22.6	22.0
13	42.8	...	36.5	...	33.1	...	30.8	...	29.4
14	42.8	...	36.5	...	33.1	...	30.8	...	29.4
15	42.8	...	36.5	...	33.1	...	30.8	...	29.4
16	42.8	...	36.5	...	33.1	...	30.8	...	29.4
17	42.8	...	36.5	...	33.1	...	30.8	...	29.4
18	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
19	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
20	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
21	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
22	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
23	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
24	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
25	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
26	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
27	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
28	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
29	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
30	45.0	41.3	39.3	37.4	35.7	34.2	32.9	31.8	30.8
31	38.0	34.3	32.0	30.0	28.2	26.6	25.4	24.3	23.5
32	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
33	35.0	33.1	31.5	29.9	28.5	27.4	26.6	26.1	25.7
34	25.0	24.1	23.6	23.2	22.9	22.7	22.4	22.1	21.8
35	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
36	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
37	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
38	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
39	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
40	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
41	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
42	30.0	28.5	27.7	27.1	26.6	26.2	25.8	25.5	25.1
43	40.0	...	37.0	...	35.5	...	34.4	...	33.5
44	47.0	...	43.4	...	41.7	...	40.4	...	39.5
45	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)										
1	21.2	20.7	20.2	19.8	19.4	19.1	...	...	...	...
2	21.2	20.7	20.2	19.8	19.4	19.1	...	...	...	...
3	21.2	20.7	20.2	19.8	19.4	19.1	...	...	...	...
4	21.2	20.7	20.2	19.8	19.4	19.1	...	...	...	...
5	21.2	20.7	20.2	19.8	19.4	19.1	...	...	...	...
6	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
7	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
8	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
9	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
10	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
11	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
12	21.5	21.0	20.6	20.1	19.7	19.3	18.9	18.5	18.2	17.9
13	...	28.3	27.9	27.4	27.0	26.5	...	...	...	...
14	...	28.3	27.9	27.4	27.0	26.5	...	...	...	...
15	...	28.3	27.9	27.4	27.0	26.5	...	...	...	...
16	...	28.3	27.9	27.4	27.0	26.5	...	...	...	...
17	...	28.3	27.9	27.4	27.0	26.5	...	...	...	...
18	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
19	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
20	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
21	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
22	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
23	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
24	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
25	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
26	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
27	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
28	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
29	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
30	29.9	29.1	28.5	27.9	27.4	27.0	26.6	26.2	...	...
31	22.9	22.4	22.0	21.8	21.5	21.4	21.2	21.1	21.1	21.1
32	25.3	24.7	23.8	...	...	...	...	...	...	...
33	25.3	24.7	23.8	...	...	...	...	...	...	...
34	21.5	21.2	20.9	20.6	20.3	19.9	19.6	19.3	19.0	18.8
35	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
36	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
37	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
38	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
39	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
40	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
41	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
42	24.8	24.5	24.1	23.8	23.5	23.2	22.9	22.7	22.4	22.1
43	...	32.6	32.2	31.8	31.4	31.0	...	...	...	...
44	...	38.7	38.7	...	...	...	...	...	...	...
45	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
7	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
8	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
9	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
10	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
11	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
12	17.6	17.3	16.9	16.4	16.0	15.4	14.8	14.2	13.5	12.7	11.8	10.8	9.8
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
36	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
37	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
38	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
39	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
40	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
41	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
42	21.8	21.2	20.4	19.6	18.6	17.5	16.2	14.7	13.0	11.1	...	...	...
43	29.0	28.2	27.3	26.1	24.8	23.3	21.6	19.6	17.3	14.8	...	...	...
44	34.1	33.1	32.0	30.7	29.2	27.4	25.3	23.0	20.4	17.4	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	32Ni-44Fe-21Cr	Smls. pipe & tube	SB-407	...	N08801	Ann./stabilized
2	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08810	Annealed
3	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08810	Annealed
4	33Ni-42Fe-21Cr	Bar	SB-408	...	N08810	Annealed
5	33Ni-42Fe-21Cr	Plate	SB-409	...	N08810	Annealed
6	33Ni-42Fe-21Cr	Wld. pipe	SB-514	...	N08810	Annealed
7	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08810	Annealed
8	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08810	Annealed
(25) 9	42Fe-33Ni-21Cr	Forgings	SA-182	FNIC10	N08810	...
(25) 10	42Fe-33Ni-21Cr	Smls. tube	SA-213	800H	N08810	...
(25) 11	42Fe-33Ni-21Cr	Plate	SA-240	800H	N08810	...
(25) 12	42Fe-33Ni-21Cr	Wld. tube	SA-249	800H	N08810	...
(25) 13	42Fe-33Ni-21Cr	Bar	SA-276	800H	N08810	...
(25) 14	42Fe-33Ni-21Cr	Smls. pipe	SA-312	800H	N08810	...
(25) 15	42Fe-33Ni-21Cr	Wld. pipe	SA-312	800H	N08810	...
(25) 16	42Fe-33Ni-21Cr	Wld. pipe	SA-358	800H	N08810	...
(25) 17	42Fe-33Ni-21Cr	Bar	SA-479	800H	N08810	...
(25) 18	42Fe-33Ni-21Cr	Wld. tube	SA-688	800H	N08810	...
(25) 19	42Fe-33Ni-21Cr	Forgings	SA-965	FNIC10	N08810	...
20	33Ni-42Fe-21Cr	Smls. tube	SB-163	...	N08811	Annealed
21	33Ni-42Fe-21Cr	Smls. pipe & tube	SB-407	...	N08811	Annealed
22	33Ni-42Fe-21Cr	Bar	SB-408	...	N08811	Annealed
23	33Ni-42Fe-21Cr	Plate	SB-409	...	N08811	Annealed
24	33Ni-42Fe-21Cr	Wld. tube	SB-515	...	N08811	Annealed
25	33Ni-42Fe-21Cr	Forgings	SB-564	...	N08811	Annealed
26	42Ni-21.5Cr-3Mo-2.3Cu	Smls. tube	SB-163	...	N08825	Annealed
27	42Ni-21.5Cr-3Mo-2.3Cu	Smls. & wld. fittings	SB-366	...	N08825	Annealed
28	42Ni-21.5Cr-3Mo-2.3Cu	Smls. pipe & tube	SB-423	...	N08825	Cold worked/ann.
29	42Ni-21.5Cr-3Mo-2.3Cu	Plate	SB-424	...	N08825	Annealed
30	42Ni-21.5Cr-3Mo-2.3Cu	Bar, rod	SB-425	...	N08825	Annealed
31	42Ni-21.5Cr-3Mo-2.3Cu	Forgings	SB-564	...	N08825	Annealed
32	42Ni-21.5Cr-3Mo-2.3Cu	Wld. tube	SB-704	...	N08825	Annealed
33	42Ni-21.5Cr-3Mo-2.3Cu	Wld. pipe	SB-705	...	N08825	Annealed
34	44Fe-25Ni-21Cr-Mo	Forgings	SA-182	...	N08904	Annealed
35	44Fe-25Ni-21Cr-Mo	Smls. tube	SA-213	...	N08904	Annealed
36	44Fe-25Ni-21Cr-Mo	Plate, sheet, strip	SA-240	...	N08904	Annealed
37	44Fe-25Ni-21Cr-Mo	Wld. tube	SA-249	...	N08904	Annealed
38	44Fe-25Ni-21Cr-Mo	Smls. & wld. pipe	SA-312	...	N08904	Annealed
39	44Fe-25Ni-21Cr-Mo	Fittings	SA-403	...	N08904	Annealed
40	44Fe-25Ni-21Cr-Mo	Bar	SA-479	...	N08904	Annealed
41	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SB-625	...	N08925	Annealed
42	25Ni-20Cr-6Mo-Cu-N	Bar, wire	SB-649	...	N08925	Annealed
43	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SB-673	...	N08925	Annealed
44	25Ni-20Cr-6Mo-Cu-N	Wld. tube	SB-674	...	N08925	Annealed
45	25Ni-20Cr-6Mo-Cu-N	Smls. pipe & tube	SB-677	...	N08925	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	65	25	...
2	...	65	25	...
3	...	65	25	...
4	...	65	25	...
5	...	65	25	...
6	...	65	25	...
7	...	65	25	...
8	...	65	25	...
9	...	65	25	...
10	...	65	25	...
11	...	65	25	...
12	...	65	25	...
13	...	65	25	...
14	...	65	25	...
15	...	65	25	...
16	...	65	25	...
17	...	65	25	...
18	...	65	25	...
19	...	65	25	...
20	...	65	25	...
21	...	65	25	...
22	...	65	25	...
23	...	65	25	...
24	...	65	25	...
25	...	65	25	...
26	...	85	35	...
27	...	85	35	...
28	...	85	35	...
29	...	85	35	...
30	...	85	35	...
31	...	85	35	...
32	...	85	35	...
33	...	85	35	...
34	...	71	31	...
35	...	71	31	...
36	...	71	31	...
37	...	71	31	...
38	...	71	31	...
39	...	71	31	...
40	...	71	31	...
41	...	87	43	...
42	...	87	43	...
43	...	87	43	...
44	...	87	43	...
45	...	87	43	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
2	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
3	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
4	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
5	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
6	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
7	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
8	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
9	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
10	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
11	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
12	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
13	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
14	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
15	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
16	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
17	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
18	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
19	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
20	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
21	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
22	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
23	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
24	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
25	25.0	23.8	23.0	22.3	21.7	21.0	20.4	19.8	19.3
26	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
27	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
28	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
29	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
30	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
31	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
32	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
33	35.0	33.0	32.1	31.2	30.5	29.7	29.1	28.4	27.8
34	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
35	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
36	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
37	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
38	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
39	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
40	31.0	26.8	25.1	23.8	22.7	21.7	20.8	19.9	19.0
41	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
42	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
43	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
44	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
45	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
2	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
3	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
4	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
5	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
6	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
7	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
8	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
9	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
10	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
11	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
12	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
13	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
14	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
15	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
16	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
17	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
18	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
19	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
20	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
21	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
22	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
23	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
24	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
25	18.8	18.3	17.9	17.4	17.1	16.7	16.4	16.1	15.8	15.5
26	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
27	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
28	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
29	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
30	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
31	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
32	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
33	27.2	26.7	26.3	26.0	25.7	25.6	25.4	25.3	25.1	24.8
34	18.4	17.8	17.4	17.1	...	...	...	...	...	...
35	18.4	17.8	17.4	17.1	...	...	...	...	...	...
36	18.4	17.8	17.4	17.1	...	...	...	...	...	...
37	18.4	17.8	17.4	17.1	...	...	...	...	...	...
38	18.4	17.8	17.4	17.1	...	...	...	...	...	...
39	18.4	17.8	17.4	17.1	...	...	...	...	...	...
40	18.4	17.8	17.4	17.1	...	...	...	...	...	...
41	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
42	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
43	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
44	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
45	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
3	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
4	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
5	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
6	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
7	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
8	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
9	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
10	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
11	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
12	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
13	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
14	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
15	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
16	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
17	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
18	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
19	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6 (25)
20	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
21	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
22	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
23	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
24	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
25	14.9	14.6	14.3	13.9	13.5	13.1	12.6	12.1	11.5	10.9	10.2	9.4	8.6
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
(25) 1	25Ni-20Cr-6Mo-Cu-N	Plate, sheet, strip	SA-240	...	N08925	...
(25) 2	25Ni-20Cr-6Mo-Cu-N	Bar	SA-276	...	N08925	...
(25) 3	25Ni-20Cr-6Mo-Cu-N	Bar	SA-479	...	N08925	...
(25) 4	25Ni-20Cr-6Mo-Cu-N	Wld. pipe	SA-312	...	N08925	...
(25) 5	25Ni-20Cr-6Mo-Cu-N	Smls. pipe	SA-312	...	N08925	...
(25) 6	25Ni-20Cr-6Mo-Cu-N	Smls. tube	SA-213	...	N08925	...
7	62Ni-28Mo-5Fe	Plate	SB-333	...	N10001	Annealed
8	62Ni-28Mo-5Fe	Smls. & wld. fittings	SB-366	...	N10001	Annealed
9	62Ni-28Mo-5Fe	Wld. pipe	SB-619	...	N10001	Solution ann.
10	62Ni-28Mo-5Fe	Smls. pipe & tube	SB-622	...	N10001	Solution ann.
11	62Ni-28Mo-5Fe	Wld. tube	SB-626	...	N10001	Solution ann.
12	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
13	62Ni-28Mo-5Fe	Rod	SB-335	...	N10001	Annealed
14	62Ni-28Mo-5Fe	Sheet, strip	SB-333	...	N10001	Annealed
15	70Ni-16Mo-7Cr-5Fe	Smls. & wld. fittings	SB-366	...	N10003	Annealed
16	70Ni-16Mo-7Cr-5Fe	Plate, sheet, strip	SB-434	...	N10003	Annealed
17	70Ni-16Mo-7Cr-5Fe	Rod	SB-573	...	N10003	Annealed
18	62Ni-25Mo-8Cr-2Fe	Smls. & wld. fittings	SB-366	...	N10242	Annealed
19	62Ni-25Mo-8Cr-2Fe	Plate, sheet, strip	SB-434	...	N10242	Annealed
20	62Ni-25Mo-8Cr-2Fe	Forgings	SB-564	...	N10242	Annealed
21	62Ni-25Mo-8Cr-2Fe	Rod	SB-573	...	N10242	Annealed
22	62Ni-25Mo-8Cr-2Fe	Wld. pipe	SB-619	...	N10242	Solution ann.
23	62Ni-25Mo-8Cr-2Fe	Smls. pipe & tube	SB-622	...	N10242	Solution ann.
24	62Ni-25Mo-8Cr-2Fe	Wld. tube	SB-626	...	N10242	Solution ann.
25	54Ni-16Mo-15Cr	Smls. & wld. fittings	SB-366	...	N10276	Solution ann.
26	54Ni-16Mo-15Cr	Forgings	SB-462	...	N10276	Solution ann.
27	54Ni-16Mo-15Cr	Forgings	SB-564	...	N10276	Solution ann.
28	54Ni-16Mo-15Cr	Rod	SB-574	...	N10276	Solution ann.
29	54Ni-16Mo-15Cr	Plate, sheet, strip	SB-575	...	N10276	Solution ann.
30	54Ni-16Mo-15Cr	Wld. pipe	SB-619	...	N10276	Solution ann.
31	54Ni-16Mo-15Cr	Smls. pipe & tube	SB-622	...	N10276	Solution ann.
32	54Ni-16Mo-15Cr	Wld. tube	SB-626	...	N10276	Solution ann.
33	62Ni-22Mo-15Cr	Smls. & wld. fittings	SB-366	...	N10362	Solution ann.
34	62Ni-22Mo-15Cr	Forgings	SB-462	...	N10362	Solution ann.
35	62Ni-22Mo-15Cr	Forgings	SB-564	...	N10362	Solution ann.
36	62Ni-22Mo-15Cr	Rod	SB-574	...	N10362	Solution ann.
37	62Ni-22Mo-15Cr	Plate, sheet, strip	SB-575	...	N10362	Solution ann.
38	62Ni-22Mo-15Cr	Wld. pipe	SB-619	...	N10362	Solution ann.
39	62Ni-22Mo-15Cr	Smls. pipe & tube	SB-622	...	N10362	Solution ann.
40	62Ni-22Mo-15Cr	Wld. tube	SB-626	...	N10362	Solution ann.
41	Ni-28Mo-3Fe-1.3Cr-0.25Al	Plate, sheet, strip	SB-333	...	N10629	Solution ann.
42	Ni-28Mo-3Fe-1.3Cr-0.25Al	Rod	SB-335	...	N10629	Solution ann.
43	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. & wld. fittings	SB-366	...	N10629	Solution ann.
44	Ni-28Mo-3Fe-1.3Cr-0.25Al	Forgings	SB-564	...	N10629	Solution ann.
45	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. pipe	SB-619	...	N10629	Solution ann.

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	87	43	...
2	...	87	43	...
3	...	87	43	...
4	...	87	43	...
5	...	87	43	...
6	...	87	43	...
7	...	100	45	...
8	...	100	45	...
9	...	100	45	...
10	...	100	45	...
11	...	100	45	...
12	$>1\frac{1}{2}$	100	46	...
13	$\frac{5}{16} < t \leq 1\frac{1}{2}$	115	46	...
14	...	115	50	...
15	...	100	40	...
16	...	100	40	...
17	...	100	40	...
18	...	105	45	...
19	...	105	45	...
20	...	105	45	...
21	...	105	45	...
22	...	105	45	...
23	...	105	45	...
24	...	105	45	...
25	...	100	41	...
26	...	100	41	...
27	...	100	41	...
28	...	100	41	...
29	...	100	41	...
30	...	100	41	...
31	...	100	41	...
32	...	100	41	...
33	...	105	45	...
34	...	105	45	...
35	...	105	45	...
36	...	105	45	...
37	...	105	45	...
38	...	105	45	...
39	...	105	45	...
40	...	105	45	...
41	...	110	51	...
42	...	110	51	...
43	...	110	51	...
44	...	110	51	...
45	...	110	51	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
2	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
3	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
4	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
5	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
6	43.0	37.0	34.8	33.2	31.9	30.8	29.6	28.5	27.5
7	45.0	42.2	40.8	39.6	38.6	37.7	36.9	36.2	35.6
8	45.0	42.2	40.8	39.6	38.6	37.7	36.9	36.2	35.6
9	45.0	42.2	40.8	39.6	38.6	37.7	36.9	36.2	35.6
10	45.0	42.2	40.8	39.6	38.6	37.7	36.9	36.2	35.6
11	45.0	42.2	40.8	39.6	38.6	37.7	36.9	36.2	35.6
12	46.0	43.1	41.7	40.5	39.4	38.5	37.7	37.0	36.4
13	46.0	43.1	41.7	40.5	39.4	38.5	37.7	37.0	36.4
14	50.0	46.9	45.3	44.0	42.8	41.9	41.0	40.2	39.6
15	40.0	37.8	36.3	34.9	33.7	32.6	31.7	30.9	30.2
16	40.0	37.8	36.3	34.9	33.7	32.6	31.7	30.9	30.2
17	40.0	37.8	36.3	34.9	33.7	32.6	31.7	30.9	30.2
18	45.0	...	42.3	...	39.2	...	37.0	...	35.9
19	45.0	...	42.3	...	39.2	...	37.0	...	35.9
20	45.0	...	42.3	...	39.2	...	37.0	...	35.9
21	45.0	...	42.3	...	39.2	...	37.0	...	35.9
22	45.0	...	42.3	...	39.2	...	37.0	...	35.9
23	45.0	...	42.3	...	39.2	...	37.0	...	35.9
24	45.0	...	42.3	...	39.2	...	37.0	...	35.9
25	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
26	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
27	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
28	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
29	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
30	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
31	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
32	41.0	38.8	37.3	35.9	34.5	33.2	32.0	30.9	29.8
33	45.0	...	40.1	...	36.7	...	34.1	...	32.1
34	45.0	...	40.1	...	36.7	...	34.1	...	32.1
35	45.0	...	40.1	...	36.7	...	34.1	...	32.1
36	45.0	...	40.1	...	36.7	...	34.1	...	32.1
37	45.0	...	40.1	...	36.7	...	34.1	...	32.1
38	45.0	...	40.1	...	36.7	...	34.1	...	32.1
39	45.0	...	40.1	...	36.7	...	34.1	...	32.1
40	45.0	...	40.1	...	36.7	...	34.1	...	32.1
41	51.0	...	47.1	...	44.4	...	42.2	...	40.5
42	51.0	...	47.1	...	44.4	...	42.2	...	40.5
43	51.0	...	47.1	...	44.4	...	42.2	...	40.5
44	51.0	...	47.1	...	44.4	...	42.2	...	40.5
45	51.0	...	47.1	...	44.4	...	42.2	...	40.5

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)										
1	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
2	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
3	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
4	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
5	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
6	26.6	25.9	25.5	25.3	25.3	25.3	...	...	...	...
7	35.0	34.6	34.1	33.8	33.4	33.2	...	...	...	...
8	35.0	34.6	34.1	33.8	33.4	33.2	...	...	...	...
9	35.0	34.6	34.1	33.8	33.4	33.2	...	...	...	...
10	35.0	34.6	34.1	33.8	33.4	33.2	...	...	...	...
11	35.0	34.6	34.1	33.8	33.4	33.2	...	...	...	...
12	35.8	35.3	34.9	34.5	34.2	33.9	...	...	...	...
13	35.8	35.3	34.9	34.5	34.2	33.9	...	...	...	...
14	38.9	38.4	37.9	37.5	37.2	36.9	...	...	...	...
15	29.6	29.1	28.6	28.3	28.0	27.7	27.5	27.4	27.2	27.1
16	29.6	29.1	28.6	28.3	28.0	27.7	27.5	27.4	27.2	27.1
17	29.6	29.1	28.6	28.3	28.0	27.7	27.5	27.4	27.2	27.1
18	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
19	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
20	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
21	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
22	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
23	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
24	...	35.5	35.4	35.2	34.8	34.3	33.6	33.0	32.5	32.4
25	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
26	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
27	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
28	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
29	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
30	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
31	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
32	28.9	28.0	27.3	26.7	26.1	25.7	25.3	25.1	24.9	24.8
33	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
34	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
35	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
36	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
37	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
38	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
39	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
40	...	30.8	30.4	30.0	29.7	29.4	...	...	...	...
41	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
42	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
43	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
44	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
45	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	(25)
2	...	...	...	...	...	...	...	...	...	...	...	...	(25)
3	...	...	...	...	...	...	...	...	...	...	...	...	(25)
4	...	...	...	...	...	...	...	...	...	...	...	...	(25)
5	...	...	...	...	...	...	...	...	...	...	...	...	(25)
6	...	...	...	...	...	...	...	...	...	...	...	...	(25)
7	...	...	...	...	...	...	...	...	...	...	...	...	
8	...	...	...	...	...	...	...	...	...	...	...	...	
9	...	...	...	...	...	...	...	...	...	...	...	...	
10	...	...	...	...	...	...	...	...	...	...	...	...	
11	...	...	...	...	...	...	...	...	...	...	...	...	
12	...	...	...	...	...	...	...	...	...	...	...	...	
13	...	...	...	...	...	...	...	...	...	...	...	...	
14	...	...	...	...	...	...	...	...	...	...	...	...	
15	27.0	26.9	26.8	26.7	...	...	...	...	...	...	...	...	
16	27.0	26.9	26.8	26.7	...	...	...	...	...	...	...	...	
17	27.0	26.9	26.8	26.7	...	...	...	...	...	...	...	...	
18	...	...	...	...	...	...	...	...	...	...	...	...	
19	...	...	...	...	...	...	...	...	...	...	...	...	
20	...	...	...	...	...	...	...	...	...	...	...	...	
21	...	...	...	...	...	...	...	...	...	...	...	...	
22	...	...	...	...	...	...	...	...	...	...	...	...	
23	...	...	...	...	...	...	...	...	...	...	...	...	
24	...	...	...	...	...	...	...	...	...	...	...	...	
25	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
26	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
27	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
28	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
29	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
30	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
31	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
32	24.6	24.5	24.5	24.5	24.4	...	...	...	...	...	...	...	
33	...	...	...	...	...	...	...	...	...	...	...	...	
34	...	...	...	...	...	...	...	...	...	...	...	...	
35	...	...	...	...	...	...	...	...	...	...	...	...	
36	...	...	...	...	...	...	...	...	...	...	...	...	
37	...	...	...	...	...	...	...	...	...	...	...	...	
38	...	...	...	...	...	...	...	...	...	...	...	...	
39	...	...	...	...	...	...	...	...	...	...	...	...	
40	...	...	...	...	...	...	...	...	...	...	...	...	
41	...	...	...	...	...	...	...	...	...	...	...	...	
42	...	...	...	...	...	...	...	...	...	...	...	...	
43	...	...	...	...	...	...	...	...	...	...	...	...	
44	...	...	...	...	...	...	...	...	...	...	...	...	
45	...	...	...	...	...	...	...	...	...	...	...	...	

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Design./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	Ni-28Mo-3Fe-1.3Cr-0.25Al	Smls. pipe & tube	SB-622	...	N10629	Solution ann.
2	Ni-28Mo-3Fe-1.3Cr-0.25Al	Wld. tube	SB-626	...	N10629	Solution ann.
3	65Ni-28Mo-2Fe	Smls. & wld. fittings	SB-366	...	N10665	Annealed
4	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Annealed
5	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Annealed
6	65Ni-28Mo-2Fe	Plate, sheet, strip	SB-333	...	N10665	Solution ann.
7	65Ni-28Mo-2Fe	Rod	SB-335	...	N10665	Solution ann.
8	65Ni-28Mo-2Fe	Forgings	SB-462	...	N10665	Solution ann.
9	65Ni-28Mo-2Fe	Forgings	SB-564	...	N10665	Solution ann.
10	65Ni-28Mo-2Fe	Wld. pipe	SB-619	...	N10665	Solution ann.
11	65Ni-28Mo-2Fe	Smls. pipe & tube	SB-622	...	N10665	Solution ann.
12	65Ni-28Mo-2Fe	Wld. tube	SB-626	...	N10665	Solution ann.
13	65Ni-29.5Mo-2Fe-2Cr	Plate, sheet, strip	SB-333	...	N10675	Solution ann.
14	65Ni-29.5Mo-2Fe-2Cr	Rod	SB-335	...	N10675	Solution ann.
15	65Ni-29.5Mo-2Fe-2Cr	Smls. & wld. fittings	SB-366	...	N10675	Solution ann.
16	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-462	...	N10675	Solution ann.
17	65Ni-29.5Mo-2Fe-2Cr	Forgings	SB-564	...	N10675	Solution ann.
18	65Ni-29.5Mo-2Fe-2Cr	Wld. pipe	SB-619	...	N10675	Solution ann.
19	65Ni-29.5Mo-2Fe-2Cr	Smls. pipe & tube	SB-622	...	N10675	Solution ann.
20	65Ni-29.5Mo-2Fe-2Cr	Wld. tube	SB-626	...	N10675	Solution ann.
21	37Ni-30Co-28Cr-2.7Si	Plate, sheet, strip	SB-435	...	N12160	Solution ann.
22	37Ni-30Co-28Cr-2.7Si	Forgings	SB-564	...	N12160	Solution ann.
23	37Ni-30Co-28Cr-2.7Si	Bar	SB-572	...	N12160	Solution ann.
24	37Ni-30Co-28Cr-2.7Si	Wld. pipe	SB-619	...	N12160	Solution ann.
25	37Ni-30Co-28Cr-2.7Si	Smls. pipe & tube	SB-622	...	N12160	Solution ann.
26	37Ni-30Co-28Cr-2.7Si	Wld. tube	SB-626	...	N12160	Solution ann.
27	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. & wld. fittings	SB-366	...	R20033	Solution ann.
28	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Forgings	SB-564	...	R20033	Solution ann.
29	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. pipe	SB-619	...	R20033	Solution ann.
30	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Smls. pipe & tube	SB-622	...	R20033	Solution ann.
31	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Plate, sheet, strip	SB-625	...	R20033	Solution ann.
32	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Wld. tube	SB-626	...	R20033	Solution ann.
33	33Cr-31Ni-32Fe-1.5Mo-0.6Cu-N	Rod	SB-649	...	R20033	Solution ann.
34	21Ni-30Fe-22Cr-18Co-3Mo-3W	Plate, sheet, strip	SB-435	...	R30556	Annealed
35	21Ni-30Fe-22Cr-18Co-3Mo-3W	Rod	SB-572	...	R30556	Annealed
36	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. pipe	SB-619	...	R30556	Annealed
37	21Ni-30Fe-22Cr-18Co-3Mo-3W	Smls. pipe & tube	SB-622	...	R30556	Annealed
38	21Ni-30Fe-22Cr-18Co-3Mo-3W	Wld. tube	SB-626	...	R30556	Annealed
39	Co-26Cr-9Ni-5Mo-3Fe-2W	Rod	SB-815	...	R31233	Solution ann.
40	Co-26Cr-9Ni-5Mo-3Fe-2W	Plate, sheet, strip	SB-818	...	R31233	Solution ann.
41	Ti	Plate, sheet, strip	SB-265	1	R50250	Annealed
42	Ti	Smls. & wld. tube	SB-338	1	R50250	Annealed
43	Ti	Bar, billet	SB-348	1	R50250	Annealed
44	Ti	Forgings	SB-381	F-1	R50250	Annealed
45	Ti	Smls. pipe	SB-861	1	R50250	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	110	51	...
2	...	110	51	...
3	...	110	51	...
4	...	110	51	...
5	...	110	51	...
6	...	110	51	...
7	...	110	51	...
8	...	110	51	...
9	...	110	51	...
10	...	110	51	...
11	...	110	51	...
12	...	110	51	...
13	...	110	51	...
14	...	110	51	...
15	...	110	51	...
16	...	110	51	...
17	...	110	51	...
18	...	110	51	...
19	...	110	51	...
20	...	110	51	...
21	...	90	35	...
22	...	90	35	...
23	...	90	35	...
24	...	90	35	...
25	...	90	35	...
26	...	90	35	...
27	...	109	55	...
28	...	109	55	...
29	...	109	55	...
30	...	109	55	...
31	...	109	55	...
32	...	109	55	...
33	...	109	55	...
34	...	100	45	...
35	...	100	45	...
36	...	100	45	...
37	...	100	45	...
38	...	100	45	...
39	...	130	55	...
40	...	130	55	...
41	...	35	20	...
42	...	35	20	...
43	...	35	20	...
44	...	35	20	...
45	...	35	20	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	51.0	...	47.1	...	44.4	...	42.2	...	40.5
2	51.0	...	47.1	...	44.4	...	42.2	...	40.5
3	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
4	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
5	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
6	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
7	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
8	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
9	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
10	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
11	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
12	51.0	49.2	47.9	46.6	45.4	44.3	43.4	42.6	41.9
13	51.0	...	47.8	...	45.4	...	43.2	...	41.1
14	51.0	...	47.8	...	45.4	...	43.2	...	41.1
15	51.0	...	47.8	...	45.4	...	43.2	...	41.1
16	51.0	...	47.8	...	45.4	...	43.2	...	41.1
17	51.0	...	47.8	...	45.4	...	43.2	...	41.1
18	51.0	...	47.8	...	45.4	...	43.2	...	41.1
19	51.0	...	47.8	...	45.4	...	43.2	...	41.1
20	51.0	...	47.8	...	45.4	...	43.2	...	41.1
21	35.0	...	30.8	...	27.5	...	24.7	...	22.5
22	35.0	...	30.8	...	27.5	...	24.7	...	22.5
23	35.0	...	30.8	...	27.5	...	24.7	...	22.5
24	35.0	...	30.8	...	27.5	...	24.7	...	22.5
25	35.0	...	30.8	...	27.5	...	24.7	...	22.5
26	35.0	...	30.8	...	27.5	...	24.7	...	22.5
27	55.0	...	46.3	...	42.1	...	39.2	...	37.1
28	55.0	...	46.3	...	42.1	...	39.2	...	37.1
29	55.0	...	46.3	...	42.1	...	39.2	...	37.1
30	55.0	...	46.3	...	42.1	...	39.2	...	37.1
31	55.0	...	46.3	...	42.1	...	39.2	...	37.1
32	55.0	...	46.3	...	42.1	...	39.2	...	37.1
33	55.0	...	46.3	...	42.1	...	39.2	...	37.1
34	45.0	40.8	38.4	36.4	34.7	33.2	32.0	31.0	30.2
35	45.0	40.8	38.4	36.4	34.7	33.2	32.0	31.0	30.2
36	45.0	40.8	38.4	36.4	34.7	33.2	32.0	31.0	30.2
37	45.0	40.8	38.4	36.4	34.7	33.2	32.0	31.0	30.2
38	45.0	40.8	38.4	36.4	34.7	33.2	32.0	31.0	30.2
39	55.0	...	48.2	...	42.8	...	38.3	...	35.1
40	55.0	...	48.2	...	42.8	...	38.3	...	35.1
41	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
42	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
43	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
44	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
45	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
Nonferrous Materials (Cont'd)										
1	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
2	...	39.2	38.7	38.3	37.9	37.7	37.4	37.3	37.1	...
3	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
4	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
5	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
6	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
7	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
8	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
9	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
10	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
11	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
12	41.3	40.8	40.3	39.8	39.3	38.7	38.0	37.3	36.5	35.8
13	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
14	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
15	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
16	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
17	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
18	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
19	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
20	...	39.4	38.7	38.1	37.6	37.3	37.0	36.8	36.6	36.3
21	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
22	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
23	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
24	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
25	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
26	...	21.1	20.7	20.4	20.3	20.3	20.3	20.3	20.3	20.3
27	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
28	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
29	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
30	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
31	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
32	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
33	...	35.7	35.2	34.7	34.3	33.9	33.6	33.2	...	...
34	29.5	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.5	26.2
35	29.5	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.5	26.2
36	29.5	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.5	26.2
37	29.5	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.5	26.2
38	29.5	28.9	28.4	28.0	27.6	27.3	27.0	26.7	26.5	26.2
39	...	33.0	32.3	31.8	31.3	30.8	30.2	29.4	28.3	26.8
40	...	33.0	32.3	31.8	31.3	30.8	30.2	29.4	28.3	26.8
41	5.7	5.3	...	...	...	...	...	...	...	...
42	5.7	5.3	...	...	...	...	...	...	...	...
43	5.7	5.3	...	...	...	...	...	...	...	...
44	5.7	5.3	...	...	...	...	...	...	...	...
45	5.7	5.3	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	Ti	Wld. pipe	SB-862	1	R50250	Annealed
2	Ti	Castings	SB-367	C-2	R50400	...
3	Ti	Plate, sheet, strip	SB-265	2	R50400	Annealed
4	Ti	Smls. & wld. tube	SB-338	2	R50400	Annealed
5	Ti	Bar, billet	SB-348	2	R50400	Annealed
6	Ti	Forgings	SB-381	F-2	R50400	Annealed
7	Ti	Smls. pipe	SB-861	2	R50400	Annealed
8	Ti	Wld. pipe	SB-862	2	R50400	Annealed
9	Ti	Plate, sheet, strip	SB-265	2H	R50400	Annealed
10	Ti	Smls. & wld. tube	SB-338	2H	R50400	Annealed
11	Ti	Bar, billet	SB-348	2H	R50400	Annealed
12	Ti	Smls. fittings	SB-363	WPT2H	R50400	Annealed
13	Ti	Wld. fittings	SB-363	WPT2HW	R50400	Annealed
14	Ti	Forgings	SB-381	F-2H	R50400	Annealed
15	Ti	Smls. pipe	SB-861	2H	R50400	Annealed
16	Ti	Wld. pipe	SB-862	2H	R50400	Annealed
17	Ti	Plate, sheet, strip	SB-265	3	R50550	Annealed
18	Ti	Smls. & wld. tube	SB-338	3	R50550	Annealed
19	Ti	Bar, billet	SB-348	3	R50550	Annealed
20	Ti	Castings	SB-367	C-3	R50550	Annealed
21	Ti	Forgings	SB-381	F-3	R50550	Annealed
22	Ti	Smls. pipe	SB-861	3	R50550	Annealed
23	Ti	Wld. pipe	SB-862	3	R50550	Annealed
24	Ti-Pd	Plate, sheet, strip	SB-265	11	R52250	Annealed
25	Ti-Pd	Plate, sheet, strip	SB-265	17	R52252	Annealed
26	Ti-Ru	Plate, sheet, strip	SB-265	27	R52254	Annealed
27	Ti-Pd	Plate, sheet, strip	SB-265	7	R52400	Annealed
28	Ti-Pd	Smls. & wld. tube	SB-338	7	R52400	Annealed
29	Ti-Pd	Bar, billet	SB-348	7	R52400	Annealed
30	Ti-Pd	Forgings	SB-381	F-7	R52400	Annealed
31	Ti-Pd	Smls. pipe	SB-861	7	R52400	Annealed
32	Ti-Pd	Wld. pipe	SB-862	7	R52400	Annealed
33	Ti-0.15Pd	Plate, sheet, strip	SB-265	7H	R52400	Annealed
34	Ti-0.15Pd	Smls. & wld. tube	SB-338	7H	R52400	Annealed
35	Ti-0.15Pd	Bar, billet	SB-348	7H	R52400	Annealed
36	Ti-0.15Pd	Smls. fittings	SB-363	WPT7H	R52400	Annealed
37	Ti-0.15Pd	Wld. fittings	SB-363	WPT7HW	R52400	Annealed
38	Ti-0.15Pd	Forgings	SB-381	F-7H	R52400	Annealed
39	Ti-0.15Pd	Smls. pipe	SB-861	7H	R52400	Annealed
40	Ti-0.15Pd	Wld. pipe	SB-862	7H	R52400	Annealed
41	Ti-0.05Pd	Plate, sheet, strip	SB-265	16H	R52402	Annealed
42	Ti-0.05Pd	Smls. & wld. tube	SB-338	16H	R52402	Annealed
43	Ti-0.05Pd	Bar, billet	SB-348	16H	R52402	Annealed
44	Ti-0.05Pd	Smls. fittings	SB-363	WPT16H	R52402	Annealed
45	Ti-0.05Pd	Wld. fittings	SB-363	WPT16HW	R52402	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	35	20	...
2	...	50	40	...
3	...	50	40	...
4	...	50	40	...
5	...	50	40	...
6	...	50	40	...
7	...	50	40	...
8	...	50	40	...
9	...	58	40	...
10	...	58	40	...
11	...	58	40	...
12	...	58	40	...
13	...	58	40	...
14	...	58	40	...
15	...	58	40	...
16	...	58	40	...
17	...	65	55	...
18	...	65	55	...
19	...	65	55	...
20	...	65	55	...
21	...	65	55	...
22	...	65	55	...
23	...	65	55	...
24	...	35	20	...
25	...	35	20	...
26	...	35	20	...
27	...	50	40	...
28	...	50	40	...
29	...	50	40	...
30	...	50	40	...
31	...	50	40	...
32	...	50	40	...
33	...	58	40	...
34	...	58	40	...
35	...	58	40	...
36	...	58	40	...
37	...	58	40	...
38	...	58	40	...
39	...	58	40	...
40	...	58	40	...
41	...	58	40	...
42	...	58	40	...
43	...	58	40	...
44	...	58	40	...
45	...	58	40	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
2	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
3	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
4	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
5	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
6	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
7	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
8	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
9	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
10	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
11	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
12	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
13	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
14	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
15	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
16	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
17	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
18	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
19	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
20	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
21	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
22	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
23	55.0	48.4	44.0	39.8	35.7	32.0	28.6	25.5	22.5
24	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
25	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
26	20.0	16.1	14.0	12.3	10.8	9.4	8.2	7.1	6.3
27	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
28	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
29	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
30	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
31	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
32	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
33	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
34	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
35	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
36	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
37	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
38	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
39	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
40	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
41	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
42	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
43	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
44	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
45	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	5.7	5.3	...	...	...	...	...	...	...	...
2	12.6	11.4	...	...	...	...	...	...	...	...
3	12.6	11.4	...	...	...	...	...	...	...	...
4	12.6	11.4	...	...	...	...	...	...	...	...
5	12.6	11.4	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...
7	12.6	11.4	...	...	...	...	...	...	...	...
8	12.6	11.4	...	...	...	...	...	...	...	...
9	12.6	11.4	...	...	...	...	...	...	...	...
10	12.6	11.4	...	...	...	...	...	...	...	...
11	12.6	11.4	...	...	...	...	...	...	...	...
12	12.6	11.4	...	...	...	...	...	...	...	...
13	12.6	11.4	...	...	...	...	...	...	...	...
14	12.6	11.4	...	...	...	...	...	...	...	...
15	12.6	11.4	...	...	...	...	...	...	...	...
16	12.6	11.4	...	...	...	...	...	...	...	...
17	19.8	17.1	...	...	...	...	...	...	...	...
18	19.8	17.1	...	...	...	...	...	...	...	...
19	19.8	17.1	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...
21	19.8	17.1	...	...	...	...	...	...	...	...
22	19.8	17.1	...	...	...	...	...	...	...	...
23	19.8	17.1	...	...	...	...	...	...	...	...
24	5.7	5.3	...	...	...	...	...	...	...	...
25	5.7	5.3	...	...	...	...	...	...	...	...
26	5.7	5.3	...	...	...	...	...	...	...	...
27	12.6	11.4	...	...	...	...	...	...	...	...
28	12.6	11.4	...	...	...	...	...	...	...	...
29	12.6	11.4	...	...	...	...	...	...	...	...
30	12.6	11.4	...	...	...	...	...	...	...	...
31	12.6	11.4	...	...	...	...	...	...	...	...
32	12.6	11.4	...	...	...	...	...	...	...	...
33	12.6	11.4	...	...	...	...	...	...	...	...
34	12.6	11.4	...	...	...	...	...	...	...	...
35	12.6	11.4	...	...	...	...	...	...	...	...
36	12.6	11.4	...	...	...	...	...	...	...	...
37	12.6	11.4	...	...	...	...	...	...	...	...
38	12.6	11.4	...	...	...	...	...	...	...	...
39	12.6	11.4	...	...	...	...	...	...	...	...
40	12.6	11.4	...	...	...	...	...	...	...	...
41	12.6	11.4	...	...	...	...	...	...	...	...
42	12.6	11.4	...	...	...	...	...	...	...	...
43	12.6	11.4	...	...	...	...	...	...	...	...
44	12.6	11.4	...	...	...	...	...	...	...	...
45	12.6	11.4	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	Ti-0.05Pd	Forgings	SB-381	F-16H	R52402	Annealed
2	Ti-0.05Pd	Smls. pipe	SB-861	16H	R52402	Annealed
3	Ti-0.05Pd	Wld. pipe	SB-862	16H	R52402	Annealed
4	Ti-Ru	Plate, sheet, strip	SB-265	26	R52404	Annealed
5	Ti-Ru	Smls. & wld. tube	SB-338	26	R52404	Annealed
6	Ti-Ru	Bar, billet	SB-348	26	R52404	Annealed
7	Ti-Ru	Smls. fittings	SB-363	WPT26	R52404	Annealed
8	Ti-Ru	Wld. fittings	SB-363	WPT26W	R52404	Annealed
9	Ti-Ru	Forgings	SB-381	F-26	R52404	Annealed
10	Ti-Ru	Smls. pipe	SB-861	26	R52404	Annealed
11	Ti-Ru	Wld. pipe	SB-862	26	R52404	Annealed
12	Ti-0.10Ru	Plate, sheet, strip	SB-265	26H	R52404	Annealed
13	Ti-0.10Ru	Smls. & wld. tube	SB-338	26H	R52404	Annealed
14	Ti-0.10Ru	Bar, billet	SB-348	26H	R52404	Annealed
15	Ti-0.10Ru	Smls. fittings	SB-363	WPT26H	R52404	Annealed
16	Ti-0.10Ru	Wld. fittings	SB-363	WPT26HW	R52404	Annealed
17	Ti-0.10Ru	Forgings	SB-381	F-26H	R52404	Annealed
18	Ti-0.10Ru	Smls. pipe	SB-861	26H	R52404	Annealed
19	Ti-0.10Ru	Wld. pipe	SB-862	26H	R52404	Annealed
20	Ti-0.3Mo-0.8Ni	Plate, sheet, strip	SB-265	12	R53400	Annealed
21	Ti-0.3Mo-0.8Ni	Smls. & wld. tube	SB-338	12	R53400	Annealed
22	Ti-0.3Mo-0.8Ni	Bar, billet	SB-348	12	R53400	Annealed
23	Ti-0.3Mo-0.8Ni	Forgings	SB-381	F-12	R53400	Annealed
24	Ti-0.3Mo-0.8Ni	Smls. pipe	SB-861	12	R53400	Annealed
25	Ti-0.3Mo-0.8Ni	Wld. pipe	SB-862	12	R53400	Annealed
26	Ti-4Al-2.5V-1.5Fe	Plate, sheet, strip	SB-265	38	R54250	Annealed
27	Ti-4Al-2.5V-1.5Fe	Smls. tube	SB-338	38	R54250	Annealed
28	Ti-4Al-2.5V-1.5Fe	Wld. tube	SB-338	38	R54250	Annealed
29	Ti-4Al-2.5V-1.5Fe	Bar, billet	SB-348	38	R54250	Annealed
30	Ti-4Al-2.5V-1.5Fe	Smls. fittings	SB-363	WPT38	R54250	Annealed
31	Ti-4Al-2.5V-1.5Fe	Wld. fittings	SB-363	WPT38W	R54250	Annealed
32	Ti-4Al-2.5V-1.5Fe	Forgings	SB-381	F-38	R54250	Annealed
33	Ti-4Al-2.5V-1.5Fe	Smls. pipe	SB-861	38	R54250	Annealed
34	Ti-4Al-2.5V-1.5Fe	Wld. pipe	SB-862	38	R54250	Annealed
35	Ti-3Al-2.5V	Plate, sheet, strip	SB-265	9	R56320	Annealed
36	Ti-3Al-2.5V	Smls. & wld. tube	SB-338	9	R56320	Annealed
37	Ti-3Al-2.5V	Bar, billet	SB-348	9	R56320	Annealed
38	Ti-3Al-2.5V	Smls. fittings	SB-363	WPT9	R56320	Annealed
39	Ti-3Al-2.5V	Wld. fittings	SB-363	WPT9W	R56320	Annealed
40	Ti-3Al-2.5V	Forgings	SB-381	F-9	R56320	Annealed
41	Ti-3Al-2.5V	Smls. pipe	SB-861	9	R56320	Annealed
42	Ti-3Al-2.5V	Wld. pipe	SB-862	9	R56320	Annealed
43	Ti-3Al-2.5V-0.1Ru	Plate, sheet, strip	SB-265	28	R56323	Annealed
44	Ti-3Al-2.5V-0.1Ru	Smls. & wld. tube	SB-338	28	R56323	Annealed
45	Ti-3Al-2.5V-0.1Ru	Bar, billet	SB-348	28	R56323	Annealed

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	58	40	...
2	...	58	40	...
3	...	58	40	...
4	...	50	40	...
5	...	50	40	...
6	...	50	40	...
7	...	50	40	...
8	...	50	40	...
9	...	50	40	...
10	...	50	40	...
11	...	50	40	...
12	...	58	40	...
13	...	58	40	...
14	...	58	40	...
15	...	58	40	...
16	...	58	40	...
17	...	58	40	...
18	...	58	40	...
19	...	58	40	...
20	...	70	50	...
21	...	70	50	...
22	...	70	50	...
23	...	70	50	...
24	...	70	50	...
25	...	70	50	...
26	...	130	115	...
27	...	130	115	...
28	...	130	115	...
29	...	130	115	...
30	...	130	115	...
31	...	130	115	...
32	...	130	115	...
33	...	130	115	...
34	...	130	115	...
35	...	90	70	...
36	...	90	70	...
37	...	90	70	...
38	...	90	70	...
39	...	90	70	...
40	...	90	70	...
41	...	90	70	...
42	...	90	70	...
43	...	90	70	...
44	...	90	70	...
45	...	90	70	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
Nonferrous Materials (Cont'd)									
1	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
2	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
3	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
4	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
5	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
6	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
7	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
8	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
9	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
10	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
11	40.0	34.5	31.5	28.6	25.6	22.6	19.6	17.0	14.8
12	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
13	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
14	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
15	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
16	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
17	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
18	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
19	40.0	34.9	32.2	28.4	25.2	22.0	18.6	16.3	14.1
20	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
21	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
22	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
23	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
24	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
25	50.0	45.0	41.5	38.1	35.0	32.2	29.4	27.7	26.0
26	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
27	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
28	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
29	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
30	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
31	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
32	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
33	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
34	115.0	106.5	100.8	95.4	90.2	85.5	81.4	77.8	74.6
35	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
36	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
37	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
38	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
39	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
40	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
41	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
42	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
43	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
44	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
45	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	12.6	11.4	...	...	...	...	...	...	...	...
2	12.6	11.4	...	...	...	...	...	...	...	...
3	12.6	11.4	...	...	...	...	...	...	...	...
4	12.6	11.4	...	...	...	...	...	...	...	...
5	12.6	11.4	...	...	...	...	...	...	...	...
6	12.6	11.4	...	...	...	...	...	...	...	...
7	12.6	11.4	...	...	...	...	...	...	...	...
8	12.6	11.4	...	...	...	...	...	...	...	...
9	12.6	11.4	...	...	...	...	...	...	...	...
10	12.6	11.4	...	...	...	...	...	...	...	...
11	12.6	11.4	...	...	...	...	...	...	...	...
12	12.6	11.4	...	...	...	...	...	...	...	...
13	12.6	11.4	...	...	...	...	...	...	...	...
14	12.6	11.4	...	...	...	...	...	...	...	...
15	12.6	11.4	...	...	...	...	...	...	...	...
16	12.6	11.4	...	...	...	...	...	...	...	...
17	12.6	11.4	...	...	...	...	...	...	...	...
18	12.6	11.4	...	...	...	...	...	...	...	...
19	12.6	11.4	...	...	...	...	...	...	...	...
20	24.8	24.0	...	...	...	...	...	...	...	...
21	24.8	24.0	...	...	...	...	...	...	...	...
22	24.8	24.0	...	...	...	...	...	...	...	...
23	24.8	24.0	...	...	...	...	...	...	...	...
24	24.8	24.0	...	...	...	...	...	...	...	...
25	24.8	24.0	...	...	...	...	...	...	...	...
26	71.9	69.5	67.3	...	...	...	...	...	...	...
27	71.9	69.5	67.3	...	...	...	...	...	...	...
28	71.9	69.5	67.3	...	...	...	...	...	...	...
29	71.9	69.5	67.3	...	...	...	...	...	...	...
30	71.9	69.5	67.3	...	...	...	...	...	...	...
31	71.9	69.5	67.3	...	...	...	...	...	...	...
32	71.9	69.5	67.3	...	...	...	...	...	...	...
33	71.9	69.5	67.3	...	...	...	...	...	...	...
34	71.9	69.5	67.3	...	...	...	...	...	...	...
35	43.4	41.3	...	...	...	...	...	...	...	...
36	43.4	41.3	...	...	...	...	...	...	...	...
37	43.4	41.3	...	...	...	...	...	...	...	...
38	43.4	41.3	...	...	...	...	...	...	...	...
39	43.4	41.3	...	...	...	...	...	...	...	...
40	43.4	41.3	...	...	...	...	...	...	...	...
41	43.4	41.3	...	...	...	...	...	...	...	...
42	43.4	41.3	...	...	...	...	...	...	...	...
43	43.4	41.3	...	...	...	...	...	...	...	...
44	43.4	41.3	...	...	...	...	...	...	...	...
45	43.4	41.3	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding

Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
Nonferrous Materials (Cont'd)													
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...
22	...	...	...	...	...	...	...	...	...	...	...	...	...
23	...	...	...	...	...	...	...	...	...	...	...	...	...
24	...	...	...	...	...	...	...	...	...	...	...	...	...
25	...	...	...	...	...	...	...	...	...	...	...	...	...
26	...	...	...	...	...	...	...	...	...	...	...	...	...
27	...	...	...	...	...	...	...	...	...	...	...	...	...
28	...	...	...	...	...	...	...	...	...	...	...	...	...
29	...	...	...	...	...	...	...	...	...	...	...	...	...
30	...	...	...	...	...	...	...	...	...	...	...	...	...
31	...	...	...	...	...	...	...	...	...	...	...	...	...
32	...	...	...	...	...	...	...	...	...	...	...	...	...
33	...	...	...	...	...	...	...	...	...	...	...	...	...
34	...	...	...	...	...	...	...	...	...	...	...	...	...
35	...	...	...	...	...	...	...	...	...	...	...	...	...
36	...	...	...	...	...	...	...	...	...	...	...	...	...
37	...	...	...	...	...	...	...	...	...	...	...	...	...
38	...	...	...	...	...	...	...	...	...	...	...	...	...
39	...	...	...	...	...	...	...	...	...	...	...	...	...
40	...	...	...	...	...	...	...	...	...	...	...	...	...
41	...	...	...	...	...	...	...	...	...	...	...	...	...
42	...	...	...	...	...	...	...	...	...	...	...	...	...
43	...	...	...	...	...	...	...	...	...	...	...	...	...
44	...	...	...	...	...	...	...	...	...	...	...	...	...
45	...	...	...	...	...	...	...	...	...	...	...	...	...

INTENTIONALLY LEFT BLANK

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Nominal Composition	Product Form	Spec. No.	Type/Grade	Alloy Desig./UNS No.	Class/Condition/ Temper
Nonferrous Materials (Cont'd)						
1	Ti-3Al-2.5V-0.1Ru	Smls. fittings	SB-363	WPT28	R56323	Annealed
2	Ti-3Al-2.5V-0.1Ru	Wld. fittings	SB-363	WPT28W	R56323	Annealed
3	Ti-3Al-2.5V-0.1Ru	Forgings	SB-381	F-28	R56323	Annealed
4	Ti-3Al-2.5V-0.1Ru	Smls. pipe	SB-861	28	R56323	Annealed
5	Ti-3Al-2.5V-0.1Ru	Wld. pipe	SB-862	28	R56323	Annealed
6	99.2Zr	Forgings	SB-493	...	R60702	Annealed
7	99.2Zr	Smls. & wld. tube	SB-523	...	R60702	Annealed
8	99.2Zr	Bar, wire	SB-550	...	R60702	Annealed
9	99.2Zr	Plate, sheet, strip	SB-551	...	R60702	Annealed
10	99.2Zr	Smls. fittings	SB-653	PZ-2	R60702	Annealed
11	99.2Zr	Wld. fittings	SB-653	PZ-2W	R60702	Annealed
12	99.2Zr	Smls. & wld. pipe	SB-658	...	R60702	Annealed
(25) 13	99.2Zr	Castings	SB-752	702C	R61702	...
14	95.5Zr + 2.5Nb	Forgings	SB-493	...	R60705	Annealed
15	95.5Zr + 2.5Nb	Smls. & wld. tube	SB-523	...	R60705	Annealed
16	95.5Zr + 2.5Nb	Bar, wire	SB-550	...	R60705	Annealed
17	95.5Zr + 2.5Nb	Plate, sheet, strip	SB-551	...	R60705	Annealed
18	95.5Zr + 2.5Nb	Smls. fittings	SB-653	PZ-5	R60705	Annealed
19	95.5Zr + 2.5Nb	Wld. fittings	SB-653	PZ-5W	R60705	Annealed
20	95.5Zr + 2.5Nb	Smls. & wld. pipe	SB-658	...	R60705	Annealed
(25) 21	95.5Zr + 2.5Nb	Castings	SB-752	705C	R61705	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Line No.	Size/Thickness, in.	Min. Tensile Strength, ksi	Min. Yield Strength, ksi	Notes
Nonferrous Materials (Cont'd)				
1	...	90	70	...
2	...	90	70	...
3	...	90	70	...
4	...	90	70	...
5	...	90	70	...
6	...	55	30	...
7	...	55	30	...
8	...	55	30	...
9	...	55	30	...
10	...	55	30	...
11	...	55	30	...
12	...	55	30	...
13	...	55	40	...
14	...	70	55	...
15	...	80	55	...
16	...	80	55	...
17	...	80	55	...
18	...	80	55	...
19	...	80	55	...
20	...	80	55	...
21	...	70	50	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding									
Line No.	100	150	200	250	300	350	400	450	500
	Nonferrous Materials (Cont'd)								
1	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
2	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
3	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
4	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
5	70.0	65.1	61.1	58.1	55.3	52.5	49.7	46.9	44.8
6	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
7	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
8	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
9	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
10	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
11	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
12	30.0	25.8	23.1	20.4	18.0	15.9	14.0	12.4	11.0
13	40.0	33.3	30.1	27.1	24.2	21.5	18.9	16.5	14.5
14	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
15	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
16	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
17	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
18	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
19	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
20	55.0	43.1	37.5	33.1	29.6	26.8	24.6	22.7	21.2
21	50.0	41.9	37.5	33.6	30.1	27.1	24.5	22.0	20.0

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding										
Line No.	550	600	650	700	750	800	850	900	950	1000
	Nonferrous Materials (Cont'd)									
1	43.4	41.3	...	...	...	...	...	...	...	...
2	43.4	41.3	...	...	...	...	...	...	...	...
3	43.4	41.3	...	...	...	...	...	...	...	...
4	43.4	41.3	...	...	...	...	...	...	...	...
5	43.4	41.3	...	...	...	...	...	...	...	...
6	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
7	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
8	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
9	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
10	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
11	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
12	9.9	9.0	8.4	7.9	7.6	7.5	...	...	...	...
13	13.1	11.9	...	...	...	...	...	...	...	...
14	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
15	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
16	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
17	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
18	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
19	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
20	19.9	18.7	17.8	17.1	16.7	16.7	...	...	...	...
21	18.3	16.8	...	...	...	...	...	...	...	...

Table Y-1 (Cont'd)
Yield Strength Values, S_y , for Ferrous and Nonferrous Materials

Yield Strength, ksi (Multiply by 1000 to Obtain psi), for Metal Temperature, °F, Not Exceeding													
Line No.	1050	1100	1150	1200	1250	1300	1350	1400	1450	1500	1550	1600	1650
	Nonferrous Materials (Cont'd)												
1	...	...	...	...	...	...	...	...	...	...	...	...	...
2	...	...	...	...	...	...	...	...	...	...	...	...	...
3	...	...	...	...	...	...	...	...	...	...	...	...	...
4	...	...	...	...	...	...	...	...	...	...	...	...	...
5	...	...	...	...	...	...	...	...	...	...	...	...	...
6	...	...	...	...	...	...	...	...	...	...	...	...	...
7	...	...	...	...	...	...	...	...	...	...	...	...	...
8	...	...	...	...	...	...	...	...	...	...	...	...	...
9	...	...	...	...	...	...	...	...	...	...	...	...	...
10	...	...	...	...	...	...	...	...	...	...	...	...	...
11	...	...	...	...	...	...	...	...	...	...	...	...	...
12	...	...	...	...	...	...	...	...	...	...	...	...	...
13	...	...	...	...	...	...	...	...	...	...	...	...	...
14	...	...	...	...	...	...	...	...	...	...	...	...	...
15	...	...	...	...	...	...	...	...	...	...	...	...	...
16	...	...	...	...	...	...	...	...	...	...	...	...	...
17	...	...	...	...	...	...	...	...	...	...	...	...	...
18	...	...	...	...	...	...	...	...	...	...	...	...	...
19	...	...	...	...	...	...	...	...	...	...	...	...	...
20	...	...	...	...	...	...	...	...	...	...	...	...	...
21	...	...	...	...	...	...	...	...	...	...	...	...	...

(25)

(25)

NOTES TO TABLE Y-1**GENERAL NOTES**

- (25) (a) The following abbreviations are used: ann., annealed; cond., condenser; CW, cold worked; extr., extruded; fin., finished; fr., from; HW, Hot worked; N, Normalized; NT, Normalized and tempered; QT, Quenched and tempered; rel., relieved; rld., rolled; Smls., Seamless; Sol., Solution; SR, stress relieved; treat., treated; and Wld., Welded.
- (b) The tabulated values of yield strength are those which the Committee believes are suitable for use in design calculations. At temperatures above room temperature, the yield strength values correspond to the yield strength trend curve adjusted to the minimum specified room temperature yield strength. The yield strength values do not correspond exactly to "minimum" or "average" as these terms are applied to a statistical treatment of a homogeneous set of data. Neither the ASME Material Specifications nor the rules of Sections I, III, VIII, or XII require elevated temperature testing for yield strengths of production material for use in Code components. It is not intended that results of such tests, if performed, be compared with these tabulated yield strength values for ASME Code acceptance/rejection purposes for materials. If some elevated temperature test results on production material appear lower than the tabulated values by a large amount (more than the typical variability of material and suggesting the possibility of some error), further investigation by retest or other means should be considered.
- (c) Notes limiting applications of these materials appear in Tables 1A, 1B, 2A, 2B, 3, 4, 5A, and 5B.
- (d) These values represent yield strength design values that are appropriate for use in any section of the ASME Boiler & Pressure Vessel Code in which the material is permitted and not otherwise restricted by applicability temperature limits, application limits, or notes.
- (e) Where specifications, grades, classes, and types are listed in this Table, and where the material specification in Section II, Part A or Part B is a dual-unit specification (e.g., SA-516/SA-516M), the values listed in this Table shall be applicable to either the customary U.S. version of the material specification or the SI units version of the material specification. For example, the values listed for SA-516 Grade 70 shall be used when SA-516M Grade 485 is used in construction.
- (f) The values in this Table may be interpolated to determine values for intermediate temperatures. The values at intermediate temperatures shall be rounded to the same number of decimal places as the value at the higher temperature between which values are being interpolated. The rounding rule is: when the next digit beyond the last place to be retained is less than 5, retain unchanged the digit in the last place retained; when the digit next beyond the last place to be retained is 5 or greater, increase by 1 the digit in the last place retained.
- (g) Where a size limit appears in the Size/Thickness column, the limit applies to the dimension appropriate to the product form: wall thickness of tubing, pipe, pipe fittings, and hollow forgings; thickness of plate, flat bar and forgings, and polygonal bar; diameter of solid bar and bolting; and thickest cross-section of other pressure parts, e.g., castings and forgings.

NOTE

- (1) Strength values for intermediate thickness may be interpolated.

Table Y-2
Factors for Limiting Permanent Strain in
Austenitic Stainless Steels, High-Nickel
Alloy Steels, Nickel, Nickel Alloys, Copper,
and Copper Alloys

Strain, %	Factors
0.10	0.90
0.09	0.89
0.08	0.88
0.07	0.86
0.06	0.83
0.05	0.80
0.04	0.77
0.03	0.73
0.02	0.69
0.01	0.63

GENERAL NOTE: This Table lists multiplying factors that, when applied to the yield strength values shown in Table Y-1, will give a value that will result in lower levels of permanent strain. If this value is less than the maximum allowable stress value listed in Table 1A, Table 1B, Table 2A, Table 2B, Table 5A, or Table 5B, or the design stress intensity value listed in Table 2A or Table 2B, the lower value shall be used.

SUBPART 2

PHYSICAL PROPERTIES TABLES

INTRODUCTION

Section II, Part D, [Subpart 2](#) provides, to the extent possible, physical properties for most of the alloys used in Code construction. Included in this Subpart are tables of thermal expansion (instantaneous, mean, and linear), thermal conductivity and thermal diffusivity, and modulus of elasticity. These values are all listed as a function of temperature from 70°F to as high as 1,850°F. [Subpart 2](#) also contains tables of density and Poisson's ratio for ferrous and nonferrous alloys.

All of the properties provided in [Subpart 2](#) are considered typical. They are neither average nor minimum. Thermal-physical properties such as thermal expansion, thermal conductivity, and thermal diffusivity are affected more by alloy content than by crystal structure or heat treatment. Due to the permitted range for elements comprising alloys (specification ranges of chemical compositions), the thermal-physical properties described in [Tables TE-1](#) through [TE-5](#) and [Table TCD](#) should be considered to have an associated uncertainty of $\pm 10\%$.

Moduli of elasticity and Poisson's ratio are also typical values, but the values of modulus of elasticity, shown as a function of temperature in [Tables TM-1](#) through [TM-5](#), tend to be closer to average values since their temperature dependency is factored against an "average" room-temperature value.

The physical properties listed in this Subpart are for information only, unless invoked by a Boiler & Pressure Vessel Code (Sections I, III, IV, VIII, X, XI, and XII). When a user of the Code has data supporting the use of values different from those in this Subpart, such other values may be used in lieu of the values in this Subpart.

Values for temperatures between those tabulated may be obtained by linear interpolation.

For those alloys for which physical properties are not yet addressed in [Subpart 2](#), the user of the Code may use other authoritative sources for the needed information. In those instances, or when alternative values are used, the user is encouraged to submit the values and supporting data to the attention of the ASME Boiler and Pressure Vessel Committee II on Materials for its consideration in improving and revising the values in [Subpart 2](#). Information should be directed to:

Secretary
ASME Boiler and Pressure Vessel Committee II on
Materials
Two Park Avenue
New York, NY 10016-5990

(25)

Table TE-1
Thermal Expansion for Ferrous Materials

Temperature, °F	Coefficients for Carbon and Low Alloy Steels (Group 1) [Note (1)]			Coefficients for Other Alloy Steels (Group 2) [Note (2)]			Coefficients for 5Cr-1Mo and 29Cr-7Ni-2Mo-N Steels		
	A	B	C	A	B	C	A	B	C
70	6.4	6.4	0	7.0	7.0	0	6.4	6.4	0
100	6.6	6.5	0.23	7.1	7.1	0.26	6.6	6.5	0.23
150	6.8	6.6	0.63	7.3	7.2	0.69	6.8	6.6	0.63
200	7.0	6.7	1.0	7.5	7.3	1.1	7.0	6.7	1.0
250	7.2	6.8	1.5	7.6	7.3	1.6	7.1	6.8	1.5
300	7.3	6.9	1.9	7.8	7.4	2.0	7.2	6.9	1.9
350	7.5	7.0	2.4	7.9	7.5	2.5	7.3	6.9	2.3
400	7.7	7.1	2.8	8.0	7.6	3.0	7.3	7.0	2.8
450	7.8	7.2	3.3	8.1	7.6	3.5	7.4	7.0	3.2
500	8.0	7.3	3.7	8.3	7.7	4.0	7.4	7.1	3.7
550	8.2	7.3	4.2	8.4	7.8	4.5	7.5	7.1	4.1
600	8.3	7.4	4.7	8.4	7.8	5.0	7.6	7.2	4.6
650	8.5	7.5	5.2	8.5	7.9	5.5	7.7	7.2	5.0
700	8.7	7.6	5.7	8.6	7.9	6.0	7.7	7.2	5.5
750	8.8	7.7	6.3	8.7	8.0	6.5	7.8	7.3	5.9
800	9.0	7.8	6.8	8.8	8.0	7.0	7.9	7.3	6.4
850	9.1	7.9	7.4	8.8	8.1	7.6	8.0	7.4	6.9
900	9.2	7.9	7.9	8.9	8.1	8.1	8.1	7.4	7.4
950	9.3	8.0	8.5	9.0	8.2	8.6	8.1	7.4	7.9
1,000	9.4	8.1	9.0	9.0	8.2	9.2	8.2	7.5	8.4
1,050	9.4	8.1	9.6	9.0	8.3	9.7	8.3	7.5	8.8
1,100	9.5	8.2	10.1	9.1	8.3	10.3	8.3	7.6	9.3
1,150	9.5	8.3	10.7	9.1	8.3	10.8	8.4	7.6	9.8
1,200	9.5	8.3	11.3	9.1	8.4	11.4	8.4	7.6	10.3
1,250	9.5	8.4	11.9	9.1	8.4	11.9	8.5	7.7	10.9
1,300	9.5	8.4	12.4	9.1	8.4	12.5	8.6	7.7	11.4
1,350	...	...	...	9.1	8.5	13.0	8.7	7.7	11.9
1,400	...	...	...	9.0	8.5	13.5	8.9	7.8	12.4
1,450	...	...	...	8.9	8.5	14.1	...	...	...
1,500	...	...	...	8.8	8.5	14.6	...	...	...

Table TE-1
Thermal Expansion for Ferrous Materials (Cont'd)

Temperature, °F	Coefficients for 9Cr-1Mo Steels (Including Grades 9, 91, 911, and 92)			Coefficients for 5Ni- $\frac{1}{4}$ Mo Steels			Coefficients for 7Ni Steels		
	A	B	C	A	B	C	A	B	C
70	5.8	5.8	0	6.2	6.2	0	5.9	5.9	0
100	5.9	5.9	0.21	6.4	6.3	0.23	6.1	6.0	0.22
150	6.1	5.9	0.57	6.6	6.4	0.61	6.3	6.1	0.59
200	6.2	6.0	0.94	6.8	6.5	1.0	6.6	6.2	0.97
250	6.3	6.1	1.3	6.9	6.6	1.4	6.8	6.4	1.4
300	6.5	6.2	1.7	7.1	6.7	1.8	7.0	6.5	1.8
350	6.6	6.2	2.1	7.2	6.8	2.3	7.1	6.6	2.2
400	6.7	6.3	2.5	7.3	6.8	2.7	7.2	6.6	2.6
450	6.8	6.3	2.9	7.5	6.9	3.2	7.3	6.7	3.1
500	6.9	6.4	3.3	7.6	7.0	3.6	7.4	6.8	3.5
550	7.0	6.5	3.7	7.7	7.1	4.1	7.5	6.9	3.9
600	7.1	6.5	4.1	7.9	7.1	4.5	7.6	6.9	4.4
650	7.2	6.6	4.6	8.0	7.2	5.0	7.7	7.0	4.8
700	7.3	6.6	5.0	8.1	7.3	5.5	7.8	7.1	5.3
750	7.4	6.7	5.4	8.2	7.3	6.0	7.9	7.1	5.8
800	7.5	6.7	5.9	8.3	7.4	6.5	8.0	7.2	6.3
850	7.5	6.8	6.3	8.4	7.5	7.0	8.1	7.2	6.7
900	7.6	6.8	6.8	8.5	7.5	7.5	8.1	7.3	7.2
950	7.7	6.9	7.3	8.6	7.6	8.0	8.0	7.3	7.7
1,000	7.8	6.9	7.7	8.7	7.6	8.5	7.8	7.3	8.2
1,050	7.9	7.0	8.2	8.8	7.7	9.1	...	...	...
1,100	8.1	7.0	8.7	9.0	7.8	9.6	...	...	...
1,150	8.2	7.1	9.2	9.3	7.8	10.1	...	...	...
1,200	8.4	7.1	9.7	9.7	7.9	10.7	...	...	...
1,250	8.6	7.2	10.2	...	...	...	...	...	...
1,300	...	...	...	...	...	...	...	...	...
1,350	...	...	...	...	...	...	...	...	...
1,400	...	...	...	...	...	...	...	...	...
1,450	...	...	...	...	...	...	...	...	...
1,500	...	...	...	...	...	...	...	...	...

Table TE-1
Thermal Expansion for Ferrous Materials (Cont'd)

Temperature, °F	Coefficients for 8Ni and 9Ni Steels			Coefficients for 12Cr, 12Cr-1Al, 13Cr, and 13Cr-4Ni Steels			Coefficients for 15Cr and 17Cr Steels		
	A	B	C	A	B	C	A	B	C
70	5.5	5.5	0	5.9	5.9	0	5.3	5.3	0
100	5.7	5.6	0.20	6.1	6.0	0.22	5.4	5.4	0.19
150	6.0	5.8	0.56	6.2	6.1	0.59	5.6	5.5	0.53
200	6.3	5.9	0.92	6.4	6.2	0.97	5.7	5.5	0.86
250	6.6	6.1	1.3	6.5	6.2	1.3	5.8	5.6	1.2
300	6.8	6.2	1.7	6.6	6.3	1.7	6.0	5.7	1.6
350	6.9	6.3	2.1	6.6	6.4	2.1	6.1	5.7	1.9
400	7.0	6.4	2.5	6.7	6.4	2.5	6.2	5.8	2.3
450	7.1	6.5	3.0	6.7	6.4	2.9	6.3	5.8	2.7
500	7.1	6.6	3.4	6.8	6.5	3.3	6.4	5.9	3.0
550	7.2	6.6	3.8	6.8	6.5	3.7	6.4	6.0	3.4
600	7.2	6.7	4.2	6.9	6.5	4.2	6.5	6.0	3.8
650	7.3	6.7	4.7	6.9	6.6	4.6	6.6	6.0	4.2
700	7.4	6.8	5.1	7.0	6.6	5.0	6.6	6.1	4.6
750	7.5	6.8	5.6	7.1	6.6	5.4	6.7	6.1	5.0
800	7.6	6.9	6.0	7.1	6.7	5.8	6.7	6.2	5.4
850	7.7	6.9	6.5	7.2	6.7	6.3	6.8	6.2	5.8
900	7.6	7.0	6.9	7.2	6.7	6.7	6.8	6.2	6.2
950	7.3	7.0	7.4	7.3	6.8	7.1	6.8	6.3	6.6
1,000	6.8	7.0	7.8	7.3	6.8	7.6	6.8	6.3	7.0
1,050	...	...	...	7.4	6.8	8.0	6.9	6.3	7.4
1,100	...	...	...	7.4	6.8	8.5	6.9	6.4	7.9
1,150	...	...	...	7.4	6.9	8.9	7.0	6.4	8.3
1,200	...	...	...	7.4	6.9	9.4	7.0	6.4	8.7
1,250	...	...	...	7.4	6.9	9.8	7.1	6.4	9.1
1,300	...	...	...	7.4	6.9	10.2	7.2	6.5	9.5
1,350	...	...	...	7.4	7.0	10.7	7.4	6.5	10.0
1,400	...	...	...	7.5	7.0	11.1	7.6	6.5	10.4
1,450	...	...	...	7.5	7.0	11.6	7.9	6.6	10.9
1,500	...	...	...	7.6	7.0	12.0	8.3	6.6	11.4

Table TE-1
Thermal Expansion for Ferrous Materials (Cont'd)

Temperature, °F	Coefficients for 27Cr Steels			Coefficients for Austenitic Stainless Steels (Group 3) [Note (3)]			Coefficients for Other Austenitic Stainless Steels (Group 4) [Note (4)]		
	A	B	C	A	B	C	A	B	C
70	5.0	5.0	0	8.5	8.5	0	8.2	8.2	0
100	5.1	5.1	0.18	8.7	8.6	0.31	8.3	8.2	0.30
150	5.2	5.1	0.49	9.0	8.8	0.84	8.6	8.4	0.81
200	5.3	5.2	0.81	9.4	8.9	1.4	8.8	8.5	1.3
250	5.3	5.2	1.1	9.6	9.1	2.0	9.0	8.6	1.9
300	5.4	5.2	1.4	9.9	9.2	2.5	9.2	8.7	2.4
350	5.4	5.3	1.8	10.1	9.4	3.1	9.3	8.8	3.0
400	5.5	5.3	2.1	10.2	9.5	3.8	9.4	8.9	3.5
450	5.6	5.3	2.4	10.4	9.6	4.4	9.5	9.0	4.1
500	5.6	5.4	2.8	10.5	9.7	5.0	9.6	9.1	4.7
550	5.7	5.4	3.1	10.6	9.8	5.6	9.7	9.1	5.3
600	5.8	5.4	3.5	10.6	9.9	6.3	9.8	9.2	5.8
650	5.9	5.5	3.8	10.7	9.9	6.9	9.9	9.2	6.4
700	6.0	5.5	4.2	10.8	10.0	7.5	10.0	9.3	7.0
750	6.1	5.5	4.5	10.8	10.0	8.2	10.1	9.3	7.6
800	6.2	5.6	4.9	10.9	10.1	8.8	10.2	9.4	8.2
850	6.2	5.6	5.3	11.0	10.2	9.5	10.3	9.4	8.8
900	6.3	5.7	5.6	11.1	10.2	10.2	10.4	9.5	9.5
950	6.4	5.7	6.0	11.2	10.3	10.8	10.5	9.6	10.1
1,000	6.4	5.7	6.4	11.4	10.3	11.5	10.6	9.6	10.7
1,050	6.5	5.8	6.8	11.5	10.4	12.2	10.7	9.7	11.4
1,100	6.5	5.8	7.2	11.7	10.4	12.9	10.9	9.7	12.0
1,150	6.5	5.8	7.6	11.8	10.5	13.6	11.0	9.8	12.7
1,200	6.5	5.9	8.0	12.0	10.6	14.3	11.1	9.8	13.3
1,250	6.6	5.9	8.4	12.0	10.6	15.0	11.3	9.9	14.0
1,300	6.7	5.9	8.7	12.0	10.7	15.8	11.4	9.9	14.7
1,350	6.8	6.0	9.2	11.9	10.7	16.5	11.5	10.0	15.4
1,400	7.0	6.0	9.6	11.7	10.8	17.2	11.7	10.1	16.1
1,450	7.3	6.0	10.0	11.2	10.8	17.9	11.8	10.1	16.8
1,500	7.7	6.1	10.4	10.5	10.8	18.5	12.0	10.2	17.5

Table TE-1
Thermal Expansion for Ferrous Materials (Cont'd)

Temperature, °F	Coefficients for Ductile Cast Iron			Coefficients for Precipitation Hardened 17Cr-4Ni-4Cu Stainless Steels, Condition 1075			Coefficients for Precipitation Hardened 17Cr-4Ni-4Cu Stainless Steels, Condition 1150		
	A	B	C	A	B	C	A	B	C
70	5.7	5.7	0	6.2	6.2	0	6.4	6.4	0
100	5.8	5.8	0.21	6.2	6.2	0.22	6.5	6.4	0.23
150	6.1	5.9	0.57	6.3	6.3	0.60	6.6	6.5	0.62
200	6.3	6.0	0.94	6.3	6.3	0.98	6.8	6.6	1.0
250	6.6	6.1	1.3	6.3	6.3	1.4	6.9	6.7	1.4
300	6.9	6.3	1.7	6.4	6.4	1.8	7.1	6.7	1.9
350	7.2	6.4	2.2	6.4	6.4	2.2	7.2	6.8	2.3
400	7.4	6.6	2.6	6.5	6.5	2.6	7.3	6.9	2.7
450	7.6	6.7	3.1	6.5	6.5	3.0	7.4	6.9	3.2
500	7.7	6.8	3.5	6.5	6.5	3.4	7.5	7.0	3.6
550	7.8	6.9	4.0	6.6	6.6	3.8	7.5	7.0	4.1
600	7.9	7.0	4.5	6.6	6.6	4.2	7.5	7.1	4.5
650	7.9	7.1	4.9	6.7	6.7	4.6	7.6	7.1	5.0
700	8.0	7.1	5.4	6.7	6.7	5.1	7.6	7.2	5.4
750	8.0	7.2	5.9	6.7	6.7	5.5	7.6	7.2	5.9
800	8.1	7.3	6.4	6.8	6.8	5.9	7.6	7.2	6.3
850	8.1	7.3	6.8	...	...	...	7.7	7.2	6.8
900	8.3	7.4	7.3	...	...	...	7.8	7.3	7.2
950	8.5	7.4	7.8	...	...	...	8.0	7.3	7.7
1,000	8.7	7.5	8.4	...	...	...	8.4	7.4	8.2
1,050	...	...	...	...	...	...	...	...	...
1,100	...	...	...	...	...	...	...	...	...
1,150	...	...	...	...	...	...	...	...	...
1,200	...	...	...	...	...	...	...	...	...
1,250	...	...	...	...	...	...	...	...	...
1,300	...	...	...	...	...	...	...	...	...
1,350	...	...	...	...	...	...	...	...	...
1,400	...	...	...	...	...	...	...	...	...
1,450	...	...	...	...	...	...	...	...	...
1,500	...	...	...	...	...	...	...	...	...

GENERAL NOTE: Coefficient A is the instantaneous coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F). Coefficient B is the mean coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F) in going from 70°F to indicated temperature. Coefficient C is the linear thermal expansion (in./100 ft) in going from 70°F to indicated temperature.

NOTES:

(1) Group 1 alloys (by nominal composition):

Carbon steel	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}$	$\frac{3}{4}\text{Ni}-\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$
C-Mn-Cb	$1\frac{1}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Si}$	$\frac{3}{4}\text{Ni}-\frac{1}{2}\text{Cu}-\text{Mo}$
C-Mn-Si-Cb	$1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Cu}$	$\frac{3}{4}\text{Ni}-\frac{1}{2}\text{Mo}-\frac{1}{3}\text{Cr}-\text{V}$
C-Mn-Si-V	$1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{Ti}$	$\frac{3}{4}\text{Ni}-\frac{1}{2}\text{Mo}-\text{Cr}-\text{V}$
C-Mn-Ti	$2\text{Cr}-\frac{1}{2}\text{Mo}$	$\frac{3}{4}\text{Ni}-1\text{Mo}-\frac{3}{4}\text{Cr}$
C-Si-Ti	$2\frac{1}{4}\text{Cr}-1\text{Mo}$	$1\text{Ni}-\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$
C- $\frac{1}{4}\text{Mo}$	$3\text{Cr}-1\text{Mo}$	$1\frac{1}{4}\text{Ni}-1\text{Cr}-\frac{1}{2}\text{Mo}$
C- $\frac{1}{2}\text{Mo}$	$3\text{Cr}-1\text{Mo}-\frac{1}{4}\text{V}-\text{Cb}-\text{Ca}$	$1\frac{3}{4}\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$
$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}$	$3\text{Cr}-1\text{Mo}-\frac{1}{4}\text{V}-\text{Ti}-\text{B}$	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{4}\text{Mo}$
$\frac{1}{2}\text{Cr}-\frac{1}{5}\text{Mo}-\text{V}$	$\text{Mn}-\frac{1}{4}\text{Mo}$	$2\text{Ni}-\frac{3}{4}\text{Cr}-\frac{1}{3}\text{Mo}$
$\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{Si}$	$\text{Mn}-\frac{1}{2}\text{Mo}$	$2\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$
$\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}$	$\text{Mn}-\frac{1}{2}\text{Mo}-\frac{1}{4}\text{Ni}$	$2\frac{1}{2}\text{Ni}$
$\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Ni}-\text{Cu}$	$\text{Mn}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Ni}$	$2\frac{3}{4}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$
$\frac{3}{4}\text{Cr}-\frac{3}{4}\text{Ni}-\text{Cu}-\text{Al}$	$\text{Mn}-\frac{1}{2}\text{Mo}-\frac{3}{4}\text{Ni}$	$3\frac{1}{2}\text{Ni}$
$1\text{Cr}-\frac{1}{5}\text{Mo}$	$\text{Mn}-\text{V}$	$3\frac{1}{2}\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\frac{1}{2}\text{Mn}$
$1\text{Cr}-\frac{1}{5}\text{Mo}-\text{Si}$	$\frac{1}{2}\text{Ni}-\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}$	$3\frac{1}{2}\text{Ni}-1\frac{3}{4}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$
$1\text{Cr}-\frac{1}{2}\text{Mo}$	$\frac{1}{2}\text{Ni}-\frac{1}{2}\text{Cr}-\frac{1}{4}\text{Mo}-\text{V}$	$4\text{Ni}-1\frac{1}{2}\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$
$1\text{Cr}-\frac{1}{2}\text{Mo}-\text{V}$	$\frac{1}{2}\text{Ni}-\frac{1}{2}\text{Mo}-\text{V}$	

NOTES (CONT'D):

(2) Group 2 alloys (by nominal composition):

18Cr-5Ni-3Mo-N	23Cr-4Ni-Mo-Cu	27Cr-7.5Ni-4.5Mo-Co-N
22Cr-2Ni-Mo-N	25Cr-6Ni-Mo-N	
22Cr-5Ni-3Mo-N	25Cr-7Ni-4Mo-N	

(3) Group 3 alloys (by nominal composition):

16Cr-12Ni-2Mo	18Cr-10Ni-Cb	18Cr-18Ni-2Si
16Cr-12Ni-2Mo-N	18Cr-10Ni-Ti	19Cr-9Ni-Mo-W
16Cr-12Ni-2Mo-Ti	18Cr-11Ni	21Cr-11Ni-N
18Cr-8Ni	18Cr-13Ni-3Mo	
18Cr-8Ni-N	18Cr-15Ni-4Si	

(4) Group 4 alloys (by nominal composition):

14Cr-16Ni-6Si-Cu-Mo	22Cr-13Ni-5Mn	25Cr-20Ni-2Mo
25Ni-15Cr-2Ti	23Cr-12Ni	31Ni-31Fe-29Cr-Mo
29Ni-20Cr-3Cu-2Mo	24Cr-22Ni-6Mo-2W-Cu-N	44Fe-25Ni-21Cr-Mo
18Cr-20Ni-5.5Si	25Cr-12Ni	47Fe-25Ni-23Cr-5.5Mo-N
20Cr-18Ni-6Mo	25Cr-20Ni	

Table TE-2
Thermal Expansion for Aluminum Alloys

Temperature, °F	Coefficients for Aluminum Alloys		
	A	B	C
70	12.1	12.1	0
100	12.6	12.4	0.45
150	13.2	12.7	1.2
200	13.5	13.0	2.0
250	13.7	13.1	2.8
300	14.0	13.3	3.7
350	14.3	13.4	4.5
400	14.7	13.6	5.4
450	15.1	13.8	6.3
500	15.3	13.9	7.2
550	15.4	14.1	8.1
600	15.2	14.2	9.0

GENERAL NOTES:

- (a) Aluminum alloys represented by these thermal expansion coefficients include:

A03560	A93003	A95254
A24430	A93004	A95454
A91060	A95052	A95456
A91100	A95083	A95652
A92014	A95086	A96061
A92024	A95154	A96063

- (b) Coefficient A is the instantaneous coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F). Coefficient B is the mean coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F) in going from 70°F to indicated temperature. Coefficient C is the linear thermal expansion (in./100 ft) in going from 70°F to indicated temperature.

Table TE-3
Thermal Expansion for Copper Alloys

Temperature, °F	Coefficients for Copper Alloys, C1XXXX Series			Coefficients for Bronze Alloys [Note (1)]			Coefficients for Brass Alloys [Note (2)]			Coefficients for Copper-Nickel (70Cu-30Ni) [Note (3)]			Coefficients for Copper-Nickel (90Cu-10Ni) [Note (4)]		
	A	B	C	A	B	C	A	B	C	A	B	C	A	B	C
70	9.3	9.3	0	9.6	9.6	0	9.3	9.3	0	8.1	8.1	0	...	...	...
100	9.5	9.4	0.34	9.8	9.7	0.35	9.6	9.4	0.34	8.3	8.2	0.30	...	...	...
150	9.6	9.5	0.91	10.1	9.9	0.95	9.9	9.6	0.92	8.6	8.4	0.81	...	...	...
200	9.7	9.6	1.5	10.2	10.0	1.6	10.1	9.8	1.5	8.8	8.5	1.3	...	...	...
250	9.9	9.6	2.1	10.3	10.1	2.2	10.3	9.9	2.1	9.0	8.6	1.9	...	...	...
300	10.0	9.7	2.7	10.4	10.1	2.8	10.5	10.0	2.8	9.2	8.7	2.4	...	...	...
350	10.1	9.8	3.3	10.4	10.2	3.4	10.8	10.1	3.4	9.4	8.8	3.0	...	...	...
400	10.2	9.8	3.9	10.5	10.2	4.0	11.1	10.2	4.1	9.5	8.9	3.5	...	...	...
450	10.3	9.9	4.5	10.6	10.3	4.7	11.3	10.4	4.7	9.7	9.0	4.1	...	...	...
500	10.3	9.9	5.1	10.8	10.3	5.3	11.5	10.5	5.4	9.7	9.1	4.7	...	...	...
550	10.3	10.0	5.7	10.9	10.4	6.0	11.6	10.6	6.1	9.6	9.1	5.3	9.5	9.5	5.5
600	10.4	10.0	6.4	11.0	10.4	6.6	11.7	10.7	6.8	9.5	9.2	5.8	...	...	...
650	...	...	...	11.1	10.5	7.3	11.9	10.8	7.5	9.3	9.2	6.4	...	...	...
700	...	...	...	11.1	10.5	8.0	12.2	10.9	8.2	9.2	9.2	7.0	...	...	...
750	...	...	...	11.1	10.6	8.6	13.0	11.0	9.0	...	...	...	...	...	...
800	...	...	...	11.0	10.6	9.3	14.5	11.2	9.8	...	...	...	...	...	...

GENERAL NOTE: Coefficient A is the instantaneous coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F). Coefficient B is the mean coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F) in going from 70°F to indicated temperature. Coefficient C is the linear thermal expansion (in./100 ft) in going from 70°F to indicated temperature.

NOTES:

- (1) Includes C6XXXX, C8XXXX, C92XXX, C93XXX, and C95XXX alloys.
- (2) Includes C2XXXX, C3XXXX, and C4XXXX alloys.
- (3) Includes C71XXX, C72XXX, and C97600 alloys.
- (4) Includes C70XXX and C96200 alloys.

Table TE-4
Thermal Expansion for Nickel Alloys

Temperature, °F	Coefficients for N02200 and N02201			Coefficients for N04400 and N04405			Coefficients for N06002		
	A	B	C	A	B	C	A	B	C
70	6.6	6.6	0	7.7	7.7	0	7.3	7.3	0
100	6.9	6.8	0.24	7.9	7.8	0.28	7.4	7.4	0.27
150	7.3	7.0	0.67	8.2	7.9	0.76	7.6	7.4	0.71
200	7.7	7.2	1.1	8.4	8.1	1.3	7.7	7.5	1.2
250	7.9	7.4	1.6	8.6	8.2	1.8	7.8	7.6	1.6
300	8.1	7.5	2.1	8.8	8.3	2.3	7.9	7.6	2.1
350	8.2	7.6	2.6	8.9	8.4	2.8	7.9	7.7	2.6
400	8.3	7.7	3.1	9.1	8.5	3.4	8.0	7.7	3.1
450	8.4	7.8	3.6	9.1	8.6	3.9	8.2	7.8	3.5
500	8.5	7.9	4.1	9.2	8.7	4.5	8.3	7.8	4.0
550	8.7	8.0	4.6	9.3	8.7	5.0	8.4	7.9	4.5
600	8.8	8.0	5.1	9.3	8.8	5.6	8.6	7.9	5.0
650	8.9	8.1	5.6	9.3	8.8	6.1	8.7	8.0	5.6
700	9.0	8.2	6.2	9.4	8.9	6.7	8.9	8.1	6.1
750	9.1	8.2	6.7	9.4	8.9	7.3	9.1	8.1	6.6
800	9.2	8.3	7.3	9.4	8.9	7.8	9.2	8.2	7.2
850	9.3	8.4	7.8	9.5	9.0	8.4	9.4	8.3	7.7
900	9.4	8.4	8.4	9.5	9.0	9.0	9.6	8.3	8.3
950	9.5	8.5	9.0	9.5	9.0	9.5	9.7	8.4	8.9
1,000	9.5	8.5	9.5	9.6	9.1	10.1	9.8	8.5	9.5
1,050	9.6	8.6	10.1	9.6	9.1	10.7	10.0	8.6	10.1
1,100	9.6	8.6	10.7	9.7	9.1	11.3	10.1	8.6	10.7
1,150	9.7	8.7	11.3	9.7	9.1	11.8	10.2	8.7	11.3
1,200	9.7	8.7	11.8	9.8	9.2	12.4	10.3	8.8	11.9
1,250	9.8	8.8	12.4	9.9	9.2	13.0	10.4	8.8	12.5
1,300	10.0	8.8	13.0	9.9	9.2	13.6	10.5	8.9	13.1
1,350	10.2	8.9	13.6	10.0	9.2	14.2	10.7	9.0	13.8
1,400	10.6	8.9	14.2	10.0	9.3	14.8	10.9	9.0	14.4
1,450	...	...	...	10.0	9.3	15.4	11.2	9.1	15.1
1,500	...	...	...	10.1	9.3	16.0	11.7	9.2	15.8
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N06007			Coefficients for N06022			Coefficients for N06030		
	A	B	C	A	B	C	A	B	C
70	7.4	7.4	0	6.9	6.9	0	6.7	6.7	0
100	7.5	7.4	0.27	6.9	6.9	0.25	6.9	6.8	0.24
150	7.5	7.5	0.72	6.9	6.9	0.66	7.3	7.0	0.67
200	7.6	7.5	1.2	6.9	6.9	1.1	7.6	7.1	1.1
250	7.7	7.5	1.6	6.9	6.9	1.5	7.8	7.3	1.6
300	7.7	7.6	2.1	6.9	6.9	1.9	8.0	7.4	2.1
350	7.8	7.6	2.6	6.9	6.9	2.3	8.2	7.6	2.5
400	8.0	7.7	3.0	7.0	6.9	2.7	8.4	7.7	3.0
450	8.1	7.7	3.5	7.1	6.9	3.2	8.5	7.8	3.5
500	8.3	7.8	4.0	7.3	7.0	3.6	8.6	7.9	4.1
550	8.6	7.8	4.5	7.4	7.0	4.0	8.7	8.0	4.6
600	8.8	7.9	5.0	7.6	7.0	4.5	8.8	8.0	5.1
650	9.0	8.0	5.6	7.8	7.1	4.9	8.9	8.1	5.6
700	9.3	8.1	6.1	8.1	7.2	5.4	9.0	8.2	6.2
750	9.5	8.2	6.7	8.3	7.2	5.9	9.1	8.2	6.7
800	9.8	8.3	7.3	8.6	7.3	6.4	9.3	8.3	7.3
850	10.0	8.4	7.9	8.8	7.4	6.9	9.4	8.4	7.8
900	10.1	8.5	8.5	9.1	7.5	7.5	9.6	8.4	8.4
950	10.2	8.6	9.1	9.3	7.6	8.0	9.8	8.5	9.0
1,000	10.3	8.7	9.7	9.6	7.7	8.6	10.0	8.6	9.6
1,050	10.4	8.8	10.3	9.8	7.8	9.2	10.1	8.7	10.2
1,100	10.4	8.8	10.9	10.0	7.9	9.8	10.2	8.7	10.8
1,150	10.4	8.9	11.6	10.2	8.0	10.4	10.2	8.8	11.4
1,200	10.3	9.0	12.2	10.4	8.1	11.0	10.1	8.9	12.0
1,250	10.4	9.0	12.8	10.5	8.2	11.6	9.7	8.9	12.6
1,300	10.5	9.1	13.4	10.7	8.3	12.2	9.2	8.9	13.2
1,350	10.7	9.2	14.1	10.9	8.4	12.9	8.3	8.9	13.7
1,400	11.1	9.2	14.7	11.2	8.5	13.6	7.0	8.9	14.2
1,450	11.8	9.3	15.4	11.5	8.6	14.2	...	...	...
1,500	12.9	9.4	16.1	11.9	8.7	14.9	...	...	...
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N06045			Coefficients for N06059 and N06686			Coefficients for N06230		
	A	B	C	A	B	C	A	B	C
70	6.1	6.1	0	6.5	6.5	0	6.9	6.9	0
100	6.6	6.4	0.23	6.5	6.5	0.23	6.9	6.9	0.25
150	7.4	6.8	0.65	6.6	6.5	0.62	7.0	6.9	0.66
200	8.0	7.1	1.1	6.7	6.6	1.0	7.1	7.0	1.1
250	8.3	7.4	1.6	6.8	6.6	1.4	7.2	7.0	1.5
300	8.6	7.7	2.1	6.9	6.7	1.8	7.3	7.1	2.0
350	8.8	7.8	2.6	7.0	6.7	2.3	7.4	7.1	2.4
400	8.8	8.0	3.2	7.1	6.8	2.7	7.5	7.2	2.8
450	8.9	8.1	3.7	7.2	6.8	3.1	7.6	7.2	3.3
500	8.9	8.2	4.2	7.2	6.9	3.6	7.7	7.3	3.7
550	8.9	8.3	4.8	7.3	6.9	4.0	7.9	7.3	4.2
600	8.9	8.3	5.3	7.3	7.0	4.4	8.0	7.4	4.7
650	9.0	8.4	5.8	7.3	7.0	4.9	8.1	7.4	5.2
700	9.1	8.4	6.4	7.4	7.0	5.3	8.3	7.5	5.7
750	9.2	8.5	6.9	7.4	7.0	5.7	8.4	7.6	6.2
800	9.3	8.5	7.5	7.5	7.1	6.2	8.5	7.6	6.7
850	9.5	8.6	8.0	7.6	7.1	6.6	8.7	7.7	7.2
900	9.7	8.7	8.6	7.7	7.1	7.1	8.8	7.7	7.7
950	9.9	8.7	9.2	7.7	7.2	7.6	8.9	7.8	8.2
1,000	10.1	8.8	9.8	7.6	7.2	8.0	8.9	7.9	8.8
1,050	10.3	8.9	10.4	7.3	7.2	8.5	9.0	7.9	9.3
1,100	10.5	8.9	11.0	...	7.2	8.9	9.1	8.0	9.9
1,150	10.7	9.0	11.7	...	...	...	9.1	8.0	10.4
1,200	10.8	9.1	12.3	...	...	...	9.2	8.1	11.0
1,250	10.9	9.2	13.0	...	...	...	9.3	8.1	11.5
1,300	11.0	9.2	13.6	...	...	...	9.3	8.2	12.1
1,350	11.0	9.3	14.3	...	...	...	9.5	8.2	12.6
1,400	11.0	9.4	15.0	...	...	...	9.6	8.3	13.2
1,450	11.0	9.4	15.6	...	...	...	9.9	8.3	13.8
1,500	11.1	9.5	16.3	...	...	...	10.2	8.4	14.4
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N06455			Coefficients for N06600			Coefficients for N06617		
	A	B	C	A	B	C	A	B	C
70	5.8	5.8	0	6.8	6.8	0	7.0	7.0	0.0
100	6.0	5.9	0.21	7.0	6.9	0.25	7.1	7.0	0.25
150	6.2	6.0	0.58	7.2	7.0	0.67	7.1	7.1	0.66
200	6.5	6.2	0.97	7.4	7.1	1.1	7.2	7.1	1.1
250	6.8	6.3	1.4	7.6	7.2	1.6	7.3	7.1	1.6
300	7.0	6.4	1.8	7.7	7.3	2.0	7.4	7.2	2.0
350	7.2	6.5	2.2	7.9	7.4	2.5	7.5	7.2	2.4
400	7.4	6.7	2.6	8.0	7.5	3.0	7.6	7.3	2.9
450	7.5	6.8	3.1	8.2	7.6	3.5	7.7	7.3	3.4
500	7.7	6.9	3.5	8.3	7.6	3.9	7.8	7.4	3.8
550	7.7	7.0	4.0	8.4	7.7	4.4	7.9	7.4	4.3
600	7.8	7.0	4.5	8.5	7.8	5.0	8.0	7.5	4.8
650	7.9	7.1	4.9	8.6	7.9	5.5	8.2	7.5	5.3
700	7.9	7.2	5.4	8.7	7.9	6.0	8.3	7.6	5.8
750	7.9	7.2	5.9	8.8	8.0	6.5	8.4	7.6	6.3
800	7.9	7.3	6.4	8.9	8.0	7.0	8.6	7.7	6.8
850	7.9	7.3	6.8	9.1	8.1	7.6	8.7	7.8	7.3
900	7.9	7.3	7.3	9.2	8.2	8.1	8.9	7.8	7.8
950	7.9	7.4	7.8	9.3	8.2	8.7	9.0	7.9	8.4
1,000	8.0	7.4	8.3	9.5	8.3	9.3	9.2	8.0	8.9
1,050	8.0	7.4	8.7	9.7	8.4	9.8	9.4	8.0	9.5
1,100	8.0	7.5	9.2	9.9	8.4	10.4	9.5	8.1	10.0
1,150	8.1	7.5	9.7	10.1	8.5	11.0	9.7	8.2	10.6
1,200	8.1	7.5	10.2	10.3	8.6	11.6	9.9	8.2	11.2
1,250	8.1	7.5	10.7	10.5	8.6	12.2	10.1	8.3	11.8
1,300	8.1	7.6	11.2	10.6	8.7	12.9	10.3	8.4	12.4
1,350	8.0	7.6	11.7	10.8	8.8	13.5	10.5	8.5	13.0
1,400	7.9	7.6	12.1	11.0	8.9	14.2	10.7	8.5	13.7
1,450	7.6	7.6	12.6	11.1	9.0	14.8	10.9	8.6	14.3
1,500	7.2	7.6	13.0	11.1	9.0	15.5	11.1	8.7	15.0
1,550	...	...	...	...	...	...	11.3	8.8	15.6
1,600	...	...	...	...	...	...	11.5	8.9	16.3
1,650	...	...	...	...	...	...	11.8	9.0	17.0
1,700	...	...	...	...	...	...	12.0	9.1	17.7
1,750	...	...	...	...	...	...	12.2	9.1	18.5

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N06625			Coefficients for N06690			Coefficients for N07718		
	A	B	C	A	B	C	A	B	C
70	6.7	6.7	0	7.7	7.7	0	7.1	7.1	0
100	6.9	6.8	0.24	7.8	7.8	0.28	7.1	7.1	0.26
150	7.2	7.0	0.67	7.9	7.8	0.75	7.2	7.2	0.69
200	7.4	7.1	1.1	8.0	7.9	1.2	7.4	7.2	1.1
250	7.4	7.2	1.6	8.0	7.9	1.7	7.5	7.3	1.6
300	7.5	7.2	2.0	8.1	7.9	2.2	7.6	7.3	2.0
350	7.5	7.3	2.4	8.2	8.0	2.7	7.7	7.4	2.5
400	7.5	7.3	2.9	8.3	8.0	3.2	7.9	7.5	3.0
450	7.5	7.3	3.3	8.5	8.1	3.7	8.0	7.5	3.4
500	7.5	7.4	3.8	8.6	8.1	4.2	8.0	7.6	3.9
550	7.6	7.4	4.2	8.7	8.2	4.7	8.1	7.6	4.4
600	7.7	7.4	4.7	8.7	8.2	5.2	8.2	7.7	4.9
650	7.8	7.4	5.2	8.7	8.3	5.8	8.3	7.7	5.4
700	8.0	7.5	5.6	8.5	8.3	6.3	8.4	7.8	5.9
750	8.2	7.5	6.1	8.3	8.3	6.8	8.5	7.8	6.4
800	8.4	7.6	6.6	8.1	8.3	7.3	8.6	7.9	6.9
850	8.7	7.6	7.1	...	...	...	8.7	7.9	7.4
900	8.9	7.7	7.7	...	...	...	8.8	8.0	7.9
950	9.1	7.8	8.2	...	...	...	8.9	8.0	8.5
1,000	9.4	7.9	8.8	...	...	...	9.1	8.1	9.0
1,050	9.6	7.9	9.3	...	...	...	9.2	8.1	9.6
1,100	9.8	8.0	9.9	...	...	...	9.4	8.2	10.1
1,150	9.9	8.1	10.5	...	...	...	...	...	...
1,200	10.1	8.2	11.1	...	...	...	...	...	...
1,250	10.2	8.3	11.7	...	...	...	...	...	...
1,300	10.4	8.4	12.3	...	...	...	...	...	...
1,350	10.5	8.4	13.0	...	...	...	...	...	...
1,400	10.7	8.5	13.6	...	...	...	...	...	...
1,450	10.9	8.6	14.2	...	...	...	...	...	...
1,500	11.3	8.7	14.9	...	...	...	...	...	...
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N07750			Coefficients for N08031 and N08367			Coefficients for N08330		
	A	B	C	A	B	C	A	B	C
70	6.7	6.7	0	7.7	7.7	0	8.1	8.1	0
100	6.8	6.8	0.24	7.8	7.7	0.28	8.2	8.1	0.29
150	7.1	6.9	0.66	7.9	7.8	0.75	8.3	8.2	0.79
200	7.3	7.0	1.1	8.1	7.9	1.2	8.5	8.3	1.3
250	7.5	7.1	1.5	8.3	8.0	1.7	8.7	8.4	1.8
300	7.7	7.2	2.0	8.4	8.0	2.2	8.8	8.5	2.3
350	7.8	7.3	2.5	8.5	8.1	2.7	8.9	8.5	2.9
400	7.8	7.4	2.9	8.7	8.2	3.2	9.0	8.6	3.4
450	7.8	7.4	3.4	8.7	8.3	3.8	9.1	8.7	4.0
500	7.7	7.5	3.9	8.8	8.3	4.3	9.2	8.7	4.5
550	7.7	7.5	4.3	8.9	8.4	4.8	9.3	8.8	5.1
600	7.7	7.5	4.8	9.0	8.4	5.4	9.5	8.8	5.6
650	7.8	7.6	5.3	9.0	8.5	5.9	9.7	8.9	6.2
700	8.1	7.6	5.7	9.1	8.5	6.4	9.9	9.0	6.8
750	8.6	7.6	6.2	9.2	8.6	7.0	9.9	9.0	7.4
800	9.4	7.7	6.8	9.3	8.6	7.6	9.6	9.1	8.0
850	...	...	...	9.3	8.7	8.1	...	...	...
900	...	...	...	9.4	8.7	8.7	...	...	...
950	...	...	...	9.4	8.7	9.2	...	...	...
1,000	...	...	...	9.3	8.8	9.8	...	...	...
1,050	...	...	...	9.1	8.8	10.3	...	...	...
1,100	...	...	...	8.8	8.8	10.9	...	...	...
1,150	...	...	...	...	...	...	...	...	...
1,200	...	...	...	...	...	...	...	...	...
1,250	...	...	...	...	...	...	...	...	...
1,300	...	...	...	...	...	...	...	...	...
1,350	...	...	...	...	...	...	...	...	...
1,400	...	...	...	...	...	...	...	...	...
1,450	...	...	...	...	...	...	...	...	...
1,500	...	...	...	...	...	...	...	...	...
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N08354			Coefficients for N08800, N08801, N08810, and N08811			Coefficients for N08825		
	A	B	C	A	B	C	A	B	C
70	7.6	7.6	0	7.9	7.9	0	7.5	7.5	0
100	7.8	7.7	0.30	8.1	8.0	0.29	7.6	7.5	0.27
150	7.9	7.8	0.77	8.5	8.2	0.79	7.8	7.6	0.73
200	8.0	7.9	1.2	8.7	8.4	1.3	8.0	7.7	1.2
250	8.1	7.9	1.7	8.9	8.5	1.8	8.1	7.8	1.7
300	8.2	8.0	2.2	9.1	8.6	2.4	8.2	7.9	2.2
350	8.3	8.0	2.7	9.2	8.7	2.9	8.2	7.9	2.7
400	8.4	8.1	3.2	9.3	8.8	3.5	8.3	8.0	3.2
450	8.5	8.1	3.7	9.4	8.9	4.0	8.3	8.0	3.7
500	8.6	8.2	4.2	9.5	8.9	4.6	8.5	8.1	4.2
550	7.7	8.2	4.8	9.5	9.0	5.2	8.7	8.1	4.7
600	8.7	8.3	5.3	9.6	9.0	5.7	8.9	8.2	5.2
650	8.8	8.3	5.8	9.7	9.1	6.3	9.2	8.3	5.8
700	8.9	8.4	6.3	9.7	9.1	6.9	9.2	8.3	6.3
750	9.1	8.4	6.9	9.8	9.2	7.5	8.9	8.4	6.9
800	9.1	8.4	7.4	9.9	9.2	8.1	7.8	8.4	7.4
850	...	...	...	10.0	9.3	8.7	...	...	...
900	...	...	...	10.1	9.3	9.3	...	...	...
950	...	...	...	10.2	9.4	9.9	...	...	...
1,000	...	...	...	10.3	9.4	10.5	...	...	...
1,050	...	...	...	10.4	9.5	11.1	...	...	...
1,100	...	...	...	10.5	9.5	11.8	...	...	...
1,150	...	...	...	10.6	9.6	12.4	...	...	...
1,200	...	...	...	10.8	9.6	13.0	...	...	...
1,250	...	...	...	10.9	9.7	13.7	...	...	...
1,300	...	...	...	11.1	9.7	14.4	...	...	...
1,350	...	...	...	11.3	9.8	15.0	...	...	...
1,400	...	...	...	11.6	9.8	15.7	...	...	...
1,450	...	...	...	11.9	9.9	16.4	...	...	...
1,500	...	...	...	12.4	10.0	17.1	...	...	...
1,550	...	...	...	13.0	10.1	17.9	...	...	...
1,600	...	...	...	13.7	10.2	18.7	...	...	...
1,650	...	...	...	14.7	10.3	19.6	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N10001			Coefficients for N10003			Coefficients for N10242		
	A	B	C	A	B	C	A	B	C
70	6.0	6.0	0	6.2	6.2	0	5.8	5.8	0
100	6.2	6.1	0.22	6.3	6.2	0.22	5.9	5.8	0.21
150	6.3	6.2	0.60	6.5	6.3	0.60	6.0	5.9	0.57
200	6.4	6.3	0.98	6.6	6.4	1.0	6.2	6.0	0.94
250	6.5	6.3	1.4	6.8	6.5	1.4	6.4	6.1	1.3
300	6.5	6.3	1.8	6.9	6.6	1.8	6.5	6.1	1.7
350	6.5	6.4	2.1	7.0	6.6	2.2	6.7	6.2	2.1
400	6.5	6.4	2.5	7.0	6.7	2.6	6.8	6.3	2.5
450	6.6	6.4	2.9	7.1	6.7	3.1	6.9	6.4	2.9
500	6.6	6.4	3.3	7.1	6.8	3.5	7.0	6.5	3.3
550	6.7	6.5	3.7	7.2	6.8	3.9	7.0	6.5	3.8
600	6.9	6.5	4.1	7.4	6.9	4.4	7.0	6.6	4.2
650	7.0	6.5	4.5	7.6	6.9	4.8	7.0	6.6	4.6
700	7.2	6.6	5.0	7.7	7.0	5.3	7.0	6.6	5.0
750	7.4	6.6	5.4	7.8	7.0	5.7	7.0	6.7	5.4
800	7.6	6.7	5.9	7.7	7.1	6.2	7.0	6.7	5.8
850	7.7	6.7	6.3	...	...	...	7.0	6.7	6.3
900	7.9	6.8	6.8	...	...	...	7.0	6.7	6.7
950	8.1	6.9	7.3	...	...	...	7.2	6.7	7.1
1,000	8.2	6.9	7.7	...	...	...	7.3	6.8	7.5
1,050	8.4	7.0	8.2	...	...	...	7.6	6.8	8.0
1,100	8.5	7.1	8.8	...	...	...	8.0	6.8	8.5
1,150	8.6	7.1	9.3	...	...	...	8.4	6.9	9.0
1,200	8.7	7.2	9.8	...	...	...	9.0	7.0	9.5
1,250	8.8	7.3	10.3	...	...	...	9.8	7.1	10.0
1,300	9.0	7.3	10.8	...	...	...	10.6	7.2	10.6
1,350	9.3	7.4	11.4	...	...	...	11.7	7.4	11.3
1,400	9.8	7.5	12.0	...	...	...	12.9	7.6	12.1
1,450	10.4	7.6	12.6	...	...	...	14.2	7.8	12.9
1,500	11.3	7.7	13.2	...	...	...	15.8	8.0	13.8
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N10276			Coefficients for N10629			Coefficients for N10665		
	A	B	C	A	B	C	A	B	C
70	6.0	6.0	0	5.5	5.5	0	5.3	5.3	0
100	6.1	6.1	0.22	5.6	5.5	0.20	5.5	5.4	0.19
150	6.4	6.2	0.60	5.8	5.6	0.54	5.8	5.6	0.54
200	6.6	6.3	0.98	5.9	5.7	0.89	6.0	5.7	0.89
250	6.8	6.4	1.4	6.0	5.8	1.2	6.1	5.8	1.3
300	7.0	6.5	1.8	6.2	5.9	1.6	6.2	5.9	1.6
350	7.2	6.6	2.2	6.3	5.9	2.0	6.3	6.0	2.0
400	7.3	6.7	2.7	6.3	6.0	2.4	6.4	6.0	2.4
450	7.5	6.8	3.1	6.4	6.0	2.7	6.5	6.1	2.8
500	7.7	6.9	3.6	6.5	6.1	3.1	6.5	6.1	3.2
550	7.8	7.0	4.0	6.6	6.1	3.5	6.6	6.2	3.6
600	7.9	7.1	4.5	6.7	6.2	3.9	6.7	6.2	4.0
650	8.0	7.1	5.0	6.8	6.2	4.3	6.9	6.3	4.4
700	8.1	7.2	5.5	6.8	6.3	4.7	7.0	6.3	4.8
750	8.2	7.3	5.9	6.9	6.3	5.2	7.1	6.4	5.2
800	8.3	7.4	6.4	6.9	6.4	5.6	7.2	6.4	5.6
850	8.4	7.4	6.9	6.9	6.4	6.0	7.3	6.5	6.1
900	8.5	7.5	7.5	7.0	6.4	6.4	7.3	6.5	6.5
950	8.6	7.5	8.0	7.0	6.5	6.8	7.3	6.6	6.9
1,000	8.7	7.6	8.5	7.0	6.5	7.2	7.3	6.6	7.4
1,050	8.8	7.7	9.0	7.0	6.5	7.7	7.2	6.6	7.8
1,100	8.9	7.7	9.5	7.1	6.5	8.1	7.1	6.7	8.2
1,150	8.9	7.8	10.1	7.2	6.6	8.5	7.0	6.7	8.7
1,200	9.0	7.8	10.6	...	...	...	6.9	6.7	9.1
1,250	9.1	7.9	11.2	...	...	...	6.8	6.7	9.5
1,300	9.2	7.9	11.7	...	...	...	6.8	6.7	9.9
1,350	9.2	8.0	12.3	...	...	...	7.0	6.7	10.3
1,400	9.3	8.0	12.8	...	...	...	7.3	6.7	10.7
1,450	9.2	8.1	13.4	...	...	...	7.9	6.8	11.2
1,500	9.2	8.1	13.9	...	...	...	8.8	6.8	11.7
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

Table TE-4
Thermal Expansion for Nickel Alloys (Cont'd)

Temperature, °F	Coefficients for N10675			Coefficients for N12160			Coefficients for R20033		
	A	B	C	A	B	C	A	B	C
70	...	5.7	0	6.9	6.9	0	7.8	7.8	0
100	...	5.7	0.21	7.0	7.0	0.25	7.9	7.9	0.28
150	...	5.8	0.56	7.3	7.1	0.68	8.2	8.0	0.77
200	...	5.8	0.90	7.5	7.2	1.1	8.4	8.1	1.3
250	...	5.9	1.3	7.7	7.3	1.6	8.6	8.2	1.8
300	...	5.9	1.6	7.9	7.4	2.0	8.7	8.3	2.3
350	...	6.0	2.0	8.1	7.5	2.5	8.8	8.4	2.8
400	...	6.1	2.4	8.2	7.6	3.0	8.7	8.5	3.3
450	...	6.1	2.8	8.3	7.7	3.5	8.7	8.5	3.9
500	...	6.2	3.2	8.4	7.8	4.0	8.6	8.5	4.4
550	...	6.3	3.6	8.5	7.9	4.5	8.7	8.5	4.9
600	...	6.3	4.0	8.6	7.9	5.0	8.8	8.5	5.4
650	...	6.4	4.4	8.6	8.0	5.6	9.0	8.6	6.0
700	...	6.4	4.9	8.7	8.0	6.1	9.4	8.6	6.5
750	...	6.5	5.3	8.7	8.1	6.6	9.7	8.7	7.1
800	...	6.5	5.7	8.8	8.1	7.1	9.9	8.8	7.7
850	...	6.5	6.1	8.9	8.2	7.7	9.9	8.8	8.3
900	...	6.5	6.5	9.0	8.2	8.2	9.3	8.9	8.9
950	...	6.5	6.9	9.2	8.3	8.7	...	...	...
1,000	...	6.5	7.3	9.3	8.3	9.3	...	...	...
1,050	...	6.6	7.7	9.5	8.4	9.9	...	...	...
1,100	...	6.6	8.1	9.8	8.4	10.4	...	...	...
1,150	...	6.6	8.5	10.1	8.5	11.0	...	...	...
1,200	...	6.6	9.0	10.4	8.6	11.6	...	...	...
1,250	...	6.7	9.4	10.6	8.7	12.3	...	...	...
1,300	...	6.7	9.9	10.9	8.8	12.9	...	...	...
1,350	...	6.8	10.5	11.1	8.8	13.6	...	...	...
1,400	...	7.0	11.1	11.2	8.9	14.2	...	...	...
1,450	...	7.2	11.9	11.2	9.0	14.9	...	...	...
1,500	...	7.4	12.7	10.9	9.1	15.6	...	...	...
1,550	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...

GENERAL NOTE: Coefficient A is the instantaneous coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F). Coefficient B is the mean coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F) in going from 70°F to indicated temperature. Coefficient C is the linear thermal expansion (in./100 ft) in going from 70°F to indicated temperature.

Table TE-5
Thermal Expansion for Titanium Alloys

Temperature, °F	Coefficients for Titanium Alloy, Grades 1, 2, 2H, 3, 7, 7H, 11, 12, 16, 16H, 17, 26, 26H, and 27			Coefficients for Titanium Alloy, Grades 9 and 28			Coefficients for Titanium Alloy, Grade 38		
	A	B	C	A	B	C	A	B	C
70	4.6	4.6	0	4.7	4.7	0	4.8	4.8	0
100	4.7	4.7	0.17	4.8	4.7	0.17	4.9	4.9	0.18
150	4.8	4.7	0.45	4.8	4.8	0.46	4.9	4.9	0.47
200	4.8	4.7	0.73	4.9	4.8	0.75	5.0	5.0	0.78
250	4.8	4.8	1.0	5.1	4.9	1.1	5.0	5.0	1.1
300	4.9	4.8	1.3	5.2	4.9	1.4	5.1	5.0	1.4
350	4.9	4.8	1.6	5.3	5.0	1.7	5.1	5.0	1.7
400	5.0	4.8	1.9	5.3	5.0	2.0	5.2	5.0	2.0
450	5.0	4.8	2.2	5.3	5.1	2.3	5.2	5.0	2.3
500	5.1	4.9	2.5	5.3	5.1	2.6	5.3	5.1	2.6
550	5.1	4.9	2.8	5.5	5.1	2.9	5.3	5.1	2.9
600	5.2	4.9	3.1	6.4	5.2	3.3	5.4	5.1	3.2
650	5.3	4.9	3.4	...	...	...	5.4	5.1	3.5
700	5.5	5.0	3.8	...	...	...	5.4	5.2	3.9
750	5.9	5.0	4.1	...	...	...	5.5	5.2	4.2
800	6.6	5.1	4.5	...	...	...	5.5	5.2	4.6

GENERAL NOTE: Coefficient A is the instantaneous coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F). Coefficient B is the mean coefficient of thermal expansion $\times 10^{-6}$ (in./in./°F) in going from 70°F to indicated temperature. Coefficient C is the linear thermal expansion (in./100 ft) in going from 70°F to indicated temperature.

(25)

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal Diffusivity (TD)

Temp., °F	Carbon and Low Alloy Steels		Carbon and Low Alloy Steels		Carbon and Low Alloy Steels		Carbon and Low Alloy Steels		Carbon and Low Alloy Steels	
	Material Group A [Note (1)] Plain Carbon		Material Group B [Note (2)]		Material Group C [Note (3)]		Material Group D [Note (4)]		Material Group E [Note (5)]	
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	34.9	0.700	27.3	0.530	23.7	0.459	21.0	0.408	15.9	0.311
100	34.7	0.676	27.6	0.520	23.6	0.451	21.0	0.401	16.2	0.311
150	34.2	0.641	27.8	0.504	23.5	0.437	21.2	0.392	16.7	0.312
200	33.7	0.611	27.8	0.487	23.5	0.424	21.3	0.384	17.1	0.313
250	33.0	0.585	27.6	0.471	23.4	0.412	21.4	0.377	17.5	0.312
300	32.3	0.560	27.3	0.455	23.4	0.401	21.5	0.371	17.8	0.311
350	31.6	0.537	26.9	0.440	23.3	0.390	21.5	0.364	18.0	0.308
400	30.9	0.516	26.5	0.426	23.1	0.379	21.5	0.357	18.2	0.304
450	30.1	0.495	26.1	0.412	23.0	0.368	21.5	0.350	18.4	0.299
500	29.4	0.474	25.7	0.399	22.7	0.357	21.4	0.342	18.5	0.294
550	28.7	0.454	25.3	0.386	22.5	0.347	21.3	0.333	18.5	0.287
600	28.0	0.433	24.9	0.373	22.2	0.336	21.1	0.324	18.5	0.280
650	27.3	0.414	24.5	0.360	21.9	0.325	20.9	0.314	18.5	0.273
700	26.6	0.394	24.1	0.346	21.6	0.314	20.7	0.304	18.5	0.265
750	26.0	0.375	23.7	0.333	21.3	0.303	20.5	0.294	18.4	0.258
800	25.3	0.356	23.2	0.319	21.0	0.292	20.2	0.284	18.3	0.250
850	24.6	0.337	22.8	0.305	20.6	0.281	20.0	0.274	18.2	0.242
900	23.8	0.318	22.3	0.291	20.3	0.269	19.7	0.263	18.1	0.234
950	23.1	0.301	21.7	0.277	20.0	0.258	19.4	0.253	17.9	0.226
1,000	22.4	0.283	21.1	0.263	19.7	0.247	19.1	0.242	17.8	0.217
1,050	21.6	0.266	20.5	0.250	19.4	0.235	18.8	0.230	17.6	0.208
1,100	20.9	0.249	19.8	0.234	19.1	0.223	18.5	0.218	17.4	0.199
1,150	20.1	0.232	19.0	0.219	18.7	0.212	18.3	0.205	17.2	0.188
1,200	19.4	0.215	18.3	0.204	18.3	0.200	18.0	0.192	17.0	0.177
1,250	18.6	0.199	17.6	0.185	17.7	0.183	17.7	0.177	16.8	0.164
1,300	17.9	0.179	16.9	0.157	16.6	0.164	17.3	0.160	16.5	0.150
1,350	17.2	0.138	16.2	0.120	15.7	0.137	16.3	0.137	16.2	0.135
1,400	16.6	0.083	15.7	0.078	15.3	0.077	15.6	0.073	15.8	0.117
1,450	16.0	0.155	15.2	0.160	15.1	0.128	15.4	0.124	15.6	0.143
1,500	15.5	0.166	14.9	0.172	15.1	0.200	15.3	0.197	15.7	0.161
1,550	...	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal Diffusivity (TD) (Cont'd)

Temp., °F	Carbon and Low Alloy Steels (Cont'd)		Ductile Cast Iron		High Chrome Steels		High Chrome Steels		High Alloy Steels		High Alloy Steels	
	Material Group F [Note (6)]		Material Group G [Note (7)]		Material Group H [Note (8)]		Material Group I [Note (9)]		Material Group J [Note (10)]			
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	12.8	0.256	21.7	0.439	14.2	0.276	11.6	0.221	10.0	0.188	8.6	0.151
100	13.1	0.257	22.0	0.445	14.2	0.271	11.6	0.220	10.1	0.189	8.7	0.152
150	13.6	0.258	22.5	0.455	14.3	0.265	11.7	0.217	10.3	0.189	9.0	0.154
200	14.0	0.260	22.9	0.463	14.3	0.260	11.7	0.214	10.6	0.190	9.3	0.156
250	14.4	0.261	23.2	0.430	14.4	0.256	11.8	0.211	10.9	0.190	9.6	0.158
300	14.7	0.262	23.4	0.434	14.4	0.251	11.8	0.208	11.2	0.190	9.8	0.160
350	15.0	0.262	23.5	0.436	14.4	0.246	11.9	0.205	11.5	0.190	10.1	0.162
400	15.2	0.260	23.5	0.436	14.5	0.242	11.9	0.203	11.7	0.190	10.4	0.165
450	15.4	0.258	23.5	0.436	14.5	0.237	12.0	0.200	12.0	0.190	10.6	0.167
500	15.6	0.254	23.4	0.434	14.5	0.231	12.0	0.198	12.3	0.190	10.9	0.169
550	15.8	0.250	23.3	0.399	14.6	0.226	12.1	0.195	12.5	0.190	11.1	0.172
600	15.9	0.245	23.1	0.396	14.6	0.221	12.2	0.193	12.8	0.189	11.3	0.174
650	16.0	0.239	23.0	0.394	14.6	0.216	12.2	0.190	13.0	0.188	11.6	0.177
700	16.0	0.233	...	...	14.6	0.210	12.3	0.187	13.1	0.187	11.8	0.179
750	16.1	0.227	...	...	14.6	0.205	12.3	0.183	13.3	0.184	12.0	0.182
800	16.1	0.220	...	...	14.7	0.200	12.4	0.179	13.4	0.181	12.3	0.184
850	16.1	0.214	...	...	14.7	0.196	12.5	0.174	13.6	0.177	12.5	0.186
900	16.1	0.207	...	...	14.7	0.191	12.6	0.169	13.7	0.171	12.7	0.189
950	16.1	0.200	...	...	14.7	0.186	12.6	0.163	13.8	0.166	12.9	0.191
1,000	16.1	0.193	...	...	14.7	0.180	12.7	0.158	13.9	0.159	13.1	0.194
1,050	16.0	0.185	...	...	14.7	0.174	12.8	0.153	14.0	0.152	13.4	0.196
1,100	16.0	0.176	...	...	14.7	0.167	12.9	0.148	14.0	0.144	13.6	0.198
1,150	15.9	0.166	...	...	14.8	0.159	13.0	0.152	14.1	0.136	13.8	0.201
1,200	15.8	0.155	...	...	14.8	0.149	13.1	0.159	14.3	0.130	14.0	0.203
1,250	15.7	0.142	...	...	14.8	0.137	13.2	0.168	14.4	0.138	14.3	0.205
1,300	15.6	0.127	...	...	14.8	0.123	13.4	0.176	14.5	0.153	14.5	0.208
1,350	15.4	0.111	...	...	14.8	0.107	13.5	0.183	14.7	0.171	14.7	0.210
1,400	15.3	0.147	...	...	14.8	0.158	13.7	0.189	14.9	0.185	14.9	0.212
1,450	15.1	0.165	...	...	14.8	0.172	13.8	0.194	15.2	0.194	15.1	0.214
1,500	14.9	0.177	...	...	14.9	0.173	14.0	0.199	15.5	0.200	15.3	0.216
1,550	...	...	...	...	...	...	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...	...	...

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal
Diffusivity (TD) (Cont'd)

Temp., °F	High Alloy Steels (Cont'd)		High Alloy Steels		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys	
	Material Group K [Note (11)]		Material Group L [Note (12)]		Nickel N02200		Low C-Nickel N02201		Ni-Cu N04400	
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	8.2	0.139	6.4	0.115	...	...	...	...	12.6	0.224
100	8.3	0.140	6.6	0.116	...	...	...	...	12.9	0.228
150	8.6	0.142	6.9	0.118	...	...	...	...	13.4	0.234
200	8.8	0.145	7.1	0.121	38.7	...	42.5	...	13.9	0.241
250	9.1	0.147	7.4	0.124	38.0	...	41.8	...	14.5	0.247
300	9.3	0.150	7.7	0.126	37.2	...	40.7	...	15.0	0.254
350	9.5	0.152	8.0	0.129	36.3	...	39.5	...	15.6	0.261
400	9.8	0.155	8.2	0.132	35.5	...	38.2	...	16.1	0.268
450	10.0	0.157	8.5	0.135	34.8	...	37.0	...	16.6	0.275
500	10.2	0.160	8.8	0.138	34.1	...	35.9	...	17.0	0.280
550	10.5	0.162	9.1	0.141	33.3	...	35.0	...	17.5	0.285
600	10.7	0.165	9.3	0.143	32.5	...	34.2	...	17.9	0.289
650	10.9	0.167	9.6	0.146	31.8	...	33.7	...	18.4	0.291
700	11.2	0.170	9.9	0.149	31.7	...	33.3	...	18.9	0.292
750	11.4	0.172	10.1	0.152	32.2	...	33.1	...	19.3	0.293
800	11.6	0.175	10.4	0.155	32.5	...	33.0	...	19.9	0.293
850	11.9	0.177	10.7	0.158	32.8	...	33.1	...	20.4	...
900	12.1	0.180	10.9	0.161	33.1	...	33.3	...	20.9	...
950	12.3	0.182	11.2	0.164	33.4	...	33.6	...	21.5	...
1,000	12.5	0.184	11.4	0.167	33.8	...	34.0	...	22.0	...
1,050	12.8	0.187	11.7	0.170	...	...	34.4	...	...	...
1,100	13.0	0.189	11.9	0.173	...	...	34.9	...	...	...
1,150	13.2	0.191	12.2	0.176	...	...	35.3	...	...	...
1,200	13.4	0.194	12.5	0.178	...	...	35.7	...	...	...
1,250	13.6	0.196	12.7	0.181	...	...	36.1	...	...	...
1,300	13.8	0.198	13.0	0.184	...	...	36.4	...	...	...
1,350	14.1	0.200	13.2	0.186	...	...	36.7	...	...	...
1,400	14.3	0.203	13.5	0.188	...	...	37.0	...	...	...
1,450	14.5	0.205	13.7	0.190	...	...	37.4	...	...	...
1,500	14.7	0.207	14.0	0.191	...	...	37.8	...	...	...
1,550	...	...	...	0.192	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal
Diffusivity (TD) (Cont'd)

	High Nickel Alloys (Cont'd)		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys	
	Ni-Cu N04405		Ni-Cr-Mo-Fe N06002		Ni-Cr-Fe- Mo-Cu N06007		N06022		N06030	
Temp., °F	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	12.6	...	5.2	0.088	5.8	0.117	5.6	...	5.9	...
100	12.9	...	5.5	0.092	6.0	0.116	5.8	...	6.1	...
150	13.4	...	5.9	0.098	6.2	0.116	6.0	...	6.5	...
200	13.9	...	6.3	0.105	6.4	0.116	6.4	...	6.9	...
250	14.5	...	6.6	0.111	6.7	0.118	6.7	...	7.3	...
300	15.0	...	7.0	0.116	6.9	0.120	7.0	...	7.6	...
350	15.6	...	7.3	0.122	7.2	0.122	7.4	...	8.0	...
400	16.1	...	7.6	0.127	7.4	0.125	7.8	...	8.4	...
450	16.6	...	7.9	0.132	7.7	0.128	8.1	...	8.7	...
500	17.0	...	8.2	0.136	7.9	0.131	8.5	...	9.1	...
550	17.5	...	8.5	0.141	8.2	0.133	8.8	...	9.5	...
600	17.9	...	8.8	0.145	8.4	0.136	9.1	...	9.8	...
650	18.4	...	9.1	0.149	8.6	0.139	9.4	...	10.2	...
700	18.9	...	9.4	0.153	8.9	0.142	9.7	...	10.5	...
750	19.3	...	9.7	0.156	9.2	0.145	10.1	...	10.8	...
800	19.9	...	10.1	0.160	9.4	0.148	10.4	...	11.1	...
850	20.4	...	10.4	0.163	9.7	0.151	10.7	...	11.4	...
900	20.9	...	10.7	0.166	9.9	0.154	11.0	...	11.6	...
950	21.5	...	11.0	0.169	10.2	0.157	11.4	...	11.9	...
1,000	22.0	...	11.4	0.172	10.5	0.160	11.7	...	12.1	...
1,050	...	...	11.7	0.174	10.7	0.163	12.0	...	12.2	...
1,100	...	...	12.0	0.176	10.9	0.166	12.3	...	12.4	...
1,150	...	...	12.3	0.178	11.1	0.168	...	...	...	...
1,200	...	...	12.6	0.180	11.2	0.171	...	...	...	...
1,250	...	...	12.9	0.182	...	...	...	...	...	...
1,300	...	...	13.2	0.183	...	...	...	...	...	...
1,350	...	...	13.5	0.183	...	...	...	...	...	...
1,400	...	...	13.8	0.184	...	...	...	...	...	...
1,450	...	...	14.2	0.183	...	...	...	...	...	...
1,500	...	...	14.6	0.182	...	...	...	...	...	...
1,550	...	...	...	0.181	...	...	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal Diffusivity (TD) (Cont'd)

Temp., °F	High Nickel Alloys (Cont'd)		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys	
	N06045		N06059		N06230		Ni-Mo-Cr-Low C N06455 and N06686		Ni-Cr-Fe N06600		52Ni-22Cr-13Co-9Mo N06617	
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	7.5	0.125	6.0	0.113	5.2	0.095	5.8	0.110	8.6	0.154	6.1	0.112
100	...	...	6.3	...	5.4	0.097	5.9	0.112	8.7	0.154	6.3	0.114
150	...	...	6.6	...	5.6	0.100	6.2	0.115	8.9	0.155	6.6	0.118
200	...	...	6.9	...	5.9	0.104	6.5	0.118	9.1	0.156	6.9	0.122
250	...	...	7.2	...	6.2	0.107	6.8	0.121	9.3	0.158	7.2	0.125
300	...	...	7.4	...	6.6	0.111	7.1	0.124	9.6	0.160	7.5	0.129
350	...	...	7.7	...	6.9	0.114	7.4	0.127	9.8	0.163	7.8	0.132
400	...	...	7.9	...	7.2	0.117	7.7	0.130	10.1	0.165	8.1	0.136
450	...	...	8.2	...	7.5	0.121	8.0	0.134	10.3	0.168	8.4	0.139
500	...	...	8.5	...	7.9	0.124	8.2	0.137	10.6	0.170	8.7	0.142
550	...	...	8.7	...	8.2	0.127	8.5	0.140	10.8	0.172	9.0	0.145
600	...	...	9.0	...	8.5	0.130	8.8	0.144	11.1	0.175	9.3	0.149
650	...	...	9.3	...	8.9	0.133	9.1	0.147	11.3	0.177	9.5	0.152
700	...	...	9.5	...	9.2	0.136	9.3	0.151	11.6	0.179	9.8	0.155
750	...	...	9.8	...	9.5	0.139	9.6	0.154	11.8	0.181	10.0	0.158
800	...	...	10.1	...	9.8	0.141	9.9	0.158	12.1	0.183	10.3	0.161
850	...	...	10.3	...	10.2	0.144	10.2	0.161	12.4	0.184	10.5	0.164
900	...	...	10.6	...	10.5	0.147	10.5	0.165	12.6	0.186	10.8	0.167
950	...	...	10.8	...	10.8	0.150	10.8	0.169	12.9	0.188	11.0	0.171
1,000	...	...	11.1	...	11.1	0.152	11.1	0.173	13.2	0.189	11.3	0.174
1,050	...	...	11.4	...	11.4	0.155	11.5	0.177	13.4	0.191	12.1	0.177
1,100	...	...	11.7	...	11.7	0.158	11.8	0.181	13.7	0.192	13.2	0.181
1,150	...	...	...	...	12.0	0.160	12.1	0.185	14.0	0.194	14.1	0.184
1,200	...	...	...	...	12.3	0.163	12.5	0.189	14.3	0.196	14.6	0.188
1,250	...	...	...	...	12.7	0.165	...	...	14.6	0.197	14.9	0.192
1,300	...	...	...	...	13.0	0.166	...	...	14.9	0.199	14.8	0.194
1,350	...	...	...	...	13.3	0.168	...	...	15.2	0.201	14.7	0.191
1,400	...	...	...	...	13.6	0.168	...	...	15.5	0.204	14.6	0.189
1,450	...	...	...	...	13.9	0.168	...	...	15.8	0.206	14.5	0.188
1,500	...	...	...	...	14.2	0.167	...	...	16.0	0.208	14.6	0.189
1,550	...	...	...	...	...	...	...	...	...	0.210	14.7	0.191
1,600	...	...	...	...	...	...	...	...	...	...	14.9	0.193
1,650	...	...	...	...	...	...	...	...	...	...	15.1	0.196
1,700	...	...	...	...	...	...	...	...	...	...	15.5	0.199
1,750	...	...	...	...	...	...	...	...	...	...	15.9	0.203

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal
Diffusivity (TD) (Cont'd)

Temp., °F	High Nickel Alloys (Cont'd)		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys	
	Ni-Cr-Mo-Cb N06625		Ni-Cr-Fe N06690		Ni-Cr-Fe- Mo-Cb N07718		70Ni-16Cr- 7Fe- Ti-Al N07750		Cr-Ni-Fe-Mo- Cu-Cb N08020	
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	5.7	0.110	6.8	0.125	6.4	0.119	6.9	0.132	...	0.121
100	5.8	0.113	7.0	0.127	6.6	0.122	7.0	0.132	6.9	0.123
150	6.0	0.116	7.3	0.131	6.8	0.127	7.2	0.132	7.2	0.126
200	6.3	0.119	7.6	0.134	7.1	0.130	7.4	0.133	7.5	0.130
250	6.5	0.121	7.9	0.137	7.4	0.133	7.6	0.134	7.8	0.133
300	6.7	0.124	8.2	0.141	7.7	0.135	7.8	0.135	8.0	0.137
350	7.0	0.126	8.5	0.144	7.9	0.138	8.0	0.136	8.3	0.140
400	7.2	0.128	8.8	0.147	8.2	0.140	8.2	0.138	8.6	0.144
450	7.5	0.130	9.1	0.150	8.5	0.143	8.4	0.141	8.8	0.147
500	7.7	0.132	9.4	0.154	8.8	0.147	8.6	0.143	9.1	0.151
550	7.9	0.134	9.7	0.157	9.0	0.151	8.8	0.146	9.4	0.154
600	8.2	0.136	10.0	0.160	9.3	0.155	9.1	0.148	9.7	0.158
650	8.4	0.138	10.3	0.164	9.6	0.160	9.3	0.151	10.0	0.161
700	8.7	0.140	10.6	0.167	9.9	0.165	9.5	0.153	10.2	0.165
750	8.9	0.142	10.9	0.171	10.1	0.169	9.8	0.156	10.5	0.168
800	9.1	0.144	11.2	0.174	10.4	0.174	10.0	0.158	10.8	0.172
850	9.4	0.146	11.5	0.177	10.7	0.178	10.2	0.160	11.0	...
900	9.6	0.148	11.8	0.181	11.0	0.181	10.5	0.162	11.3	...
950	9.8	0.150	12.2	0.184	11.2	0.183	10.7	0.165	11.6	...
1,000	10.1	0.152	12.5	0.187	11.5	0.184	10.9	0.169	11.9	...
1,050	10.3	0.154	12.8	0.190	11.8	0.183	...	...	...	...
1,100	10.5	0.156	13.1	0.192	12.0	0.182	...	...	...	...
1,150	10.8	0.158	13.4	0.195	12.3	0.179	...	...	...	...
1,200	11.0	0.159	13.7	0.197	12.6	0.175	...	...	...	...
1,250	11.3	0.161	14.0	0.199	12.8	0.171	...	...	...	...
1,300	11.5	0.163	14.3	0.201	13.1	0.167	...	...	...	...
1,350	11.8	0.165	14.6	0.203	13.3	0.163	...	...	...	...
1,400	12.0	0.167	14.9	0.204	13.6	0.160	...	...	...	...
1,450	12.3	0.169	15.2	0.206	13.8	0.160	...	...	...	...
1,500	12.6	0.172	15.5	0.208	14.1	0.162	...	...	...	...
1,550	...	0.175	...	0.211	...	0.169	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...

Table TCD
Nominal Coefficients of Thermal Conductivity (TC) and Thermal Diffusivity (TD) (Cont'd)

Temp., °F	High Nickel Alloys (Cont'd)		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys		High Nickel Alloys	
	N08031 and N08367		Ni-Fe-Cr-Si N08330		N08354		Ni-Fe-Cr N08800, N08801, N08810, N08811		Ni-Fe-Cr-Mo-Cu N08825		Ni-Mo N10001	
	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD	TC	TD
70	6.7	0.122	7.1	0.131	6.4	0.115	6.7	0.122	...	0.132	...	...
100	6.9	...	7.3	0.131	6.7	0.118	6.8	0.125	...	0.129	6.1	0.115
150	7.2	...	7.5	0.135	7.1	0.122	7.1	0.129	...	0.127	6.2	0.115
200	7.5	...	7.7	0.141	7.5	0.127	7.4	0.133	7.1	0.126	6.4	0.115
250	7.8	...	7.9	...	7.9	0.131	7.7	0.137	7.3	0.127	6.5	0.116
300	8.1	...	8.2	...	8.2	0.136	8.0	0.140	7.6	0.128	6.7	0.117
350	8.4	...	8.5	...	8.6	0.140	8.3	0.144	7.9	0.129	6.8	0.118
400	8.7	...	8.8	...	8.9	0.144	8.5	0.147	8.1	0.130	7.0	0.119
450	9.0	...	9.1	...	9.3	0.148	8.8	0.150	8.4	0.131	7.2	0.120
500	9.3	...	9.4	...	9.6	0.152	9.1	0.153	8.6	0.132	7.4	0.121
550	9.6	...	9.7	...	9.9	0.156	9.3	0.156	8.9	0.133	7.5	0.122
600	9.8	...	10.0	...	10.2	0.159	9.6	0.159	9.1	0.133	7.7	0.124
650	10.1	...	10.3	...	10.5	0.162	9.8	0.161	9.3	0.133	8.0	0.125
700	10.4	...	10.6	...	10.8	0.164	10.1	0.164	9.6	0.133	8.2	0.127
750	10.6	...	10.9	...	11.0	0.167	10.3	0.167	9.8	0.133	8.4	0.129
800	10.9	...	11.2	...	11.3	0.168	10.6	0.169	10.0	0.133	8.7	0.132
850	11.2	...	11.5	...	...	...	10.8	0.171	10.2	0.133	9.0	0.135
900	11.5	...	11.8	...	...	...	11.1	0.174	10.4	0.132	9.3	0.138
950	11.8	...	12.1	...	...	...	11.3	0.176	10.7	0.131	9.7	0.142
1,000	12.0	...	12.4	...	...	...	11.6	0.178	10.9	0.128	10.0	0.146
1,050	12.3	...	12.7	...	...	...	11.8	0.181	11.1	...	10.4	0.149
1,100	12.6	...	13.0	...	...	...	12.1	0.183	11.4	...	10.7	0.153
1,150	...	...	13.3	...	...	...	12.4	0.185	11.6	...	11.1	0.156
1,200	...	...	13.5	...	...	...	12.7	0.187	11.8	...	...	...
1,250	...	...	13.8	...	...	...	13.0	0.189	12.1	...	...	...
1,300	...	...	...	...	...	...	13.3	0.191	12.4	...	...	...
1,350	...	...	...	...	...	...	13.6	0.193	12.7	...	...	...
1,400	...	...	...	...	...	...	13.9	0.194	13.0	...	...	...
1,450	...	...	...	...	...	...	14.2	0.196	13.3	...	...	...
1,500	...	...	...	...	...	...	14.5	0.198	13.6	...	...	...
1,550	...	...	...	...	...	...	...	0.200	...	...	...	...
1,600	...	...	...	...	...	...	...	...	...	...	...	...
1,650	...	...	...	...	...	...	...	...	...	...	...	...
1,700	...	...	...	...	...	...	...	...	...	...	...	...
1,750	...	...	...	...	...	...	...	...	...	...	...	...