

TECHNICAL REPORT

**Superconductivity –
Part 20: Superconducting wires – Categories of practical superconducting
wires – General characteristics and guidance**

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2014 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 14 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 55 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IECNORM.COM : Click to view the full text of IEC 61878-20:2014

TECHNICAL REPORT

**Superconductivity –
Part 20: Superconducting wires – Categories of practical superconducting
wires – General characteristics and guidance**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

R

ICS 29.050

ISBN 978-2-8322-1779-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms and definitions	7
4 Categories of practical SC wires	7
5 Technical sheet assisting in the specification and the use of practical SC wires	8
6 Class of practical SC wires	8
7 Product parameters	8
8 Joints	8
9 Appearance	8
10 Quality assurance	8
11 Test methods	8
12 Inspection	9
13 Shipping label	9
Annex A (informative) Structural characteristics of practical SC wires	10
A.1 General	10
A.2 Overview of SC materials	10
A.3 Overview of functional components	10
A.3.1 Matrix materials	10
A.3.2 Stabilizer	11
A.3.3 Reinforcing component	11
A.3.4 Insulation	11
Annex B (informative) Classes of practical SC wires	13
B.1 Nb-Ti group	13
B.2 Nb ₃ Sn group	13
B.3 MgB ₂	14
B.4 BSCCO group	15
B.5 REBCO group	15
Annex C (informative) Technical information assisting in the specification and use of practical SC wires	17
C.1 General	17
C.2 Product parameters	17
C.3 Appearance	17
C.4 Quality assurance	17
C.5 Test methods	17
C.6 Technical record	18
Bibliography	19

Table B.1 – Constituents composing the Nb-Ti group SC wires	13
Table B.2 – Constituents composing the Nb ₃ Sn group SC wires	14
Table B.3 – Constituents composing the MgB ₂ SC wires	14
Table B.4 – Constituents composing the BSCCO SC wires	15
Table B.5 – Constituents composing REBCO SC wires	16

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –**Part 20: Superconducting wires –
Categories of practical superconducting wires –
General characteristics and guidance**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 61788-20, which is a technical report, has been prepared by IEC technical committee 90: Superconductivity.

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
90/335/DTR	90/344/RVC

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61788-20 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014

INTRODUCTION

Superconducting (SC) wires are a central and often enabling technology of many important industrial products. Consensus-based standards for SC wires greatly facilitate the creation of procurement specifications, design and engineering of components, certification of quality, description of operating devices, and generalization of use in industrial technologies.

The present technical report (TR IEC61788-20) provides a description of the general features of practical SC wires. The practical low temperature superconducting (LTS) wires have been used extensively in a variety of applications since the late 1960s. These applications include magnetic resonance imaging magnets, research and accelerator magnets, and systems for cutting-edge scientific research. High temperature superconductors (HTS), discovered in 1986, allow operation of superconductor-based technologies with less expensive and more efficient refrigeration systems. These new materials will provide wires that will enable new applications, some of which may not be possible with LTS wires. Many fabrication routes and conductor architectures are well established for superconducting wires, and these engineering routes have a number of general characteristics that are fundamental to enabling industrial products.

Practical superconducting wires are those forms of SC wires that are nearly identical to other common electrical conductors such as those made from copper or aluminium. The appearance of low temperature superconductive wires is, for instance, very similar to commercial electrical copper wires or tin-plated copper wires, because they are covered with stabilization or reinforcing components consisting of metallic elements. Often practical SC wires are supplied in long lengths on wire spools. As such, practical SC wires can be used in products and applications almost interchangeably with common wires. The technical aspects of superconductivity impose, however, certain considerations that might be taken into account in specifications for procurement, design and engineering, testing and certification, quality control, and other commerce. These aspects can be complicated, making practical SC wires less accessible to the non-technical user despite the best efforts of SC wire suppliers to market their products. This document intends to provide descriptions of the technical aspects of practical SC wires in terms of simple general characteristics to assist in the specification and use of superconducting wire products. It might be noted that this document gives some general characteristics of practical SC wires at the present state, but not any type of specifications for the wires or for the processing of the wire.

Thus the present technical report that provides general characteristics and guidance with respect to practical SC wires is recommended as a first priority for both producers and users of superconducting technology.

SUPERCONDUCTIVITY –

Part 20: Superconducting wires – Categories of practical superconducting wires – General characteristics and guidance

1 Scope

This part of IEC 61788, which is a technical report, provides general characteristics and guidance on practical SC wires. Particular focus is given to the characteristics that are different from those of ordinary copper and aluminium wires, since practical SC wires have appearance nearly identical to common electrical wires and can be used interchangeably with them. On the other hand, the practical SC wires are typically composite materials consisting of several functional materials as described in Annex A.

Many forms of SC wires are described in Section 4 of IEC 60050-815, including single core wires, multi-filamentary superconducting wires, composite superconductors and coated conductors. These wires as well as others that might be described as monolithic composite superconducting wires will be the focus in this technical report. A wire is considered as being practical if it can be procured in sufficiently continuous lengths under ordinary commercial transactions to build devices.

Conductors made of multiple wires, such as cables, for example, are not included in this scope.

Since this report only addresses the characteristics of practical wires, other wires such as prototype, test sample and developmental wires are not included in the scope of this technical report.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050 (all parts), *International Electrotechnical Vocabulary* (available at: <<http://www.electropedia.org>>)

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-815 apply.

4 Categories of practical SC wires

Industrially available SC materials are classified into two categories by IEC 60050-815. The low temperature superconductors have a critical temperature less than 25 K. They are typically in the Nb-Ti group and Nb₃Sn group, which is an intermetallic compound. The other category consists of high temperature superconductors such as BSCCO and REBCO and the intermetallic compound MgB₂. In the present document, the five types of SC wire based on the aforementioned five superconductor materials may be prescribed as practical SC wires, of which the additional details are mentioned in Annexes A and B. When a new superconducting

material is industrialized into wire form in the future, the current general requirements should be modified by introducing it as a new practical SC wire.

5 Technical sheet assisting in the specification and the use of practical SC wires

General items to agree between the supplier and the customer at the time of contract or purchase order are listed as follows. Except the recommended items mentioned here, additional items providing for the specification are described in Annex C. The technical sheet may be executed.

6 Class of practical SC wires

One of the practical SC wires described in Clause 4 may be specified.

Additional informative items are mentioned in Annex B.

7 Product parameters

- Dimension may be settled in terms of the diameter of the round wire or the width / thickness of the rectangular wire together with the tolerance.
- Length and/or weight may be definitely settled.
- The necessity of insulation may be designated.
- The type of spooling may be designated.
- The shipping label designated in Clause 13 may be attached on the shipped product.

Additional informative items are mentioned in Annex C.

8 Joints

Unless otherwise agreed upon by a customer and a supplier, no joints may be made in the completed wire. If joints are permitted within the wire, the customer and supplier are required to agree on the quantity and properties of the joints.

9 Appearance

The appearance of the wire should be free from any imperfection not consistent with commercial practice.

Additional informative items are mentioned in Annex C.

10 Quality assurance

A representative critical current value may be designated together with tolerance.

Additional informative items are mentioned in Annex C.

11 Test methods

Tests to determine conformance to requirements on product parameter and quality may be performed according to the instruction of the document (see Bibliography).

12 Inspection

Unless otherwise specified in the contract or purchase order, the supplier may be responsible for the performance of all inspection and test requirements specified.

Unless otherwise agreed upon between the customer and the supplier, conformance of the wire to the various requirements listed in this specification may be determined on samples taken from each lot of wire presented for acceptance.

13 Shipping label

The following information may be supplied with the product shipping label:

- a heading title “Superconducting wire” and/or the name of the principal SC material, and/or product identification such as a trade name;
- manufacturer;
- manufacturing date;
- country of origin;
- information guaranteeing traceability by the manufacturer, such as lot number or billet number.

Further information is mentioned in Annex C.

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014

Annex A (informative)

Structural characteristics of practical SC wires

A.1 General

Practical SC wires are designed with a composite structure to meet the desired engineering characteristics by expert selection of materials and design of the architecture. SC wires typically possess a complicated internal architecture, the constituents of which include the SC material plus additional functional components, such as a metal matrix material and stabilizers or reinforcements. The functional components are engineered so that the SC wire possesses electrical and mechanical integrity to withstand fabrication into equipment and operating conditions in application.

An overview of the types of SC materials and the role of the functional components are explained below in Clauses A.2 and A.3, respectively. As mentioned above, low temperature superconducting wires are typically similar in appearance to standard copper wire. Practical high temperature superconducting wires come in a variety of shapes. Their cross section is flat or round in accordance with fabrication techniques. Some HTS wires are also covered by stabilization or reinforcing components. Descriptions of the construction of low temperature and high temperature superconducting wires, including typical choices of materials for the functional components, follow in Annex B.

A.2 Overview of SC materials

Five types of superconducting materials are designated as members of practical SC wires, of which the details are described in Annex B. Practical SC wires are used at temperatures sufficiently lower than their inherent critical temperature and under magnetic fields lower than an irreversibility magnetic field.

Practical SC wires also differ from common electrical wires by having the ability to carry hundreds or thousands of times higher electrical current for the copper wire with the same diameter. Under such conditions, the energy stored in the form of currents and their associated magnetic fields can exceed other thermodynamic energies, leading to the possibility of spontaneous and uncontrollable energy release. Since the electromagnetic energy per unit volume is proportional to the physical dimension of the superconductor, it is often common practice to sub-divide the superconductor material into small volume. Therefore, practical SC wire architectures sub-divide the superconducting material, usually by the formation of parallel superconducting filaments, resulting in multifilamentary superconducting wire.

Some uses of practical SC wires require the electric current to vary with time, or for the electric current to be carried under time-varying external magnetic field. Certain losses arise from superconducting behaviour under these conditions, which can be minimized by twisting the wire about its axis so as to impart a helical pattern to the filaments.

A.3 Overview of functional components

A.3.1 Matrix materials

Often a plurality of the superconducting material in a composite wire is present as filaments or thin layer. The filaments can have a diameter ranging between sub-micrometers to tens or even hundreds of micrometers or thin layers with thickness between one to tens of microns. The superconducting filaments are embedded in, and in direct contact with, matrix materials.

The function of the matrix materials with respect to the filaments can be multi-purpose, including: to support them mechanically, facilitate their formation, provide conductive electrical connections, promote transfer of heat to the cooling environment, and/or limit degradation of superconducting properties. In the case of MgB_2 , the superconducting multifilaments are surrounded by sheath, outer sheath and/or barrier materials. In the case of REBCO group (see Clause B.4), the matrix consists of substrate, buffer layer, cap layer and protection layer. The details for individual SC wires are described more precisely in Clause B.5.

A.3.2 Stabilizer

A stabilization component can absorb the Joule heat and allow the supercurrent to reroute around a local break-down of superconductivity. At very low temperatures such as 4,2 K, there is greater necessity for a stabilization component because the heat capacity of all materials is generally lower as temperature decreases, even though the resistivity also changes with temperature.

Practical SC wires attain the superconducting state when cooled below their critical temperature. A good thermal conductor, called the stabilizer, is required to transmit heat to a refrigerant or some other cooling agent. Since good conductors of electricity are also good conductors of heat, pure copper, silver, or aluminium components of composite superconductors also serve as the stabilizer. Moreover, since most applications surround the wire with the coolant, the stabilizer typically forms the outside of the wire.

All practical SC wires are designed to carry electrical current through the stabilizer. Therefore, it is permissible to refer to the intended electrical conductor in the normal conducting state as the stabilizer.

As mentioned above, the contribution of the stabilizer is essential for designing the practical SC wires. The following indexes are usually designated.

- Copper volume fraction and superconductor volume fraction, which are used to specify the volume fraction of components in a composite wire, for the example where the stabilizer is copper.
- Copper to non-copper volume ratio and copper to superconductor volume ratio, which are the ratios of the volume of stabilizer to the volume of other components in a composite wire for the example where the stabilizer is copper.

In the case of Nb-Ti wires, in order to improve the thermal and/or flux jump stability as well as to reduce the coupling loss, a Cu alloy such as Cu-Ni and/or aluminium are composed as a stabilizer.

In the case of MgB_2 , the stabilization components can be provided through materials inside and/or outside the outer sheath and/or with electro-deposition or soldering on the outer sheath surface.

A.3.3 Reinforcing component

Some metallic components are used in order to increase the strength. A high strength thin layer can be distributed in the interior of the low temperature superconducting wire. Thin metallic sheets can also be used to increase the strength of high temperature superconductors, which are soldered or electrodeposited on the surface of wires.

A.3.4 Insulation

The surface of practical SC wires is often coated by an insulating resin or wound with an insulating tape in order to prevent short-circuiting caused by contact between wires with the surrounding conducting substances, and to avoid dielectric breakdown or arcing depending on the voltage requirements of the application.

Practical SC wires can be supplied with insulation. Insulation materials that are used for common electrical wires may also be applied to practical SC wires. Also, the heat treatment and end use of the practical SC wire may determine other materials for insulation.

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014

Annex B (informative)

Classes of practical SC wires

B.1 Nb-Ti group

The Nb-Ti practical SC wires usually contain two components composed of SC Nb-Ti-based filaments and Cu matrix, as listed in Table B.1. The most practical Nb-Ti alloy is the simple Nb-Ti two-component system, with a composition of 46 % to 48 % titanium by mass, but for specific applications, ternary and multi-component alloys such as Nb-Ti-Hf and Nb-Ti-Ta-Zr were developed. The role of the matrix is to provide conductive electrical connections and promote transfer or conduction of heat to the cooling environment: for instance, copper is in direct contact with the Nb-Ti filaments of a multi-filamentary wire composite. In order to improve the thermal and/or flux jump stability as well as to reduce the coupling loss, the Cu alloy such as Cu-Ni and/or the aluminium are composed as stabilizer.

The fabrication process of Nb-Ti wires is applied to common electrical wires, using similar machinery and tooling, including: forging, swaging, rolling, extruding, and drawing. Heat treatments may be applied to assist the forming process; however, special properties of the superconducting material will generally govern the applicability of heat treatment as described below.

Raw material specifications apply to forms of Nb-Ti alloy used at the beginning of the manufacture of practical SC wire. These specifications also address methods of manufacture, chemical composition, physical and mechanical properties, dimensions and mass of product, workmanship and appearance, tolerances and variations, and other issues of direct commerce between the industrial supplier of practical SC wires and the raw material supplier.

Table B.1 – Constituents composing the Nb-Ti group SC wires

Constituent	Material
Superconductor	Nb-Ti alloy
Matrix	Copper or copper alloy
Stabilizer	Aluminium, copper or copper alloy
Insulation	Resin for coating
	Tape for winding
	Braided fiber for sheathing

B.2 Nb₃Sn group

This category of superconductors belongs to A15 type intermetallic compounds including Nb₃Sn, Nb₃Al and so on. Several kinds of manufacturing processes have been developed, including among them, the bronze process, the internal/ external diffusion process, the jelly roll process, and the powder-in-tube process. In the case of Nb₃Sn practical SC wires as shown in Table B.2, the matrix contacting directly with the superconductor is the Cu-Sn alloy and niobium. In order to operate stably, high conductivity copper is utilized as stabilizer, while the niobium or tantalum thin layer is inserted as diffusion barrier between the matrix and the copper stabilizer because it prevents contamination from the matrix during the heat treatment. Due to the final heat treatment at high temperature during the fabrication process, the SC wire becomes soft mechanically. To enhance mechanical strength, the SC wire is reinforced by adding a copper alloy component. Due to the brittleness of Nb₃Sn components, the so called “wind and react” process is adopted for many cases, by which the unreacted wire is finished in the final shape of the product prior to the heat treatment for forming the Nb₃Sn compound.

Several standard specifications for niobium, copper, and copper-tin alloy (bronze) raw materials exist. These specifications address many issues of direct commerce between the supplier of practical SC wires and the raw material suppliers.

Three sub-classes of practical Nb₃Sn wires exist: internal-tin wires, bronze-route wires, and powder-in-tube wires. In most circumstances, the details of the sub-class do not affect the end use.

All sub-classes of practical Nb₃Sn SC wires require a heat treatment to form the intermetallic compound by a diffusion reaction between a source of tin and a source of niobium. Because the wire is brittle after heat treatment, all Nb₃Sn wires are received in the state before heat treatment. Vendors should provide a recommendation for the time and temperature schedule for the heat treatment as well as the acceptable heat treatment environments.

Table B.2 – Constituents composing the Nb₃Sn group SC wires

Constituent	Material
Superconductor	Nb ₃ Al intermetallic compound or Nb ₃ Sn intermetallic compound
Matrix	Copper, copper alloy or niobium
Diffusion barrier	Niobium or tantalum
Stabilizer	Copper
Reinforcing member	Copper alloy
Insulation	Resin for coating Tape for winding or wrapping Braided fiber for sheathing

B.3 MgB₂

The MgB₂ practical wires are fabricated by means of in-situ or ex-situ techniques by using as starting materials an Mg and B precursor or an MgB₂ reacted compound. As shown in Table B.3, the materials contacting directly with the MgB₂ core and forming the monofilament should have no reactivity, or a well-controlled reactivity, with Mg, B and MgB₂. Usually, as a barrier, a material with no reactivity at all can be used. At the present state, the materials mostly used in the MgB₂ wire architecture are listed in Table B.3.

MgB₂ practical SC wire can be specified for delivery in a heat-treated or a non heat-treated state.

Table B.3 – Constituents composing the MgB₂ SC wires

Constituent	Material
Superconductor	MgB ₂ or doped MgB ₂
Matrix	Sheath and outer sheath
	Barrier
Stabilizer	Copper or copper alloy
Insulation	Resin for coating Tape for winding

B.4 BSCCO group

As shown in Table B.4, two types of bismuth-based oxide superconductors with the chemical formula $((\text{Bi}, \text{Pb})_2\text{Sr}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+4})$, where $n = 2$ or 3 , are used as practical SC wires. In either case, superconducting filaments are embedded into a pure silver matrix.

- Bi-2223

In the Bi-2223 wires, a silver alloy outer sheath surrounds the matrix for increasing mechanical strength. Bi-2223 wires are exclusively made in flat tape-shaped form. Wires are commercially available in which thin metallic sheets of copper alloy or stainless steel are soldered on both sides of the SC tapes in order to improve the strain dependence of the critical current and the mechanical properties.

- Bi-2212

According to the characteristic feature of microstructure control for Bi-2212 wire, its outer shape is round, while superconducting filaments are embedded into a pure silver matrix. In principle, the wire is so soft that the wind and react process is adopted to fabricate final products such as Rutherford cables.

Bi-2212 may be specified as round wires or as conductors with a high aspect ratio. It is recommended to clarify the form of the conductor as part of the procurement documentation.

Table B.4 – Constituents composing the BSCCO SC wires

Constituent	Material
Superconductor	Bi-2212 ($\text{Bi}_2\text{Sr}_2\text{Ca}_1\text{Cu}_2\text{O}_8$) or Bi-2223 ($\text{Bi}_2\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_{10}$)
Matrix	Silver or silver alloy
Reinforcing member	Copper alloy or stainless steel
Insulation	Resin for coating Tape for winding

B.5 REBCO group

The rare-earth-based oxide superconductor with the chemical formula, $\text{RE}_1\text{Ba}_2\text{Cu}_3\text{O}_7$ is used as a practical SC wire, where the rare-earth element RE is Y, Gd, Nd, Ho and Sm. This type of practical SC wire is usually called a REBCO coated conductor. As shown in Table B.5, a typical architecture consists of a substrate of Hastelloy, stainless steel or Ni-W alloy, and a few thin oxide layers including a buffer layer of Al_2O_3 , Y_2O_3 , CeO_2 , YSZ, MgO, a cap layer of CeO_2 or LaMnO_3 , an SC layer, and a protection layer of Ag. The cap layer acts as a template to facilitate the well-oriented epitaxial growth of the SC layer. Although not all components of substrate, buffer layer, cap layer and protection layer are in direct contact with the superconducting material, for convenience they are categorized as matrix material since they are either critical for the proper growth of the superconducting material (substrate, buffer layer and cap layer) or in direct contact with the superconductor (cap layer and protection layer) and provide thermal and/or electrical contact to the rest of the composite structure.

Table B.5 – Constituents composing REBCO SC wires

Constituent		Material
Superconductor		RE-123 ($\text{RE}_1\text{Ba}_2\text{Cu}_3\text{O}_{7-x}$; RE=Y, Nd, Sm, Gd, Ho)
Matrix	Substrate	Hastelloy, Ni-W alloy or stainless steel
	Buffer layer	Al_2O_3 , CeO_2 , $\text{Gd}_2\text{Zr}_2\text{O}_7$, MgO , Y_2O_3 , or YSZ
	Cap layer	CeO_2 or LaMnO_3
	Protection layer	Ag
Stabilizer		Copper, copper alloy or other material for stabilization
Reinforcing member		Ferrous alloy, nickel alloy or stainless steel
Insulation		Resin for coating
		Tape for winding

IECNORM.COM : Click to view the full PDF of IEC TR 61788-20:2014

Annex C (informative)

Technical information assisting in the specification and use of practical SC wires

C.1 General

When contracting or ordering, further informative terms are selected from the following lists for fixing the specification, because it depends on individual application. Their technical meaning is interpreted in Annexes A and B.

C.2 Product parameters

- Constituent materials include the additional terms of matrix, barrier, reinforcing member, insulation and others.
- The interior structure is characterized by the following terms of filament diameter, number of filaments, twisting, twist pitch, matrix ratio, Cu/non-Cu ratio, silver ratio, and snapping rate.
- Insulation is complemented by the additional terms of thickness and dielectric strength.
- Length and/or weight are definitely settled in terms of single length, number of pieces, total length, weight of piece and/or total weight.
- The type of packing is complemented by the following additional terms of drum or reel, regular winding, pancake winding, and/or wrapping.
- The shipping label is additionally recommended to include the following terms when it is requested: (i) purchase order number, (ii) gross, tare, and net weights, (iii) number of pieces, (iv) diameter and length, (v) stabilizer material, etc.

C.3 Appearance

Inspection of the finished product may find the exterior free from harmful defects, wrench, billowing, stains, and other imperfections, as much as possible.

C.4 Quality assurance

- Properties referring to the operation of SC wires include the additional terms of n value, their bending and/or tensile stress/strain tolerance, critical temperature, critical magnetic and irreversibility fields, AC loss, etc.
- Properties related to implementation and engineering include dielectric strength, RRR, modulus of elasticity, tensile strength, etc.

Test methods necessary for quality assurance are described in the IEC 61788 series (see the Bibliography).

C.5 Test methods

Tests to determine the conformance to requirements necessary to the product parameter and quality may be performed according to the direction of the IEC 61788 series.