
International Standard



7724/1

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

**Paints and varnishes — Colorimetry —
Part 1: Principles**

Peintures et vernis — Colorimétrie — Partie 1: Principes

First edition — 1984-10-01

STANDARDSISO.COM : Click to view the full PDF of ISO 7724-1:1984

UDC 667.6 : 535.65

Ref. No. ISO 7724/1-1984 (E)

Descriptors : paints, varnishes, colorimetry.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council. They are approved in accordance with ISO procedures requiring at least 75 % approval by the member bodies voting.

International Standard ISO 7724/1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*.

STANDARDSISO.COM : Click to view the full PDF of ISO 7724-1:1984

Contents

	Page
0 Introduction	1
1 Scope and field of application	1
2 References	1
3 Colour co-ordinates	1
3.1 Colour co-ordinates in the CIE 1964 supplementary standard colorimetric system	1
3.2 Colour co-ordinates in the CIE 1976 ($L^*a^*b^*$) colour space	2
4 Standard illuminants	4
5 Spectral radiometric characteristics	4
5.1 General	4
5.2 Illumination and viewing conditions	5

STANDARDSISO.COM : Click to view the full PDF of ISO 7724-1:1984

This page intentionally left blank

STANDARDSISO.COM : Click to view the full PDF of ISO 7724-1:1984

Paints and varnishes — Colorimetry — Part 1: Principles

0 Introduction

This International Standard, ISO 7724, comprises the following parts :

Part 1 : Principles.

Part 2 : Colour measurement.

Part 3 : Calculation of colour differences.

Parts 1, 2 and 3 of ISO 7724 describe methods for the instrumental determination of the colour co-ordinates and colour differences of paint films, as required for such purposes as

- a) the objective description of colour differences between a test specimen (a test panel coated with a paint, or a specimen from a painted article) and a reference specimen;
- b) determining colour deviations in the production of painted articles so that the results may be used for the control or regulation of the process;
- c) the objective description of changes in colour caused by weathering and other chemical or physical influences;
- d) the objective supervision of colour reference standards.

NOTE — Colour reference standards are subject to ageing, which may lead in the course of time to pronounced changes in colour. High accuracy colorimetry is required for the timely detection of these changes. This is of particular importance when ordering against such reference standards.

1 Scope and field of application

This part of ISO 7724 describes the colorimetric terms and fundamental requirements necessary for determining the colour co-ordinates of paint films and related materials.

2 References

ISO 2813, *Paints and varnishes — Measurement of specular gloss of non-metallic paint films at 20°, 60° and 85°.*

ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints.*

ISO 7724/2, *Paints and varnishes — Colorimetry — Part 2 : Colour measurement.*

ISO 7724/3, *Paints and varnishes — Colorimetry — Part 3 : Calculation of colour differences.*

CIE Publication No. 15, *Colorimetry, Official CIE Recommendations.*

CIE Publication No. 15, Supplement No. 2, *Recommendations on uniform color spaces — Color difference equations — Psychometric color terms.*

CIE Publication No. 38, *Radiometric and photometric characteristics of materials and their measurement.*

3 Colour co-ordinates

A colour is uniquely characterized for a defined observer and a defined light source by the co-ordinates of a point in a space formed by three mutually perpendicular vectors. From among the various colour co-ordinates recommended by the Commission Internationale de l'Éclairage (CIE), the colour co-ordinates given in 3.1 and 3.2 are specified for colorimetric measurements on paint films in accordance with this International Standard.

3.1 Colour co-ordinates in the CIE 1964 supplementary standard colorimetric system

The colour co-ordinates in this system (see CIE Publication No. 15) are the tristimulus value Y_{10} and the chromaticity co-ordinates x_{10} and y_{10} .

$$Y_{10} = k_{10} \sum_{\lambda=l}^{\lambda=u} \varphi(\lambda) \bar{y}_{10}(\lambda) \Delta\lambda$$

$$x_{10} = \frac{X_{10}}{X_{10} + Y_{10} + Z_{10}}, \quad y_{10} = \frac{Y_{10}}{X_{10} + Y_{10} + Z_{10}}$$

The chromaticity co-ordinates are formed by the tristimulus values

$$X_{10} = k_{10} \sum_{\lambda=l}^{\lambda=u} \varphi(\lambda) \bar{x}_{10}(\lambda) \Delta\lambda,$$

$$Z_{10} = k_{10} \sum_{\lambda=l}^{\lambda=u} \varphi(\lambda) \bar{z}_{10}(\lambda) \Delta\lambda \text{ and}$$

$$Y_{10}$$

where

$\varphi(\lambda)$ denotes the colour stimulus function, which is the product of the relative spectral power distribution S_{λ} for the standard illuminant (see clause 4) and the spectral function that characterizes the reflectance of the paint film (see clause 5);

$\bar{x}_{10}(\lambda)$, $\bar{y}_{10}(\lambda)$ and $\bar{z}_{10}(\lambda)$ are the colour-matching functions (see note 1) used to define the CIE 1964 standard colorimetric observer for observation fields of angular subtense larger than 4° (10° observer) (see table 1);

l and u are the respective summation limits for the short-wave and long-wave limits of the visible spectrum;

$\Delta\lambda$ is the width of the wavelength interval (for the choice of l and u , and $\Delta\lambda$, see ISO 7724/2);

k_{10} is a normalizing factor calculated by using the equation

$$k_{10} = 100 \left/ \left(\sum_{\lambda=l}^{\lambda=u} S_{\lambda} \bar{y}_{10}(\lambda) \Delta\lambda \right) \right.$$

which causes the tristimulus value Y_{10} for the perfect reflecting diffuser to assume a value of 100.

In this system, the colour co-ordinates do not provide a perceptually uniform colour space (see 3.2).

NOTES

1 The coefficients $\bar{x}_{10}(\lambda)$, $\bar{y}_{10}(\lambda)$ and $\bar{z}_{10}(\lambda)$ were formerly termed CIE spectral tristimulus values or CIE trichromatic weighting coefficients.

2 Colour co-ordinates in the CIE 1931 standard colorimetric system are defined by analogous equations using the colour-matching functions $\bar{x}(\lambda)$, $\bar{y}(\lambda)$ and $\bar{z}(\lambda)$ of the CIE 1931 standard colorimetric observer for the 2° observation field. Colour-matching functions at 5 nm wavelength intervals are given in CIE Publication No. 15.

The 10° observation field corresponds more closely with practice than the 2° observation field and is consistent with the viewing conditions recommended in ISO 3668 for the visual comparison of the colour of paints.

3.2 Colour co-ordinates in the CIE 1976 ($L^* a^* b^*$) colour space

In comparison with the CIE 1964 colorimetric system (see 3.1), the colour co-ordinates in the perceptually more uniform CIE 1976 ($L^* a^* b^*$) colour space (see CIE Publication No. 15 Supplement No. 2) are specified for the evaluation of colour differences.

The colour co-ordinates are calculated from the following equations:

$$L^* = 116 (Y/Y_n)^{1/3} - 16 \quad \text{for } Y/Y_n > 0,008856$$

$$L^* = 903,3 (Y/Y_n) \quad \text{for } Y/Y_n < 0,008856$$

$$a^* = 500 [f(X/X_n) - f(Y/Y_n)]$$

$$b^* = 200 [f(Y/Y_n) - f(Z/Z_n)]$$

where

$$f(X/X_n) = (X/X_n)^{1/3} \quad \text{for } X/X_n > 0,008856$$

$$f(X/X_n) = 7,787 (X/X_n) + 16/116 \quad \text{for } X/X_n < 0,008856$$

$$f(Y/Y_n) = (Y/Y_n)^{1/3} \quad \text{for } Y/Y_n > 0,008856$$

$$f(Y/Y_n) = 7,787 (Y/Y_n) + 16/116 \quad \text{for } Y/Y_n < 0,008856$$

$$f(Z/Z_n) = (Z/Z_n)^{1/3} \quad \text{for } Z/Z_n > 0,008856$$

$$f(Z/Z_n) = 7,787 (Z/Z_n) + 16/116 \quad \text{for } Z/Z_n < 0,008856$$

X, Y, Z denote the 10° tristimulus values of the paint film;

X_n, Y_n, Z_n are the 10° tristimulus values of the perfect reflecting diffuser under the chosen standard illuminant (see table 2).

NOTE — If 2° tristimulus values are used, L^*, a^*, b^* co-ordinates for the 2° observer will be obtained. The corresponding values for X_n and Z_n can be calculated from the 2° chromaticity co-ordinates for the standard illuminants D 65 and A (see CIE Publication No. 15) with $Y_n = 100$.

It is sometimes convenient to express colour not in terms of the rectangular co-ordinates L^*, a^*, b^* , but in terms of the rectilinear lightness and the polar co-ordinates chroma and hue (see CIE Publication No. 15 Supplement No. 2).

These may be calculated from L^*, a^*, b^* to give

CIE 1976 psychometric lightness L^*

CIE 1976 $a b$ chroma $C_{ab}^* = (a^{*2} + b^{*2})^{1/2}$

CIE 1976 $a b$ hue angle $h_{ab} = \arctan (b^*/a^*)$
between 0° and 360°

Table 1 — Colour-matching functions for the 10° observer at 5 nm wavelength intervals

λ nm	$\bar{x}_{10}(\lambda)$	$\bar{y}_{10}(\lambda)$	$\bar{z}_{10}(\lambda)$	λ nm	$\bar{x}_{10}(\lambda)$	$\bar{y}_{10}(\lambda)$	$\bar{z}_{10}(\lambda)$
380	0,0002	0,0000	0,0007	600	1,1240	0,6583	0,0000
385	0,0007	0,0001	0,0029	605	1,0891	0,5939	0,0000
390	0,0024	0,0003	0,0105	610	1,0305	0,5280	0,0000
395	0,0072	0,0008	0,0323	615	0,9507	0,4618	0,0000
				620	0,8563	0,3981	0,0000
400	0,0191	0,0020	0,0860	625	0,7549	0,3396	0,0000
405	0,0434	0,0045	0,1971	630	0,6475	0,2835	0,0000
410	0,0847	0,0088	0,3894	635	0,5351	0,2283	0,0000
415	0,1406	0,0145	0,6568	640	0,4316	0,1798	0,0000
420	0,2045	0,0214	0,9725	645	0,3437	0,1402	0,0000
				650	0,2683	0,1076	0,0000
425	0,2647	0,0295	1,2825	655	0,2043	0,0812	0,0000
430	0,3147	0,0387	1,5535	660	0,1526	0,0603	0,0000
435	0,3577	0,0496	1,7985	665	0,1122	0,0441	0,0000
440	0,3837	0,0621	1,9673	670	0,0813	0,0318	0,0000
445	0,3867	0,0747	2,0273				
				675	0,0579	0,0226	0,0000
450	0,3707	0,0895	1,9948	680	0,0409	0,0159	0,0000
455	0,3430	0,1063	1,9007	685	0,0286	0,0111	0,0000
460	0,3023	0,1282	1,7454	690	0,0199	0,0077	0,0000
465	0,2541	0,1528	1,5549	695	0,0138	0,0054	0,0000
470	0,1956	0,1852	1,3176				
				700	0,0096	0,0037	0,0000
475	0,1323	0,2199	1,0302	705	0,0066	0,0026	0,0000
480	0,0805	0,2536	0,7721	710	0,0046	0,0018	0,0000
485	0,0411	0,2977	0,5701	715	0,0031	0,0012	0,0000
490	0,0162	0,3391	0,4153	720	0,0022	0,0008	0,0000
495	0,0051	0,3954	0,3024				
				725	0,0015	0,0006	0,0000
500	0,0038	0,4608	0,2185	730	0,0010	0,0004	0,0000
505	0,0154	0,5314	0,1592	735	0,0007	0,0003	0,0000
510	0,0375	0,6067	0,1120	740	0,0005	0,0002	0,0000
515	0,0714	0,6857	0,0822	745	0,0004	0,0001	0,0000
520	0,1177	0,7618	0,0607				
				750	0,0003	0,0001	0,0000
525	0,1730	0,8233	0,0431	755	0,0002	0,0001	0,0000
530	0,2365	0,8752	0,0305	760	0,0001	0,0000	0,0000
535	0,3042	0,9238	0,0206	765	0,0001	0,0000	0,0000
540	0,3768	0,9620	0,0137	770	0,0001	0,0000	0,0000
545	0,4516	0,9822	0,0079				
				775	0,0000	0,0000	0,0000
550	0,5298	0,9918	0,0040	780	0,0000	0,0000	0,0000
555	0,6161	0,9991	0,0011				
560	0,7052	0,9973	0,0000				
565	0,7938	0,9824	0,0000				
570	0,8787	0,9556	0,0000				
575	0,9512	0,9152	0,0000				
580	1,0142	0,8689	0,0000				
585	1,0743	0,8256	0,0000				
590	1,1185	0,7774	0,0000				
595	1,1343	0,7204	0,0000				

Table 2 — 10° tristimulus values for the perfect reflecting diffuser for standard illuminants D 65 and A

Tristimulus value	Standard illuminant	
	D 65	A
X_n	94,81	111,14
Y_n	100,00	100,00
Z_n	107,34	35,20

4 Standard illuminants

The CIE standard illuminant D 65 which corresponds to natural daylight at a correlated colour temperature of about 6 500 K (see CIE Publication No. 15), should be specified for colour measurements in accordance with this International Standard.

NOTE — The standard illuminant C corresponds to natural daylight at a correlated colour temperature of 6 744 K. Its spectral distribution does not approach that of natural daylight so closely as that of standard illuminant D 65, especially in the ultraviolet region.

The standard illuminant A, which represents the light of a tungsten lamp and corresponds in its spectral distribution to a perfect black body at a temperature of 2 856 K, should be

specified for the colorimetric determination of a special metamerism index (see clause 5 of ISO 7724/2).

Numerical values for the relative spectral power distribution S_λ of standard illuminants D 65 and A are given in table 3.

5 Spectral radiometric characteristics

5.1 General

Of the various possible spectral radiometric characteristics that describe the reflecting properties of materials (see CIE Publication No. 38), the three characteristics defined in 5.1.1 to 5.1.3 are used in this part of ISO 7724 for paint film colorimetry.

Table 3 — Relative spectral power distribution S_λ of standard illuminants D 65 and A at 5 nm wavelength intervals

λ nm	S_λ , D 65	S_λ , A	λ nm	S_λ , D 65	S_λ , A
380	50,0	9,80	600	90,0	129,04
385	52,3	10,90	605	89,8	132,70
390	54,6	12,09	610	89,6	136,35
395	68,7	13,35	615	88,6	139,99
400	82,8	14,71	620	87,7	143,62
405	87,1	16,15	625	85,5	147,23
410	91,5	17,68	630	83,3	150,84
415	92,5	19,29	635	83,5	154,42
420	93,4	21,00	640	83,7	157,98
425	90,1	22,79	645	81,9	161,52
430	86,7	24,67	650	80,0	165,03
435	95,8	26,64	655	80,1	168,51
440	104,9	28,70	660	80,2	171,96
445	110,9	30,85	665	81,2	175,38
450	117,0	33,09	670	82,3	178,77
455	117,4	35,41	675	80,3	182,12
460	117,8	37,81	680	78,3	185,43
465	116,3	40,30	685	74,0	188,70
470	114,9	42,87	690	69,7	191,93
475	115,4	45,52	695	70,7	195,12
480	115,9	48,24	700	71,6	198,26
485	112,4	51,04	705	73,0	201,36
490	108,8	53,91	710	74,3	204,41
495	109,1	56,85	715	68,0	207,41
500	109,4	59,86	720	61,6	210,36
505	108,6	62,93	725	65,7	213,27
510	107,8	66,06	730	69,9	216,12
515	106,3	69,25	735	72,5	218,92
520	104,8	72,50	740	75,1	221,67
525	106,2	75,79	745	69,3	224,36
530	107,7	79,13	750	63,6	227,00
535	106,0	82,52	755	55,0	229,59
540	104,4	85,95	760	46,4	232,12
545	104,2	89,41	765	56,6	234,59
550	104,0	92,91	770	66,8	237,01
555	102,0	96,44	775	65,1	239,37
560	100,0	100,00	780	63,4	241,68
565	98,2	103,58			
570	96,3	107,18			
575	96,1	110,80			
580	95,8	114,44			
585	92,2	118,08			
590	88,7	121,73			
595	89,3	125,39			