
**Nanotechnologies — Standard terms
and their definition for cellulose
nanomaterial**

*Termes normalisés et leur définition pour les nanomatériaux à base
de cellulose*

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20477:2017



STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20477:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
3.1 Core nanotechnology terms related to cellulose nanomaterials	1
3.2 Prerequisite non-nanotechnology terms related to cellulose nanomaterials	2
3.3 Terms specific to cellulose nanomaterials	3
Annex A (informative) Cellulose micromaterials	5
Bibliography	6
Index	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 229, *Nanotechnologies*.

Introduction

Cellulose is a polymer produced by nature. In plants, animals, algae and bacteria, cellulose is extruded from terminal enzyme complexes (TC). TCs are made up of many identical subunits, each containing at least one catalytic site from which a single cellulose chain is synthesized. Cellulose chains from a single TC combine to form an elementary fibril. As TCs in plants, animals, algae, and bacteria have different numbers and configurations of subunits, the elementary fibrils they produce have different geometries. [4] Whether cellulose nanomaterials are separated by industrial processes or produced directly by organisms, they all contain a common structural component, which is the elementary fibril. This common component, the elementary fibril, provides a way to describe cellulose nanomaterials from all manufacturing methods and cellulose sources.

In industrial productions, cellulose nanomaterials can be manufactured by conversion of wood pulp through chemical, biological or mechanical processes. In the case of bacterium-based cellulose nanomaterials, they are produced directly by bacteria and can be further acid-hydrolysed to smaller dimensions. Besides trees and bacteria, algae is another potential sources of cellulose nanomaterials for industrial applications. Due to their renewable nature and unique properties, cellulose nanomaterials have developed into platform materials that have application potential in a wide range of products including those that currently utilize petroleum-based ingredients.

In the current stage of development, several terms to describe cellulose nanomaterials coexist and have created confusion among users. Rather than delaying standards development until knowledge accumulated with market maturity is available, we have an opportunity to define a standard vocabulary for cellulose nanomaterials as they enter the market place. It is anticipated that as the market for cellulose nanomaterials matures, so too will the standard vocabulary. Beginning to define a standard vocabulary now will facilitate future communication, eliminate confusion, remove trade barriers and provide policy makers and regulators with a set of consensus-based terms.

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20477:2017

Nanotechnologies — Standard terms and their definition for cellulose nanomaterial

1 Scope

This document defines terms and definitions for different types of cellulose nanomaterials including secondary components found in cellulose nanomaterials due to their manufacturing processes. The document also gives information on cellulose micromaterials in [Annex A](#).

Where necessary, terms from the ISO/IEC 80004 vocabulary series are included in this document. Terms in this document are applicable to all types of cellulose nanomaterials regardless of production methods and their origin (plants, animals, algae or bacteria).

2 Normative references

There are no normative references in this document.

3 Terms and definitions

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 Core nanotechnology terms related to cellulose nanomaterials

3.1.1

nanoscale

length range approximately from 1 nm to 100 nm

Note 1 to entry: Properties that are not extrapolations from larger sizes are predominately exhibited in this length range.

[SOURCE: ISO/TS 80004-1:2015, 2.1]

3.1.2

nanomaterial

material with any external dimension in the *nanoscale* ([3.1.1](#)) or having internal structure or surface structure in the *nanoscale*

Note 1 to entry: This generic term is inclusive of *nano-object* ([3.1.3](#)) and *nanostuctured material* ([3.1.5](#)).

Note 2 to entry: See also definitions of engineered nanomaterial, manufactured nanomaterial and incidental nanomaterial in ISO/TS 80004-1:2015.

[SOURCE: ISO/TS 80004-1:2015, 2.4]

3.1.3

nano-object

discrete piece of material with one, two or three external dimensions in the *nanoscale* ([3.1.1](#))

Note 1 to entry: The second and third external dimensions are orthogonal to the first dimension and to each other.

[SOURCE: ISO/TS 80004-1:2015, 2.5]

3.1.4

nanostructure

composition of inter-related constituent parts in which one or more of those parts is a *nanoscale* (3.1.1) region

Note 1 to entry: A region is defined by a boundary representing a discontinuity in properties.

[SOURCE: ISO/TS 80004-1:2015, 2.6]

3.1.5

nanostuctured material

material having internal *nanostructure* (3.1.4) or surface nanostructure

Note 1 to entry: This definition does not exclude the possibility for a *nano-object* (3.1.3) to have internal structure or surface structure. If external dimension(s) are in the *nanoscale* (3.1.1), the term nano-object is recommended.

[SOURCE: ISO/TS 80004-1:2015, 2.7]

3.1.6

nanofibre

nano-object (3.1.3) with two similar external dimensions in the *nanoscale* (3.1.1) and the third dimension significantly larger

Note 1 to entry: The largest external dimension is not necessarily in the *nanoscale*.

Note 2 to entry: Nanofibril and nanofilament are alternative terms for nanofibre.

Note 3 to entry: See Note 1 to entry of nanoparticle in ISO/TS 80004-2:2015.

[SOURCE: ISO/TS 80004-2:2015, 4.5]

3.1.7

nanocrystal

nano-object (3.1.3) with a crystalline structure

[SOURCE: ISO/TS 80004-2:2015, 4.15]

3.2 Prerequisite non-nanotechnology terms related to cellulose nanomaterials

3.2.1

crystalline

solid structure where its ions, molecules, or atoms are in an ordered, three-dimensional arrangement

3.2.2

amorphous

solid structure where its ions, molecules, or atoms are oriented randomly, lacking any order

3.2.3

paracrystalline

structure in the intermediate state between crystalline and amorphous, having short and medium range ordered lattice structure and lacking long range order in at least one direction

3.2.4

cellulose

linear polymeric chains of β (1 $\rightarrow$ 4) linked D-glucopyranose units

3.2.5

elementary fibril

structure, originating from a single terminal enzyme complex, having a configuration of cellulose chains specific to each cellulose-producing plant, animal, algal and bacterial species

3.2.6

hemicellulose

non-cellulose polysaccharides in organisms, typically containing monomers such as, but not limited to, xylose, glucose, mannose, galactose, arabinose and glucuronic acid

Note 1 to entry: Hemicellulose can be branched polymers.

Note 2 to entry: Hemicellulose is usually extractable with dilute alkaline solutions.

3.3 Terms specific to cellulose nanomaterials

3.3.1

cellulose nanomaterial

CNM

material composed predominantly of *cellulose* (3.2.4), with any external dimension in the *nanoscale* (3.1.1), or a material having internal structure or surface structure in the nanoscale, with the internal structure or surface structure composed predominantly of cellulose

Note 1 to entry: The terms nanocellulose (NC) and cellulosic nanomaterial (CNM) are alternative terms for cellulose nanomaterial (CNM).

Note 2 to entry: Some cellulose nanomaterials can be composed of chemically modified cellulose.

Note 3 to entry: This generic term is inclusive of *cellulose nano-object* (3.3.2) and *cellulose nanostructured material* (3.3.3).

3.3.2

cellulose nano-object

nano-object (3.1.3) composed predominantly of *cellulose* (3.2.4)

3.3.3

cellulose nanostructured material

nanostructured material (3.1.5) of which the internal or surface *nanostructure* (3.1.4) is predominantly composed of *cellulose* (3.2.4)

3.3.4

cellulose nanofibre

nanofibre (3.1.6) composed predominantly of *cellulose* (3.2.4)

3.3.5

cellulose nanocrystal

CNC

nanocrystal (3.1.7) predominantly composed of *cellulose* (3.2.4) with at least one *elementary fibril* (3.2.5), containing predominantly *crystalline* (3.2.1) and *paracrystalline* (3.2.3) regions, with aspect ratio of usually less than 50 but usually greater than 5, not exhibiting longitudinal splits, inter-particle entanglement, or network-like structures

Note 1 to entry: The dimensions are typically 3-50 nm in cross-section and 100 nm to several µm in length depending on the source of the cellulose nanocrystal.

Note 2 to entry: The aspect ratio refers to the ratio of the longest to the shortest dimension.

Note 3 to entry: Historically cellulose nanocrystals have been called nanocrystalline cellulose (NCC), whiskers such as cellulose nanowhiskers (CNW), and microfibrils such as cellulose microfibrils; they have also been called spheres, needles or nanowires based on their shape, dimensions and morphology; other names have included cellulose micelles, cellulose crystallites and cellulose microcrystals.

3.3.6

cellulose nanofibril

CNF

cellulose (3.2.4) nanofibre (3.1.6) composed of at least one *elementary fibril* (3.2.5), containing *crystalline* (3.2.1), *paracrystalline* (3.2.3) and *amorphous* (3.2.2) regions, with aspect ratio usually greater than 10, which may contain longitudinal splits, entanglement between particles, or network-like structures

Note 1 to entry: The dimensions are typically 3-100 nm in cross-section and typically up to 100 µm in length.

Note 2 to entry: The aspect ratio refers to the ratio of the longest to the shortest dimensions.

Note 3 to entry: The terms nanofibrillated cellulose (NFC), nanofibrillar cellulose (NFC), microfibrillated cellulose (MFC), microfibrillar cellulose (MFC), cellulose microfibril (CMF) and cellulose nanofibre (CNF) have been used to describe cellulose nanofibrils produced by mechanical treatment of plant materials often combined with chemical or enzymatic pre-treatment steps.

Note 4 to entry: Cellulose nanofibrils produced from plant sources by mechanical processes usually contain *hemicellulose* (3.2.6), and in some cases lignin.

Note 5 to entry: Some cellulose nanofibrils might have functional groups on their surface as a result of the manufacturing process.

Note 6 to entry: The term cellulose nanoribbon has been used to describe cellulose nanofibrils from bacterial sources.

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20477:2017

Annex A

(informative)

Cellulose micromaterials

A cellulose microcrystal (CMC) is a cellulose object composed primarily of cellulose with a degree of polymerization typically less than 400. Less than 10% of the cellulose microcrystals in a production batch have diameters of less than 5 μm and aspect ratio of usually less than 2. The crystalline structure of cellulose microcrystal is composed of predominantly crystalline and paracrystalline regions.

CMCs may be manufactured by partially depolymerizing high purity cellulose such as α -cellulose. Alternative names for cellulose microcrystals include microcrystalline cellulose (MCC) or cellulosic microcrystals. The use of the abbreviation CMC in this context is not to be confused with its use for either 'carboxymethyl cellulose' or 'carboxymethylated cellulose' or 'critical micelle concentration'.