



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 3243C
Superseding AMS 3243B

Issued 1-15-57
Revised 7-15-77

CHLOROPRENE RUBBER Flame-Resistant 55 - 65

1. SCOPE:

1.1 Form: This specification covers a chloroprene rubber in the form of sheet, strip, tubing, molded shapes, and extrusions.

1.2 Application: Primarily for parts, such as grommets, seals, and line supports, on the firewall of aircraft or wherever flame resistance is of prime importance.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc. 400 Commonwealth Drive, Warrendale, PA 15096

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2810 - Identification and Packaging, Elastomeric Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D297 - Rubber Products - Chemical Analysis

ASTM D395 - Rubber Property - Compression Set

ASTM D412 - Rubber Properties in Tension

ASTM D471 - Rubber Property - Effect of Liquids

ASTM D573 - Rubber Deterioration in an Air Oven

ASTM D624 - Rubber Property - Tear Resistance

ASTM D635 - Rate of Burning or Extent and Time of Burning, or Both, of Self-Supporting Plastics in a Horizontal Position

ASTM D2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics

ASTM D2240 - Rubber Property - Durometer Hardness

ASTM F64 - Corrosive and Adhesive Effects of Gasket Materials on Metal Surfaces

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a compound based on a chloroprene elastomer suitably cured to produce a product meeting the requirements of 3.2.

SAE Technical Board rules provide that: "All technical reports, including standards, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

| | | | |
|---------|---|--------------------------------|--|
| 3.2.1.1 | Hardness, Durometer "A" or equiv. | 60 \pm 5 | ASTM D2240 |
| 3.2.1.2 | Tensile Strength, min | 900 psi (6.2 MPa) | ASTM D412, Die B or C |
| 3.2.1.3 | Elongation, min | 200% | ASTM D412, Die B or C |
| 3.2.1.4 | Tear Resistance, min | 70 lb per in. (12.3 kN/m) | ASTM D642, Die B |
| 3.2.1.5 | Specific Gravity | Qualification Value \pm 0.02 | ASTM D297 |
| 3.2.2 | <u>Petroleum Hydraulic Oil Resistance:</u> (Immediate Deteriorated Properties) | | ASTM D471 |
| 3.2.2.1 | Tensile Strength Change, max | -60% | Medium: ASTM Oil No. 3 Temperature: 100°C \pm 1 (212°F \pm 1.8) Time: 22 hr \pm 0.5 |
| 3.2.2.2 | Elongation Change, max | -60% | |
| 3.2.2.3 | Volume Change | +40 to +100% | |
| 3.2.2.4 | Decomposition | None | |
| 3.2.2.5 | Surface Tackiness | None | |
| 3.2.3 | <u>Aromatic Fuel Resistance:</u> (Immediate Deteriorated Properties) | | ASTM D471 |
| 3.2.3.1 | Tensile Strength Change, max | -75% | Medium: ASTM Ref. Fuel B Temperature: 20° - 30°C (68° - 86°F) Time: 22 hr \pm 0.5 |
| 3.2.3.2 | Elongation Change, max | -50% | |
| 3.2.3.3 | Volume Change | 0 to +80% | |
| 3.2.3.4 | Decomposition | None | |
| 3.2.3.5 | Surface Tackiness | None | |
| 3.2.4 | <u>Dry Heat Resistance:</u> | | ASTM D573 |
| 3.2.4.1 | Hardness Change, Durometer "A" or equiv. | 0 to +20 | Temperature: 125°C \pm 2 (257°F \pm 3.6) Time: 70 hr \pm 0.5 |
| 3.2.4.2 | Tensile Strength Change, max | -30% | |
| 3.2.4.3 | Elongation Change, max | -50% | |
| 3.2.4.4 | Bend (flat) | No cracking or checking | |

| | | | | | | |
|---------|---|---|--------------|--|--|--|
| 3.2.5 | <u>Compression Set:</u> | ASTM D395, Method B | | | | |
| 3.2.5.1 | Percent of Original Deflection, max | Temperature: $100^{\circ}\text{C} \pm 1$ $(212^{\circ}\text{F} \pm 1.8)$ | | | | |
| | | 50 | Time: | $70 \text{ hr} \pm 0.5$ | | |
| 3.2.6 | <u>Low Temperature Resistance:</u> | ASTM D2137, Method A | | | | |
| 3.2.6.1 | Brittleness | Pass | Temperature: | $-35^{\circ}\text{C} \pm 1$ $(-31^{\circ}\text{F} \pm 1.8)$ | | |
| 3.2.7 | <u>Flame Resistance:</u> | | | | | |
| | Flameout time, max | 10 sec | 4.5.1 | | | |
| 3.2.8 | <u>Weathering:</u> When specified, the product shall have weather resistance acceptable to the purchaser, determined by a procedure agreed upon by purchaser and vendor. | | | | | |
| 3.2.9 | <u>Corrosion:</u> The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable. Method of test and standards for acceptance shall be as agreed upon by purchaser and vendor. ASTM F64 is a recommended method of test. | | | | | |
| 3.3 | <u>Quality:</u> The product shall be uniform in quality and condition, clean, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to fabrication, appearance, or performance of parts. | | | | | |
| 3.4 | <u>Tolerances:</u> Unless otherwise specified, the following tolerances shall apply: | | | | | |
| 3.4.1 | <u>Sheet and Strip:</u> | | | | | |

TABLE I

| Nominal Thickness Inches | Tolerance, Inch plus and minus |
|-----------------------------|-----------------------------------|
| Up to 0.125, incl | 0.016 |
| Over 0.125 to 0.500, incl | 0.031 |
| Over 0.500 | 0.047 |

TABLE I (SI)

| Nominal Thickness Millimetres | Tolerance, Millimetres plus and minus |
|----------------------------------|--|
| Up to 3.18, incl | 0.41 |
| Over 3.18 to 12.70, incl | 0.79 |
| Over 12.70 | 1.19 |

3.4.2 Tubing:

3.4.2.1 Diameter:TABLE II

| Nominal OD or ID (Not both), Inches | Tolerance plus and minus | Ovality, % (See 3.4.2.1.1) |
|--|-----------------------------|-------------------------------|
| Up to 0.500, incl | 0.020 in. | 10 |
| Over 0.500 to 1.000, incl | 0.030 in. | 15 |
| Over 1.000 | 4% | 15 |

TABLE II (SI)

| Nominal OD or ID (not both), Millimetres | Tolerance plus and minus | Ovality, % (See 3.4.2.1.1) |
|---|-----------------------------|-------------------------------|
| Up to 12.70, incl | 0.51 mm | 10 |
| Over 12.70 to 25.40, incl | 0.76 mm | 15 |
| Over 25.40 | 4% | 15 |

3.4.1.1.1 Ovality applies to tubing ordered in straight lengths with wall thickness of 0.063 in. (1.60 mm) and over, and shall be computed from the difference between the minor and major axis diameter measurements, taken at the same transverse plane on the tube, expressed as a percentage of the nominal diameter.

3.4.2.2 Wall Thickness:TABLE III

| Nominal Wall Thickness Inches | Tolerance plus and minus |
|-------------------------------------|-----------------------------|
| Up to 0.063, excl 0.063 and over | 0.005 in. 10% |

TABLE III (SI)

| Nominal Wall Thickness Millimetres | Tolerance plus and minus |
|---------------------------------------|-----------------------------|
| Up to 1.60, excl 1.60 and over | 0.13 mm 10% |

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests: