

AEROSPACE MATERIAL SPECIFICATION

SAE AMS3668

REV. E

Issued 1967-04
Reaffirmed 2003-05
Revised 2010-05
Stabilized 2011-08

Superseding AMS3668D

Polytetrafluoroethylene (PTFE) Moldings
Premium Grade, As Sintered

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE AMS P, Polymeric Materials Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3668E

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3668E>**

1. SCOPE

1.1 Form

This specification covers two types of virgin, unfilled polytetrafluoroethylene (PTFE) in the form of molded rods, tubes, and shapes. This specification does not apply to product over 12 inches (305 mm) in length, rods under 0.750 inch (19.05 mm) in diameter, and tubes having wall thickness under 0.500 inch (12.70 mm).

1.2 Application

These moldings have been used typically for parts requiring chemical inertness up to 500 °F (260 °C), and better mechanical and/or electrical properties than AMS3660, but usage is not limited to such applications. For applications such as bearings, seals, and back-up rings that do not require dielectric properties it is recommended to use AMS3678/1 Grade A.

1.3 Safety - Hazardous Materials

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

1.4 Types 1 and 2, which were defined in previous revisions of this specification, have been combined. For documentation which specifies Type 1 or Type 2 of this specification, all of the requirements of this specification now apply.

SAENORM.COM : Click to view the full PDF of AMS3668E

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS3660	Polytetrafluoroethylene (PTFE) Moldings, General Purpose Grade, As Sintered
AMS3678	Polytetrafluoroethylene (PTFE) Moldings and Extrusions, Unfilled, Pigmented and Filled Compounds

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM D 149	Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies
ASTM D 792	Specific Gravity (Relative Density) and Density of Plastics by Displacement
ASTM D 4894	Standard Specification for Polytetrafluoroethylene (PTFE) Granular Molding and Ram Extrusion Materials

2.3 U.S. Government Publications

Available from the Document Automation and Production Service (DAPS), Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6257, <http://assist.daps.dla.mil/quicksearch/>.

MIL-STD-2073-1 Military Packaging, Standard Practice for

3. TECHNICAL REQUIREMENTS

3.1 Material

The product shall be molded by either compression or isostatic process from virgin polytetrafluoroethylene (PTFE) powder conforming to ASTM D 4894 Type IV or Type V without admixture of fillers, pigments, or adulterants and shall be sintered. . "Virgin" shall mean no previous heat or pressure history.

3.2 Color

Shall be predominantly white. Surface discoloration from sintering and/or annealing may vary from white to mottled gray or brown. Small gray, brown, or black spots shall not in themselves be unacceptable provided they do not have an adverse effect on the end usage of the finished product.

3.3 Properties

Moldings shall conform to requirements shown in Table 1; tests shall be performed on the product supplied and in accordance with specified test methods, insofar as practicable.

3.4 Tolerances

The tolerances shown in Table 2, Table 3, and Table 4 apply at 73 to 86 °F (23 to 30 °C):

TABLE 1 - PROPERTIES

Paragraph	Property	Requirement	Test Method
3.3.1	Tensile Strength at 73 °F $\pm$ 2 (23 °C $\pm$ 1), minimum	4000 psi (27.6 MPa)	4.5.1
3.3.2	Elongation at 73 °F $\pm$ 2 (23 °C $\pm$ 1), minimum	300%	4.5.1
3.3.3	Specific Gravity at 73 °F $\pm$ 5 (23 °C $\pm$ 3)	2.14 to 2.20	ASTM D 792 Add 2 drops of wetting agent to the water
3.3.4	Dielectric Strength, Short Time Test, minimum; applicable only to Type 1 moldings	1000 volts per mil (39.4 kV/min)	4.5.2

3.4.1 Rods

Shall be as shown in Table 2.

TABLE 2 - DIAMETER TOLERANCES

Nominal Diameter or Distance Between Parallel Sides Inches	Nominal Diameter or Distance Between Parallel Sides Millimeters	Tolerance Inch (Millimeter) plus only
0.750 to 2.000	19.05 to 50.80	0.062 (1.57)
Over 2.000 to 3.000 incl	Over 50.80 to 76.20 incl	0.125 (3.18)
Over 3.000 to 5.000 incl	Over 76.20 to 127.00 incl	0.187 (4.75)
Over 5.000 to 12.000 incl	Over 127.00 to 304.80 incl	0.250 (6.35)

3.4.2 Tubes

Shall be as shown in Table 3.

TABLE 3 - DIAMETER TOLERANCES

Nominal OD or ID Inches	Nominal OD or ID Millimeters	ID Tolerance, Inch (millimeters) Minus Only	OD Tolerance, Inch (millimeters) Plus Only
Up to 2.000 incl	Up to 50.80 incl	0.0625 (1.57)	0.0625 (1.57)
Over 2.000 to 3.000 incl	Over 50.80 to 76.20 incl	0.125 (3.18)	0.125 (3.18)
Over 3.000 to 5.000 incl	Over 76.20 to 127.00 incl	0.187 (4.75)	0.187 (4.75)
Over 5.000 to 12.000 incl	Over 127.00 to 304.8 incl	0.250 (6.35)	0.250 (6.35)

3.4.2.1 Out of Roundness

Shall be as shown in Table 4.

TABLE 4A - MAXIMUM OUT OF ROUNDNESS TOLERANCES, INCH/POUND UNITS

Nominal OD Inches	Nominal OD Millimeters	Out of Round Inch (millimeters) (See 3.5.2.2.1)
Up to 2.00 incl	Up to 50.8 incl	0.062 (1.57)
Over 2.00 to 3.00 incl	Over 50.8 to 76.2 incl	0.093 (2.36)
Over 3.00 to 5.00 incl	Over 76.2 to 127.0 incl	0.125 (3.18)
Over 5.00 to 8.00 incl	Over 127.0 to 203.0 incl	0.187 (4.75)
Over 8.00 to 12.00 incl	Over 203.0 to 304.8 incl	0.250 (6.35)

3.4.2.1.1 Out of Round is half the difference of the largest and smallest OD measurements (total indicator reading) at locations 90 degrees apart at any distance along a tube.

3.4.3 Shapes

As agreed upon by purchaser and supplier.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The manufacturer of moldings shall supply all test coupons and shall be responsible for all required tests for each lot of moldings. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the moldings conform to specified requirements. Manufacturer of machined parts shall furnish substantiating test data acquired by the manufacturer of moldings or extrusions. Purchaser of parts machined from moldings or extrusions also reserves the right to perform confirmatory testing provided the parts will yield test coupons that conform to the testing procedure(s) listed in 4.5.

4.2 Classification of Tests

4.2.1 Acceptance Tests

All technical requirements are acceptance tests and shall be performed on each lot of moldings (See 4.3.1).

4.3 Sampling and Testing

Shall be as follows

- 4.3.1 Sufficient test coupons shall be taken at random from each production molding lot to perform all required tests. Otherwise test samples shall be machined from a test or other suitable extrusion from the same resin lot. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.
- 4.3.2 A lot of moldings shall be all the rods or tubes of the same configuration made from the same batch of PTFE resin in one continuous run and presented for manufacturer's inspection at one time. Where multiple shipments are made from one lot of moldings, lot traceability shall be maintained. A lot shall consist of not more than 200 pounds (91 kg) of moldings.
- 4.3.3 A statistical sampling plan, acceptable to purchaser, may be used in lieu of sampling as in 4.3.1 and the report of 4.6 shall state that such plan was used.

4.4 Approval

- 4.4.1 Test results from sample product shall be approved by purchaser before production moldings are supplied, unless such approval is waived by purchaser. Results of tests on samples from the production lot shall be essentially equivalent to those on the approved sample. Production product made by a revised procedure shall not be shipped prior to receipt of reapproval. If necessary to make any change in parameters or the process control factors, manufacturer shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample product or test coupons shall be provided.
- 4.4.2 Manufacturer of the product shall make no significant change in material, processes, or control factors from those on which the approval was based, unless the change is approved by the purchaser's engineering department. A significant change is one which, in the judgment of the purchaser's engineering department, could affect the properties or performance of the product.

4.5 Test Methods

Shall be as follows

- 4.5.1 Tensile strength and elongation shall be determined in accordance with ASTM D 4894 and the test specimens shall be prepared from either a production molding as specified or if not possible, from a sample molding of sufficient size from the same resin batch. Test specimens for rods and tubes, where size permits, shall conform to ASTM D 4894, Figure 11. Specimens shall be prepared from slices 0.031 inch $\pm$ 0.002 (0.79 mm $\pm$ 0.05) thick cut from the product. Rods 0.250 inch (6.35 mm) and under in diameter may be tested in full cross-section. The initial jaw separation shall be 0.875 inch $\pm$ 0.005 (22.2 mm $\pm$ 0.13) and the speed of testing shall be 2 inches (50 mm) per minute. All results shall be reported.
- 4.5.2 For compression molded product the tensile strength coupon shall be pulled in the direction of molding (axial direction); for isostatically molded product, the tensile strength coupon may be pulled in either the axial or circumferential direction. The values shown are the minimum values required.
- 4.5.3 Specific Gravity shall be determined in accordance with ASTM D 792, Method A, with two drops of wetting agent added to the water.
- 4.5.4 Dielectric Strength shall be determined in accordance with ASTM D 149 under oil on 0.020 inch $\pm$ 0.002 (0.51 mm $\pm$ 0.05) thick specimens. When practicable, specimens shall be 1 inch (25 mm) in nominal diameter but may be 0.50 inch (12.7 mm) in nominal diameter if 1 inch (25 mm) diameter specimens cannot be obtained from the product. Electrodes shall be of corrosion-resistant steel, nominally 0.250 inch (6.35 mm) in diameter with 0.031 inch (0.79 mm) radius at the edges for 1 inch (25 mm) diameter specimens and nominally 0.062 inch (1.57 mm) in diameter with rounded edges for 0.50 inch (12.7 mm) diameter specimens.

4.6 Reports

The supplier of moldings shall furnish with each shipment a report from the manufacturer showing the results of tests on each lot to determine conformance to tensile strength, elongation, specific gravity, and dielectric strength and stating that the extrusions conform to the other technical requirements. This report shall include the purchase order number, lot number, AMS3668E, vendors compound number, form and size or part number, and quantity.

4.7 Resampling and Retesting

If any specimen used in the above tests fails to meet the specified requirements, disposition of the moldings may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the moldings represented. Results of all tests shall be reported.