

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4015

REV. L

Issued Revised Reaffirmed 1939-12 2007-02 2012-05

Superseding AMS4015K

Aluminum Alloy, Sheet and Plate 2.5Mg - 0.25Cr (5052-0) Annealed (Composition similar to UNS A95052)

RATIONALE

PDF of ams AO151 AMS4015L has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of sheet and plate.

1.2 Application

These products have been used typically for formed parts requiring moderate strength and good corrosion resistance and where welding may be required in fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), or www.sae.org.

AMS 2355

Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought

Reducts, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

AMS 2772

Heat Treatment of Aluminum Alloy Raw Materials

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions. Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

877-606-7323 (inside USA and Canada) TO PLACE A DOCUMENT ORDER: Tel:

+1 724-776-4970 (outside USA) Tel: 724-776-0790

Fax:

Email: CustomerService@sae.org

http://www.sae.org

SAE values your input. To provide feedback on this Technical Report, please visit http://www.sae.org/technical/standards/AMS4015L

SAE WEB ADDRESS:

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, or www.astm.org.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
ASTM B 666/B 666M Identification Marking of Aluminum and Magnesium Products

2.3 ANSI Publications

Available from American National Standards Institute, 25 West 43rd Street, New York, NY 10036, Tel: 212-642-4900, or www.ansi.org.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355.

TABLE 1 - COMPOSITION

Element	Jmin J	max
Silicon	1/2	0.25
Iron .	N	0.40
Copper		0.10
Manganese 🙀 🔾		0.10
Magnesium	2.2	2.8
Chromium	0.15	0.35
Zinc		0.10
Other Elements, each		0.05
Other Elements, total		0.15
Aluminum	remainder	

3.2 Condition

Annealed in accordance with AMS 2772

3.3 Properties

The product shall conform to the following requirements, determined in accordance with AMS 2355 on the mill produced size.

3.3.1 Tensile Properties

Shall be as specified in Table 2.

TABLE 2A - TENSILE PROPERTIES, INCH/POUND UNITS

	Tensile	Yield Strength	Elongation in
Nominal Thickness	Strength	at 0.2% Offset	2 Inches or 4D
Inches	ksi	ksi	%
0.006 to 0.007, incl	25.0 to 31.0	9.5	
Over 0.007 to 0.012, incl	25.0 to 31.0	9.5	14
Over 0.012 to 0.019, incl	25.0 to 31.0	9.5	15
Over 0.019 to 0.031, incl	25.0 to 31.0	9.5	16
Over 0.031 to 0.050, incl	25.0 to 31.0	9.5	18
Over 0.050 to 0.113, incl	25.0 to 31.0	9.5	19
Over 0.113 to 0.249, incl	25.0 to 31.0	9.5	20
Over 0.249 to 3.000, incl	25.0 to 31.0	9.5	18

TABLE 2B - TENSILE PROPERTIES, SI UNITS

		<u> </u>	
	Tensile	Yield Strength	Elongation in
Nominal Thickness	Strength	at 0.2% Offset	50.8 mm or 4D
Millimeters	MPa	MPa	%
0.15 to 0.18, incl	172 to 214	65.5	
Over 0.18 to 0.30, incl	172 to 214	65.5	14
Over 0.30 to 0.48, incl	172 to 214	65.5	15
Over 0.48 to 0.79, incl	172 to 214	65.5	16
Over 0.79 to 1.27, incl	172 to 2140	65.5	18
Over 1.27 to 2.87, incl	172 to 214	65.5	19
Over 2.87 to 6.32, incl	172 to 214	65.5	20
Over 6.32 to 76.20, incl	172 to 214	65.5	18

3.3.2 Bending

Product 0.249 inch (6.32 mm) and under in nominal thickness shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.4 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances

Shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are acceptance tests and, except for composition, shall be performed on each lot.

4.2.2 Periodic Tests

Bending (3.3.2) is a periodic test and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS 2355.

4.4 Reports

The vendor of the product shall furnish with each shipment a report stating that the product conforms to the composition and tolerances and showing the numerical results of tests on each inspection lot to determine conformance to the other acceptance test requirements. This report shall include the purchase order number, inspection lot number(s), AMS 4015L, size, and quantity. The report shall also identify the producer, the product form, and size from the mill.

4.5 Resampling and Retesting

Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY

5.1 Identification

Shall be in accordance with ASTM B 666/B 666M

5.2 Packaging

- 5.2.1 Flat sheet, plate, and circles 2 inches (305 mm) and over in nominal diameter shall be coated, prior to shipment, with a light corrosion-inhibiting oil.
- 5.2.2 The product shall be prepared for shipment in accordance with ASTM B 660 and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance with safe delivery.

ACKNOWLEDGMENT

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS

Product not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES

8.1 A change bar (I) located in the left margin is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. An (R) symbol to the left of the document title indicates a complete revision of the specification, including technical revisions. Change bars and (R) are not used in original publications, nor in specifications that contain editorial changes only.