

UNS N02201

NICKEL SHEET AND STRIP  
Low (0.02 max) Carbon  
Annealed

1. SCOPE:

1.1 Form: This specification covers nickel in the form of sheet and strip.

1.2 Application: Primarily for parts requiring excellent corrosion resistance and/or strong magnetic properties.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2262 - Tolerances, Nickel, Nickel-Base, and Cobalt-Base Alloy Sheet, Strip, and Plate

AMS 2269 - Chemical Check Analysis Limits, Wrought Nickel Alloys and Cobalt Alloys

AMS 2350 - Standards and Test Methods

AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

# AMS 5553C

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E18 - Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials

ASTM E39 - Chemical Analysis of Nickel

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform the the following percentages by weight,  $\emptyset$  determined by wet chemical methods in accordance with ASTM E39, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Nickel + Cobalt	99.0	--
Carbon	--	0.02
Manganese	--	0.35
Silicon	--	0.35
Sulfur	--	0.010
Iron	--	0.40
Copper	--	0.25

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition: Cold rolled, annealed, and, unless annealing is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to a commercial corrosion-resistant steel No. 2D finish; standards for acceptance shall be as agreed upon by purchaser and vendor.

3.3 Properties: The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as shown in Table I, determined in accordance with ASTM E8.

TABLE I

Nominal Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi	Elongation in 2 in. %, min
0.005 to 0.010, excl	45,000	--	--
0.010 to 0.015, incl	50,000	30,000, max	30
Over 0.015 to 0.049, incl	50,000	12,000, min	30
Over 0.049 to 0.109, incl	50,000	12,000, min	35
Over 0.109 to 0.250, incl	50,000	12,000, min	40

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa	Elongation in 50 mm %, min
0.12 to 0.25, excl	310	--	--
0.25 to 0.38, incl	345	205, max	30
Over 0.38 to 1.25, incl	345	85, min	30
Over 1.25 to 2.70, incl	345	85, min	35
Over 2.70 to 6.25, incl	345	85, min	40

3.3.2 Hardness: Should be not higher than 66 HRB or equivalent, determined in accordance with ASTM E18, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2262.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

# AMS 5553C

4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling: Shall be in accordance with AMS 2371.

4.4 Reports:

4.4.1 The vendor of the product shall furnish with each shipment three copies of a report showing the results of tests for chemical composition of each heat and for tensile properties and hardness of each lot. This report shall include the purchase order number, heat number, AMS 5553C, size, and quantity from each heat.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, AMS 5553C, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification and shall include in the report either a statement that the material conforms or copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each sheet and strip shall be marked on one face, in the respective location indicated below, with AMS 5553C, heat number, manufacturer's identification, and nominal thickness. The characters shall be of such size as to be legible, shall be applied using a suitable marking fluid, and shall be removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling.

5.1.1 Flat Strip 6 In. (150 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm).

5.1.2 Flat Sheet and Flat Strip Over 6 In. (150 mm) in Width: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 ft (900 mm), the rows being spaced not more than 6 in. (150 mm) apart and alternately staggered.