

AEROSPACE MATERIAL SPECIFICATION



AMS 6304H

Issued AUG 1955
Revised JUL 1994
Reaffirmed SEP 2000

Superseding AMS 6304G

Low-Alloy Steel, Heat-Resistant, Bars, Forgings, and Tubing 0.95Cr - 0.55Mo - 0.30V (0.40 - 0.50C)

UNS K14675

1. SCOPE:

1.1 Form:

This specification covers an aircraft-quality, low-alloy, heat-resistant steel in the form of bars, forgings, mechanical tubing, and forging stock procured in inch/pound units.

1.1.1 MAM 6304 is the metric version of this AMS.

1.2 Application:

These products have been used typically for parts, such as shafts and fasteners, in service up to 1000 °F, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2251	Tolerances, Low-Alloy Steel Bars
AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2301	Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 (Continued):

AMS 2806 Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys

AMS 2808 Identification, Forgings

AS1182 Standard Machining Allowance, Aircraft-Quality and Premium Aircraft-Quality Steel Bars and Mechanical Tubing

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM A 370 Mechanical Testing of Steel Products

ASTM E 112 Determining the Average Grain Size

ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

ASTM E 381 Macroetch Testing, Inspection, and Rating Steel Products, Comprising Bars, Billets, Blooms, and Forgings

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	0.40	0.50
Manganese	0.40	0.70
Silicon	0.15	0.35
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	0.80	1.10
Molybdenum	0.45	0.65
Vanadium	0.25	0.35
Nickel	--	0.25
Copper	--	0.35

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition; hardness and tensile strength shall be determined in accordance with ASTM A 370:

3.2.1 Bars:

3.2.1.1 Bars 0.500 Inch and Under in Nominal Diameter or Distance Between Parallel Sides: Cold finished having tensile strength not higher than 125 ksi.

3.2.1.2 Bars Over 0.500 Inch in Nominal Diameter or Distance Between Parallel Sides: Hot finished and annealed having hardness not higher than 229 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 248 HB, or equivalent (See 8.2).

3.2.2 Forgings: Annealed having hardness not higher than 248 HB, or equivalent (See 8.2).

3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 25 HRC, or equivalent, except that tubing ordered hot finished and annealed shall have hardness not higher than 99 HRB, or equivalent (See 8.2).

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements; hardness testing shall be performed in accordance with ASTM A 370:

- 3.3.1 Macrostructure: Visual examination of transverse full cross-sections from bars, billets, tube rounds or tubes, and forging stock, etched in hot hydrochloric acid in accordance with ASTM E 381, shall show no pipe or cracks. Except as specified in 3.3.1.1, porosity, segregation, inclusions, and other imperfections shall be no worse than the macrographs of ASTM E 381 shown in Table 2.

TABLE 2 - Macrostructure Limits

Cross-Sectional Area	
Square Inches	Macrographs
Up to 36, incl	S2 - R1 - C2
Over 36 to 100, incl	S2 - R2 - C3

- 3.3.1.1 If tubes are produced directly from ingots or large blooms, transverse sections may be taken from tubes rather than tube rounds. Macrostructure standards for such tubes shall be as agreed upon by purchaser and vendor.
- 3.3.2 Average Grain Size: Shall be ASTM No. 5 or finer, determined in accordance with ASTM E 112 (See 8.3).
- 3.3.3 Response to Heat Treatment: Specimens as in 4.3.3 shall have hardness at the center of the specimen not lower than 331 HB, or equivalent (See 8.2), for cross-sections 2 inches and under and not lower than 302 HB, or equivalent, for larger cross-sections after being heated to 1750 °F ± 25, held at heat for 60 to 90 minutes, cooled in still air, reheated to 1100 °F ± 15, held at heat for 6 hours ± 0.25, and cooled in air.
- 3.3.4 Decarburization:
- 3.3.4.1 Bars and tubing ordered ground, turned, or polished shall be free from decarburization on the ground, turned, or polished surfaces.
- 3.3.4.2 Allowable decarburization of bars, billets, tube rounds, and tubing ordered for redrawing or forging or to specified microstructural requirements shall be as agreed upon by purchaser and vendor.
- 3.3.4.3 Decarburization of bars to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 3.

TABLE 3 - Maximum Depths of Decarburization

Nominal Diameter or Distance Between Parallel Sides Inches	Depth of Decarburization Inch
Up to 0.375, incl	0.015
Over 0.375 to 0.500, incl	0.017
Over 0.500 to 0.625, incl	0.019
Over 0.625 to 1.000, incl	0.022
Over 1.000 to 1.500, incl	0.025
Over 1.500 to 2.000, incl	0.030
Over 2.000 to 2.500, incl	0.035
Over 2.500 to 3.000, incl	0.040
Over 3.000 to 4.000, incl	0.045

3.3.4.3.1 Limits for depth of decarburization of bars over 4.000 inches in nominal diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.

3.3.4.4 Decarburization of tubing to which 3.3.4.1 or 3.3.4.2 is not applicable shall be not greater than shown in Table 4.

TABLE 4 - Maximum Depths of Decarburization

Nominal Wall Thickness Inches	Depth of Decarburization Inch ID	Depth of Decarburization Inch OD
Up to 0.109, incl	0.008	0.020
Over 0.109 to 0.203, incl	0.010	0.025
Over 0.203 to 0.400, incl	0.012	0.030
Over 0.400 to 0.600, incl	0.015	0.035
Over 0.600 to 1.000, incl	0.017	0.040
Over 1.000	0.020	0.045

3.3.4.5 Decarburization shall be measured by the microscopic method or by Rockwell Superficial 30-N scale or equivalent hardness testing method on hardened but untempered specimens protected during heat treatment to prevent changes in surface carbon content. Depth of decarburization, when measured by a hardness method, is defined as the perpendicular distance from the surface to the depth under that surface below which there is no further increase in hardness. Such measurements shall be far enough away from any adjacent surface to be uninfluenced by any decarburization or lack of decarburization thereon.

- 3.3.4.5.1 When determining the depth of decarburization, it is permissible to disregard local areas provided the decarburization of such areas does not exceed the above limits by more than 0.005 inch and the width is 0.065 inch or less.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

- 3.4.1 Steel shall be aircraft quality conforming to AMS 2301.

- 3.4.2 Bars and mechanical tubing ordered hot rolled or cold drawn or ground, turned, or polished shall, after removal of the standard machining allowance in accordance with AS1182, be free from seams, laps, tears, and cracks open to the ground, turned, or polished surfaces.

- 3.4.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings showing no evidence of re-entrant grain flow.

3.5 Tolerances:

Shall be as follows:

- 3.5.1 Bars: Shall conform to all applicable requirements of AMS 2251.

- 3.5.2 Mechanical Tubing: Shall conform to all applicable requirements of AMS 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be as follows:

- 4.3.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

- 4.3.2 Forgings: In accordance with AMS 2372.

4.3.3 Specimens for response to heat treatment (3.3.3) shall be not shorter than twice the nominal diameter or distance between parallel sides or 6 inches, whichever is less, and shall have the full cross-section of the product from which they were cut except that sections over 2 to 4 inches, inclusive, in nominal diameter or distance between parallel sides shall be reduced to 2.00 inches $\pm$ 0.01 and sections over 4 inches shall be reduced to 4.00 inches $\pm$ 0.01.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition, macrostructure, average grain size, and frequency-severity cleanliness rating of each heat and for response to heat treatment of each lot. This report shall include the purchase order number, heat and lot number, AMS 6304H, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Mechanical Tubing, and Forging Stock: In accordance with AMS 2370.

4.5.2 Forgings: In accordance with AMS 2372.

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 to 20 feet but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet.

5.2 Identification:

Shall be as follows:

5.2.1 Bars and Mechanical Tubing: In accordance with AMS 2806.

5.2.2 Forgings: In accordance with AMS 2808.

5.2.3 Forging Stock: As agreed upon by purchaser and vendor.

5.3 Packaging:

5.3.1 Bars and tubing ordered cold drawn, cold rolled, ground, turned, or polished shall be coated with a corrosion-preventive compound prior to shipment.