



SURFACE VEHICLE STANDARD

J860™

APR2022

Issued 1963-06
Revised 2015-06
Reaffirmed 2022-04

Superseding J860 JUN2015

Test Method for Measuring Mass (Weight) of Organic Trim Materials

RATIONALE

Change test conditions in 3.1 to $\pm 10\%$ RH.

SAE J860 has been reaffirmed to comply with the SAE Five-Year Review policy.

1. SCOPE

This SAE Standard is used to determine the mass per unit area, in grams per square meter, of materials used for trimming automobile interiors.

2. REFERENCES

There are no referenced publications specified herein.

3. PROCEDURE

- 3.1 Condition all test specimens in a standard atmosphere of $23 \pm 2^\circ\text{C}$ and $50\% \pm 10\%$ relative humidity for 24 h.
- 3.2 Cut three specimens 100 mm X 100 mm or as designated by the contractual parties. For roll goods two specimens shall be taken approximately one tenth the width of the material from each selvage and one specimen at approximately the middle of the width of the material. The three specimens shall be staggered as much as feasible in the length of the roll goods. For materials other than roll goods, cut three specimens from the representative areas as designated by the contractual parties.
- 3.3 Measure the length and width of each specimen to the nearest 0.5 mm with a ruler or tape and calculate the area of each in square millimeters.
- 3.4 Weigh each of the three test specimens to the nearest milligram.

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2022 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit

https://www.sae.org/standards/content/J860_202204/